This is a digital copy of a book that was preserved for generations on library shelves before it was carefully scanned by Google as part of a project to make the world's books discoverable online.

It has survived long enough for the copyright to expire and the book to enter the public domain. A public domain book is one that was never subject to copyright or whose legal copyright term has expired. Whether a book is in the public domain may vary country to country. Public domain books are our gateways to the past, representing a wealth of history, culture and knowledge that's often difficult to discover.

Marks, notations and other marginalia present in the original volume will appear in this file - a reminder of this book's long journey from the publisher to a library and finally to you.

Usage guidelines

Google is proud to partner with libraries to digitize public domain materials and make them widely accessible. Public domain books belong to the public and we are merely their custodians. Nevertheless, this work is expensive, so in order to keep providing this resource, we have taken steps to prevent abuse by commercial parties, including placing technical restrictions on automated querying.

We also ask that you:

+ *Make non-commercial use of the files* We designed Google Book Search for use by individuals, and we request that you use these files for personal, non-commercial purposes.

+ *Refrain from automated querying* Do not send automated queries of any sort to Google's system: If you are conducting research on machine translation, optical character recognition or other areas where access to a large amount of text is helpful, please contact us. We encourage the use of public domain materials for these purposes and may be able to help.

+ *Maintain attribution* The Google "watermark" you see on each file is essential for informing people about this project and helping them find additional materials through Google Book Search. Please do not remove it.

+ *Keep it legal* Whatever your use, remember that you are responsible for ensuring that what you are doing is legal. Do not assume that just because we believe a book is in the public domain for users in the United States, that the work is also in the public domain for users in other countries. Whether a book is still in copyright varies from country to country, and we can't offer guidance on whether any specific use of any specific book is allowed. Please do not assume that a book's appearance in Google Book Search means it can be used in any manner anywhere in the world. Copyright infringement liability can be quite severe.

About Google Book Search

Google's mission is to organize the world's information and to make it universally accessible and useful. Google Book Search helps readers discover the world's books while helping authors and publishers reach new audiences. You can search through the full text of this book on the web at `http://books.google.com/`

HARVARD UNIVERSITY

LIBRARY OF THE
MINERALOGICAL
LABORATORY

UNIVERSITY MUSEUM

Digitized by Google

HARVARD UNIVERSITY
CAMBRIDGE, MASS.
JAN 11 1922
Dept. of Mineralogy & Petrography

Digitized by Google

Digitized by Google

Digitized by Google

Digitized by Google

Digitized by Google

Digitized by Google

DEPARTMENT OF THE INTERIOR
JOHN BARTON PAYNE, Secretary

UNITED STATES GEOLOGICAL SURVEY
GEORGE OTIS SMITH, Director

MINERAL RESOURCES

OF THE

UNITED STATES

1917

H. D. McCASKEY
Geologist in Charge, Division of Mineral Resources

PART I—METALS

H. D. McCASKEY, Geologist in Charge

WASHINGTON
GOVERNMENT PRINTING OFFICE
1921

Digitized by Google

Digitized by Google

CONTENTS.

[The dates of publication of the separate chapters are given in parentheses.]

	Page.
The economic limits to domestic independence in minerals, by George Otis Smith (Dec. 28, 1918)	1A
International control of minerals, by C. K. Leith (Dec. 31, 1918)	7A
Mineral production of the United States, by H. D. McCaskey and M. B. Clark (June 28, 1920)	17A
Prefatory note to the reports on gold, silver, copper, lead, and zinc, by H. D. McCaskey	77A
Bauxite and aluminum, by J. M. Hill (June 21, 1918)	1
Platinum and allied metals, by J. M. Hill (June 21, 1918)	11
Arsenic, by J. B. Umpleby (June 19, 1918)	23
Bismuth, by J. B. Umpleby (June 19, 1918)	29
Selenium, by J. B. Umpleby (June 19, 1918)	33
Tellurium, by J. B. Umpleby (June 19, 1918)	35
Chromite, by J. S. Diller (Aug. 8, 1918)	37
Cadmium, by C. E. Siebenthal (July 12, 1918)	49
Gold, silver, copper, lead, and zinc in the Eastern States, by J. M. Hill (July 29, 1918)	55
Tin, by Adolph Knopf (Sept. 16, 1918)	63
Silver, copper, lead, and zinc in the Central States, by J. P. Dunlop and B. S. Butler (Oct. 24, 1918)	73
Gold, silver, copper, and lead in Alaska, by G. C. Martin (Nov. 21, 1918)	131
Magnesium, by R. W. Stone (Dec. 11, 1918)	147
Gold, silver, copper, and lead in South Dakota by C. W. Henderson (Jan. 27, 1919)	153
Gold, silver, and copper in Wyoming, by C. W. Henderson (Jan. 27, 1919)	161
Gold, silver, copper, lead, and zinc in Utah, by V. C. Heikes (Feb. 8, 1919)	167
Gold, silver, copper, lead, and zinc in California, by C. G. Yale (Feb. 18, 1919)	203
Gold, silver, copper, and lead in Oregon, by C. G. Yale (Feb. 18, 1919)	243
Gold, silver, copper, lead, and zinc in Nevada, by V. C. Heikes (Feb. 18, 1919)	253
Secondary metals, by J. P. Dunlop (Feb. 19, 1919)	299
Gold, silver, copper, lead, and zinc in Montana, by V. C. Heikes (Feb. 21, 1919)	331
Quicksilver, by F. L. Ransome, with a bibliography by I. P. Evans (Mar. 18, 1919)	367
Gold, silver, copper, lead, and zinc in Idaho, by C. N. Gerry (Apr. 3, 1919)	457
Gold, silver, copper, lead, and zinc in Washington, by C. N. Gerry (Apr. 3, 1919)	493
Gold, silver, copper, lead, and zinc in Arizona, by V. C. Heikes (Apr. 1, 1919)	509
Iron ore, pig iron, and steel, by E. F. Burchard (Apr. 28, 1919)	557
Gold and silver (general report), by H. D. McCaskey and J. P. Dunlop (May 9, 1919)	605
Antimony, by E. S. Bastin (May 13, 1919)	653
Manganese and manganiferous ores, by D. F. Hewett (Oct. 31, 1919)	665
Gold, silver, copper, lead, and zinc in New Mexico, by C. W. Henderson (Nov. 8, 1919)	697

Digitized by Google

Page.
Gold, silver, copper, lead, and zinc in Texas, by C. W. Henderson (Nov. 8, 1919). 721
Copper (general report), by B. S. Butler (Mar. 13, 1920) 723
Gold, silver, copper, lead, and zinc in Colorado, by C. W. Henderson (Mar. 1, 1920) 797
Zinc (general report), by C. E. Siebenthal (Apr. 6, 1920) 855
Lead (general report), by C. E. Siebenthal (May 8, 1920) 881
Cobalt, by F. L. Hess (Aug. 31, 1920) 899
Molybdenum, by F. L. Hess (Aug. 31, 1920) 907
Nickel, by F. L. Hess (Aug. 31, 1920) 917
Titanium, by F. L. Hess (Aug. 31, 1920) 929
Tungsten, by F. L. Hess (Aug. 31, 1920) 931
Radium, uranium, and vanadium, by F. L. Hess (Aug. 31, 1920) 955
Index 961

ILLUSTRATIONS.

Page.
PLATE I. Map showing world's output of tin in 1916, in short tons 70
II. Map showing the location of those quicksilver deposits of the world, some output from which is on record 386
III. Map showing the location of the known quicksilver deposits of the United States 388
IV. Curves showing production and value of gold and silver in the world, 1860–1917 612
V. Diagram showing imports of antimony and average prices of ordinary grades of antimony metal in New York market, by months, 1914 to 1918, inclusive 654
VI. Map of world showing location of principal copper-producing centers. 728
VII. Curves showing weekly average prices of zinc at St. Louis and London and of zinc concentrates at Joplin; also weekly production of zinc concentrates in the Joplin region, 1914–1917 878
VIII. Average weekly price of lead at New York and London in 1914–1917. 896
FIGURE A. Curves showing the value of the mineral production of the United States, 1880–1917 34A
1. Map of North America showing known deposits of chromic iron ore. 39
2. Average yearly prices, in cents per pound, of Straits tin in New York, and world's output of tin, in metric tons, 1900–1917 68
3. Diagram showing quantity and value of quicksilver produced in the United States from 1850 to 1917, inclusive 369
4. Diagram showing variations of monthly average market quotations for domestic quicksilver at San Francisco from 1913 to 1917, inclusive 377
5. Diagram showing prices of quicksilver in London, New York, and San Francisco in 1917 380
6. Curves showing annual production of iron ore, pig iron, and steel in the United States, 1870 to 1917 559
7. Source and destination of iron ore imported into the United States in 1917 579
8. Curve showing prices of basic pig iron at blast furnaces in Mahoning and Shenango valleys, Ohio and western Pennsylvania, 1912 to 1917, by months 589

Digitized by Google

Page.

FIGURE 9. Curve showing production of coke and anthracite pig iron in the United States, 1912–1917, by months 592
10. Curves showing production and value of gold and silver and price per fine ounce of silver in the United States, 1871–1917 609
11. Diagram showing stocks of metallic antimony in bonded warehouse at end of each month in 1917 and 1918 654
12. Diagram showing contract prices of ferromanganese, spiegeleisen, and manganese ore, 1912–1917 681
13. Curves showing the principal features of the copper industry, 1907–1918 727
14. Production of copper by countries, 1913 and 1917 728
15. Relative production, consumption, imports, and exports of copper by the principal copper producing and consuming countries in 1913 729
16. Labor employed and copper produced in the different classes of copper mines, 1916 and 1917 734
17. Diagram showing prices of molybdenum ore and of molybdenum in ferromolybdenum, 1917 908
18. Graph showing prices for tungsten ore carrying 60 per cent of WO_3 and of tungsten in ferrotungsten carrying 72 to 78 per cent of tungsten 935

INSERT.

Mineral products of the United States, 1908–1917 ..... In pocket.

Digitized by Google

Digitized by Google

MINERAL RESOURCES OF THE UNITED STATES, 1917—PART I.

THE ECONOMIC LIMITS TO DOMESTIC INDEPENDENCE IN MINERALS.

By GEORGE OTIS SMITH.

The war demands placed upon the United States created many new problems in connection with the supply of raw materials. Not only were former sources of supply cut off by the war's interference with commerce, but the large industrial expansion due to the world's larger need of American manufactured products caused in turn increased consumption of raw materials; the net result was an unprecedented and a too largely unexpected call upon the basal industries of the country—agriculture, forestry, and mining.

Already the United States had become more nearly independent than any other industrial nation in the production of minerals; our output in 1913 was 36 per cent of the total for the world and included even larger percentages of the mineral fuels and copper, aluminum, zinc, and sulphur. Yet there were on the other side of the Nation's ledger notable deficiencies in tin, platinum, nickel, manganese, chrome, potash, and nitrates, and the domestic supply of some of these minerals continues to be hopelessly inadequate. To meet the war demand for every mineral raw material was the larger task set before the mineral industry, and the degree of success attained and its cost are the basal facts in any inquiry as to the economic limits that must be recognized in developing the domestic supply.[1]

The conditions presented in the four years of war have been novel and have changed from month to month. Yet in no sense have these changing conditions been outside the realm of economic law. Premises previously unthought of because they involved facts outside former experience, such as destruction of cargo ships or shortage of freight cars, have formed the basis for action incredible in its novelty yet so necessary that the term "war times" was used to express the excuse for every act seemingly in violation of both business sense and economic law. In fact, however, both economic law and business

[1] The writer neither overlooks nor minimizes the international phase of the utilization of mineral resources, but because of the many-sided nature of the whole subject, the arrangement has been made for Prof. Leith to present the broader outlook in the paper which follows. It is hoped in this way to suggest more of the facts and principles that must be kept in mind by one who approaches the solution of this economic problem.

Digitized by Google

sense were being applied to new problems and in new ways in obtaining the raw materials for a nation's expanded industry.

Under these special conditions of supply and demand some minerals have taken on new values—indeed, certainty of supply has had larger significance than price. These new values may persist for varying periods, but for some products they must be recognized as only temporary.

It is enlightening, however, to note how large a family of inventions and improvisations can be credited to necessity, and how these substitutes born in time of need develop into lively competitors with the older commodities. Thus, certain potassium salts may never recover the industrial fields that were temporarily (it was thought) given over to the equivalent salts of sodium, and sintered dolomite already competes with magnesite, even though a domestic supply of magnesite is now assured and the imported magnesite may be again available as shipping conditions become normal.

The peace readjustment of the mineral industry requires immediate consideration, involving as it does the future of war-born infant industries but first of all the recalculation of the country's needs. It may be only suggested here that the real issue is to what extent it is of national benefit that this or that new industry should be continued, and that national benefit is to be measured in terms of the premise that industry is the basis of social welfare, not an end unto itself or an opportunity for profit to the few. So it becomes a debatable economic question how much influence can be properly exercised on the natural course of commercial evolution. American experience has shown that some industries soon outgrow the need of governmental fostering but that others never grow up. An all-important element in the problem is whether the product meets an essential need of the country.

In speaking of the expected war demands for raw materials the present writer earlier made the statement that "the mineralogic curiosity of one decade may become the valuable ore of the next." As the years of war have passed many illustrations of this truth have come to the notice of the Survey's investigators. Perhaps no better example can be cited than that of the Leucite Hills, in Wyoming. The Government geologist who was classifying the public coal lands in that vicinity desired to add to our knowledge of this unique occurrence of interesting rock types, and before the Survey could publish his scientific contribution the world potash situation gave potential economic value to his field study. His quantitative estimates of possibly available potash content are now the incentive to large expenditures in working out extraction processes on a commercial scale, and quarry sites have been selected where he mapped this peculiar rock. The latest example of an unforeseen use of scientific data is the connection that has recently been developed between the shipping program and the Survey's investigations of the quality of water. These studies of the surface waters of the United States were begun years ago, and their basis has been geologic as well as chemical. The practical usefulness of the results has, of course, been realized from the start, in connection with steam making and other industrial uses of river water, but recently it was found that with a supply of brass tubes sufficient only for the con-

Digitized by Google

densers of the naval and merchant vessels under construction, steel tubes must be substituted wherever possible in other condenser installations, and the extent of this substitution, as ordered by the War Industries Board, was conditioned by the quality-of-water data furnished by the Geological Survey.

The war program, with its reaction upon industry, has opened the eyes of many to old facts. Mineral raw materials have won a recognition based upon the new realization of their value. De Launay's recent and apt characterization of coal and iron as the two "grand seigneurs" of the mineral world[1] is in strong contrast with the ancient idea of nobility among metals. The new measure of value is usefulness.

Economic geology is useful geology—the theoretical science applied to meet the material needs of man. These human needs as presented in the last four years have demanded a specialized type of geology—the application of geology in terms of commerce. Geology to be most useful in these days of world problems must take the world view of values, and we find ourselves working in commercial geology—that is, geology applied in terms of commerce. The world is the field of commerce, and the requirements of commercial geology are simply that the geologic relations of a Nevada ore deposit, for example, must be observed with an eye trained to see far beyond the Basin range; the geologist needs to compare the quality and quantity of the unmined ore here with similar facts of nature that give value to the ores in other districts, as in Peru or Burma. Whether the investigator is called a geologist, mining engineer, or economist, his vision must take in not simply the ore minerals as they have been deposited, segregated, or enriched by the processes of nature, but also the smelted ore and the refined metal on their way to the markets of the world, where they can serve mankind. Thus to broaden and extend the investigator's view is not to commercialize his science; it is rather to make geology more useful, and in that way to give the science a higher rank.

Geology must needs continue to furnish the basal facts, but the geologist has a call to go further than he has gone heretofore in the interpretation of his facts—not simply by translating his technical words into the language of the market place, but, more than that, by showing the relation of geology to national life.[2]

In terms of commercial geology, therefore, ore deposits take on competitive relationships, and in terms of national interest there must be a determination of relative worth. The practical question concerns not simply the quantity of metal present in the ore but the quantity that can be won to the profit of mankind. First of all, then, in fixing the economic limits to the utilization of domestic mineral deposits, comes the balancing of cost of production with the value of the product. This requirement, which holds good in any business undertakings, however small, is none the less operative in an industry viewed in its national aspect. Economic profit is attained only by reducing cost or increasing value until the margin appears on the right side of the account.

[1] France—Allemagne, p. 225, 1917.

[2] The series of interesting papers issued by the U. S. National Museum (Bull. 102) represents a timely effort in this direction. In these papers Messrs. Gilbert and Pogue have interpreted mineral resources as related to public interest.

Digitized by Google

Into the cost of production enter the items of transportation, investment, and labor. An industrial leader like Mr. Schwab[1] appreciates the "handicap of distance," although with a sportsman-like spirit he and other industrial leaders regard this handicap as simply another incentive to American ingenuity, not as a plea for preferential freight rates. The transportation factor has played a noteworthy part in every large production enterprise in the United States, where commonly mine and market are separated by hundreds if not thousands of miles.

Improvement in transportation, whether interstate or international, tends to the equalization of opportunity: the peoples of the world are brought closer together. Artificial rates, however, in either interstate or international commerce will impose burdens rather than confer benefits, and we can not afford to throw back to the era of rebates. Therefore the facts of transportation must be written into the statement of production costs; the geologist and the engineer must from the start be geographers, for distance can not be eliminated from any commercial problem. The place factor enters so largely into the determination of value of mineral raw materials that many a promoter would gladly have the scientific investigator close his eyes to the facts regarding the accessibility of the deposit under examination. Yet the transportation cost is too often the cause of financial disaster, even when the geologic and other engineering facts have been correctly determined and are favorable to success.

Investment and labor costs come less under the purview of the geologic engineer in his study of mineral resources, yet the power element is one that touches both of these items and is not to be overlooked by any student of industrial problems. It becomes more and more evident that the use of power, either steam or water, will become the deciding factor in American industry. The statistics of man power cited by Butler[2] furnish the most convincing arguments as to the stability of our copper industry and its ability to dominate the world markets. The community of interest between some of the largest mining and power corporations is therefore to be regarded as a natural development along economic lines—not as an artifice in restraint of trade. Whether cheap power is made available for mine use by private initiative or by public control, the result is the same—cheap raw materials for other industries.

During the war period the value of raw materials was in large part due to the emergency demand, and the experience should leave its realization of the exigency element in the determination of value. Under war conditions no one questions the great advantage of domestic independence in raw materials, and then adequate supply rather than low price is all-desirable. Nearness of source of raw materials is advantageous at other times, but the amount that can then be added to the value on that account is less easily determined. The purchasing agent of a large manufacturing plant may favor the near-by to the distant source of raw material and the domestic to the foreign producer as a matter of assurance that there will be no interruption to "keeping the works running." Yet the spirit of cost accounting leads usually to the cheapest market. Again it hap-

[1] American problems of reconstruction, p. 143, 1918.
[2] Butler, B. S., Copper: U. S. Geol. Survey Mineral Resources, 1917, pt. 1, pp. —— (in preparation).

Digitized by Google

pens that when a productive industry so contributes to some larger business or group of industries as to be absolutely essential to their continuance this key industry takes on a larger significance than its size suggests.

In the consideration of any domestic industry the factor of home consumption must not be overlooked; indeed, home consumption is more directly connected with national welfare than exports. Our high per capita consumption of copper, for instance, means more to the Nation than our exportable surplus of the same metal, the true value of which is indirect through the means it furnishes for trade or exchange for imports of other commodities for our own consumption. A nation that robs its domestic consumers so as to have an exportable surplus or to sell that surplus at a price below cost will be copying a German blunder in economics. Increased consumption of metals and mineral fuels means expansion of all industries, which in turn should mean a larger home market for all the things that go with a higher standard of living.

The mineral control act of 1918 furnishes a too long delayed expression of the emergency value of mineral independence. The exigencies of war revealed many deficiencies in industrial preparedness, and although over one-third of the world output in essential minerals was credited to the United States at the beginning of the war period, the largest part of the raw materials found to be inadequately supplied included minerals and their derivatives. Interruption to the importation of a relatively few ores brought immediate realization of the industrial advantages of a domestic supply, and the coincident shortage in rail transportation showed that the disadvantage of an international long haul differs only in degree from that of too long an interstate haul. The premium that industry can afford to pay for the assurance of an uninterrupted supply of raw material provides the answer to this question of the emergency value of either national or local independence.

The proper valuation of national independence in raw materials therefore requires a careful weighing of the emergency factor, which introduces the insurance idea, as well as an estimating of future possibilities of lower costs as the industry develops. The incidental or the ultimate advantage may be so large as not to be seen by those who take too close a view of cost accounting or are shortsighted in their outlook on the Nation's business. The old contradiction of penny-wise and pound-foolish holds true to-day in matters of cents and dollars.

In every business there are elements of value that do not appear on the cost sheets. The war record of American business will not be complete except as it includes the story of those producers who kept up their output regardless of the losses involved—a type of patriotism not spectacular but exceedingly helpful. So, too, in time of peace there may be conditions under which, viewed in the larger way, it pays to do business at a loss.

A composite diagram of either current output or future reserves of the essential minerals for the countries of the world would show so large a centralization in North America as to suggest that here is a group of nature-favored nations. This strategic advantage expresses itself in the well-recognized large degree of self-sufficiency of the United States, so that the question of economic limits to domestic in-

Digitized by Google

dependence concerns a relatively small number of minerals and makes our problem quite different from that in other and less favored nations. However, whether the debatable list includes only chromite, manganese, pyrite, and potash or is much longer, clear analysis of the economic problem is needed, for cost keeping on a national scale is the only safeguard against a loss which is real even though not at once apparent.

Whether wisest utilization of mineral resources means full utilization is debatable, and every student of natural resources realizes that the time of utilization is often an element in the degree of wisdom shown. It is not necessarily prodigal wastefulness that only the richest ore is mined when a new district is discovered; creation of transportation facilities, construction of smelters and mills, and general advance in technology are the intermediate steps between bonanza exploitation and the highly organized operation of low-grade deposits. Utah had a long history as a mining State and its contributions to the world's wealth were large before Bingham started a new epoch in copper mining. So, too, the reworking of dumps and of tailings ponds furnishes illustrations of the complete utilization that is evolved in these changing conditions, and the appreciation of this truth should warn us against too hasty, off-hand determination of the economic limitations placed by nature upon mining development. By the very nature of things many successful mining ventures are at the start unprofitable, and many ore deposits can be fully developed only through actual mining operation. In a national sense it may prove that "nothing venture, nothing have."

The largest degree of national usefulness will be won from our mineral resources only through the highest industrial efficiency, which is in turn secured by engineering advance and the linking up of mechanical power and man power. This means to the end is typically American, but too much emphasis can not be put upon the importance of governmental action that is constructive in its cooperation with industry. While, unfortunately, public regulation seems to start usually with measures that are wholly restrictive in effect, because too often abuse of privilege has led to the legislative action, yet regulatory measures can be truly promotive, as has been shown in the recent cooperation of business and the Government. Public interest and private interest in the long run are less antagonistic than either the captain of industry or the public servant has suspected. It is true that the measure of economic worth must be the welfare of the individual, the community, and the people of the Nation, and not the dollar of profit to the corporation or the State, yet only a successful industry can be made to serve both owner and workman and the public as well. If the product is not actually worth its whole cost, no camouflage of bounty or tax exemption or import duty will long conceal the inherent weakness of the industry. The basic importance of the raw material resources to the country makes it a prime public duty of citizens generally to know the facts regarding the mineral industry, and to ascertain these facts the intensive study of our own resources is not enough: we must also acquire a comprehension of what minerals other countries contain to supplement what we have at home.

Digitized by Google

INTERNATIONAL CONTROL OF MINERALS.

By C. K. Leith.[1]

WORLD MOVEMENT OF MINERALS.

The annual world production of minerals approximates 1,700,000,000 tons, over 90 per cent of which consists of coal and iron. Of this amount about two-thirds is used within the countries where the minerals are produced and one-third is shipped to other countries. The mineral production of the United States amounts to about one-third of the total.

In the discussion of mineral resources in their international aspects we are concerned primarily with the 33 per cent of the mineral output which moves between countries. It may be assumed that the consumption within the countries of origin is a matter of national rather than international concern.

One of the several interesting facts in this world movement of minerals is that the movement of most of them shows a rather remarkable concentration. For instance, manganese moves from three principal sources and converges at four or five consuming centers. Chromite moves from two principal sources; tungsten also from two. Even for certain commodities which are widely distributed and move in large amounts the concentration of movement is rather marked—for instance, the world movement of coal is controlled by the United States, England, and Germany. In other words, although the world movement of mineral commodities is widespread and exhibits many complex features, most of the individual minerals follow two or three salient lines of movement. This means in general that for each mineral there are certain sources of limited geographic extent, which, because of location, grade, relation to transportation, cost—in short, all the factors that enter into availability—are drawn upon heavily for the world's chief demands. The convergence of these materials toward a few consuming centers indicates generally concentration of coal production necessary to smelting, high development of manufacturing, large per capita use, concentration of facilities, strong financial control, and, not least, a large element of enterprise which has taken advantage of more or less favorable conditions.

Another significant fact which emphasizes the interdependence of nations and the importance of international considerations is that no country is entirely self-sustaining in its mineral requirements.

[1] Mineral adviser of War Industries and Shipping boards.

Digitized by Google

MOVEMENT OF MINERALS UNDER PRE-WAR CONDITIONS OF INTERNATIONAL TRADE.

If the world pre-war movement of minerals is considered broadly, it may be regarded as conforming essentially to normal trade conditions of supply and demand. There have been barriers to overcome, such as tariffs and trade controls and monopolies of various kinds, but these barriers have not prevented the major movements between the best sources of supply and the principal consuming centers. These movements may be regarded as a more or less spontaneous internationalization of mineral resources by private enterprise. The aim of free trade or unrestricted commerce was equality of trade opportunities, but such conditions of unrestricted competition tended to concentrate trade in the hands of the strongest interests and to prevent equality of opportunity.

The efforts made to promote or hinder international mineral movement by tariffs, bonuses, embargoes, subsidies, transport control, patents, Government management, financial pressure, and other means have been incited mainly by national or imperial self-interest and have thus been to some extent inimical to an internationalization based on the principle of the greatest good to the greatest number. It may be supposed that in any effort to attain supernational or international control, motives and measures based on national self-interest of the sort here mentioned will continue to play an important part. The question to be determined is the extent to which national interest can and will be subordinated to international interest.

CHANGES BROUGHT ABOUT BY THE WAR.

The war wrought fundamental changes in the world movement of minerals. The character and distribution of the demands changed. Customary sources of supply were cut off. Financial disturbances and ship shortage profoundly modified the nature, distribution, and extent of the world movement. Our domestic mineral industry was abruptly brought to a realization of its vital relations with international trade. To illustrate, the large movement of manganese from India and Russia to the United States was abruptly stopped, and we had to develop a source of supply in Brazil. The stoppage of pyrite importations from Spain as a means of saving ships required the development of pyrite and sulphur supplies in the United States. The export of oil from the United States to European countries was greatly stimulated, and the export to other countries was correspondingly decreased. The world movements of coal were vitally affected, principally by the limitation of the coal shipments from England and the United States to South America and the concentration of shipments to European countries. The closing of German coal supplies to near-by countries had far-reaching consequences. The cutting off of the German potash left the world for the time being almost unsupplied with this vital fertilizing ingredient. The Chilean nitrates, on which the world had relied for fertilizer, were diverted almost exclusively to the manufacture of powder. The total annual imports of mineral commodities into the United States were reduced by 1,200,000 tons. Our exports, though they continued in large vol-

Digitized by Google

ume, were mainly concentrated in Europe. The story of these disturbances in the world movement of minerals, though highly interesting, is too long to be told here.

INTERNATIONAL CONTROL AS A WAR MEASURE.

Out of these sweeping and rapid changes in the world movement of mineral commodities there arose, partly as cause and partly as effect, international agreements for the allocation of minerals, as a means of insuring the proper proportions of supplies to the different countries for the most effective prosecution of the war. Inter-Allied purchasing committees in London and in Paris found it necessary to make an inter-Allied allocation of the output of Chilean nitrate, because the sum of the demands exceeded the total supply by a considerable fraction, and to agree on distribution and price of the world's supplies of tin, tungsten, and platinum. For many other commodities agreements of various sorts were made. For instance, the United States entered into an agreement with England and France for the purchase of iron ore and molybdenum from Scandinavia to keep it out of Germany. The United States and England agreed as to supplying Canada with ferromanganese. New problems of world allocation came up almost daily.

POSSIBILITY OF POST-WAR INTERNATIONAL CONTROL.

We now face the immediate and pressing question whether the centralized international control required by the war shall be retained or extended as a means of furthering the aims of a league of nations. When such a league was first proposed emphasis was placed mainly on political and military considerations. It now seems to be recognized that these are so closely interlocked with economic considerations that any league of nations, to be effective as a means of minimizing future international discord, must make provision for some degree of international or supernational control of business. Recent statements by officials of Great Britain and France seem to indicate a definite purpose to urge such control.

Some of the reasons which have been urged for the international control of the movements of minerals are as follows:

1. To insure equitable distribution of certain minerals, such as tungsten, vanadium, platinum, and gold, of which there may be a world shortage.

2. To mitigate a world shortage of ships by international allocation of ship space, which would entail limitations on the movement of minerals.

3. To prevent nations which are more advantageously situated in regard to finance, location, and general control of trade from monopolizing the business in any commodity at the expense of other nations—in other words, to insure equality of opportunity in regard to basic raw materials. The control of many mineral commodities now approaches national monopoly.

4. To reach some agreement as to division of markets for commodities such as iron, steel, and coal, which are available in so great abundance that several of the larger nations have considerable ex-

Digitized by Google

portable surplus, in order to prevent international difficulties due to unrestricted competition.

5. To maintain equilibrium of price.

6. To insure common and equitable contribution of supplies for rehabilitation of the devastated countries.

7. To serve as a means of disciplining any nation that will not conform to any code or control established by a league of nations. To many this has been a dominant consideration.

8. In general to prevent economic friction that might vitiate any world political agreements.

9. To replace the crude and cumbersome arrangements for international control through complex treaties and tariffs by a more centralized system.

The foregoing is merely a list of suggestions that have been made; it is not a unit statement of the requirements of the situation.

SPECIFIC PLANS OF INTERNATIONAL CONTROL OF MINERALS.

The various schemes proposed to meet these requirements center fundamentally about allocation of supplies.

There seem to be two main lines of approach to this problem. One leads to equality of economic opportunity through means expressed as follows by the League of Free Nations Association of New York:

(*a*) No state shall accord to one neighbor privileges not accorded to others—this principle to apply to the purchase of raw material as well as to access to markets.

(*b*) States exercising authority in non self-governing territories shall not exercise that power as a means of securing a privileged economic position for their own nationals; economic opportunity in such territories shall be open to all peoples on equal terms, the peoples of nations possessing no such territories being in the same position economically as those that possess great subject empires. Investments and concessions in backward countries should be placed under international control.

(*c*) Goods and persons of the citizens of all states should be transported on equal terms on international rivers, canals, straits, or railroads.

(*d*) Landlocked states must be guaranteed access to the sea on equal terms both by equality of treatment on communications running through other states, and by the use of seaports.

The other main line of approach to the problem leads to definite international allocation of raw materials as a means of preventing the strong nations from crowding out the weak, an inequity which would be possible under even ideal arrangements for insuring equal economic opportunities. More specifically it is proposed that the exportable surplus of selected minerals from the countries that enter into a league of nations shall be distributed as may be mutually agreed. This proposal means presumably continuance of Government control of international trade through licenses and ships. It means a curbing of private initiative and a sacrifice of the self-interest of the stronger in favor of the weaker.

The purpose of this paper is to discuss some of the specific relations of this arrangement to the mineral industry of the United States, that we may weigh the advantages and disadvantages of international control.

Digitized by Google

POSITION OF THE UNITED STATES IN REGARD TO INTERNATIONAL CONTROL OF MINERALS.

The United States is more nearly self-sustaining in regard to mineral commodities as a whole than any other country on the globe. The following statement summarizes qualitatively our position:

1. Minerals of which there is an adequate supply or exportable surplus in the United States:
   - A. Minerals of which our exportable surplus dominates the world situation:
     - Copper.
     - Petroleum.
   - B. Minerals of which our exportable surplus constitutes an important but not a dominant factor in the world trade:
     - Sulphur.
     - Phosphates.
     - Silver.
     - Iron and steel.
     - Coal.
     - Cement.
     - Uranium and radium.
   - C. Minerals of which our exportable surplus is not an important factor in world trade. Small amounts of most of these minerals have been and will doubtless continue to be imported because of special grades, backhaul, or cheaper sources of foreign supply, but these imports are for the most part incidental:
     - Lead.
     - Zinc.
     - Aluminum and bauxite.
     - Gold.
     - Tungsten.
     - Molybdenum.
     - Asphalt and bitumen.
     - Pyrite.
     - Barite.
     - Fluorspar.
     - Building stone (except Italian marble).
     - Cadmium.
     - Gypsum.
     - Lime.
     - Tripoli and diatomaceous earth.
     - Mineral paints (except umber, sienna, and ocher from France and Spain).
     - Pumice.
     - Garnet.
     - Salt (except special classes).
     - Talc.
     - Arsenic.
     - Bismuth.
     - Bromine.
     - Artificial abrasives, corundum, and emery (except Naxos emery).
     - Fuller's earth.
     - Mercury.
2. Minerals for which the United States demand must continue to be met by imports:
   - A. Minerals for which the United States must depend almost entirely on other countries:
     - Tin.
     - Nickel.
     - Platinum and metals of the platinum group.

Digitized by Google

2. Minerals for which the United States demand must continue to be met by imports—Continued.
   B. Minerals for which the United States will depend on foreign sources for a considerable fraction of the supply:
      Antimony.
      Vanadium.
      Zirconium.
      Mica.
      Monazite.
      Graphite.
      Asbestos.
      Ball clay and kaolin.
      Chalk.
      Cobalt.
      Naxos emery.
      Grinding pebbles.
3. Minerals normally imported into the United States which in future can be largely produced from domestic sources if it seems desirable:
   A. The following minerals were mainly imported before the war, but under war conditions the domestic resources have been developed to such an extent that the United States can become self-sustaining if desirable, though at so great a cost that a protective tariff will be necessary if these industries are to survive:
      Nitrates (except potassium nitrates).
      Potash.
      Manganese.
      Chromite.
      Magnesite.

No attempt will be made here to present the detailed figures on which the above generalizations are based. In view of the present disturbance in production and consumption, any judgment as to future demands or available surplus must take into account several factors which can not be accurately measured, such as financial control in foreign countries, possible tariffs, and foreign competition. For this reason the above statement should be regarded as only tentative, though it is the result of a rather exhaustive study of conditions in relation to the world control of shipping. The classes named overlap to some extent, and it is to be expected that some of the commodities placed in one class may in the near future be transferred to another.

GENERAL CONCLUSIONS AS TO THE INTERNATIONAL CONTROL OF MINERALS FROM THE STANDPOINT OF THE UNITED STATES.

1. It is clear that a league of nations offers but little advantage as a means of insuring adequate supplies for the United States, and that the limitations on the distribution of exportable mineral supplies would probably weigh more heavily on the United States than on any other country. The few minerals for which the United States is dependent on foreign countries are offset by so many in which we have a dominance of supply and our financial position is so strong that it appears certain that the United States does not need the aid of a league of nations to insure adequate supplies even of these few minerals. In short, in this respect our entrance into a league of nations would not be based on self-interest. We would sacrifice to some extent an independent and dominant position. In our dealings with other nations this fact should give weight to whatever emphasis the United States may wish to put on the desirability of international

Digitized by Google

control of minerals. At the same time it imposes a hard task on the United States to arouse the mineral interests to the support of a measure that involves so much self-sacrifice. The value of our annual potential exportable surplus of minerals approximates a billion dollars; that of our necessary mineral imports about $175,000,000. Our active allies, Great Britain, France, and Italy, together have a maximum annual exportable surplus worth perhaps $325,000,000, and their necessary imports amount to $265,000,000.

2. It seems clear that our effort to make this country entirely self-sustaining in regard to raw materials, which has been especially marked during the war, will need to be modified if we are to adapt ourselves to conditions of international control. Although we may be able to become self-sustaining in respect to essential commodities like manganese, chromite, and potash, by so doing we are cutting off the export market of other countries where these commodities exist in such quantities and grades that they would be, under conditions of free trade, our principal sources of supply. By drawing on such sources we not only get a cheaper and higher grade of product, but we develop a return market for the products in respect to which our natural advantages entitle us to a share in the export trade. The potash situation will illustrate the problem. The war cut off German supplies. We made every possible effort to meet the deficiency. Prices rose tenfold. Now, are we to continue this effort at high cost? Our instinctive answer is, Yes. But suppose at the peace table it is mutually agreed that for the welfare of France and Spain we should absorb a certain part of their output, or even that we should take German potash as an indirect way of collecting indemnity? This question is put for the purpose of making the problem concrete, and no answer is attempted here, though I venture to suggest that the practicable course will be found to lie between the two extreme alternatives.

If all countries take the stand that they must be self-sustaining in regard to natural resources, they can accomplish their purpose only by high artificial barriers to offset inequalities in the factors which determine the availability of the several commodities, with the result that the world movement of raw materials will be greatly lessened. Instead of free circulation of essential basic commodities vitalizing any world agreement there will be a series of compartments in which trade is maintained at different levels, under different pressures and conditions—a situation difficult to maintain and inimical to world agreements based on mutual concessions. It is clear that if each of the States of the United States should adopt the principle of making the State self-sustaining in minerals so far as possible, the result would be to increase largely the chances of interstate friction and to lower efficiency in the United States as a whole.

3. Following President Wilson, the League of Free Nations Association, before quoted, states: "Equality of economic opportunity does not mean the abolition of all tariffs or the abolition of the right of self-governing states to determine whether free trade or protection is to their best interests." If the view expressed in conclusion 2 is correct, it follows that the United States, as a member of a league of nations, would not be free to impose tariffs dictated by national self-interest beyond such minor duties as might tend to equalize the

Digitized by Google

labor element of cost of production. Also, when we remember the remarkable degree to which many of the leading mineral commodities are geographically concentrated, it is clear that a tariff on any particular commodity will usually affect mainly some one or two foreign nations—a result which does not accord with the principle that a state shall not give to one neighbor privileges that it withholds from others.

More might be said for a temporary tariff designed to let down easily, for example, the manganese, chromite, and potash industries, which face large losses because of overdevelopment to meet war needs. The Mineral Act perhaps might be used for this purpose. If this principle were adopted for a few minerals, however, it probably would soon be extended to others and into more general nonmineral fields, thereby presenting a problem of enormous difficulty.

In passing it may be noted that as long as shipping is inadequate, as it may be for some years, high and slowly declining freight rates may serve much the same purpose as a tariff for low-priced commodities of much bulk, like manganese, though not for high-priced commodities like tungsten.

Something might also be said for tariffs intended to insure the smelting of ores and their conversion to usable forms within the country of origin, thus reducing the tonnage to be transported and supporting the largest industry within the country; but it must be remembered that the distribution of coal resources and centers of production marks certain world centers of smelting and manufacturing, which are entitled by natural advantage to an unhampered movement of raw materials from other countries.

The question of protective tariffs is becoming acute at present, owing to the release of the restrictions imposed by the War Trade Board as a means of saving ships.

4. The interests of conservation clearly call for an international viewpoint in the handling of our mineral resources. The deposits of most minerals are so highly concentrated in their distribution and general availability that the principal sources for the world are in comparatively few places. When all factors of conservation are taken into account, including labor and efficient use of the product, it would seem that the minerals should be drawn from these natural sources of supply. To illustrate, the chromite and manganese deposits of the United States are relatively small and of low grade as compared with other sources of supply. Insistence on the use of the domestic material would mean early exhaustion of local supplies, lowered efficiency in use, and higher cost. As cost includes not only the intrinsic value of a product but items for labor and transportation, it appears that the use of these domestic materials means a higher expenditure of human effort than is necessary.

There is perhaps as much need of specializing in mineral output as there is of specializing in manufacturing. The thought that every country on the globe should be self-sustaining in regard to mineral supplies is of somewhat the same order as the thought that every family should produce all its own raw materials rather than take advantage of the more favorable conditions existing elsewhere and so specialize in human effort. If for a certain amount of capital and labor we can produce copper more cheaply than any other country

Digitized by Google

and thus dominate the world's markets, it is not economy to divert this capital and labor to the production of ores of manganese or chromite, which because of natural conditions can be produced much more cheaply elsewhere.

5. Extension of international control of minerals seems to offer possibilities of loss and gain—loss through a considerable sacrifice of national trade and a narrowing of the field for private initiative in trade; gain through the possibility of attaining certain ends which are attainable only by international agreement, such as an allocation of supplies which will be to the advantage of the greater number of nations rather than to the advantage of the few that are strong enough to dominate the situation and which will in general prevent economic friction from endangering a league of nations based on political and policing considerations.

In a world governed by good will the effective internationalization of trade might well be gained by leaving trade unrestricted. In proportion as the actual condition may depart from this ideal condition, some sort of international agreement as to control seems justified. Such control would by no means eliminate international rivalries and jealousies; it would transfer them to the international governing body. The duties of such a body would be onerous and perplexing. It might even be supposed that nationalistic aspirations might be so strenuously presented and so firmly backed by national steps in the way of embargoes and protective tariffs that the international control would amount to little. But it may be further supposed that a league of nations whose members enter into it voluntarily and with mutual good faith might control the situation sufficiently to bring recalcitrant members into line. The questions thus suggested are difficult to answer.

6. It is sometimes argued that any attempt to control the movement of raw materials, for whatever purpose, defeats itself because it leads to the automatic development in the restricted area of increased exploration, new sources of supply, substitutions, etc. Restriction unquestionably has this effect, but nevertheless such measures are expensive makeshifts and offset the effects of limitation only in part, as is clearly proved by the experiences of the war.

7. The purpose of this paper is primarily to state the problem of international control of minerals, rather than to present an argument for it. Such control entails difficulties which are especially burdensome on the United States and which at present may be insuperable. The interests of conservation clearly require international control. Moreover, the lesson of the war points to the necessity of overhauling old international understandings and machinery, even though such a task would encounter great difficulties, not the least of which lie in the persistence of human habits and inertia. Whether the time has come to establish a league of nations with economic control can be determined only by our individual and collective answers to the question whether we are willing to make the necessary economic sacrifices, individually and nationally, in the interest of world harmony. The mineral industry should fully understand that with international control efforts to promote export will need to be modified and curtailed; that expansion of our trade in many lines will mean equivalent loss of trade to other nations; that the almost

Digitized by Google

universal conception that expansion of foreign trade is a meritorious aim and end in itself, without regard to its effect on other countries, will need revision. It is necessary only to cite the present movement to create great export associations under the Webb Act to show that present tendencies for definite action do not take into account the possible conflict of such action with the economic requirements of a league of nations.

8. Whatever action may be taken in regard to international control, it is clear that the war has brought the United States into such world relations that it has become imperative for us to study and understand the world mineral situation much more comprehensively than before, in the interest not only of intelligent management of our own industries but of far-sighted handling of international relations. When the European war began we found our mineral industries vitally affected by international developments which we only partly understood. Government mineral organizations, as well as those outside the Government, had given relatively little attention to foreign mineral resources and markets. Information and statistics were scattered and incomplete. Under the stress of war the Government, especially the Geological Survey, the Bureau of Mines, and the several war boards, found it necessary to use extraordinary efforts to obtain even elementary information on the international features of mineral trade. Much progress has been made, but only a start. I would like to make a plea for definite recognition of the necessity of a systematic study of the world's mineral resources from the world's standpoint to supplement the studies made of the domestic resources, both by the mineral industry itself and by governmental and other agencies. A plan is under way to transfer the special mineral activities of the war boards to the Department of the Interior. This will throw additional burdens on the Bureau of Mines and the Geological Survey. It is equally clear that organizations like the American Institute of Mining Engineers and our technical publications have the same reason for extending their current surveys of mineral conditions to cover the world.

Digitized by Google

MINERAL PRODUCTION OF THE UNITED STATES.

INTRODUCTION.

By H. D. McCaskey.

SCOPE OF REPORT.

The two parts of the report Mineral Resources of the United States (Part I, Metals, and Part II, Nonmetals), of which this chapter forms the introduction and summary, constitute the final official record of the mineral production of the United States for the year 1917. The statistical work on minerals during this war year was in general carried on in greater detail, on a basis of greater frequency, and with greater expedition than in any previous year, in order to supply the Government and the public with a part of the economic information required for successful military operations. The information collected was placed immediately and informally at the disposal of the war boards and the military branches of the Government, and much of it was promptly made public through the newspapers and the technical press. The expansion of the informational service on minerals with little or no increase either in funds or in personnel was accomplished by more arduous work and longer hours, and by the abandonment, for the time being, of some classes of Geological Survey work that were not of war utility. It has resulted, also, in delaying the preparation of a number of the chapters of Mineral Resources. These chapters were, however, published in separate form as fast as completed, many of them months or even a year in advance of the assembled report.

Mineral Resources for 1917 contains the statistics of production in the United States, the imports and exports for that year and for several preceding years, and the records of important new developments during 1917. The reader in search of full information in regard to a particular mineral industry is advised to consult also the volumes of Mineral Resources for previous years, in which many details not repeated in later reports will be found. For statistics carried forward, however, the reader should consult the latest volume, as it contains any revision made, not only of the reports for the years preceding but also of the reports published separately in advance of the volume. Each volume is a supplement to all that have preceded. Special features of an industry are discussed more fully in some years than in others. The volumes issued during the past decade and containing particularly full reviews of the several mineral industries are listed below. Figures of production and value of each mineral since 1880, by years, are given in the summary of mineral production for 1915.

Digitized by Google

Mineral Resources volumes, 1908–1917, which contain particularly full reviews of various industries.

Mineral.	Year.	Special features.
METALLIC.		
Aluminum	1914	Bibliography.
Antimony	1916	Do.
	1917	Full report.
Arsenic	1914	Do.
	1915	Bibliography.
Bauxite	1914	Do.
	1917	List of users.
Bismuth	1914	Full report.
	1915	Bibliography.
Cadmium	1908	Full report.
Chromic iron ore	1914	Bibliography.
	1916	Sectional drawings; additional bibliography.
	1917	Map of North America showing location of known deposits of chromic iron ore; list of mine owners.
Copper	1915	Map of United States showing location of copper-producing districts and reduction plants (pocket).
	1917	Maps; plates; foreign data.
Gold, silver, copper, lead, and zinc (mines reports):		
Alaska	1915	Gold production since 1880, by years and producing districts.
	1917	Metal production since 1880, by years.
Arizona	1914	Bibliography of Survey publications.
	1917	List of reduction mills, by counties.
California	1912	Do.
Central States	1914	Historical sketch of lead and zinc mining in upper Mississippi Valley region.
	1917	Bibliography of Survey publications.
Colorado	1911	Flow sheet of Leadville ores.
	1912	List of reduction mills, by counties; bibliography of Survey publications.
Eastern States	1912	Bibliography of Survey publications.
	1914	Historical review of gold production of southern Appalachian States since 1799; additional bibliography.
Idaho	1911	List of reduction mills, by counties.
	1913	Ore sold or treated, number of producers, and metal output of Coeur d'Alene region since beginning of mining in 1884, by years.
	1914	Metal production of State since beginning of mining in 1863, by 10-year periods; metal production of Blaine (Alturas) County since 1880, by years; gold and silver production of Boise County since 1863, by years; gold and silver production of Owyhee County since 1863, by years; bibliography of Survey publications.
Montana	1911	List of reduction mills, by counties.
	1913	Metal production of Silver Bow County since 1882, by years.
	1914	Bibliography of Survey publications.
Nevada	1911	List of reduction mills, by counties.
	1912	Zinc-lead ore dressing at Goodsprings, with flow sheet of mill.
	1914	Bibliography of Survey publications.
New Mexico	1912	List of reduction mills, by counties; bibliography of Survey publications.
Oregon	1912	List of reduction mills, by counties.
	1913	Bibliography of Survey publications.
South Dakota	1914	Gold and silver production since 1876, by years; bibliography.
	1917	List of reduction mills, by counties.
Texas	1912	List of reduction mills, by counties; bibliography of Survey publications.
	1914	Metal production since 1885, by years.

Digitized by Google

Mineral Resources volumes, 1908–1917, which contain particularly full reviews of various industries—Continued.

Mineral.	Year.	Special features.
METALLIC—continued.		
Gold, silver, copper, lead, and zinc (mines reports)—Continued.		
Utah	1911	List of reduction mills, by counties; flow sheet of Park City ore.
	1913	Ore sold or treated, number of mines producing, and metal output of State since 1865, by years; of Beaver County since 1860, by years; of Tintic district since beginning of mining in 1869, by years; of West Mountain (or Bingham) district since 1865, by years; of Park City mining region since 1870, by years.
	1914	Ore and metal production of American Fork district, 1870–1900, by 10-year periods, and 1901–1914, by years; of Big and Little Cottonwood mining districts since 1867; bibliography of Survey publications.
Washington	1911	List of reduction mills, by counties.
	1913	Ore sold or treated, number of mines producing, and metal output since beginning of mining in 1860, by years.
	1914	Bibliography of Survey publications.
Wyoming	1914	Metal production since 1842, by years.
	1916	Ore and metal production of Albany County since 1868; of Carbon County since 1898, by years; of Hartville district, Platte County, since 1882.
	1917	List of reduction mills, by counties.
Iron	1908	Maps showing distribution of ore and location of blast furnaces (pocket).
	1909	Map showing distribution of Lake Superior iron ore (pocket).
	1911	Iron ore reserves of Michigan, with map, by C. K. Leith; notes on prospecting.
	1915	Beneficiation of Lake ores.
	1916	Essential features of a deposit; bibliography.
Lead	1915	Bibliography (in chapter on zinc).
Manganese and manganiferous ores.	1917	Full report with bibliography.
Nickel	1915	List of nickel minerals; forms of occurrence; nickel resources of United States; analyses of nickel alloys; bibliography.
Platinum and allied metals.	1914	Assaying.
	1915	Mining; bibliography.
	1916	Occurrence.
	1917	Uses.
Quicksilver	1917	Map of United States showing known quicksilver deposits; map showing those quicksilver deposits of world from which some output is on record; bibliography.
Selenium	1914	Full report.
	1915	Bibliography.
Tellurium	1914	Full report.
	1915	Bibliography.
Tin	1917	Map showing world's output of tin in 1916; bibliography.
Tungsten	1910	Occurrence in United States.
	1911	Uses.
	1912	Mining in Burma.
	1916	World's production; mining conditions; bibliography.
Uranium and vanadium (radium).	1912	Resources of United States and foreign countries with special maps and plates; bibliography.
	1915	Bibliography.
Zinc	1908	Full report.
	1915	Map of United States showing location of important zinc-producing districts, zinc smelters, zinc oxide plants, and electrolytic zinc plants.
Secondary metals	1917	Full report
NONMETALLIC.		
Asbestos	1912	Maps of United States; flow sheet of mill.
	1914	Maps of Arizona and California; illustrations of deposits.
	1916	Bibliography.
	1917	Map of Arizona; illustrations of deposits.

Digitized by Google

Mineral Resources volumes, 1908–1917, which contain particularly full reviews of various industries—Continued.

Mineral.	Year.	Special features.
NONMETALLIC—continued.		
Asphalt	1911	Classification; characteristics; foreign occurrence.
	1914	Bibliography.
	1917	Paved and unpaved streets in 185 cities of United States; production in principal countries.
Barytes	1914	Bibliography.
	1915	Map of United States showing location of barytes deposits and works manufacturing barium products; notes on geology of deposits.
Borax	1913	History of industry.
	1914	World's production; bibliography.
	1916	Map showing location of domestic deposits.
Briquets (fuel)	1915	Full report.
Bromine	1910	Map of United States showing location of salt deposits and bromine works (pocket).
	1917	Full report.
Calcium chloride	1910	Map of United States showing location of salt deposits and calcium chloride works (pocket).
	1916	Uses.
	1917	Method of making.
Cement	1910	Materials and industry of United States.
	1911	Technologic notes.
	1916	Map of United States showing distribution of plants and outlines of Portland cement commercial districts; standard specifications; bibliography.
	1917	Section on concrete ships; bibliography of concrete shipbuilding industry.
Clay	1910	Notes on kaolin of Real (Edwards) County, Tex.
	1912	Notes on the occurrence of different varieties of clays; their classification; their geologic and geographic distribution.
	1913	Notes on occurrence and use of flint clay; bibliography of its occurrence.
	1914	Bibliography of clay-working industries
Coal	1910	Maps of coal fields; bibliography.
	1914	World's production; additional bibliography.
	1917	Production; distribution; consumption.
Coke	1915	Map of United States showing distribution of coke ovens.
Cryolite	1916	Bibliography.
Feldspar	1915	Do.
Flint pebbles for grinding	1914	Bibliography on flint pebbles and substitutes therefor.
Fluorspar	1916	Bibliography.
	1917	Optical fluorite; buyers of fluorspar.
Garnet (abrasive)	1913	Notes on abrasive garnet industry (in chapter on abrasive materials).
Gas (artificial) and by-products.	1915	Full report.
Gas (natural)	1908	Map of United States showing known productive oil and gas fields (pocket).
	1913	Analyses of gases; carbon black from natural gas.
	1914	Bibliography of Survey publications on oil and gas fields of United States (in chapter on petroleum).
Gems and precious stones	1915	Bibliography.
	1916	Selected bibliography for 1916.
	1917	List of gem names.
Graphite	1911	Foreign deposits (Ceylon in particular); bibliography.
	1913	Map showing location of principal graphite mines in Massachusetts, New Jersey, New York, and Pennsylvania; foreign deposits; bibliography.
	1917	World's production; additional bibliography.

Digitized by Google

Mineral Resources volumes, 1908–1917, which contain particularly full reviews of various industries—Continued.

Mineral.	Year.	Special features.
NONMETALLIC—contd.		
Gypsum	1910	Bibliography.
	1911	Occurrence in United States; additional bibliography.
	1913	Occurrence in United States.
	1916	Map of United States showing location of mills using domestic gypsum.
	1917	Uses.
Lime	1911	Analyses of lime and limestone by States and counties; notes on technologic investigations of lime; bibliography; maps showing location of limekilns in States east of Mississippi River (in chapter on stone).
	1912	Occurrence of limestone and uses to which adapted; maps showing location of limekilns in Great Plains and Rocky Mountain States (in chapter on stone).
	1913	Source, manufacture, and use of lime; additional bibliography; maps showing location of limekilns in States west of Rocky Mountains (in chapter on stone).
Lithium minerals	1916	Only report.
Magnesite	1913	Map of part of California showing distribution of magnesite deposits; uses; foreign occurrence; magnesia cement; bibliography.
	1914	Map of part of California showing distribution of magnesite deposits; derived products; additional bibliography.
	1917	Description of Washington deposits.
Mica	1912	Bibliography.
	1916	World's production.
Mineral paints	1913	Bibliography.
	1914	Additional bibliography.
Mineral waters	1911	Concentration of mineral waters in relation to therapeutic activity.
	1913	Bibliography of published analyses of American mineral waters; discussion of their radioactivity; selected bibliography on radium, radioactivity, and radiotherapy.
	1916	Comparison of American and European mineral waters; bibliography on mineral waters, chiefly American.
Monazite	1911	Bibliography.
	1916	Full report and additional bibliography.
Natural gas	.....	See "Gas (natural)."
Oilstones	1911	Oilstones in Arkansas (in chapter on abrasive materials).
Peat	1917	Map of United States showing distribution of peat deposits; industry in foreign countries; bibliography.
Petroleum	1908	Map of United States showing known productive oil and gas fields (pocket).
	1913	Analyses of various oils.
	1914	Bibliography of Survey publications on oil and gas fields of United States.
Phosphate rock	1915	Map of United States showing location of phosphate deposits; conservation; substitutes; tests; bibliography of Survey publications.
Potash	1917	Full report with map, analyses, and bibliography.
Pyrite	1910	Map of United States showing location of pyrite deposits (pocket).
	1917	Domestic deposits.
Salt	1910	Map of United States showing location of salt deposits (pocket).
	1914	Bibliography.
Sand and gravel	1909	Analyses of various sands.
	1911	Glass sand—requirements, preparation, deposits, and analyses.
	1912	Uses and definitions; bibliography.
	1915	Glass sand occurrence; weight per cubic yard of sand and gravel.
Slate	1911	Maps showing location of slate quarries in States east of Mississippi River (in chapter on stone).
	1912	Paper on commercial qualities of slate, by T. Nelson Dale; maps showing location of slate quarries in Great Plains and Rocky Mountain States (in chapter on stone).
	1913	Maps showing location of slate quarries in States west of Rocky Mountains (in chapter on stone).
	1914	Bibliography (in chapter on stone).
	1915	List of colors, uses, location of quarries, and names of producers.

Digitized by Google

Mineral Resources volumes, 1908–1917, which contain particularly full reviews of various industries—Continued.

Mineral.	Year.	Special features.
NONMETALLIC—contd.		
Sodium salts	1917	Full report.
Stone	1911	Maps showing location of stone quarries in States east of Mississippi River; requirements of limestone for glass making (in chapter on sand and gravel); analyses of limestone by States and counties (in chapter on lime).
	1912	Maps showing location of stone quarries in Great Plains and Rocky Mountain States; occurrence of limestone and uses to which adapted (in chapter on lime).
	1913	Maps showing location of stone quarries in States west of Rocky Mountains.
	1914	Domestic marble; basalt in paper-making machinery; bibliography.
	1916	Weights per cubic yard of various kinds of crushed stone.
Strontium ore	1915	Map of United States and Alaska showing location of strontium ore deposits.
	1916	Full report.
Sulphur	1910	Map of United States showing location of sulphur deposits (pocket); foreign deposits; map of Sicily.
	1916	Notes on all domestic deposits.
Sulphuric acid	1911	Manufacture from smelter fumes at Ducktown, Tenn.
Talc and soapstone	1912	Full report with maps showing location of talc mines and soapstone quarries of Atlantic States, talc mines of California, talc mines and mills of New York, and flow sheet of mill.
	1916	Bibliography of notable recent publications.
Zircon	1911	Bibliography.
	1916	Full report and additional bibliography.
Miscellaneous	1913	Discussion of mineral production by States (in chapter on mineral products of the United States).
	1915	Quantity and value of each mineral from 1880 to 1915, by years (in summary of mineral production).

For a brief historical review of the development of the mineral industries of the United States from 1880 to 1916, inclusive, the reader is referred to the introduction to Mineral Resources for 1916. For a statistical summary of mineral production going back to 1880 the reader is referred to the summary chapter, by Miss Martha B. Clark, in the volume of Mineral Resources for 1915.

VALUE ASSIGNED TO OUTPUT.

The value of the contribution or our metallic output to our industrial needs is best shown by determining the value of the refined or partly refined metal—the marketable product. This value is, of course, ordinarily greater than the value of the ores from which the products are obtained, and the movement of bullion, matte, and refined metal does not at all indicate the volume of ore transported by the railroads and other carriers or the demands made on the transportation lines by the mineral industry as compared with the agricultural and other industries. During recent years the compilation of the statistics of the production of pig iron has been supplemented by an accurate determination of the quantity and value of the iron ore produced, but the quantity and value of pig iron have been retained as units for the iron industry. Many of the ores of the precious and semiprecious metals are complex associations of several metals and gangues, and the same ore may have different values, or none. its value depending

Digitized by Google

on the metallurgic and other treatment it may require. The quantities and values of such ores are therefore best measured by the metal actually extracted from them and made marketable. Chromic iron ore, manganese ore, manganiferous ore, and bauxite, on the other hand, are marketed as such. The quantities and the values of the nonmetals are likewise placed upon the products in the condition in which they are first sold. The quantities and values of the fuels, phosphate rock, and some other nonmetals therefore represent raw or only very slightly dressed products, in the condition in which they first become articles of trade. Salt appears as the content of brine, in various refined conditions, or as rock salt. Gypsum is sold as crude, as ground, or as calcined. Cement, however, is the commercial product reported, rather than the raw material from which it is made. The clay products, except very small quantities of special clays that are sold raw, first appear in statistics as brick, terra cotta, tile, porcelain, pottery, etc. As quarry products are sold in three forms—rough, partly dressed, or finished—there is no way of determining their quantities and values except by considering them in the condition in which they are first marketed.

ACKNOWLEDGMENTS.

The United States Geological Survey is in touch with practically all mineral producers, smelters, refiners, and millmen in this country; with many manufacturers, exporters, and importers of mineral products; and with most operators of prospects, mines, quarries, and wells not producing but undergoing some development or merely held by development work; and it is therefore impossible to make more than general acknowledgment for the vast amount of data contributed by them. Opportunity is taken here, however, to make this acknowledgment as best it may be made and to express grateful appreciation of the trouble taken by correspondents to make the reports of real value. The total number of these correspondents was well over 100,000 in 1917. In the few months succeeding the entrance of the United States into the world war Survey geologists made special field investigations of mineral resources urgently needed and received many courtesies and much aid in this work. Special acknowledgment is made to the miners and millmen for these personal courtesies. Not only through the mails, but also by conferences and by field work of its specialists, the United States Geological Survey continues to keep in close touch with every branch of the mineral industries, and the value of its reports is therefore unique.

ORGANIZATION.

The division of mineral resources of the United States Geological Survey, which is responsible for the annual reports "Mineral Resources of the United States" and related work, was divided during 1917 as in previous years into two sections—the "metals section," which prepares the reports of Part I, and the "nonmetals section," which prepares those of Part II, including fuels, structural materials other than metals, chemical materials, mineral fertilizers, and other nonmetallic products. G. F. Loughlin was the geologist in charge of the nonmetals section, and the writer was charged with adminis-

Digitized by Google

trative supervision of the division, of the metals section, of the western offices, and of cooperative relations with the State geologists.

The western offices were established primarily for the collection and compilation of data for the annual mines reports on the precious and base metals of the Western States, but they have been brought so closely into touch with the mineral industries from the Rocky Mountains to the Pacific coast generally that they now cooperate with the Washington office on many branches of the mineral-resources work and also serve the mining industries and the public at large throughout the West as general bureaus of information and of distribution of Survey publications. The statisticians in charge, all of whom are technically trained along mineral lines, are Charles W. Henderson, 409 New Post Office Building, Denver, Colo.; Victor C. Heikes, 312 Post Office Building, Salt Lake City, Utah; and Charles G. Yale, 305 Customhouse, San Francisco, Calif. Mr. Henderson is author of the mines reports for Colorado, South Dakota, Wyoming, New Mexico, and Texas; Mr. Heikes (assisted by C. N. Gerry) is responsible for the mines reports for Utah, Nevada, Arizona, Montana, Idaho, and Washington; and Mr. Yale contributes the mines reports for California and Oregon, and is coauthor also of the reports on borax and magnesite for the entire country.

The division of mineral resources works in close cooperation with other divisions of the geologic branch, and most of the reports on mineral resources have been written in recent years by geologists working in more than one division, who specialize on the subjects treated by them. The advantage of this arrangement is to utilize the full resources of the Survey in the service of specialists familiar with the occurrence, treatment, and use of the mineral substances covered.

The authors of the reports for 1917 were as follows:

General:
- G. O. Smith—The economic limits to domestic independence in minerals.
- C. K. Leith—International control of minerals.
- H. D. McCaskey—Mineral production of the United States (introduction).
- Martha B. Clark—Mineral production of the United States (summary).

Metals:
- E. S. Bastin—Antimony.
- E. F. Burchard—Iron ore, pig iron, and steel.
- B. S. Butler—Copper; silver and copper in Michigan (mines reports).
- J. S. Diller—Chromite.
- J. P. Dunlop—Silver, copper, lead, and zinc in Central States, except Michigan (mines reports); secondary metals; gold and silver (with H. D. McCaskey).
- C. N. Gerry—Gold, silver, copper, lead, and zinc in Idaho and Washington (mines reports).
- V. C. Heikes—Gold, silver, copper, lead, and zinc in Arizona, Montana, Nevada, and Utah (mines reports).
- C. W. Henderson—Gold, silver, copper, lead, and zinc in Colorado, New Mexico, South Dakota, Texas, and Wyoming (mines reports).
- F. L. Hess—Cobalt, molybdenum, nickel, titanium, tungsten, radium, uranium, and vanadium.
- D. F. Hewett—Manganese and manganiferous ores.
- J. M. Hill—Bauxite and aluminum; gold, silver, copper, lead, and zinc in Eastern States (mines reports); platinum and allied metals.
- Adolph Knopf Tin.
- H. D. McCaskey—Gold and silver (with J. P. Dunlop).
- G. C. Martin—Gold, silver, copper, and lead in Alaska (mines reports).
- F. L. Ransome—Quicksilver.
- C. E. Siebenthal—Cadmium; lead; zinc.
- R. W. Stone—Magnesium.
- J. B. Umpleby—Arsenic, bismuth, selenium, and tellurium.
- C. G. Yale—Gold, silver, copper, lead, and zinc in California and Oregon (mines reports).

Digitized by Google

Nonmetals:
E. F. Burchard—Cement; fluorspar and cryolite.
A. T. Coons—Stone (with G. F. Loughlin).
J. S. Diller—Asbestos; talc and soapstone.
A. J. Ellis—Mineral waters.
H. G. Ferguson—Graphite.
H. S. Gale—Potash (with W. B. Hicks).
W. B. Hicks—Potash (with H. S. Gale).
J. M. Hill—Barytes and barium products; strontium.
F. J. Katz—Abrasive materials; feldspar; silica.
C. E. Lesher—Coal; coke (with W. T. Thom, jr.); fuel briquetting.
G. F. Loughlin—Lime; slate; stone (with A. T. Coons).
Jefferson Middleton—Clay-working industries and building operations in the larger cities; fuller's earth; sand-lime brick.
J. D. Northrop—Asphalt, related bitumens, and bituminous rock; natural gas and natural-gas gasoline; petroleum.
C. C. Osbon—Peat.
W. T. Schaller—Gems and precious stones; mica.
P. S. Smith—Sulphur, pyrites, and sulphuric acid.
R. W. Stone—Gypsum; magnesite (with C. G. Yale); phosphate rock; salt, bromine, and calcium chloride; sand and gravel.
W. T. Thom, jr.—Coke (with C. E. Lesher).
R. C. Wells—Sodium salts.
C. G. Yale—Magnesite (with R. W. Stone).

Once more the writer makes acknowledgment of the work done by his colleagues in the preparation of the reports and of the loyal and efficient service given by the statistical, clerical, and stenographic assistants. The group of specialists includes many of the ablest economic geologists, chemists, and engineers of the Survey, and the contributions they make are of special value because of their training in field and office, which especially fits them for the well-rounded study of their respective subjects. Many of the clerical staff have now been connected so long and in so responsible a way with the collection and tabulation of statistics assigned to them that they are most creditably identified with their subjects. Their intelligent scrutiny and criticism of the returns and their skillful interpretation of the results are invaluable in saving the time of the specialists, and their conscientious devotion to duty has maintained the high standards set for accuracy and completeness of the reports.

COOPERATION WITH STATE GEOLOGICAL SURVEYS.

In the collection of data for the reports on mineral resources the United States Geological Survey has had since 1910 the cooperation of many of the corresponding State organizations. The statistics obtained by pooling efforts and field and office facilities are jointly checked and are the official figures of both State and Federal surveys. The objects aimed at in cooperation are mainly the avoidance of duplication of effort on the part of both compilers and operators, and also of divergent sets of figures bearing the official stamp.

Cordial acknowledgment for helpful and most satisfactory cooperation is made to the following State officials for the statistical campaign for 1917:

Alabama: Dr. Eugene A. Smith, State geologist, University.
Florida: Dr. E. H. Sellards, State geologist, Tallahassee.
Georgia: Dr. S. W. McCallie, State geologist, Atlanta.
Illinois: Mr. F. W. De Wolf, director, Urbana.
Iowa: Mr. George F. Kay, director, Iowa City.

Digitized by Google

Maryland: Dr. Edward B. Mathews, State geologist, Baltimore.
Michigan: Mr. R. C. Allen, director, Lansing.
Minnesota: Dr. W. H. Emmons, director, Minneapolis.
Missouri: Mr. H. A. Buehler, director, Rolla.
New Jersey: Dr. Henry B. Kümmel, State geologist, Trenton.
New York: Dr. John M. Clarke, State geologist, Albany.
North Carolina: Dr. Joseph Hyde Pratt, State geologist, Chapel Hill.
Oregon: Prof. H. M. Parks, director, Portland.
Pennsylvania: Mr. Richard R. Hice, State geologist, Beaver.
Virginia: Dr. Thomas L. Watson, director, Charlottesville.
Washington: Mr. Henry Landes, State geologist, Seattle.
Wisconsin: Dr. W. O. Hotchkiss, State geologist, Madison.

Informal cooperation has been had for some time past between the San Francisco and Washington offices of the United States Geological Survey, on the one hand, and the California State Mining Bureau, under Mr. F. McN. Hamilton, State mineralogist, assisted by Mr. Walter N. Bradley and Mr. E. S. Boalich, on the other; and a most cordial and generous assistance has always been given by this efficient California administration.

Many of the State mine inspectors also ably and cordially cooperated with the United States Geological Survey, especially with regard to the production of fuels.

Digitized by Google

SUMMARY.

By Martha B. Clark.

GENERAL REMARKS.

The unit of measurement used by the United States Geological Survey for each mineral product in the reports on the mineral resources is that common to the industry concerned, and the variation in these units makes it impracticable, if not impossible, to combine and compare the different minerals except in their value.

In 1899, for the first time, the total value of the mineral production of the United States exceeded $1,000,000,000; in 1905 and 1906 it was more than $1,500,000,000, and in 1907 it exceeded $2,000,000,000. Financial depressions and recoveries from 1907 to 1912 carried the value down and up, with a general advance to 1913, when the total was more than $2,441,000,000. In 1914 the value declined to about $2,118,000,000, but in 1915 it increased to nearly $2,398,000,000, falling short of the record value of 1913 by less than 2 per cent.

In 1916, owing to the demand for increased production of war minerals and to their greater value, especially the metals, the total value (nearly $3,515,000,000) was the greatest in the history of the country up to that time, increasing $1,117,000,000, or 47 per cent, over the $2,398,000,000 recorded for 1915 and exceeding the value of the former record year (1913) by more than $1,000,000,000.

In 1917 the value of mineral production reached a total of nearly $5,008,000,000, advancing $1,500,000,000, or more than 40 per cent, over the great value recorded in 1916. As may be clearly seen from the table on page 30a, this increase does not mean, however, that the mines of the United States contributed in 1917 an additional 40 per cent to the mineral needs of the world. There were decreases in the production of such essential metals as copper, iron, and lead, as well as of gold and silver, and also in the production of practically all building materials and in various other products. The decline in output was, however, not so general among the nonmetallic as among the metallic minerals. The furnace products (pig iron and ferroalloys) together with copper, coal, and petroleum, contributed nearly $3,708,000,000, or 74 per cent, of the total value of minerals produced, and their combined increases were $1,322,000,000, or 89 per cent, of the total increase.

The metals established a new record for value in 1917, exceeding for the first time $2,000,000,000 and representing 42 per cent of the value of all mineral products. They showed an increase of $466,000,000, or 29 per cent, over the former record of $1,620,000,000 in 1916. The increase in the furnace products (pig iron and ferroalloys) and copper was more than $464,000,000, or 99 per cent of the total increase in metallic minerals

Digitized by Google

The value of the nonmetallic products in 1917 was $2,891,000,000, or 58 per cent of the value of all minerals, increasing more than $1,013,000,000, or 54 per cent, from the former record of $1,878,000,000 in 1916 to $2,891,000,000 in 1917. The increase in coal alone was 66 per cent of the total increase of the nonmetals, and the combined increases of coal and petroleum were 85 per cent of that increase.

As heretofore, coal and iron were the most valuable of our mineral products. The value of coal in 1917 was $1,533,000,000, and that of iron (pig iron) $1,054,000,000. The fuels—coal, natural gas, and petroleum—increased from $1,318,000,000 in 1916 to nearly $2,198,000,000 in 1917, a gain of about $879,000,000, or 67 per cent.

The unspecified products (metallic and nonmetallic), valued in 1917 at $30,110,000 and including the value of antimony other than content of antimonial lead, bismuth, cadmium sulphide, chats or tailings from Missouri zinc mines, chert, a considerable production of diatomaceous earth for special uses, flint lining for tube mills, ilmenite, iron ore sold for magnets and paint, lithium minerals, lithographic stone, magnesium, marls, molybdenum, monazite, pebbles for grinding, selenium, silica sand and sandstone (finely ground), sodium salts (carbonate, bicarbonate, and sulphate) from natural sources, strontium ore, sulphur, and tellurium, and an estimate of the value of miscellaneous mineral products not collected annually by the Geological Survey, bring the total value of the mineral production for 1917 up to $5,007,937,000.

The arrangement of the minerals alphabetically in the metallic and nonmetallic groups will, it is believed, prove to be the most convenient form for reference. It is the plan of the Geological Survey to publish the figures in detail for all years beginning with 1880 in Mineral Resources every fifth year. The detailed figures for the early years appeared in the report for 1915 and will next be shown in the report for 1920. For the intervening years the mineral chart (showing 10 years in detail and totals for all years) will be inclosed in a pocket, as has been the custom in the past, and the chart showing production and value of mineral products through 1917 will be found in the pocket in this report.

The imports cited in this summary are imports "for consumption" (so far as such figures are available) for the calendar year and may or may not be identical with "general" imports. Merchandise brought into the country late in December, for example, may be entered for consumption, or it may be put into a warehouse and not withdrawn for consumption until the following calendar year. It is then credited "for consumption" to the year of its withdrawal from the warehouse.

From the totals shown in the following table, "Mineral products of the United States in 1916 and 1917," duplication has been eliminated wherever practicable. For instance, the value of the coke has been excluded from the totals, as the value of the coal used in its manufacture enters into the statistics of coal production. In mineral paints, the chemically manufactured pigments (white lead, red lead, lithopone, litharge, and orange mineral), whose aggregate value has exceeded $20,000,000 annually for the last 13 years, are not given in the table, as the base from which they are made is included in the output

Digitized by Google

of lead or zinc, whereas the zinc and lead pigments (zinc white or zinc oxide, zinc-lead, leaded zinc oxide, sublimed blue lead, and sublimed white lead) are included, being made in large part directly from the ores and therefore not entering into the lead or zinc totals. The value of the pig iron, rather than that of the iron ore, is included in the total, being considered the best means of presenting the statistics of iron in its first marketable condition. Similarly, the value of the products of the clay industries is included as representing the first marketable condition of the greater part of the clay produced. The quantity and value of the clay mined and sold in the raw state by miners to manufacturers of clay are shown separately, but the value is not included in the total.

Digitized by Google

Mineral products of the United States in 1916 and 1917.

Product.	1916		1917		Increase or decrease in 1917.		Percentage of increase or decrease in 1917.	
	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.
METALLIC.								
Aluminum.....pounds..		$33,900,000		$45,882,000		+ $11,982,000		+ 35
Antimonial lead [a].....short tons (2,000 pounds)..	24,038	4,483,582	18,646	3,781,560	− 5,392	− 702,022	− 22	− 16
Antimony [b].....do....	(c)	(c)	5,199	[b] 2,152,386				
Bauxite.....long tons (2,240 pounds)..	425,100	2,296,400	568,690	3,119,058	+ 143,590	+ 822,658	+ 34	+ 36
Cadmium.....pounds..	135,212	210,931	207,408	305,097	+ 72,196	+ 94,166	+ 53	+ 45
Chromic iron ore.....long tons..	47,035	726,243	43,725	1,049,400	− 3,310	+ 323,157	− 7	+ 44
Copper [d], sales value.....pounds....	1,927,850,548	474,288,000	1,886,120,721	514,911,000	− 41,729,827	+ 40,623,000	− 2	+ 9
Ferroalloys.....long tons..	589,738	50,281,692	634,021	83,731,724	+ 44,283	+ 33,450,032	+ 8	+ 67
Gold [e].....troy ounces..	4,479,056	92,590,300	4,051,440	83,750,700	− 427,616	− 8,839,600	− 10	− 10
Iron:								
Ore [f].....long tons..	77,870,553	[f] 181,902,277	75,573,207	[f] 238,260,444	− 2,297,346	+ 56,358,167	− 3	+ 31
Pig.....do....	39,126,324	663,478,118	38,612,546	1,053,785,975	− 513,778	+ 390,307,857	− 1	+ 59
Lead (re-fined) [d]. {1916: Value at New York City / 1917: Sales value}.....short tons..	552,228	76,207,000	548,450	94,333,000	− 3,778	+ 18,126,000	− .7	+ 24
Manganese ore (35 per cent or more Mn.)..long tons..	31,474	656,278	129,405	4,109,722	+ 97,931	+ 3,453,444	+ 311	+ 526
Manganiferous ore (5 to 35 per cent Mn.).....do....	544,326	1,976,630	860,944	3,406,061	+ 316,618	+ 1,429,431	+ 58	+ 72
Nickel [g] value at New York City.....short tons..	918	671,192	402	331,556	− 516	− 339,636	− 56	− 51
Platinum and allied metals (value at New York City).....troy ounces..	28,088	2,301,762	38,831	4,023,757	+ 10,743	+ 1,721,995	+ 38	+ 75
Quicksilver (value at San Francisco).....flasks (75 pounds net)..	29,932	3,768,139	36,159	3,808,266	+ 6,227	+ 40,127	+ 21	+ 1
Silver.....troy ounces..	74,414,802	48,953,000	71,740,362	59,078,100	− 2,674,440	+ 10,125,100	− 4	+ 21
Tin (metallic equivalent).....short tons..	140	122,000	110	135,600	− 30	+ 13,600	− 21	+ 11
Titanium ore (rutile).....do....	110	16,500	206	32,960	+ 96	+ 16,460	+ 87	+ 100
Tungsten ore (60 per cent concentrates).....do....	5,923	12,074,000	6,144	6,783,000	+ 221	− 5,291,000	+ 4	− 44
Uranium and vanadium minerals.....do....		500,000		617,000		+ 117,000		+ 23
Zinc [d] sales value.....do....	563,451	151,005,000	584,597	119,258,000	+ 21,146	− 31,747,000	+ 4	− 21
Total value of metallic products (approximate)..		1,620,507,000		2,086,234,000		+ 465,727,000		+ 29
NONMETALLIC.								
Arsenious oxide.....short tons..	5,986	555,187	6,151	1,118,313	+ 165	+ 563,126	+ 3	+ 101
Asbestos.....do....	1,479	448,214	1,683	506,056	+ 204	+ 57,842	+ 14	+ 13
Asphalt.....do....	786,811	7,102,132	782,713	8,470,615	− 4,098	+ 1,368,483	− .5	+ 19
Barytes (crude).....do....	221,952	1,011,232	206,888	1,171,184	− 15,064	+ 159,952	− 7	+ 16
Borax (crude).....do....	103,525	2,409,459	108,875	3,609,632	+ 5,350	+ 1,200,173	+ 5	+ 50
Bromine.....pounds..	728,520	951,932	895,499	402,703	+ 166,979	− 459,229	+ 23	− 48
Calcium chloride.....short tons..	[h] 27,709	[h] 224,997	30,503	451,480	+ 2,794	+ 226,483	+ 10	+ 101
Cement.....barrels (376 pounds net)..	95,394,433	104,689,090	91,342,930	123,210,488	− 4,051,503	+ 18,521,398	− 4	+ 18

Digitized by Google

Clay:												
Products			207,260,091		248,023,368		+	40,763,277			+	20
Raw[f]	short tons	2,932,500	[f] 5,751,774	3,113,844	[f] 8,042,546	+	181,254	+	2,290,772	+ 6	+	40
Coal:												
Bituminous[i]	do	502,519,662	665,116,077	551,790,563	1,249,272,837	+	49,270,881	+	584,156,760	+ 10	+	88
Pennsylvania anthracite	long tons	78,195,083	202,009,561	88,939,117	283,650,723	+	10,744,034	+	81,641,162	+ 14	+	40
Coke[f]	short tons	54,533,585	[f] 170,841,197	55,606,828	[f] 298,243,017	+	1,073,243	+	127,401,820	+ 2	+	75
Diatomaceous (infusorial) earth and tripoli			[f] 241,553		[f] 123,784			−	117,769		−	49
Emery (also corundum in 1917)	short tons	15,282	123,901	17,135	241,050	+	1,853	+	117,149	+ 12	+	95
Feldspar	do	132,681	702,278	141,924	728,838	+	9,243	+	26,560	+ 7	+	4
Fluorspar	do	155,735	922,554	218,828	2,287,722	+	63,093	+	1,365,068	+ 41	+	148
Fuller's earth	do	67,822	706,951	72,567	772,087	+	4,745	+	65,136	+ 7	+	9
Garnet for abrasive purposes	do	6,171	208,850	4,996	198,327	−	1,176	−	10,523	− 19	−	5
Gems and precious stones			217,793		131,012			−	86,781		−	40
Graphite:												
Amorphous	short tons	2,622	20,723	8,301	73,481	+	5,679	+	52,758	+ 217	+	255
Crystalline	pounds	10,931,989	914,748	10,584,080	1,094,398	−	347,909	+	179,650	− 3	+	20
Grindstones and pulpstones			766,140		1,147,784			+	381,644		+	50
Gypsum	short tons	2,757,730	7,969,032	2,696,226	11,116,452	−	61,504	+	3,157,420	− 2	+	40
Lime	do	4,073,433	18,509,305	3,786,364	23,807,877	−	287,069	+	5,298,572	− 7	+	29
Magnesite (crude)	do	154,974	1,393,693	316,838	2,899,818	+	161,864	+	1,506,125	+ 104	+	108
Mica:												
Scrap	do	4,433	69,906	3,429	52,908	−	1,004	−	16,998	− 23	−	24
Sheet	pounds	865,863	524,485	1,276,533	753,874	+	410,670	+	229,389	+ 47	+	44
Millstones			44,559		43,489			−	1,070		−	2
Mineral paints:												
Natural pigments[k]	short tons	(k)	(k)	(k)	(k)		(k)		(k)	(k)	(k)	
Zinc and lead pigments[l]	do	135,606	23,515,803	140,636	26,972,137	+	5,030	+	3,456,334	+ 4	+	15
Mineral waters	gallons sold	55,928,461	5,735,035	46,784,419	4,931,710	−	9,144,042	−	803,325	− 16	−	14
Natural gas			120,227,468		142,089,334			+	21,861,866		+	18
Natural-gas gasoline	gallons	103,492,689	14,331,148	217,884,104	40,188,956	+	114,391,415	+	25,857,808	+ 111	+	180
Oilstones, etc			154,573		168,704			+	14,131		+	9
Peat	short tons	52,506	369,104	97,363	709,900	+	44,857	+	340,796	+ 85	+	92
Petroleum	barrels (42 gallons)	300,767,158	330,899,868	335,315,601	522,635,213	+	34,548,443	+	191,735,345	+ 12	+	58
Phosphate rock	long tons	1,982,385	5,896,993	2,584,287	7,771,084	+	601,902	+	1,874,091	+ 30	+	32
Potash (K_2O)	short tons	9,720	4,242,730	32,573	13,980,577	+	22,853	+	9,737,847	+ 235	+	230
Pumice	do	33,320	82,263	35,298	84,814	+	1,973	+	2,551	+ 6	+	3
Pyrite	long tons	423,556	1,965,702	462,662	2,485,435	+	39,106	+	519,733	+ 9	+	26
Salt	short tons	6,362,906	13,645,947	6,978,177	19,940,442	+	615,271	+	6,294,495	+ 10	+	46

[a] From both domestic and foreign ores.
[b] From all sources. Values excluded from metallic totals as the values of the antimony contained in antimonial lead are included in the antimonial lead values, and the remainder under last item ("Unspecified").
[c] Figures not available. Estimate of value of the antimony other than that entering into antimonial lead included under last item ("Unspecified").
[d] Product from domestic ores only.
[e] Value, $20.671834625323 an ounce.
[f] Value not included in total value.
[g] By-product in electrolytic copper refining.
[h] Figures for 1916 revised in 1917.
[i] Includes brown coal and lignite, and anthracite mined elsewhere than in Pennsylvania.
[j] Exclusive of considerable production for special uses which is included under last item ("Unspecified").
[k] Canvass discontinued after 1915. Value of iron ore sold for paint included under last item ("Unspecified").
[l] Sublimed blue lead, sublimed white lead, leaded zinc oxide, zinc oxide, and zinc lead.

Digitized by Google

Mineral products of the United States in 1916 and 1917—Continued.

Product.	1916		1917		Increase or decrease in 1917.		Percentage of increase or decrease in 1917.	
	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.
NONMETALLIC—continued.								
Sand:								
Glass.....short tons..	2,018,317	$1,957,797	1,942,675	$2,665,014	− 75,642	+ $727,217	− 4	+ 37
Molding, building, etc., and gravel.....do....	87,073,415	27,852,198	74,476,650	32,611,918	− 12,596,765	+ 4,759,720	− 14	+ 17
Sand-lime brick.....	.....	1,474,073	.....	1,420,330	.....	− 53,743	.....	− 4
Silica (quartz).....short tons..	88,514	242,786	142,673	318,069	+ 54,159	+ 75,283	+ 61	+ 31
Slate.....	.....	5,338,837	.....	5,749,966	.....	+ 411,129	.....	+ 8
Stone.....short tons..	91,831,000	[a] 79,069,683	83,562,000	82,215,671	− 8,269,000	+ 3,145,988	− 9	+ 4
Sulphur.....long tons..	(b)	(b)	(b)	(b)	(b)	(b)	(b)	(b)
Sulphuric acid (60° Baumé) from copper and zinc smelters.....short tons..	[c] 1,162,391	14,099,927	[c] 1,455,257	16,890,545	+ 292,866	+ 2,790,618	+ 25	+ 20
Talc and soapstone (exclusive of fibrous talc)...do....	119,725	1,292,293	144,177	1,411,416	+ 24,452	+ 119,123	+ 20	+ 9
Talc, fibrous.....do....	93,236	961,510	74,671	881,462	− 18,565	− 80,048	− 20	− 8
Thorium minerals (monazite).....pounds..	37,872	3,400	(b)	(b)	.....	.....	.....	.....
Total value of nonmetallic products (approximate).....	.....	1,878,463,000	.....	2,891,593,000	.....	+1,013,130,000	.....	+ 54
SUMMARY.								
Total value of metallic products.....	.....	1,620,507,000	.....	2,086,234,000	.....	+ 465,727,000	.....	+ 29
Total value of nonmetallic products.....	.....	1,878,463,000	.....	2,891,593,000	.....	+1,013,130,000	.....	+ 54
Total estimated value of "unspecified" (metallic and nonmetallic) products [d].....	.....	15,630,000	.....	[d] 30,110,000	.....	+ 14,480,000	.....	+ 93
Grand total approximate value of all mineral products.....	.....	3,514,600,000	.....	5,007,937,000	.....	+1,493,337,000	.....	+ 42

[a] Figures for 1916 revised in 1917.
[b] Value included under last item ("Unspecified").
[c] Includes 92,802 tons in 1916 and 119,048 tons in 1917 of stronger acid, reported as oleum, etc., not converted to 60° Baumé.
[d] Includes in 1917 antimony other than content of antimonial lead, bismuth, cadmium sulphide, chats, chert, diatomaceous earth for special uses, flint lining for tube mills, ilmenite, iron ore sold for magnets and paint, lithium minerals, lithographic stone, magnesium, marls, molybdenum, monazite, pebbles for grinding, selenium, silica sand and sandstone (finely ground), sodium salts (carbonate, bicarbonate, and sulphate) from natural sources, strontium ore, sulphur, tellurium, and an estimate of the value of miscellaneous mineral products statistics for which are not collected annually by the Survey.

Digitized by Google

MINERAL PRODUCTION FROM 1880 TO 1917.

The following table and the accompanying diagram show the value of the mineral production of the United States from 1880 to 1917, by years, separating the totals into values for metallic, nonmetallic, and unspecified products. The same principles have been followed in the eliminating of duplication from the totals for the earlier years as were followed for 1916 and 1917. For statistical data regarding any mineral prior to 1880, the first year for which general mineral statistics are available, the reader should consult the special chapter on the mineral concerned. Detailed figures by minerals for the years 1908 to 1917 will be found in the chart which is inclosed in the pocket.

Total value of mineral products of the United States from 1880 to 1917.

Year.	Metallic.	Nonmetallic.	Unspecified (metallic and nonmetallic).	Total.
1880	$187,880,880	$173,581,917	$6,000,000	$367,462,797
1881	189,413,459	207,207,019	6,500,000	403,120,478
1882	215,820,070	230,785,547	6,500,000	453,105,617
1883	197,881,610	243,679,889	6,500,000	448,061,499
1884	180,284,208	221,755,346	5,000,000	407,039,554
1885	172,218,218	242,332,845	5,000,000	419,551,063
1886	204,399,872	250,985,090	800,000	456,184,962
1887	240,791,068	294,041,980	800,000	535,633,048
1888	242,010,000	310,888,983	900,000	553,798,983
1889	250,324,369	291,001,413	1,000,000	542,325,782
1890	303,440,430	310,988,907	1,000,000	615,429,337
1891	280,484,844	319,363,338	1,000,000	600,848,182
1892	283,715,295	337,516,444	1,000,000	622,231,739
1893	223,153,770	321,339,395	1,000,000	545,493,165
1894	186,835,353	362,409,394	1,000,000	550,244,747
1895	248,033,089	393,658,063	1,000,000	642,691,122
1896	252,075,130	387,965,870	1,000,000	641,041,000
1897	269,934,178	380,677,600	1,000,000	651,611,778
1898	308,247,446	417,794,018	1,000,000	727,041,464
1899	483,520,531	525,571,880	1,000,000	1,010,092,411
1900	513,731,959	594,194,796	1,000,000	1,108,926,755
1901	493,313,578	660,764,256	1,000,000	1,155,077,834
1902	604,517,044	722,433,728	1,000,000	1,327,950,772
1903	588,753,010	905,628,365	1,000,000	1,495,381,375
1904	501,114,224	859,074,529	400,000	1,360,588,753
1905	702,584,608	921,181,524	400,000	1,624,166,132
1906	886,179,981	1,016,390,015	200,000	1,902,769,996
1907	904,068,201	1,165,748,197	100,000	2,069,941,398
1908	550,744,388	1,043,702,454	250,000	1,594,696,842
1909	754,940,809	1,131,615,921	300,000	1,886,756,730
1910	749,876,234	1,241,039,986	300,000	1,991,216,220
1911	680,888,929	1,245,676,783	250,000	1,926,815,712
1912	866,381,073	1,378,310,236	500,000	2,245,191,309
1913	883,222,012	1,557,976,159	420,000	2,441,618,171
1914	691,081,734	1,426,754,508	470,000	2,118,306,242
1915	991,729,648	1,398,565,121	7,450,000	2,397,744,769
1916	1,620,507,000	1,878,463,000	15,630,000	3,514,600,000
1917	2,086,234,000	2,891,593,000	30,110,000	5,007,937,000
Grand total	19,990,357,000	28,262,558,000	109,780,000	48,362,695,000

Digitized by Google



FIGURE A.—Curves showing the value of the mineral production of the United States, 1880-1917.

Digitized by Google

IMPORTS AND EXPORTS.[1]

Value of imports for consumption and of exports of mineral products in the calendar years 1916 and 1917.

Metallic products.

Product.	1916	1917
IMPORTS.		
Aluminum:		
Crude, plates, sheet, leaf, wire, utensils, and manufactures	$1,785,870	$56,890
Aluminum salts	68,660	39,088
Antimony (crude and ore)	1,072,340	1,006,884
Antimony (metal or regulus)	3,548,507	2,957,819
Antimony (oxide and salts of)	109,832	5,368
Bauxite, crude	87	28,989
Bismuth	195,975	142,300
Brass, fit only for remanufacture	6,578,653	9,949,524
Cerium, cerite, or cerium ore	7	6,700
Chromic iron ore	1,548,402	1,110,659
Chromium salts	75	5,037
Cobalt, and cobalt ore and zaffer	175,286	369,950
Cobalt, oxide of	192,009	275,821
Copper in ore, matte, ingots, manufactures	94,469,458	135,233,853
Copper, sulphate of, or blue vitriol		9,799
Ferroalloys:		
Ferrochrome (and chromium)	1,998	
Ferromanganese	9,240,528	5,710,988
Ferrophosphorus		5,458
Ferrosilicon	384,384	691,684
Ferrotitanium (and titanium)	8,126	
Ferrotungsten (and tungsten)	157,711	3,606
Iron:		
Spiegeleisen		291,594
Tantalum	2,000	
Ore	4,566,514	3,655,392
Lead, in ore, base bullion, pigs, sheets, etc	1,014,959	776,638
Manganese, oxide, and ore of	8,640,065	10,262,929
Nickel, in ore, matte, and oxide, sheets, strips, and manufactures of	9,925,220	9,662,411
Platinum and allied metals:		
Ores of platinum, and unmanufactured	3,138,087	2,406,188
Vases, retorts, all other	21,872	1,347
Iridium, osmium, palladium, rhodium, and ruthenium	533,615	522,206
Osmiridium	17,241	25,456
Quicksilver	515,919	448,032
Tin, bars, blocks, pigs	51,802,232	63,860,340
Scrap (tin plate)	144,281	114,029
Tungsten-bearing ore	7,353,691	4,465,590
Type metal	83,816	
Uranium salts and oxide, including some radium salts	5,065	2,930
Zinc in ore, pigs, sheets, dust, manufactures	4,184,745	1,217,211
Total	211,487,180	255,324,710
Increase in 1917		43,837,530
Percentage of increase in 1917		21
EXPORTS.		
Aluminum and manufactures	15,417,134	[a] 9,029,458
Ingots, metal and alloys		[b] 4,269,643
Plates and sheets		[b] 301,550
All other manufactures		[b] 985,816
Bauxite concentrates	987,454	1,323,926
Brass, scrap and old	1,305,050	1,758,384
Copper:		
Ore	1,006,826	1,410,072
Concentrates, matte, and regulus	232,241	205,888
Unrefined, black blister, in pigs, bars, etc	5,193,278	4,614,843
Refined copper in ingots, pigs, bars, etc	186,266,158	306,847,639
Composition metal		[b] 350,561
Old and scrap	203,493	300,609
Pipes and tubes		[b] 3,023,563
Plates and sheets	6,874,571	12,995,503
Wire, except insulated	6,386,674	8,975,078
All other manufactures	25,752,591	16,957,876
Copper, sulphate of (blue vitriol)	2,803,833	3,038,380

[a] Figures cover six months January to June. Classification changed July 1.
[b] Classification changed July 1. Figures cover six months July to December..

[1] Compiled by James A. Dorsey from records of the Bureau of Foreign and Domestic Commerce, of the Department of Commerce.

Digitized by Google

Value of imports for consumption and of exports of mineral products in the calendar years 1916 and 1917—Continued.

Metallic products—Continued.

Product.	1916	1917
EXPORTS—continued.		
Iron:		
Ore	$3,702,496	$4,464,111
Pig	15,381,431	[a] 12,998,026
Ferromanganese		[b] 498,402
Ferrosilicon		[b] 719,626
All others		[b] 9,820,997
Ferrovanadium	2,035,276	2,953,260
Tungsten and ferrotungsten	1,352,631	4,122,653
Scrap and old, fit only for remanufacture	3,699,675	3,362,562
Lead:		
Pigs, bars, etc	13,494,065	9,560,598
Other manufactures of	2,522,416	2,287,305
Nickel, nickel oxide, and matte	12,952,493	8,936,620
Manufactures of	1,674,600	1,527,353
Platinum:		
Unmanufactured	97,988	234,433
Manufactured	83,864	65,415
Quicksilver	670,475	998,470
Tin, in pigs, bars	365,176	232,401
Zinc:		
Ore	3,992	63,043
Dross	10,801	2,126,909
In pigs, slabs, etc	46,770,901	32,905,767
Rolled in sheets, strips, etc	4,540,146	5,730,792
All other manufactures	572,229	570,352
Total	362,349,958	480,267,884
Increase in 1917		117,917,926
Percentage of increase in 1917		33

Nonmetallic products.

IMPORTS.		
Arsenic, sulphides, etc	$232,694	$674,875
Sheep dip	20,134	15,848
Asbestos:		
Unmanufactured	3,303,470	4,521,172
Manufactured	24,282	15,646
All other	113,636	47,041
Asphalt	734,712	993,115
Barium products:		
Manufactured barytes	2,072	1,743
Lithopone (including zinc sulphides)	414,592	35,718
Barium carbonate—		
Natural	18,169	17,321
Manufactured		1,554
Barium binoxide	6,590	
Barium chloride	608	
Blanc-fixe	17,810	3,333
Barytes, crude	245	63
Borax (including crude, refined, and boracic acid, etc.)	20,043	21,206
Burrstones and millstones	19,816	18,227
Cement, hydraulic	4,942	6,076
Chalk:		
Crude	112,671	126,605
Ground or bolted		6,241
Precipitated	27,713	29,980
Cubes, blocks, sticks, tailor's, etc	4,096	6,563
French, cut, powdered, washed, etc	628	222
Manufactures of (not elsewhere specified)	249	340
Clay:		
Kaolin or china clay	1,326,684	1,315,769
Other than kaolin	177,549	126,290
Clay products:		
Brick and tile	164,247	307,802
Flattening stones	833	1,457
Pipes, common tobacco pipes, and pipe bowls of clay	10,378	8,209
Pottery, etc	5,590,207	6,325,105
Coal:		
Anthracite	7,202	18,155
Bituminous	4,736,631	4,823,478

[a] Figures cover six months January to June. Classification changed July 1.
[b] Classification changed July 1. Figures cover six months July to December.

Digitized by Google

Value of imports for consumption and of exports of mineral products in the calendar years 1916 and 1917—Continued.

Nonmetallic products—Continued.

Product.	1916	1917
IMPORTS—continued.		
Coke	$249,514	$146,451
Corundum and emery	240,737	210,602
Cryolite	165,222	218,500
Diatomaceous earth, rotten stone, and tripoli	37,573	17,864
Explosives:		
Fulminates, fulminating powders, etc.—		
Suitable for miners	.....	75,839
All other	229,194	1,848,802
Gunpowder and all other substances (not elsewhere specified)	7,256,814	2,539,249
Mining, blasting, or safety fuses of all kinds	3,378	5,016
Percussion caps	3,123	525
Blasting caps	2,453	.....
Bombs, rockets, Roman candles, and fireworks	1,507	3,413
Fire crackers	291,830	384,696
Fertilizers:		
Crude guano, kainite, manure salts, and phosphate	4,104,647	4,914,233
Potassium chloride	348,961	158,410
Potassium sulphate	81,684	21,702
Other potassium salts	1,921,803	1,034,284
Sodium nitrate	38,131,364	60,727,100
Flint, flints, and flint stones	313,120	197,156
Fluorspar	54,000	114,598
Fuller's earth	139,664	176,417
Gems and precious stones (including diamond dust and bort)	38,930,117	34,846,351
Granite	75,697	35,042
Graphite	7,279,884	8,961,988
Grindstones, finished and unfinished	63,277	57,950
Gypsum	356,473	381,252
Keenes cement, or other cement of which gypsum is chief value	9,890	8,003
Hones, oilstones, and whetstones	10,614	10,636
Ichthyol	93,762	36,232
Lead paints, litharge, orange mineral, red lead, white lead	21,783	6,870
Lime	71,663	70,505
Lithographic stones, not engraved	983	.....
Magnesia	19,743	17,761
Magnesite	338,630	464,706
Marble and stone (exclusive of granite)	883,670	646,433
Mica	1,071,356	1,430,048
Mineral waters	624,302	268,665
Mineral salts, obtained by evaporation from mineral waters	.....	4,858
Monazite sand and thorium oxide	197,870	355,017
Ocher	181,153	234,490
Peat	27,859	4,966
Petroleum:		
Crude	12,602,811	16,400,017
Benzine, gasoline, and naphtha	185,286	1,411,453
Ozokerite	196,185	90,510
Paraffin oil	75,925	3,514
Paraffin wax	510,689	638,700
All other	1,023,241	2,793,701
Carbon made entirely from petroleum coke	3,925	.....
Pumice stone	116,543	147,278
Pyrite	6,728,318	5,981,457
Salt	342,588	280,135
Sand	87,144	142,586
Selenium	302	2,236
Sienna and sienna earths	82,999	57,330
Slate	2,200	1,024
Strontium salts	11,049	23,216
Sulphur or brimstone	404,784	29,340
Talc	230,875	269,497
Thorium nitrate	3,884	2,359
Umber	69,470	42,620
Venetian red	10,811	5,967
Zinc oxide	185,395	53,525
Total	144,305,641	168,482,249
Increase in 1917	.....	24,176,608
Percentage of increase in 1917	.....	17

Digitized by Google

Value of imports for consumption and of exports of mineral products in the calendar years 1916 and 1917—Continued.

Nonmetallic products—Continued.

Product.	1916	1917
EXPORTS.		
Abrasives:		
Wheels, emery and other	$2,240,237	$4,481,600
All other	2,035,951	1,941,512
Asbestos:		
Ore and unmanufactured	6,133	116,580
Manufactured	1,209,076	1,932,551
Asphalt:		
Unmanufactured	759,769	587,256
Manufactures of	494,895	585,472
Cement	3,828,231	5,328,536
Clay:		
Fire	144,552	268,093
All other	145,970	178,764
Coal:		
Anthracite	22,470,147	30,909,798
Bituminous	[a] 45,828,092	[a] 79,502,654
Coke	4,202,236	8,543,746
Earthen, stone, and chinaware:		
Brick—		
Building	189,668	196,207
Fire	2,406,184	4,011,546
Chinaware	292,119	422,641
Earthen and stoneware	600,377	805,784
Sanitary earthenware	214,076	323,558
Tiles except drain	403,184	450,422
All other	779,922	743,105
Fertilizers:		
Phosphate rock, ground or unground—		
High-grade hard rock	286,948	113,392
Land pebble	863,078	548,203
All other	6,365	173,450
Graphite:		
Unmanufactured	98,118	349,563
Manufactured	1,339,259	891,687
Lime	132,769	168,671
Mica:		
Unmanufactured	4,544	3,073
Manufactures of	74,127	71,412
Paints:		
Red lead	.....	[b] 267,238
White lead	2,137,072	2,089,659
Zinc oxide	2,394,709	3,148,898
Petroleum and petroleum products:		
Crude	7,029,923	7,668,312
Gasoline	33,614,957	49,049,647
Naphtha	35,045,924	44,084,597
Illuminating	55,862,906	48,953,610
Fuel oil and gas oil	[c] 26,990,552	[c] 45,549,282
Lubricating and heavy paraffin oil	43,027,371	[d] 26,108,011
Paraffin oil	.....	[b] 1,192,297
All other	.....	[b] 30,264,556
Jelly, etc	1,041,408	1,246,901
Paraffin and paraffin wax	14,820,440	17,906,706
Residuum	149,658	107,164
Plaster, builder's and common	129,872	159,875
Wall board (suitable for plaster)	108,505	106,118
Potash:		
Chlorate	.....	[b] 475,434
All other	.....	[b] 638,768
Salt	567,441	1,000,773
Sand and gravel	233,310	494,251
Soda	17,003,998	[d] 9,322,233
Caustic	.....	[b] 5,832,598
Sal soda	.....	[b] 97,772
Silicate	.....	[b] 216,828
Soda ash	.....	[b] 2,884,569
Other salts of soda	.....	[b] 4,030,196

[a] Not including bunker coal laden as fuel on vessels in the foreign trade, which aggregated in value $27,491,822 in 1916 and $31,844,799 in 1917.

[b] Classification changed July 1. Figures cover six months July to December.

[c] Not including fuel or bunker oil laden as fuel on vessels in the foreign trade, which aggregated in value $5,583,222 in 1916 and $7,391,985 in 1917.

[d] Figures cover six months January to June. Classification changed July 1.

Digitized by Google

Value of imports for consumption and of exports of mineral products in the calendar years 1916 and 1917—Continued.

Nonmetallic products—Continued.

Product.	1916	1917
EXPORTS—continued.		
Stone, including marble:		
Unmanufactured	$403,303	$572,097
Manufactures of—		
Grindstones	176,563	198,772
Roofing slate	27,630	27,113
All other	1,077,447	1,108,185
Sulphur or brimstone	2,505,857	3,500,819
Total	335,374,863	451,952,555
Increase in 1917		116,577,692
Percentage of increase in 1917		35

Summary.

Imports:		
Metallic	$211,487,180	$255,324,710
Increase		43,837,530
Percentage of increase		21
Nonmetallic	144,305,641	168,482,249
Increase		24,176,608
Percentage of increase		17
Exports:		
Metallic	362,349,958	480,267,884
Increase		117,917,926
Percentage of increase		33
Excess of exports over imports	150,862,778	224,943,174
Excess of exports over imports (percentage)	71	88
Nonmetallic	335,374,863	451,952,555
Increase		116,577,692
Percentage of increase		35
Excess of exports over imports	191,069,222	283,470,306
Excess of exports over imports (percentage)	132	168
Grand total value:		
Imports of metallic and nonmetallic products	355,792,821	423,806,959
Increase		68,014,138
Percentage of increase		19
Exports of metallic and nonmetallic products	697,724,821	932,220,439
Increase		234,495,618
Percentage of increase		34
Excess of exports over imports	341,932,000	508,413,480
Excess of exports over imports (percentage)	96	120

Digitized by Google

PRODUCTION BY STATES.

In the following tables are shown (1) the value of the mineral production of the United States in 1917 arranged by minerals in order of value, with the States leading in the production of each mineral, and the percentage which each mineral represents of the total value for the entire country, and (2) the quantity and value of the principal metals, fuels, and structural materials in 1916 and 1917 arranged in groups in order of value in 1917, with States leading in the production of each mineral, and with the increase or decrease by minerals and by groups in 1917.

It is of interest to note that more than 51 per cent of the total value of mineral production may be credited to coal and pig iron, and that with the addition of petroleum and copper these minerals yielded nearly three-fourths of the entire value. Pennsylvania was the leading State in the production of 11 mineral products and California of 7. Coal was the product of greatest value in 16 States in 1917. The leading States in value of output in 1917 were as follows: Pennsylvania, West Virginia, Oklahoma, Illinois, Ohio, Arizona, California, and Michigan; 1916: Pennsylvania, Arizona, West Virginia, Oklahoma, Illinois, Ohio, Montana, and Michigan.

Mineral products of the United States in 1917, in order of value.

Rank.	Mineral.	Principal producing States (in order of value).[a]	Value.	Percentage of total for United States.
1	Coal:			
	Bituminous	Pennsylvania, West Virginia, Illinois, Ohio	$1,249,272,837	24.95
	Pennsylvania anthracite.	Pennsylvania	283,650,723	5.66
2	Iron, pig	Pennsylvania, Ohio, Illinois, Alabama	1,053,785,975	21.04
3	Petroleum	Oklahoma, California, Kansas, Texas	522,635,213	10.44
4	Copper	Arizona, Montana, Michigan, Utah	514,911,000	10.28
5	Coke	Pennsylvania, Alabama, Ohio, Indiana	[b] 298,243,017	[b] 5.96
6	Clay products	Ohio, Pennsylvania, New Jersey, Illinois	248,023,368	4.95
7	Iron ore	Minnesota, Michigan, Alabama, New York	[b] 238,260,444	[b] 4.76
8	Natural gas	West Virginia, Pennsylvania, Ohio, Oklahoma	142,089,334	2.84
9	Cement	Pennsylvania, Indiana, Missouri, California	123,210,458	2.46
10	Zinc	Missouri, New Jersey, Montana, Oklahoma	119,258,000	2.38
11	Lead	Missouri, Idaho, Utah, Colorado	94,333,000	1.88
12	Gold	California, Colorado, Alaska, South Dakota	83,750,700	1.67
13	Ferroalloys	Pennsylvania, Illinois, Maryland, Alabama	83,731,734	1.67
14	Stone	Pennsylvania, Ohio, Vermont, New York	82,215,671	1.64
15	Silver	Utah, Montana, Idaho, Nevada	59,078,100	1.18
16	Aluminum	New York, Tennessee, North Carolina	45,882,000	.92
17	Natural-gas gasoline	Oklahoma, West Virginia, California, Pennsylvania	40,188,956	.80
18	Sand and gravel	Pennsylvania, Ohio, Illinois, New York	35,296,932	.70
19	Mineral paints (zinc and lead pigments.	Pennsylvania, Wisconsin, Kansas, Missouri	26,972,137	.54
20	Sulphur	Louisiana, Texas, Wyoming, Nevada	[c]	[c]
21	Lime	Pennsylvania, Ohio, Virginia, Missouri	23,807,877	.48
22	Salt	Michigan, New York, Ohio, Kansas	19,940,442	.40
23	Sulphuric acid from copper and zinc smelters.	Pennsylvania, Illinois, Ohio, Tennessee	16,890,545	.34
24	Potash (K_2O)	Nebraska, California, Utah, Maryland	13,980,577	.28
25	Gypsum	New York, Iowa, Michigan, Ohio	11,116,452	.22
26	Asphalt	Texas, California, Oklahoma, Illinois	8,470,615	.17
27	Clay, raw	Missouri, Pennsylvania, New Jersey, Illinois	[b] 8,042,546	[b] .16
28	Phosphate rock	Florida, Tennessee, South Carolina, Kentucky	7,771,084	.16
29	Tungsten ore	California, Colorado, South Dakota, Nevada	6,783,000	.14
30	Slate	Pennsylvania, Vermont, Maine, Virginia	5,749,966	.11

[a] Rank of States in metal production (except pig iron) arranged according to mines reports, not smelter output.
[b] Not included in total value.
[c] Included under last item ("Unspecified").

Digitized by Google

Mineral products of the United States in 1917, in order of value—Continued.

Rank.	Mineral.	Principal producing States (in order of value).	Value.	Percentage of total for United States.
31	Mineral waters	Wisconsin, New York, California, Maine	$4,931,710	0.10
32	Manganese ore	Montana, Virginia, Arizona, Arkansas	4,109,722	
33	Platinum and allied metals.	Nevada, California, Wyoming, Oregon	4,023,757	
34	Quicksilver	California, Texas, Nevada, Oregon	3,806,266	
35	Antimonial lead	Not separable by States	3,781,560	
36	Borax (crude)	California	3,609,632	
37	Manganiferous ore	Minnesota, Colorado, Arizona, Michigan	3,406,061	
38	Bauxite	Arkansas, Georgia, Alabama, Tennessee	3,119,058	
39	Magnesite (crude)	California, Washington	2,899,818	
40	Pyrite	Virginia, New York, California, Georgia	2,485,435	
41	Talc and soapstone	New York, Vermont, Virginia, Georgia	2,292,878	
42	Fluorspar	Illinois, Kentucky, Colorado, New Hampshire	2,287,722	
43	Antimony [a]	Nevada, Alaska, Utah, Idaho	a 2,152,386	
44	Sand-lime brick	Michigan, Minnesota, New York, Massachusetts	1,420,330	
45	Barytes (crude)	Georgia, Missouri, Tennessee, Kentucky	1,171,184	
46	Graphite	Alabama, New York, Pennsylvania, Rhode Island	1,167,879	
47	Grindstones and pulpstones.	Ohio, West Virginia, Michigan	1,147,784	
48	Arsenious oxide	Not separable by States	1,118,313	
49	Chromic iron ore	California, Oregon, Maryland, Washington	1,049,400	
50	Mica	North Carolina, New Hampshire, Virginia, Georgia	806,782	
51	Fuller's earth	Florida, Georgia, Texas, Arkansas	772,087	
52	Feldspar	Maine, North Carolina, Pennsylvania, Connecticut	728,838	
53	Peat	New Jersey, Illinois, California, Massachusetts	709,900	1.00
54	Uranium and vanadium minerals.	Colorado, Utah	617,000	
55	Asbestos	Arizona, Georgia, California, Wyoming	506,056	
56	Bromine	Michigan, Ohio, West Virginia, Pennsylvania	492,708	
57	Calcium chloride	Michigan, Ohio, West Virginia, California	451,480	
58	Nickel	Not separable by States	331,556	
59	Silica (quartz)	Massachusetts, Pennsylvania, Wisconsin, North Carolina.	318,069	
60	Cadmium	Not separable by States	305,097	
61	Emery and corundum	New York, North Carolina, Virginia	241,050	
62	Garnet for abrasive purposes.	New York, New Hampshire, North Carolina	198,327	
63	Oilstones, etc	Arkansas, Indiana, Ohio, Vermont	168,704	
64	Tin	Alaska, South Dakota	135,600	
65	Gems and precious stones.	Montana, Nevada, California, Maine	131,012	
66	Diatomaceous (infusorial) earth and tripoli.	California, Pennsylvania, Illinois, Washington	b 123,784	
67	Pumice	Kansas, Nebraska, California	84,814	
68	Millstones	New York, Virginia, North Carolina, Pennsylvania	43,489	
69	Titanium ore (rutile)	Virginia	32,960	
	Total estimated value of "Unspecified" products.		30,110,000	.60
	Grand total (approximate).	Pennsylvania, West Virginia, Oklahoma, Illinois, Ohio, Arizona.	5,007,937,000	100.00

[a] Value excluded from total, except value of antimony other than that entering into antimonial lead which is included under last item ("Unspecified"). States are arranged in order of value of antimony ore produced.

[b] Exclusive of considerable production for special uses which is included under last item ("Unspecified").

Digitized by Google

Production and value of principal metals, fuels, and structural materials in the United States, 1916 and 1917.

Mineral.	Principal producing States in 1917 (in order of value).[a]	1916			1917			Increase (+) or decrease (−) in value.			
								By minerals.		By groups.	
		Quantity.	Value.	Value by groups.	Quantity.	Value.	Value by groups.	Amount.	Per cent.	Amount	Per cent.
Metals (from domestic ores):											
Pig iron, long tons.	Pennsylvania, Ohio, Illinois, Alabama.	38,361,474	$647,481,362		38,107,330	$1,039,404,779		+$391,923,417	+61		
Copper...pounds..	Arizona, Montana, Michigan, Utah.	1,927,850,548	474,288,000		1,886,120,721	514,911,000		+ 40,623,000	+ 9		
Zinc...short tons..	Missouri, New Jersey, Montana, Oklahoma.	563,451	151,005,000		584,597	119,258,000		− 31,747,000	−21		
Lead..short tons..	Missouri, Idaho, Utah, Colorado.	552,228	76,207,000	$1,490,524,662	548,450	94,333,000	$1,910,735,579	+ 18,126,000	+24	+$420,210,917	+28
Gold.troy ounces..	California, Colorado, Alaska, South Dakota.	4,479,056	92,590,300		4,051,440	83,750,700		− 8,839,600	−10		
Silver.troy ounces.	Utah, Montana, Idaho, Nevada.	74,414,802	48,953,000		71,740,362	59,078,100		+ 10,125,100	+21		
Fuels:											
Coal...short tons..	Pennsylvania, West Virginia, Illinois, Ohio.	590,098,175	867,125,638		651,402,374	1,532,923,560		+665,797,922	+77		
Petroleum.barrels.	Oklahoma, California, Kansas, Texas.	300,767,158	330,899,868	1,318,252,974	335,315,601	522,635,213	2,197,648,107	+191,735,345	+58	+879,395,133	+67
Natural gas.....	West Virginia, Pennsylvania, Ohio, Oklahoma.	.....	120,227,468		.....	142,089,334		+ 21,861,866	+18		

Digitized by Google

Structural materials:										
Clay products (brick and tile).	Pennsylvania, Ohio, Illinois, Missouri.	.....	159,042,849	404,418,791	.....	191,800,846	473,258,202	+ 32,817,907	+21	+ 68,839,411 +17
Cement...barrels..	Pennsylvania, Indiana, Missouri, California.	95,394,433	104,689,090		91,342,930	123,210,458		+ 18,521,368	+18	
Stone..short tons..	Pennsylvania, Ohio, Vermont, New York.	91,831,000	79,069,683		83,562,000	82,215,671		+ 3,145,988	+ 4	
Sand and gravel, ...short tons..	Pennsylvania, Ohio, Illinois, New York.	89,091,732	29,809,995		76,419,325	35,296,932		+ 5,486,937	+18	
Lime.....do....	Pennsylvania, Ohio, Virginia, Missouri.	4,073,433	18,509,305		3,786,364	23,807,877		+ 5,298,572	+29	
Gypsum....do....	New York, Iowa, Michigan, Ohio.	2,757,730	7,959,032		2,696,226	11,116,452		+ 3,157,420	+40	
Slate.....	Pennsylvania, Vermont, Maine, Virginia.	.....	5,338,837		.....	5,749,966		+ 411,129	+ 8	

a Rank of States in metal production (except pig iron) arranged according to mines reports, not smelter output.

The following tables show (1) the value of the mineral production of the United States in 1916 and 1917, arranged by States in order of productive value in 1917, with leading products in each State, increase or decrease in each State, and percentage of total for the United States represented by each State in 1917; (2) value of mineral production by States, arranged alphabetically, from 1911 to 1917; and (3) table of production for each State alphabetically for 1916 and 1917, giving quantity and value of each mineral produced in the State and total value of the State's output.

For more detailed accounts of the products the reader should consult the chapters of Mineral Resources on the different minerals.

Digitized by Google

Rank of States in value of mineral production in 1916 and 1917.

State.	Principal mineral products in 1917 (in order of value).[a]	1916		1917				
		Rank.	Value.	Rank.	Value.	Increase or decrease.	Percentage of increase or decrease.	Percentage of total for United States.
Pennsylvania	Coal, clay products, cement, natural gas	1	$554,501,375	1	$880,220,510	+$325,719,135	+ 58.7	21.6
West Virginia	Coal, natural gas, petroleum, clay products	3	187,043,011	2	306,916,191	+ 119,873,180	+ 64.1	7.5
Oklahoma	Petroleum, natural-gas gasoline, zinc, natural gas	4	169,556,331	3	259,134,377	+ 89,578,046	+ 52.8	6.4
Illinois	Coal, petroleum, clay products, cement	5	146,359,792	4	236,934,229	+ 90,574,437	+ 61.9	5.8
Ohio	Coal, clay products, petroleum, natural gas	6	145,088,485	5	218,181,419	+ 73,092,934	+ 50.4	5.4
Arizona	Copper, silver, gold, zinc	2	192,622,991	6	212,615,978	+ 19,992,987	+ 10.4	5.2
California	Petroleum, gold, copper, cement	9	137,284,754	7	175,401,518	+ 38,116,764	+ 27.8	4.3
Michigan	Copper, iron ore, salt, cement	8	140,666,124	8	163,997,853	+ 23,331,729	+ 16.6	4.0
Minnesota	Iron ore, clay products, cement, manganiferous ore	10	113,662,522	9	152,490,554	+ 38,828,032	+ 34.2	3.7
Montana	Copper, zinc, silver, coal	7	142,650,179	10	123,733,415	− 18,916,764	− 13.3	3.0
Utah	Copper, lead, silver, coal	12	99,734,209	11	113,589,282	+ 13,855,073	+ 13.9	2.8
Kansas	Petroleum, coal, natural gas, cement	21	41,847,955	12	106,753,055	+ 64,915,100	+155.1	2.6
Missouri	Lead, zinc, coal, clay products	11	102,424,953	13	105,320,378	+ 2,895,425	+ 2.8	2.6
Indiana	Coal, cement, clay products, stone	15	56,926,558	14	85,079,370	+ 28,152,812	+ 49.5	2.1
Colorado	Coal, gold, zinc, silver	13	77,642,778	15	80,586,021	+ 2,943,243	+ 3.8	2.0
Texas	Petroleum, sulphur, coal, cement	19	47,711,571	16	77,552,369	+ 29,840,798	+ 62.5	1.9
Kentucky	Coal, petroleum, clay products, stone	23	40,015,935	17	77,177,421	+ 37,161,486	+ 92.9	1.9
Alabama	Coal, iron ore, clay products, stone	22	40,922,462	18	65,371,469	+ 24,449,007	+ 59.7	1.6
New Jersey	Zinc, clay products, cement, iron ore	14	59,430,705	19	57,710,181	− 1,720,524	− 2.9	1.4
Nevada	Copper, silver, gold, lead	16	53,510,559	20	55,410,190	+ 1,899,631	+ 3.6	1.4
Idaho	Lead, silver, zinc, copper	17	49,249,134	21	55,224,026	+ 5,974,892	+ 12.1	1.4
New York	Clay products, iron ore, cement, stone	20	45,619,119	22	52,123,552	+ 6,504,433	+ 14.3	1.3
New Mexico	Copper, coal, zinc, silver	24	37,123,501	23	43,312,947	+ 6,189,446	+ 16.7	1.1
Alaska	Copper, gold, silver, coal	18	48,521,513	24	40,710,655	− 7,810,858	− 16.1	1.0
Iowa	Coal, clay products, cement, gypsum	25	30,210,284	25	39,336,372	+ 9,126,088	+ 30.2	1.0
Tennessee	Coal, zinc, copper, cement	26	28,277,365	26	36,910,448	+ 8,633,083	+ 30.5	.9
Louisiana	Petroleum, sulphur, natural gas, natural-gas gasoline	27	28,020,543	27	36,204,387	+ 8,183,844	+ 29.2	.9
Virginia	Coal, lime, clay products, stone	29	20,560,956	28	32,243,648	+ 11,682,692	+ 56.8	.8
Wyoming	Coal, petroleum, iron ore, copper	30	19,683,292	29	29,567,250	+ 9,883,958	+ 50.2	.7
Wisconsin	Zinc, iron ore, stone, mineral waters	28	27,062,175	30	24,976,780	− 2,105,395	− 7.8	.6
Maryland	Coal, clay products, cement, stone	32	13,335,013	31	19,617,596	+ 6,282,583	+ 47.1	.5
Washington	Coal, cement, clay products, lead	31	14,521,014	32	18,576,052	+ 4,055,038	+ 27.9	.5
Arkansas	Coal, bauxite, zinc, clay products	33	9,508,001	33	12,061,702	+ 2,553,701	+ 26.9	.3
Vermont	Stone, slate, talc and soapstone, lime	35	8,297,104	34	8,980,573	+ 683,469	+ 8.2	.2
South Dakota	Gold, tungsten ore, stone, silver	34	8,996,680	35	8,348,684	− 347,996	− 4.0	.2
Nebraska	Potash (K_2O), clay products, stone, sand and gravel	43	3,436,774	36	7,943,729	+ 4,506,955	+131.1	.2
Georgia	Clay products, stone, barytes, cement	36	6,779,828	37	7,650,553	+ 870,725	+ 12.8	.2

Digitized by Google

Florida	Phosphate rock, stone, fuller's earth, clay products	38	5,666,745	38	7,294,407	+	1,627,662	+	28.7	2
Massachusetts	Stone, clay products, lime, sand and gravel	37	6,497,444	39	7,223,750	+	726,306	+	7.9	2
North Carolina	Stone, clay products, mica, iron ore	39	4,605,451	40	5,246,791	+	641,340	+	14.2	1
Oregon	Gold, copper, stone, clay products	40	4,494,622	41	4,774,247	+	279,625	+	6.4	1
Connecticut	Clay products, stone, lime, sand and gravel	41	3,940,676	42	3,981,203	+	40,527	+	1.0	1
Maine	Stone, lime, clay products, mineral waters	42	3,539,461	43	3,725,121	+	185,660	+	5.3	1
North Dakota	Coal, clay products, mineral waters, sand-lime brick	46	1,283,800	44	1,740,849	+	456,740	+	36.3	
New Hampshire	Stone, clay products, mica, sand and gravel	44	1,617,723	45	1,894,864	+	228,139	+	12.3	
South Carolina	Clay products, stone, phosphate rock, mineral waters	45	1,392,073	46	1,393,297	+	1,224	+	.1	2
Mississippi	Clay products, sand and gravel, mineral waters, stone	47	890,566	47	966,135	+	75,569	+	8.5	
Rhode Island	Stone, clay products, graphite, mineral waters	48	789,208	48	717,123	−	72,085	−	9.1	
Delaware	Stone, clay products, sand and gravel, mineral waters	49	336,172	49	522,991	+	187,819	+	55.9	
District of Columbia	Clay products, sand-lime brick, stone, mineral waters	50	179,436	50	204,936	+	25,500	+	14.2	

a In this table iron ore, not pig iron, is taken as the basis of iron valuation, and in the case of other metals mine production (recoverable content of metals) is the basis.

Digitized by Google

Value of mineral production, 1911 to 1917, by States.[a]

State.	1911	1912	1913	1914	1915	1916	1917
Alabama	$28,005,785	$30,641,983	$34,660,545	$30,879,288	$29,458,157	$40,922,462	$65,371,469
Alaska	20,866,122	22,732,947	19,645,498	19,177,051	32,854,011	48,521,513	40,710,655
Arizona	44,503,873	67,497,838	71,429,705	60,420,362	91,552,049	192,622,991	212,615,978
Arkansas	5,864,822	6,258,726	6,780,760	5,787,199	6,558,693	9,508,001	12,061,702
California	90,620,644	93,219,149	100,791,369	101,013,199	98,198,538	137,284,754	175,401,518
Colorado	52,522,416	58,167,399	54,294,281	52,161,660	64,300,026	77,642,778	80,586,021
Connecticut	3,151,588	3,716,480	3,795,297	3,023,192	3,332,330	3,940,676	3,981,203
Delaware	491,657	425,360	541,542	288,516	282,292	336,172	523,991
District of Columbia	277,295	300,336	246,582	219,680	205,592	179,436	204,936
Florida	10,250,228	10,272,594	10,508,016	8,497,688	4,855,690	5,666,785	7,294,467
Georgia	6,172,857	6,306,140	6,525,792	5,704,856	5,094,688	6,779,828	7,650,553
Idaho	19,441,545	21,816,390	24,565,826	24,913,223	33,612,194	49,249,134	55,224,026
Illinois	106,275,115	122,986,424	131,701,551	117,005,441	114,112,315	146,359,792	236,934,229
Indiana	37,430,187	42,289,193	46,502,633	42,864,267	41,381,456	56,926,558	85,079,370
Iowa	21,112,896	22,900,350	25,602,015	26,287,115	27,048,177	30,210,284	39,336,372
Kansas	24,890,043	25,795,267	26,770,302	25,324,035	28,436,446	41,847,955	106,763,055
Kentucky	19,296,614	22,477,530	26,845,579	26,668,474	27,278,627	40,015,935	77,177,421
Louisiana	12,710,958	15,357,841	21,011,828	21,890,025	18,215,847	28,020,543	36,204,387
Maine	4,645,630	3,925,526	4,429,584	3,975,890	3,301,907	3,539,481	3,726,121
Maryland	9,386,515	10,851,671	11,292,723	10,587,564	10,581,224	13,235,013	19,617,596
Massachusetts	6,623,077	6,654,514	7,044,529	6,292,833	6,286,860	6,697,444	7,225,750
Michigan	65,275,324	80,062,486	72,143,211	57,743,555	93,938,255	140,666,124	163,997,853
Minnesota	53,395,881	66,672,729	85,814,533	45,680,965	62,391,440	113,662,522	152,490,554
Mississippi	1,052,842	1,242,528	1,143,472	1,104,197	666,143	890,566	966,135
Missouri	50,967,074	57,343,307	53,011,088	47,607,593	74,033,623	102,424,953	105,320,378
Montana	53,498,194	71,620,873	69,307,056	54,244,889	89,147,138	142,650,179	123,733,415
Nebraska	1,316,168	1,490,582	1,433,718	1,166,787	1,514,171	3,436,774	7,943,729
Nevada	34,501,832	39,111,828	37,842,084	29,984,338	35,991,891	53,510,559	55,410,190
New Hampshire	1,727,645	1,949,876	2,218,925	2,029,835	1,907,949	1,817,723	1,594,584
New Jersey	34,458,865	37,195,940	35,931,191	31,756,503	38,818,422	59,430,705	57,710,181
New Mexico	8,176,229	14,391,355	17,862,369	18,072,919	25,549,161	37,123,501	43,312,947
New York	34,317,594	38,431,910	41,709,002	36,420,134	36,414,038	45,619,119	52,123,552
North Carolina	2,793,825	3,368,923	3,739,696	3,519,245	3,365,805	4,595,551	5,246,391
North Dakota	957,425	1,025,741	1,055,676	1,063,540	985,885	1,283,809	1,749,549
Ohio	97,090,284	111,229,656	121,795,892	101,661,384	105,198,086	145,068,485	218,181,419
Oklahoma	43,036,253	53,614,130	80,168,820	78,744,447	83,672,991	169,556,331	259,134,377
Oregon	3,192,679	2,553,549	3,563,919	3,331,132	3,656,562	4,498,632	4,074,247
Pennsylvania	409,213,802	438,995,247	499,680,694	445,264,824	448,935,291	554,501,375	880,220,510
Rhode Island	1,253,656	942,842	813,952	777,716	855,007	789,208	717,123
South Carolina	1,303,579	1,606,989	1,464,150	1,414,294	1,129,709	1,392,073	1,393,297
South Dakota	8,047,259	8,436,240	7,909,059	7,861,601	8,093,670	8,696,680	8,348,684
Tennessee	17,899,882	19,362,209	21,008,938	19,647,145	22,166,494	28,277,365	36,910,448
Texas	18,798,837	22,797,015	31,666,910	30,363,426	29,220,951	47,711,571	77,552,369

Digitized by Google

Utah	43, 774, 331	51, 004, 942	53, 606, 520	45, 630, 198	62, 889, 261	90, 734, 209	113, 589, 282
Vermont	8, 434, 616	9, 067, 560	9, 647, 985	8, 665, 867	7, 838, 410	8, 297, 104	8, 980, 573
Virginia	13, 713, 566	14, 869, 922	17, 167, 630	16, 400, 347	16, 994, 786	20, 560, 036	32, 243, 648
Washington	15, 805, 277	16, 347, 313	17, 579, 743	13, 830, 739	11, 455, 715	14, 521, 014	18, 575, 052
West Virginia	101, 632, 248	122, 847, 812	143, 591, 272	138, 633, 229	136, 070, 173	187, 043, 011	306, 916, 191
Wisconsin	11, 418, 968	13, 326, 104	11, 789, 590	10, 414, 110	13, 739, 343	27, 082, 175	24, 976, 780
Wyoming	11, 483, 377	13, 374, 088	13, 632, 091	12, 417, 752	12, 708, 238	19, 653, 292	29, 567, 280

a In this table iron ore, not pig iron, is taken as the basis of valuation of iron, and in the case of other metals mine production (recoverable content of metals) is the basis.

Digitized by Google

Mineral production of Alabama in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Barytes.....short tons..	7,631	$27,198	1,976	$8,868
Bauxite.....long tons..	(a)	(a)	8,231	52,317
Cement.....barrels..	1,442,575	1,410,104	1,329,833	1,494,879
Chert.....short tons..	.....	.....	17,500	11,000
Clay products.....	.....	1,520,301	.....	2,106,516
Clay, raw.....short tons..	41,479	b 51,053	58,667	b 84,763
Coal.....do....	18,086,197	24,859,331	20,068,074	45,616,992
Coke.....do....	4,298,417	b 15,019,139	4,892,589	b 28,394,272
Ferroalloys.....long tons..	9,943	(a b)	(a b)	(a b)
Gold.....fine ounces (troy)..	418	8,650	109	2,262
Graphite, crystalline.....pounds..	5,226,940	492,407	6,223,095	719,575
Iron ore.....long tons..	6,801,839	10,843,231	7,101,586	13,049,535
Iron, pig.....do....	2,672,498	b 38,994,660	2,971,626	b 64,309,714
Lime.....short tons..	67,524	312,531	66,744	383,211
Manganese ore.....long tons..	(a)	(a)	264	10,538
Mica.....	.....	5,615	.....	3,808
Millstones.....	.....	(a)	.....	(a)
Mineral waters.....gallons sold..	103,944	12,174	56,270	5,509
Natural gas.....	.....	(a)	.....	(a)
Potash (K_2O).....short tons..	.....	.....	2	748
Pyrite.....long tons..	.....	.....	(a)	(a)
Sand and gravel.....short tons..	726,650	184,216	476,678	222,011
Sand and sandstone (finely ground).....do....	.....	.....	(a)	(a)
Silver.....fine ounces (troy)..	53	35	11	9
Stone.....	.....	1,202,256	.....	1,611,497
Miscellaneous c.....	.....	1,529,744	.....	4,504,428
Total value, eliminating duplications.....	.....	40,922,462	.....	65,371,469

a Value included under "Miscellaneous."
b Value not included in total value for State.
c 1916: Bauxite, ferroalloys, manganese ore, millstones, and natural gas; 1917: Ferroalloys, millstones natural gas, pyrite, and sand and sandstone (finely ground).

Mineral production of Alaska in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Antimony ore.....short tons..	841	$10,306	84	$3,433
Chromic iron ore.....long tons..	.....	.....	(a)	(a)
Coal.....short tons..	13,073	52,317	53,955	265,317
Copper.....pounds..	119,854,839	29,484,291	88,793,400	24,240,598
Gold.....fine ounces (troy)..	834,068	17,241,713	709,049	14,657,353
Graphite, crystalline.....pounds..	.....	.....	(a)	(a)
Gypsum.....short tons..	(b)	(b)	(b)	(b)
Lead.....do....	820	113,160	852	146,584
Petroleum.....barrels..	(a)	(a)	(a)	(a)
Platinum.....fine ounces (troy)..	.....	.....	76	7,845
Silver.....do....	1,379,171	907,495	1,239,150	1,021,060
Stone.....	.....	(a)	.....	(a)
Tin (metallic equivalent).....short tons..	139	120,874	100	123,300
Tungsten ore (60 per cent concentrates)....do....	47	69,518	32	45,000
Miscellaneous c.....	.....	521,839	.....	200,165
Total value, eliminating duplications.....	.....	48,521,513	.....	40,710,655

a Value included under "Miscellaneous."
b Calcined in Washington State. Value included under "Miscellaneous."
c 1916: Gypsum, petroleum, and stone; 1917: Chromic iron ore, crystalline graphite, gypsum, petroleum, and stone.

Digitized by Google

Mineral production of Arizona in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Antimony ore.....short tons..	.....	$3	.....	.....
Asbestos.....do....	(a)	(a)	950	$481,490
Clay products.....	.....	106,149	.....	135,474
Clay, raw.....short tons..	.....	.....	(a b)	(a b)
Copper.....pounds..	721,833,169	177,570,960	712,166,891	194,421,561
Fluorspar.....short tons..	(a)	(a)	(a)	(a)
Gems and precious stones.....	.....	4,878	.....	6,819
Gold.....fine ounces (troy)..	192,801	3,985,559	245,174	5,068,193
Gypsum.....short tons..	(a)	(a)	(a)	(a)
Lead.....do....	13,531	1,867,284	11,733	2,018,028
Lime.....do....	15,173	94,540	15,856	119,995
Manganese ore.....long tons..	3,060	113,060	14,802	479,971
Manganiferous ore.....do....	7,392	39,904	34,449	200,342
Molybdenum.....pounds..	203,580	203,000	344,950	487,985
Quicksilver.....flasks..	5	629	40	4,213
Sand and gravel.....short tons..	(a)	(a)	17,268	5,799
Sand and sandstone (finely ground).....do....	.....	.....	(a)	(a)
Silica (quartz).....do....	(a)	(a)	.....	.....
Silver.....fine ounces (troy)..	7,212,039	4,745,522	6,983,913	5,754,744
Stone.....	.....	306,579	.....	319,724
Strontium ore.....short tons..	(a)	(a)	.....	.....
Sulphuric acid c.....do....	.....	.....	(a)	(a)
Tungsten ore (60 per cent concentrates)..do....	218	385,292	150	173,700
Zinc.....do....	9,839	2,636,845	10,447	2,131,276
Miscellaneous d.....	.....	562,787	.....	806,679
Total value, eliminating duplications.....	.....	192,622,991	.....	212,615,978

a Value included under "Miscellaneous."
b Value not included in total value for State.
c From copper smelting.
d 1916: Asbestos, fluorspar, gypsum, sand and gravel, silica (quartz), and strontium ore; 1917: Raw clay, fluorspar, gypsum, sand and sandstone (finely ground), and sulphuric acid from copper smelting.

Mineral production of Arkansas in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Antimony ore.....short tons..	250	$1,236	.....	.....
Bauxite.....long tons..	375,910	2,011,590	506,556	$2,724,007
Clay products.....	.....	a 521,569	.....	a 672,766
Clay, raw.....short tons..	(b c)	(b c)	.....	.....
Coal.....do....	1,994,915	3,836,845	2,143,579	5,492,777
Fuller's earth.....do....	(b)	(b)	(b)	(b)
Gems and precious stones.....	.....	2,250	.....	4,260
Iron ore {Sold to furnaces.....long tons..	.....	.....	40	(b)
Iron ore {Sold for magnets.....do....	5	(b)	5	(b)
Lead.....short tons..	272	37,536	382	65,704
Lime.....do....	19,199	102,663	17,350	117,598
Manganese ore.....long tons..	6,318	180,722	10,140	448,511
Manganiferous ore.....do....	3,682	22,665	9,100	83,227
Marl, calcareous.....short tons..	(b)	(b)	(b)	(b)
Mineral waters.....gallons sold..	1,152,505	100,616	1,020,463	78,141
Natural gas.....	.....	210,964	.....	315,612
Oilstones.....	.....	(b)	.....	(b)
Sand and gravel.....short tons..	543,902	170,068	582,063	176,923
Stone.....	.....	374,465	.....	371,732
Zinc.....short tons..	6,815	1,826,420	6,691	1,364,964
Miscellaneous d.....	.....	118,183	.....	145,485
Total value, eliminating duplications.....	.....	9,508,001	.....	12,061,702

a Exclusive of pottery, value for which is included under "Miscellaneous."
b Value included under "Miscellaneous."
c Value not included in total value for State.
d 1916: Pottery, raw clay, fuller's earth, iron ore, calcareous marl, and oilstones; 1917: Pottery, fuller's earth, iron ore, calcareous marl, and oilstones.

Digitized by Google

Mineral production of California in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Antimony ore.....short tons..	899	$6,159	42	$1,594
Asbestos.....do....	(a)	(a)	(a)	(a)
Asphalt.....do....	276,065	2,004,048	226,303	2,119,699
Barytes.....do....	(a)	(a)	(a)	(a)
Borax (crude).....do....	103,525	2,409,459	108,875	3,609,632
Briquets (fuel).....do....	(a b)	(a b)	(a b)	(a b)
Calcium chloride.....do....			(a)	(a)
Cement.....barrels..	5,218,324	7,407,290	5,659,547	7,426,097
Chromic iron ore.....long tons..	43,758	682,937	36,774	875,248
Clay products.....		4,163,426		4,828,607
Clay, raw.....short tons..	106,330	b 133,950	137,892	b 151,348
Coal.....do....	(a)	(a)	(a)	(a)
Copper.....pounds..	55,897,118	13,750,691	48,153,139	13,145,807
Diatomaceous earth.....		(a)		(a)
Feldspar.....short tons..	1,400	6,550	7,874	18,543
Ferroalloys.....long tons..	(a b)	(a b)	2,113	b 544,650
Fuller's earth.....short tons..	(a)	(a)	(a)	(a)
Gems and precious stones.....		54,885		15,972
Gold.....fine ounces (troy)..	1,035,745	21,410,741	971,733	20,087,504
Graphite, crystalline.....pounds..	(a)	(a)	(a)	(a)
Gypsum.....short tons..	32,575	109,061	30,552	96,718
Iron ore.....long tons..	2,970	11,880	2,207	8,828
Iron, pig.....do....	154	(a b)		
Lead.....short tons..	6,204	856,117	10,934	1,880,702
Lime.....do....	56,820	393,930	78,401	597,528
Lithium minerals.....do....	(a)	(a)	(a)	(a)
Magnesite.....do....	154,259	1,388,331	211,663	2,116,630
Manganese ore.....long tons..	6,136	122,592	14,196	328,501
Manganiferous ore.....do....	139	(a)	152	1,760
Marl (calcareous).....short tons..	(a)	(a)	(a)	(a)
Mineral waters.....gallons sold..	2,651,471	503,775	2,566,491	455,360
Molybdenum.....pounds..	666	700	(a)	(a)
Natural gas.....		5,440,277		6,816,524
Natural-gas gasoline.....gallons..	17,158,754	2,293,822	28,817,604	4,438,022
Peat.....short tons..			(a)	(a)
Pebbles for grinding.....do....	6,000	36,000	9,278	48,775
Petroleum.....barrels..	90,951,936	53,702,733	93,877,549	86,161,764
Platinum and allied metals.fine ounces (troy)..	687	55,979	297	29,014
Potash (K_2O).....short tons..	3,823	1,403,199	12,127	5,446,918
Pumice.....do....	(a)	(a)	(a)	(a)
Pyrite.....long tons..	145,762	565,699	115,817	333,501
Quicksilver.....flasks..	21,045	2,649,355	23,938	2,521,151
Salt.....short tons..	157,393	656,975	215,154	933,429
Sand and gravel.....do....	4,489,498	1,036,085	3,781,388	1,138,128
Sand-lime brick.....		c 3,337		(a)
Silica (quartz).....short tons..	5,648	11,533	7,325	18,197
Silver.....fine ounces (troy)..	2,564,354	1,687,345	1,775,431	1,462,955
Slate.....		(a)		(a)
Sodium salts (carbonate, bicarbonate, and sulphate) from natural sources.....short tons..	10,666	528,696	20,713	891,997
Stone.....		3,133,305		2,911,462
Strontium ore.....short tons..	(a)	(a)	3,861	77,220
Sulphuric acid (60° Baumé) d.....do....	(a)	(a)	(a)	(a)
Talc and soapstone.....do....	685	10,969	4,152	74,000
Tungsten ore (60 per cent concentrates)..do....	2,171	4,098,999	2,781	3,010,300
Volcanic ash.....		967		
Zinc.....short tons..	7,628	2,044,369	5,436	1,109,017
Miscellaneous e.....		3,762,921		565,141
Total value, elimfnating duplications.....		137,284,754		175,401,518

a Value included under "Miscellaneous."
b Value not included in total value for State.
c Exclusive of fancy brick, value for which is included under "Miscellaneous."
d From copper smelting.
e 1916: Asbestos, barytes, fuel briquets, coal, diatomaceous earth, ferroalloys, fuller's earth, crystalline graphite, pig iron, lithium minerals, manganiferous ore, calcareous marl, pumice, fancy brick (sand-lime), slate, strontium ore, and sulphuric acid from copper smelting; 1917: Asbestos, barytes, fuel briquets, calcium chloride, coal, diatomaceous earth, fuller's earth, crystalline graphite, lithium minerals, calcareous marl, molybdenum peat, pumice, sand-lime brick, slate, and sulphuric acid from copper smelting.

Digitized by Google

Mineral production of Colorado in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Asphalt.....short tons..	(a)	(a)	700	$37,500
Barytes.....do....	481	$3,005	.....	.....
Briquets (fuel).....do....	(a b)	(a b)	(a b)	(a b)
Cement.....barrels..	(a)	(a)	(a)	(a)
Clay products.....	.....	1,930,039	.....	2,579,267
Clay, raw.....short tons..	76,936	b 77,830	106,775	b 103,376
Coal.....do....	10,484,237	16,964,104	12,483,336	27,669,129
Coke.....do....	1,053,553	b 3,736,467	1,112,449	b 5,479,734
Copper.....pounds..	8,624,081	2,121,524	8,122,004	2,217,307
Ferroalloys.....long tons..	(a b)	(a b)	30,415	b 1,614,701
Fluorspar.....short tons..	(a)	(a)	17,104	196,633
Gems and precious stones.....	.....	10,818	.....	7,205
Gold.....fine ounces (troy)..	926,566	19,153,821	760,901	15,729,224
Graphite, amorphous.....short tons..	(a)	(a)	(a)	(a)
Gypsum.....do....	(a)	(a)	(a)	(a)
Iron ore.....long tons..	(a)	(a)	(a)	(a)
Iron, pig.....do....	367,629	(a b)	332,562	(a b)
Lead.....short tons..	35,457	4,893,072	33,995	5,847,141
Lime.....do....	5,479	36,473	6,212	54,676
Manganese ore.....long tons..	110	1,670	114	(a)
Manganiferous ore.....do....	107,113	318,027	124,861	303,802
Mica.....	.....	(a)	.....	(a)
Mineral waters.....gallons sold..	542,185	120,509	442,815	65,169
Molybdenum.....pounds..	.....	.....	(a)	(a)
Natural gas.....	.....	(a)	.....	(a)
Natural-gas gasoline.....gallons..	(a)	(a)	(a)	(a)
Petroleum.....barrels..	197,235	217,139	121,231	128,100
Potash (K_2O).....short tons..	.....	.....	(a)	(a)
Pyrite.....long tons..	15,576	(a)	20,000	(a)
Sand and gravel.....short tons..	244,208	93,259	150,063	74,540
Silica (quartz).....do....	(a)	(a)	.....	.....
Silver.....fine ounces (troy)..	7,456,544	5,038,006	7,304,353	6,018,787
Stone.....	.....	975,794	.....	823,904
Sulphur.....long tons..	.....	.....	(a)	(a)
Sulphuric acid c.....short tons..	(a)	(a)	(a)	(a)
Tungsten ore (60 per cent concentrates)...do....	2,401	4,666,301	2,707	2,994,000
Uranium and vanadium ores.....do....	.....	490,000	.....	587,700
Zinc.....do....	67,143	17,994,252	60,158	12,272,209
Miscellaneous d.....	.....	9,056,582	.....	9,188,718
Total value, eliminating duplications.....	.....	77,642,778	.....	80,586,021

a Value included under "Miscellaneous."
b Value not included in total value for State.
c From zinc smelting.
d 1916: Asphalt, fuel briquets, cement, ferroalloys, fluorspar, amorphous graphite, gypsum, iron ore, pig iron, mica, natural gas, natural-gas gasoline, pyrite, silica (quartz), and sulphuric acid from zinc smelting; 1917: Fuel briquets, cement, amorphous graphite, gypsum, iron ore, pig iron, manganese ore, mica, molybdenum, natural gas, natural-gas gasoline, potash, pyrite, sulphur, and sulphuric acid from zinc smelting.

Digitized by Google

Mineral production of Connecticut in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Clay products		$1,865,329		$1,887,537
Clay, raw, short tons	(a b)	(a b)	(a b)	(a b)
Diatomaceous earth		(a)		(a)
Feldspar, short tons	12,333	76,979	10,937	73,932
Gems and precious stones		(a)		(a)
Iron ore, long tons	(a)	(a)	(a)	(a)
Iron, pig, do	4,978	(a b)	5,343	(a b)
Lime, short tons	85,063	589,257	64,389	492,678
Mica		(a)		
Mineral waters, gallons sold	2,837,878	133,768	1,964,096	103,978
Sand and gravel, short tons	89,682	53,040	213,034	127,530
Sand-lime brick		(a)		
Silica (quartz), short tons	(a)	(a)		
Stone		1,143,011		1,238,684
Tungsten ore (60 per cent concentrates), short tons	3	8,400		
Miscellaneous c		235,348		243,997
Total value, eliminating duplications		3,940,676		3,981,203

a Value included under "Miscellaneous."
b Value not included in total value for State.
c 1916: Raw clay, diatomaceous earth, gems and precious stones, iron ore, pig iron, mica, sand-lime brick, and silica (quartz); 1917: Raw clay, diatomaceous earth, gems and precious stones, iron ore, and pig iron.

Mineral production of Delaware in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Clay products		$187,388		$197,310
Clay, raw, short tons	12,844	a 101,384	11,243	a 85,330
Mineral waters, gallons sold	(b)	(b)	(b)	(b)
Sand and gravel, short tons	9,487	9,721	166,413	101,252
Stone		121,354		216,346
Miscellaneous		17,709		9,063
Total value, eliminating duplications		336,172		523,991

a Value not included in total value for State.
b Value included under "Miscellaneous."

Mineral production of the District of Columbia in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Clay products		a $129,394		$160,242
Mineral waters, gallons sold	(b)	(b)	(b)	(b)
Sand-lime brick		(b)		(b)
Stone		3,315		4,615
Miscellaneous c		46,727		40,079
Total value, eliminating duplications		179,436		204,936

a Exclusive of pottery, value for which is included under "Miscellaneous."
b Value included under "Miscellaneous."
c 1916: Pottery, mineral waters, and sand-lime brick; 1917: Mineral waters and sand-lime brick.

Digitized by Google

Mineral production of Florida in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Clay products		$226,362		$229,406
Clay, raw short tons	(a b)	(a b)	(a b)	(a b)
Flint lining for tube mills do			(a)	(a)
Fuller's earth do	(a)	(a)	(a)	(a)
Ilmenite do			(a)	(a)
Lime do	8,666	49,536	9,914	56,903
Mineral waters gallons sold	202,970	15,676	142,080	9,850
Monazite sand pounds	(a)	(a)		
Peat short tons	(a)	(a)	(a)	(a)
Phosphate rock long tons	1,515,845	4,170,165	2,022,599	5,464,493
Sand and gravel short tons	86,452	42,352	262,971	145,579
Sand-lime brick		90,794		95,158
Stone		479,837		654,845
Miscellaneous c		794,099		904,469
Total value, eliminating duplications		5,666,785		7,294,467

a Value included under "Miscellaneous."
b Value not included in total value for State.
c 1916: Raw clay, fuller's earth, monazite sand, and peat; 1917: Raw clay, flint lining for tube mills, fuller's earth, ilmenite, and peat.

Mineral production of Georgia in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Asbestos short tons	(a)	(a)	(a)	(a)
Barytes do	104,784	$401,295	111,300	$601,895
Bauxite long tons	40,388	239,089	52,901	337,498
Cement barrels	(a)	(a)	(a)	(a)
Clay products		2,361,982		2,426,671
Clay, raw short tons	193,791	b443,147	187,355	b599,359
Coal do	173,554	310,093	119,028	301,391
Coke do	47,127	b232,630	39,589	b322,175
Copper pounds	803,699	197,710	930,691	254,079
Feldspar short tons	(a)	(a)		
Fuller's earth do	(a)	(a)	(a)	(a)
Gold fine ounces (troy)	1,090	22,539	333	6,889
Iron ore Sold to furnaces long tons	252,143	413,259	211,501	524,175
Iron ore Sold for paint do			(a)	(a)
Iron, pig do			6,627	(a b)
Manganese ore do	(a)	(a)	3,614	89,888
Manganiferous ore do	(a)	(a)	13,281	118,368
Mica		2,094		13,541
Mineral waters gallons sold	618,367	45,210	411,127	37,441
Pyrite long tons	(a)	(a)	23,242	155,560
Sand and gravel short tons	483,615	126,799	380,154	138,182
Sand-lime brick		(a)		(a)
Silver fine ounces (troy)	74	49	46	37
Stone		1,799,210		1,797,098
Talc short tons	3,080	88,364	3,819	94,314
Miscellaneous c		772,135		998,526
Total value, eliminating duplications		6,779,828		7,650,553

a Value included under "Miscellaneous."
b Value not included in total value for State.
c 1916: Asbestos, cement, feldspar, fuller's earth, manganese and manganiferous ores, pyrite, and sand-lime brick; 1917: Asbestos, cement, fuller's earth, iron ore sold for paint, pig iron, and sand-lime brick.

Digitized by Google

Mineral production of Idaho in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Antimony ore.....short tons..	259	$2,946	39	$1,715
Asbestos.....do....	(a)	(a)	(a)	(a)
Clay products.....	.....	(a)	.....	(a)
Clay, raw.....short tons..	(a b)	(a b)	(a b)	(a b)
Coal.....do....	(a)	(a)	(a)	(a)
Copper.....pounds..	8,478,281	2,085,657	7,827,574	2,136,928
Gems and precious stones.....	.....	(a)	.....	(a)
Gold.....fine ounces (troy)..	53,977	1,115,810	38,933	804,809
Lead.....short tons..	187,541	25,880,643	196,780	33,846,119
Lime.....do....	4,389	31,786	7,228	62,331
Mica.....	.....	(a)	.....	(a)
Phosphate rock.....long tons..	.....	.....	(a)	(a)
Quicksilver.....flasks..	.....	.....	5	526
Salt.....short tons..	44	511	16	216
Sand and gravel.....do....	(a)	(a)	(a)	(a)
Sand-lime brick.....	.....	(a)	.....	(a)
Silver.....fine ounces (troy)..	12,300,873	8,093,974	12,029,338	9,912,175
Stone.....	.....	96,382	.....	94,644
Tungsten ore (60 per cent concentrates), ...short tons..	101	113,470	2	1,933
Zinc.....do....	43,253	11,591,699	39,927	8,145,122
Miscellaneous c.....	.....	237,460	.....	219,248
Total value, eliminating duplications....	.....	49,249,134	.....	55,224,026

a Value included under "Miscellaneous."
b Value not included in total value for State.
c 1916: Asbestos, clay products, raw clay, coal, gems and precious stones, mica, sand and gravel, and sand-lime brick; 1917: Asbestos, clay products, raw clay, coal, gems and precious stones, mica, phosphate rock, sand and gravel, and sand-lime brick.

Mineral production of Illinois in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Asphalt.....short tons..	155,406	$1,285,470	110,756	$1,317,855
Cement.....barrels..	a 3,562,659	a 3,386,431	a 4,378,233	a 6,090,158
Clay products.....	.....	17,633,351	.....	19,565,420
Clay, raw.....short tons..	197,701	b 378,440	195,693	b 789,589
Coal.....do....	66,195,336	82,457,954	86,199,357	162,281,822
Coke.....do....	2,320,400	b 10,619,066	2,289,833	b 14,455,539
Ferroalloys.....long tons..	(b c)	(b c)	(b c)	(b c)
Fluorspar.....short tons..	(c)	(c)	156,676	1,373,333
Iron, pig.....long tons..	3,857,391	b 67,764,309	3,458,126	b 91,094,541
Lead.....short tons..	1,072	147,936	1,439	247,508
Lime.....do....	90,012	369,038	83,409	501,320
Mineral paints (zinc and lead pigments)..do....	(b c)	(b c)	(b c)	(b c)
Mineral waters.....gallons sold..	1,777,741	94,056	1,370,461	66,042
Natural gas.....	.....	396,357	.....	479,072
Natural-gas gasoline.....gallons..	2,260,288	262,664	4,934,009	866,033
Peat.....short tons..	(c)	(c)	(c)	(c)
Petroleum.....barrels..	17,714,235	29,237,168	15,776,860	31,358,069
Potash (K_2O).....short tons..	.....	.....	(c)	(c)
Pyrite.....long tons..	20,482	51,432	24,596	89,998
Sand and gravel.....short tons..	8,365,225	2,587,437	9,120,698	3,658,799
Sand and sandstone (finely ground).....do....	(c)	(c)	386,866	630,256
Sand-lime brick.....	.....	(c)	.....	.....
Silver.....fine ounces (troy)..	5,684	3,740	7,186	5,921
Stone.....	.....	3,403,094	.....	3,322,041
Sulphuric acid d.....short tons..	.....	2,999,548	.....	3,902,831
Tripoli.....	.....	82,968	.....	31,338
Zinc.....short tons..	3,404	912,272	4,267	870,468
Miscellaneous e.....	.....	5,559,903	.....	6,343,662
Total value, eliminating duplications....	.....	146,359,792	.....	236,934,229

a Exclusive of natural cement, value for which is included under "Miscellaneous."
b Value not included in total value for State.
c Value included under "Miscellaneous."
d From zinc smelting.
e 1916: Natural cement, ferroalloys, fluorspar, zinc and lead pigments, peat, sand and sandstone (finely ground), and sand-lime brick; 1917: Natural cement, ferroalloys, zinc and lead pigments, peat, and potash.

Digitized by Google

Mineral production of Indiana in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Cement.....barrels..	[a] 10,350,105	[a] $11,487,893	[a] 8,148,678	[a] $11,084,930
Clay products.....	.....	9,667,313	.....	10,999,474
Clay, raw.....short tons..	69,748	[b] 65,537	73,863	[b] 78,463
Coal.....do....	20,093,528	25,506,246	26,539,329	52,940,106
Coke.....do....	3,489,660	[b] 16,096,479	3,540,718	[b] 21,831,302
Gems and precious stones.....	.....	[c]	.....	.....
Iron, pig.....long tons..	1,735,428	[b c]	2,162,872	[b c]
Lime.....short tons..	121,306	495,283	118,530	646,555
Mineral waters.....gallons sold..	609,544	188,645	521,758	152,469
Natural gas.....	.....	503,373	.....	453,310
Oilstones and scythestones.....	.....	25,521	.....	27,693
Peat.....short tons..	[c]	[c]	[c]	[c]
Petroleum.....barrels..	769,036	1,207,565	759,432	1,470,548
Pyrite.....long tons..	772	2,445	[c]	[c]
Sand and gravel.....short tons..	8,165,989	1,879,073	5,906,196	1,591,158
Sand-lime brick.....	.....	54,148	.....	60,201
Stone.....	.....	4,657,813	.....	4,449,809
Sulphuric acid [d].....short tons..	[c]	[c]	[c]	[c]
Miscellaneous [e].....	.....	27,482,752	.....	51,582,551
Total value, eliminating duplications.....	.....	56,926,558	.....	85,079,370

[a] Exclusive of natural cement, value for which is included under "Miscellaneous."
[b] Value not included in total value for State.
[c] Value included under "Miscellaneous."
[d] From zinc smelting.
[e] 1916: Natural cement, gems and precious stones, pig iron, peat, and sulphuric acid from zinc smelting; 1917: Natural cement, pig iron, peat, pyrite, and sulphuric acid from zinc smelting.

Mineral production of Iowa in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Cement.....barrels..	4,853,789	$6,165,547	4,428,765	$6,870,863
Clay products.....	.....	[a] 7,379,289	.....	7,540,213
Clay, raw.....short tons..	21,829	[b] 2,427	5,488	[b] 3,012
Coal.....do....	7,260,800	13,530,383	8,965,830	21,096,408
Ferroalloys.....long tons..	950	[b c]	[b c]	[b c]
Gypsum.....short tons..	522,293	1,496,795	461,864	2,041,997
Iron ore.....long tons..	10,151	[c]	22,612	[c]
Lead.....short tons..	14	1,932	34	5,848
Lime.....do....	[c]	[c]	[c]	[c]
Mineral waters.....gallons sold..	148,732	14,404	99,103	12,125
Natural gas.....	.....	275	.....	225
Sand and gravel.....short tons..	3,321,691	980,272	2,909,441	1,060,586
Stone.....	.....	561,084	.....	520,083
Zinc.....short tons..	21	5,628	18	3,672
Miscellaneous [d].....	.....	157,325	.....	539,662
Total value, eliminating duplications.....	.....	30,210,284	.....	39,336,372

[a] Exclusive of pottery, value for which is included under "Miscellaneous."
[b] Value not included in total value for State.
[c] Value included under "Miscellaneous."
[d] 1916: Pottery, ferroalloys, iron ore, and lime; 1917: Ferroalloys, iron ore, and lime.

Digitized by Google

Mineral production of Kansas in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Asphalt.....short tons..	(a)	(a)	(a)	(a)
Cement.....barrels..	b 4,298,097	b $4,613,609	b 3,772,884	b $5,271,721
Clay products.....	.....	2,747,803	.....	2,695,722
Coal.....short tons..	6,881,455	12,252,723	7,184,975	16,618,277
Gems and precious stones.....	.....	(a)	.....	.....
Gypsum.....short tons..	78,257	322,785	79,331	424,611
Lead.....do....	1,648	227,424	3,025	520,300
Lime.....do....	(a)	(a)	.....	.....
Mineral paints (zinc and lead pigments)..do....	(a c)	(a c)	(a c)	(a c)
Mineral waters.....gallons sold..	237,790	58,792	289,493	67,776
Natural gas.....	.....	4,855,389	.....	5,701,436
Natural-gas gasoline.....gallons..	215,000	35,030	1,174,980	241,219
Petroleum.....barrels..	8,738,077	10,339,958	36,536,125	67,120,573
Pumice.....short tons..	23,804	51,648	(a)	(a)
Salt.....do....	639,071	1,302,359	746,976	2,027,468
Sand and gravel.....do....	1,164,995	303,630	823,403	195,578
Stone.....	.....	603,490	.....	673,831
Sulphuric acid (60° Baumé) d.....short tons..	(a)	(a)	(a)	(a)
Zinc.....do....	12,448	3,336,064	20,249	4,130,796
Miscellaneous e.....	.....	1,717,111	.....	2,285,603
Total value, eliminating duplications.....	.....	41,847,955	.....	106,763,055

a Value included under "Miscellaneous."
b Exclusive of natural cement, value for which is included under "Miscellaneous."
c Value not included in total value for State.
d From zinc smelting.
e 1916: Asphalt, natural cement, gems and precious stones, lime, zinc and lead pigments, and sulphuric acid from zinc smelting; 1917: Asphalt, natural cement, zinc and lead pigments, pumice, and sulphuric acid from zinc smelting.

Mineral production of Kentucky in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Asphalt.....short tons..	(a)	(a)	(a)	(a)
Barytes.....do....	11,068	$54,995	6,720	$36,084
Cement.....barrels..	(a)	(a)	(a)	(a)
Clay products.....	.....	3,559,257	.....	5,040,255
Clay, raw.....short tons..	62,247	b 170,984	91,727	b 320,365
Coal.....do....	25,393,997	30,193,047	27,807,971	60,297,653
Coke.....do....	802,526	b 2,225,186	863,071	b 4,119,263
Ferroalloys.....long tons..	40,431	(a b)	(a b)	(a b)
Fluorspar.....short tons..	(a)	(a)	43,639	697,566
Iron, pig.....long tons..	144,444	b 2,595,600	192,204	b 5,532,357
Lead.....short tons..	153	21,114	123	21,156
Lime.....do....	1,236	6,304	723	3,783
Lithographic stone.....do....	20	1,500	3	489
Mineral waters.....gallons sold..	377,246	52,305	301,748	40,189
Natural gas.....	.....	752,638	.....	580,380
Natural-gas gasoline.....gallons..	725,467	141,347	3,818,209	763,186
Oilstones.....	.....	(a)	.....	(a)
Petroleum.....barrels..	1,202,569	2,188,495	3,088,160	7,033,714
Phosphate rock.....long tons..	(a)	(a)	(a)	(a)
Pyrite.....do....	.....	.....	(a)	(a)
Sand and gravel.....short tons..	1,053,431	474,216	905,414	490,546
Sand-lime brick.....	.....	(a)	.....	(a)
Stone.....	.....	1,429,838	.....	1,118,434
Zinc.....short tons..	1,096	293,728	751	153,204
Miscellaneous c.....	.....	1,668,158	.....	1,698,558
Total value, eliminating duplications.....	.....	40,015,935	.....	77,177,421

a Value included under "Miscellaneous."
b Value not included in total value for State.
c 1916: Asphalt, cement, ferroalloys, fluorspar, oilstones, phosphate rock, and sand-lime brick; 1917: Asphalt, cement, ferroalloys, oilstones, phosphate rock, pyrite, and sand-lime brick.

Digitized by Google

Mineral production of Louisiana in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Asphalt.....short tons			(a)	(a)
Clay products		[b] $360,855		$447,941
Mineral waters.....gallons sold	429,650	31,068	270,000	19,490
Natural gas		2,660,445		3,262,987
Natural-gas gasoline.....gallons	2,113,159	269,564	4,979,754	814,747
Petroleum.....barrels	15,248,138	14,669,774	11,392,201	17,224,602
Potash (K_2O).....short tons	(a)	(a)	(a)	(a)
Salt.....do	(a)	(a)	(a)	(a)
Sand and gravel.....do	1,579,701	535,968	1,514,522	639,807
Sand-lime brick				(a)
Stone		(a)		(a)
Sulphur.....long tons	(a)	(a)	(a)	(a)
Miscellaneous [c]		9,492,869		13,794,813
Total value, eliminating duplications		28,020,543		36,204,387

[a] Value included under "Miscellaneous."
[b] Exclusive of pottery, value for which is included under "Miscellaneous."
[c] 1916: Pottery, potash, salt, stone, and sulphur; 1917: Asphalt, potash, salt, sand-lime brick, stone, and sulphur.

Mineral production of Maine in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Clay products		[a] $546,725		[a] $531,870
Copper.....pounds			30,406	8,301
Feldspar.....short tons	28,006	235,922	35,527	291,252
Gems and precious stones		8,458		10,870
Lime.....short tons	162,100	956,371	124,199	950,811
Magnesium.....pounds	[b c]	[b c]	[b c]	[b c]
Mineral waters.....gallons sold	1,038,861	353,792	1,014,084	343,587
Peat.....short tons	[b]	[b]		
Potash (K_2O).....do	[b]	[b]		
Sand and gravel.....do	[b]	[b]	8,169	7,358
Silica (quartz).....do			[b]	[b]
Slate		[b]		[b]
Stone		1,068,485		1,254,637
Miscellaneous [d]		405,747		389,061
Total value, eliminating duplications		3,539,481		3,726,121

[a] Exclusive of pottery, value for which is included under "Miscellaneous."
[b] Value included under "Miscellaneous."
[c] Value not included in total value for State.
[d] 1916: Pottery, magnesium, peat, potash, sand and gravel, and slate; 1917: Pottery, magnesium, silica (quartz), and slate.

Digitized by Google

Mineral production of Maryland in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Asbestos.....short tons..			(a)	(a)
Briquets, fuel.....do..	(a b)	(a b)		
Cement.....barrels..	(a)	(a)	(a)	(a)
Chromic iron ore.....long tons..	(a)	(a)	(a)	(a)
Clay products.....		$1,825,870		$2,468,138
Clay, raw.....short tons..	45,975	b82,667	42,364	b114,027
Coal.....do....	4,460,046	6,947,623	4,745,924	11,667,852
Coke.....do....	489,962	b1,387,009	518,810	b3,925,418
Copper.....pounds..	158,780	39,060	291,501	79,580
Diatomaceous earth.....		(a)		(a)
Feldspar.....short tons..	23,928	83,957	15,779	56,958
Ferroalloys.....long tons..	(a b)	(a b)	33,097	b4,448,031
Gold.....fine ounces (troy)..			3	66
Iron ore.....long tons..	(a)	(a)	10,780	40,423
Iron, pig.....do....	465,365	(a b)	393,813	(a b)
Lime.....short tons..	157,673	574,998	133,087	694,576
Mineral waters.....gallons sold..	1,312,788	99,020	1,036,045	86,938
Potash (K_2O).....short tons..	(a)	(a)	792	341,885
Sand and gravel.....do....	1,872,159	900,061	1,727,440	923,463
Silica (quartz).....do....	7,203	31,712	3,251	22,633
Silver.....fine ounces (troy)..	575	378	1,092	900
Slate.....		71,737		67,938
Stone.....		921,909		938,637
Talc and soapstone.....short tons..	(a)	(a)	(a)	(a)
Miscellaneous c.....		15,519,309		11,740,502
Total value, eliminating duplications.....		13,335,013		19,617,596

a Value included under "Miscellaneous."
b Value not included in total value for State.
c 1916: Fuel briquets, cement, chromic iron ore, diatomaceous earth, ferroalloys, iron ore, pig iron, potash, and talc and soapstone; 1917: Asbestos, cement, chromic iron ore, diatomaceous earth, pig iron, and talc and soapstone.

Mineral production of Massachusetts in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Clay products.....		$1,802,558		$1,971,980
Clay, raw.....short tons..	802	a1,296	847	a1,329
Coke.....do....	563,048	(a b)	595,113	(a b)
Diatomaceous earth.....		(b)		
Fuller's earth.....short tons..	(b)	(b)	(b)	(b)
Gems and precious stones.....		(b)		(b)
Iron ore.....long tons..	(b)	(b)	11,019	(b)
Iron, pig.....do....	(a b)	(a b)	5,061	(a b)
Lime.....short tons..	145,020	811,402	134,937	916,569
Mineral waters.....gallons sold..	3,124,096	128,478	2,908,638	139,075
Peat.....short tons..	(b)	(b)	(b)	(b)
Potash (K_2O).....do....	(b)	(b)	(b)	(b)
Sand and gravel.....do....	1,049,577	533,308	1,005,952	694,960
Sand-lime brick.....		110,333		127,695
Silica (quartz).....short tons..	(b)	(b)	(b)	(b)
Stone.....		3,138,165		3,113,423
Talc.....short tons..	(b)	(b)	(b)	(b)
Miscellaneous c.....		2,359,380		4,279,961
Total value, eliminating duplications.....		6,697,444		7,225,750

a Value not included in total value for State.
b Value included under "Miscellaneous."
c 1916: Coke, diatomaceous earth, fuller's earth, gems and precious stones, iron ore, pig iron, peat, potash, silica (quartz), and talc; 1917: Coke, fuller's earth, gems and precious stones, iron ore, pig iron, peat, potash, silica (quartz), and talc.

Digitized by Google

Mineral production of Michigan in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Briquets, fuel.....short tons..	(a b)	(a b)		
Bromine.....pounds..	513,208	$685,445	735,654	$405,059
Calcium chloride.....short tons..	17,122	159,358	22,679	294,693
Cement.....barrels..	5,151,818	6,017,911	4,313,771	6,122,887
Clay products.....		3,497,770		4,034,245
Clay, raw.....short tons..	3,454	b11,153	5,746	b13,627
Coal.....do....	1,180,360	2,653,182	1,374,805	4,426,314
Coke.....do....	(a b)	(a b)	(a b)	(a b)
Copper.....pounds..	273,692,525	67,328,361	255,710,128	69,808,865
Gems and precious stones.....		113		95
Graphite, amorphous.....short tons..	(a)	(a)	(a)	(a)
Grindstones.....		(a)		(a)
Gypsum.....short tons..	457,375	1,066,599	375,803	1,568,655
Iron ore:				
Sold to furnaces.....long tons..	18,995,797	49,054,340	17,712,916	62,833,624
Sold for paint.....do....	2,358	(a)	1,445	(a)
Iron, pig.....do....	505,646	b8,351,361	611,446	b18,300,501
Lime.....short tons..	86,447	385,341	135,920	892,682
Magnesium.....pounds..			(a)	(a)
Manganiferous ore.....long tons..			52,198	(a)
Mineral waters.....gallons sold..	996,875	108,867	1,069,164	105,641
Natural gas.....		948		1,013
Petroleum.....barrels..	(a)	(a)	(a)	(a)
Potash (K_2O).....short tons..	314	207,175	381	299,395
Salt.....do....	2,088,559	4,612,567	2,250,939	6,877,202
Sand and gravel.....do....	4,407,475	1,306,256	3,814,445	1,641,748
Sand-lime brick.....		499,711		370,723
Scythestones.....		(a)		(a)
Silica (quartz).....short tons..	(a)	(a)	(a)	(a)
Silver.....fine ounces (troy)..	716,640	471,549	688,551	567,366
Stone.....		2,494,284		3,423,825
Miscellaneous c.....		3,207,501		5,791,496
Total value, eliminating duplications.....		140,666,124		163,997,858

a Value included under "Miscellaneous."
b Value not included in total value for State.
c 1916: Fuel briquets, coke, amorphous graphite, grindstones, iron ore sold for paint, petroleum, scythestones, and silica (quartz); 1917: Coke, amorphous graphite, grindstones, iron ore sold for paint, magnesium, manganiferous ore, petroleum, scythestones, and silica (quartz).

Mineral production of Minnesota in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Cement.....barrels..	868,300	$911,705	1,552,250	$2,143,671
Clay products.....		a 2,064,362		a 2,197,664
Clay, raw.....short tons..	(b c)	(b c)	(b c)	(b c)
Coke.....do....	431,319	c 1,968,675	490,272	c 3,468,355
Flint lining for tube mills.....do....			(b)	(b)
Gems and precious stones.....		(b)		(b)
Iron ore.....long tons..	45,869,251	106,628,784	44,962,127	142,901,148
Iron, pig.....do....	377,132	(b c)	363,180	(b c)
Lime.....short tons..	20,150	103,000	18,072	119,704
Manganiferous ore.....long tons..	240,403	790,762	451,163	2,055,335
Mineral waters.....gallons sold..	4,188,434	145,582	3,004,546	109,964
Pebbles for grinding.....short tons..			(b)	(b)
Sand and gravel.....do....	1,468,530	491,270	1,209,455	488,089
Sand-lime brick.....		178,828		152,531
Stone.....		1,833,800		1,711,318
Miscellaneous d.....		6,210,674		9,993,125
Total value, eliminating duplications.....		113,662,522		152,490,554

a Exclusive of pottery, value for which is included under "Miscellaneous."
b Value included under "Miscellaneous."
c Value not included in total value for State.
d 1916: Pottery, raw clay, gems and precious stones, and pig iron; 1917: Pottery, raw clay, flint lining for tube mills, gems and precious stones, pig iron, and pebbles for grinding.

Digitized by Google

Mineral production of Mississippi in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Clay products		$520,618		$553,565
Clay, raw.....short tons	(a b)	(a b)	(a b)	(a b)
Mineral waters.....gallons sold	399,248	48,439	197,555	49,796
Sand and gravel.....short tons	1,435,460	321,509	1,414,048	360,664
Stone				(a)
Miscellaneous [c]		100		51,000
Total value, eliminating duplications		890,566		966,135

[a] Value included under "Miscellaneous."
[b] Value not included in total value for State.

Mineral production of Missouri in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Barytes.....short tons	58,223	$365,111	59,046	$391,363
Briquets, fuel.....do	(a b)	(a b)	(a b)	(a b)
Cement.....barrels	5,732,001	6,333,567	5,800,988	8,248,007
Chats.....short tons	2,890,970	433,646	1,426,716	285,343
Clay products		7,640,995		10,339,049
Clay, raw.....short tons	439,583	[b] 988,884	497,267	[b] 1,396,338
Coal.....do	4,742,146	9,044,505	5,670,549	13,755,864
Coke.....do	(a b)	(a b)	(a b)	(a b)
Copper.....pounds	386,200	95,005	365,013	99,649
Gems and precious stones		(a)		
Iron ore.....long tons	34,914	116,484	38,770	134,906
Iron, pig.....do	39,018	(a b)	83,266	(a b)
Lead.....short tons	233,088	32,166,144	234,156	40,274,832
Lime.....do	199,260	956,300	234,936	1,435,914
Mineral paints (zinc and lead pigments).....do	(a b)	(a b)	(a b)	(a b)
Mineral waters.....gallons sold	1,394,092	109,814	401,776	57,175
Natural gas		17,594		8,230
Petroleum.....barrels	(a)	(a)		
Potash (K_2O).....short tons	(a)	(a)		
Pyrite.....long tons	(a)	(a)	(a)	(a)
Sand and gravel.....short tons	3,643,205	877,634	2,274,072	1,101,745
Silver.....fine ounces (troy)	129,450	85,178	61,586	50,747
Stone		2,242,742		1,983,300
Tripoli		[c] 92,248		[c] 16,606
Tungsten ore (60 per cent concentrates).....short tons	5	2,657		
Zinc.....do	155,960	41,797,280	132,918	27,115,272
Miscellaneous [d]		3,141,535		5,630,279
Total value, eliminating duplications		102,424,953		105,320,378

[a] Value included under "Miscellaneous."
[b] Value not included in total value for State.
[c] Includes small product from Oklahoma. Not separable.
[d] 1916: Fuel briquets, coke, gems and precious stones, pig iron, zinc and lead pigments, petroleum, potash, and pyrite; 1917: Fuel briquets, coke, pig iron, zinc and lead pigments, and pyrite.

Digitized by Google

Mineral production of Montana in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Cement.....barrels..	(a)	(a)	(a)	(a)
Clay products.....	.....	b $717,551	.....	3663,815
Clay, raw.....short tons..	(a c)	(a c)	7,083	c 26,710
Coal.....do...	3,632,527	6,286,197	4,226,699	8,919,136
Copper.....pounds..	352,928,373	86,820,360	274,462,574	74,928,283
Gems and precious stones.....	.....	108,263	.....	59,130
Gold.....fine ounces (troy)..	220,130	4,550,494	170,147	3,517,253
Graphite, crystalline.....pounds..	(a)	(a)	(a)	(a)
Gypsum.....short tons..	(a)	(a)	(a)	(a)
Iron ore.....long tons..	.....	.....	(a)	(a)
Lead.....short tons..	6,798	988,064	10,976	1,887,805
Lime.....do....	(a)	(a)	5,281	35,512
Manganese ore.....long tons..	6,418	87,978	61,109	1,797,842
Manganiferous ore.....do....	.....	.....	1,568	(a)
Mineral waters.....gallons sold..	181,800	12,294	211,133	9,570
Natural gas.....	.....	38,855	.....	81,406
Petroleum.....barrels..	44,917	44,019	99,399	146,272
Sand and gravel.....short tons..	296,787	58,185	597,642	139,384
Silver.....fine ounces (troy)..	16,494,866	10,853,293	13,128,142	10,817,589
Stone.....	.....	261,460	.....	255,835
Sulphuric acid (60° Baumé) d.....short tons..	(a)	(a)	(a)	(a)
Tungsten ore (60 per cent concentrates)..do....	1	1,163	16	21,500
Zinc.....do....	114,630	30,720,716	93,180	18,998,452
Miscellaneous e.....	.....	1,221,380	.....	1,454,631
Total value, eliminating duplications.....	.....	142,650,179	.....	123,733,415

a Value included under "Miscellaneous."
b Exclusive of pottery, value for which is included under "Miscellaneous."
c Value not included in total value for State.
d From copper smelting.
e 1916: Cement, pottery, raw clay, crystalline graphite, gypsum, lime, and sulphuric acid from copper smelting; 1917: Cement, crystalline graphite, gypsum, iron ore, manganiferous ore, and sulphuric acid from copper smelting.

Mineral production of Nebraska in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Cement.....barrels..	.....	.....	(a)	(a)
Clay products.....	.....	b $943,553	.....	b $1,160,508
Clay, raw.....short tons..	(a c)	(a c)	1,980	c 4,412
Mineral waters.....gallons sold..	8,440	946	(a)	(a)
Potash (K_2O).....short tons..	(a)	(a)	14,558	5,879,534
Pumice.....do....	9,259	25,155	5,051	16,707
Sand and gravel.....do....	1,267,998	289,872	1,327,152	358,414
Stone.....	.....	406,707	.....	476,307
Miscellaneous d.....	.....	1,772,522	.....	52,259
Total value, eliminating duplications.....	.....	3,436,774	.....	7,943,729

a Value included under "Miscellaneous."
b Exclusive of pottery, value for which is included under "Miscellaneous."
c Value not included in total value for State.
d 1916: Pottery, raw clay, and potash; 1917: Cement, pottery, and mineral waters.

Digitized by Google

Mineral production of Nevada in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Antimony ore.....short tons..	1,400	$13,216	872	$46,609
Barytes.....do....	(a)	(a)	(a)	(a)
Clay products.....	.....	(a)	.....	(a)
Clay, raw.....short tons..	.....	.....	(a b)	(a b)
Copper.....pounds..	105,116,813	26,858,736	122,794,704	33,522,954
Diatomaceous earth.....	.....	(a)	.....	(a)
Gems and precious stones.....	.....	15,734	.....	17,851
Gold.....fine ounces (troy)..	426,904	8,866,287	336,664	6,959,468
Graphite, amorphous.....short tons..	(a)	(a)	(a)	(a)
Gypsum.....do....	(a)	(a)	(a)	(a)
Iron ore.....long tons..	9,910	(a)	1,010	(a)
Lead.....short tons..	12,819	1,768,972	13,839	2,380,302
Lime.....do....	(a)	(a)	(a)	(a)
Manganese ore.....long tons..	(a)	(a)	3,450	91,907
Manganiferous ore.....do....	122,429	(a)	122,872	142,543
Mineral waters.....gallons sold..	346,260	4,160	(a)	(a)
Molybdenum.....pounds..	.....	.....	(a)	(a)
Pebbles for grinding.....short tons..	(a)	(a)	(a)	(a)
Platinum and allied metals..fine ounces (troy)..	(a)	(a)	507	55,021
Quicksilver.....flasks..	2,198	276,706	997	105,004
Salt.....short tons..	(a)	(a)	(a)	(a)
Sand and gravel.....do....	(a)	(a)	75,466	8,813
Silver.....fine ounces (troy)..	13,837,525	9,105,092	11,269,969	9,286,454
Stone.....	.....	.....	.....	31,625
Sulphur.....long tons..	(a)	(a)	(a)	(a)
Tungsten ore (60 per cent concentrates), ...short tons..	689	2,240,619	143	187,500
Zinc.....do....	16,222	4,347,387	11,154	2,275,402
Miscellaneous c.....	.....	1,013,700	.....	299,757
Total value, eliminating duplications.....	.....	53,510,559	.....	55,410,190

a Value included under "Miscellaneous."
b Value not included in total value for State.
c 1916: Barytes, clay products, diatomaceous earth, amorphous graphite, gypsum, iron ore, lime, manganese and manganiferous ores, pebbles for grinding, platinum and allied metals, salt, sand and gravel, and sulphur; 1917: Barytes, clay products, raw clay, diatomaceous earth, amorphous graphite, gypsum, iron ore, lime, mineral waters, molybdenum, pebbles for grinding, salt, and sulphur.

Mineral production of New Hampshire in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Clay products.....	.....	a $473,434	.....	a $411,876
Diatomaceous earth.....	.....	(b)	.....	.....
Feldspar.....short tons..	(b)	(b)	(b)	(b)
Fluorspar.....do....	(b)	(b)	(b)	(b)
Garnet, abrasive.....do....	(b)	(b)	(b)	(b)
Gems and precious stones.....	.....	550	.....	(b)
Lead.....short tons..	47	6,433	48	8,256
Mica.....	.....	75,239	.....	169,051
Mineral waters.....gallons sold..	269,860	14,935	105,181	6,975
Sand and gravel.....short tons..	(b)	(b)	258,638	28,070
Scythestones.....	.....	(b)	.....	(b)
Silver.....fine ounces (troy)..	945	622	120	99
Stone.....	.....	1,141,810	.....	921,943
Zinc.....short tons..	36	9,681	45	9,190
Miscellaneous c.....	.....	95,019	.....	39,124
Total value, eliminating duplications.....	.....	1,817,723	.....	1,594,584

a Exclusive of pottery, value for which is included under "Miscellaneous."
b Value included under "Miscellaneous."
c 1916: Pottery, diatomaceous earth, feldspar, fluorspar, abrasive garnet, sand and gravel, and scythestones; 1917: Pottery, feldspar, fluorspar, abrasive garnet, gems and precious stones, and scythestones.

Digitized by Google

Mineral production of New Jersey in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Briquets, fuel.....short tons..	(a b)	(a b)		
Cement.....barrels..	2,592,302	$2,534,623	2,397,069	$2,962,592
Clay products.....		20,814,402		22,529,282
Clay, raw.....short tons..	371,916	b 790,796	380,362	b 1,035,708
Coke.....do....	210,766	(a b)	423,361	(a b)
Ferroalloys.....long tons..			6,228	(a b)
Gems and precious stones.....				(a)
Iron ore.....long tons..	528,084	1,877,056	474,708	2,341,160
Iron, pig.....do....	75,433	(a b)	187,753	b 6,618,536
Lime.....short tons..	7,110	26,084	5,002	18,978
Manganiferous zinc residuum c.....long tons..	198,817	(a)	155,332	(a)
Marl, greensand.....short tons..	1,220	610	(a)	(a)
Mineral paints (zinc and lead pigments)..do....			(a b)	(a b)
Mineral waters.....gallons sold..	1,560,028	130,993	1,283,157	115,188
Peat.....short tons..	26,864	197,754	42,361	320,550
Potash (K_2O).....do....	(a)	(a)		
Sand and gravel.....do....	3,936,020	1,517,473	3,782,457	2,025,324
Sand and sandstone (finely ground).....do....			(a)	(a)
Sand-lime brick.....		(a)		
Slate.....		(a)		(a)
Stone.....		1,655,692		1,860,397
Sulphuric acid d.....short tons..				(a)
Talc.....do....	(a)	(a)	(a)	(a)
Zinc.....do....	112,020	(a)	120,846	(a)
Miscellaneous e.....		34,658,439		30,022,147
Total value, eliminating duplications.....		59,430,705		57,710,181

a Value included under "Miscellaneous."
b Value not included in total value for State.
c Ore mined in New Jersey; smelted in Pennsylvania.
d From copper smelting.
e 1916: Fuel briquets, coke, pig iron, manganiferous zinc residuum, potash, sand-lime brick, slate, talc, and zinc; 1917: Coke, ferroalloys, gems and precious stones, greensand marl, zinc and lead pigments, sand and sandstone (finely ground), slate, sulphuric acid from copper smelting, talc, and zinc.

Mineral production of New Mexico in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Clay products.....		$257,561		$257,876
Clay, raw.....short tons..	3,602	a 9,511	2,269	a 8,931
Coal.....do....	3,703,011	5,580,369	4,000,527	7,455,166
Coke.....do....	502,812	a 1,718,976	577,679	a 2,805,277
Copper.....pounds..	92,747,289	22,815,333	105,568,000	28,820,064
Gems and precious stones.....		675		(b)
Gold.....fine ounces (troy)..	66,877	1,382,480	51,479	1,064,158
Gypsum.....short tons..	(b)	(b)	(b	(b)
Iron ore.....long tons..	157,779	168,157	231,604	381,275
Lead.....short tons..	4,107	566,779	4,554	783,357
Lime.....do....	1,582	11,670	1,829	12,327
Manganese ore.....long tons..	(b)	(b)	2,603	54,143
Manganiferous ore.....do....	16,068	(b)	15,900	(b)
Mineral paints (zinc and lead pigments)..... short tons..			(a b)	(a b)
Mineral waters.....gallons sold..	35,450	3,965	48,325	2,330
Salt.....short tons..	(b)	(b)	(b)	(b)
Sand and gravel.....do....	(b)	(b)	(b)	(b)
Silver.....fine ounces (troy)..	1,766,274	1,162,208	1,394,365	1,148,957
Stone.....		77,290		72,411
Tungsten ore (60 per cent concentrates)..... short tons..	16	39,227	(b)	(b)
Zinc.....do....	18,285	4,900,467	15,100	3,080,400
Miscellaneous c.....		156,320		188,984
Total value, eliminating duplications.....		37,123,501		43,312,947

a Value not included in total value for State.
b Value included under "Miscellaneous."
c 1916: Gypsum, manganese and manganiferous ores, salt, and sand and gravel; 1917: Gems and precious stones, gypsum, manganiferous ore, zinc and lead pigments, salt, sand and gravel, and tungsten ore.

Digitized by Google

Mineral production of New York in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Aluminum.....pounds..	(a b)	(a b)	(a b)	(a b)
Cement.....barrels..	5,707,892	35,804,444	5,466,355	37,092,051
Clay products.....	.....	11,755,012	.....	11,428,399
Clay, raw.....short tons..	11,158	b 36,413	11,894	b 51,505
Coke.....do....	775,014	b 3,033,276	993,184	b 6,899,424
Diatomaceous earth.....	.....	(a)	.....	(a)
Emery.....short tons..	15,282	123,901	15,941	170,223
Feldspar.....do....	17,426	82,461	13,462	62,003
Ferroalloys.....long tons..	(a b)	(a b)	12,677	b 3,289,472
Garnet, abrasive.....short tons..	5,840	198,200	4,786	193,440
Gems and precious stones.....	.....	(a)	.....	.....
Graphite:				
Artificial.....pounds..	8,397,281	(a b)	10,474,649	(c)
Crystalline.....do....	(a)	(a)	2,941,040	261,548
Gypsum.....short tons..	579,827	1,459,587	606,268	2,293,418
Iron ore:				
Sold to furnaces.....long tons..	1,464,917	5,571,429	1,356,011	7,381,333
Sold for paint.....do....	13,011	34,296	11,212	(a)
Iron, pig.....do....	2,289,606	b 40,537,240	2,276,367	b 52,318,661
Lime.....short tons..	117,490	636,668	108,788	892,855
Magnesium.....pounds..	39,163	b 187,443	83,000	b 168,000
Marl, calcareous.....short tons..	(a)	(a)	(a)	(a)
Mica.....	.....	(a)	.....	.....
Millstones.....	.....	10,287	.....	22,103
Mineral waters.....gallons sold..	7,746,490	697,650	7,819,314	562,874
Natural gas.....	.....	2,355,320	.....	2,499,303
Natural-gas gasoline.....gallons..	213,055	34,888	154,882	28,377
Peat.....short tons..	(a)	(a)	2,619	6,027
Petroleum.....barrels..	874,087	2,190,195	879,685	2,850,378
Potash (K_2O).....short tons..	(a)	(a)	5	2,086
Pyrite.....long tons..	(a)	(a)	(a)	(a)
Salt.....short tons..	1,972,285	3,698,798	2,164,069	5,371,713
Sand and gravel.....do....	8,098,097	2,644,829	7,119,013	3,046,447
Sand-lime brick.....	.....	d 109,087	.....	130,626
Silica (quartz).....short tons..	(a)	(a)	(a)	(a)
Slate.....	.....	21,345	.....	55,207
Stone.....	.....	5,342,954	.....	5,399,403
Talc, fibrous.....short tons..	93,236	961,510	74,671	881,462
Zinc.....do....	4,507	1,207,973	5,192	1,059,186
Miscellaneous e.....	.....	28,406,455	.....	33,468,130
Total value, eliminating duplications.....	.....	45,619,119	.....	52,128,552

a Value included under "Miscellaneous."
b Value not included in total value for State.
c Data not available.
d Exclusive of fancy brick, value for which is included under "Miscellaneous."
e 1916: Aluminum, diatomaceous earth, ferroalloys, gems and precious stones, artificial graphite, crystalline graphite, calcareous marl, mica, peat, potash, pyrite, fancy brick (sand-lime), and silica (quartz). 1917: Aluminum, diatomaceous earth, iron ore sold for paint, calcareous marl, pyrite, and silica (quartz).

Digitized by Google

Mineral production of North Carolina in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Aluminum.....pounds..	(a b)	(a b)	(a b)	(a b)
Barytes.....short tons..	878	$3,246	1,019	$5,080
Chromic iron ore.....long tons..			(a)	(a)
Clay products.....		1,551,436		1,662,307
Clay, raw.....short tons..	17,562	b 151,823	17,426	b 182,176
Copper.....pounds..	9,800	2,411	124,991	34,123
Corundum.....short tons..			820	67,461
Feldspar.....do....	34,670	77,446	47,559	131,442
Garnet, abrasive.....do....	(a)	(a)	(a)	(a)
Gems and precious stones.....		343		(a)
Gold.....fine ounces (troy)..	1,269	26,237	590	12,187
Graphite, amorphous.....short tons..	(a)	(a)		
Iron ore.....long tons..	64,306	(a)	90,957	445,898
Lead.....short tons..			1	222
Lime.....do....	(a)	(a)	(a)	(a)
Manganese ore.....long tons..			102	(a)
Marl (calcareous).....short tons..	7,500	12,000	11,728	29,261
Mica.....		422,580		577,341
Millstones.....		(a)		(a)
Mineral waters.....gallons sold..	137,817	19,010	103,659	15,664
Monazite sand.....pounds..	(a)	(a)	(a)	(a)
Sand and gravel.....short tons..	554,381	150,209	543,364	231,813
Silica (quartz).....do....	(a)	(a)	(a)	(a)
Silver.....fine ounces (troy)..	663	436	1,110	915
Stone.....		1,975,876		1,896,554
Talc.....short tons..	1,787	41,824	2,175	41,766
Tin (metallic equivalent).....do....	(a)	(a)		
Miscellaneous c.....		854,897		4,223,737
Total value, eliminating duplications.....		4,595,551		5,246,391

a Value included under "Miscellaneous."
b Value not included in total value for State.
c 1916: Aluminum, abrasive garnet, amorphous graphite, iron ore, lime, millstones, monazite sand, silica (quartz), and tin; 1917: Aluminum, chromic iron ore, abrasive garnet, gems and precious stones, lime, manganese ore, millstones, monazite sand, and silica (quartz).

Mineral production of North Dakota in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Briquets, fuel.....short tons..			(a b)	(a b)
Clay products.....		$264,457		$294,016
Clay, raw.....short tons..	(a b)	(a b)	(a b)	(a b)
Coal.....do....	634,912	946,082	790,548	1,425,750
Mineral waters.....gallons sold..	766,000	14,500	556,000	12,837
Natural gas.....		(a)		(a)
Sand and gravel.....short tons..	(a)	(a)	5,750	4,425
Sand-lime brick.....		(a)		(a)
Miscellaneous c.....		59,283		22,527
Total value, eliminating duplications.....		1,283,809		1,749,549

a Value included under "Miscellaneous."
b Value not included in total value for State.
c 1916: Raw clay, natural gas, sand and gravel, and sand-lime brick; 1917: Fuel briquets, raw clay, natural gas, and sand-lime brick.

Digitized by Google

Mineral production of Ohio in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Bromine.....pounds..	78,773	$87,361	(a)	(a)
Calcium chloride.....short tons..	(a)	(a)	(a)	(a)
Cement.....barrels..	b 2,142,931	b 2,517,949	1,565,394	$2,328,432
Clay products.....	.....	44,947,877	.....	52,466,716
Clay, raw.....short tons..	324,722	c 309,369	396,796	c 568,687
Coal.....do....	34,728,219	46,150,907	40,748,734	100,897,148
Coke.....do....	1,803,268	c 6,894,619	3,694,302	c 23,473,764
Ferroalloys.....long tons..	91,032	c 2,179,338	79,951	c 3,754,745
Grindstones and pulpstones.....	.....	637,919	.....	894,380
Gypsum.....short tons..	286,678	927,859	270,538	1,304,497
Iron ore.....long tons..	1,800	(a)	.....	.....
Iron, pig.....do....	8,689,030	c 136,855,228	8,469,052	c 231,165,093
Lime.....short tons..	570,972	2,702,953	479,856	2,975,466
Mineral waters.....gallons sold..	4,102,922	161,160	3,113,093	136,710
Natural gas.....	.....	15,601,144	.....	18,434,814
Natural-gas gasoline.....gallons..	2,638,571	470,804	5,439,560	1,051,376
Oilstones and scythestones.....	.....	(a)	.....	(a)
Petroleum.....barrels..	7,744,511	16,154,940	7,750,540	21,104,483
Potash (K_2O).....short tons..	(a)	(a)	25	14,077
Pyrite.....long tons..	13,551	36,114	13,218	29,557
Salt.....short tons..	938,867	2,038,749	1,026,803	2,839,575
Sand and gravel.....do....	8,359,250	3,559,952	6,192,602	4,375,549
Sand and sandstone (finely ground).....do....	(a)	(a)	(a)	(a)
Sand-lime brick.....	.....	(a)	.....	(a)
Stone.....	.....	6,611,266	.....	6,486,605
Sulphuric acid d.....short tons..	(a)	(a)	196,079	2,501,029
Miscellaneous e.....	.....	2,481,531	.....	341,005
Total value, eliminating duplications.....	.....	145,088,485	.....	218,181,419

a Value included under "Miscellaneous."
b Exclusive of natural cement, value for which is included under "Miscellaneous."
c Value not included in total value for State.
d From zinc smelting.
e 1916: Calcium chloride, natural cement, iron ore, oilstones and scythestones, potash, sand and sandstone (finely ground), sand-lime brick, and sulphuric acid from zinc smelting; 1917: Bromine, calcium chloride, oilstones and scythestones, sand and sandstone (finely ground), and sand-lime brick.

Digitized by Google

Mineral production of Oklahoma in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Asphalt:				
Natural.....short tons..	15,431	$112,555	5,793	$34,344
Oil.....do....	(a)	(a)	(a)	(a)
Cement.....barrels..	1,712,116	2,188,325	1,736,761	2,633,479
Clay products.....	.....	1,410,657	.....	1,857,546
Coal.....short tons..	3,608,011	7,525,427	4,386,844	12,335,413
Gems and precious stones.....	.....	(a)	.....	.....
Gypsum.....short tons..	161,661	429,350	158,017	562,767
Lead.....do....	12,115	1,671,870	26,358	4,533,576
Lime.....do....	(a)	(a)	(a)	(a)
Mineral paints (zinc and lead pigments)..do...	(a b)	(a b)	(a b)	(a b)
Mineral waters.....gallons sold..	1,353,513	40,189	852,381	26,997
Natural gas.....	.....	12,014,706	.....	13,984,656
Natural-gas gasoline.....gallons..	48,359,602	5,895,145	115,123,424	21,541,905
Petroleum.....barrels..	107,071,715	128,463,805	107,507,471	181,646,981
Salt.....short tons..	(a)	(a)	(a)	(a)
Sand and gravel.....do....	574,844	196,206	463,233	244,432
Silver.....fine ounces (troy)..	606	399	.....	.....
Stone.....	.....	621,056	.....	625,048
Tripoli.....	.....	(c)	.....	(c)
Zinc.....short tons..	28,754	7,706,272	85,835	17,510,340
Miscellaneous d.....	.....	1,380,722	.....	1,721,273
Total value, eliminating duplications....	.....	169,556,331	.....	259,134,377

a Value included under "Miscellaneous."
b Value not included in total value for State.
c Included in Missouri figures. Not separable.
d 1916: Oil asphalt, gems and precious stones, lime, zinc and lead pigments, and salt; 1917: Oil asphalt, lime, zinc and lead pigments, and salt.

Mineral production of Oregon in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Antimony ore.....short tons..	344	$2,772	.....	.....
Briquets, fuel.....do....	(a b)	(a b)	(a b)	(a b)
Cement.....barrels..	(a)	(a)	(a)	(a)
Chromic iron ore.....long tons..	3,099	37,806	6,701	$164,032
Clay products.....	.....	c 299,993	.....	c 331,546
Clay, raw.....short tons..	(a b)	(a b)	(a b)	(a b)
Coal.....do....	42,592	113,976	28,327	95,663
Copper.....pounds..	3,581,886	881,144	2,474,487	675,535
Gems and precious stones.....	.....	4,492	.....	3,355
Gold.....fine ounces (troy)..	92,018	1,902,179	72,166	1,491,798
Gypsum.....short tons..	(a)	(a)	(a)	(a)
Lead.....do....	14	1,932	.....	.....
Lime.....do....	4,225	35,289	4,498	40,065
Mineral waters.....gallons sold..	30,920	7,961	13,741	2,842
Platinum and allied metals..fine ounces (troy)..	20	1,780	89	9,208
Quicksilver.....flasks..	303	38,145	388	40,864
Sand and gravel.....short tons..	904,078	283,493	698,351	242,529
Silver.....fine ounces (troy)..	231,342	152,223	125,656	103,541
Stone.....	.....	443,524	.....	413,867
Tungsten ore (60% concentrates)...short tons..	.....	.....	.....	71
Miscellaneous d.....	.....	377,399	.....	533,862
Total value, eliminating duplications....	.....	4,498,632	.....	4,074,247

a Value included under "Miscellaneous."
b Value not included in total value for State.
c Exclusive of pottery, value for which is included under "Miscellaneous."
d 1916 and 1917: Fuel briquets, cement, pottery, raw clay, and gypsum.

Digitized by Google

Mineral production of Pennsylvania in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Briquets, fuel.....short tons..	19,038	[a] $73,000	84,394	[a] $265,979
Bromine.....pounds..			[b]	[b]
Calcium chloride.....short tons..			[b]	[b]
Cement.....barrels..	[c] 28,748,546	[c] 27,915,298	[c] 27,709,442	[c] 34,512,388
Clay products.....		32,110,660		49,162,650
Clay, raw.....short tons..	577,147	[a] 1,098,129	511,405	[a] 1,365,870
Coal:				
Anthracite.....do....	87,578,493	202,009,561	99,611,811	283,650,723
Bituminous.....do....	170,295,424	221,685,175	172,448,142	421,268,808
Coke.....do....	31,279,695	[a] 84,710,305	27,912,025	[a] 135,698,040
Copper.....pounds..	625,000	153,750	459,200	125,362
Feldspar.....short tons..	7,342	56,323	10,013	91,206
Ferroalloys.....long tons..	346,370	[a] 34,494,480	356,462	[a] 53,980,132
Gems and precious stones.....		165		[b]
Graphite, crystalline.....pounds..	1,095,716	103,377	804,945	77,475
Iron ore:				
Sold to furnaces.....long tons..	558,556	702,633	548,674	873,320
Sold for paint.....do....			[b]	[b]
Iron, pig.....do....	16,351,131	[a] 293,437,782	15,423,262	[a] 460,677,474
Lime.....short tons..	972,343	3,857,553	936,209	5,900,056
Magnesium.....pounds..	[a b]	[a b]		
Manganiferous ore.....long tons..	451	[b]		
Marl, calcareous.....short tons..	[b]	[b]	[b]	[b]
Mica.....		[b]		
Millstones.....		[b]		[b]
Mineral paints (zinc and lead pigments), ...short tons..	[a b]	[a b]	[a b]	[a b]
Mineral waters.....gallons sold..	1,671,637	145,133	1,603,090	147,021
Natural gas.....		24,513,119		28,716,492
Natural-gas gasoline.....gallons..	9,714,926	1,726,173	13,826,250	2,778,098
Oilstones.....		[b]		
Peat.....short tons..	[b]	[b]	[b]	[b]
Petroleum.....barrels..	7,592,394	19,149,855	7,733,200	25,154,290
Potash (K_2O).....short tons..	[b]	[b]	280	91,505
Pyrite.....long tons..	[b]	[b]	[b]	[b]
Salt.....short tons..			[b]	[b]
Sand and gravel.....do....	7,442,452	4,023,692	6,354,635	5,283,000
Sand and sandstone (finely ground).....do....	[b]	[b]	[b]	[b]
Sand-lime brick.....		94,328		83,123
Silica (quartz).....short tons..	[b]	[b]	113,346	80,699
Slate.....		3,124,743		3,306,704
Stone.....		11,021,655		14,048,158
Sulphuric acid [d].....short tons..	[b]	[b]	274,932	4,407,588
Talc.....do....	[b]	[b]	[b]	[b]
Tripoli.....		[b]		[b]
Miscellaneous [e].....		21,852,877		22,856,328
Total value, eliminating duplications.....		554,501,375		880,220,510

[a] Value not included in total value for State.
[b] Value included under "Miscellaneous."
[c] Exclusive of natural cement, value for which is included under "Miscellaneous."
[d] From zinc smelting.
[e] 1916: Natural cement, magnesium, manganiferous ore, calcareous marl, mica, millstones, zinc and lead pigments, oilstones, peat, potash, pyrite, sand and sandstone (finely ground), silica (quartz), sulphuric acid from zinc smelting, talc, and tripoli; 1917: Bromine, calcium chloride, natural cement, gems and precious stones, iron ore sold for paint, calcareous marl, millstones, zinc and lead pigments, peat, pyrite, salt, sand and sandstone (finely ground), talc, and tripoli.

Digitized by Google

Mineral production of Rhode Island in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Clay products		(a)		(a)
Graphite, amorphous.....short tons	(a)	(a)	(a)	(a)
Lime.....do	(a)	(a)	(a)	(a)
Mineral waters.....gallons sold	449,453	$33,050	368,976	$24,975
Sand and gravel.....short tons	(a)	(a)	(a)	(a)
Soapstone.....do	(a)	(a)		
Stone		632,452		518,785
Miscellaneous[b]		123,706		173,363
Total value, eliminating duplications		789,208		717,123

[a] Value included under "Miscellaneous."
[b] 1916: Clay products, amorphous graphite, lime, sand and gravel, and soapstone; 1917: Clay products, amorphous graphite, lime, and sand and gravel.

Mineral production of South Carolina in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Barytes.....short tons	(a)	(a)	(a)	(a)
Clay products		$607,151		$662,801
Clay, raw.....short tons	32,881	[b] 170,070	40,448	[b] 173,706
Gems and precious stones				(a)
Gold.....fine ounces (troy)	15	320	52	1,083
Manganese ore.....long tons			405	(a)
Manganiferous ore.....do			650	(a)
Marl, calcareous.....short tons	(a)	(a)	(a)	(a)
Mica		(a)		
Mineral waters.....gallons sold	427,905	63,818	289,094	45,729
Phosphate rock.....long tons	53,047	211,125	33,485	138,482
Pyrite.....do	(a)	(a)		
Sand and gravel.....short tons	54,018	21,211	98,068	42,162
Silver.....fine ounces (troy)	28	18	3	2
Stone		447,940		427,531
Miscellaneous[c]		40,490		75,507
Total value, eliminating duplications		1,392,073		1,393,297

[a] Value included under "Miscellaneous."
[b] Value not included in total value for State.
[c] 1916: Barytes, calcareous marl, mica, and pyrite; 1917: Barytes, gems and precious stones, manganese and manganiferous ores, and calcareous marl.

Digitized by Google

Mineral production of South Dakota in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Clay products		$115,474		$47,213
Clay, raw short tons			(a b)	(a b)
Coal do	8,886	18,021	8,042	23,346
Copper pounds			10,707	2,923
Gold fine ounces (troy)	360,909	7,460,644	356,245	7,364,233
Gypsum short tons	(a)	(a)	(a)	(a)
Lead do	18	2,443	34	5,855
Lime do	5,772	44,033	4,463	37,589
Lithium minerals do	548	10,970	(c)	(a)
Mica		59,770		11,006
Mineral waters gallons sold	470,725	20,512	443,167	13,545
Natural gas		(a)		(a)
Pyrite long tons	145	966	(a)	(a)
Sand and gravel short tons	1,095,594	133,755	194,520	49,654
Sand-lime brick		32,139		(a)
Silver fine ounces (troy)	215,205	141,605	186,765	153,894
Stone		205,497		182,907
Tin short tons			10	12,300
Tungsten ore (60 per cent concentrates) do	239	404,775	270	299,644
Miscellaneous c		46,076		147,062
Total value, eliminating duplications		8,696,680		8,348,684

a Value included under "Miscellaneous."
b Value not included in total value for State.
c 1916: Gypsum and natural gas; 1917: Raw clay, gypsum, lithium minerals, natural gas, pyrite, and sand-lime brick.

Mineral production of Tennessee in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Aluminum pounds	(a b)	(a b)	(a b)	(a b)
Barytes short tons	32,416	$123,986	16,972	$79,058
Bauxite long tons	(a)	(a)	(a)	(a)
Cement barrels	(a)	(a)	(a)	(a)
Clay products		1,963,957		1,969,226
Clay, raw short tons	101,617	b 209,951	106,535	b 280,126
Coal do	6,137,449	7,522,445	6,194,221	13,592,998
Coke do	382,175	b 1,062,065	411,326	b 2,081,272
Copper pounds	14,679,794	3,611,229	16,083,749	4,377,213
Ferroalloys long tons	12,966	(a b)	30,987	b 1,445,132
Flint lining for tube mills short tons			(a)	(a)
Gold fine ounces (troy)	278	5,739	258	5,326
Iron ore long tons	467,741	736,397	520,460	1,235,718
Iron, pig do	329,342	b 4,981,538	346,638	b 9,102,441
Lead short tons	16	2,274	2,531	435,326
Lime do	109,533	378,017	101,836	504,599
Manganese ore long tons	429	8,380	1,996	75,066
Manganiferous ore do			83	(a)
Mineral waters gallons sold	799,346	48,416	758,193	47,362
Natural gas		1,150		2,450
Petroleum barrels	677	1,317	12,196	28,448
Phosphate rock long tons	409,803	1,500,418	506,679	2,101,040
Potash (K_2O) short tons			6	5,000
Pyrite long tons	(a)	(a)	(a)	(a)
Sand and gravel short tons	1,092,270	414,225	885,957	489,577
Sand and sandstone (finely ground) do			(a)	(a)
Silica (quartz) do	(a)	(a)		
Silver fine ounces (troy)	94,701	62,313	99,063	81,619
Slate				(a)
Stone		1,753,180		1,635,573
Sulphuric acid (60° Baumé) c short tons	(a)	(a)	(a)	(a)
Zinc do	26,428	7,062,634	28,498	5,813,501
Miscellaneous d		9,898,286		13,148,928
Total value, eliminating duplications		28,277,365		36,910,448

a Value included under "Miscellaneous."
b Value not included in total value for State.
c From copper smelting.
d 1916: Aluminum, bauxite, cement, ferroalloys, pyrite, silica (quartz), and sulphuric acid from copper smelting; 1917: Aluminum, bauxite, cement, flint lining for tube mills, manganiferous ore, pyrite, sand and sandstone (finely ground), slate, and sulphuric acid from copper smelting.

Digitized by Google

Mineral production of Texas in 1916 and 1917.

Product.		1916		1917	
		Quantity.	Value.	Quantity.	Value.
Asphalt:					
Natural	short tons	(a)	(a)	(a)	(a)
Oil	do	127,259	$1,621,920	160,739	$2,292,036
Cement	barrels	2,327,559	3,177,104	2,358,944	3,661,328
Clay products			2,837,960		3,451,806
Clay, raw	short tons	2,936	b 10,531	4,446	b 22,477
Coal	do	1,987,503	3,092,663	2,355,815	4,177,608
Copper	pounds	99,569	24,494	23,132	6,315
Fuller's earth	short tons	(a)	(a)	(a)	(a)
Gems and precious stones			908		(a)
Gold	fine ounces (troy)	20	414	1	22
Graphite, crystalline	pounds	(a)	(a)	(a)	(a)
Gypsum	short tons	197,785	653,288	257,328	906,262
Lead	do	25	3,445	1	214
Lime	do	54,049	307,759	52,742	361,306
Manganese ore	long tons	(a)	(a)	25	(a)
Manganiferous ore	do			135	(a)
Mineral waters	gallons sold	708,002	97,513	541,178	72,175
Natural gas			3,143,871		3,192,625
Natural-gas gasoline	gallons	1,292,811	201,023	6,920,405	1,149,441
Petroleum	barrels	27,644,605	25,760,335	32,413,287	42,891,555
Quicksilver	flasks	6,306	793,862	10,791	1,136,508
Salt	short tons	75,762	427,119	85,181	564,039
Sand and gravel	do	2,617,409	957,794	1,580,939	716,457
Sand-lime brick			45,002		65,102
Silver	fine ounces (troy)	653,455	429,973	595,789	490,930
Stone			698,449		607,540
Strontium ore	short tons			(a)	(a)
Sulphur	long tons	(a)	(a)	(a)	(a)
Zinc	short tons	116	31,140	11	2,313
Miscellaneous c			3,395,445		11,626,795
Total value, eliminating duplications			47,711,571		77,552,369

a Value included under "Miscellaneous."
b Value not included in total value for State.
c 1916: Natural asphalt, fuller's earth, crystalline graphite, manganese ore, and sulphur; 1917: Natural asphalt, fuller's earth, gems and precious stones, crystalline graphite, manganese and manganiferous ores, strontium ore, and sulphur.

Digitized by Google

Mineral production of Utah in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Antimony ore.....short tons..	73	$590	25	$3,125
Asphalt.....do....	26,874	633,440	35,192	569,235
Cement.....barrels..	802,596	1,467,564	899,599	1,461,686
Clay products.....	.....	[a] 885,357	.....	952,882
Clay, raw.....short tons..	(b c)	(b c)	4,079	c8,265
Coal.....do....	3,567,428	5,795,944	4,125,230	8,531,382
Coke.....do....	(b c)	(b c)	(b c)	(b c)
Copper.....pounds..	240,275,222	59,107,705	246,674,153	67,842,044
Diatomaceous earth.....	.....	.....	.....	(b)
Gems and precious stones.....	.....	3,265	.....	(b)
Gold.....fine ounces (troy)..	172,938	3,574,947	162,306	3,355,158
Gypsum.....short tons..	27,727	83,994	(b)	(b)
Iron ore.....long tons..	45,514	(b)	43,058	(b)
Lead.....short tons..	100,745	13,902,815	89,261	15,352,885
Lime.....do....	12,472	77,133	9,130	63,574
Manganese ore.....long tons..	1,282	22,597	4,195	118,927
Manganiferous ore.....do....	(b)	(b)	136	(b)
Mineral waters.....gallons sold..	(b)	(b)	.....	.....
Molybdenum.....pounds..	824	800	(b)	(b)
Phosphate rock.....long tons..	(b)	(b)	(b)	(b)
Potash (K_2O).....short tons..	(b)	(b)	3,144	1,234,719
Salt.....do....	60,653	289,457	79,195	352,145
Sand and gravel.....do....	185,569	24,048	307,596	82,707
Silver.....fine ounces (troy)..	13,253,037	8,720,498	13,479,133	11,106,806
Slate.....	.....	(b)	.....	(b)
Stone.....	.....	368,705	.....	305,968
Sulphuric acid[d].....short tons..	.....	.....	(b)	(b)
Tungsten ore (60% concentrates).....do....	20	29,766	33	36,065
Uranium and vanadium ores.....do....	.....	10,000	.....	29,173
Zinc.....do....	14,786	3,962,719	10,643	2,171,261
Miscellaneous[e].....	.....	2,551,809	.....	2,411,359
Total value, eliminating duplications.....	.....	99,734,209	.....	113,589,282

[a] Exclusive of pottery, value for which is included under "Miscellaneous."
[b] Value included under "Miscellaneous."
[c] Value not included in total value for State.
[d] From copper smelting.
[e] 1916: Pottery, raw clay, coke, iron ore, manganiferous ore, mineral waters, phosphate rock, potash, and slate; 1917: Coke, diatomaceous earth, gems and precious stones, gypsum, iron ore, manganiferous ore, molybdenum, phosphate rock, slate, and sulphuric acid from copper smelting.

Digitized by Google

Mineral production of Vermont in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Clay products		394,779		393,344
Clay, raw, short tons	5,397	[a] 40,684	2,766	[a] 27,032
Copper, pounds	273,430	67,264	153,900	42,014
Feldspar, short tons	(b)	(b)		
Gold, fine ounces (troy)			3	71
Lime, short tons	43,365	236,123	46,109	364,071
Mineral waters, gallons sold	72,590	15,395	94,500	17,705
Sand and gravel, short tons	68,892	34,481	51,827	40,624
Scythestones		(b)		(b)
Silver, fine ounces (troy)	2,501	1,646	497	410
Slate		1,607,901		1,868,307
Stone		5,729,676		5,920,709
Talc and soapstone, short tons	73,215	501,175	93,960	625,150
Miscellaneous		8,654		13,078
Total value, eliminating duplications		8,297,104		8,980,573

[a] Value not included in total value for State. [b] Value included under "Miscellaneous."

Mineral production of Virginia in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Asbestos, short tons	(a)	(a)	(a)	(a)
Barytes, do	(a)	(a)	(a)	(a)
Briquets, fuel, do	(a b)	(a b)	(a b)	(a b)
Cement, barrels	(a)	(a)	(a)	(a)
Clay products		[c]$1,676,723		$1,658,042
Clay, raw, short tons	(a b)	(a b)	3,724	[b] 6,263
Coal, do	9,707,474	10,261,424	10,087,091	20,125,713
Coke, do	1,242,332	[b] 3,024,913	1,304,220	[b] 5,785,934
Copper, pounds	553,800	136,235	36,630	10,000
Emery, short tons			(a)	(a)
Feldspar, do	(a)	(a)		
Ferroalloys, long tons			7,217	[b] 1,759,170
Gems and precious stones		565		2,677
Gold, fine ounces (troy)	43	885	65	1,343
Gypsum, short tons	(a)	(a)	(a)	(a)
Iron ore, long tons	486,798	1,000,118	472,337	1,182,449
Iron, pig, do	444,491	[b] 7,140,002	562,299	[b] 15,708,295
Lead, short tons	728	100,453	859	147,794
Lime, do	326,812	1,279,658	307,195	1,820,446
Manganese ore, long tons	4,417	113,342	12,360	588,806
Manganiferous ore, do	37,700	104,794	34,396	185,968
Marl, calcareous, short tons	30,243	51,675	27,800	52,850
Mica		20,954		25,540
Millstones		25,752		18,980
Mineral waters, gallons sold	2,313,616	248,906	2,518,050	237,788
Peat, short tons			(a)	(a)
Pyrite, long tons	148,502	925,243	170,382	1,378,043
Salt, short tons	(a)	(a)	(a)	(a)
Sand and gravel, do	641,595	226,373	1,126,527	532,310
Sand and sandstone (finely ground), do			(a)	(a)
Silica (quartz), do	(a)	(a)		
Silver, fine ounces (troy)	783	515	4,518	3,723
Slate		165,483		135,380
Stone		1,580,161		1,612,118
Talc and soapstone, short tons	28,355	564,228	26,667	489,062
Titanium minerals:				
Ilmenite, do	95	1,900	259	6,576
Rutile, do	110	16,500	206	32,960
Zinc, do	2,276	609,866	1,703	347,352
Miscellaneous [d]		1,474,780		1,725,817
Total value, eliminating duplications		20,560,956		32,243,648

[a] Value included under "Miscellaneous."
[b] Value not included in total value for State.
[c] Exclusive of pottery, value for which is included under "Miscellaneous."
[d] 1916: Asbestos, barytes, fuel briquets, cement, pottery, raw clay, feldspar, gypsum, salt, and silica (quartz); 1917: Asbestos, barytes, fuel briquets, cement, emery, gypsum, peat, salt, and sand and sandstone (finely ground).

Digitized by Google

Mineral production of Washington in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Antimony ore.....short tons..	400	$3,355	.....	.....
Briquets, fuel.....do....	(a b)	(a b)	(a b)	(a b)
Cement.....barrels..	1,575,919	2,447,779	1,408,191	$2,267,045
Chromic iron ore.....long tons..	.....	.....	(a)	(a)
Clay products.....	.....	c 1,589,574	.....	1,533,039
Clay, raw.....short tons..	1,840	b 6,251	1,613	b 9,248
Coal.....do....	3,038,588	6,907,428	4,009,902	10,727,362
Coke.....do....	(a b)	(a b)	(a b)	(a b)
Copper.....pounds..	2,645,022	630,675	2,199,518	600,468
Diatomaceous earth.....	.....	10,700	.....	18,910
Ferroalloys.....long tons..	.....	.....	(a b)	(a b)
Gems and precious stones.....	.....	850	.....	(a)
Gold.....fine ounces (troy)..	27,944	577,655	23,816	492,324
Iron, pig.....long tons..	.....	.....	2,361	(a b)
Lead.....short tons..	2,700	372,550	4,895	841,913
Lime.....do....	26,895	166,653	23,328	156,553
Magnesite.....do....	715	5,362	105,175	783,188
Manganese ore.....long tons..	(a)	(a)	.....	.....
Manganiferous ore.....do....	(a)	(a)	.....	.....
Mineral waters.....gallons sold..	151,528	9,476	155,265	7,265
Molybdenum.....pounds..	.....	.....	(a)	(a)
Platinum and allied metals.fine ounces (troy)..	.....	.....	(a)	(a)
Potash (K_2O).....short tons..	(a)	(a)	.....	.....
Quicksilver.....flasks..	75	9,442	.....	.....
Sand and gravel.....short tons..	1,401,237	337,337	895,120	199,565
Sand-lime brick.....	.....	(a)	.....	(a)
Silica (quartz).....short tons..	(a)	(a)	.....	.....
Silver.....fine ounces (troy)..	335,121	220,510	282,320	232,632
Stone.....	.....	903,635	.....	454,594
Strontium ore.....short tons..	(a)	(a)	(a)	(a)
Tungsten ore (60 per cent concentrates)..do....	11	15,230	10	13,500
Zinc.....do....	847	228,960	598	121,945
Miscellaneous d.....	.....	1,037,350	.....	1,809,700
Total value, eliminating duplications.....	.....	14,521,014	.....	18,576,052

a Value included under "Miscellaneous."
b Value not included in total value for State.
c Exclusive of pottery, value for which is included under "Miscellaneous."
d 1916: Fuel briquets, pottery, coke, manganese and manganiferous ores, potash, sand-lime brick, silica (quartz), and strontium ore; 1917: Fuel briquets, chromic iron ore, coke, ferroalloys, gems and precious stones, pig iron, molybdenum, platinum and allied metals, sand-lime brick, and strontium ore.

Digitized by Google

Mineral production of West Virginia in 1916 and 1917.

Product.		1916		1917	
		Quantity.	Value.	Quantity.	Value.
Bromine	pounds	136,544	$179,126	74,947	$42,431
Calcium chloride	short tons	5,924	42,263	3,691	63,644
Cement	barrels	(a)	(a)	(a)	(a)
Clay products			7,634,321		9,608,065
Clay, raw	short tons	122,944	[b] 126,283	127,024	[b] 189,672
Coal	do	86,460,127	102,366,092	86,441,667	200,659,368
Coke	do	2,521,309	[b] 6,567,505	3,349,761	[b] 16,715,083
Grindstones and pulpstones			(a)		162,310
Iron ore	long tons	3,605	(a)	4,632	(a)
Iron, pig	do	348,743	(a b)	355,956	(a b)
Lime	short tons	277,721	1,008,021	245,569	1,268,343
Marl, calcareous	do			(a)	(a)
Mineral waters	gallons sold	287,466	46,686	156,267	37,529
Natural gas			47,603,396		57,389,161
Natural-gas gasoline	gallons	18,765,056	3,025,293	32,668,647	6,511,813
Petroleum	barrels	8,731,184	21,914,080	8,379,285	27,246,960
Salt	short tons	33,389	122,669	24,844	191,044
Sand and gravel	do	1,054,878	777,952	877,679	966,763
Sand and sandstone (finely ground)	do	(a)	(a)	(a)	(a)
Stone			1,500,809		1,841,071
Sulphuric acid [c]	short tons			(a)	(a)
Miscellaneous [d]			6,470,753		10,141,380
Total value, eliminating duplications			187,043,011		306,916,191

[a] Value included under "Miscellaneous."
[b] Value not included in total value for State.
[c] From zinc smelting.
[d] 1916: Cement, grindstones and pulpstones, iron ore, pig iron, and sand and sandstone (finely ground); 1917: Cement, iron ore, pig iron, calcareous marl, sand and sandstone (finely ground), and sulphuric acid from zinc smelting.

Mineral production of Wisconsin in 1916 and 1917.

Product.		1916		1917	
		Quantity.	Value.	Quantity.	Value.
Briquets, fuel	short tons	(a b)	(a b)	(a b)	(a b)
Clay products			[c] $905,910		$1,122,121
Clay, raw	short tons	(a b)	(a b)	(a b)	(a b)
Coke	do	(a b)	(a b)	(a b)	(a b)
Iron ore:					
Sold to furnaces	long tons	1,529,459	3,644,542	1,179,709	3,913,437
Sold for paint	do	1,599	(a)	982	(a)
Iron, pig	do	423,973	[b] 7,534,327	402,732	[b] 11,082,274
Lead	short tons	3,043	419,934	4,139	711,908
Lime	do	266,805	1,207,059	169,650	1,037,578
Manganiferous ore	long tons	3,982	6,570		
Mineral paints (zinc and lead pigments)	short tons	(a b)	(a b)	(a b)	(a b)
Mineral waters	gallons sold	7,696,813	1,507,679	6,296,634	1,362,498
Potash (K_2O)	short tons	125	67,625	277	259,928
Pyrite	long tons	(a)	(a)	(a)	(a)
Sand and gravel	short tons	3,544,766	894,202	3,609,869	1,080,860
Sand-lime brick			(a)		(a)
Silica (quartz)	short tons	(a)	(a)	(a)	(a)
Stone			2,757,790		2,787,023
Sulphuric acid [d]	short tons	(a)	(a)	(a)	(a)
Zinc	do	56,803	15,223,204	59,742	12,187,368
Miscellaneous [e]			5,251,992		9,017,291
Total value, eliminating duplications			27,082,175		24,976,780

[a] Value included under "Miscellaneous."
[b] Value not included in total value for State.
[c] Exclusive of pottery, value for which is included under "Miscellaneous."
[d] From zinc smelting.
[e] 1916: Fuel briquets, pottery, raw clay, coke, iron ore sold for paint, manganiferous ore, zinc and lead pigments, pyrite, sand-lime brick, silica (quartz), and sulphuric acid from zinc smelting; 1917: Fuel briquets, raw clay, coke, iron ore sold for paint, zinc and lead pigments, pyrite, sand-lime brick, silica (quartz), and sulphuric acid from zinc smelting.

Digitized by Google

Mineral production of Wyoming in 1916 and 1917.

Product.	1916		1917	
	Quantity.	Value.	Quantity.	Value.
Asbestos.....short tons..	.....	.....	(a)	(a)
Chromic iron ore.....long tons..	(a)	(a)	.....	.....
Clay products.....	.....	$90,199	.....	$106,833
Clay, raw.....short tons..	(a b)	(a b)	(a b)	(a b)
Coal.....do....	7,910,647	12,239,707	8,575,619	16,503,283
Copper.....pounds..	2,610,622	642,213	2,027,857	553,605
Gems and precious stones.....	.....	(a)	.....	(a)
Gold.....fine ounces (troy)..	995	20,566	182	3,762
Gypsum.....short tons..	46,964	141,408	55,844	197,867
Iron ore.....long tons..	545,774	(a)	543,846	(a)
Lime.....short tons..	(a)	(a)	(a)	(a)
Manganese ore.....long tons..	.....	.....	30	(a)
Mineral waters.....gallons sold..	53,891	7,269	53,726	7,880
Natural gas.....	.....	(a)	.....	(a)
Petroleum.....barrels..	6,234,137	5,644,080	8,978,680	11,047,876
Phosphate rock.....long tons..	(a)	(a)	(a)	(a)
Platinum and allied metals..fine ounces (troy)..	(a)	(a)	(a)	(a)
Sand and gravel.....short tons..	769,739	86,972	(a)	(a)
Silver.....fine ounces (troy)..	5,524	3,635	3,415	2,814
Sodium salts from natural sources..short tons..	(a)	(a)	(a)	(a)
Stone.....	.....	64,509	.....	156,180
Sulphur.....long tons..	(a)	(a)	(a)	(a)
Miscellaneous c.....	.....	744,694	.....	899,105
Total value, eliminating duplications.....	.....	19,683,292	.....	29,567,250

a Value included under "Miscellaneous."
b Value not included in total value for State.
c 1916: Chromic iron ore, raw clay, gems and precious stones, iron ore, lime, natural gas, phosphate rock, platinum and allied metals, sodium salts from natural sources, and sulphur; 1917: Asbestos, raw clay, gems and precious stones, iron ore, lime, manganese ore, natural gas, phosphate rock, platinum and allied metals, sand and gravel, sodium salts from natural sources, and sulphur.

Digitized by Google

PREFATORY NOTE TO THE REPORTS ON GOLD, SILVER, COPPER, LEAD, AND ZINC.

By H. D. McCaskey.

In the mining industry five metals are closely related in both the genesis and the geologic occurrence of their ores. They also hold together in mining and in metallurgical treatment. They are gold, silver, copper, lead, and zinc. Of their ores some contain all five metals, many contain three or four, and few contain only one. Gold and silver, for instance, on the one hand, and lead and zinc, on the other, almost always stand in close genetic relations, and the ores of each two are usually mined together. Copper ores almost invariably produce some silver and gold as well as copper, and lead ores, with certain exceptions, produce notable supplies of silver. Zinc ores in the Western States contribute also to the production of silver. In the same mine sometimes, and in the same mining district frequently, all five metals occur in commercial quantity.

This situation is recognized by the United States Geological Survey in its publication of the annual reports on the mineral resources of the country. Hence the general treatment of each of the five metals in the general reports and the grouping together of the related metals in the various mines reports descriptive of individual or geographically grouped States.

To facilitate advance publication, the complete report upon these five metals is therefore divided into 16 sections, each of which is published separately. The first four sections give figures of output for the calendar year in marketable form for the metals named as obtained from the smelters, refineries, and mints, and general reviews of the respective industries for the entire country. The last 12 sections give the production (called "mine production") as obtained from the mines so far as possible in terms of recoverable metal in ores and other material sold or treated during the calendar year and supply information in detail relative to the mining industry in the respective States, counties, and mining districts. The figures given in the general reports are the final official statistics of production for the country and of the States. The general report on gold and silver includes the statistics of recovered precious metals as determined jointly by the Bureau of the Mint and the United States Geological Survey.

Digitized by Google

The 16 sections, which appear as separate chapters in this volume, are as follows:

Gold and silver (general report).
Copper (general report).
Lead (general report).
Zinc (general report).
Gold, silver, copper, lead, and zinc in the Eastern States (mines report).
Silver, copper, lead, and zinc in the Central States (mines report).
Gold, silver, copper, and lead in Alaska (mines report).
Gold, silver, copper, lead, and zinc in Arizona (mines report).
Gold, silver, copper, lead, and zinc in California and Oregon (mines report).
Gold, silver, copper, lead, and zinc in Colorado (mines report).
Gold, silver, copper, lead, and zinc in Idaho and Washington (mines report).
Gold, silver, copper, lead, and zinc in Montana (mines report).
Gold, silver, copper, lead, and zinc in Nevada (mines report).
Gold, silver, copper, lead, and zinc in New Mexico and Texas (mines report).
Gold, silver, copper, and lead in South Dakota and Wyoming (mines report).
Gold, silver, copper, lead, and zinc in Utah (mines report).

In measurements of ores, concentrates, and similar material the short ton of 2,000 pounds is used throughout. The ore classification is necessarily arbitrary in part. An ore is generally understood to be worked at a profit for one or more metals. The complex nature of western ores especially and the gradations from one well-recognized class to another render essential some fixed measures for the terminology used. The dry or siliceous ores comprise gold and silver ores proper, as well as fluxing ores carrying considerable quantities of iron and manganese oxides and very small quantities of gold and silver, and also precious metal bearing ores carrying copper, lead, or zinc in quantities too low to classify them as copper, lead, zinc, or mixed ores. The copper ores include those carrying more than 2.5 per cent of copper, or even less in the cases of the great disseminated copper deposits of the West and of the copper ores of the Lake Superior region. In general, the lead ores are those containing more than 4.5 per cent of lead and the zinc ores are those containing 25 per cent or more of zinc, both irrespective of their precious-metal content; but some ores of lower grade in lead, and especially in zinc, are treated profitably for these metals, and of course they are then classified as lead or zinc ores, as the case may be. The mixed ores are combinations of the ores enumerated.

Digitized by Google

The prices used by the United States Geological Survey for calculation of values for the years 1850–1917, inclusive, are as follows:

Prices of silver, copper, lead, and zinc, 1850–1917.

Year.	Silver.[a]	Copper.[b]	Lead.[c]	Zinc.[d]	Year.	Silver.[a]	Copper.[b]	Lead.[c]	Zinc.[d]
	Fine ounce.	*Pound.*	*Pound.*	*Pound.*		*Fine ounce.*	*Pound.*	*Pound.*	*Pound.*
1850	$1.32	$0.22	$0.05	.....	1884	$1.11	$0.13	$0.037	$0.044
1851	1.34	.166	.05	.....	1885	1.07	.108	.040	.043
1852	1.33	.22	.05	.....	1886	.99	.111	.046	.044
1853	1.35	.22	.06	$0.055	1887	.98	.138	.045	.046
1854	1.35	.22	.06	.....	1888	.94	.168	.044	.049
1855	1.34	.27	.07	.....	1889	.94	.135	.039	.05
1856	1.34	.27	.066	.....	1890	1.05	.156	.045	.055
1857	1.35	.25	.06	.....	1891	.99	.128	.043	.05
1858	1.34	.23	.06	.....	1892	.87	.116	.041	.046
1859	1.36	.22	.055	.....	1893	.78	.108	.037	.04
1860	1.35	.23	.056	.....	1894	.63	.095	.033	035
1861	1.33	.22	.05	.....	1895	.65	.107	.032	.036
1862	1.35	.22	.06	.....	1896	.68	.108	.03	.039
1863	1.345	.34	.06	.....	1897	.60	.12	.036	.041
1864	1.345	.47	.07	.139	1898	.59	.124	.038	.046
1865	1.337	.392	.066	.....	1899	.60	.171	.045	.058
1866	1.339	.342	.07	.....	1900	.62	.166	.044	.044
1867	1.33	.254	.065	.....	1901	.60	.167	.043	.041
1868	1.326	.23	.065	.....	1902	.53	.122	.041	.048
1869	1.325	.242	.06	.....	1903	.54	.137	.042	.054
1870	1.328	.212	.06	.....	1904	.58	.128	.043	.051
1871	1.325	.241	.06	.....	1905	.61	.156	.047	.059
1872	1.322	.356	.064	.....	1906	.68	.193	.057	.061
1873	1.297	.280	.06	.....	1907	.66	.20	.053	.059
1874	1.278	.220	.06	.....	1908	.53	.132	.042	.047
1875	1.24	.227	.058	.07	1909	.52	.13	.043	.054
1876	1.16	.21	.061	.072	1910	.54	.127	.044	.054
1877	1.20	.19	.055	.06	1911	.53	.125	.045	.057
1878	1.15	.166	.036	.049	1912	.615	.165	.045	.069
1879	1.12	.136	.041	.052	1913	.604	.155	.044	.056
1880	1.15	.214	.05	.055	1914	.553	.133	.039	.051
1881	1.13	.182	.048	.052	1915	.507	.175	.047	.124
1882	1.14	.191	.049	.053	1916	.658	.246	.069	.134
1883	1.11	.165	.043	.045	1917	.824	.273	.086	.102

[a] Report of Director of the Mint, pp. 212–213, 1914. Equivalent value of fine ounce based on average price and average rate of exchange. For 1916 and 1917 dealers' buying price, New York.

[b] Weed, W. H., Copper handbook, vol. 11, pp. 1339, 1343, for years 1850–1903. By computation from data for years 1850–1860, p. 1339. Survey computations for electrolytic copper since 1904. For 1916 and 1917, average sales price all marketable grades.

[c] New York price, Ingalls, W. R., Lead and zinc in the United States, p. 203, 1908. U. S. Geological Survey since 1904. For 1916, outside spot quotations, New York. for 1917, average sales price.

[d] New York price, 1875–1904, Ingalls, W. R., Lead and zinc in the United States, p. 342, 1908. St. Louis price, U. S. Geological Survey since 1904. The zinc price for 1915, 1916, and 1917, is average sales price for zinc, all grades. Oral communication from C. E. Siebenthal for 1853 and 1864.

It is to be understood, of course, that market values are not received by producers for metals in ore and intermediate products, nor always for metals in marketable form; that payment is made in accordance with contracts for treatment or sale; and that, therefore, average daily quotations do not necessarily agree with average prices received.

Each of the 16 sections mentioned is published in a separate pamphlet for advance distribution, and copies can be obtained, as long as the supply lasts, on request made to the Director, United States Geological Survey, Washington, D. C.

Digitized by Google

Digitized by Google

BAUXITE AND ALUMINUM.

By JAMES M. HILL.[1]

BAUXITE.

DOMESTIC PRODUCTION.

The quantity of bauxite marketed in the United States in 1917 was 568,690 long tons, which had a value at the mines of $3,119,058, an increase over the production of 1916 of about 34 per cent in quantity and about 36 per cent in value. The production from the Georgia, Alabama, and Tennessee field in 1917 was 62,134 long tons, an increase of about 26 per cent, and the Arkansas production of 506,556 long tons showed an increase of approximately 35 per cent.

Bauxite produced and consumed in the United States, 1913–1917.

Year.	Domestic production.					
	Georgia, Alabama, and Tennessee.		Arkansas.		Total.	
	Quantity (long tons).	Value.	Quantity (long tons).	Value.	Quantity (long tons).	Value.
1913	40,370	$150,710	169,871	$846,988	210,241	$997,698
1914	24,071	92,508	195,247	976,686	219,318	1,069,194
1915	28,245	144,345	268,796	1,370,489	297,041	1,514,834
1916	49,190	284,810	375,910	2,011,590	425,100	2,296,400
1917	62,134	395,051	506,556	2,724,007	568,690	3,119,058

Year.	Imports.		Exports.[a]		Domestic consumption.	
	Quantity (long tons).	Value.	Quantity (long tons).	Value.	Quantity (long tons).	Value.
1913	21,456	$85,746	(b)	(b)	231,697	$1,083,444
1914	24,844	96,500	[c] 5,374	$240,084	238,788	925,610
1915	3,420	17,107	16,082	717,186	284,379	814,755
1916	30	87	18,032	987,454	407,098	1,309,033
1917	7,691	28,989	21,791	1,323,926	554,590	1,824,121

[1] The statistical data in this report were prepared by Miss H. M. Gaylord, of the United States Geological Survey.

[a] Includes bauxite concentrates.

[b] Included in "All other articles."

[c] From July 1, 1914, includes bauxite concentrates.

Digitized by Google

Apparently the producers of aluminum consumed about 375,000 tons, the makers of chemicals about 82,000 tons, makers of abrasives about 110,000 tons, and the makers of refractories about 2,400 tons of bauxite in 1917.

As will be seen by the table, though the domestic consumption of bauxite in 1917 also increased 36 per cent over the consumption in 1916, the domestic deposits were able to supply nearly the whole demand. The larger exports were apparently made to Canadian aluminum and abrasive makers.

MARKET AND PRICES.

The market for bauxite in the United States is east of Mississippi River, and the largest consumers are located at or near the cities of East St. Louis and Aurora, Ill.; Detroit, Mich.; Cincinnati, Ohio; Knoxville, Tenn.; Philadelphia and Erie, Pa.; Niagara Falls and New York City, N. Y.; and Boston, Mass. Recently a number of municipal and industrial waterworks have installed small plants for the manufacture of aluminum sulphate for local use in purification of water. A complete list of those known to the United States Geological Survey to be users of bauxite follows:

USERS OF BAUXITE.

Aluminum Co. of America, Pittsburgh, Pa.
Booth Chemical Co., P. O. Box 203, Elizabeth, N. J.
Carborundum Co., Niagara Falls, N. Y.
Charles Lennig & Co. (Inc.), 112 South Front Street, Philadelphia, Pa.
Charles Taylor Sons Co., Cincinnati, Ohio.
Columbus Waterworks, R. D. 5, Columbus, Ohio.
Cumberland Waterworks, R. D. 3, Cumberland, Md.
Detroit Chemical Works, 238 Junction Avenue, Detroit, Mich.
E. I. du Pont de Nemours Powder Co., Wilmington, Del.
Erie Chemical Works, 31 Union Square W., New York, N. Y.
Exolon Co., 156 Sixth Street, Cambridge, Mass.
General Abrasives Co., Niagara Falls, N. Y.
General Refractories Co., Trinity Building, New York, N. Y.
Harbison-Walker Refractories Co., Pittsburgh, Pa.
Jarecki Chemical Co., St. Bernard Station, Cincinnati, Ohio.
Laclede-Christy Clay Products Co., St. Louis, Mo.
Massillon Stone & Fire Brick Co., Massillon, Ohio.
Merrimac Chemical Co., 33 Broad Street, Boston, Mass.
Metropolitan Water District of Omaha, Omaha, Nebr. (R. B. Howell, general manager.)
Montclair Waterworks, Little Falls, N. J.
Norton Co., Worcester, Mass. (also Niagara Falls, N. Y.).
Pennsylvania Salt Manufacturing Co., Widener Building, Philadelphia, Pa.
Springfield Waterworks, Springfield, Mass.
Superior Chemical Co., Joliet, Ill.

Bauxite is graded according to its chemical composition and is sold to the consuming industries on the basis of analysis. Apparently low content of silica and titanium is essential to the aluminum industry, but the content of iron may be fairly high, though bauxites low in iron and titanium are preferred by the makers of alum and aluminum sulphate. Makers of abrasive appear to be able to use bauxites of lower grade and containing larger proportions of silica and iron than are permissible in bauxite for other uses, but most abrasives are made from bauxites low in silica and iron. The bauxite used for refractories must apparently be fairly low in iron.

Digitized by Google

The prices received for bauxite in 1917, as reported by producers, ranged from $4.75 to $10.50 a long ton; the average price paid for the whole of the domestic bauxite sold in the country was $5.48 a long ton at the shipping point.

WORLD'S PRODUCTION.

Data on the output of the French bauxite mines have been withheld since the beginning of the war.

World's production of bauxite, 1913–1916.

Country.	1913		1914		1915		1916	
	Quantity (long tons).	Value.	Quantity (long tons).	Value.	Quantity (long tons).	Value.	Quantity (long tons).	Value.
United States	210,241	$997,698	219,318	$1,069,194	297,041	$1,514,834	425,100	$2,296,400
France	304,407	(a)	(a)	(a)	(a)	(a)	(a)	(a)
United Kingdom	6,055	7,606	8,286	10,507	11,723	15,393	10,329	(a)
Italy	6,843	16,101	3,844	9,046	6,504	15,942	8,746	(a)
India	1,184	161	514	156	(a)	141	750	2,253

a Statistics not available.

From British Guiana it is reported [1] that no further applications for bauxite lands will be granted till after the war. It is also understood that bauxite mined on concessions granted before the ruling was made is under Government control and its exportation may be prohibited at the discretion of the Government. Development [2] on the concessions already granted has been continued, and similar deposits have been found in other parts of the colony.

The Dutch Government has apparently followed the British in stopping the granting of licenses for exploration for bauxite. The Government of The Hague has recently dispatched two engineers to Dutch Guiana to study the bauxite deposits, apparently with the idea of obtaining an adequate knowledge of their potential value before taking further action.

OCCURRENCE AND CHARACTER OF BAUXITE IN THE UNITED STATES.

The known commercial bauxite deposits of the United States are in Calhoun, Cherokee, and Dekalb counties, Ala.; Pulaski and Saline counties, Ark.; Bartow, Floyd, Meriwether, Sumter, and Wilkinson counties, Ga.; and Carter and Hamilton counties, Tenn. A brief description of the geology of the domestic deposits was given in the report for 1916,[3] and detailed descriptions of the deposits in central Georgia have been published by the Georgia Geological Survey.[4]

The bauxite from all localities in the United States, though it may vary in chemical composition, is on the whole similar in gen-

[1] Commerce Repts., No. 300, p. 1139, Dec. 24, 1917.
[2] Supplement to Commerce Repts., Ann. Ser. 44–A, p. 3, Oct. 29, 1917.
[3] Hill, J. M., Bauxite and aluminum in 1916: U. S. Geol. Survey Mineral Resources, 1916, pt. 1, pp. 161–165, 1917.
[4] Shearer, H. K., A report on the bauxite and fuller's earth of the Coastal Plain of Georgia: Georgia Geol. Survey Bull. 31, 1917.

Digitized by Google

eral appearance, with the exception of the "granitic bauxite" of the Arkansas field. The greater part of the American bauxite appears to be made up of rounded pebble-like bodies set in a fine-grained matrix, which may also consist of small rounded particles or may be as fine grained as the finest clay. The pebble or pisolite form is so general that it is the conspicuous characteristic of American bauxite.

There is only one way to determine the value of bauxite, and that is by chemical analysis, which should show total silica, alumina, titanium oxide, iron oxide, and water. Bauxites of commercial grade should carry at least 52 per cent of alumina.

A few characteristics that indicate in a general way the quality of baxuite may be mentioned, though none of them are to be depended on. In general, bauxite of fair grade will not show the marks of a hammer when it is hit a glancing blow, though some bauxite has been shipped which can be cut with the hammer. Good bauxite that has been dried either in the open or in kilns when thrown on a hard floor has a distinct rattle, which bauxite clay does not have. The pisolites of the lighter-colored bauxites of the central Georgia field have a peculiar brownish-buff color and look something like horn or flint; they ordinarily can not be broken or marked with the finger nail in bauxites of good grade.

Some measure of the relative quality of dried bauxite can be had by grinding a sample in an agate mortar for half a minute. A bauxite of good grade will be found hard to grind and will stick to the mortar with such tenacity that it will have to be scoured out; a poor bauxite or bauxite clay will grind much more easily and will stick very little, if at all; and clay or kaolin grinds with ease and does not stick to the mortar. Similar results are found if the sample is rubbed on glass; the glass will not be scratched by even high-grade bauxite.

NOTES ON THE UNITED STATES BAUXITE MINES.

Alabama.—During 1917 three companies were operating in the Alabama field—the E. I. du Pont de Nemours Co., at the Snider mine, north of Piedmont; the Republic Mining & Manufacturing Co., near Rock Run, Cherokee County; and the Consolidated Mining Co., near Fort Payne, Dekalb County.

The production of bauxite from Alabama in 1917 showed an increase of about 44 per cent over the production in 1916. The output was used for the manufacture of alumina chemicals to the extent of 53 per cent; abrasive, 44 per cent; and refractories, 3 per cent.

Arkansas.—The American Bauxite Co., Globe Bauxite Co., E. I. du Pont de Nemours Co., and Republic Mining & Manufacturing Co. mined bauxite from deposits in Saline and Pulaski counties, Ark. The largest production was made from the deposits near Bauxite, Saline County.

The production from Arkansas in 1917 showed an increase of 35 per cent over the production in 1916, and it is believed that should the demand arise the Arkansas deposits are capable of much greater output and contain considerable reserves. The bauxite mined from

Digitized by Google

the Arkansas deposits is of high grade, as is shown by the fact that more than 71 per cent of the output in 1917 was used for the manufacture of aluminum, nearly 19 per cent from abrasives, 9 per cent for chemicals, and 1 per cent for refractories.

Georgia.—The total production of bauxite from Georgia in 1917 was approximately 52,000 tons, an increase of about 31 per cent over the production in 1916. Wilkinson County produced the largest quantity, Sumter County was second, Floyd County third, Bartow County fourth, and Meriwether County fifth in rank of output.

Georgia bauxite appears to be more suitable for the manufacture of alumina chemicals than for other purposes. The output in 1917 was distributed as follows: 59 per cent for alumina chemicals, 21 per cent for aluminum, and 20 per cent for abrasives.

In Bartow and Floyd counties in 1917 five companies were mining bauxite from deposits near Adairsville, Cave Springs, Hall, Hermitage, Linwood, and Pinson. The total quantity of bauxite shipped from the north Georgia area was approximately 15,000 tons, of which approximately 53 per cent was used for alumina chemicals, 33 per cent for abrasives, and 14 per cent for aluminum.

There was a small production of bauxite from the deposits near Warm Springs, in Meriwether County, which was used for alumina chemicals. It is reported that an eastward extension of these peculiar deposits has been found and will be developed during 1918.

In the central Georgia field three operators reported production of bauxite from deposits in Sumter County and five operators from deposits in Wilkinson County. The production of bauxite from this area was approximately 37,000 long tons, of which 61 per cent was used for alumina chemicals, 23 per cent for aluminum, and 16 per cent for abrasives.

Tennessee.—The bauxite deposits on Missionary Ridge were reported idle during 1917. A small output was made at the mines near Elizabethton, Carter County, but car shortage hampered operations. A new deposit of bauxite has been discovered near Hixon, 15 miles north of Chattanooga.

ALUMINUM.

DOMESTIC PRODUCTION AND CONSUMPTION.

The value of primary aluminum produced in the United States in 1917 was $45,882,000, an increase of 35 per cent over the value of the output in 1916. This increase is due in part to the increased price and in part to the greater output of primary aluminum in 1917. The secondary aluminum recovered during 1917 had a value of $16,711,800, a decrease of about 29 per cent from the value of the output in 1916. Information concerning this phase of the aluminum industry will be found in the chapter of Mineral Resources on secondary metals in 1917, which is now in preparation.

Digitized by Google

Value of aluminum produced and consumed in the United States, 1913–1917.

Year.	Domestic production.		Imports.[b]	Exports.[c]	Apparent consumption.
	Primary metal.	Secondary metal.[a]			
1913	$9,450,000	$2,199,480	$4,784,302	$966,094	$15,467,688
1914	10,080,000	1,673,140	4,074,583	1,546,510	14,281,213
1915	16,280,000	5,802,100	1,841,779	3,682,117	20,241,762
1916	33,900,000	23,430,200	1,785,870	15,417,134	43,698,936
1917	45,882,000	16,711,800	56,890	14,586,467	48,064,223

[a] Value based on average open market price, as quoted by Eng. and Min. Jour.
[b] Imports for consumption, figures from Department of Commerce reports. Includes aluminum in crude form, leaf, sheets, plates, bars, strips, wire, rods, and all manufactures of; table, kitchen, and hospital ware.
[c] Exports of aluminum and manufactures of; figures from Department of Commerce reports.

MARKET AND PRICES OF ALUMINUM.

In the United States the quoted prices for primary or "virgin" aluminum ranged from 62 cents a pound, in January, to 37 cents a pound, in October, a price which was maintained to the end of the year. The average for the year was 51.59 cents a pound, as compared with 60.71 cents in 1916. These prices are for small lots and immediate delivery, offered in the open market, and do not represent the price received by the single producer of primary aluminum in this country.

Prices of aluminum, 1913–1917, in cents per pound.[a]

Year.	Average open market price, small lots.	Contract price.
1913	23.64	(b)
1914	18.63	(b)
1915	33.98	20-31
1916	60.71	31-37
1917	51.59	31-37

[a] Eng. and Min. Jour. quotations in annual review numbers.
[b] No figures published, but it seems reasonable to believe that contracts were made on approximately the same basis as for 1912.

On March 5, 1918, announcement was made in the papers of Washington, D. C., that the President had fixed the maximum base price of virgin aluminum, 98–99 per cent pure, for lots of 50 tons or over, at 32 cents a pound. This price is subject to revision June 1, 1918.

Secondary aluminum, 98–99 per cent pure, recovered from scrap materials, sold for 56.40 cents a pound at the beginning of 1917. Its price followed the decline of virgin metal to a low of 35 cents a pound in the later part of October, a price which was maintained to the end of 1917.

Digitized by Google

NOTES ON THE ALUMINUM INDUSTRY.

The Aluminum Co. of America is now operating four electrolytic plants in the United States at which aluminum is made—at Massena and Niagara Falls, N. Y., Maryville, Tenn., and Badin, N. C. The Badin plant made its initial run in 1916, but was not producing much aluminum until August, 1917. Additional power is under development for the Maryville plant, which will further increase the producing capacity of the United States.

The British Aluminum Co. is reported[1] to be enlarging its aluminum works at Kinlochleven, in Scotland. On February 28, 1917,[2] the ministry of munitions took under control the secondary aluminum industry, establishing prices for purchase and resale of various grades of remelted materials containing aluminum and issuing rules for the makers and refiners of such materials, called "aluminum scrap and swaf." It will be recalled that the primary aluminum industry was placed under control December 7, 1915.

USES OF ALUMINUM.

The uses of aluminum have been changed somewhat by war conditions. Pleasure-car automobile makers have restricted the use of metal in bodies and parts of various kinds. Four makers of pleasure cars are making aluminum-alloy engines. Much aluminum is being used for military equipment of all kinds. It is believed that the domestic producers will be able to supply the demand for 1918,[3] but uncertainty as to what the demand will be makes predictions dangerous.

OTHER BAUXITE PRODUCTS.

Nearly 65 per cent of the domestic output of bauxite in 1917 went into aluminum, manufacturers of aluminum salts used nearly 13 per cent, 19 per cent was consumed in the manufacture of bauxite abrasives, and 3 per cent was used by makers of "high-alumina refractories," also called bauxite brick.

Within the last two years many foreign and domestic patents have been issued relating to the use of bauxite in the fixation of nitrogen, the manufacture of aluminum salts, and the fabrication of abrasives and refractories. Copies of these patents may be obtained from the United States Patent Office, Washington, D. C.

ALUMINUM SALTS.

The principal aluminum salts made in the United States are alumina, alums, usually ammonium and sodium alums, aluminum sulphate, and aluminum chloride. Alumina is largely consumed in the manufacture of aluminum, and no figures of domestic production are available for publication.

Alums of various qualities are produced at 9 plants in the eastern United States, the total production of alum in 1917 being 19,714

[1] Eng. and Min. Jour., vol. 103, p. 880, May 19, 1917.
[2] Min. Jour. (London), vol. 116, p. 129, Mar. 3, 1917.
[3] Aluminum industry in 1917: Metal Industry, vol. 16, p. 21, January, 1918.

Digitized by Google

short tons, valued at $1,017,083, a decrease of approximately 28 per cent in quantity and of 14 per cent in value from the production in 1916. The average price reported by makers of alums was $51.60 a short ton. The wholesale market quotations ranged from 4 to 5½ cents a pound, or $80 to $102 a short ton. The quotations on lump alum were fairly constant at 4 to 4¼ cents up to May, when an increase to 4½ to 5 cents was made. This price remained steady till November, when it dropped to 4 to 4½ cents. Ground alum at the first of the year was quoted at 4⅛ to 4⅜ cents, but prices rose to 4⅝ to 5⅛ cents about the middle of May and remained stationary until the last of September, when they began to drop, and reached 4 1/10 to 5 cents at the end of 1917.

Aluminum sulphate is made at 24 plants, 7 of which are at municipal or industrial waterworks, which consume their entire output. The total quantity of aluminum sulphate produced in the United States in 1917 was 178,738 short tons, of which 4,947 short tons did not enter the market but was used for water purification at the place of manufacture. The quantity of domestic aluminum sulphate which entered the market, 173,791 short tons, was greater than the quantity in 1916 by approximately 18 per cent, and the total domestic production increased about 16 per cent. The price reported by makers of aluminum sulphate for the 1917 output averaged $32.15 a short ton. Market quotations for low-grade aluminum sulphate ranged from a low of 2 cents to a high of 4 cents a pound, or $40 to $80 a short ton. Low-grade aluminum sulphate was quoted at 2 to 2½ cents a pound until October, when quotations rose to 2 to 3½ cents, but fell to 2 to 3 cents during the second week of November, and closed at 1¾ to 2¼ cents a pound at the end of the year.

Aluminum chloride is used for various purposes, among which may be mentioned the refining of mineral oils. This salt was produced at 3 plants in 1917, and the total output reported to the Geological Survey was 4,702 short tons, valued at $311,900, or approximately $66 a short ton. Market quotations on aluminum chloride remained stationary throughout the year at 4 to 4 1/10 cents a pound, or $80 to $82 a short ton.

Alum and aluminum sulphate produced in the United States and aluminum salts imported, 1913–1917.

Year.	Production.						Imports.[a]	
	Alum.			Aluminum sulphate.			Quantity (short tons).	Value.
	Quantity (short tons).	Value.	Price per ton.	Quantity (short tons).	Value.	Price per ton.		
1913.....	9,605	$312,822	$32.57	157,749	$2,977,708	$18.88	2,702	$66,549
1914.....	18,238	565,989	31.03	164,954	2,942,572	17.84	2,891	73,028
1915.....	24,915	699,256	28.07	169,153	3,224,495	19.06	1,408	34,320
1916.....	27,257	1,177,881	43.21	153,860	4,410,741	28.67	1,247	68,660
1917.....	19,714	1,017,083	51.60	178,738	5,746,427	32.15	507	39,088

[a] Includes alumina, aluminum hydrate or refined bauxite, alum, alum cake, aluminum sulphate, aluminous cake, and alum in crystals or ground.

Digitized by Google

BAUXITE ABRASIVES.

Bauxite abrasives sold under various trade names, such as alundum, aloxite, exolon, and lionite, are made by fusing bauxite in an electric furnace. These products are sold in the form of powders, cloth, grinding stones, and wheels of various shapes for a multitude of uses.

The total marketed production of artificial abrasives made from domestic bauxite in 1917 was 48,460 short tons, valued at approximately $6,970,000, or about $144 a short ton. This is an increase over the production in 1916 of 58 per cent in quantity and of 200 per cent in value. The average value is deceptive, however, in that the prices received for the product depend on many factors, among which hardness, size of grain, degree of finishing, and many others may be mentioned.

HIGH-ALUMINA REFRACTORIES.

There are two classes of high-alumina refractories now on the market. What are commonly called bauxite brick are made by mixing various proportions of calcined bauxite or high-alumina clay with a bonding material such as fire clay, sodium silicate, or lime. Refractories of this character are being made by the Laclede Christy Clay Products Co., the Harbison Walker Refractories Co., Charles Taylor & Sons, and the Massillon Stone & Fire Brick Co. Not all the refractories made by these companies are sold as bauxite brick, and in fact some do not contain bauxite. The other class of high-alumina refractories consists of those made by the electric fusing of bauxite. These are manufactured by the companies that make artificial abrasives.

The use of high-alumina refractories seems to be expanding, particularly in the construction of copper, iron, and lead furnaces and of cement kilns. No figures are now (March, 1918) available to show the production of high-alumina refractories, though it is known that at least 2,313 long tons of bauxite was consumed in making refractories.

Digitized by Google

Digitized by Google

PLATINUM AND ALLIED METALS.

By James M. Hill.

USES OF THE PLATINUM METALS.

In discussing the uses of platinum in war it is not practicable to confine the discussion to that metal alone, for several metals of the platinum group are useful in war and must be considered together. These metals are platinum, iridium, palladium, rhodium, osmium, and ruthenium. The first four named are of commercial and military value; the last two are, so far as known, of little commercial value. The natural alloy of osmium and iridium, that is called osmiridium or iridosmine, is used commercially in a small way.

Pure platinum is required by the Government in very large quantities for use in the "contact process" of making sulphuric acid and for use at the new plants erected for the fixation of nitrogen. It is needed also for making utensils and apparatus at a great number of chemical laboratories, which control our whole industry. Finally, large quantities of platinum and iridium are required for all kinds of electrical equipment.

The so-called platinum used in electrical work is an alloy of platinum and iridium, and the alloy used for some work may carry as high as 50 per cent of iridium. Each telephone and telegraph instrument has platinum contacts; every high-grade magneto for an airplane, automobile, motor boat, or gas engine has from two to six contacts of platinum; and the multitude of contacts on telephone switchboards and the relay instruments of both telephone and telegraph lines are of platinum. For some purposes in electrical work satisfactory substitutes for platinum have been found and are being used; for other purposes substitutes will probably soon be used; but for many high-duty electrical contacts no satisfactory substitutes have yet been found.

Pure iridium is apparently of little commercial use. It is employed principally as a hardening element in the platinum-iridium alloys used in the electrical industry and by jewelers. Jeweler's platinum contains an average of 10 per cent of iridium, though some alloys that run as high as 15 per cent of iridium are used for certain work. Therefore, every 100 ounces of platinum used in the jewelry trade contains 10 ounces of iridium, to produce which it is necessary to obtain and refine approximately 200 ounces of Russian or 630 ounces of Colombian crude platinum. The alloys used in the electrical industry contain from 15 to 50 per cent of iridium, and the average alloy used in electrical work doubtless contains 20 per cent of iridium. To obtain 100 ounces of electrical platinum it is therefore necessary to refine 400 ounces of Russian or 1,260 ounces of Colombian crude platinum.

Digitized by Google

Palladium is employed chiefly in making palladium-gold alloys, which are now extensively used in dentistry and to some extent in the jewelry and chemical industries. Palladium may be considered valuable as a war metal to the extent that it replaces platinum in dental and jewelry work, for to that extent its employment releases platinum for military uses.

Rhodium is of little commercial use, being employed principally in making rhodium-platinum alloys, which form one element in thermocouples made for the electrical control of heat.

Apparently there is little or no market for osmium, though a suggestion was made in 1913 that it be used in place of iridium for hardening platinum. This suggestion has not been adopted, however, perhaps because of the danger of handling osmium under temperatures at which it will oxidize.

To summarize: Platinum, iridium, and palladium are essential for the conduct of the war; platinum, principally for the chemical industry; iridum, chiefly for the electrical industry; and palladium, for the dental industry, in order that more platinum may be released for chemical work.

SUPPLY.

Practically all the platinum metals in the world's supply have come from placer mines—deposits of gravel and sand in which the metals are found in grains and nuggets and are cleaned from waste material by water. Platinum was first recognized as a new mineral in material found in the Choco district, Colombia, South America; later it was identified in the gold placers of the Ural Mountains, in Russia, and it has since been found at a number of other places.

Duparc [1] states that the known Russian deposits, if mined at the pre-war rate, can last only 12 years. The Australasian deposits, in Tasmania, New South Wales, and New Zealand, have made small additions to the world's supply, but the deposits now known in these countries are not capable of supplying a hundredth part of the world's demand, and some of them are reported to be nearly exhausted. The deposits in Borneo have been worked, but they seem to be small. The deposits in North America appear to be capable of yielding some increase, but do not hold out much promise of a large output. The Spanish deposits give some promise, but are apparently not large. South America, especially Colombia, possesses a considerable reserve, and more scientific working of the deposits will unquestionably add to the world's supply. The search for new platiniferous fields in the world has not yet been highly successful. Little, however, is known of the possibilities of the Siberian placer fields.

In 1916 it was estimated [2] that the total world's supply of platinum metals was approximately 5,000,000 ounces. This estimate was based on certain assumptions and was not checked by an extensive survey of the literature on platinum. Thanks to Prof. James Lewis Howe, of Washington and Lee University, who has gone through the literature thoroughly, it is now possible to revise this

[1] Duparc, L., Le platine et les gîtes platinifères del l'Oural: Soc. ing. civils France Mém. Bull. janvier-mars, 1916, p. 48.

[2] Hill, J. M., Platinum and allied metals in 1916: U. S. Geol. Survey Mineral Resources, 1916, pt. 1, p. 1, 1917.

Digitized by Google

estimate, and, happily, the revision shows larger resources. Prof. Howe's figures,[1] which appear to be essentially correct, indicate the total world production of platinum shown in the following table:

Estimated total production of crude platinum in the world to January, 1917, in troy ounces.

	Minimum.	Maximum.
Russia	7,115,482	10,128,308
Colombia	700,000	735,000
Borneo	175,000	200,000
New South Wales and Tasmania	9,000	10,000
Canada	9,000	10,000
United States	10,000	12,000
	8,018,482	11,095,308

The total supply of platinum metals in the world is probably more than 10,000,000 ounces, of which about 1,000,000 ounces of platinum and 400,000 ounces of other metals of the platinum group are now in the United States.

During the war the United States has not been receiving so much platinum as is normally consumed here. New industries and machines that require platinum have been built at a much faster rate, and the stock of platinum metals available for use during 1918 is evidently small and is constantly growing smaller.

The available supply of platinum metals can be increased somewhat by establishing a stable market at prices high enough to induce miners to save platinum and to stimulate imports of the metal—a step that has been taken by fixing the maximum price at which platinum can be imported at $105. The other means available is to husband the present supply of platinum metals. The supply is so short and the demand for essential war industries is so great that it may become necessary to commandeer stocks of partly manufactured platinum jewelry to meet the demand, though it is hoped that judicious administration of the metals already commandeered may obviate the necessity of such drastic action

The shortage was considerably relieved by the receipt, late in 1917, of about 21,000 ounces of platinum from Russia, consigned to the Secretary of Commerce. This shipment was immediately commandeered by the War Department for Government use.

DOMESTIC PRODUCTION.

CRUDE PLATINUM.

Crude platinum was produced in Alaska, California, Oregon, and Washington in 1917. Buyers and refiners report purchases of 605 ounces from producers in these States, which, at the average price ($90 an ounce), would have a value of $54,450. Incomplete returns from placer mines that produce crude platinum indicate that the production in 1917 fell off about 100 ounces from that of 1916, when it was 710 ounces. In view of the high prices for crude platinum in 1917 this decrease is rather difficult to understand, but part of it may be due to the fact that some of the miners held their platinum for higher prices.

[1] Personal letter to J. M. Hill.

Digitized by Google

Reports received from refiners indicate that 31,921 ounces of foreign crude platinum were refined. This figure does not include the 21,000 ounces of Russian crude received in December and not refined in 1917. Most of this material came from Colombia; the rest mainly from British Columbia, Java, and Russia.

REFINED PLATINUM.

Reports received from refiners of platinum, gold bullion, nickel, and copper indicate that 38,831 troy ounces of refined new metals of the platinum group were recovered, of which about 7,384 troy ounces are believed to be of domestic origin.

New platinum and allied metals recovered by refiners, 1915–1917, in troy ounces.

Year.	Platinum.	Iridium.	Iridosmine-osmiridium.	Palladium.
1915	6,495	274	355	1,541
1916	24,518	370	315	2,885
1917	33,009	210	833	4,779

Dealers and refiners reported sales in 1917 of 72,186 ounces of secondary platinum metals derived from refining scrap and sweeps. The figures that make up this total probably represent some duplication, as the same metal may be handled as scrap several times in a year. The large increase in the sales of scrap metals indicate clearly that, owing to the greatly decreased imports of crude platinum and the high prices paid for scrap, much attention was given to the collection and refining of all kinds of scrap containing platinum metals.

Secondary platinum and allied metals sold, 1915–1917, in troy ounces.

Year.	Platinum.	Iridium.	Palladium.
1915	42,149	863	958
1916	45,156	1,535	1,284
1917	59,007	9,832	3,347

WORLD'S PRODUCTION.

Statistics of the world's production of platinum and allied metals are at best estimates, though they are derived from the most reliable information obtainable. The statistics given in the table below are believed to be fairly accurate, though the figures for Russia are open to question, some estimates of the Russian production in 1917 being as high as 100,000 ounces.

Estimated world's production of crude platinum, 1910–1917, in troy ounces.

Country.	1910	1911	1912	1913	1914	1915	1916	1917
Borneo and Sumatra	200	.....	.....	200	(a)	(a)	(a)	(a)
Canada	30	30	30	50	30	100	60	80
Colombia	10,000	12,000	12,000	15,000	17,500	18,000	25,000	32,000
New South Wales and Tasmania	332	470	778	1,500	1,248	303	222	(a)
Russia	275,000	300,000	300,000	250,000	241,200	124,000	63,900	50,000
United States	390	628	721	483	570	742	750	605
	285,952	313,128	313,529	267,233	260,548	143,145	89,932	82,685

a No basis for estimate.

Digitized by Google

IMPORTS.

The imports of platinum and allied metals for consumption in 1917, exclusive of the 21,000 ounces of Russian platinum received in December, which do not appear in the reports of the Bureau of Foreign and Domestic Commerce for 1917, were about 57 per cent of the imports in 1916 and about 25 per cent of the pre-war imports.

Platinum and allied metals imported for consumption in the United States, 1916–17.

Metal.	1916		1917	
	Quantity (troy ounces).	Value.	Quantity (troy ounces).	Value.
Platinum or crude platinum and unmanufactured products, ingots, bars, sheets, wires	53,522	$3,128,067	30,207	$2,408,188
Platinum, manufactured products, vases, retorts, etc.	(a)	21,872	(a)	1,347
Iridium	3,346	250,705	3,619	378,678
Osmiridium	414	17,241	259	25,456
Osmium			400	23,359
Palladium	6,513	282,910	1,239	117,192
	63,795	3,710,815	35,724	2,954,220

a Quantity not given.

Platinum imported into the United States, 1916 and 1917.[a]

	Unmanufactured.		Ingots, bars, etc.		Manufactured products, vases, etc.	Total value.
	Quantity (fine ounces).	Value.	Quantity (fine ounces).	Value.		
1916.						
France	26	$1,841	2,006	$111,068	$16,471	$129,380
Chile	686	55,412	15	800	269	56,481
Netherlands	21	1,604	106	4,941	1,818	8,363
Norway			120	6,280		6,280
Spain	7	311	46	2,065		2,376
Peru	7	475				475
England	15,256	733,198	9,475	469,815		1,203,013
Canada	42	2,599	464	36,164	332	39,095
Panama	92	6,560				6,560
Mexico	93	6,231	11	489	33	6,753
Brazil	221	19,797				19,797
Colombia	24,774	1,677,805				1,677,805
Venezuela	11	698				698
Australia			5	243		243
	41,236	2,506,531	12,248	631,865	18,923	3,157,319
1917.						
France	192	20,422	1,705	143,162	80	163,664
Netherlands					254	254
England	2,044	144,570	1,570	102,763		247,333
Canada	46	3,792	420	37,495	48	41,335
Panama	38	2,629	5	470		3,099
Mexico	9	749	29	3,000		3,749
Brazil			3	300		300
Chile	83	6,800				6,800
Colombia	23,445	1,893,922	438	32,193		1,926,115
Venezuela	174	14,136				14,136
Dutch East Indies	49	4,430				4,430
China	66	3,940				3,940
	26,146	2,095,390	4,170	319,383	382	2,415,155

a Does not include platinum manufactures "Not specially provided for" in the tariff act, upon which a duty of 50 per cent is imposed.

Digitized by Google

The tables show that the imports from Europe have continued to decline and that the great bulk of those for 1917 came from South America. The imports from China are probably Russian platinum. The platinum imported from Dutch East Indies is presumably a by-product recovered by the tin dredges and may be an accumulation of several years' work.

MARKET AND PRICES.

REFINED METALS.

The quoted price of refined platinum in the New York market was $80 to $82 a troy ounce in January, 1917, but it increased to $102 to $105 in February and remained nearly stationary throughout the year. The average price for the year was $102.80 a troy ounce.

Average prices of refined platinum per troy ounce in the New York market, 1913–1917.[1]

1913	$44.88	1917: June	$104.75
1914	45.06	July	103.88
1915	49.63	August	104.55
1916	83.40	September	104.13
1917: January	87.83	October	104.00
February	103.75	November	104.52
March	103.33	December	104.38
April	103.77		
May	105.00	Average	102.82

After the War Department had commandeered all crude and refined platinum on March 2, 1918, a maximum price of $105 an ounce for all imports was set by the War Industries Board.

Refined palladium was quoted at $70 to $85 a troy ounce at the beginning of 1917, but prices advanced continuously throughout the year, being $115 to $125 for the period from August to November and reaching a maximum of $130 to $135 the last of December. Refined iridium was apparently sold only by special bargaining, and no very definite information is available concerning its price. Apparently $110 was the nominal quotation in January, but sales in the last months of 1917 are said to have been made at $180 to $185 an ounce.

The prices reported to the United States Geological Survey by refiners of the platinum group of metals varied considerably in 1917. In the following table fair average prices are given, and these prices have been used by the Survey in all computations.

Average price per troy ounce of refined metals of the platinum group, 1914–1917.

Metal.	1914	1915	1916	1917
Platinum	$45	$55	$84	$103
Iridium	65	83	94	150
Iridosmine	33	35	45	80
Palladium	44	56	67	110

[1] Eng. and Min. Jour., vol. 105, No. 2, p. 51, 1918.

Digitized by Google

No prices of osmium, rhodium, and ruthenium are available.

In England the platinum market is under control of the Government, for which Johnson, Matthey & Co. are the buyers. The buying price was 200 shillings ($48.67) an ounce and the selling price was 220 shillings ($53.53). On February 10, 1918, the prices were revised to 18 pounds sterling ($87) to 20 pounds sterling ($97) an ounce, a little below the prices ruling in the United States.

CRUDE PLATINUM.

United States.—The miners of California and Oregon received from $43 to $100 an ounce for their crude platinum in 1916. In 1917 the price of crude platinum in the United States ranged from $59 to $100 and averaged about $90 an ounce, which is the price that has been used by the United States Geological Survey in all computations. The principal buyers of crude platinum in the United States are:

American Platinum Works, Newark, N. J.
Baker & Co. (Inc.), Newark, N. J.
Belais & Cohn, 13 Dutch Street, New York, N. Y.
Pacific Platinum Works, Los Angeles, Cal.
R. & H. Platinum Works, 100 William Street, New York, N. Y.
Shreve & Co., San Francisco, Cal.
H. A. Wilson Co., Newark, N. J.

Colombia.—The price of crude platinum in Colombia in 1917, as the Survey is informed, ranged from $80 to $102 an ounce, the average price for the year being nearer the higher than the lower figure. Colombian crude platinum is estimated at 84 to 85 per cent fine.

Russia.—It is impossible to give any estimate of the prices paid for crude platinum in Russia. In March [1] it was reported that the miners were not satisfied with $80.36 an ounce, the price fixed by the Government. Later it was reported [2] that sales had been made at as high as $107.80 per ounce of crude metal 83 per cent pure.

NOTES ON PLATINUM DEPOSITS.

UNITED STATES.

GENERAL CONDITIONS.

A report on field work done in 1917 by the United States Geological Survey on the platinum deposits of California and Oregon is now in preparation. A summary of this report is given in a press bulletin [3] of the Survey, as follows:

> The important facts regarding the occurrence of platinum in California and Oregon are their widespread distribution and their lack of concentration in high value at any particular locality. In most placers the proportion of the platinum metals to the gold is very small. At one placer where large quantities of gravel were being handled the proportion of platinum to gold was about one-tenth of 1 per cent by weight. In a few small operations the proportion of platinum was reported to be equal to the gold, and in still fewer it was reported to be more than the gold.
>
> The problem of increasing the production of the platinum metals is closely involved with the production of placer gold and may be resolved into the problems of saving a larger proportion of platinum from the ground now mined and of finding new productive areas.

[1] Eng. and Min. Jour., vol. 103, p. 913, May 19, 1917.
[2] Idem, p. 1175, June 30, 1917.
[3] U. S. Geol. Survey Press Bull. 356, February, 1918.

Digitized by Google

DREDGING.

The modern dredge, which is capable of handling as much as 200,000 cubic yards of gravel a month, has become a highly efficient tool, but it is capable of still further improvement. If the gravel is clean and comparatively free from sediment, the dredge recovers most of the gold and platinum from the gravel that is handled, but if a large amount of fine mud or sediment is mixed with the gravel, it is not so effective.

By careful experiment one dredge operator estimated that his dredge has been losing 4¼ ounces of platinum a month. A dredge working in more favorable ground probably loses less, but the losses seem to have been studied in detail at only a few localities. The limit in methods of improvement must be found at the critical point where the cost of the improvement offsets the increase in returns. New methods or apparatus must add to the income or be abandoned. Where dredges must work rapidly in order to handle a large "yardage" the difficulties of making a great output of metal are increased, but the introduction of improvements like the jig and the elimination of as much barren material as possible from the sluicing apparatus will probably save a higher percentage of fine gold and platinum. It therefore seems that more efficient methods may yield some increase in the quantity of platinum recovered.

The chief problem is to find new ground for dredging. There are areas in northern California and southern Oregon that seem to be favorable for successful dredging, but it will be difficult to find ground as favorable as that now being dredged. Good ground can be found only through close investigation by those who are most familiar with dredging.

DRIFT MINING.

Old stream channels that are buried hundreds of feet beneath the lava on the western slopes of the Sierra Nevada formed the feeders of the gravels in the areas along the foothills that are now being dredged. These buried channels are mined by drifting or tunneling under the lavas, bringing the gravels to the surface, and recovering the placer gold. Some of these old channels carry considerable platinum aside from the gold, and at a few places attempts are being made to mine them more extensively. Drift mining on a scale approaching that of dredge mining would doubtless recover an equivalent quantity of the platinum metals.

HYDRAULIC MINING.

The hydraulic mines in northern California and southern Oregon are producing some platinum along with the gold. The proportion of the value of the platinum to that of the gold produced at some of these mines is about 1 to 20. Unmined gravel deposits along streams in this area contain platinum as well as gold and should yield a considerable quantity of the platinum metals. The main problem at most of these deposits is to get sufficient water for mining, and any adequate investigation of them must determine not only the quantity of gold and platinum in the gravel but also the quantity of water available for mining. These deposits can be successfully mined only by bringing water to them from considerable distances—several miles, at least. Large reserves of the platinum metals are probably locked up in these unmined gravels, but they can be recovered only when the cost of mining is reduced by more favorable conditions.

BEACH SAND MINING.

The beach sands along the coast of Oregon and California have long yielded gold and platinum. The sands mined include not only those of the present beaches, but those of old beaches that, through changes in the relation of the land to sea level, now stand about 200 feet higher than the present beaches. The sands of the present beaches were in places so rich that in the early days they caused one of the great stampedes recorded in the history of California. That was the time when the metal which had accumulated by long-continued wave action was ready to be gathered in by the miners. Even yet the hard winter storms bring metal to the miners, who are engaged every winter in a small way in working these sands. The outfit of these miners is generally simple. The long tom forms its foundation. At some places a small power plant is employed. The winnings of individual workers have been good.

The problem of mining the black sands of the beaches has been an alluring one, and many attempts have been made to mine on a large scale both the sands of the present beaches and those of the elevated beaches. A successful method of mining these sands must be based on a thorough prospecting of the material to be handled, which varies in richness not only vertically, layers of black sands alternating with

Digitized by Google

layers of barren sands, but horizontally. In any method of mining these sands many a streak of lean must be handled with the fat.

The prospecting of these sands is difficult. The average value of the ground can be determined only by closer attention than is usually given to it. Similar sands occur in Australia, and similar difficulties of prospecting and mining have been encountered there. Dredging, hydraulic mining, and drifting have been so perfected as to handle large quantities of material successfully, but no reliable method has yet been found to handle these beach sands, though during the season of 1917 preparations were being made at several places for working them on a large scale.

SUMMARY.

The possibility of increasing the production of the platinum metals, then, depends on improvements in the methods of saving now used, on the extension of these methods to areas that are known to contain these metals but that have not yet been mined, and on the discovery of new productive ground in northwestern California and southwestern Oregon, where the prospects seem to be good. Streams that carry insufficient gold and platinum to pay for mining at the prices formerly prevailing might now yield a profit. Streams that drain areas of serpentine would seem to be particularly favorable for prospecting. At no place are the platinum metals concentrated in large quantities. Being rarer than gold, they are harder to find than gold. Iridium is in great demand, and the fact that it forms 10 to 40 per cent of the platinum metals in nearly all the placer deposits in the United States is a special incentive to the search for more of them.

The elimination of litigation and the equitable settlement of questions regarding surface rights and underground rights in drift mining and regarding the distribution of water for irrigation, power plants, and mining might also increase the output. The present price of the platinum metals, which is higher than that of gold, does its share in encouraging production.

ALASKA.

During 1917, 81 ounces of platinum were saved at Alaska platinum mines—66 ounces at mines on Seward Peninsula and 15 ounces at mines in the Copper River country.

The place at which the largest production of platinum was made on Alaska was Dime Creek, where 17 placers were in operation. On this stream about 1 ounce of platinum is recovered to every $5,000 worth of gold. Some platinum is also produced on Bear and Sweepstakes creeks, in the same general vicinity.

From placers on Boob Creek, in the Tolstoi district, lower Yukon, 30 ounces of platinum were taken during 1917. Platinum occurs in the gravels of Kahiltna River, a branch of Susitna River, about 50 miles northwest of Anchorage. These gravels are now being tested for platinum. A small quantity of platinum was taken from the beaches of Kodiak Island in 1917.

CALIFORNIA.

Only about 460 ounces of crude platinum produced from California placers appears to have been sold to refiners in 1917, but more crude platinum may have been produced than was sold, though at this time (Mar. 28, 1918) the final figures showing the mine output are not available. As usual, the largest output was made by the dredges in Butte, Yuba, Calaveras, and Stanislaus counties. Some platinum was won in Trinity, Siskiyou, and Humboldt counties, the largest output in these counties being won by dredging at Junction City.

Digitized by Google

NEVADA.

The Boss mine, near Goodsprings, Nev., was extensively worked in 1917, according to the published report of the company dated January 15, 1918. Shipments were made of 442.53 tons of copper-gold-platinum ore, which carried 107 ounces of platinum and 400 ounces of palladium. Early in 1917 this ore was refined in New Jersey, but during the summer it was refined at the plant of the Palau Metals Co. near Los Angeles, then just completed.

OREGON.

The beach deposits near Bullards and Marshfield were the largest producers of platinum in Oregon, reporting a total of over 65 ounces won in 1917. A little platinum was saved by the dredges near Sumpter and in the hydraulic and sluice mines near Waldo and Kerby.

WASHINGTON.

Refiners reported the purchase of several ounces of platinum produced in Washington, which may have come from the beach deposits, from South Fork of Lewis River, or possibly from the Tulameen district in British Columbia.

WYOMING.

The Rambler mine, near Holmes, Albany County, Wyo., continues to produce platinum and palladium bearing copper ores. During the year about 350 tons of concentrates were refined, which carried considerable palladium and about one-third as much platinum. It is reported that recent work at greater depth in the mine has disclosed a new ore body that carries both platinum and palladium in workable amounts.

OTHER COUNTRIES.

CANADA.

The Tulameen district in British Columbia produced at least 75 ounces of platinum in 1917 and probably nearer 90 ounces. Some new platinum placers are said to have been found farther north in the Rockies, one of which appears to be a deposit that at the present prices of platinum might be profitably worked.

COLOMBIA.

The production of platinum in Colombia has increased steadily for several years and our imports from that country in 1917, as shown by refiners' reports, were 31,737 ounces of crude platinum. The American interests, which are operating one dredge on the Condoto, hope to have in operation during the summer of 1918 a second dredge, which should materially add to the Colombian output. If the prices now paid for Colombian crude platinum, about $102 an ounce in New York, are maintained, we can expect a considerably larger pro-

Digitized by Google

duction in Colombia, for at those prices the native labor will be content to remain in the platinum country instead of returning to the gold region, in which they prefer to live. No word has yet reached the Survey of any large undertakings in this promising field, though it is reported that a new company has been organized in England for working the Opogoda properties and that the old Certigue or Quito properties on the Upper Atrato are being refinanced.

RUSSIA.

Little can be said of the Russian platinum fields. Engineers returning from Russia report that none of the dredges are working and that it will take some time to put them in shape for operation. The platinum now produced is won by hand methods, and under the chaotic conditions that have prevailed in Russia not much platinum can be expected from that country for some time.

Digitized by Google

Digitized by Google

ARSENIC.

By JOSEPH B. UMPLEBY.

CONDITION OF THE INDUSTRY.

The production of arsenic or arsenious oxide in the United States in 1917 amounted to 6,151 short tons, valued at $1,118,313, an increase over 1916 of less than 3 per cent in quantity and of more than 101 per cent in value. The value of the output is somewhat uncertain, however, as in some returns it represents the value f. o. b. destination in carload lots and in others the value at the reduction plant. Throughout, however, the value reported by the producers is much lower than that quoted in the trade journals.

Nearly all the output in 1917 was recovered as a smelter by-product. One plant only, at Brinton, Va., began late in the year to mine and treat ore primarily for its content of arsenic. For this reason it is impossible to distribute the production according to the source of the ore. In 1917, as in previous years, however, Butte, Mont., and Tintic, Utah, have been important sources of arsenical ores. At Butte the sulpharsenite of copper, enargite, is, after chalcocite, the most abundant valuable mineral in the deposits. It has been estimated that in smelting these ores 14,000 or 15,000 short tons of arsenic trioxide is liberated each year.[1] Of this amount only a small part is recovered, but with the addition of a new Cottrell treater for flue dust at Anaconda the quantity of arsenic saved will be greatly increased. It is thought that this installation will be in operation by January, 1919.

Arsenic is found in most of the ores of the Tintic district, and large quantities of it are released in their treatment. The arsenic-bearing minerals are enargite and tennantite, together with tetrahedrite and famatinite, in which arsenic replaces part of the antimony.

The smelter at Tacoma, Wash., recovers large quantities of arsenic, which presemably comes from ores mined in Washington, Oregon, British Columbia, and Alaska. Indeed, arsenic is present in most of the ores mined in the Western States and large quantities of it escape through the flues of the smelters that reduce the ores. It has been estimated that "at least 25,000 tons of white arsenic could be saved each year as a by-product."[2] The limiting factors in a prompt response of production to a suddenly increased demand are the time required to install additional collecting equipment and the assurance of a continued demand sufficient to warrant the expense of the installation.

[1] Hess, F. L., U. S. Geol. Survey Mineral Resources, 1914, pt. 1, p. 958, 1916.
[2] Idem, p. 960.

Digitized by Google

The unusual demand for insecticides incident to increased gardening led the Government to place the industry under license late in the year. Early in 1918 the Food Administration, after exhaustive investigation during the later part of 1917, fixed a maximum price of 9 cents a pound to be charged by producers for white arsenic in carload lots delivered anywhere in the United States. Half a cent a pound additional is permitted for shipments in less than carload lots.

DEVELOPMENT DURING 1917.

During the year 1917 the American Metals Co. (Ltd.) resumed production at its smeltery, the Compañía de Minerales y Metales, at Mapimi, Mexico, and the Chipman Chemical Co. reopened the old arsenic plant at Brinton, Va. Preparations were also made for recovering the arsenic from a large quantity of accumulated flue dust at Great Falls, Mont., and progress was made on the installation of a new Cottrell treater at Anaconda.

The Mexican product is largely imported into the United States, and most if not all of it comes from the Mapimi reduction works, as is shown by the increased imports recorded from Mexico after that plant was opened. The arsenic at this plant is a by-product from the smelting of silver-lead ore originating at the company's Ojuela mine, in the State of Durango. Additional capacity for collecting arsenic from the flue dust at Mapimi is being provided and is expected to be ready for operation sometime during the summer of 1918.

The Brinton deposit, in Virginia, described by Hess [1] contains ore that is valuable principally for its content of arsenic.

During the year the old producers maintained about the same rate of output as in 1916.

The outstanding feature of the year's development was the large increase in the requirements of the manufacturers of insecticides. In December, 1917, in response to a detailed canvass by C. W. Merrill, of the Food Administration, the manufacturers of insecticides estimated that, in preparing for the growing season of 1918, they needed 6,900 short tons of arsenic. This, together with 1,000 tons estimated as the requirement of the manufacturers of sheep dip, nearly equals the total annual supply from production and imports for each year since 1913 and exceeds the total supply for each previous year. Yet under normal conditions from one-third to one-half of the arsenic consumed in the United States is used by the manufacturers of glass. The increased demand for insecticides is doubtless in large part a direct result of the campaign for home gardens. Most of this is probably a necessary outcome of existing conditions, but it seems likely that much more than usual is wasted, because of the overzealousness of the novice in combating garden pests.

PRODUCTION.

Arsenic was produced in 1917 at seven plants operated by four companies. The table below shows the production of arsenic from the opening of the first plant at Everett, Wash., in 1901, to the end of 1917.

[1] Hess, F. L., The arsenic deposits of Brinton, Va.: U. S. Geol. Survey Bull. 470, pp. 205–211, 1911.

Digitized by Google

White arsenic (As_2O_3) produced in the United States, 1901–1917.

Year.	Quantity (short tons).	Value.	Year.	Quantity (short tons).	Value.
1901	300	$18,000	1910	1,497	$52,305
1902	1,353	81,180	1911	3,132	73,408
1903	611	36,691	1912	3,141	190,757
1904	36	2,185	1913	2,513	159,236
1905	754	35,210	1914	[b] 4,670	313,147
1906	737	63,460	1915	[c] 5,498	302,116
1907	1,751	163,000	1916	[d] 5,986	555,187
1908	[a]	[a]	1917	6,151	1,118,313
1909	1,214	52,946			

[a] Only two firms produced arsenic in the United States in 1908, so that the figures can not be published without disclosing confidential returns.
[b] This quantity includes 200 tons of crude arsenic trioxide carrying about 97.5 per cent As_2O_3.
[c] This quantity includes 353 tons of crude arsenic trioxide carrying about 97.5 per cent As_2O_3.
[d] This quantity includes 152 tons of crude arsenic trioxide carrying about 97.5 per cent As_2O_3.

The refined arsenic produced is reported to be above 99.5 per cent As_2O_3.

The small increase in the domestic production of arsenic and the great increase in its value in 1917 are noteworthy features shown by the table.

IMPORTS.

The imports of white arsenic and arsenic sulphide, or orpiment, increased from 2,163 short tons in 1916 to 3,955 short tons in 1917, or nearly 83 per cent. This increase should be compared with a decrease of 32 per cent in 1916 and is due to the resumption of production in Mexico as well as to increased imports from Canada. The Mexican source of supply has already been mentioned on page 24. The Canadian output is derived as a by-product in the smelting of ores from Cobalt and adjacent silver deposits in northern Ontario.

Arsenic compounds imported and entered for consumption in the United States, 1909–1917.

Year.	Arsenic or arsenious acid (white arsenic, As_2O_3).		Arsenic and sulphide of, or orpiment.		Sheep dip.		Paris green and London purple.	
	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (pounds).	Value.	Quantity (pounds).	Value.
1909	445	$31,235	3,591	$272,493	1,574	$9,615	183,765	$20,370
1910	1,348	76,282	3,791	238,024	.....	24,279	181,363	14,648
1911	1,921	116,948	2,175	127,375	.....	20,642	126,191	4,972
1912	3,103	200,616	3,053	228,125	.....	41,556	162,272	6,950
1913	1,519	133,597	3,182	276,849	.....	40,036	99,692	4,431
1914	1,594	109,121	2,034	164,592	.....	34,556	15,476	2,235
1915	1,400	113,677	1,783	154,099	.....	19,916	21,056	4,069
1916	1,071	107,876	1,092	124,818	.....	20,134	23,461	5,028
1917	1,178	264,534	2,777	410,341	.....	15,848	48	189

It is impossible from information available to group the total imports by countries, because the source is recorded for only one of the two principal classes of material. The ports of entry, however, afford a fairly satisfactory idea of the source of the other principal class.

Digitized by Google

The table below shows that in 1916 about 87 per cent of the class listed as "arsenic and sulphide of, or orpiment," came from Canada, and that of the "arsenic and arsenious acid" 96 per cent entered through Buffalo and Michigan ports—presumably also from Canadian deposits. Similar figures for 1917 indicate approximately 42 per cent and 90 per cent, respectively, from Canada. The production from Mexico in 1916 was negligible, but in 1917 it amounted to nearly 57 per cent of the class designated as "arsenic and sulphide of, or orpiment." It is likely also that most of the arsenious acid entering through the port of New York came by coastwise boats from Mexico.

Arsenic imported into the United States in 1916 and 1917.

Arsenic and sulphide of, or orpiment.

Country.	1916.		1917.	
	Quantity (short tons).	Value.	Quantity (short tons).	Value.
Belgium	116	$18,647	14	$7,171
British Honduras	0.1	26	.....	.....
Canada	950	95,912	1,172	262,552
England	2	1,808	2	1,407
France	17	6,517	.....	.....
Germany	6	696	.....	.....
Japan	.....	.....	1	301
Mexico	1	1,212	1,588	138,910
	1,092	124,818	2,777	410,341

Arsenic or arsenious acid.

Port of entry.	1916.		1917.	
	Quantity (short tons).	Value.	Quantity (short tons).	Value.
Buffalo	986	$99,823	980	$215,776
Michigan	45	4,495	.....	.....
New York	40	3,558	113	26,193
Ohio	.....	.....	85	22,565
	1,071	107,876	1,178	264,534

PRICE.

The price of arsenic during any year is much more difficult to determine than that of metals which are produced in larger quantities and for which there is a wider market. A comparison of the quantity and value reported by the different producers shows a much wider discrepancy in the price received than is warranted by differences in freight rates from the several smelting centers to the eastern market. A similar comparison of figures recorded in the commerce reports for the several ports of entry reveals similar discrepancies. Also the "spread" between producer's price and the price on the New York market is far from a fixed percentage of the cost of arsenic to the jobbers.

Digitized by Google

The price per pound of white arsenic in New York in 1917, as quoted by the Oil, Paint, and Drug Reporter, ranged from 8 cents in January to 20 cents in May, June, and July, after which it fell, reaching 15½ cents in December. The average price paid to producers, however, seems to have been between 9 and 11 cents, and the maximum price paid to producers is understood to have been 16 cents.

OUTLOOK FOR 1918.

The deficiency in arsenic is not confined to the United States. In England and France prices even higher than those in the United States clearly reflect a shortage in the supply of arsenic, although both these countries are large producers of arsenic, England from the Cornwall deposits and France principally from the auriferous arsenopyrite deposits in the Department of Maine-et-Loire.

The extent to which arsenic may hereafter be used in preparing poisonous gases for use in trench warfare is not known, but it is believed that more poisonous constituents of gases are more readily available. The use of arsenic in weed-killing compounds is likely to increase to the limit of the supply. The shortage of labor available for keeping rights of way and cemeteries free of weeds is causing many inquiries concerning the uses of arsenic compounds for this purpose. In some of the Southern States arsenic compounds are used in killing trees preliminary to clearing land for agricultural use. These and many other demands for arsenic are likely to increase as long as there is a serious shortage of labor.

The present demand for arsenic consumes about 12,000 short tons a year, whereas the available supply in 1917 from both domestic production and imports was only to about 10,000 short tons. The supply in 1917, however, was much larger than in previous years. The average yearly supply from all sources for the period from 1911 to 1916, inclusive, was a little less than 8,150 tons. During 1918 the domestic production may be expected to increase and unless the output from Mexico and Canada finds another market the imports will also increase. On the other hand, the demand for arsenic will almost certainly increase and probably at a more rapid rate than production. It seems likely that a scarcity of arsenic will persist throughout 1918 and that the price will hold close to the maximum fixed by the Food Administration.

Digitized by Google

Digitized by Google

BISMUTH.

By JOSEPH B. UMPLEBY.

PRODUCTION.

The demand for bismuth, unlike that for most other metals, has not greatly increased during the war. There continue to be only two producers of bismuth in this country, so that the production may not be given, but it was very little in excess of that for 1916, and the wholesale price is understood to have been about 6 cents a pound lower. The bismuth produced in this country is almost entirely a by-product obtained in the refining of lead bullion. Market conditions have not heretofore justified the recovery of bismuth at many plants where it could be obtained from flue dust or bullion, and as the cost of mining and delivery to these plants is charged against other constituents of the ore, it is doubtful whether ore that is primarily valuable for bismuth will ever command a ready market in this country unless the use of the metal is greatly extended.

USES.

Little has been published relating to the uses of bismuth, but as it possesses the special property of expanding on cooling and of forming alloys of exceptionally low melting point, the following extensive quotation from a paper prepared by the Queensland Government geologist[1] is believed to be justified.

Numerous useful alloys are made by fusing bismuth with other metals, such as copper, tin, lead, and antimony. A small amount added to copper makes this metal red-short, or brittle when heated, and an alloy made by melting one part of copper to two parts of bismuth expands considerably on solidification; while one part of copper fused with four parts of bismuth produces a red crystalline alloy. Small quantities added to lead give toughness without brittleness, and two parts of bismuth with three of lead has ten times the hardness and twenty times the tenacity of lead, while two parts of lead and one of bismuth makes a very fusible and ductile alloy. Antimony fused with bismuth produces an alloy which expands when changing from a molten to a solid state, and equal quantities of both in an alloy produces a greater expansion than any other metal on solidification. Bismuth with tin forms alloys which are very sonorous, and to produce this effect in a marked degree some of the many plate and bell metals are made with bismuth as part of their composition. One part of bismuth to twenty-four of tin forms a malleable metal, which becomes brittle as the amount of bismuth is increased. Mercury is capable of absorbing a large quantity of bismuth in the formation of amalgams. Two of mercury to one part of bismuth forms a pasty mass, while with four parts of mercury the amalgam is in a liquid state. In the latter condition the amalgam is used in silvering both mirrors and the interior of vacuum flasks, although another alloy containing two parts of mercury and one each of bismuth, lead, and tin is used for the same purpose.

Bismuth is alloyed with two or more suitable metals to produce [a compound which will show] expansion when cooling down to a solid state, and which at the same time should be an easily fusible composition, the principal metals used in producing these two effects being lead and tin, with zinc, antimony, cadmium, and mercury as accessory constituents. In making solders the melting point can be lowered if bismuth is alloyed with them, and soldering can be effected under boiling water if the right proportion, as shown in the table, is present.

[1] Dunstan, B., Queensland mineral deposits (bismuth): Queensland Gov. Min. Jour., January, 1917, pp. 17–22.

Digitized by Google

Fusible bismuth alloys.

[Fusible below the boiling point of water, 212° F.

	Bismuth, melting point 520° F.	Lead, melting point 621.1° F.	Copper, melting point 1,981.5° F.	Tin, melting point 449.4° F.	Cadmium, melting point 609.6° F.	Mercury, melting point 37.7° F.	Antimony, melting point 1,166° F.	Melting point of alloy, °F.
Charpy's eutectic	8	5	.....	2½	.....	.....	.....	204°
Newton's metal	8	5	.....	3	.....	.....	.....	201°
D'Arcet's metal	8	4	.....	4	.....	.....	.....	199°
Rose's metal	8	8	.....	3	.....	.....	.....	174°
Onion's mercuric	8	5	.....	3	.....	1½	.....	170°
Lipowitz's metal	8	5	.....	2	1	.....	.....	150°
Lipowitz's mercuric	8	4	.....	2	2	1	.....	143°
Wood's metal	7½	4	.....	2	2	.....	.....	140°
Guthrie's eutectic	8	3	.....	3	2½	.....	.....	[1]
D'Arcet's mercuric	8	4	.....	4	.....	20	.....	113°

[1] Very fusible.

The variations in expansion and contraction of bismuth alloys indicate that in making castings it is better, when convenient, to allow the metal to cool to a semifluid condition and to press instead of pour the metal into the molds, as then it is nearing its minimum contraction. Stereotype metal and other metals used in printing are only occasionally made up with bismuth as one of the constituents, but where rough usage is expected, or where firmness and sharpness is specially desired, no other metal produces these qualities so effectively as bismuth.

Bismuth is useful in the processes of steel tempering. The exact degree of heat required for the purpose can be fixed automatically by using baths of molten alloys containing bismuth, which can be made up of varying proportions and giving fixed melting points.

As stated already, the presence of bismuth in an alloy gives low fusibility combined with hardness and sharp definition. The addition of cadmium to the bismuth-tin-lead series further lowers the fusing point, while the addition of mercury brings the temperature of fusion down to its lowest limits.

Safety plugs for boilers are made of an alloy of which bismuth is one of the constituents. The automatic sprinklers or fire extinguishers placed in the ceilings of buildings are also made of a bismuth composition and are set in action when material in a room takes fire, the rise in temperature immediately melting the easily fusible bismuth plugs and causing jets of water to play all over the room.

Electric fuses are sometimes made of a bismuth alloy, and are so constructed that if too great a charge of current is passed through them the easily fusible wire melts. This causes a disconnection and prevents any damage to the instruments or appliances within the circuit.

Bismuth is extremely diamagnetic, that is, opposed to magnetic influence. Antimony is another diamagnetic metal and with bismuth forms the couple of a delicate thermopile, an instrument used for measuring by thermoelectric force, indicated by a galvanometer, extremely minute changes in the heat of metals.

Bismuth bronzes suitable for spoons, jugs, teapots, etc., are alloys made up of a number of metals and are said to be unoxidizable, to keep a good color, and to be easily polished. Two such bronzes are of the following composition, respectively: (1) Copper, 25 parts; nickel, 24; antimony, 50; bismuth, 1; (2) copper, 69; nickel, 10; tin, 15; zinc, 20; aluminum, 1; bismuth, 1.

Bismuth subnitrate is used in surgical operations, in porcelain painting, as a medicine, and as a cosmetic. In medicine the carbonate is used much more than the subnitrate, as it is very easily assimilated. The oxychloride of bismuth as a medicine is of special use as a preliminary to surgical operations on the stomach. Four ounces of this is taken and assimilated, after which the stomach and intestines are photographed by X rays, the whole of the outline of these digestive organs and their defects being clearly defined as a result of the sensitiveness of the bismuth to these rays. Bismuth salicylate, gallate, lactate, and other organic compounds are used as medicine and in surgical operations, but the demand for them is much smaller than that for the carbonate, subnitrate, and the oxychloride.

The oxide is used in porcelain painting and also in glass staining, the object of its introduction and also that of the subnitrate being to prevent certain substances producing color which otherwise are useful fluxes. In gilding porcelain the oxide or the subnitrate is mixed with 15 times its weight of gold, applied with a brush, and then

Digitized by Google

fired. The subnitrate gives a colorless but iridescent glaze to porcelain and produces a yellow glaze when mixed with chromic oxide. The addition of 5 per cent of gold to the oxide makes a good copper-red glaze mixture, which has also the quality of producing a golden luster by reflected light. With less gold the color may be varied, and beautiful blue and violet shades can be produced by other proportions and manipulations of the same ingredients. In porcelain painting and enameling the bismuth compounds may be generally used as a flux for increasing the fusibility of other coloring oxides, and therefore become a vehicle for the oxides of manganese, chromium, and copper. Mixed with the oxide of antimony the subnitrate forms Merinee's antimony yellow, which is a good body pigment, and quite permanent.

IMPORTS.

The imports of bismuth in 1917 were somewhat less than in 1916, although greater than in 1915. Prior to the last decade the supply of bismuth in this country was almost entirely imported, but in recent years most of the imports have been displaced by the domestic product. The industry, however, is not a large one in this country, probably less than 250 short tons annually being sufficient to meet the demand.

The imports are shown in the following table:

Metallic bismuth imported and entered for consumption in the United States, 1906-1917.

Year.	Quantity (pounds).	Value.	Year.	Quantity (pounds).	Value.
1906	254,733	$318,452	1912	182,840	$316,440
1907	259,881	325,015	1913	117,747	213,257
1908	164,793	257,397	1914	90,505	165,208
1909	183,413	286,516	1915	44,362	108,288
1910	198,174	332,668	1916	76,723	195,975
1911	172,993	311,771	1917	69,250	142,300

The bismuth imported into the United States in 1917 came from England and from South American countries, but it is probable that much of the bismuth shipped to the United States was imported into the country to which it is credited in the following table. Bismuth is not produced in England, although much of the Australian ore is reduced there. Bolivia has been the world's principal source of bismuth in recent years, and it is likely that most of the imports from South America originated in that country.

Bismuth imported into the United States, 1917.

Country.	Quantity (pounds).	Value.
England	38,453	$103,684
Argentina	6,674	16,757
Chile	21,799	17,792
Uruguay	2,324	4,067
	69,250	142,300

Digitized by Google

Digitized by Google

SELENIUM.

By JOSEPH B. UMPLEBY.

For the first time in recent years more than two companies reported a production of selenium in 1917, so that figures may now be given. The output in 1917 was 39,630 pounds, valued at $70,000. The producing companies are the American Smelting & Refining Co., the Raritan Copper Works, and the United States Smelting, Refining & Mining Co.

Selenium, it is understood, was in demand in 1917, and the principal producing company reports that its output has been contracted for well into the future. This is in keeping with the fact that the value of imports for consumption of selenium and salts of selenium rose from $59 in 1915 and $302 in 1916 to $2,236 in 1917.

The shortage of imported manganese suitable for the glass industry has compelled the manufacturers of glass to seek a substitute, and it is reported that selenium has been found to be the most satisfactory.

Most of the selenium produced is a by-product in the electrolytic refining of copper.[1] It is the opinion of metallurgists that if market conditions warranted the domestic production would be greatly increased.

Uses.—Selenium is used to impart a red color in the manufacture of glass and enamel ware and to mask the green color in glass. Its most interesting uses, however, are based on its being a good conductor of electricity in the light and a poor one in the dark. Thus it finds use in measuring the Roentgen rays, in appliances for automatically turning on the light at night and for extinguishing the light in daytime, in wireless telegraphy, and in burglar alarms. Many electrical inventions are based on this property, but none have called for sufficient material to cause great increase in the demand.

Experiments have been made recently in vulcanizing rubber by selenium, but its high melting point, 217° C., discourages its use as a vulcanizer "for rubber, which is not capable of withstanding such a temperature."[2]

Selenium compounds have found a limited use in treating some of the so-called "incurable diseases."

Price.—Prices at the refinery ranged from $1.29 to $3 a pound, but as usual the price for small lots was much higher and ranged between wide limits, depending largely on the quantity purchased.

[1] A summary of published information concerning the occurrence of selenium in blister copper and in various ores is recorded by F. L. Hess in U. S. Geol. Survey Mineral Resources, 1914, pt. 1, pp. 971–972, 1916.

[2] Boggs, C. R., Vulcanization of rubber by selenium: Jour. Ind. and Eng. Chemistry, p. 117, February, 1918.

Digitized by Google

Digitized by Google

TELLURIUM.

By JOSEPH B. UMPLEBY.

There continues to be little market for tellurium and a correspondingly small production. Only two refiners, the Raritan Copper Works and the United States Smelting, Refining & Mining Co., reported a production in 1917.

Tellurium, like selenium, is a by-product from the electrolytic refining of copper. The domestic production is capable of large expansion if market conditions should warrant, as almost all blister copper contains recoverable quantities of tellurium. Much of this would be saved, if a demand existed, at prices of $1.50 to $2.50 a pound. In 1917 prices at the refinery averaged about $3 a pound, but a very small additional output would probably have flooded the market.

Digitized by Google

Digitized by Google

CHROMITE.

By J. S. DILLER.[1]

COMPOSITION AND USES OF CHROMITE.

Chromium is one of the important war metals, being extensively used as an alloy to harden steel in the manufacture of munitions.

About a dozen minerals contain chromium, but chromite, often called chrome ore or chromic iron ore, is the only mineral of commercial importance as a source of chromium. Its theoretical composition is represented by the chemical formula $FeO.Cr_2O_3$, according to which it contains 68 per cent Cr_2O_3 (chromic oxide) and 32 per cent FeO (ferrous oxide). In nature, however, more or less of the chromium is replaced by aluminum or iron, so that the percentage of chromic oxide varies with the degree of replacement from more than 60 per cent down to less than 10 per cent. The value of chromite depends on the content of chromic oxide, and the price of any grade of ore is based on the percentage of chromic oxide that the ore contains. High-grade domestic ore contains 40 per cent or more of chromic oxide. Much of the domestic chromite is of low grade, although the greater portion of it is reported to be of high grade.

The principal present applications of chromite are for metallurgic use in the manufacture of ferrochrome to make munitions of war and for furnace lining in the form of crude ore or chrome brick. Several special steels, as automobile steel and airplane steel, contain chromium, but not all of them are of special importance in the war program.

The principal chemical uses of chromite are in the manufacture of bichromate of soda, bichromate of potash, chromic acid, and chrome alum, which are employed in the manufacture of dyes and pigments and for tanning leather.

For both metallurgic and chemical uses high-grade ores are much desired. Low-grade ores can be used to greater advantage in making the alloy ferrochrome than in making chemicals. This adaptability in the manufacture of ferrochrome renders it possible greatly to extend the production and utilization of the low-grade domestic ores.

SUPPLIES.

The available supplies are made up of domestic production and imports, as is shown in the following table:

Available supplies of chromite, 1913–1917.

Year.	Domestic production (long tons).	Imports (long tons).	Quantity available (long tons).
1913	256	65,180	65,435
1914	591	74,686	75,277
1915	3,281	76,455	79,736
1916	47,035	115,945	162,980
1917	43,725	72,063	115,788

[1] The statistics for this chapter were compiled chiefly by Miss H. M. Gaylord, of the United States Geological Survey.

Digitized by Google

The total available chromite in 1913 probably represents closely the demands for normal consumption. It is probable that in 1914 and 1915, however, in order to accumulate a stock on hand to meet war conditions, more was imported than was actually needed. With greatly increased demands in the last two years, both domestic production and imports have been greatly enlarged and the consumption has more than doubled.

Although the returns from producers of chromite in the United States in 1917 may not all have been received (March, 1918), it appears probable that the production was 43,725 long tons. In this connection the Geological Survey would like to emphasize the importance of each producer making a prompt report on his operations, as it is only with full cooperation that the Survey is in turn able to furnish accurate data necessary to the Shipping Board. Several thousand tons have been reported unsold. As the domestic production in 1916 was 47,035 long tons, there was apparently a considerable decrease in production in 1917.

DOMESTIC PRODUCTION.

GENERAL STATEMENT.

The domestic production in 1917, so far as may be judged from reports already received by the Geological Survey, was 43,725 long tons. It came mainly from California, where the output was more than 36,700 long tons. Oregon ranks second, with a production of about 6,700 long tons. Alaska produced nearly 1,000 tons, and the remainder, less than 300 long tons, came from Washington, Maryland, and North Carolina. The accompanying map of North America (fig. 1) shows approximately the distribution of the producing chrome mines and important deposits not only in the United States but elsewhere in North America. As a considerable number of supposed producers have not yet reported, it is possible that the total production may turn out finally to be somewhat greater. It seems probable that the total domestic production in 1917 was about 3,000 tons less than in 1916. If so, the decline deserves special consideration in view of the constantly increasing demand.

CAUSES AFFECTING DOMESTIC PRODUCTION.

To discover, if possible, the causes of decline in the production of chromite in 1917, the United States Geological Survey sent out a questionnaire to all the chrome producers on its list, asking for statements of the maximum possible production of the mine during the last quarter of 1917 and the actual shipments of chromite from the mine during the same period, the difference being the deficiency in production due to one or more causes, of which the following may be noted: Bad weather, poor roads in winter, lack of funds, lack of shipping facilities, especially lack of cars as the result of the freight embargo, low prices, and uncertainty of market, particularly for low-grade ore. The last two are the most potent causes affecting small producers.

Digitized by Google

PRICES.

Significant articles [1] have appeared recently in the mining journals concerning a higher and more equitable price to the man who mines



FIGURE 1.—Map of North America showing known deposits of chromic iron ore.

and markets the chrome ore used in making ferrochrome now selling at $400 a ton. The Geological Survey has suggested an increased and more stable price for chromite as a most effective means of in-

[1] Rapp, F. A., The domestic production of chrome: Min. and Sci. Press, vol. 116, p. 113, Jan. 26, 1918. Lee, W. P., The ferrochrome situation: Eng. and Min. Jour., vol. 105, p. 244, Feb. 2, 1918

Digitized by Google

creasing domestic production by encouraging and arousing the small producer to do his utmost.

The price of 40 per cent chromite at the beginning of 1917 was $15 a ton, that is, 37½ cents a unit of chromic oxide, but at the end of the year the price had been raised to 70 cents a unit, or $28 a ton. The actual price reported to the Geological Survey ranged from $10 to $50 a ton and the average price of the ore sold during the year by producers was a little more than $24 a ton. Early in 1918 the price for 40 per cent ore reached 85 cents a unit ($34 a ton). The impending crisis resulting from lack of ships to import the ore needed for war purposes has impelled the principal consumer, the Electro-Metallurgical Co., of New York, to advance prices greatly in the hope of increasing domestic production. The statement of the company was published March 17, 1918, in the form of an appeal, as follows:

YOUR COUNTRY NEEDS CHROME ORE.

To Pacific coast prospectors and miners:

The California Chrome Co., which has operated in California and Oregon for the last two years, will contract for the balance of this year for chrome ore at a minimum price of $1.25 per unit for 38 per cent chromic oxide and upward.

Premiums will be paid for early delivery.

Advances will be made on good prospects for development work.

Settlements in full will be made on independent chemists' sampling and analysis on receipt of bills of lading and weight certificate.

This appeal ought to stimulate chrome mining on the Pacific coast and to arouse the prospector and miner to vigorous activity. Fixing the minimum price at $47.50 a ton for 38 per cent ore for the rest of the year, premiums for early delivery, advances for developing good prospects, and just terms of settlement will undoubtedly give a great impulse to increase of domestic production.

GRADE OF DOMESTIC ORE.

The block chrome ore sold on the Pacific coast in the summer of 1917 ranged in composition from 30 to 55 per cent chromic oxide and the average composition was 42 per cent.

Of the chromite mined and sold in the United States in 1917 22 per cent of the total quantity contained from 45 to 50 per cent of chromic oxide, 32 per cent contained from 41 to 45 per cent of chromic oxide, 36 per cent contained from 38 to 41 per cent of chromic oxide, and 10 per cent contained from 30 to 38 per cent of chromic oxide.

Of the ore marketed on the Pacific coast in 1917 nearly nine-tenths contained 38 per cent or more of chromic oxide and fell within the price of $1.25 a unit now offered. Important contracts for chromite ranging from 30 to 35 per cent chromic oxide have recently been signed, but the prices for that grade of ore have not yet greatly increased. It is hoped, however, that the large consumers of chrome ore for refractory purposes as well as for ferrochrome may further stabilize prices not only by adopting this scale of prices but by establishing a corresponding minimum price for ore below the grade of 38 per cent chromic oxide and thus contribute greatly to the increased production of low-grade ores and incidentally aid in promoting concentration.

Digitized by Google

CONCENTRATION OF CHROME ORE.

The importance of concentrating lower grades of chromite to fit them for higher uses and to save freight is fully recognized, and concentrating plants in considerable number are now either in operation, in course of construction, or in contemplation. In the gold region of the Pacific coast the miners are so familiar with crushing and concentrating auriferous quartz ores that they should readily take to the concentration of chromite. A concentrating plant was operated in San Luis Obispo County [1] more than 25 years ago, and two new concentrating mills will soon be at work in the same region. Ore was concentrated at the Collard mine during the summer of 1917, and the plant is now (March, 1918) improved and enlarged. An effective plant was built by the Placer Chrome Co. near Rattlesnake Bridge, in Eldorado County, 6 miles south of Newcastle. It has recently been enlarged and another mill is being built at Salmon Falls. In the same County (Eldorado) a short distance farther south, near Negro Hill, the Noble Electric Steel Co. is reported to have erected at its mine a concentrating plant with a daily capacity of 60 tons. Another concentrator is in course of construction at Folsom with a rated capacity of 50 tons daily. Machinery has been bought for a mill on the road between Auburn and Grass Valley, Placer County. In Tehama County, 7 miles from Lowry on the Klenisorge property, a 10-stamp mill with two tables has been recently placed in commission, and it is reported that another concentrating plant is to be erected in the same region. The Mineral Products Co. has a concentrator in Stanislaus County, and the Western Ores Co. reports one in course of construction in Butte County, 5½ miles east of Paradise. Another mill is reported to be running near Nevada City, in Placer County. Much has been said concerning a proposed mill in the Red Mountain region of Fresno County, and it is probable that before the end of the summer of 1918 there may be more than a dozen mills operating in California alone and a number of others elsewhere. North Carolina has a mill near Webster, in Jackson County, and there should be others at different points in the same county as well as in Buncombe and Yancey Counties, for North Carolina has a high grade of chrome ore. Concentrating mills are likely to follow farther north in Maryland and Pennsylvania, where chromite was extensively mined years ago.

All low-grade chrome ores can not be concentrated to advantage. This is especially true of low-grade ores in which the chromium has been replaced by aluminum and iron. Chrome ore rich in magnetite may under some conditions be successfully handled by a magnetic separator.

Concentrating plants have been a feature of the chrome industry in Canada ever since 1898 and two of the latest types of mills erected in that region are briefly described in this report for 1916.[2] It is believed that by a more extensive introduction of concentrating plants on the Pacific coast some low-grade ores not now available may be readily so beneficiated as greatly to aid in providing the needed supply for war purposes.

---

[1] Mineral Industry, p. 153, 1893.
[2] Diller, J. S., Chromite: U. S. Geol. Survey Mineral Resources, 1916, pt. 1, pp. 35-37, 1917.

Digitized by Google

IMPORTS.

The most striking feature of the imports in 1917, shown in the accompanying table, is the great decrease in the total from 115,945 long tons in 1916 to 72,063 long tons in 1917. This decrease is due wholly to restricted shipping facilities on account of the war and affects particularly imports from South Africa and New Caledonia, which require long overseas transportation. On the other hand, the imports from Canada have greatly increased and those from Guatemala appear for the first time. Only 17 tons have come from Cuba, but recent developments indicate that Cuba and also Brazil will soon be large contributors to our needs of chromite.

Chromic iron ore imported into the United States, 1913–1917, in long tons.[a]

	1913	1914	1915	1916	1917
Cuba				34	17
Canada		533	10,087	12,220	19,012
England		58	2	5	5
Greece	4,600	8,155	4,305	7,900	
Japan	79				
French Oceania	21,850	30,860	28,081	[b] 30,950	10,300
Australia				[b] 2,986	
British South Africa			22,800	[c] 23,000	4,750
Portuguese Africa	30,001	23,200	11,230	[c] 38,850	37,800
Turkey in Asia	8,650	11,880			
Guatemala					179
	65,180	74,686	76,455	115,945	72,063

[a] Statistics compiled from records of Bureau of Foreign and Domestic Commerce, U. S. Dept. Commerce.
[b] E. J. Lavino & Co., importers, credit New Caledonia with all ore listed under French Oceania and Australia, amounting to 33,936 long tons.
[c] E. J. Lavino & Co., importers, credit Rhodesia with all ore listed under British South Africa and Portuguese Africa, amounting to 61,850 long tons.

Chromium compounds imported for consumption, 1915–1917.[a]

	1915			1916			1917		
	Quantity.	Value.	Price per unit.	Quantity.	Value.	Price per unit.	Quantity.	Value.	Price per unit.
Chromic iron ore.....long tons..	76,455	$780,061	$10.20	115,945	$1,548,402	$13.35	72,063	$1,110,659	15.41
Chromic acid.....pounds..	3,571	755	.211						
Chromate and bichromate of potash.....pounds..	32,942	2,902	.088	459	75	.16	2,402	962	.40
Chrome or chromium and ferrochrome or ferro chromium .....long tons..	32	1,662	51.94	10	1,998	199.80			
Chromate and bichromate of soda.....pounds..				6,154	3,630	.59	22,025	4,075	.19

[a] Statistics compiled from records of Bureau of Foreign and Domestic Commerce, U. S. Dept. Commerce.

NEEDS FOR CONSUMPTION.

The measure of normal annual consumption of chromite for all the various uses before the war may best be expressed by the sum of domestic production and imports in 1913, about 65,000 long tons. On account of the greatly augmented demands of war conditions it has been estimated by the committee on mineral imports and ex-

Digitized by Google

ports of the Shipping and War Trade boards that the needs of the United States in 1918 will be equivalent to about 130,000 long tons of 50 per cent ore, of which 67,500 tons will be needed for ferrochrome, 40,000 tons for making bichromates and other chemicals for tanning, etc., and 22,500 tons for refractory purposes.

RECOMMENDATIONS.

The supplies available by imports, since those of Rhodesia and New Caledonia may be wholly or in large part cut off, are uncertain. The problem for the United States is to save shipping by increasing domestic production of chromite to its maximum capacity. The offer of the California Chrome Co. of a high price throughout the year for a relatively low-grade ore, with premiums for early delivery, reasonable terms of settlement, and advances to develop promising prospects if well backed up by the company should call forth from the prospectors and miners on the Pacific coast their best endeavors to supply the chromite needed for munitions to win the war.

The region attracting most attention, on account of its promising prospects, includes the adjacent portions of Del Norte County, Cal., and Curry County, Oreg. Facilities for mining and marketing this ore are urgently needed. A branch railroad is already in operation from Grants Pass to Waters Creek; if this road could be extended through the chromite region to Crescent City, it would have a great effect. Wagon roads should be provided in the national forests, and the little harbor of Crescent City should be improved to furnish adequate facilities for the needed transportation along the coast. It is believed that by hearty cooperation of all concerned the domestic production of chromite can be so increased as largely to release the shipping that would be required for imports.

Under the impulse of a great need and the favorable opportunity offered to arouse miners to strenuous efforts it is hoped and expected that the production of chrome ore in the United States in 1918 will be as much as 65,000 long tons of all grades, as noted in the following table:

Possible production of chromite and chromic oxide in 1918.

Grade of ore.	Quantity (long tons).	Content of chromic oxide (Cr_2O_3) (long tons).
38 per cent or more and concentrates	50,000	19,000+
30 to 37 per cent	10,000	3,500
25 to 29 per cent	5,000	1,350
	65,000	23,850

This output would be equivalent to 47,700 long tons of 50 per cent ore.

To this may be added 1,000 tons from Alaska, 25,000 tons of low-grade ore from Canada, with some from Newfoundland, as well as about 30,000 long tons from Cuba, Brazil, and Guatemala, and there would remain more than 40,000 long tons of various grades to be imported from New Caledonia and Greece.

Digitized by Google

LIST OF OWNERS AND OPERATORS OF DOMESTIC DEPOSITS OF CHROMITE.[1]

CALIFORNIA.

Adams, R. D., 1311 Humboldt Bank Building, San Francisco.
Agard, W. A. T., 268 Market Street, San Francisco.
Alexander, F. A., 633 Monadnock Building, San Francisco.
Altshuler, Samuel, 251 Montgomery Street, San Francisco.
American Exploration & Contracting Co., Grants Pass, Oreg.
Arata, P. A. H., Wade Building, San Luis Obispo.
Asbill, Frank, Alderpoint.
Atherton, F., Jamestown.
Ausmaier, S , 1127 Monterey Street, San Luis Obispo.
Aurora Mining Co., The, Idria.
Auspach, William, Dunsmuir.
Austin, H. C., 56 Bacon Building, Oakland.
Avery & Son, Porterville.
Baldwin, W. T., Telephone Building, Oroville.
Barnes, G. W., Watts Valley.
Barton, G. S., Grants Pass, Oreg.
Bawman, B. C., Cazadero.
Beckwith, Robert, Jamestown.
Belknap & Co., Yreka.
Bell, L. C., St. James Hotel, San Luis Obispo.
Berlin, J. F., Newman.
Biggs, H. C., 2190 Sutter Street, San Francisco.
Bingham, Alonzo, Callahan.
Blockman Co., 224 Granger Block, San Diego.
Bones, W. H., Occidental.
Bonetti Bros., Latrobe.
Booker, W. E., Jamestown.
Brandon, R. G., Latrobe.
Brandon, Madison, Latrobe.
Brust, F. P., 3431 Harper Court, Oakland.
Bryant, Cullen, Latrobe.
Bunker, H. H., Michigan Bluff.
Burnett, F. L., Folsom.
Burnham, W. A., Copperopolis.
Burrows, I. A., Newville.
Butcher Co., L. H., 341 Montgomery Street, San Francisco.
California Chrome Co., J. B. Huffard, Prest., 1107 Kohl Building, San Francisco.
Carr, E. H., Mount Springs Chrome Co., R. F. D. 79, Ione.
Carson, Frank, Visalia.
Chaix, S., Latrobe.
Chase, H. B., Monticello.
Chastain, F. S., Gazelle.
Clark, B. F., Yankee Hill.
Clarke & McDonald, Livermore.
Clary, W. H., Canyon City, Oreg.
Coggins, Arthur L., Dunsmuir.
Collier, B. K., Yreka.
Conklin, Wells, Newville.
Copsey, A., Middletown.
Cory, W. C., Jamestown.
Courtwright, George, R. D. 79, Ione.
Crisle, John, Sanger.
Curran, W. E., Currans Ranch, Sanger.
Curtis, M. L. & Co., Seeley.
Dack, Walter, Hazel Creek.
Davis, J. C., Copperopolis.
Dean, P. S., Felix.
DeKruse, E., Iowa Hill.
Delano, M. A., Grants Pass, Oreg.
Demasters, S. D., Star Route, Sanger.
Dibble, C. H., 433 California Street, San Francisco.
Dodson, R. L., Latrobe.
Dooley, E. D., Plymouth.
Dolbear, S. H., 1411 Humboldt Bank Building, San Francisco.
Doolittle, E. B., Happy Camp.
Dougherty, C. F., Hazel Creek.
Dwyer, J. F., Yreka.
Egling & Williams, Chinese Camp.
Elzey, R. H., Santa Rosa.
Esper, J. E., Cool.
Evans, J. C., Clarksville.
Facey Bros. & Williams, Callahan.
Ferbrache, J. A., 63 Rosanna Street, Gilroy.
Ferzeck & Burns, Sonora.
Finster, G. L., Patterson.
Fledderman Bros., Yreka.
Fleischbein & Kinney, Folsom.
Ford, A. L., Auburn.
Forni, J. C., El Dorado.
Fritz, L. W., Pine Flat.
Fuqua, T. L., Lower Lake.
Garcia, C. M., San Simeon.
Garrison, E. A., Forest Hill.
Gastman, A. L., Arcata.
Geisendorfer, C. A., Weimar.
Geisendorfer, J. F., 2107 Fourth Avenue, Sacramento.
Gibbons, W. W., Watts Valley.
Gillis, C. A., Angels Camp.
Glenn, P. E., Fair Oaks.
Grant, J. M., Etna Mills.
Gravlin, C. W., Grants Pass, Oreg.
Green, W. C., Georgetown.
Griffin, Turner & Hopfield, Folsom.
Guthrie, Alexander, Harris.
Hampton, John, Patterson.
Harp Bros., Corcoran.
Hawkins, E. J., Crescent City.

[1] Anyone knowing the owner or operator of a domestic chrome deposit whose name does not appear in this list should send the name at once to the Director, U. S. Geological Survey, Washington, D. C.

Digitized by Google

Hearst, Mrs. Phoebe, Hearst Building, San Francisco.
Hill, S. W., Box 393, Red Bluff.
Hodges, J. R., Towle.
Hoeft, Miss Eleanor, Nevada City.
Hogan, Thomas, Nevada City.
Holbrook & McGuire, 1002 Crocker Building, San Francisco.
Hole, Theodore C., Watts Valley.
Hollister & Pierce, San Luis Obispo.
Hothersal, G. J., Nevada City.
Hoy, E. K., Hazel Creek.
Hughes-Kibbler Co., Santa Margarita.
Hyatt, R. E., 523 Rialto Building, San Francisco.
Hyde, George, Smith River.
Irish, C. F., Mgr., Consolidated Chrome Co., Georgetown.
Irwin Co., Yreka, Cal.
Jens, J. C., Belmont.
Jewett, C. H., Grass Valley.
Johnson, William, 4346 Townsend Avenue, Oakland.
Johnston, U. J., & Co., San Jose.
Kahl, Joseph, Jamestown.
Kelly, M. A., P. O. Box 45, Newcastle.
Khoeery, K. J., Takilma, Oreg.
Kilday, M., Los Gatos.
Kipp, J. W., Watts Valley.
Kleinsorge, W. E., P. O. Box 1126, Sacramento.
Krunich & Ninkovich, Porterville.
Lacey, Thomas, Academy.
Lambert, M., Magalia.
Latchens, E. C., Callahan.
Laton, A. H., Cazadero.
Lawley, C. A., Calistoga.
LeMay, Florian & Charles, Box 464, Yreka.
Levensaler-Speir Corporation, 681 Market Street, San Francisco.
Linder, R. E., Alta.
Logan, L. D., 235 Montgomery Street, San Francisco.
Luce, Alonzo, Willows.
Luchessa, A., San Luis Obispo.
Lyons, A. M., Fosteria.
M. and L. Chrome Co., F. S. Morgan, Mgr., Nevada City.
McAfee, David, Valley Springs.
McCormick, Robert, Sonora.
McFall, J. H., Copperopolis.
McMullen, J. R., P. O. Box 245, Dinuba.
McMurtry, William, Watts Valley.
MacBridge, George, Callahan.
Mackey, Peter, Jamestown.
Madeira, George, sr., 1550 Page Street, San Francisco.
Madrid, John, Angels Camp.
Maguire, William, Dutch Flat.
Maltby, C. S., 1311 Humboldt Bank Building, San Francisco.
Marks & Grant, Etna Mills.
Marris, E. A., Healdsburg.
Masterson, G. J., Callahan.
Matthews, G. C., Cloverdale.
Maxwell, Grover, Garden Valley.
Maxwell, J. A., Felix.
Maydell Co., Sheldon Building, San Francisco.
Mayfield, Solon, Cambria.
Mefford, Mrs. J. E., R. F. D. 79, Ione.
Mercer, Charles, Watts Valley.
Meyer, Fred, Weimer.
Miles, D. E., Hazel Creek.
Milsap, Oscar, Newville.
Mineral Products Co., 334 Rialto Building, San Francisco.
Moore, Vincent, Star Route, Sanger.
Morse, S. F. B., Crocker Building, San Francisco.
Morton & Boyer, Bayles.
Moscatelli, Robert, Washington.
Mott, G. L., San Luis Obispo.
Mullally, William, Monticello.
Mundrini, Michael, Latrobe.
Neely, F. M., 70 Fremont Street, San Francisco.
Neil, T. L., Pope Valley.
Neilsen & Donnelly, Folsom.
Netherton, W. P., Mgr., Placer Chrome Co., Santa Cruz.
Nettleton & Swanton, Newcastle.
Nichelini, A., St. Helena.
Niles, Walter, Washington.
Noble Electric Steel Co., 995 Market Street, San Francisco.
Noise Co., San Luis Obispo.
Norcross, D. C., 430 California Street, San Francisco.
Null, J. E., Chinese Camp.
O'Brien, James, Plymouth.
Ogden, B. A., Knights Ferry.
Ogle, E. C., Volcanoville (Georgetown).
Osborn, Samuel, Altaville.
Page, J. E., Willits.
Palmer, F. S., 244 California Street, San Francisco.
Patterson, Schroeder & Woldenburg, Canyon City.
Payne, L. R., Academy.
Pereira, W. M., Chinese Camp.
Peri, Frank, Copperopolis.
Pfeifer, William, Latrobe.
Philpot, C. H., Mill Valley.
Pierce, W. W., Morro.
Pierce & Hollister, San Luis Obispo.
Pilliken, G. J., Folsom.
Plattner, J. H., Livermore.
Quigg, C. M., Jamestown.
Rice, Charles, Watts Valley.
Riffe, J. S., Sanger (Star Route).
Riffe, Sloane, Watts Valley.
Roeper, J. C., Independence.
Rohrer, G. C., Pulga.
Root, Frank, 1152 Sacramento Street, San Francisco.
Rose, Frank, Sanger.
Ross, William, & Co., Takilma, Oreg.
Rowen, R. J., Grants Pass, Oreg.
Rushing, J. H., Jamestown.
Saint, R. E., Watts Valley.
Sanger Mining Co., Sanger.
Sawyer Tanning Co., Napa.

Digitized by Google

Schoettgin, F. J., Columbia.
Schroeder, H. C., Nevada City.
Schuler & Park, Happy Camp.
Scoble, John, Watts Valley.
Scott, George, Towle.
See, Jacob, Santa Margarita.
Sell, J. A., Sonora.
Shafer & Atherton, Jamestown.
Shanks, D. W., 1106 Merchants National Bank Building, San Francisco.
Shelden, G. E., 302 Key System Building, Oakland.
Siebert, J. B., Star Route, Sanger.
Sims, Henry, Chinese Camp.
Simmons, D. B., Yankee Hill.
Snow, C. S., Academy.
Sowers, H. F., Smith River.
Stokes, L. R., Yankee Hill.
Stratton, Dr. D. E., Chinese Camp.
Strickland, C. E., Callahan.
Stuck, W. R., care of Patterson & Western Ry., Patterson.
Sullivan, D. J., Dutch Flat.
Swayne Lumber Co., R. N. Swayne, 430 Sansome Street, San Francisco.
Sweet, John, Wolf.
Tedoc Co., W. A. T. Agard, Mgr., 268 Market Street, San Francisco.
Terrill, William, Trimmer.
Terry, C. W., Sonora.
Thompson, H., Wolf.
Trinidad Mining Co., 341 Montgomery Street, San Francisco.
Tucker, Henry, Calistoga.
Turner, R. C., Grass Valley.
Turner, R. L., Colfax.
Uldall, N. J., Red Bluff.
Union Chrome Co., 180 Sutter Street, San Francisco.
Vance, Homer, Star Route, Sanger.
Vanderford Bros., Elk Creek.
Van Fleet, J. R., Supt., California Chrome Co., Kohl Building, San Francisco.
Van Winkle, Walton, 149 California Street, San Francisco.
Vaughn, D. A., Estate, Porterville.
Visalia Land & Investment Co., Frank Carson, Visalia.
Wait, A. L., Drytown.
Wakeham, A. L., Magalia.
Wallace, R. W., Pope Valley.
Walsh, C. H., East Auburn.
Walter, C., San Luis Obispo.
Ward, George, Fosteria.
Wear, E. T., Paso Robles.
Welker, A. J., Callahan.
Wells, H. Bulkeley, Holbrook Building, San Francisco.
Wells, John, Yankee Hill
Wentworth, G. E., Placerville.
West, W. M., Towle
Westover, William, Hazel Creek.
Whitney, John, Yreka.
Wiley, D. E., Folsom City.
Williams, William, Calistoga.
Williamson, O. S., Iowa Hill.
Wood, Charles, Placerville.
Wood, G. E., Star Route, Sanger
Zaar, Frank, Smith River.
Zerfing Bros., Cayucos.
Zenith Chrome Mining Co., 2101 East Twelfth Street, Oakland.

MARYLAND.

Maryland Chrome Corp., Canton National Bank Building, Baltimore.

MONTANA.

Brophy, J. F., Washoe.
Grupp, A. F. E., Twin Bridges.
Purdy, S. C., Great Falls.

NORTH CAROLINA.

Carolina Chrome Co., Webster, N. C.
Nickel Co., J. J. Hooker, Mgr., Sylva.
Ray Heirs, G. D., J. B. Roy, Burnsville.
Wilson, J. H., Sylva.

OREGON.

Adams, E. F., Oregon Nickel Mining Co., Oakland, Cal.
Barton, G. S., Box 646, Grants Pass.
Brown, C. W., Canyon City.
Brown, W. Q., Riddle.
Butler, D. M., Canyon City.
California Chrome Co., Kohl Building, San Francisco, Cal.
Cane, Frank, Riddle.
Collard, G. W., Kerby.
Costelloe & Keaton, Harbor.
Cunningham, A. A., 434 Harrison Street, Portland.
Curl, R. M., Canyon City.
Delano, M. A., Grants Pass.
Dunn, A. W., John Day.
Davis & Patrick, Ashland.
Fehely, R. C., Grants Pass, Kerby.
Finch & Johnson, Box 106, Kerby.
Geitsfield Bros., Canyon City.
George, L. L., Canyon City.
Gilmore, W. E., Kerby.
Gorman, Thomas, Rye Valley.
Grant Chrome Co., Prairie City.
Glasscock, Roy, Mount Vernon.
Hamer, Shelby & Delore, Dayville.
Hanenkrat, A. E., Prairie City.
Hazeltine, I. B., Canyon City.
Kight, F. M., Prairie City.
Kromite Mining Co., T. F. Adams, Payette, Idaho.
Lyon, Frank, Unity.
Lyon, H. T., Canyon City.
McCorkle & Andrus, Canyon City.
MacIntyre, L. H., Canyon City.

Digitized by Google

Mascall, O. R., Dayville.
Page, J. E., Willits.
Patterson, Otis, Canyon City.
Patterson, Schroeder & Woldenberg, Canyon City.
Peet, F. W., Prairie City.
Powers, D. W., Canyon City.
Reddy, T. F., Grants Pass.
Reese, R. C., Prarie City.
Rowen, R. J., Selma.
Smith, F. F., Galice.
Smith, W. H., Canyon City.
Stockwell, M. F., Canyon City.
Stone & Hawkins, Mount Vernon.
Uldall, Martin, Grants Pass.
Vancil, W. N., Seneca.
Ward, G. F., Canyon City.
Williams, Dr. J. J., Pacific Grove, Cal.
Woldenberg, L., Canyon City.
Zenith Chrome Mining Co., 2101 East Twelfth Street, Oakland, Cal.

PENNSYLVANIA.

Squier, Lee W., secretary Chrome Mining Co., Finance Building, Philadelphia.

WASHINGTON.

Joiner, George, Anacortes.
Smith, Mrs. G. B., Seattle.

Digitized by Google

Digitized by Google

CADMIUM.

By C. E. Siebenthal.

INTRODUCTION.

A brief account of the production, resources, metallurgy, and uses of cadmium was given as a chapter in Mineral Resources, 1908. A more detailed report is in preparation and will be published as a bulletin of the United States Geological Survey. The present report gives the production of cadmium in the United States since the beginning of the industry in 1907, the chief sources of the metal in the United States, the principal uses, the imports for 1903 and later years, the range of fluctuation in price in 1917, and the yearly average selling price since 1907.

PRODUCTION.

Cadmium was first produced in the United States by the Grasselli Chemical Co. in 1907. One by one other companies began the recovery of cadmium until there are now six producing companies, as follows: American Smelting & Refining Co.; Grasselli Chemical Co.; Krebs Pigment & Chemical Co.; Mammoth Copper Mining Co.; Midland Chemical Co.; and United States Smelting, Refining & Mining Co. As cadmium residue resulting from the production of electrolytic spelter is accumulating at several plants there will doubtless be other producers before long.

Cadmium is produced in the United States in two forms—metallic cadmium and the pigment, cadmium sulphide. The domestic production of metallic cadmium in 1907 was nearly sufficient to supply the home demand, a fact shown by the small imports for that year, but in 1908 the quantity of cadmium imported was almost doubled, and in 1909–1912 the imports were back at the figures that prevailed before cadmium had been produced in the United States. Since 1912, however, the domestic production has made great strides, and as a result the imports of cadmium are again small. As the imports came largely from Germany they have been practically stopped for the last four years.

The following table, compiled from reports by each producer of cadmium in the United States and from official reports of the German Government, shows that the production of cadmium in the United States since 1910 has made rapid gains on that of Germany. Taken together the production of these two countries constitutes practically the whole cadmium production of the world.

95186°—M R 1917, PT 1——4

Digitized by Google

Metallic cadmium and cadmium sulphide produced in the United States and Germany, 1907–1917.

Year.	United States.						Germany.		
	Metallic cadmium.			Cadmium sulphide.			Metallic cadmium.		
	Quantity (pounds).	Value.	Average price per pound.	Quantity (pounds).	Value.	Average price per pound.	Quantity (pounds).	Value.	Average price per pound.
1907	14,000	$14,350	$1.025	(a)			72,639	$60,757	$0.84
1908	8,000	6,000	.75	(a)			72,741	48,590	.67
1909	5,300	2,783	.525	(a)			81,982	46,777	.57
1910	4,700	2,585	.55	(a)			90,516	39,309	.43
1911	26,152	17,566	.67	2,392	$1,674	$0.70	93,861	53,372	.57
1912	52,508	39,875	.76	8,998	6,400	.71	94,262	63,507	.67
1913	54,198	41,838	.77	17,302	12,136	.70	81,993	63,641	.78
1914	[b] 91,409	81,205	.89	22,723	20,241	.88	(c)		
1915	91,415	108,443	1.19	10,624	12,057	1.13	(c)		
1916	135,212	210,931	1.56	22,176	27,942	1.26	(c)		
1917	207,408	305,097	1.47	50,169	70,939	1.41	(c)		
	660,302	830,673		134,384	151,389				

[a] No production.
[b] Exclusive of 4,225 pounds of cadmium in residues sold for export.
[c] No figures showing the cadmium production in Germany later than 1913 are available.

SOURCES.

Before cadmium was produced in the United States in large quantity its greatest output came from the zinc-producing regions of Silesia, where it is recovered as a by-product in the distillation of zinc. No cadmium is recovered in the United States in the distillation of zinc ores, but most of the output is derived from baghouse dusts at lead smelters that treat lead ores containing more or less zinc. In England and in the United States some cadmium is recovered in purifying the solution of zinc sulphate used in making lithopone. Another source of cadmium is the residue left in making zinc chloride from low-grade zinc ores and from zinc ashes and drosses. Still other sources which may become important are the anode muds resulting from the electrolytic refining of spelter and the muds that are precipitated in purifying the electrolyte preparatory to depositing zinc in the reduction of zinc ores by leaching and electrolytic deposition. In view of the increasing number of electrolytic zinc plants this source offers great promise for a large output of cadmium. The presence of more than 0.05 per cent of cadmium in spelter prevents its being classed as grade A in the Navy specifications of June 1, 1917, so that electrolytic plants now remove cadmium from the electrolyte usually by precipitation with zinc dust.

The fumes driven off in making brass are richer in cadmium than the spelter used, for the more volatile cadmium is driven off in greater proportion than the zinc and is thus concentrated in the fumes. Zinc-oxide flue dusts recovered from brass works show 2 to 3 per cent of cadmium. The use of these zinc dusts in making lithopone would permit also the recovery of the cadmium, which would be further concentrated in the vats. It has been estimated that 400 pounds of cadmium is lost daily in fumes from the brass foundries at Waterbury, Conn.[1]

[1] Parsons, C. L., Jour. Ind. and Eng. Chemistry, vol. 4, p. 186, 1912.

Digitized by Google

USES.

Cadmium is used in metallic form chiefly in alloys, and its various salts are used in the arts, in medicine, and in electroplating.

ALLOYS.

Cadmium lowers the melting point of alloys in which it is used and is therefore employed in making easily fusible alloys and soft solders, such as those used in the fusible plugs of automatic sprinkler systems. It is also used in making fusible safety plugs for boilers and electric fuses. Cadmium cliché metal is superior to the corresponding bismuth cliché metal for making stereotype plates.

Since tin has become scarce cadmium has been increasingly used as a substitute for tin in solders, such as the "half and half" lead-tin solder. Though cadmium is worth half as much again as tin it can be profitably substituted for tin in some solders, for less cadmium and more lead is used; moreover the tin available is required for uses for which there is no substitute. The supply of cadmium can easily be increased to meet any reasonable demand. It is highly desirable that some research laboratory undertake an intensive study of cadmium, particularly of cadmium alloys, to determine fully the availability of cadmium as a substitute for tin and to discover new uses for it.

Cadmium and cadmium compounds have been declared contraband of war by nearly all the belligerents, hence they must have military uses, but naturally there is not much authoritative information about such uses. A fraction of 1 per cent of cadmium is used in copper telegraph and telephone wires and cables in France and Italy. It is reported that such cables heavily charged with electricity are used in the wire entanglements before the trenches at the front. Cadmium is reported to be used in smoke bombs for signaling.

It is reported that relatively large quantities of cadmium were exported to Germany before the war for use in making small-arms ammunition. A cadmium band on the hard-jacketed cartridge ball is said to take the rifling with little wear on the barrel and thus prolong the life of the gun.

SALTS OF CADMIUM.

The sulphide of cadmium is the brilliant pigment cadmium-yellow or jaune brillant. Properly prepared it is one of the most permanent pigments known, and it is unaffected by hydrogen sulphide gas from coal smoke, whereas the common yellow pigments (lead chromes) are blackened in a smoky atmosphere. Cadmium-yellow is therefore employed as a protective coating over chrome-yellow in painting street cars and the passenger coaches on some railway lines.

Sulphide of cadmium is extensively used to give color and luster to glass and porcelain.

Other cadmium salts are used in dentistry, dyeing, photography, and electroplating.

Digitized by Google

IMPORTS.

Cadmium is imported into the United States as metallic stick cadmium and as the pigment, cadmium sulphide. The former is free of duty; the latter is dutiable at 30 per cent ad valorem. The value of the imports for consumption of metallic cadmium for 1903 to 1917, inclusive, is given in the table below, which is taken from the records of the Bureau of Foreign and Domestic Commerce. The quantities are not there recorded previous to July, 1909, and for the period preceding that time they have been computed by dividing the values of the imports by the average price of cadmium for the corresponding year in Germany, from which country the cadmium was imported. The quantity and value of cadmium imported as a pigment are not recorded separately by the Bureau of Foreign and Domestic Commerce.

Cadmium imported and entered for consumption in the United States, 1903–1917.

Year.	Quantity (pounds).	Value.	Year.	Quantity (pounds).	Value.
1903	[a]8,679	$4,565	1910	4,060	$2,295
1904	[a]7,655	4,524	1911	5,367	3,870
1905	[a]8,138	5,298	1912	5,250	3,764
1906	[a]13,808	10,522	1913	1,656	1,232
1907	[a]1,953	1,633	1914	441	368
1908	[a]3,567	2,390	1915	269	284
1909 first half	[a]6,659	4,559	1916	.....	.....
1909 second half	2,203		1917	.....	.....

[a] Prior to July, 1909, the quantities are computed as noted above.

EXPORTS.

Complete statistics of the exports of cadmium are not available, but it is known that domestic cadmium has been largely exported during the war. According to the Bureau of Foreign and Domestic Commerce the following quantities of cadmium were exported through the port of New York in the last quarter of 1916: In October, 33,244 pounds, valued at $55,259; in November, 4,900 pounds, valued at $5,100; and in December, 1,044 pounds, valued at $1,530. Of the exports in October, 23,210 pounds went to France, 9,984 pounds to Italy, and 50 pounds to Dutch Guiana.

Unrefined cadmium in cadmium residues has also been exported, as noted above.

PRICES AND VALUE.

The price of stick cadmium throughout the first half of 1917 was listed in retail lots as nominal at $1.50 a pound. During the last half of the year the quotations remained practically stationary at $1.40 to $1.75 a pound. The average price for 1917 as calculated from sales was $1.47 a pound, as compared with an average of $1.56 a pound in 1916. The price in London during the first four months of 1917 was 7s. 7½d. ($1.75) a pound; during the next five months it was 8s. 1½d. ($1.90) a pound, and for the remainder of the year it was from 7s. 3d. to 7s. 7½d. ($1.70 to $1.75) a pound.

The average selling price of cadmium sulphide in the United States in 1917 was $1.41 a pound, as compared with $1.26 a pound in 1916.

Digitized by Google

The value of the output of cadmium in the United States in 1917, calculated at the average selling price, was $305,097, as compared with $210,931 in 1916, and the value of the cadmium sulphide produced was $70,939, as against $27,942 in 1916.

The total value of the output of metallic cadmium in the United States since the beginning of production in 1907 is $830,673 and of cadmium sulphide $151,389, both together equal to nearly a million dollars.

BIBLIOGRAPHY.

The following list of books and articles on cadmium includes only the longer and more important papers which have appeared in recent years:

BLASSETT, EMMANUEL, jr., The electrodeposition of cadmium: Metal Industry, vol. 9, pp. 509–510, 1911.

INGALLS, W. R., The metallurgy of zinc and cadmium, p. 701, 1906.

——— Memorandum respecting the quality of spelter suitable for the manufacture of cartridge brass and other high-grade brass; with an appendix containing reprints of various articles from the Engineering and Mining Journal and discussion of papers read at the American Institute of Metals. Pamphlet, privately printed, p. 44, 1917.

JENSCH, EDMUND, Das Cadmium, sein Vokommen, seine Darstellung und Verwendung: Samml. chem. u. chem.-tech. Vorträge, vol. 3, pp. 201–232, 1908.

JURETZKA, FRANZ, Metallurgy of cadmium—raw materials, technique and economics: Met. and chem. Eng., vol. 16, pp. 146–148, 1917; translated by O. C. Ralston from Metall und Erz, vol. 12, p. 235, 1915.

LIEBIG, MAX, Zink und Cadmium, p. 598, 1913.

MATHER, F. C., and MARBLE, H. M., The electrodeposition of cadmium: Am. Electrochem. Soc. Trans., vol. 25, pp. 297–333, 1914.

SCHNABEL, CARL, Cadmium: Handbook of metallurgy, translated by Henry Louis, vol. 2, pp. 317–328, 1907.

SIEBENTHAL, C. E., Cadmium: U. S. Geol. Survey Mineral Resources, 1908, pt. 2, pp. 793–803, 1909.

SPEIER, PAUL, Cadmium: Min. Jour. [London], vol. 82, p. 573, Nov. 9, 1907.

Digitized by Google

Digitized by Google

Digitized by Google

Revision Slip.

Because of revisions received too late for incorporation in this chapter, the changes given below are necessary. Certain of these revisions appear on pp. 63A and 862-864.

Page 55:

Line 2 - $37,521,025 instead of $42,073,581;
14 per cent instead of 7.
5 - $31,881,814 instead of $36,434,370.
Table should read:

	Ore sold or treated.	Zinc.	Total value.
1916	2,241,113	290,533,687	$43,378,715
1917	2,709,201	312,566,805	37,521,025
Inc.or dec.	+468,088	+22,033,118	-5,857,690

Strike out footnote.

Page 57:

Line 1 - 312,566,805 instead of 310,336,805.
2 - $31,881,814 instead of $36,434,370;
22,033,118 instead of 22,447,118.
Strike out from "It will be noted" to end of paragraph.

Page 59:

Line 3 - 727,496 instead of 720,561.
4 - 241,692,000 instead of 239,462,000.
5 - Strike out "calculated as zinc in oxide and spelter."

Digitized by Google

GOLD, SILVER, COPPER, LEAD, AND ZINC IN THE EASTERN STATES.

(MINES REPORT.)

By JAMES M. HILL.

MINE PRODUCTION.

The total value of the output of gold, silver, copper, lead, and zinc in the Eastern States was $42,073,581 in 1917, a decrease of about 7 per cent from the production in 1916. The total value is distributed among the various metals as follows: Gold, $29,227; silver, $87,714; copper, $4,930,672; lead, $591,598; zinc, $36,434,370.

As will be seen from the following table, the decrease in value is due to the decreased output of gold and to the reduction of the average value for zinc and is not an index of the quantity of metals produced in the Eastern States, which increased considerably.

Mine production of gold, silver, copper, lead, and zinc in the Appalachian States, 1916–17.

Year.	Ore sold or treated.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.[a]
	Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	2,241,113	$64,370	100,323	17,104,303	1,582,034	287,889,687	$45,260,290
1917	2,702,266	29,227	106,450	18,061,068	6,879,053	310,336,805	42,073,581
Increase or decrease	+461,153	−35,143	+6,127	+956,765	+5,297,019	+22,447,118	−3,186,709

[a] The value of the production of zinc in 1916 and 1917 is not all calculated at the average zinc price used by the Survey.

GOLD.

The mine production of gold in the Eastern States in 1917 was only 1,413.86 fine ounces, having a total value of $29,227, as compared with 3,113.90 fine ounces valued at $64,370 in 1916. Of this output the placers yielded 336.41 ounces, the siliceous gold ores 416.17 ounces, and copper ores 661.28 ounces. As was to be expected, very few gold mines were worked during 1917, owing to the increased cost of operation and the fixed price of the product. On the other hand, the copper mines increased their operations and made greater recoveries of both gold and silver.

Digitized by Google

SILVER.

In 1917 the mine production of silver in the Eastern States was 106,450 fine ounces, valued at $87,714, an increase of about 6,100 ounces over the output in 1916. The largest production was from copper ores and the smallest from placer mines, as is shown by the second table below. There was a considerable increase in the silver recovered from copper ores mined in Tennessee and Virginia, and some silver was derived from lead-zinc ores mined in the latter State.

Mine production of gold and silver in the Eastern States in 1917, by States.

State.	Gold.		Silver.		Increase or decrease in value compared with 1916.	
	Quantity.	Value.	Quantity.	Value.	Gold.	Silver.
	Fine ounces.		*Fine ounces.*			
Alabama and Georgia	442.68	$9,151	57	$46	−$22,038	− $38
Maryland, New Hampshire, and Vermont	6.62	137	1,709	1,409	+ 137	− 1,237
North Carolina	589.55	12,187	1,110	915	− 14,050	+ 479
South Carolina	52.39	1,083	3	2	+ 763	− 16
Tennessee	257.65	5,326	99,053	81,619	− 413	+19,306
Virginia	64.97	1,343	4,518	3,723	+ 458	+ 3,208
	1,413.86	29,227	106,450	87,714		
Increase or decrease	1,700.04	−35,143	+6,127	+21,702	− 35,143	+21,702

Mine production of gold and silver in the Eastern States in 1917, by sources, in fine ounces.

State.	Gold.			Silver.		
	Placers.	Dry or siliceous ores.	Copper ores.	Placers.	Dry or siliceous ores.	Copper ores.
Alabama and Georgia	135.99	306.69		9	48	
Maryland, New Hampshire, and Vermont			6.62			1,709
North Carolina	192.48	65.08	[a] 332.04	34	97	[a] 979
South Carolina	7.94	44.45			3	
Tennessee			257.65			99,053
Virginia			[a] 64.97			[a] 4,518
Total, 1917	336.41	416.17	661.28	43	148	106,259
Total, 1916	803.81	1,984.91	325.18	148	411	[a] 99,764

[a] Includes some gold and silver from lead ore.

COPPER.

The mine production of copper in the Eastern States in 1917 was 18,061,068 pounds, valued at $4,930,672, an increase in quantity over 1916 of 956,765 pounds and in value of $723,013. This copper was largely derived from Tennessee ores, but some came from the copper-bearing magnetite ores of Pennsylvania and from copper ores mined in Georgia, Maine, Maryland, North Carolina, Vermont, and Virginia. The total quantity of ore and tailings treated to pro-

Digitized by Google

duce this copper was 923,251 tons, showing an average yield of copper of approximately 0.9 per cent, or about 18 pounds a ton.

LEAD.

The mine production of lead in the Eastern States in 1917 was 6,879,053 pounds, valued at $591,598, an increase of nearly 335 per cent in quantity and of about 440 per cent in value. Tennesssee mines produced 5,061,937 pounds, but more than 1,700,000 pounds were produced in Virginia, and there was also a considerable production from New Hampshire and a small quantity from North Carolina.

ZINC.

The production of zinc in the Eastern States in 1917 was 310,336,805 pounds, valued at $36,434,370, an increase in quantity of 22,447,118 pounds over the production in 1916. It will be noted that this value is more than it would be if the zinc content of the ore were calculated as spelter at 10.2 cents a pound, which was the average sales price of all grades of spelter in 1917. The difference is because of the fact that the zinc ore mined in New Jersey is not all used for the manufacture of spelter and its value is therefore calculated on a basis which gives a combined value of the zinc oxide and of the high-grade spelter produced.

New Jersey produced more zinc than all the remaining Eastern States, and Tennessee was second, with an output of nearly 57,000,000 pounds. New York and Virginia were next in rank with approximately 10,300,000 and 3,400,000 pounds, respectively. There was also a small output from New Hampshire.

REVIEW BY STATES.

ALABAMA.

Only one mine in Alabama, the Gold Log, near Talladega, marketed metals during 1917. Apparently no one worked at the placer mines near Arbacoochee, but some development was done on the Jemison property in Chilton County and at the Pinetuckey mine in Randolph County.

GEORGIA.

In 1917 mines in Georgia produced 333.26 ounces of gold, valued at $6,889, 46 ounces of silver, valued at $37, and 930,691 pounds of copper, a decrease of $15,650 in the value of gold and of 28 ounces in the quantity of silver from the production in 1916. The production of copper in 1917 was due to the reopening of some of the mines in the Ducktown district, which lie in Fannin County, Ga.

Of the output in 1917, placer mining furnished 135.99 ounces of gold and 9 ounces of silver, the remainder coming from deep mines. The deep gold mines in operation in the State treated 44,610 tons of siliceous ore, from which 197.27 ounces of gold and 37 ounces of silver were recovered.

Digitized by Google

Mine production of gold, silver, and copper in Georgia, 1916–17.

Year.	Number of mines.		Ore sold or treated.	Gold.[a]	Silver.[a]	Copper.	Total value.
	Placer.	Deep.					
			Short tons.		*Fine ozs.*	*Pounds.*	
1916	20	6	46,944	$22,539	74	803,699	$220,298
1917	13	6	44,610	6,889	46	930,691	261,005
Increase or decrease in 1917	−7	.....	−2,334	−15,650	−28	+126,992	+40,707

[a] Includes placer gold and silver.

Placer mines numbering 13 were operated in Dawson, Cherokee, Haralson, Lumpkin, Rabun, White, and Wilkes counties. Five placers in Lumpkin County produced 55.36 ounces of gold. The White County placers, including the Loud mine, made nearly as much gold and considerably more silver than those of Lumpkin County.

Five deep gold mines reported production in 1917. The Pine Mountain mine in Douglas County, near Villa Rica, was operated by T. H. Aldrich, jr., part of the year but is reported closed down at present. In Lumpkin County gold and silver were produced from deep mines on the Crown Mountain and Lockhart properties. Prospecting was continued at the Royal mine in Haralson County.

The Columbia mine in McDuffie County was operated by the American Venture & Mines Corporation.

It is reported that the Bell Star mine near Woodstock, Cherokee County, is being developed.

The Georgia Copper Co. is opening a mine near Lincolnton, Lincoln County, and expects to begin production about the middle of 1918.

MAINE.

The American Smelting & Refining Co. have reopened the old Douglas mine, at Blue Hill, Me., and treated the siliceous chalcopyrite ore by flotation, making a small production of copper.

MARYLAND.

The New London mine, near Frederick, Md., was operated during 1917 and produced silver-bearing copper ore, and the Liberty Bell mine, near Union Bridge, produced some copper and silver from ore and tailings. Prospect work near Great Falls has been stopped for the present, but it is reported that the project has not been abandoned.

NEW HAMPSHIRE.

The Silver Lake mines, in Carroll County, N. H., were operated in 1917 and produced 3,000 tons of lead and zinc ore, from which 96,000 pounds of lead and 90,100 pounds of zinc were obtained. None of the other metal mines in the State reported operations during that year.

Digitized by Google

NEW JERSEY.

The production of New Jersey is, as usual, confined to the output of the Mine Hill and Stirling mines at Franklin Furnace, Sussex County. There were 720,561 tons of crude ore produced at those mines in 1917, which yielded a total of 239,462,000 pounds of zinc calculated as zinc in oxide and spelter. It should be understood that only part of the zinc ore mined at Franklin Furnace is used directly for the manufacture of spelter. The greater part of this zinc is normally converted into oxide at works located in Pennsylvania.

NEW YORK.

The Northern Ore Co., operating the Brown and White mines, near Edwards, St. Lawrence County, N. Y., was the only producer in the State in 1917. It treated 47,961 tons of zinc-bearing ore, which yielded about 10,384,000 pounds of zinc.

The Old Ellenville mine, Ulster County, is being unwatered by the Empire State Zinc & Copper Co.

NORTH CAROLINA.

The gold, silver, copper, and lead produced in North Carolina in 1917 had a value of $47,447, distributed as follows: Gold, 589.55 ounces, valued at $12,187; silver, 1,110 ounces, valued at $915; copper, 124,991 pounds, valued at $34,123; and lead, 2,583 pounds, valued at $222. Of the gold about 67 per cent was obtained from siliceous gold ores and the remainder from placer deposits. Of the silver, about 97 per cent came from siliceous gold ores and the rest from placers. The gold ores treated yielded an average of $5 a ton in precious metals. The copper was derived from ore and tailings from Ashe and Union counties, which yielded approximately 100 pounds of copper a ton.

As will be seen from the following table, the production of gold fell below the low of 1916, as was to be expected, but the production of silver and base metals increased materially. The most notable feature of the operations in 1917 is the production of lead, which came largely from the dumps of the Silver Hill mine in Davidson County.

Mine production of gold, silver, copper, and lead in North Carolina, 1916–17.

Year.	Number of mines.		Ore sold or treated	Gold.[a]	Silver.[a]	Copper.	Lead.	Total value.
	Placer.	Deep.						
			Short tons.		*Fine ounces.*	*Pounds.*	*Pounds*	
1916	20	6	8,918	$26,237	663	9,800	.....	$29,064
1917	14	7	2,087	12,187	1,110	124,991	2,583	47,447
Increase or decrease, 1917	−6	+1	−1,831	−14,050	+447	+115,191	+2,583	+18,383

[a] Includes placer

Digitized by Google

There were 14 operators of placer mines in North Carolina in 1917, the largest being W. E. Sudlow, at the Biggerstaff and Melton mines, Golden, Rutherford County. Placer gold was won in Burke, Cabarrus, Caldwell, McDowell, Montgomery, and Stanley counties, but the number of operators in each county and their individual production was relatively small. It is possible that some of the gold reported as from placer mines actually was obtained by reworking old dumps and cleaning up abandoned mills.

Seven deep mines were in operation for a part or the whole of the year in Ashe, Cabarrus, Davidson, Montgomery, Randolph, and Union counties. The largest production from deep mines was made by the Ore Knob mine, in Davidson County, but it is reported that work has been stopped.

It is said that new interests are investigating the Pioneer Mill mine in Cabarrus County.

The slag and tailing dumps at the Silver Hill mine, in Davidson County, were reworked, though only small shipments were made owing to car shortage.

The Copper King mine, in Person County, and the Gardner Hill mine, in Guilford County, together with the Seaboard mine, in Halifax County, Va., have been taken over by Baltimore interests and a 50-ton smelter to handle the ores from all of these properties is being built at Virgilina.

Apparently the Rich Cog, Steel, and Reynolds mines are the only properties under development in Montgomery County.

A little gold was won in Rowan and Stanley counties, most of which apparently came from reworking dumps and a little from sluice operations. It is stated, however, that the dumps of the Union mine will be milled in 1918.

The Clinchfield Gold Mining Co. is operating a mine near Logan, Rutherford County. Most of the gold produced in the county is won by placer mining, there being a number of small operators, particularly in Golden Valley.

At the Howie mine, Union County, the new 50-ton cyanide mill was completed and a considerable production of gold and silver made at both the mill and from the ore shipped to the smelter.

PENNSYLVANIA.

The Cornwall iron mines, in Lebanon County, Pa., now operated by the Bethlehem Steel Co., produced a copper concentrate from pyritiferous magnetite ore.

SOUTH CAROLINA.

In 1917 mines in South Carolina produced 52.39 ounces of gold and 3 ounces of silver, having a total value of $1,085, the largest part of which came from deep mines near McCormick, McCormick County, though a small quantity of placer gold was obtained during prospect work near Tamassee, Oconee County.

TENNESSEE.

The mine production of precious metals in Tennessee in 1917 was 257.65 ounces of gold and 99,053 ounces of silver, having a combined value of $86,945, all of which was derived from the copper ores

of Polk County. This is a reduction from the output of gold of 1916, but an increase of 4,352 ounces of silver. No gold or silver ores were treated in the State, nor were the placer deposits of Monroe County operated. There were 589,004 tons of copper ore treated in Polk County, from which 16,033,749 pounds of copper were produced. Tennessee produced about 5,062,000 pounds of lead, which was obtained from mines in Washington and Union counties. The production of zinc in 1917 was 56,995,107 pounds, an increase of 4,139,627 pounds over the output in 1916. Lead and zinc ores were also produced at mines in Claiborne, Jefferson, Knox, Washington, and Union counties. The average content of zinc ore from Tennessee smelted direct in 1917 was 37 per cent, and the milling ore averaged 3 per cent zinc. Lead was produced from lead-zinc ore carrying 3.5 per cent lead.

Mine production of gold, silver, copper, lead, and zinc in Tennessee, 1916–17.

Year.	Number of mines.		Ore sold or treated.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
	Copper.	Lead and zinc.							
			Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	2	6	1,184,821	$5,739	94,701	14,679,794	32,960	52,855,480	$10,764,189
1917	2	5	1,533,983	5,326	99,053	16,033,749	5,061,937	56,995,107	10,712,985
Increase or decrease, 1917	.....	−1	+349,162	−413	+4,352	+1,353,955	+5,028,977	+4,139,627	−51,204

VERMONT.

The Eureka mine, Orange County, Vt., was operated by the Pike Hills Mines Co., which has installed a 100-ton flotation mill.

It is reported that the Ely Copperfield Associates will reopen the old Ely mine at Copperfield, as well as the Orange, Green Mountain, and Walker properties.

VIRGINIA.

The mine production of gold, silver, copper, lead, and zinc in Virginia in 1917 was valued at $510,212, distributed as follows: Gold, 64.97 ounces, valued at $1,343; silver, 4,518 ounces, valued at $3,723; copper, 36,630 pounds, valued at $10,000; lead 1,718,533 pounds, valued at $147,794; zinc, 3,405,420 pounds, valued at $347,352.

Copper ores were mined in the Virgilina district, lead-bearing zinc ores in Spotsylvania and Louisia counties and also in Wythe County, and zinc ores in Russell county. No gold mines were operated in the State during 1917, the gold and silver reported being contained in lead, zinc, and copper ores.

Digitized by Google

Mine production of gold, silver, copper, lead, and zinc in Virginia, 1916–17.

	Number of mines.	Ore sold or treated.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	11	39,262	$885	783	553,800	1,455,844	4,551,237	$847,955
1917	5	35,551	1,343	4,518	36,630	1,718,533	3,405,420	510,212
Increase or decrease, 1917	−6	−3,711	+458	+3,735	−517,170	+262,689	−1,145,817	−337,743

The Seaboard mine, Halifax County, together with several other properties in the Virgilina district, has been taken over by Baltimore interests. A 50-ton smelter is under construction near Virgilina to handle the ores from the consolidated mines.

The Valcooper (Alla Cooper) and Valzinco (Holladay) mines in Louisa and Spottsylvania counties were operated successfully by the Virginia Lead & Zinc Corporation. The ores are handled by a 50-ton mill and flotation experiments are under way. Lead and zinc concentrates are produced.

The Austinville mine was operated by the Bertha Mineral Co., and tailings from the Bertha mine were treated at the Austinville mill, which resulted in a production of lead and zinc concentrates. The Ivanhoe Furnace Co., at Ivanhoe, Wythe County, shipped lead and zinc carbonate ores.

Digitized by Google

TIN.

By ADOLPH KNOPF.

GENERAL STATEMENT.

The metallic tin estimated as recoverable from ore of domestic origin mined in 1917 was 110 short tons, a decrease of 30 short tons from the output of 1916. As in recent years, the bulk of the tin-bearing concentrate was obtained by dredges in Alaska, whose working season is limited by climatic conditions to less than 100 days a year. Part of the concentrate was shipped from Seattle to Singapore to be smelted and part was sent to the smelter at Perth Amboy, N. J.

The tin imported in 1917 as metal and metal in concentrate reached the record quantity of 77,866 short tons, or 57 per cent of the world's output for the year. The metal imported and entered for consumption was 72,166 short tons, and the domestic smelter output was 6,000 tons. The total supply of new tin available for consumption was, therefore, 78,000 tons. It is estimated that an additional 17,500 tons of tin became available by recovery from drosses and waste metals.

The unprecedentedly high prices of tin that prevailed during the latter part of 1917 and that still prevail have stimulated interest in the deposits of tin ore in the United States. References to the most recent published information on these deposits are given on pages 71–72. The known deposits are unfortunately small in number, and but few of these are commercially promising. Governmental stimulation, therefore, is not likely to add significantly to the domestic supply of tin. It is not probable that the country will achieve in 1918 an output much in excess of 200 tons of metallic tin from ores of domestic origin. The largest amount heretofore produced in any one year was 140 tons, or 0.2 per cent of the imports for that year.

The total quantity of tin produced from domestic ore in the United States, exclusive of Alaska, since the beginning of tin mining is 300 tons. Of this output the largest single item is the 135 tons produced in 1891 and 1892 by the Cajalco mine, in southern California, at a time when tin was at one-fourth its present price.

DOMESTIC PRODUCTION AND DEVELOPMENT.

ALASKA.[1]

Alaska produced 171 short tons of stream tin in 1917, a decrease of 61 tons from the preceding year. As this concentrate averaged 60 per cent of metallic tin, the output of recoverable metal is estimated at 100 tons. The York district, 100 miles northwest of Nome,

[1] The writer is indebted to G. L. Harrington, of the U. S. Geological Survey, for first-hand information on recent developments in Alaska.

Digitized by Google

yielded the bulk of the Alaskan output. Two dredges were operated, one working on Buck Creek and the other working on Grouse Creek downstream from the mouth of Buck Creek. There was a decrease in Alaskan shipments, owing largely to the fact that the bulk of the concentrate of one of the two principal operators, the American Tin Dredging Co., was not shipped before the close of the season and can not therefore be marketed before the reopening of navigation late in June, 1918. The York Dredging Co., which is working on Grouse Creek, finds that the concentrate won from the gravels is becoming increasingly heavier in pyrite as operations progress downstream from the confluence of Buck Creek, the source of the placer tin. This change is evidently due to the fact that the pyrite, being of lower specific gravity than cassiterite, has been carried farther downstream from the bedrock source of the minerals, which has been shown to be mainly in the hills at the head of Buck Creek.

The reserves of gravel available for dredging are estimated to be sufficient for five years' operations at the present rate of exhaustion.

In addition to the tin recovered by the dredges, two men, using a string of three sluice boxes, took out a few tons of cassiterite from Iron Creek, a short tributary of Sutter Creek, the principal affluent of Buck Creek. The gravel worked contained about 15 pounds of cassiterite to the cubic yard, but this rich ground has been nearly worked out.

The rest of the Alaskan output of tin was a by-product of gold-placer mining on Sullivan and Woodchopper creeks, in the Hot Springs district, in the sector between Yukon and Tanana rivers.

At the Lost River lode tin mine, which is 15 miles southeast of the mouth of Buck Creek, little more than the annual assessment work was done. Of the few known tin lodes in the United States that hold out some promise of being profitably workable, this lode is among the more encouraging. The lode, called the Cassiterite lode, consists of a soft mineralized granite porphyry dike cut by stringers of cassiterite and wolframite, with which occur minor quantities of pyrite, arsenopyrite, zinc blende, and galena.[1] It has been partly opened by development work for a horizontal distance of 1,420 feet and a vertical distance of 410 feet above creek level.

In examining the concentrates obtained in placer-gold mining in the Yentna district, north of Cook Inlet, J. B. Mertie, of the United States Geological Survey, found that they contain as much as 20 per cent of cassiterite. This is a new locality for tin in Alaska, and the recognition that cassiterite occurs here should lead to systematic prospecting to determine its distribution and bedrock sources.

The total output of tin from Alaska since 1902, when tin mining began, is 867 short tons, almost all of which has been won from placers.

NEVADA.

F. L. Ransome, of the United States Geological Survey, recently made a brief visit to the tin deposits in northern Lander County, Nev., and has furnished the following note on recent developments:

Efforts to find workable deposits of tin ore in place near the Izenhood ranch, north of Battle Mountain, have not proved successful, and no mining was in progress in

[1] Knopf, Adolph, Geology of the Seward Peninsula tin deposits: U. S. Geol. Survey Bull. 358, pp. 49–50, 1908.

Digitized by Google

October, 1917. A shaft 40 feet deep has been sunk in the rhyolite and shows some cassiterite (wood tin) as incrustations on the walls of small unfilled fissures, accompanied by specularite.

Cassiterite is apparently distributed through the rhyolite over an area of several square miles but has nowhere been found in sufficient quantity to be shipped as ore. At the time of visit an examination was in progress to determine whether the alluvial deposits that flank the tin-bearing rhyolite contain enough cassiterite to justify the building of a concentrating mill. Were water abundant and the general operating conditions more favorable, it is not unlikely that portions of the rhyolite itself might be successfully worked by crushing and concentration.

Some small masses extremely rich in cassiterite were found during 1917 in the Majuba Hill copper mine, operated by the Mason Valley Mines Co., in the northern part of the Trinity Range, in Humboldt County, Nev. Unfortunately, this material does not occur in commercial quantities. Under the microscope the material is seen to be an intimate intergrowth of cassiterite, tourmaline, and quartz. Thus it differs widely from the wood-tin ore of northern Lander County and probably belongs to an older epoch of mineralization. It is the first known occurrence of its kind in Nevada and doubtless merits further investigation.

OTHER STATES.

South Dakota.—There was some tin mining in the Black Hills,[1] the main activity being near Hill City, Pennington County, S. Dak. Early in 1917 the American Tin & Tungsten Co. worked the Cowboy mine, milling the ore in the old mill that the Harney Peak Tin Co. had built. Work ceased in April and a labor lien was put on the property by the employees. About 23 tons of concentrate carrying 50 per cent of tin were shipped to Perth Amboy as a result of these operations.

North Carolina and South Carolina.—In the Carolina tin belt some mill-run tests were made on the property of the United States Tin Co. near Lincolnton, N. C. At the Ross mine, near Gaffney, S. C., one man was employed in sluicing hillside wash derived from a tin-bearing pegmatite dike. A set of sluice boxes, without riffles and having a total length of 30 feet, was employed. Even with this crude equipment some cassiterite was profitably saved.[2]

Texas.—The El Paso tin mine, 14 miles north of El Paso, Tex., in the Franklin Mountains, which had been in the hands of receivers for several years, was sold to Davis Bros., of El Paso, late in 1917. This mine was last operated by the El Paso Tin Mining & Smelting Co. in 1910 and 1911, and about 8 tons of high-grade ingot tin was smelted in an oil-fired reverberatory furnace on the property.

SMELTING.

During 1917 the American Smelting & Refining Co.'s plant at Perth Amboy, N. J., produced 6,065 short tons of tin,[3] almost wholly from Bolivian concentrate. At the end of the year the plant was operating at the rate of 10,000 tons of tin a year and will probably produce 14,000 tons in 1918.

[1] Late in the year Messrs. Thomas Varley and R. R. Hornor, of the Bureau of Mines, examined the tin-bearing deposits of the Black Hills in order to determine whether these deposits can supply ore in commercial quantities.

[2] Information from H. G. Ferguson, of the U. S. Geological Survey.

[3] American Smelting & Refining Co. Nineteenth Ann. Rept., for 1917, p. 13, 1918.

Digitized by Google

The Williams Harvey Corporation endeavored to expedite the completion of its tin-smelting plant, which is being built on Jamaica Bay, Brooklyn, N. Y., but was seriously hindered by delay in the receipt of the necessary material. This plant also will smelt Bolivian concentrates. It is now expected that the plant will be ready for operation in July, 1918, and the estimated capacity is 10 tons of tin a day. A one-third interest in the corporation has been sold to Simon I. Patiño, owner of the Salvadora and Huanuni tin mines in Bolivia, thus insuring an adequate supply of concentrate.[1]

During 1917 somewhat less than one-fourth of the Bolivian exports of concentrate were shipped to the United States to be smelted and the remaining three-fourths were shipped to England for treatment. Manifestly it is an uneconomical use of shipping to transport this large quantity of concentrate to England to be smelted and then to ship the tin, or the equivalent in metal smelted from other concentrate, back to the United States, which is by far the world's largest consumer of tin.

Electric smelting was attempted at La Paz, Bolivia, in 1917, and 70 short tons of metal was produced, but many technical difficulties have hampered this pioneer enterprise.

The recently completed smelting plant at Arica, Chile, began operations in February, 1918, with a daily capacity of 15 tons of pig tin, and is expected to attain shortly a capacity of 30 tons. This plant is owned by the Compañía chilena de fundición de estaño (Chilean Tin Smelting Co.), a subsidiary of the Llallagua Tin Co.,[2] whose mines, 42 miles southeast of Machacamarca, Bolivia, supply the concentrate that is smelted.

Before the war a large proportion of the Bolivian concentrate went to Germany to be smelted. In 1912 Germany imported 17,961 metric tons from Bolivia and smelted 15,853 metric tons.[3] In 1913 Germany imported 18,652 metric tons of tin concentrate, of which 16,699 tons came from Bolivia.

IMPORTS.

The total importation of tin in 1917 was 77,866 short tons. This amount is the sum of two quantities—72,166 short tons of tin in bars, blocks, pigs, or grain or granulated, and 5,700 short tons of tin estimated as recoverable (63 ± per cent) from the 9,054 short tons of Bolivian concentrate imported during the year. The imports, as determined from the "general imports" (which in 1917 were slightly less than the tin entered for consumption) came from the following countries:

Tin imported into the United States in 1917.

	Short tons.		Short tons.
Straits Settlements	26,598	Australia	2,872
England	19,840	China	2,461
Dutch East Indies	15,843	Other countries	603
Bolivia (tin in concentrate)	5,700		
Hongkong	3,601		77,518

[1] National Lead Co. Ann. Rept. for 1917, p. 8, 1918.
[2] Commerce Repts., Mar. 23, 1917, p. 1092.
[3] Sonderabdruck aus den Vierteljahrsheften zur Statistik des Deutschen Reichs, Jahrg. 23, Heft I, p. 11, 1914.

Digitized by Google

The real origin of the tin is not wholly disclosed by this table, as the Straits Settlements produce no tin ore themselves but smelt concentrate from the Malay States, Siam, Billiton, and Singkep, South Africa, Australia, and even Alaska, all of which thus becomes Straits tin. The English tin also may be of diverse origin—from Bolivia, Nigeria, Portugal, as well as Cornwall—or may be reexports of Straits tin.

Tin imported and entered for consumption in the United States, 1906–1917.[a]

Year.	Quantity (short tons).	Value.	Year.	Quantity (short tons).	Value.
1906	50,477	$37,447,315	1912	58,016	$50,372,478
1907	41,257	32,074,263	1913	52,329	46,927,213
1908	41,267	28,923,560	1914	47,530	32,881,613
1909	47,662	27,558,546	1915	57,792	38,736,909
1910	52,528	33,913,255	1916	69,085	51,802,232
1911	53,527	43,346,394	1917	72,166	63,860,340

[a] Compiled from the records of the Bureau of Foreign and Domestic Commerce.

Tin ore imported into the United States, 1916–17.

Year.	Quantity (short tons).	Value.
1916	9,304	$4,096,821
1917	9,054	4,743,099

PRICES.

The average price of Straits tin in New York was 61.65 cents a pound for the year, as compared with 43.48 cents for 1916. The course of the market during the year is shown in the following table:

Average monthly prices, in cents per pound, of Straits tin in New York, in 1917.[1]

January	44.19	July	62.60
February	51.37	August	62.68
March	54.36	September	61.68
April	55.91	October	61.85
May	63.30	November	74.42
June	62.09	December [2]	85.35

The average price for the year in London was £237 13s. per ton of 2,240 pounds. The lowest price was £180¾ and the highest was £309.[3]

The course of the average yearly price of tin in New York since 1900 is shown in figure 1, together with the yearly output of tin. The prices are taken from Metal Statistics and the figures for output prior to 1913 from Mines and Quarries (London), Part IV, colonial and foreign statistics. These data have been plotted upon the so-called ratio chart in order that the two curves might be directly compared. On this chart if two curves run parallel they represent

[1] Metal Statistics, 1918, p. 275.
[2] Market strictly nominal December 12–31; 86 cents used for the period as arbitrary basis in computing the month's average.
[3] Quin's Metal Handbook and Statistics, 1918, p. 92.

Digitized by Google

equal percentage rates of change.[1] From figure 2 it will be seen that the fluctuations in the price of tin have been much more violent than the fluctuations in output; that the long-time trend of the production curve shows that the production is slowly increasing (at the rate of 2.5 per cent yearly); that the price of tin is steadily rising, despite the cyclic fluctuations shown; and that the price of tin is rising at a rate somewhat faster than the rate of increase in the world's output of tin.

As the estimate of the world's output of tin in 1917 indicates, the extremely high prices that tin reached in the closing months of the year were not due to shortage of production, as the output probably slightly exceeded that of 1916. They were the results of shortage of



FIGURE 2.—Average yearly prices, in cents per pound, of Straits tin in New York, and world's output of tin, in metric tons, 1900–1917.

shipping, of losses of tin in transit by submarine sinkings, and of restrictions upon the free movement of trade.

The complete blockade of the Central Empires has added 21,000 short tons of tin to the available supply of the rest of the world, 21,000 tons being the domestic consumption of Germany and Austria in 1913.[2] As shown by the rising prices, this additional supply has been easily absorbed, principally by the United States, which now consumes 57 per cent of the yearly output of tin.

WORLD'S OUTPUT.

The world's output of tin in 1917 is estimated to be 147,620 short tons, or a fair increase over that of 1916. The output in the various tin-producing regions from 1913 to 1917 is shown in the accompanying table. The figures given are based in the main on official reports,

[1] Fisher, Irving, The "ratio" chart for plotting statistics: Am. Stat. Assoc. Quart. Pub., vol. 15, p. 597, 1917.

[2] Metallgesellschaft, Statistische Zusammenstellungen, Jahrg. 20, pp. 78, 83, 1914.

Digitized by Google

and represent as near as possible the recoverable metal contained in the "ore" or concentrate obtained during the calendar years. Where the average assay content of the concentrate is given in the original sources, 95 per cent of this assay value has here been used in computing the recoverable content of tin, in order to allow for the loss in smelting.[1]

World's output of metallic tin, 1913–1917, in short tons.

[Recoverable metal in ore and concentrate.]

	1913	1914	1915	1916	1917
Federated Malay States	56,140	54,930	52,380	49,130	44,610
British Protected Malay States	a 2,000	a 3,000	4,600	4,900	5,000
Bolivia [b]	29,500	24,600	24,100	23,500	31,200
Banca [c]	17,560	16,120	15,060	15,940	14,900
Billiton and Singkep [c]	5,840	6,720	7,430	7,480	8,000
China [d]	9,250	7,950	8,820	8,410	13,230
Siam	7,340	7,430	9,400	9,880	9,900
Nigeria	3,250	5,060	5,100	5,680	7,270
Australia	8,990	6,080	6,260	6,120	5,400
Cornwall	5,920	5,660	5,560	5,260	4,600
Union of South Africa	2,260	2,200	2,260	2,100	2,000
Other countries	1,500	1,500	1,500	1,500	2,000
Total in metric tons	149,550 135,700	141,250 128,200	142,470 129,300	139,900 126,900	147,620 133,800

a Estimate.
b Commerce Reports, 1916, p. 973. The figures given there relate to exports of concentrate. The recoverable tin content of the concentrate is here computed on the basis of 60 per cent, which is undoubtedly somewhat low, especially for the exports since 1914. The output for 1917 is computed on the basis of 61 per cent of recoverable tin.
c The official statistics of the Dutch East Indies are given in part for fiscal years ending March 31.
d Exports from all ports (Ricard and Freiwald, Statistics of tin, Feb. 28, 1918).

The countries included under "Other countries" in the table produced in 1913 as follows: India, 340 tons; Japan, 320 tons; Swaziland, 200 tons; Spain, 160 tons; German Southwest Africa, 140 tons; Indo-China, 110 tons; Portugal, 100 tons; German Empire (Kingdom of Saxony), 60 tons [2]; United States, 50 tons; and Italy, 10 tons. A small quantity also was produced in Katanga Province, Belgian Kongo. In 1912 (the last year for which official statistics are at hand), the tin-smelting plant at Graupen, Bohemia, produced only 0.2 ton of tin from concentrate of domestic origin; in the same year 660 tons of tin ore carrying 1.5 per cent of tin was mined, but the bulk of it did not leave the mine from which it was produced.[3] The main change since 1913 in the production of the countries supplying minor quantities of tin is that in 1917 Portugal has probably taken the leading position.

The outstanding features of the world's production of tin in 1917 are the continued decrease in output of the Federated Malay States and the remarkable increase of production shown by Bolivia, which more than counterbalances the decrease in the output of Federated Malay States.

[1] The accuracy of statistics of output of metallic tin based on records of production is about 1 in 70, but this does not prevent statistical organizations, with few exceptions, from giving figures that are apparently significant to the last digit. This procedure implies for the figures of Bolivian output, for example, an accuracy of 1 in 25,000, but as a matter of fact neither the average assay content of the Bolivian concentrate nor the smelting loss are accurately known, and 60 per cent is customarily assumed to represent the equivalent in fine tin.
[2] Output for the year 1912 (Jahrb. Berg. u. Hüttenwesen im Königreiche Sachsen, Jahrg. 1913, pp. B 37, B 63). The output for 1913 was 190 tons of tin concentrate carrying about 40 tons of recoverable tin (Glückauf, Jahrg. 51, p. 117, 1915).
[3] Statistik des Bergbaues in Oesterreich, 1912, pp. 88–89, 1913.

Digitized by Google

The Federated Malay States[1] have long been the premier tin field, yielding as much as 50 per cent of the world's yearly output. They attained their greatest output in 1904, with 58,300 tons, though this output was nearly reached again in 1913, but since 1913 the production has been declining at an increasing rate. By 1917 the production had declined to 31 per cent of the world's total. This decline is attributed in part to a decrease in the labor supply, 224,804 laborers having been engaged in tin mining in 1913 and 138,056 in 1916. The output per laborer during this period has increased, however, from 0.25 ton a year to 0.36 ton, an increase caused in part by the installation of large hydraulic plants and dredges. Possibly the increase is due in part also to more continuous employment, but the statistics are not full enough to attempt to analyze them more closely. The more fundamental reason for the declining production is that the richer, more easily worked deposits are approaching exhaustion, that expensive installations will be necessary to work the lower-grade deposits profitably, and that restraining works will be required to impound the tailings in order to prevent damage to agricultural interests.

In 1914 mines under Chinese management produced about 76 per cent of the total output of the Federated Malay States; in 1915 the proportion had decreased to 72 per cent. At the beginning of 1915 three dredges were at work, but by the end of the year the number had increased to 10, which were capable of handling a total of 30,000 cubic yards a day. They recovered 3,117 tons of concentrate, equivalent to 2,180 tons of tin. In 1916 the number of dredges had further increased to 14. The largest dredging operator is Malayan Tin Dredging (Ltd.), which during the fiscal year 1916–17 worked 3,141,300 cubic yards of gravel. From this gravel 976 short tons of cassiterite concentrate were obtained, an average of 0.62 pound to the cubic yard, equivalent to 0.43 pound of metallic tin to the cubic yard. The profit for the year was £32,353, from which dividends of £24,200 were paid.[2]

It is not generally recognized that the Federated Malay States have become an important producer of lode tin and now rank next to Cornwall, the second leading country. In 1915 the Federation's output of lode tin was 3,730 short tons,[3] or 7 per cent of its total output of tin. The bulk of the world's tin won from lodes comes from Bolivia, Cornwall, the Federated Malay States, South Africa, and Australia, and in 1917 it amounted to about 42,000 short tons. Consequently, 31 per cent of the tin produced in 1917 came from lodes and 69 per cent from placers. In 1916 these proportions were 27 per cent and 73 per cent, respectively.[4]

The world's production of tin in 1916 is shown in Plate I. The locations of the centers of production in the countries enumerated in the table are given, except that in the illustration the outputs of the Federated Malay States, of the British Protected Malay States, and of Siam (all of which comes from the Siamese Malay States) have been added together and accredited to Malaya.

[1] Federated Malay States Mines Dept. Repts. for 1914, 1915, and 1916.
[2] Mining Jour. (London), vol. 119, p. 780, 1917.
[3] Federated Malay States Mines Dept. Rept. for 1915, pp. 11, 12, 13, 1916.
[4] The official figures for the lode output of the Federated Malay States, which were not available to the writer in 1917, have allowed him to refine the rough estimate given in the chapter on tin in 1916 (U. S. Geol. Survey Mineral Resources, 1916, pt. 1, p. 620, 1917).

Digitized by Google



98189°—M B 1917, PT 1. (T

Digitized by Google



Digitized by Google

In 1917 almost exactly 50 per cent of the world's output of tin was produced within the British Empire.

PUBLICATIONS.

The following list includes the more recent publications relating to tin deposits in the United States. The Survey publications, except those to which a price is affixed, may be obtained free by applying to the Director, United States Geological Survey, Washington, D. C. The priced publications may be purchased from the Superintendent of Documents, Washington, D. C. Those marked "Exhausted" and the other publications can be consulted at the large public or university libraries of the country.

COLLIER, A. J., Tin ore at Spokane, Wash.: U. S. Geol. Survey Bull. 340, pp. 295–305, 1908. 30c.

The tin ore is cassiterite, which is apparently an original constituent of pegmatite. About 125 tons, containing 4 per cent of metallic tin, were extracted.

DARTON, N. H., U. S. Geol. Survey Geol. Atlas, Sundance folio (No. 127), 12 pp., 1905. Exhausted.

Gives a geologic map and structure sections of the Tinton (Nigger Hill) tin-bearing area of the northern Black Hills. The deposits are briefly described.

EAKIN, H. M., A geologic reconnaissance of a part of the Rampart quadrangle, Alaska: U. S. Geol. Survey Bull. 535, pp. 37–38, 1913. 20c.

Cassiterite occurs in gold placers and is recovered as a by-product of the gold placer mining.

——— Tin mining in Alaska: U. S. Geol. Survey Bull. 622, pp. 81–94, 1915.

A concise but full description of the geology of the Alaskan tin deposits, both lode and placer, and of the condition of the tin-mining industry. 30c.

FAIRBANKS, H. W., The tin deposits at Temescal, southern California: Am. Jour. Sci., 4th ser., vol. 4, pp. 39–42, 1897.

The tin deposits are at Cajalco Hill, near Corona, Riverside County, in southern California. The ore occurs in irregular shoots in quartz-tourmaline veins inclosed in granite. The principal vein was opened to a depth of 180 feet by two shafts 300 feet apart. The ore milled averaged 5 per cent of cassiterite.

FERGUSON, H. G., Tin deposits near Irish Creek, Va.: Virginia Geol. Survey Bull. 15–A, pp. 1–19, 1918.

The tin ore occurs in quartz veins, which are inclosed in a granite of a peculiar type, a hypersthene granodiorite. The ore probably forms shoots of variable size and content of tin, but the present condition of the workings and the extent of the developments are such as not to afford conclusive evidence on these features. The deposits are considered promising and to merit new exploration.

GRATON, L. C., Reconnaissance of some gold and tin deposits in the southern Appalachians: U. S. Geol. Survey Bull. 293, 134 pp., 1906. 15c.

The tin ore of the Carolinas occurs as an original constituent of pegmatite dikes. Detailed descriptions of the deposits are given.

HESS, F. L., Tin, tungsten, and tantalum deposits of South Dakota: U. S. Geol. Survey Bull. 380, pp. 131–163 (tin, pp. 134–149), 1909. 40c.

Describes the tin deposits of the Black Hills. The ore occurs in small shoots in pegmatite dikes and quartz veins.

HESS, F. L. and EVA, Bibliography of the geology and mineralogy of tin: Smithsonian Misc. Coll., vol. 58, No. 2, 408 pp., 1912.

Is an exhaustive bibliography of the geology, mineralogy, mining, milling, metallurgy, history, and statistics of tin.

HESS, F. L., and GRATON, L. C., The occurrence and distribution of tin: U. S. Geol. Survey Bull. 260, pp. 161–187, 1905. Exhausted.

Is a concise account of the geologic occurrence and distribution of tin deposits throughout the world.

INGALLS, W. R., Mineral Industry, vol. 5, p. 587, 1897.

Describes briefly the metallurgical operations at the Temescal or Cajalco Hill tin mine, in southern California. The concentrate, which averaged 65 per cent of tin, was smelted in a Cornish reverberatory furnace, California oil being used for fuel and New Mexico coal for reducing agent. The tin smelted was of good quality, and 135 tons were produced before the mine shut down [in September, 1892].

Digitized by Google

JOHNSON, B. L., Occurrence of wolframite and cassiterite in the gold placers of Deadwood Creek, Birch Creek district, Alaska: U. S. Geol. Survey Bull. 442, pp. 246–250, 1910. 40c.

The gold-bearing gravels average 1 to 2 pounds of concentrate (chiefly wolframite and cassiterite, with some magnetite and garnet).

KEITH, ARTHUR, and STERRETT, D. B., Tin resources of the Kings Mountain district, North Carolina and South Carolina: U. S. Geol. Survey Bull. 660, pp. 123–146, 1917 (Bull. 660–D).

Describes the geology of the Carolina tin belt and the tin deposits, except some near Lincolnton, N. C. The development work done to date is described.

KNOPF, ADOLPH, Geology of the Seward Peninsula tin deposits: U. S. Geol. Survey Bull. 358, 72 pp., 1908. 15c.

The geology and tin deposits of the York district and of Ear Mountain, both in the western part of Seward Peninsula, Alaska, are described in detail.

——— Tin ore in northern Lander County, Nev.: U. S. Geol. Survey Bull. 640, pp. 125–138, 1916. 30c.

The recently discovered lode and alluvial tin deposits are described. The lode tin ore consists of wood tin associated with specular hematite, chalcedony, lussatite, tridymite, and opal. The veins occur in rhyolite flows of middle Tertiary age.

RICHARDSON, G. B., Tin in the Franklin Mountains, Tex.: U. S. Geol. Survey Bull. 285, pp. 146–149, 1906. Exhausted.

——— U. S. Geol. Survey Geol. Atlas, El Paso folio (No. 166), pp. 9–10, 1909. To be obtained from the Geological Survey for 5c.

Narrow quartz veins carrying cassiterite traverse post-Carboniferous granite.

SCHALLER, W. T., Cassiterite in San Diego County, Cal.: U. S. Geol. Survey Bull. 620, pp. 351–354, 1916. 30c.

A pocket of cassiterite crystals was found in a pegmatite dike.

UMPLEBY, J. B., Geology and ore deposits of Lemhi County, Idaho: U. S. Geol. Survey Bull. 528, pp. 74, 76, 1913. 40c.

Some wood tin has been found in the gravels of Silver and Panther creeks.

Digitized by Google

SILVER, COPPER, LEAD, AND ZINC IN THE CENTRAL STATES.

(MINES REPORT.)

By J. P. DUNLOP and B. S. BUTLER.

INTRODUCTION.

By J. P. DUNLOP.

The following is an account of the production of silver, copper, lead, and zinc in 1917 by the mines of the Central States, including Arkansas, Illinois, Kansas, Kentucky, Michigan, Missouri, Oklahoma, and Wisconsin. The territory thus embraced lies in the great interior valley province of the United States which extends from the Appalachian system to the Rocky Mountain front, excluding the Black Hills. Most of the mines are developed in the Paleozoic sedimentary rocks of this province, but the copper range of northern Michigan comprises lavas and intercalated sediments of pre-Cambrian age.

The statistics of production in these States have been compiled by the United States Geological Survey from confidential reports by each mine in operation and represent the quantity of metals recovered or paid for in the ore that was treated or sold during the year.

The method of marketing and recording the mine output in the lead and zinc regions of the United States differs from that employed in the Western States. In the Western States the miner usually sells his ore according to the assay content of metal at a certain price per unit. In the lead and zinc regions of the Central States, however, where the material sold is principally concentrates,[1] payment is made according to a basis price for a certain quality of concentrates. The details of this method are given in the pages devoted to Missouri in this report for 1914. The figures reported to the Survey by producers represent the quantity and assay content of concentrates sold and the amount received in payment. The total metal produced is calculated from the first two of these items.

The operators in Michigan report the quantity of concentrates produced and the actual recovery of copper from concentrates smelted.

In any year the mines may produce more or less concentrates than are smelted during the same period. The copper content of concentrates produced but not smelted during the year has been estimated on the basis of the average copper recovery per ton for the year of the company producing it.

[1] In local usage the ore as mined is called "dirt" and the concentrates are classed as "ore." Where the capacity of a concentrating plant is given, such capacity is to be understood as based on a 10-hour shift unless otherwise stated.

Digitized by Google

In order to expedite the preparation and the printing of this report for the year 1917, much of the information relating to individual properties given under the district reviews for the various States has been eliminated. All essential data formerly given under the district reviews are included in the State reviews.

TENOR OF LEAD AND ZINC ORES OF THE CENTRAL STATES.

Much of the ore mined in the Western States is crude smelting ore; that is, it can be smelted directly without preliminary concentration. All but a very small portion of the ore from the Central States is of such tenor that it requires concentration. The only fair basis for comparison of the relative magnitude of mining operations in different States is that of quantity of crude ore, or "dirt," as it is usually called in the lead and zinc regions of the Central States. In the Joplin and upper Mississippi Valley regions the number of cans of ore hoisted is usually recorded and the approximate weight of the cans is generally known. Thus each company knows, in a general way, about what percentage of concentrates the run of mine is yielding. Knowing the total production of concentrates and the average yield of concentrates from crude ores, one can arrive at a close estimate of the crude ore raised. Only the actual operating companies have the data, however, and it was the practice of the Survey, in order to shorten the list of producers as much as possible, to send requests only to the owners of the mining land or the companies holding first leases and to depend upon them to report the whole production of the tract. Since 1911 not only the first lessees of the land have reported to the Survey, but also most of the sublessees have given data regarding both concentrates produced and "dirt" or ore milled. The tables of tenor of ore which follow in the sections devoted to the respective States show the comparative percentages for the last two years.

In Kentucky and southern Illinois the lead and zinc concentrates are recovered as by-products in the concentration of the fluorspar which they accompany, and it was not possible to make calculations of the metal content of the crude ore raised.

Tenor of copper, lead, and zinc ores of Central States, 1915–17.

State.	1915		1916		1917	
	Crude ore.	Metal content.[a]	Crude ore.	Metal content.[a]	Crude ore.	Metal content.[a]
	Short tons.	*Per cent.*	*Short tons.*	*Per cent.*	*Short tons.*	*Per cent.*
Arkansas	110,000	3.31	249,000	3.15	203,600	3.89
Illinois (northern)	316,000	2.35	288,100	1.60	327,340	1.81
Iowa					1,000	
Kansas	709,400	2.42	774,400	1.98	903,400	2.82
Michigan	12,334,700	1.07	12,364,114	1.08	12,400,723	1.03
Missouri	[b]15,573,700	2.32	[b]18,664,024	2.18	17,024,000	2.24
Oklahoma	891,800	2.68	1,406,900	3.13	3,523,200	3.45
Wisconsin	1,934,000	2.77	3,066,500	2.36	3,014,800	2.57
	31,969,600		36,813,038		37,398,063	

[a] The percentages given in this column represent the metal content of the ore in so far as it is recovered in the concentrates. In Michigan the metal so recovered is copper, in the other Central States the metals are lead and zinc, the relative proportions of which are shown in the table on another page and in the tables of tenor of ore given in the sections devoted to the respective States.

[b] A small quantity of copper ore included.

Digitized by Google

This table shows that from the copper, lead, and zinc mines of the Central States an increase of about 585,000 short tons of ore was treated in 1917, following an increase of 5,000,000 tons in 1916. The production of ore from the copper mines of Michigan increased only 36,000 tons, and the production of ore in Missouri decreased more than 1,640,000 tons, of which decrease 800,000 tons was due to the "sheet ground" mines. The mines of the disseminated lead district in southeastern Missouri increased their output about 420,000 tons. Other States which had a slightly decreased output of lead and zinc ore in 1917 were Arkansas and Wisconsin. The increase in 1917 in the other States was as follows: Oklahoma, 150 per cent; Kansas, 17 per cent; and Illinois, 14 per cent.

The low average tenor of the metal content of all crude ore mined in the Central States in 1917 is best shown by the fact that the average value of the total recoverable metal content was only $4.85 a ton of crude ore treated and that this value is $0.13 more than it was in 1916. The 24,997,340 tons of zinc, lead, and lead-zinc ores treated in the Central States in 1917 yielded lead and zinc concentrates which sold for $77,597,763, so that the mine operators realized an average of $3.10 a ton of ore mined and treated, against $2.68 a ton of ore realized in 1916. The increase was entirely in the value of the lead in the ores mined, for the average value of the zinc concentrates decreased in 1917 and there was an increase in the cost of labor, powder, fuel, and other supplies.

PRODUCTION.

The total value of the mine production of silver, copper, lead, and zinc in the Central States in 1917 was $180,249,464, an increase of $6,470,474, or about 4 per cent, compared with the value for 1916. The total value of the production of these metals for the years 1907 to 1917, inclusive, was $993,579,265, of which $422,221,935 was for copper, $341,861,422 for zinc, $226,145,624 for lead, and $3,350,284 for silver. Only in 1915 and 1916 has the value of the recoverable zinc exceeded that of copper.

SILVER.

The production of silver in the Central States in 1917 was 757,323 fine ounces, which, at the average price of 82.4 cents per fine ounce (16.6 cents higher than in 1916), was valued at $624,034, as compared with 852,380 fine ounces, valued at $560,866, in 1916. Nearly all the silver that is produced in the Central States is recovered incidentally in the production of other metals. Of this production 688,551 ounces came from the copper lodes of Michigan, a decrease of 28,089 ounces. About 25 per cent of the concentrates from lead ores mined in southeastern Missouri was desilverized and yielded nearly all the silver from that State recovered in 1917, and a small output of silver was also derived from copper ore and from copper concentrates recovered in dressing lead ores. The total recovery of silver from Missouri amounted to 61,586 ounces.

The lead-zinc-fluorspar deposits of the Kentucky-Illinois field also carry silver, and from the lead concentrates derived from Illinois 7,186 ounces of silver were recovered, an increase of 1,502 ounces.

Digitized by Google

COPPER.

The mine production of copper in the Central States in 1917 was from Michigan and Missouri, the first-named State, as in other years, contributing nearly the entire output, which amounted to 256,075,141 pounds. The copper production of Michigan in 1917 was 255,710,128 pounds, which, at the average sales price of 27.3 cents a pound, was valued at $69,808,865, as against a yield of 273,692,525 pounds, valued at $67,328,361, in 1916. The copper produced in Missouri in 1917, amounting to 365,013 pounds, valued at $99,649, was derived mainly from concentrates recovered in dressing the lead ores of southeastern Missouri, but a small part came from ore carrying copper and silver, which was shipped from the Racola mine in Washington County.

The total mine production of copper from Michigan and Missouri in 1917 was 18,003,584 pounds less than in 1916 and was about 21,000,000 more than the output of any other year, other than 1916, since 1907, when these figures were first compiled.

LEAD.

The mine production of lead in the Central States in 1917 was 269,656 short tons, which, rated at the average sales price for all grades for the metal for the year of 8.6 cents a pound ($172 a ton), was valued at $46,380,832, as compared with 251,405 short tons, valued at $34,693,890, in 1916. The output of lead increased 18,251 tons in 1917, and the value increased $11,686,942. In 1917 Missouri produced 87 per cent of the yield of lead in the Central States, and the recoverable lead content of galena and lead carbonate concentrates mined in Missouri in 1917 equaled 36.6 per cent of the refined primary lead recovered in the United States from domestic ore. Of the total output of lead in Missouri the "disseminated lead" district of southeastern Missouri produced 204,255 tons, an increase of 2,623 tons, again exceeding the yield from the Coeur d'Alene district of Idaho and retaining first place in production of lead in the United States. Southwestern Missouri was the next largest producing district in the Central States, with an output of 29,611 tons, or 1,845 tons less than in 1916. The Oklahoma production increased from 12,115 tons in 1916 to 26,358 tons in 1917, and the output of the Miami district in 1918 will exceed that of all regions other than southeastern Missouri.

The output of lead in 1917 from mines in Kentucky was less and that from mines in Arkansas, Illinois, Wisconsin, Iowa, and Kansas was considerably greater than it was in 1916. The total production of lead from mines in the southern Illinois-Kentucky region, Arkansas, Kansas, and the upper Mississippi Valley region amounted to only 3.5 per cent of the output of the Central States.

ZINC.

The production of zinc in the Central States in 1917, based on mine returns with a deduction for separating and smelting losse, was 310,471 short tons, valued at $63,336,084. The value is computed at 10.2 cents a pound (spelter $204 a ton), the average sales price reported by the smelters for all grades of the metal.

The output in 1917 was the largest recorded yield from mines in the Central States, exceeding that of the year 1916 by 45,170 tons in quantity. The value, notwithstanding the large increase in quan-

Digitized by Google

tity, decreased $7,764,784. The production of spelter in the Central States was about 53 per cent of the total production of primary spelter from domestic ores in the United States in 1917.

The State of Missouri, with a decrease in output of 23,042 tons, was again in 1917 much the largest producer of zinc in the United States. Its production was 132,918 tons, against 155,960 tons in 1916. Wisconsin produced 59,742 tons in 1917, against 56,803 tons in 1916. Arkansas decreased in output from 6,815 tons to 6,691 tons, Kentucky from 1,096 tons to 751 tons. The production in Oklahoma increased from 28,754 tons in 1916 to 85,835 tons in 1917, or nearly 200 per cent. The output of zinc from Oklahoma in 1918 will doubtless exceed that of Missouri.

The production of zinc from Kansas mines increased from 12,448 tons in 1916 to 20,249 tons in 1917, and the mines located in northern Illinois produced 4,267 tons, an increase of 863 tons.

SUMMARY OF PRODUCTION BY STATES.

Mine production of silver, copper, lead, and zinc in the Central States in 1917.

State.	Silver.		Copper.	
	Quantity.	Value.	Quantity.	Value.
	Fine ounces.		*Pounds.*	
Illinois	7,186	$5,921		
Michigan	688,551	567,366	255,710,128	$69,808,865
Missouri	61,586	50,747	365,013	99,649
Total, 1916	757,323	624,034	256,075,141	69,908,514
	852,380	560,866	274,078,725	67,423,366

State.	Lead.		Zinc		Total value.
	Quantity.	Value.	Quantity.	Value.	
	Short tons.		*Short tons.*		
Arkansas	382	$65,704	6,691	$1,364,964	$1,430,668
Illinois	1,439	247,508	4,267	870,468	1,123,897
Iowa	34	5,848	18	3,672	9,520
Kansas	3,025	520,300	20,249	4,130,796	4,651,096
Kentucky	123	21,156	751	153,204	174,360
Michigan					70,376,231
Missouri	234,156	40,274,832	132,918	27,115,272	67,540,500
Oklahoma	26,358	4,533,576	85,835	17,510,340	22,043,916
Wisconsin	4,139	711,908	59,742	12,187,368	12,899,276
Total, 1916	269,656	46,380,832	310,471	63,336,084	180,249,464
	251,405	34,693,890	265,301	71,100,868	173,778,990

LEAD AND ZINC PRODUCTION, BY REGIONS.

The productive lead and zinc territory in the Central States naturally falls into seven regions, three of which are not limited to any single State. For statistical purposes the tables showing the production of lead and zinc by States are necessary and are so given. For practical purposes, however, it is desirable to compile the production by the natural regions irrespective of State lines.

The seven regions are, in order of importance of output, (1) the Joplin region, comprising the district in southwestern Missouri, southeastern Kansas, and northeastern Oklahoma; (2) southeastern Missouri, containing the great disseminated lead deposits; (3) the upper Mississippi Valley region, including all the lead and zinc mines

Digitized by Google

in southwestern Wisconsin, Iowa, and northwestern Illinois; (4) northern Arkansas; (5) the Kentucky-Illinois fluorspar region in southern Illinois and northern Kentucky; (6) central Missouri; (7) the Arbuckle Mountain region in southern Oklahoma.

The southeastern Missouri region produced about 75 per cent of the lead output of the Central States and about 32 per cent of the production of primary lead recovered from domestic ore smelted or refined in the United States in 1917. The Joplin region produced 22 per cent of the lead and 77 per cent of the zinc of the Central States in 1917, and was much the largest producer of zinc in the United States, yielding about 41 per cent of the total spelter production from domestic ores in 1917, as against 35 per cent in 1916. The upper Mississippi Valley region produced 1.7 per cent of the lead and 20.6 per cent of the zinc in the Central States in 1917. The production of zinc in the northern Arkansas region amounted to about 2.1 per cent of that of the Central States in 1917.

The lower zinc content of the zinc concentrates produced in the upper Mississippi Valley region is clearly indicated by the fact that notwithstanding that the mines in the region yielded about 34 per cent of the total output of zinc concentrates of all classes the recoverable zinc content of such concentrates was only about 20.6 per cent of the recoverable zinc from mines in the Central States.

Mine production of lead and zinc in the Central States in 1917.

Region.	Concentrates.				
	Lead.[a]		Zinc.[b]		Total value.
	Quantity (short tons).	Value.	Quantity (short tons).	Value.	
Joplin	75,744	$7,638,502	460,662	$31,126,468	$38,764,970
Southeastern Missouri	306,473	30,070,995	479	23,489	30,094,484
Upper Mississippi Valley[d]	6,375	615,857	244,497	7,149,954	7,765,811
Northern Arkansas	474	47,593	17,969	708,409	756,002
Kentucky-southern Illinois	1,380	133,931	2,299	78,368	212,299
Arbuckle Mountain, Oklahoma	.....	.....	144	4,197	4,197
Total, 1916	390,446	38,506,878	726,050	39,090,885	77,597,763
	371,753	26,070,323	626,089	39,311,185	65,381,508

Region.	Metal.				
	Lead.		Zinc.		Total value.
	Quantity (short tons).	Value.	Quantity (short tons).	Value.	
Joplin	58,994	$10,146,968	238,768	$48,708,672	$58,855,640
Southeastern Missouri	204,545	35,181,740	188	38,352	35,220,092
Upper Mississippi Valley[d]	4,767	819,924	64,027	13,061,508	13,881,432
Northern Arkansas	382	65,704	6,691	1,364,964	1,430,668
Kentucky-southern Illinois	968	166,493	751	153,204	319,700
Arbuckle Mountain, Oklahoma	.....	.....	46	9,384	9,384
Total, 1916	269,656	46,380,832	310,471	63,336,084	109,716,916
	251,405	34,693,890	265,301	71,100,868	105,794,758

[a] Includes both galena and lead carbonate concentrates.
[b] Includes sphalerite, zinc carbonate, and zinc silicate concentrates.
[c] Includes a small production from the central Missouri region.
[d] Includes Iowa, northern Illinois, and Wisconsin.

Digitized by Google

The volume of Mineral Resources for 1914 contains brief reviews of the history of lead and zinc mining in the Central States, the yearly production of each State for the period 1907 to 1914, inclusive, and historical notes and estimates of the total production of lead and zinc produced in each State before 1907. The separate chapter entitled "Silver, copper, lead, and zinc in the Central States in 1914" can be obtained on application to the Director, United States Geological Survey, Washington, D. C.

ARKANSAS.

By J. P. DUNLOP.

PRODUCTION.

The value of the recoverable lead and zinc from Arkansas mines, which had increased from $801,754 in 1915 to $1,863,956 in 1916, was $1,430,668 in 1917. The decrease was caused almost entirely by the low price of zinc.

The production of galena increased considerably, while that of sphalerite decreased, though the total yield of these ores was small as compared with that of other regions. The shipments of zinc carbonate and zinc silicate concentrates in 1917 were slightly greater than in 1916.

Mine production of lead and zinc in Arkansas, 1907–1917.[a]

Year.	Ores.						Metal content.			
	Lead concentrates (galena).		Zinc concentrates.				Lead.		Zinc.	
			Sphalerite.		Silicate and carbonate.					
	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.
1907	15	$800	538	$15,233	663	$16,210	12	$1,272	474	$55,982
1908	18	985	516	18,270	939	21,469	15	1,260	605	56,870
1909	30	1,800	896	33,948	98	2,736	24	2,064	510	52,080
1910	80	3,714	1,857	74,136	128	2,641	63	5,544	994	107,352
1911	80	4,321	1,407	40,425	183	4,239	64	5,760	664	75,996
1912	39	2,180	1,419	56,235	462	11,231	31	2,790	748	103,224
1913	23	1,179	594	16,916	680	15,050	18	1,584	478	53,536
1914	52	2,408	743	19,406	1,143	25,187	41	3,198	608	62,016
1915	79	4,961	606	41,341	7,925	408,079	63	5,922	3,209	795,832
1916	339	28,097	1,670	112,726	16,609	940,224	272	37,536	6,815	1,826,420
1917	474	47,593	916	57,824	17,053	650,585	382	65,704	6,691	1,364,964

[a] In calculating the metal content of the ores from assays allowance has been made for smelting losses of zinc but not of lead. In comparing the values of ore and of metal it should be borne in mind that the value given for the ore is that actually received by the producer, whereas the value of the lead is calculated from the average sales price of all grades and that of zinc from the average sales price of all grades reported by the smelters.

Digitized by Google

Tenor of lead and zinc ore and concentrates produced in Arkansas in 1916 and 1917.

		1916	1917
Total crude ore	short tons	249,000	203,600
Total concentrates in crude ore:			
Lead	per cent	0.13	0.23
Zinc	do	7.35	8.82
Metal content of crude ore:			
Lead	do	.11	.19
Zinc	do	3.04	3.70
Average lead content of galena concentrates	do	80.2	80.5
Average zinc content of sphalerite concentrates [a]	do	57.1	58.4
Average zinc content of zinc silicate and carbonate [a]	do	39.9	40.5
Average value per ton:			
Galena concentrates		$82.88	$100.41
Sphalerite concentrates		$67.50	$63.13
Zinc silicate and carbonate		$56.61	$38.15

[a] Includes some mixed carbonate and sphalerite.

NORTHERN ARKANSAS.

Considerable prospecting and some mining were carried on in northern Arkansas for many years, but the present development has mainly been accomplished since 1899, when there was a great rush to that field. The mines are principally in Boone and Marion counties and in the adjoining portions of Searcy and Newton counties, though there are also numerous mines and prospects in Baxter, Izard, Sharp, Lawrence, and other counties to the east, and deposits have been worked in Washington and Sevier counties, on the extreme western border of the State.

The ores are galena, sphalerite, and smithsonite, and the concentrates produced are generally of high grade and free from or very low in iron or lime. The sphalerite has frequently assayed 2 or 3 per cent above the price basis of 60 per cent metallic zinc content. The sphalerite and smithsonite are shown by analysis to contain appreciable quantities of cadmium, especially in a yellow variety of smithsonite, known locally as "turkey fat," which shows as high as 0.8 per cent of cadmium. The ore bodies occur in fissures or crevices, in fault breccias, and in solution breccias. The ore deposits are for the most part found in limestone of early Ordovician age, but some also are found in the Boone limestone of Mississippian (lower Carboniferous) age.

The number of concentrating plants that treated sphalerite was less than in 1916 and all the plants were operated intermittently. Some mixed sphalerite and zinc carbonate concentrates were sold and these shipments are partly given under sphalerite.

The estimated quantity of ore treated decreased from 249,000 tons in 1916 to 203,600 tons in 1917 and the average recovery of concentrates from such ore increased from 7.48 per cent to 9.05 per cent. This increase was the natural result of the decreased quantity of sphalerite ores and also of carbonate ores milled, especially in the Rush and other districts in Marion County.

Although there were several large operators, such as the J. C. Shepherd Mining Co., Morning Star Mining Co., Howard Mining Co., Lon Brown, Gloria Mining Co., and Lucky Dog Mining Co., in 1917, a large part of the production was from mines worked on a small scale. This is best shown by the fact that the total yield of all

Digitized by Google

classes of concentrates, amounting to 18,443 tons, was derived from more than 150 mines or prospects.

The shipments of sphalerite, 916 tons, were made from 14 mines, and the largest shipment from any one mine was less than 200 tons. It is probable that the unsatisfactory condition of the market for zinc ore will result in a decreased output from Arkansas in 1918, although the development made and the mills erected in 1917 would, under normal conditions, result in a very much larger output.

Some improvement was made on the wagon roads in the mining districts, but long wagon hauls over poor roads still hamper mining in many sections.

The Cowan Barrens Development Co., which is prospecting by means of churn drilling the plateau lying between Rush and Yellville, is reported to have located good bodies of ore lying at depths between 120 and 200 feet. Three drill rigs are being used. The operators are very optimistic over the result of the drilling done and state that thorough tests will be made so that outside capital can be invested on a large scale with a reasonable assurance of a large supply of ore.

The Rush district in Marion County was in 1917, as in 1916, the largest producer of zinc concentrates, and Marion County produced more than half of all zinc concentrates from Arkansas. Boone, Newton, and Searcy counties had a larger production in 1917 than in 1916, and Searcy County with fewer mines in operation was a larger producer than Boone County. The assistance rendered to the Survey in obtaining statistics by R. W. Willett and J. H. Hand, of Yellville, and by other mine operators is gratefully acknowledged. It is to be regretted that many operators of mines in Arkansas, particularly the owners of small prospects, do not keep an accurate record of the quantity of dirt or ore mined and treated, the quantity of lead and zinc concentrates sold, the average assay of each class of concentrates, and the actual selling value of concentrates.

The shipments of lead concentrates from mines increased from 339 tons in 1916 to 474 tons in 1917. The production of sphalerite concentrates was 916 tons, or 754 tons less than in 1916, and the value decreased from $112,726 in 1916 to $57,824 in 1917. The sales of zinc carbonate concentrates increased in quantity from 16,609 tons in 1916 to 17,053 tons in 1917, but the value decreased from $940,224 to $650,585. The recoverable lead content of galena concentrates shipped amounted to 382 tons, valued at $65,704, and the recoverable zinc from zinc concentrates was 6,691 tons, valued at $1,364,964, in 1917. Mines in Marion, Boone, Newton, Searcy, Baxter, and Lawrence counties produced all the zinc concentrates shipped in 1917, and mines in Newton County produced 467 tons of the total shipments (474 tons) of galena concentrates. Mines in Lawrence County shipped 21 tons of sphalerite and 190 tons of zinc carbonate in 1917. The output was made by the Lucky Dog mill from dirt obtained from the Hoppe mine, the Louisiana-Arkansas Mining & Milling Co., the Mint Land Co., and the Raney mine now owned by the Seewald King Co.

Considerable development work was done at prospects in Baxter County and a crusher and hand jigs were installed on the Shiras land. The only zinc concentrates shipped in 1917 was a small quantity of hand cobbed carbonate from the Temple mine in the Buffalo district.

Digitized by Google

The shipments from Boone County were 3 tons of galena, 159 tons of sphalerite, and 3,458 tons of zinc carbonate. The shipments of zinc carbonate, which were about 900 tons more than in 1916, were mainly from mines in the vicinity of Zinc, especially from lessees on the Coon Hollow and Almy lands. Most of the sphalerite was derived from the K. M. mine of the Continental Mining Co., 3½ miles southeast of Harrison.

From mines principally in the Cave Creek district, in the eastern part, and the Ponca and Jasper districts, in the western part of Newton County, there were shipped 467 tons of galena, 16 tons of sphalerite, and 2,134 tons of zinc carbonate. Most of the galena and a large part of the zinc carbonate was shipped from Ponca. Although the new Confederate mill at Cave Creek was not operated in 1917, there was a large production of zinc carbonate shipped from the Bald Hill, North Slope, and other leases, on the lands of the American Lead, Zinc & Smelting Co. The Eleventh Hour lease on the Bennett land at Ponca was transferred to Victor Primrose and later sold by him to the Allied Mining Co. The Kilgore Mining Co. acquired the leases on the Baker and adjoining lands, which have been the largest producers of galena in Arkansas, and the production will probably be greatly increased.

From the mines in Searcy County there was shipped in 1917 8 tons of sphalerite concentrates and 4,183 tons of zinc carbonate, which was double the quantity shipped in 1916. About 65 per cent of the zinc carbonate came from the Big Hurricane mine of the J. C. Shepherd Mining Co., which was the largest producer of zinc ores in Arkansas in both 1916 and 1917. The other large producers were the Howard Mining Co., which purchased the Churchill, Evening Star, and Redwine mines in the Water Creek district, and the Lucky Dog Mining Co., near St. Joe.

The total shipments from mines in Marion County in 1917 were 4 tons of galena concentrates, 712 tons of sphalerite concentrates, and 7,083 tons of zinc carbonate concentrates, which was 6 tons of galena, 628 tons of sphalerite, and 2,209 tons of zinc carbonate less than in 1916.

The largest producers of sphalerite in Marion County in 1917 were the Bonanza mine in the Buffalo district, the Bear Hill mine near Dodd City, now owned by the Continental Mining Co., and the Silver Hollow mine at Rush Creek. A large number of mines in various districts shipped zinc carbonate concentrates, but all the larger producers of zinc carbonate, including the Morning Star, Philadelphia, Monte Cristo, Yellow Rose, and Edith, are in the Rush district. Other mines, which are equipped with mills and which made good shipments, were the Liberty on the Willett land at Hall Mountain, Sure Pop No. 1 and Sure Pop No. 2 on Water Creek, and the Standard at Helva.

ILLINOIS.

By J. P. Dunlop.

PRODUCTION.

In the chapter entitled "Silver, copper, lead, and zinc in the Central States" of Mineral Resources for 1914 were given a historical review and a bibliography of the literature relating to the mining of

Digitized by Google

lead and zinc in the northern and southern districts of the State of Illinois. Estimates were also given of the total quantity of concentrates and metal produced to the end of 1914.

Mine production of lead and zinc in Illinois in 1917.[a]

District.	Ores.				Metal content			
	Lead concentrates (galena).		Zinc concentrates (sphalerite).		Lead.		Zinc.	
	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.
Northern Illinois	788	$78,666	18,221	$477,003	594	$102,168	4,267	$570,468
Southern Illinois	1,196	118,516	.....	.....	845	145,340	.....	.....
	1,984	197,182	18,221	477,003	1,439	247,508	4,267	570,468
Total, 1916	1,553	113,604	15,211	461,045	1,072	147,936	3,404	912,272

[a] In calculating the metal content of the ores from assays allowance has been made for smelting losses of zinc but not of lead. In comparing the values of ore and metal it should be borne in mind that the value given for the ore is that actually received by the producer, whereas the value of the lead is calculated from the average daily sales price (all grades) and that of zinc from the average sales price (all grades) reported by the smelters.

Mine production of silver in southern Illinois, 1907–1917.

	Silver.		Lead concentrates, silver bearing.			Silver.		Lead concentrates, silver bearing.	
	Quantity (fine ounces).	Value.	Quantity (short tons).	Ounces of silver per ton.		Quantity (fine ounces).	Value.	Quantity (short tons).	Ounces of silver per ton.
1907	2,852	$1,882	497	5.74	1913	3,541	$2,139	507	7.00
1908	2,051	1,087	359	5.71	1914	2,112	1,168	308	6.86
1909	1,011	526	253	3.90	1915	3,864	1,959	641	6.03
1910	2,022	1,092	398	5.08	1916	5,634	3,740	874	6.50
1911	3,036	1,809	482	6.25	1917	7,186	5,921	1,239	5.80
1912	4,731	2,909	748	6.31					

Tenor of lead and zinc ore and concentrates produced in Illinois, 1916 and 1917.

	1916	1917
NORTHERN ILLINOIS.		
Total crude ore, short tons	288,100	327,340
Total concentrates in crude ore:		
Lead, per cent	0.23	0.24
Zinc, do	5.28	5.56
Metal content of crude ore:		
Lead, do	.16	.18
Zinc, do	1.44	1.68
Average lead content of galena concentrates, do	68.2	75.4
Average zinc content of sphalerite concentrates, do	27.4	29.3
Average value per ton:		
Galena concentrates	$99.30	$99.83
Sphalerite concentrates	$30.31	$26.13
SOUTHERN ILLINOIS.		
Average lead content of galena concentrates, per cent	70.0	70.7
Average value per ton of galena concentrates	$76.38	$99.10

Digitized by Google

The lead concentrates produced in southern Illinois are recovered in concentrating the fluorspar. To speak of the total crude ore raised as crude lead ore would be misleading. No attempt has been made, therefore, at calculating the quantity or the tenor of the crude ore.

The value of the mine production of silver, lead, and zinc in Illinois in 1917 was $1,123,897, as compared with $1,063,948 in 1916. The lead concentrates produced amounted to 1,984 short tons, which was 434 tons more than in 1916, and the recoverable lead content increased from 1,072 tons in 1916 to 1,439 tons in 1917.

The output of sphalerite concentrate increased from 15,211 tons in 1916 to 18,221 tons in 1917, the recoverable zinc content of the concentrates increased from 3,404 tons in 1916 to 4,267 tons in 1917, but the value decreased $41,804.

The silver recovered from lead concentrates amounted to 7,186 fine ounces, valued at $5,921, against 5,684 fine ounces, valued at $3,740, in 1916.

The lead and zinc deposits of Illinois fall into two distinct regions marked by different mineral association and structural environment. Those of southern Illinois belong to the Kentucky-Illinois fluorspar district; those of northern Illinois belong to the upper Mississippi Valley region.

NORTHERN ILLINOIS.

The lead and zinc mines of northern Illinois are all in Jo Daviess County, the extreme northwestern county of the State. The ores have the same structural relations as in the upper Mississippi district generally, that is, they occur disseminated through the limestone, or in openings in it called "crevices," "pitches," or "flats," depending on their attitude to the horizontal. These openings have in general, an east and west trend, known as their "range." The ore bodies are sometimes continuous for long distances along these "ranges," which for that reason largely control the prospecting, both by shafts and by drilling. The ore deposits occur in the Galena dolomite and in the upper part of the Platteville limestone, both of Ordovician age.

The ores are galena, smithsonite, and sphalerite, though the two latter are much less common now than formerly, when the deposits worked were mostly shallow and above water level. In early years the galena ores only were mined and the ore was taken from shallow pockets in quantities ranging from a few tons to several thousand.

Although the lead output of northern Illinois, Wisconsin, and Iowa has been large in the past and the ores have been smelted near the mines,[1] the output in recent years has been comparatively small and no ores have been smelted in those States.[2] The galena is practically nonargentiferous, and the zinc ores are not known to contain cadmium. Iron pyrites is very commonly associated with the ores, generally in such quantity as to necessitate roasting and magnetic separation.

As none of the operators in the Sand Prairie district or in the Elizabeth district reported any production in 1917 the entire output of northern Illinois is included under the Galena district, which

[1] Cox, G. H., Lead and zinc deposits of northwestern Illinois: Illinois Geol. Survey Bull. 21, p. 14, 1914.
[2] Pulsifer, H. B., History of lead smelting in Wisconsin: Min. and Eng. World, May 2, 1914, p. 821

Digitized by Google

comprises the mines in the vicinity of Fever River to the Wisconsin State line. The production of lead concentrates was 788 tons, valued at $78,666, as compared with 676 tons, valued at $46,853, in 1916.

There were 18,221 tons of sphalerite concentrates, valued at $477,003, produced in 1917, an increase of 3,010 tons in quantity and of $15,958 in value.

The tonnage of crude ore mined increased from 288,100 tons in 1916 to 327,340 tons in 1917. The average recovery of zinc concentrates from the ore milled increased 0.29 per cent, and the percentage of lead was slightly greater than in 1916.

The average zinc content of the sphalerite concentrate increased from 27.4 per cent in 1916 to 29.3 per cent in 1917.

The largest production of lead and zinc concentrates in northern Illinois in 1917, as in 1916, 1915, and 1914, was derived from the old Marsdon-Black Jack mine of the Mineral Point Zinc Co. The mill has a capacity of 600 tons in 24 hours and is driven by electric power. The mine is equipped with a steel head frame and a double-compartment mill shaft and the ore is hoisted in skips. The Graham mine, of the Vinegar Hill Zinc Co., was the second largest producer. This mine was first operated in 1917 and is equipped with a 250-ton concentrating plant, which milled ore hoisted through a 200-foot shaft.

The Bartell & Sherrill Mining Co. had a considerable output of lead mined at 45 feet, which was also from a lease on the Graham land. The North Unity mine of the Vinegar Hill Zinc Co., on the Curran land, had a production nearly as large as that of the Black Jack and Graham mines. The shaft at this mine is 175 feet deep and the mill has a capacity of 20 tons an hour.

The Birkbeck mine and 150-ton mill were operated only for about three months and the mill was dismantled. The Eadie and Merry Widow mines shipped high-grade galena concentrates. New equipment was placed on both properties. The surface equipment of the Merry Widow mine was destroyed by fire in February, 1918, and the property is reported to have been sold to the Burr Mining Co.

The Little Corporal mine, of the Field Mine & Milling Co., had a small output before the property was abandoned by the lessees.

SOUTHERN ILLINOIS.

The lead and zinc deposits of southern Illinois are found in Pope and Hardin counties in rocks of Mississippian age in the northern extension of the Kentucky-Illinois fluorspar district.

The principal product of the mines in recent years has been fluorspar, and the yield of galena is small compared with the output from other districts in the Central States. The total production of galena concentrates for southern Illinois, 1906 to 1917, inclusive, has been 6,515 tons, most of which has been shipped from the Fairview and Rosiclare mines. The shipments of zinc ores from the district have been comparatively small and scattered. The only recorded shipments of zinc carbonate were made from the Empire mine in 1903 or 1904, and in 1906 four companies made shipments aggregating 103 tons.

The structural relations and the mineralogic association are similar to those of the deposits of western Kentucky and in striking contrast to those of the deposits of northern Illinois. The ores occur in fissure veins, in association with jointing and faulting. The

Digitized by Google

mines have been worked to depths of 300 and 500 feet without disclosing any decrease in the dimensions of the ore bodies. Dikes and sheets of lamprophyre and dikes of mica peridotite occur in the vicinity, but not in direct connection with the ore deposits. Galena is the most important metallic mineral. Formerly, and nearer the surface, large bodies of galena were worked, but it is at present produced incidentally in the concentration of the fluorspar. For this reason it would be misleading to give the quantity of crude ore. As the district is not reached by railway, the product of the mines is dependent on river transportation.

The galena of southern Illinois is notably argentiferous as compared with the rest of the Mississippi Valley ores, the silver content being as much as 14 fine ounces per tone of lead concentrate and averaging for the last seven years from 5 to 7 fine ounces per ton of lead concentrate. Sphalerite, or zinc blende, is the next important metallic mineral, but it occurs much less plentifully than galena. It is recovered as zinc middlings in the concentration of the fluorspar. The difficulty of making a clean separation of the zinc middlings has kept down the production of zinc. None has been sold from southern Illinois in the last nine years. The principal vein minerals are fluorspar, calcite, and barite.

The shipments of galena concentrates increased 322 tons in quantity, and the silver content recovered in treating the concentrates increased from 5,684 ounces in 1916 to 7,186 ounces in 1917. The average lead content of the concentrates increased from 70 per cent in 1916 to 70.7 per cent in 1917. The average silver content per ton recovered from lead concentrates decreased from 6.50 ounces in 1916 to 5.80 ounces in 1917.

The Fairview Fluorspar & Lead Co., which was much the largest producer of galena, operates on the Good Hope vein, which was first developed in 1862. The ore mined in 1917 was hoisted through three shafts, which are respectively 500, 400, and 300 feet in depth. This company also took over and operated the Franklin mine, which is about 5½ miles from Marion, Ky.

The Rosiclare Lead & Fluorspar Co. operates on an ore body which is probably continuous with that of the Fairview. The main shaft at the Rosiclare has reached a depth of 520 feet, and the other two shafts operated are 300 feet and 400 feet deep. The steel and concrete mill, entirely fireproof, is designed to handle 500 tons a day and is provided with special facilities for saving the lead and zinc both by jigs and by tables.

IOWA.

By J. P. Dunlop.

The lead and zinc deposits of Iowa extend along Mississippi River for nearly 80 miles, in Dubuque, Clayton, and Allamakee counties. They are found in the Galena dolomite, of Ordovician age.

In early days the Dubuque mines were the most important source of lead in the United States, and in later years the mines, especially those in the vicinity of Durango, yielded considerable quantities of zinc-carbonate ore. Nearly all this earlier mining was done above water level, and only within the last few years has there been much attempt to mine below water level. Therefore the production, par-

Digitized by Google

ticularly of zinc-blende ore, for these years, though small, is noteworthy, since it represents the attempt to mine at deeper levels.

The ore deposits of the Dubuque district occur in crevices and in caves or "openings" along these crevices. Of these openings there are five or six, the "top," "middle," and "third" being the most prolific of ore. The "flats" and "pitches," common in the Wisconsin mines, have been found in only one or two places in Iowa. The crevices have an east-west trend and sometimes extend considerable distances, being mined at different places, in which case they are known as "ranges."

The estimated output of 60 tons of zinc carbonate and 43 tons of galena concentrates in 1917 was derived from shallow workings by a number of small operators, Weston & Anderson being the largest producers. The estimated recoverable metal content of the concentrates shipped was 34 tons of lead, valued at $5,848, and 18 tons of zinc, valued at $3,672.

KANSAS.

By J. P. Dunlop.

PRODUCTION.

Production of lead and zinc in Kansas, 1917.[a]

District.	Ores.					
	Lead concentrates.		Zinc concentrates.			
	Galena.		Sphalerite.		Carbonate and silicate.	
	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.
Badger-Peacock	99	$9,394	2,264	$186,022	.....	.....
Lawton-Waco	116	12,138	5,658	408,070	.....	.....
Blue Mound-Baxter Springs	1,005	101,292	12,070	849,351	.....	.....
Galena	2,709	246,163	18,774	1,229,725	21	$930
	3,929	368,987	38,766	2,673,168	21	930
Total, 1916	2,217	162,103	24,277	1,824,069	5	196

District.	Metal content.			
	Lead.		Zinc.	
	Quantity (short tons).	Value.	Quantity (short tons).	Value.
Badger-Peacock	79	$13,588	1,206	$246,024
Lawton-Waco	92	15,824	3,060	624,240
Blue Mound-Baxter Springs	817	140,524	6,595	1,345,380
Galena	2,037	350,364	9,388	1,915,152
	3,025	520,300	20,249	4,130,796
Total, 1916	1,648	227,424	12,448	3,336,064

[a] In calculating the metal content of the ores from assays, allowance has been made for smelting losses of zinc but not of lead. In comparing the values of ore and metal it should be borne in mind that the value given for the ore is that actually received by the producer, whereas the value of the lead is calculated from the average sales price for all grades and that of zinc in 1916 and 1917 from the average sales price reported by the smelters.

Digitized by Google

Tenor of lead and zinc ore and concentrates produced in Kansas, 1916 and 1917.

	1916	1917
Total crude ore.....short tons..	774,400	903,400
Total concentrates in crude ore:		
Lead.....per cent..	0.29	0.43
Zinc.....do....	3.15	4.29
Metal content of crude ore:		
Lead.....do....	.20	.33
Zinc.....do....	1.73	2.49
Average lead content of galena concentrates.....do....	74.3	77.0
Average zinc content of sphalerite concentrates.....do....	57.0	58.0
Average zinc content of zinc silicate and carbonate.....do....	38.0	40.0
Average value per ton:		
Galena concentrates	$73.12	$93.91
Sphalerite concentrates	$75.13	$68.96
Zinc silicate and carbonate	$39.20	$44.29

The lead and zinc deposits of Kansas, so far as developed, are limited to the southeastern portion of the State, in Cherokee County. They comprise the western extension of the ore deposits of the Joplin region and display the general characteristics of that area, except that here typical sheet-ground deposits have not been extensively developed. The ores are galena and lead carbonate, sphalerite or zinc blende, and zinc carbonate and silicate. The galena is practically nonargentiferous, carrying but a small fraction of an ounce of silver to the ton of lead concentrates.

It is difficult to obtain the production for early years or to segregate the Kansas ores from those produced in the adjoining portion of the Joplin region in Missouri. If to the figures obtained and published by the State Geological Survey of Kansas for the years 1886–1903 [1] are added those for the years 1904–1917, published by the United States Geological Survey, a total output of 1,084,247 tons of zinc concentrates and of 153,368 tons of lead concentrates is shown as the approximate production of Kansas for the years 1886–1917, inclusive.

The value of the mine production of lead and zinc in Kansas in 1917 was $4,651,096, against $3,563,488 in 1916.

The value of the recoverable lead in galena concentrates shipped from Kansas mines in 1917 was $520,300, more than double that of 1916. The production of lead concentrates increased from 2,217 tons in 1916 to 3,929 tons in 1917, and the metal content from 1,648 tons to 3,025 tons. The percentage of lead concentrates in crude ore milled increased from 0.29 per cent in 1916 to 0.43 per cent in 1917. This increase was mainly due to the working of new mines near Blue Mound and to a slightly increased output from small diggings worked under the stimulus of the much higher average price of galena in 1917.

The average lead content of the galena concentrates sold was 2.7 per cent more in 1917 than in 1916, and the average price received for such concentrates was $93.91 a ton, against $73.12 in 1916.

The production of zinc carbonate and silicate was only 21 tons, valued at $930, or 16 tons more than in 1916.

The production of sphalerite concentrates in 1917 was 38,766 tons, valued at $2,673,168, an increase of 14,489 tons in quantity and of $849,099 in value, as compared with 1916. The average zinc content of the sphalerite concentrates shipped was 1 per cent more in 1917

[1] Haworth, Erasmus, and others, History, geography, geology, and metallurgy of Galena-Joplin lead and zinc: Kansas Univ. Geol. Survey, vol. 8, 1904.

Digitized by Google

than in 1916. Owing to the much richer ore mined in the new Waco and Blue Mound districts, the total per cent of sphalerite concentrates recovered from crude ore treated in Kansas increased from 3.15 per cent in 1916 to 4.29 per cent in 1917.

The production of the Badger-Peacock district in 1917 was about double that of 1916, and many leases west of Badger, near Shawnee, were drilled and a few shafts were sunk. Included among the operators in this section were T. R. Harrington, Badger Mining & Development Co., Shanklin & Neff, and the Chanute Spelter Co. The output of sphalerite in the Lawton camp in 1917 was less than in 1916, as the working level of the Eastern Zinc & Lead Co.'s property was being lowered and considerable low-grade dirt was hoisted and milled. Drilling resulted in the discovery of good ore bodies at depths ranging from 215 to 240 feet, and from 270 to 315 feet. The maximum depth of the ore mined in 1917 was 165 feet. Although the only producing mines in the Waco district, lying partly in Kansas and partly in Missouri, were the Acme, the Liberal, and Waco No. 1, the production was greater than that of the older Lawton camp. Waco was one of the most active camps in the Joplin region. The Waco Mining Co. was the largest producer of sphalerite in 1917, though its No. 2 mill was not completed until 1918.

The Butte-Kansas Mining Co.'s mill, on the Kansas side of the Waco field, was destroyed by fire a few days after it was completed. The mill has been reconstructed and the Acme mine has been purchased and will be equipped with a large mill. The Liberal mine, which has been purchased by the Freehold Oil & Gas Co., had a large output from the small quantity of dirt milled. Many leases on the Irwin, Hurlbut, Bennett, Houston, Nicholls, Dobbs, and other lands were drilled and practically all the land in the vicinity of Waco was leased. Some of the lessees and operators are Thomas Coyne, T. J. Franks, High Five Mining Co., Blue Rock Mining Co., and Noel Mining Co.

The production of lead concentrates in the Galena district in 1917 was 2,709 tons, valued at $246,163, as compared with 2,136 tons, valued at $155,389, in 1916. The shipments of zinc concentrates (all of which was sphalerite, except 21 tons) amounted to 18,795 tons, a decrease of only 658 tons; but, owing to the lower prices paid for zinc concentrates, the total value of the zinc concentrates was $216,864 less in 1917 than in 1916. The metal content of the lead concentrates was 2,037 tons in 1917, against 1,584 tons in 1916.

The average zinc content of sphalerite sold in the Galena district in 1917, according to the reports of the operators, was 55.6 per cent, which is a very close agreement with the average zinc assay of more than 2,600 sample lots made by A. J. Lusk, of Galena. The assays made by Lusk were used by buyers and sellers in settlements for ore and represent the average assay of sphalerite shipped from Galena and other adjacent camps. The average assay of 2,637 lots, regardless of the weight of each lot sold, was 56.33 per cent zinc and 2.21 per cent iron.

Many of the small leases at Galena are not equipped with concentrating plants, and a considerable part of the production is milled at custom mills or sold to chatters. Early in the year these custom

Digitized by Google

plants had an ample supply of ore, but the lower prices during the last part of the year caused many of the small mines to close.

There were not many transfers of mining property and only a few new producing mines were developed in 1917. There was, however, more drilling done than in former years and ore bodies at much lower levels than any now opened were located. The Wayland Mining Co. completed a 300-foot shaft and also did considerable drilling on the Wyandotte and other leases. Ore has been found by drills at a depth of about 300 feet on the Williams, Empire, Southside, Page & Cobb, Schermerhorn, and Giessinger lands.

The activity in that part of Cherokee County, Kans., which was caused by the progressive northerly development of the Miami field, continued throughout 1917. Most of the land lying north of the Oklahoma-Kansas State line and west and north of Baxter Springs had been leased in 1916, and the lessees or the sublessees utilized several hundred drill rigs to prove their holdings. Holes were drilled 8 or 9 miles west of Baxter Springs and to the north as far as Crestline and Columbus. The only producing properties in 1917 were the Blue Mound and Blue Diamond mines of the Blue Mound Mining Co., and the Barr mine of the Vinegar Hill Zinc Co., although many new shafts were sunk and mills were erected. The shipments for the new district amounted to 1,005 tons of galena and 12,070 tons of sphalerite, and the average recovery in concentrates from dirt milled exceeded 8 per cent. In the territory north of the Oklahoma State line and west of Blue Mound, shafts are down and concentrating plants erected at the following mines: Inspiration (Huttig Lead & Zinc Co.), Webber (Commerce), Mineral State, Southern, Thomas (United Zinc Smelting Corporation), Kansouri, National, D'Armand, Silver Fox, Kanoma, and Broom Factory (Commerce). A flotation plant was also erected by Fred De Mier on the Blue Mound lease.

West and north of Baxter Springs, shafts have been sunk and mills were built or will be erected by the Quaker Valley Mining Co., Chanute Spelter Co., and the Pershing Mining Co. North of Hockerville and southwest of Baxter Springs there was much prospecting, and mills were erected or shafts sunk by the Lucky O. K. Mining Co., Admiralty Zinc Co., Buckshot Mining Co., and others.

The Southwest Missouri Electric Railway completed its extension from Galena, Kans., as far as Hockerville, early in 1918. The Oklahoma, Kansas & Missouri Interurban Railway reaches as far as Treece, near Blue Mound, and can quickly be extended so as to furnish transportation to the mines north and west of Treece.

KENTUCKY.

By J. P. Dunlop.

PRODUCTION.

Lead and zinc deposits are found in both central and western Kentucky. None of the mines in Franklin, Mercer, Scott, Owen, or Henry counties, in the central districts, reported any lead or zinc concentrates shipped in 1917. The mines in the fluospar region of western Kentucky are chiefly in Crittenden, Caldwell, and Livingston counties and form a continuation of the southern Illinois lead and zinc region. The earliest available records of the occurrence of

Digitized by Google

fluorspar and the associated galena in the Kentucky-Illinois region appeared in the first, second, and third volumes of the American Journal of Science, published in 1818, 1820, and 1821.[1]

The presence of zinc blende was recognized in 1854–1857 during the first geological survey of the State of Kentucky by David Duke Owen and his assistant, Sidney S. Lyon. The first lead smelter using galena from Kentucky was erected by the River Valley Mining Co. at the Royal mine [2] about 1870.

Considerable quantities of galena ores have been produced in former years, but at the present time lead is obtained solely as a by-product in the recovery and concentration of fluorspar, which is the principal economic mineral. The galena recovered is argentiferous, the silver content varying from a very small quantity to more than 3 ounces a ton, but no recovery of this silver content has been reported by the smelters during the last six years. The lead concentrate shipped in any one year from Kentucky does not necessarily represent the actual recovery of lead from fluorspar mined in that year, for, being merely accessory to the fluorspar and produced in small quantities, it is frequently held until a considerable quantity has accumulated or until lead prices are high.

Production of lead and zinc in Kentucky, 1907-1917.

Year.	Ores.						Metal content.			
	Lead concentrates (galena).		Zinc concentrates.				Lead.		Zinc.	
			Sphalerite.		Zinc carbonate.					
	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.
1907	54	$2,850	.....	.....	.....	.....	34	$3,604	.....	.....
1908	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
1909	12	620	.....	.....	150	$1,701	10	860	64	$6,912
1910	56	1,980	.....	.....	30	300	41	3,608	6	648
1911	.....	.....	.....	.....	467	10,604	.....	.....	158	18,012
1912	151	6,827	498	$25,391	750	16,006	106	9,540	491	67,758
1913	40	1,422	198	5,206	696	13,811	22	1,936	327	36,624
1914	26	800	27	1,120	644	12,168	16	1,248	230	23,460
1915	376	17,103	.....	.....	2,172	106,079	251	23,594	764	189,472
1916	227	16,868	125	6,407	2,923	126,875	153	21,114	1,096	293,728
1917	184	15,415	.....	.....	2,299	78,368	123	21,156	751	153,204

The shipments of zinc carbonate decreased from 2,923 tons, valued at $126,875, in 1916 to 2,299 tons, valued at $78,368, in 1917. The estimated recoverable zinc content in 1917 was 751 tons, valued at $153,204.

The shipments of galena concentrates reported in 1917 were 184 tons, valued at $15,415, compared with 227 tons, valued at $16,868, in 1916. The average lead content was 66.8 per cent, compared with 68 per cent in 1916. The recoverable metallic content of the galena in 1917 was 123 tons, valued at $21,156.

[1] Ulrich, E. O., and Smith, W. S. T., The lead, zinc, and fluorspar deposits of western Kentucky: U. S. Geol. Survey Prof. Paper 36, pp. 16–17, 1905.
[2] Fohs, F. J., Fluorspar deposits of Kentucky: Kentucky Geol. Survey Bull. 9, 1907.

Digitized by Google

The total value of the lead and zinc concentrates shipped from Kentucky mines was $93,783, as against $150,150 in 1916.

The principal sellers of galena concentrates were the Roberts Fluorspar & Lead Co., the Kentucky Fluorspar Co., J. M. Persons, and the Fairview Fluorspar & Lead Co. The galena sold by the Roberts Fluorspar & Lead Co. was obtained from ore mined by means of five shafts, the deepest of which was about 200 feet. The fluorspar jigged yielded less than 1 per cent galena.

The galena shipped by the Kentucky Fluorspar Co. came from various mines operated by the company. The Franklin mine of the Fairview Fluorspar & Lead Co. produced fluorspar ore containing galena from a 300-foot shaft. The galena shipped by J. M. Persons was from the mines of the Ohio Valley Fluorspar Co.

The American Spar Co. operated the Hudson mine of the Eagle Fluorspar Co., near Salem, in Livingston County, and shipped most of the zinc carbonate. The ore was taken from an open cut about 85 feet in depth and treated in two double log washers before shipment.

Zinc carbonate ore was also mined and shipped from the Dearborn and Masser mines by Avery H. Reed. The Pigmy Mining Co. (Inc.) was developing its property near Mexico. There are two shafts each 200 feet deep at this mine, and a 100-ton mill was being erected.

MICHIGAN.

By B. S. Butler.

PRODUCTION.

In 1917 the mines of Michigan produced 255,710,128 pounds of copper, valued at $69,808,865, and 688,551 fine ounces of silver, valued at $567,366, a total value in copper and silver of $70,376,231. This is an increase of $2,576,321 in value over the production of 1916.

The average price of copper per pound for 1917 was $0.273; for 1916 it was $0.246. The average price of silver per fine ounce for 1917 was $0.824; for 1916 it was $0.658. Owing to the increase in the price of copper, there was an increase from $5.45 in 1916 to $5.63 in 1917 in the average value of copper per ton of "rock" treated.

The smelter production or the output of refined copper for 1917 was 268,508,000 pounds, as compared with 269,794,531 pounds in 1916. The difference between the mine and the smelter production is due to the fact that the quantity of "mineral" produced is not the same as the quantity smelted. A company may produce either more or less "mineral" than it smelts during the year.

Production was seriously hampered throughout the year by shortage and inefficiency of labor. There was a considerable extension of power haulage, which aided in relieving the labor situation, but a shortage of labor is likely to continue for the period of the war.

Digitized by Google

Value of silver and copper produced at Michigan mines in 1916 and 1917.

Year.	Silver.	Copper.		Combined silver and copper.
		Total.	Per ton of "rock."	
1916	$471,549	$67,328,361	$5.45	$67,799,910
1917	567,366	69,808,865	5.63	70,376,231
Increase	95,817	2,480,504	.18	2,576,321

The entire Michigan output of copper and silver is from the Keweenaw district. Both metals occur native in lodes remarkable for their great extent and uniformity. These lodes may be divided into two general classes—the amygdaloid, in which the metals occur together with gangue minerals, such as epidote, calcite, and zeolites, in the cellular portions of lava flows; and the conglomerate, in which the metals and gangue minerals cement and to some extent replace the pebbles forming the conglomerate. Native copper and copper minerals occur in fissures in the district, but the present output from this type of deposit is of little importance. The "rock" [1] is of low grade and requires milling, which produces "mineral" carrying an average of about 65 per cent copper. A small quantity of "barrel" and "mass" copper is sorted at the mines and sent direct to the smelters.

In 1917 there were 12,400,723 short tons of "rock" milled, which yielded 410,262,995 pounds of "mineral" and 255,710,128 pounds of copper.[2]

The average recovery of refined copper per ton of "rock" milled in 1917 was 19.9 pounds, as compared with 21.7 pounds in 1916.

There were 688,551 ounces of silver derived from the electrolytic treatment of 70,329,000 pounds of copper.

Mine production of silver, copper, "mineral," and "rock" in Michigan in 1916 and 1917.

Year.	Silver (fine ounces).	Copper.			"Mineral."		"Rock" (short tons).
		Quantity (pounds).	Yield.		Quantity. (pounds).	Yield (per cent).	
			Pounds per ton of "rock."	Per cent.			
1916	716,640	[a] 273,692,525	21.7	1.08	[b] 436,977,306	62.63	12,364,114
1917	688,551	[a] 255,710,128	19.9	.99	[b] 410,262,995	62.33	12,400,723
Increase or decrease	−28,089	−17,982,297	−1.8	−.09	−26,714,311	−.30	+36,609

[a] Includes copper from sands. [b] Includes "mineral" from sands.

[1] Some of the terms used to designate the different materials entering into the mining industry differ for the Lake district from those employed in any other part of the country. Ore is known as "rock," or (if unmained) "copper ground"; the product of concentration is known as "mineral"; and the term "ore" is used to designate the copper minerals (arsenides and sulphides) that occur to a limited extent in the district. Large bodies of native copper are known as "mass" and smaller ones are designated as "barrel work." In this report the local terms will be used, as it does not seem desirable to employ the more usual terms to the exclusion of the local, and a mixture of the two is confusing.

[2] The figures are based on the actual recovery of copper from "mineral" smelted and the estimated recovery from "mineral" that was not smelted during 1916.

Digitized by Google

Three counties—Houghton, Keweenaw, and Ontonagon—contributed to the output of copper and silver. The following table shows the relative importance of these counties in output of copper and silver for 1916 and 1917:

Mine production of silver and copper in Michigan in 1916 and 1917, by counties.

County.	Silver (fine ounces).	Copper.			"Mineral."		"Rock" (short tons).
		Quantity (pounds).	Yield. Pounds per ton of "rock."	Yield. Per cent.	Quantity (pounds).	Yield (per cent).	
1916.							
Houghton	562,295	[a] 213,109,436	22.4	1.12	[b] 346,927,476	61.4	9,266,357
Keweenaw	78,667	48,196,482	20.1	1.00	70,597,440	68.3	2,395,517
Ontonagon	75,678	12,387,607	17.6	.88	19,452,390	63.7	702,240
Total and average	716,640	273,692,525	21.7	1.08	436,977,306	62.6	12,364,114
1917.							
Houghton	558,465	[a] 195,446,231	21.0	1.05	[b] 320,257,671	61.0	9,297,322
Keweenaw	62,581	49,126,614	20.1	1.00	72,539,079	67.4	2,443,551
Ontonagon	67,505	11,137,283	16.9	.84	17,166,245	64.9	659,850
Total and average	688,551	255,710,128	19.9	.99	410,262,995	62.3	12,400,723

[a] Includes copper from sands. [b] Includes "mineral" from sands.

In the following reviews of the operations at the individual mines of the district during 1917, the statements concerning the quantity, character, and tenor of "rock" developed, the quantity of "rock" stamped, the copper recovered per short ton of "rock" stamped, and the cost of production are based on the published reports of the companies. In the few cases in which reports are not published a general statement of the character of operations is made from the best information available.

HOUGHTON COUNTY.

In 1917 the mines of Houghton County produced 195,446,231 pounds of copper and 558,465 ounces of silver. The county occupies the central portion of the copper belt and contains 15 of the 23 mines that produced copper in 1917 and 5 of the 9 mines that produced silver.

"Rock" and "mineral" produced and average yield in silver and copper in Houghton County in 1916 and 1917.

Year.	Silver (fine ounces).	Copper.			"Mineral."		"Rock" (short tons).
		Quantity (pounds).	Yield. Pounds per ton of "rock."	Yield. Per cent.	Quantity (pounds).	Yield (per cent).	
1916	562,295	[a] 213,109,436	22.4	1.12	[b] 346,927,476	61.4	9,266,357
1917	558,465	[a] 195,446,231	21.0	1.05	[b] 320,257,671	61.0	9,297,322

[a] Includes copper from sands. [b] Includes "mineral" from sands.

Digitized by Google

The output of the county shows a decrease of 17,663,205 pounds of copper and of 3,830 fine ounces of silver for 1917.

Calumet & Hecla.—The Calumet & Hecla Mining Co. has been one of the most successful copper-mining companies in the world. To the close of 1917 the company had distributed $145,250,000 in dividends.

The company's ground contains three copper-bearing lodes—the Calumet & Hecla conglomerate, the Osceola amygdaloid, and the "Kearsarge" amygdaloid. A large percentage of the production in the past has come from the conglomerate lode, but with the decrease in copper content of this lode and its approaching exhaustion, the mining from the amygdaloid lodes has increased.

The company's annual report shows the details of operation for 1917 as follows:

During 1917 there were 3,159,570 short tons of "rock" treated, yielding 68,419,826 pounds of copper, or an average of 21.65 pounds of copper per ton of "rock." This compares with a yield of 22.53 pounds for 1916. The total cost per pound of copper was 13.01 cents for 1917, as compared with 11.63 cents for 1916. The recovery of copper from old sands added to the recovery from "rock" made a total production of 77,495,283 pounds.

In 1917 the conglomerate lode produced 1,751,621 tons of "rock," yielding 50,415,860 pounds of copper, or an average of 28.78 pounds per ton of "rock," as compared with 29.97 pounds for 1916.

The Osceola lode has an average width of 30 to 35 feet, though at some points it is much wider. The mineralization is confined principally to the hanging and the foot walls. The lode is opened by drift stopes along the hanging wall, where the mineralization is rather uniform. Crosscuts are extended to the foot wall, where the mineralization is far less regular. During 1917 this lode produced 1,407,949 tons of "rock," yielding 18,003,966 pounds of copper, or 12.79 pounds per ton of "rock." This compares with a yield of 13.6 pounds per ton of "rock" for 1916.

Development on the Kearsarge lode in Calumet & Hecla ground has not been encouraging, though the lode has proved very productive farther north. There was no output from the Kearsarge lode in 1917.

The reclamation plant for treating old tailings from Torch Lake treated 730,543 tons, having an average copper content of 17.06 pounds per ton. A total of 9,075,457 pounds of copper was recovered, or an average of 12.42 pounds per ton, at an average cost, exclusive of smelting and selling, of 5.94 cents per pound.

The regrinding plant treated 512,172 tons of coarse tailings containing 12.74 pounds of copper per ton, making a recovery of 2,222,419 pounds, or 4.34 pounds per ton, at a cost, exclusive of smelting and selling, of 6.48 cents per pound.

The leaching plant treated 643,911 tons of material assaying 0.571 per cent copper, from which 5,250,331 pounds of copper was recovered, or an average of 8.15 pounds per ton, at a cost, exclusive of smelting and selling, of 6.41 cents per pound.

Experimental work with a flotation process for recovering copper from slimes has proven so successful that the company has decided to install this process in the mills.

Digitized by Google

During the year the Calumet & Hecla Mining Co. acquired all the assets of the Tamarack Mining Co. and the latter company was dissolved.

Tamarack.—The Tamarack Mining Co. was dissolved during the year, its assets having been acquired by the Calumet & Hecla Mining Co. The company had a long and successful career, distributing $9,420,000 in dividends since 1888. In recent years, however, the cost of producing copper from the mine has been high and little profit has resulted since 1907.

Osceola.—In 1917 the Osceola Co. operated the three branches—the Osceola, the South Kearsarge, and the North Kearsarge. Since 1878 this company has distributed dividends to the amount of $16,602,575.

The Osceola branch lies directly south of the Calumet & Hecla and is worked on the Osceola amygdaloid. The property contains the Calumet & Hecla conglomerate lode, but the only portion of it in Osceola ground that has been shown to carry copper in paying quantities was worked out in the early days of the mine.

A total of 203,288 tons of "rock" was produced in 1917, yielding 2,516,736 pounds of copper or an average of 12.38 pounds per ton.

The North Kearsarge lies north of the Wolverine and is worked on the Kearsarge lode. This branch produced 691,263 tons of "rock," yielding 8,667,441 pounds of copper, or an average of 12.54 pounds per ton.

The South Kearsarge lies south of the Wolverine and east of the Centennial on the Kearsarge lode.

This branch produced 343,254 tons of "rock," yielding 4,900,781 pounds of copper, or an average of 14.28 pounds per ton.

In 1917 the company treated 1,237,805 tons of "rock," producing 16,084,958 pounds of copper, an average yield of 13 pounds of refined copper per ton of "rock." This compares with a yield of 15.2 pounds in 1916. The total cost of refined copper per pound was 13.86 cents for 1917 as compared with 11.69 cents in 1916.

Dividends were declared in 1917 to the amount of $1,346,100.

Centennial.—The Centennial ground lies north of the Calumet & Hecla and west of the South Kearsarge and the Wolverine. It contains the Calumet & Hecla, the Osceola, and the Kearsarge lodes, the last being the only one of proved value in the property, and to this lode operations are at present confined.

"Rock" to the amount of 148,332 tons was stamped during the year, producing 2,002,857 pounds of refined copper or 13.50 pounds of refined copper per ton of "rock" stamped. The average cost of refined copper per pound was 18.67 cents, as compared with 13.44 cents for 1916.

Dividends were paid during the year to the amount of $90,000.

Wolverine.—The Wolverine is located between the North Kearsarge and the South Kearsarge branches of the Osceola Co. Its operations are on the "Kearsarge" amygdaloid, though the West lode, parallel with the Kearsarge lode and about 80 feet to the west, has been opened to a small extent. The mine has the distinction of having the richest rock, mined in the district. The operations on the Osceola lode have thus far proved disappointing. The Kearsarge lode in the Wolverine ground shows great uniformity of mineralization and is opened for the full length. In the upper levels the "rock" averaged

Digitized by Google

from 16 to 18 pounds per ton, but as the lower levels were opened it showed marked improvement. As the bottom limits are approached there is a notable decrease in the copper content of the rock.

During the fiscal year ending June 30, 1917, there were stamped 352,845 tons of "rock," which produced 8,753,945 pounds of "mineral," yielding 5,856,889 pounds of copper, or 16.60 pounds of refined copper per ton of "rock" stamped. The total cost per pound of refined copper was 11.62 cents.

Since its organization to June 30, 1917, the company has produced 157,159,999 pounds of copper. Operations have resulted in profits amounting to $10,648,933, of which $9,540,000 has been paid in dividends. Two dividends paid during the fiscal year amounted to $780,000.

Franklin.—The Franklin and the Rhode Island, which is controlled by the Franklin, are located southeast of the La Salle. The property carries several lodes, but in the past exploration has been principally on the "Pewabic" amygdaloid and the Allouez or "Albany and Boston" conglomerate.

The production for the year was mainly from the conglomerate lode, though developments on the amygdaloid lode opened the best ground yet found in that lode.

An output of 303,625 tons of "rock" stamped yielded 3,155,574 pounds of copper.

Quincy.—The Quincy mine is situated just north of the east-west arm of Portage Lake. The property is traversed by most of the lodes of the district, but has derived its principal output in the past from the Pewabic lode, with a small quantity from the West lode.

Dividends to the amount of $1,980,000 were paid in 1917. The total disbursement in dividends from 1862 to 1917 is $25,517,500.

In 1917 there were mined 1,280,837 tons of "rock," which yielded 35,785,490 pounds of "mineral" and 22,195,577 pounds of copper, an average of 17.33 pounds per ton of rock.

Isle Royale.—The Isle Royale mine is situated south of the east-west arm of Portage Lake, near Houghton. The property contains several copper-bearing lodes, of which the Isle Royale is the main producer at present.

During 1917 "rock" amounting to 922,160 tons was treated, yielding 13,480,921 pounds of copper, or an average of 14.6 pounds of copper per ton. The average cost per pound of copper was 15.74 cents as compared with 15.32 cents in 1916.

Dividends were paid to the amount of $600,000.

Baltic, Champion, and Trimountain.—These three mines are located on the Baltic lode southwest of Houghton and are under the management of the Copper Range Consolidated Co. The Baltic is an exceptionally strong lode, having a stoping width varying from 15 to 80 feet. The lode has produced considerable "mass" copper and also contains veinlets of copper minerals, including chalcocite, bornite, and copper arsenides. These minerals are recovered in the mill, and the arsenides probably account in part for the arsenical character of the Copper Range output.

During 1917 a total of 325,342 tons of "rock" from the Baltic mine was stamped, producing 11,214,861 pounds of refined copper, or 34.47 pounds of refined copper per ton of "rock" stamped. The cost per pound of refined copper was 13.769 cents.

Digitized by Google

A total of 264,655 tons of "rock" from the Trimountain was stamped, yielding 6,278,097 pounds of refined copper, or an average of 23.72 pounds per ton. The average cost per pound of copper was 15.223 cents.

Since its organization the company has produced 116,808,125 pounds of copper at a profit of $4,790,329, of which $1,450,000 has been disbursed as dividends.

The Champion Copper Co. is controlled jointly by the Copper Range Consolidated Co. and the St. Mary's Mineral Land Co. A total of 776,036 tons of "rock" was stamped, yielding 27,550,343 pounds of refined copper, a yield of 35.50 pounds per ton of "rock" stamped. The cost of refined copper per pound was 10.404 cents.

From its organization to the close of 1917 the Champion Co. has produced 286,423,553 pounds of copper at a profit of $24,236,646, of which $21,994,540 has been disbursed as dividends.

Superior.—During the year 129,587 tons of "rock" from the Superior was stamped, producing 2,201,672 pounds of copper, or 16.99 pounds per ton of "rock" stamped. The cost of copper a pound was 16.88 cents. The second dividend of $100,000 was paid in 1917.

La Salle.—The La Salle Co. produced 185,014 tons of "rock," yielding 1,919,775 pounds of copper, or an average of 10.38 pounds per ton of "rock." The net cost per pound of copper was 10.38 cents.

Winona.—The Winona produced 112,082 tons of "rock," which yielded 2,640,780 pounds of "mineral" and 1,494,472 pounds of refined copper, an average of 13.33 pounds of refined copper per ton of "rock" stamped.

The production from the mine after October 1 was by tributers.

Hancock.—The Hancock Consolidated Mining Co. treated 302,725 tons of "rock," which yielded 4,005,882 pounds of refined copper, an average of 13.223 pounds per ton.

New Arcadia.—The new Arcadia Copper Co. shipped 4,900 tons of "rock," yielding 53,278 pounds of refined copper.

Houghton.—The Houghton Copper Co. produced 15,628 tons of rock, yielding 291,500 tons of mineral and 179,012 pounds of copper, or an average of 11.45 pounds per ton.

Other companies.—Other companies were active in development work.

KEWEENAW COUNTY.

In 1917 Keweenaw County produced 49,126,614 pounds of copper and 62,581 fine ounces of silver. The county occupies the northern portion of the copper belt.

"Rock" and "mineral" produced and average yield in silver and copper in Keweenaw County in 1916 and 1917.

Year.	Silver (fine ounces).	Copper.			"Mineral."		"Rock" (short tons).
		Quantity (pounds).	Yield.		Quantity (pounds).	Yield (per cent).	
			Pounds per ton of "rock."	Per cent.			
1916	78,667	48,195,482	20.1	1.00	70,597,440	68.3	2,396,517
1917	62,581	49,126,614	20.1	1.00	72,839,079	67.4	2,443,551

Digitized by Google

Ahmeek.—The Ahmeek mine, lying north and east of the Allouez, is located on the Kearsage lode.

A total of 1,271,275 tons of "rock" were stamped, yielding 27,919,812 pounds of refined copper, or 22 pounds of refined copper per ton of "rock." The total cost per pound of refined copper was 9.42 cents.

During the year dividends were declared to the amount of $2,800,000. Total dividends to the close of 1917 amounted to $9,650,000.

Allouez.—The Allouez mine is north of the North Kearsarge, and in 1917, as in recent years, operations were confined to the Kearsarge lode. As this lode does not outcrop on Allouez property the shafts were started in the hanging wall at a steep angle and flattened to the dip of the copper-bearing bed just before reaching it. This plan avoids the expense of long crosscuts necessitated by vertical shafts.

A total of 566,674 tons of "rock" was stamped during 1917, yielding 8,892,915 pounds of refined copper, an average of 15.69 pounds of refined copper per ton of "rock." The total cost per pound of refined copper was 13.84 cents.

Dividends declared during the year amounted to $1,050,000. Total dividends to April, 1918, amounted to $2, 300, 000.

Mohawk.—The Mohawk mine, lying east of the Ahmeek, carries the outcrop of the Kearsarge lode for more than a mile and also contains several cross fissures carrying arsenides of copper, which have been mined to a considerable extent in the past.

A total of 605,202 tons of "rock" were stamped, yielding 17,775,200 pounds of "mineral," and 12,313,887 pounds of copper, or an average of 20.35 pounds per ton of "rock." The total cost per pound of refined copper was 11.32 cents.

Since organization the Mohawk Co. has produced 159,454,802 pounds of copper, at a profit of $9,880,440, of which amount $7,625,000 has been disbursed as dividends.

Keweenaw.—The Keweenaw Copper Co. treated 41,148 tons of "rock," yielding 619,413 pounds of "mineral" and 380,536 pounds of copper or 9.248 pounds per ton of "rock."

ONTONAGON COUNTY.

In 1917, Ontonagon County produced 11,137,283 pounds of copper. Ontonagon County contains the southwestern portion of the copper belt. This portion has not been so thoroughly developed as the others and consequently the geology is less understood than in the more northern counties. So far as developed, the lodes are more "bunchy" than to the north and have produced a relatively high percentage of mass copper. The production of 1917 was derived wholly from amygdaloid rock.

"Rock" and "mineral" produced and average yield in silver and copper in Ontonagon County in 1916 and 1917.

Year.	Silver (fine ounces).	Copper.			"Mineral."		"Rock" (short tons).
		Quantity (pounds).	Yield.		Quantity (pounds).	Yield (per cent).	
			Pounds per ton of "rock."	Per cent.			
1916	75,678	12,387,607	17.6	0.88	19,452,390	63.7	702,240
1917	67,505	11,137,283	16.9	.84	17,166,245	64.9	659,850

Digitized by Google

Mass.—The Mass mine adjoining the Adventure on the southwest, carries six known copper-bearing amygdaloid lodes—the Knowlton, the Mass, the North Butler, the Butler, the Ogima, and the Evergreen. In addition, the position of the property makes it probable that the newly discovered lodes in this part of the district may be present in Mass ground. The main developments for the year were from "B" and "C" shafts on the Butler and Evergreen lodes and continued to show as satisfactory conditions with respect to copper values as in previous years.

A total of 244,671 tons of "rock" was stamped in 1917, yielding 6,082,820 pounds of "mineral" and 3,984,616 pounds of refined copper, an avernge of 16.29 pounds of refined copper per ton of "rock" stamped. The average cost per pound of refined copper was 19.81 cents.

Victoria.—The Victoria is the most southwesterly of the Lake mines that have made important production. The present production is from the Forest lode. "Rock" amounting to 137,286 tons was stamped, yielding 2,631,693 pounds of "mineral" and 1,612,640 pounds of copper.

White Pine.—The White Pine Copper Co. treated 212,889 tons of "rock," yielding 4,067,529 pounds of copper at a cost per pound of 14.99 cents per pound.

The Lake mine was a producer in 1917.

The Michigan Copper Co. produced 2,091 tons of "rock," which with "mass" and "barrel" copper yielded 35,400 pounds of copper.

The Adventure Consolidated Copper Co. operated until late in October, when it was closed. Sales of 652,977 pounds of copper yielded $198,562.

The South Lake Mining Co. shipped during the year. Shipments from May, 1916, to December 31, 1917, amounted to 68,388 tons of "rock" which produced 754,433 pounds of refined copper, or 11.03 pounds per ton.

The Wyandotte Copper Co. made two test shipments of "rock," which were treated at the Winona mill, and gave encouraging results.

Other companies were active in exploration and development.

MISSOURI.

By J. P. Dunlop.

PRODUCTION.

VALUE.

The value of the mine production of recoverable silver, copper, lead, and zinc in Missouri in 1917 was $67,540,500, compared with $74,143,607 in 1916. The value of the copper production showed an increase of $4,645 and that of lead increased $8,108,688. The value of the silver decreased $34,431 and that of zinc decreased $14,682,008, so that the large decrease in the total value was caused almost entirely by the lower average price of zinc in 1917, compared with 1916. The recoverable lead content of Missouri lead concentrates sold in 1917 was equal to 36.6 per cent of the smelter production of primary lead in the United States derived from domestic ores, and

Digitized by Google

the recoverable spelter content from Missouri zinc concentrates sold in 1917 was 22.7 per cent of the primary spelter produced by smelters from domestic ores in 1917.

Mine production of silver and copper in Missouri, 1910–1917.

Year.	Copper.		Silver.		Lead concentrates, silver bearing (short tons).
	Quantity (pounds).	Value.	Quantity (fine ounces).	Value.	
1910	94,452	$11,955	33,096	$17,872	35,002
1911	640,411	80,051	49,867	26,430	51,109
1912	440,725	72,719	35,438	21,794	31,183
1913	576,204	89,312	35,620	21,514	35,854
1914	44,463	5,914	61,168	33,826	61,995
1915	462,160	70,378	57,756	29,282	64,377
1916	386,200	95,005	129,450	85,178	88,081
1917	365,013	99,649	61,586	50,747	76,222

For several years prior to 1913 the entire production of silver in Missouri had been derived from refining lead concentrates, but in each of the last five years a small quantity of silver has been obtained from oxidized copper ore shipped from mines in Ste. Genevieve, Washington, and other counties. The quantities given in the fourth column of the foregoing table are those of recovered silver. The silver content of the lead ores is so small that it is disregarded in the assay and sale of the concentrates. For this reason the smelter reports must be relied on for the silver production. As may be seen by inspection of the table, the quantity of silver produced in any year bears no direct ratio to the quantity of lead concentrates smelted during that year. The reason for this is that the silver content is so small in quantity that the silver bullion is stored and refined in batches. If a series of years be taken into account, the concentrates are seen to average less than 1 ounce of silver to the ton.

The production of copper in Missouri in 1917 was 365,013 pounds, valued at $99,649, as compared with 386,200 pounds, valued at $95,005, in 1916. The North American mine now owned by the Missouri Cobalt Co., which produced some copper as well as nickel and cobalt in the years 1908 and 1909, marketed no copper in 1917, although some ore was mined. Nearly all the copper output for 1917 was derived from concentrates recovered in dressing lead ore mined in St. Francois County, in southeastern Missouri. Some copper ore was mined and shipped from the Racola mine in Washington County. In addition to the copper the ore is reported to have yielded some silver.

LEAD AND ZINC.

The total value of the recoverable metallic content of the lead and zinc concentrates produced in Missouri in 1917 was $67,390,104, a decrease of $6,573,320 from that of 1916. The production of lead concentrates in Missouri in 1917 (of which all but 394 tons was galena) was 345,513 short tons, valued at $34,038,976, as compared with an output of 347,869 tons, valued at $24,172,965, in 1916, a

Digitized by Google

decrease of 2,356 tons in quantity but an increase of $9,866,011 in value. Of this production in 1917 of lead concentrates 306,473 tons, valued at $30,070,995, was derived from southeastern and central Missouri, a decrease of 552 tons in quantity and an increase of $9,350,258 in value. The average metal content of the lead concentrates from these districts was 66.7 per cent, as compared with 65.66 per cent in 1916, and the value per ton in 1917 was $98.01. The quantity of recoverable lead in southeastern and central Missouri concentrates in 1917 amounted to 204,545 tons, an increase of 2,913 tons. The output was equal to about 32 per cent of the primary lead smelted or refined from domestic ores in the United States in 1917.

Shipments of lead concentrates from southwestern Missouri were 39,040 tons, valued at $3,967,981, as compared with 40,844 tons, valued at $3,452,228, in 1916. The lead carbonate concentrates amounted to 394 tons, valued at $30,087, an increase of 367 tons. The quantity of recoverable lead from southwestern Missouri, or the Joplin region, was 29,611 tons, valued at $5,093,092, a decrease of 1,845 tons. The average metal content of the galena concentrates from southwestern Missouri was 76 per cent and the average price per ton was $101.90, or $17.36 more per ton than in 1916.

The quantity of zinc blende concentrates sold from Missouri mines in 1917 was 231,588 tons, valued at $16,453,629, a decrease of 45,588 tons in quantity and of $6,424,586 in value, when compared with the figures for 1916. All the blende concentrate except 186 tons was produced in southwestern Missouri. The average price received per ton was $71.04 and the average recoverable zinc content reported by the sellers was 58.5 per cent. The average price paid per ton in 1916 was $82.55 and the average recoverable zinc content was 58.7 per cent.

The zinc content of the sphalerite concentrates derived from "sheet ground" mines, which was 58.6 per cent in the years 1911 and 1912, declined to 58.3 per cent in 1913, increased to 58.4 per cent in 1914, to 59.1 per cent in 1915, and to 59.2 per cent in 1916, and decreased to 58.6 per cent in 1917. The average price received for all sphalerite concentrates in 1917 was $11.51 a ton less than in 1916.

The zinc carbonate and silicate concentrates sold in 1917 amounted to 30,986 tons, valued at $1,254,975. This was 4,092 tons more in quantity and $95,406 less in value than the sales in 1916. The output in 1917 was mainly from southwestern Missouri, the shipments from southeastern and central Missouri being only 293 tons, valued at $7,145, as compared with 1,030 tons, valued at $42,129, in 1916. The average metal content of the zinc carbonate and silicate concentrates was 39.7 per cent in 1917. The average value per ton in 1916 was $40.50 as compared with $50.21 in 1916.

The combined value of lead and zinc concentrates from southeastern and central Missouri in 1917 (which produced about 89 per cent of the lead concentrates) was $30,094,484, or $9,317,218 more than in 1916.

The total value of the southwestern Missouri lead and zinc concentrates was $21,653,096, as compared with $27,624,295 in 1916, a decrease of $5,971,199.

Digitized by Google

The total quantity of crude ore or "dirt" mined and treated in 1917 amounted to 17,024,000 short tons, a decrease of about 1,640,000 tons, or approximately 9 per cent less than the quantity mined and treated in 1916. As the total amount received for all classes of lead and zinc concentrates sold in 1916 was $51,747,580 the average value per ton of crude ore or "dirt" mined and treated was $3.04, as compared with $2.60 in 1916, with $2.20 in 1915, $1.65 in 1914, $1.72 in 1913, and $1.86 in 1912. The increase of 44 cents a ton was entirely from the lead ores mined in southeastern Missouri.

The small quantity of copper ore mined and shipped in 1917 is excluded from these calculations.

In the following tables showing the tenor of crude ore ("dirt") and concentrates from Missouri it has been considered advisable to segregate the ores of different nature. For instance, the disseminated lead ore of southeastern Missouri differs radically from the lead and zinc ores of the so-called "soft ground" deposits of southwestern Missouri, and these in turn differ from the "sheet ground" deposits of the same region. Each class of ore has its peculiar problems of mining and ore dressing. This fact makes desirable the separate treatment of the statistical data. In general, the tables reflect very closely the conditions of the industry.

Production of lead and zinc in Missouri in 1917.

District.	Lead concentrates.			
	Galena.		Carbonate.	
	Quantity (short tons).	Value.	Quantity (short tons).	Value.
Southwestern Missouri:				
Alba-Neck City	389	$39,593		
Ash Grove-Everton	8	800		
Aurora	229	21,337	25	$1,189
Carl Junction				
Carthage	93	9,996		
Cave Springs	209	22,450		
Diamond		9		
Duenweg-Porto Rico	6,010	602,569	354	28,129
Fairview and Pioneer	5	500		
Granby	540	47,611		
Joplin	7,072	704,389	7	387
McDowell-Stark City	5	400		
Oronogo	2,331	228,801		
Sarcoxie-Reeds				
Sherwood-Thoms station	271	27,761		
Spring City-Beef Branch	387	42,113	3	107
Springfield	172	10,579		
Spurgeon-Seneca	138	13,287	5	275
Stott City				
Webb City-Carterville-Prosperity	20,650	2,143,772		
Wentworth	10	1,100		
Zincite-Klondike	77	6,522		
Christian County	49	5 233		
Ozark, Howell, Wright, and Taney counties	1	72		
	38,646	3,937,894	394	30,087
Central and southeastern Missouri	306,473	30,070,995		
State total, 1917	345,119	34,008,889	394	30,087
1916	347,842	24,171,305	27	1,660

Digitized by Google

District.	Zinc concentrates.			
	Sphalerite.		Silicate and carbonate.	
	Quantity (short tons).	Value.	Quantity (short tons).	Value.
Southwestern Missouri:				
Alba-Neck City	9,001	$607,099	474	$17,486
Ash Grove-Everton			1,719	52,367
Aurora	3,123	209,749	4,717	176,103
Carl Junction	320	24,553		
Carthage	4,827	333,742	5	97
Cave Springs	1,603	123,661		
Diamond	798	62,630	98	4,731
Duenweg-Porto Rico	38,093	2,628,085	3,057	150,149
Fairview and Pioneer			50	1,850
Granby	6,126	413,491	15,828	656,561
Joplin	52,525	3,620,429	1,532	67,356
McDowell-Stark City			30	1,022
Oronogo	9,918	642,602		
Sarcoxie-Reeds	1,542	109,212		
Sherwood-Thoms station	1,465	102,641	65	2,850
Spring City-Beef Branch	294	20,434	1,379	56,589
Springfield	1,583	118,478		
Spurgeon-Seneca	2,702	161,038	419	17,063
Stott City	604	45,465		
Webb City-Carterville-Prosperity	86,415	6,230,272		
Wentworth	6,250	380,088	293	10,894
Zincite-Klondike	4,154	300,321		
Christian County	52	2,578	520	20,289
Ozark, Howell, Wright, and Taney counties	7	417	507	12,424
	231,402	16,437,285	30,693	1,247,830
Central and southeastern Missouri	186	16,344	293	7,145
State total, 1917	231,588	16,453,629	30,986	1,254,975
1916	277,176	22,878,215	26,894	1,350,381

District.	Metal content.[a]			
	Lead.		Zinc.	
	Quantity (short tons).	Value.	Quantity (short tons).	Value.
Southwestern Missouri:				
Alba-Neck City	306	$52,632	4,889	$997,356
Ash Grove-Everton	6	1,032	571	116,484
Aurora	191	32,852	3,290	671,160
Carl Junction			173	35,292
Carthage	74	12,728	2,609	532,236
Cave Springs	165	28,380	844	172,176
Diamond			467	95,268
Duenweg-Porto Rico	4,779	821,988	21,181	4,320,924
Fairview and Pioneer	4	688	17	3,468
Granby	387	66,564	8,855	1,806,420
Joplin	5,402	929,144	28,568	5,827,872
McDowell-Stark City	4	688	11	2,244
Oronogo	1,760	302,720	5,313	1,083,852
Sarcoxie-Reeds			869	177,276
Sherwood-Thoms station	216	37,152	779	158,916
Spring City-Beef Branch	309	53,148	649	132,396
Springfield	137	23,564	874	178,296
Spurgeon-Seneca	106	18,232	1,522	310,488
Stott City			337	68,748
Webb City-Carterville-Prosperity	15,659	2,693,348	45,103	9,201,012
Wentworth	8	1,376	3,200	652,800
Zincite-Klondike	59	10,148	2,238	456,552
Christian County	38	6,536	214	43,656
Ozark, Howell, Wright, and Taney counties	1	172	157	32,028
	23,611	5,093,092	132,730	27,076,920
Central and southeastern Missouri	204,545	35,181,740	188	38,352
State total, 1917	234,156	40,274,832	132,918	27,115,272
1916	233,088	32,166,144	155,960	41,797,280

[a] In calculating the metal content of the ores from assays allowance has been made for smelting losses in zinc but not in lead. In comparing the values of ore and metal it should be borne in mind that the value given for the ore is that actually received by the producer, whereas the value of the lead is calculated from the average sales price (all grades) and the value of the zinc from the average sales price of all grades reported by smelters.

Digitized by Google

Tenor of crude lead and zinc ore and concentrates produced in southwestern Missouri in 1916 and 1917.[a]

	1916	1917
SOFT GROUND.		
Total crude ore.....short tons..	4,711,700	3,447,850
Total concentrates in crude ore.....per cent..	3.38	4.04
Lead.....do....	.28	.33
Zinc.....do....	3.10	3.71
Metal content of crude ore.....do....	1.92	2.24
Lead.....do....	.22	.25
Zinc.....do....	1.70	1.99
Average lead content of galena concentrates.....do....	78.0	76.1
Average lead content of lead carbonate concentrates.....do....	55.5	62.2
Average zinc content of sphalerite concentrates.....do....	58.1	58.3
Average zinc content of silicates and carbonates.....do....	39.4	39.7
Average value per ton:		
Galena concentrates.....	$82.09	$97.94
Lead carbonate concentrates.....	$61.48	$76.36
Sphalerite concentrates.....	$77.94	$69.50
Zinc silicates and carbonates.....	$50.21	$40.50
SHEET GROUND.		
Total crude ore.....short tons..	8,484,700	7,688,250
Total concentrates in crude ore.....per cent..	2.19	2.11
Lead.....do....	.33	.36
Zinc.....do....	1.86	1.75
Metal content of crude ore.....do....	1.35	1.31
Lead.....do....	.25	.28
Zinc.....do....	1.10	1.03
Average lead content of galena concentrates.....do....	76.5	75.9
Average content of sphalerite concentrates.....do....	59.2	58.6
Average value per ton:		
Galena concentrates.....	$85.62	$103.51
Sphalerite concentrates.....	$86.02	$72.16

[a] Including also the small production of lead and zinc ores in southeastern and central Missouri.

Tenor of crude lead ore and concentrates in southeastern Missouri disseminated lead ore in 1916 and 1917.

	1916	1917
Total crude lead ore.....short tons..	5,467,500	5,887,900
Galena concentrates in crude ore.....per cent..	5.60	5.03
Lead content in crude ore.....do....	3.68	3.47
Average lead content of galena concentrates.....do....	65.66	66.7
Average value per ton of galena concentrates.....	$67.47	$98.01

In Mineral Resources for 1914, Part I, pages 72–77 and 97–100, was given a brief history of lead and zinc mining in the southeastern Missouri and Joplin regions, together with data relating to the total lead and zinc production, the mining and milling practice, and the methods of selling ore and concentrates. The separate chapter entitled "Silver, copper, lead, and zinc in the Central States in 1914" is available for distribution and can be obtained upon application to the Director, United States Geological Survey, Washington, D. C.

In order to expedite the prompt publication and distribution of this report much of the data relating to individual properties as given in previous reports under the reviews by districts has been omitted. All the essential data relating to the districts are included in the yearly State review of the regions.

Digitized by Google

SOUTHWESTERN MISSOURI.

AREA, ORES, DEPOSITS.

The southwestern Missouri lead and zinc areas includes the largest part of the Joplin region, the remaining portion lying in southeastern Kansas and in northeastern Oklahoma. The Missouri part of the region was first developed, then that in Kansas, followed at a considerably later period by that in Oklahoma.

The ore in southwestern Missouri occurs in the Mississippian Boone limestone, in beds of Kinderhook age. The ore deposits are found in Jasper, Newton, Lawrence, Greene, and adjoining counties. This area produced in 1917 only 56 per cent of the lead and zinc ore mined in the Joplin region, compared with 78 per cent in 1916.

The lead ores are galena, with a small quantity of lead carbonate, locally known as "dry bone." The zinc ores are sphalerite or zinc blende, or "jack," zinc carbonate (smithsonite), and zinc silicate (calamine), both of the latter locally called "silicate." The galena contains but a small fraction of an ounce of silver to the ton of lead concentrates, and although ordinarily it is not desilverized, yet occasionally the refineries find it advantageous to add lead from the Joplin region to their charges, without, however, making any record of the silver content. In this way an unknown but small quantity of silver is recovered from southwestern Missouri lead ore. The zinc ores, sphalerite, smithsonite, and calamine, contain notable quantities of cadmium, being fully as rich in this respect as the zinc ores of Silesia, which are the source of the cadmium production of Europe. Discussion of the cadmium content of these ores is taken up in the chapters entitled "Cadmium," in Mineral Resources for 1908 and for 1917.

The ore deposits of the Joplin district vary in character with the depth of mining. The shallower ores beginning at the surface are universally pockety and are found in residual clays or in "runs" in the basal breccias of the region. The breccias and the forms of the "runs" are largely, if not altogether, due to solution of the limestone strata. One form of run, which is fairly numerous, is the "circle" deposit, which, in the popular view, has come to be nearly synonymous with rich deposits. Small veins, vertical sheets, and thin crevice deposits are often met with in prospecting, but unless they develop into stringers leading into paying ore bodies are forgotten in the multitude of rich pockety deposits which the district has yielded. The blanket deposits or "sheet ground" are found in the Grand Falls chert member of the Boone limestone at depths varying from 100 to 275 feet, according to the topography and the geologic structure. Below this horizon there are, in the beds of Kinderhook age, deposits of disseminated ore. They have been found in prospect shafts or drill holes near Springfield, Aurora, Granby, Carterville, Joplin, Hornet, and Cave Springs, in Missouri; at Galena, in Kansas; and at Quapaw, in Oklahoma.

Digitized by Google

Lead and zinc concentrates produced in the Missouri part of the Joplin region, 1907–1917.

	Quantity (short tons).	Value.
Lead concentrates	407,556	$25,189,452
Sphalerite concentrates	2,509,336	130,027,468
Zinc carbonate and silicate concentrates	249,689	7,757,329
	3,166,581	162,974,249

The average price per ton received for sphalerite concentrates during the period 1907 to 1917 was $51.82, and that for zinc silicate and carbonate was $31.07.

ASSAYS.

Several of the assayers in the Joplin district make a practice of saving the remnants of blende samples analyzed during the year. At the close of the year the lot is thoroughly mixed and carefully sampled, from which sample an average or composite assay for the year is made. Each assay thus represents several thousand lots. Two representative series of such composite assays are given below. In most cases each sample included in the composite assay represents a carload lot of concentrates.

The first series, by W. W. Petraeus and Evans W. Buskett, of Joplin, gives the result of analyses of composite samples from the general district for the last 16 years. The analyses for 1897–1905, inclusive, were published in the Lead and Zinc News, volume 9, page 8, January 15, 1906. The analyses for 1906–1913 were kindly communicated by Mr. Petraeus and those for 1914–1917 by Mr. Buskett. Iron was not taken into account until 1900. Some 400 scattering assays, made in 1895–96, are excluded from the table.

Composite assays of zinc blende from the Joplin region, 1897–1917.

[W. W. Petraeus, analyst, 1897–1913; Evans W. Buskett, analyst, 1914–1917.]

Year.	Number of lots in the composite.	Percentage.				
		Zinc.	Iron.	Lead.	Copper.	Cadmium.
1897	600	56.64	.....	.....	.....	.....
1898	1,299	56.99	.....	.....	.....	.....
1899	3,715	56.67	.....	.....	.....	.....
1900	3,500	57.36	0.22	.....	.....	.....
1901	3,683	57.53	2.02	.....	.....	.....
1902	5,776	57.08	2.24	.....	.....	.....
1903	6,014	57.30	2.00	.....	.....	.....
1904	6,220	57.24	2.10	.....	.....	.....
1905	4,628	57.97	1.84	1.00	0.001	0.198
1906	5,644	57.2	2.00	.....	.....	.....
1907	6,813	56.8	1.93	.....	.....	.....
1908	7,837	56.4	1.76	.....	.....	.....
1909	9,002	56.3	2.00	.....	.....	.....
1910	8,892	56.6	2.10	1.02	.06	.399
1911	8,920	57.1	2.40	.....	.....	.....
1912	9,474	57.7	2.40	.....	.....	.....
1913	7,010	57.1	2.40	.....	.....	.....
1914	420	56.40	2.70	.....	.....	.....
1915	1,806	56.76	2.36	.....	.....	.....
1916	2,190	57.0	2.30	.54	.....	.....
1917	a3,000	57.3	2.25	.52	.....	.....

a Estimate.

Digitized by Google

The next series of composite assays was communicated by Prof. W. George Waring and Bruce Williams, of Webb City. The original samples were of ores from the different camps of the district except where otherwise indicated. The methods used in making these assays have been published.[1]

Composite assays of zinc blende from the Joplin region, 1900–1917.

[W. George Waring and Bruce Williams, analysts.]

Year	Number of lots in the composite.	Percentage.				
		Zinc.	Iron.	Lead.	Cadmium.	Copper.
1900	3,894	57.30	3.03			
1901	5,172	56.00	3.30			
1901	2,577	55.30	3.86			
1901	[a] ±2,000	55.90	3.47			
1902	2,270	57.08	2.65	0.904	0.337	0.050
1903	2,145	57.75	2.32	1.072	.398	.049
1904	[a] 3,800	58.26	2.23	.701	.304	.049
1904	[b] 2,691	58.46	1.97	.720	.430	.050
1904	1,984	58.95	2.10			
1905	4,520	58.95	2.00			
1906	4,638	58.40	2.20			
1906	3,968	58.20	2.29			
1907–8	±4,000	58.70	2.00			
1909		[c] 57.40	2.60			
1910	6,377	[c] 57.90	2.60			
1911	5,653	58.20	2.35	.856	.450	.034
1912	6,709	56.72	2.50	1.070	.256	.022
1913	7,364	56.82	2.81	1.112	.209	.036
1914	7,981	56.56	2.80	1.30	.287	.033
1915	9,240	57.19	2.40	.935		
1916	10,451	57.95	2.20	.720	.262	.054
1917	10,041	58.10	2.65	.630	.324	.046

[a] Joplin. [b] Webb City. [c] The composite sample included some lots of silicate ores.

The complete analysis of the composite sample of the 3,800 lots of concentrate from the Joplin region in 1904, sampled by C. V. Millar and analyzed by Waring, is as follows:

Analysis of composite sample of zinc blende from the Joplin region.

Zinc	58.26	Calcium carbonate	1.88
Cadmium	.304	Magnesium carbonate	.85
Lead	.70	Barium sulphate	.82
Iron	2.23	Silica	3.95
Manganese	.01		
Copper	.049		99.773
Sulphur	30.72		

Analysis of a representative sample of sphalerite jig concentrates from "sheet-ground ore" from the Cartersville, Mo., area.

[Waring & Williams Laboratories, Webb City, Mo., analyst.]

Zinc	59.20	Germanium, gallium, and indium (spectroscopic determination)	Traces.
Cadmium	.058	Calcium carbonate	Traces.
Lead	.293	Silica (possibly including traces of barium sulphate)	6.971
Iron	1.900		
Copper	.054		99.777
Sulphur	31.301		
Manganese			
Nickel and cobalt	Traces.		

[1] Waring, W. G., The volumetric determination of zinc: Am. Chem. Soc. Jour., vol. 26, No. 1, January, 1904. In addition to the composite assays for 1902 and 1903, shown in the table, the article gives the lead, copper, and cadmium content of a number of ores from individual mines in Missouri, Kentucky, and Illinois.

Digitized by Google

The year 1917 proved very unsatisfactory to operators of zinc mines in southwestern Missouri. There was no reduction in the high cost of operating as set forth in detail in this report for 1916, and the selling price of sphalerite was in many cases below the cost of production after May, 1917. Development in the "sheet ground" areas ceased entirely. Many of the mills were closed, as it was not possible to operate profitably many mines where the dirt ran from 2 to 2.75 per cent in concentrates. In many cases the mills were moved to mines in the Miami district. On account of the scarcity of mill material and the delays in shipping it was possible to obtain prices for second-hand milling and mining equipment very much in excess of the ordinary prices. There were very few transfers of mining property in the old camps in southwestern Missouri and few new concentrating plants were built. In outlying camps considerable drilling and development was done and some mills were built. The production of zinc carbonate and silicate, mainly by small operators, increased about 4,800 tons, although the output of sphalerite decreased more than 45,000 tons. Efforts were made to fix a price for prime western spelter which would enable most of the mines to obtain a price for medium and low-grade sphalerite concentrates which would make operating profitable, but the efforts were without result. In May, 1918, the producers of high-grade sphalerite that contained little or no lead made an arrangement by which certain smelters producing high-grade spelter agreed to purchase a limited quantity of sphalerite at $75 a ton. This tonnage was allocated to the various producers of high-grade sphalerite. As this production is in excess of the smelter requirements, the anomaly is presented of part of the production of a mine selling at $75 a ton and the remainder for as little as $55 to $60 a ton.

The quantity of sphalerite concentrates at the mines was negligible at the beginning of 1917, but the stocks increased during the last months of the year, and in addition to the quantity unsold there were several thousand tons sold but not shipped on account of scarcity of cars and the delay caused by an unusually heavy snowstorm in December. The quantity of concentrates on hand, sold and unsold, at the end of 1917 was estimated at between 25,000 and 30,000 tons. Stocks of galena concentrates, which were very small at the beginning of 1917, were also larger at the end of 1917, though there was very little galena at Missouri mines other than that which was sold but not shipped.

As indicated by the total production for 1917, the average weekly output of concentrates from mines in southwestern Missouri was 4,450 tons of sphalerite, 570 tons of zinc carbonate and silicate, and 580 tons of galena. In December many of the mines had been closed down entirely or were operating single shift, and the weekly shipment of sphalerite was less than 2,500 tons.

As in 1916, the conspicuous feature of the ore market was the great difference between the base prices offered for sphalerite. There was usually a difference of at least $10 a ton, and occasionally as much as $20 a ton, between the base price offered for lead-free or nearly lead-free sphalerite and the medium and low-grade sphalerite concentrates containing above 0.5 per cent of lead. The average quoted base prices for 60 per cent sphalerite were highest in February, when a small quantity of concentrates sold for about $100 a ton.

Digitized by Google

In the first week in January the base prices quoted were from $74 to $83 a ton. Base prices for the lower grades advanced to $80, and for high grades to $90 in the last half of February and in March. In April base prices declined to $65 and $70 for low-grade concentrates and to $75 to $80 for high grade. In July, August, and September the prevailing quotations ranged from $65 to $75. The October base price for low-grade concentrates declined $5. Prices then gradually declined during November and December, when the base prices reached $50 for low-grade concentrates and $70 for high-grade concentrates. The actual average selling price of all concentrates was about $30 a ton less in December than in February.

Base prices for calamine or zinc silicate ores followed the sphalerite quotations. The lowest base prices were in November and December, when they ranged from $30 to $35 a ton, and the highest were in February, when they ranged from $50 to $55 a ton.

The quoted price for 80 per cent galena showed wide variations, opening in January at $90 a ton and closing in December at $70 to $75 a ton. During the year galena sold for as much as $135.50 a ton in April and August and for as little as $64 at the end of November. The high prices did not stimulate the production of lead from southwestern Missouri, for there was a slight decrease in production. There will be a further decrease in 1918, owing to the closing of most of the mines working "sheet ground."

The average price per ton paid for sphalerite or blende in 1917 was $71.04, as compared with $82.60 in 1916, $76.25 in 1915, $38.74 in 1914, $40.70 in 1913, and $50.44 in 1912; and for zinc silicate or carbonate concentrates it was $40.50 in 1917, $50.21 in 1916, $45 in 1915, $21.13 in 1914, $22.45 in 1913, and $28.95 in 1912. The average price paid for galena concentrates was $101.90 in 1917, as compared with $84.29 in 1916, $52.52 in 1915, $46.83 in 1914, $51.50 in 1913, $55.36 in 1912, and $55.75 in 1911. These prices are not average base price quotations but are the actual average prices calculated from the quantity sold and the values reported to the United States Geological Survey by the sellers.

The prices received by the producers show that the average actual selling price of sphalerite in 1917 was $11.56 a ton less than in 1916, a decrease of 14 per cent, and that the corresponding decrease in prices for zinc carbonate and silicate in 1917 was $9.71, a larger percentage of decrease than in the price of sphalerite.

The average metal content of sphalerite concentrates derived from "soft ground" increased from 58.1 per cent in 1916 to 58.3 per cent in 1917, and the content of those derived from "sheet ground" decreased from 59.2 per cent in 1916 to 58.6 per cent in 1917. The average metal content of the galena concentrates derived from "soft ground" was 1.9 per cent less than in 1916. The average metal content of the galena derived from "sheet ground" was 0.6 per cent less than in 1916.

The recovery of sphalerite and galena concentrates from "sheet ground" declined from 2.19 per cent in 1916 to 2.11 per cent in 1917. The decrease was entirely in the sphalerite concentrates and the large increase in the price paid for galena aided the operators of "sheet ground." Many continued to operate their "sheet ground," hoping for an advance in the price of sphalerite, which did not materialize.

Digitized by Google

The average recovery of concentrates from "soft ground" increased from 3.38 per cent in 1916 to 4.04 per cent in 1917. This was due to the larger quantity of zinc silicate ore mined and to the shutting down of a great many of the larger mines.

The total ore or "dirt" treated decreased from 13,196,400 tons in 1916 to 11,136,100 tons in 1917. The "dirt" treated from "sheet ground" was 7,688,250 tons, a decrease of about 796,000 tons, and that from "soft ground" was 3,447,850 tons, a decrease of about 1,264,000 tons.

In 1917 the sphalerite concentrates derived from "sheet ground" mines amounted to 134,778 tons and the galena concentrates to 28,159 tons. In 1917 "soft ground" mines yielded 96,810 tons of sphalerite, 10,889 tons of galena, and all of the lead carbonate, zinc silicate, and zinc carbonate concentrates. The production of sphalerite concentrates from "sheet ground" decreased 23,026 tons, and that of galena increased 82 tons. The decrease of sphalerite from "soft ground" was 22,562 tons and that of galena 2,374 tons, though the quantity of zinc carbonate and silicate increased 4,092 tons.

The total value of all concentrates derived from "sheet ground" mines was $12,639,983, and from "soft ground" mines $9,080,080. This shows that the value of the production of concentrates from "soft ground" in 1917 amounted to $3,559,903 less than the production from "sheet ground," whereas it was $4,334,681 less in 1916.

The Webb City-Carterville-Prosperity district, which includes many of the "sheet ground" mines, was again much the largest producer of both blende and galena concentrates in southwestern Missouri. It produced 53 per cent of the galena concentrates and 38 per cent of the sphalerite sold in 1917.

The quantity of crude ore or "dirt" raised is a better indication of the extent of mining activity than the production of concentrates, for the "sheet ground" ore is of lower average tenor than the "soft ground" ore. The leading position of the district is more adequately shown by the fact that the estimated quantity of ore mined in the Webb City-Carterville-Prosperity district in 1917 was about 4,952,800 tons, or nearly 45 per cent of the total crude ore raised in southwestern Missouri, and that the output in 1917 was about 1,150,000 tons less than in 1916.

Unfortunately, the large decrease in the quantity of ore treated in 1917 in the Webb City-Carterville-Prosperity district does not convey an adequate idea of the great changes that occurred in 1917 and that have since culminated in the closing down of most of the large mines in the district and the removal of the concentrating plants. The large pumps at the Providence mine have been pulled and the water level is gradually rising. As many of the mines in the north and central Webb City camps are connected underground, it will be very expensive to unwater the properties, even if better ore prices make profitable the mining of "sheet ground" containing from 2 to 2.30 per cent in concentrates. The only new concentrating plant built in 1917 was by the O. & M. Mining Co., on the Fremont land. In the entire territory from Oronogo on the north to beyond Duenweg-Porto Rico on the south, the only large mills in operation in June, 1918, were the Bertha A., Coahuila, Hurry Up, Fairhope, Athletic, Ben Franklin, Kirkwood, Orange, and Davey. The following mills have

Digitized by Google

been sold and removed: Wingfield, Milan, Sunshine, Nearby, Red Bird, McDonald, Victor, National No. 1, Cumberland, Bessemer, Schenley, Latoka, Cisco, Sunflower, and Chapman.

The production of lead and zinc concentrates in the Joplin district increased 7 per cent in 1917. Nearly all the increased output was in galena and zinc silicate. Mining was brisk during the early part of 1917, though new work was practically confined to "soft ground." Only a few of the "sheet ground" mines in the west Joplin camp were being worked at the end of the year, and the new mines opened were mainly those requiring the investment of only a small amount of money.

Some of the new concentrating plants built in 1917 were the King David on Connor land, Malsbury on Freeman land, Malcona on Johnson land, Little Bill on Higgins land, St. Regis No. 2, Cliff on American Zinc, Lead & Smelting Co.'s land, Fifteenth Street and Yellowstone on Missouri Lead & Zinc Co.'s land.

Duenweg-Porto Rico had a production of zinc and lead concentrates in 1917 which in the aggregate was only about 1,000 tons less than in 1916. More than 80 per cent of the output was from "sheet ground" mines, and as the only mines of that class in operation in June, 1918, are the Athletic and the Coahuila there will be a very large decrease in the production.

New mills were constructed in 1917 by the Hartford Mining Co. on the Barratt land, by Scott Mining Co. (rebuilt after destruction by fire) on the Irwin land, by C. M. & H. Mining Co. (dismantled also in 1917) on the Hackett land, and by M. M. & B. Mining Co. on the Carter land.

The Granby district produced 15,828 tons of zinc silicate and carbonate, which was more than 50 per cent of the total output of that class of zinc ore in Missouri in 1917. There were also shipments of 540 tons of galena and 6,126 tons of sphalerite, so that the value of the concentrates sold from that district was only exceeded in value by the shipments from Webb City, Joplin, and Duenweg. There was considerable drilling done outside the land of the American Zinc, Lead & Smelting Co., and a good production was made from the Zogg and the Douglas lands.

The quantity and value of the concentrates shipped from the Oronogo district in 1917, though less than in 1916, exceeded the quantity and value of the Alba-Neck City district, which had an output of about 5,000 tons less sphalerite concentrates than in 1916. There were no striking developments in either district other than the work continued at the Oronogo Circle mine in removing the overburden by means of steam shovels in order to obtain a large supply of ore for the new 1,000-ton mill.

The less productive mining districts in the Joplin region which showed an increased output of lead and zinc in 1917 were Wentworth, Carthage, Spurgeon-Seneca, and Diamond. New mills were constructed at Carthage by the Coahuila Zinc & Lead Co. and at Diamond by the Neosho & Granby Mining Co. The Sarcoxie-Reeds, Spring City, Cave Springs, Zincite-Klondike, and Thoms Station districts all had much decreased outputs and the only mine of any importance at Sarcoxie was that of the Flannery Zinc Co., which rebuilt the plant destroyed by fire in December, 1916.

Digitized by Google

The only plant at Carl Junction operated in 1917 was the Lucky Shot and the tailing plants built at Stott City in 1916 were abandoned in 1917 after short runs.

Several new plants were constructed near Springfield, Mo., early in 1917 and operated for a few months until the low price of sphalerite forced them to cease operations.

The production at Aurora was only slightly less in 1917 than in 1916. A new mill was built by Matthes, Phelps Co., and the Daisy Bell mill was moved to the Schmook land.

The principal producers in Christian County were the W. N. Fink Mining Co. on the W. E. Bain land, the Robertson Mining Co. on the Deeds land, and the Bray Mining Co. on the Arnold land. All the mines are in the Ozark district, and concentrating plants were erected at the two first-mentioned properties.

Considerable prospecting and drilling was done near Seymour, in Webster County, by the Chaffin-Simmons Mining Co., and near Mansfield, in Wright County. A small quantity of ore was shipped from Mansfield by the R. S. & T. Mining Co and the Red Bird Mining Co., and the Mansfield Mining & Development Co. has drilled its leases and erected concentrating plants.

The production from Howell and Taney counties in 1917 was confined to a few tons of zinc carbonate and silicate and the only output from Ozark County was that of Nixon, Gunn & Brosius, from the old Alice mine and that of the Southwestern Zinc Co.'s property, near Sharpe.

CENTRAL AND SOUTHEASTERN MISSOURI.

The ore deposits of central and southeastern Missouri reach in a more or less connected belt from the region of Benton, Pettis, Morgan, Moniteau, Cole, and Miller counties on the northwest to the northern and eastern flanks of the St. Francis Mountains on the southeast. It is also true that there are scattered areas where more or less mining has been done all the way between the northwest end of this belt and the Joplin region, so that strictly speaking the lead and zinc deposits of Missouri practically form a zone around the northern half of the Ozark dome. A brief description of the ore deposits in central and southeastern Missouri is given in the separate chapter entitled "Silver, copper, lead, and zinc in the Central States in 1915," which can be obtained upon application to the Director, United States Geological Survey, Washington, D. C.

The ore in the southeastern Missouri region is almost wholly lead, although a considerable zinc deposit occurs at Valle mines, some 6 miles north of the Bonneterre district, and a considerable quantity of zinc silicate is mined in various parts of Washington and Jefferson counties. A certain percentage of zinc is also found in the disseminated lead ore, the ore from one shaft being reported to run occasionally as high as 2 per cent of zinc for a week at a time. The zinc occurs more plentifully in the Leadwood-Flat River district and may lie near the contact of the Bonneterre limestone with the Lamotte sandstone or some distance above it. In the lead concentrates zinc ranges from 1 to 5 or more. In the maximum proportions mentioned the zinc makes trouble in lead smelting, and for this reason some of the concentrating plants remove the zinc as a table middling.

Digitized by Google

Copper, nickel, and cobalt also occur in the ore, in considerable quantity in the vicinity of Fredericktown, and in small quantity, irregularly, in nearly all the deep mines. It is only near Fredericktown that the copper, nickel, and cobalt content of the ore has been the object of mining, yet a concentrate of these metals has been recovered as a table middling at several plants in other parts of the district, and 3,115 tons of copper concentrates were shipped in 1915, 2,878 tons in 1916, and 2,304 tons in 1917. From these copper concentrates 354,753 pounds of copper were recovered in 1917. In the disseminated ore district the production since 1869 increased rapidly and is estimated by Buckley to have amounted to 1,202,607 tons of lead concentrates, valued at $59,869,354, for the period between 1869 and 1906, inclusive. The mine production of southeastern and central Missouri has been reported to the United States Geological Survey since 1907.

Mine production of lead and zinc concentrates in southeastern and central Missouri, 1907–1917.

Year.	Lead concentrates—galena.		Zinc concentrates.			
			Sphalerite.		Carbonate and silicate.	
	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.
1907	156,663	$7,910,398	100	$3,500	1,095	$15,330
1908	183,095	6,906,116	42	1,050	1,360	20,496
1909	210,620	8,823,297	41	938	1,264	17,334
1910	210,890	9,360,309	.....	.....	929	19,000
1911	219,145	10,293,400	113	3,990	510	11,576
1912	218,803	9,849,854	40	1,292	1,051	21,020
1913	219,511	9,580,803	33	574	639	13,491
1914	249,165	9,710,125	40	700	497	11,283
1915	278,104	12,773,579	43	1,064	1,061	39,460
1916	307,025	20,720,737	365	14,400	1,030	42,129
1917	306,473	30,070,995	156	16,344	293	7,145

A comparison of the estimates for the period of years to 1906 given by Winslow and Buckley for Washington and St. Francois counties (which have supplied a very large proportion of the galena ores from southeastern and central Missouri) with the figures in the preceding table indicates a production of galena concentrates during the last 11 years much greater than the entire output of southeastern and central Missouri prior to 1907.

The lead ore of southeastern Missouri carries a small proportion of silver, the average being less than 1 troy ounce to the ton of lead concentrates. The resulting pig lead likewise carries silver, together with a little copper, nickel, cobalt, and traces of antimony and arsenic, and is sometimes commercially known as "Missouri chemical" lead in contradistinction to "Missouri soft" lead from the Joplin region. An average of about 15 per cent of the total lead concentrates from southeastern Missouri is desilverized. The silver so recovered does not pay for the refining charges, but the desilverized lead commands a slightly higher price, making up the difference. As the silver content of the concentrates is so small, it is disregarded in their sale, and therefore the smelter reports are relied upon for the produc-

Digitized by Google

tion of silver. As already explained, the quantity of silver produced during any year bears no direct ratio to the quantity of silver-bearing lead concentrates smelted during that year, for the reason that the silver bullion is stored and refined in batches at convenient times.

The output of silver in Missouri in 1917 was derived almost entirely from lead concentrates, the only other source of production being about 2,400 ounces recovered from copper ore and from copper concentrates recovered in dressing lead ores, which were shipped to smelters.

The production of silver in southeastern Missouri was 61,586 fine ounces in 1917, as compared with 129,450 fine ounces in 1916, 57,756 fine ounces in 1915, 61,168 fine ounces in 1914, 35,620 fine ounces in 1913, 35,438 fine ounces in 1912, 49,867 fine ounces in 1911, 33,096 fine ounces in 1910, 14,188 fine ounces in 1909, and 49,131 fine ounces in 1908. The production of silver in 1917 was recovered from 76,222 tons of lead concentrates and from copper ore and concentrates that averaged a little more than 1 ounce a ton.

The crude lead ore mined in the disseminated lead district in 1917 amounted to 5,887,900 short tons, against 5,467,500 short tons in 1916, 5,067,400 short tons in 1915, 4,718,300 short tons in 1914, 4,250,800 short tons in 1913, and 4,064,366 short tons in 1912. The crude ore in 1917 yielded 5.03 per cent of lead concentrates, which averaged 66.7 per cent of lead. The average value per ton of the lead concentrates in 1917 was $98.01, as compared with $67.47 in 1916, and the concentrates were slightly higher in lead content than in 1916. The output of galena concentrates was 306,473 tons, valued at $30,070,995, in 1917, against 307,025 tons, valued at $20,720,737 in 1916. As several of the large producers not only mine but also smelt their lead concentrates, the values given for concentrates are arbitrary to a certain extent. The galena concentrates produced in the southwestern Missouri region containing a higher lead content are mainly sold on bids from various purchasers, and the prices for those lead concentrates are not comparable with prices given for concentrates of the disseminated lead district.

Analyses of ores mined in disseminated lead district in southeastern Missouri and of the various grades of resulting concentrates.[a]

	Ag	Cu	Pb	SiO_2	Fe	Al_2O_3	CaO	MgO	Zn	S	Ni and Co
	Ozs. per short ton.	*Per cent.*	*Per cent.*	*Per cent.*	*Per cent.*	*Per cent.*	*Per cent.*	*Per cent.*	*Per cent.*	*Per cent.*	*Per cent.*
Ore (crude)	0.12	0.06	5.7	5.0	4.1	4.9	25.5	14.2	0.8	2.0	.....
High-grade concentrates	.7	.13	73.2	1.0	3.5	.....	2.6	.8	.4	15.0	0.05
Medium-grade concentrates	1.3	.12	68.6	1.4	4.6	.....	3.1	1.4	.8	15.5	.06
Low-grade concentrates	1.0	.30	65.8	.5	3.1	.5	4.3	2.8	1.7	13.7	.....
Flotation slimes, concentrates	.....	.50	45.0	9.6	4.4	3.1	7.5	4.2	4.0	12.3	.....
Flotation slimes, high-grade concentrates	3.7	.05	57.8	6.0	2.7	.....	2.2	1.4	9.4	15.5	.....
Joplin (southwestern Missouri) concentrates	.....	.....	80.2	1.1	1.0	.....	.4	.....	1.7	13.3	.....

[a] Garlichs, Herman, Metallurgy of lead ores in the lower Mississippi Valley: Am. Inst. Min. Eng. Bull., July, 1917, pp. 1041-1046.

NOTE.—A typical analysis of southeastern Missouri undesilverized lead is as follows: Ag, 0.0080 (2.4 oz. per short ton); As, trace; Sb, 0.0080; Bi, trace; Cu, 0.0800; Fe, 0.0015; Zn, trace; Ni and Vo, 0.0080; lead by difference, 99.8995.

Digitized by Google

The production of sphalerite from central and southeastern Missouri in 1917 amounted to only 186 tons, valued at $16,344, which was only one-half the production of 1916. The production of zinc carbonate from southeastern Missouri in 1917 amounted to 293 tons, against 1,030 tons in 1916.

Nearly all the zinc carbonate was shipped by the Merseal Allee Timber Co. and the Valle Mining Co., both in Jefferson County, and the sphalerite was shipped by the Bluff Springs Mining Co. and by the Pearce Mining Co., in Morgan County. The Bluff Springs Mining Co. abandoned the mine near Tipton and is opening a barytes and lead deposit near Centertown, in Cole County. The production of galena and zinc carbonate from the Valle mines was much less than usual and very few lessees were working. The company's work was mainly that of sinking new shafts.

The quantity of galena recovered from shallow diggings in Washington and Jefferson counties was only about 400 tons. The high wages paid by the large mines in St. Francois and Madison counties attracted miners and laborers who normally lease and work many of the shallow diggings. The ore, which occurs at shallow depths and in association with barytes, is mined in a small way and at odd times by the barytes miners. This ore is all hand picked and cleaned, there being no concentrating plants. There are numerous other shallow lead and barytes diggings scattered over Washington County which are worked by small operators and farmers, who sell their product to the country merchants and to ore buyers. Much of this ore was purchased by J. F. Evans, of Potosi, and P. G. Higginbotham, of Fertile.

Although the production of galena concentrates from the disseminated lead district was about the same in 1917 as in 1916, the value of the output showed a large increase. The foreign laborers were attacked by the native miners in July, 1917, and military authority was necessary before order was restored. Few lives were lost but considerable damage was done to property of foreigners.

The St. Joseph Lead Co., which includes the old Doe Run property, produced more than one-half the lead production of southeastern Missouri. Seven shafts, ranging from 400 to 500 feet in depth, were operated in 1917. The concentrating plant operated in the Flat River district has a capacity of 4,000 tons a day, that at Bonne Terre 2,400 tons, and that at Leadwood 1,800 tons. All mill machinery, mine hoists, pumps, and compressors are motor driven. The two gas-producer electric plants at Rivermines and Bonne Terre were shut down upon the completion of the new 6,000-kilowatt steam turbine plant at Rivermines, which with the steam turbine plant at Leadwood now supplies power for all mining and milling operations.

The Desloge Lead Co. also had an increased output. Three shafts having an average depth of 366 feet were operated in 1917 and a new filter plant and other equipment were added to the concentrating plant, which has a capacity of 1,500 tons a day. The installation of Myers-Whaley shoveling machines and gasoline motors for underground haulage reduced the cost of mining very considerably.

The Federal Lead Co. operated four shafts in 1917, mining and milling 1,870,000 tons of crude ore. Early in 1917 a new concentrating plant of 3,000 tons capacity per day was put in commission and was served by the new No. 12 shaft. This mill, which is known

Digitized by Google

as No. 4 mill, is most substantially constructed of reinforced concrete and steel and represents the latest practice in lead concentration of southeastern Missouri ores. The older mill, known as mill No. 3, has a capacity of 4,800 tons.

The mines and mills of the Federal Lead Co. are at and near Flat River, St. Francois County, Mo.

The Phoenix Lead Co. and the Fleming property in Madison County, near Fredericktown, Mo., were operated under lease by the Federal Lead Co., but operations there were closed at the end of the year.

The mines of the St. Louis Smelting & Refining Co. are in the vicinity of the village of St. Francois, about 1 mile north of Flat River. The concentrating plant is modern, having a capacity of 2,500 tons per day of 24 hours, and is equipped with Hancock jigs, Overstrom classifiers, and Butchart tables, and slime and settling tanks. A central steam-power plant drives air compressors and electric generators. The mill, hoists, and pumps are operated by electricity as well as the underground haulage and the trams for handling the ore from the shafts to the mill. This company also operates a lead smelter and refinery at Collinsville, and the lead concentrates produced by the mines and also those derived from crude ore purchased from the Baker Lead Co. and the Boston Elvin Lead Co. were smelted at that plant.

The Baker Lead Co., which owns the Jake Day tract near Big River, operated one shaft 400 feet in depth. There is no concentrating plant on the property and the ore was hauled to the National mill of the St. Louis Smelting & Refining Co., to which the crude ore was sold.

The Boston Elvins Lead Co., which owns a 40-acre tract at Elvins, also sold its crude ore. The shaft at this mine is 650 feet deep and 3-ton skips were used for hoisting ore. Operations were commenced in April, 1917, and continued until July, when the pumping equipment broke down and the mine remained flooded until the end of the year. A new centrifugal pump has been installed and the mine will be unwatered.

The old Mine La Motte property, in Madison County, which was taken over by the Missouri Metals Corporation, in addition to the shipment of lead concentrates to the St. Louis Smelting & Refining Co., produced and shipped a considerable quantity of copper concentrates. In certain parts of the property copper and nickel-cobalt sulphides occur, but the mining of such ores had been avoided in recent years until the Missouri Metals Corporation took over the property. Some silver was recovered from the copper concentrates in 1917, but no nickel or cobalt was recovered.

The ore deposits at Mine La Motte are relatively shallow, and the mine development during 1917 was largely in the nature of diamond drilling and in stripping the overburden to bed rock so that the property can be worked by open cuts and all underground mining can be suspended. The crushing plant had been completed and the large picking plant under construction will be finished and operated in July, 1918. The concentrating tables and other mill machinery have been rearranged to accommodate the increased quantity of ore handled by the new crushing plant.

Digitized by Google

The Buckeye or North American mine at Fredericktown was unwatered by the Missouri Cobalt Co. There were two shafts in operation, and a concentrating plant of 300 tons capacity and a 100-ton smelter were completed in 1917. A new refinery for the treatment of cobalt, nickel, and copper was under construction. The lead concentrates produced will be smelted at the Federal plant and the copper concentrates containing nickel and cobalt will be shipped to the Commercial Acid Co., of St. Louis, for making sulphuric acid. The cinders from the copper concentrates will then be returned to the smelter and refinery of the Missouri Cobalt Co. for the recovery of the cobalt, nickel, and copper.

OKLAHOMA.

By J. P. DUNLOP.

PRODUCTION.

Production of lead and zinc in Oklahoma in 1917.

District.	Ores.					
	Lead concentrates (galena).		Zinc concentrates.			
			Sphalerite.		Carbonate and silicate.	
	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.
Ottawa County:						
Miami	32,557	$3,280,853	158,722	$10,704,968	.....	.....
Quapaw	208	19,781	934	57,356	.....	.....
Peoria	10	900	.....	.....	124	$4,931
Murray County—Davis	.....	.....	.....	.....	144	4,197
Total, 1916	32,775	3,301,534	159,656	10,762,324	268	9,128
	15,344	1,283,789	55,124	4,118,723	509	25,621

District.	Metal content.[a]			
	Lead.		Zinc.	
	Quantity (short tons)	Value.	Quantity (short tons).	Value.
Ottawa County:				
Miami	26,186	$4,503,992	85,266	$17,394,264
Quapaw	164	28,208	478	97,512
Peoria	8	1,376	45	9,180
Murray County—Davis	.....	.....	46	9,384
Total, 1916	26,358	4,533,576	85,835	17,510,340
	12,115	1,671,870	28,754	7,706,272

[a] In calculating the metal content of the ores for assays, allowance has been made for smelting losses of zinc, but not of lead. In comparing the values of ore and metal it should be borne in mind that the value given for the ore is that actually received by the producer, whereas the value of the lead is calculated from the average sales price of all grades. The zinc price is the average sales price of all grades reported by smelters.

Digitized by Google

The following table gives the output of crude lead and zinc ore for the whole State of Oklahoma, but it was thought advisable to calculate the tenor of crude ore and concentrates as well as assay content and value of concentrates separately for the Miami and Quapaw districts, inasmuch as the character of the ground operated in these districts has, until the new mines in the easterly extension of the Miami district, near Quapaw, were opened in 1918, differed so radically that general calculations for the State would be valueless:

Tenor of lead and zinc ore and concentrates produced in Oklahoma, 1916 and 1917.

	1916	1917
Total crude ore milled in Oklahoma.....short tons..	1,406,900	3,523,200
Miami district:		
Total concentrates in crude ore:		
Lead.....per cent..	1.15	0.94
Zinc.....do....	4.03	4.56
Metal content of crude ore:		
Lead.....do....	.91	.76
Zinc.....do....	2.33	2.72
Average lead content of galena concentrates.....do....	79.0	80.4
Average zinc content of sphalerite concentrates.....do....	57.77	59.6
Average value per ton:		
Galena concentrates.....	$83.94	$100.77
Sphalerite concentrates.....	$74.80	$67.44
Quapaw district:		
Total concentrates in crude ore:		
Lead.....per cent..	.07	.51
Zinc.....do....	2.42	2.30
Metal content of crude ore:		
Lead.....do....	.06	.41
Zinc.....do....	1.31	1.32
Average lead content of galena concentrates.....do....	77.0	78.8
Average zinc content of sphalerite concentrates.....do....	54.2	56.9
Average value per ton:		
Galena concentrates.....	$71.79	$95.10
Sphalerite concentrates.....	$75.30	$61.41

The chapter on the production of lead and zinc in Oklahoma in Mineral Resources for 1914 contains a brief history of mining in the various districts and also the estimated total production of each district, by years.

Mine production of lead and zinc concentrates in Oklahoma, 1891–1917.

District.	Lead concentrates (mainly galena).		Zinc concentrates.			
			Sphalerite.		Zinc silicate and carbonate	
	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.
Peoria.....	2,042	$96,098	97	$3,129	2,679	$71,724
Quapaw.....	3,829	241,860	31,589	1,368,632	164	2,692
Miami.....	90,043	6,744,824	336,395	19,542,614	.....	.....
Davis.....	.....	.....	558	27,399	899	24,592
	95,914	7,082,782	368,639	20,941,774	3,742	99,008

The total value of the lead and zinc concentrates produced in Oklahoma in 1917 was approximately 159 per cent greater than in 1916 and followed an increase of 127 per cent in 1916.

Digitized by Google

The lead and zinc deposits of northeastern Oklahoma, so far as known, are confined to the limits of Ottawa County and form the southwestern extension of the Joplin region. There are three camps, Peoria, Quapaw, and Miami, in this county, in which extensive mining has been done, and a fourth, the Sycamore Creek district, along the Seneca fault block from 2 to 3 miles southwest of Seneca, Mo., in which considerable prospecting has been done and some ore mined.

The lead and zinc deposits in southern Oklahoma are near Ravia, at the southeast end of the Arbuckle Mountains, and near Davis, Murray County, at the northwest end of the same range.

The quantity of crude ore milled in Oklahoma increased from 1,406,900 tons in 1916 to 3,523,200 tons in 1917, notwithstanding that the quantity of ore milled by the old mines near Commerce was less in 1917 than in 1916.

The value of the recoverable lead and zinc produced at mines in Oklahoma in the year 1917 was $22,043,916, compared with $9,378,142 in 1916. The metal content of lead concentrates increased from 12,115 tons, valued at $1,671,870, in 1916, to 26,358 tons, valued at $4,533,576, in 1917, and the recoverable zinc increased from 28,754 tons, valued at $7,706,272, to 85,835 tons, valued at $17,510,340.

In 1917 the lead concentrates produced in the Oklahoma districts were of considerably higher grade than those shipped in 1916. The average metal content of the sphalerite concentrates from Miami ore increased from 51.8 per cent in 1912 to 53.6 per cent in 1913, to 54.8 per cent in 1914, to 55.7 per cent in 1915, to 55.77 per cent in 1916, and to 59.6 per cent in 1917, and was 2.7 per cent more than the average metal content of the sphalerite from the Quapaw district in 1917.

The lead concentrates from Oklahoma sold in 1917 were 17,431 tons more in quantity and $2,017,745 greater in value than in 1916. Miami district produced more lead than any other district in the Joplin region, exceeding the Webb City-Carterville district by about 12,000 tons, and its yield was equal to about 43 per cent of the production of the Joplin region. The Oklahoma shipments of sphalerite in 1917 amounted to 159,656 tons, valued at $10,762,324, an increase of 104,532 tons in quantity and of $6,643,601 in value.

The shipments of zinc carbonate and silicate decreased from 509 tons in 1916 to 268 tons, valued at $9,128 in 1917. The Miami district yielded about 96 per cent of the sphalerite concentrates and more than 99 per cent of the galena concentrates sold in Oklahoma in 1917.

Peoria district.—The production at Peoria, the oldest mining camp in the State, was only a few tons of galena and 124 tons of zinc silicate, most of which was mined by R. E. Lauck, on the Geboe land. This property was purchased by the Silver Crown Mining Co., and it is reported that a sublessee, the Mount Nebo Lead & Zinc Co., is building a mill.

Davis district.—The production from the Davis district, in Murray County, southern Oklahoma, in 1917, was 144 tons of zinc silicate, which was mined at shallow levels and shipped by the Grace Mining Co., I. Adler, and McGuire & Coffee.

Quapaw district.—There was a large amount of drilling, shaft sinking, and mill construction in the Quapaw district, especially in

Digitized by Google

that part lying in the immediate vicinity of the town of Quapaw. The total production of concentrates, however, was less in 1917 than in 1916. The sales of galena increased from 61 tons in 1916 to 208 tons in 1917, and those of sphalerite decreased from 1,986 tons in 1916 to 934 tons in 1917. The total value of the concentrates sold in 1917 was $77,137, a decrease of about 50 per cent. There should be a large increase in the production of both lead and zinc in 1918, even if only a part of the new mills built and now under construction are operated. Many leases at the Lincolnville and Sunnyside camps were acquired by new owners and drilled to levels lower than the ore bodies worked in former years. Many new mines were opened in the town of Quapaw, and immediately south, north, and west of that town, which has grown from a small village to a bustling, business community. Among the new mines and old properties which have been opened and reopened, most of which have been equipped with concentrating plants or hand jigs, are the Sambo and the Myrtle on the Buck land, the Aurora Mining Co., Old Reliable Mining Co., Canton Mining Co. (old Mission), O. T. Oil & Gas Co. (old Katy), Hawkins Lead & Zinc Co., Lead Boy Mining Co., Morgan Zinc Co., Red Rose Mining Co., True Blue Mining Co., Benson Kirtley Mining Co., Bethlehem Zinc Co., National Lead & Zinc Co., Muskogee Lead & Zinc Co., Red Eagle Mining Co., Hare Development & Operating Co., Quajack Mining Co., McCurdy Mining Co., Springfield Mining Co., Kentex Mining Co., Miami District Mining Co., White Swan Mining Co., Allied Mining Co., Prairie Dog Mining Co., Scott Eagle Mining Co., Associated Lead & Zinc Co., Doris Mining Co., and St. Louis Lead & Zinc Co.

Miami district.—A history of the mining in this district, including the output by years for the period 1908 to 1914, and the location of the mines and mills, was given in this report for the year 1914, copies of which can be obtained on request. The reports for the years 1915 and 1916 contain full reviews of the production, new territory prospected, new mines opened, and new mills erected in those years.

A brief description of the ore deposits in the Miami district of Oklahoma is given in the separate chapter of Mineral Resources entitled "Zinc in 1915," [1] which can be obtained upon application to the Director, United States Geological Survey, Washington, D. C.

The mines of the Miami district in 1917 shipped 32,557 short tons of galena concentrates, valued at $3,280,853, and 158,722 short tons of sphalerite concentrates, valued at $10,704,968, an increase of 17,412 tons of galena concentrates and of 105,776 tons of sphalerite concentrates when compared with the output of 1916. The average price of the galena concentrates increased about $23 a ton, but the average price of sphalerite concentrates, of which 5 times as much was shipped, decreased $14 a ton.

The unusual increase of more than 100 per cent in the quantity of galena and of 200 per cent in the quantity of sphalerite does not adequately show the active development which continued from 1916 into 1917. It is difficult to realize the possibilities of the output had there not been some shortage of labor and supplies and lower prices of sphalerite. It is questionable whether it was advis-

[1] See also Siebenthal, C E., Zinc: U. S. Geol. Survey Mineral Resources, 1915, pt. 1, pp. 888-890, 1917.

Digitized by Google

able to force such rapid development, or rather production, in face of high operating costs and declining values. Many of the mines recovered large quantities of galena which made operation profitable, notwithstanding the much lower selling price of sphalerite. The operating costs at Miami are greater than in most of the districts in the Joplin region and the royalties paid average 50 per cent more. The "dirt" or ore mined in 1917 averaged 1.50 per cent more in concentrates than that of all the "dirt" from "soft ground" treated in southwestern Missouri, and the average quantity of galena in the "dirt" at Miami was three times as great. The increased recovery of concentrates in the Miami district compensated for the higher operating costs, but it is certain that some of the Miami mines could not have profitably mined ore during the last part of 1917.

The extension of the Mineral Belt Railway to the northerly end of the district and the completion of the extension of the Southwestern Missouri Electric Railway from Galena, Kans., to the Hockerville and Picher camps have provided adequate transportation facilities for the entire district.

The production in 1917 in the Miami district was that of about 80 mills, of which 15 were in the old Commerce camp and the remainder in the territory north and northeast to the Kansas State line and east to Quapaw. Many of the mills were not operated until the latter part of the year and others were operated intermittently. It is estimated that in June, 1918, there were more than 200 concentrating plants—many of them of large capacity—built or under construction in Ottawa County. It is impossible to give a close estimate of the output in 1918 other than that the production of sphalerite concentrates in the Miami district will probably exceed 225,000 tons, even if the prices of sphalerite do not advance. The only mines which are at present having difficulty in controlling an excessive quantity of water are those lying southeast of Picher and north of Quapaw. Many properties north and west of Treece are delayed in producing concentrates on account of the heavy flow of water. These properties, though in the extension of the Miami district, are in Kansas.

The quantity of crude ore mined and milled increased from approximately 1,314,800 tons in 1916 to 3,479,900 tons in 1917. The percentage of concentrates recovered from crude ore milled was larger than in any other district in the Joplin region, and, with increased operations in the northern part of the district, the ore treated showed an increase in percentage of concentrates recovered from 5.18 per cent in 1916 to 5.50 per cent in 1917. The average increase in recovery from ore was larger than the figures indicate, for a considerable quantity of old tailings was rerun in the old Commerce camp. As a larger proportion of the output of the Miami district in 1917 was derived from mines north of Commerce, which usually yield zinc concentrates of higher grade than those near Commerce, the average metal content of all blende concentrates sold increased from 57.77 per cent in 1916 to 59.6 per cent in 1917. The average metal content was 51.8 per cent in 1912, 53.6 per cent in 1913, 54.8 per cent in 1914, and 57.7 per cent in 1915, so that the total increase in the zinc content of the sphalerite sold has been more than 7 per cent in five years.

The separate assays reported showed the zinc content to range from 48 to 63 per cent, but most of the blende assayed between 55

Digitized by Google

and 59 per cent. Assays of 741 lots of zinc concentrates in 1917 by Thor Relling, of Miami, showed an average content of 59.10 per cent zinc, 1.30 per cent lead, 1.90 per cent iron, and 0.95 per cent lime, and the average content of 240 lots of galena concentrates assayed was 79 per cent lead and 1 per cent iron. These assays reported by Relling very closely approximate the average lead content of galena concentrates and the zinc content of sphalerite concentrates given in the table for the Miami district, though his assays did not include any of the high-grade concentrates produced at the Picher mines. The average selling price of galena concentrates increased from $83.94 in 1916 to $100.77 in 1917, and that of blende concentrates decreased from $74.80 in 1916 to $67.44 in 1917.

The recovery of galena concentrates from all the mines averaged about 1 ton to 5 tons of sphalerite, which is much higher than in any other district in the Joplin region. The proportion of galena concentrates recovered from the "dirt" mined showed wide variations, ranging in different mines from less than 1 ton of galena to 100 tons of sphalerite to 1.4 tons of galena to 1 ton of sphalerite. The mines lying north and northeast of the Quapaw mine near Commerce reported 27,999 tons of galena and 150,336 tons of sphalerite; those lying southwest of the Quapaw mine to the southern limits of the district reported 4,558 tons of galena and 8,387 tons of sphalerite.

The only production in the Horse Shoe Lake camp and the small area lying southwest of Commerce was that of a small quantity of sphalerite from the McConnell land. A new concentrating plant was built by the Green Zinc Co., which was not operated because of an inadequate supply of water for milling.

The old mines at Commerce, the Mispah mine, the farthest south, those on the northwesterly ore run extending to the old Haymaker mine, and those on the northeasterly ore run as far as the Quapaw mine are located on the Emma Gordon and the Commerce Mining & Royalty Co. leases. The producers on Emma Gordon land that shipped concentrates in 1917 were the Standifer Mining Co., High Five Mining Co., Miami Zinc & Lead Co., H. C. & S. Mining Co. (Prairie), and the Haynes Mining Co. which acquired all the interest of the Welch Mining Co. in the Carson mines. The Haynes Mining Co. sunk a winze to the depth of 360 feet, but the development of the ore found at that level was discontinued until prices of ore were better.

The productive mines on leases in the immediate vicinity of Commerce on land of the Commerce Mining & Royalty Co., were the Cactus (Tango shaft), Lost Trail, Mispah, Turkey Fat, King Jack (The Concentrating Co.), Midas, Old Chief, Miami Amalgamated (Sullivan), and the Eureka, now called the T. H. C. Mining Co. Of these mines the Mizpah, Cactus, and Turkey Fat mines were operated by the controlling interests in the Commerce Mining & Royalty Co.

The Worley Mining Co., which was being operated on old tailings and ore from the Old Chief mine was burned in July, 1917, and was not rebuilt. The Quapaw and the Lennan mines on Commerce land at the northeastern limits of the town of Commerce, hoisted ore taken from levels as low as 375 feet, which was the deepest mining in the district.

Those mines situated in the new camps in the vicinity of Tar River, Picher, Douthat, St. Louis, and Hockerville, treated about 3,100,000 tons of crude ore, which yielded 27,999 tons of galena

Digitized by Google

concentrates and 150,335 tons of sphalerite, an average recovery of 0.90 per cent in galena concentrates and 4.86 per cent in sphalerite concentrates and a total recovery of 5.76 per cent. As some of the large mines reported a recovery as high as 7 to 10 per cent, many of the mines must have treated ore that yielded only 3 to 4 per cent, or even less, in concentrates. It is difficult to segregate the producing mines according to camps, but most of the production in 1917 came from the vicinity of Picher, Tar Creek, and Douthat (Century), as the mines near St. Louis and Hockerville were developed last.

The total shipments of those properties which may properly be classed as in the Tar River-Douthat area, of which there were a greater number than in the other areas, were 19,863 tons of galena and 101,512 tons of sphalerite. Slightly less than 2,100,000 tons of "dirt" was milled, so that the recovery in concentrates averaged about 6 per cent. A few of the mines yielded nearly as much galena as sphalerite, in other mines the proportion of galena was as little as 2 per cent.

Among the large producers of galena were the O. M. Bilharz Mining Co., Commerce Mining & Royalty Co. (Blue Goose and Beaver mines), Oklahoma Woodchuck Zinc Lead Co., Central Lead & Zinc Co., Velie Mines Corp., and the Admirality Zinc Co. The largest shippers of sphalerite in 1917 were the Skelton Lead & Zinc Co., Admiralty Zinc Co., Montreal mine, Bethel and Croesus mines, U. S. Smelting & Mining Co., and the Underwriters Land Co.

The other properties in the Tar River-Douthat camp from which were shipped lead or zinc concentrates were the Roanoke, Golden Rod (Nos. 1, 2, 3, and 4), Laclede, Jay Bird, Kitty, Lucky Junction, Republic, Wireck, Vinegar Hill (Wilson mine), Goodeagle, Mihoma, Anna Beaver, Missouri Mule, Potosi, Rialto, Ramage, Manhattan, and Lucky Kid, all of which properties are equipped with one or more concentrating plants, many of which are of large capacity.

Many transfers of lands and leases, some of them reported to be for considerations in excess of a million dollars, were made. The Welch Mining Co. leases equipped with four mills were acquired by the Skelton Lead & Zinc Co. The Golden Rod Mining & Smelting Co. took over a large area of proved ground, including the Mihoma and old McConnell mines, and now own 7 mills, of which 4 produced concentrates in 1917. Aikins, Curtis & Cosden bought the Admiralty Zinc Co. leases and 4 concentrating plants. The O. M. Bilharz Mining Co. has 3 mills, one each at the Blue Bird, Short Horn, and Chapman mines. The Velie Mines Corp. also has 3 mills called the Lion, Panther, and Leopard.

The following mines have been equipped with shafts and milling plants which were not completed or not operated in 1917: Carnegie, Federal, Greening, Kanoak, Pittsburg-Miami, Imperial, Niangua, Boomerang, Lucky Syndicate, Wingfield, Larsh, Triangle, Early Bird, Dorothy Bill, and Sinden.

Although many drills were operated, shafts sunk, and new concentrating plants built in the Hockerville and St. Louis camps east of Picher, there were only five mines from which concentrates were shipped in 1917. About 54,000 tons of ore were milled and 120 tons of galena and 3,859 tons of sphalerite concentrates recovered. The sphalerite averaged more than 60 per cent zinc content and the output of galena was proportionately much less than in other parts

Digitized by Google

of the Miami district. The St. Louis Smelting & Refining Co. has 2 mills of 500 tons capacity each, which are among the best in the Joplin region. No. 1 mill was operated in 1917, but heavy water prevented No. 2 mill from being started. Underwriters mill No. 2, which is northwest of the St. Louis No. 2, had a large output for the short period operated after completion. The other producing mines in this section were the Mahutska, Lucky Jack, and Sequoyah, and shafts were sunk and mills have been built at the following mines; Farmington, Golden Eagle, Merrill (Huttig), Lucky Strike, Choctaw Chief, Blue Bonne, Mary Ann, Black Eagle, and Melrose.

The production of the mines in the vicinity of Picher showed a large increase in 1917. The total quantity of ore treated was 947,800 tons, and 8,016 tons of galena and 44,964 tons of sphalerite concentrates were shipped. Most of the output was that of the Eagle Picher Lead Co., which operated the Whitebird, Bingham, Crawfish, Netta, Goodwin, Perin, and Potter mills, and three flotation plants. The production of both galena and sphalerite by this company was much larger than any other operator in the Miami district. In addition to the output of the mines and mills operated by this company there was a large production from ground subleased to the Vantage Mining Co., St. Joe Mining Co., Piokee Mining Co., Dewdrop Mining Co., and William F. White Mining Co. Other mines from which concentrates were shipped in 1917 were the Acme Mining Co., Commonwealth Mining Co., Walker Mining Co., Trustee Mining Co., and Hare Mining & Milling Co.

Mills which have been constructed but which were not operated in 1917 are the Tiger, Texas, Standard, Ottawa, Billiken, Buffalo, Royal, Premier, Chicago-Miami, New Chicago, Big Chief, Keltner, Leonora, Producers, Beulah B., Grace Walker, Midas, Santa Fe, and Swift.

WISCONSIN.

By J. P. Dunlop.

PRODUCTION.

Production of lead and zinc in Wisconsin in 1917.

District.	Ores.					
	Lead concentrates.		Zinc concentrates.			
	Galena.		Sphalerite.		Silicate and carbonate.	
	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.
Benton-New Diggings	2,779	$266,930	134,186	$3,870,772	430	$12,850
Cuba City	57	5,789	955	19,350	.....	.....
Dodgeville	130	14,245	1,769	45,180	.....	.....
Hazel Green	123	8,925	10,991	287,710	18	540
Highland	301	23,390	2,977	90,523	1,206	43,963
Linden	724	67,348	14,442	377,727	.....	.....
Livingston	408	43,741	26,570	639,037	.....	.....
Mifflin	174	17,462	15,036	426,072	.....	.....
Mineral Point-Montfort	71	6,527	1,195	58,690	646	10,481
Platteville and Potosi	325	33,562	10,623	501,509	.....	.....
Shullsburg	452	44,662	5,172	286,147	.....	.....
Total, 1916	5,544	532,581	223,916	6,602,717	2,300	67,834
	4,187	291,397	201,220	7,395,600	4,261	68,544

Digitized by Google

Production of lead and zinc in Wisconsin in 1917—Continued.

District.	Metal content.[a]			
	Lead.		Zinc.	
	Quantity (short tons).	Value.	Quantity (short tons).	Value.
Benton-New Diggings	2,095	$360,340	36,026	$7,349,304
Cuba City	45	7,740	166	33,864
Dodgeville	101	17,372	493	100,572
Hazel Green	71	12,212	2,363	482,052
Highland	204	35,088	1,040	212,160
Linden	524	90,128	3,514	716,856
Livingston	323	55,556	5,500	1,122,000
Mifflin	134	23,048	3,536	721,344
Mineral Point-Montfort	52	8,944	562	114,648
Platteville and Potosi	245	42,140	4,084	833,136
Shullsburg	345	59,340	2,458	501,432
Total, 1916	4,139	711,908	59,742	12,187,368
	3,043	419,934	56,903	15,223,204

[a] In calculating the metal content of the ores for assays allowance has been made for smelting losses in the case of zinc, but not in the case of lead. In comparing the values of ore and metal it should be borne in mind that the value given for the ore is that actually received by the producer, whereas the value of the lead is calculated from the average sales price of all grades. The zinc price is the average sales price of all grades reported by smelters.

Tenor of lead and zinc ore and concentrates produced in Wisconsin, 1916 and 1917.

	1916	1917
Total crude ore.....short tons..	3,066,500	3,014,800
Total concentrates in crude ore:		
Lead.....per cent..	0.14	0.18
Zinc.....do....	6.72	7.42
Metal content in crude ore:		
Lead.....do....	.10	.13
Zinc.....do....	2.26	2.44
Average lead content of galena concentrates.....do....	72.7	74.7
Average zinc content of sphalerite concentrates.....do....	34.4	32.8
Average zinc content of zinc carbonate concentrates.....do....	21.0	26.7
Average value per ton:		
Galena concentrates	$69.59	$96.06
Sphalerite concentrates	$36.75	$29.48
Zinc carbonate concentrates	$16.32	$29.49

The lead and zinc mines of Wisconsin are in Grant, Iowa, and Lafayette counties and comprise the most important part of the ore deposits of the upper Mississippi Valley region, a historical review of which is given in the Illinois section of this report in Mineral Resources for 1914. A detailed description of the Wisconsin lead and zinc districts and of the mines in each district to the year 1906 is given by Bain.[1] Although mining development has continued and many new mines have been opened, worked out, and abandoned, the area of the mining region has not been enlarged to any extent. The development of the mines subsequent to Bain's report and the output of Wisconsin mines have been given in the reports in Mineral Resources of the United States for the years 1907 to 1916.

The ore deposits occur in the Galena dolomite and in the upper part of the Platteville limestone, both of Ordovician age. The ores are galena, sphalerite or zinc blende, with smithsonite or zinc carbon-

[1] Bain, H. F., Zinc and lead deposits of the upper Mississippi Valley: U. S. Geol. Survey Bull. 294, pp. 81–148, 1906.

Digitized by Google

ate, the last locally known as "dry bone." As a lead region the district has been known from the earliest settlement days. In time the building of smelters near by made a market for the zinc ores. The first zinc ore to be mined was the carbonate found in association with lead in the shallow working above ground-water level. When all the main deposits were worked out down to water level there was a lull in mining in the region. Though the carbonate was known to give place to zinc blende and the lead to continue on below water, it was not deemed profitable to mine when continued pumping was necessary. About 1900 the higher price of zinc led to the opening of some of the deposits below water level, since which time zinc mining has increased until Wisconsin ranks among the largest of the zinc-producing States. The ore bodies are found in perpendicular, horizontal, or inclined cavities known as "openings" or "crevices," "flats," and "pitches." The openings sometimes extend for a considerable distance in a straight line called a "range," and may be mined at different places by different companies. When a range is once established it becomes an important guide in prospecting.

The galena of the district is nonargentiferous, and so far as known the zinc ores are free from cadmium. In some of the mines marcasite is so plentiful that the zinc blende concentrates are reduced to a very low grade. Owing to their nearness in specific gravity, marcasite and blende are very difficult to separate cleanly by hydraulic methods.

Roasting and electromagnetic separation have been utilized in the district for many years—and especially in the last three years—to produce a marketable zinc product. The green sulphide concentrates are roasted in cylindrical roasters to drive off a little sulphur and render the iron sulphide magnetic after which they are treated on electromagnetic separators and yield blende concentrates assaying from 56 to 60 per cent and pyrites tailings, which are purchased by manufacturers of sulphuric acid. Comparatively few of the concentrating plants are equipped with roasters, but practically all the larger mining interests own or control separating plants. Two plants for making sulphuric acid are now under construction which will use the residues from the roasting plants and also the output of some mines which yield a marcasite ore containing small quantities of zinc sulphide.

The roasting and separating plants operated in 1917 were those of the Mineral Point Zinc Co., at Mineral Point, the Linden Zinc Co., at Linden, the Champion plant of the Wisconsin Zinc Co., at New Diggings, the National Zinc Separating Co. and the Zinc Concentrating Co., at Cuba City, the Utt-Thorne Co., at Benton, the Kistler & Stevens Co., at Platteville, and the Oliver Mining Co., at Shullsburg, in Wisconsin, and the Wisconsin Zinc Co., at Galena, Ill.

The average zinc content of the raw sphalerite concentrates sold in 1917 was 32.8 per cent and the average price per ton was $29.48; the corresponding content and price for 1913 were 38 per cent and $21.53; for 1914, 35.05 per cent and $17.73; for 1915, 36.5 per cent and $38.37; and for 1916, 34.4 per cent and $36.75.

The percentage of concentrates recovered from crude ore is much higher than in the Joplin region, but the zinc concentrates average 22 to 25 per cent less in zinc content. On account of these conditions, at many mines no close recovery is made, and the tailings, containing large quantities of zinc, are seldom reworked. The new concentrat-

Digitized by Google

ing plants, however, are being equipped with more tables than formerly. The concentrates from the tables have a very high iron content, but this can be remedied by roasting.

The crude ore yields from 5 to more than 20 per cent of concentrates. The average recovery in concentrates increased from 6.86 per cent in 1916 to 7.60 per cent in 1917, which was a natural reflection of the lower price of sphalerite concentrates. The mining methods are largely determined by the mode of occurrence of the ores, but otherwise are similar to those in vogue in working the pockety ores at Joplin. The milling methods used in the Wisconsin field have been given by Walter Schultz,[1] of the Wisconsin Zinc Co.

The zinc carbonate ore, which is mined principally in the Highland, Benton, and Mineral Point districts, is purchased mainly by the Mineral Point Zinc Co., and made into zinc oxide in the plant at Mineral Point, Wis.

The metal content of the raw sphalerite concentrates sold by the mines varied in 1917 from 18.3 to 56 per cent. The larger portion of the concentrates sold ranged between 28 and 38 per cent. The zinc content of the roasted sphalerite concentrates shipped varied from 57 to 60 per cent.

The value of the mine output of lead and zinc in Wisconsin for the year 1917 was $12,899,276, against $15,643,138 in 1916, a decrease of $2,743,862.

The lead concentrates sold increased from 4,187 tons, valued at $291,397 in 1916 to 5,544 tons, valued at $532,581, in 1917. The sphalerite concentrates sold increased from 201,220 tons to 223,916 tons, though the value of such concentrates decreased from $7,395,609 to $6,602,717.

The quantity of zinc carbonate concentrates shipped decreased from 4,261 tons in 1916 to 2,300 tons in 1917, and the value decreased from $68,544 to $67,834.

The metal content of the lead concentrates in 1917 was 1,096 tons more than in 1916. The recoverable zinc content of the sphalerite and zinc carbonate concentrates in 1917 increased 2,939 tons.

There was less than the normal amount of development work done, as the scarcity of labor, high cost of supplies, and the declining price of sphalerite discouraged many small investors and prospectors. The increase in the production of sphalerite was entirely that of a few large operating companies. The higher prices paid for galena concentrates resulted in greater activity at those mines which recover galena from ore bodies at shallow levels. The concentrating plants built or moved and reconstructed in 1917 were the Bearcat and Hird No. 3, of the Frontier Mining Co., at Benton; the Hoskins, of the Mineral Point Zinc Co., at New Diggings; the Meloy, at New Diggings, and the Jefferson, at Hazel Green, of the Vinegar Hill Zinc Co.; the North Survey, at Dodgeville; the C. S. & H. (old Roosevelt), at Cuba City; Lucky Six No. 2 (under construction), at Linden; New Empire and the New Rose, at Platteville; the Copeland, of the Wisconsin Zinc Co., at Shullsburg, and the Mud Range, at Potosi.

The larger mining interests in the Wisconsin field, which include the Mineral Point Zinc Co., Wisconsin Zinc Co., Vinegar Hill Zinc Co., Frontier Mining Co., and Field Mining & Milling Co., had a combined

[1] Schultz, Walter, Milling Wisconsin lead-zinc ores: Eng. and Min. Jour., July 14, 1917, pp. 82-84.

Digitized by Google

output approximately equal to 50 per cent of all the lead concentrates and 74 per cent of all the zinc concentrates shipped from Wisconsin mines in 1917. Mines controlled by the Optimo Mining Co., Cleveland Mining Co., Saxe, Pollard & Co., and Utt, Thorne & Co., contributed substantially to the output in 1917.

For descriptions of the old mines and concentrating plants on which no essential changes were made during 1917, the reader is referred to the corresponding section of this report in Mineral Resources for 1914, 1915, and 1916.

The Benton-New Diggings district produced about 50 per cent of the galena, 19 per cent of the zinc carbonate, and 60 per cent of the sphalerite shipped from Wisconsin in 1917. Its output was more than five times that of Livingston, the next largest producing district. The districts in Wisconsin that had a smaller production of zinc concentrates in 1917 than in 1916 were Cuba City, Linden, Platteville, Montfort, and Hazel Green. The quantity of ore treated was about 62,000 tons less in 1917 than in 1916, and the quantity of green sphalerite concentrates recovered was 11 per cent larger than in 1916. The average zinc content decreased from 34.4 per cent in 1916 to 32.8 per cent in 1917.

The shipments from the Benton part of the Benton-New Diggings district in 1917 were 1,499 tons of galena, 60,328 tons of sphalerite, and 165 tons of zinc carbonate. The shipments from New Diggings camp were 1,280 tons of galena, 73,858 tons of sphalerite, and 265 tons of zinc carbonate.

The Indian Mound mine at New Diggings was sold to the Laurence Mining Co., and the Connecting Link mine at Cuba City and the Optimo Mining Co. at Linden are reported to be building new concentrating plants in 1918.

The following mines were closed down or abandoned in 1917: Hodge, Klar Piquette, Bell, and West Hill at Platteville, Winskill and Crawhall at Benton, and the Rundell at Livingston. The operation of other properties has been suspended until higher ore prices or reduced costs make it possible to operate them profitably.

UNITED STATES GEOLOGICAL SURVEY PUBLICATIONS ON GOLD, SILVER, COPPER, LEAD, AND ZINC IN THE CENTRAL STATES.[1]

ADAMS, G. I., Zinc and lead deposits of northern Arkansas: Bull. 213, pp. 187–196, 1903. 25 cents.

ADAMS, G. I., and others, Zinc and lead deposits of northern Arkansas: Prof. Paper 24, 118 pp., 1904. 40 cents.

BAIN, H. F., Lead and zinc deposits of Illinois: Bull. 225, pp. 202–207, 1904. 35 cents.

——— Lead and zinc resources of the United States: Bull. 260, pp. 251–273, 1905. 40 cents.

——— Zinc and lead ores in 1905: Mineral Resources U. S. for 1905, pp. 379–392, 1906. $1.

——— Zinc and lead deposits of northwestern Illinois: Bull. 246, pp. 56, 1905. 15 cents.

——— Zinc and lead deposits of the upper Mississippi Valley: Bull. 294, 155 pp., 1906. 75 cents.

——— Reported gold deposits of the Wichita Mountains, Okla.: Bull. 225, pp. 120–122, 1904. 35 cents.

[1] The publications for which a price is given are no longer available for free distribution but can be purchased from the Superintendent of Documents, Washington, D. C.; others can be obtained free on application to the Director of the United States Geological Survey. Some are out of print but may be examined in libraries.

Digitized by Google

BAIN, H. F., VAN HISE, C. R., and ADAMS, G. I., Preliminary report on the lead and zinc deposits of the Ozark region: Twenty-second Ann. Rept., pt. 2, pp. 23–228, 1902. $2.25.

BAIN, H. F., and ULRICH, E. O., The copper deposits of Missouri: Bull. 260, pp. 233–235, 1905. 40 cents.

BUTLER, B. S., and SIEBENTHAL, C. E., Silver, copper, lead, and zinc in the Central States in 1909 (mine production): Mineral Resources U. S. for 1909, pt. 1, pp. 495–531, 1911. 60 cents.

BUTLER, B. S., and DUNLOP, J. P., Silver, copper, lead, and zinc in the Central States in 1910 (mine production): Mineral Resources U. S. for 1910, pt. 1, pp. 611–674, 1911. 75 cents.

——— Idem. For 1911, pp. 793–872, 1912. 90 cents.

——— Idem. For 1912, pp. 437–521, 1913. 90 cents.

——— Idem. For 1913, pp. 81–171, 1914. 70 cents.

——— Idem. For 1914, pp. 27–124, 1915. 75 cents.

CLERC, F. L., The mining and metallurgy of lead and zinc in the United States: Mineral Resources U. S. for 1882, pp. 358–386, 1883. 50 cents.

DUNLOP, J. P., and BUTLER, B. S., Silver, copper, lead, and zinc in the Central States in 1915 (mines report): Mineral Resources U. S. for 1915, pt. 1, pp. 45–137, 1917. See also Butler, B. S., and Dunlop, J. P.

——— Idem. For 1916, pp. 53–157, 1917.

ELLIS, E. E., Zinc and lead mines near Dodgeville, Wis.: Bull. 260, pp. 311–315, 1905. 40 cents.

GRANT, U. S., Zinc and lead deposits of southwestern Wisconsin: Bull. 260, pp. 304–310, 1905. 40 cents.

GRANT, U. S., and BURCHARD, E. F., Geol. Atlas, Lancaster-Mineral Point folio (No. 145), 1907. 5 cents.

IRVING, R. D., The copper-bearing rocks of Lake Superior: Mon. 5, 464 pp., 1883. $1.85.

LINDGREN, WALDEMAR, Resources of the United States in gold, silver, copper, lead, and zinc: Bull. 394, pp. 114–156, 1909. 40 cents.

——— Tests for gold and silver in shales from western Kansas: Bull. 202, 21 pp., 1902. 5 cents.

SIEBENTHAL, C. E., Mineral resources of northeastern Oklahoma: Bull. 340, pp. 187–228, 1908. 30 cents.

——— Origin of the zinc and lead deposits of the Joplin region, Missouri, Kansas, and Oklahoma: Bull. 606, 283 pp., 11 pls., 1915. 25 cents.

SMITH, W. S. T., Lead and zinc deposits of the Joplin district, Missouri-Kansas: Bull. 213, pp. 197–204, 1903. 25 cents.

SMITH, W. S. T., and SIEBENTHAL, C. E., Geol. Atlas, Joplin district folio (No. 148), 1907. 50 cents. Apply to Geological Survey.

ULRICH, E. O., and SMITH, W. S. T., Lead, zinc, and fluorspar deposits of western Kentucky: Bull. 213, pp. 205–213 (25 cents), 1903; Prof. Paper 36, 218 pp., 1905. 40 cents.

VAN HISE, C. R., and LEITH, C. K., The geology of the Lake Superior Region: Mon. 52, 1911. $2.50.

WINSLOW, ARTHUR, The disseminated lead ores of southeastern Missouri: Bull. 132, 31 pp., 1896. 5 cents.

Digitized by Google

GOLD, SILVER, COPPER, AND LEAD IN ALASKA.

(MINES REPORT.)

By G. C. MARTIN.

INTRODUCTION.[1]

The mineral output of Alaska in 1917 was valued at about $40,000,000. This is less than the output in 1916, which was nearly $50,000,000, including metals and nonmetals, but is greater than the output in any other year. The decrease was chiefly in copper, the production of which fell from 119,854,839 pounds, valued at $29,484,291, in 1916, to 88,793,400 pounds, valued at $24,240,598, in 1917. The reduction in the output of copper was due largely to labor troubles, which included a strike at the Kennecott mine and a shortage of labor at other mines. The production of gold declined about $2,500,000, and was the smallest since 1904. The reduction in output of gold was due chiefly to curtailment of operations because of the scarcity of labor and the high cost of materials, but in part also to the disaster from cave-in at the Treadwell mine in the month of April and to the depletion of some of the richer placers. There was a reduction in the output of silver, which was due to the decrease in production of gold and copper. The value of the silver produced in Alaska in 1917 was, however, the greatest in the history of mining in that Territory. The production of lead increased slightly.

PRODUCTION.

The following table gives an estimate of the total production of gold, silver, copper, and lead since the beginning of mining in 1880. The figures for the earlier years, especially for silver, are probably far from being correct, but they are based on the best information now available.

[1] The data on mining conditions and production here given are abstracted from a paper by G. C. Martin, published in United States Geological Survey Bulletin 692. Mr. Martin was assisted in the statistical work by T. R. Burch. The original paper and the papers that accompany it treat the subject at greater length than is desired here and should be consulted by those who require the more detailed information. Some of the figures here given are revisions of those in the original paper.

Digitized by Google

Gold, silver, copper, and lead produced in Alaska, 1880–1917.

Year.	Gold.	Silver.		Copper.		Lead.	
		Quantity (fine ounces).	Commercial value.	Quantity (pounds).	Value.	Quantity (tons).	Value.
1880	$20,000			3,933	$826	.....	.....
1881	40,000			.....	.....	.....	.....
1882	150,000			.....	.....	.....	.....
1883	301,000	10,320	$11,146	.....	.....	.....	.....
1884	201,000			.....	.....	.....	.....
1885	300,000			.....	.....	.....	.....
1886	446,000			.....	.....	.....	.....
1887	675,000			.....	.....	.....	.....
1888	850,000	2,320	2,181	.....	.....	.....	.....
1889	900,000	8,000	7,490	.....	.....	.....	.....
1890	762,000	7,500	6,071	.....	.....	.....	.....
1891	900,000	8,000	7,920	.....	.....	.....	.....
1892	1,080,000	8,000	7,000	.....	.....	30	$2,400
1893	1,038,000	8,400	6,570	.....	.....	40	3,040
1894	1,282,000	22,261	14,257	.....	.....	35	2,310
1895	2,328,500	67,200	44,222	.....	.....	20	1,320
1896	2,861,000	145,300	99,087	.....	.....	30	1,800
1897	2,439,000	116,400	70,741	.....	.....	30	2,160
1898	2,517,000	92,400	54,575	.....	.....	30	2,240
1899	5,602,000	140,100	84,276	.....	.....	35	3,150
1900	8,166,000	73,300	45,494	.....	.....	40	3,440
1901	6,932,700	47,900	28,598	250,000	40,000	40	3,440
1902	8,283,400	92,000	48,590	360,000	41,400	30	2,460
1903	8,683,000	143,600	77,843	1,200,000	156,000	30	2,520
1904	9,160,000	198,700	114,934	2,043,586	275,676	30	2,580
1905	15,630,000	132,174	80,165	4,805,236	749,617	30	2,620
1906	22,036,794	203,500	136,345	5,871,811	1,133,260	30	3,420
1907	19,349,743	149,784	98,857	6,308,786	1,261,757	30	3,180
1908	19,292,818	135,672	71,906	4,585,362	605,267	40	3,360
1909	20,411,716	147,950	76,934	4,124,705	536,211	69	5,934
1910	16,126,749	157,850	85,239	4,241,689	538,695	75	6,600
1911	16,853,256	460,231	243,923	27,267,878	3,408,485	51	4,590
1912	17,145,951	515,186	316,839	29,230,491	4,823,031	45	4,050
1913	15,626,813	362,563	218,988	21,659,958	3,357,293	6	528
1914	15,764,259	394,805	218,327	21,450,628	2,852,934	28	1,344
1915	16,702,144	1,071,872	543,393	86,509,312	15,139,129	437	41,118
1916	17,241,713	1,379,171	907,495	119,854,839	29,484,291	820	113,160
1917	14,657,353	1,239,150	1,021,060	88,793,400	24,240,598	852	146,584
	292,758,009	7,541,609	4,750,466	428,561,614	88,644,470	2,933	369,348

A small quantity of zinc was reported from one mine in 1917.

GOLD AND SILVER.

The following table gives an estimate, based on the best available data, of the source of the gold and silver produced in Alaska since mining began in 1880. About $65,100,000 in gold, or nearly one-fourth of the total estimated output, was produced before 1905, and there is only scant information regarding its source. For the production since that time fairly complete statistical returns are available, and the figures presented in the following table are probably approximately correct. The estimates given for the silver recovered from placer gold and from siliceous ores are perhaps less accurate than those for the gold. Copper mining did not begin in Alaska until 1901, and the figures for the gold and silver derived from that source are therefore a close approximation to the actual output.

Digitized by Google

Gold and silver produced in Alaska, 1880–1917, by sources.

	Gold.		Silver.	
	Quantity (fine ounces).	Value.	Quantity (fine ounces).	Value.
Siliceous ores[a]	4,066,066	$84,053,030	1,230,793	$842,129
Copper ores	75,561	1,561,987	4,607,493	2,946,627
Placers	10,020,542	207,142,992	1,703,323	961,710
	14,162,169	292,758,009	7,541,609	4,750,466

[a] Including small quantity of lead ore.

This table shows that about 28.5 per cent of the total gold produced in Alaska has been obtained from siliceous ores taken from auriferous lode mines. In 1917 the lode gold produced was 31 per cent of the total produced; in 1916, 38 per cent; in 1915, 37 per cent; in 1914, 32 per cent; in 1913, 31.6 per cent; and in 1912, 29 per cent. In the following table the production of precious metals in 1917 has been distributed as to sources:

Gold, silver, copper, and lead produced in Alaska in 1917, by sources.

Source.	Ore.	Gold.	Silver.	Copper.	Lead.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*
Placers		474,558.75	64,410		
Dry or siliceous ores	3,414,664	221,505.73	131,631		1,688,168
Copper ore	659,951	12,830.16	1,040,185	88,790,310	
Lead, lead-zinc, and copper-lead ores	42	154.81	2,924	3,090	16,292
	4,074,657	709,049.45	1,239,150	88,793,400	1,704,460

LODE MINING.

Thirty-one lode gold mines were operated in 1917 and 9 prospects or small mines also produced gold but were not in regular operation. In 1916 29 lode mines were in operation. The value of the output of lode gold decreased from $5,912,736 in 1916 to $4,581,453 in 1917. Southeastern Alaska, especially the Juneau district, is still the only large quartz-mining region in the Territory. Next in lode output is the Willow Creek district. There was also considerable lode mining on Prince William Sound. The production in the Fairbanks district increased slightly, but lode-mine owners of Fairbanks are still awaiting the cheapening of operating costs, especially of fuel, which will be brought about by the Government railroad. Of the producing deep mines, 10 were in southeastern Alaska, 3 on Prince William Sound, 4 on Kenai Peninsula, 5 in the Willow Creek district, and 9 in the Fairbanks district. In 1917 the average value of the gold and silver contents for all siliceous ores mined was $1.37 a ton; the average for 1916 was $1.70 a ton. These averages show the dominance of the large quantity of low-grade ores treated in the Juneau district.

The production, by districts, of gold and silver in 1917 from lode mines, including small quantities from lead-silver mines (which can not be given separately without disclosing individual productions), is given in the following table:

Digitized by Google

Gold and silver produced from lode mines in Alaska in 1917.

District.	Mine operated.	Ore mined (short tons).	Gold.		Silver.		Average value per ton of ore in gold and silver.
			Quantity (fine ounces).	Value.	Quantity (fine ounces).	Value.	
Southeastern Alaska	10	3,400,120	205,107	$4,239,914	129,691	$106,865	$1.28
Prince William Sound	[a] 3	5,350	4,509	93,208	697	575	17.53
Kenai Peninsula	4	140	223	4,614	124	102	33.68
Willow Creek	5	7,885	9,465	195,662	713	588	24.89
Fairbanks district [b]	[c] 9	1,200	2,311	47,781	2,217	1,827	41.34
Seward Peninsula [d]	(e)	5	13	274	145	119	78.60
	31	3,414,700	221,628	4,581,453	133,587	110,076	1.37

[a] Also five prospects.
[b] Includes some lead ore.
[c] Also two prospects.
[d] Lead ore.
[e] One prospect on Seward Peninsula, also one shipment from an unknown locality.

PLACER MINING.

The value of the placer gold produced in Alaska in 1917 was about $9,810,000; in 1916 it was $11,140,000. The decrease was due chiefly to restriction of operations by the high cost of supplies and the scarcity of labor. These adverse conditions were felt in all parts of Alaska and everywhere tended to reduce the output of gold. Production was increased only where local conditions permitted an expansion of the industry notwithstanding increased costs. Such conditions prevailed in some of the newly discovered camps, and consequently there was an increase in the output of placer gold in the Tolovana, Marshall, Tolstoi, and Koyuk or Dime Creek districts. The production of the Ruby district increased slightly owing to the very successful operation of the Greenstone dredge. There was also an apparent increase in the output of the Kuskokwim region, but this may be due to underestimates of the production in 1916.

About 610 placer mines were operated in the summer of 1917 and 200 during the preceding winter, but many mines were operated for only a part of the season. About 3,550 men were engaged in productive placer mining in the summer and 950 in the winter. In addition several hundred men were prospecting or were engaged in other nonproductive work relating to placer mining. The only new placer-bearing areas discovered in 1917 were in the Kuskokwim region, and these have not yet produced much gold.

The following table is based in part on returns made by operators of placers and in part on certain other information which is not available for 1917. The figures for 1917 are based on the assumption that the ratio of the recovery per cubic yard for the mines that supplied complete information to the recovery per cubic yard for all the mines is the same as in 1916. Therefore, although the table is only approximately correct it probably indicates the magnitude of the true figures.

Digitized by Google

Estimated quantity of gravel sluiced in Alaskan placer mines and value per cubic yard of gold recovered, 1908–1917.

Year.	Total quantity of gravel (cubic yards).	Value of gold recovered per cubic yard.	Year.	Total quantity of gravel (cubic yards).	Value of gold recovered per cubic yard.
1908	4,275,000	$3.74	1913	6,800,000	$1.57
1909	4,418,000	3.66	1914	8,500,000	1.26
1910	4,036,000	2.97	1915	8,100,000	1.29
1911	5,790,000	2.17	1916	7,100,000	1.57
1912	7,050,000	1.70	1917	5,900,000	1.68

This table shows that from 1908 to 1914 there was a decline in the average gold content of the gravels mined. This decline is a result of improved methods of placer mining, especially of the use of dredges, and if figures were available to show the average recovery of gold prior to 1908 they would indicate a far greater decline. The increase in the average recovery from 1914 to 1917 was made largely because most of the Alaskan dredges were working on far richer placer gravels and because in 1916 and 1917 a larger percentage of the placer gold came from the rich deposits of the newer districts, where gold recoveries of $7 to $20 a cubic yard are not uncommon. The movement of the miners away from the lower-grade placers, made evident by the average recoveries for 1915 to 1917, is the result of economic conditions due to the war, which affect gold mining more adversely than most other industries.

Thirty-six gold dredges were operated in Alaska in 1917, 2 more than in 1916. Twenty-eight dredges were in Seward Peninsula, 3 in the Iditarod, and 1 each in the Ruby, Fairbanks, Circle, Fortymile, and Yentna districts. These dredges handled about 3,700,000 cubic yards of gravel and produced gold valued at about $2,500,000. In 1916 the 34 dredges handled about 3,900,000 cubic yards of gravel and produced gold valued at $2,679,000. The average gold recovery per cubic yard was about 67½ cents in 1917 and 69 cents in 1916. The gold dredges of Seward Peninsula made an average recovery of 49 cents a cubic yard in 1917 and 53 cents in 1916. The dredges of the Alaska Yukon districts are working on placers of relatively high gold tenor, the value of gold recovery per cubic yard in 1917 being about 94 cents, whereas in 1916 it was about 85 cents.

Though dredges were built for use in the Alaska Yukon as early as 1898 and at Nome in 1900, this method of placer mining was not profitable until 1903, when two small dredges were successfully operated in Seward Peninsula. Dredging began in the Fortymile district in 1907; in the Iditarod, Birch Creek, and Fairbanks districts in 1912; and in the Yentna district in 1916. Up to the end of 1917 gold to the value of $17,610,000 had been mined by dredges. The distribution of this output by years is shown in the following table:

Digitized by Google

Estimate of gold produced from dredge mining in Alaska, 1903–1917.

Year.	Number of dredges operated.	Value of output of gold.	Year.	Number of dredges operated.	Value of output of gold.
1903	2	$20,000	1912	38	$2,200,000
1904	3	25,000	1913	36	2,200,000
1905	3	40,000	1914	42	2,350,000
1906	3	120,000	1915	35	2,330,000
1907	4	250,000	1916	34	2,679,000
1908	4	171,000	1917	36	2,500,000
1909	14	425,000			
1910	18	800,000		.....	17,610,000
1911	27	1,500,000			

COPPER.

The production of copper in Alaska in 1917 was about 88,793,400 pounds, valued at $24,240,598. This is less than the production in 1916, which was 119,854,839 pounds, valued at $29,484,291, but is greater than the production in any other year. The reduction in the output for the year was due largely to scarcity of labor and to a strike at the Kennecott-Bonanza mine. During the year 17 copper mines were operated, compared with 18 in 1916. Of these mines 7 are in the Ketchikan district, 7 in the Prince William Sound district, and 3 in the Chitina district. Small shipments of copper were also made from nine prospects or mines not in regular operation.

Output of Alaskan copper mines, by districts, in 1917.

	Number of mines.	Ore.	Copper.		Gold.		Silver.	
		Quantity (short tons).	Quantity (pounds).	Value.	Quantity (fine ounces).	Value.	Quantity (fine ounces).	Value.
Ketchikan district	[a] 7	41,060	2,646,553	$722,509	2,338	$48,337	20,500	16,891
Chitina district	[b] 3	267,541	70,587,110	19,270,281	1	6	887,880	731,614
Prince William Sound [c]	[d] 7	351,356	15,559,737	4,247,808	10,524	217,557	132,773	109,405
	.....	659,957	88,793,400	24,240,598	12,863	265,900	1,041,153	857,910

[a] Also small shipments from 2 prospects.
[b] Also a small quantity of placer copper and small shipments from 4 prospects.
[c] Including a small amount from Cook Inlet.
[d] Also small shipments from 3 prospects.

The average copper content of the ores mined in 1917 was 6.7 per cent. The ores also yielded an average of $0.40 in gold and $1.30 in silver per ton. The average yield for 1916 was 9.7 per cent of copper and $1.60 per ton in gold and silver. The decrease in the copper content in 1917 was due to the smaller proportion of high-grade Kennecott ores in the total production. The following table shows the total production of copper in Alaska:

Digitized by Google

Copper produced in Alaska, 1880–1917.

Year.	Ore mined (short tons).	Copper produced.	
		Quantity (pounds).	Value.
1880		3,933	$826
1901		250,000	40,000
1902	[a] 40,000	360,000	41,400
1903		1,200,000	156,000
1904		2,043,586	275,676
1905	52,199	4,805,236	749,617
1906	105,729	5,871,811	1,133,260
1907	98,927	6,308,786	1,261,757
1908	51,509	4,585,362	605,267
1909	34,669	4,124,705	536,211
1910	39,365	4,241,689	538,695
1911	68,975	27,267,878	3,408,485
1912	93,452	29,230,491	4,823,031
1913	135,756	21,659,958	3,357,293
1914	153,605	21,450,628	2,852,934
1915	369,600	86,509,312	15,139,129
1916	617,264	119,854,839	29,484,291
1917	650,957	88,793,400	24,240,598
	2,521,007	428,561,614	88,644,470

[a] Estimated.

Among the noteworthy features of copper mining in Alaska in 1917 was the continued enormous output of the Kennecott-Bonanza mine in the Chitina district which, as in previous years, overshadowed all other operations. The total output of the coastal mines increased in 1917. This increase was due largely to the greater production of the Beatson mine, although the aggregate production of the so-called independent mines was also larger than in 1916, notwithstanding the shortage of labor and ships. The larger production from the smaller low-grade mines is of course due to the high price of copper and will not be permanent for all the mines. However, some mines that are now being made productive or that are being worked on a large scale under the stimulus of high prices will perhaps be able to maintain their output when copper sells at a lower price, and the copper industry of Alaska will probably in general continue to advance, though it will doubtless meet temporary setbacks. Work preparatory to the production of copper was continued energetically on several of the nonproducing mines and prospects in all three of the Alaska copper districts. No new discoveries of note were reported.

LEAD.

The production of lead in Alaska in 1917 is estimated to have been 852 short tons, valued at $146,584, the largest production in the history of mining in Alaska. The production in 1916, the next largest, was 820 tons, valued at $113,160. Alaska lead is still, as in past years, derived chiefly from the concentrates at the gold mines at Juneau. The production in 1917 includes small quantities derived from the galena ores of the Fairbanks district and Seward Peninsula and from the copper-lead ores of southeastern Alaska. Though deposits of silver-lead ores are found in many parts of Alaska, most of them have not yet been opened for commercial mining. The production of lead in Alaska for the period 1892–1917, so far as it can be determined from available data, was 2,933 short tons.

Digitized by Google

REVIEW BY REGIONS.

SOUTHERN ALASKA.

LODE MINING.

Ten lode gold mines and 8 copper mines were operated in southeastern Alaska in 1917. The value of the mineral output of these mines was: Gold, $4,325,251; copper (2,646,553 pounds), $721,687; silver, $123,825; and lead, $145,182.

The largest mining operations in 1917, as in preceding years, were at the gold mines in the Juneau district. As a result of a cave-in at the Treadwell, 700-foot, and Mexican mines on April 21, these mines are now flooded with sea water and are not in operation.

All the productive copper mining in southeastern Alaska was done in the Ketchikan district. The development of the copper lodes of this district, particularly on Kasaan Peninsula, has at several places uncovered large bodies of magnetic iron ore, which are now being considered as possible commercial sources of iron.

Mining on Chichagof Island continued on about the same scale as in 1916. Development work on the group of copper claims near Pinta Bay, about 15 miles northwest of Chichagof, was also continued.

PLACER MINING.

Placer mining in southeastern Alaska was limited to the Porcupine district and to small beach operations at Yakataga and Lituya Bay.

COPPER RIVER REGION.

The largest mining operations in the Copper River region in 1917, as in several preceding years, were at the Jumbo and Kennecott-Bonanza copper mines. Considerable copper was also shipped from the Mother Lode mine, and small shipments were made from several other properties. The Jumbo and Kennecott-Bonanza mines and the mill at Kennecott were operated on a large scale throughout the year, although the production was considerably smaller than in 1916. This reduction in the output was due to a strike in midsummer of 1917 and to shortage of labor during much of the year.

Hydraulic placer mining continued on a large scale in the Nizina district, where 2 mines employing 4 miners were in operation in the winter of 1916–17 and 6 mines employing 91 miners in the summer of 1917. These mines produced about $120,000 in placer gold and a little placer copper. No important developments or discoveries were reported.

Placer mining on Slate Creek, in the Chistochina district, was continued on a large scale. The production of this district is estimated at about $100,000 in gold and 15 or 20 ounces of platinum.

PRINCE WILLIAM SOUND.

The value of the mineral production of the mines on Prince William Sound was $4,567,929 in 1917 as compared with about $3,000,000 in 1916. This figure represents the value of the product of 7 copper

Digitized by Google

mines and 3 gold mines, which can be classed as regular producers, and of additional small shipments from 8 other small mines or prospects. The Beatson-Bonanza, Ellamar, and Midas mines were the largest producers. These mines and the Blackbird group, which began shipping after lying idle for several years, and the Schlosser and the Mackintosh properties employed more than 550 men during the year.

KENAI PENINSULA.

The mining production of Kenai Peninsula includes about $30,000 of placer gold, $4,600 of lode gold, a small quantity of silver obtained incidentally to the mining of gold, a considerable quantity of chromite mined at Port Chatham, and some lignite. There was very little activity in lode gold mining and little development was reported. The largest placer mining operations were on Resurrection and Crow creeks. Heavy rains in the fall caused serious damage at the placer mines throughout the district.

SUSITNA REGION.

WILLOW CREEK DISTRICT.

The mineral production of the Willow Creek district in 1917 included $195,662 in gold and $588 in silver, all derived from quartz mines. The quantity of ore milled was 7,885 tons. A promising new quartz vein which was opened at the Gold Cord mine, at the head of Fishhook Creek, has already been traced for the length of several claims.

YENTNA DISTRICT.

The Cache Creek district continues to be the principal source of placer gold in the Yentna basin. A dredge, burning local coal, was operated on Cache Creek, and 15 hydraulic plants were working on Cache and Peters creeks during the summer. More than 100 men were employed and produced placer gold valued at between $125,000 and $150,000. The operations at the end of the season were hampered by protracted rains and serious floods, which caused considerable damage to several mining plants. Late in the fall a Hudson dry dredge, which is to begin mining in the spring of 1918, was installed on ground along the north side of Kichatna River.

Platinum occurs in the gravels of the lower Kahiltna River, where prospecting for that metal was carried on by two companies. It occurs also at many other places in the Susitna basin, including Cache, Peters, Camp, and Lake creeks, as well as on Kichatna and Chulitna rivers, and commercial platinum placers may ultimately be found.

SUSITNA VALLEY.

The mineral production of the upper Susitna Valley is still restricted to the placer gold of the Valdez Creek district, but lodes in the Broad Pass and Talkeetna districts are being prospected. In 1916 and 1917 some twenty groups of claims were staked on gold and copper bearing lodes in the basin of Iron Creek, a tributary of Talkeetna River, but practically no underground work has yet been done. A new copper discovery is reported from the head of Maclaren River.

Digitized by Google

SOUTHWESTERN ALASKA.

The known mineral production in southwestern Alaska in 1917 consisted of small amounts of copper ore from the vicinity of Kamishak Bay and of placer gold from the Kodiak beaches, from a creek near Katmai Bay, and from Portage Creek, in the Clark Lake district.

YUKON BASIN.

GENERAL STATEMENT.

The value of the gold produced by the placer mines of the Alaska Yukon districts in 1917 is estimated to have been $6,583,000, compared with $7,550,000 in 1916. About 380 placer mines were operated in the summer of 1917, giving employment to about 2,550 men, and about 165 placer mines, employing about 790 men, were operated in the winter. Nine lode mines, all in the Fairbanks district, were productive in 1917. The following table gives the estimated gold output of the principal Yukon placer camps:

Estimated value of gold produced from placers in the Yukon Basin, 1917.

District.	Value.	District.	Value.
Iditarod	$1,500,000	Koyukuk	$250,000
Fairbanks	1,310,000	Circle	200,000
Tolovana	1,150,000	All others	413,000
Ruby	885,000		
Hot Springs	450,000		6,583,000
Marshall	425,000		

The Yukon placer mines also produced silver valued at about $39,000 in 1917. The figures in the table do not include the output of the lode mines, which in 1917 produced gold and silver valued at $49,607.

There was also a small output of tin from the Hot Springs district, and considerable tungsten ore and some antimony ore were mined in the Fairbanks district. The total value of the entire mineral production from the Alaska Yukon in 1917 was $6,747,835; that in 1916 was $7,839,757. Since mining began in 1880, the Alaska Yukon has produced minerals to the value of $110,800,000, most of which has been derived from the gold placers.

The most noteworthy feature of the placer mining of the year was the increased output of the Tolovana placers. There was also an increased production in the Marshall, Tolstoi, and Ruby districts. The other districts show a decrease in output, due chiefly to a general retrenchment by operators because of the high cost of supplies and the scarcity of labor.

FAIRBANKS DISTRICT.

The mineral production of the Fairbanks district in 1917 included placer gold, valued at $1,310,000; lode gold, valued at $47,781; placer silver, valued at $6,904; lode silver, valued at $1,827; and lead, tungsten, and antimony, valued at $58,257. The total value of the mineral output in 1917 was $1,424,769. The aggregate value of the

Digitized by Google

entire mineral output of the district up to the close of 1917 is $70,417,000. Much the larger part of this amount represents the value of the placer gold, the production of which is shown by years in the subjoined table. In addition to the actual production of the district, about $1,000,000 in gold mined in tributary areas passes through Fairbanks each year.

Placer gold and silver produced in the Fairbanks district, 1903–1917.

Year.	Gold.		Silver.	
	Quantity (fine ounces).	Value.	Quantity (fine ounces).	Value.
1903	1,935.00	$40,000	348	$188
1904	29,025.00	600,000	5,225	2,821
1905	290,250.00	6,000,000	52,245	28,212
1906	435,375.00	9,000,000	78,367	42,318
1907	387,000.00	8,000,000	69,660	37,616
1908	445,050.00	9,200,000	79,909	43,151
1909	466,818.75	9,650,000	84,027	45,375
1910	295,087.50	6,100,000	53,116	28,683
1911	217,687.50	4,500,000	52,245	27,690
1912	200,756.25	4,150,000	48,182	29,632
1913	159,638.50	3,300,000	20,274	12,245
1914	120,937.50	2,500,000	29,024	16,050
1915	118,518.75	2,450,000	28,444	14,421
1916	87,075.00	1,800,000	11,058	7,276
1917	63,371.25	1,310,000	8,379	6,904
	3,318,525.00	68,600,000	620,503	342,582

No new discoveries or important developments in placer mining were made in 1917. A large dredge will be installed on upper Fairbanks Creek to begin operations in 1918.

Gold-lode mining in the Fairbanks district declined from 1913 to 1916, but showed a slight increase in production in 1917. The cost of supplies and fuel has become so high that many operators will wait for more favorable conditions rather than work at a low profit or run the risk of actual loss. Eight lode gold mines were worked in a small way and five of these operated their own mills. One silver-lead deposit is being worked and made an output in 1917. The following table shows the production of gold and silver from the Fairbanks lode mines since lode mining began:

Lode gold and silver produced in the Fairbanks district, 1910–1917.

Year.	Crude ore (short tons).	Gold.		Silver.	
		Quantity (fine ounces).	Value.	Quantity (fine ounces).	Value.
1910	148	841.19	$17,339	106	$57
1911	875	3,103.02	64,145	582	308
1912	4,708	9,416.54	194,657	1,578	971
1913	12,237	16,904.98	349,457	4,124	2,491
1914	6,526	10,904.75	225,421	2,209	1,222
1915	5,845	10,534.91	217,776	1,796	910
1916	1,111	1,904.81	39,376	140	92
1917	1,200	3,311.38	47,781	2,217	1,826
	32,650	55,921.58	1,155,952	12,752	7,877

Digitized by Google

CHISANA DISTRICT.

Placer mines were operated on Bonanza, Big Eldorado, Gold Run, and Little Eldorado creeks. These mines employed 44 men and produced gold valued at about $40,000. The population of this district is growing smaller year by year, although considerable prospecting is done on neighboring creeks in winter.

FORTYMILE DISTRICT.

The mineral production of the Fortymile district in 1917 consisted of gold valued at about $80,000, derived from 25 mines employing 68 miners, which were operated during the winter of 1916–17, and 35 mines employing 93 miners, which were operated in the summer of 1917. In addition to these mines a small dredge was operated in the summer of 1917.

EAGLE DISTRICT.

Twelve placer mines employing 25 men were operated in the Eagle district in 1917 and yielded gold valued at about $13,000. The largest number of mines and miners and the largest production was on American Creek.

CIRCLE DISTRICT.

Owing to unfavorable conditions, chiefly lack of rain during the later part of August and in September, the gold production from nearly all the creeks in the Circle district was greatly curtailed. The production was about $200,000, which is about $100,000 less than in 1916. About the same number of mines were operated and the same number of men were employed as in 1916. The chief developments in 1917 included the installation of a hydraulic plant on Independence Creek.

RAMPART DISTRICT.

The gold produced in the Rampart district in 1917 was valued at about $33,000 and was obtained from 2 mines, employing 5 men, in the winter of 1916–17 and 10 mines, employing 26 men, in the summer of 1917. The largest output was made on Hunter and Little Minook creeks.

TOLOVANA DISTRICT.

The output of the placer mines of the Tolovana district in 1917 was about $1,150,000, which is an increase of 50 per cent over that in 1916. About 50 mines were operated.

HOT SPRINGS DISTRICT.

The production of gold in the Hot Springs district in 1917 was about $450,000. Placer mines employing 190 men were operated on 30 claims, on Eureka, Sullivan, American, and Boulder creeks. The decrease in production is due in part to the cessation of large operations on Woodchopper Creek and in part to the high cost of food and mining supplies, which has prevented the working of any except high-grade ground.

Digitized by Google

RUBY DISTRICT.

The mining operations in the Ruby district in 1917 were conducted on about the same scale as in 1916 and resulted in the production of placer gold valued at $885,000, a little more than the production in 1916. It is reported that 19 mines, employing 310 men, were at work in the summer of 1917 and 19 mines, employing 520 men, in the winter of 1916–17. The largest production was made on Greenstone, Poorman, Long, Spruce, and Tamarack creeks. The dredge on Greenstone Creek had a successful season, but the dredging ground has been worked out and the dredge will be moved.

INNOKO DISTRICT.

The production of gold in the Innoko district in 1917 is estimated at $125,000. About 7 mines, employing 46 men, operated in the winter of 1916–17 and 20 mines, employing 78 men, in the summer of 1917.

TOLSTOI DISTRICT.

A stampede to the Tolstoi district took place in the winter of 1916–17. At times there were as many as 400 men in the camp, but not more than 50 remained in July. About $50,000 in gold was taken out during the winter and summer, the result of the operations of about 25 men on 5 plants, most of the production being on Boob Creek. Boob Creek is the only creek in the district that produced platinum. The platinum was not separated from the gold but was sold with it to the bank in Iditarod. The platinum in the gold was said to amount to about 1 per cent, so that about 30 ounces of platinum was produced.

IDITAROD DISTRICT.

The production of placer gold in the Iditarod district in 1917 was about $1,500,000, or $450,000 less than in 1916. The decrease was due largely to repeated breakdowns of the Otter Creek dredge. Detailed information concerning mining in this district is not available, but it is believed that in addition to the 3 dredges there were about 15 mines, employing nearly 400 men, at work in the summer of 1917 and 2 mines, employing about 10 men, in the winter of 1916–17.

KOYUKUK DISTRICT.

The total value of the gold produced in the Koyukuk district in 1917 was about $250,000, which is considerably less than the production in 1916. In the Indian River district 8 men were at work in the summer of 1917 on Indian Creek, Felix Fork, and Black Creek, and they produced about $4,000 in placer gold.

MARSHALL DISTRICT.

The production at Marshall was about $425,000, as compared with $270,000 in 1916. Most of this gold was produced by 5 mines on Willow Creek, employing about 200 men, but some smaller plants were at work on Willow, Disappointment, and Elphant creeks. A little platinum is found with the gold on some of the creeks at Marshall, but it is not saved.

Digitized by Google

SMALLER YUKON DISTRICTS.

At least four placers, employing 9 men, were in operation in the Chandalar district, where about $15,000 in gold was produced.

The Richardson district, of the Tanana region, apparently produced less than in 1916. No production has been reported from the Goodpaster region, though considerable prospecting has been done there.

There was no production of gold in the Gold Mountain district, but dead work was done preparatory to mining in 1918.

KUSKOKWIM REGION.

The production of gold in the Kuskokwim region in 1917, according to the best information at hand, was valued at $135,000. The largest production was on Candle and Moore creeks. The dredge that was shipped in the preceding year is to be placed at the upper end of Candle Creek. Another discovery is reported from Wahmus or Watermouse, in the Goodnews Bay district, where it is said that 4 men took out between $12,000 and $20,000 in three weeks.

SEWARD PENINSULA.

The mines of Seward Peninsula produced gold to the value of about $2,600,000 in 1917 as against $2,950,000 in 1916. The value of the total gold produced on Seward Peninsula since mining began in 1897 is about $76,892,000. Nearly all this gold was taken from placers. Silver and tin have been produced to the value of about $1,027,600, making the total value of the mineral output of Seward Peninsula to the end of 1917 about $77,900,000.

About 750 men were employed in placer mining in Seward Peninsula, exclusive of those employed on dredges. About half the number was employed in the Nome and Council precincts. One hundred and seventy plants were in operation.

Twenty-eight gold dredges were operated on the peninsula in 1917. Of these 7 were in the Nome district, 5 in the Solomon River district, 10 in the Council district, 2 in the Port Clarence district, 2 in the Fairhaven district, and 2 in the Kougarok district.

The production of gold on Dime Creek in 1917 was greater than in 1916, six plants making a very large part of the $150,000 produced by deep mining during late winter and early spring. An additional $20,000 will cover summer production, mostly from three open cuts. In all 17 plants worked during the winter and summer, employing about 85 men. This mining was done on four claims. Dime Creek produced about 35 ounces of platinum. The platinum content of the gold is about 1 ounce of platinum to $5,000 gold on the lower claims of the creek and on the bench claims, but is somewhat higher on claims near the head of the creek.

About $10,000 in gold was produced on Sweepstakes Creek, between Bear and Dime creeks, by 4 plants employing 11 men. About an ounce of platinum was separated from this gold.

Four plants, employing 14 men, worked on Bear Creek in 1917. The production of gold is not known, but this gold also contains platinum.

Digitized by Google

Exclusive of dredge production the gold produced in the Port Clarence precinct is estimated at $27,000. That produced in the Kougarok precinct, likewise exclusive of dredge production, is estimated at $55,000.

Most of the lode-mining developments on Seward Peninsula consisted of the necessary assessment work. The high prices of lead and silver gave an impetus to the search for those metals in the vicinity of Lost River and on the Kugruk, and considerable work was done in both localities.

KOBUK RIVER.

The production of the Kobuk district was probably about $25,000. Most of the mining was done on Klery Creek, but about 9 mines employing 16 men, were operated on Lynx, Riley, and Dahl creeks and on Shungnak River and made an estimated output of $5,000.

95186°—M R 1917, PT 1——10

Digitized by Google

Digitized by Google

MAGNESIUM.

By RALPH W. STONE.

PRODUCTION.[1]

The production of metallic magnesium is a new industry in the United States, the first output on a commercial scale having been made in 1915. Prior to that year several firms had experimented in the isolation of the metal, but as the demand was small, as the known uses were few, and as a supply could be obtained from Germany, little progress was made toward commercial production. When the European war began not only was the German supply of the metal and of magnesium chloride from which it is extracted cut off but at the same time there arose a large demand. Whereas formerly only a small quantity, perhaps a few thousand pounds, had been used for flash lights in photography, the demand came for large quantities to be used in war materials.

In 1915 the total production of three firms was 87,500 pounds, valued at about $440,000. In 1916 four firms produced 75,400 pounds of magnesium, valued at $311,462. This production represented a reduction in 1916 of nearly 14 per cent in quantity and 29 per cent in value from the production of 1915. The average price fell from $5 a pound in 1915 to $4.13 a pound in 1916.

The output in 1917 was 115,813 pounds, valued at $233,626, and the total production in three years to December 31, 1917, as closely as can be determined from reports made by producers to the Geological Survey, was 278,713 pounds or about 139 short tons. This does not include small quantities which may have been made in an experimental way before 1915, nor is it exact because some of the producers, for lack of data, could report only in round numbers. The total value of the product in the first three years of the industry as determined from sales and from estimates based on average prices for the year, is $985,088.

The growth of the industry and improvements resulting in decreased cost of production are reflected in the following table:

Production of metallic magnesium.

Year.	Number of producers.	Quantity (pounds).	Value.	Average price per pound.
1915	3	87,500	$440,000	$5.00
1916	4	75,400	311,462	4.13
1917	5	115,813	233,626	2.02

[1] Statistical data in this report collected by Frank L. Hess, of the United States Geological Survey.

Digitized by Google

PRODUCERS.

The producers of magnesium at the end of 1917 were the American Magnesium Corporation, Niagara Falls, N. Y.; the Norton Laboratories (Inc.), Lockport, N. Y.; and the Rumford Metal Co., Rumford, Me. Other firms have produced or been interested in the production of metallic magnesium, but for one reason or another have dropped from the active list. The General Electric Co., at Schenectady, N. Y., was the pioneer producer on a commercial scale and made the principal output in 1915. Its primary reason for beginning the production of this metal was to assure a supply to the United States, and when in the latter part of 1917 there was a sufficient number of companies prepared to meet the demand it discontinued the production of magnesium. The Norton Laboratories (Inc.) began isolating magnesium about August 1, 1915, at Lockport, N. Y., where electric power from Niagara Falls is available. The office of this company is 296 Madison Avenue, New York City. The Electric Reduction Co. began producing magnesium in the fall of 1915 at Washington, Pa., and continued through part of 1916, until it was found more profitable to use the power for other purposes. The Aviation Materials Corporation, Niagara Falls, N. Y., which was reported ready for production at the end of 1915, was engaged during 1916 in perfecting a new process of isolating magnesium, and at the end of the year had accomplished this. It was succeeded by the American Magnesium Corporation, which was organized and began producing the metal in 1917. The Magnesium Manufacturing Corporation was completing its plant at the end of 1915 and began production the following year. This firm became the Rumford Metal Co., with an office at 200 Fifth Avenue, New York City, and operated throughout 1917. The Dow Chemical Co. has a metallic magnesium plant with a large capacity at Midland, Mich., but was unable to operate it in 1917, except in an experimental way, because of the lack of coal. This plant did not operate in 1916 and made only a small production in 1917.

PRICE.

Imported German magnesium was quoted at about $1.65 a pound in 1913, but after the European war cut off the foreign supply prices rose to $5 or even $6 a pound for sticks and $6.50 a pound for powdered material. These prices continued through 1915. During 1916 the price fell off, and at the beginning of 1917, 99 per cent pure bar magnesium was selling for $2.50 to $3 a pound. This price gradually declined, and at the end of 1917 magnesium in bars was selling for $1.85 to $2 a pound, according to the quantity bought.

Although the figures in the table above give an average price of $4.13 a pound for all production in 1916, one company reported an average price of $2.53, another $4.25, and a third $5. The reports for 1917 are in closer harmony, however, only one differing much from the general average of about $2 a pound.

IMPORTS AND EXPORTS.

The Bureau of Foreign and Domestic Commerce of the Department of Commerce records imports and exports of "barium, calcium, magnesium, sodium, and potassium, and alloys of which said metals are the component material of chief value," in one class, which is

Digitized by Google

subject to a 25 per cent duty. Magnesium ribbon is subject to a 20 per cent duty, although it is in a more advanced state of fabrication than magnesium bars. No information is obtained by the customs officials regarding the imports and exports of magnesium alone. It is probable that little or none was imported in 1917 and that there was an increasing quantity exported to our allies.

CHARACTER.

Magnesium is the lightest of the metals now known that remain comparatively unaltered under atmospheric conditions. Its specific gravity is 1.74, or only two-thirds that of aluminum, which is 2.58. Magnesium is chemically inert, tough, and malleable, properties which should make the metal valuable in commerce.

Magnesium is a beautiful silvery-white metal. It is molded into round and square sticks from five-eighths of an inch to 2 inches thick and from 14 to 18 inches long. It is readily malleable and is ductile when heated. Magnesium ribbon is made by pressing the semifluid metal into wire and then flattening it. When heated in air, powdered magnesium burns rapidly with an intense white light and gives off abundant white smoke.

SOURCE OF METAL.

The metal has been obtained from magnesium chloride derived from bitterns left after the extraction of salt and bromide from brines at Midland, Mich., and from magnesite, the magnesium carbonate, which occurs as veins in serpentine at many localities in California and in beds like dolomite at Grenville, Quebec. Other possible sources of supply are dolomite, the magnesium-calcium carbonate, which occurs abundantly in the Eastern States, and the waters of the oceans and salt lakes. Ocean water contains only about 0.14 per cent of magnesium, but bitterns made around San Francisco Bay, Cal., by extracting salt from sea water contain from 2.3 to 8.6 per cent of magnesium. Magnesium chloride can be made from these bitterns, and some day the commercial production of magnesium from sea water near San Francisco may be a reality.

USES.

Magnesium is used in three forms, as a silvery powder or gray granular substance, as narrow ribbon, and as round or square sticks. Although its application in art, science, and manufacture is at present neither large nor varied, there is reason to believe that present conditions will develop new uses or so reduce the cost of production that magnesium can replace aluminum in some of its applications.

Magnesium in powdered form has been used for many years for flash lights in photography. Its value in this work is due to the fact that the intense white light it produces is rich in actinic rays, or those rays that produce chemical reaction on the photographic plate. In order that it may burn very rapidly, magnesium designed for this purpose is reduced to powder that will pass a 200-mesh screen. For taking moving pictures in dark places, which requires an intense and long-burning light, magnesium is mixed with a variety of other less inflammable constituents to lengthen the time of burning. Coarse powdered magnesium is used in the chemical laboratory in qualitative tests for phosphorus, and material not so fine as flash-

light powder is used in fireworks, because of the beautiful effect of the brilliant white light and clouds of white smoke it gives off. The quantity used for this purpose never was large and with the change in method of celebrating festal occasions is probably decreasing. Magnesium powder is used in making war munitions and flares for military purposes. It is put in shrapnel shells so that the burning magnesium, which makes a white cloud by day and a dazzling white light by night, will show the gunners and observers where the shells are bursting. Magnesium is used in large quantities in aerial bombs and rockets for lighting contested territory at night, and it has other important military uses.

Magnesium in ribbon form is used in small quantity in chemical laboratories in the determination of potash and in qualitative tests for phosphorus. There are other special uses, such as the ignition of thermite mixtures, that consume a small quantity of ribbon annually.

Magnesium in massive form, as sticks or rods, is used in alloys both as a deoxidizing agent and as a constituent, as a dehydrating agent, and as an electrode in electrolysis. These four uses of massive magnesium may be briefly described as follows: A deoxidizing metal is a substance whose oxide is more stable or insoluble than the material to be deoxidized. The use of a metal for this purpose is called scavenging—that is, clearing up oxides of other metals and making denser and more homogeneous alloys. In alloying other metals various other substances as silicon, phosphorus, and aluminum are used to remove oxygen. The oxide of magnesium is more stable at high temperatures than any of these, and therefore metallic magnesium would seem to offer promising possibilities in this use, especially to replace aluminum as a deoxidizer of steel. The value of magnesium as a deoxidizer is utilized by adding it to Monel metal (nickel and copper) or nickel when melted for casting. It has been used in steel for the same purpose and in the reduction of boron. It can be used as a scavenger for copper, brass, bronze, and other metals and alloys.

Magnesium is used as an alloy with aluminum. Aluminum containing a small percentage of magnesium is used in the construction of airplanes and automobiles. This alloy is lighter than aluminum, has greater tensile strength and resistance to shock, is apparently equally resistant to corrosion, and is equal to aluminum also in electrical conductivity. Several United States patents have been issued for alloys of magnesium with other metals in varying proportions. An alloy consisting of 92 per cent magnesium and 8 per cent aluminum, which is covered by U. S. patent 965485 (1910), is reported to have a specific gravity of 1.75 and a strength equal to that of gun metal. An aluminum-magnesium alloy containing not over 2 per cent magnesium and known as magnalium is used in Europe for kitchen utensils, forks, knives, spoons, tableware, funnels, piano frames, skates, and parts of spinning, weaving, and milling machines; and in military equipment magnalium has found use in saddle skeletons, horseshoes, tent poles, instruments for surgical, optical, and chemical purposes, telegraph, telephone, and wireless apparatus, watch cases, and medals.

Magnesium may be used in dehydrating oils. When introduced in the form of small sticks it decomposes the water at 35° C., giving off hydrogen and forming magnesium oxide (MgO), which separates out.

Digitized by Google

This method has been used in Europe to free aniline from its small content (about 2 per cent) of water.

The use of magnesium has been suggested as a cathode in electrolysis where it is wished to prevent the reduction at the cathode in neutral or alkaline solutions which contain no ions of the heavy metals, and also in the electrolysis of alkali chlorides for hypochlorite. Magnesium anodes can be used in the contact process for producing galvanoplastic deposits of nickel and cobalt.

In consequence of the improvement in methods of production, reduction in cost, and experience derived from the present demands, it is reasonable to assume that the uses of magnesium and its alloys will increase in this country until eventually magnesium may become as common as aluminum.

DEMAND AND SUPPLY.

Because of its high price and few known uses the demand for magnesium before 1915 was small. During 1916 and 1917 the use increased rapidly, especially for war materials, and it is safe to say that the quantity of magnesium consumed by the Allies on the western front in 1918 will be hundreds of tons.

The world's principal source of magnesium before the war was Germany, because that country was a large producer of magnesite and magnesium chloride, the materials from which the metal is derived. The elimination of that source has caused England, France, and Italy to turn to this country and to Canada for magnesium. To meet this call the three plants in the United States and one in Canada increased their output in 1917 more than 50 per cent over that of 1916, and in 1918 they will doubtless more than double the production of 1917.

The supply of raw material is inexhaustible. If magnesium chloride produced in the evaporation of brine for the extraction of salt and bromine is not obtained in sufficient quantity to meet all needs, there are large deposits of magnesite, the magnesium carbonate, in California, Washington, and other States and in Canada. Furthermore, this country has extensive deposits of dolomite, the calcium-magnesium carbonate, in readily accessible and easily quarried beds in the Eastern States, and the oceans themselves may be considered as reserve sources of magnesium.

Digitized by Google

Digitized by Google

GOLD, SILVER, COPPER, AND LEAD IN SOUTH DAKOTA.

(MINES REPORT.)

By CHARLES W. HENDERSON.

PRODUCTION.

The total value of the gold, silver, copper, and lead produced at mines in South Dakota in 1917 was $7,526,905, a decrease of $77,787 from the value in 1916. The output of gold was 356,244.77 fine ounces, valued at $7,364,233 almost 98 per cent of the total value. The decrease in the output of gold for the year was 4,663.88 fine ounces in quantity and $96,411 in value. The production of silver decreased from 215,205 fine ounces to 186,765 fine ounces but the value increased from $141,605 to $153,894. Smelting ore shipped from South Dakota carried 10,707 pounds of copper and 68,081 pounds of lead. The output of placer gold was 44.70 fine ounces. There were 30 producing mines of which 23 were deep and 7 were placer, a decrease of 6 deep and 9 placer mines as compared with 1916.

The total quantity of ore mined and treated in 1917 was 1,868,310 short tons, averaging in recovered gold 0.1907 ounce or $3.94 per ton as compared with 1,870,783 short tons averaging $3.99 per ton in 1916. The mills of the State treated 1,867,583 tons of ore, which yielded as bullion $7,350,460 in gold and 181,051 fine ounces of silver, valued at $149,186, an average recovery per ton of $3.94 in gold and 0.10 ounce in silver, as compared with $3.98 in gold and 0.11 ounce in silver in 1916. The crude ore shipped to smelters amounted to 727 tons, having an average content per ton of 0.855 fine ounce of gold, valued at $17.67, and of 7.85 ounces in silver.

Gold and silver bullion produced at mills in South Dakota in 1917.

Process.	Ore treated.	Gold in bullion.	Silver in bullion.
	Short tons.	*Fine ounces.*	*Fine ounces.*
Amalgamation	1,677,623	228,018.51	61,759
Cyanidation	[a]1,809,417	127,560.01	119,292
	.....	355,578.52	181,051

[a] Includes 1,619,457 tons of tailings from part of ore amalgamated.

In 1917 the mines in South Dakota consumed 13,199 pounds of quicksilver and 384,938 pounds of sodium cyanide, equivalent to 1 pound of quicksilver for every 17.28 ounces of gold or every 127 tons of ore treated, and 0.21 pound of sodium cyanide for every ton of ore or tailings treated and 0.33 ounce of gold for every pound of cyanide used.

Digitized by Google

Mine production of gold, silver, copper, and lead in South Dakota in 1916 and 1917.

Year.	Number of mines producing.	Ore.	Gold.[a]		Silver.[a]	
			Quantity.	Value.	Quantity.	Value.
		Short tons.	*Fine ozs.*		*Fine ozs.*	
1916	45	1,870,783	360,908.65	$7,460,644	215,205	$141,605
1917	30	1,868,310	356,244.77	7,364,233	186,765	153,894
Increase or decrease	−15	−2,473	−4,663.88	−96,411	−28,440	+12,289

Year.	Number of mines producing.	Copper.		Lead.		Total value.
		Quantity.	Value.	Quantity.	Value.	
		Pounds.		*Pounds.*		
1916	45	.....	.....	35,406	$2,443	$7,604,692
1917	30	10,707	$2,923	68,081	5,855	7,526,905
Increase or decrease	−15	+10,707	+2,923	+32,675	+3,412	−77,787

[a] Includes placer production.

Mine production of gold and silver in South Dakota, 1876–1917.[a]

Period.	Gold.	Silver.		Total value (commercial).
		Quantity.	Commercial value.	
		Fine ounces.		
1876–1880	$11,255,843	80,292	$92,452	$11,348,295
1881–1890	30,800,000	1,472,580	1,515,224	32,315,224
1891–1900	48,005,555	1,729,873	1,155,691	49,161,246
1901–1910	65,242,196	1,790,365	1,013,349	66,255,545
1911	7,439,874	203,755	107,990	7,547,864
1912	7,891,370	206,460	126,973	8,018,343
1913	7,319,294	172,702	104,312	7,423,606
1914	7,333,508	176,642	97,683	7,431,191
1915	7,406,305	199,864	101,331	7,507,636
1916	7,460,644	215,205	141,605	7,602,249
1917	7,364,233	186,765	153,894	7,518,127
	207,518,822	6,434,503	4,610,504	212,129,326

[a] For yearly output and authority for each, see U. S. Geol. Survey Mineral Resources, 1913, pt. 1, p. 240, 1914.

Mine production of gold and silver in South Dakota in 1917.

Source.	Number of mines.	Ore.	Gold.		Silver.		Total value.
			Quantity.	Value.	Quantity.	Value.	
		Short tons.	*Fine ounces.*		*Fine ounces.*		
Deep mines:							
Siliceous ore	16	1,867,859	356,168.17	$7,362,650	182,023	$149,987	$7,512,637
Lead ore	5	369	31.05	641	4,608	3,797	4,438
Copper ore	2	82	.85	18	130	107	125
	23	1,868,310	356,200.07	7,363,309	186,761	153,891	7,517,200
Placer mines	7	.....	44.70	924	4	3	927
	30	1,868,310	356,244.77	7,364,233	186,765	153,894	7,518,127

Digitized by Google

MINING INDUSTRY.

GENERAL CONDITIONS.

The Homestake mines and mills were operated without interruption in 1917. The shaft on the Oro Hondo mine, adjoining the Homestake property, was sunk from 2,000 feet to 2,200 feet and considerable drifting and diamond drilling was done. The Golden Reward mill was operated steadily on siliceous ores obtained from its own mines. The Mogul mill was operated steadily, chiefly on custom ore. The Trojan mill was operated continuously on company and custom ore. The Bismarck mine and mill were operated for a short period. The Wasp No. 2 Co. did not operate its mine or mill during the year and the mill has been dismantled. The New Reliance mine and mill were idle. The Deadwood-Standard mill was operated on ore from the Elk Mountain mines during part of the year.

The Rattlesnake Jack mine, in the Galena district, was idle, but considerable lead-silver ore was shipped from the district.

A small output of placer gold was made in Lawrence and Pennington counties. Small shipments of copper ore were made from the Keystone and Rochford district and of gold ore from the Keystone district.

A small shipment of lead ore was made from the Spokane mine, near Custer.

REDUCTION MILLS.

Reduction mills in operation in South Dakota in 1917, by counties.[a]

[A, active; B, building; I, idle.]

Name.	Location.	Process.	Equipment.	Approximate daily maximum capacity.
				Short tons.
Custer County:				
Ruberta (I)	Custer	Amalgamation and cyanidation.	10 stamps, plates, cyanide annex, 2 percolation tanks.	25
Ruby (I)	do	Amalgamation and concentration.	Gates crusher, 10 stamps, 2 Frue vanners, 2 concentrating tables.	30
Spokane (B)	do	Concentration	Rolls, ball mill, jigs, tables, slime tables.	100
Lawrence County:				
Custer Peake	Roubaix	do	10 stamps, Hartz jigs, 4 Wilfley tables.	40
Deadwood-Standard (A).	Cyanide	Cyanidation	1 Gates No. 4 crusher, 2 roller mills, 4 tanks.	100
Deadwood Zinc and Lead (B).	Deadwood	Concentration	10 stamps, 4 tables	40
Golden Reward[b] (A).	do	Cyanidation	1 Gates crusher, 2 Chilean mills, 3 Akins classifiers, 6 Dorr thickeners, 12 tanks (6 percolation, 6 agitation), 1 Portland filter.	200
Golden Reward Roaster (A).[c]	Terry		Wedge roaster	75
Puritan (I)	(Strawberry Gulch).	Cyanidation	20 stamps, 2 Dorr classifiers, tanks.	100
Branch Mint (I)	Galena	do	120 stamps	400
Clover Leaf (I)	do	Amalgamation	60 stamps, plate amalgamation	240

[a] U. S. Geol. Survey Mineral Resources, 1913, pt. 1, pp. 43–45, contains a complete list of reduction mills in South Dakota in that year, with a description of equipment and process. See Parmelee, H. C., Cyanide practice in the Black Hills, S. Dak.: Met. and Chem. Eng., July, 1913, pp. 395–398; August, 1913, pp. 435–438; September, 1913, pp. 500–502.

[b] For description, see Min. and Eng. World, June 7, 1913, pp. 1103–1104.

[c] For description, see Willard, C. G., The Golden Reward roaster; South Dakota School of Mines Pahasapa Quart., June, 1916, pp. 40–45.

Digitized by Google

Reduction mills in operation in South Dakota in 1917, by counties—Continued.

Name.	Location.	Process.	Equipment.	Approximate daily maximum capacity.
Lawrence County—continued.				*Short tons.*
Gilt Edge (I)	Galena	Concentration	1 Gates crusher, McFarlane rolls, cone classifiers, 2 Monell slimers, 12 Monell concentrating tables.	150
Golden Crest (I)	do	Cyanidation	Blake crusher, 40 stamps, 2 Dorr classifiers, Abbe tube mill, 4 tanks, Moore filter.	250
Rattlesnake Jack (I).	do	Cyanidation and concentration.	10 stamps, Hardinge rolls, tanks, Oliver filter, 2 Wilfley tables.	50
Homestake (A)[a]	Lead	Amalgamation and cyanidation.	6 wet-crushing stamp mills aggregating 1,020 stamps, 20 Gates crushers, 3 tube mills, 131 cone, 37 gravity, and 5 Dorr classifiers; 2 cyanide sand plants (capacity, 75,000 tons per month), 1 cyanide slime plant (capacity 55,000 tons per month), 25 percolation tanks, 12 Dorr thickeners, 25 percolation tanks, 31 Merrill filters.	4,200
Do	do	Tungsten concentration.	5 stamps, 2 dewatering cones, 1 Wilfley, 3 slime tables.	20
Minnesota (I)	Maitland	Cyanidation	1 Austin crusher, 2 roughing rolls, 2 slow-speed Chilean mills, 19 tanks.	200
North Homestake (I).	do	do	40 stamps, cone classifiers, 8 slime and 6 sand tanks, cyanidation by agitation and percolation.	150
Safe Investment (I).	Novak	Cyanidation and concentration.	40 stamps, concentrating tables, cyanide annex.	200
Mogul (A)	Terry	Cyanidation	Gyratory crusher, 2 Trent Chilean mills, 1 Abbe tube mill, 2 Dorr classifiers, continuous decantation and counter current treatment of slime, using 4 Dorr thickeners; 1 Portland filter.	150
Victoria (I)	Portland	do	2 Gates crushers, Davis rolls, Allis-Chalmers rolls, trommels, 5 tanks, dry-crushing and leaching.	200
Lundberg, Dorr & Wilson (I).	Terry	do	Chilean mill, No. 4 Gates crusher, 1 Dorr classifier, 1 Dorr thickener, 4 sand tanks (110 tons); 4 percolation, 1 agitation tank Moore process.	100
New Reliance	Trojan	do	1 Gates crusher, 30 stamps, 1 Dorr classifier, 4 Dorr thickeners, slime tanks, Portland filter.	120
Trojan (A)	do	do	1 Gates No. 5-K crusher, two 7-foot Chilean mills, 1 Ball mill, 3 Dorr classifiers, 1 Weigand classifier, 5 Dorr thickener tanks, 5 agitation tanks, 6 percolation tanks, 3 Portland filters.	400
Bismarck (A)[c]	Yellow Creek (Flat Iron).	do	1 (5-K) and 2 (3-D) Gates crushers, 2 sets rolls, 6 tanks, dry crushing and leaching.	260
Wasp No. 2 (I)[d]	do	do	Steam shovel for stripping, 4 Gates crushers, 4 McFarlane rolls, 6 percolation tanks. Dismantled.	500

[a] Clark, A. J., and Sharwood, W. J., Metallurgy of the Homestake ores: Inst. Min. and Met. Bull. 98, Nov. 14, 1912. Abstracted, Eng. and Min. Jour., Jan. 18, 1913, pp. 161–166, and Jan. 25, 1913, pp. 215–219; also Min. and Eng. World, Dec. 7, 1912, pp. 1035–1039, and Dec. 14, 1912, pp. 1090–1094, and Dec. 21, 1912, pp. 1142–1147, and Dec. 28, 1912, pp. 1189–1192; also Min. and Sci. Press, Jan. 11, 1913, p. 108; also Met. and Chem. Eng., January, 1913, p. 50. Clark, A. J., Notes on Homestake metallurgy: Am. Inst. Min. Eng. Bull. 103, July, 1915, pp. 1381–1400; also Min. and Sci. Press, July 17, 1915, pp. 87–91, and Min. and Eng. World, July 10, 1915, pp. 49–53. Sharwood, W. J., Loss of quicksilver in gold mills: Min. and Sci. Press, Apr. 6, 1918, pp. 483–484.

[b] For description, see Min. and Eng. World, Sept. 28, 1912, p. 571.

[c] For description, see Min. and Sci. Press, Feb. 22, 1913, p. 320.

[d] For description, see Min. and Eng. World, Jan. 4, 1913, p. 11; May 3, 1913, p. 849.

Digitized by Google

Reduction mills in operation in South Dakota in 1917, by counties—Continued.

Name.	Location.	Process.	Equipment.	Approximate daily maximum capacity.
Pennington County:				*Short tons.*
Black Tom (I)...	Castle Creek...	Amalgamation.....	2 crushers, 10 stamps, plates.....	20
Inca (I).....	.....do.....	Amalgamation and concentration.	10 stamps, 2 Wilfley tables.....	30
Hymalulu (I)....	.....do.....	Amalgamation.....	2 stamps.....	15
James G. Blaine (I).	.....do.....	.....do.....	Chilean mill.....	2
Golden Summit (I).	Hill City.....	.....do.....	1 Blake crusher, 10 stamps, plates.	30
Slipper (I).....	.....do.....	.....do.....	5 stamps, plates.....	15
Lisbon (I)..... (Blue Bird)....	Keystone.....	.....	.....	
Otho (I).....	.....do.....	Amalgamation and concentration.	3 crushers, 3 Chilean mills, 3 roller mills, 6 Wilfley tables, Frue vanners.	100
Holy Terror (I)..	.....do.....	Amalgamation, concentration, cyanidation.	1 20-stamp concentration mill, 1 15-stamp concentration mill, 1 cyanide mill (bad state of repair).	80
Clara Belle.....	Oreville.....	Amalgamation and cyanidation.	10 stamps, plates, tanks.....	50
Cochran (I).....	Rochford.....	Amalgamation.....	Huntington mill.....	20
Gold King (I) (Cordelia).	.....do.....	.....do.....	1 crusher, 10 stamps, plates.....	40
Golden West (I)..	.....do.....	.....do.....	Chilean mill, amalgamating plates.	50
North Star (I)....	.....do.....	.....do.....	25-ton Chilean mill, amalgamation plates.	25
Stanby (I).....	.....do.....	.....do.....	3 Blake crushers, formerly 60 stamps (out of repair).	(?)
Home Lode (Silver City (I).	Rapid Creek..	Amalgamation and concentration.	1 crusher, 1 Chilean mill, 2 Simplex sand tables, 2 Simplex slime tables.	30

REVIEW BY COUNTIES.

CUSTER COUNTY.

During the year the Spokane mine, between Custer and Keystone, was reopened and shipped several cars of lead ore. A 100-ton concentrating plant was under construction at this mine.

LAWRENCE COUNTY.[a]

Mine production of gold, silver, copper, and lead in Lawrence County, S. Dak., 1904–1917.

Year.	Number of mines producing.	Ore.	Gold.[b]	Silver.[b]	Copper.	Lead.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	
1904.....	44	1,801,524	$7,346,086	161,216	.....	.....	$7,439,282
1905.....	19	1,826,177	6,955,690	182,597	.....	.....	7,065,979
1906.....	27	1,771,377	6,816,196	150,537	.....	22,719	6,918,351
1907.....	22	1,470,154	4,134,667	93,830	.....	.....	4,196,595
1908.....	17	1,927,844	7,650,523	248,686	.....	23,046	7,783,295
1909.....	17	1,609,260	6,561,628	191,044	3,977	1,512	6,661,553
1910.....	19	1,522,986	5,380,795	118,716	.....	14,136	5,445,523
1911.....	16	1,940,719	7,408,356	203,350	.....	64,311	7,519,025
1912.....	19	1,901,310	7,875,401	206,356	.....	22,845	8,003,338
1913.....	20	1,899,162	7,317,320	172,688	290	10,205	7,422,117
1914.....	21	2,019,016	7,331,638	176,585	.....	2,766	7,429,397
1915.....	25	1,889,970	7,405,552	199,797	.....	.....	7,506,849
1916.....	29	1,870,572	7,455,136	215,127	.....	35,406	7,599,127
1917.....	24	1,868,143	7,360,266	186,436	736	60,905	7,519,328
Increase or decrease..	−5	−2,429	−94,870	−28,691	+736	+25,499	−79,799

[a] For information on the geology of this county see Irving, J. D., Ore deposits of the northern Black Hills: U. S. Geol. Survey Bull. 225, pp. 123–140, 1904. Irving, J. D., and Emmons, S. F., Economic resources of northern Black Hills: U. S. Geol. Survey Prof. Paper 26, pp. 53–212, 1904.

[b] Includes both placer and deep mines.

Digitized by Google

The following table shows the total ore milled, the value of the product, and the dividends paid from 1875 to 1917 by the companies now consolidated in the Homestake Mining Co. The production for 1916 and 1917 is that reported by Blackstone.[1]

Production of Homestake mine, 1875–1917.

	Ore milled.	Value of product.	Value per ton.	Dividends.
	Short tons.			
Homestake Mining Co., to May 31, 1900		$31,204,685.28		$8,668,750.00
Highland Mining Co., to May 31, 1900		13,359,398.95		3,834,717.69
Caledonia Gold Mining Co., to May 31, 1900		2,341,130.92		192,000.00
Deadwood-Terra Mining Co., to May 31, 1900		9,001,002.61		1,350,000.00
Deadwood Mining Co., to May 31, 1900		834,192.28		275,000.00
Father de Smet Mining Co., to May 31, 1900		3,421,199.01		1,125,000.00
Gopher Mining Co., to May 31, 1900		71,140.41		
Clara Consolidated Mining Co., to May 31, 1900		13,590.56		
Total to June 1, 1900		60,246,340.02		15,445,467.69
Homestake Mining Co.:				
June 1, 1900, to June 1, 1901		3,63[illegible],232.03		1,260,000.00
June 1, 1901, to June 1, 1902		4,30[illegible],977.57		1,260,000.00
June 1, 1902, to June 1, 1903		4,52[illegible],942.04		819,000.00
June 1, 1903, to June 1, 1904		4,80[illegible],558.48		655,200.00
June 1, 1904, to June 1, 1905		5,22[illegible],089.30		819,000.00
June 1, 1905, to June 1, 1906		5,10[illegible],445.49		1,310,400.00
June 1, 1906, to June 1, 1907		4,54[illegible],096.07		1,201,200.00
June 1, 1907, to June 1, 1908		4,717,746.20		546,000.00
June 1, 1908, to June 1, 1909		5,72[illegible],046.67		1,365,000.00
June 1, 1909, to June 1, 1910	1,237,381	4,49[illegible],751.11	$3.6357	982,800.00
June 1, 1910, to June 1, 1911	1,468,263	5,251,453.75	3.5766	1,310,400.00
June 1, 1911, to Dec. 31, 1911	888,057	3,661,151.60	4.1205	764,400.00
Calendar year 1912	1,528,923	6,600,953.12	4.3174	1,310,400.00
Calendar year 1913	1,540,961	6,18[illegible],651.78	4.0148	2,146,224.60
Calendar year 1914	1,587,774	6,160,160.59	3.8798	2,210,208.00
Calendar year 1915	1,573,822	6,42[illegible],736.56	4.0848	2,210,208.00
Calendar year 1916	1,600,220	6,531,003.34	4.0813	2,210,208.00
Calendar year 1917	1,677,623	6,619,573.94	3.9458	1,959,048.00
Grand total		154,760,959.66		39,785,164.29

The Homestake Co.'s public report for the calendar year 1917 shows that during the year 1917 the Homestake mine and its reduction works have been operated without interruption. The tungsten mine kept the concentrating mill supplied with profitable ore during the year, and the outlook is encouraging for another year's supply. The big Nordberg hoist, with its skips, has been in satisfactory operation during the most of the year and has demonstrated that it can easily handle all the ore required for the Homestake mills. Loading pockets are in operation at the 800-foot, 1,100-foot, and 1,550-foot levels. A system of ventilating the lower levels by electrically driven fans is now under construction.

During the year 11,075 feet of development drifts, 2,349 feet of development raises, and 5,896 feet of prospecting drifts were driven. The engineers report that 1,919,177 tons of ore were broken down and now remain in the stopes and that a large supply of profitable ore is blocked out in the mine and is readily accessible for continuous excavation.

An electric drive has replaced the high-pressure air compressor installed for haulage and is running very satisfactorily. The Hanna steam pumps have been replaced by electrically driven turbine pumps.

A second water-power plant was built on Spearfish Creek during the year and is now in successful operation.

[1] Blackstone, Richard, A history of the Homestake mine, S. Dak.: Min. and Eng. World, July 15, 1916, pp. 99–102; South Dakota School of Mines Pahasapa Quart., June, 1916, pp. 16–30.

Digitized by Google

Every department of the Homestake's plant is reported to be in first-class condition for continuous operation and output.

In addition to gold and silver, the Homestake Co. sold tungsten ores, for which it received $226,535.

The Oro Hondo shaft, adjoining the Homestake property, was sunk from 2,000 to 2,200 feet and much diamond drilling and drifting was done.

The mines of the Golden Reward group in the Bald Mountain area and the Portland district were operated throughout the year and shipped oxidized ore to the mill at Deadwood. The roasting plant of this company at the Astoria shaft, previously used for a preliminary roast for the unoxidized ore, was idle. The Mogul cyanidation mill, at Terry, was operated chiefly on custom ore shipped from the mines of the Ofer Co.

The capacity of the Trojan mill was materially increased and it was used to treat much custom ore in addition to ore from the company's mines. Small shipments of unoxidized ores were made direct to smelters from the Golden Reward mines and from the Trojan mine. The new Reliance mine and mill were idle. The Elk Mountain mine was operated for a period, the ore being treated at the Deadwood-Standard mill. Other producing mines were the Crown Hill, Decorah, Gold Dollar, and Two Johns.

In the Bear Butte district shipments of lead ore were made from the General Merritt No. 2, General Merritt No. 1, St. Anthony, and New Silver Queen mines. The 50-ton mill on the Rattlesnake Jack mine was not operated.

In the Custer Peake district only development work was done.

In the Maitland district shipments were made from the Republic mine to the Trojan mill. In the Two-Bit district shipments were made from the Heidelberg mine and from the Monarch mine.

In the Yellow Creek area, the Wasp No. 2 mine and mill were idle, and early in 1917 the mill was dismantled. The Bismarck mine and mill were operated for a period.

In the Rawlings district, near Tinton, a reduced yield of placer gold was made from several placers located chiefly in Bear Gulch and Potato Creek.

PENNINGTON COUNTY.

Mine production of gold, silver, copper, and lead in Pennington County, S. Dak., 1904–1917.

Year.	Number of mines producing.	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	
1904	16	1,511	$10,500	274	.....	.....	$10,657
1905	8	11,218	33,096	149	.....	.....	33,186
1906	6	9,281	24,586	335	.....	.....	24,810
1907	7	969	3,190	62	.....	.....	3,231
1908	8	1,235	5,320	72	.....	.....	5,358
1909	13	4,481	14,897	3,208	114,408	.....	31,438
1910	7	943	21,462	84	.....	.....	21,508
1911	16	5,408	31,209	401	.....	.....	31,422
1912	16	341	14,782	101	.....	.....	14,844
1913	5	.....	1,780	13	.....	.....	1,788
1914	8	229	1,664	52	.....	1,131	1,737
1915	10	.....	344	2	.....	.....	345
1916	6	211	5,391	78	.....	.....	5,442
1917	5	146	3,963	147	9,971	.....	4,084
Increase or decrease...	−1	−65	−1,428	+69	+9,971	.....	−1,358

[a] Includes both deep and placer mines.

Digitized by Google

A car of copper ore was shipped from the Maloney Blue Lead mine, near Hill City, and from the property of the Black Hills Copper Co., at Rockford. Several cars of gold ore were shipped from the Columbia mine, near Keystone.

A small quantity of placer gold was recovered from Battle and Rapid creeks.

Digitized by Google

GOLD, SILVER, AND COPPER IN WYOMING.

(MINES REPORT.)

By CHARLES W. HENDERSON.

PRODUCTION.

The total value of the gold, silver, and copper produced at mines in Wyoming in 1917 was $560,181, as compared with $666,414 in 1916. The copper alone was valued at $553,605. There were 17 producing mines, of which 16 were deep and 1 placer, a decrease of 8 deep and 3 placer, as compared with 1916. The quantity of ore sold or treated was 6,335 tons, as compared with 8,876 tons in 1916. The deep mines yielded $3,728 in gold, 3,415 ounces of silver, and 2,027,857 pounds of copper. The placer gold produced amounted to only $34, in 1917, as against $349 in 1916.

Mine production of gold, silver, and copper in Wyoming, 1916 and 1917.

Year.	Ore.	Gold.[a]		Silver.[a]		Copper.		Total value.
		Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	
	Short tons.	*Fine ounces.*		*Fine ounces.*		*Pounds.*		
1916	8,876	994.88	$20,566	5,524	$3,635	2,610,622	$642,213	$666,414
1917	6,335	181.98	3,762	3,415	2,814	2,027,857	553,605	560,181
Decrease	2,541	812.90	16,804	2,109	821	582,765	88,608	106,233

[a] Includes placer gold and silver.

Mine production of gold, silver, and copper in Wyoming, 1842–1917.[a]

Period.	Gold.	Silver.		Copper.		Total value.
	Value.	Quantity.	Commercial value.	Quantity.	Value.	
		Fine ounces.		*Pounds.*		
1842–1867	(b)					
1867–1870	$396,100	3,170	$4,098			$400,198
1871–1880	400,000	3,240	4,115			404,115
1881–1890	67,500	2,940	3,126	1,395,287	$230,521	301,147
1891–1900	131,700	1,400	943	7,541,647	1,257,649	1,390,292
1901–1910	130,259	45,983	26,896	16,906,466	2,579,095	2,736,250
1911	19,200	725	884	120,499	16,312	35,396
1912	22,235	265	163	25,080	4,138	26,536
1913	24,184	957	578	385,239	59,712	84,474
1914	5,006	116	64	17,421	2,317	7,387
1915	14,592	840	426	447,246	78,268	93,286
1916	20,566	5,524	3,635	2,610,622	642,213	666,414
1917	3,762	3,415	2,814	2,027,857	553,605	560,181
	1,235,104	68,575	47,242	31,487,364	5,423,830	6,706,176

[a] For yearly output and authority for each, see U. S. Geol. Survey Mineral Resources, 1912, pt. 1, p. 925, 1913.

[b] Small; unknown.

Digitized by Google

Mine production of gold and silver in Wyoming, 1916 and 1917.

Source.	Number of mines.	Ore.	Gold.		Silver		Total value.
			Quantity.	Value.	Quantity.	Value.	
		Short tons.	*Fine ounces.*		*Fine ounces.*		
Deep mines, 1917:							
Siliceous ore	2	49	92.30	$1,908	33	$27	$1,935
Copper ore	14	6,286	88.04	1,820	3,382	2,787	4,607
Total deep mines:							
1916	24	8,876	978.00	20,217	5,523	3,634	23,851
1917	16	6,335	180.34	3,728	3,415	2,814	6,542
Decrease	8	2,541	797.66	16,489	2,108	820	17,309
Placer mines, 1916	4	.....	16.88	349	1	1	350
Placer mines, 1917	1	.....	1.64	34	.....	.....	34
Decrease	3	.....	15.24	315	1	1	316
Total deep and placer mines, 1917.	17	6,335	181.98	3,762	3,415	2,814	6,576

REDUCTION MILLS.

Reduction mills in Wyoming in 1917.

[I, idle; B, building; E, experimental; C, clean-up.]

Name.	District.	Process.	Equipment.	Approximate maximum daily capacity.
				Short tons.
Albany County:				
Rambler (I)	Douglas Creek.	Concentration	1 crusher, 3 rolls, 5 Wilfley and 1 Deister tables, home-construction classifiers.	75
Fram (I)	Centennial	Amalgamation and concentration.	3 stamps, 1 concentrating table	12
Snowy Range (I)	do	Amalgamation	1 Chilean mill	5
Gould (B)	do	Amalgamation and cyanidation.	1 crusher, 2 rolls, 1 tube mill, 6 tanks, roaster.	50
Carbon County:				
Penn Wyoming [a] (I).	Encampment.	Concentration	Blake crusher, elevator, revolving screens, roughing rolls, 2 Hancock jigs, capacity 700 tons per day, rolls, 12 No. 5 Wilfley tables, and slime treatment equipment. Idle for many years.	1,000
Penn-Seminole	Seminole	Amalgamation	20 stamps, amalgamating plates	80
Crook County:				
Reuter (I)	Bear Lodge	Cyanidation	5-foot Huntington mill, 10 by 5 feet percolation tank, 2 Gates crushers.	30
Bock (E)	do	Amalgamation and cyanidation.	1 Gates crusher, 10 stamps, amalgamating plates, tanks.	30
Fremont County:				
Duncan [b] (I) (Beck).	Atlantic City	do	1 Blake crusher, 4 Nissen crushers, 1 Akins classifier, 2 cone classifiers, 5-foot Wheeler type pan tube mill, 4 cyanidation tanks, 3 Dorr thickeners, cyanidation by agitation and decantation, 1 mechanical agitation tank, 1 sand filter tank.	30
Barr (I)	do	Amalgamation	5-foot Huntington mill, 10 stamps.	25
Carissa (C) (Federal).	do	Amalgamation and concentration.	Crusher, 10 stamps 850 pounds each, 1 Frue vanner.	25
Mary Ellen (I)	do	Amalgamation	Denver quartz mill	25
Miners Delight (I).	do	Amalgamation and concentration.	10 stamps, tables	25
Timbah Bah [b] (Dexter) (I).	do	Amalgamation and cyanidation.	Stamps, plates, Dorr classifiers, 6 tanks.	100
Johnson County:				
Onion Creek (I)	Buffalo	Amalgamation	5 stamps, plates, Pierce rifles	10

[a] Beeler, H. C., Mineral resources of Wyoming, p. 23, Wyoming State Board of Immigration, 1907.
[b] Trumbull, L. W., Atlantic City gold mining district, Fremont County, Wyo.: Wyoming State Geologist Bull. 7, ser. B, 1914.

Digitized by Google

MINING INDUSTRY.

The Hartville district, Platte County, with shipments slightly in excess of material shipped in 1916 in weight of ore but of lower content of copper, maintained its place as the principal producing district in Wyoming in 1917. The increased shipments of copper-platinum-palladium ore from the Rambler property, at Holmes, Albany County, made that district the second most important in Wyoming. Various shipments of copper-bearing material from the Encampment district, Carbon County (long idle) contributed an appreciable quantity of copper to the State's output. Reopening of properties in the Copper Mountain district, Fremont County, resulted in shipments of copper ore from the Williams-Luman and the McGrath mines. Small shipments of copper ore were made from the Muskrat Creek (or Manville) district, Goshen County; a car of copper ore was shipped from the Cokeville district, Lincoln County; and one car of copper ore from Tie Siding, Albany County. Small shipments of gold ore and of placer gold bullion were made from the Atlantic City district, Fremont County.

REVIEW BY COUNTIES.[1]

ALBANY COUNTY.[2]

At the Rambler mine, near Holmes, operations were continuous in opening old caved ground and blocking out ore. A considerably increased quantity of ore containing platinum, palladium, copper, silver, and gold was shipped during the year to eastern refineries. The mine is opened by a 180-foot vertical shaft and 5,000 feet of drifts and crosscuts. There is a 50-ton concentration mill on the property, abandoned for the present as unsuitable for the treatment of the ore now being mined.

A car of copper ore was shipped from the Copper King mine, near Tie Siding.

Some development work was done in the Centennial district. A 50-ton mill was built by the Gould Mining & Leasing Co.

BIG HORN COUNTY.[3]

No mining was done in the county in 1917.

CARBON COUNTY.[4]

Some development work was done at the Elkhorn mine in the Elk Mountains district.

The mine and mill on the Penn-Seminole-King group, in the Seminole district, were idle.

---

[1] In this review the footnote references indicate publications containing information on the geology of the respective regions.

[2] Emmons, S. F., Platinum in copper ores in Wyoming: U. S. Geol. Survey Bull. 213, pp. 94–97, 1903. Kemp, J. F., Platinum in the Rambler mine, Wyo.: U. S. Geol. Survey Mineral Resources, 1902, pp. 244–250, 1904. Platinum in Wyoming: Eng. and Min. Jour., Mar. 4, 1911, p. 460. Concentration of platiniferous copper ore at the Rambler mine, Wyo.: Met. and Chem. Eng., February, 1911, pp. 75–78. Spencer, A. C., The Atlantic gold district and the North Laramie Mountains.: U. S. Geol. Survey Bull. 626, pp. 56–77, 1916.

[3] Darton, N. H., U. S. Geol. Survey Geol. Atlas, Bald Mountain-Dayton folio (No. 141), and Cloud Peak-Fort McKinney folio (No. 142), 1906; Geology of the Bighorn Mountains: U. S. Geol. Survey Prof. Paper 51, 1906. Fisher, C. A. Geology and water resources of Bighorn Basin, Wyo.: U. S. Geol. Survey Prof. Paper 53, 1906.

[4] Spencer, A. C., Mineral resources of the Encampment copper region, Wyo.: U. S. Geol. Survey Bull. 213, pp. 158–162, 1903; also Copper deposits of the Encampment district, Wyo.: U. S. Geol. Survey Prof. Paper 25, 107 pp., 1904. See also Spencer, A. C., Reconnaissance examination of the copper deposits at Pearl, Colo.: U. S. Geol. Survey Bull. 213, pp. 163–169, 1903.

Digitized by Google

In the Encampment district, several cars of copper-bearing material were shipped from various sources and a car of copper ore was shipped from the Portland Copper Co.'s property.

CONVERSE COUNTY.[1]

No work was done in the North Laramie Peak district nor in the Cottonwood Creek district.

CROOK COUNTY.

Apparently no gold was recovered in the Hurricane district, northwest of Tinton, S. Dak., or if any small quantity were produced, it is included in the Rawlings district, Pennington County, S. Dak., adjoining on the east. In the Bear Lodge district[2] a very small button of gold was yielded in 1917 from the Warren Peak Co.'s mill.

FREMONT COUNTY.

Atlantic City (South Pass) district.[3]—A small shipment of copper ore was made from the Elenor mine, and small shipments of gold ore and gold bullion from the Ben Hur—Lucky Strike property.

Copper Mountain district.—A car of copper ore was shipped from the McGrath mine as a test lot.

Several cars of copper ore were shipped from the Williams-Luman property, reopened in October, 1916, after an idleness of several years.

Gold placers on Wind and Big Horn rivers.[4]—No yield was made from these deposits.

GOSHEN COUNTY.

Two cars of silver-copper ore were shipped from the Muskrat Creek district.

JOHNSON COUNTY.[5]

No work was done in the Big Goose, Bull Camp, and Kelly Creek districts.

LARAMIE COUNTY.

The properties in the Silver Crown district, near Hecla, were idle.

LINCOLN COUNTY.[6]

A car of silver-copper ore was shipped from Cokeville.

NATRONA COUNTY.

Assessment work was done on the Nettie M. mine, in the Casper Mountain district, 10 miles south of Casper.

---

[1] Spencer, op. cit. pp. 66–71, 80–81.

[2] Darton, N. H., U. S. Geol. Survey Geol. Atlas, Sundance folio (127), 1905.

[3] Trumbull, L. W., Atlantic City gold mining district, Fremont County, Wyo.: Wyoming State Geologist Bull. 7, ser. B, 1914. Spencer, A. C., The Atlantic gold district and the North Laramie Mountains: U. S. Geol. Survey Bull. 626, pp. 1–45, 1916.

[4] Schrader, F. C., Gold placers on Wind and Big Horn rivers, Wyo.: U. S. Geol. Survey Bull. 580, pp. 127–145, 1915.

[5] Darton, N. H., U. S. Geol. Survey Geol. Atlas, Bald Mountain-Dayton folio (No. 141), and Cloud Peak-Fort McKinney folio (No. 142), 1906; also Geology of the Bighorn Mountains: U. S. Geol. Survey Prof. Paper 51, 1906.

[6] Schultz, A. R., Gold developments in central Uinta County, Wyo., and at other points on Snake River: U. S. Geol. Survey Bull. 315, pp. 71–88, 1907.

Digitized by Google

PARK COUNTY.

Very little work was done in the Sunlight and Kirwin district.[1]

PLATTE COUNTY.[2]

Shipments of copper-silver ore were continued from the Hartville district[3] in 1917, chiefly from the Sunrise mine, near Sunrise.

SHERIDAN COUNTY.

No work was done on the prospects in the Black Mountain, Wolf Creek, and Tongue River districts.

UINTA COUNTY.[4]

No output has been recorded from Uinta County since 1915. The present Uinta County includes only the southern part of the former Uinta County, the northern part (about four-fifths) having been set off in 1915 as Lincoln County.

---

[1] Hewett, D. F., The ore deposits of Kirwin, Wyo.: U. S. Geol. Survey Bull. 540, pp. 121–132, 1914.
[2] The northwestern part of Laramie County prior to 1913.
[3] Smith, W. S. T., U. S. Geol. Survey Geol. Atlas, Hartville folio (No. 91), 1903. Ball, S. H., Copper deposits of the Hartville uplift, Wyoming: U. S. Geol. Survey Bull. 315, pp. 93–107, 1907.
[4] Schultz, A. R., Gold developments in central Uinta County, Wyo., and at other points on Snake River: U. S. Geol. Survey Bull. 315, pp. 71–88, 1907.

Digitized by Google

Digitized by Google

GOLD, SILVER, COPPER, LEAD, AND ZINC IN UTAH.[1]

(MINES REPORT.)

By V. C. Heikes.

PRODUCTION.

GENERAL STATEMENT.

In 1917 the output of gold, silver, copper, lead, and zinc from Utah mines was valued at $99,328,155, an increase of $10,059,471, compared with 1916. There were 331 lode producers and 3 placers, as against 310 lode producers and 8 placers in 1916. There was increase in the output of ore and in the production of silver and copper, as well as in the value of those metals. Gold decreased from $3,574,947 in 1916 to $3,355,156 in 1917, and silver increased in value from $8,720,498 to $11,106,806. Lead decreased in quantity but increased in value to $15,352,888, or $1,450,073 more than in 1916. The value of recoverable zinc decreased from $3,962,719 to $2,171,261 in 1917, and the placer output of gold decreased from $1,250 in 1916 to $112 in 1917.

Mine production of gold, silver, copper, lead, and zinc in Utah in 1916–17.

Year.	Number of producers.	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	318	13,920,643	$3,574,947	13,253,037	240,275,222	201,490,075	29,572,528	$89,268,684
1917	334	15,358,481	3,355,156	13,479,133	246,674,153	178,521,958	21,296,871	99,328,155
Increase or decrease in 1917	.....	+1,437,838	−219,791	+226,096	+6,398,931	−22,968,117	−8,285,657	+10,059,471
1864–1917	.....	.....	93,119,333	366,020,527	1,962,162,413	3,975,600,157	191,957,609	[b]916,155,337

[a] Includes small placer production.
[b] The total, by years, to the end of 1913, appears in Mineral Resources, 1913, pt. 1, p. 366, 1914.

Since the year 1864 Utah mines have produced gold, silver, copper, lead, and zinc valued at $916,155,337. This includes $93,119,333 in gold, $271,788,824 in silver, $346,681,440 in copper, $188,715,846 in lead, and $15,849,894 in zinc. Dividends paid by 21 producers in

[1] The statistical tables in this report were compiled by Bessie N. Patchell, of the United States Geological Survey.

Digitized by Google

1917 amounted to the sum of $29,471,015. In the history of the State dividends paid to stockholders of mining property, representing more than 85 mines, have amounted to $182,245,816.

ORE.

There were sold or treated in 1917 15,358,481 short tons of ore, containing recoverable metals valued at $99,328,043—an increase of 1,437,838 tons, compared with the production of 1916. The total average value per ton was $6.47 in 1917, against $6.41 in 1916, and the gold and silver value per ton increased from 88 cents to 94 cents. There was an increased quantity of low-grade disseminated copper ore produced in 1917, and many old mine and tailing dumps continued to yield profitable material for the mills and smelters.

The output of dry or siliceous ore increased from 89,363 tons in 1916 to 164,057 tons in 1917. This classification includes 14,728 tons of siliceous gold ores, averaging $6.57 in gold, 3.83 ounces of silver, and 3.92 pounds of copper per ton. Gold and silver mixed ores, dry or siliceous in character, aggregated 25,318 tons and averaged per ton $3.97 in gold, 6.01 ounces of silver, and 40.34 pounds of copper. The siliceous silver ores mined in 1917 by 50 producers amounted to 124,011 tons and averaged per ton $1.81 in gold, 17.19 ounces of silver, 7.90 pounds of copper, and 7.87 pounds of lead, against 83,718 tons produced by 40 operators in 1916, which averaged $1.81 in gold, 13.31 ounces of silver, 16.84 pounds of copper, and 1.81 pounds of lead. The Dragon Consolidated mine in the Tintic district was the heaviest producer of silver ore, followed by the Iron Blossom, Chief Consolidated, and Victoria mines. The Ontario mine, at Park City, was next in importance as a shipper of silver ore. The chloridizing roasting process was operated only in the Tintic district in 1917, and 60,767 tons of siliceous silver ores were directly treated, yielding a base bullion of copper, silver, and gold. This bullion was treated at eastern refineries.

The copper ore mined by 122 producers amounted to 14,121,671 tons, which contained 14 cents in gold and 0.16 ounce of silver per ton, and 0.84 per cent of copper, and averaged $4.83 a ton in value. Comparison with ore of similar character in 1916 shows that the quantity increased 1,445,519 tons, the gold and silver content decreased slightly, and the copper content was nearly the same. Of the copper ore mined, the larger part, or 13,326,810 tons, was from the low-grade disseminated deposits. This ore produced 648,907 tons of copper concentrates, which were smelted. There were 617,156 tons of copper ore smelted directly, of which 447,230 tons were sulphide ore, assaying $1.46 in gold and 1.55 ounces of silver per ton, and 1.91 per cent of copper, and valued in all, per ton, at $13.18; and 169,926 tons were oxidized ore, assaying $1.59 in gold and 5.91 ounces of silver per ton, and 3.29 per cent of copper, valued in all, per ton, at $24.41.

Less lead ore was mined in 1917 than in 1916. The output of 190 producers aggregated 638,071 tons and averaged 88 cents in gold and 11.74 ounces of silver per ton, and 0.49 per cent of copper and 10.75 per cent of lead, and $31.73 in total value per ton. Of this output 446,786 tons of sulphide and oxidized ores in about equal quantities were shipped directly to the smelters, the total quantity averaging

Digitized by Google

$1.09 in gold and 15.38 ounces of silver per ton, 0.59 per cent of copper and 13.56 per cent of lead, and $40.30 in value per ton. Of the lead ores, 179,907 tons were concentrated, yielding 44,630 tons of lead concentrate averaging $1.63 in gold and 13.73 ounces of silver per ton, and 1.09 per cent of copper and 17.89 per cent of lead, and $49.69 in total value per ton. Lead concentrate from 241,593 tons of lead-zinc ore aggregated 86,260 tons, averaging $4.55 in gold and 12.33 ounces of silver per ton, and 0.67 per cent of copper and 20.51 per cent of lead, and $53.65 in total value per ton.

Zinc ore shipped from 22 properties in 1917 aggregated 6,535 tons, against 18,400 tons from 32 producers in 1916. All the zinc ores produced in 1917 was of smelting grade and averaged 28.04 per cent of recoverable zinc, with a little lead. Of this product 6,404 tons were oxidized or mixed carbonate and silicate ores, averaging 27.96 per cent of recoverable zinc, and 131 tons were sulphide ore, averaging 31.54 per cent of recoverable zinc. Zinc was produced electrolytically from zinc concentrate at the Judge reduction plant near Park City. This plant was still in the experimental stage in 1917. Zinc concentrates saved from lead-zinc ore milled aggregated 14,094 tons and averaged 41 cents in gold and 9.34 ounces of silver per ton, 0.60 per cent of copper, 2.33 per cent of lead, and 32.67 per cent of recoverable zinc. There were also zinc concentrates recovered from tailings averaging 34.69 per cent of recoverable zinc.

There were 27 lead-zinc producers in 1917 who reported 421,704 tons of ore and old tailings re-treated. The ore was milled, making a lead concentrate and a zinc concentrate. The tailings yielded 12,924 tons of lead-zinc concentrates, which averaged 91 cents in gold and 10.37 ounces of silver per ton, and 0.85 per cent of copper, 7.52 per cent of lead, 29.62 per cent of zinc, and $87.46 in value per ton. There were 3,413 tons of lead-zinc ore shipped to smelters, averaging 11.05 per cent of recoverable zinc and 11.74 per cent of lead, valued at $42.90 per ton.

Copper-lead ore, most of it oxidized or carbonates, decreased from 9,645 tons produced by 19 mines in 1916 to 6,443 tons produced by 28 mines in 1917. Of this ore, 6,326 tons was of smelting grade and averaged 25 cents in gold and 14.46 ounces of silver per ton, and 3.05 per cent of copper, and 11.18 per cent of lead, and $48.04 in value per ton. The remainder of the copper-lead product was 117 tons of sorted slag.

Concentrates of all kinds produced in Utah in 1917, including those heretofore mentioned, aggregated 813,287 tons, contained more than 45 per cent of the gold, against more than 40 per cent in 1916; more than 18 per cent of the silver, against nearly 19 per cent in 1916; more than 85 per cent of the copper, against more than 84 per cent; 30 per cent of the lead, about the same as in 1916; and more than 79 per cent of the zinc, against about 60 per cent in 1916. In 1917 the recoverable metal content of the concentrates was valued at $67,283,690, or a total average value per ton of $82.73, as against a total value in 1916 of $59,571,419, or a total average value per ton of $79.50.

Crude ore of all kinds shipped directly to the smelters represented more than 7.67 per cent, or 1,178,002 tons, of the total output and produced nearly 54 per cent of the gold in 1917, as against more than

Digitized by Google

59 per cent in 1916; nearly 78 per cent of the silver, against nearly 80 per cent; more than 14 per cent of the copper, against more than 15 per cent; nearly 70 per cent of the lead, against nearly 69 per cent; and nearly 21 per cent of the zinc, against nearly 39 per cent in 1916. In 1917 the total value of the crude ore shipped to smelters was $31,344,169, or an average value per ton of $26.61, as against a total value in 1916 of $29,202,373, or an average value per ton of $22.79.

At mills using cyanidation and amalgamation a negligible quantity of gold and silver was recovered from 190 tons of ore. The value of the gold and silver recovered from ore was $2,929, or $15.42 per ton. In 1916 the recovery of gold and silver from ores given similar treatment was valued at $6,613, or an average value per ton of $4.65.

Ore and metals produced in Utah in 1917.

Source of production.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Placers	3	.....	$112	.....	.....	.....	.....
Dry or siliceous	58	164,057	421,594	2,340,537	2,579,070	976,227	.....
Copper	122	14,121,671	1,960,617	2,225,119	235,899,850	14,372	.....
Lead	190	638,071	560,527	7,490,650	6,256,268	137,245,961	.....
Zinc	22	6,535	.....	.....	.....	60,078	3,664,962
Copper-lead	28	6,443	1,907	93,296	393,079	1,436,782	.....
Lead-zinc	27	421,704	410,399	1,329,531	1,545,886	38,788,038	17,621,909
		15,358,481	3,355,156	13,479,133	246,674,153	178,521,958	21,286,871

Ore sold or treated in Utah in 1917, in short tons.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-lead ore.	Lead-zinc ore.	Total.
Beaver	96	239,643	18,894	1,311	253	47,841	308,038
Box Elder	197	10,547	2,064	1,151	.....	30	13,989
Cache	.....	57	.....	.....	.....	.....	57
Emery	.....	17	.....	.....	.....	.....	17
Garfield	15	9	.....	.....	.....	.....	24
Grand	46	40	.....	.....	.....	.....	86
Iron	3	.....	446	.....	.....	.....	449
Juab	137,365	96,907	128,269	1,540	3	276	364,360
Millard	.....	147	31	.....	.....	.....	178
Morgan	.....	.....	171	.....	.....	.....	171
Piute	75	53	2,000	.....	.....	.....	2,128
Salt Lake	9,545	13,743,334	270,142	9	604	240,046	14,263,680
San Juan	.....	28	.....	.....	.....	.....	28
Sanpete	.....	.....	16	.....	.....	.....	16
Summit	12,034	44	87,797	.....	.....	75,045	174,920
Tooele	263	30,466	93,307	2,149	5,583	280	132,048
Uinta	.....	4	1	.....	.....	.....	5
Utah	4,175	51	27,672	375	.....	.....	32,273
Wasatch	243	.....	7,261	.....	.....	58,186	65,690
Washington	.....	324	.....	.....	.....	.....	324
	[a] 164,057	14,121,671	638,071	6,535	6,443	421,704	15,358,481
Value per ton in gold and silver	$14.33	$0.27	$10.55	.....	$12.23	$3.57	$0.94

[a] Includes 14,728 tons of gold ore, 25,318 tons of gold and silver ore, and 124,011 tons of silver ore.

GOLD.

The mine production of gold reported from all sources by Utah producers in 1917 was $3,355,156—a decrease of $219,791, compared with 1916. The largest part of the gold was contained in ores produced in Salt Lake County and amounted to $2,268,684, against

Digitized by Google

$2,513,096 in 1916. Juab County ranked next, with $843,609, against $856,474 in 1916. Bingham district produced $2,241,152, and Tintic district $868,547; in 1916 these outputs were, respectively, $2,490,158 and $855,454. Tooele County mines were credited with $32,344, against $18,882 in 1916. Placer gold was produced in Grand and Uinta counties and amounted in value to $112, against $1,250 in 1916. Ores treated in mills equipped for amalgamation produced $2,908 in gold in 1917 from 190 tons of ore mined in Beaver, Box Elder, and Garfield counties. No cyanidation of ore was reported in 1917. The gold extracted by amalgamation averaged $15.31 a ton of ore treated, as against $6.90 a ton treated in 1916. Concentrates of copper, lead, lead-zinc, and zinc, and a small quantity of siliceous concentrate contained altogether $1,522,982 in gold, against $1,433,992 in 1916. Copper concentrates contained the largest quantity of gold, or 50,280.80 ounces, against 47,028.69 ounces in 1916, 37,836.53 ounces in 1915, 35,863.89 ounces in 1914, and 29,699.38 ounces in 1913; the lead concentrates contained 22,522.72 ounces, against 21,875.79 ounces in 1916; and the zinc concentrates 294.14 ounces, against 126.88 ounces in 1916. Lead-zinc concentrates in 1917 produced 571 ounces of gold, against 337.73 ounces in 1916.

A large part of the gold produced in Utah is a by-product of the copper and lead ores. Ranking first in 1917, the Utah Copper property is credited with 51,111.71 ounces. The United States property reported about two-thirds of its output of gold as contained in lead ores and the remainder in copper ores. Next in importance as producers of gold, named in order of production, were the Highland Boy, with 13,530 ounces; the Centennial-Eureka, and the Chief Consolidated, which reported 9,175 ounces.

Mine production of gold in Utah in 1917, in fine ounces.

County.	Placers.	Dry or siliceous ore.	Copper ore.	Lead ore.	Copper-lead ore.	Lead-zinc ore.	Total.
Beaver	.....	3.44	606.88	1,308.48	0.93	272.33	2,192.06
Box Elder	.....	121.74	.20	58.38	.....	.....	188.32
Garfield	.....	12.42	17.24	.....	.....	.....	29.66
Grand	1.60	.87	.24	.....	.....	.....	2.80
Iron	.....	1.94	.....	1.98	.....	.....	3.92
Juab	.....	19,522.28	12,314.75	8,972.17	.39	.....	40,809.59
Millard	.....	.....	18.62	.....	.....	.....	18.62
Piute	.....	138.87	12.91	887.94	.....	.....	1,039.72
Salt Lake	.....	94.98	81,296.87	9,393.32	27.97	18,934.45	109,747.59
Summit	.....	378.28	.....	4,305.44	.....	206.17	4,889.89
Tooele	.....	29.87	537.54	932.73	62.96	1.54	1,564.64
Uinta	3.73	.....	.....	.....	.....	.....	3.73
Utah	.....	79.23	39.60	1,233.64	.....	.....	1,352.47
Wasatch	.....	2.69	.....	21.41	.....	438.56	462.66
	5.42	[a]20,394.61	94,844.85	27,115.49	92.25	19,853.05	162,305.67

[a] Includes 4,678.60 ounces from gold ore, 4,864.68 ounces from gold and silver ore, and 10,851.33 ounces from silver ore.

SILVER.

The mine production of silver in Utah in 1917 was 13,479,133 ounces, valued at $11,106,806, an increase of 226,096 ounces in quantity and of $2,386,308 in value. The largest production was from Juab County, credited with 4,988,005 ounces, against 4,892,439 ounces in 1916. Salt Lake County had the next largest output, 3,769,884

Digitized by Google

ounces in 1917, against 3,863,264 ounces in 1916. The Bingham district in Salt Lake County produced 2,786,120 ounces, or more than 73 per cent of the county total; Tintic district, in Juab and Utah counties, 5,558,763 ounces, and the Park City region, in Summit and Wasatch counties, 2,937,438 ounces. Concentrates produced at milling plants yielded 2,469,804 ounces of silver, against 2,473,132 ounces in 1916. The copper ores milled produced 525,923 ounces, against 488,742 ounces in 1916, 412,745 ounces in 1915, 358,486 ounces in 1914, and 324,586 ounces in 1913. Lead concentrates from low-grade lead ore contained 1,675,899 ounces of silver, or an average per ton of 12.80 ounces, against 1,792,713 ounces, or an average of 10.87 ounces, in 1916; zinc concentrates contained 9.34 ounces per ton, against 4.61 ounces per ton in 1916. The lead-zinc concentrate contained 10.37 ounces per ton in 1917.

The silver content of bullion produced from ores treated by amalgamation was 26 ounces, against 146 ounces in 1916. No cyanidation of silver ores was reported in 1917. One mill in Utah, at Silver City, using a chloridizing roast on ores, recovers a rich silver bullion, from which 497,915 ounces were reported in 1917.

Six properties produced more than 500,000 ounces of silver in 1917. The Chief Consolidated, in the Tintic district, ranked first with an output of 1,534,907 ounces, followed by the Silver King Coalition, United States mines, at Bingham, Centennial-Eureka, Utah Copper, and Eagle & Blue Bell mine.

Mine production of silver in Utah in 1917, in fine ounces.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Copper-lead ore.	Lead-zinc ore.	Total.
Beaver	1,105	31,962	175,340	3,427	85,999	297,833
Box Elder	1,423	2,607	16,434	.....	.....	20,464
Cache	.....	52	.....	.....	.....	52
Emery	.....	17	.....	.....	.....	17
Garfield	3	36	.....	.....	.....	39
Grand	3,986	706	.....	.....	.....	4,692
Iron	948	.....	493	.....	.....	1,441
Juab	1,532,513	845,897	2,609,480	115	.....	4,988,005
Millard	.....	332	42	.....	.....	374
Morgan	.....	.....	703	.....	.....	703
Piute	909	885	44,946	.....	.....	46,740
Salt Lake	378,215	1,211,092	1,445,595	15,393	719,589	3,769,884
San Juan	.....	113	.....	.....	.....	113
Summit	360,356	228	1,794,045	.....	121,954	2,276,583
Tooele	8,472	130,699	578,138	74,361	1,595	793,265
Uinta	.....	18	2	.....	.....	20
Utah	47,800	431	569,778	.....	.....	618,009
Wasatch	4,807	.....	255,654	.....	400,394	660,855
Washington	.....	44	.....	.....	.....	44
	[a]2,340,437	2,225,119	7,490,650	93,296	1,329,531	13,479,133

[a] Includes 56,383 ounces from gold ore, 152,231 ounces from gold and silver ore, and 2,131,923 ounces from silver ore.

COPPER.

The production of copper in 1917 in Utah was 246,674,153 pounds, valued at $67,342,044—an increase of 6,398,931 pounds in quantity and of $8,234,339 in value. Bingham or West Mountain district produced 225,411,675 pounds of copper in 1917, against 223,619,609 pounds in 1916, 176,593,414 pounds in 1915, 141,924,811 pounds in

Digitized by Google

1914, 144,920,494 pounds in 1913, 116,621,793 pounds in 1912, and 129,995,865 pounds in 1911; Tintic district produced 9,117,723 pounds in 1917, against 7,106,645 pounds in 1916; Park City region produced 1,285,308 pounds, against 1,512,578 pounds in 1916; Beaver County, 3,702,085 pounds, against 3,203,688 pounds in 1916; and Tooele County, 4,181,231 pounds, against 2,836,678 pounds in 1916.

Concentrates of all kinds produced at Utah milling plants contained 210,127,703 pounds of copper, against 202,854,684 pounds in 1916. Copper concentrates contained 207,603,875 pounds, against 199,997,786 pounds in 1916; lead concentrates, 2,134,184 pounds, against 2,726,091 pounds in 1916; zinc concentrates, 168,483 pounds, against 25,440 pounds in 1916; and lead-zinc concentrates, 219,167 pounds, against 105,367 pounds in 1916. Crude ore shipped to smelters contained 35,688,301 pounds of copper, against 36,830,473 pounds in 1916. The crude copper ore smelted contained 28,282,873 pounds, of which 17,114,351 pounds were from sulphide ores and 11,168,522 pounds were from oxidized ores. Lead ores smelted produced 5,259,363 pounds of copper, the sulphide ores yielding 3,878,101 pounds and the oxidized ores 1,381,262 pounds. Copper-lead ores, which were mostly sulphides, contained 385,688 pounds of copper. The dry or siliceous ores, used principally for fluxing at smelting plants, contained 1,760,377 pounds, against 977,497 pounds in 1916. Copper ore from the low-grade copper-bearing disseminated ores contained 208,768,759 pounds of copper, against 199,996,870 pounds in 1916, 156,040,257 pounds in 1915, 125,777,441 pounds in 1914, 126,364,491 pounds in 1913, and 102,662,335 pounds in 1912. Part of the tailing of the Cactus mill, in Beaver County, was reworked and the output is included above.

The leading producers of copper named in order of production were the Utah Copper Co., reporting 206,174,442 pounds; the Highland Boy, 7,968,165 pounds; and the Ohio Copper Co.

Mine production of copper in Utah in 1917, in dry pounds.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Copper-lead ore.	Lead-zinc ore.	Total.
Beaver	2,114	3,377,849	250,593	15,556	55,973	3,702,085
Box Elder	.....	1,361,119	222	.....	.....	1,361,341
Cache	.....	4,717	.....	.....	.....	4,717
Emery	.....	6,063	.....	.....	.....	6,063
Garfield	.....	2,749	.....	.....	.....	2,749
Grand	1,667	12,772	.....	.....	.....	14,439
Iron	.....	.....	78	.....	.....	78
Juab	2,530,137	6,217,154	313,103	171	.....	9,060,565
Millard	.....	16,267	.....	.....	.....	16,267
Piute	.....	4,004	14,766	.....	.....	18,770
Salt Lake	27,925	222,800,919	2,796,520	57,693	1,091,333	226,774,390
San Juan	.....	14,918	.....	.....	.....	14,918
Summit	13,406	6,214	708,085	.....	44,416	772,121
Tooele	1,012	1,925,944	1,931,818	319,659	2,798	4,181,231
Uinta	.....	4,098	.....	.....	.....	4,098
Utah	544	5,687	81,527	.....	.....	87,758
Wasatch	2,265	.....	159,556	.....	351,366	513,187
Washington	.....	139,376	.....	.....	.....	139,376
	a2,579,070	235,899,350	6,256,268	393,079	1,545,886	246,674,153

a Includes 577,971 pounds from gold ore, 1,021,380 pounds from gold and silver ore, and 979,719 pounds from silver ore.

Digitized by Google

LEAD.

The mine production of lead in Utah in 1917 was 178,521,958 pounds, and was 22,968,117 pounds less than the output of 1916. Bingham or West Mountain district produced 73,523,708 pounds, a decided decrease in 1917 as compared with 85,996,490 pounds in 1916, 80,004,006 pounds in 1915, 76,453,128 pounds in 1914, 71,001,138 pounds in 1913, and 43,822,495 pounds in 1912. The greatest part of the production at Bingham came from the Utah Apex, Utah Metal, Highland Boy, and Dalton & Lark mines. Park City region produced 33,715,565 pounds of lead, against 33,233,794 pounds in 1916. Tintic district produced 35,078,948 pounds, against 39,294,351 pounds in 1916. The combined production of Ophir and Rush Valley districts, in Tooele County, aggregated 12,896,789 pounds, against 18,275,389 pounds in 1916. The output in Beaver County decreased from 5,948,220 pounds in 1916 to 5,321,400 pounds in 1917. Lead contained in total concentrate recovered at milling plants and shipped to smelters amounted to 53,956,225 pounds, against 61,315,355 pounds in 1916. The lead concentrates from lead and lead-zinc ores averaged 19.61 per cent of lead in 1917, against 18.18 per cent in 1916; zinc concentrates contained 655,534 pounds, averaging 2.33 per cent of lead in 1917, against 1.05 per cent in 1916. The total crude ore of shipping grade contained 124,429,731 pounds, against 138,628,633 pounds in 1916. Sulphide lead ore contained 61,284,562 pounds of lead, against 67,837,865 pounds in 1916. The oxidized lead ores carried 59,881,443 pounds, against 67,067,162 pounds in 1916.

Of the zinc ores shipped in 1917, the oxidized ores contained 49,598 pounds of lead and the sulphide ores 10,480 pounds. Of the copper-lead ores, the oxidized or carbonate ores contained 510,242 pounds and the sulphide ores 904,681 pounds of lead.

Ranking first in the output of lead in 1917 was the Utah Apex mine, at Bingham, followed by the Silver King Coalition, Highland Boy, and Chief Consolidated, named in order of production. Each of these was credited with more than 10,000,000 pounds. Those closely following were the Eagle & Blue Bell, Cardiff, and Silver King Consolidated.

Mine production of lead in Utah in 1917, in dry pounds.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-ore.	Lead-zinc ore.	Total.
Beaver	1,220	10,132	4,072,422	11,366	71,299	1,154,961	5,311,400
Box Elder	.....	.....	790,246	40,600	.....	8,437	839,283
Iron	.....	.....	156,243	.....	.....	.....	156,243
Juab	1,392	.....	30,288,586	.....	818	76,790	30,367,586
Millard	.....	.....	8,322	.....	.....	.....	8,322
Morgan	.....	.....	75,400	.....	.....	.....	75,400
Piute	.....	.....	540,476	.....	.....	.....	540,476
Salt Lake	571,151	4,740	56,205,040	.....	126,737	29,956,282	86,863,950
Sanpete	.....	.....	5,814	.....	.....	.....	5,814
Summit	389,871	.....	23,702,318	.....	.....	1,429,585	25,521,774
Tooele	5,854	.....	13,729,845	8,112	1,237,928	49,782	15,031,521
Uinta	.....	.....	1,328	.....	.....	.....	1,328
Utah	.....	.....	5,595,070	.....	.....	.....	5,595,070
Wasatch	6,739	.....	2,074,851	.....	.....	6,112,201	8,193,791
	a976,227	14,872	137,245,961	60,078	1,436,782	38,788,038	178,521,958

a All from silver ore.

Digitized by Google

ZINC.

Tintic, North Tintic, Park City, Ophir, Rush Valley, Bingham districts, and Beaver County were important producers of zinc. The total mine production of recoverable zinc in Utah in 1917 was 21,286,871 pounds, valued at $2,171,261, against 29,572,528 pounds, valued at $3,962,719, in 1916. The mines of the Park City region yielded 5,201,756 pounds of recoverable zinc, compared with 5,136,353 pounds in 1916. Most of the production was from the Daly Judge property, and a considerable quantity was derived from the old tailings on the flats below the town. Salt Lake County, with Bingham the principal source, produced 8,826,658 pounds of recoverable zinc, against 11,376,384 pounds in 1916. Beaver County increased its output from 3,969,405 pounds in 1916 to 4,133,464 pounds in 1917. The Promontory district of Box Elder County yielded 574,357 pounds of zinc in 1917, against 2,668,401 pounds in 1916. Tintic district decreased in output from 3,711,156 to 1,182,941 pounds.

Lead-zinc ore and old tailings aggregating 421,704 tons were smelted or milled, of which 3,413 tons of ore were shipped directly to the smelters and 241,593 tons of ore and 176,198 tons of old tailings were concentrated, yielding 86,260 tons of lead concentrate, 14,094 tons of zinc concentrate, and 12,924 tons of lead-zinc concentrate. The old tailings yielded 2,720 tons of lead concentrate, 1,564 tons of zinc concentrate, and all of the lead-zinc concentrate mentioned above. The lead-zinc ore and tailing concentrates shipped to smelting works contained 17,621,909 pounds of recoverable zinc, of which 754,339 pounds were contained in crude lead-zinc ore, 9,210,334 pounds in zinc concentrate, and 7,657,236 pounds in lead-zinc concentrate. The old tailings re-treated at Frisco, Midvale, and Park City yielded 1,564 tons of zinc concentrate containing 1,085,195 pounds of recoverable zinc, and 12,924 tons of lead-zinc concentrate containing 7,657,236 pounds of recoverable zinc.

Most of the last-named product was shipped to the electrolytic zinc plant at Great Falls, Mont. Crude zinc ores and lead-zinc ores smelted contained 4,419,301 pounds of zinc, of which 3,664,962 pounds were derived from zinc ores and 754,339 pounds from lead-zinc ores. In 1917 the oxidized zinc and lead-zinc ores predominated and produced, respectively, 3,582,308 pounds and 146,507 pounds of recoverable zinc, the sulphide zinc ores 82,654 pounds, and the sulphide lead-zinc ore 607,832 pounds.

Leading in the output of zinc in 1917 were the Daly-Judge property, near Park City, and the two tailing mills, at Midvale and Frisco, followed by the Utah Apex and United States mines, at Bingham.

Mine production of recoverable zinc in Utah in 1917, in dry pounds.

County.	Zinc ore.	Lead-zinc ore.	Total.
Beaver	670,760	3,462,704	4,133,464
Box Elder	596,718	12,319	609,037
Juab	897,243	94,833	992,076
Salt Lake	4,721	8,821,937	8,826,658
Summit	.....	1,247,303	1,247,303
Tooele	1,278,614	28,360	1,306,974
Utah	216,906	.....	216,906
Wasatch	.....	3,954,453	3,954,453
	3,664,962	17,621,909	21,286,871

Digitized by Google

Zinc ore and concentrates produced from Utah mines and mills sold in 1917.

Classification.	County.	Quantity, dry weight.	Average zinc content of ore or concentrates.
		Short tons.	*Per cent.*
Sulphide ore	Beaver and Salt Lake	[a] 3,137	12.95
Mixed carbonate and siliceous ore	Beaver, Box Elder, Juab, Salt Lake, Tooele, and Utah.	6,811	32.20
Concentrates	Beaver, Salt Lake, Summit, Tooele, and Wasatch.	27,018	37.15
		36,966	34.18

[a] All of this ore, chiefly from Bingham and some from Frisco, contained lead and zinc sold to oxide manufacturers in the Eastern States.

METAL-MINING INDUSTRY IN UTAH IN 1917.

Although the Utah mining industry was prosperous throughout 1917, the war conditions were such that many mines were restricted in their output, first by a shortage of railroad cars and afterward by a scarcity of skilled labor. For a part of the year the smelting companies had to refuse the full quantity of ore contracted from the mine operators. Notwithstanding these conditions the quantity of ore mined and the total value of the output in 1917 were greater than in 1916. West Mountain (Bingham), Park City, American Fork, Ophir, the Cottonwood districts, and Beaver County produced continually, except as curtailed by the conditions mentioned. Electric power lines in Utah are continually being extended where most needed. The Wasatch Power Co., owned by the Wasatch Mines Co., supplied all the Cottonwood district with power from its hydroelectric plant in Little Cottonwood Canyon. This company connected its line with a branch line of the Utah Power & Light Co., which was constructed over the divide from the Cardiff mine, in the South Fork of Big Cottonwood Canyon.

The narrow-gage railroad in Little Cottonwood Canyon was completed to the old Columbus mill site, near Alta. Considerable trouble was caused by poor railroad equipment, and not much hauling of ore was done in 1917. This narrow-gage road connects at Wasatch with the Salt Lake & Alta Railroad, which, on September 1, 1917, was taken over by the Denver & Rio Grande Railroad Co., operating the line between Wasatch and Midvale.

In the Deep Creek region the branch line of the Western Pacific, extending 43 miles from Wendover to Gold Hill, was operated continuously and a considerable quantity of ore was carried to the smelters.

METALLURGIC INDUSTRY.

GENERAL STATEMENT.

There was no cyanidation of ores in Utah in 1917. One mill, however, was constructed to use the cyanide process in connection with the flotation process. It is expected to be in operation in 1918. This mill is to treat the ores of the Deer Trail mine, situated near Marys-

Digitized by Google

vale. Some gold was reported from the amalgamation of ores mined in Beaver, Box Elder, and Garfield counties. The Susannah property in the Park Valley district of Box Elder County was the largest producer. About 5 pounds of quicksilver is estimated to have been consumed at the amalgamation mills. The output for 1917 from gold and silver mills was derived from 190 short tons of ore from Beaver, Box Elder and Garfield counties, and consisted of 140.66 fine ounces of gold and 26 fine ounces of silver, recovered by amalgamation. The total value was $2,929.

Of the 27 plants operated in 1917 in Utah, 2 were amalgamation plants and 25 were concentration plants. Of the latter, 11 were equipped with tables followed by the oil flotation process and 3 used flotation alone. One plant was equipped for wet concentration followed by magnetic separation. There were 2 leaching plants, of which one, near Park City, used the electrolytic method of recovering zinc from solution and the other plant, at Silver City, gave the ores a chloridizing roast. After leaching, the solutions from this roasted ore were passed over iron scrap and the resulting precipitates were melted into a base bullion containing copper, silver, and gold.

The Midvale Minerals Co., operated a 250-ton flotation plant on tailings from the United States concentrator at Midvale and shipped lead-zinc concentrate, which was sold to the Anaconda Co., at Great Falls, Mont. The Childers Leasing Co., working on a different part of the same tailing dump, also with a flotation plant, produced lead-zinc concentrate, which went to Kansas zinc plants.

At Frisco the old tailings of the Horn Silver mill were treated in the Caldo 150-ton flotation and table concentration mill, producing a lead-zinc concentrate and a lead concentrate containing silver and gold. The lead-zinc product was shipped to Colorado and the lead concentrate smelted at Midvale. At Park City the large tailing mills, the Big Four and Broadwater, were closed indefinitely in September owing to the operation being unprofitable.

Crude ore treated at concentration mills and the metals contained in the concentrates produced and smelted in 1917 are given in the following table:

Mine production of metals from Utah concentrates in 1917.

By counties.

County.	Ore to concentrating mills.	Concentrates produced.						Total value of concentrates.
		Quantity.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	
	Short tons.	*Short tons.*	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
Beaver	1,152	11,784	700.36	98,189	1,917,490	1,154,961	3,462,704	$1,071,384
Salt Lake	13,561,679	751,158	71,039.34	1,373,503	207,128,242	35,233,683	8,197,105	63,012,491
Summit	56,297	17,357	1,389.89	421,861	165,033	7,320,472	1,247,308	1,177,998
Tooele	38,472	13,898	102.47	160,744	563,578	3,749,709	6,005	611,515
Utah	2,874	958	12.65	15,113	1,994	385,199	.....	46,385
Wasatch	56,186	18,132	438.56	400,394	351,366	6,112,201	3,954,453	1,363,917
	13,718,660	813,287	73,674.27	2,469,804	210,127,703	53,956,225	16,867,570	67,283,690

Digitized by Google

Mine production of metals from Utah concentrates in 1917—Continued.

By kinds of concentrates.

Description.	Quantity.	Gold.	Silver	Copper.	Lead.	Recoverable zinc.	Total value of concentrates.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds*	*Pounds.*	*Pounds.*	
Siliceous	120	5.61	2,391	1,994			$2,630
Copper	655,259	50,280.80	525,923	207,603,875			58,143,614
Lead	130,890	22,522.72	1,675,899	2,134,184	51,356,311		6,845,802
Zinc	14,094	294.14	131,615	168,453	655,534	9,210,334	1,156,357
Lead-zinc	12,924	571.00	133,976	219,167	1,944,380	7,657,236	1,130,287

All of the four smelting plants situated near Salt Lake City were operated at capacity during 1917. The United States smelter operated 7 furnaces on lead ore, the Murray plant of the American Smelting & Refining Co. had 8 furnaces treating lead ore, and its Garfield copper plant was operated at full capacity. At the International plant near Tooele 3 or 4 out of the 5 copper reverberatory furnaces were operated. There were smelted at International[1] in 1917, 320,510 tons of copper ore and 334,273 tons of lead ore, from which were produced 17,385,090 pounds of fine copper, 85,726,315 pounds of fine lead, 4,439,290 ounces of silver, and 31,495.23 ounces of gold. On account of the accumulation of ores and the shortage of railroad cars it became necessary at times for the smelters to declare embargoes in order to catch up with production of ore. The crude ores directly smelted in 1917 and their metallic content are given in the following table:

Mine production of metals from Utah crude ore shipped to smelters in 1917.

By counties.

County.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
Beaver	52,739	1,487.69	199,373	1,783,858	4,145,170	670,760	$1,106,931
Box Elder	13,819	62.32	20,441	1,361,341	839,283	609,037	524,078
Cache	57		52	4,417			1,331
Emery	17		17	6,063			1,669
Garfield	9	17.24	26	2,749			1,139
Grand	86	1.11	4,692	14,439			7,831
Iron	449	3.94	1,441	78	156,243		14,726
Juab	202,218	39,465.91	4,522,805	8,242,017	30,366,194	992,076	9,505,379
Millard	178	18.60	374	16,267	8,322		5,550
Morgan	171		703		75,400		7,063
Piute	2,128	1,039.73	46,740	18,770	540,476		111,612
Salt Lake	637,086	38,670.29	2,393,459	19,624,867	51,596,816	629,553	12,630,725
San Juan	28		113	14,918			4,166
Sanpete	16				5,814		500
Summit	53,253	3,508.98	1,854,722	607,088	18,201,302		3,331,875
Tooele	82,455	1,454.67	630,504	3,600,215	11,201,922	1,300,909	2,628,528
Uinta	5		20	4,098	1,328		1,250
Utah	25,460	1,275.87	562,132	85,619	5,209,871	216,906	783,119
Wasatch	7,504	24.08	260,461	161,821	2,081,590		438,311
Washington	324		44	139,376			38,086
	1,178,002	87,030.43	10,498,129	35,688,301	124,429,731	4,419,301	31,344,169

[1] Anaconda Copper Mining Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

Mine production of metals from Utah crude ore shipped to smelters in 1917—Continued.

By kinds of ore.

Kind of ore.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
Dry or siliceous	97,786	18,846.31	1,834,547	1,760,377	974,835	.....	$2,465,674
Copper	617,156	44,546.28	1,698,521	28,282,873	12,772	.....	10,042,757
Lead	446,786	23,560.56	6,872,954	5,259,363	121,166,005	.....	18,006,437
Zinc	6,535	.....	.....	.....	60,078	3,664,962	378,993
Copper-lead	6,326	75.28	91,447	385,688	1,414,923	.....	303,884
Lead-zinc	3,413	2.00	660	.....	801,118	754,339	146,424

PRODUCTION BY COUNTIES.

GENERAL FEATURES.

The total output of the State by counties in 1917 and the mine production of each metal, with its total value, are shown in a table below; a second table shows production of ore and average value per ton by counties in 1916 and 1917; and a review describes the mining industry in each county and each producing mining district.

Mine production of gold, silver, copper, lead, and zinc in Utah in 1917.

County.	Gold.					Silver.	
	Placers.		Deep mines.		Total value.	Quantity (fine ounces).	Value.
	Quantity (fine ounces).	Value.	Quantity (fine ounces).	Value.			
Beaver	.....	.....	2,192.06	$45,314	$45,314	297,833	$245,415
Box Elder	.....	.....	188.32	3,893	3,893	20,464	16,862
Cache	.....	.....	.....	.....	.....	52	43
Emery	.....	.....	.....	.....	.....	17	14
Garfield	.....	.....	29.66	613	613	39	32
Grand	1.69	$35	1.11	23	58	4,692	3,866
Iron	.....	.....	3.92	81	81	1,441	1,187
Juab	.....	.....	40,809.59	843,609	843,609	4,988,005	4,110,116
Millard	.....	.....	18.62	385	385	374	308
Morgan	.....	.....	.....	.....	.....	703	579
Piute	.....	.....	1,039.72	21,493	21,493	46,740	38,514
Salt Lake	.....	.....	109,747.59	2,268,684	2,268,684	3,769,884	3,106,385
San Juan	.....	.....	.....	.....	.....	113	93
Sanpete	.....	.....	.....	.....	.....	.....	.....
Summit	.....	.....	4,889.89	101,083	101,083	2,276,583	1,875,904
Tooele	.....	.....	1,564.64	32,344	32,344	792,265	653,650
Uinta	3.73	77	.....	.....	77	20	17
Utah	.....	.....	1,352.47	27,958	27,958	618,009	509,240
Wasatch	.....	.....	402.66	9,564	9,564	660,855	544,545
Washington	.....	.....	.....	.....	.....	44	36
	5.42	112	162,300.25	3,355,044	3,355,156	13,479,133	11,106,806

Digitized by Google

Mine production of gold, silver, copper, lead, and zinc in Utah in 1917—Con

County.	Copper.		Lead.		Recoverable zinc.		Total value.
	Quantity (pounds).	Value.	Quantity (pounds).	Value.	Quantity (pounds).	Value.	
Beaver	3,702,085	$1,010,669	5,321,400	$457,640	4,133,464	$421,613	$2,180,651
Box Elder	1,361,341	371,646	839,283	72,178	609,037	62,122	526,701
Cache	4,717	1,288					1,331
Emery	6,063	1,655					1,669
Garfield	2,749	751					1,396
Grand	14,439	3,942					7,866
Iron	78	21	156,243	13,437			14,726
Juab	9,060,565	2,473,534	30,367,586	2,611,612	992,076	101,192	10,140,063
Millard	16,267	4,441	8,322	716			5,850
Morgan			75,400	6,484			7,063
Piute	18,770	5,124	540,476	46,481			111,612
Salt Lake	226,774,390	61,909,408	86,863,950	7,470,300	8,826,658	900,319	75,655,096
San Juan	14,918	4,073					4,166
Sanpete			5,814	500			500
Summit	772,121	210,789	25,521,774	2,194,873	1,247,303	127,225	4,509,874
Tooele	4,181,231	1,141,476	15,031,521	1,292,711	1,306,974	133,311	3,253,492
Uinta	4,098	1,119	1,328	114			1,327
Utah	87,758	23,958	5,595,070	481,176	216,906	22,125	1,064,457
Wasatch	513,187	140,100	8,193,791	704,666	3,954,453	403,354	1,802,229
Washington	139,376	38,050					38,086
	246,674,153	67,342,044	178,521,958	15,352,888	21,286,871	2,171,261	99,328,155

Ore sold or treated, number of deep mines producing, and value of ores in Utah in 1916 and 1917.

County.	Ore sold or treated.		Number of deep mines producing.		Average total value per ton.[a]		Average value per ton in gold and silver.[a]	
	1917	Increase or decrease.	1916	1917	1916	1917	1916	1917
	Short tons.	*Short tons.*						
Beaver	308,038	+ 31,897	49	60	$7.33	$7.08	$1.06	$0.94
Box Elder	13,989	− 1,218	6	12	45.26	37.65	.33	1.48
Cache	57	− 24	3	1	27.53	23.35	.79	.75
Emery	17	+ 17		1		98.18		.82
Garfield	24	− 6	1	1	8.66	58.17	8.66	26.87
Grand	86	+ 71	2	7	55.07	91.06	7.20	45.22
Iron	449	− 162	3	3	17.12	32.80	1.93	2.82
Juab	364,360	+ 11,579	58	51	24.65	27.83	11.55	13.60
Millard	178	+ 130	2	5	38.85	32.86	1.65	3.89
Morgan	171	+ 71	2	1	30.03	41.30	2.07	3.39
Piute	2,128	+ 1,802	7	7	56.91	52.45	42.09	28.20
Salt Lake	14,263,680	+1,432,019	81	80	5.36	5.30	.39	.38
San Juan	28	− 40	1	1	129.14	148.78	2.63	3.32
Sanpete	16	+ 16		1		31.25		
Sevier		− 9	1		85.44		1.11	
Summit	174,920	− 58,925	17	14	17.47	25.78	7.18	11.30
Tooele	132,048	+ 7,353	48	61	23.48	24.64	4.82	5.19
Uinta	5		1	3	270.20	250.00	3.66	3.40
Utah	32,273	+ 14,162	18	16	38.85	32.98	12.60	16.64
Wasatch	65,690	− 1,063	3	3	19.27	27.43	5.10	8.44
Washington	324	+ 160	7	3	51.09	117.55	2.77	.11
	15,358,481	+1,427,838	310	331	6.41	6.47	.88	.94

[a] Value per ton, placer product excluded.

Digitized by Google

BEAVER COUNTY.

Mine production in Beaver County, Utah, 1916–17.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ozs.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	49	276,141	$41,832	381,862	3,203,688	5,948,220	3,969,405	$2,023,531
1917	60	308,038	45,314	297,833	3,702,085	5,321,400	4,133,464	2,180,651
Increase or decrease, 1917		+31,897	+3,482	−84,029	+498,397	−626,820	+164,059	+157,120
Total, 1860–1917			767,739	21,160,906	49,638,383	411,403,954	33,507,519	49,392,527

Since 1860 this country has a record of gold, silver, copper, lead, and zinc amounting in total value to $49,392,527. This includes $767,739 in gold, $19,588,392 in silver, $8,478,593 in copper, $17,980,774 in lead, and $2,577,029 in zinc. The corresponding table of production by years is given to the end of the year 1913 in Mineral Resources for 1913, Part I, page 389.

Sixty mines in 1917 produced 308,038 tons of ore, against 49 mines and 276,141 tons of ore in 1916. The total value of the output of gold, silver, copper, lead, and zinc increased from $2,023,531 in 1916 to $2,180,651 in 1917. The quantity of the metals, with the exception of silver and lead, increased, and the total value of all the metals increased except that of silver and zinc. The value of the gold increased from $41,832 in 1916 to $45,314 in 1917; copper, from $788,107 to $1,010,669; and lead, from $410,427 to $457,640. Silver decreased from $251,265 to $245,415, and zinc from $531,900 to $421,613. The average value per ton of the ore, including some old slag, decreased from $7.33 in 1916 to $7.08 in 1917, and the gold and silver value per ton in this ore from $1.06 to 94 cents.

The decrease in the value per ton was caused by the treatment of considerable low-grade tailing. Of the ore mined, 1,152 tons were concentrated and produced lead and zinc concentrates. One plant treated a large quantity of tailing, yielding lead-zinc concentrates containing gold, silver, and copper. Copper concentrate continued to be produced from the re-treatment of the old Cactus mine tailings at Newhouse. Altogether there were 11,784 tons of concentrates having a total value of $1,071,384, or $90.82 per ton. Crude ore shipped, mostly oxidized, aggregated 52,739 tons, which yielded at the smelters gold, silver, copper, lead, and zinc having a total value of $1,106,931, or an average value per ton of $20.99.

Beaver Lake district.—Six producers shipped 341 tons of ore, which was principally oxidized copper ore. The total content of these ores was $186 in gold, 438 ounces of silver, 33,795 pounds of copper, and 2,277 pounds of lead, valued in all at $9,969, or an average value per ton of $29.23. The O. K. mine was the largest producer of copper ore, followed by smaller production from the Copper Mountain, Larkspur, Success, and Utah-United properties.

Bradshaw district.—Two small lots of lead ore containing silver were shipped from the Summit and Lower Cave properties.

Digitized by Google

Granite district.—The King of the Hills and the Amazon properties were operated and yielded a small tonnage of oxidized copper ore containing gold and silver.

Lincoln district.—Most of the ore produced in 1917 containing copper came from the Rattler property, and some test lots of lead ore came from the Croff mine. Part of this ore was milled and produced, besides the lead, a little copper and zinc accompanied by gold and silver. The Creole and the Stampede properties were also producers.

Newton district.—Very little work beyond that required in annual assessment was performed in 1917. A small quantity of gold and silver bullion, probably from previous operations, was reported from one property.

North Granite district.—One carload of low-grade oxidized copper ore, which barely paid its way to the smelter, was shipped from the Mammoth Copper property.

Preuss district.—The Indian Queen, Klondyke, and Galena properties were all producers of lead ore carrying small quantities of copper accompanied by a little gold and silver.

Rocky district.—Important developments on the Montreal property allowed the operators to ship a large quantity of oxidized copper-iron ore. This ore carried an average of 30 per cent of iron and 16 per cent of silica, making it valuable at the smelter as fluxing ore. The property is opened by an adit 1,000 feet long, in which there are drifts aggregating 1,500 feet. The Old Hickory mine, another producer of oxidized copper ore with higher silica and a lower average in iron, shipped a large quantity of ore. The Copper Ranch property also produced copper ore. In 1917 the district produced altogether 29,869 tons of ore, containing $2,005 in gold, 11,493 ounces of silver, 1,322,271 pounds of copper, valued in all at $372,455, or an average value per ton of $12.47.

Frisco district.—There were seven producers reporting the output and treatment of 266,134 tons of ore and old tailings, containing $27,439 in gold, 216,021 ounces of silver, 2,132,726 pounds of copper, 3,541,814 pounds of lead, and 3,538,898 pounds of recoverable zinc, valued in all at $1,453,237, or an average value per ton of $5.46. Of this production there were 11,107 tons of crude ore shipped directly to the smelter. From the old tailings and some crude ore of milling grade treated 11,724 tons of concentrates were shipped. In 1916 there were 12,425 tons of concentrates and 10,013 tons of crude ore shipped directly to the smelters. A new reduction plant known as the Quad Metals mill, was built in 1917, at the Carbonate Rattler mine, 2 miles north of Frisco. It is equipped to treat the ores by flotation. The Horn Silver mine continued to be the largest producer of ore and yielded mixed lead sulphide and carbonate, also copper, and some zinc sulphide ores. Some of the ore was of milling grade and produced lead and zinc concentrates at the Midvale concentrator.

At Frisco the old tailing dump under lease to the Caldo Leasing Co., supplied material for the flotation mill, which produced a high-grade lead and zinc concentrate containing good values in silver. According to the annual report of the Horn Silver Co.,[1] the ore

[1] Horn Silver Mining Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

mined in 1917 came entirely from the upper levels, more especially from the 300 level, where small pockets of ore were found. Development work was continued on other levels above the 900. A portion of the shipments consisted of old "fillings." Developments on the 1,200-foot level have not progressed far enough to determine the question as to the occurrence of ore with depth.

At Newhouse the Utah Leasing Co. continued with its 700-ton flotation mill to treat the old Cactus mine tailing assaying about 0.65 per cent of copper, which yielded a copper concentrate containing gold and silver. There were also shipments from four other properties, including a small output from the Imperial property, operated by a lessee.

Star districts (North and South).—These districts in 1917 yielded from their mines 10,689 tons of ore, containing $14,688 in gold, 65,951 ounces of silver, 175,170 pounds of copper, 1,703,957 pounds of lead, and 588,106 pounds of recoverable zinc, valued in all at $323,380, or an average value per ton of $30.25. The largest producers were the Moscow and the Monitor properties. The former property ceased operations in September. It is said the mine was closed indefinitely on account of the low grade of the ore and the higher mining costs. There were three grades of ore shipped from the Moscow in 1917, consisting of copper, lead, and zinc oxidized ores. The property is opened by a vertical shaft 1,400 feet deep and two others 500 and 200 feet deep. Altogether there are about 10,000 feet of drifting. The other properties yielding more than 200 tons of ore were the Rebel & Wild Bill, Red Warrior, Paloma, and Cedar Talisman. Some lead ore was also shipped from the Blue John, Boston, Commonwealth, Magnolia, Hoosier Boy, and Osceola properties.

Washington district.—There were small quantities of oxidized copper ore shipped from the Mono and Copper Queen properties. The Mono produced also a small quantity of oxidized lead ore. All these ores carried some gold and silver.

BOX ELDER COUNTY.

Ashbrook district.—A small quantity of silver ore carrying a little gold was shipped from the Vipont mine in 1917.

Box Elder district.—A small production of lead ore carrying a little copper and silver was reported from one property in the district.

Lucin district.—Six producers reported the output of 12,023 tons of ore, containing $1,196 in gold, 19,016 ounces of silver, 1,359,169 pounds of copper, 521,209 pounds of lead, and 34,680 pounds of recoverable zinc, valued in all at $436,279, or an average value per ton of $36.29. All of the ore produced was of smelting grade, with the exception of that shipped for its zinc content, which is reported to have been stored at the smelting works at Murray for future treatment. The largest production of copper ore was that made by lessees on the property of the Salt Lake Copper Co., which shipped the output.

Considerable lead ore was shipped from the old Tecoma mine, which had been idle for 40 years. Occasionally shipments were made by lessees. The company operating the property also shipped some oxidized zinc ore, containing about 18 per cent of zinc, 44 per cent of iron, and a low percentage of silica. The Cunapah (which

Digitized by Google

was erroneously listed on the Nevada side of the line in the Tecoma district in 1916) produced in 1917 considerable oxidized lead ore carrying a little silver and gold. There were also shipments of oxidized lead ore from the Lucin Copper and Mineral Mountain properties.

Newfoundland district.—The Mineral Monarch was a producer of a small quantity of oxidized copper ore in 1917.

Park Valley district.—The Susannah property was operated by a lessee, and some gold and silver bullion was produced by amalgamation.

Promontory district.—The Lake View and Big Pine properties were the only producers, both of them yielding some lead ore. The largest part of the output of the Lakeview, the principal producer, consisted of oxidized zinc ore shipped to eastern smelting plants.

CACHE COUNTY.

Paradise district.—The Wolf Mountain copper property, which is opened by a 45-foot vertical shaft and also an incline shaft 40 feet deep, yielded a small quantity of copper ore containing a little silver.

EMERY COUNTY.

Lost Springs district.—A small shipment of copper ore containing a little silver was reported from this locality.

GARFIELD COUNTY.

Imperial district.—The Fortuna Independence Co., operating the Bromide property, shipped a small quantity of gold bullion and crude smelting ore, which contained gold, silver, and copper.

GRAND COUNTY.

Klondyke district.—The Rambler property is reported to have produced a small quantity of ore carrying copper and silver, shipped directly to the smelter.

La Sal district.—There were six small shipments of copper ore in 1917 aggregating 73 tons, valued at $7,374, principally for the silver content.

IRON COUNTY.

Calumet district.—From the Calumet property there were shipped 443 tons of oxidized lead ore carrying an average of about 20 per cent of lead and 1 ounce of silver per ton. Sahara station on the Salt Lake Route, 28 miles from the mine, was the loading point for the ore.

Stateline district.—Very little work was done in the district in 1917. Several small shipments of silver product were reported, which probably came from previous operations.

JUAB COUNTY.

Fifty-one producers in 1917 mined an output of 364,360 tons of ore, containing gold, silver, copper lead, and zinc, valued at $10,140,063—an increase of 11,579 tons in quantity and of $1,443,402 in

Digitized by Google

value, as compared with the output of 58 producers in 1916 of 352,781 tons, valued at $8,686,661. The output was mainly from the Tintic district.

Detroit district.—The Ibex Gold property produced a small quantity of oxidized copper ore carrying considerable gold and a little silver.

Fish Springs district.—At the Utah mine a concentration mill is being erected to treat the old ore dumps. In 1917 there were several shipments of lead ore carrying silver.

Mount Nebo district.—From the Emma property a few tons of lead sulphide ore carrying silver were shipped to the smelter. There were also shipments from the Highland property, and zinc-lead ore and lead ore from the Mount Nebo mine and a property operated by the Gunnison Development Co.

Tintic district.—The total value of the metals produced in this district from 1869 to the end of 1917 was $180,401,804, distributed as follows: Gold, $32,556,936; silver, $83,343,232; copper, $27,552,435; lead, $35,358,411; zinc, $1,590,790.

The larger part of the Tintic district is in Juab County and the remainder in Utah County.

Mine production in Tintic district, Utah, 1916–1917.

County.	Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
			Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
Juab	1916	44	348,737	$834,841	4,848,047	7,085,704	35,425,153	2,414,089	$8,535,763
	1917	42	363,746	842,593	4,975,854	9,045,595	30,132,739	966,035	10,102,095
Utah	1916	10	17,212	20,613	265,519	20,941	3,869,198	1,297,067	641,258
	1917	7	28,640	25,954	582,909	72,128	4,946,210	216,906	973,461
	1916	54	365,949	855,454	5,113,566	7,106,645	39,294,351	3,711,156	9,177,021
	1917	49	392,386	868,547	5,558,763	9,117,723	35,078,949	1,182,941	11,075,556
Total, 1869–1917				32,556,936	125,271,682	171,493,635	752,049,426	16,803,653	180,401,804

The value of the metals produced in 1917 was distributed as follows: Gold, $868,547, against $855,454 in 1916; silver, $4,580,421, against $3,364,727 in 1916; copper, $2,489,138, against $1,748,234 in 1916; lead, $3,016,789, against $2,711,311 in 1916; zinc, $120,661, against $497,295 in 1916.

Altogether there were 49 producers in the district whose output was valued at $11,075,556, or an average per ton of ore sold or treated of $28.23. In 1916 the output was valued at $9,177,021, or an average value per ton of $25.08. As in the two preceding years there was a large quantity of old mine-dump material of sufficient value to ship at the prevailing high prices for the metals. The following table gives the quantity and kinds of ore produced in the district in 1917, the number of producers, and the metallic content of each kind of ore:

Digitized by Google

Mine production in Tintic district, Utah, in 1917, by kinds of ore.

Kind of ore.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.
		Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Dry or siliceous	26	141,520	19,601.50	1,530,119	2,530,681	1,392	.....
Copper	21	96,844	12,292.05	846,010	6,207,754	.....	.....
Lead	30	151,878	10,122.05	3,132,519	379,117	35,003,567	.....
Zinc	10	1,883	.....	.....	.....	.....	1,096,807
Copper-lead	1	3	.38	115	171	818	.....
Lead-zinc	2	253	.....	.....	.....	73,172	86,134
		392,386	42,015.98	5,558,763	9,117,723	35,078,949	1,182,941

Of interest to Tintic mine operators is the driving of a drainage adit, 6 miles long, by the Tintic Drain Tunnel Co., a Knight enterprise. The adit starts from the Goshen slope and runs to the porphyry section at the southern end of the district, in the direction of the Dragon Consolidated property. When completed the adit will have an approximate depth of 2,200 feet below the collar of the Iron Blossom and Dragon shafts.

Another development work recently started was the sinking of the North-Beck shaft, which, at the end of 1917, had attained a depth of nearly 1,000 feet. This is a shaft sunk for the purpose of prospecting for ore in the northern extension of the western ore zone of the camp on which the Eureka Hill, Centennial Eureka, Bullion Beck, and Gemini properties are located.

At the Standard mine new ore deposits were added to the reserve and about 300 cars were shipped directly to the smelters. The new No. 2 shaft disclosed ore on the 1,260-foot level, which assays 75 ounces of silver and $10 in gold per ton, and 10 per cent of lead and about 2 per cent of copper. Picked samples are said to have assayed as high as 410 ounces of silver and $36 in gold per ton. The Standard has paid a total of $81,941 in dividends, all of which was distributed in 1917.

The Chief Consolidated enlarged its main shaft to a 2-compartment shaft extending to the water level depth at 1,800 feet, without interfering with the production. Some unusually rich ore was reported at about water level and high-grade ore was stoped below water level, but little mining was done pending the installation of permanent pumps. Several cars of ore valued at $10,000 were shipped from this part of the mine. According to the company's report,[1] the total shipments of dry ore in 1917 aggregated 59,950 tons, which yielded, after payment of smelting, transportation, and sampling charges, a net value of $1.554,714. This value is greater and the tonnage is less than that of the output in 1916.

The metals contained in the output of silver, lead, and zinc ores for 1917 were 9,175 ounces of gold, 1,534,907 ounces of silver, 10,780,540 pounds of lead, and 600,236 pounds of zinc. The zinc-lead ores contained 90,511 pounds of zinc and 66,170 pounds of lead. The average content was 0.153 ounce of gold and 25.6 ounces of silver per ton, and 11.92 per cent of lead (in lead ore) and 36.16 per cent

[1] Chief Consolidated Mining Co. Ninth Ann. Rept., for year ending Dec. 31, 1917.

Digitized by Google

of zinc (in zinc ore). The zinc-lead ore contained 20.29 per cent of zinc and 14.84 per cent of lead. The ore was classified as 45,231 tons of silver-lead ore, 13,666 tons of dry ore (with no lead or copper), 830 tons of zinc ore, and 223 tons of zinc-lead ore. The total average value per ton of the ore shipped in 1917 was $40.12, as against $31.52 in 1916 and $20.55 in 1915, and the net value, respectively, was $25.93, $18.64, and $9.96. The total dividends paid since February 3, 1913, amount to $836,969, including $309,451 paid in 1917. The following paragraph is from the company's annual report:

The new ore channel on the 1,800 level, referred to in the last quarterly report, has given a continual product of ordinary lead carbonate ore. This ore was followed down to and below the water level and then proved to be of higher grade.

The ore production during this year was principally derived from the 700, 800, 1,600 and 1,800 levels. During the latter part of the year, as mentioned in the preceding quarterly report, the ore shipments were curtailed on account of the insufficient capacities of the smelters. This condition exists today, together with higher treatment charges, taxes, and operating costs. This makes it imperative to ship the highest-grade ores, as only a small tonnage will be accepted by the smelters. On account of these adverse conditions practically all development work has been suspended until a more auspicious time. As this work has been carried well ahead, its neglect will not hamper the mining operations for some time.

The Iron Blossom mine is opened by one of its shafts to a depth of 2,200 feet. In 1917 this property[1] produced 10,458 tons of siliceous ore, which contained 1,406.37 ounces of gold and 239,246.91 ounces of silver. In 7,010 tons of copper ore there were 166.72 ounces of gold, 42,310.94 ounces of silver, 684,275 pounds of copper, and 5,491 pounds of lead; and in 4,466 tons of lead ore there were 422.58 ounces of gold, 104,535.92 ounces of silver, and 619,056 pounds of lead. This output included one lot of zinc ore containing 12,210 pounds of zinc. Lessees added to the above output by shipping 3,487 tons of lead ore and 1,318 tons of copper ore and siliceous ore. There were 8,355 tons of milling ore shipped to the Silver City mill, which was treated by the chloridizing roasting process. This ore contained 669.55 ounces of gold, 82,645.80 ounces of silver, and 148,870 pounds of copper. Siliceous ore also treated—14,057 tons—contained 1,644.18 ounces of gold and 271,311.82 ounces of silver. From all ore sales the total amount received was $526,909. Dividends in 1917 amounted to $250,000. The company report says:

With the object in view of getting through the siliceous beds of lime on the 1,900 level and developing a more soluble lime more susceptible to minerals, we have commenced sinking No. 1 shaft to a depth of 2,200 feet, 300 feet deeper than the 1,900 foot level. * * *

The 1,100 drift on the east vein at No. 1 shaft has been continued south to a point near the Dragon north end line, and has developed a commercial body of low-grade copper and silver ore, suitable for the mill treatment. This ore has every appearance of extending down to deeper levels. * * *

Due to the scarcity of labor and the advisability of mining smaller streaks of ore from the old stopes, the system of leasing has been adopted for the greater part of the mine, which has given very satisfactory results. The system of leasing is on the following royalty basis: Up to $10 per ton, 20 per cent royalty was paid; $10 to $15 per ton, 25 per cent; $15 to $20 per ton, 30 per cent; $20 to $25 per ton, 35 per cent; $25 to $30 per ton, 40 per cent; and $30 and up, 50 per cent.

[1] Iron Blossom Consolidated Mining Co. Ann. Rept. for year ending Nov. 30, 1917.

Digitized by Google

The ores from the "Van" stope, which comprise most of the ore shipped to the Tintic Milling Co., and the copper ores from what is known as the 600 winze copper stopes, are mined under company operations.

At the Centennial-Eureka mine[1] 50,132 tons of ore were produced. Developments were carried on mostly in the vicinity of old stopes, and extraction obtained mainly from these stopes. The Bullion Beck & Champion property[2] yielded 5,700 dry tons of ore, most of which was produced by lessees.

In 1917 the Eagle & Blue Bell mine[3] produced 33,252 dry tons of lead carbonate and sulphide ore, and 1,205 tons of silicious gold and silver ore carrying a little copper. The lead ore contained 2,608.99 ounces of gold, 507,350 ounces of silver, 9,069,091 pounds of lead, and 1,007 pounds of copper, and the dry siliceous ore contained 210.05 ounces of gold, 12,530 ounces of silver, and 3,082 pounds of copper. The total value of the ore was $1,068,836.92, an increase of $537,986 over the value in 1916. Notwithstanding the embargoes by railroads and smelters on the movement of ore, the output in 1917 exceeded that of 1916 by 8,862 tons. Dividends paid, beginning in the year 1913 and including the dividend in 1917 of $357,258.40, amounted to $893,146. The workings in the North Extension claims continue to produce lead-silver ore from the 1,000-foot level, and the ore is being followed in a more or less irregular way along a general northwesterly course through these claims. The company's report continues as follows:

From the 1,700 level up to a point within 60 feet vertically below the 1,350 level, making a total vertical distance of 290 feet, stoping and development work has been under way all the year with most satisfactory results. The present working faces in this immediate vicinity indicate a continuation of ore from which we can expect a fair tonnage for some time. An extension of the ore body has also been followed below the 1,700 level, and at a point 60 feet above the 1,875 level a fair sized stope has been made. We expect this deposit to persist to greater depth and at different horizons show as marked continuity as above.

The Tintic Milling Co.[4] reports receiving $542,180 in 1917 for precipitates and base bullion containing principally silver and copper recovered from custom ores. Treatment of the ores consists of a chloridizing roast and the leaching of the residue. The ores treated were produced chiefly from the Dragon and Iron Blossom mines and a number of others known as the Knight properties. Several shippers in the district took advantage of lower milling rates offsetting the railroad haul and charges at smelters for low-grade ores.

The Victoria mine[5] produced almost twice as much ore in 1917 as in 1916. There were produced 2,761 tons of lead-silver ore, containing 599.88 ounces of gold, 102,664 ounces of silver, 515,993 pounds of lead, and 16,825 pounds of copper; and 10,782 tons of siliceous ore contained 2,275.48 ounces of gold, 236,087 ounces of silver, and 102,728 pounds of copper. The Victoria is operated through the Eagle & Blue Bell shaft No. 1, and most of the high-grade lead-silver and siliceous ore was mined from the 1,050-foot

[1] United States Smelting, Refining & Mining Co. Twelfth Ann. Rept., for year ending Dec. 31, 1917.
[2] Idem.
[3] Eagle & Blue Bell Mining Co. Ann. Rept. for year ending Dec. 31, 1917.
[4] Tintic Milling Co. Ann. Rept. for year ending Dec. 31, 1917.
[5] Bingham Mines Co. Ninth Ann. Rept., for year ending Dec. 31, 1917.

Digitized by Google

level. Some of this ore also carries high gold values. The deposit is being followed to the north and south.

West Tintic district.—Copper ore from the Desert Mountain property and oxidized lead ore carrying silver from the Scotia and Imperial lead properties, were the only shipments from the district in 1917.

MILLARD COUNTY.

Antelope district.—A small shipment of oxidized lead ore was made from the Antelope Star property in 1917.

Detroit district.—Oxidized copper ore, containing gold and silver, was shipped from the Copper Head, Columbus, and one other property in this district in 1917.

Leamington district.—From the Silver Maple property lessees shipped some lead sulphide ore carrying a little silver.

MORGAN COUNTY.

Argenta district.—The Carbonate group was operated in 1917 and yielded a small quantity of lead ore of shipping grade containing silver.

PIUTE COUNTY.

Gold Mountain district.—A few tons of gold ore from the Annie Laurie property was shipped to the smelter in 1917.

Mount Baldy district.—The Deer Trail property was equipped with a modern milling plant, which was nearly ready for operation at the close of 1917. There were shipments of lead ore, containing gold, silver, and a little copper, made directly to the smelters during the year. The Pluto property produced copper ore, containing gold and silver.

Ohio district.—The Great Western, Wedge, Bullion, and Shamrock properties were producers in 1917 of small quantities of shipping ore, the first-named property being the largest producer of lead sulphide ore carrying gold, silver, and a little copper.

SALT LAKE COUNTY.

In Salt Lake County 80 operators produced 14,263,680 tons of ore, which was 1,432,019 tons more than was produced in 1916 by 81 operators. The total average value per ton of the ore for the gold, silver, copper, lead, and zinc content decreased from $5.36 to $5.30, and the gold and silver average value per ton of this ore decreased from 39 cents to 38 cents. A review of the principal districts follows:

Big Cottonwood and Little Cottonwood districts.—From 1867 to the end of 1917 these districts have a record of producing 429,495 tons of ore, valued at $25,722,553, which includes $500,529 in gold, $13,215,039 in silver, $1,741,962 in copper, $10,225,640 in lead, and $39,283 in zinc. The table of production by years is given to the end of 1914 in a recent report[1] of the Survey.

[1] U. S. Geol. Survey Mineral Resources, 1914, pt. 1, p. 740, 1915.

Digitized by Google

Mine production in Big Cottonwood and Little Cottonwood mining districts, Utah, 1916–17.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	31	41,960	$21,414	755,980	819,192	15,061,273	60,746	$1,767,738
1917	32	48,203	18,611	917,512	1,163,084	11,927,552	21,721	2,120,149
Increase or decrease, 1917	.....	+6,243	−2,803	+161,532	+343,892	−3,133,721	−39,025	+352,411
Total, 1867–1917	.....	429,495	500,529	13,140,345	9,855,917	180,616,785	320,934	25,722,553

Thirty-two producers in 1917 shipped directly to the smelters 48,203 tons of ore, of which 29,760 tons came from the mines in the vicinity of Alta and the remainder was principally from the Cardiff and Maxfield properties in the Big Cottonwood Canyon. The ore produced in these districts contained $18,611 in gold, 917,512 ounces of silver, 1,163,084 pounds of copper, 11,927,552 pounds of lead, and 21,721 pounds of recoverable zinc, valued in all at $2,120,149, or an average value per ton of $43.98. Shipments from Big Cottonwood were reported from the American Consolidated, Big Cottonwood Coalition, Cardiff, Iowa Copper, Maxfield, Prince of Wales, and Woodlawn. From Little Cottonwood the producers were the Albion, Alta Consolidated, Alta Michigan, Alta Utah, Cabin, Wasatch Mines, Columbus Rexall, Emma, Michigan-Utah, Peruvian, Sells, South Hecla, South Hecla Extension, and Alta Wasatch.

The Wasatch Mines Co. in June continued to work on its new drainage adit, started in the Little Cottonwood Canyon 5,000 feet from the main workings, and drove 1,700 feet in an easterly direction in 1917. This adit is expected to unwater the old Columbus Consolidated stopes.

Work on the Alta tunnel project, which started from near the head of Silver Fork Canyon on the Big Cottonwood side of the divide, was completed for a length of 3,000 feet.

Nearly 9,000 tons of ore of an average value of $30.58, mainly for silver and lead, were reported to have been shipped from the old Emma mine.

On July 9 the Columbus Rexall miners, working under the summit of the Little and Big Cottonwood divide at a depth of almost 1,700 feet and 5,000 feet from the portal of its transportation adit, opened a deposit of copper ore, replacing lime shale. This deposit where encountered was only a few inches thick, but subsequently widened to an average of 21 feet, dipping about 30° E. At the end of 1917 the ore body had been followed in an upraise 60 feet westerly on its dip, and at this writing (June, 1918) the face of the upraise is about 200 feet from the adit level. In May, 1918, the adit was continued in its northerly course, and at a point 60 feet from where the first ore body was encountered a similar deposit was opened on June 2. The ore shipped to the smelters in 1917 aggregated 2,778 tons, containing 8 to 9 per cent of copper, and 8 to 15 ounces of silver and 50 to 65 cents per ton in gold. The insoluble matter in this ore

Digitized by Google

averaged about 5 per cent, with 31 per cent of sulphur, 4 per cent of speiss, and less than 1 per cent of zinc.

The Michigan-Utah mines,[1] operated largely by lessees in 1917, yielded 12,014 tons of ore, containing 227.49 ounces of gold, 148,317.65 ounces of silver, 384,906 pounds of copper, and 1,865,379 pounds of lead. The sum received from sales of ore amounted to $226,408. Most of the ore was mined from the City Rocks vein through Copper Prince tunnel, which opens a large body of medium-grade copper ore situated near the portal. Average assays of the ore give 0.025 ounce of gold, 1.84 per cent of copper, 52.2 per cent of iron, 7.8 per cent of insoluble, 2.65 per cent of sulphur, and 0.6 per cent of manganese. On Patsy Marley Hill the openings made by lessees have disclosed a good body of copper ore in the Florida claim. At the present time this company operates an aerial tramway 4½ miles to Tanners Flat, where the ore is loaded on wagons and hauled 3½ miles to Wasatch, thence by the Denver & Rio Grande Railroad to Midvale.

From the South Hecla property[2] 3,798 tons of ore mined on company account and 727 tons by lessees contained a total of 164.23 ounces of gold, 76,784 ounces of silver, 711,896 pounds of lead, and 29,058 pounds of copper, valued in all at $117,664.34. The ore developments have been confined principally to the Wedge vein, which has been opened near the western end of the property by the so-called Wedge shaft, by levels driven along the vein at an average depth of 120 feet on its dip, and by some limited but important workings on the east end of the vein system over a mile away from the main development.

Smelter district.—Old tailing, sorted slag dump material, and a little ore, aggregating 65,083 tons, yielded principally concentrate. The total output contained $8,921 in gold, 66,252 ounces of silver, 199,631 pounds of copper, 1,412,690 pounds of lead, and 4,201,463 pounds of recoverable zinc, valued in all at $668,052. There were 8,122 tons of concentrate containing zinc, lead, gold, and silver, and 64,915 tons of old tailing and slag shipped directly to the smelter; also 168 tons of ore picked up from the railroad yards was sold to the smelters by a number of track pickers. The tailing dumps were worked by the Midvale Minerals Co. and the Childers Leasing Co., both treating the material from the milling operations of early days as well as from recent work.

Bingham or West Mountain district.—The output of the Bingham district from 1865 to 1917, inclusive, is valued at $31,318,190 in gold, $35,665,120 in silver, $296,608,198 in copper, $52,429,453 in lead, and $3,678,727 in zinc, a total gross value of $419,699,688, out of which dividends (partly estimated) amounting to $88,912,019 have been paid. The table giving the production by years may be consulted in Mineral Resources for 1913, Part I, page 399.

[1] Michigan-Utah Consolidated Mines Co. First Ann. Rept., for year ending Dec. 31, 1917.
[2] South Hecla Mining Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

Mine production in Bingham or West Mountain district, Utah, 1916–17.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	45	12,777,683	$2,490,158	3,095,335	223,619,609	85,996,490	10,765,192	$66,913,606
1917	33	14,150,394	2,241,152	2,786,120	225,411,675	73,523,708	4,603,474	72,866,895
Increase or decrease, 1917		+1,372,711	− 249,006	− 309,215	+ 1,792,066	−12,472,782	−6,161,718	+5,953,289
Total, 1865–1917			31,318,190	48,415,824	1,658,686,866	1,058,092,538	40,052,718	419,099,688

The district in 1917 yielded 14,150,394 tons of ore, against 12,777,683 tons in 1916, 9,693,184 tons in 1915, 7,800,661 tons in 1914, and 9,190,374 tons in 1913. The total metallic value of the ores in 1917 was $72,866,895, or an average value per ton of $5.15, against a total of $66,913,606, with an average value per ton of $5.24 in 1916. The value of the output of gold decreased from $2,490,158 in 1916 to $2,241,152 in 1917; silver increased from $2,036,730 to $2,295,763. The value of the copper increased from $55,010,424 to $61,537,387; lead, from $5,933,758 to $6,323,039; and zinc decreased from $1,442,536 to $469,554. Shipments of ore to the smelters amounted to 588,715 tons, against 741,840 tons in 1916, 539,939 tons in 1915, 532,130 tons in 1914, 655,634 tons in 1913, and 502,682 tons in 1912. The output of concentrating ores was 13,561,679 tons, against 12,034,343 tons in 1916, 9,152,918 tons in 1915, 7,268,472 tons in 1914, and 8,527,755 tons in 1913. The quantity of concentrates produced was 743,036 tons in 1917, against 676,557 tons in 1916, 523,753 tons in 1915, 435,903 tons in 1914, and 443,640 tons in 1913.

The crude smelting ore in 1917 consisted principally of low-grade copper and lead sulphides and contained 37,760.36 ounces of gold, 1,472,528 ounces of silver, 18,455,113 pounds of copper, 39,618,966 pounds of lead, and 607,832 pounds of recoverable zinc, valued in all at $10,501,418, or an average value per ton of $17.84. Milling ores produced 743,036 tons of copper, lead, and zinc concentrates that contained 70,655.35 ounces of gold, 1,313,592 ounces of silver, 206,955,348 pounds of copper, 33,904,712 pounds of lead, and 3,995,642 pounds of recoverable zinc, valued in all at $62,365,146, or an average value per ton of $83.93.

Mine production in Bingham district, Utah, in 1917.

Kind of ore.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.
		Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Dry or siliceous	2	425	21.93	1,850	6,539	454	.....
Copper	23	13,739,880	81,136.28	1,177,906	222,301,095	2,640	.....
Lead	25	234,711	8,709.04	947,226	2,185,602	44,896,903	.....
Lead-zinc	7	175,378	18,548.46	659,138	918,439	28,623,711	4,603,474
		14,150,394	108,415.71	2,786,120	225,411,675	73,523,708	4,603,474

Digitized by Google

In 1917 the mines of the Utah Copper Co.[1] produced 12,542,000 tons of concentrating ore mined by the steam-shovel method and in addition 38,708 tons of ore containing copper, lead, and zinc mined by underground methods from the Sulphide mine and shipped directly to the smelter. These figures compare with a total of 10,994,000 tons of ore concentrated and 18,026 tons directly smelted in 1916. At the Magna concentrator 7,077,200 tons of ore were milled and at the Arthur plant 5,464,800 tons, or an average of 19,390 tons and 14,972 tons, respectively, each day during 1917. The gross production of copper from concentrates for 1917 was 204,855,118 pounds, and the shipments of crude ore contained an additional 1,319,324 pounds. After making smelter deductions, the net production was 195,837,111 pounds. In addition, there were produced 51,112 ounces of gold and 498,820 ounces of silver. The total dividends paid by this company amount to $75,770,882.50, including $23,555,105 paid in 1917. The following paragraphs are taken from the company's annual report:

No effort was made to add to the ore-bearing area of 226.3 acres, but the churn drilling done during the year increased the calculated average thickness of developed and partially developed ore from 524 to 538 feet. Revised estimates show that previous to January 1, 1918, there had been developed in the property 438,972,700 tons of ore, averaging 1.40 per cent copper, of which quantity 270,000,000 tons are classed as fully developed and 168,972,700 tons as partly developed. There was mined from the entire property prior to January 1, 1918, a total of 67,220,700 tons of ore, averaging 1.428 per cent copper, and the total reserves remaining therefore amount to 371,752,000 tons, averaging 1.39 per cent copper. The year's addition to reserves was 1,906,442 tons in excess of the tonnage mined during that period. * * *

The average grade of the ore milled at both plants (Magna and Arthur) was 1.337 per cent copper, as compared with 1.435 per cent copper for 1916. This reduction in grade was due to the fact that it was necessary to mine a considerable quantity of low-grade ore on the upper and lower-grade steam shovel levels. The average recovery at both plants was 61.10 per cent, corresponding to 16.3335 pounds of copper per ton, as compared to 62.34 per cent, or 17.8963 pounds per ton, for the previous year. The percentage of recovery was low because of the unsettled operating conditions in the mills, due to the various improvements under way, the unusually large tonnage treated, and comparatively low copper content in the headings. The average normal and metallurgically economical capacity of the two plants during the year was about 24,000 tons per day, whereas in order to maintain maximum production of copper a daily average of 34,362 tons was milled.

The milling cost at Magna was 62.28 cents per ton and at Arthur 78.40 cents per ton, as compared with 35.35 cents and 40.94 cents, respectively, for the year 1916. The average cost at both plants was 69.30 cents per ton, as compared with 37.82 cents for the previous year, or an increase of 31.48 cents per ton. This very great increase was due partly to the higher costs of labor and supplies and partly to the lower grade of the ore, but in great part to the necessarily large charge made against operations for increased State and Federal taxes. * * *

The production of copper for the year, from all sources, by quarters, and for the years 1915 and 1916, was as follows:

Quarter.	1915	1916	1917
	Pounds.	*Pounds.*	*Pounds.*
First	26,415,995	36,673,007	43,060,480
Second	40,799,825	48,726,304	56,845,059
Third	44,766,841	61,181,870	54,999,468
Fourth	44,224,715	50,836,299	51,269,465
	156,207,376	197,417,480	206,174,442

[1] Utah Copper Co. Thirteenth Ann. Rept., for year ending Dec. 31, 1917.

Digitized by Google

The average cost per net pound of copper produced from concentrates, after allowing for smelter deductions and after crediting precious metal values and miscellaneous income in Utah, was 10.952 cents, as compared with 6.918 cents for 1916. The net value of the gold and silver recovered amounted to 0.70 cent per pound. The miscellaneous income in Utah, including that from the Bingham & Garfield Railway, amounted to 0.988 cent per pound. This cost includes depreciation, all taxes as estimated and set up in tax reserves during the year, all general, fixed, and maintenance charges of every kind, and all expenses of smelting, transportation, refining, and selling. The average net cost, on the same basis, for all copper produced was 10.995 cents per pound. The operating costs on concentrating ore, including all fixed, general, and maintenance charges, for the years 1910 to 1917, inclusive, are shown in the table below:

Average cost per ton of mining, transportation, and milling in property of Utah Copper Co., 1910–1917.

Year.	Tonnage.	Mining.	Transportation.	Milling.	Total.
1910	4,340,245	$0.4097	$0.2978	$0.4663	$1.1738
1911	4,680,801	.4479	.3078	.4168	1.1725
1912	5,315,321	.4233	.2848	.4158	1.1239
1913	7,519,392	.3288	2797	.3676	.9761
1914	6,470,166	.3232	.2782	.3536	.9550
1915	8,494,300	.2441	.2781	.3402	.8624
1916	10,994,000	.2781	.2792	.3782	.9355
1917	12,542,000	.4446	.2794	.6930	1.4170

With the exception of a few minor changes and additions, the leaching plant was completed and put in operation during the month of December. Since then operations have been hampered by the difficulties usually experienced in starting a new plant, as well as by cold and stormy weather. * * * The indications are that it will have a capacity of from 2,000 to 4,000 tons per day. * * *

Construction of the acid plant, the ownership of which is divided equally between the Utah Copper Co. and the Garfield Smelting Co., was delayed on account of slow delivery of materials. * * * It has now attained an average rate of about 115 tons of 50° acid per day, for all of which there is a ready market. * * * It is expected that minor improvements and additions will be completed about May 1, 1918.

The United States Mining Co.'s properties yielded 85,402 dry tons of copper ore and 120,669 dry tons of lead ore. Some ore in addition to this was mined by lessees. The company's annual report contains the following paragraph[1]:

The improved facilities made it possible not only to replace by development work the large tonnage extracted, but to add materially to the reserves in sight. Indications are very good for equally good developments in the future. It may be stated as an important fact that developments on the Niagara tunnel level have demonstrated that the ore bodies continue with undiminished strength to this level, and may be expected to continue for some depth below it.

The Bingham Mines Co., owning the Dalton & Lark mine, produced lead-silver and copper ores. It did some development work on the Yosemite but did not operate the Commercial mine.

The Dalton & Lark property[2] produced 7,057 dry tons of lead sulphide ore, 18,345 tons of copper sulphide ore, and 374 tons of iron sulphide ore. Altogether the ores shipped from these mines contained 1,872.05 ounces of gold, 139,240 ounces of silver, 1,681,848

[1] United States Smelting, Refining & Mining Co. Twelfth Ann. Rept., for year ending Dec. 31, 1917.
[2] Bingham Mines Co. Ninth Ann. Rept., for year ending Dec. 31, 1917.

Digitized by Google

pounds of lead, and 679,007 pounds of copper. Lessees operating in these properties mined 8,336 tons of lead and copper ore. The iron sulphide ore was purchased by the smelter for experimental purposes and was said to assay 39.6 per cent of sulphur, 25 per cent of iron, 0.03 ounce of gold, and 1.75 ounces of silver. The operations of this group of properties in 1917 were confined to the exploitation of every available showing and the development for the continuation of known ore deposits.

The Ohio Copper Mill, at Lark, was remodeled to use the flotation process, which is expected to be in operation and to treat 3,000 tons of ore daily in the summer of 1918. Mineral Separation machines, Hardinge mills, and Dorr thickeners and classifiers were installed.

The Montana-Bingham Co. continued driving its tunnel under the Fortuna ground recently purchased. Low-grade pyritic copper ores were shipped, and a mill was built at the Fortuna mine, and concentrates were produced.

The Highland Boy mine[1] produced 7,968,165 pounds of copper, 13,014,841 pounds of lead, 408,560 ounces of silver, and 13,530 ounces of gold, contained in ore as follows:

Average assay per ton of crude ore shipped from the Highland Boy mine, Utah, in 1917.

Material.	Dry ore.	Gold.	Silver.	Copper.	Lead.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Per cent.*	*Per cent.*
Copper-iron sulphide ore	226,536	0.050	0.764	1.797	.....
Lead sulphide ore	58,247	.039	4.567	.610	13.913

At the Utah Apex property[2] operations were unfortunately delayed about three months by a fire which occurred in the mine during the early part of 1917. The total ore produced aggregated 118,694 tons, of which 101,057 tons were of shipping grade and 17,637 tons were lead ore of milling grade. The metals contained in this output were 3,551 ounces of gold, 396,989 ounces of silver, and 24,414,451 pounds of lead.

In 1917 the Utah Metal & Tunnel Co.[3] produced from its ores 4,612 ounces of gold, 242,003 ounces of silver, 659,127 pounds of copper, and 5,348,610 pounds of lead, valued in all at $884,687.88. This output includes the ore mined from the Bingham-New Haven property taken under control by the Utah Metal Co. in 1915. The dividends paid in 1917 amounted to $553,261.67.

SAN JUAN COUNTY.

In October the 300-ton mill erected on the Big Indian property was reported to be complete, and there was plenty of ore in the bins to commence operations. The plant is designed for the sulphurous acid leaching process, patented by Niels C. Christensen, for the treatement of copper ore. Sufficient sulphur for the first operation was hauled from the railroad. The mill was operated a short time.

[1] Utah Consolidated Mining Co. Ann. Rept., for year ending Dec. 31, 1917.
[2] Utah Apex Mining Co. Ann. Rept. for year ending Aug. 31, 1917.
[3] Utah Metal & Tunnel Co. Third Ann. Rept., for year ending Dec. 31, 1917.

Digitized by Google

but closed, it is said, for certain alterations, which were not completed at the end of 1917.

White Canyon district.—The Copper Point property produced 28 tons of ore, averaging about 25 per cent of copper, and 3½ ounces of silver per ton.

SANPETE COUNTY.

Ephraim district.—The Sanpete Central property, 6 miles west of Ephraim, was a producer of a small quantity of lead ore in 1917.

SUMMIT AND WASATCH COUNTIES.

The principal producing area in Summit and Wasatch counties is the Park City region, which embraces the Blue Ledge, Snake Creek, and Uinta district. All but the first-named were credited with an output in 1917 of gold, silver, copper, lead, and zinc, valued at $6,312,103. This value added to the value of the production of metals since 1870 amounts to the sum of $169,814,024, which includes $4,367,178 in gold, $99,202,886 in silver, $4,917,960 in copper, $56,374,893 in lead, and $4,951,107 in zinc. The total amount of the dividends from the district for the period 1870–1917 is $43,544,700.

Mine production in Park City mining region, Utah, 1916–17.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	20	300,598	$111,236	2,900,718	1,512,578	33,233,794	5,136,353	$5,373,405
1917	17	240,610	110,647	2,937,438	1,285,308	33,715,565	5,201,756	6,312,103
Increase or decrease, 1917	.....	−59,988	−589	+36,720	−227,270	+481,771	+65,403	+938,698
Total, 1870–1917	.....	.....	4,367,178	135,193,810	31,028,556	1,252,444,864	66,191,185	160,814,024

The output in 1917 was 240,610 tons, as against 300,598 tons in 1916. The crude ore shipped directly to the smelters consisted of mixed lead carbonates and sulphides aggregating 60,757 tons and contained 3,533.10 ounces of gold, 2,115,183 ounces of silver, 768,909 pounds of copper, and 20,282,892 pounds of lead, valued in all at $3,770,187, or an average value per ton of $62.05. The remainder of the ore (114,483 tons) was milled, the bulk of it producing 35,489 tons of concentrates, including those from 65,370 tons of creek tailings. The concentrates contained 1,819.45 ounces of gold, 822,255 ounces of silver, 516,399 pounds of copper, 13,432,673 pounds of lead, and 5,201,756 pounds of zinc, valued in all at $2,541,915, or an average value per ton of $71.63. In 1916 the average value per ton of shipping ore was $62.60 and of concentrates $70.64.

During 1917 the Silver King Coalition mine and mill were operated steadily, and crude lead ore and lead concentrates shipped aggregated nearly 29,000 tons. The company distributed in dividends $729,660 in 1917, which, added to dividends paid in the past from all its holdings, makes a total of $15,064,545.

Digitized by Google

The Ontario mine[1] in recent years has been in the hands of lessees most of the time who worked the upper levels, mining little ore but shipping large quantities of the old fillings. In 1917 the company reported ore sales amounting to $315,158, and gives the following notes:

During the earlier part of the year the shaft was retimbered and the 1,700-foot level was unwatered and reopened. Shipments from stopes on the 1,700-foot level were started in April in a small way. The ore body, which was struck on the 1,600-foot level during 1916, was prospected by about 500 feet in drifts and 175 feet in raises. This development has shown a large amount of mineralization with varying values, the larger part of the material developed being too low grade to be treated profitably under present conditions. * * *

A large tonnage has been shipped by the company during the past year, much of it low-grade ore on which there was but a small margin. This included a low-grade product from old fillings and old dumps. It is estimated that a considerable amount of ore of this character remains.

At this writing (March, 1918) the Ontario management reports that the ore on the 1,600-foot level has increased greatly in value and that a good body of ore has been found on the 1,700-foot level.

The Silver King Consolidated property[2] was equipped with a concentration plant having a capacity of 50 to 70 tons per day and produced during 11 months of 1917 ore and concentrates aggregating 10,260 tons, against 10,082 tons for the preceding 12 months. In 1917 the output contained 451,627 ounces of silver, 5,016,627 pounds of lead, 403 ounces of gold, and 248,771 pounds of copper. The net smelter returns amounted to $642,467 and dividends to $383,287. The output in 1917 compared well with the full year of 1916.

In December the California & Comstock property was purchased by the Silver King Consolidated, thus adding 135 acres of mineral territory equipped with a 125-ton milling plant, hoisting works, and necessary buildings. This ground has a production record of many thousand tons of ore near the surface, and in 1917 it was again a producer of milling ore which yielded lead concentrate containing silver with a little copper and zinc. These properties are to be developed by the Spiro tunnel, which, at the close of 1917, was 5,000 feet from its portal and progressing at the rate of 10 feet a day. The company report says:

A total distance of about 15,000 feet will place it directly under the Comstock shaft at a depth of about 1,730 feet below the surface. The tunnel is 6 feet wide at the top by 7 feet 4 inches wide at the bottom, by 7 feet high inside of the timbers. It is perfectly straight, with a grade of 0.03 per cent, and is well equipped with an ample ditch, air pipes, and heavy rails. The tunnel crosses the strike of the sediments at an acute angle. It started in the Thaynes formation, but has not passed a considerable distance into the Woodside shales. It is expected to pass through the Woodside shales and into the Park City formation before reaching the California-Comstock ground.

The Daly-Judge property attracted considerable attention in the completion and operation of its electrolytic zinc plant, which began the production of high-grade spelter in February, 1917. According to the annual report of the company,[3] the total output of ore from the mine was 65,427 tons, dry weight, which is 524 tons less than the output of 1916. The report continues with the following paragraphs:

[1] Ontario Silver Mining Co. Ann. Rept. for the year ending Dec. 31, 1917.
[2] Silver King Consolidated Mining Co. Ann. Rept. for 11 months ending Dec. 31, 1917.
[3] Judge Mining & Smelting Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

One gratifying feature is the comparison of the increased production of 3,083 tons of crude or smelting grade ore over that of 1916, being 7,247 tons as against 4,164 tons. The products from the concentrating mill were 11,736 tons of lead concentrates and 5,470 tons of zinc concentrates, the latter being the product treated in our zinc reduction plant. The metal contents of all products sold, follow: 585,680 ounces of silver, 531.5 ounces gold, 7,919,720 pounds lead, 428,000 pounds copper, and 976,406 pounds of recoverable zinc. * * *

The total receipts from all sources were $992,863.59, against expenditures of $934,313.69, which, together with our dividend payment of $480,000, has reduced our available cash balance to $133,839.71.

Average content of crude ore and concentrates of Judge Mining & Smelting Co., Utah, in 1917.

Kind of material.	Dry ore.	Gold (per ton).	Silver (per ton).	Copper.	Lead.	Zinc.	Iron.	Sold for—
	Short tons.	*Fine ounce.*	*Fine ounces.*	*Per cent.*	*Per cent.*	*Per cent.*	*Per cent.*	
Crude ore shipped	7,247	0.023	35.18	1.10	14.26	.....	9.18	$36.38
Lead concentrates shipped	11,736	.029	26.62	1.03	24.59	.....	20.00	54.44
Zinc concentrates shipped	926	.020	19.86	1.30	4.30	43.11	.....	36.32

The Three Kings property continued development by crosscutting and sinking from the 500-foot level. At the American Flag mine some lessees mined ore. Both the Big Four and Broadwater concentration mills, working on tailings, were closed in September. Other producers were the New Quincy, Naildriver, and California-Comstock.

TOOELE COUNTY.

The production of 132,048 tons of ore by 61 producers in 1917, was 7,353 tons greater than the output by 48 producers in 1916. The average value per ton of the ore increased from $23.48 in 1916 to $24.64 in 1917, and the value per ton in gold and silver from $4.82 to $5.19. The total value of the ore sold or treated, containing gold, silver, copper, lead, and zinc, was $3,253,492, against $2,928,420 in 1916. The county output consisted of 1,564.64 ounces of gold, valued at $32,344; 793,265 ounces of silver, valued at $653,650; 4,181,231 pounds of copper, valued at $1,141,476; 15,031,521 pounds of lead, valued at $1,292,711; and 1,306,974 pounds of recoverable zinc, valued at $133,311. The increases were: Gold, $13,462; and copper, 1,344,553 pounds in quantity and $443,653 in value. The decreases were: Silver, 91,138 ounces in quantity, but an increase of $71,713 in value; lead, 3,696,150 pounds in quantity, but an increase of $502 in value; and zinc, 1,212,198 pounds in quantity and decrease of $204,258 in value.

There were 82,455 tons of crude shipping ore of various kinds. The zinc ore produced was 2,149 tons, all of which was of shipping grade and an oxidized product. The quantity of dry or siliceous ore decreased from 823 tons in 1916 to 263 tons in 1917. The output of copper ore of shipping grade was 30,466 tons, nearly all of which was oxidized, and the lead ore was 43,922 tons, of which there were 9,309 tons oxidized and 34,613 tons sulphides. There were also 5,583 tons of copper-lead ore. The crude ore shipped directly to the smelters contained $30,071 in gold, 630,504 ounces of silver, 3,600,215

Digitized by Google

pounds of copper, 11,201,922 pounds of lead, and 1,300,969 pounds of recoverable zinc, having a total value of $2,628,528, or an average value per ton of $31.88. Concentrating and jigging plants produced 13,898 tons of concentrates from the treatment of 38,472 tons of ore and yielded $2,118 in gold, 160,744 ounces of silver, 563,578 pounds of copper, 3,749,709 pounds of lead, and 6,005 pounds of recoverable zinc, valued in all at $611,515, or an average value per ton of $44.

Blue Bell district.—The R. E. P. property yielded a small quantity of lead sulphide ore carrying some silver.

Clifton district.—Seventeen producers in 1917 shipped 33,960 tons of ore, all of which went directly to the smelters and contained $11,665 in gold, 161,204 ounces of silver, 1,894,731 pounds of copper, 513,929 pounds of lead, valued in all at $705,957, or an average value per ton of $20.79. The principal part of the production came from the Gold Hill property of the Western Utah Copper Co., which shipped oxidized copper ore and oxidized lead ore to the smelters near Salt Lake City. The Woodman property was also a producer of copper and lead ore, both oxidized, carrying gold and silver values, and containing an average of about 9 per cent of iron and 51 per cent of silica. Other producers of more than 100 tons of ore were the Copperopolis, Garrison Monster, and Pole Star.

At the Western Utah property[1] the principal production and development in 1917 were confined to the Gold Hill group. There were shipped 28,718 tons of copper ore and 3,305 tons of lead ore, containing altogether 70 ounces of gold, 150,767 ounces of silver, 371,418 pounds of lead, and 1,710,984 pounds of copper. From ore sold to the smelters the sum of $470,477.73 was received. The company's report says:

> The greatest part of development work done during the year has been done toward the surface from the 80-foot level, on the 110-foot level, and on the 300-foot and 400-foot levels.
>
> On the 80-foot level and for some distance above and below this level the largest copper ore body occurred. In the regular course of mining this body of ore there was found quite a large tonnage of hematite iron in the core or center. This carried less than 1 per cent copper and reduced the ore reserves very materially. Late developments, however, on the 110-foot level show a very good grade of copper ore, which partly makes up for the large body of hematite described above.
>
> Quite a tonnage of silver-lead ore of low grade has been developed on the 300-foot and 400-foot levels.
>
> A small tonnage of lead-silver ore of very good grade has been developed on the 110-foot level.

Tungsten and molybdenum ores were produced from the Seminole property, though little of the latter ore was shipped. Oxidized bismuth ore in less than carload lots was shipped from the Wilson Consolidated property.

Columbia district.—The Old Sharp mine and the New Erie property produced a total of 1,016 tons of lead ore carrying a little silver.

Dugway district.—There was considerable activity in the district in 1917, but only a small quantity of ore was marketed. Certain promoters promised that a copper smelter would be in operation before the close of 1917, but at this writing (August, 1918) not even the necessary funds have been raised to purchase the equipment.

[1] Western Utah Cooper Co. First Ann. Rept., for year ending Dec. 31, 1917.

Digitized by Google

There were three properties producing, of which two, the Dugway and American Leasing, shipped copper ore, and the Laurel shipped a car of 50 per cent lead ore.

Erickson district.—Four properties reported the production of ore, the principal part coming from the Happy Jack, Indian Springs, and O. K. Silver properties.

Free Coinage district.—The Last Chance property yielded a carload of oxidized lead ore in 1917.

Lakeside district—The Monarch property, under option to one of the smelting companies in the Salt Lake Valley, produced lead ore averaging about 1 ounce of silver to the ton. This property has been opened by several tunnels, incline shafts, and drifts, all of which are said to be in ore, though most of its is too low grade to ship at a profit. The fissure in which the ore occurs is over 40 feet wide, and samples taken across its entire face show it to be a lead-silver ore of fine milling grade. The ore is hauled 7 miles north of the property to Delle, on the Western Pacific Railroad, and is shipped to a smelter.

North Tintic district—The improvement in zinc prices was the cause of an important production of ore from the Scranton mine, which also shipped some lead ore. The total output of the district amounted to 4,738 tons of lead and zinc ores.

Ophir district—Fifteen producers reported 80,944 tons of ore, which included 10,402 tons of old tailings re-treated. Half of the ore produced from the mines was milled and produced concentrates. There were shipped directly to the smelters 36,074 tons of crude ore, which included 891 tons of zinc ore containing 567,523 pounds of recoverable zinc. The principal producers of the district were the Cliff, Ophir Coalition, Hidden Treasure, and Ophir Hill. There were also shipments from the Buffalo Consolidated, Commodore, Eureka Ophir, Kearsarge, Chloride Point, Mono, Thad Stevens, and Utah Queen mines.

Rush Valley district—There were 10 producers reporting 10,713 tons of ore, including 719 tons of slag cleaned up from the old smelter operations. There were 5,590 tons of ore shipped directly to the smelters, and 4,004 tons were milled and yielded lead concentrate carrying a little copper and good silver values. The total output contained $14,647 in gold, 79,797 ounces of silver, 43,335 pounds of copper, 3,315,077 pounds of lead, and 56,490 pounds of recoverable zinc, valued in all at $383,089, or an average value per ton of $35.76. The Bullion Coalition was the principal producer of the milling ore and of more than half the ore shipped directly to the smelters. Reports of production were also received from the Cyclone, Galena King, Muerbrook, New Stockton, and Southport properties.

Silver Islet district.—Small outputs of lead ore containing a little copper and silver were reported from three properties in 1917.

Third Term district.—An important quantity of oxidized lead ore was shipped from the Third Term mine, an old property worked in the seventies. This ore was hauled by wagon to the smelter near Tooele.

Digitized by Google

UINTA COUNTY.

Carbonate district.—From the Kate lode on Grizzly Mountain, near Vernal, lead ore was shipped to the smelters, and 51 per cent copper ore was shipped from the Uinta Bonanza claim.

UTAH COUNTY.

Sixteen operators reported the production of 32,273 tons of ore in 1917, against 18,111 tons of ore produced by 18 operators in 1916. The total value of the output in 1917 was $1,064,457, against $703,569 in 1916. The total average value per ton of the ore decreased from $38.85 in 1916 to $32.98 in 1917, and the gold and silver value per ton increased from $12.60 to $16.64. Most of the ore produced (25,460 tons) was of shipping grade, and the remainder (2,874 tons) was milled and produced concentrate containing gold, silver, copper, and lead. There were also 3,939 tons of ore containing gold, silver, and copper treated at the Silver City mill.

American Fork district.—Seven producers reported 3,610 tons of ore, containing $2,004 in gold, 35,021 ounces of silver, 15,630 pounds of copper, and 641,990 pounds of lead, valued in all at $90,339, or an average value per ton of $25.02. The largest part of the ore produced was milled and yielded a lead concentrate, which, with 736 tons of crude ore, was shipped directly to the smelters. A small mill erected to treat lead ore produced from the Pacific property was replaced in 1917 by a larger plant nearer the mine. Ore produced from the Dutchman mine, operated by the same interests, was treated in the new mill. Lead ore was also produced from the Yankee, the Bay State, and the old Miller property.

The Fissures Exploration Co., operating the Pacific mine, increased its mill capacity, and toward the end of 1917 was treating 150 tons of ore a day. The Pacific fissure was drifted upon for 700 feet. The ore fissure is about 8 feet wide and has a proved depth of 300 feet. The Miller Hill property, adjoining the Pacific, started a new adit which was driven over 2,000 feet and will give a depth of 500 feet under old workings.

Mine production in American Fork district, Utah, 1916–17.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	6	868	$895	48,360	31,189	250,460	27,319	$ 61,332
1917	7	3,610	2,004	35,021	15,630	641,990	.....	90,339
Increase or decrease, 1917...		+2,742	+1,109	−13,339	−15,559	+391,530	−27,319	+29,007
Total, 1870-1917		64,217	371,373	1,887,596	159,091	28,586,796	46,911	3,895,050

Provo district.—A small shipment of lead ore was reported from the Monarch property in 1917.

Santaquin district.—From the Delsa property, one shipment of lead ore was made in 1917. Development work only was carried on at the Union Chief, which was a producer the preceding year.

Digitized by Google

Tintic district.—In 1917 the producers on the Utah County side were the Colorado Consolidated, May Day, Sioux, Tintic Standard, Uncle Sam, Utah Consolidated, and Yankee properties. The production of the district is reviewed under Juab County, under which the operations of the more important properties in 1917 are described.

WASHINGTON COUNTY.

Bull Valley district.—A small quantity of copper ore was shipped from one property in 1917. Work on the gold properties was practically abandoned during the year, there being no development performed beyond annual assessment work.

Harrisburg district.—The Adah property yielded a carload of oxidized copper ore in 1917.

Tutsagubet district.—Renewed operations by lessees at the Apex mine, owned by the Utah Southern Mining Co., resulted in an output of oxidized copper ore, which was shipped directly to the smelters in the Salt Lake Valley.

Digitized by Google

GOLD, SILVER, COPPER, LEAD, AND ZINC IN CALIFORNIA.

(MINES REPORT.)

By CHARLES G. YALE.

INTRODUCTION.

Notwithstanding the increase in the cost of labor and supplies due to the war and the consequent closing down of smaller properties and curtailment of the operations of larger ones the output of the metal mining industry of California shows a decrease in value of only a little more than $2,000,000 in 1917 as compared with 1916. The gold, silver, copper, and zinc mines of the State made a smaller output, and the lead-producing mines made a larger output in both quantity and value. Metal mines of all kinds have been short of skilled labor, many men having been called into the Army or Navy and many others having quit mining to engage in other industrial occupations that brought higher remuneration. These conditions have affected the metal-mining industry of the State very materially, and the operators have been compelled to employ much less efficient labor.

California, as a metal-producing State, has always been best known as the leader in output of gold, a position it has annually maintained for about 70 years, except in a few years. The gold-mining industry of the State has, however, now entered a condition of temporary decadence. There was a material decline in 1916 as compared with 1915, and the decline in 1917 from 1916 is still more marked—amounting to $1,323,237. Owing to the exigencies of the war skilled labor became much scarcer and more expensive, so that operations were curtailed, especially in the larger deep mines. Materials and supplies were scarcer and more expensive, so that many of the smaller and less profitable mines were compelled to cease operations. This condition naturally brought about a reduction in the number and output of the mines. Many miners working for themselves or for wages quit gold mining and began to search for chrome, manganese, magnesite, and tungsten or to work in mines of those minerals.

The decrease in the production of gold in California is due entirely to the reduction in the output of the deep mines, for the placers, particularly the dredges, have made a larger output. The production of the deep mines in 1917 decreased more than 14 per cent, whereas that of the placers increased nearly 6 per cent. The gold recovered from placers in 1917 was about 45 per cent of the total output of the State. Of this placer output the gold dredges produced 91 per cent. Since the beginning of the gold-dredging industry in California in 1898, the gold recovered from this source to the end of 1917 has been $95,193,995. Before gold dredging was begun the placer mining had been steadily declining and it was asserted that

Digitized by Google

placer mining in California was virtually at an end. Yet, these dredges produced 41 per cent of the total production of gold in 1917, and thus far, have shown no diminution of product, although the output of one of the larger fields is declining because so much ground has been worked out. Meantime the other large fields continue production, and at numerous isolated sections dredges have been profitably engaged. There are now 55 gold dredges in operation in California, or 5 less than in 1916.

The number of producing gold mines in the State has been gradually reduced until there are now only about 500. It is expected that this number will continue to decrease during 1918 and until the war is over and normal conditions are resumed. Many mines, especially on the Mother Lode, have been working on such a narrow margin of profit that increased costs have nearly or entirely wiped this margin out, so that gold mining is no longer an attractive industry in California. There was a scarcity of water both for power and for washing gravel during the year owing to the prevalent "dry season" in California. This shortened the period during which gravel could be washed in placers and compelled the "hanging up" of part of the stamps in quartz mills. The falling off in the purchasing power of gold has also been a serious matter, and with high costs in all directions the operators consider that their gold only brings them $10 to $12 an ounce, as compared with several years ago. The cost per ounce in the production of gold has steadily advanced, and in some cases has reached $14 to $16, as compared with an average of $12 three years ago.

Another serious complaint made by the drift and quartz miners is the insistence of the War Department on the construction of concrete dams for the impounding of tailings, when formerly timber dams sufficed or none at all were required. It is argued by the miners that at a time when everything required in construction work is so expensive and costs of labor are excessive, the burden added by the construction of such concrete dams in nonnavigable streams might well be postponed during the war. Many of these dams and impounding works cost $25,000 or $30,000 each, and in some places the expense has become prohibitive and the mines involved have ceased operation. In a large section of Butte County, for example, every drift mine, even those already having timber dams, has ceased operations for the present at least, and some have been abandoned entirely and the plants removed. This condition has materially affected quartz-mining interests on portions of the Mother Lode, a long distance from any navigable streams.

The only counties in California showing an increased output of gold in 1917 were Amador, Calaveras, Del Norte, Fresno, Humboldt, Nevada, Placer, Sacramento, Trinity, and Yuba. The combined increase of these counties was only a little more than a million dollars, of which Yuba County contributed about half from its dredges. The other counties had a combined decrease of $2,344,194, so that the total decrease in gold output for the year was $1,323,237, or about 6 per cent.

The other metals produced in the State were also affected by some of the existing conditions mentioned in connection with gold mining. The silver yield fell off 13 per cent in value; the copper was less by 14 per cent in quantity and 4 per cent in value; and the zinc was less

by 29 per cent in quantity and 46 per cent in value. The only metal showing an increase was lead, which increased in quantity 76 per cent and in value 119 per cent. The total combined value of all the metals was $37,685,985, or 5 per cent less in 1917 than in 1916. A little more than 3,000,000 tons of ore from deep mines of all classes was treated in 1917, with an average value in all metals of $9.52 a ton, which average differs little from that of 1916.

The details of mining work in the Mother Lode counties are given in the section on production by counties. A condensed statement is given in the following table:

Gold and silver produced at mills in Mother Lode counties in California in 1917.

County.	Ore treated (short tons).	Gold and silver recovered in bullion.		
		Gold.	Silver (fine ounces).	Average value in gold and silver per ton of ore.
Amador	798,952	$2,223,613	17,044	$2.800
Calaveras	352,641	473,205	4,720	1.353
Eldorado	2,506	3,067	32	1.230
Mariposa	41,548	268,471	2,387	6.509
Tuolumne	41,256	233,866	8,550	5.839
	1,236,903	3,202,212	32,733	2.610

County.	Concentrates produced.				Value of total recovery.	
	Quantity (short tons).	Gold.	Silver (fine ounces).	Average value in gold and silver per ton of concentrates.	Total.	Average per ton of ore.
Amador	18,456	$1,422,404	8,608	$77.45	$3,667,154	$4.589
Calaveras	[a] 26,209	349,574	4,734	[a] 13.44	830,569	[b] 2.355
Eldorado	66	2,543	2	38.57	5,628	2.245
Mariposa	711	41,008	982	58.81	312,255	7.515
Tuolumne	1,585	73,432	890	46.79	315,076	7.637
	47,117	1,888,961	15,216	[c] 40.35	5,130,682	4.148

[a] Includes 17,875 tons of concentrates from copper ores concentrated; exclusive of copper concentrates the average recovery was $41.96 a ton.
[b] Exclusive of copper ores concentrated.
[c] Average value exclusive of copper concentrates was $65.03 a ton.

A comparison of this table with the corresponding one for 1916 shows a total decrease in ore treated at gold and silver mills in the five Mother Lode counties in 1917 of 156,885 tons. Each of these counties shows more or less decrease of tonnage except Amador, which increased its output of ore by 68,854 tons.

In the Mother Lode counties in 1917 there were treated at gold and silver mills 1,236,903 tons of ore, yielding in gold and silver $5,130,682, or an average of $4.148 per ton, as compared with 1,393,788 tons in 1916, yielding $5,853,618, and averaging $4.199 a ton; as compared with 1,521,847 tons in 1915, yielding $6,349,772, and averaging $4.17 a ton; 1,243,529 tons in 1914, yielding $5,075,522, an average of $4.08 a ton; 1,242,343 tons in 1913, yielding $4,728,450, an average of $3.81 a ton; 1,299,988 tons in 1912, yielding $4,803,935, or $3.69 a ton; and 1,377,084 tons in 1911, yielding $4,910,358, or $3.57 a ton.

Digitized by Google

The average value of gold and silver in the concentrates per ton was $40.35 in 1917, as compared with $56.83 in 1916, and $56.56 in 1915. Excluding copper concentrates the average value per ton was $65.03 in 1917. There was 47,117 tons of concentrates obtained from the 1,236,903 tons of siliceous milled ore and 148,078 tons of copper ore concentrated in these counties in 1917.

The total quantity of ore treated at gold and silver mills from the deep mines of the State in 1917 was 1,809,017 short tons, which was 288,120 tons less than in 1916. Of the total ore milled, 68 per cent came from the Mother Lode counties in 1917. Amador, the largest producer of the Mother Lode counties, produced 44 per cent of the total quantity of ore milled in the State in 1917, and 65 per cent of the ore milled in the Mother Lode counties.

Crude ore sold or treated in California in 1917, in short tons.

County.	Siliceous ores.	Copper ores.	Lead and lead-zinc ores.	Silver ores.	Silver-lead ores.	Zinc ores.	Total.
Amador	804,852	23					804,875
Butte	349						349
Calaveras	407,700	189,124					596,824
Del Norte, Humboldt, Riverside, Sacramento, and San Diego [a]	515	70					585
Eldorado	2,506						2,506
Fresno	601						601
Imperial	154						154
Inyo	2,169	382	27,714		53,954	135	84,354
Kern	123,140	2,417		92			125,649
Madera	2,111	4,119					6,230
Mariposa	41,690	186					41,876
Mono	18,776						18,776
Nevada	480,869						480,869
Placer	14,080	2,574					16,654
Plumas	13,879	176,094					189,973
San Bernardino	1,165	20,630	366	77	10,045		32,283
Shasta	9,673	484,511		285			494,469
Sierra	50,042						50,042
Siskiyou	2,237	3,616					5,853
Trinity	186	8,615					8,801
Tuolumne	41,309	218					41,527
	2,018,003	892,579	28,080	454	63,999	135	3,003,250
Increase or decrease	−174,010	−41,143	+26,444	+389	+32,872	[b]−28,944	−184,392
Average value per ton in gold and silver	$5.133	$1.565	$4.937	$13.32	$8.621	$0.171	$4.146

[a] Yield of single mine in each county combined to conceal separate output.
[b] Considerable quantity of ore classed as lead and lead-zinc ores.

Value of ore mined and treated in California in 1917.

Class.	Ore.	Total value.		Average value per ton.	
	Quantity (short tons).	In gold and silver.	In all metals.	In gold and silver.	In all metals.
Siliceous	2,018,003	$10,359,517	$10,380,060	$5.133	$5.143
Copper	892,579	1,396,972	14,871,637	1.565	16.661
Lead	28,080	138,631	1,129,811	4.937	40.235
Silver	454	7,048	8,176	13.32	18.239
Silver-lead	63,999	551,778	2,187,900	8.621	34.186
Zinc	135	23	11,911	.1717	88.230
	3,003,250	12,453,969	28,589,495	4.146	9.519

The value of all metals obtained from ores mined and treated in California in 1917 (not including placer mine output) was $28,589,495, an average of $9.52 a ton. In 1916 the value was $31,154,122, an

Digitized by Google

average of $9.77 a ton; in 1915 it was $23,636,028, an average of $7.87 a ton. In 1914 the figures, respectively, were $16,610,509 and $6.74; in 1913, $17,954,941 and $7.19; in 1912, $17,716,357 and $6.71; in 1911, $16,167,193 and $5.49; in 1910, $18,109,008 and $6.71; and in 1909, $19,715,314 and $6.48.

Gold and silver produced in California in 1917, by methods of treatment.

County.	Ore to gold and silver mills.			Ore to concentrating mills.	Concentrates produced.		
	Quantity.	Gold.	Silver.	Quantity.	Quantity.	Gold.	Silver.
	Short tons.		*Fine ounces.*	*Short tons.*	*Short tons.*		*Fine ounces.*
Amador	798,952	$2,223,613	17,044	.....	18,456	$1,422,404	8,608
Butte	140	1,751	5	.....	.....	.....	.....
Calaveras	352,641	473,205	4,720	148,690	26,299	349,574	4,734
Del Norte, Humboldt, Riverside, Sacramento, and San Diego [1]	193	1,902	6	.....	6	930	9
Eldorado	2,506	3,057	32	.....	66	2,543	2
Fresno	119	1,265	4	.....	.....	.....	.....
Inyo	9,709	29,803	682	.....	201	21,354	10,053
Kern	123,140	532,880	5,949	.....	20	1,988	118
Madera	2,111	11,065	52	.....	41	3,488	6
Mariposa	41,548	268,471	2,387	.....	711	41,008	982
Mono	18,090	208,416	5,186	.....	.....	.....	.....
Nevada	337,596	3,292,110	34,432	.....	1,096	54,175	2,238
Placer	14,080	89,340	1,573	.....	117	8,765	667
Plumas	13,870	51,326	335	172,306	12,409	25,902	80,848
Shasta	864	17,196	159	101,173	13,391	2,835	2,393
Sierra	49,779	320,728	1,769	.....	1	343	1
Siskiyou	2,237	17,095	234	.....	2	196	1
Trinity	186	2,366	23	.....	8	589	11
Tuolumne	41,256	233,866	8,550	.....	1,585	73,432	890
	1,809,017	7,774,455	83,142	422,169	74,409	2,009,526	111,561
Average value per ton	.....	$4.297	$0.038	.....	.....	$27.00	$1.235

County.	Crude ore to smelter.			Old tailings treated.		
	Quantity.	Gold.	Silver.	Quantity.	Gold.	Silver.
	Short tons.		*Fine ounces.*	*Short tons.*		*Fine ounces.*
Amador	23	.....	12	5,900	$11,990	233
Butte	209	$2,906	258	.....	.....	.....
Calaveras	40,503	65,660	94,774	54,990	65,435	110
Del Norte, Riverside, and San Diego [1]	392	.....	84	.....	.....	.....
Fresno	482	1,993	340	.....	.....	.....
Imperial	154	919	6	.....	.....	.....
Inyo	74,645	74,237	638,050	.....	.....	.....
Kern	2,509	1,984	3,411	.....	.....	.....
Madera	4,119	3,797	533	.....	.....	.....
Mariposa	328	2,481	535	.....	.....	.....
Mono	.....	.....	.....	686	5,624	1,686
Nevada	.....	.....	.....	143,273	320,292	26,792
Placer	2,574	22,180	12,964	.....	.....	.....
Plumas	3,797	1,511	9,039	.....	.....	.....
San Bernardino	31,283	152,766	107,394	1,000	1,310	528
Shasta	392,432	464,556	628,083	.....	.....	.....
Sierra	170	1,634	5	93	580	2
Siskiyou	3,616	5,170	18,833	.....	.....	.....
Trinity	8,615	17,901	9,788	.....	.....	.....
Tuolumne	218	.....	.....	53	4,568	11
	566,069	819,694	1,524,109	205,995	409,799	29,362
Average value per ton	.....	$1.448	$2.218	.....	$1.989	$0.117

[1] Yield of single mine in each county combined to conceal separate output.

In 1917 there was treated at gold and silver mills and at concentrating plants 2,231,186 tons of ore yielding altogether $9,783,981 in

Digitized by Google

gold and 194,703 fine ounces of silver, valued at $160,435, a total value of $9,944,416 in gold and silver and an average value per ton of $4.46 in both metals. The average value in 1916 was $5.04; in 1915, $5.56; in 1914, $5.44; in 1913, $5.57; in 1912, $5.08; in 1911, $4.64; in 1910, $5.25; and in 1909, $4.88.

There was recovered in 1917 as bullion in mills $7,774,455 in gold and 83,142 fine ounces of silver, valued at $68,508, a total of $7,842,963 in gold and silver and an average of $4.33 in both metals. From 1,809,017 tons of gold milling ore and 422,169 tons of concentrating ores, 74,409 tons of concentrates were obtained, containing $2,009,526 in gold and 111,561 fine ounces of silver, valued at $91,927. There was a yield of gold and silver of $2,101,453 recovered from the concentrates, or an average of $28.24 a ton.

Of smelting ores 566,069 tons were treated having an output of gold of $819,694, and of 1,524,109 fine ounces of silver, valued at $1,255,865. The total yield of gold and silver was $2,075,559, or an average of $3.67 a ton.

There were treated also 205,995 tons of tailings, yielding $409,799 in gold and 29,362 ounces of silver, valued at $24,195. The total gold and silver produced from tailings was valued at $433,994, an average of about $2.11 a ton.

PRODUCTION.

GENERAL STATEMENT.

Gold, silver, copper, lead, and zinc produced in California, 1907–1917.

Year.	Number of mines producing.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
		Short tons.	*Value.*	*Fine ozs.*	*Pounds.*	*Pounds.*	*Pounds.*	
1907	1,061	2,054,653	$16,727,928	1,138,858	28,528,020	2,625,419	233,550	$23,338,104
1908	1,054	2,546,908	18,761,550	1,647,278	38,776,881	1,237,548	.....	24,806,141
1909	1,127	3,041,688	20,237,870	2,098,253	57,288,281	1,502,597	.....	28,841,050
1910	1,079	2,697,885	19,715,440	1,840,085	48,700,756	2,870,977	.....	27,020,405
1911	1,181	2,797,261	19,738,908	1,270,445	36,316,136	1,398,111	2,807,035	25,174,577
1912	1,041	2,641,497	19,713,478	1,300,136	33,451,672	1,144,731	4,345,591	26,383,946
1913	796	2,495,958	20,406,958	1,378,399	34,575,007	3,514,342	1,057,485	26,812,487
1914	658	2,465,485	20,653,496	1,471,859	30,507,092	4,251,923	389,471	25,710,645
1915	608	3,002,779	22,442,296	1,678,756	40,751,625	4,579,245	13,094,032	32,263,844
1916	589	3,187,642	21,410,741	2,564,354	55,897,118	12,407,493	15,256,485	39,749,263
1917	490	3,003,250	20,087,504	1,775,431	48,153,139	21,868,628	10,872,716	37,685,985
Increase or decrease, 1917...	−99	−184,392	−1,323,237	−788,923	−7,743,979	+9,461,135	−4,383,769	−2,063,278

In 1917 there were 490 properties reporting production in California, of which 241 were deep mines and 249 placers. The producing deep mines of 1917 may be classified by chief metallic product as follows: Gold, 145; copper, 48; silver, 3; silver-lead, 24; lead, 19, and zinc, 2. Of the placer mines 71 were hydraulic, 16 less than in 1916; 55 were dredges, 5 less than in 1916; 53 were drift, 14 less than in 1916, and 70 were surface or sluicing mines, 8 less than in 1916. There were altogether 43 less placer mines producing than in 1916. Of the deep mines there were 59 less gold mines, 12 less copper, 2 more silver, 6 more silver-lead, and 1 less zinc; there were, therefore, 56 less deep mines producing in 1917 than in 1916. The dredges are enumerated by the number of boats at work, some companies operating only one and others several.

Digitized by Google

Mine production of gold, silver, copper, lead, and zinc in California in 1917.

County.	Ore treated.	Deep-mine gold.		Placer gold.		Total gold.	
		Quantity.	Value.	Quantity.	Value.	Quantity.	Value.
	Short tons.	*Fine ounces.*		*Fine ounces.*		*Fine ounces.*	
Amador	804,875	176,956.09	$3,658,007	297.84	$6,157	177,253.93	$3,664,164
Butte	349	225.23	4,656	44,389.63	917,615	44,614.86	922,271
Calaveras	596,824	46,143.65	953,874	25,037.35	517,568	71,181.00	1,471,442
Del Norte	289			66.42	1,373	66.42	1,373
Eldorado	2,506	270.90	5,600	926.77	19,158	1,197.67	24,758
Fresno	601	157.61	3,258	120.31	2,487	277.92	5,745
Humboldt	73	77.01	1,592	1,039.77	21,494	1,116.78	23,086
Imperial	154	44.46	919			44.46	919
Inyo	84,354	6,065.93	125,394			6,065.93	125,394
Kern	125,649	25,970.21	536,852	48.38	1,000	26,018.59	537,852
Madera	6,230	887.68	18,350	27.28	564	914.96	18,914
Mariposa	41,876	15,091.06	311,960	64.63	1,336	15,155.69	313,296
Mono	18,776	10,112.31	209,040			10,112.31	209,040
Nevada	480,869	177,370.66	3,666,577	791.90	16,370	178,162.56	3,682,947
Placer	16,654	5,818.79	120,285	20,240.15	418,401	26,058.94	538,686
Plumas	189,973	3,809.00	78,739	2,574.32	53,216	6,383.32	131,955
Sacramento	120	59.99	1,240	92,799.74	1,918,341	92,859.73	1,919,581
San Bernardino	32,283	7,453.43	154,076	43.54	900	7,496.97	154,976
Shasta	494,469	23,441.90	484,587	14,054.78	290,538	37,496.68	775,125
Sierra	50,042	15,638.91	323,285	2,957.79	61,143	18,596.70	384,428
Siskiyou	5,853	1,086.55	22,461	14,661.93	303,089	15,748.48	325,550
Trinity	8,801	1,008.91	20,856	28,115.16	581,192	29,124.07	602,048
Tuolumne	41,527	15,086.52	311,866	445.97	9,219	15,532.49	321,085
Yuba				177,907.43	3,677,673	177,907.43	3,677,673
Merced, Riverside, San Diego, and Stanislaus [a]	103			12,345.11	255,196	12,345.11	255,196
	3,003,250	532,776.80	11,013,474	438,956.20	9,074,030	971,733.00	20,087,504
Total, 1916	3,187,642	620,897.19	12,835,084	414,847.40	8,575,657	1,035,744.59	21,410,741
Increase or decrease	−184,392	−88,120.39	−1,821,610	+24,108.80	+498,373	−64,011.59	−1,323,237

County.	Deep-mine silver.		Placer silver.		Total silver.	
	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.
	Fine ounces.		*Fine ounces.*		*Fine ounces.*	
Amador	25,897	$21,339	23	$19	25,920	$21,358
Butte	263	217	3,367	2,774	3,630	2,991
Calaveras	104,339	85,975	2,438	2,009	106,777	87,984
Del Norte			10	8	10	8
Eldorado	34	28	69	57	103	85
Fresno	344	283	7	6	351	289
Humboldt	4	3	112	92	116	95
Imperial	6	5			6	5
Inyo	648,785	534,599			648,785	534,599
Kern	9,478	7,810	4	3	9,482	7,813
Madera	591	487	2	2	593	489
Mariposa	3,904	3,217	5	4	3,909	3,221
Mono	6,871	5,662			6,871	5,662
Nevada	63,462	52,293	51	42	63,513	52,335
Placer	15,204	12,528	1,647	1,357	16,851	13,885
Plumas	90,222	74,343	143	118	90,365	74,461
Sacramento	11	9	5,434	4,478	5,445	4,487
San Bernardino	107,922	88,928	2	2	107,924	88,930
Shasta	630,635	519,643	1,286	1,060	631,921	520,703
Sierra	1,778	1,465	199	164	1,977	1,629
Siskiyou	19,068	15,712	1,421	1,171	20,489	16,883
Trinity	9,822	8,093	2,340	1,928	12,162	10,021
Tuolumne	9,450	7,787	25	21	9,475	7,808
Yuba			7,999	6,591	7,999	6,591
Merced, Riverside, San Diego, and Stanislaus [a]	84	69	673	554	757	623
	1,748,174	1,440,496	27,257	22,460	1,775,431	1,462,955
Total 1916	2,534,743	1,667,861	29,611	19,484	2,564,354	1,687,345
Increase or decrease	−786,569	−227,366	−2,354	+2,976	−788,923	−224,390

[a] Yield of single mine in each county combined to avoid disclosing separate output.

Digitized by Google

Mine production of gold, silver, copper, etc., in California in 1917—Continued.

County.	Copper.		Lead.		Zinc.		Total value.
	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	
	Pounds.		*Pounds.*		*Pounds.*		
Amador	2,381	$650			7,716	$787	$3,686,959
Butte							925,262
Calaveras	8,052,978	2,198,463	1,105	$95	1,833	187	3,758,171
Del Norte	30,000	8,190					9,571
Eldorado							26,843
Fresno	33,000	9,009					15,043
Humboldt							23,181
Imperial	7,000	1,911					2,835
Inyo	737,582	201,360	19,671,732	1,601,769	3,956,343	403,547	2,956,669
Kern	260,000	70,980					616,645
Madera	423,901	115,725					135,128
Mariposa	36,502	9,965					326,482
Mono							214,702
Nevada							3,735,282
Placer	633,747	173,013					725,584
Plumas	7,471,092	2,039,008					2,246,024
Sacramento							1,924,068
San Bernardino	1,572,125	429,190	2,195,791	188,838	45,216	4,612	866,546
Shasta	26,658,879	7,277,874			6,320,529	644,694	9,218,396
Sierra							386,057
Siskiyou	896,846	244,839			541,079	55,190	642,462
Trinity	1,304,901	356,238					968,307
Tuolumne	12,000	3,276					332,169
Yuba							3,684,264
Merced, Riverside, San Diego, and Stanislaus [a]	20,205	5,516					261,335
	48,153,139	13,145,807	21,868,628	1,880,702	10,872,716	1,109,017	37,685,965
Total, 1916	55,897,118	13,750,691	12,407,493	856,117	15,256,485	2,044,369	39,749,263
Increase or decrease	−7,743,979	−604,884	+9,461,135	+1,024,585	−4,383,769	−935,352	−2,063,278

[a] Yield of single mine in each county combined to avoid disclosing single output.

GOLD.

The total production of gold in California in 1917 was 971,733.00 fine ounces, valued at $20,087,504, a decrease of 64,011.59 fine ounces, valued at $1,323,237. The deep mines of the State yielded 532,776.80 fine ounces of gold, valued at $11,013,474. Of the deep mine gold 93 per cent was derived from siliceous ore, 6 per cent from copper ore, and the remainder from lead, silver-lead, and zinc ores.

While the production of gold from deep mines materially decreased, that from the placers increased $498,373, due mainly to larger returns from dredging operations. The dredges yielded $544,300 more in 1917 than in 1916. Since gold dredging began in California in 1898, the total output of gold from that source to the end of 1917 has been $95,186,985. Since 1898 the Oroville (Butte County) dredging field has yielded $30,160,486, not including $2,148,444 derived in the last eight years from adjacent districts in the same county. The Marysville (Yuba County) field has produced from 1903 to 1917, inclusive, $28,119,067 in gold; the Folsom (Sacramento County) field has yielded since 1902 from dredging, gold valued at $21,835,675. Quite a large number of dredges operated in various localities in other counties of the State, but their output of gold is not included in these figures relating to the more extensive dredge fields named. The placer yield of gold in 1917 in California was 438,956.20 fine ounces, valued at $9,074,030. The placer mines produced 45 per cent of the gold yield of 1917, and the deep mines 55 per cent, as compared with 40 per cent for the placers in 1916 and 60 per cent for the deep mines.

Digitized by Google

The dredges produced 41 per cent of the total gold yield from all sources in 1917. Of the total placer gold, the dredges produced 91.6 per cent, the hydraulic mines about 3 per cent, the drift mines 4 per cent, and the surface or sluicing mines 1.4 per cent. It is probable that this percentage from surface placers is too high, for in the reports received at the office of the United States Geological Survey large numbers of miners classify themselves as working placers without specifying the exact kind. Some of these may have been small hydraulic or drift mines instead of mere surface or sluicing mines. Although the three larger and more important dredging fields of the State are at Oroville, in Butte County; Folsom, in Sacramento County; and Marysville, in Yuba County, dredges are also operated in 7 other counties—5 in Calaveras, 1 in Merced, 3 in Placer, 3 in Shasta, 3 in Siskiyou, 1 in Stanislaus, and 4 in Trinity. The Yuba County dredges, 12 in number, made the largest output of gold in 1917, the value being $3,659,211, an increase of $519,061 as compared with 1916. Sacramento County with 12 dredges at work made an output of $1,913,504, an increase of $84,026. In Butte County (including Oroville and the "outside" districts) 11 dredges produced $893,141, or $317,733 less than in 1916. This statement shows that $285,354 more gold was obtained in these three districts in 1917 than in 1916, although one of them, the oldest, showed a material decrease.

Of the 26 counties producing gold in 1917 in California, 3 yielded no placer gold, and 4 yielded no gold from deep mines. Five counties produced more than $1,000,000 each in gold in 1917 as follows: Nevada, $3,682,947; Yuba, $3,677,673; Amador, $3,664,164; Sacramento, $1,919,581; and Calaveras, $1,471,442. The leading hydraulic mining county was Siskiyou; the greatest producer of gold from drift mines was Placer; the largest producer of gold from dredges was Yuba; and the largest producer of gold from surface or sluicing mines was Siskiyou. The largest increase—$509,950—in gold in 1917, as compared with 1916, was in Yuba County, which was followed by Trinity, with $166,555; Calaveras, $115,322; Placer, $110,286; Sacramento, $85,726; Nevada, $13,069; Medera, $8,608; Fresno, $5,052; Amador, $3,614; Humboldt, $1,807; and Del Norte, $968. The counties which showed a decreased output of gold in 1917, as compared with 1916, were as follows: Tuolumne, $547,152; Sierra, $339,828; Eldorado, $337,063; Butte, $334,960; Kern, $209,190; Shasta, $161,760; San Bernardino, $124,837; Siskiyou, $115,757; Mariposa, $88,422; Mono, $28,044; Imperial, $22,419; Modoc, $2,729; Stanislaus, $12,348; Plumas, $1,430; Riverside, $7,855; and Inyo, $6,328.

Digitized by Google

Mine production of gold in California in 1917, in fine ounces.

County.	Placers.	Deep mines.							Grand total.
		Siliceous ores.	Copper ores.	Lead ores.	Silver ores.	Silver-lead ores.	Zinc ores.	Total.	
Amador	297.84	176,956.09						176,956.09	177,253.93
Butte	44,389.63	225.23						225.23	44,614.86
Calaveras	25,037.35	42,923.38	3,220.27					46,143.65	71,181.00
Del Norte	66.42								66.42
Eldorado	926.77	270.90						270.90	1,197.67
Fresno	120.31	157.61						157.61	277.92
Humboldt	1,039.77	77.01						77.01	1,116.78
Imperial		44.46						44.46	44.46
Inyo		1,315.46	16.01	123.02		4,611.44		6,065.93	6,065.93
Kern	48.38	25,970.21						25,970.21	26,018.59
Madera	27.28	704.00	183.68					887.68	914.96
Mariposa	64.63	15,091.06						15,091.06	15,155.69
Mono		10,112.31						10,112.31	10,112.31
Nevada	791.90	177,370.66						177,370.66	178,162.56
Placer	20,240.15	4,745.83	1,072.96					5,818.79	26,058.94
Plumas	2,574.32	2,514.87	1,294.13					3,809.00	6,383.32
Sacramento	92,799.74	59.99						59.99	92,859.73
San Bernardino	43.54	150.45	7,244.01		6.97	52.00		7,458.43	7,496.97
Shasta	14,054.78	5,187.01	18,254.89					23,441.90	37,496.68
Sierra	2,957.79	15,638.91						15,638.91	18,596.70
Siskiyou	14,661.93	836.45	250.10					1,086.55	15,748.48
Trinity	28,115.16	142.95	865.96					1,008.91	29,124.07
Tuolumne	445.97	15,086.52						15,086.52	15,532.49
Yuba	177,907.43								177,907.43
Merced, Riverside, San Diego, and Stanislaus [a]	12,345.11								12,345.11
Total, 1916	438,956.20	495,581.36	32,402.01	123.02	6.97	4,663.44		532,776.80	971,733.00
	414,847.40	574,515.59	44,644.11	144.55		1,572.96	19.98	620,897.19	1,035,744.59
Increase (+) or decrease (−)	+24,108.80	−78,934.23	−12,242.10	−21.53	+6.97	+3,090.48	−19.98	−88,120.39	−64,011.59

[a] Yield of single mine in each county combined to avoid disclosing separate output.

Digitized by Google

Value and source of placer gold mined in California in 1917.

County.	Hydraulic.	Dredging.	Drift.	Surface placers.	Total.
Amador			$2,408	$3,749	$6,157
Butte		$893,141	13,984	10,490	917,615
Calaveras		499,785	12,378	5,405	517,568
Del Norte	$225			1,148	1,373
Eldorado			8,889	10,269	19,158
Fresno, Kern, Madera, and San Bernardino[a]				4,951	4,951
Humboldt	19,138			2,356	21,494
Mariposa				1,336	1,336
Merced and Stanislaus[b]		254,948		248	255,196
Nevada	7,019		9,351		16,370
Placer		131,250	269,087	18,064	418,401
Plumas	22,321		22,972	7,923	53,216
Sacramento		1,913,504	4,837		1,918,341
Shasta		282,239		8,299	290,538
Sierra	29,710		13,267	18,166	61,143
Siskiyou	101,920	182,855	101	18,213	303,089
Trinity	80,836	496,594	1,654	2,108	581,192
Tuolumne			7,111	2,108	9,219
Yuba	5,934	3,659,211	720	11,808	3,677,673
	267,103	8,313,527	366,759	126,641	9,074,030

[a] Yield of single mine in each county combined to avoid disclosing separate output.
[b] Yield of single dredge in each county combined to avoid disclosing separate output.

From the siliceous ore and tailings the recovery of gold by methods of treatment in California in 1917 was as follows: By amalgamation, 376,089.25 fine ounces, valued at $7,774,455; by cyanidation, 22,649.32 fine ounces, valued at $468,203; by chlorination, 9,100.74 fine ounces, valued at $188,129; from concentrates sent to smelters for treatment, 85,284.79 ounces, valued at $1,762,993. These figures are approximate only, as the smaller operators, many in number, keep no separate accounts and the larger companies do not always segregate the quantities of gold gained by separate systems of treatment.

The 249 productive placer mines in California in 1917 yielded gold valued at $9,074,030, and 27,257 ounces of silver, valued at $22,460, a total value of $9,096,490. The increase in placer gold was $498,373 and the increase in the value of silver was $2,976. In production of gold the dredge properties showed an increase of $544,300, the hydraulic mines a decrease of $122,912, the drift mines an increase of $115,462, and the surface or sluicing mines a decrease of $38,477.

SILVER.

The deep mine production of silver in California in 1917 was 1,748,174 ounces, valued at $1,440,495, a decrease in quantity of 786,569 ounces and in value of $227,366. The larger portion of the output, 1,524,109 ounces, valued at $1,255,865, was derived from crude smelting ores. Siliceous ores, milled and smelted, yielded 139,492 ounces, valued at $114,941. The largest output of silver in 1917 came from Inyo County (not from Shasta as has been usual for years), which produced from copper ores 661 ounces, valued at $545; from siliceous ore, 550 ounces, valued at $453; from lead ores, 164,115 ounces, valued at $135,231; from silver-lead ores, 483,431 ounces, valued at $398,347; and from zinc ores, 28 ounces, valued at $23. This makes a total yield of silver from Inyo County of 648,785

Digitized by Google

ounces, valued at $534,599. Shasta County followed Inyo in yield of silver, the output being 631,921 fine ounces, valued at $520,703, as compared with 1,695,245 ounces in quantity and $1,115,471 in value in 1916. The total silver derived from deep mines of all classes and from placer mines in California in 1917 was 1,775,431 ounces, valued at $1,462,955. The silver obtained from refining placer gold mined in the State in 1917 was 27,257 ounces, valued at $22,460. The largest producer of placer silver was Yuba County—7,999 ounces, valued at $6,591.

Silver, lead, and silver-lead mines are more numerous and productive since the advance in the price of silver. Silver derived from purely silver ores in 1917 amounted to 8,378 fine ounces, valued at $6,903. From 63,999 tons of silver-lead ores there was derived 552,641 fine ounces of silver, valued at $455,376, as well as $96,402 in gold; from 28,080 tons of lead ore was obtained 165,155 ounces of silver, valued at $136,088; and from 135 tons of zinc ore, the silver yield was 28 ounces, valued at $23.

Mine production of silver in California in 1917, by sources, in fine ounces.

County—	Placers.	Deep mines.							Grand total.
		Siliceous ores.	Copper ores.	Lead ores.	Silver ores.	Silver-lead ores.	Zinc ores.	Total.	
Amador	23	25,885	12					25,897	25,920
Butte	3,367	263						263	3,630
Calaveras	2,438	8,078	96,261					104,339	106,777
Del Norte	10								10
Eldorado	69	34						34	103
Fresno	7	344						344	351
Humboldt	112	4						4	116
Imperial		6						6	6
Inyo		550	661	164,115		483,431	28	648,785	648,785
Kern	4	6,067			3,411			9,478	9,482
Madera	2	58	533					591	593
Mariposa	5	3,540	364					3,904	3,909
Mono		6,871						6,871	6,871
Nevada	51	63,462						63,462	63,513
Placer	1,647	2,240	12,964					15,204	16,851
Plumas	143	337	89,885					90,222	90,365
Sacramento	5,434	11						11	5,445
San Bernardino	2	533	35,838	1,040	1,301	69,210		107,922	107,924
Shasta	1,286	9,674	617,295		3,666			630,635	631,921
Sierra	199	1,778						1,778	1,977
Siskiyou	1,421	235	18,833					19,068	20,489
Trinity	2,340	34	9,788					9,822	12,162
Tuolumne	25	9,450						9,450	9,475
Yuba	7,999								7,999
Merced, Riverside, San Diego, and Stanislaus[a]	673	38	46					84	757
	27,257	139,492	882,480	165,155	8,378	552,641	28	1,748,174	1,775,431
Total, 1916	29,611	171,600	1,969,783	2,129	7,599	323,339	60,293	2,534,743	2,564,354
Increase or decrease	−2,354	−32,108	−1,087,303	+163,026	+779	+229,302	−60,265	−786,569	−788,923

[a] Yield of single mine in each county combined to avoid disclosing separate output.

From the siliceous ore and old tailings treated in California in 1917 the recovery of silver by amalgamation was 83,142 ounces, valued at $68,508; by cyanidation, 29,937 ounces, valued at $24,668; by chlorination, 283 ounces, valued at $233; and from concentrates sent to smelters, 110,705 ounces, valued at $91,221. From smelting ores silver was recovered amounting to 1,524,109 fine ounces, and valued at $1,255,865. These figures do not include the comparatively small quantity of silver recovered from the gold in placer mining operations.

Digitized by Google

COPPER.

The mine production of copper in California in 1917 was 48,153,139 pounds, valued at $13,145,807, a decrease of 7,743,979 pounds in quantity and $604,884 in value from the production of 1916. Copper was produced in Amador, Calaveras, Fresno, Imperial, Inyo, Kern, Madera, Mariposa, Placer, Plumas, Riverside, San Bernardino, San Diego, Shasta, Siskiyou, Trinity, and Tuolumne counties. The largest production came as usual, from Shasta County, which produced 26,658,879 pounds, valued at $7,277,874, a decrease of 13,100,593 pounds in quantity and of $2,502,956 in value, as compared with 1916. Altogether, in the State, there were 892,579 tons of copper ore treated in 1917, or 41,143 tons less than in 1916. The smelting plant of the Mammoth Copper Co., at Kennett, Shasta County, is the most extensive in the State. It not only handles its own copper ores, but those of some other large copper-producing mines in the county. The Mountain Copper Co., Keswick, Shasta County, ships ores and concentrates from its mines 250 miles by rail to its smelter at Martinez, on San Francisco Bay. The ore of the Engels copper mine and some other mines in Plumas County is concentrated by the flotation process and the concentrates are shipped to smelters in Salt Lake City, Utah. The Calaveras Copper Co., Calaveras County, also concentrates its ores by flotation and ships concentrates to smelters. The Penn Mining Co., Calaveras County, has a 200-ton smelter and ships blister copper. A number of smaller mines in other counties having no reduction works of their own ship their ores to smelters. The copper ores of California in 1917 yielded, in addition to the copper, 32,402.01 fine ounces of gold, valued at $669,809, and 882,480 ounces of silver, valued at $727,164.

LEAD.

The mine production of lead in California in 1917 was 21,868,628 pounds, valued at $1,880,702, as compared with 12,407,493 pounds, valued at $856,117, in 1916. From lead ore was obtained also 123.02 fine ounces of gold, valued at $2,543, and 165,155 fine ounces of silver, valued at $136,088. The total value of the output from the lead-mining industry of the State in 1917 in lead and contained value of gold and silver was $1,129,811, as compared with $860,508, in 1916. This refers to ores classified as lead ores only, and does not include gold and silver obtained from ores classified as silver-lead. The silver-lead ores produced 4,663.44 fine ounces of gold, valued at $96,402, and 552,641 fine ounces of silver, valued at $455,376. The total value of the output from the silver-lead mines of the State in 1917 in lead and contained value of gold, silver, copper, and zinc, was $2,187,900.

ZINC.

The mine production of recoverable zinc in California in 1917 was 10,872,716 pounds, valued at $1,109,017, as compared with 15,256,485 pounds, valued at $2,044,369, in 1916, a decrease for 1917 of 4,383,769 pounds in quantity and of $935,352 in value. The zinc output of the State in 1917 was from the counties of Shasta, Inyo, Siskiyou, San

Digitized by Google

Bernardino, Amador, and Calaveras, in the order named. Arrangements are being made for a much larger output of zinc in the State, especially in Shasta County.

PRODUCTION BY COUNTIES.

AMADOR COUNTY.

Amador County continued in 1917 to lead all the other counties of California in quantity of ore produced and treated with 804,875 tons, exceeding the next county in rank, Calaveras, by 208,051 tons. Amador ranked third in the production of gold, being displaced in rank by Nevada and Yuba counties in 1917. The gold produced in Amador County in 1917 was valued at $3,664,164, the silver at $21,358, the copper at $650, and the zinc at $787. There were 14 producing deep mines in the county in 1917 and 4 placers. The quantity of ore decreased for the year but there was a small increase in the quantity of gold produced.

Of the total output of ore 23 tons of copper ore were shipped to smelters and 798,952 tons were treated at gold and silver mills. From this milling ore $2,223,613 in gold, and 17,044 ounces of silver, valued at $14,044, were saved as bullion, and 18,456 tons of concentrates were obtained, which yielded $1,422,404 in gold and 8,608 ounces of silver, valued at $7,093. The value of the total gold and silver from milling ore was $3,667,154, or $4.589 a ton. Some 5,900 tons of tailings were also worked, yielding $11,990 in gold and 233 ounces of silver, valued at $192, a total of $12,182. The ore shipped to the smelters yielded no gold, but yielded 10 ounces of silver, valued at $8, in addition to the copper and zinc. The increase of gold from placers was $1,544 in 1917, as compared with 1916. The total increase in values of all metals in the county for the year was $6,107.

There are four important producing deep mines at or near Amador City. The Bunker Hill Consolidated is opened by an incline shaft 2,900 feet deep and drifts on various levels. The reduction works consist of a 40-stamp mill with Deister Overstrom tables, tube mill, and vanners. Five Deister tables and a ball mill were added to the equipment in 1917. The Darrow Leasing Co., which treats tailing from the Bunker Hill mill, moved and rebuilt its plant in 1917. This plant concentrates 400 tons of tailing to approximately 5 tons. The slime tailing is concentrated and the concentrate cyanided by agitation. The Keystone Mines property is opened by an incline shaft 2,960 feet deep and 5,500 feet of drifts, 900 feet of which were cut in 1917. The mine is equipped with a 40-stamp amalgamation and concentration mill, concentrates being shipped to the smelter. The mine of the Original Amador Consolidated Mines Co. is opened by an incline shaft 1,270 feet deep, and 21,627 feet of drifts, raises, and crosscuts. The shaft was sunk 305 feet deeper in 1917 and 1,627 feet of drifts and raises were made. The equipment consists of a 250-ton amalgamating and concentrating mill and an 8-ton cyanide plant for concentrates. Ore is crushed by one ball mill and one pebble mill and the concentrates are cyanided after the pulp has been run over the amalgamating plates. The Treasure Mining Co. mine is opened by a vertical shaft 1,600 feet deep and a winze of 700 feet. The reduction

Digitized by Google

plant consists of a 120-ton ball mill, with regrinding, amalgamation, and concentrating appliances. All these mines at Amador City were operated the entire year. The Fremont Consolidated Mining Co., at Drytown, includes the Gover, North Gover, Loyal Lode, and Fremont mines, all being worked as one property. The property is operated through two incline shafts, 1,550 and 2,800 feet deep, respectively. The reduction equipment consists of a 40-stamp amalgamation and concentration mill in which the ore is crushed wet and concentrated on Frue vanners; the tailings and slimes are treated by the California Slimes Consolidated Co. at the mine. The concentrates are shipped to a smelter. The Ione Coal & Iron Co., at Ione, produced a small quantity of copper and silver.

In and around Jackson and Sutter Creek are the most important of the Mother Lode mines in the State. The Argonaut at Jackson is opened by an incline shaft 4,700 feet deep, with the usual drifts, crosscuts, and raises. During 1917 the old 40-stamp mill was abandoned and a new 60-stamp amalgamating and concentrating mill completed. The concentrates obtained are shipped to a smelter. The Kennedy Mining & Milling Co. has the deepest vertical shaft in the State—4,012 feet, of which 46 feet was sunk in 1917. The property is equipped with a 100-stamp amalgamation and concentration mill and one of the few chlorination plants in the State for treatment of the concentrates. At Sutter Creek the Central Eureka is developed by an incline shaft 3,425 feet deep, and by 5,000 feet of drifting from the 2,540 level down. The reduction equipment consists of a 40-stamp amalgamation and concentration mill, concentrates being shipped to a smelter. The South Eureka is developed by an incline shaft 2,730 feet deep and a vertical shaft of 2,260 feet in depth; there are also two winzes, respectively, 400 and 450 feet, with many drifts and crosscuts. The reduction plant consists of an 80-stamp mill and concentrators at the South Eureka mine and 25 stamps and 11 concentrators at the Oneida mine, a continuation of the South Eureka under the same management.

At Plymouth is the extensive property of the Plymouth Consolidated Gold Mines (Ltd.), owned by English capitalists. The mine is developed by a vertical shaft to the 1,600-foot level and thence by incline (60-foot) in the footwall to the 2,600-foot level. Considerable development was done during 1917. The reduction plant consists of a 30-stamp mill, with Hardinge mills, amalgamating and concentrating in two sizes, regrinding and reamalgamating tailings. The concentrates are sent to a smelting plant. Seventy-five per cent of recovery values is due to free milling operations, and 25 per cent is in the sulphides. A plant for regrinding tailing was added in 1917. In that year the mill extracted $3.72 a ton by amalgamation and $1.56 by concentration, a total of $5.28, equal to 86.37 per cent of the average assay content of $6.12 a ton. The bullion yield was 32,795 ounces of gold and 7,688 ounces of silver. As the tailing assayed higher than before, due to a change in the character of the ore, two Hardinge mills and more copper plates were added. Costs were 46 cents for development, $2 for mining, 38 cents for milling, 24 cents for bullion and concentrate expenses, and 31 cents for maintenance and general expense, a total of $3.39 a ton.

A little placer gold was derived from small mines in this county at Plymouth and Volcano.

Digitized by Google

BUTTE COUNTY.

In 1917 there were 26 mines reporting production from Butte County. Only 349 tons of ore were reported from deep mines, nearly 1,600 tons less than in 1916. The total gold output of the county in 1917 was $922,271, a decrease of $334,960, as compared with 1916. The total value of gold and silver produced in the county in 1917 was $925,262, a decrease of $335,301. The 11 dredges in the county recovered gold valued at $893,141, which was $317,733 less than 14 dredges produced in 1916. The number of dredges operating was three less than in 1916, several having worked out their available ground and ceased operations. The few drift mines produced $1,980 more gold than 1916; and the surface or sluicing mines $4,879 less gold. The total gold output from placers of all kinds was $917,615, as compared with $1,238,247 in 1916, a decrease of $320,632. The output of deep gold mines in gold was $4,656, a decrease of $14,328 from 1916. Butte County, formerly the leading producer for many years in dredge gold, is now third in rank in this respect, being now exceeded by both Yuba and Sacramento counties.

In 1917 the Oroville district proper yielded from dredging operations $717,782 in gold, which was $252,627 less than in 1916. The following table shows the output of gold from the Oroville dredging field for several years, with the annual increase or decrease:

Mine production of gold of Oroville dredging district, California, 1903–1917, with increase or decrease, by years.

Year.	Production.	Increase or decrease.	Year.	Production.	Increase or decrease.
1903	$1,329,998		1911	$1,987,294	−$112,334
1904	1,632,507	+$302,509	1912	2,080,229	+ 92,935
1905	2,261,887	+ 629,380	1913	1,918,050	− 162,179
1906	2,768,782	+ 506,895	1914	1,422,407	− 495,643
1907	2,697,092	− 71,630	1915	1,171,315	− 251,092
1908	3,043,151	+ 346,059	1916	970,409	− 200,906
1909	2,743,232	− 299,919	1917	717,782	− 252,627
1910	2,099,628	− 643,604			

The combined dredges in the county in the Honcut and Butte Creek fields, outside of Oroville district, yielded $175,359 in gold, as compared with $240,465 in 1916.

In 1917 the following dredges were operating in the Oroville field, each with one machine unless otherwise noted: Natomas Co. of California (3), Oroville Dredging Co. (Ltd.), (2), American Gold Dredging Co. (formerly Oro Water, Light & Power Co.), Pacific, and Oroville Union. The last named company has worked out its ground.

The companies producing at Butte Creek and Honcut, outside the Oroville district, are the Pacific, Honcut, and Kentucky Ranch.

Smaller placers were more or less productive at Bangor, Cherokee, Chico, Enterprise, Magalia, Nimshew, Oroville, and Stirling City.

The small producing deep mines of the county are the Springer Consolidated, at De Sablo; Crystal Peak and the Edel, at Enterprise; and California Gold Mines Co., at Oroville.

Digitized by Google

CALAVERAS COUNTY.

Calaveras, one of the Mother Lode counties, had a production of 596,824 tons of ore in 1917, an increase of 78,644 tons over 1916. The total yield of gold for the county in 1917 was $1,471,442, an increase of $115,322, as compared with 1916; of silver 106,777 ounces, valued at $87,984, a decrease of 20,340 ounces; and of copper, 8,052,978 pounds, an increase of 1,592,685 pounds. The total value of all metals increased by $729,176 in 1917, as compared with 1916. The value of the output of copper in the county in 1917 was $2,198,463, as compared with $1,589,232 in 1916, an increase of $609,231. In 1917 producing mines to the number of 33 reported—12 deep gold mines, five copper mines, five gold dredges, seven drift mines, and four surface placers. From the placers gold recovered by dredges in 1917 amounted to $499,785, an increase over 1916 of $201,305; that from drift mines was $12,378, a decrease of $15,985; and that from surface placers was $5,405, a decrease of $1,860.

The average value per ton of 352,641 tons of milling ore treated at gold and silver mills in the county in 1917 was $2.35 in gold and silver, compared with $2.32 in 1916. This very low average, which has persisted for several years, materially reduces the average value per ton of the five Mother Lode counties when considered as a whole. It is due to the fact that in one large mine development work has been carried on in search of profitable ores, at lower levels, when it was known that the ore mined during the year was of too low a grade to pay for mining and milling. The quantity of ore sold or treated in Calaveras County in 1917 was 596,824 tons, which yielded gold valued at $953,874; 104,339 fine ounces of silver, valued at $85,975; and 8,052,978 pounds of copper, valued at $2,198,463. The placer output was $517,568 in gold, and 2,438 ounces of silver, valued at $2,009. The output of the county in 1917 in gold, silver, copper, lead, and zinc, was $3,758,171.

There were 352,641 tons of ore treated at gold and silver mills, from which was obtained $473,205 in gold in bullion and 4,720 ounces of silver, valued at $3,889. The total saving in bullion was valued at $477,094, or $1.35 a ton. From the 352,641 tons of ore directly milled and 148,690 tons of ore sent to concentrating plants were obtained 26,299 tons of concentrates yielding $349,574 in gold and 4,734 ounces of silver, valued at $3,901, an average in gold and silver of $13.44 a ton. The recovery of copper from ore concentrated was 3,432,904 pounds. There were 40,503 tons of smelting ore sold or treated yielding $65,660 in gold and 94,774 fine ounces of silver, valued at $78,094, or $3.55 a ton in gold and silver; and 4,620,074 pounds of copper, valued at $1,261,280. The total value of the smelting ore was $1,405,316, or $34.70 a ton. In addition there were treated 54,990 tons of old tailings yielding $65,435 in gold and 111 ounces of silver, valued at $91, a total of $65,526, or an average of $1.19 a ton.

The Angels Quartz Mining Co., at Angels, again became productive in 1917, after some time spent in opening old ground. The Royal Gold Mines, after some years of idleness, were reopened and became productive. The Utica Mining Co. is the largest producing property at Angels, ore coming from both the Utica and the Gold Cliff claims. This property is opened by three shafts, one 1,400 feet, one 2,900

Digitized by Google

feet, and one 2,700 feet deep. There are two mills on the property, one of 60 and one of 40 stamps, using amalgamation and concentration; the concentrates are shipped to a smelter. The most productive mine in the county is that of the Penn Mining Co., at Campo Seco, a copper mine yielding also largely in gold and silver. This mine is opened by an incline shaft 2,900 feet deep. The equipment consists of a 200-ton smelter, where the crude ore is smelted, and whence blister copper is shipped to the American Metal Co., New York. The Tullock is a small gold mine at Carson Hill. The extensive property of the Calaveras Copper Co. is at Copperopolis. It is opened by one incline shaft 740 feet deep, one incline shaft 896 feet deep, and one vertical shaft 140 feet deep. Development work in 1917 consisted of 470 feet of shaft sinking, 2,430 feet of drifts, and 490 feet of adits. The reduction plant is a concentration mill consisting of one Allis-Chalmers and two Hardinge ball mills and other equipment, which has a capacity of 600 tons daily. The crude ore is treated by the oil flotation process and the concentrates are shipped to a smelter at Tacoma, Wash. During 1917 the discovery shaft was extended to the tenth level and a new shaft was started on the North Keystone Claim, which was sunk 140 feet and drifts started. In addition to company work considerable ore was mined by lessees at this mine. The Plymouth Rock, at Jenny Lind, is opened by two small shafts and about 1,000 feet of drifts. Only a few carloads of ore were shipped during the year, although continuous development has been going on. The Melones Mining Co. operates one of the larger of the Mother Lode mines, at Melones. The property is opened by an adit 5,000 feet long and an incline winze 2,000 feet deep. About 2,300 feet of development work was accomplished in 1917. The reduction plant consists of a 100-stamp amalgamating, concentrating, and cyaniding mill. The process consists of amalgamation, concentrating on Wilfley tables, classification sands to leaching tanks, slimes to Dorr dewaterer, Devereux agitators, and Oliver filter, concentrates being ground in tube mills and cyanided in Devereux agitators. The Carson Hill gold mines, also at Melones, are opened by an adit 2,160 feet long. During 1917 the company did 200 feet of sinking, 1,200 feet of drifting, 250 feet of crosscutting, and 1,000 feet of raising. There are two amalgamating and concentrating mills on the property, one of 3 and one of 10 stamps, which were only in operation a part of the year. The Copper Crescent is a small copper mine producing near Milton. The Napoleon copper mine, also near Milton, is opened by a 250-foot shaft. There is a 50-ton flotation plant on the property and the concentrates are shipped to the smelter at Tacoma, Wash. The Quail Hill Mining Co. is working a copper mine in the same vicinity and has a 270-foot vertical shaft. Shaft sinking and drifting were done in 1917. The company has no plant in operation, but shipped crude ores to the Mammoth Copper Co. and to the Tacoma Smelting Co. The Pacific Gold Mining & Milling Co. (formerly the Mokelumne Mines Co.) has its property at Mokelumne Hill. The mine is opened by an adit 2,000 feet long and a vertical shaft 190 feet deep and 1,500 feet of lateral work from the shaft. In 1917 2,359 feet of development work was done. There is an amalgamation and concentration plant of 100 tons daily capacity. The ore is crushed in a ball mill to 20

Digitized by Google

mesh, and amalgamation is followed by table concentration. Concentrates are shipped to the smelter on San Francisco Bay. The metallurgical plant was idle for two months of the year while the shaft was being sunk. The Comet and Josephine are small gold mines at Railroad Flat; and the Deer Foot and Newman are small gold mines at West Point.

The most important placers in the county are those operated on Mokelumne River by the American Gold Dredging Co., the successor of the old Oro Water, Light & Power Co. The work is being done on low bench gravel. Three dredges are operated by this company in the vicinity of Camanche. As a matter of fact, however, all these dredges are not in Calaveras County, but their combined output is reported as from Camanche and is so considered in this report. No. 1 dredge is on the river 2 miles from Camanche, in Calaveras County; No. 2 is 7 miles from Camanche in San Joaquin County; and No. 3 is 4 miles from Camanche, in Amador County. The Butte Dredge Co. operated a dredge on stream gravel in Calaveras River near Jenny Lind for 322 days in 1917 and then shut down finally. The Ivy L. Borden Co. began operating a dredge on stream and bench gravel near Jenny Lind in June, 1917. Small placer mines produced more or less gold at Angels, Camanche, Jenny Lind, Mountain Ranch, Railroad Flat, San Andreas, and Sheep Ranch. The Stockton Ridge Consolidated Mining Co. operated a drift mine for some months at Mokelumne Hill, but expenses due to war condition caused a permanent shut down there, and at other mines in the vicinity. The Oneta and Steward placers both made small outputs at San Andreas, as did the Vandalia, at Sheep Ranch.

DEL NORTE AND HUMBOLDT COUNTIES.

In Del Norte County the Salt Lake & California Copper Co. made a small output of copper at Smith River. Most of the productive placers are small ones at or near Crescent City. These are the Craigs Creek, French Hill, Myrtle Creek, and a few smaller sluicing claims.

In Humboldt County the only deep mine reporting was the Prospect Hill Co., at Orleans, which has a 2-stamp mill. At Orleans are the Croton Bar hydraulic, Jungle sluicing mine, Reynolds Creek hydraulic, Rocky Bar hydraulic, and sundry smaller placers. At Weitchpec the Klamath River Mining Co. is sluicing in ancient river beds and the Weitchpec Bar mine is hydraulicking. There are some smaller placers at this place also.

ELDORADO COUNTY.

Eldorado is one of the five Mother Lode counties of California, but its mining activities are by no means so great as formerly and no extensive deep mining operations are now being conducted in the county. The placer mines also are less productive and very much less in number than in the past. The principal reason for the very marked falling off in output of gold is the fact that the Pacific Gold Dredging Co., formerly working on the Eldorado side of American River, was in 1917 working on the Placer County side, so that its output is properly credited to Placer County instead of to Eldorado, as formerly. There is not a single deep mine of any productive

Digitized by Google

prominence now at work in the county, whereas there were formerly several.

The output of gold of the county in 1917 was only $24,758 as compared with $361,821 in 1916, and that of silver was valued at $85, as compared with $1,496 in 1916. There was a decrease of 9,988 tons of ore treated and a decrease of $337,063 in gold and of 2,170 ounces of silver. The decrease in total value of metallic output of the county in 1917, as compared with 1916, was $338,474, which is the greatest percentage of loss in any county in the State. The ore treated at gold and silver mills, amounting to 2,506 tons, yielded bullion valued at $3,083, or an average per ton of $1.23 in gold and silver, as compared with an average of $4.89 per ton in 1916. There were 66 tons of concentrates derived from the milling ore, which yielded $2,545, or $38.57 a ton in gold and silver, as compared with $46.94 a ton in 1916. The milling ore yielded in bullion and concentrates a total value of gold and silver of $5,628, or $2.25 a ton, as compared with $74,370, or $6.09 a ton in 1916.

The placer mines of the county yielded $19,158 in gold, and 69 ounces of silver, valued at $57, as compared with $284,930 in gold and 1,588 ounces of silver, valued at $1,045, in 1916. There were 14 mines (11 placer and 3 deep mines) of the county which reported production, as compared with 25 mines in 1916.

The Marigold & Frog Pond Consolidated mines, at Garden Valley, crushed a few hundred tons in its 2-stamp mill in 1917. There was also a small output from the Morning Star and Lucky Boy, at Georgetown. The mine of the Guildford Gold Mining Co., at Placerville, was the only deep producing mine of any note in the county, and this was operated for only three months of the year.

Of the placers the Blue Rock in the Georgia Slide district, near Georgetown, carried on drifting operations for seven months of the year. A few small placers were producers in the same region. A small output was made from the Grizzly Flat drift gravel mine, at Grizzly Flat, and from the Jinkerson drift mine, at Indian Diggings. A few small placers were worked at Omo Ranch. At Placerville the placers operated productively were the Live Oak, and the Rising Hope. The Deadman Flat ground sluicing placer, and the Friedman, made a small output at Rescue, and there were a few producing placers at Shingle. The Fort Jim drift mine, at Smith Flat, made a nominal yield.

INYO COUNTY.

In 1917 there were 37 producing deep mines in Inyo County. Of these mines 4 were gold, 4 copper, 16 silver-lead, 11 lead, and 2 zinc. The total value of the metallic output for the year was $2,956,669, or $971,056 more than in 1916. The value of the gold was $125,394, or $6,328 less than in 1916. The silver yield amounted to 648,785 ounces, valued at $534,599, making this county the first in rank of output of silver in the State, displacing for the first time in many years Shasta as the leading silver county. The increase in the yield of silver in Inyo County in 1917, as compared with 1916, was 295,531 fine ounces in quantity and $302,158 in value. The output of copper in 1917 was 737,582 pounds, valued at $201,360, an increase in quantity of 531,436 pounds and in value of $150,648. The output of lead

Digitized by Google

in the county was 19,671,732 pounds, valued at $1,691,769, as compared with 11,497,015 pounds, valued at $793,294, an increase in quantity of 8,174,717 pounds and in value of $898,475. The production of zinc in 1917 was 3,956,343 pounds, valued at $403,547, a decrease in quantity of 1,845,478 pounds and in value of $373,897, as compared with 1916.

There were sold or treated in 1917 in Inyo County 84,354 tons of ore, of which 2,169 tons were siliceous ore, 382 tons copper ore, 27,714 tons lead ore, 53,954 tons silver-lead ore, and 135 tons zinc ore. The deep mines in 1917 yielded gold valued at $125,394 and 648,785 ounces of silver, valued at $534,599. Of the gold 1,315.46 fine ounces, valued at $27,193, was obtained from siliceous ore, $331 from copper ore, $2,543 from lead ore, and $95,327 from silver-lead ore. The production of silver from siliceous ore was 550 fine ounces, valued at $453; from copper ores 661 fine ounces, valued at $545; from lead ores 164,115 fine ounces, valued at $135,231; from silver-lead ores, 483,431 fine ounces, valued at $398,347; and from zinc ores 28 fine ounces, valued at $23. The siliceous ore, therefore, yielded $27,646 in gold and silver; the copper ores $876; the lead ores $137,774; the silver-lead ores $493,674; and the zinc ores $23; a total of $659,993 in gold and silver.

At Big Pine the Base Metals Mining Co. is working a lead mine. At the same place ore from the Fish Springs Hill mine was worked in an arrastre and also shipped to smelters at Salt Lake City, Utah. The Roberts mines are producing silver-lead ore which is shipped to Nevada. On this property there are three shafts each about 125 feet deep. The Montezuma is a silver-lead mine, with ores of low grade. At Darwin lead ores were produced by the Argus Sterling Mining Co. The Christmas Gift, a silver-lead property, is opened by a 255-foot incline shaft and a 150-foot winze. The ores are shipped to smelters at Salt Lake City. The Columbia is a small producer of copper ores, and the Custer Mining Co. produces silver-lead ores. The Coso Mining Co. proluced a small quantity of copper. The silver-lead mines of the Darwin Lead & Silver Mines Development Corporation yield gold, silver, copper, and lead. The Inyo County Mining & Development Co. mines lead ores only, and the same is true of the Rip Van Winkle. Zinc ores mined by the Utacal Exploration Co. were shipped to Salt Lake City. Several small mines at Darwin shipped more or less silver-lead, lead, and copper ores. At Independence the Black Eagle is opened by a 310-foot vertical shaft, and has a 2-stamp mill, and the Golden Star produced some copper ore. The most productive property in the county is that of the Cerro Gordo Mines Co., at Keeler, mainly worked for lead, but producing also largely in zinc and silver, with some gold. The Estelle Mining Co. operates the Consolidated Morning Star group of 41 claims at Keeler. The property is opend by an adit 7,300 feet long, which was extended 190 feet in 1917. Nearly 500 feet of drifts, raises, and winzes were also cut. The working force at the mine was somewhat disorganized by enlistment of men in the United States service. The company owns no reduction plant, but ships its silver-lead ore to a smelter. The Santa Rosa Lead & Silver Mining Co. shipped considerable silver-lead ore containing some copper to the smelters. Other shippers at Keeler were the Spear (lead), San

Digitized by Google

Lucas (copper), Royal Group (silver-lead), and Ygnacio (silver-lead). Ore from the Nellie H., at Lone Pine, is crushed in a horse-power arrastre, but some small shipments of crude ore were made to a smelter. The Reward, at Owenyo, is opened by an incline shaft 300 feet deep, an adit of 800 feet, and 5,000 feet of drifts. During 1917, 723 feet of drifting, 632 feet of crosscutting, and 386 feet of raising was done. The reduction works consist of a 20-stamp concentration-flotation mill, and 10 stamps, and concentrating tables. The process consists of stamping, classifying, tabling, and regrinding in ball mills. Sometimes higher grade ore is shipped to the Selby smelter. The ores carry gold, silver, lead, and copper. Oil flotation gave poor results and tables were added to remove the oxides and carbonates of lead, copper, and iron so as to leave as little as possible in the pulp treated by flotation. The Madison is a small zinc mine at Shoshone. Some gold was shipped from the Skidoo Mines Co., but the property was later closed down. Lead ores were shipped from Tecopa by both the Ore Gulch and Speculator mines, but the principal mine is that of the Tecopa Consolidated Mining Co., which produces lead, silver, and gold. The concentrating plant was burned in June, and in December work was started on a new 100-ton concentrating mill. Considerable ore was shipped to smelters in Utah, The mines owned by the company are the Gunsite, Noonday, Giant, and Columbia. The Slate Range Minerals Co. operated the Copper Queen mine, the nearest post office to which is Trona. The ores carry lead, silver, copper, and gold. The crude ore is sorted and shipped to a smelter at Salt Lake City. The Ophir mine, near Trona, produced silver-lead ores, which were shipped for reduction to smelters at Salt Lake City. The ores of the Carbonate Lead Mines Co., at Zabriskie, carry principally lead and silver, but also contain some copper and gold. From this same vicinity the Blue Mountain and Ibex & Arcturus mines shipped lead ores in 1917, and the Fraser shipped a small quantity of copper ores.

KERN COUNTY.

Nineteen deep mines reported production from Kern County in 1917 and only one placer. The total value of the metallic output of the county decreased from $760,707 in 1916 to $616,645 in 1917. The total production of gold was $537,852 in 1917, as compared with $747,042 in 1916. The silver output in 1917 was 9,482 ounces, valued at $7,813, as compared with 13,290 ounces, valued at $8,745, in 1916. Copper to the amount of 260,000 pounds, valued at $70,980, was produced in 1917, as compared with 20,000 pounds, valued at $4,920, in 1916.

There were treated or sold 125,649 tons of ore in 1917, of which 123,140 tons were siliceous ore, 2,417 tons copper ore, and 92 tons of silver ore. A total of 123,140 tons were sent to gold and silver mills, and 2,509 tons to the smelters. The yield in bullion from the ore treated at gold and silver mills was $532,880 in gold and 5,949 ounces of silver, a total bullion value of $537,782 in gold and silver, and an average value per ton of $4.36. No concentrates were derived from this ore. From the 2,509 tons of ore sent to smelters there was obtained $4,795 in gold and silver, or an average of $1.91 a ton. In addition, the 2,509 tons of ore sent to the smelters yielded 260,000

Digitized by Google

pounds of copper. The total yield of the county in gold, silver, and copper from the deep mines was $615,642, an average of $4.90 a ton. The single placer made a nominal production of gold.

The Glen Olive mine at Bodfish, worked under lease, produced a small quantity of gold, as did the Early Sunrise mine at Isabella. The Mammoth Mountain mining property at the same place, is opened by a 4,000-foot adit and a vertical shaft of 210 feet. Prospecting for an ore body was carried on much of the time. The mine is equipped with a 10-stamp mill, but only a small output was made. The Keys Mining & Milling Co., which has a 5-stamp mill, is opened by an adit of 900 feet, a vertical shaft of 325 feet, and some 1,200 feet of drifts. The Shipsey Mining Co., operating the King Solomon group of mines at Johannesburg, has on its property three incline shafts from 100 to 450 feet deep, and it sunk a 100-foot shaft in 1917. There is a small mill on this property. The Zenda Mining & Milling Co. worked a mine producing silver ore only. The Trio Mining Co., Mojave, operated to July 10, 1917, and then closed. On this mine is a 10-foot Layne mill with Senn concentrators. The Black Hawk group, at Randsburg, was worked by the Yellow Aster Mining Co. under option after May, 1917. The Butte Lode Mining Co., at Randsburg, made some output of gold. The Consolidated Mines Co., after making a small output, discontinued work in the mine. The Pay Day, Santa Ana, and Windy, at Randsburg, each made a small output. Several lessees worked on the Royal Bohee. The most important of the gold producers at Randsburg, as for many years, was the Yellow Aster group. Though worked last year mostly from the "glory hole," this property has about 8 miles of tunnels, shafts, and drifts. The mine was operated for about nine months during 1917 and then closed down to hasten the building of the crushing and screening plants. There is a 100-stamp mill on the property, which uses the amalgamation process only with no concentrating. The Tropico Mill & Mining Co., at Rosamond, added 100 feet to its 600-foot incline shaft and straightened the shaft. Mill work was suspended during this time. There is a 10-stamp mill and a 35-ton cyanide plant on the property. The Blue Mountain Mining Co., at White River, has a 5-stamp amalgamating and concentrating mill and deepened its shaft 80 feet and ran 800 feet of drifts in 1917. The Weringer Mines Co., at Woody, produced considerable copper ore.

MADERA COUNTY.

Madera County in 1917 produced a total of $135,128 in value of metals, as compared with $53,661 in 1916, an increase of $81,467. The 6,230 tons of ore treated or sold and the few small placers yielded $18,914 in gold; 593 fine ounces of silver, valued at $489; and 423,901 pounds of copper, valued at $115,725, a total of $135,128. Three deep gold mines and 4 copper mines reported production in 1917, and 1 placer mine had a nominal output.

The Kroromick (formerly called the Texas Flat), at Coarsegold, is developed by an incline shaft 900 feet deep, with levels each 125 feet. The mine is equipped with a 20-stamp amalgamation and concentration plant, but only 10 stamps were used during 1917. At the Gambetta mine, Grub Gulch, most of the time in 1917 was spent in installing a transmission line and new equipment. The mine is

Digitized by Google

developed through an 860-foot incline shaft, with some 2,000 feet of drifts. There is a 100-ton ball mill and concentrating plant on the property. The Mud Springs & Keating mine, at O'Neals, made a nominal output in gold. The Buchanan Copper Co. mine, at Raymond, was worked by lessees and the ore was shipped to the Mammoth Copper Co's. smelter at Kennett, Shasta County. Other copper-ore producers near Raymond were the Bussolini, Copper Queen, and Madera County mines. A few small placers at Coarsegold yielded some gold.

MARIPOSA COUNTY.

Mariposa, which is one of the mother lode counties of California, showed a decrease of $119,289 in the value of its total metallic ouput in 1917, as compared with 1916. The total value in 1917 was $326,482; in 1916 it was $445,771. Of the 13 mines reporting production in 1917, 11 were deep mines. The output of ore decreased by 27,125 tons. The output of gold was $313,296 in 1917, as compared with $401,718 in 1916, a decrease of $88,422. The silver output decreased 164 ounces and the copper decreased 131,681 pounds.

The deep mines of the county produced 41,876 tons of ore, of which 328 tons went to the smelters. The 41,548 tons of ore which went to the gold and silver mills yielded $268,471 in gold as bullion, and 2,387 ounces of silver, valued at $1,967, the total gold and silver value of the bullion being $270,438, or an average value of $6.51 a ton. From this ore were also derived 711 tons of concentrates, which yielded $41,008 in gold and 982 ounces of silver, valued at $809, a total of $41,817. The yield of the concentrates is thus shown to have been $58.81 in gold and silver a ton. The 328 tons of ore shipped to smelters yielded $2,481 in gold, 535 ounces of silver, valued at $441, and 36,502 pounds of copper, valued at $9,965, an average value per ton for gold, silver, and copper of $39.29. The siliceous ore yielded on the plates and from the concentrates a total value of $312,255 in gold and silver, an average value per ton of $7.51.

A small amount of gold came from the Red Banks property, at Bagby, and a few small properties in that neighborhood. The White Gulch Mining Co. (Virginia mine), at Coulterville, made a considerable output. This property is developed by an incline shaft 700 feet deep, of which 284 feet was sunk in 1917. There are also about 4,800 feet of drifts and crosscuts. The reduction works consist of a 10-stamp amalgamation and concentration mill. The ore is crushed in a Blake crusher and stamped through a 40-mesh screen and then passed over check, lip, and sluice plates, and a 6-foot Union concentrator. The Original, at El Portal, is opened by a 680-foot vertical shaft, a 551-foot adit, and 4,500 feet of drifts. The shaft is in the adit tunnel level and the collar is 185 feet below the surface. Some 1,800 feet of work was done in 1917. On this property is a 10-stamp amalgamating and concentrating mill. The mine was worked throughout the year and the mill was run about eight months. At the Ruth Pierce mine, Hornitos, new electric motors were put in both mine and mill during 1917. There is at the mine a 10-stamp mill with Frue concentrators. Several small mines near Hornitos were worked productively during 1917. The Early, Revel, and Louise mines at or near Jerseydale, made small outputs of gold.

Digitized by Google

The Johnny Green mine, at Lewis, produced some copper ore which was shipped to Tacoma, Wash., and Kennett, Cal. The Mariposa Commercial & Mining Co., at Mount Bullion, did no mining on its own account, but milled some gold ore mined by lessees on its property. The Mountain King mine, at Mountain King, is developed by an adit of 1,600 feet, a vertical shaft of 450 feet, and 6,000 feet of drifts. It is equipped with a 30-stamp amalgamation and concentration mill. The Green Mountain mines, at Raymond, made a small output of copper. The Somersville mine, at Whitlock, made a small yield of placer gold, as did a few mines at Jerseydale.

MONO COUNTY.

The total value of the metal output in Mono County decreased from $240,690 in 1916, to $214,702 in 1917, or $25,988. The decrease in gold was $28,044. The output of silver increased from 5,480 ounces, valued at $3,606, in 1916 to 6,871 ounces, valued at $5,662, in 1917, or 1,391 ounces in quantity and $2,056 in value.

There were 18,090 tons of crude ore treated at the gold and silver mills, which yielded $203,416 in gold, and 5,186 fine ounces of silver, valued at $4,273, a total value of $207,689, or an average value of $11.48 a ton in gold and silver. The average value of this ore per ton in 1916 was $21.18, which accounts for the reduction in total value of output of the county in 1917. No concentrates were reported. There were 686 tons of old tailings treated, which yielded $7,013 in gold and silver, or an average of $10.22 a ton. The total value for the 18,776 tons of ore and tailings was, therefore, $214,702 in gold and silver, or an average value of $11.43 a ton, as compared with the average value in 1916 of $20.90 per ton. The old Standard mine at Bodie, now owned by an individual instead of a company, is still a producer, although by no means so large a one as formerly. There is on this mine a 20-stamp amalgamating mill and 100-ton cyaniding plant. The Serita Mining Co., at Masonic, made a considerable output of gold during 1917.

NEVADA COUNTY.

Nevada County outranked all the other counties of California in the production of gold in 1917, as also in 1916. It is also one of the three counties which exceeded a three-million dollar output of gold, its total yield of gold having been $3,682,947, as compared with Yuba County with $3,677,673, and with Amador County with $3,664,164. The production of gold from deep mines increased $30,599; that from placers decreased $17,530. The average value per ton of ore treated in gold and silver mills in this county was nearly $10 as compared with $8.95 in 1916.

The quantity of ore and old tailings treated in the county in 1917 was 480,869 short tons. There were 22 producing mines that reported, of which 18 were deep or quartz gold mines and 4 placers. The hydraulic mines produced in gold $7,019, and the drift mines $9,351, a total value of $16,370 from the placers. The deep mines produced gold valued at $3,666,577 and silver valued at $52,293, a total value of $3,718,870.

There were 337,596 tons of siliceous ore treated at gold and silver mills. The value of the gold in the mill bullion was $3,292,110, an

Digitized by Google

average value of $9.75 a ton, and the silver output from the same source was 34,432 fine ounces, valued at $28,372, or $0.08 a ton. The total value of the gold and silver recovered in the mill bullion was $3,320,482, an average value of $9.83 a ton. From the milling ore there were obtained 1,096 tons of concentrates which carried $54,175 in gold and 2,238 ounces of silver, valued at $1,844. The total value of the concentrates was $56,019 in gold and silver, or an avereage value of $51.11 a ton. From the 337,596 tons of milling ore there was recovered from both bullion and concentrates $3,346,285 in gold and 36,670 ounces of silver, valued at $30,216. The total value of the gold and silver recovered from bullion and concentrates was $3,376,501, the average value per ton being $10 in gold and silver. There were 143,273 tons of tailings treated, yielding $320,292 in gold and 26,792 ounces of silver, valued at $22,077. Doubtless a large proportion of this quantity was not "old" tailings, but those treated at once after the ordinary milling process was completed and before being allowed to pass away into the streams or impounding dams. They were simply reported as "tailings" with the resultant yield.

At the Republic Mining & Milling Co., Graniteville, no development work was done on account of the high cost of powder and other supplies. Only a small quantity of ore was milled. There is a 10-stamp mill on the property and a 6-foot Huntington mill was added during the year. Very little was done at the Ben Harrison mine, Grass Valley, but some development work was carried on. At this mine there is a 10-stamp amalgamation and concentration mill. On the mine of the Brunswick Consolidated Gold Mining Co. there is one vertical shaft of 1,350-foot depth and an incline shaft of 1,250 feet with several miles of drifts. The property is equipped with two 20-stamp amalgamation and concentration mills, the concentrates being sent to a smelter. At the mine of the Central Consolidated Mining Co. a small crew carried on work until July when the mine was put in the hands of lessees. This mine is opened by an adit 1,000 feet in length and an incline shaft of 500 feet, with some 9,000 feet of drifts. There is on the property a 20-stamp amalgamation and concentration mill. The Empire Mines Co., one of the most productive of the deep-mine operators of the State, worked the Empire mine and Pennsylvania Shaft as one property. There are two incline shafts, one 5,000 feet deep and one 2,600 feet deep. The reduction equipment consists of one 60-stamp mill and cyanide plant and one 20-stamp mill and cyanide plant. The mine was worked continuously through the year. The Golden Center of Grass Valley Mining Co. sunk 120 feet of shaft and did 1,674 feet of drifting during the year, but struck a bad flow of water in July which partly flooded the shaft. The company is working the old Dromedary location, which was worked from the surface as far back as 1855. The property is equipped with a 20-stamp amalgamation and concentration mill. The North Star Mines is one of the most important of the deep gold producers of California, and its mill is provided with an extensive cyanide plant. During the year the Central mill was equipped with sixty 1,500-pound stamps and the Central cyanide plant was enlarged to perform the work formerly done by two 40-stamp mills and separate cyanide plants. After working until May the old North Star mill was dismantled. The yield per ton of ore crushed in 1917 was

Digitized by Google

$1.01 more than in 1916, but the cost per ton of operation was $1.15 more than in 1916, principally due to increased cost of supplies. The total cost per ton of operation and development together in 1917 was $7.19, as compared with $6.26 in 1916. Of the total production of $1,148,684 in 1917, 82.06 per cent was obtained in the mills by amalgamation, and 17.94 per cent was recovered by cyanidation. It is estimated that the value lost in the tailings was about 40 cents per ton of ore crushed. According to the published annual report the profit for the year was $426,260 and dividends amounting to $250,000, or 10 per cent on the capital stock, were paid during the year, making $5,337,040 to date. No development work was done below the 4,400-foot level. This company owns the Champion group of mines at Nevada City, which was also operated throughout the year but without very much encouragement. The production was $188,329, which resulted in a deficit. During the year 41,650 tons of rock were crushed, yielding $4.52 per ton. The rock came from the 2,700-foot level of the Champion and Providence veins. Some fair ore has been developed above the 2,700-foot level in the Providence which shows signs of improvement in depth. The Union Hill mines made a small output during the year.

At Nevada City are several producers, among them the Montana Relief Hill, and Bear Valley Mining Co. The Oustamah has diverted its mill to the crushing and concentration of chrome ores. The Black Bear Mining Co., at Rough and Ready, with a 10-stamp mill, made a small output. The Columbia Consolidated Mining Co., at Washington, got its property equipped and opened in 1917, and made a small production. The Gaston Gold Mining Co. has a 10-stamp mill doing amalgamation only, no concentrates having been produced. Several of the mills at Washington are now at work concentrating chrome ores instead of gold ores. Sundry small placers were operated productively at French Corral and North Bloomfield. Lessees operated the You Bet Mining Co.'s property when water was available. This property is 7 miles east of Colfax. The Omega hydraulic mine at the head of Scotchmans Creek, 4 miles from Washington, was worked for a short time only.

PLACER COUNTY.

The Placer County production of gold and silver in 1917 was valued at $552,571, as compared with $453,328 in 1916, an increase of $99,243, entirely due to the increased output of the placers, mainly dredges. The total yield of gold was $538,686 and that of silver was 16,851 fine ounces, valued at $13,885.

The deep mines produced from 16,654 tons of ore gold valued at $120,285; 15,204 fine ounces of silver, valued at $12,528; and 633,747 pounds of copper, valued at $173,013. The placer mine yield was $418,401 in gold and 1,647 ounces of silver, valued at $1,357, a total of $419,758. The yield from placer mines was $171,905 more in 1917 than in 1916. The decrease in gold from deep mines was $61,037. The total metallic output of the county in 1917 was valued at $725,584, an increase of $97,990, as compared with 1916. There were 21 producing placers in the county in 1917, and 5 productive deep mines, a total of 26. Placer County continues to be the leading drift mining county of the State.

Digitized by Google

Of the deep mines the Oro Fino Mining Co., at Auburn, operated full time until June, when a shortage of labor compelled a reduction of operations for the remainder of the year. During some months they employed two shifts a day and in others only one shift. The mine is opened by a 600-foot incline shaft, of which 200 feet were sunk during 1917; 2,434 feet of drifting was also done. The reduction plant consists of a 10-stamp amalgamation and concentration mill, the concentrates being shipped to a smelter on San Francisco Bay. Very little productive work was done on the Reno Consolidated mine, at Forest Hill. The most productive deep mine in the county was the Dairy Farm copper mine, owned by the Van Trent Mining Co., near Lincoln, which was operated for nine months and then closed down and abandoned. There was no reduction plant at the mine, the copper ores having been shipped to smelters. The Valley View copper mine, near Lincoln, carried on development and experimental work most of the year, but shipped some concentrates to a smelter. During the year a 30-ton ball mill and concentrators were put in. The Pioneer Gold Mining Co., at Towle, operated productively during the year.

On Quartz Flat, near Auburn, the Lincoln gold dredge worked bench gravel from January to July 10, 1917. The Pacific Gold Dredge Co. dredged stream gravel on Middle Fork of American River, near Auburn, for eight months, half of the time in virgin gravel. A few small surface placers in the vicinity of Auburn were producers. The Haub drift mine worked an ancient river channel 5 miles from Blue Canyon for 10 months of the year; and the Lost Camp, a mile and a half from Blue Canyon, worked quartz gravel by sluicing, and obtained a good many nuggets during the work. The Eldorado and Placer Counties Gold Mining & Power Co. dredged stream gravel at the Poverty Bar mine on Middle Fork of American River, three-quarters of a mile from Butcher Ranch. The work was continued from January 1 to August 20, on which date the dredge sunk and operations were not renewed until December 8. A nominal output of gold was obtained from sluicing at the old Miner claim, at Colfax. The Union placer, at Dutch Flat, and a number of small claims produced some gold. Small amounts of gold were produced by the Golden Channel, at Emigrant Gap, and by the Dardanelles at Forest Hill, where some smaller mines also produced. The largest producing drift mine in the county was the Excelsior, or Reamer Mining Co., at Forest Hill. At Iowa Hill, the Gleason Consolidated and other drift mines made considerable production. At Last Chance, the following drift mines were producers: Red Star, Dixie Queen, Home Ticket (Frankmont), Glen, and Pacific Slab. There was some output from Chinese miners at Michigan Bluff.

PLUMAS COUNTY.

The total yield in metals from Plumas County in 1917 was $799,196 greater in value than in 1916, and in 1916 it was $713,725 greater than in 1915, which increase really shows the marked growth of the copper mining industry in the county, as the output of gold has decreased slightly. The quantity of ore treated in the county in 1917 was 8,995 tons larger than in 1916.

The production of gold from deep mines was $78,739; the silver amounted to 90,222 fine ounces, valued at $74,343, and the copper to

Digitized by Google

7,471,092 pounds, valued at $2,039,608. The increase in the copper was 2,321,088 pounds in quantity and $772,707 in value. There were 189,973 tons of ore treated, of which 13,879 tons was siliceous ore and 176,094 tons copper ore. The copper ores of the county yielded a concentrate high in copper but low in gold and silver. The ore sent to gold and silver mills produced $51,326 in gold in the bullion, and 335 ounces of silver, valued at $276, a total of $51,602. From the ore treated at concentrating plants there were derived 12,409 tons of concentrates yielding $25,902 in gold and 80,848 ounces of silver, valued at $66,619, or an average per ton of $7.45 in gold and silver. The 3,797 tons of ore sent to smelters yielded $1,511 in gold and 9,039 ounces of silver, valued at $7,448, or a total of $8,959. The 7,471,092 pounds of copper was derived partly from the concentrates and partly from crude ore shipped to smelters. Of the producing mines 20 were placers and 12 deep mines. Of the placers 7 were hydraulic mines, 7 were drift, and 6 were surface placers. The hydraulic mines produced $22,361 in gold and silver, the drift mines $23,028, and the surface placers $7,945, a total of $53,334. There was an increase of $4,260 in the production of gold from all classes of placer mines in 1917.

Of the deep mines the Last Chance copper property was the only producer at Chilcoot. The Five Bears, at Genesee, produced copper ore carrying some silver but no gold. The Jamison Mining Co., at Johnsville, a gold mine, was compelled to close down early in November until provision was made for the storage of mill tailings, which is one of the burdens imposed by the Government on gold mining in California. This property is opened by a shaft 165 feet deep, an 1,800-foot drain tunnel, and 5,532 feet of drifts, raises, and crosscuts. It is equipped with a 20-stamp amalgamation mill. The Plumas-Eureka Corporation, at Johnsville, is opened through an adit of 7,300 feet in length, though there was a small yield, only prospecting was under way in 1917. The mine has a 20-stamp amalgamation mill. The Walker Mining Co. (copper), at Portola, installed in 1917 a new Marcy mill, a Dorr thickener, an Ingersoll-Rand 9-mill compressor, new bunk houses and dwellings, and a power line 14 miles long. A 100-ton flotation plant was also installed. The concentrates are shipped to Utah for treatment. Among the smaller producers were the Crown Point group, at Quincy; Empire Mines Co., at Seneca; Seneca Consolidated Gold Mining Co., at Seneca; Beetle (copper), Sierra Range Copper Co., and Ruby Copper, at Taylorsville. The largest producing deep mine in the county was the Engels Copper Mining Co., at Taylorsville, which is opened principally by adits having a total length of 11,000 feet. Two 3-compartment shafts were being sunk in 1917. The reduction works consist of a 500-ton concentrating plant at the copper mine and a 600-ton unit of a new mill at Superior, completed at the last of the year. Ball and tube mills are used for crushing the ore and the oil flotation process for concentration; concentrates are shipped to Garfield, Utah. The Missouri Bar, Oak Flat, and a few other small placers were producers at Belden. At Crescent Mills the placer producers were the Golden Key and Great Divide. There were also some small placers producing at Greenville; and at Johnsville the Continental mine and the

Digitized by Google

Standard Mining Co. reported some output. The Consolidated Alturas Placer Mining Co. made a considerable output from river bed gravels and old tailings on Slate Creek, near Laporte; and the Menifee, Plumas Grass Valley, and a few smaller properties were producers in the same region. The New York hydraulic, at Meadow Valley, and the Golden Eagle placer, at Quincy, were producers in a small way. The Seneca Development Co. recovered considerable gold from its drift mine on North Fork of Feather River, near Seneca; and the Yankee Bar, or Dean mine, in the same section made a small output. The Spring Garden Mining Co., about 3 miles from Spring Garden, obtained its gold by the use of a "shooter" with an automatic gate.

SACRAMENTO COUNTY.

Sacramento was fourth in rank among California gold-producing counties, and its total output of gold in 1917 was $1,919,581, or $85,726 more than in 1916. The total yield of gold and silver was $1,924,068, or $86,635 more than in 1916. Virtually the entire output of the county was produced by gold-dredging operations in the vicinity of Folsom. Twelve dredges were at work in 1917, of which 11 were owned by the Natomas Co. of California, and the remaining one by the Indiana Gold Dredging Co. The dredge output of gold in the county was $84,026 more in 1917 than in 1916. Considerable platinum was obtained during the dredging operations of the Natomas Co. Some gold was obtained by drift and surface placers near Folsom, and one deep mine near the same place had an output of gold.

SAN BERNARDINO COUNTY.

There was a decrease in the quantity of ore treated in San Bernardino County in 1917, as compared with 1916, and in the gold and zinc recovered, but an increase in copper, lead, and silver. The total decrease in 1917 in value of all metals produced was $129,476. The production of gold decreased $124,837. Silver increased 5,879 fine ounces; copper, 46,259 pounds; lead, 1,304,820 pounds; and zinc decreased 1,538,538 pounds. The output of gold was valued at $154,976. The silver amounted in 1917 to 107,924 fine ounces, valued at $88,930; copper, 1,572,125 pounds, valued at $429,190; lead, 2,195,791 pounds, valued at $188,838; and zinc, 45,216 pounds, valued at $4,612. Two deep gold mines, nine copper mines, one silver mine, eight silver-lead mines, eight lead mines, and one placer mine, a total of 29, reported production in this county in 1917. There were 1,165 tons of siliceous ore sold or treated in 1917, 20,630 tons of copper ore, 366 tons of lead ore, 77 tons of silver ore, and 10,045 tons of silver-lead ore. No distinctively zinc ores were mined, the zinc being derived from other ores.

There were 31,283 tons of crude ore sent to smelters, which yielded $152,766 in gold and 107,394 fine ounces of silver, valued at $88,493. In addition 1,000 tons of old tailings were worked, which yielded $1,310 in gold and 528 ounces of silver, valued at $435. The copper ores produced 7,244.01 fine ounces of gold and 35,838 fine ounces of silver; the lead ores produeed no gold, but 1,040 ounces of silver; the

Digitized by Google

silver ores yielded 6.97 ounces of gold and 1,301 ounces of silver; the silver-lead ores 52 fine ounces of gold and 69,210 ounces of silver.

The War Eagle mine, at Bagdad, is a lead mine yielding some silver. The Bagdad-Chase, at Barstow, is equipped with a 50-ton cyanide plant, but it was worked for only two months of the year on tailings. The Goldstone Mining Co., at the same place, made a small output of lead. The Sagamore Mining Co. operated a silver-lead mine at Barnwell. The Copper World, at Cima, started a matte smelter of 100 tons capacity in November and its product was shipped to the smelter at Garfield, Utah. Other copper producers at Cima, are the Express & Domingo, and the Standard; and the lead producers are the New Era Mining Co. and Piute. The old Waterloo mine, at Daggett, made a small output, as did some few other silver claims at the same place. The Belle McGilroy, at Goffs, produced copper ore carrying considerable silver. Other producers at Goffs were the Bonanza King, Louisiana–California Mining Co., and Stemwinder Mining Co. The Bullion mine, at Ivanpah, yielded some copper ore; and silver-lead ore was derived from the Peterson lease, at Maruba. Ores carrying both copper and zinc were produced at the Emperor mine, at Nipton. The Carbonate King mine was operated for five months of the year and its ore was shipped from Roach, Nev. The Horn Copper Co., the nearest postoffice to which is Parker, Ariz., shipped some copper ore, as did the Denver Group at Silver Lake. The Pacific, at Stagg, was closed down from June to October, during which time a 150-ton concentrating mill was constructed. The company worked the Bagdad-Chase and Roosevelt mines during the rest of the year and made quite a large output of gold, silver, and copper. The Sunshine Copper Co., at the same place, produced copper ore only.

The Crystal Dome Mining Co., of Trona, shipped sulphide and carbonate of lead and a few tons of molybdite of lead during the year. The Minetta and Mohawk are producing silver-lead mines near Trona. A small quantity of copper ore was mined during assessment work by the Mount Whipple Gold Mining Co., of Vidal; and the Ibex Spring Mining Co. shipped ore carrying lead, zinc, and silver. The only dry-washing mine reporting production in the State was the Coolgardie Mining Co., 14 miles from Barstow. It was not operated commercially, but some gold was obtained by a hand dry-washer while assessment work was being done. The gold was taken from an ancient river bed formation.

SHASTA COUNTY.

The total value of the metallic output of Shasta County in 1917 was $9,218,396, which is $3,668,596 less than it was in 1916. The main decrease was in copper and zinc, but there was some decrease in gold also. The number of producing mines in the county was 23, or 7 less than in 1916. The output of gold was valued at $775,125, a decrease in 1917 of $161,760, as compared with 1916. The yield of silver in 1917 was 631,921 ounces, valued at $520,703, a decrease in quantity of 1,063,324 ounces and in value of $594,768. The output of copper in the county in 1917 was 26,658,879 pounds, valued at $7,277,874, a decrease of 13,100,593 pounds in quantity and of

Digitized by Google

$2,502,956 in value, as compared with 1916. The recoverable zinc was 6,320,529 pounds, valued at $644,694, a decrease of 1,543,695 pounds in quantity and of $409,112 in value, as compared with 1916. Shasta, notwithstanding its serious decrease in value for the year 1917, continues to be the leading county of the State in total value of metallic output. It also leads all other counties in the values of copper and zinc, but, for the first time in many years, its silver output has been exceeded by that of Inyo County.

The total number of deep mines from which production was reported in Shasta County in 1917 was 17, as against 21 in 1916. Of these 8 were gold mines, 1 was silver, and 8 were copper. The output of 494,469 tons of ore was made up of 9,673 tons of siliceous ore, 484,511 tons of copper ore, and 285 tons of silver ore. The placer mines of the county in 1917 yielded 14,054.78 fine ounces of gold, valued at $290,538. This production came from three dredges and three surface placers.

The gold from deep mines amounted to 23,441.90 ounces, valued at $484,587, and the silver to 630,635 fine ounces, valued at $519,643. The gold derived from siliceous ore amounted to 5,187.01 fine ounces, valued at $107,225, and that from copper ores to 18,254.89 ounces, valued at $377,362. The production of silver from siliceous ore was 9,674 ounces, valued at $7,971; from copper ores 617,295 ounces, valued at $508,651; and from silver ore 3,666 ounces, valued at $3,021. The siliceous ore, therefore, yielded $115,196 in gold and silver and the copper ores $886,013 in gold and silver.

The gold and silver mills in Shasta County in 1917 treated 864 tons of ore, which yielded in gold bullion $17,196 and 159 fine ounces of silver, valued at $131. The total recovery of mill bullion was valued at $17,327, or an average value per ton of $20.05 in gold and silver. This ore yielded 15 tons of concentrates with a gold value of $1,698 and a silver content of 27 ounces, valued at $22, a total value of concentrates of $1,720. In addition 101,173 tons of ore were shipped directly to concentrating mills from which 13,376 tons of concentrates were derived. The average value per ton of all concentrates was $0.21 in gold and $0.14 in silver in addition to copper content.

The crude ore sent to smelters, amounting to 392,432 tons, yielded (in addition to the copper) $464,556 in gold, an average of $1.18 a ton, and 628,083 ounces of silver, valued at $517,540, or $1.32 a ton. The total value of gold and silver recovered from ore sent to smelters was $982,096, or an average value of $2.50 a ton, as against an average of $3.29 a ton in 1916.

The National Potosi and Old Veteran mines, at Buckeye, were worked in a small way in 1917. The ore of the Ruby-Pearl mine, at Castella, is worked in a small mill on the property. The Balaklala Consolidated Copper Co., at Coram, operated 11 months of the year, but was closed the other month by reason of labor troubles. The mine is developed by adits totaling 10,000 feet in length and by 500 feet of diamond core drilling. The ore is a cupriferous pyrite, which is sold to the smelter of the Mammoth Copper Mining Co. at Kennett, there being no reduction works in operation at the mine. The Shasta Hills Mining Co., at French Gulch, owns a group of contiguous mines with development amounting to some 1,500 feet. The ore was treated at a custom mill in 1917, but later the company provided its own mill. Among other producers at French Gulch were

Digitized by Google

the El Dorado and Eureka group, the Summit mine, and the Western Exploitation Co. The Afterthought Copper Co., at Ingot, produced copper, lead, zinc, and silver in 1917. The zinc concentrate was shipped to the Bartleville Zinc Co. and the copper concentrates to the Tacoma Smelting Co. The company has a 300-ton flotation mill running 24 hours when at full capacity. The Mammoth Copper Co. is the largest producer of copper, zinc, and silver in the State, and the yield of gold is also considerable. The total value of the output of this property is much greater than that of any other in California. The reduction plant consists of a smelter with five furnaces (of which three were in use), two converters, and a picking or sorting plant for zinc ores. Straight pyritic smelting is carried on, and the copper is shipped as blister to the refinery at Chrome, N. J. The copper plant and mine were regularly operated in 1917. The zinc was sorted at the smelter on a picking belt and shipped to Altoona, Iola, or La Harpe, Kans. A great deal of siliceous ore from various gold mines in the country was treated at the Mammoth smelter, and a considerable output of gold resulted. The Mountain Copper Co. (Ltd.), of Keswick, is a very large producer of copper and has some output also of gold and silver. The mines and mill were in operation approximately 11 months in 1917, and the smelting plant during the whole year. The smelter is at Martinez on the shores of San Francisco Bay, about 250 miles from the mines. The concentration mill of 500 tons daily capacity is at Minnesota, 5 miles from the mine. There are three contiguous mines, the Iron Mountain, Hornet, and No. 8 mine. The sulphide ore is roasted to manufacture sulphuric acid and then the calcines, with suitable mixture of other ores, are smelted in reverberatories. The copper matte carrying the gold and silver is converted to blister, which is shipped to the Baltimore Smelting & Rolling Co., Baltimore, Md. The Parker Metal Mining Co., near Redding, operates one of the few purely silver mines in the State. The Greenhorn Mountain Copper Co. is a productive copper property near Shasta. The Evening Star Mining Co., Whitehouse, produces considerable gold and silver. The Bully Hill Copper & Smelting Co., at Winthrop, reopened its mine in February, 1917, and ore shipments to the Mammoth smelter began in June. The Rising Star shaft was unwatered 400 feet, mine workings were reopened, and some new development was done. The property is opened by a 600-foot vertical shaft and about 10,000 feet of drifts. The mine is equipped with a 300-ton smelter (not used) and a railroad to Pitt, 17 miles long. Experiments are being made for the recovery of zinc. The Arps Copper Co. is a small producer of copper, silver, and gold at Ydalpom. A combustion-engine compressor plant was added to the equipment in 1917. The ore is sold to the Mammoth smelter at Kennett.

Of the placer mines in the county the most important are those operated by the three dredging companies. The Shasta Dredge Co. is working stream gravel with one dredge on Cottonwood Creek, a mile east of Gas Point. Lawrence Gardella operated a dredge on stream gravel at Clear Creek, near Redding, and was building another dredge at the same place. The Shasta Mining & Dredge Co. used one dredge in working stream and bench gravel on Cottonwood Creek. Some small placer mines were worked with small production near Redding, Taylor, and other points in the county.

Digitized by Google

SIERRA COUNTY.

The total production of metals in Sierra County in 1917 was valued at $386,057, as compared with $727,547 in 1916, a decrease of $341,490. The deep-mine gold decreased $332,028 and the placer gold $7,800. There were 49,779 tons of siliceous ore treated in gold and silver mills in 1917, yielding $320,728 in gold and 1,769 ounces of silver, valued at $1,458, a total of $322,186 in gold and silver. These ores also produced 1 ton of concentrates which yielded $343 in gold and 1 fine ounce of silver. In addition 170 tons of crude ore shipped to smelters yielded $1,634 in gold and 5 ounces of silver, valued at $4, a total of $1,638. There were also treated 93 tons of old tailings yielding $580 in gold and 2 ounces of silver, valued at $2, or an average of $6.25 a ton. The output of the placers of the county in 1917 was 2,957.79 ounces of gold, valued at $61,143 and 199 ounces of silver, valued at $164, a total of $61,307. Of the placer gold $29,710 came from hydraulic mines, $13,267 from drift mines, and $18,166 from surface placers. There were 30 productive mines in the county in 1917, of which 11 were deep gold mines. Of the 19 placers, 4 were hydraulic mines, 8 drift, and 7 surface placers.

The mine of the Croesus Gold Mining Co., Alleghany, has a 20-stamp mill, and the plant was operated throughout the year. Some of the arsenical ore from this mine is roasted before grinding. The mine of Mariposa Mine Association is opened by a 300-foot vertical shaft, a 700-foot adit, and about 1,000 feet of drifts. There is a 5-stamp mill on the property. The Original 16 to 1 Mine is opened by a 730-foot vertical shaft, a 200-foot adit, and 5,000 feet of drifts. A small ball mill is used to reduce the ore. Litigation hampered operations to some extent. The Durston Gold Mining Co. did not complete its 10-stamp mill until December, 1917, so that the output was small. The Twenty-One Mining Co. operated irregularly during 1917. The mine is developed by a main adit 1,940 feet long, with drifts, crosscuts, and raises aggregating 1,600 feet. There is a 10-stamp plate amalgamation mill on the property. The Tightner Mines Co. did 4,672 feet of development work in 1917. There is on the property a 20-stamp amalgamation and concentration mill, but the concentrates are "stacked" for future treatment. The El Dorado Mines Co. is among other small producers at Alleghany. The Cliff Leasing Co., a Milwaukee, Wis., corporation, operated the Oxford quartz mines at Downieville. The Mexican mine made a 10-stamp mill out of its old 5-stamp mill in 1917. The Four Hills Mining Co., at Johnsville, was worked by lessees for high-grade ore, which was crushed in a 2-stamp mill, though there is a 20-stamp mill on the property.

Of the few placers near Alleghany the Morning Glory mine made a small output. The Brandy City Mining Co. worked by hydraulic process ancient river bed gravels between Cherokee and Canyon Creeks, half a mile from Brandy City. The Depot Hill hydraulic mine, at Camptonville, had only a three months water season. The Orient, 6 miles from the same place, made a small output by hydraulicking ancient river gravel. The Grizzly Ridge drift mine, Downieville, breasted out some rim gravel, but the main channel deposit has not been reached by the bedrock tunnel. The Lassiat, Wide Awake

Digitized by Google

drift, and some other placers reported small yields at or near Downieville. The Mugwamp Mines Co. has a tunnel 2,000 feet long, to which 200 feet was added in 1917, and some raise and crosscut work was also done. This company has a 50-ton ball mill tumbler to free converted gravel before washing in sluices. Considerable gold output was made by the Kirkpatrick Mining Co. by drifting an ancient river channel through a tunnel between Forest and Goodyear Bar. The Bope and the Confidence mines were among small producers at Pike. The Caledonia worked claims at Cedar Grove ridge between Slate and Canyon creeks. The Klondike drift mine at Sierra City had a small crew on development work the entire year, and some gold was recovered. The Pig Canyon mine sluiced out some gold at Sierra City with snow water. The Howland Flat Mines Co. and Winkeye (Table Rock Mining Co.) worked an ancient river bed by drift mining at Table Rock, operating 11 months in 1917. There was some gold produced from small placers at Sierra City, Scales, and other points in the county.

SISKIYOU COUNTY.

In 1917 Siskiyou County produced 15,748.48 fine ounces of gold, valued at $325,550; 20,489 ounces of silver, valued at $16,883; 896,846 pounds of copper, valued at $244,839; and 541,079 pounds of zinc, valued at $55,190, a total of $642,462. This was an increase of $192,201, as compared with 1916. There were 7 deep mines producing as compared with 11 in 1916. They produced 5,853 tons of ore, yielding gold valued at $22,461, and 19,068 ounces of silver, valued at $15,712, a total of $38,173, as compared with $55,636 in 1916. The 40 producing placer mines yielded gold valued at $303,089, and 1,421 ounces of silver, valued at $1,171, a total of $304,260, as compared with $387,983 in 1916. Thus it is seen that the placers yielded $266,087 more in gold and silver than the deep mines of the county. The number of producing mines (47) in Siskiyou County was larger than in any other county of the State, although there were 13 less than in 1916. Of the placers 32 hydraulic mines produced $101,920 in gold; the 3 dredges $182,855; the one drift mine and 4 surface placers $18,314. The hydraulic mines produced $36,257 less and the dredges $46,629 less gold in 1917 than in 1916.

Of the deep mines the Facey, at Callahan, produced considerable gold and a small quantity of silver. The Dewey Mines Co., at Gazelle, after an idleness of 10 years, started up and began using electricity on account of the high cost of wood for fuel. The mine is equipped with a 10-stamp amalgamation and concentration mill. The Polar Bear mine, at the same place, was only operated from September until the middle of November. The Blue Ledge copper mines in the extreme upper corner of the county, shipped ore to Tacoma, Wash., and also produced a large quantity of ore which was not marketed. Both copper and zinc, with considerable silver and some gold were produced by these mines. The Eureka & W. Y. O. D. property at Rollin, and the Oregonian Group at Sawyers Bar, were small producers of gold. The latter has a small 3-stamp mill. The Gipsy, at Yreka, produced a small amount of gold.

Of the placers the Baines and the Wendell, at Black Bear, sluiced out some gold. At Callahan, the Sugar Hill and some other mines

Digitized by Google

produced in a small way. The Banner hydraulic, at Cecilville, had about a six months' run, and some other placers at the same place were producers. The Michigan Salmon Mining Co. worked bench gravel by hydraulicking for five months at Forks of Salmon, and there was some output from smaller placers at the same place. The Siskiyou Dredge Co. worked stream gravel on McAdams Creek near Fort Jones, with one dredge. A number of small placer mines in the same vicinity produced considerable gold during the year. The Sulphur Springs hydraulic operated in a small way at Gottville, and there were a few productive placers near Greenview. At Hamburg, the Morris hydraulic, Kunz Flat hydraulic, Nigger Creek, and some other smaller placers reported production. The Siskiyou Mines Co. worked gravel and sand by hydraulic process in the Klamath River, 6 miles from Happy Camp, for nine months of 1917. The South Fork, Squirrel Creek, and other placers were productive in the same region. There was also some output of placer gold at Hornbrook. The Frazier hydraulic in Eddy's Gulch, near Rollin, made a small output. At Sawyers Bar, the Forks of Salmon, Gold Hill, Cronin, Multum in Parvo, Thomain, Burns, and others were producing hydraulic mines. At Scott Bar, the Quartz Hill hydraulic mine was the principal producer. The Jack Lowden hydraulic, at Seiad Valley, Blue Nose hydraulic, at Blue Nose, some small placers at Somes Bar, and the Crary, at Walker, all produced more or less gold. The Klamath Dredging Co. used one dredge in working stream gravel on Klamath River bars near Walker. El Oro Dredge Co. operated one dredge on Greenhorn Creek, near Yreka, working stream gravel continuously throughout the year. Some smaller placers in that vicinity were also producers.

TRINITY COUNTY.

In 1917 Trinity County produced 29,124.07 fine ounces of gold, valued at $602,048, and 12,162 ounces of silver, valued at $10,021. The total value of all metals including copper was $968,307, an increase of $137,732 over 1916. The increase in gold was $166,555. Twenty-nine mines reported production in 1917, or 19 less than in 1916. Of these 3 were deep gold mines and 1 was a copper mine; and of the placers 17 were hydraulic, 4 were dredges, and 3 were surface placers. The deep mines produced from 8,801 tons of ore 1,008.91 fine ounces of gold, valued at $20,856, and 9,822 ounces of silver, valued at $8,093, a total of $28,949 in gold and silver, as compared with $66,261 in 1916, a decrease of $37,312. The ore treated was less by 4,858 tons than in 1916. The 25 placers yielded 28,115.16 fine ounces of gold, valued at $581,192, and 2,340 ounces of silver, valued at $1,928, a total of $583,120, and an increase of $206,297.

Of the deep mines very little output was made at the Brown Bear, at Deadwood, formerly the largest producer in the county. The Island Copper Co. in Island Mountain district, shipped ore carrying, in addition to the copper, considerable gold and silver for reduction to the smelter at Tacoma. The Five Pines and Surprise mines, at Trinity Center, made only a small gold output. The Foster Gold Mining Co. operated the Bonanza group of mines near Carrville; it is opened by a 2,300-foot adit and is the only "gravity" quartz gold

Digitized by Google

mine in California—that is, the only mine with no pumping or hoisting. The present workings are 1,000 feet below the croppings.

There are some small producing placers at Big Bar; and at Burnt Ranch the McAtee Bar did a little hydraulicking. The Pacific Gold Dredge Co. is a new enterprise on Trinity River, 2 miles from Carrville, which carried on dredging for only 33 days in 1917. At Coffee are the Schlomberg and the Underground Treasure mines. The Slide Creek Mining Co. and a few other hydraulic mines made outputs at Denny, and there were some small placers working at Douglas City. At Hayfork, the Carrier Gulch, Murphy & Layman, and a few other mines were productive. The Chapman & Fisher, and Red Hill were producing hydraulic mines at Junction City. The Valdor Dredge Co. operated an electrically driven 7-foot bucket, California type of dredge, along Trinity River, 3 to 6 miles below Junction City, and was the most productive placer property in the county. Considerable gold was obtained from small placer operations in the vicinity of Junction City. The Bablew Mines Co. (hydraulic), Donnelly Gulch (drift), and Trinity Dredge Co. were the principal producers at and near Lewiston, but there was a considerable gold output from smaller properties. Some output was made by Mistake Nos. 1 and 2 mines in Bridge Gulch, 4 miles from Peanut, in Hayfork district. The Estabrook Gold Dredging Co. operated a 7½ cubic foot bucket dredge on stream gravel for 11 months in the vicinity of Trinity Center. The Horseshoe hydraulic mine worked on Kincaid Gulch, a tributary of Weaver Creek, a mile and a half from Weaverville, but they only had about one month's supply of water from December, 1916, to July, 1917. The La Grange Mining Co. near Weaverville, formerly the most productive hydraulic mine in the State, made considerable output of gold, but less than usual owing to lack of water supply. The Gem is a small hydraulic mine at Willow Creek.

TUOLUMNE COUNTY.

In Tuolumne County in 1917 there was a decrease of five in the number of producing mines and a decrease in both quantity of ore and the value of gold produced. The output of gold was 15,532.49 fine ounces, valued at $321,085; of silver 9,475 ounces, valued at $7,808, and of copper 12,000 pounds, valued at $3,276. The total value for the year was $332,169, a decrease of $553,107 as compared with 1916. The deep mines of the county produced 41,527 tons of ore which yielded 15,086.52 fine ounces of gold, valued at $311,866 and 9,450 ounces of silver, valued at $7,787, not including the copper. The total metal value from the deep mines was $322,929 as compared with $875,385 in 1916. There were 18 producing mines in the county in 1917, of which four were placers and 14 were deep mines. The three drift mines and one surface placer yielded 445.97 fine ounces of gold, valued at $9,219, and 25 ounces of silver, valued at $21, a total yield of $9,240.

The total quantity of ore sold or treated in the county in 1917 amounted to 41,527 tons, or 183,538 tons less than in 1916. There were treated 41,256 tons in gold and silver mills, yielding $233,866 in gold bullion, and 8,550 ounces of silver, valued at $7,045, a total in mill bullion of $240,911, or an average of $5.84 a ton in gold and

Digitized by Google

silver. From the milling ore 1,585 tons of concentrates were obtained, which yielded $73,432 in gold and 890 ounces of silver, valued at $733, a total of $74,165 in gold and silver, and a total average yield of $46.79 a ton.

The ore milled and concentrated yielded a total value of $307,298 in gold and $7,778 in silver. The total yield of gold and silver on the plates and from the concentrates was valued at $315,076, or $7.64 a ton, as compared with $3.88 a ton in 1916.

In addition 218 tons of ore were sent to smelters, which yielded no gold or silver. There were also 35 tons of old tailings worked, which yielded a small output of gold and silver.

The great falling off in total output of gold in the county is readily accounted for by the idleness of the Harvard mine, at Jamestown, formerly a large producer and the materially reduced production of such prominent mines as the Dutch-Sweeney at Jamestown, Eagle-Shawmut at Shawmut, Black Oak at Soulsbyville, and Nyman at Stent, besides other smaller properties in the county and also in view of the lesser number of producers.

Of the deep mines of the county the Gold Bug & Little Wonder, at Big Oak Flat, made a small output. The Experimental Gulch mine, at Columbia, worked about eight months while water for power was available. On this property are two mills, one of 5 stamps and one of 3 stamps. The App (operated by the Dutch-Sweeney Mining Co.), at Quartz, is opened by an incline shaft 1,276 feet deep. The old mill has been dismantled and the ore was treated at the Dutch-Sweeney mill. The Dutch-Sweeney is opened by an incline shaft 2,207 feet deep. The main shaft was sunk 506 feet in 1917. The ore is treated by amalgamation, gravity concentration, and flotation. The Greenstone mine, at Quartz, produced a small quantity of copper. The Eagle-Shawmut Mining Co., at Shawmut, operated its plant to April 1, 1917. Mine development and mill reconstruction has been done since February, 1917, by the Tonopah-Belmont Development Co. The mine is opened by an incline shaft 2,250 feet deep from the face of the adit level 2,000 feet long. In 1917 the shaft was deepened 451 feet and 1,400 feet of drifting was done. The property is equipped with a 100-stamp amalgamation and concentration mill and a 22-ton chlorination plant. The ore is treated by stamping, amalgamating, concentrating, and chlorinating by barrel treatment after roasting. The deep mine producers of Sonora are the Hope Mining Co., Sugarman, and a number of smaller properties. At Soulsbyville, are the Addis and the Black Oak. On the latter mine is a 100-ton cyanide plant. The ore is crushed in solution, and reground in a tube mill, followed by Pachuca agitation, continuous filtration, and zinc-dust precipitation. The Jumper-California, at Stent, was operated continuously during the year on the leasing system. The mine is opened by a 1,450-foot incline shaft and a 500-foot vertical shaft. The Nyman Consolidated Mines Co., at Stent, ceased all work in September, 1917. The mine is opened by a vertical shaft 850 feet deep, an adit 100 feet long, and some 15,000 feet of drifts. The reduction plant consists of a 20-stamp amalgamation and concentration plant. On the Star King mine, at Tuolumne, only one month's work was done in 1917, when operations ceased. The mine is opened by an incline shaft 565 feet deep, and has a 5-stamp amalgamation and concentration mill.

Digitized by Google

Of the placers producing in the county the Saratoga is a drift mine at Columbia, and there are some few placers at Columbia and near Jamestown.

YUBA COUNTY.

Yuba County in 1917 was second in relative rank among gold-producing counties of the State, being exceeded only by Nevada County, where deep quartz mines predominate. Yuba County in 1917 produced more placer gold than any other county in California, almost entirely from its extensive dredging operations. The output of the county in 1917 was $3,677,673 in gold and 7,999 ounces of silver, valued at $6,591, a total of $3,684,264 in gold and silver, and an increase of $510,607, as compared with 1916. The dredges in 1917 produced $3,659,211 in gold, which is $519,061 more than in 1916. Twelve dredges were in operation in the county in 1917, and, including these dredges, there were 21 productive placers.

The Yuba Consolidated Gold Fields, operated by the Hammon Engineering Co., in Yuba river, near Hammonton, is the most extensive dredging enterprise in the county and in the United States. It had 9 dredges working the full 12 months of 1917. The Marysville Dredging Co. operated 3 dredges the whole year on the old gravel plain deposited by Yuba River near Marigold. Both these dredging companies obtained considerable platinum with their gold. Other producing placers in the county were the Bright Star and Landers Bar at Browns Valley, some small mines at Dobbins, Archimedes at Marysville, and Julius Cæsar drift at Smartsville.

OTHER COUNTIES.

Fresno County.—This county produced in 1917 metals valued at $15,043, of which $5,745 was gold; and there were 351 ounces of silver, valued at $289; and 33,000 pounds of copper, valued at $9,009. The Copper King Mining Co., of Clovis, shipped its ore to the International Smelter, Utah; Garfield Smelter, Utah; Mammoth Smelter, Kennett, Cal.; and Tacoma Smelter, Tacoma, Wash. Before the end of 1918 the company expects to be shipping 50 tons of ore daily. The Imperial Copper Co. was a small producer of copper at Clovis. Small quantities of gold were produced by the Sunnyside mine, at Piedra, and the M & M Co., at Dunlap. The Grant Rock & Gravel Co. operates a gravel plant in San Joaquin River at Friant, but saves considerable gold by sluicing in the gravel washing plant which does not interfere with the gravel operations.

Imperial County.—This county produced $919 in gold, 6 fine ounces of silver, valued at $5, and 7,000 pounds of copper, valued at $1,911, the total value of the metals being $2,835. The few producing mines are at Ogilby.

Merced and Stanislaus counties.—In these counties there were two dredge companies and one surface placer operating in 1917, with a combined gold output of about $21,000 less than in 1916.

Riverside and San Diego counties.—Only two mines operated in these counties in 1917, one in each, making a combined output valued at $5,585.

Digitized by Google

Digitized by Google

GOLD, SILVER, COPPER, AND LEAD IN OREGON.

(MINES REPORT.)

By CHARLES G. YALE.

INTRODUCTION.

The total metal output of Oregon decreased in value more than 22 per cent in 1917, as compared with 1916. Much of this deficit was due to the lessened yield of the larger deep mines of the State, the principal ones reporting a much smaller production than in 1916. From only a few mines was an increased output reported.

The gold mining industry in Oregon was affected unfavorably by the same conditions as in other Western States during 1917. Prices of supplies increased materially, and skilled labor was high and scarce. There has been, for these reason, a certain curtailment of operations involving decreased outputs, especially in most of the deep mines. Moreover, the value of the siliceous ore obtained from the deep mines declined 66 cents a ton in average value in 1917, as compared with 1916, and the quantity of such ore treated or sold was about 24,000 tons less. All the larger copper properties except two showed a decreased output in both quantity and value. The older dredging fields of the State showed a material decline in production of gold, and one dredge was idle at the end of 1916, the profitable ground having been exhausted. Two new dredges were put in operation during 1916 and 1917 and are working profitably in new areas. Very few new gold or copper mining enterprises were inaugurated in Oregon in 1917 and none of any magnitude. The State evidently must have outside capital to develop the better known districts and to assist prospectors in searching for new deposits.

As the gold mining industry is at present in a depressed condition, there seems to be little incentive for investment in properties of this character, and until the end of the war it is not probable that many new mines of any size will be developed and equipped. Nevertheless, there are, in Oregon, quite a number of mines which could be made much more productive if additional capital were available. At the present time there are few large mining enterprises being carried on productively in Oregon. The deep mines which have an annual production exceeding $100,000 are those of the Baker Mines Co., Cornucopia Mines Co., Homestead Iron Dyke Co., and Queen of Bronze Mining Co. The only placers exceeding the figure named in value of output are the Powder River Gold Dredge Co. and the Empire Gold Dredge Co.

Digitized by Google

The southwestern counties of Oregon,[1] which form an extension of the California gold belt, are Benton, Coos, Curry, Douglas, Jackson, Josephine, and Lane. These counties (with the exception of Benton, which reported no production) reported in 1917 a combined production of $117,075 in gold, and 758 ounces of silver, valued at $625. The production of placer gold in this region in 1917 was $90,017, a decrease of $41,310, and the production of gold from deep mines was $27,058, a decrease of $13,904. The total decrease in output of gold in these southwestern counties in 1917, as compared with 1916, was, therefore, $55,214. The output of gold in Coos County was slightly increased by the placers. In Curry County the decrease of about $6,800 was all from the placers. Two of the largest hydraulic mines at Marial were idle, one at Port Orford did assessment work only, and one at Wedderburn went out of business. There was little difference in the output of the mines in Douglas County in 1917 and 1916. From Jackson County the deep mines all reported reduced returns. Of the placers one mine at Layton showed some increase, but at Rogue River, Jacksonville, and Medford the returns were less from placer mines. The largest proportion of the decrease of the county was from Jacksonville. Of the deep mines of Josephine County the largest producer at Galice in 1916 was idle in 1917. With one exception the deep mines at Takilma showed increase in output of both gold and copper. Of the placer mines of Josephine County, the largest producer at Holland in 1916 was abandoned during 1917. Most of the placers at Galice, Leland, Kerby, Merlin, Waldo, and Grants Pass showed reduced outputs of gold as compared with 1916. In Lane County the largest producer of 1916 showed a reduced output for 1917.

Northeastern Oregon comprises the counties of Baker, Crook, Grant, Harney, Malheur, Umatilla, Union, Wallowa, and Wheeler. In 1917 no metallic output was reported from Harney, Umatilla, Union, or Wallowa counties. The combined gold output of the five producing counties in this region in 1917 was $1,374,723, of which Baker County contributed $1,228,199, or 90 per cent. There was a decrease for 1917 in these counties, as compared with 1916, of $353,494. The yield of placer gold in 1917 was $637,349, a decrease of $103,841, or 14 per cent. The lode mines produced in gold $737,374 in 1917, as compared with $987,027 in 1916, a decrease of $249,653, or 25 per cent. It may be also stated that there was a decrease from this source of 27 per cent in 1916, as compared with 1915. The total decrease of gold output in this region in 1917, as compared with 1916, was $353,494. The greatest decrease in gold in any county was in Baker—$412,427. Only one county, Grant, showed an appreciable increase in 1917. As to the deep mines of Baker County, all the larger properties in the Cornucopia district showed very material decrease in yield of gold. The same may be said of both deep and placer mines in the Cracker Creek district, one deep mine which was a large producer in 1916 having been closed entirely at the end of that year. The Mormon Basin district also shows a material decrease from its principal gold mines. At the mines at Homestead there was an increase in gold, but a decrease in copper. There were fewer "small

[1] Diller, J. S., Mineral resources of southwestern Oregon: U. S. Geol. Survey Bull. 546, pp. 9–127, 1914. Diller, J. S., and Kay, G. F., Mines of the Riddles quadrangle, Oreg.: U. S. Geol. Survey Bull. 340, pp. 134–152, 1908.

Digitized by Google

mines" operating in Baker County in 1917 than in 1916, so far as returns show. One dredging company at Bridgeport had a material increase, but the placers at Robinette, Rye Valley, and Home produced less than usual. There was very little difference in the output in Crook County for 1917 and 1916. In Grant County the principal deep mine at Granite showed a material increase in the output of gold, as did the dredging operations in the John Day district. Although there was some falling off in the output of the smaller mines, the large increase in the districts named resulted in the county being the only one in Oregon that increased its yield of gold in 1917. In Wheeler County the production was about the same in 1917 as in 1916.

PRODUCTION.

GENERAL STATEMENT.

Gold, silver, copper, and lead produced in Oregon, 1907–1917.

Year.	Number of mines producing.	Ore.	Gold.	Silver.	Copper.	Lead.	Total value.
		Short tons.		*Fine oz.*	*Pounds.*	*Pounds.*	
1907	206	110,698	$1,129,261	86,718	554,104	.....	$1,297,316
1908	239	50,684	865,076	43,602	291,377	2,138	926,737
1909	162	59,281	781,964	27,827	235,000	400	827,001
1910	180	82,132	679,488	35,978	13,861	.....	700,676
1911	176	98,558	633,407	45,221	93,136	.....	669,016
1912	210	90,945	770,041	57,081	260,429	39,317	849,886
1913	173	155,901	1,627,710	179,036	43,330	87,207	1,746,402
1914	105	124,331	1,591,461	142,552	39,248	16,436	1,676,153
1915	95	155,791	1,861,796	117,947	451,172	62,957	2,003,509
1916	108	159,071	1,902,179	231,342	3,581,886	28,000	2,937,478
1917	76	142,438	1,491,798	125,656	2,474,487	.....	2,270,874
Decrease	−32	−16,633	−410,381	−105,686	−1,107,399	−28,000	−666,604

The total metal output of Oregon decreased in value $666,604 in 1917, as compared with 1916. The quantity of ore treated decreased 10.4 per cent; the gold decreased 21.5 per cent in value; the silver decreased 45.6 per cent in quantity; the copper decreased 31 per cent in quantity; and no production of lead was reported.

The mine production of Oregon, having a total value of $2,270,874 in 1917, was derived from 76 producing mines, of which 53 were placer and 23 were deep. The producing placers which reported decreased in number by 22 in 1917 and the producing deep mines by 10. The total quantity of ore sold or treated was 142,438 short tons, a decrease of 16,633 tons. This ore averaged $6.05 a ton in gold and silver, aside from copper, as compared with $7.39 a ton in gold and silver in 1916.

GOLD.

The total recoverable gold content of ores and the gold from placers in Oregon in 1917 was 72,165.73 fine ounces, valued at $1,491,798, a decrease of 19,852.18 fine ounces in quantity and of $410,381 in value. The largest yield of gold from one county was $1,228,199 and came as usual from Baker County and was a decrease of $412,427, as compared with the yield in 1916. The next county in rank of production of gold was Grant, with $137,720, or an in-

Digitized by Google

crease of $74,127, due almost entirely to dredging operations. Other counties in relative rank of production as named were Josephine, Douglas, Jackson, Crook, Lane, Malheur, Coos, Curry and Wheeler. The placer mines of the State produced $727,366 in gold in 1917, as compared with $872,517 in 1916, a decrease of $145,151. The hydraulic mines produced $106,991 in 1917, or $57,557 less than in 1916; the drift mines, $1,350 or $3,082 less; the surface placers and dredges combined $619,025, or $84,512 less. There were 46 hydraulic mines in 1917, as compared with 61 in 1916; and 4 dredge, 2 drift, and 1 surface placer mines were productive in 1917.

The total output of gold from deep mines in 1917 was 36,979.40 fine ounces, valued at $764,432, which was 12,830.50 ounces less in quantity and $265,230 less in value than in 1916. Of the gold derived from deep mines, $207,534 was recovered by amalgamation, $520,805 by cyanidation, and $36,093 by smelting. There were no chlorination plants in operation in Oregon in 1917, and the concentrates obtained in milling operations were shipped generally to smelters for treatment.

Mine production of gold in Oregon in 1917, in fine ounces.

County.	Placers.	Deep mines.				Grand total.
		Siliceous ore.	Copper ore.	Lead ore.	Total.	
Baker	25,010.65	33,124.49	1,278.99	.....	34,403.48	59,414.13
Coos	48.37	.....	.....	.....	.....	48.37
Crook	.....	290.01	.....	.....	290.01	290.01
Curry	4.98	.....	.....	.....	.....	4.98
Douglas	1,080.65	.....	.....	.....	.....	1,080.65
Grant	5,685.22	976.98	.....	.....	976.98	6,662.20
Jackson	839.45	16.98	.....	.....	16.98	856.43
Josephine	2,381.12	49.97	1,146.00	.....	1,195.97	3,577.09
Lane	.....	95.98	.....	.....	95.98	95.98
Malheur	91.53	.....	.....	.....	.....	91.53
Marion	.....	.....	.....	.....	.....	.....
Wheeler	44.36	.....	.....	.....	.....	44.36
	35,186.33	34,554.41	2,424.99	.....	36,979.40	72,165.73
Increase or decrease	−7,021.68	−12,860.69	+190.17	−159.98	−12,830.50	−19,852.18

Value of placer gold produced in Oregon in 1917.

County.	Hydraulic.	Drift.	Dredging.	Surface placers.	Total.
Baker	$12,535	$350	a$618,922	.....	$631,807
Coos	.....	1,000	.....	.....	1,000
Curry	.....	.....	.....	$103	103
Douglas	22,339	.....	.....	.....	22,339
Grant	2,733	.....	.....	.....	2,733
Jackson	17,353	.....	.....	.....	17,353
Josephine	49,222	.....	.....	.....	49,222
Malheur	1,892	.....	.....	.....	1,892
Wheeler	917	.....	.....	.....	917
	106,991	1,350	618,922	103	727,366

a Includes dredging in Grant county.

SILVER.

The recoverable silver content of ores and the silver from placers in Oregon in 1917 aggregated 125,656 fine ounces, valued at $103,541, a decrease in quantity of 105,686 ounces and in value of $48,682.

Digitized by Google

Baker County in 1917 made the largest output of silver, 100,668 fine ounces, valued at $82,950. Grant County produced 23,052 fine ounces, valued at $18,995. The placer mines of Oregon produced 7,160 fine ounces, valued at $5,900, as compared with 9,249 ounces, valued at $6,086, in 1916. The deep mines produced 118,496 fine ounces, valued at $97,641; of this quantity 31,375 ounces were derived from copper ores, and the remainder, 87,121 ounces, from siliceous ore. By amalgamation 57,160 ounces, valued at $47,100, were recovered and 36,237 ounces, valued at $29,859, by cyanidation. At the smelters 25,099 ounces, valued at $20,682, were recovered.

Mine production of silver in Oregon in 1917, in fine ounces.

County.	Placers.	Deep mines.				Grand total.
		Siliceous ore.	Copper ore.	Lead ore.	Total.	
Baker	6,263	63,092	31,313	.....	94,405	100,668
Coos	2	.....	.....	.....	.....	2
Crook	.....	1,160	.....	.....	1,160	1,160
Curry	1	.....	.....	.....	.....	1
Douglas	63	.....	.....	.....	.....	63
Grant	518	22,534	.....	.....	22,534	23,052
Jackson	87	2	.....	.....	2	89
Josephine	208	5	62	.....	67	275
Lane	.....	328	.....	.....	328	328
Malheur	13	.....	.....	.....	.....	13
Marion	.....	.....	.....	.....	.....	.....
Wheeler	5	.....	.....	.....	.....	5
	7,160	87,121	31,375	.....	118,496	125,656
Decrease	2,089	31,022	72,447	128	103,597	105,686

COPPER.

The mine production of copper in Oregon in 1917 was 2,474,487 pounds, valued at $675,535, as compared with 3,581,886 pounds, valued at $881,144 in 1916, a decrease for 1917 of 1,107,399 pounds in quantity and of $205,609 in value.

MINING INDUSTRY.

Gold and silver produced in Oregon in 1917, by methods of treatment.

County.	Ore to gold and silver mills.			Ore to concentrating mills.	Concentrates produced.			Crude ore to smelter.		
	Quantity.	Gold.	Silver.		Quantity.	Gold.	Silver.	Quantity.	Gold.	Silver.
	Short tons.		*Fine ounces.*	*Short tons.*	*Short tons.*		*Fine ounces.*	*Short tons.*		*Fine ounces.*
Baker	93,397	$675,855	57,266	36,676	7,522	$26,439	31,256	126	$3,556	903
Crook	.....	.....	.....	.....	.....	.....	.....	218	5,995	1,160
Grant	.....	.....	.....	4,600	233	20,196	22,534	.....	.....	.....
Jackson	20	351	2	.....	.....	.....	.....	.....	.....	.....
Josephine	16	165	1	.....	.....	.....	.....	6,347	24,558	66
Lane	.....	.....	.....	.....	.....	.....	.....	24	1,984	328
Marion	.....	.....	.....	.....	.....	.....	.....	5	.....	.....
	93,433	676,371	57,269	41,276	7,755	46,635	53,790	6,720	36,093	2,457
Average per ton	.....	$7.24	0.612	.....	.....	$6.01	6.93	.....	$5.37	0.365

There were treated at gold and silver mills in 1917 in Oregon, 93,433 tons of ore, yielding $676,371 in gold, and 57,269 ounces

Digitized by Google

of silver, valued at $47,190. From 41,276 tons of ore sent to concentrating plants were recovered 7,755 tons of concentrates, having a value in gold of $46,635 and 53,790 ounces of silver, valued at $44,323, a total of $90,958. Crude ore shipped to smelters amounted to 6,720 tons, and contained $36,093 in gold and 2,457 ounces of silver. The 43,041 tons of copper ore shipped yielded 2,474,487 pounds of copper, or an average of about 57.5 pounds a ton. There were 1,009 tons of old tailings treated in 1917, yielding $5,333 in gold and 4,980 ounces of silver, valued at $4,104, or $9.35 a ton, in gold and silver.

Ore sold or treated in Oregon in 1917, in short tons.

County.	Siliceous ore.	Copper ore.	Lead ore.	Total ore.
Baker	94,434	36,774	.....	131,208
Crook	218	.....	.....	218
Grant	4,600	.....	.....	4,600
Jackson	20	.....	.....	20
Josephine	101	6,262	.....	6,363
Lane	24	.....	.....	24
Marion	.....	5	.....	5
	99,397	43,041	.....	142,438
Increase or decrease	−24,216	+7,632	−49	−16,633
Value per ton in gold and silver	$7.91	$1.76	.....	$8.05

Mine production of gold, silver, and copper in Oregon in 1917.

County.	Ore.	Quartz gold.		Placer gold.		Total.	
		Quantity.	Value.	Quantity.	Value.	Quantity.	Value.
	Short tons.	*Fine ounces.*		*Fine ounces.*		*Fine ounces.*	
Baker	131,208	34,403.48	$711,183	25,010.65	$517,016	59,414.13	$1,228,199
Coos	.....	.....	.....	48.37	1,000	48.37	1,000
Crook	218	290.01	5,995	.....	.....	290.01	5,995
Curry	.....	.....	.....	4.98	103	4.98	103
Douglas	.....	.....	.....	1,080.65	22,339	1,080.65	22,339
Grant	4,600	976.98	20,196	5,685.22	117,524	6,662.20	137,720
Jackson	20	16.98	351	839.45	17,353	856.43	17,704
Josephine	6,363	1,195.97	24,723	2,381.12	49,222	3,577.09	73,945
Lane	24	95.98	1,984	.....	.....	95.98	1,984
Malheur	.....	.....	.....	91.53	1,892	91.53	1,892
Marion	5	.....	.....	.....	.....	.....	.....
Wheeler	.....	.....	.....	44.36	917	44.36	917
	142,438	36,979.40	764,432	35,186.33	727,366	72,165.73	1,491,798

County.	Quarts silver.		Placer silver.		Total silver.		Copper.		Total value.
	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	
	Fine ounces.		*Fine ounces.*		*Fine ounces.*		*Pounds.*		
Baker	94,405	$77,790	6,263	$5,160	100,668	$82,950	1,386,271	$378,452	$1,689,601
Coos	.....	.....	2	2	2	2	.....	.....	1,002
Crook	1,160	956	.....	.....	1,160	956	.....	.....	6,951
Curry	.....	.....	1	1	1	1	.....	.....	104
Douglas	.....	.....	63	52	63	52	.....	.....	22,391
Grant	22,534	18,568	518	427	23,052	18,995	.....	.....	156,715
Jackson	2	2	87	72	89	74	.....	.....	17,778
Josephine	67	55	208	171	275	226	1,087,216	296,810	370,981
Lane	328	270	.....	.....	328	270	.....	.....	2,254
Malheur	.....	.....	13	11	13	11	.....	.....	1,903
Marion	.....	.....	.....	.....	.....	.....	1,000	273	273
Wheeler	.....	.....	5	4	5	4	.....	.....	921
	118,496	97,641	7,160	5,900	125,656	103,541	2,474,487	675,535	2,270,874

Digitized by Google

PRODUCTION BY COUNTIES.

BAKER COUNTY.

The total value of all metals mined in Baker County in 1917 was $1,689,601, as compared with $2,428,503 in 1916, a decrease of $738,902. The production of gold from deep mines in 1917 decreased $267,368, silver 111,002 ounces, and copper 1,245,456 pounds, as compared with 1916, a total decrease in value from deep mines of $593,689. The placer mines of the county produced $517,016 in gold in 1917, or $145,059 less than in 1916. The placer silver produced in 1917 was 6,263 ounces, valued at $5,160, a decrease in value of $154 for the year. There were 21 producing mines of all kinds in the county in 1917, as compared with 27 in 1916. The number of producing deep mines was 11 and of placer mines 10. The total output of siliceous ore mined and treated in the county in 1917 was 94,434 tons, or 25,737 tons less than in 1916. The gold from this ore was valued at $684,744, and the silver amounted to 63,092 ounces, valued at $51,988. The average recoverable value of the ore per ton in gold and silver was $7.79. The 93,397 tons of siliceous ore treated at gold and silver mills produced $675,855 in gold and 57,266 fine ounces of silver (valued at $47,187), an average per ton of $7.74 in gold and silver. From the 36,676 tons of ores concentrated were derived 7,522 tons of concentrates producing $26,439 in gold and 31,256 ounces of silver (valued at $25,755), a total value of $52,194, or an average value per ton of $6.93. The total yield of the 130,073 tons of milling ore from the plates, from direct cyanidation, and from the concentrates, was $702,294 in gold and $72,942 in silver, an average per ton in gold and silver of $5.96. In addition 126 tons of ore were shipped to smelters and yielded in gold $3,556 and in silver 903 ounces, valued at $744, a total value of smelting ores of $4,300 in gold and silver, or an average value per ton of $34.12, exclusive of the value of the copper. There were also 1,009 tons of old tailings treated, which yielded $5,333 in gold and 4,980 ounces of silver (valued at $4,103), or $5.28 a ton in gold and $4.06 a ton in silver.

Baker district.—No deep mines and only one placer reported product from this district in 1917. The old Clark Creek Farm Co. sold part of its holdings at the confluence of Clark Creek and Burnt River to the Oregon Dredging Co., which in the summer of 1917 installed a flume dredge and operated it for about two months of the year. The remainder of the Clark Creek Farm is held under option by the same company and is being prospected with a view of purchase.

Cornucopia district.—This district is third in order of rank of output among the productive mining districts of Oregon. The four deep mines produced metals valued at $421,107 in 1917, of which $370,460 was for gold, $50,051 was for silver, and the remainder for a small quantity of copper. The most important mine of the district is that of the Baker Mines Co., and next in productive rank are the properties of the Cornucopia Mines Co., of New York. The Queen of the West Mines Co. operated its mine and 50-ton cyanide plant and concentrating mill from April until the end of October. The ore is crushed in a cyanide solution, the concentrates taken out on a vanner, reground, and treated in an agitating plant. On the Connor Creek Co.'s property work was done the entire year, but the

Digitized by Google

mill was only run for three months. The plant consists of a 10-stamp amalgamating and concentrating mill.

Cracker Creek district.—The productive mines in this district consist of 1 deep mine, 1 drift mine, and 2 gold dredge mining properties, which made a combined yield in 1917 of $501,069, of which $495,974 was for gold, making this the most productive of the Oregon mining districts, exceeding the total yield of either the Cornucopia or Iron Dyke districts. The Whited is the only deep mine in the district and was worked under a lease and had a small output. The Surprise is a drift mine, which was only operated for three months of the year. The most important mining enterprise in the district (and in Oregon) is that of the Powder River Gold Dredging Co., which had two dredges operating in 1917, one of which ceased work at the end of the year.

Homestead district.—There was only a nominal output from this district in 1917, made by a deep mine, the Snake River Mining Co.

Iron Dyke district.—The property of the Homestead Iron Dyke Mines Co. (Inc.), next to that of the Powder River Gold Dredging Co., the most productive in Oregon, is located in this district. Most of the values from the mines are in copper. The Arkansas mine, in the same district, made a small production in 1917.

Mormon Basin district.—The deep mines in this district are the Commercial Mining Co., and the Deer Creek, and, in addition to the Rye Valley placers, there are several other smaller hydraulic mines. The total output of the district in 1917 was $315,504, of which $313,588 was for gold and the remainder for silver. The Commercial Mining Co., the most important in the district, is working the Rainbow mine, on which is a 100-ton cyanide plant, with a mill and amalgamation plant. The Deer Creek, another deep mine, was a small producer.

Pine Creek district.—In this district the following hydraulic mines made some output in 1917: Bull Dog, Cow Creek, Hamm Gold Mining Co., and some smaller claims.

Weatherby district.—The Little Hill Quartz mine operated in this district in 1917 in a small way. There is a 2-stamp mill on the claim.

COOS, CROOK, AND CURRY COUNTIES.

The only property reporting output from Coos County in 1917 was the Eagle mine, near Bullards. This is a "beach sand" drift mine where the "black sand" is about 8 feet deep. In addition to the gold, this mine produced a larger quantity of platinum than any other Oregon mine in 1917. In Crook County the only mine reporting product was the Ophir Mayflower Mining Co. (deep), in Howard district. This mine has a 5-stamp mill and concentrating plant.

In Curry County the Kalamazoo beach sand mine, near Wedderburn, in Denmark district, made a small output by sluicing.

DOUGLAS COUNTY.

This county produced $22,391 in gold and silver in 1917, all from hydraulic mines in Coffee Creek, Green Mountain, and Myrtle Creek districts. The water season was a poor one and some of the mines were only operated from 30 to 40 days. The productive placer mines were the Farquhar, Midget, Boulder, and a few more smaller ones.

Digitized by Google

GRANT COUNTY.

The production of Grant County in 1917 was $137,720 in gold and 23,052 ounces of silver, valued at $18,995, a total of $156,715, or an increase of $91,774 over the production in 1916. This output was derived from 1 deep and 5 placer mines. The placers are mostly in Canyon district, and the principal one is the Empire Gold Dredge, at John Day. Hydraulic mines producing were the Caledonia, Quartz Gulch, Maise Ridge, and some smaller ones. The only deep mine reporting production was the Ben Harrison, in Granite district which is developed by an 800-foot crosscut intersecting the vein at a depth of about 450 feet, the vein is opened to a further depth of 100 feet by a shaft. The reduction plant consists of a 20-stamp mill with concentrators and flotation plant, but the stamps are being replaced by a ball mill.

JACKSON COUNTY.

The total output of Jackson County in 1917 was $17,778 in gold and silver, derived from 2 deep mines and 8 hydraulic properties. A decrease of $25,350 is shown in the total yield, as compared with the year 1916. The two small deep mines are the Gold Ridge in Kanes Creek district and Pearl Mining Co. in Pearl district. The hydraulic mines of the county had a very short water season, which accounts for the falling off in gold yield for the year. The producing hydraulic mines were the Pacific Placer Co. (formerly the Layton) in Applegate district; Pearce Mining Co., Spaulding Mining Co., and Sterling Mining Co., in Forest Creek district; and Duffield & Burns in Galls Creek district. Several smaller operators made small outputs in each of the districts named.

JOSEPHINE COUNTY.

The total output of gold, silver, and copper in Josephine County in 1917 was valued at $370,981, as compared with $336,157 in 1916, an increase of $34,824, this increase being entirely due to the quantity and value of the copper produced. In 1917 the gold yield was $73,945; the silver was 275 ounces, valued at $226. The deep mines of the county produced from 6,363 tons of ore, $24,723 in gold and 67 ounces of silver, valued at $55, but the largest values were in copper. The total output of placer gold in the county, valued at $49,222, was derived from hydraulic mines, and was $15,442 less than the placer production in 1916. The decrease in total gold yield of the county in 1917, as compared with 1916, was $20,536. With the exception of a very small quantity all the ore produced in the county in 1917 was treated at smelters; and a very large proportion of the gold and silver from the deep mines was obtained in the smelting of copper ores.

The producing hydraulic mines in the Althouse district were the Goldsby, Little Gem, and Surprise.

The Corliss & Dean and a few other small hydraulic mines or placers were the only producers in the Galice district. The Almeda Consolidated Mines Co., formerly a large producing deep mine in this district, made no output in 1917.

Digitized by Google

From the Grave Creek district the only property reporting production was the Goff-Abbott hydraulic mine. The Archer and the Norton mines, both producers in 1916, were idle in 1917.

Four deep and two hydraulic mines reported production from Josephine district in 1917. The Anderson, on Illinois River, was the most productive hydraulic mine and made also a considerable output of platinum. This mine had a four months run, which was larger than most of the hydraulic mines in Oregon reported for the year. The other hydraulic mine in this district reporting production was the Gold Leaf group, near Kerby. The most important deep mine was the Queen of Bronze copper mine, at Takilma, which is opened by three tunnels, and on which about 600 feet of drifts and 350 feet of raises were made during the year. The product of this mine, after hand sorting, is shipped to the Tacoma smelter. The mine was operated with 36 men continuously during 1917. Considerable gold is contained in the copper ore from this mine, but very little silver. The Waldo is operated chiefly by open cut or quarrying method. The ore, carrying mainly copper, with some gold and very little silver, is treated at the Tacoma smelter. The mine was operated most of the time during 1917. The Waldo Copper Co., at Takilma, has a jig plant of 40-ton capacity. The reduction process is water concentration, jigs, Frue vanners, Standard tables, and Pinder concentrator. The concentrates are sold to the smelter. The St. Lilly and Diamond Drill mines made a small output of copper. The total value of the output of this district in 1917 was $327,903.

In the Jump-off-Joe district the Hydraulic Mining Co. is operating a hydraulic mine on upper Jump-off-Joe Creek. This was formerly known as the Cook & Howland mine. The Swastika hydraulic claims are on Jump-off-Joe, Jacks, and Horse creeks in this same district. The Ohio No. 5 and some smaller hydraulic mines are also operating in this district.

In the Pickett Creek district the only producers were the Farrer and a few other small hydraulic mines. In the Placer district the Columbia Mines Co. operated an extensive hydraulic mine and there were a few smaller ones reporting production. In the Sucker Creek district the January First, a deep mine, made a small output. The Fry Gulch and Osgood hydraulic mines were the only producers in Waldo district. The Blue Channel hydraulic is the only placer mine reporting from the Wolf Creek district; and the Thompson group was the only deep mine.

LANE, MALHEUR, MARION, AND WHEELER COUNTIES.

In Lane County the West Coast Mines Co., in the Bohemia district, whose property is extensively developed by adits and drifts and is equipped with a 30-stamp mill and concentrating plant, did very little beyond making repairs during 1917. In Malheur County the Boswell hydraulic and a few other placers in the Malheur Basin district were the only producers. In the Elkhorn district, Marion County, the Consolidated Copper & Power Co. was the only producer. The only mines reporting production from Wheeler County were the Mule Gulch and Sand Gulch hydraulic mines, in the Spanish Gulch district.

Digitized by Google

GOLD, SILVER, COPPER, LEAD, AND ZINC IN NEVADA.[1]

(MINES REPORT.)

By V. C. Heikes.

PRODUCTION.

GENERAL STATEMENT.

Mines in Nevada in 1917 produced 6,473,519 tons of ore, which, with placer bullion, contained gold, silver, copper, lead, and zinc valued at $54,424,580. This total represents an increase in value of $4,478,156, as compared with $49,946,424 in 1916 from 5,941,165 tons of ore and placer bullion. There were 943 producers of ore and bullion in 1917, of which 91 were placers, against 714 lode producers and 65 placers in 1916. The value of the production of copper represented nearly 62 per cent of the total value, or $33,522,954, an increase of $7,664,218. There was a decrease in the value of the production of recoverable zinc from $4,347,387 in 1916 to $2,275,402 in 1917. Silver decreased in quantity, but increased in value, owing to a higher price. The production of gold from all sources in 1917 was valued at $6,959,468, against $8,866,237 in 1916, a decrease of $1,906,769, or more than 21 per cent. The gold from placer mines decreased from $354,313 in 1916 to $292,584 in 1917. Sixteen mining companies in Nevada, some of which owned property in other States, paid dividends in 1917 amounting to $11,899,557.

Mine production of gold, silver, copper, lead, and zinc in Nevada, in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead.	Recoverable zinc.	Total value.[a]
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	779	5,941,165	$8,866,237	13,837,525	105,116,813	25,637,278	32,443,189	$49,946,424
1917	943	6,473,519	6,959,468	11,269,969	122,794,704	27,677,928	22,307,868	54,424,580
Increase or decrease, 1917	.....	+532,354	−1,906,769	−2,567,556	+17,677,891	+2,040,650	−10,135,321	+4,478,156
Total, 1904–1917	.....	46,358,897	161,538,140	156,240,386	743,868,871	161,609,267	135,987,572	411,093,218

[a] Includes placer production.

[1] The statistical tables of this report were compiled by Bessie N. Patchell, of the United States Geological Survey.

Digitized by Google

ORE.

Nevada mines produced 6,473,519 short tons of ore in 1917, an increase of 532,354 tons, compared with the production of 1916. The average total metallic value per ton was $8.36, against $8.35 in 1916, but the value per ton in gold and silver decreased from $2.96 in 1916 to $2.46 in 1917. The largest decrease in production of ore was in Churchill, Nye, Esmeralda, Clark, and Elko counties. The output of dry or siliceous ores decreased from 1,688,661 tons in 1916 to 1,413,929 tons in 1917. Under this classification for 1917 are included 589,228 tons of low-grade siliceous gold ores, averaging $6.03 in gold and 0.91 ounce of silver per ton, and carrying small quantities of copper and lead. Gold and silver mixed ores, dry or siliceous in character, aggregated 17,614 tons and averaged per ton $3.64 in gold and 5.46 ounces of silver. The output of siliceous silver ores in 1917 amounted to 807,087 tons, mined by 130 producers, averaging per ton $2.40 in gold and 11.83 ounces of silver, and carrying small quantities of copper and lead, as against 858,231 tons, mined in 1916 by 117 producers, whose ore averaged per ton $2.77 in gold and 13.94 ounces of silver. A total of 123,588 tons of oxidized iron manganese ore, which was produced entirely in the vicinity of Pioche, is included in the silver ore. This ore contained lead and small quantities of gold and silver and was particularly valuable as flux.

The production of copper ore by 247 operators amounted to 4,945,482 tons and contained 49,419.80 ounces of gold, 327,751 ounces of silver, 122,422,830 pounds of copper, and 20,876 pounds of lead, the value per ton averaging $7.02. The output of lead ores increased from 37,513 tons in 1916 to 66,614 tons in 1917. Lead ore of smelting grade amounted to 31,023 tons. In this smelting ore the oxidized ore, largely carbonates, increased in quantity from 14,428 in 1916 to 26,260 tons in 1917 and averaged $2.38 in gold, 13.17 ounces of silver, 4.48 pounds of copper, 350.85 pounds of lead, and $44.62 in total value per ton. The smelting sulphide ores of lead amounted to 4,763 tons and averaged $1.53 in gold, 22.83 ounces of silver, 6.37 pounds of copper, 680.23 pounds of lead, and $80.58 in total value per ton. Zinc ores of shipping grade decreased from 31,886 tons in 1916 to 18,393 tons in 1917, were all oxidized or carbonate ores, and averaged 642.51 pounds of zinc per ton. Production of copper-lead ores, including some old slag, decreased from 2,846 tons in 1916 to 1,158 tons in 1917, all of which was shipped to smelters. All of the first-class ore, 1,110 tons in quantity, was oxidized or carbonate copper-lead ores, averaging $4.62 in gold, 19.53 ounces in silver, 111.68 pounds of copper, 232.54 pounds of lead, and having a total value per ton of $71.20. There were 27,943 tons of lead-zinc ore produced, the largest part of which, or 27,228 tons, was concentrated into 330 tons of lead concentrate, 1,666 tons of zinc concentrate, and 94 tons of lead-zinc concentrate. Only 715 tons of lead-zinc ore was of shipping grade, and most of this (633 tons) was sulphide.

The output of milling ores was 5,649,565 tons, of which 1,125,255 tons were treated by amalgamation or cyanidation, and the remainder, 4,524,310 tons, by concentration, followed by smelting. The ores and tailings treated by cyanidation—1,057,898 tons of the former and 145,767 tons of the latter—contained an average per ton

Digitized by Google

of $3.87 in gold and 7.66 ounces of silver. The ores amalgamated, 67,357 tons, yielded bullion averaging per ton $6.67 in gold and 0.31 ounce of silver.

Mine production of gold, silver, copper, lead, and zinc in Nevada in 1917.

Source of production.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.
		Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Placers	91	.....	14,153.75	6,278	.....	.....	.....
Dry or siliceous ore	374	1,413,929	268,671.85	10,176,717	69,231	7,193,631	.....
Copper ore	247	4,945,482	49,419.80	327,751	122,422,830	20,876	.....
Lead ore	256	66,614	3,939.81	556,706	172,265	15,355,354	.....
Zinc ore	56	18,393	8.22	2,620	.....	43,027	11,817,692
Copper-lead ore	23	1,158	283.74	21,967	127,459	265,113	.....
Lead-zinc ore	9	27,943	207.09	177,930	2,919	4,799,927	10,490,176
	.....	6,473,519	336,664.26	11,269,969	122,794,704	27,677,928	22,307,868

Ore sold or treated in Nevada in 1917, in short tons.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-lead ore.	Lead-zinc ore.	Total.
Churchill	60,520	14	21	.....	32	.....	60,587
Clark	24,466	3,115	23,607	17,925	15	20,922	90,050
Douglas	11	10	2	.....	.....	.....	23
Elko	19,609	4,613	2,547	438	176	400	27,783
Esmeralda	257,364	90,338	1,326	30	97	.....	349,655
Eureka	706	248	6,079	.....	132	.....	7,165
Humboldt	94,649	7,518	2,397	.....	.....	.....	104,564
Lander	5,055	17,472	1,228	.....	93	.....	23,848
Lincoln	124,041	5,287	18,070	.....	94	6,595	154,087
Lyon	6,974	322,928	8	.....	.....	.....	329,910
Mineral	246,599	26,879	1,059	.....	34	.....	274,571
Nye	513,261	43	1,031	.....	.....	26	514,361
Ormsby	37	.....	.....	.....	.....	.....	37
Storey	59,805	.....	.....	.....	.....	.....	59,805
Washoe	434	151	2,235	.....	.....	.....	2,820
White Pine	398	4,466,366	7,004	.....	485	.....	4,474,253
	[a]1,413,929	4,945,482	66,614	18,393	1,158	27,943	6,473,519
Average value per ton in gold and silver	$9.86	$0.26	$8.10	$0.13	$20.34	$5.40	$2.46

[a] Includes 589,228 tons of gold ore, 17,614 tons of gold and silver ore, and 807,087 tons of silver ore. The last named includes 123,588 tons of oxidized iron ore.

GOLD.

The mine production of gold was valued at $6,959,468 in 1917, a decrease of $1,906,769, as compared with 1916. Nye County is credited with the largest production of gold, amounting to $2,007,234, against $2,505,714 in 1916. Esmeralda County dropped to second place in production with $1,986,001, against $2,684,688 in 1916. Goldfield district, which produced $751,076 less than in 1916, is credited with most of this output. The counties whose gold output was increased were White Pine, Lincoln, Mineral, and Douglas. The largest decreases were in Esmeralda, Nye, and Humbolt counties. Placer gold was produced in greatest quantity in Nye, Lander, and Eureka counties, the value of the total placer gold being $292,584, against $354,313 in 1916. Ore was milled in 1917 by amalgamation in 14 counties and by cyanidation in 12 counties. From these two meth-

Digitized by Google

ods of treatment $5,127,799 in gold was produced from 1,125,255 tons of ore and 145,167 tons of old tailings. The total average gold recovery from ore and tailings milled was $4.03 a ton. The gold extracted by amalgamation averaged $6.67 a ton of ore treated, as against $5.86 a ton in 1916, and by cyanidation it averaged $3.87 a ton of ore and tailings treated, as against $4.44 in 1916. From all concentrates, including siliceous, copper, lead, lead-zinc, and iron sulphide concentrates, 50,465.61 ounces of gold were produced, against 48,459.53 ounces in 1916. The gold in dry or siliceous concentrates was 4,057.75 ounces in 1917, against 13,235.26 ounces in 1916, and was principally from iron sulphide concentrates. The copper concentrates contained 46,030.84 ounces, against 34,482.46 ounces in 1916; the lead concentrates, 327.76 ounces, against 430.81 ounces in 1916; and the zinc concentrates, 49.26 ounces, against 291 ounces in 1916.

Fifteen producers furnished nearly three-fourths of the total gold in 1917. These properties which yielded more than 6,000 ounces each were the Goldfield Consolidated, with 69,632.04 ounces, followed by the Nevada Consolidated Copper mine, at Ely; the Belmont, at Tonopah; Aurora Consolidated, Tonopah Mining, Tonopah Extension; Elko Prince at Midas; Round Mountain Mining Co., in Nye County; Jim Butler, at Tonopah; Florence, at Goldfield; Olympic, in Mineral County; Nevada Wonder, in Churchill County; Union Consolidated, at Virginia City; and West End Consolidated, at Tonopah.

Mine production of gold in Nevada in 1917, in fine ounces.

County.	Placers.	Deep mines.						Total.
		Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-lead ore.	Lead-zinc ore.	
Churchill	.....	8,407.81	0.10	0.27	.....	0.17	.....	8,408.35
Clark	.....	8,911.25	980.20	700.21	8.22	.....	.....	10,599.88
Douglas	14.51	23.23	.....	.04	.....	.....	.....	37.78
Elko	29.32	11,768.07	9.72	12.92	.....	4.71	.....	11,824.74
Esmeralda	.....	85,208.90	10,644.74	217.78	.....	1.38	.....	96,072.80
Eureka	133.56	385.39	.....	934.77	.....	11.17	.....	1,464.89
Humboldt	58.34	11,717.02	43.70	112.39	.....	.....	.....	11,931.45
Lander	3,228.84	869.19	165.84	207.73	.....	227.35	.....	4,698.95
Lincoln	.....	919.34	54.62	1,186.75	.....	.26	204.52	2,365.49
Lyon	3.58	2,413.16	23.53	.49	.....	.....	.....	2,440.76
Mineral	20.70	33,656.42	688.95	125.11	.....	.34	.....	34,491.52
Nye	10,600.46	86,331.08	1.29	164.54	.....	.....	2.57	97,099.94
Ormsby	.....	3.68	.....	.....	.....	.....	.....	3.68
Storey	.....	17,457.33	.....	.....	.....	.....	.....	17,457.33
Washoe	5.81	496.81	21.50	1.91	.....	.....	.....	526.03
White Pine	58.63	103.17	36,785.61	274.90	.....	18.36	.....	37,240.67
	14,153.75	[a]268,671.85	49,419.80	3,939.81	8.22	263.74	207.09	336,664.26

[a] Includes 171,815.25 ounces from gold ore, 3,099.45 ounces from gold and silver ore, and 93,757.15 ounces from silver ore.

SILVER.

The mine production of silver in Nevada in 1917 was 11,269,969 ounces, valued at $9,286,454, a decrease of 2,567,556 ounces in quantity but an increase of $181,362 in value, as compared with the output of 1916. Nye County was again the largest producer, with 7,172,642 ounces, against 8,868,267 ounces in 1916; and Churchill County produced 887,765 ounces, against 1,386,524 ounces in 1916.

Digitized by Google

Milling plants using amalgamation and cyanidation in the extraction of the precious metals produced 9,241,543 ounces of silver, of which 21,191 ounces were recovered by amalgamation and 9,220,352 ounces by cyanidation. Nye County was credited with the largest production of silver by cyanidation—6,840,570 ounces—from ores treated principally in the Tonopah district. In Churchill County, 878,619 ounces of silver were recovered by cyanidation. Concentrates from milling plants yielded 713,459 ounces of silver against 1,107,119 ounces in 1916. Siliceous concentrates contained 309,160 ounces, against 759,370 ounces in 1916; copper concentrates produced 150,950 ounces, against 99,152 ounces in 1916. Lead concentrates contained 191,989 ounces of silver, or an average per ton of 27.89 ounces, against 133,827 ounces, or an average per ton of 26.53 ounces, in 1916. Zinc concentrates contained 61,315 ounces, or an average per ton of 3.36 ounces, and the lead-zinc concentrates contained 45 ounces, or 0.48 ounce per ton.

About 65 per cent of the total silver was produced in 1917 from six mines. The Belmont mines yielded 1,946,757 ounces, followed by the Tonopah Mining, Tonopah Extension, and Jim Butler, all at Tonopah, the Nevada Wonder, in Churchill County, and the West End, at Tonopah.

Mine production of silver in Nevada in 1917, in fine ounces.

County.	Placers.	Deep mines.						Total.
		Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-lead ore.	Lead-zinc ore.	
Churchill	.....	885,801	1,243	317	.....	404	.....	887,765
Clark	.....	92,807	10,594	63,581	2,620	145	150,089	319,836
Douglas	2	6	3	88	.....	.....	.....	99
Elko	8	187,128	30,973	42,626	.....	3,295	211	264,241
Esmeralda	.....	81,984	42,611	31,732	.....	891	.....	157,218
Eureka	16	9,760	124	60,754	.....	1,606	.....	72,269
Humboldt	10	816,182	18,973	24,672	.....	.....	.....	859,837
Lander	460	72,056	11,063	36,910	.....	5,581	.....	126,070
Lincoln	.....	321,673	30,416	143,101	.....	1,167	27,042	523,399
Lyon	2	4,163	1,446	151	.....	.....	.....	5,762
Mineral	14	317,920	57,640	31,216	.....	512	.....	407,302
Nye	5,754	7,136,986	1,185	28,129	.....	.....	588	7,172,642
Ormsby	.....	1,662	.....	.....	.....	.....	.....	1,662
Storey	.....	243,072	.....	.....	.....	.....	.....	243,072
Washoe	2	895	1,171	40,153	.....	.....	.....	42,221
White Pine	10	4,613	120,309	53,276	.....	8,366	.....	186,574
	6,278	[a] 10,176,717	327,751	556,706	2,620	21,967	177,930	11,269,969

[a] Includes 534,499 ounces from gold ore, 96,125 ounces from gold and silver ore, and 9,546,093 ounces from silver ore.

COPPER.

Ores mined and treated or shipped in 1917 yielded 122,794,704 pounds of copper, valued at $33,522,954, an increase of 17,677,891 pounds in quantity and of $7,664,218 in value. The Nevada Consolidated mines at Ely, in White Pine County, produced the largest share of the State total, followed by the mines in the Yerington district of Lyon County. White Pine County mines produced 93,786,328 pounds in 1917, against 93,107,945 pounds in 1916; Lyon County mines, 19,397,002 pounds, against 3,491,390 pounds in 1916; Mineral County mines, 3,461,969 pounds, against 2,986,361 pounds; Lander

Digitized by Google

County mines, 2,480,602 pounds, against 576,493 pounds; and Elko County mines, 887,371 pounds, against 1,771,689 pounds. Concentrates recovered at milling plants contained 86,901,725 pounds of copper, against 88,117,957 pounds in 1916. Of the output in 1917, copper concentrates contained 86,896,898 pounds, against 88,077,620 pounds in 1916. Crude ore shipped to smelters contained 35,565,796 pounds of copper, against 16,764,814 pounds in 1916. The crude copper ores smelted contained 35,228,249 pounds, of which 440,195 pounds were produced from sulphide ores and 34,788,054 pounds from oxidized ores. Lead ores of smelting grade produced 148,039 pounds of copper—30,388 pounds from sulphide ores and 117,651 pounds from oxidized ores. Copper-lead ores shipped, all of which were oxidized, contained 123,969 pounds of copper.

Eight mines produced 95 per cent of the total copper in 1917. The Nevada Consolidated and the Consolidated Copper mines, near Ely, had the greatest output, followed by the Mason Valley, and the Nevada Douglas, in Lyon County; the Copper Canyon, in Lander County; the Wall Street, in Mineral County; and the Goldfield Consolidated in Esmeralda County.

Mine production of copper in Nevada in 1917 in pounds.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Copper-lead ore.	Lead-zinc ore.	Total
Churchill	.....	1,728	80	2,222	.....	4,030
Clark	281	857,835	16,876	3,654	.....	878,646
Douglas	.....	1,986	.....	.....	.....	1,986
Elko	310	852,352	12,773	21,936	.....	887,371
Esmeralda	28,240	705,447	23,104	5,836	.....	762,627
Eureka	315	42,763	20,384	9,379	.....	72,841
Humboldt	250	567,052	308	.....	.....	567,610
Lander	4,968	2,443,834	9,765	22,035	.....	2,480,602
Lincoln	12,397	351,160	67,419	6,302	2,919	440,197
Lyon	.....	19,396,954	48	.....	.....	19,397,002
Mineral	18,030	3,439,358	1,501	3,080	.....	3,461,969
Nye	342	8,406	6,781	.....	.....	15,529
Ormsby	363	.....	.....	.....	.....	363
Washoe	1,110	36,443	50	.....	.....	37,603
White Pine	2,625	93,717,512	13,176	53,015	.....	93,786,328
	[a] 69,231	122,422,830	172,265	127,459	2,919	122,794,704

[a] Includes 29,079 pounds from gold ore, 502 pounds from gold and silver ore, and 39,650 pounds of silver ore.

LEAD.

The mine production of lead in Nevada in 1917 was 27,677,928 pounds, valued at $2,380,302, against 25,637,278 pounds, valued at $1,768,972, in 1916, an increase in 1917 of 2,040,650 pounds in quantity and $611,330 in value. Lincoln County mines continued to have the largest output, 10,714,152 pounds, in 1917, followed by Clark County mines, with 9,373,817 pounds, and by White Pine County mines, with 2,437,908 pounds. More than 25 per cent of the output of lead was derived from concentrates and more than 72 per cent from crude ore shipped directly to smelters. Lead concentrates (carbonates and sulphides) shipped to smelters from the milling plants of the State contained 5,865,304 pounds, against 4,983,673 in 1916, and averaged 42.60 per cent of lead in 1917, against 49.40 per cent in 1916. Zinc concentrates shipped in 1917 contained 1,137,697

Digitized by Google

pounds of lead and averaged 3.12 per cent. The total crude ore of shipping grade contained 20,068,411 pounds of lead, against 19,189,934 pounds in 1916. The iron-manganese ores, classified under dry or siliceous ores, contained 7,142,452 pounds of lead. Oxidized lead ore shipped to smelters contained 9,213,315 pounds of lead and suphide ore, 3,239,963 pounds, against 5,711,549 pounds and 3,862,549 pounds, respectively, in 1916. Zinc ores shipped produced 43,027 pounds of lead, all of which was from oxidized ores, and copper-lead ores of shipping grade, all oxidized, produced 258,124 pounds of lead. The oxidized lead-zinc ores of smelting grade produced 15,285 pounds of lead, and sulphide lead zinc ores contained 91,492 pounds of lead.

About 41 per cent of the lead was from five mines and the remainder from numerous properties. The leading producer was the Prince Consolidated mine, near Pioche, Lincoln County, followed by the Groom mine, also in Lincoln County, the Union mines, in Eureka County, and the Bullion mine, in the Yellowpine district of Clark county.

Mine production of lead in Nevada in 1917, in pounds.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-lead ore.	Lead-zinc ore.	Total.
Churchill	.....	.....	17,145	.....	16,806	.....	33,951
Clark	4,956	.....	4,746,807	43,027	3,428	4,575,599	9,373,817
Douglas	.....	.....	1,226	.....	.....	.....	1,226
Elko	.....	13,305	956,275	.....	33,717	60,848	1,064,145
Esmeralda	23,910	.....	389,806	.....	34,715	.....	448,431
Eureka	1,334	.....	1,736,591	.....	46,008	.....	1,783,933
Humboldt	3,629	.....	507,592	.....	.....	.....	511,221
Lander	11,368	.....	284,102	.....	12,918	.....	308,388
Lincoln	7,142,452	6,710	3,396,277	.....	11,881	156,832	10,714,152
Lyon	.....	.....	2,250	.....	.....	.....	2,250
Mineral	2,607	.....	344,113	.....	11,156	.....	357,876
Nye	764	861	421,752	.....	.....	6,648	430,025
Washoe	393	.....	210,212	.....	.....	.....	210,605
White Pine	2,218	.....	2,341,206	.....	94,484	.....	2,437,908
	[a]7,193,631	20,876	15,355,354	43,027	265,113	4,799,927	27,677,928

[a] Includes 6,469 pounds from gold ore, 2,482 pounds from gold and silver ore, and 7,184,680 pounds from silver ore.

ZINC.

The mine production of recoverable zinc from zinc and lead-zinc ores mined in Nevada in 1917 is calculated at 22,307,868 pounds, valued at $2,275,402, against 32,443,189 pounds, valued at $4,347,387, in 1916. Clark County is credited with the largest part of the output, or 20,660,549 pounds of zinc, most of which came from the Yellowpine district. The remainder of the zinc output was from the Pioche district, in Lincoln County, and from Elko, Esmeralda, and Nye counties. Zinc concentrates amounted to 18,237 tons and averaged 27.94 per cent of zinc. Lead-zinc concentrates contained an average of 37.59 per cent of recoverable zinc, against 25 per cent in 1916. The shipments of crude zinc ore amounted to 18,393 tons, were all oxidized or carbonate ores, and averaged 32.13 per cent of recoverable zinc. The lead-zinc ore, most of which was from one mine at Pioche, averaged 15.97 per cent of recoverable zinc, and was shipped east to an oxide plant.

Digitized by Google

Nearly 80 per cent of the total zinc was from the ores from four mines, the Yellowpine, Potosi, and Ingomar, all in Clark County, and the Amalgamated Pioche mines, in Lincoln County.

Mine production of recoverable zinc in Nevada in 1917, in pounds.

County.	Zinc ore.	Lead-zinc ore.	Total.
Clark	11,579,611	9,080,938	20,660,549
Elko	222,679	70,675	293,354
Esmeralda	15,402	.....	15,402
Lincoln	.....	1,332,521	1,332,521
Nye	.....	6,042	6,042
	11,817,692	10,490,176	22,307,868

Zinc-producing ores and concentrates from Nevada mines sold in 1917.

Classification.	County.	Quantity.	Average zinc assay of ore and concentrate.[a]
		Short tons.	*Per cent.*
Sulphide lead-zinc ore	Lincoln and Nye	633	17.61
Oxidized zinc ore	Clark, Elko, and Esmeralda	18,393	37.80
Oxidized lead-zinc ore	Clark	82	28.11
Zinc concentrates	Clark and Lincoln	18,237	37.90
Lead-zinc concentrates	Elko	94	44.23
		37,439	35.07

[a] Actual assay content.

MINING INDUSTRY.

The year 1917 was one in which mining operations everywhere faced unusual difficulties, caused to a great extent by war conditions. It was especially trying for new enterprises or companies that were endeavoring to increase the capacity of their plants. The two principal gold and silver camps recorded large decreases in those metals—Goldfield in gold and Tonopah in silver. Discoveries and shipments of silver ore of good grade were made from virgin deep workings on the Comstock lode where pumping lowered the water below the 3,000-foot level. The copper output was increased by the resumption of operations in February at the Mason Valley smelter at Thompson. Several milling plants throughout the State were built or enlarged. The Consolidated Copper Mines Co. completed its 1,000-ton flotation plant at Kimberly, and at Manhattan, Round Mountain, Tuscarora, and Rochester new mills were built or new processes were installed in old mills.

Ores of various kinds were milled at 79 plants, against 84 plants in 1916. Many of these were operated for only short periods each year. Twenty plants used the amalgamation process, against 27 in 1916; 8, both amalgamation and table concentration, against 6 in 1916; 1, amalgamation and cyanidation, against 3 in 1916; and 3 used amalgamation, table concentration, and cyanidation. Eighteen plants, against 15 in 1916, used concentration, of which four were equipped with the oil flotation process in conjunction with tables.

Digitized by Google

and 2 were equipped for oil flotation only. Twenty-five straight cyanidation mills were operated in 1917, against 31 in 1916; and 3 mills used cyanidation and concentration, against 2 in 1916. At one plant, in Lyon County, experimental work with the leaching process was done.

During 1917 there were 839 pounds of quicksilver consumed at amalgamation mills. At cyanide mills, 130 pounds of potassium cyanide and 1,925,038 pounds of sodium cyanide were used, or 1,925,168 pounds of both. There was a consumption of 0.02 pound of mercury per ounce of gold and silver bullion produced and of 0.012 pound of mercury per ton of ore treated; the consumption of cyanide was 0.20 pound per ounce of gold and silver bullion produced and 1.60 pounds per ton of ore and tailings treated.

The total value of bullion recovered from ore and tailings was $12,742,830, against $14,295,539 in 1916.

Gold and silver produced from Nevada mills in 1917.

County.	Ore.	Bullion recovered from ore by—				Total value.
		Amalgamation.		Cyanidation.		
		Gold.	Silver.	Gold.	Silver.	
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Fine ounces.*	*Fine ounces.*	
Churchill	60,493	5.35	2	8,261.16	878,619	$894.868
Clark	[a] 14,415	1,636.63	9,230	[b] 6,101.69	[b] 69,615	224,933
Douglas	10	19.83	2	.....	.....	412
Elko	19,468	166.32	99	11,402.85	179,991	387,550
Esmeralda	168,698	1,967.08	639	[c] 70,625.06	[c] 51,519	1,544,004
Eureka	450	116.04	39	.....	.....	2,431
Humboldt	[d] 93,677	3,841.15	3,419	[e] 7,351.89	[e] 782,569	879,035
Lander	[f] 2,801	91.25	88	470.98	1,394	12,843
Lincoln	453	.....	.....	226.75	67	4,742
Lyon	2,353	1,950.27	1,424	[g] 441.42	[g] 2,736	52,869
Mineral	[h] 202,748	275.48	125	[i] 32,704.52	[i] 188,780	837,415
Nye	[j] 509,692	8,999.66	4,131	[k] 75,313.46	[k] 6,840,570	7,382,941
Storey	[l] 49,640	2,170.60	1,755	[m] 13,412.04	[m] 224,458	508,521
Washoe	341	469.15	235	.....	.....	9,892
White Pine	16	11.71	3	4.96	31	374
	1,125,255	21,740.52	21,191	226,316.78	9,220,352	12,742,830

[a] Also yielded 111 tons of concentrates.
[b] Includes bullion from 10,000 tons of old tailings.
[c] Includes bullion from 81,885 tons of old tailings.
[d] Also yielded 38 tons of concentrates.
[e] Includes bullion from 310 tons of old tailings.
[f] Also yielded 14 tons of concentrates.
[g] Includes bullion from 4,620 tons of old tailings.
[h] Also yielded 2 tons of concentrates.
[i] Includes bullion from 37,217 tons of old tailings.
[j] Also yielded 851 tons of concentrates.
[k] Includes bullion from 1,650 tons of old tailings.
[l] Also yielded 170 tons of concentrates.
[m] Includes bullion from 10,085 tons of old tailings.

Mills equipped for the concentration of low-grade ore treated 4,524,310 tons, or nearly 70 per cent of the total ore sold or treated. The concentrates aggregated 627,416 tons and contained $1,043,217 in gold, 713,459 ounces of silver, 86,901,725 pounds of copper, 7,019,812 pounds of lead, and 10,261,726 pounds of recoverable zinc, valued in all at $27,005,678, or a total average value per ton of $43.04.

Digitized by Google

Mine production of gold, silver, copper, lead, and zinc from Nevada concentrates in 1917.

By counties.

County.	Ore to concentrating mills.	Concentrates.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value of concentrates.
	Short tons.	*Short tons.*	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
Churchill	.....	54	52.53	6,818	.....	.....	.....	$6,704
Clark	38,748	21,600	781.12	179,082	281	5,872,856	9,042,002	1,591,137
Elko	400	133	.....	211	.....	60,849	70,675	12,616
Esmeralda	88,600	5,943	10,479.97	40,024	513,369	.....	.....	389,770
Eureka	40	17	.....	106	.....	4,082	.....	438
Humboldt	125	51	245.18	4,901	.....	1,626	.....	9,246
Lander	1,658	158	41.10	11,792	945	59,859	.....	15,973
Lincoln	5,988	2,926	340.95	34,214	2,984	499,131	1,149,049	196,183
Mineral	93	19	4.63	146	3,404	1,745	.....	1,295
Nye	1,360	885	1,748.06	269,257	342	.....	.....	258,097
Storey	.....	170	1,201.49	7,027	.....	.....	.....	30,627
Washoe	2,066	298	1.83	40,087	50	198,878	.....	50,188
White Pine	4,385,232	595,162	35,568.75	119,794	86,380,350	330,787	.....	24,443,404
	4,524,310	627,416,	50,465.61	713,459	86,901,725	7,019,812	10,261,726	27,005,678
By kinds of concentrates.								
Dry or siliceous	.....	1,344	4,057.75	309,160	1,787	6,323	.....	$339,661
Copper	.....	600,857	46,030.84	150,950	86,896,898	.....	.....	24,798,778
Lead	.....	6,884	327.76	191,989	3,040	5,865,304	.....	670,221
Zinc	.....	18,237	49.26	61,315	.....	1,137,697	10,191,051	1,188,870
Lead-zinc	.....	94	.....	45	.....	10,488	70,675	8,148

All the higher grade ores were shipped crude to the smelters, the copper ores in greatest quantity and in value. There were 658,447 tons of ore smelted in 1917, as compared with 371,053 tons in 1916. The output of smelting ores by counties follows:

Mine production of gold, silver, copper, lead, and zinc from Nevada crude ore shipped to smelters in 1917.

By counties.

County.	Quantity.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
Churchill	94	89.31	2,326	4,030	33,951	.....	$7,782
Clark	26,444	1,702.88	60,770	806,765	3,500,961	11,618,547	1,791,697
Douglas	13	3.44	95	1,986	1,226	.....	796
Elko	7,915	226.25	83,932	887,371	1,003,297	222,679	425,086
Esmeralda	10,472	12,980.69	65,036	207,003	448,431	15,402	418,573
Eureka	5,861	934.99	66,757	57,997	1,702,115	.....	236,531
Humboldt	5,935	412.74	59,177	434,110	120,412	.....	186,161
Lander	19,389	866.78	112,336	2,479,657	248,529	.....	808,802
Lincoln	137,090	1,730.04	483,953	427,946	10,099,224	183,472	1,438,616
Lyon	322,371	45.49	1,600	19,350,592	2,250	.....	5,285,165
Mineral	32,154	1,398.80	171,632	3,458,565	356,131	.....	1,145,157
Nye	1,605	407.59	51,495	15,187	430,025	6,042	92,602
Ormsby	37	3.68	1,662	363	.....	.....	1,544
Storey	80	673.20	9,832	.....	.....	.....	22,018
Washoe	263	49.24	1,897	37,553	11,727	.....	13,841
White Pine	88,724	1,581.13	66,446	7,396,671	2,110,132	.....	2,288,199
	658,447	23,105.25	1,238,946	35,565,796	20,068,411	12,046,142	14,162,570
By kinds of ore.							
Dry or siliceous	137,700	15,952.72	576,337	65,539	7,186,329	.....	$1,440,590
Copper	469,506	3,495.27	172,435	35,229,249	20,876	.....	9,833,448
Lead	31,023	3,370.52	454,566	148,039	12,453,278	.....	1,555,634
Zinc	18,393	8.25	2,620	.....	43,027	11,817,692	1,211,433
Copper-lead	1,110	248.24	21,680	123,969	258,124	.....	79,037
Lead-zinc	715	30.25	11,308	.....	106,777	228,450	42,428

Digitized by Google

PRODUCTION BY COUNTIES.

The following tables show the State output, by counties, in 1917, the production of each metal, and the total value; also the production of ore, the average value per ton by counties, in 1916 and 1917; and the statistics of placer mines. The tables are followed by a review of the mining industry for each county and each producing mining district.

Mine production of gold, silver, copper, lead, and zinc in Nevada in 1917.

County.	Gold.					Silver.	
	Placers.		Deep mines.		Total value.	Quantity.	Value.
	Quantity.	Value.	Quantity.	Value.			
	Fine ounces.		*Fine ounces.*			*Fine ounces.*	
Churchill			8,408.35	$173,816	$173,816	887,765	$731,518
Clark			10,599.88	219,119	219,119	319,836	263,545
Douglas	14.51	$300	23.27	481	781	99	81
Elko	29.32	606	11,795.42	243,833	244,439	264,241	217,734
Esmeralda			96,072.80	1,986,001	1,986,001	157,218	129,548
Eureka	133.56	2,761	1,331.33	27,521	30,282	72,269	59,550
Humboldt	58.34	1,206	11,873.11	245,439	246,645	859,837	708,506
Lander	3,228.84	66,746	1,470.11	30,390	97,136	126,070	103,882
Lincoln			2,365.49	48,899	48,899	523,399	431,281
Lyon	3.58	74	2,437.18	50,381	50,455	5,762	4,748
Mineral	20.70	428	34,470.82	712,575	713,003	407,302	335,617
Nye	10,600.46	219,131	86,499.48	1,788,103	2,007,234	7,172,642	5,910,257
Ormsby			3.68	76	76	1,662	1,369
Storey			17,457.33	360,875	360,875	243,072	200,291
Washoe	5.81	120	520.22	10,754	10,874	42,221	34,790
White Pine	58.63	1,212	37,182.04	768,621	769,833	186,574	153,737
	14,153.75	292,584	322,510.51	6,666,884	6,959,468	11,269,969	9,286,454

Mine production of gold, silver, copper, lead, and zinc in Nevada in 1917.

County.	Copper.		Lead.		Recoverable zinc.		Total value.
	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	
	Pounds.		*Pounds.*		*Pounds.*		
Churchill	4,030	$1,100	33,951	$2,920			$909,354
Clark	878,646	239,870	9,373,817	806,148	20,660,549	$2,107,376	3,636,058
Douglas	1,986	542	1,226	106			1,510
Elko	887,371	242,252	1,064,145	91,517	293,354	29,922	825,864
Esmeralda	762,627	208,197	448,431	38,565	15,402	1,571	2,363,882
Eureka	72,841	19,886	1,783,933	153,418			263,136
Humboldt	567,610	154,958	511,221	43,965			1,154,074
Lander	2,480,602	677,204	308,388	26,521			904,743
Lincoln	440,197	120,174	10,714,152	921,417	1,332,521	135,917	1,657,688
Lyon	19,397,002	5,295,382	2,250	194			5,350,779
Mineral	3,461,969	945,117	357,876	30,777			2,024,514
Nye	15,529	4,239	430,025	36,982	6,042	616	7,959,328
Ormsby	363	99					1,544
Storey							561,166
Washoe	37,603	10,266	210,605	18,112			74,042
White Pine	93,786,328	25,603,668	2,437,908	209,660			26,736,898
	122,794,704	33,522,954	27,677,928	2,380,302	22,307,868	2,275,402	54,424,580

Digitized by Google

Production from deep mines in Nevada in 1916 and 1917.

County.	Ore sold or treated.		Number of deep mines producing.		Average value per ton.[a]		Average value per ton in gold and silver.[a]	
	1917	Increase or decrease.	1916	1917	1916	1917	1916	1917
	Short tons.	*Short tons.*						
Churchill	60,587	− 50,356	20	13	$10.81	$15.01	$10.78	$14.94
Clark	90,050	− 13,324	85	106	50.64	40.38	5.56	5.36
Douglas	23	− 61	3	4	17.82	52.52	.31	24.35
Elko	27,783	− 12,946	75	77	26.99	29.70	11.25	16.61
Esmeralda	349,655	− 39,696	59	61	8.14	6.76	7.18	6.05
Eureka	7,165	− 14,917	30	40	18.86	36.34	9.01	12.15
Humboldt	104,564	− 5,119	84	100	9.13	11.03	8.78	9.12
Lander	23,848	+ 7,749	30	47	21.22	35.12	11.55	5.61
Lincoln	154,087	− 8,066	23	23	9.77	10.76	2.48	3.12
Lyon	329,910	+298,488	44	64	30.61	16.22	3.28	.17
Mineral	274,571	+ 8,388	93	129	6.56	7.37	3.73	3.82
Nye	514,361	− 50,089	73	79	14.47	15.04	14.45	14.96
Ormsby	37	− 70	3	1	6.46	41.73	6.15	39.05
Storey	59,805	− 3,382	24	33	10.64	9.38	10.62	9.38
Washoe	2,820	− 2,241	28	31	25.68	26.21	14.19	16.15
White Pine	4,474,253	+417,996	40	44	5.88	5.98	.21	.21
	6,473,519	+532,354	714	852	8.35	8.36	2.96	2.46

[a] Value per ton, placer product excluded.

Production from placer mines in Nevada in 1916 and 1917.

County.	1916					1917				
	Mines.		Gold.	Silver.	Total value.	Mines.		Gold.	Silver.	Total value.
	Hydraulic.	Drift.				Hydraulic.	Drift.			
				Fine ounces.					*Fine ounces.*	
Douglas	2	.....	$88	.....	$88	1	.....	$300	2	$302
Elko	1	.....	48	1	49	3	.....	606	8	613
Eureka	6	.....	10,373	44	10,402	5	.....	2,761	16	2,774
Humboldt	6	5	7,174	90	7,233	3	1	1,206	10	1,214
Lander	1	10	153,698	1,050	154,389	27	6	66,746	460	67,125
Lyon	3	.....	2,328	40	2,354	.....	1	74	2	76
Mineral	2	1	743	11	750	3	1	428	14	43[c]
Nye	24	3	179,165	4,501	182,127	24	11	219,131	5,754	223,872
Washoe	.....	.....	.....	.....	.....	2	.....	120	2	122
White Pine	1	.....	696	7	701	3	.....	1,212	10	1,220
	46	19	354,313	5,744	358,093	71	20	292,584	6,278	297,757

CHURCHILL COUNTY.

There were 60,587 tons of ore mined in Churchill County in 1917 by 13 producers, against an output of 110,943 tons mined by 20 producers in 1916. The total average value per ton increased from $10.81 in 1916 to $15.01 in 1917. Only a small quantity of ore containing copper and lead was shipped. The larger part of the output was of milling grade and yielded gold and silver bullion at cyanidation plants. Some concentrate from a gold and silver mill was shipped directly to the smelters, as was also 94 tons of crude ore containing gold and silver, with some copper and lead.

Eagleville district.—The Golden Extension property was reported as a producer of siliceous gold ore carrying a little silver.

Eastgate district.—Several small prospects produced altogether 49 tons of ore, yielding principally lead with some gold and silver and a little copper.

Digitized by Google

Fairview district.—The Nevada Hills property, after steadily producing for more than 9 years, was given its final clean-up, after which it was closed. Some gold and silver bullion and concentrate were shipped. According to the annual report of the company[1] 4,683 tons of ore were milled and cyanided, and yielded silver bullion valued at $18,811.93. From the treasury $319,706 was paid out in dividends during 1917.[1] The company report contains the following:

> Your company operated its property and mill during the months of January and February, 1917, at which time a cold wave struck the State causing the lowest temperature that had visited Nevada in a number of years. The water supply line became frozen and necessitated the shutting down of operations until the month of May. In that month operations were resumed, but despite the increased price of silver it was found that it was impossible to operate the property at a profit. The ore reserves had become so depleted and the mineral content so low that the recovery would not meet the expenses. Therefore in the month of June the property was permanently shut down and preparation made for disposal of the plant as junk and second-hand material.

Jessup district.—A small lot of silver ore, containing a little gold, was shipped from the district in 1917.

Wonder district.—The principal production of the district continues to come from the Nevada Wonder mine,[2] which produced 55,800 tons of ore in 1917, averaging 0.141 ounce of gold and 16.65 ounces of silver per ton. This ore was treated by the cyanide process and yielded bullion containing 7,512 ounces of gold and 816,852 ounces of silver, valued at $822,940, representing a recovery of 95.32 per cent of the gold content and 87.9 per cent of the silver. The silver saving in 1916 was 91.9 per cent, and its decreased recovery in 1917 is discussed in the company's annual report as follows:

> The low recovery of silver contents was caused by a change from the readily soluble silver minerals in the ore to the more complex and less soluble silver minerals found at depth in the mine. * * * The only remedy for this was the installation of concentrators for removing the less soluble sulphides. It was decided to install four Senn concentrators, and the concentrator unit will be ready for service about January 15, 1918, after which date it is thought the silver recovery will approach the former excellent record.

The direct mining cost per ton of ore treated was $4.46 per ton in 1916, against $5.41 per ton in 1917. The indirect costs were 83 cents and 97 cents per ton, respectively. The following table gives the combined mining and milling costs and the profits per ton of the ore mined and milled, compared with those of the three previous years:

	1914	1915	1916	1917
Total mining costs per ton of ore, including transportation	$4.70	$4.19	$5.33	$6.43
Total milling costs per ton of ore	3.37	2.81	3.31	4.12
Marketing costs per ton of ore	.28	.27	.26	.23
Total costs per ton	8.35	7.27	8.90	10.78
Average value per ton of ore	15.52	13.97	15.40	16.55
Loss in tailing per ton of ore	1.06	.82	1.13	1.80
Recovery per ton	14.46	13.15	14.27	14.75
Less total costs per ton	8.35	7.27	8.90	10.78
Profit per ton of ore mined and milled	6.11	5.88	5.37	3.97

[1] Nevada Hills Mining Co. Ann. Rept. for year ending Dec. 31, 1917.
[2] Nevada Wonder Mining Co. Eleventh Ann. Rept., for year ending Dec. 31, 1917.

Digitized by Google

Altogether the dividends paid Nevada Wonder stockholders since May 20, 1913, amount to $1,196,886.95, of which $281,681.80 was paid in 1917.

CLARK COUNTY.

Mine production in Clark County, Nev., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	85	103,374	$308,272	404,788	573,088	8,405,796	29,400,537	$5,235,275
1917	106	90,050	219,119	319,836	878,646	9,373,817	20,660,549	3,636,058
Increase or decrease, 1917	.....	−13,324	−89,153	−84,952	+305,558	+968,021	−8,739,988	−1,599,217

The production in 1917 of 90,050 tons of ore by 106 producers was 13,324 tons less than was produced by 85 mines in 1916. The total average value per ton decreased from $50.64 in 1916 to $40.38 in 1917, and the gold and silver value per ton in this ore decreased from $5.56 to $5.36. Of the total ore, 26,444 tons were shipped directly to the smelters and produced $35,201 in gold, 60,770 ounces of silver, 806,765 pounds of copper, 3,500,961 pounds of lead, and 11,618,547 pounds of recoverable zinc, valued at $1,791,697, or an average value per ton of $67.74. There were 37,748 tons of ore treated by concentration or separation processes, which produced lead concentrates, zinc concentrates, and a small quantity of lead-zinc and copper-lead concentrates. The 21,600 tons of concentrates produced had a metal content of $16,147 in gold, 179,082 ounces of silver, 281 pounds of copper, 5,872,856 pounds of lead, and 9,042,002 pounds of recoverable zinc, valued in all at $1,591,137, or an average value per ton of $73.66. At gold and silver mills, 14,415 tons of ore were treated and produced $159,965 in gold and 78,845 ounces of silver.

Crescent district.—Very little activity was reported in the district, and only one small lot of lead ore was shipped.

Eldorado Canyon district.—Seven operators reported 12,689 tons, yielding $137,079 in gold, 90,618 ounces of silver, 281 pounds of copper, and 4,956 pounds of lead, valued in all at $212,251, or an average value per ton of $16.73. The bulk of this ore was treated in gold and silver mills and yielded some gold and silver concentrate containing a little lead and copper. There were only 6 tons of crude gold and silver ore shipped from the district. The principal producer was the Techatticup mine, on which a 50-ton cyanide plant was operated. The ore produced is both oxidized and sulphide with a siliceous gangue. The Rand mine, which yielded bullion from treatment by amalgamation and a little lead concentrate, was the next in importance as a producer of milling ore. The Lombard, Lucky Jim, Flagstaff, and Carnation mines were also producers.

Gas Peak district.—From the June Bug property some oxidized zinc ore was shipped during three months' operation of the property in 1917.

Digitized by Google

Gold Butte district.—The Lincoln property yielded copper ore of shipping grade, and some oxidized zinc ore was shipped from the Black Jack claim.

Las Vegas district.—The Johnnie Stump prospect, situated about 8 miles west of Las Vegas, was a producer of a small quantity of oxidized copper ore.

Searchlight district.—There were 14 producers who reported 12,866 tons of ore, containing $71,213 in gold, 9,073 ounces of silver, 98,923 pounds of copper, and 59,453 pounds of lead, valued in all at $110,808, or an average value per ton of $8.61. More than half of the ore was of milling grade, yielding bullion in gold and silver mills, and 1,134 tons were shipped directly to the smelter and contained 1,526.64 ounces of gold, 7,101 ounces of silver, and all the copper and lead. There were also about 10,000 tons of old tailings re-treated by the cyanidation process, yielding some gold and silver bullion. The Quartette property, worked largely by lessees, was the principal producer of gold and silver. Some of the ore containing copper was shipped directly to the smelter. The Duplex mine was also a producer of gold and silver bullion, and also yielded some oxidized lead ores containing copper. Other producers were the Chief of the Hills, Cyrus Noble, Spokane, and Parallel properties.

Yellow Pine district.—Seventy-nine producers reported the production of 64,260 tons of ore, containing $10,656 in gold, 219,789 ounces of silver, 764,733 pounds of copper, 9,298,706 pounds of lead, and 20,535,768 pounds of recoverable zinc, valued in all at $3,294,870, or an average value per ton of $51.27. More than half of the ore, or 38,748 tons, was milled and yielded 21,489 tons of concentrate containing 166,674 ounces of silver, 5,867,900 pounds of lead, and 9,042,002 pounds of recoverable zinc. The ore shipped directly to the smelters, some of it through the Jean sampling works, amounted to 25,069 tons, containing 137.94 ounces of gold, 51,976 ounces of silver, 693,133 pounds of copper, 3,430,806 pounds of lead, and 11,493,766 pounds of recoverable zinc. The principal producer was the Yellow Pine mine, and other producers of more than 1,000 tons of ore were the Bullion, Anchor, Ingomar, Campbell Estate, Potosi, and Sultan. The ore sampling company, which completed a plant at Jean in April, was preparing to close and dismantle it at the end of the year, having had very little profitable business. In addition to the producing properties mentioned, the output of the Boss mine was an important one. The ore shipped to the Palau metal works at Los Angeles was reported to contain 49 ounces of gold and 85 ounces of combined platinum and palladium. This ore is the plumbojarosite, which, according to Knopf,[1] carries the rare metals. The experimental mill at the Boss mine was not successfully operated, so after June nearly all of the ore was shipped to various smelters, the low-grade copper ore containing small quantities of the rare metals going to Garfield, Utah, and Irvington, N. J. The total output of the Boss mine[2] was 1,098.7 tons of ore, of which 359.91 tons averaged per ton 0.8364 ounce of gold, 2.61 ounces of silver, 0.2573 ounce of platinum, and 0.9842 ounce of pal-

[1] Knopf, Adolph, A gold-platinum-palladium lode in southern Nevada: U. S. Geol. Survey Bull. 620, pp. 1–18, 1916.
[2] Boss Gold Mining Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

ladium. In addition to this, the ore contained 8.5 per cent of copper, which, with all the other metals, yielded the company $42,193.77. The straight copper ore, 621.17 tons, contained 9.74 per cent of copper and also contained an average per ton of 0.0925 ounce of gold, 2.083 ounces of silver, and 0.075 ounce of combined platinum and palladium. This ore netted the company $20,645.74, making a total of $62,839.51 received from the smelters in 1917.

At the Yellow Pine mine[1] 20,047.24 tons of ore were mined at an average cost of $4.516 per ton. Of this quantity, 464.83 tons were shipped as crude ore and 19,582.4 tons were milled. The lowest depth yet attained in the mine is the 900-foot level, but the most important ore developments of 1917 occurred at the north end of the mine in the vicinity of the 700-foot level, where a very large ore body of unusually good grade was encountered, evidently an extension of the ore zone above, faulted to the hanging wall. The ore was developed for a distance of 250 feet along the strike and 120 feet on the dip, with an average thickness of about 30 feet and the exact limits undetermined. Assays taken of the ore show 30 per cent zinc and 18 per cent lead, and also 12 ounces of silver per ton. Concerning the products from the mill, the company report gives the following:

A marked difference in ore market conditions now existing has resulted in the determination of your directors to make a radical change in our future operations. Our contract for zinc ore products, which has existed the past five years, expires on February 1, 1918, and the present market for the class of ore we have been producing is such that it has been deemed advisable to discontinue milling, and hereafter to ship all ore in the crude state.

In consequence, our milling plant will be closed on February 1, and a large proportion of our product will be shipped to oxide plants as a mixed lead-zinc ore. It is our intention to improve sorting facilities at the mine, so that a considerable portion of the crude lead ore and crude zinc ore may be sorted out and shipped separately. For the balance of the product, we have recently entered into a favorable one-year contract covering 14,000 to 18,000 tons of mixed ore annually. During the first six months of the contract, the price has been made irrespective of metal markets and thereafter dependent upon the rise and fall of the lead and zinc markets. * * *

No attempt has been made to estimate accurately available tonnage in the mine, as the newer ore bodies are not sufficiently blocked, but it may be stated safely that ample tonnage for the next twelve months is absolutely assured. * * *

During 1917, the mill operated 5,502.5 hours or a total of 344 sixteen-hour days, treating a total of 19,976 tons, or an average of 3.63 tons per hour. The average cost per ton was $1.95.

From a mill head averaging 14.85 per cent lead, 29.1 per cent zinc, and 7.55 ounces silver per ton, there were produced 3,157.9 tons of lead concentrate, averaging 52.6 per cent lead, 13.6 per cent zinc, and 29.8 ounces silver per ton; 12,904.9 tons of zinc concentrate, averaging 5.15 per cent lead, 32.0 per cent zinc, and 3.18 ounces silver per ton; and 3,512.7 tons of slime, averaging 6.9 per cent lead, 32.2 per cent zinc, and 3.53 ounces silver per ton. Waste sorted from the belt amounted to 393.6 tons. * * *

[1] Yellow Pine Mining Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

Product from Yellow Pine mine in 1917.

Class of ore.	Quantity.	Lead.	Zinc.	Silver.	Net value.	Total value.
	Short tons.	*Per cent.*	*Per cent.*	*Ounces.*	*Per ton.*	
Lead concentrate	3,157.9470	52.60	13.60	29.80	$80.11	$253,999.89
Zinc concentrate	12,904.9665	5.15	32.00	3.18	23.72	306,053.75
Zinc slimes	3,512.6930	6.90	32.20	3.53	23.30	81,853.13
Crude zinc ore	411.1775	3.50	37.90	1.54	32.71	13,442.57
Crude lead ore	2.6800	63.10	5.65	21.60	109.16	292.56
Crude mixed ore	50.9730	16.00	27.20	11.50	24.76	1,263.42
	20,040.4270	.....	.....	.....	.....	656,905.32

Dividends disbursed in 1917 amounted to $360,000.

DOUGLAS COUNTY.

Five producers reported the output of 23 tons of ore, of which 13 tons were shipped directly to the smelter and 10 tons treated at gold and silver mills. The total value per ton of the ore was $52.52 and the gold and silver value was $24.35. The placer production amounted to $300 in gold.

Gardnerville district.—A small quantity of ore containing gold was mined from the Emerald property and a small lot of similar ore came from the Pine Nut Consolidated mine.

Mount Siegel district.—A small gold production, taken out in doing assessment work on the Ancient Gold placer, was reported.

Red Canyon district.—The Winters property, near Gardnerville, produced a little lead ore in 1917.

ELKO COUNTY.

Mine production in Elko County, Nev., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	76	40,729	$282,154	268,156	1,771,689	1,098,911	963,438	$1,099,363
1917	80	27,783	244,439	264,241	887,371	1,064,145	293,354	825,864
Decrease, 1917	.....	12,946	37,715	3,915	884,318	34,766	670,084	273,499

[a] Includes placer production.

The output of ore reported by 77 deep-mine producers was 27,783 tons in 1917, which was 12,946 tons less than was produced by 75 operators in 1916. The total average value per ton of the ore increased from $26.99 in 1916 to $29.70 in 1917, and the gold and silver value per ton from $11.25 to $16.61. A large part of the ore (19,468 tons) was treated at gold and silver mills, and yielded bullion containing $239,156 in gold and 180,090 ounces of silver. A small quantity of lead concentrate and lead-zinc concentrate was produced at one of the mills. The ore shipped was 7,915 tons, containing gold, silver, copper, lead, and zinc, valued at $425,086, or an average value

Digitized by Google

per ton of $53.71. Placer operators reported the production of $606 in gold and 8 ounces of silver.

Aura district.—Some silver ore containing a little gold from the Big Four property, operated by a lessee, was the only production reported in the district.

Centennial district.—Small test lots of ore came from the Gold Dollar and Red Cloud properties in 1917.

Contact district.—All the ore produced in the district, reported by eight operators, was of shipping grade, and amounted to 253 tons, containing 1.88 ounces of gold, 746 ounces of silver, 65,665 pounds of copper, and 5,215 pounds of lead. Production was reported from the Bellevue, Valley View, Champ Clark, Bonanza, Blue Bird, and Hanks copper properties.

Delkar district.—A lessee operated the Copper Belt property and shipped to the smelters an oxidized copper ore.

Ferber district.—The Salt Lake group was operated by the Ferber Copper Co. There were two kinds of ore produced, oxidized copper ore and lead ore. The ore was hauled to Erickson on the Deep Creek branch line of the Western Pacific Railroad operated from Wendover to Gold Hill, Utah.

Ferguson district.—The Bullion group and two other properties were producers of copper and lead oxidized ores.

Gold Circle district.—Sixteen producers reported the production of 19,523 tons of ore containing $242,198 in gold and 182,844 ounces of silver, valued in all at $392,861, or an average value per ton of $20.12. Only 102 tons of gold and silver ore were shipped from the district directly to smelters. The remainder of the production was milled, yielding gold and silver bullion by cyanidation. The principal producer was the Elko Prince property, which is opened by a 700-foot adit and a 450-foot shaft. The cyanide mill on the property has a capacity of 50 tons. There was also a 2-stamp amalgamation mill operated in the district which treated some ore from the Esperanza and Queen properties. The Rand & Masey, Missing Link, June Bell, Lucky Boy, and Rex properties were also producers.

An interesting paper[1] recently published describes the Elko Prince mine and mill and gives a brief history of the district as follows:

> The Elko Prince mine is in the Gold Circle district, Nevada, about 1½ miles (2.4 kilometers) from the town of Midas, 55 miles (88.5 kilometers) west of Battle Mountain, and 50 miles (80.5 kilometers) northeast of Golconda. The district is described by Emmons in United States Geological Survey Bulletin 408, 1910. Little was said of the Elko Prince, however, as only a small amount of work had then been completed.
>
> The geological structure of the region is simple. The oldest exposed formation, covering most of the area, is rhyolite, which has a light-colored devitrified groundmass inclosing phenocrysts of feldspar, quartz, and magnetite. It has been somewhat weathered and partially stained with oxide of iron. There are several outcrops of andesite which cut the rhyolite. The ore deposits occur as fissure veins, replacement veins, and sheeted zones. The Elko Prince vein is of the first type. The rhyolite near the veins is silicified, stained with oxide of iron, and, at some localities, replaced by ore, or is so permeated by metals as to be classed as ore. The vein filling consists chiefly of quartz, and the values consist entirely of gold and silver. Part of the gold exists as the native metal and part is associated with pyrite. Silver occurs free and as argentite in

[1] Dorr, J. V. N., and Dougan, L. D., Elko Prince mine and mill: Am. Inst. Min. Eng. Bull. 140, pp. 1235–1254, August, 1918.

Digitized by Google

banded streaks through the vein. These veins trend in a northwesterly direction, with dips varying from 65° to vertical.

Gold was discovered in the district in the fall of 1907, and a characteristic rush followed. The town of Midas was laid out and shortly had 2,000 inhabitants. Several small mills were built, one of which, the Rex, ran several years. After the first excitement, the people drifted away rapidly, and at present only about 150 remain. The Elko Prince claims were located in 1907 by Paul Ehlers, a prospector, and 10 claims were patented in 1913 after considerable development work had been done. * * *

The outcrop of the Prince vein is insignificant, only a narrow seam of low-grade quartz, or an obscure fissure containing no quartz or metals. The first work on the property was a 60-foot shaft sunk on the cropping. A narrow seam of mineralized quartz was followed, but nothing of importance was found; then a 240-foot drift on the vein gave similar results. Later, a 700-foot crosscut reached the vein 270 feet below surface, and cut an ore shoot almost in the center. Subsequent work developed a vein having an average width of 14 to 15 inches, a total tonnage of 30,000, and a gross value of approximately $1,000,000, the limits of the ore body being quite well defined.

In June, 1915, the Elko Prince Mining Co. made an agreement with the Dorr Co., whereby the latter was to design, finance, and build a cyanide mill of at least 40 tons daily capacity, furnish additional mine equipment, and operate the property until certain financial results had been attained. Milling was begun in November, 1915, and the original terms were completed in June, 1917, but the Dorr Co., operating through the Elko Prince Leasing Co., has continued in charge of the property to the present time.

The Prince vein has a uniform northwest-southeast strike and a dip varying from vertical to 85° NE. One horizontal fault of a few feet occurs in the 1,400 feet of development on the property, and a second, of much greater extent, probably occurs just beyond the south end line.

The vein filling is hard but brittle quartz, with a very small amount of sulphides. Partial oxidation extends from the surface to the deepest openings. Manganese in oxidized form is found in spots. No enrichments due to leaching and redeposition have been observed, except as to a small portion of silver. The gold is mainly free but very fine; about 50 per cent can be amalgamated. Thin flakes of native silver are found in the footwall and penetrate its seams in places to a depth of an inch. The silver exists chiefly as argentite and polybasite, giving the quartz the characteristic banded appearance that usually accompanies the presence of these minerals.

A characteristic analysis of the ore is:

	Per cent.		Per cent.		Per cent.
SiO_2	85.0	S	0.1	Ignition loss	2.0
Al_2O_3	2.0	As	.1	Cu	.0
Fe	3.0	Sb	.1	Au (ounce per ton)	.7
Cao	4.0	Mn	Trace.	Ag (ounces per ton)	10.0

A second vein, the June Bell, is parallel to the Prince, and lies a short distance to the west. It is of the same type but much smaller, and gives promise of producing but little metal. * * * The financial arrangements allowed the mill to be designed so that when the ore body already developed had been worked out and the plant scrapped, the greatest net profit would have been made. The treatment of 50 tons of sorted ore daily promised a life of about three and one-half years, with the chance of an extension by finding other ore bodies or obtaining custom ore.

Labor was scarce in the district, and, although there was no labor union, the Tonopah scale of $4 minimum for eight hours had been paid.

Redhouse, on the Western Pacific, the nearest freight station, is 34 miles away, and hauling by wagon costs from $13.50 to $15 per ton. The road from Redhouse to Midas is a good desert road, with a large increase in grade in the last 5 miles. The chance of heavy snow at the upper end in winter, and the certainty of very heavy hauling in spring, made it essential to stock up by December to run until May. Hauling by team has proved more satisfactory than by motor truck. Oil storage of 22,000 gallons was provided at the mill. No electric power was available. * * *

The treatment follows the standardized lines of ball-mill crushing and fine grinding with countercurrent decantation and zinc-dust precipitation. * * *

Water is pumped from a well below the town of Midas, a distance of 11,000 feet with a lift of 700 feet. A crude-oil engine was first installed, but it re-

Digitized by Google

quired so much attention that it was replaced with a 10-horsepower motor; the water pipe is used as the return electrical circuit. * * *

As electric power was not available, and coal was too expensive, an oil engine was the only motive power considered. A 150-horsepower Fairbanks-Morse engine on the property might have furnished a large part of the power needed; but, as fuel oil cost 12 cents per gallon delivered, and the rated consumption of the engine was double that of a Diesel, the initial saving would have been lost in operating. * * *

The following figures, representing costs of construction in 1915, are, unfortunately, only of historical value today:

Mill, complete (including power plant)	$67,509.06
Refinery	2,560.11
Oil storage and wagons	2,162.05
Office, assay office, and other buildings and equipment	8,071.48
Total surface expenditures, except water line already installed	80,302.70

The total cost of the mill machinery and tanks, at shipping point, was $33,647.18, checking rather closely the common estimate that a mill erected would cost double the cost of the machinery.

The lumber, 205 M. costing $48 per M. at the site, cost $20.42 per M. to erect; machinery, 145 tons, cost $22.40 per ton to install; and 10 tons of piping was placed for $44.77 per ton.

Island Mountain district.—The Hammond Exploration Co. was building in December, 1917, a small mill in Patterson Gulch, 2½ miles northwest of Gold Creek. The plant will be equipped with a Huntington mill and other necessary machinery for amalgamation and cyanidation. Concentration tables will be added in the spring of 1918.

Jarbidge district.—The only production was from the Flaxie property, which yielded ore containing gold and silver, recovered in an amalgamation mill. According to a recently published article[1] plans had been nearly completed for the building of a railroad from Twin Falls, Idaho, to Jarbidge. It was also said the Elkoro Mines Co. had reached the main ore body of the Long Hike mine in the lower workings, and that a wide body of excellent ore was exposed. It is estimated by the engineers in charge of the property that gold ore valued at $3,000,000 has been developed on the main levels. The mill of the company is nearing completion. This plant is situated on Jarbidge River at the mouth of Long Hike Gulch and is to operate in the spring of 1918 as a cyanidation plant treating 100 tons of ore daily. The ores will come from the Long Hike and Starlight mines.

Kinsley district.—Oxidized lead ore was shipped from the Kinsley-Star property in 1917.

Lee district.—Sulphide ore containing lead was shipped from the B. B. property.

Leroy district.—The Alabama, Jay Bird, and Pickup claims produced small lots of oxidized ore containing silver, lead, and copper.

Merrimac district.—A few tons of oxidized copper ore containing a little silver was shipped from the Copper Queen, Ironside, and Pacific properties.

Proctor district.—The Nick Del Duke prospect, situated a mile north of the Western Pacific Railroad at Proctor, produced a small quantity of silver ore, which was shipped to the smelter. There were also a few tons of silver ore shipped from the Silver Hoard property.

[1] Min. and Sci. Press., Mar. 10, 1917, p. 352.

Digitized by Google

Railroad district.—Seventeen producers reported the production of 3,324 tons of ore, containing $249 in gold, 39,252 ounces of silver, 595,931 pounds of copper, and 165,078 pounds of lead, valued in all at $209,478, or an average value per ton of $63.02. All this ore was of shipping grade and was produced largely by lessees operating the Gray Eagle property. There were also important shipments from the Bunker Hill, Kentucky, Ennor, Hale & Peterson, Sweepstake, Sylvania, Bald Mountain Chief, and Copper Bell mines.

Ruby Mountain Range district.—The principal production of ore came from the Michigan claim situated on the eastern slope of the Ruby Mountains on Battle Creek. The ore, which contained principally zinc, was concentrated in a 50-ton mill, and yielded lead and zinc concentrates.

Spruce Mountain district.—Operations at the Black Forest property resulted in the shipment of silver bearing lead ore and copper ore.

Tecoma district.—Lead ore from the S. & W. Lease and the California property represented the output of the district.

Tuscarora district.—Although there was great activity in the opening of some of the older properties, there was produced only 11 tons of shipping ore, containing principally silver. The larger part of the district output in 1917 came from the Surprise property.

Warm Creek district.—Oxidized zinc ore was shipped from the Polar Star property, operated by the Nevada Zinc Mining Co., but the output was much less than during 1916.

ESMERALDA COUNTY.

Mine production of Esmeralda County, Nev., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	50	389,351	$2,684,688	170,677	1,391,392	408,534	17,680	$3,169,833
1917	61	349,655	1,986,001	157,218	762,627	448,431	15,402	2,363,882
Increase or decrease, 1917		−39,696	−698,687	−13,459	−628,765	+39,897	−2,278	−805,951

There were 349,655 tons of ore mined by 61 producers, 39,696 tons less than in 1916. Of the total ore, 165,299 tons treated by cyanidation and 3,399 tons by amalgamation, yielded $1,501,026 in gold and 52,158 ounces of silver, or an average value per ton of $9.15. There were 88,600 tons of ore treated at milling plants, which yielded 5,943 tons of concentrates containing gold, silver, and copper. These concentrates, with 10,472 tons of crude ore, were shipped to the smelters. The crude ore contained $268,335 in gold, 65,036 ounces of silver, 207,003 pounds of copper, 448,431 pounds of lead, and 15,402 pounds of zinc, valued in all at $418,573, or an average value per ton of $39.97. There was no placer production reported in 1917.

Crow Springs district.—Oxidized lead ore, produced from the Walker property, was hauled to McLeans on the Tonopah & Goldfield branch of the Southern Pacific Railroad.

Digitized by Google

Cuprite district.—Ore containing lead was produced in 1917 from the Ella claim, which is opened by a shaft 60 feet deep.

Desert district.—The Carrie property was a producer of sulphide ore, containing lead, silver, and some gold. This property is opened by a 200-foot shaft.

Goldfield district.—All metals produced in 1917 decreased in quantity and the value was $897,481 less than in 1916, as is shown in the following table:

Mine production of Goldfield district, Nev., 1904–1917.

Year.	Ore.	Gold.	Silver.	Copper.	Lead.	Total value.
	Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	
1916	383,456	$2,651,158	129,781	1,317,400	2,418	$3,060,801
1917	339,488	1,900,082	78,184	728,255	.....	2,163,320
Decrease, 1917	43,968	751,076	51,597	589,145	2,418	897,481
Total, 1904–1917	.....	80,252,177	1,206,713	6,864,858	26,080	82,246,712

Seventeen producers in 1917 reported the production of ore with an average value per ton of $6.37, against an average value of $7.98 in 1916. The larger part of the output, or 161,955 tons, was treated at milling plants by the cyanidation process and yielded 69,642.81 ounces of gold and 30,466 ounces of silver. There were also 88,600 tons of ore concentrated, yielding 5,921 tons of concentrate, which contained 9,996.08 ounces of gold, 38,578 ounces of silver, and 511,470 pounds of copper. In addition to the ore, there were 81,885 tons of old tailings re-treated. The ore of shipping grade amounted to 7,048 tons and contained 12,277.59 ounces of gold, 9,140 ounces of silver, and 174,530 pounds of copper. The principal producers of these ores were the Goldfield Consolidated, Atlanta, Florence, Diamondfield Daisy, Great Bend, and Jumbo Extension.

Regular shipments of sulphide copper ore were made from the Atlanta mines, and considerable gold ore came from the Florence mine, under control of a new organization.

From the Goldfield Consolidated mines[1] a total of 250,550 tons of mill ore was produced in 1917, averaging $8.14 per ton in gold and silver, with a recovery of $7.04 per ton. At the same time, 81,885 tons of tailing of an average value of $1.27 were taken from the tailing pond, yielding a profit of 32 cents per ton. The total recovery of gold and silver from the product treated was $1,825,296.59. The following extract is from the annual report of the company:

> No dividends were paid during the year owing to the reduced earnings and the desire of the management to conserve its financial resources to the end that other possible operations may result in greater earning capacity.

[1] Goldfield Consolidated Mines Co. Eleventh Ann. Rept., for year ending Dec. 31, 1917.

Digitized by Google

Production of Goldfield Consolidated Mines Co., 1917.

	Production (short tons).	Total value.	Average per ton.
Tons of ore milled	250,550	$2,039,103.49	$8.14
Loss in tailing and smelter discount		276,133.44	1.10
Value recovered		1,762,970.05	7.04
Tons of tailing treated	81,885	103,843.49	1.27
Loss in tailing		41,516.95	.51
Value recovered		62,326.54	.76
Total value recovered from ore and tailing		1,825,296.59	
Cost of ore purchased and amount paid lessees		85,649.32	
Value realized		1,739,647.27	
Net costs		1,543,012.82	
Net realization from operations		196,634.45	
Expenditures, account exploration and development		68,133.69	
Net realization		128,500.76	

Within the year 14,770 tons of ore of average value of $14.75 and gross value of $217,905.33 were produced by lessees, of which amount $82,237.40 was paid to lessees. From this sum lessees paid expenses of labor and powder. The records show approximately 18,000 shifts of labor have been employed by lessees during this period of production, which indicates that taken as a whole the lessees have made no profit. Some individual leases have been profitable, but to no great extent. This result has been most disappointing, since it has been hoped lessees would open up new ore bodies. There are now 40 sets of lessees at work employing 80 men, and as rapidly as the company withdraws from a section of a mine it is opened to lessees, and this policy will be continued.

It is not possible to offer more liberal terms to lessees, since the present deduction of $4 per ton is scarcely enough to pay the expenses of handling lease ore. Costs have naturally increased with the reduction in tonnage milled per day. Further, it does not seem probable leasing would be stimulated even if more liberal terms were made, since many of the blocks already opened have been leased several times. * * *

The entire tonnage produced within the year has been milled at your company's milling plant. Of this, 161,950 tons were treated by the cyanide process and 88,600 tons were treated by flotation. The flotation plant, operating on low-grade copper ores, was placed in service in March and has been in continuous operation since that date. For the first three months the concentrate resulting from the flotation process was treated locally in your concentrate treatment plant with indifferent success. It has been demonstrated, not only in your plant but in the laboratory and from tests made by independent metallurgists that this product can not be treated profitably by the cyanide process unless subjected to a chloridizing roast, which is impracticable. In June arrangements were made to market the flotation concentrate through custom smelters.

Total production of Goldfield Consolidated Mines Co. from prior to Oct. 31, 1908, to Dec. 31, 1917.

Property.	Ore sold or treated.	Average value.	Total value.
	Dry tons.	*Per ton.*	
Combination	572,500	$25.65	$14,682,718.08
Mohawk	1,288,825	21.50	27,709,199.48
Clermont-Jumbo No. 2	585,402	34.23	20,040,135.30
Laguna-Red Top	480,593	18.19	8,741,524.81
Dumps	135,092	4.75	641,614.37
Contractors	31,940	20.91	667,873.17
			72,483,065.21

Digitized by Google

During its fiscal year the Jumbo Extension[1] produced 8,143 dry tons of smelting ore averaging per ton $26.94 in gold and silver, with a little copper. There were also 807 tons of dump ore sold on a flat rate of $1 per ton.

Gold Mountain district.—Ore of shipping grade reported from 11 properties amounted to 187 tons, containing $4,811 in gold, 3,150 ounces of silver, 4,136 pounds of copper, and 23,149 pounds of lead, valued in all at $10,527, or an average value per ton of $56.29. The principal producers were the Butte, Little George, and May Day.

Hornsilver district.—The principal producers, the Silver Mines Corporation and the Orleans property, yielded milling ore, the larger part of which was treated in the 100-ton cyanide plant of the former property. This is a new mill, and it was reported that custom ore would also be treated. The ore from the Orleans property was shipped to the Belmont mill at Tonopah. All of the ore produced gold and silver bullion.

Klondyke district.—The largest part of the district output was silver ore and oxidized lead ore from the Original Klondyke property. The mine is opened by a vertical shaft 150 feet deep and an adit 300 feet long.

Lida district.—Seven producers reported the production of 55 tons of ore, containing $145 in gold, 7,052 ounces of silver, 824 pounds of copper, and 19,026 pounds of lead, valued in all at $7,817, or an average value per ton of $142.12. The Eagle & Tip Top was the principal producer.

Lone Mountain district.—Nine producers reported the output of 1,016 tons of ore, containing $1,123 in gold, 19,585 ounces of silver, 24,159 pounds of copper, 286,245 pounds of lead, and 15,402 pounds of recoverable zinc, valued in all at $50,044, or an average value per ton of $49.26. The principal part of the production came from the General Thomas property and consisted of oxidized lead ore. The Lone Star was also a producer, yielding copper ore, copper-lead ore, and some zinc ore.

Montezuma district.—The Montezuma mine dump yielded a small quantity of sorted ore, which was shipped to the smelter.

Palmetto district.—The property of the Desert Holly Mining Co. was operated and produced a small quantity of lead ore, and some ore of similar character was shipped from the Treasure State claim.

Silverpeak district.—The Mary mine, operated by lessees, yielded ore which was milled and produced gold and silver bullion. Some ore was also shipped to the smelter from the Black Warrior property.

EUREKA COUNTY.

Mine production in Eureka County, Nev., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	36	22,082	$114,752	143,686	79,066	2,804,981	34,935	$426,972
1917	45	7,165	30,282	72,269	72,841	1,783,933	.....	263,136
Decrease, 1917	.....	14,917	84,470	71,417	6,225	1,021,048	34,935	163,836

[a] Includes placer production.

[1] Jumbo Extension Mining Co. Ann. Rept. for year ending June 30, 1917.

Digitized by Google

Forty operators produced 7,165 tons of ore, 14,917 tons less than was produced by 30 operators in 1916. The total average value per ton increased from $18.86 in 1916 to $36.34 in 1917 and the gold and silver value in this ore from $9.01 to $12.15 per ton. Of the ore, 450 tons were treated in gold and silver mills and yielded bullion containing $2,399 in gold and 39 ounces of silver, which had an average total value of $5.40 per ton. There were 5,861 tons shipped directly to smelters, containing $19,308 in gold, 66,757 ounces of silver, 57,997 pounds of copper, and 1,702,115 pounds of lead, valued in all at $236,531, or an average value per ton of $40.36. Placed bullion reported from five sources amounted to $2,761 in gold and 16 ounces of silver.

Antelope district.—Lessees operating the Prince of Wales group shipped a small quantity of copper sulphide ore.

Cortez district.—The post office of Cortez is in Lander County, but some of the mines are in Eureka County. Ore was produced in 1917 and was reported from Lander County.

Eureka district.—There were 31 producers reporting the production of 3,304 tons of ore, containing $20,131 in gold, 39,708 ounces of silver, 31,771 pounds of copper, and 693,757 pounds of lead, valued in all at $121,188, or an average value per ton of $36.68. There were 2,450 tons of ore and 814 tons of old slag shipped directly to the smelters. Only 40 tons were milled, yielding 17 tons of lead concentrate. The principal producers were the Connelly, California & Silver King, Bullwhacker, and Holly mines. Most of the old slag came from the Richmond Eureka property, and some from the Diamond.

Lynn district.—Five placer producers reported the production of gold bullion, and one quartz mine the production of gold ore, valued in all at $9,544. All the ore was milled in an amalgamation plant on the Big Six property. This mill, constructed in 1917, treated about 5 tons of ore a day during its operation. In 1916 the output of ore and placer bullion from the district was $19,398 in gold and 63 ounces of silver. Placer producers report a very small flow of water for the season of 1917 as the cause of the large decrease in the output of gold.

Maggie Creek district.—The Copper King property, operated by a lessee, yielded a small tonnage of oxidized copper ore of shipping grade.

Mineral Hill district.—Three producers reported 3,010 tons of ore, containing $360 in gold, 27,837 ounces of silver, 2,448 pounds of copper, and 1,062,996 pounds of lead, valued in all at $115,384, or an average value per ton of $38.33. The largest part of the production came from the Union Mines Co. There was also some ore from the property of the Mineral Hill Consolidated.

Safford district.—Two small shipments were made from the Zenoli property. There were also small shipments from two other claims.

Digitized by Google

HUMBOLDT COUNTY.

Mine production in Humboldt County, Nev., in 1916 and 1917.

Year.	Number of producers.	Ore	Gold.[a]	Silver.[a]	Copper.	Lead.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	
1916	95	109,683	$398,231	869,424	135,180	75,734	$1,008,792
1917	104	104,564	246,645	859,837	567,610	511,221	1,154,074
Increase or decrease, 1917	.....	−5,119	−151,586	−9,587	+432,430	+435,487	+145,282

[a] Includes placer production.

Humboldt County had 100 producers of ore in 1917, against 84 producers in 1916. The total average value per ton increased from $9.13 in 1916 to $11.03 in 1917. Milling plants using amalgamation and cyanidation, but principally the latter process, treated 93,677 tons of ore, which yielded $231,381 in gold and 785,988 ounces of silver, having an average value per ton of $9.38. Some gold and silver concentrate and a little lead concentrate were also produced at the milling plants and shipped to smelters. Ore of shipping grade aggregated 5,935 tons and contained $8,532 in gold, 59,177 ounces of silver, 434,110 pounds of copper, and 120,412 pounds of lead, valued in all at $186,161, or an average value per ton of $31.37. There were also some shipments of old tailing and slag containing copper and lead. The placer output reported from 4 sources amounted to $1,206 in gold and 10 ounces of silver, as against $7,174 in gold and 90 ounces of silver in 1916.

Amos district.—In 1917 the 30-ton amalgamation and concentration mill of the Oklahoma property was built in Buckroo Canyon of the Pine Forest range. The plant is expected to be in operation in the spring of 1918.

Antelope district.—The Majuba Hills property, recently under option to the Mason Valley Mining Co., was operated and produced silver-bearing copper ore, which was shipped to its smelter at Thompson. Some oxidized lead ore was produced from the Last Chance property. The 25-ton concentration mill of the Antelope Springs Co. was enlarged in 1917 to a 50-ton oil flotation plant using the K. and K. system in addition to four Wilfley tables, a ball mill, and one Blake crusher. The plant is reported to be ready for operation.

Central or Mill City district.—Copper ore was produced from the 56 Copper Mines Co's. property in 1917.

Dun Glen district.—The Sheba mine was active and some ore was treated in its concentration mill, and yielded lead concentrate which carried considerable silver.

Gold Run district.—Seventeen producers of ore reported 7,116 tons containing $2,624 in gold, 28,331 ounces of silver, 488,760 pounds of copper, and 42,725 pounds of lead, valued in all at $163,075, or an average value per ton of $22.92. The ore of shipping grade aggregated 4,360 tons, and also 2,670 tons of old tailing containing copper and silver were shipped from the old dump of the

Digitized by Google

Glasgow & Western milling plant. The largest producers of ore were the Yerington Mountain Copper and Adelaide properties. The Caroline property was also an important shipper of oxidized copper ore. A small production of gold, taken out in development work, was reported from the Gold Run placer.

Kennedy district.—Oxidized lead ore, containing silver and gold, came from the Henrietta and Abe Lincoln group, and a small output of bullion from the experimental plant of the Roylance Reduction Co. Gold ore from the Virginia property was treated at this mill by an electrochemical amalgamation process.

National district.—The milling plant of the National Mines Co. was reported idle during the year. The property was operated by a lessee who produced a small quantity of gold and silver bullion.

Rochester district.—Nineteen ore producers reported 88,371 tons containing $152,855 in gold, 799,865 ounces of silver, 646 pounds of copper, and 14,521 pounds of lead, valued in all at $813,369, or an average value per ton of $9.20. The placer output amounted to $717 in gold and 6 ounces of silver. There were 87,839 tons of ore milled, yielding gold and silver bullion, and 532 tons of ore, containing gold, silver, copper, and lead, were shipped directly to the smelters. There were also some values in sweepings from the mill ponds of the cyanide plants. The largest producer of milling ore was the Rochester Mines Co., which operated its 200-ton cyanidation mill almost continuously during the year. The next largest producer was the Packard property, equipped with a 100-ton cyanide plant. Some gold and silver bullion was produced in a two-stamp amalgamation mill treating ore from the Lincoln Hill mine. The other producers in the district were the American in South American Canyon, Buck & Charley, Octopus, and Rochester Merger. In drifting for a vein on the Bonanza claim, some gold was recovered by sluicing. This property is 2 miles north of Rochester. Machinery and other necessary equipment for a 500-ton cyanidation plant was put in place on the Rochester-Combined mill site, near the Packard mill, during 1917. It is expected this mill will begin operations some time in 1918.

Rosebud district.—Seven producers reported the production of 53 tons of ore of shipping grade, containing $16 in gold, 2,694 ounces of silver, 5,386 pounds of copper, valued in all at $3,706, or an average value per ton of $69.92. The principal properties operated were the Abe Lincoln and the Grubstake, and the remaining part of the output came from the dumps of small prospects.

Seven Troughs district.—The reports received from 18 producers gave an output of 5,552 tons of ore, containing $81,830 in gold, and 6,554 ounces of silver, valued in all at $87,231, or an average value per ton of $15.73. All of the ore, with the exception of 6 tons, which was shipped to a smelter, was milled, and produced gold and silver bullion and a few tons of gold and silver concentrate. The Seven Troughs Coalition, Delaware, Mazuma Hills, Fairview, Monarch, and Signal Peak properties were the principal producers of milling ore.

Sonoma Mountain district.—The Wolverine property yielded a small quantity of copper ore carrying silver.

Sierra district.—Six producers reported 149 tons of ore and old tailings, containing $406 in gold, 2,540 ounces of silver, and 8,625

Digitized by Google

pounds of lead. There was also a small quantity of copper in one shipment. The total value of the metals was $3,265, or an average value per ton of $21.91. There were 44 tons of ore shipped directly to the smelters. The principal producers were the Gem Five, Tululah, and Sunshine properties.

Trinity district.—The Electric Mining and Reduction Co. operated the old Arabia property, from which ore containing antimony and lead was shipped to the smelter. Shipments of old slag from early operations of the Montezuma smelter contained antimonial lead and silver. Some crude ore from the Montezuma mine was also shipped.

Unionville district.—The Arizona property yielded a few tons of silver ore, which was shipped directly to the smelter.

Warm Springs district.—The Ashdown & Vicksburg property was operated for a short period, yielding gold and silver bullion.

Winnemucca Mountain district.—Ten producers reported 350 tons of ore, containing $3,013 in gold, 4.039 ounces of silver, and 4,050 pounds of lead, valued in all at $6,689, or an average value per ton of $19.11. There were 258 tons of ore milled, producing gold and silver bullion, and 92 tons of lead ore were shipped directly to the smelter. Bullion was produced from the Neshobe and Winnemucca Mountain properties.

LANDER COUNTY.

Forty-seven producers reported the output of 23,848 tons of ore, 7,749 tons more than was reported by 30 producers in 1916. The total average value of the ore increased from $21.22 in 1916 to $35.12 in 1917. At gold and silver mills, 2,801 tons of ore yielded $11,622 in gold and 1,482 ounces of silver, an average value of $4.59 per ton. The ore of shipping grade amounted to 19,389 tons, containing $17,917 in gold, 112,336 ounces of silver, 2,479,657 pounds of copper, and 248,529 pounds of lead, valued in all at $808,802, or an average value per ton of $41.71. The placer output reported by 33 operators was $66,746 in gold and 460 ounces of silver, against a production in 1916 by 11 operators of $153,698 in gold and 1,050 ounces of silver.

Battle Mountain district.—Producers of ore from 20 properties reported 18,162 tons, containing $4,881 in gold, 18,595 ounces of silver, 2,431,247 pounds of copper, and 98,978 pounds of lead, valued in all at $692,445, or an average value per ton of $38.13. The greater part of this ore was of shipping grade, amounting to 17,597 pounds, containing 122.62 ounces of gold, 16,109 ounces of silver, all of the copper, and 40,486 pounds of lead. There were 458 tons of ore milled, which produced lead concentrate carrying silver, and 107 tons of ore yielded gold and silver bullion. The largest shipper of oxidized copper ore was the Copper Canyon Mining Co. There were also important shipments from the Copper Queen property. Reports from 33 placer producers showed an output of $66,746 in gold and 460 ounces of silver. Most of this gold output was made by drift mining, and the gold was recovered by sluicing the gravel of an ancient river bed situated in Copper Canyon. Smaller lots of gold were obtained from other placers in the Battle Mountain Range, partly from Piute Gulch. On the Gold Top property a 36-ton amalgamation and concentration plant, built in Pedro Gulch

Digitized by Google

about 9 miles from Battle Mountain, was completed in September, 1917. An ordinary jaw crusher with a ball mill will prepare the ore for further treatment on an Eccleston concentration table. The plant will not operate until 1918.

Cortez district.—Lead ore was shipped from the Utah property, and reports of shipments of lead ore and siliceous silver ore were also made by the Tenabo Mining & Milling Co., and the Mount Tenabo Mining Co. The ore is all shipped to the smelter from Beowawe, on the Southern Pacific Railroad.

Hilltop district.—Most of the ore mined in the district was milled, yielding gold and silver bullion, chiefly by cyanidation. There were also 457 tons of ore, containing gold, silver, copper, and lead, shipped directly to the smelters. The Kimberly Consolidated Mines Co. treated the largest part of the milling ore, and the Gray Eagle mine produced a silver ore and a lead ore.

Lander or Bullion district.—From the Maysville property, silver ore containing a small quantity of copper and gold was shipped directly to the smelter. The Exile and Quartz claims were also producers.

Lewis District—Ore of shipping grade, containing principally silver and a little lead, copper, and gold, was shipped to the smelters from the Eagle, Monitor, and Star Grove groups.

Reese River District—Seven producers of ore reported 101 tons, containing $155 in gold, 3,455 ounces of silver, 284 pounds of copper, and 10,476 pounds of lead, valued in all at $3,980, or an average value per ton of $39.41. The properties operated were the Austin Dakota, Eclipse, and Austin claims. A 75-ton cyanidation plant, situated at New Pass, 21 miles from Austin, was completed in February, 1918, by the Nevada Austin Mines Co.

LINCOLN COUNTY.

Mine production in Lincoln County, Nev., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	23	162,153	$34,305	559,045	806,938	10,356,926	2,002,105	$1,583,574
1917	23	154,087	48,899	523,399	440,197	10,714,152	1,332,521	1,657,688
Increase or decrease, 1917	.....	—8,066	+14,594	—35,646	—366,741	+357,226	—669,584	+74,114

In 1917, 23 operators reported 8,066 tons of ore less than was produced by the same number of operators in 1916. The average value per ton increased from $9.77 to $10.76, and the gold and silver value from $2.48 to $3.12 per ton. The greater part of the ore, 137,090 tons, was of shipping grade and contained $35,763 in gold, 483,953 ounces of silver, 427,946 pounds of copper, 10,099,224 pounds of lead, and 183,472 pounds of zinc, valued in all at $1,438,616, or an average value per ton of $10.49. Ore treated at gold and silver mills aggregated 453 tons and yielded bullion valued at $4,742. At concentrating plants, 5,988 tons of ore yielded 2,926 tons

Digitized by Google

of concentrates containing $7,048 in gold, 34,214 ounces of silver, 2,984 pounds of copper, 499,131 pounds of lead, and 1,149,049 pounds of zinc, valued in all at $196,183, or an average value per ton of $67.05. No placer production was reported in 1917.

Atlanta district.—Some old tailings concentrated from the Silver Park dump yielded lead concentrate carrying silver and a little gold.

Caliente district.—The Gold Chief and Peerless properties were the chief producers of gold-silver ore and some lead ore.

Groom district.—The Groom mine continues to be a good producer of high-grade lead sulphide ore containing silver. The property is opened by a shaft 200 feet deep. All of the ore is hauled by motor truck to the railroad and contains from 35 to 61 per cent of lead and 11 to 22 ounces of silver, with 0.5 per cent of copper, 3 per cent of zinc, 2.5 per cent of iron, and 12 per cent of insoluble, 8 per cent of sulphur, and 9 per cent of lime.

Jack Rabbit district.—Four producers reported 6,709 tons of ore, containing $1,466 in gold, 45,059 ounces of silver, 381,315 pounds of copper, and 146,368 pounds of lead, valued in all at $155,282, or an average value per ton of $23.15. The principal part of the output was reported from the Uvada Copper property, which yielded ore of shipping grade, most of which was oxidized copper ore and the remainder oxidized lead ore. The Ida May, Fortuna, and Silsbee properties were also producers.

Pioche district.—Eleven producers reported 144,996 tons of ore, containing $41,989 in gold, 450,517 ounces of silver, 40,233 pounds of copper, 9,099,551 pounds of lead, and 1,332,521 pounds of recoverable zinc, valued in all at $1,342,677, or an average value per ton of $9.26. The greater part of the total output, or 128,702 tons, was of shipping grade, which, with 10,306 tons of old slag was shipped directly to the smelters. There were also 2,911 tons of concentrate produced containing gold, silver, copper, lead, and zinc. The greatest part of the district output was from the Prince Consolidated, which shipped low-grade iron manganese ore, containing small quantities of gold, silver, copper, and lead. Old tailings were re-treated in the Bullionville mill by oil flotation, and yielded considerable lead concentrate containing silver and gold. Equal quantities of ore were shipped from the Mendha and Hamburg mines, and from a lease on the Amalgamated Pioche property, the owners of which also shipped zinc-lead concentrate on company account.

Viola district.—A small shipment of copper ore carrying silver was shipped from the Viola property.

LYON COUNTY.

The output of 329,910 tons of ore, reported by 64 producers in 1917, was 298,488 tons more than was reported by 44 producers in 1916. The total average value per ton decreased from $30.61 in 1916 to $16.22 in 1917, and the gold and silver value of the ore from $3.28 to 17 cents per ton. There were 2,353 tons of ore and 4,620 tons of old tailings treated at amalgamation and cyanidation plants and yielded $49,441 in gold and 4,160 ounces of silver, valued in all at $52,869, or an average value per ton of $7.58. There were 322,371 tons of ore shipped to smelters, containing $940 in gold, 1,600 ounces of silver, 19,350,592 pounds of copper, and 2,250 pounds of lead,

Digitized by Google

valued in all at $5,285,165, or an average value per ton of $16.39. The placer output was small.

Pine nut district.—A small quantity of lead ore was shipped from a prospect in the district.

Ramsey district.—From the Ramsey-Comstock property tailings and some gold bullion were recovered.

Silver City district.—Twenty-eight producers reported 3,091 tons of ore and old tailings, which yielded gold and silver bullion. The output consisted of $44,704 in gold and 4,149 ounces of silver. Most of the ore was treated in the district by amalgamation, but the tailings were cyanided.

Talapoosa district.—Two mine operators reported a small production of oxidized copper ore containing a little silver from prospects in the district.

Yerington district.—Thirty-two deep-mine producers reported 322,945 tons of ore, containing $1,162 in gold, 1,571 ounces of silver, 19,396,536 pounds of copper, and 2,046 pounds of lead, valued in all at $5,297,888, or an average value per ton of $16.40. The greater part of this ore, or 322,367 tons, was of shipping grade, most of it being smelted at Thompson. There were also 566 tons of ore leached at the Nevada Douglas experimental plant in the district, and a small quantity of bullion was recovered at two other plants from ore treated by amalgamation. The largest part of the district output, consisting of copper ore, was from the Mason Valley property, with considerable quantities from the Bluestone and Nevada Douglas properties. The Empire Nevada, O'Connell, and Montana Yerington also produced copper ore.

The Mason Valley mines[1] produced 114,273 tons of copper ore, which was treated at the Thompson smelter. From outside sources 194,075, tons of copper ore were smelted, yielding altogether 7,038 tons of blister copper, containing 1,036.64 ounces of gold, 46,257.71 ounces of silver, and 13,914,764 pounds of copper. The company is operating, besides the Mason Valley mines, the Majuba Hills property, a group of 88 claims situated 16 miles from Humboldt on the Southern Pacific Railroad, in Humboldt County, and the Gray Eagle group in the Happy Camp district of Siskiyou County, Cal.

From the Nevada-Douglas property[2] there were shipped 52,451 tons of copper ore, from which the smelters returned to the company 4,430,725 pounds of copper, valued at $1,138,248.88. All of the smelting ore was shipped to the Mason Valley smelter at Thompson. Experiments were continued at the 50-ton leaching plant at Ludwig, and 28 tons of 68 per cent cement copper were reported[3] to have been shipped. Construction work on the leaching plant was not complete at the close of 1917 and the success of the process is still in doubt.

MINERAL COUNTY.

One hundred twenty-nine producers reported 274,571 tons of ore, or 8,388 tons more than was reported by 93 producers in 1916. The total average value per ton increased from $6.56 in 1916 to $7.37 in 1917, and the value of the gold and silver from $3.73 to $3.82. The larger

[1] Mason Valley Mines Co. Eighth Ann. Rept., for year ending Dec. 31, 1917.
[2] Nevada Douglas Copper Co. financial statement for year ending Dec. 31, 1917.
[3] Letters of Nevada-Douglas mines published in market stock letter of A. J. Orem & Co., Boston, Mass., Oct. 24 and Dec. 5, 1917.

Digitized by Google

part of the ore (202,748 tons) was treated at gold and silver mills, most of it by cyanidation, and yielded $681,757 in gold and 188,905 ounces of silver. This bullion included the recoveries made from 37,217 tons of old tailings re-treated by cyanidation. There were 32,154 tons of crude ore shipped to smelters, which contained $28,915 in gold, 171,632 ounces of silver, 3.458,565 pounds of copper, and 356,131 pounds of lead, valued in all at $1,145,157, or an average value per ton of $35.61. The output reported from 4 placers amounted to $428 in gold and 14 ounces of silver, against $743 in gold and 11 ounces of silver in 1916.

Aurora or Esmeralda district.—During 1917 the Aurora Consolidated mines[1] produced 175,477 tons of ore, containing $2.819 in gold and silver per ton; of which 50.3 cents per ton was lost in tailing. The total value recovered by cyanidation was $406,277.52, at a cost of 92.6 cents per ton for mining and $1.297 per ton for milling expenses. The property has been operated at a loss, according to the annual report of the company, which continues as follows:

Within the year 175,477 tons of ore of $2.819 grade were produced, from which resulted an operating loss of $18,788.26.

Interest on indebetedness was paid to the amount of $18,279.12, making a total loss for the year of $37,067.38.

In August it became apparent that the ore exposed in your property would not yield a profit. It was deemed advisable to push development work as rapidly as possible toward the old Juniata workings for the purpose of proving or disproving the stories regarding the vein and ore values in this section which has been caved and under water since 1872.

On the 4th of November an intermediate 85 feet above the main haulage tunnel encountered the shaft, which fortunately had not caved for 70 feet above this intermediate and gave access to what is believed to be the second level of the old Juniata mine. At this elevation the vein is exposed for 260 feet, of which 130 feet had been stoped in the early days. The vein is 8 feet wide at the most westerly exposure, where it has been square set and filled by the early day operators. At this elevation in the west end there is a 90-foot unstoped section 8 feet wide, cut samples from which average $4.50. Samples from the fill range from $4 to $6, and one cut across the back for 10 feet averages $20. The most encouraging features of the exposure are the vein apparently widens to the east and also widens with depth. * * *

The encouraging development in the Juniata ground, together with the lease on the Silver Lining claims, gives your company the most promising outlook for profitable operations that it has ever had. * * *

After the mill operations have ceased it will be possible to realize $100,000 through a thorough clean-up of the plant. This clean-up will result from dismantling the mill and burning all material which has been in contact with the rich solutions, and it can not be accomplished until the plant is entirely out of commission.

Bell district.—From the Olympic mine considerable ore was produced in 1917, yielding gold and silver bullion in a 100-ton cyanide plant. This mine is opened by a 235-foot incline shaft, and the mill has been operating continuously since April 27.

Buena Vista district.—All the ore shipped from three properties was valued at $4,137 for its content of gold, silver, copper, and lead. The Queen and Friday properties were producers of lead ore carrying principally silver and a little copper.

Cedar Range district.—This district is situated about 24 miles east of Mina, on the Tonopah & Goldfield branch of the Southern Pacific Railroad. The Copper Bell property, the only producer in 1917, yielded copper ore of shipping grade containing gold and a little silver.

[1] Goldfield Consolidated Mines Co. Eleventh Ann. Rept., for year ending Dec. 31, 1917.

Digitized by Google

Columbus district.—Eleven producers reported the production of 5,032 tons of ore of shipping grade and 39,176 tons of old tailings, part of which was treated by cyanidation and the remainder smelted. Altogether the district yielded $34,071 in gold, 255,765 ounces of silver, 39,379 pounds of copper, and 244,923 pounds of lead, valued in all at $276,635, or an average value per ton of $6.26. The old tailings milled came from the property owned by the Belleville Tailings Association, and that shipped directly to the smelter was from the dump owned by the Candelaria Syndicate. The shipping ore originated from the Lucky Hill, Argentum, Diablo, and Simon lead properties.

Hawthorne district.—The reports of 15 producers gave the production of 535 tons of ore containing $1,376 in gold, 17,445 ounces of silver, 35,558 pounds of copper, and 28,828 pounds of lead, valued in all at $27,937, or an average value per ton of $52.22. The production of placer gold was small. The Emerald Copper, Buster Boy, Garfield, and Lucky Boy were producers of ore. From the Pamlico region some drift mining in eroded material yielded gold by dry washing.

Mount Grant district.—The treatment of a small quantity of ore from the Mammoth property in a 2-stamp mill equipped for cyanidation yielded a small quantity of gold bullion. There were also a few tons of ore produced from the Congress property.

Pine Grove district.—At the Wheeler gold mines some gold and silver bullion was recovered from old tailings re-treated. The largest producer, the Pittsburg-Dolores, produced gold and silver bullion from the treatment of ore in its 75-ton cyanide plant.

Rand district.—Nine producers reported 2,795 tons of ore, containing $2,189 in gold, 2,390 ounces of silver, 374,395 pounds of copper, and 9,034 pounds of lead, valued in all at $107,145, or an average value per ton of $38.33. The bulk of the ore produced was of shipping grade, and only 8 tons were treated in a mill and yielded gold and silver bullion. The largest part of the output, consisting of copper ore containing gold and silver, came from the Copper Mountain property. Other producers were the Golden Pen, Nevada Rand, and Silver Cloud. The Copper Mountain property,[1] bonded by the Jumbo Extension Mining Co., comprises five patented claims and 13 nonpatented claims, which were being prospected in 1917. At the same time promising results were obtained from the sale of copper ore shipped by lessees. Nolan, a station on the Southern Pacific Railroad, is the nearest loading station.

Rawhide district.—From five properties there were 298 tons of ore produced, containing $8,748 in gold and 10,397 ounces of silver, valued in all at $17,315, or an average value per ton of $58.10. The greater part of the ore was treated by cyanidation at the mill of the Nevada New Mines Co., and only 45 tons of ore, principally siliceous silver ore, were shipped directly to the smelter. A little placer gold was also recovered from washing eroded surface material.

Santa Fe district.—Forty-nine producers reported 19,932 tons of ore, containing $2,009 in gold, 50,007 ounces of silver, 2,590,756 pounds of copper, and 35,799 pounds of lead, valued in all at $753,570, or an average value per ton of $37.81. Most of this ore was copper

[1] Jumbo Extension Mining Co. Ann. Rept. for year ending June 30, 1917.

Digitized by Google

bearing and was shipped to the smelter at Thompson, and a small quantity of ore containing lead was shipped to a Salt Lake smelter. There were only 78 tons from which gold and silver bullion was recovered. The most important producers of copper ore were the Wall Street, Calavada, Tip Top, Green Tunnell, Iron Gate, Mayflower, Champion, Iroquois, St. Patrick, Vacation, and Taft properties.

Silver Star district.—There were 2,651 tons of ore reported by 22 operators, which contained $2,218 in gold, 9,038 ounces of silver, 283,473 pounds of copper, and 24,033 pounds of lead, valued in all at $89,120, or an average value per ton of $33.62. The larger part, or 2,541 tons of ore, was shipped directly to the smelter and contained 100.65 ounces of gold, 9,033 ounces of silver, 280,075 pounds of copper, and 24,033 pounds of lead. There were 80 tons of ore treated in a concentration mill, producing copper concentrate, and a small quantity of bullion was recovered in a gold and silver plant. The principal producers of copper ore were the Olga, Copper King, and Silver Dike.

Walker Lake district.—The Northern Light property yielded a small quantity of oxidized copper ore shipped directly to the smelter.

NYE COUNTY.

Mine production in Nye County, Nev., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	100	564,450	$2,505,714	8,868,267	6,023	135,355	.....	$8,351,855
1917	114	514,361	2,007,234	7,172,642	15,529	430,025	6,042	7,959,328
Increase or decrease, 1917	.....	−50,089	−498,480	−1,695,625	+9,506	+294,670	+6,042	−392,527

[a] Includes placer production.

The output of 514,361 tons of ore was reported in 1917 by 79 opertors of deep mines. This was 50,089 tons less than was reported by 73 operators in 1916. The total average value per ton increased from $14.47 in 1916 to $15.04 in 1917. The value of the ore in both years was practically that of the gold and silver. Nearly all of the ore (509,692 tons) was treated at gold and silver mills, and yielded bullion containing $1,742,907 in gold and 6,844,701 ounces of silver, having an average value per ton of $14.49, and 851 tons of concentrates, which were shipped to smelters, containing 1,747.72 ounces of gold and 261,067 ounces of silver. These and 34 tons of concentrates produced at concentration mills contained altogether $36,136 in gold, 269,257 ounces of silver, and 342 pounds of copper, having a total value of $258,097, or an average value per ton of $291.63. The ore of shipping grade amounted to 1,605 tons and contained $8,425 in gold, 51,495 ounces of silver, 15,187 pounds of copper, 430,025 pounds of lead, and 6,042 pounds of zinc, valued in all at $92,602, or an average value per ton of $57.70. The placer gold reported from 35 operators amounted to $219,131 in gold and

Digitized by Google

5,754 ounces of silver, against a production in 1916 of $179,165 in gold and 4,501 ounces of silver.

Antelope Springs district.—A small lot of sorted ore containing 70 ounces of silver a ton was shipped from the Antelope mine.

Bellehellen district.—Two properties near Clifford produced milling ore, part of which was treated in a small stamp mill on the property, and about 400 tons were shipped to the West End mill at Tonopah. These ores carried principally silver with some gold.

Belmont or Philadelphia district.—The Monitor Belmont property, on which operations were commenced in 1916, was closed in 1917, having probably worked over the best part of the old tailing dumps.

Bullfrog district.—There were only 34 tons of ore produced in the district in 1917. The largest part, or 29 tons, containing gold, silver, and copper, was shipped to the smelter, and the remainder produced a little gold and silver bullion. This bullion was from a clean-up around the mill of the Pioneer Consolidated Co., which was said to be closed as a result of the Nevada California Power Co. discontinuing the electric power service in the district.

Cloverdale district.—The Orizaba mine, worked by lessees, produced a small quantity of silver ore, containing a little gold.

Ellendale district.—The Dividend property yielded a small quantity of oxidized copper ore of shipping grade containing silver with a little gold.

Johnnie district.—There were three producers, the Johnnie and the Eureka Johnnie treating gold ore at their respective milling plants, and the Black Jack producing lead sulphide ore of shipping grade containing silver. A small amalgamation mill was built in 1917 a short distance southwest of Johnnie to treat Eureka ore. It was equipped with a crusher and two 1,000-pound stamps, and worked a few tons of ore containing gold and silver.

Mammoth district.—The Illinois property produced shipping ore containing lead and silver with a little copper and gold. On this property there is a 100-ton lead smelter, which has been closed for 10 years. The larger part of the crude ore shipped had been in the smelter bins since the closing of the furnaces. Included with the ore was some material from the clean-up of the flue chambers and furnaces.

Manhattan district.—Nineteen mine producers reported 25,427 tons of ore, containing $113,008 in gold and 1,899 ounces of silver, valued in all at $114,573, or an average value per ton of $4.51. In 1916 there were 11 producers with an output of 41,725 tons of ore, valued at $123,299. The placer output reported by 31 producers in 1917 amounted to $64,677 in gold and 1,202 ounces of silver, having a total value of $65,667, against an output in 1916 by 25 placer operators who produced $75,359 in gold and 1,380 ounces of silver, with a total value of $76,267. Most of the ore produced in 1917 came from the White Caps and the Mayflower & Big Pine properties. The White Caps mine has been newly equipped with a 150-ton all-slime cyanidation plant. This mill was finished in September, 1917, and started the treatment by cyanidation after the ore was roasted. The mine is opened by a vertical shaft 500 feet deep with various drifts and crosscuts. The character of the ore mined was largely sulphide with a siliceous gangue. The other important producers

Digitized by Google

of milling ore were the Manhattan Dexter, Verde, Mustang, Seyler-Humphrey, Union Amalgamated, and Big Four properties. The placer properties producing were the Bulldog, Edith, Auction, Thursday Fraction, African, and China.

Northumberland Canyon district.—This district, in which the Blue Bell mine is situated, is 30 miles north of Belmont. The property was a producer of silver ore in the early seventies and again in 1917.

Oak Springs district.—The nearest railroad point is Indian Springs, from which a small quantity of copper ore containing a little silver was shipped to the smelter from the Horseshoe claim.

Reveille district.—Nine producers reported the production of 416 tons of ore, containing $417 in gold, 7,427 ounces of silver, 4,874 pounds of copper, and 233,300 pounds of lead, valued in all at $27,932, or an average value per ton of $67.14. The principal producer was the Southwestern Nevada Mines Co., which shipped oxidized lead ores containing silver and a little gold.

Round Mountain district.—Nine producers reported 13,584 tons of ore against the output of eight operators producing 29,927 tons of ore in 1916. The total output, including the production of three placers, consisted of gold, silver, and a little lead, valued at $269,635. The placer bullion contained $154,323 in gold and 4,548 ounces of silver, against a production in 1916 of $103,806 in gold and 3,121 ounces of silver. The property of the Round Mountain Mining Co. was the principal producer of gold ore and of placer gold. Bullion was also recovered from ore mined from the Fairview and Blue Jacket mines. The Seevers property yielded some oxidized lead ore and silver ore, which was shipped to the smelter. Most of the placer gold was recovered from erosion material from Round Mountain, and some gold was recovered by drift mining and sluicing the material from the Eureka claim, situated on Shoshone Creek, 3 miles from Round Mountain. The Kaurohat property,[1] in Jefferson Canyon, was reported to have its 150-ton mill in good condition by replacing its stamp batteries with ball mills and equipping the rest of the plant for treating the ore by cyanidation and oil flotation.

With a number of improvements inaugurated at the Round Mountain Co.'s[2] holdings in 1917, the production of gold was increased, according to the following extracts from its annual report:

* * * 12,118.29 tons of ore, having a gross value of $87,366.21, were mined and milled, yielding $78,483.83 in bullion, representing an extraction of 89.8 per cent of the gross value of the ore. Figures per ton are as follows: Gross value, $7.209; tailings loss, $0.733, and net recovery, $6.476. The total operating cost, exclusive of depreciation and certain overhead and administrative expenses apportioned to both lode and placer operations, was $52,834.11, of which $26,462.20 was for milling. The total operating cost per ton was $4.359, including $2.183 for milling.

In addition, your company received in royalties on lode leases $1,817.27, in returns from leasing operations on the Blue Jacket group $318.68, and as miscellaneous earnings $1,987.53. The total revenue, therefore, from lode operations was $82,607.31, or $6.816 per ton, or a total lode realization, after deducting operating costs, of $29,773.20, or $2.457 per ton. * * *

During the year ending December 31, 1917, 127,788 cubic yards of placer gravel were moved, yielding 10,992.69 ounces of bullion, worth $140,016.62. Total operating costs were $47,678.52. Total realization was $93,978.07, which includes $2,961.96 received in royalties from bedrock lessees. * * * The

[1] Min. and Sci. Press, Oct. 30, 1917, p. 590.
[2] Round Mountain Mining Co. Twelfth Ann. Rept., for year ending Dec. 31, 1917.

Digitized by Google

gross value recovered on company account represents $1.0956 per yard, the operating cost $0.373 per yard and the realization, inclusive of royalties, $0.7354 per yard. * * *

In 1917 your company cleaned 107,678 square feet of bedrock, at an average cost of $0.0699 per square foot. The gross value recovered was $15,353.36 or $0.1426 per square foot. Bedrock leasers cleaned 163,745 square feet, yielding $12,289.51, or $0.075 per square foot. Your company realized $2,961.96, or $0.0181 per square foot. * * *

The main tail race on January 1, 1918, measured 4,280.2 feet. During the year 1,269.4 feet of flume were added, 744 feet at the head and 525.4 feet at the dump end. The bottom of the flume is lined for its entire length with five longitudinal rows of 25 pound rails. * * *

The final clean-up of the main tail race was made in October, 1917, and yielded $22,899.63 in bullion, of which amount $12,613.38 was cleaned up in the usual manner and $10,286.25 was recovered from milling 165 tons of concentrates averaging $62.34 per ton. In 1916 your company's recovery from the main tail race was $9,026.70 from 175,477 yards, the gross value of which was $139,912.16, the clean-up representing 6.5 per cent of the total value recovered. In 1917 the clean-up was $22,899.63 from 127,788 yards, the gross value of which was $140,016.52, this clean-up representing 16.3 per cent of the total value recovered.

San Antone district.—From the Hudson property two kinds of ore were produced; siliceous ore was treated by cyanidation at Tonopah, and the lead ore shipped to the smelter.

Tonopah district.—

Mine production of Tonopah district, Nev., 1904–1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	
1916	21	455,140	$1,941,441	8,734,726	.....	.....	$7,688,891
1917	20	470,122	1,539,529	7,068,737	.....	.....	7,364,168
Increase or decrease, 1917	.....	+14,982	−401,912	−1,665,989	.....	.....	−324,723
Total, 1904–1917	.....	4,783,726	24,972,732	113,966,413	12,113	214,523	92,333,975

Nearly all the output in 1917 shown above, or 469,730 tons, yielded gold and silver bullion at cyanidation plants, some of which were equipped for concentration, recovering 849 tons of silver concentrate. The mill bullion contained 72,651 ounces of gold and 6,798,077 ounces of silver, and the concentrates contained 1,732.27 ounces of gold and 260,680 ounces of silver. There were only 340 tons of silver ore shipped from the district. The average bullion recovery per ton of ore cyanided was valued at $15.12, and the average value of the concentrates per ton was $295.18. The principal producers of ore, named in order of production, were Tonopah Belmont, Tonopah Extension, Tonopah Mining, West End, Jim Butler, Rescue Eula, Montana Tonopah, and McNamara.

From the Tonopah Belmont mine[1] there were produced during the fiscal year 162,051 wet tons of crude ore, from which 27,458 wet tons of waste rock were culled. Altogether 131,100 dry tons of ore, valued at $2,170,993.93 in gold and silver, were treated by cyanidation. This ore averaged per ton 0.159 ounce of gold and 16.86 ounces of silver, valued at $16.56, in 1917, as compared with 0.20

[1] Tonopah-Belmont Development Co. Fifteenth Ann. Rept., for year ending Feb. 28, 1918.

Digitized by Google

ounce of gold and 19.70 ounces of silver, valued at $17.54, in 1916. Dividends paid by the company in 1917 amounted to $375,009.39, making a total of $9,518,063.32 since June 21, 1906. The annual printed report of the company gives the following information:

The total metals recovered from the Belmont mine ores were 19,953 ounces of gold and 1,946,757 ounces of silver. The entire gold production was sold at $20.5534 per ounce. The entire production of silver was sold, as produced, at an average price of 84.13 cents per ounce.

During the latter half of the year a contract for the purchase and treatment of the mine production of the Tonopah Mining Co. of Nevada was executed. With this extra tonnage, in addition to the available tonnage from the Jim Butler Tonopah Mining Co., which had previously been treated at Millers, the economy of treating all the ores at the Tonopah mill became apparent. Equipment for the handling of the foreign ore from railroad cars to the mill was installed and on December 1 the Jim Butler ores were diverted to the Tonopah mill, and since January 1, 1918, the Tonopah Mining Co.'s ores have been received at this plant. During the last quarter 15,040 dry tons of outside ores have been treated, at a profit of $3,889.94.

The royalties from the leases on the slimes ponds at Tonopah have amounted to $7,026.45.

The slimes re-treatment or "sweepings" plant at Tonopah began its second operating season on April 16, 1917, and was operated steadily and successfully throughout the "sweeping" season, or until November 14, 1917, with a net profit of $18,278.97.

The Millers cyanide mill was operated continuously during the first nine months of the fiscal year, and in this time handled 31,462 tons of custom ore, with a resulting profit of $44,952.86, including a miscellaneous profit of $364.40. Royalties from the leases on the slimes ponds at Millers amounted to $1,851.26 in addition to the above. Because the available tonnage of custom ore was insufficient to allow of the most economical operating cost, the mill was shut down—the last ore being received on November 27, 1917—and the plant was cleaned up. A considerable part of the machinery has been sold and shipped to plants of the Belmont Co.'s subsidiaries, and the mill will be further dismantled. * * *

During the fiscal year 1917–18 the Tonopah mill treated 146,140 dry tons of ore of a total metal content of 23,647.557 ounces of gold and 2,320,945.67 ounces of silver and an average metal content of 0.162 ounce of gold and 15.88 ounces of silver. The metals recovered in bullion, concentrates, etc., aggregated 22,547.126 ounces of gold and 2,170,518.92 ounces of silver. The extraction was 95.35 per cent of the gold and 93.52 per cent of the silver, or a combined extraction of 94.05 per cent—0.7 per cent higher than in the previous year.

Custom ore to the amount of 15,040 tons was purchased and treated, the recovered metals from these aggregating 2,593.64 ounecs of gold and 223,761.92 ounces of silver.

The average direct milling cost per ton of ore was $2.863, or $0.315 higher than for the previous year. The average indirect milling cost was $0.218 per ton, or $0.008 higher than for the previous year. The total milling cost per ton of $3.081 is higher by $0.323, or 11.71 per cent, than in the previous year. The advanced costs of supplies and labor account for the difference. The milling cost of producing 1 ounce of Dore bullion advanced from $0.1492 in 1916–17 to $0.2062 in 1917–18, or 38.2 per cent. * * *

The plant for the re-treatment of "sweepings" from the slimes tailings ponds, built in 1916, commenced its second season's operations on April 16, 1917, and during the summer's campaign, until November 14, 1917, the plant operated steadily, treating 5,492 tons of sweepings. The plant was cleaned up at the close of the campaign, leaving it clean of absorptions. * * *

It is of interest to note that, during the 11 years of life of the Millers plant, it handled 568,345 tons of ore, of a gross value of $11,989,512.56, and that since August, 1912, operated as a custom mill, the plant handled 341,542 tons of ore, from which a profit of $180,906.03 was derived.

The royalties accruing from the leases on the slimes tailings ponds at Tonopah and Millers during the year have amounted to $8,860.85. The profitable operations of these "sweeping" leases on the ponds is due, in great part, to the re-treatment plant at Tonopah, which has reduced the expense of shipping and marketing the material and made possible the gathering of lower grade sweepings.

Digitized by Google

The Tonopah Mining Co.[1] reports that the most successful saving in its history was accomplished in the cyanidation mill in 1917. There were milled 109,835 dry tons of ore, averaging 0.163 ounce of gold and 14.19 ounces of silver per ton, yielding bullion containing 16,929 ounces of gold and 1,443,368 ounces of silver. This represents a recovery of 94.6 per cent of the gold and 92.6 per cent of the silver, or an average recovery of 91.9 per cent of both metals and a net gain over the previous year of 1.8 per cent. Relative to some of the mill difficulties, the company report says:

In May a Monarch reverberatory furnace was installed to take the place of the six Faber de Feuer furnaces for melting the precipitate. The reason for making the change was that the graphite retorts used in the Faber de Feuer furnaces had advanced in price from $14 to $46 each, and delivery was very uncertain. With the Monarch furnace it was possible to reduce the amount of fluxes used by approximately 50 per cent, and the graphite retorts were eliminated. The installation thus paid for itself in a very few months. Some difficulty was experienced in using over again the carborundum lining furnished with the furnace. This has been overcome by the substitution of graphite for carborundum, the graphite being reclaimed by grinding up the old retorts, from which a still further saving resulted.

In September, owing to the rise in silver, it was deemed advisable to put on three shifts at the mill and increase tonnage by milling ore-house reject in conjunction with mine ore. Due to the ore-house reject, consisting chiefly of porphyry, it is very difficult to settle. Also, when it reaches the filters, it makes a very sticky, impervious cake, and decreases the capacity of the filters. For this reason it has not been possible to mill as large a tonnage of mine and ore-house reject together as mine ore alone. With the aim in view to increase the tonnage, one of the agitators is being converted into a settler, and the size of the filter leaves has been increased, where the dimensions of the filter box will permit. In addition, the dump ore, ton for ton, occupies about 10 per cent more space than the mine ore, which further limits tonnage, as volume is a determining factor throughout the process.

The West End mine[2] produced 45,910 tons of ore, valued at $721,936.91, or an average of $15.73 in gold and silver. The ore contained 7,160.93 ounces of gold and 677,116.83 ounces of silver. Dividends paid to stockholders amounted to $89,424 in 1917. At the cyanidation mill, custom ore was treated beside that from the West End mine. The direct cost of mining in 1917 was $5.21 per ton, against $4.38 in 1916, and the direct milling cost $2.79, against $2.92. The following paragraphs are taken from the company's report:

The increased cost is distributed through practically every item, this being due to the increase in the cost of all supplies used, and also to the fact that a further increase in miners' wages took place during the year. The increase of cost as indicated by these figures is not fairly representative of the increase in the cost of supplies and labor, as old stocks of material which were purchased during the days of lower prices, were used during a portion of the year. Therefore, the outlook is for higher cost per ton in the future, rather than a decrease. * * *

During the year the mill treated 66,833 dry tons of ore, an average of 183 tons per day, with a value of $20.51 per ton, this being the maximum capacity at which the plant can be operated efficiently with this grade of ore. * * *

There was a daily average of 26.6 stamps dropping continuously, crushing 6.9 tons per stamp. This average is a little low due to the extreme hardness of the ore from the Ohio workings. The so-called rhodonite ore from this territory is more rebellious than from other sections of the mine, requiring finer grinding and slightly different treatment. * * *

The average recovery was 94.56 per cent of the gold and 92.67 per cent of the silver, as compared to 94.5 per cent gold and 91.19 per cent silver for the pre-

[1] Tonopah Mining Co. of Nevada Sixteenth Ann. Rept., for year ending Dec. 31, 1917.
[2] West End Consolidated Mining Co. Eleventh Ann. Rept., for year ending Dec. 31, 1917.

Digitized by Google

vious year. The recovery of values based on net smelter returns was 91.6 per cent as compared with 90.6 per cent for the previous year. * * *

During the past year the tonnage of custom ore from outside districts increased to such an extent that it became necessary in December to construct an additional 50-ton ore bin, so as to receive ore direct from railroad cars or auto trucks. * * *

During the month of April an entirely new vein was discovered in a raise from the 500-foot level, and a few weeks later pay ore was encountered. The vein was found in the California claim, lying in or adjacent to Mizpah trachyte. * * *

Like all productive veins in this portion of the district the ore bodies in this vein are irregular in shape and contain here and there blocks of low-grade ore and waste. * * *

Mizpah trachyte and West End rhyolite, the two most productive ore-bearing formations of the Tonopah district, have been proved to exist in large masses in this portion of your holdings, a location which up to a year ago was believed to be composed mainly of the intrusive lavas and volcanic débris from Mount Brougher. The fact that these formations have been encountered at this point, and that a productive vein, the existence of which has been hitherto unknown, has been discovered, indicates the possibility that further prospecting of your ground in this vicinity may result in other valuable discoveries.

The Tonopah Extension Co.[1] reports the mining and milling of 110,187.7 dry tons of ore, containing 1,296,999.43 ounces of silver (averaging 11.771 ounces per ton) and 12,848.863 ounces of gold (averaging 0.117 ounce per ton). The average price received for silver was $0.86081 per ounce and $20.6718 per ounce for the gold, making the average gross value of the ore mined and milled $12.543, of which $10.133 was silver and $2.410 was gold. The gold and silver loss in tailing was $1.19 per ton of ore treated, thus making the metal recovery 90.51 per cent, or $11.353 per ton. With these deductions, there were sold 1,169,671.15 ounces of silver and 11,809.042 ounces of gold, valued in all at $1,250,982.73. The mining cost (including all development work) was $5.26 per ton; milling, $3.21; metal losses in tailing, $1.19; freight, express, and refining, $0.17; or a total cost of $9.831 per ton, and a total profit per ton of $2.712.

The Jim Butler mine[2] produced in its fiscal year 40,297 dry tons of ore, of which 443 tons were mined and milled by the West End Consolidated from undisputed Butler territory, and the remainder was treated in the Belmont mill. Since 1913 the Jim Butler has produced 189,222 tons of ore, containing 54,039.9 ounces of gold and 4,835,639.26 ounces of silver, valued in all at $4,035,283.56, with a net realization of $1,528,868.73, representing a profit of 38 per cent. The company report contains the following concerning the 1917 production:

The total production of the property, including ores from leased ground, was 55,643 wet tons of crude ore, from which there was sorted out as waste 15,529 wet tons (26.5 per cent), leaving 42,149 wet tons containing 4.4 per cent moisture, or 40.297 dry tons of mill ore, the gross metal content of which was 11,616.95 ounces of gold and 1,017,745.80 ounces of silver, and the gross value of which was $1,052,600.67. The tonnage of crude ore mined during the period was greater by 1,735 tons than the tonnage of the previous year, but because of the greater quantity of waste sorted out the tonnage of dry mill ore was less by 6,192 tons.

The total operating costs were $11.94 per ton, an increase of $1.14 per ton over the similar costs ($10.80 per ton) of the preceding year. Mining costs were $5.17 per ton, as compared with $4.80 during the preceding year, the increase being almost entirely due to advanced rates of wages. Treatment charges were $5.33 per ton, as compared with $4.79 in 1916, the higher rates

[1] Tonopah Extension Mining Co. Ann. Rept. for year ending Mar. 31, 1918.
[2] Jim Butler Tonopah Mining Co. Ann. Rept. for year ending Sept. 30, 1917.

Digitized by Google

being entirely due to the higher costs of mill labor and supplies. General expense, including administration, taxes, bullion taxes, insurance, etc., was 73 cents per ton, an increase of 35 cents over the 38 cents per ton cost of 1916. Losses in tailings and metal losses (smelter deduction on sales of concentrates) were $1.79 per ton, an increase of 23 cents per ton over the similar losses in 1916. This increase in losses, however, was due entirely to the higher money value of the ore milled, there having been an actual decrease of losses of 1.04 per cent. The total costs and losses were $13.73 per ton for the year, an increase of $1.57 per ton over the total costs and losses of 1916. The percentage of profit, however, was 45.42 per cent, as compared with 36.27 per cent of the previous year.

Tybo district.—The entire year of 1917 was spent in equipping, dewatering, and putting the old working of the Tybo property in condition for operation. The mine is opened to depth of 400 feet by a shaft and has 3,500 feet of drifts. The 75-ton concentration plant at the mine was nearly completed in 1917. During these operations there was an important tonnage of sulphide lead ore, containing silver and gold, shipped directly to the smelter.

Union district.—Old tailings from the silver mills were re-treated by cyanidation and resulted in the recovery of silver bullion containing a little gold. A lessee on the Webster property succeeded in shipping a small quantity of silver ore, containing a little lead and gold. The principal operations on this property consisted of prospecting with a churn drill to find new ore bodies.

Willow Creek district.—One shipper of gold ore reported production in 1917.

ORMSBY COUNTY.

One deep-mine producer reported 37 tons of ore, which is 70 tons less than was produced in 1916 from 3 mines. The total average value per ton increased from $6.46 in 1916 to $41.73 in 1917, and the gold and silver value from $6.15 to $39.05 per ton.

Voltaire district.—The Panama Canal property, yielding both oxidized and sulphide ores, was a producer of ore containing silver, gold, and a little copper. The property is opened by two adits, one 400 feet and the other 375 feet.

STOREY COUNTY.

Mine production in Storey County, Nev., in 1916–1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	
1916	24	63,187	$483,137	285,827	903	11,057	$672,196
1917	33	59,805	360,875	243,072	.....	.....	561,166
Decrease, 1917	.....	3,382	122,262	42,755	903	11,057	111,030

The output of ore was 3,382 tons less than in 1916, and the total average value per ton, all of which was for gold and silver, decreased from $10.64 in 1916 to $9.38 in 1917. The entire county output came from Comstock district.

Comstock district.—Thirty-three producers reported an output of 59,805 tons of ore, containing $360,875 in gold, 243,072 ounces of silver, valued in all at $561,166, or an average value per ton of $9.38.

Digitized by Google

The principal part of the ore produced was milled at cyanide plants, where there were 49,640 tons of ore treated, yielding 15,582.64 ounces of gold, valued at $322,122, and 226,213 ounces of silver. There were also 170 tons of concentrate produced at these plants valued at $30,627, or an average value per ton of $180.15. Only 80 tons of ore, containing gold and silver, were shipped to the smelters from the district, having an average value per ton of $275.23. In 1916 there were 24 producers with a total output valued at $672,196, or an average value per ton of $10.64. The principal producers in 1917 were the Union Consolidated, Chollar & Potosi, Andes Silver, Consolidated Virginia, Silver Hill, Crown Point-Belcher-Jacket, Mexican, and Ophir Silver properties. A considerable quantity of old tailings, which originated in this district, was treated at Dayton by cyanidation. The old tailing of Comstock ores on the site of mills formerly situated 5 miles below Dayton, on Carson River, have been repeatedly tested in an attempt to extract the gold and silver profitably. In September, 1917, the Dayton Placer Recovery Corporation started a new cyanidation mill equipped with six tanks holding 1,200 tons of pulp, four Dorr agitators, and two Oliver filters. About 125 tons of tailing were treated daily, with reports of good recovery.

WASHOE COUNTY.

The output of ore by 31 producers aggregated 2,820 tons, 2,241 tons less than was produced by 28 producers in 1916. The total average value per ton increased from $25.68 in 1916 to $26.21 in 1917, and the gold and silver value in the ore from $14.19 to $16.15. The greater part of the ore was milled and yielded lead concentrate, containing silver, and having an average value per ton of $168.41. Ore treated at gold and silver mills, 341 tons, produced gold and silver bullion containing $9,698 in gold and 235 ounces of silver, with an average value per ton of $29.01. The placer output amounted to $120 in gold and 2 ounces of silver.

Eagle and Washoe Valley districts.—The Washoe claim, which is situated about 3 miles west of Carson City, was the principal producer. It is reported that the ore exposed will average $11 in gold, silver, and copper per ton, which is of too low a grade to ship without concentration.

Leadville district.—Lead ore produced from the Tohoqua property and treated in its 75-ton concentration mill yielded concentrates containing lead and silver and a small quantity of gold. Another small output of lead concentrate was reported by a lessee who sluiced some of the old tailing.

Peavine district.—A small quantity of copper ore was shipped to the smelter from the Nixon-Nevada property,[1] situated 14 miles north of Reno, and a test lot of ore came from the National Copper claim. A small quantity of ore was shipped from the Gillespie tunnel, and one lot of lead ore from the Wedekind property.

White Horse district.—From various sources, 333 tons of ore were reported, all of which, with the exception of 2 tons shipped directly to the smelter, was milled in the small gold and silver plants in the

[1] A newspaper report, probably issued by brokers, states that from the Nixon-Nevada "last summer (1917) 17 carloads of ore were shipped that averaged 25 per cent of copper and $15 in gold and silver as extracted from vein No. 4 at a depth of about 155 feet." This may have referred to 17 mine cars instead of railroad cars.

Digitized by Google

district equipped principally for amalgamation. The total district output contained $9,642 in gold and 179 ounces of silver, valued in all at $9,790. The total value of the output in 1916 was $32,895.

WHITE PINE COUNTY.

Mine production in White Pine County, Nev., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.a	Silver.a	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	41	4,056,257	$743,049	147,110	93,107,945	1,641,066	24,494	$23,860,917
1917	47	4,474,253	769,833	186,574	93,786,328	2,437,908	.....	26,736,898
Increase or decrease, 1917	.....	+417,996	+26,784	+39,464	+678,383	+796,842	−24,494	+2,875,981

a Includes placer production.

Two properties produce the greater part of the county output. Altogether 44 operators reported the production of 4,474,253 tons of ore, or 417,996 tons more than was produced in 1916, as reported by 40 operators. The total average value per ton increased from $5.88 in 1916 to $5.98 in 1917, but the gold and silver value in the ore was 21 cents, the same as in 1916. The bulk of the ore, 4,385,232 tons, was treated at concentration mills and yielded 595,162 tons of concentrates, nearly all of which, 594,898 tons, was copper concentrate. There were 254 tons of lead concentrate and 10 tons of silver concentrate. The total average value per ton of all concentrates was $41.07. There were 88,724 tons of ore directly smelted, which contained $32,685 in gold, 66,446 ounces of silver, 7,396,671 pounds of copper, and 2,110,132 pounds of lead, valued in all at $2,288,199, or an average value per ton of $25.79. There were 48 tons of old tailings and slag smelted, yielding gold, silver, copper, and lead. Gold and silver bullion was produced from 16 tons of ore treated at milling plants. The placer output amounted to $1,212 in gold and 10 ounces of silver, against an output reported in 1916 of $696 in gold and 7 ounces of silver.

Aurum district.—The principal output was from the Lucky Deposit property, which produced copper ore containing some silver. This ore is hauled to Currie, situated on the Nevada Northern Railway. There was also copper ore shipped from the Muncy Creek property, and oxidized lead ore from the Dandy claim situated in the Red Hills, near Aurum.

Cherry Creek district.—Tailings from an old concentrating mill 7 miles north of Cherry Creek were re-treated in a 50-ton flotation plant completed in 1917. These tailing were reground in a Hardinge mill and the valuable minerals separated in Callow flotation cells. The concentrate contained principally silver with a little gold and copper. There was also a small output of lead ore from the Gray Eagle claim.

Duck Creek district.—Seven producers reported the production of 155 tons of ore of shipping grade, containing $493 in gold, 2,088 ounces of silver, 255 pounds of copper, and 104,501 pounds of lead, valued in all at $11,271, or an average value per ton of $72.72. The

Digitized by Google

principal producers were the Cuba, Lead King, McGill, Success, and White Cloud properties.

Eagle district.—The Red Hills property was operated during the year and produced lead ore containing silver and gold.

Granite district.—Four operators in the district reported 29 tons of ore containing gold, silver, and lead, and having a total value of $2,482.

Hunter district.—The Vulcan Mining, Smelting & Refining Co., owning the Hunter claims, shipped product containing principally lead, copper, and silver.

Osceola district.—The output of 3 placers consisted of $1,212 in gold and 10 ounces of silver obtained from sluicing the gravel in the Osceola town gulch.

Pinto district.—A small quantity of lead ore carrying silver was shipped from the Washington and Mareland property.

Robinson (Ely) district.—There were 16 producers in 1917, but the bulk of the ore came from two mines, the Nevada Consolidated and the Consolidated Coppermines. The following table gives a comparison of the production for the last two years and the total output beginning with the year 1904:

Mine production of Robinson district, White Pine County, Nev., 1904–1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	8	4,053,950	$737,964	110,802	93,044,578	92,127	.....	$23,706,195
1917	16	4,467,709	765,376	131,825	93,627,420	512,862	.....	26,478,391
Increase, 1917	.....	413,759	27,412	21,023	582,842	420,735	.....	2,772,196
Total, 1904–1917	.....	28,201,817	4,652,117	846,425	644,940,304	2,005,334	42,651	120,029,665

Ore extraction at the Nevada Consolidated mine[1] aggregated 3,076,285 tons of sulphide ore, containing 1.28 per cent or copper, from the steam shovel pits, and 991,164 tons of sulphide ore, containing 2.01 per cent of copper, from the Ruth mine. In addition to the sulphide ore, there were 59,176 tons of siliceous carbonate ore, averaging 2.84 per cent of copper, 49,108 tons of which were received at the smelter at Steptoe, Nev., and 10,068 tons shipped to Garfield, Utah. The company's report contains the following detail:

> The net reserves of developed ore remaining in the Copper Flat and Ruth mines at the close of 1917 totaled 70,025,322 tons, containing an average of 1.58 per cent of copper. * * *
>
> There are other bodies of sulphide and carbonate ore of superior grade totaling more than 1,000,000 tons which have not been heretofore or now included in the regular calculated reserves. It is believed that further development will keep pace with ore extractions for some time to come.
>
> The production for the company's mines for the year showed a decrease of over 8,000,000 pounds, or about 9 per cent, as compared to the year 1916. This is due primarily to two causes—first, that the grade of ore was lower than that for previous year; and, second, that there was treated at the company's concentrator and smelter during the year a considerable tonnage of ores and concentrates from adjoining properties now owned by the Nevada Consolidated Co. The total tonnage from both sources treated at the concentrator for the year exceeded that for 1916 by some 300,000 tons. The total copper contents

[1] Nevada Consolidated Copper Co. Eleventh Ann. Rept., for year ending Dec. 31, 1917.

Digitized by Google

in concentrates produced at the concentrator was substantially the same for both years, but at the smelter the output of copper for the year 1917 exceeded that for the year 1916 by approximately 1,000,000 pounds. The total charge smelted exceeded that for the year 1916 by approximately 100,000 tons, equivalent to over 15 per cent. The grade of concentrates was, however, lower than that for 1916, due to the grade of ore milled being somewhat lower. * * *

The net profits for the year were $9,408,892.72, as against $15,435,359.14 for the year 1916. * * *

Distribution to stockholders during the year amounted to $8,297,746.55. The total of such disbursements from the beginning of operations up to the end of 1917 has been $35,771,608.10. * * *

Total steam-shovel mining costs of concentrating ores for the year were 33.38 cents per dry ton, of which 14.48 cents were taxes, leaving direct operating costs, including all overhead expenses other than taxes, of 18.9 cents per ton as against 12.42 cents direct operating costs for 1916. Exclusive of taxes the corresponding shovel pit mining costs in 1917 increased 52.2 per cent above the year previous. To this mining cost must be added 30 cents per dry ton of ore covering retirement of stripping suspense account. The total mining costs, including taxes and stripping suspense charge of 30 cents, amounted in 1917 to 63.38 cents, as against 53.7 cents for the previous year.

In 1917 overburden removal costs were 34.43 cents per cubic yard, as compared with 30.09 cents for 1916.

Ruth underground mining costs were $1.0251 per dry ton as compared with $1.2021 for 1916. In this mining cost is included 19.99 cents per ton covering taxes, leaving a direct mining cost of 82.52 cents as compared with $1.062 for 1916. To this mining cost must be added the development suspense charge of 30 cents per dry ton and deferred construction charge of 5 cents, making total mining cost, including taxes, $1.3751. The reduction in mining cost here as compared to that of 1916 was due in part to increased tonnage and in part to employing wholly a more economical system of mining than was first used. * * *

The total sulphide ore tonnage milled during 1917 was 4,064,095 tons averaging 1.462 per cent copper, with an actual mill extraction of 73.08 per cent, ratio of concentration 7.18 to 1, and average copper in concentrates 7.673 per cent, the ratio of concentration and grade of concentrates being somewhat lower than during the year previous owing in part to the large percentage of the ore milled being of primary character, relatively high in iron and sulphur contents.

The Consolidated Coppermines Co.[1] in 1917 produced 9,806,898 pounds of copper, at an average selling price of 24.57 cents per pound, 11,979 ounces of silver, 2,557.10 ounces of gold, and 65,309 pounds of lead, valued in all at $2,473,438.85. From the company's annual report the following paragraphs are taken:

Your company owns in fee 1,151 acres of mining properties and claims, together with 2,565 acres of ranch lands having valuable water rights. It also controls, through ownership of approximately 99 per cent of the capital stock of Giroux Consolidated Mines Co., 2,000 acres of patented mining claims, and 1,800 acres of ranch lands, which also have valuable water rights; also, through its stock ownership in the Butte & Ely Co., 209 acres of patented mining claims. The total area of properties owned and controlled by the Coppermines Co. is 3,360 acres of patented mining claims and 4,365 acres of ranch lands.

The most notable development of the period has been the opening up of the high-grade oxidized ores in the Alpha mine. This work has been productive of most excellent results. The ore has been found at various points extending from the 800 to the 1,200 foot levels, and the ore shoots are proving to be larger and more continuous on the lower levels, with the grade continuing at about 8 per cent. * * *

It has been found that three classes of copper ore occur in the properties, (1) sulphide concentrating ore, occurring in large continuous masses of monzonite porphyry; (2) direct smelting oxidized ore, forming replacement deposits in limestone in the vicinity of limestone-porphyry contacts; and (3) direct smelting sulphide ore, with high iron contents. Our underground development work has been confined to the Morris-Brooks mine, where concen-

[1] Consolidated Coppermines Co. Ann. Rept. for year ending Apr. 30, 1918.

Digitized by Google

trating porphyry ore occurs, and the Alpha, which produces direct smelting oxidized ore. * * *

In making the estimates of ore reserves herewith submitted, certain tonnages of low-grade porphyry ore have not been included which were taken into account in previous reports. On this revised basis it is estimated that there is concentrating porphyry sulphide ore, wholly or partly developed, amounting to 20,092,800 tons, averaging 1.31 per cent copper. In addition there are considerable tonnages of direct smelting ores, both oxidized and sulphides, although development work is not sufficiently advanced to permit of their accurate calculation.

Ore was mined at three different points: (1) The Morris-Brooks mine, supplying ore to our Kimberly concentrator; (2) the Alpha mine, producing direct smelting ores only; and (3) the Liberty Pit, where ore is mined by steam shovel by the Nevada Consolidated Copper Co. and concentrated at its Steptoe Reduction Works for our account.

The tonnage mined, grade of ore, and metals produced were as follows:

	Dry tons mined.	Copper.	Copper produced.	Silver produced.	Gold produced.
		Per cent.	*Pounds.*	*Ounces.*	*Ounces.*
Morris-Brook	144,204	1.69	3,320,727	3,287.29	1,505.440
Alpha	22,958	8.62	3,753,662	985.88	59.030
Liberty Pit	175,958	1.36	2,726,963	2,758.19	980.783
	343,120	.....	9,801,252	7,031.36	2,545.253

A small amount of ore was also mined by leasers, the total being 257.5 tons, which yielded 5,646 pounds of copper, 4,947.72 ounces of silver, 11.848 ounces of gold, and 65,309 pounds of lead. * * *

The remodeling of the old Kimberly concentrator, which had been begun in 1916, was completed and the mill put into operation in the early spring of 1917. The first unit gave satisfactory results and it was decided to install a second unit, bringing the capacity up to 1,000 tons per day. As the water supply is obtained from the Alpha mine, it is necessary to conserve its use as far as possible, and to this end three Dorr thickeners to dewater the mill tailings were installed and completed late last year. Considerable delay was experienced in securing delivery of equipment and completing all this work, but at the date of this report both units are in full operation.

Concentrating results for the year at our Kimberly concentrator were as follows: Tons ore milled, 145,466; tons concentrates produced, 11,883; ratio of concentration, 12.2 into 1; grade of ore, 1.69 per cent copper; grade of concentrates, 15.07 per cent copper; and percentage of recovery, 73.0 per cent.

Results of concentrating our ores at the Steptoe works were as follows: Tons ore milled, 174,056; tons concentrates produced, 17,199; ratio of concentration, 10.12 into 1; grade of ore, 1.36 per cent copper; grade of concentrates, 8.21 per cent copper; and percentage of recovery, 59.86 per cent.

Taylor or Ward district.—From two properties there were produced 3,580 tons of ore. The old Ward mine, known in the early days as the Paymaster, was the principal producer, shipping to the smelter oxidized lead ore containing silver. This property is opened by an adit 2,500 feet long. The Argus claim produced a small quantity of silver ore containing copper and lead.

White Pine district.—In 1917 there were produced 1,225 tons of ore, valued at $97,434, or an average value per ton of $79.54, reported by five producers. About half of the ore was milled, and yielded 205 tons of concentrates, containing 11.32 ounces of gold, 6,285 ounces of silver, and 257,631 pounds of lead. The ore of shipping grade (610 tons) contained 13.25 ounces of gold, 13,938 ounces of silver, 3,838 pounds of copper, and 663,458 pounds of lead. The Nevada, Young Treasure, and Jennie A. properties were the principal producers.

Digitized by Google

SECONDARY METALS.

By J. P. Dunlop.

INTRODUCTION.

SCOPE OF REPORT.

"Secondary metals" are those recovered from scrap metal, sweepings, skimmings, and drosses, and are so called to distinguish them from the metals derived directly from ores, which are termed "primary metals." The distinction does not imply that secondary metals are of inferior quality, for metals derived whether from ore or from waste material vary in purity and in adaptability for use in making certain products. The reports to the United States Geological Survey now include the secondary recoveries of copper, zinc, lead, tin, antimony, aluminum, and nickel. The figures obtained by the Survey are given as a supplement to the regular reports on primary metals in order to enable producers and consumers to form a more comprehensive idea of the quantities of metal available for consumption; in fact, they constitute an essential addition to the seven general reports on primary metals, though only a part of the recovery of waste metals is given.

RECOVERY OF WASTE MATERIAL.

NEED OF CONSERVING WASTE MATERIAL.

Never before in the United States has the need for the utilization of waste material been so urgent. Trade journals and daily newspapers are continually hammering into the public mind the economic changes that not only force conservation in the consumption of food, metals, clothing, and other commodities, but that also require the prompt recovery and putting back into trade channels of all material that can be reused. Not only must waste material be utilized but, on account of the ever-increasing scarcity of labor, methods must be adopted which will lessen the labor required to place waste materials where they can be used. Large corporations long ago recognized the great importance of properly segregating every kind of waste, and war conditions causing a rapid advance in the cost of labor, materials, and freight brought many recruits to conservation from the ranks of the smaller manufacturers and merchants. Shop and store methods had to be modified to meet changed conditions. It is the nonbusiness class, the great body of consuming householders who lack the stimulus of any substantial monetary reward but who can give the extra shove that will bring the recovery of waste to the peak. Practically all persons have aided the Government by

Digitized by Google

saving food and have also deprived themselves of comforts or pleasures to buy bonds. To segregate properly and to see that all waste reaches a place where it can be used entails no discomfort and very little expense. Most waste material sells for higher prices than ever before, but the small amount of money that can be obtained for the junk of an ordinary household or farm is not an incentive that appeals to many persons. An incentive that does appeal, however, is the fact that the Nation requires and must have service, and nothing can be substituted for it.

Nearly everyone knows that paper, wool, iron, and tin are scarce; that nonessential industries are daily finding it more difficult to obtain materials; and that even some absolutely essential industries can not obtain all the supplies they require. Natural resources are strained to the limit to provide raw material, and many demands go unsatisfied. The quantity of metal and other scrap from most dwellings, yards, stores, or farms appears insignificant, but "many a mickle makes a muckle," and the accumulation from millions of sources will amount to hundreds of thousands of tons. A small quantity of mixed material in the home or yard is merely dirt, misplaced matter, useless and usually unsightly. Sort and send that same material to a place where it becomes part of large piles and it becomes potential wealth for the community and for the Nation. It is the patriotic duty of every municipality and every individual promptly to market every bit of junk. War demands men and money; it also demands some materials in huge quantities, which will not be forthcoming unless the primary sources of production are supplemented by close recoveries from secondary sources through voluntary personal effort. Plans have been made, which are now being perfected, for the recovery of foil and collapsible tubes made wholly or partly from tin. Through an advertising campaign, through notices on the packages, and by other methods, consumers of articles are urged to save the containers and to send them to the nearest Red Cross center to be sold to dealers and smelters.

BRITISH SYSTEM OF SALVAGE.

The Waste Trade Journal, of August 3, 1918, contains the following remarks of Otto H. Kahn, of Kuhn, Loeb & Co., New York, on the salvage system adopted by the British Army:

> As a business man, I was naturally able to realize best their organization for the business side of war. They have drafted their best business brains everywhere into the service of the Government. Their supply, transportation, manufacturing, and salvage systems, for instance, are marvels of business organization.
>
> Andrew Weir, director general of supplies and, among other things, in charge of the Army salvage system, was good enough to show and explain to me his methods of operation. He told me that in the space of three years he will have saved to the nation through salvage, or, rather, in effect created for the nation, $500,000,000 out of things which formerly went into the scrap heap.
>
> Our Army is engaged in similar work, though it has not yet, of course, attained the magnitude of the British. If we find ways of applying after the war systematically in civil life the lessons now being learned as to the use and value of materials heretofore considered absolute waste, the possibility of the creation of wealth by that means in our country almost staggers the imagination.

Digitized by Google

ARMY RECLAMATION DIVISION.

The United States Army, through the Quartermaster Corps, has established a reclamation division which supervises the collection, sorting, and shipment of all wastes that accumulate at cantonments, and a special training camp is to be established at Jacksonville, Fla., to train officers to supervise this essential work in France, as well as at cantonments and Army depots and warehouses in the United States. Drafted men who have business knowledge of various wastes and who are not deemed capable of active service in the field will be assigned to this service.

ECONOMIES EFFECTED BY THE NAVY DEPARTMENT.

The annual report of the United States Navy Department[1] for the year 1917 shows that it does not lag behind in readjustments to meet business conditions:

140. The manufacture of open-hearth steel by the use of cheap unsalable scrap has been further developed, effecting considerable saving over the ordinary practice of using practically all the heavy and higher priced melting stock.

141. Notwithstanding the recent increases in the market value of pig iron the cost of liquid steel from the open-hearth furnace has remained practically the same on account of the use of cheap steel scrap, which up until this time had to be sold at prices which amounted to a loss of money to the Government.

142. Metallurgical practices brought into effect in the bronze and brass foundry during the fiscal year 1916 have been continued with steady improvements. The immense accumulation of scrap metals which existed two years ago has been very materially reduced, and in many instances it is now necessary to resort to the use of new metals on account of the scarcity of scrap metals.

143. On account of the scarcity of red bronze and composition scrap consistent efforts have been made to increase the use of naval brass and manganese bronze by making a study of the various castings and the substitution of these cheaper grades of materials, for which the present supply of scrap is still more than adequate to meet all of the demands of the foundry for metals, and the use of manganese bronze during the past year has increased from approximately 188,000 pounds to 363,000 pounds per annum, and of naval brass from 320,000 pounds to 637,000 pounds per annum, while the use of red bronze and composition has been decreased from 908,000 pounds per annum to 734,000 pounds per annum.

144. In order to utilize the large accumulation of yellow brass scrap resulting from the manufacture of cartridge cases the manufacture of naval brass forging ingots has been further extended, until at the present time practically all the requirements on the forge shop for bronze torpedo forgings are being met by the use of forging ingots manufactured at the gun factory.

145. The recent heavy demand for small-caliber cartridge cases and the existence of a surplus of lower grade cartridge-case scrap has made possible the development of the manufacture of cartridge-case slabs in the crucible furnaces in the new experimental plant established under the metallurgical and testing division, which has resulted in a considerable saving to the Government. In this operation crop ends and dirty scrap resulting from the manufacture of large-caliber cartridge cases, which were formerly considered unsuitable for further use in cartridge-case manufacture, have been melted in natural-draft crucible furnaces, and after careful treatment to free the material from foreign matter poured into slabs, which have been used with entire success in the manufacture of 1-pounder and 3-pounder cartridge cases, all of which up to the present time passed proof test satisfactorily.

146. Operations of the smelting plant at the gun factory have continued with the same satisfactory results as reported during the previous year. Immense quantities of lower grade scrap materials have been reclaimed in the

[1] U. S. Navy Dept. Ann. Rept., pp. 234–236, 1917.

Digitized by Google

form of usable ingot material for the production of casting and forging ingots, which has resulted in holding the cost of the gun-factory output of nonferrous casting below the regular market price for similar castings made by outside manufacturers, notwithstanding the increased market value of all nonferrous metals.

147. During the past year there has been produced in the smelting plant at the gun factory from scrap metals a total of 1,704,405 pounds of casting ingots, consisting of manganese bronze, 703,852 pounds; naval brass, 468,588 pounds; and phosphor bronze or composition, 531,965 pounds.

148. Based on the average market value of ingot material of similar characteristics compared with the cost of production of the above ingot material at the gun factory, the operation of the smelting plant has, during the past year, saved the Government approximately $308,775. which amount would have been absolutely lost to the Government had this scrap been sold or given to contractors on reworking contracts. With the installation and equipping of the new smelting plant, and the operation of the electric furnace for scrap recovery, it is believed that it will be possible to make still further progress in the reclaiming of scrap materials such as light yellow brass-scrap, manganese bronze turnings, etc., which will effect considerable additional saving to the Government.

149. A large increase in both buildings and machinery to care for the greatly increased output necessary for the war has been recommended, and the plans are underway so that when funds are available the work will proceed rapidly. The great advantage to the Navy of this large plant has been shown in hundreds of ways since the mobilization of the fleet.

SCRAP-IRON DEALERS.

Owing to the enormous demand for iron and steel and the shortage of scrap metal it is becoming difficult to abtain adequate supplies for war needs. Users of iron and steel who do not get priority allocations are eagerly seeking supplies, and every effort is being made to increase the supply of scrap, especially since it has become necessary to prohibit shipments to blast furnaces of certain grades of scrap which can be utilized by rolling mills.

The subcommittee on scrap iron and steel of the American Iron and Steel Institute, through its chairman, W. Vernon Phillips, Pennsylvania building, Philadelphia, has issued the following letter to members of the American Board of Scrap Iron Dealers:

At the request of the director of steel supplies of the War Industries Board, the chairman of this committee is addressing all members of your board, asking them to cooperate with the Government for the purpose of locating and reporting to this office all lots of unprepared scrap which are being withheld from the market, principally in the form of obsolete railways, old mine heads and tipples which are not being operated, unused bridges, or similar structures, old manufacturing plants not in operation, contractor's equipment and similar material which should be shipped to scrap yards for preparation.

Please have not only your office but your correspondents in various parts of the country report with as full particulars as possible, endeavoring in every case to get the name of the owner, court or trustee having charge.

Please report all instances on a sheet of the size and in the form prescribed herewith, in order that we may tabulate them properly. (Sheet is 8½ by 11 inches, ordinary letterhead size.)

We are also inclosing a list of questions which please answer for the guidance of the Government in determining the present shortage or condition of scrap.

1. Location of material_____
2. Estimated tonnage_____
3. Form and character of material_____
4. Name of owners, trustees of such information as you can procure_____
5. Availability of shipment. State whether on railroad or if necessary to use other means of transportation_____
6. Name of nearest railroad_____
7. Distance from nearest scrap yard_____
8. Name of nearest scrap yard_____
9. Other information_____

(Name and address of party reporting.)

Digitized by Google

Other questions asked of dealers, to gain an idea of tonnage available from yards are as follows:

1. How much scrap of all sorts you have on hand at the present time (irrespective of the amount sold, not including any material en route). (Make separate report for each yard.)
2. How much scrap had you on hand June 1, 1917. (Figures should represent as nearly as possible the total tonnage on all grades of iron and steel irrespective of the amount sold and should not include any material en route.)
3. Are you operating your plant to its fullest capacity.

(Name and address of party reporting.)

Throughout the United States, especially in those districts which include many plants working on rush war work, scrap yards and machine shops are being searched for tools, machinery, engines, and boilers which have been scrapped. Much of this discarded material has been reconstructed because it was possible, by replacing worn out parts, to put the articles to serviceable use where it was impossible to obtain new articles for prompt or for near future delivery.

There has been a larger and more extended use of scrap metals by foundries. Sometimes this increased use was due to the high cost of some new metals, but more frequently it was caused by the inability to obtain prompt delivery of new metal. Most foundries have used some scrap; those making small and cheap castings frequently used no new pig metals. In other foundries which specialized in castings made to strict specifications the experimental use of scrap metal had resulted in defective castings because the scrap had not been used to advantage.

It is an essential help to be able to recognize the approximate composition from the shape of a scrap casting, for such knowledge facilitates sorting. There are very few alloys that can not be made to carry some scrap to advantage by a judicious system of proportioning, and many foundries and manufacturing plants driven to experiment by necessity have become successful users of scrap metals.

There has also been a further extension of the facilities for segregating and recovering metal from scrap, drosses, ashes, and skimmings, and more efficient methods are adopted for decreasing melting losses and for the removal of deleterious substances. The use of magnetic separators for the removal of iron from nonferrous scrap, the installation of crushers, jigs, and tables for the recovery of metal from ashes, sand, grindings, and sweepings have become more common. Large users of metals, instead of selling scrap, drosses and other wastes, send the carefully segregated material to smelting plants, where it is refined on toll and returned for reuse. Clippings and light, thin-gage scrap of known analysis is cabbaged before being remelted. Many manufacturing plants accumulate large quantities of light chips, curls, or needles, which have an enormous surface area when compared with an equal weight of the same alloy or metal in ingot form. To avoid the excessive melting losses which occur when such material is remelted in crucibles, it has been necessary to briquet this kind of scrap at the plant or ship it to a smelter or refinery for treatment.

In 1917 a large quantity of light chips, curls, and needles was treated by the Eastern Brass & Ingot Corporation at its plants in Waterbury, Conn., and Chicago, Ill. This corporation does not sell, lease, or install equipment; it treats material by the Duryea process of making solid ingots and charges for the service rendered on a sliding scale, according to the quantity of material shipped to

Digitized by Google

it. It is stated that the cost of the plant, the necessity of expert supervision, and the large quantity of scrap required to maintain continuous operation prevent the Duryea process from being economically used at individual manufacturing plants. At both the Waterbury and Chicago plants each shipment is kept separate. The metal or alloy is thoroughly cleaned and all free iron removed. The cleaned material is then made into ingots ranging from 3 to 3½ inches in diameter and from 1½ to 2 inches in thickness, and weighing from 3 to 5 pounds. These ingots and all waste and dirt, equaling in weight the material received, are returned to the shipper. No heat is used and no binder; the ingots are made by combining enormous pressures with a sharp shock in such a manner as to expel the air before the shock is delivered. The expulsion of the air prevents the ingot being blown apart when charged into a crucible, and the ingot made is so dense that when sawed the even, clean exposed surface indicates that the particles of metal have flowed together. The advantages claimed for the conversion of light waste into briquet ingots include a saving in the labor of handling and in loss of metal, owing to the fact that the briquet ingots are round and so solid that they may be forked, dumped, and handled without appreciable loss by abrasion; a saving in crucibles because their shape and density of the ingots enable a maximum weight charge; a greater output at less cost for fuel and for time required in melting; a better product; and a reduction of about 80 per cent in losses by oxidation.

SOURCES OF INFORMATION.

The Geological Survey frequently receives letters inquiring as to the treatment of drosses and skimmings of alloys suitable for certain products and making other technical inquiries which it is not able to answer, though it endeavors to indicate where such information may be obtained. There are many trade papers and journals which give the source and nature of waste material and the prevailing prices of all kinds of scrap metals. They also contain replies to many questions relating to remelting, refining, and proper methods of alloying.

There never has been a time when it was so necessary for every business man to keep in touch with conditions and regulations which directly or indirectly affect his business. The daily newspapers can not possibly give adequate space to specific data relating to varied industries, nor are they competent to analyze or even correctly state the causes and results of freight embargoes, allocation of supplies, priorities, price fixations, export and import licenses, and other restrictions which are vital to the metal and other trades.

To keep in touch with the daily changes of the business world every manufacturer using metals and every buyer, seller, and broker of metals should receive some or all of the daily trade papers. Many of these papers, such as the American Metal Market, Daily Metal Reporter, and Daily Iron Trade and Metal Market Report, have special representatives at Washington and in other places who promptly report and comment upon all matters that affect metals and products made from metal. In addition to the trade papers issued daily, everyone interested in metals should obtain the more comprehensive and technical information given in weekly or monthly

Digitized by Google

trade journals, such as the Waste Trade Journal, the Metal Industry, the Brass World, Foundry, the Iron Age, and the Iron Trade Review.

The Geological Survey, in common with other Government agencies, has willingly replied to many inquiries for information, which has been widely and promptly disseminated by trade papers and the technical press. An increased circulation of the trade papers and journals will increase the knowledge of the subscribers, and, to some extent, diminish the burden imposed on the technical and statistical force of the Government engaged in the more important and necessary research connected with the war.

WARRING ON WASTE.[1]

By WILLIAM CRAWFORD HIRSCH. [Editor, Waste Trade Journal.]

MAKING THE SCRAP PILE AN ASSET.

One of the reasons the scrap pile is neglected by most factory managers is the misconception caused by applying to it the common term "junk heap." "Junk" to most of them means "worthless." This, however, is far from the truth, as the scrap pile can be made not only an asset, if well managed, but an analysis of what goes into it is also a good indicator of the solidity of the business.

For a telltale whether an industrial establishment is well managed or whether its solidity is being undermined by carelessness, the scrap heap seeks its equal. It is more symptomatic of the health or decline of a manufacturing plant than mercantile agency reports or bank references. To the astute industrial engineer it is what a patient's tongue is to a physician, enabling him to detect the seat and nature of the ailment.

Odds and ends of plates and sheets strewn about the scrap heap of an automobile plant when they might be worked up into washers are usually an infallible sign that something is wrong. No less indicative of a careless attitude is a pell-mell accumulation of iron, steel, and nonferrous metal scrap which, while awaiting a buyer, is permitted to deteriorate in value by exposure.

Perhaps not a little of the indifference in the attitude of many plant officials toward scrap is to be attributed to a misconception of the word, which in their minds has become associated with something that is useless.

There could, however, be no more fallacious notion, for the very latest machinery contains in its vitals iron and steel regenerated from scrap, and the copper in its bearings may in a previous state have done service in a kettle. To scrap is vouchsafed the return to metal as useful as that of virgin origin—provided, of course, proper care is taken of the scrap.

For much in the way of strips, cuttings, and clippings that result from the working up of sheet steel, tinplate and terneplate, copper, brass, lead or zinc sheets, a more profitable outlet can be found than the scrap heap. Considerable of this material can be sold to manufacturers of specialties whose products call for small sizes of sheet metals, such as, for instance, bottle caps. Such remnants are to be considered as scrap only when no market can be found for them otherwise.

The scrap heap should comprise nothing except metal which must be remelted to give it any value. To this injunction may be added the admonition that the scrap heap should exist only as a figure of speech. It should never be a heap, but kept as orderly and tidy as the most valuable of new material.

The dollar and cents value of order and punctilious care in the handling of scrap is illustrated perhaps best by the difference in the market value of borings and turnings properly separated and those sold as a mixture. The maximum price fixed by the War Industries Board of the Council of National Defense for cast-iron borings is $20 a gross ton. The same level was established for machine-shop turnings. In most of the large consuming scrap-iron markets these grades have virtually attained the maximum value permitted under the regulations. When borings and turnings are mixed, they command $3 a gross ton less.

[1] Factory, April, 1918.

Digitized by Google

HOW SCRAP MAY BE INCREASED IN VALUE.

By judicious organization of its scrap conservation system the average industrial plant can add considerable value to its scrap, although the final grading to make the material available for conversion must be done by the scrap dealer, for the simple reason that very few individual plants produce sufficient quantities to make this possible.

Moreover, in the case of assorting any scrap intended for consumption by steel mills, intricate specifications have to be complied with. To observe these, even though the necessary equipment, such as large shears and hydraulic presses, were available, would be unprofitable for the occasional shipper of scrap, as the work of grading calls for highly trained though not skilled labor.

One steel company excludes from its scrap purchases all pieces weighing less than 5 pounds per linear foot, while the weight limit with others ranges from 10 to 300 pounds. Weights are limited by the mechanical means of the individual consumer for handling material. The minimum weight is prescribed so as to prevent the shipping to the steel mill of too light material, which makes for excessive oxidation.

The charging boxes of the various furnaces differ, and some mills will not accept any piece of scrap that deviates in the slightest degree from the straight shape, because crooked pieces do not fit snugly into the charging boxes.

Up to the present, specifications of the various scrap-iron consuming mills vary considerably. Eventually these will be standardized, and the scrap producer will be the gainer by such a procedure fully as much as the consumer.

HOW SCRAP IS CLASSIFIED AND GRADED.

Railroads, whence emanates the largest amount of iron and steel scrap, follow, as a rule, the official specifications of the Railway Storekeepers' Association. The class of iron and steel scrap sold by the railroads differs, however, from that produced in industrial plants, and the specifications of the steel mills and foundries owe their complicated provisions chiefly to the great diversity of material found in industrial scrap.

The most important grade of scrap consumed by steel mills is known as No. 1 heavy melting steel. For this grade the Carnegie Steel Co. exacts compliance with the following qualitative specification:

> Must be one-fourth inch and over in thickness, nothing to exceed 6 feet in length, free from pipe busheling. All scrap from industrial steel. Railroad scrap in charging-box size will be acceptable under these specifications, to be free from cast iron, malleable iron, or any other foreign substance.

Many mills accept wrought scrap as heavy melting steel. Industrial plants, however, are most prolific in the production of cast-iron scrap.

WHAT IS THE BEST GRADE OF CAST-IRON SCRAP.

A model specification for the leading grade of cast-iron scrap, known as No. 1 machinery cast, is that ratified by the American Foundrymen's Association, which reads as follows:

> This material shall consist of cast-iron scrap of first quality which possesses evidence of having been machined, such as planed or turned surfaces, bored or drilled holes, or similar markings. It must be cupola size, no piece to weigh more than 100 pounds, and must not exceed 24 inches in length or width; No. 1 heavy pieces greater than 1 inch in section, No. 1 medium pieces one-half inch and not to exceed 1 inch in section, No. 1 light pieces not to exceed one-half inch in section. Scrap classified as railroad cast scrap, or under any other classification, will not be accepted under this classification.

Cast scrap, such as columns, pipes, plates, and rough castings, comes under the head of rough cast with appropriate subclassifications. A special classification is provided for burnt machinery scrap, which is known as No. 5.

Stove plate forms another important scrap grade used by the foundries. It is commonly understood to consist of broken cast-iron stoves, but must be free from all burnt parts, grates, and from malleable iron and steel parts as well. Broken radiators make up a separate scrap-iron classification.

Malleable cast scrap consists of material that has undergone the annealing process. Malleable cast-iron parts of automobiles form a grade by themselves, while miscellaneous malleable scrap consists of valves, flanges, and pipe fittings of every description.

Digitized by Google

HOW LIGHT METAL SCRAP MAY BE HANDLED.

In addition to the heavy scrap consumed by the open-hearth steel furnaces, the bulk of which comes from the railroads, they use large quantities of light steel scrap which is made up from steel springs, turnings, drillings, and borings from wrought iron and mild steel, tires, and bundled sheet scrap. Bundled sheet scrap consists of new side or end clippings and shearings which are securely bundled with wire to permit their being handled with a magnet without falling to pieces. Many firms have balers which they use for this. The amount of this light material made at a plant in a year will decide whether a baler is a profitable investment. To be handled economically sheet scrap must be baled. It is then possible to load cars to maximum weight and so help in the conservation of cars. For this many firms find it profitable to install their own baler.

Especial care should be taken to prevent rust or corrosion which would make all such scrap undesirable.

Stub ends of carbon tools, carbon-steel saw plates, wearing plates, steel horseshoes, horseshoe nails, steel buckles, steel snaps and clamps, and small soft steel castings come under the classification of crucible steel scrap.

IMPORTANCE OF STORAGE FOR WASTE.

In conclusion, it may be stated that unless proper provisions are made for the systematized collection and storage of all waste material, the best intentions will prove unavailing. For nonferrous metals the best plan in the average factory is to have compartment boxes, properly labeled and conveniently stationed for the various departments.

According to the plant's requirements separate boxes or compartments can be set aside for copper, brass, zinc, lead, and tin. There should also be a box for rubber. Preferably these boxes should have sufficient capacity so that when filled they indicate that enough material has accumulated to warrant disposal in worth-while quantities.

For the heavier scrap there must be ample space set aside in the factory grounds. If very heavy scrap is produced, it will be most advantageous to have the scrap storage space as convenient to a railroad siding as possible. The allotted space should be properly subdivided into sections, each one of which is set aside for a special grade or kind of scrap, according to individual requirements.

HOW THE SCRAP PILE MAY BE TURNED INTO AN ASSET.

Properly managed, the equipment provided for the conservation of scrap and the time and effort expended in its systematic accumulation, supervision, and disposal will prove not only directly profitable but the indirect return which will come from the enhanced care that will be accorded new material is certain to prove of incalculable value. Many plants have found this true soon after they began to dig beneath the surface of their scrap heap. As stated at the beginning of this article, there is perhaps no more reliable index to the state of an industrial enterprise than the manner in which its scrap is handled, stored, and converted to use.

CLASSIFICATION FOR OLD METALS.

The National Association of Waste Material Dealers has succeeded in remedying many trade abuses, and the metal division of the organization has grown until it includes practically every leading dealer in scrap metals and drosses. It has a grievance committee of three members to whom all disputes between members are referred. If this committee is unable to adjust a dispute it recommends arbitration. There have been disputes, but all have been adjusted, usually without an arbitration committee, and so far no member has entered suit against a fellow member. There are several sections forming the association, of which the scrap-metal section is by far the strongest and most efficient.

Digitized by Google

The classification for old metals adopted by the association is receiving more recognition every year from manufacturers, foundrymen, and other users of metals.

The following standard of classification for old metals has been adopted by the National Association of Waste Material Dealers to be effective from July 1, 1918 to July 1, 1919, at which date a new circular will be issued. Dealers or consumers wishing to have these circulars mailed to them as they are issued, should forward their request direct to the secretary, Charles M. Haskins, 185 Summer Street, Boston, Mass.

1. Delivery: (*a*) Delivery of more or less on the specified quantity up to 2½ per cent is permissible.

(*b*) If the term "about" is used, it is understood that 5 per cent more or less of the quantity may be delivered.

(*c*) Should the seller fail to make deliveries as specified in the contract the purchaser has the option of cancelling all of the uncompleted deliveries or holding the seller for whatever damages the purchaser may sustain through failure to deliver and if unable to agree on the amount of damages, the arbitration committee of the National Association of Waste Material Dealers, appointed for this purpose, to determine the amount of such damages.

(*d*) In the event that buyer should claim the goods delivered on a contract are not up to the proper standard, and the seller claims that they are a proper delivery, the dispute shall be referred to the arbitration committee of the National Association of Waste Material Dealers, to be appointed for that purpose.

(*e*) A contract for a carload, unless otherwise agreed upon, shall mean the minimum quantity recognized by the official classification tariff of the district in which the seller is located.

(*f*) A ton shall be understood to be 2,000 pounds, unless otherwise specified.

(*g*) If, through embargo, a delivery can not be made at the time specified, the contract shall remain valid, and shall be completed immediately on the lifting of the embargo, and terms of said contract shall not be changed.

2. Heavy copper: This shall consist of copper not less than ⅛ inch thick, and may include trolley wire, heavy field wire, heavy armature wire, that is not tangled, and also new copper clippings and punchings, untinned and clean, and copper segments that are clean.

3. No. 1 copper wire: To consist of clean untinned copper wire not smaller than No. 16 B. & S. wire gage to be free from burnt copper wire which is brittle and all foreign substances.

4. No. 2 copper wire: To consist of miscellaneous clean copper wire such as of necessity would be taken out of the heavy copper and the No. 1 copper wire, but to be free of hair wire and burnt wire which is brittle.

5. Light copper shall consist of the bottoms of kettles and boilers, bath tub linings, hair wire, burnt copper wire which is brittle, roofing copper, and similar copper, free from radiators, brass, lead and solder connections, readily removable iron, old electrotype shells and free of excessive paint, tar, and scale.

6. Composition or red brass shall consist of red scrap brass, valves, machinery bearings, and other parts of machinery, including miscellaneous castings made of copper, tin, zinc, and/or lead, no piece to measure more than 12 inches over any one part, to be free of aluminum and manganese, also free of railroad boxes, cocks and faucets, gates, pot pieces, ingots, and burned brass.

7. Railroad bearing shall consist of railroad boxes or car journal bearings, must be old standard used scrap, free of yellow boxes, plastic and similar bearings, also iron-packed boxes, and must be free of babbitt; also free of excessive grease and dirt.

8. Cocks and faucets: To be mixed red and yellow, free of gas cocks and beer faucets; shall be at least half red.

9. Heavy yellow brass shall consist of heavy brass castings, rolled brass, rod brass ends, brass screws, and tinned or nickel-plated brass tubing; to be free of iron and dirt and must be in pieces not too large for crucibles; no piece to measure more than 12 inches over any one part. Must also be free of aluminum and manganese mixtures. Condenser tubes shall not be considered as heavy brass.

10. Light brass shall consist of light sheet brass, forks and spoons, miscellaneous brass that is too light for heavy, to be free of any visible iron, radiators, gun shells containing paper, ashes or iron, loaded lamp bases and clock works.

Digitized by Google

11. New brass clippings shall consist of the cuttings of new sheet brass to be absolutely clean and free from any foreign substances.

12. Brass tubing shall consist of brass tubing, free of nickel plating, tinned, soldered, or tubes with cast brass connections. To be sound, clean tubes, free of sediment and condenser tubes.

13. No. 1 composition turnings: To be free of aluminum, manganese, plastic, and yellow brass turnings, not to contain over 2 per cent iron, to be free of grindings or foreign material, especially babbitt, and free from adulterations made to resemble metal. Turnings not according to this specification subject to sample.

14. No. 1 yellow brass turnings shall consist of strictly rod turnings, free of aluminum, manganese, composition, and tobin turnings. Not to contain over 3 per cent of iron, oil, or other moisture, to be free of grindings and babbitts. To avoid dispute, to be sold subject to sample.

15. No. 1 pewter shall consist of tableware and soda fountain boxes, but in any case must test 84 per cent tin. Siphon tops to be treated for separately.

16. Auto radiators: To be classed separately, must be free from iron.

17. Zinc must consist of clean sheet and cast zinc, also cast batteries to be free of loose oxide and dross, salammoniac cans, and other foreign materials.

18. Tin foil shall consist of pure foil, free of lead compositions and other foreign ingredients and matters.

19. Electrotype shells must be hand picked and free of dross.

20. Battery and lead plates shall consist of battery lead plates, free of wood, rubber, and paper.

21. New sheet aluminum clippings shall consist of new sheet aluminum and cuttings. Must be free from oil, grease, and any other foreign substances. Must be guaranteed not less than 98 per cent pure aluminum.

22. Aluminum wire shall consist of aluminum wire guaranteed 98 to 99 per cent pure aluminum, and must be free from corrosion and any other foreign substance.

23. Painted sheet aluminum shall consist of painted sheet aluminum and must be absolutely free from iron, dirt, or any other foreign substance.

24. Aluminum castings shall consist of aluminum castings, free from iron, babbitt, brass, and any other foreign substance. Must not exceed 2 per cent of oil and grease.

25. Old sheet aluminum shall consist of old and manufactured sheet aluminum. Must be free from painted sheet aluminum, iron, dirt, and any other foreign substance.

26. Aluminum borings, to avoid dispute, should be sold subject to sample.

27. Aluminum foil shall consist of pure aluminum foil, free from paper and any foreign ingredients.

28. Babbitt metal shall contain bearing metal of all kinds. Shall not contain scrap hard metal, Allen metal (which is copper and lead alloy) die cast, zinc boxes, or type metal.

29. Packages shall be good strong packages, suitable for shipment, and each package to be plainly marked with the gross and tare weights so that when packages reach their destination, their weights can be easily checked.

When goods are not packed according to the above specifications and the shipper wants his rejections returned, the cost of labor shall be charged to the shipper.

REVIEW OF THE SECONDARY METALS IN INDUSTRY IN 1917.

Dealers in and refiners and smelters of scrap metals continued to do a large business in 1917, though it is doubtful if the business done was as profitable or as large as in 1916. Stocks of some new metals, such as copper, tin, and aluminum, were small and spot shipments were not always available. On the other hand, there were ample supplies of zinc and antimony and prices for these metals decreased. Generally there was an active demand for nearly all scrap metals throughout the year. Profits were less because prices were fixed during the year for certain metals and expenses were greater on account of higher costs of labor. Freight embargoes, re-

Digitized by Google

strictions of various kinds, and changing business conditions hampered the secondary metal trade. The active demand for scrap metals stimulated the collection of scrap metal from all sources, but the increased quantity of waste material was due mainly to the vast extension of industries connected with material for war purposes. The increase was confined mostly to clean new scrap, as the scarcity of labor and supplies and the clearly defined policy of the Government restricting construction of new buildings for nonessential purposes lessened the quantity of old metal derived from the demolition of structures which under ordinary conditions would have been replaced by new buildings and equipment. A smaller quantity of zinc was used for galvanizing, consequently less zinc dross was available for redistillation or remelting, and of this reduced output a considerable part was exported to Europe for treatment.

More scrap metals were sold directly from the producer to foundries, and there were fewer resales between dealers and brokers. One result of the fixed price of aluminum is that considerable quantities of scrap aluminum and aluminum alloy are purchased directly by consumers from the producers at prices which secondary smelters and refiners making ingot can not afford to pay. New pig aluminum is barely sufficient in quantity to satisfy the requirements of priority consumers, so that the stocks available for nonessential industries are negligible. If the consumers are purchasing only heavy scrap, the losses in remelting, though large, are not serious; but if large quantities of clippings, borings, and grindings are used by foundries, there is a very large loss in remelting, which would be avoided if the light scrap went to the large refineries that specialize in the treatment of such wastes.

Part of the metal or metals contained in drosses and skimmings undoubtedly is recovered and reused several times in one year. Similar conditions prevail in the use of all junk or waste material. New clean scrap is sold and becomes mixed with old scrap contained in articles that have been used and discarded. New clean clippings of zinc, tin, and aluminum are usually carefully segregated from other scrap metals, but many dealers in metals, or smelters, do not keep separate records of other new clean scrap and old used metals. The quantity of the various metals contained in numerous alloys made partly or wholly from secondary material can not be definitely ascertained. The figures given as the result of the inquiry made by the Geological Survey are only approximate, but they are the only available data of an important industry.

Provost Marshal General Crowder has ruled that persons employed in scrap iron and steel yards are engaged in a useful occupation, and it is expected that priority rights for fuel, labor, and supplies will be granted to the scrap-metal industry, which is not only essential but is one requiring skilled and experienced labor to treat, sort, and ship its varied products properly.

The value of the secondary metals, exclusive of gold, silver, platinum, iron, steel, and ferroalloys, recovered in the United States increased from $265,377,856 in 1916 to $295,854,900 in 1917. The increase was due partly to larger use of copper and copper alloys and partly to much higher average price of aluminum, tin, and alloys containing tin.

Digitized by Google

The value of the secondary platinum, iridium, and palladium recovered in 1917 amounted to about $6,650,000, and the value of old jewelry, dental waste, silver spoons, ornaments, and other material containing gold or silver, remelted and refined, was probably more than $25,000,000. It is difficult to estimate the value of ferrous scrap remelted in 1917. Estimates of the quantity vary from 12,000,000 to 15,000,000 long tons, and the value from $400,000,000 to $450,000,000. Some of the scrap ferrous metal contained nickel, tungsten, manganese, chromium, vanadium, or other alloys, which made it many times more valuable than the more ordinary commercial products, though the market is limited and some knowledge is necessary to locate prospective purchasers. Old rails, car wheels, pipe, and other iron and steel shapes, were often sold at prices in excess of the original cost. Iron and steel scrap is used by all foundries and rolling mills, and hundreds of thousands of tons of it are collected, sorted, and shipped.

A number of railways having revenues insufficient to cover expenses were sold to dealers in junk. The prices paid for such railways were large, although as operating concerns the railways were worthless to the owners of their stocks and bonds. In some cases attempts were made to abrogate such sales, and injunctions were applied for on the ground that the scrapping of the railways would deprive the territory served by it of all transportation by rail.

One of the anomalies with reference both to scrap copper and to scrap iron and steel was that when maximum prices of virgin primary metal were promulgated the unusual demand would and did to a small extent result in the scrapping of virgin material. The danger was removed by establishing fixed prices for copper, iron, and steel scrap. Scrap-metal dealers and refiners think that though it is proper to insist on rigid specifications requiring the use of the highest-grade virgin metals in making some of the articles required by the Army and the Navy, nevertheless such specifications could be so modified for other requirements as to permit the use of lower-grade material. Such modifications would result in saving considerable money as well as in expediting deliveries.

It is impracticable and unnecessary to segregate the statistics relating to the melting, refining, and using of secondary metals according to States, but more than 90 per cent of the refining and smelting of drosses and scrap metals in the United States is confined to the territory east of St. Louis and north of Ohio River.

Nearly all the secondary aluminum was reported from the States of Ohio, Michigan, Illinois, Wisconsin, and Connecticut.

The largest recoveries from tin dross, tin scruff, and clean tin scrap were made in Pennsylvania, New York, and New Jersey. Nearly all the secondary nickel was reported from Connecticut, the recoveries of lead, zinc, and copper, and of such alloys as babbitt, bronze, brass, and pewter, were more generally distributed.

Digitized by Google

SECONDARY METALS RECOVERED.

Secondary metals recovered in the United States in 1916 and 1917.

	1916		1917	
	Quantity (short tons).	Value.	Quantity (short tons).	Value.
Secondary copper, including that in alloys other than brass	140,000	$68,880,000	159,400	$87,032,400
Remelted brass	300,000	127,440,000	320,000	141,888,000
Secondary lead	56,700	13,289,400	45,100	16,082,000
Recovered lead in alloys	39,600		48,400	
Secondary spelter	50,700	14,284,400	31,400	7,384,800
Recovered zinc in alloys other than brass	2,600		4,800	
Secondary tin	7,600	15,131,040	6,000	23,920,200
Recovered tin in alloys	9,800		13,400	
Secondary antimony	80	2,270,016	3	2,061,700
Recovered antimony in alloys	4,400		4,955	
Secondary aluminum	12,900	23,430,200	6,660	16,711,800
Recovered aluminum in alloys	6,400		9,440	
Secondary nickel[a]	16	652,800	60	774,000
Recovered nickel in alloys[a]	800		800	
		265,377,856		295,854,900

[a] Recoveries made by International Nickel Co. from scrap nickel or alloys and from nickel in scrap ferrous alloys from any source are not included.

SECONDARY COPPER.

The total quantity of secondary copper recovered in 1917, on the assumption that the brass remelted had an average copper content of 70 per cent, was 383,400 short tons, of which 39,558 tons (12,654 tons less than in 1916) was recovered by plants refining primary metals and the remainder by plants treating only secondary materials. The copper produced by smelters of the latter class includes 88,426 tons of pig copper, 31,340 tons of copper in alloys other than brass, and 224,000 tons of copper in remelted brass. These figures indicate an increase for 1917 of about 14,300 tons of pig copper, 14,400 tons of copper in brass, and about 17,300 tons in alloys other than brass. At least 188,500 tons was recovered from clean scrap made in the course of manufacture of copper and brass ware, so that less than 195,000 tons was obtained from ashes, cinders, and scrap, or from material that had actually been used and discarded. From the reports received it is quite evident that there was an increase in the quantity of old scrap brass and copper smelted, and that there was a very large proportionate increase in the quantity of clean new scrap remelted. The reports from munition factories show enormous increase in the quantity of clean scrap remelted, and apparently there was a decrease in the quantity of scrap brass from other users. The quantity of scrap brass used amounted to 320,000 tons, and of this at least 205,000 tons was clean new punchings, filings, and clippings.

The value of the copper, both as metal and in alloys, is computed at the average yearly price of 27.3 cents, the average sales price of all marketable grades of new metal. This average sales price for 1917 includes the price for the latter part of the year, when a fixed price supplanted open market quotations.

According to the Bureau of Foreign and Domestic Commerce the exports for the calendar year 1917 of scrap brass and copper, fit only

Digitized by Google

for remanufacture, were 4,149 tons of scrap brass and 535 tons of scrap copper, and the imports of scrap copper were 8,934 and of scrap brass 28,035 tons. Many railways sell or turn in the larger portion of their brass and copper scrap and other metal waste to dealers in part payment for new material, but the reports received show that the railways utilized in their own shops and foundries more than 18,820 tons of brass, in addition to 950 tons of copper and 1,120 tons of copper in alloys other than brass. The railway reports, however, frequently include alloys termed brass which should more properly be designated as bronze. There was only a very small increase in the quantity of copper alloys used by railways in 1917.

The production of copper from secondary sources in 1917 was equal to about 31 per cent of the refinery output of primary copper in the United States from all sources, or about 41 per cent of the primary copper smelted from domestic ore.

Secondary copper recovered in 1917.

	Tons of 2,000 pounds.
Copper from scrap, drosses, etc	88,442
Copper produced from alloys other than brass	31,400
	119,842
From new scrap	45,000
From old scrap	74,842
	119,842
Brass scrap melted:	
New clean scrap	205,000
Old scrap	115,000
	320,000
Copper content of brass scrap (averaging about 70 per cent copper):	
New scrap	143,500
Old scrap	80,500
	224,000
Total copper produced at secondary plants:	
From new scrap	188,500
From old scrap	155,342
	343,842

The Daily Iron Trade and Metal Market Report, published in June, 1918, a series of articles by Charles Vickers relating to the composition, adaptability, and use of various scrap metals and drosses. Some excerpts from these articles, which are both interesting and useful, are as follows:

Red brass scrap.—Composition or red brass shall consist of red brass scrap, valves, machinery bearings, and other parts of machinery, including miscellaneous castings made of copper, tin, zinc, and (or) lead, no piece to measure more than 12 inches over any one part, to be free of aluminum and manganese, also free of railroad boxes, cocks and faucets, gates, pot pieces, ingots, and burned brass.

In the utilization of secondary metals, red brass scrap is high-grade material, but to use it to the best advantage it should be picked over by some one familiar

Digitized by Google

with the alloys most generally used in castings. Thus the valves should be segregated, as it is pretty certain they contain nothing that would be injurious, such as aluminum. While the composition of the valves may vary to a considerable extent, they can usually be relied upon to produce a good red metal for general castings. They can also be used in place of tin for hardening yellow brass.

In melting valves they should never be taken from the bin and be added to a bath of molten metal, as disastrous explosions have followed this practice. This action results because they may be damp inside. If all the valves it is desired to melt in a heat can not be added with the first charge, and additions must be made, they should be superheated by being placed in a sawed off old crucible, which is placed in the furnace on top of the pot that is melting the heat. When the valves get a dull red they should be removed and thrown on the floor. They can then be added to molten metal without any danger.

Machinery bearings make good scrap. The undesirable material to be looked for is highly leaded metal and phosphor bronze. Metal with a high lead content can generally be identified by fracture, but phosphor bronze will have to be melted, when it can be identified by its great fluidity. Bearings high in tin can be identified by the fracture, which is close grained and whitish. Such castings can be used in place of tin for making red brass, especially if each heat consists in part of new metal and part of red brass scrap. A judicious mixing of the high tin scrap will make unnecessary the use of any metallic tin. Even in normal times it is desirable to economize on tin because of its high cost, and the foundryman who understands his scrap pile has a tremendous advantage over his competitors in this respect and can undersell them every time.

As a general thing all scrap machinery parts of brass contains good metal. It is always advisable, however, to break off corners and examine the fractures. A reddish speckled fracture shows excessive oxidation, and the wise melter takes his precautions against porosity of product by using care in melting and adding a deoxidizer. Miscellaneous castings of red brass are not always what they seem, in these days of aluminum and manganese bronze, as it is difficult to identify these alloys when situated amongst scrap, no matter how desirous the dealer may be of removing them. They can often be identified, however, by means of an emery wheel, by grinding them hard so as to heat the metal. Manganese bronze will show greenish yellow streaks, while aluminum bronze will heat greatly, burr over at the sides, and abrade slowly. Large castings that have to be broken up are easily identified, as when red hot they are tough and can not be broken.

When all the better grade of metal has been removed from the scrap brass, the residue of doubtful composition should be used for the less important castings.

Heavy brass scrap.—The specifications for nonferrous scrap metals adopted by the National Association of Waste Material Dealers, define "heavy copper" as copper not less than one-sixteenth of an inch thick, and may include trolley wire, heavy field wire, heavy armature wire, that is not tangled, and also new copper clippings and punchings, untinned and clean, and copper segments that are clean.

Heavy copper, while requiring a little more careful handling in melting than ingot copper, to avoid undue oxidation, upon receiving this attention is fully equal to ingot for the purpose of making alloys of brass, bronze, and other metals such as babbits containing percentages of copper. It is not suitable for making electrical copper castings where conductivity is a requirement, because there is a possibility of its containing some alloying element such as silicon, phosphorus, tin, or zinc, and for the purposes of electrical conductors, high purity is essential to high conductivity.

It is possible to make high conductivity castings from heavy copper scrap by careful selection, and this is frequently done, but such material when used indiscriminately can not be relied upon for this purpose, but for the purpose of making such alloys as bronze, 88-10-2, and kindred alloys, and for composition 85, three fives, and for yellow brass, heavy copper makes excellent material.

In melting trolley wire in crucibles, the best results are obtained when it is cut into lengths of about 18 inches for melting in a No. 40 to a No. 70 pot. For larger crucibles the wire can be cut to greater lengths, as the crucible is deeper. A good way to gauge the length of the wire for any size crucible is to make it long enough for about one-third to extend above the top of the crucible when the wire is placed upright therein. When melting trolley wire a

Digitized by Google

"deepener" should always be used on the crucible. This consists of the bilge cut from a worn out crucible usually, but they may be purchased new to fit any size crucible. The deepener protects the lengths of wire protruding out of the crucible from the furnace gases and prevents them melting off and falling outside the crucible.

Small blocks of hard wood should be placed in the deepener on top of the wire, to furnish a charcoal covering for the copper as it melts. The gases from the burning wood act as a protection to the heated copper.

Handled in this manner, trolley wire usually can be packed in the crucible so that the entire charge of copper can be contained therein cold. When it is not possible to get in all of the trolley wire at one time, and additions have to be made when part has first melted, it is well to adopt the precaution of warming the residue of the wire to drive off moisture that would otherwise produce little explosions when the cold wire was introduced into the bath of the melted copper. These explosions cause loss of copper as some of the molten charge is ejected. The loss can be kept down by a thick layer of charcoal, and by warming the wire. The latter should not be made so hot that it can not be easily handled by gloved hands, otherwise tongs have to be used, and much time is lost thereby.

After the wire is melted the additions of tin, zinc, and lead are made in the usual manner.

Light brass scrap.—Light brass shall consist of light sheet brass, forks and spoons, miscellaneous brass that is too light to be classified as heavy, to be free of any visible iron, gun shells containing paper, or iron loaded lamp bases, and of clock works.

Light brass consists of almost every article for which sheet brass is used, such as old lamps, bird cages, curtain trimmings, door knobs, musical instruments, gas fixtures, brass tubing, match boxes, belt buckles, pins, and ornamental brass work of every description. Light brass is full of impurities such as iron and steel, solder and nickel. For casting purposes neither nickel nor solder does any harm, as the lead and tin of the solder are usually in such proportion that the one metal imparts stiffness and the other easy machining qualities.

The iron and steel are undesirable impurities, and greatly limit the use of the material from a casting standpoint. The iron exists in the form of studs, nuts, rivets, pins, wire, springs, washers, and brass plated steel articles, the latter being especially difficult to identify when well brass plated, and it would prove too expensive to remove them individually with a magnet, and the pins, rivets, etc., are so firmly embedded that it would be hopeless to attempt their removal. The iron, therefore, has to be melted out, in which process no matter what care is used to keep the temperature of the metal as low as possible, some of the iron will be dissolved, owing to its affinity for the zinc. While some of this iron is chemically combined and does no harm in this condition, a considerable portion, because of its combination with carbon, always separates from the brass as the latter solidifies and exists as nodules scattered throughout the brass. When this material is used for castings, it is not practical to carry out much machine work on them because of the danger of striking one or more of these hard pieces of steel which would inevitably ruin the tools. Light brass, therefore, has to be used for such castings as have little finishing done on them, or that can be finished by grinding. This material is used for cheap car journal brasses, which consist of scrap yellow brass leaded to capacity, but for this purpose as for all other casting purposes it is necessary first to run the brass ingots and then remelt the ingots for the castings. By this practice the brass gets skimmed twice and this favors the removal of the iron. The loss in melting light brass runs from 15 to 22 per cent, due to the iron, the thinness of the metal, and to nonmetallic material concealed in some of the articles. The average composition of the material after being ingoted will be copper, 72 per cent; zinc, 28 per cent; allowing for loss of spelter and not considering solder and iron.

Light brass is a material entirely unfitted for making brass castings that require machining, and especially for castings finished by automatic tools. When light brass is smelted for its copper content, as is sometimes the case, all the iron, zinc, and other impurities are eliminated in the slag, but this method results in the waste of a large percentage of the material. For car journal bearings, light brass is melted in large heats into ingots, and the ingots are remelted with scrap copper bottoms and miscellaneous red scrap, and the resulting metal is treated with all the lead that it has been experi-

Digitized by Google

mentally determined can be held in the metal without dropping to the bottom of the castings.

Yellow brass turnings.—No. 1 yellow brass turnings shall consist of strictly rod turnings, free of aluminum, manganese, composition, and tobin turnings. They shall not contain over 3 per cent of iron, oil, or other moisture, and be free of grindings and babbitts. To avoid dispute, they shall be sold subject to sample.

Brass rods are used in enormous quantities to supply automatic machines with material from which studs, pins, rivets, screws, knobs, and thousands of other small articles can be cheaply fashioned. This results in a large production of brass chips, often the weight of the chips exceeds the weight of the articles made from the rod, consequently yellow brass turnings of this description are a standard commodity of the scrap metal trade. These chips usually are leaded, as the rod from which they are made must machine freely. They will contain from 2 to 2.5 per cent of lead, and it is easy to identify leaded brass chips by their short appearance as they are finely divided, while the unleaded brass turnings will be in the form of spirals and fibrous shavings.

The composition of screw rod chips will be approximately as follows: Copper, 62 per cent; zinc, 35.75 per cent; and lead, 2.25 per cent. Oil is used in cutting brass on the automatic machine and consequently all brass chips are more or less greasy. The amount of oil should not, however, be so great that it runs off and forms pools on the floor where the chips are stored. The oil does not hurt the chips, but as it burns away the percentage of loss is higher in the case of very oily chips. As the chips are bought subject to sample, the condition of oiliness should be taken into consideration.

A considerable amount of screw-rod chips at present made come from plants engaged in munition work, and most generally contain aluminum. This element causes much trouble in foundry operations, and before purchasing chips of unknown origin in large quantity it is always a good idea to purchase a sample of about 500 pounds, which will enable a melt to be made that will be fairly representative of the material. The presence of aluminum is easily detected when the chips are melted, and when its presence is established the proper value of the chips can be determined in a way that will preclude all chance of dispute. As it costs money to eliminate the aluminum, the price should be made accordingly. All chips for foundry purposes should be melted into ingots, and the ingots used for castings. In melting chips from aluminized stock it will be necessary to incorporate an amount of copper oxide that will have to be determined by experiment. The aluminum is thus oxidized out of the turnings and the ingot produced therefrom is clean and can be used in any place where such chips are consumed. Previous to melting, the chips should be put through a magnet machine to remove the iron, otherwise the ingot brass would fail to machine properly because of the presence of hard nodules of steel.

Clean yellow brass chips can always be used to advantage in brass foundry operations. A method in vogue in some foundries is to use chips in every pot of metal melted. A certain amount of chips are placed in the bottom of the pots, probably about one-fifth of the crucible full, and the ingots are put on top of the chips, the latter forming a cushion for the ingots. The chips melt first and wash off the ends of the ingots. The zinc in the chips acts as a deoxidizer, much of it being volatilized and condensing on the surface of the ingots, thus preventing them from being oxidized as they get heated. Where this practice prevails, it has been noticed that little difficulty is ever experienced from porosity of the castings. It is always advisable in connection with the use of chips in this manner that a little salt—about a tablespoonful—be placed on top of the chips before the copper is charged on top. The chips are not weighed with the heat when used in this manner as they are measured out with a scoop which adds a certain amount by weight. The excess zinc in the yellow chips compensates for the loss by volatilization of that in the mixture, and the metal loss is thrown on the chips.

Lamp bases and clock works.—It will be noted that the specifications for light brass state they shall be free of iron-loaded lamp bases and of clock works. It follows, therefore, that these latter have to be removed from the light brass scrap, and as it would be too costly to pound them up and remove the iron they are allowed to accumulate and are sold for what they are. The iron can be removed from the lamp bases quite easily and the brass part thrown into the light brass, but the clock works are a thing separate unto themselves and have to be accorded special treatment.

Digitized by Google

Clock works have two outlets: First, as a raw material for copper smelting; and second, as a source for making yellow brass ingots. In the first outlet all the zinc is lost, which will be seen from the composition of the brass, as it is a considerable percentage of the metal. The average composition of clock brass is copper, 62.50 per cent; zinc, 35.75 per cent, and lead, 1.75 per cent. Clock works at one time were used largely in making car journal bearings of the cheap kind. They were run down at a low temperature in crucibles holding 1,000 pounds, the metal skimmed of iron and then ingoted, and the ingots melted with a percentage of copper in the form of old copper bottoms. A comparatively large amount of lead was added.

Clock works, however, make inferior and irony metal because so many of the little screws and pieces of steel springs melt and enter the brass. The best way to utilize them is to take the loss of zinc and recover the copper only. When clock works are used for the copper content they are assayed to determine their copper value. To accomplish this it is necessary to take a half bushel sample, as nearly representative of the pile of clocks as possible, and by the use of vise, hammer, and cold chisel to remove all the steel parts from the clock works. This must be carefully done and the clock works are weighed both before and after the removal of the iron parts. When clean of iron the brass is melted under borax and ingoted and the ingot analyzed for copper. By multiplying the weight of the ingot in grams by the percentage of copper found by analysis, the content of copper in the ingot is found in grams. If this figure is multiplied by 100 and divided by the weight of the brass before being melted, and after the iron has been removed, a figure is obtained that represents the percentage of copper in the clocks. On this figure, which is the copper value, is based the price of the clocks.

SECONDARY LEAD.

The secondary lead recovered in 1917 amounted to 93,500 short tons, or about 2,800 tons less than in 1916. The secondary lead recovered as pig lead increased about 11,000 tons, and the recovery of secondary pig lead made by those smelters whose product is mainly primary metal was 4,000 tons less in 1917 than it was in 1916. A portion of the recovered lead in alloys was derived from old babbitt, solder, type metal, and white metal drosses. The main sources of secondary pig lead are old pipe, lead cable, battery lead, and lead lining of acid tanks. Regular smelters reported the recovery of 4,363 tons of lead in scrap antimonial lead. It is stated that the manufacturers of toys formerly imported from Europe consume a large quantity of impure and very low-grade lead scrap.

The quantity of scrap antimonial lead remelted by regular smelters was nearly 39 per cent less than that reported in 1916.

The total output of secondary lead was equal to about 16 per cent of the refined primary lead produced in the United States in 1917, compared with 16.8 per cent in 1916. It was exceeded by the primary domestic lead output of only three States—Missouri, Idaho, and Utah—and was more than the combined quantity of primary lead derived from the ores smelted from all other States.

Some of the sources of scrap lead and the methods of remelting and using such scrap are given in the following extracts from articles prepared by Charles Vickers for the Daily Iron Trade and Metal Market Report:

Sources of scrap lead.—Scrap lead usually is found in the form of sheet lead cuttings and old lead pipe from plumbing operations. The latter comprises a varied assortment of water pipe, soil pipe, drain pipe, joints, and traps. Scrap pipe frequently contains much foreign matter and water, which adds to its weight, especially when it is kinked.

Considerable caution is necessary in melting old lead pipe because of the water it may contain. Such material should never be plunged carelessly into a bath of molten metal, as some very disastrous explosions have followed

Digitized by Google

this practice, and trouble may be expected always, unless the pipe can be looked through from end to end to make sure there is no water or water absorbent material contained in it. Even when the pipe is seen to be entirely empty, it is advisable to use a certain amount of caution in adding it to melted metal. The open end of the pipe should never be turned in the direction of any person, when the other end is being introduced into melted metal, because should there be any dampness in the pipe it will cause it to act like a gun, and molten lead will be blown out of the open end.

Scrap lead should be carefully sorted as it is possible that block tin pipe may have become mixed with it. If there are any brass parts, such as ferrules, they should be cut off. The joints are also to be removed, as they consist of wiping solder, the composition of which is two parts lead and one part tin. These joints usually are removed by the scrap metal dealer, as they bring several cents more a pound than the straight pipe.

Clean scrap lead can be used in the foundry, but it is a question whether its use is much of an economy, as the price is little less than that of ingot lead. It is doubtful if there is any advantage in its use in brass castings, as the pig lead is much purer.

Scrap lead is very likely to contain antimony, and while this element is sometimes used in brass in place of tin, it can only be used in certain unimportant alloys and then with great caution. For this reason it is better to use pig lead and take no chances, especially in view of the fact that there is so little difference in price of the two kinds of material.

Antimony finds its way into lead pipe from the scrap material used by many pipe makers, and tin is also found in lead pipe. Neither of these metals harm the pipe, as they stiffen it and make it more resistant to corrosive influences, but when the pipe is used as a source of lead it is better to have it pure.

When melting scrap lead a flux of tallow or resin should be used on top of the metal to disentangle the dross from the metal. A small amount of either of these fluxes is all that is required to clear the surface of the bath. When the molten lead has become thick from dissolved oxides, a stick of green wood should be held in the bottom of the kettle and the lead should be allowed to boil from the wood. This will reduce the oxides and restore the lead to its accustomed state of fluidity.

Tea lead.—Tea lead is obtained from the linings of tea chests, and it is used for this purpose because it is the cheapest metal that could be obtained to inclose the leaves of tea and prevent access of moisture thereto, which would spoil the leaves. Tea lead usually is as pure as any grade of commercial lead. It is made from pig lead.

Tea lead loses considerably on being remelted as it is such thin metal, running from 0.005 inch in thickness, that a large surface is exposed to oxidation. Tea lead also is frequently covered on one side with paper which further increases the loss. It usually is considered that the loss in melting tea lead is from 200 to 300 pounds to the ton, or from 10 to 15 per cent. In the case of paper-covered lead, the loss will sometimes run over 18 per cent. It is advisable in melting tea lead first to have a bath of molten lead by melting pig lead, and then to plunge the sheet lead under the surface of the bath. In this manner it is melted with the minimum amount of oxidation. If the bath of lead be not too hot, the paper on the sheet lead will not be likely to cause an explosion.

Dross.—Lead always is more or less oxidized when it is melted, the extent of the change depending upon just how the temperature of the bath is regulated. A film of oxide forms on the surface of the metal and when disturbed new surfaces are exposed to oxidation. No method of preventing the formation of this dross is known, and as the lead is skimmed the dross accumulates and is finally removed from the kettle and stored for sale to smelters.

The dross is never pure oxide because considerable lead in a metallic state always is entangled therewith. An assay of lead dross generally shows a lead content nearly that of pure lead, as the oxide contains 92.82 per cent metallic lead, and it does not require much metallic lead to be mixed with it to increase this content considerably. Assays of lead dross show varying contents of lead, according to the condition of the dross, whether clean or dirty, finely divided or containing considerable spatters. The lead content varies from 95 per cent lead to 62 per cent lead, the latter dross being quite dirty.

It is possible to get most of the metallic lead out of the dross by putting it through a No. 20 screen. That which passes through the screen is largely oxide of lead, and that remaining in the screen includes spatters and shot or

Digitized by Google

metallic lead. In reclaiming the lead, the oxide can be screened out of the dross, and the screenings added to a kettle half full of lead and just about red hot. The liquid lead melts and absorbs the finely divided lead, and the bath is cooled, and must be allowed to become hot again before a further addition of scrap can be made. A little tallow or rosin melted on the bath greatly facilitates separation of lead and oxide.

SECONDARY ZINC.

The output of secondary zinc (including that in brass) amounted to 116,200 tons and equaled 17 per cent of the production of primary spelter in the United States in 1917, compared with 16 per cent in 1916. The recovery was about 1,200 tons more than in 1916, and all the increase was due to the increased quantity of zinc contained in brass recovered, for the recovery from zinc dross and skimmings was much less in 1917 than in 1916.

Two smelters in New Jersey, two in New York, and one each in California and Pennsylvania, which treat only zinc drosses and skimmings, use large graphite retorts of 600 to 800 pounds capacity instead of the small clay retorts used by smelters treating ore or mixed ore and drosses. The many uses of zinc drosses and skimmings create active competition for their purchase. Considerable zinc is recovered by sweating, and the residues are sold for redistillation. Secondary spelter varies in quality just as the spelter derived from ore does, but a part of the secondary spelter is reported to be of excellent quality.

The production of spelter from drosses and skimmings made by those zinc smelters that do not treat any ore was 5,151 tons less in 1917 than in 1916. This decrease was due in part to the redistillation of the low grades of spelter in order to meet the demand for spelter suitable for brass used in making war munitions, and also in part to the larger quantity of zinc residues used for other purposes. The main reason, however, was that there was a considerable decrease in the quantity of galvanized sheets, pipes, and forms produced, so that less zinc dross was shipped by galvanizing plants and a large quantity of drosses, skimmings, and ashes were exported.

The zinc recovered in alloys other than brass amounted to 4,800 tons, compared with 2,600 tons in 1916. Of the 31,400 tons of secondary zinc recovered as spelter 16,835 tons were obtained by redistillation from drosses and skimmings. Of this quantity 8,519 tons were obtained by smelters whose principal source of zinc is ore. This was about 7,677 tons less than the recovery from drosses and skimmings in 1916. In addition to the 31,400 tons of remelted and redistilled spelter it is estimated that at least 15,000 tons of zinc chloride was made, and likewise about 64,260 tons (marketed production) of the zinc pigment lithopone (containing approximately 22 per cent zinc sulphide and oxide). The zinc used in both of the last-named products is derived largely from zinc drosses and skimmings, of which 19,154 short tons was used in addition to some zinc oxide. The exports of zinc drosses, which amounted to 2,526 tons in 1914, to 3,668 tons in 1915, to 48 tons in 1916, increased to 13,302 tons in 1917.

The urgent demand for scrap steel has resulted in establishing a new industry—that of degalvanizing old zinc-coated scrap so that the steel can be utilized. The zinc coating is removed by the niter cake process and marketed as zinc carbonate or zinc sulphate.

Digitized by Google

Secondary zinc recovered in 1917.

	Short tons.
Zinc recovered by redistillation by regular smelting plants that also treat ores	8,519
Zinc recovered by redistillation by plants that treat only secondary material	8,316
Total redistilled	16,835
Zinc recovered by remelting, sweating, etc	14,565
Total zinc recovered as spelter	31,400
Zinc recovered in alloys other than brass	4,800
Zinc recovered in brass (estimated)	80,000
Total	116,200

The quantity of zinc recovered as spelter decreased from 50,700 tons in 1916 to 31,400 tons in 1917. That obtained by redistillation from drosses, skimmings, etc., decreased from 29,663 tons to 16,835 tons.

The estimated recoveries of zinc in brass increased from 61,700 tons to 80,000 tons in 1917.

SECONDARY ANTIMONY.

The production of secondary antimony, of which all but 6 tons was recovered in alloys, increased from 4,480 short tons in 1916 to 4,961 short tons in 1917. The value assigned is arbitrary and is based on the average yearly price for ordinary brands of antimony published by the American Metal Market. The regular smelters reported the recovery of 370 tons of antimony contained in antimonial lead scrap, a decrease of 158 tons. The principal materials refined or remelted which contained antimony as an alloy were hard lead drosses, babbitt, solder, pewter, and type metal. Antimony used in the rubber, glass, enamel, paint, and ceramic industries and also for war uses does not yield any secondary recoveries. The use of antimony for shrapnel bullets, for primers, for coloring rubber, and for pigments has materially increased in the last two years. The imports in 1917 of antimony as metal in ore or as oxide or salts amounted to 17,924 short tons, and the recovery from secondary sources was equal to 28 per cent of the imports. The production of antimony from antimony and antimonial lead ores of domestic origin in 1917 was about 2,502 tons, or about one-half the quantity recovered from secondary sources.

SECONDARY TIN.

Although the United States consumes more than 50 per cent of the world's production of tin, apparently there were only a few tons of domestic tin ores smelted in the United States in 1917. Part of the tin concentrates produced in Alaska, containing about 90 tons of metallic tin, were shipped to Singapore, Federated Malay States, for treatment and the remainder was sent to New Jersey. The American Smelting & Refining Co. imported and smelted tin concentrates from Bolivia at its plant in New Jersey. Tin concentrates from Bolivia were also smelted in electric furnaces by the Andes Electin Co., of New York. The capacity of the plant on Staten

Digitized by Google

Island is being doubled. Another tin smelter which will also use Bolivian concentrates is under construction on Long Island by the Williams-Harvey Corporation.

The secondary tin recovered in 1917 was equal to about 25 per cent of the tin imported, as metal or as oxide, into the United States during the year (77,866 short tons). Secondary tin recoveries increased from 17,400 tons, valued at $15,131,040, in 1916 to 19,400 tons, valued at $23,920,200, in 1917. The quantity recovered as tin was 6,000 tons and that in alloys and chemical compounds 13,400 tons. The value of the recovered tin here assigned is arbitrary and is based on the yearly average price for new metal, 61.65 cents, given by the American Metal Market. The secondary tin in alloys increased about 3,600 tons and the secondary pig tin decreased about 1,600 tons.

Nearly all clean tin-plate scrap is detinned by one of three processes—the electrolytic alkali, the chlorine, or the alkali saltpeter.[1]

By the first method the tin is recovered in the form of a spongy granulated precipitate, which can be remelted into pig tin; by the second process tetrachloride of tin is recovered for use in silk dyeing and weighting; and by the third process the tin is recovered as an oxide, which is either used as coloring in the enamel industry or is smelted into pig tin by means of a reverberatory furnace.

The recovered tin in alloys includes the tin content of products made in several plants from clean tin-plate scrap and more than 15,500 tons of old tin cans. This included some tin oxide and putty powder but consisted mainly of tin chloride. The production of these compounds is calculated as metal and not separately stated in order to avoid disclosing confidential information. As the products are made from scrap tin and thus conserve the primary metal, they are properly regarded as recovered tin.

The largest recoveries of tin were made from the scruff and drosses that occur in making tin plate and terneplate, and amounted to more than 4,800 tons. The quantity of tinplate and terneplate made in 1917 was about 265,000 tons more than in 1916.

About 3,330 tons of tin were recovered from clean scrap tin plate, either as pig tin or as tin chloride or tin oxide. Apparently only about 700 tons of pig tin were recovered from scrap-tin (not tinplate) clippings, old tin pipe, tin foil, and collapsible tubes, and it is impossible to give the separate quantities of tin recovered from these sources. Old block-tin pipe is most acceptable scrap, but the quantity available is steadily declining.

Only two plants reported using solely old tin containers, from which the tin coating and solder were first sweated and the black plate was then remelted to make sash weights. One of the makers of sash weights from old cans has stopped using such material on account of the increased cost of labor and fuel. Tin scrap and old tin cans are used in the western mining regions for their iron content for the precipitation of copper from mine waters.

Tin-plate scrap and old cans can not be profitably shipped from western points to reclaiming plants located in Illinois or New Jersey, and the high cost of fuel and labor prevent them being treated locally.

[1] A short history of the detinning industry: Met. and Chem. Eng., August, 1917, pp. 187–189.

Digitized by Google

The scarcity of scrap iron now, however, should result in a larger demand for old cans by mine operators.

An increased quantity of tin was recovered in bronze, and a considerable part of the brass remelted contains a small quantity of tin and of lead. Other alloys from which secondary tin was recovered were solder, babbitt, pewter, terne metal, and electrotype metal.

From reports received by the Geological Survey there were approximately 173,000 long tons of clean tin-plate scrap detinned in 1917. This scrap yielded 10,608,042 pounds of tin oxide, tin bichloride, and tin tetrachloride containing 4,485,745 pounds of tin, also 2,180,144 pounds of tin as metal. There were about 15,000 long tons of old tin-coated containers used, from which tin chloride containing 453,700 pounds of tin was recovered. The average metallic content of the tin oxide was given as 78.6 per cent, that of the tin bichloride as 23 per cent, and that of the tin tetrachloride as 45.4 to 46 per cent.

The average recovery of tin from old tin-coated containers was 27 to 32 pounds a long ton. The insignificant quantity of tin recovered from scrap tin plate and terneplate is shown by the fact that it is estimated that 27,600 long tons of tin were used in 1917 to coat sheets and other forms and that the total recovery of tin from tin-plate scrap and from old containers was about 3,147 tons, of which only about 400 tons was obtained from old containers.

A small quantity of old cans was used by makers of window sash weights, but nearly all the old cans utilized in 1917 were treated by the dry chlorine process at plants in New Jersey owned by the Metal & Thermit Co. and the Vulcan Detinning Co. Most of the cans were received from Washington, Philadelphia, New York, Newark, Pittsburgh, Buffalo, and Rochester, mainly from contractors gathering garbage and waste which was handled by means of picking belts. The cans purchased were classified as follows:

Class 1. Unused empty and unrusted tin cans not exceeding the 1-gallon size, with or without labels attached, but otherwise free from foreign material such as ice, water, ashes, paint, varnish, white lead, and similar insoluble (in water) contents.

Class 2. Used cans not exceeding the 1-gallon size and otherwise as described in class 1.

Class 3. Used empty and unrusted tin cans exceeding in size the 1-gallon size but not exceeding the 5-gallon size and otherwise as described in class 1.

Each class should be packed separately and shipped in quantities weighing not less than 5,000 pounds net, In order to facilitate handling and save space it is advisable to crush or bale the cans. Care must be taken that the cans are not flattened entirely. A spacing of one-half to three-quarters of an inch should be left between the sides of the cans so that they can be cleaned and treated. During the first half of 1918 the quoted prices for old tin cans were $11 to $12 a long ton (2,240 pounds) delivered at Sewaren, N. J., or Chrome, N. J.

The high prices now prevailing and the acute scarcity in the United States of pig tin and scrap steel have resulted in many inquiries as to whether old tin-coated containers could be profitably treated. Several municipalities were considering the installation of plants designed to treat all the waste material collected, including

Digitized by Google

old tin cans. Considered from a local point of view such a plant is very desirable, and the recovery of tin is most essential and of national importance. It is hoped that investigation now being conducted will determine whether a detinning plant can be profitably operated by a municipality. If the combustible part of the city refuse were used for power to operate a garbage plant the tin recovered by heat treatment of the cans would be small in quantity and of inferior quality and the burnt sheet steel would be most undesirable scrap and difficult to dispose of on account of the tin and solder attached to it. The cans if bright and clean could be cut and flattened and possibly could be sold for making toys and other small light articles.

The tin from old cans is best treated by dry chlorine gas, which practically removes all the tin and solder and leaves the sheet steel clean and desirable material for remelting except for its light weight and surface area. A plant using the chlorine process, which is patented, would be expensive and would require a large supply of cans to insure continuous operation. In addition to high costs of labor and material and the difficulty in obtaining machinery and equipment there might be difficulty in obtaining an ample and steady supply of chlorine.

The companies now operating detinning plants have stated their willingness to increase the capacity of their plants. This has not been necessary, for they have not been receiving as large shipments of old cans as they are capable of treating. Several of the shippers in 1917 have found that with increased cost of labor, cartage, and freight it is unprofitable to ship cans from Washington and other cities. At present the detinning plants can handle 800 long tons a month more than the quantity received.

The best method of increasing the recoveries of tin from old cans would be by a more systematic collection of cans that have been properly segregated by the householder. If clean, rustless old cans were collected and dumped directly into cars they could be profitably shipped. With a gross price of $12 and a net price of $6 or less a ton it is obvious that 7,000 or 8,000 cans can not be handled more than once when they are sold for about one-tenth of a cent a can.

It was stated in the report on secondary metals for 1916 that it was improbable that there would be any appreciable quantity of tin recovered from old cans treated in Great Britain. Apparently there is no necessity of modifying the statement, as the Daily Metal Reporter of August 17, 1918, quotes a report made by Borough Engineer P. H. Palmer to the Hastings Corporation (English) that he had for many years saved old tins collected with refuse from households; that up to the time of the war it had always been possible to dispose of old tins, but thereafter there had not been any sales. On the other hand, it has been announced by the British National Salvage Council that there was at least one firm which would purchase old cans provided they were clean, free from rust, and were supplied in quantities.

The British Director General of National Salvage, David Currie, has delivered a very interesting lecture[1] on the reclamation of tin from old containers and tin-plate scrap. He stated that one of the reasons why old cans seem so important to the public eye is that they

[1] The American Metal Market, June 13, 1918.

Digitized by Google

are very bulky and often gaudy objects compared with the actual amount of material fabricated and that the lack of enterprise in treating old cans was caused by the difficulty of collection and transportation. The following outline of the various methods of recovering tin from tin-plate scrap and old cans was given:

The broad principles underlying the patents taken out from 1871 to 1918 for recovering the tin and steel were as under:

(*a*) The recovery of tin as chloride by dissolving the tin from the steel in acids.

(*b*) By dissolving the tin from the steel in caustic soda or potash as a stannate solution.

(*c*) By the action of chlorine on the scrap to combine with the tin to form anhydrous tin tetrachloride.

(*d*) Recovery by dissolving tin in an aqueous solution of tin tetrachloride to form stannous chloride, which in turn is electrolyzed, the tin recovered setting free chlorine, which recombines to produce tin tetrachloride for further use.

(*e*) The recovery of tin from tin tetrachloride electrolytically.

(*f*) Recovery of tin from stannate solutions electrolytically.

There will probably be no appreciable increase in the quantity of tin recovered by detinning old cans in 1918. Owing to the active canvass inaugurated by the Red Cross and other organizations the quantity of tin recovered from tin foil and collapsible tubes should be greater in 1918 than in 1917. If everyone could be induced to save foil and tubes the total quantity of tin saved from such sources would aggregate several thousand tons. However, it is more probable that the quantity will not exceed 1,000 to 1,500 tons, though between 7,000 and 8,000 tons of tin were used in the manufacture of foil and tubes in 1917. Thousands of solid silver and gold or silver plated articles have also been collected, and most of the base metal in the plated ware contained considerable tin.

Owing to the scarcity of pig tin and the difficulty of obtaining small quantities for uses other than those classed as strictly essential, there has been a very active demand for tin scrap and for alloys containing tin, especially tin pipe and No. 1 pewter. The available supply of block-tin pipe, which never was plentiful, has practically been exhausted. Scrap No. 1 pewter is a good substitute for use by brass foundries in place of pig tin, as it should contain not less than 84 per cent tin. The conservation campaign of the Red Cross should not only cover tin foil and collapsible tubes but should include old table ware and plated articles of every kind, for in the aggregate the quantity of tin recovered would be nearly as large from pewter as from foil and tubes. A large part of the silver-plated articles collected would consist of No. 2 pewter, which is not suitable for brass-foundry alloys or for solder but which could be used in place of pig tin in making electrotype metal.

ECONOMIES IN USE OF TIN.

It has been realized that, although the quantity of tin recovered from scrap metals and drosses could be increased, such increased recovery would be proportionately small as compared with the increased consumption. It has therefore been necessary to restrict the use of tin in order that there would be an ample supply for war material and for tin plate used to make food containers. Many of the former uses have been modified or eliminated altogether, and at-

Digitized by Google

tention has been drawn to wastes caused by ignorance, carelessness, or indifference. Other materials have been substituted for tin foil and collapsible tubes, and the tin content of the foil and tubes made has been reduced. The consumption of tin plate has materially increased (estimated production for 1918 is 35,000,000 base boxes), but the increase has been due solely to the larger quantity used for food containers. The use of tin plate for roofing, for stove boards, and for fire doors has been almost eliminated. It is stated also that a large saving in tin plate has been effected by agreement with manufacturers of tobacco to use plain black or annealed or galvanized sheets instead of tin plate.

STATEMENT OF THE WAR INDUSTRIES BOARD.

The War Industries Board, at Washington, D. C., has assiduously striven to find substitutes for tin and to effect economies in the composition and use of solder, babbitt, bronze, and other bearing metals, and the tin section of the board has issued the following statement:

EXPERIMENTS TO FIND ECONOMIES.

On account of the limited supply of tin available in the world to-day and because of the hazard involved in connection with our overseas imports upon which we depend for our requirements, and, furthermore, because our war program calls for a very large tonnage of tin, it is imperative that we take immediate steps to husband our resources: First, by eliminating all waste; second, by substituting other metals wherever practicable; third, by reducing the percentage of tin used in various alloys just as far as possible; and finally, by recovering larger quantities.

The War Industries Board has conferred recently with representative manufacturers of babbitt and other bearing metals, solder, and miscellaneous tin-alloy products for the purpose of explaining the present situation, and in order to obtain suggestions as to the most practicable methods for conserving tin. In cooperation with the Bureau of Standards, a number of experiments have been conducted. * * *

The accompanying statement reports some of the findings of the Bureau of Standards resulting from their experiments and from inquiries made among a number of large manufacturers and consumers. We realize that these suggestions cover only a few means of reducing our consumption of tin. The War Industries Board will gladly welcome others, particularly as it is expected that each recipient will be influenced in his approach to the problem by consideration of the special needs of his own line of products and manufacturing equipment. It is hoped that the very wisest possible use will be permitted of any original finding that may result from a careful study of the problem.

The suggestions for conservation of tin above referred to are as follows:

BABBITT AND OTHER BEARING METALS.

Many specifications for bearing metals now in existence call for virgin tin (Banca or Straits). A large saving of these high grades of tin could be brought about by allowing the use of second-quality pig tin in making tin-base babbitt. Detrimental impurities could still be limited, but lead could be allowed to a maximum of 1 per cent. This would not be harmful in any way to a tin-base or lead-base lining metal.

There is no question but that the tin content can be reduced somewhat in all bearing alloys. In a few cases, such as for airplanes, crankshaft bearings, etc., it may not be feasible to reduce the tin content by any but a small percentage, whereas in other cases it can be cut down very considerably. In the present emergency every possible saving, however small, should be effected.

Digitized by Google

For those cases where genuine babbitt is now used and which require a very high grade of lining, alloys such as the following are suggested:

	No. 1.	No. 2.	No. 3.	No. 4.
	Per cent.	*Per cent.*	*Per cent.*	*Per cent.*
Tin	85	84	65	62
Antimony	10	8	.....	.....
Copper	5	8	3 to 6	4
Zinc	.....	.....	28 to 30	33
Aluminum	.....	.....	.....	1

One large bearing-metal manufacturing concern states that the tin should be reduced in favor of lead. Lead-base linings can be used in many cases where tin-base linings are now used, and in general are just as satisfactory. Many manufacturers already use the lead-base metals, but their use could be made more universal. Several special types of lead-base linings, hardened with alkali or alkali earth, are reported to be giving very satisfactory service in place of high-tin babbitt.

One firm states that it is using the following composition instead of Nos. 2 and 3 above in order to conserve tin:

Substitute 2:	Per cent.	Substitute 3:	Per cent.
Tin	8	Tin	5
Antimony	8	Antimony	7
Copper	4	Copper	2
Lead	80	Lead	10
		Zinc	76

These have apparently been found to do the service required of the tin-base linings in machine-tool work.

Another large manufacturer of machine tools does not use lined bearings at all, believing that bronze alone is sufficient. There is probably no question, however, but what the lined bearing is cheaper because of the less amount of machining necessary in making the bearing. It is also claimed that the cost of replacement of a lined bearing is less than that of a bronze bearing and has to be made less frequently. One way in which a lining metal can be saved is to use just as thin a lining as it is possible to have in order to maintain a high enough temperature during pouring to insure a firm bond and solid mass of metal.

In place of a bronze used for bearings containing 80 per cent copper, 10 per cent tin, and 10 per cent lead, the following might be substituted as having been thoroughly tried and found satisfactory:

	No. 5.	No. 6.	No. 7.	No. 8.	No. 9.	No. 10
	Per cent.	*Per cent.*	*Per cent.*	*Per cent.*	*Per cent.*	*Per cent.*
Copper	81	79	74	74	(a)	(a)
Tin	7	5	5	5	8	5
Lead	9	15	20	25	15	17½
Zinc	3	.....	.....	.....	1½ to 3	5
Antimony	.....	.....	.....	5	.....	.....
Phosphor copper	1	1	1	1	.....	.....

a Remainder.

With the cooperation of all in consideration of the above suggestions, it seems probable that much less tin could be used in bearing metals without in any way impairing their service. It is believed that a saving of at least 25 per cent could be brought about by a judicial selection of the proper composition of either bronze or lining to use for each particular service and insisting upon its use.

SOLDER.

There is apparently very little excuse for using a 50—50 solder or high-tin solder for any purpose whatever except in the matter of appearance of

Digitized by Google

the finished article, and in the present emergency this is of secondary importance.

For hand soldering with an iron 45—55 will answer for all purposes, but for most purposes 40—60 will be satisfactory. Wiping solder used by plumbers should not contain over 37½ per cent tin, whereas many are now using 40—60.

Can manufacturers and canners by adopting proper machinery can use 37½—62½ solder with satisfactory results. Very little solder of a higher tin content need be used in these industries.

Manufacturers of radiators need not use solder above 40—60 and in a majority of cases 35—65 will be found entirely satisfactory, and often lower tin content can be used, providing the solder is kept free from antimony. The use of pure tin in radiator construction appears extravagant. If this is used merely for tinning purposes, preparatory to soldering, the eutectic of tin and lead—63 per cent tin and 37 per cent lead—will be found to serve the purpose just as well. This should, in fact, be used generally where it is necessary to tin an article before soldering.

(In all of the foregoing paragraphs on solder the figure first mentioned refers to tin. For example, 40—60 means 40 per cent tin, 60 per cent lead.)

The possibility of using cadmium as a substitute for tin in solder appears promising. Laboratory and manufacturing tests, made by the bureau and by some of the large users of solders, have given good results. Among others the composition containing 80 per cent lead, 10 per cent cadmium, and 10 per cent tin has shown particular promise. The board will be glad to report more fully on this phase of the subject as soon as further commercial tests of cadmium solders have been made. No difficulty is anticipated in connection with the production of cadmium on a commercial basis at a price considerably less than tin as soon as it has been demonstrated that its use for this purpose can be generally extended.

RECOVERY FROM SKIMMINGS.

Probably most large consumers of both solder and babbitt metals save their skimmings and residue. In the present emergency, small consumers as well as large should make a special endeavor to see that all metal in this form is recovered. It is believed that the aggregate that is lost through these skimmings not being saved is considerable and that with a full appreciation of the importance of saving such metal the gain will be appreciable.

TIN ALLOY CASTINGS.

It is believed that the percentage of tin in most alloy castings is unnecessarily high. It has furthermore been found that aluminum, bronze, steel, brass, or other materials can often be substituted in the manufacture of tin-alloy castings. Wherever possible the percentage of tin in the alloy should be reduced or another metal substituted.

It has been stated that it is a common but questionable practice in brass foundries to look upon tin as the cure for most troubles encountered in the production of brass and bronze castings. In view of the present situation brass and bronze foundries are requested to curtail the consumption of tin wherever possible and to restrict its use to the proved essential needs.

The leading manufacturers of white metals have organized the War Service Association of the Manufacturers of Solder and Babbitt Metal, and the plans of the association include active cooperation with the Government in fixing standard formulas with tin content as low as feasible during the period of the war.

SECONDARY ALUMINUM.

The recovery of secondary aluminum as pig aluminum or in alloys in 1917 amounted to 16,100 tons, valued at $16,711,800, as compared with 19,300 tons, valued at $23,430,200, in 1916. The quantity recovered in alloys amounted to 9,440 tons.

Digitized by Google

Various products are made by smelters and refiners from scrap aluminum. One sample of pig aluminum, which was made from clean sheet-aluminum clippings, shows the following analysis:

Analysis of secondary aluminum.

Aluminum	98.75
Copper	.16
Silica	.11
Iron	.56
Manganese	.42
	100.00

The standard No. 12 alloy is the best known and most widely used of aluminum casting alloys. It contains a minimum of 92 per cent aluminum and from 7 to 8 per cent copper. Another alloy made by a large secondary aluminum smelter contains 4 per cent zinc, 8 per cent copper, and the remainder aluminum. Some of the reasons for defective aluminum castings are given by L. M. Brile.[1]

Aluminum chips from castings used in the manufacture of automobiles have become a large source of secondary aluminum. By the old methods of treatment the loss in remelting such chips was sometimes as much as 40 per cent. A publication issued by the United States Bureau of Mines[2] gives an account of experiments which resulted in reducing such losses to as little as 10 per cent.

On account of the difficulty in obtaining virgin pig aluminum for nonmilitary uses a considerable quantity of scrap aluminum is now purchased directly by foundries instead of being purchased and refined by secondary smelters. For this reason it is deemed advisable to reproduce the following article, written by Charles Vickers and published in the Daily Iron Trade and Metal Market Report of August 12, 1918:

Scrap aluminum.—New sheet aluminum clippings must consist of new sheet aluminum and cuttings, must be free from oil, grease, and any other foreign substances, and must be guaranteed not less than 98 per cent pure aluminum.

When sheet aluminum is compressed into briquettes little difficulty is experienced in using it for making aluminum castings, but it is difficult material to melt when loose, as the crucible contains only a small amount at each charge. A great deal of attention, therefore, is required, and considerable metal always is spilled into the furnace. Hence sheet clippings should always be shaped into massive forms. It is fairly good material for making castings when it has a purity of 98 per cent, but it is similar to aluminum wire in that respect, as the specifications for this material require a purity from 98 to 99 per cent also. Aluminum wire is not difficult to charge for melting provided that when cut into suitable lengths it is not permitted to untwist if be in the form of cable. Wire of single strand has to be coiled or compressed into bundles; otherwise it is a most tedious operation to melt it into ingots or castings.

The cost of melting aluminum clippings or wire will depend upon their physical condition. In the case of loose wire in short lengths, produced by the untwisting of cut aluminum cable, the melting cost in a careful test of 500 pounds of wire amounted to $2.62 per 100 pounds, and this was when labor was much cheaper than now. Included in this cost were labor, crucibles, fuel, and loss, but the labor cost was more than all the other costs combined. The loss was 7 per cent. It will be realized that if finely divided aluminum is to be melted economically, some method of forming it into packages of massive size is essential.

The metal, either wire or clippings, forms a good basic metal for ordinary castings and can be alloyed the same as the ingot metal. But owing to the

[1] Metal Industry, February, 1916, pp. 86–87.
[2] Gillett, H. W., and James, G. M., Melting aluminum chips: Bur. Mines Bull. 108, 1916.

Digitized by Google

presence of a considerable amount of impurities, trouble from excessive shrinkage of the alloys is likely to arise more often than would be the case if pure aluminum were used. Unless the material be in good shape for charging into the pots, its cost when melted would be near that of pure aluminum ingot, and this must be taken into consideration when deciding upon the particular kind of raw material to use for the work in view.

The temperature of the aluminum should be kept at about a red heat, and after the crucible is as full as desired, a flux of zinc chloride should be used to disentangle the oxide from the metal.

The scrap metal specifications insist that aluminum castings shall be free from iron, babbitt, brass, and any other foreign substance and must not exceed 2 per cent of oil and and grease.

Aluminum alloys may be divided into two groups, those that contain zinc and those that do not. The first group may contain any amount of zinc from 1 or 2 per cent up to 30 per cent, with or without copper. The second group consists of alloys of copper and aluminum, with rarely more than 8 per cent copper, this latter alloy being known as No. 12 aluminum. Since both these groups are used indiscriminately for making aluminum castings, it is obvious that an assortment of scrap will contain alloys both with and without zinc content. The result is that when melted it is impossible to keep the composition at all regular. Consequently, this chance must be taken when using this type of scrap metal.

Aluminum zinc alloys are not considered suitable for certain classes of aluminum castings, although in general they are stronger than the alloys of aluminum with copper. The aluminum zinc alloys shrink and check more than the aluminum copper alloys; and the higher the content of zinc in the alloy, the more the tendency to shrink, until with over 30 per cent of zinc a peculiar shrinkage trouble is likely to manifest itself on the lower parts of castings of heavy section. The result is that zinc is considered most undesirable in scrap aluminum, and if some easy and inexpensive method could be devised whereby the zinc could be eliminated from aluminum scrap it would be a boon to the scrap metal trade. The best that can be done at present is to alloy the aluminum with zinc-free metals to bring the zinc content down to a point where, while undesirable, it is not harmful for most purposes.

For special purposes, scrap aluminum castings are undesirable, but examples of castings where this material can be used to good advantage are numerous, as it is considerably cheaper than new aluminum or scrap rolled material. In the case of unimportant castings of such section as are easy to cast, scrap aluminum is a desirable and economical material to use, and it can be run directly into castings after it is melted down. In some cases, additional zinc can be added further to cheapen the alloy. This is not difficult provided the scrap comprises castings of similar sort, like gear casings, instead of being a heterogeneous mixture. In such a case the scrap will be of similar composition; and if a trial heat be made with zinc addition, there will be little difficulty in deciding the amount of zinc to be added to cheapen the mixture.

Scrap aluminum castings are easy to melt and recast, as the metal is broken with ease and easily charged into the crucibles. The only thing to be careful of is to keep the temperature below a cherry red between the intervals of charging new metal. When the crucible is as full as desired, a small piece of zinc chloride should be added and stirred into the metal to clear the surface. When the alloy contains much zinc, a little sal ammoniac has been found to do good, as this is the best flux to use in the case of zinc. For zinc aluminum, chloride of zinc is the best flux.

SECONDARY NICKEL.

An effort was made for the first time in 1916 to ascertain the quantity of secondary nickel as nickel or in alloys. The reports received in 1917 showed that 860 tons of nickel were recovered in that year, a considerable part of which was from clean new scrap. This does not include any nickel in scrap ferrous alloys nor the recoveries from secondary sources made by the International Nickel Co. The scrap remelted by the International Nickel Co. is included with matte and ore, and no separate recovery is attempted. The quantity

Digitized by Google

of nickel in matte and in ore imported into the United States in 1917 was 75,510,793 pounds, most of which was from the Sudbury district, in Ontario. No direct production of nickel from American nickel ores is known to have been made in the United States in recent years, but an equivalent of about 402 short tons of nickel was saved in 1917 as a by-product in the electrolytic refining of copper.

The Missouri Cobalt Co., of Fredericktown, Mo., mined ore in 1917 which contained copper, nickel, and cobalt. A new refinery has been built at which the residues returned from the ore shipped to sulphuric acid plants will be treated for the nickel, cobalt, and copper content.

As the greatest use for nickel is as an alloy in steel, and the secondary recoveries of nickel reported to the Survey in 1917 were solely from nonferrous scrap, it is evident that the 860 tons of nickel reported form a small portion only of the nickel in alloys recovered and reused. The secondary nickel reported in 1917 was nearly all recovered from old nickel anodes, German silver, and Monel metal. Analyses of various nickel alloys have been published by the United States Geological Survey.[1]

[1] Hess, F. L., Nickel: U. S. Geol. Survey Mineral Resources, 1915, pt. 1, pp. 763–765, 1917.

Digitized by Google

GOLD, SILVER, COPPER, LEAD, AND ZINC IN MONTANA.[1]

(MINES REPORT.)

By V. C. HEIKES.

PRODUCTION.

GENERAL STATEMENT.

Mines in Montana produced during the calendar year 1917 gold, silver, copper, lead, and recoverable zinc valued at $110,149,382. There were 617 producers. In 1916 there were 513 producers, and the output was valued at $133,882,947. The decrease of $23,733,565, or more than 17 per cent, in value in 1917 was due to the decreased output of copper, silver, gold, and zinc. Silver Bow County, which includes the Butte or Summit Valley district, produced more than 19 per cent of the gold, nearly 88 per cent of the silver, 98.5 per cent of the copper, more than 47 per cent of the lead, nearly 97 per cent of the zinc, and more than 93 per cent of the total value of the output from deep mines.

Mine production of gold, silver, copper, lead, and zinc in Montana in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead.	Recoverable zinc content.	Total value.
		Short tons.		*Fine oz.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	513	7,860,425	$4,550,494	16,494,366	352,928,373	13,595,136	229,259,075	$133,882,947
1917	617	6,307,164	3,517,253	13,128,142	274,462,574	21,951,220	186,259,331	110,149,382
Increase or decrease, 1917	+104	−1,553,261	−1,033,241	−3,366,224	−78,465,799	+8,356,084	−42,999,744	−23,733,565

[a] Includes placer production.

ORE.

The tctal quantity of ore sold or treated was 6,307,164 tons, and the total average value per ton increased from $16.94 in 1916 to $17.39 in 1917. The average value per ton of the gold and silver contained in this ore increased from $1.87 to $2.20. Mines in Silver Bow County are credited with the largest output of ore (5,681,058

[1] The statistical tables in this report were compiled by Bessie N. Patchell, of the United States Geological Survey.

Digitized by Google

tons), of which 4,775,213 tons, or more than 84 per cent, was copper ore; 633,901 tons, lead-zinc ore; 13,483 tons, dry or siliceous ore; and 258,461 tons, zinc ore.

The total output of dry or siliceous ore in the State was 444,222 tons, of which 411,118 tons were classified as gold ore, 7 tons as gold and silver ore, and 33,097 tons as silver ore. The largest part, or 318,823 tons, of dry or siliceous ore, together with 9,862 tons of old tailings, was treated by cyanidation, and 8,925 tons were treated by amalgamation. There were 503,023 tons shipped directly to the smelters for treatment, and 5,086,706 tons were treated at concentration mills. Phillips, Lewis and Clark, and Fergus counties, with 223,350 tons, 69,848 tons, and 38,133 tons of ore, respectively, were the largest producers of strictly siliceous ores. To Deer Lodge County there was credited 52,133 tons of dry or siliceous ore, of which 52,005 tons were oxidized iron ore. This ore, which contained more than 20 per cent excess iron and a little gold and was valuable as a flux at the smelter, was mined in the Georgetown district of Deer Lodge County, and a similar ore, of lower grade, containing gold, silver, and a little copper, was mined near Elkhorn, in Jefferson County. Iron sulphide ore aggregating 3,471 tons, containing nearly an ounce of gold per ton and a little silver and copper, continued to be mined in Broadwater County, near Radersburg.

The output of copper ore was 4,844,537 tons, of which 4,136,130 tons were of milling grade and produced 1,492,104 tons of concentrate averaging 32 cents in gold and 4.87 ounces of silver per ton and 7.14 per cent of copper and having an average value per ton of $43.33. From 3,344 tons of copper-lead ore there were 1,545 tons milled and 515 tons of copper-lead concentrate produced, which averaged $6.12 in gold and 24.88 ounces of silver per ton, 3.92 per cent of copper, and 15.18 per cent of lead and had an average value per ton of $74.15. One property in the Boulder district, Jefferson County, yielded 1,012 tons of milling ore, from which 234 tons of copper-lead-zinc concentrate were produced. The copper ore of shipping grade amounted to 380,130 tons, largely sulphides, containing 24 cents in gold and 3.73 ounces of silver per ton and 5.68 per cent of copper and having an average value of $34.36 a ton.

Most of the lead ore produced, or 20,402 tons, was shipped directly to the smelters and contained $4.18 in gold and 17.65 ounces of silver per ton, 0.06 per cent of copper, and 11.33 per cent of lead and had an average value per ton of $38.54. Lead concentrates were separated from lead-zinc ore, of which 67,783 tons were treated, and produced 7,409 tons of lead concentrate, averaging $3.26 in gold and 22 ounces of silver per ton, 0.17 per cent of copper, and 39.56 per cent of lead. The average value per ton of all lead concentrates was $84.33.

Zinc concentrates recovered from zinc ore, lead-zinc ore, and copper-lead-zinc ore aggregated 285,621 tons, averaging 45 cents in gold and 8.82 ounces of silver per ton, 0.40 per cent of copper, 1.40 per cent of lead, and 32.03 per cent of zinc, the total average value per ton being $77.65. Lead-zinc concentrates recovered from lead-zinc ore aggregated 6,178 tons, containing a trace of gold, 10.22 ounces of silver per ton, 8.40 per cent of lead, and 22.80 per cent of zinc, the average value per ton being $71.12.

Digitized by Google

Ore and metals produced in Montana in 1917.

Source of production.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.
		Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Placers	99	.....	22,594.17	3,551	.....	.....	.....
Dry or siliceous ore	215	444,222	107,172.83	954,477	543,456	268,464	.....
Copper ore	120	4,844,537	27,561.56	8,911,389	271,331,858	820	.....
Lead ore	178	28,923	4,688.65	388,435	55,780	5,554,911	.....
Zinc ore	11	258,846	1,475.24	378,239	768,690	3,539,184	34,032,936
Copper-lead ore	8	3,344	223.45	95,747	156,675	1,073,182	.....
Lead-zinc ore	16	726,280	6,373.21	2,386,824	1,580,520	11,456,659	152,101,530
Copper-lead-zinc ore	1	1,012	58.00	9,480	25,600	58,000	124,865
	.....	6,307,164	170,147.11	13,128,142	274,462,574	21,951,220	186,259,331

Ore sold or treated in Montana in 1917, in short tons.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-lead ore. ore.	Lead-zinc ore.	Copper-lead-zinc ore.	Total.
Beaverhead	5,820	1,025	3,201	.....	1,647	37	.....	11,730
Broadwater	3,547	6,376	1,199	22	.....	.....	.....	11,144
Cascade	3,665	.....	3,126	.....	.....	.....	.....	6,791
Deer Lodge	52,133	47	.....	.....	.....	.....	.....	52,180
Fergus	38,133	.....	11	.....	.....	.....	.....	38,144
Gallatin	.....	18	.....	.....	.....	.....	.....	18
Granite	16,730	4,128	263	.....	.....	.....	.....	21,121
Jefferson	5,792	30,521	10,969	363	1,001	17,974	1,012	67,632
Lewis and Clark	69,848	148	7,405	.....	.....	258	.....	77,659
Lincoln	630	.....	.....	.....	.....	61,647	.....	62,277
Madison	10,167	3,291	1,062	.....	.....	.....	.....	14,520
Meagher	.....	830	43	.....	.....	.....	.....	873
Mineral	33	22,076	93	.....	.....	363	.....	22,565
Missoula	400	214	74	.....	.....	.....	.....	688
Park	80	32	53	.....	.....	.....	.....	165
Phillips	223,350	.....	.....	.....	.....	.....	.....	223,350
Powell	411	417	1,308	.....	9	.....	.....	2,145
Ravalli	.....	.....	.....	.....	.....	12,100	.....	12,100
Sanders	.....	201	116	.....	687	.....	.....	1,004
Silver Bow	13,483	4,775,213	.....	258,461	.....	633,901	.....	5,681,058
	[a]444,222	4,844,537	28,923	258,846	3,344	726,280	1,012	6,307,164
Value per ton in gold and silver	$6.76	$1.63	$14.42	$1.32	$24.97	$2.89	$8.90	$2.20

[a] Includes 411,118 tons of gold ore, 7 tons of gold and silver ore, and 33,097 tons of silver ore.

GOLD.

The mine production of gold in Montana decreased from $4,550,494 in 1916 to $3,517,253 in 1917. Lewis and Clark County is credited with the largest total output, $872,529 from deep and placer mines; Silver Bow County followed with $690,801, and Madison County with $500,703. The output of the placers amounted to $467,063, against $723,159 in 1916, a decrease of nearly 36 per cent. The largest output of gold from deep mines came from Lewis and Clark and Silver Bow counties, followed by Deer Lodge, Phillips, and Fergus counties. At amalgamation and cyanidation plants $1,383,097 in gold was produced, or an average recovery of $4.10 per ton of ore and tailings treated. Gold in bullion from deep mines came principally from Lewis and Clark, Phillips, and Fergus counties, with a distinct increase in Lewis and Clark County, as the Piegan-Gloster & Shannon property in that county was the

Digitized by Google

largest producer from that source in Montana. The output from these counties alone was valued at $1,319,201. In 1916 these three counties produced gold valued at $1,353,263 at gold and silver mills, and Phillips County, or the Little Rockies district, was the most productive locality. Ore treated at concentration mills produced concentrates containing $675,460 in gold, or 38 cents per ton. The crude ore shipped to smelters contained $984,625 in gold, or an average per ton of $1.96. The placer gold produced was chiefly the output of one company operating 3 dredges in Alder Gulch, Madison County.

More than two-thirds of the total gold in 1917 was produced from 6 properties, which, named in order of output, were the Anaconda mines, chiefly from copper ores; the Shannon-Piegan-Gloster mines, near Marysville, from siliceous ores; the Southern Cross mine, from oxidized iron ores at Georgetown; the Conrey placers in Alder Gulch, Madison County; the Ruby Gulch mines in Phillips County; and the North Moccasin mine in Fergus County. Each of the two last-mentioned yielded gold from low-grade siliceous gold ore.

Mine production of gold in Montana in 1917, in fine ounces.

County.	Placers.	Deep mines.							Total.
		Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-lead ore.	Lead-zinc ore.	Copper-lead-zinc ore.	
Beaverhead	27.82	1,421.30	115.09	134.75	.....	62.95	.....	.....	1,761.91
Broadwater	238.54	2,183.32	37.77	413.31	.....	.....	.....	.....	2,872.94
Cascade	.....	133.86	.....	86.49	.....	.....	.....	.....	220.35
Deer Lodge	.....	22,067.29	.15	.....	.....	.....	.....	.....	22,067.44
Fergus	.....	12,985.35	.....	19.54	.....	.....	.....	.....	13,004.89
Granite	634.82	5,528.21	63.80	6.05	.....	.....	.....	.....	6,232.88
Jefferson	35.94	1,137.89	296.94	1,812.23	25.00	153.67	1,772.85	58.00	5,292.52
Lewis and Clark	300.55	41,074.00	.93	828.43	.....	.....	4.68	.....	42,208.59
Lincoln	1.11	562.17	.....	.....	.....	.....	445.00	.....	1,008.28
Madison	20,006.45	2,979.96	28.59	1,206.51	.....	.....	.....	.....	24,221.51
Meagher	29.95	.....	.38	.....	.....	.....	.....	.....	30.33
Mineral	340.13	12.99	96.62	.....	.....	.....	.....	.....	449.74
Missoula	60.08	300.02	9.19	.....	.....	.....	.....	.....	369.29
Park	12.43	104.00	.25	7.69	.....	.....	.....	.....	124.37
Phillips	.....	15,703.88	.....	.....	.....	.....	.....	.....	15,703.88
Powell	686.63	89.39	38.05	173.65	.....	1.84	.....	.....	989.56
Ravalli	40.20	.....	.....	.....	.....	.....	96.27	.....	136.47
Sanders	2.56	.....	7.11	.....	.....	4.99	.....	.....	14.66
Silver Bow	176.96	869.20	26,866.69	.....	1,450.24	.....	4,054.41	.....	33,417.50
	22,594.17	[a]107,172.83	27,561.56	4,688.65	1,475.24	223.45	6,373.21	58.00	170,147.11

[a] Includes 103,835.47 ounces from gold ore, 2.20 ounces from gold and silver ore, and 3,335.16 ounces from silver ore.

SILVER.

Mines in Montana produced 13,128,142 ounces of silver, valued at $10,817,589, in 1917. The quantity produced was more than 20 per cent less than in 1916. From copper ore 8,911,389 ounces of silver were obtained, an average of 1.84 ounces per ton. However, nearly all of the copper ore produced was milled and the concentrates averaged 4.87 ounces of silver per ton. The silver output of Silver Bow County decreased 3,472,171 ounces, but increases in other counties reduced the State decrease. Jefferson County had the largest increase in silver. Cyanidation and amalgamation mills

Digitized by Google

yielded precipitates and bullion containing 235,068 ounces, concentration mills produced concentrates containing 10,053,994 ounces, and crude ore shipped to smelters contained 2,580,608 ounces.

More than 81 per cent of the total silver was produced from six properties, the Anaconda mines leading, followed by the Butte & Superior, North Butte, Elm Orlu, and East Butte mines, all in Silver Bow County, and the Granite-Bimetallic property, in Granite County.

Mine production of silver in Montana in 1917, in fine ounces.

County.	Placers.	Deep mines.							Total.
		Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-zinc ore.	Lead-zinc ore.	Copper-lead-zinc ore.	
Beaverhead	2	35,436	4,898	21,029	.....	77,938	.....	.....	139,303
Broadwater	41	2,362	1,269	13,527	153	.....	.....	.....	17,352
Cascade	.....	67,750	.....	136,428	.....	.....	.....	.....	204,178
Deer Lodge	.....	20,228	589	.....	.....	.....	.....	.....	20,817
Fergus	.....	2,786	.....	193	.....	.....	.....	.....	2,979
Gallatin	.....	.....	3	.....	.....	.....	.....	.....	3
Granite	176	394,586	35,397	15,657	.....	.....	.....	.....	445,806
Jefferson	12	11,269	67,625	126,197	3,558	13,178	93,367	9,480	324,686
Lewis and Clark	56	103,561	329	51,659	.....	.....	502	.....	156,107
Lincoln	.....	157	.....	.....	.....	.....	89,980	.....	90,137
Madison	3,136	22,893	1,409	10,529	.....	.....	.....	.....	37,967
Meagher	4	.....	103	531	.....	.....	.....	.....	638
Mineral	10	.....	1,761	2,198	.....	.....	3,158	.....	7,125
Missoula	3	47	298	295	.....	.....	.....	.....	643
Park	1	25	18	960	.....	.....	.....	.....	1,004
Phillips	.....	131,341	.....	.....	.....	.....	.....	.....	131,341
Powell	84	503	2,739	5,181	.....	102	.....	.....	8,719
Ravalli	4	.....	.....	.....	.....	.....	16,155	.....	16,159
Sanders	.....	.....	3,056	4,053	.....	4,469	.....	.....	11,578
Silver Bow	22	161,533	8,791,855	.....	374,528	.....	2,183,662	.....	11,511,600
	3,551	a954,477	8,911,389	388,435	378,239	95,747	2,386,824	9,480	13,128,142

a Includes 281,334 ounces from gold ore, 47 ounces from gold and silver ore, and 673,096 ounces from silver ore.

COPPER.

Montana produced 274,462,574 pounds of copper in 1917, valued at $74,928,283. This total represents a decrease of 78,465,799 pounds in quantity and $11,892,097 in value in 1917. Silver Bow County, or practically the Butte district, contributed all the copper except 3,869,673 pounds. Mines in Jefferson County produced the next largest quantity, 1,215,385 pounds, followed in order by Broadwater, Mineral, and Granite counties. Crude ore of various kinds shipped to smelters in 1917 contained 43,912,757 pounds of copper, or an average of 4.36 per cent. The sulphide copper ore of smelting grade predominated and contained 41,562,810 pounds, an average of 5.89 per cent, and the oxidized copper ores contained 1,674,684 pounds, or 123 per cent. Copper precipitates produced from mine waters and the washings from old tailings contained 14,151,721 pounds. The Washoe works[1] near Anaconda treated during 1917 in the copper leaching plant 598,370.16 tons of tailings, from which there were produced 5,019.67 tons of cement copper. Ore leached, amounting to 54,009 tons, contained 810,139 pounds of copper. Concentrates

[1] Anaconda Copper Mining Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

shipped to smelters, averaging 6.01 per cent of copper, contained 215,587,957 pounds, the bulk of which was from copper concentrates. The output of copper from Butte or Summit Valley district decreased from 349,532,636 pounds in 1916 to 270,567,544 pounds in 1917. In copper production the Anaconda mines at Butte make the greatest output, followed by the North Butte, East Butte, and Davis-Daly properties.

Mine production of copper in Montana in 1917, in pounds.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-lead ore.	Lead-zinc ore.	Copper-lead-zinc ore.	Total.
Beaverhead	3,417	128,644	30,310	.....	104,263	.....	.....	266,634
Broadwater	49,518	880,258	1,583	.....	.....	.....	.....	931,359
Cascade	.....	.....	1,023	.....	.....	.....	.....	1,023
Deer Lodge	177,313	9,367	.....	.....	.....	.....	.....	186,680
Fergus	60	.....	185	.....	.....	.....	.....	245
Gallatin	.....	3,627	.....	.....	.....	.....	.....	3,627
Granite	152,749	266,760	474	.....	.....	.....	.....	419,983
Jefferson	4,739	1,043,287	5,354	4,528	30,061	101,816	25,600	1,215,385
Lewis and Clark	101	20,507	8,197	.....	.....	.....	.....	28,805
Madison	10,647	62,354	4,011	.....	.....	.....	.....	77,012
Meagher	.....	80,871	.....	.....	.....	.....	.....	80,871
Mineral	.....	518,375	.....	.....	.....	.....	.....	518,375
Missoula	.....	35,286	.....	.....	.....	.....	.....	35,286
Park	.....	1,154	.....	.....	.....	.....	.....	1,154
Powell	.....	18,376	.....	.....	483	.....	.....	18,859
Ravalli	.....	.....	.....	.....	.....	4,260	.....	4,260
Sanders	.....	53,604	4,643	.....	21,868	.....	.....	80,115
Silver Bow	144,912	268,209,383	.....	764,162	.....	1,474,444	.....	270,592,901
	a 543,456	271,331,853	55,780	768,690	156,675	1,580,520	25,600	274,462,574

a Includes 382,289 pounds from gold ore, 40 pounds from gold and silver ore, and 161,127 pounds from silver ore.

LEAD.

The mine production of lead in Montana was 21,951,220 pounds, valued at $1,887,805, in 1917, against 13,595,136 pounds, valued at $938,064, in 1916. Of this output, more than 47 per cent was derived from mines in Silver Bow County, which produced 10,352,453 pounds, against 9,195,082 pounds in 1916. The increase was due largely to the output of zinc ore and lead-zinc ore, which were concentrated from Butte mines. The next largest output of lead, or 3,927,559 pounds, came from the mines in Lincoln County, followed by Jefferson County with 2,455,350 pounds. There were large increases in Lincoln, Jefferson, Mineral, Silver Bow, and Lewis and Clark counties. Crude ore of all kinds shipped to the smelters contained about 27 per cent of the total lead (5,877,283 pounds), 15,550,225 pounds were contained in concentrates, and 523,712 pounds in old tailings and slags shipped. Lead ore shipped to smelters contained 4,623,358 pounds of lead, an average of more than 11 per cent, and the lead concentrates contained 6,279,655 pounds, an average of more than 35 per cent. The zinc concentrate contained 8,017,658 pounds of recoverable lead. Two properties at Butte supplied most of this material.

The Butte & Superior property, at Butte, produced the largest quantity of lead in 1917, followed by the Snow Storm in Lincoln County and the Anaconda mines at Butte.

Digitized by Google

Mine production of lead in Montana in 1917, in pounds.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-lead ore.	Lead-zinc ore.	Copper-lead-zinc ore.	Total.
Beaverhead	3,411	820	680,388	.....	826,298	4,604	.....	1,515,521
Broadwater	.....	.....	325,186	3,014	.....	.....	.....	328,200
Cascade	203,922	.....	1,091,141	.....	.....	.....	.....	1,295,063
Fergus	2,375	.....	2,220	.....	.....	.....	.....	4,595
Granite	.....	.....	57,087	.....	.....	.....	.....	57,087
Jefferson	7,147	.....	1,629,346	24,950	136,060	599,827	58,000	2,455,350
Lewis and Clark	50,853	.....	1,138,557	.....	.....	10,458	.....	1,199,868
Lincoln	.....	.....	.....	.....	.....	3,927,559	.....	3,927,559
Madison	756	.....	428,243	.....	.....	.....	.....	428,999
Meagher	.....	.....	26,994	.....	.....	.....	.....	26,994
Mineral	.....	.....	19,668	.....	.....	40,360	.....	60,028
Missoula	.....	.....	41,394	.....	.....	.....	.....	41,394
Park	.....	.....	38,229	.....	.....	.....	.....	38,229
Powell	.....	.....	50,776	.....	2,603	.....	.....	53,379
Ravalli	.....	.....	.....	.....	.....	32,618	.....	32,618
Sanders	.....	.....	25,682	.....	108,201	.....	.....	133,883
Silver Bow	.....	.....	.....	3,511,220	.....	6,841,233	.....	10,352,453
	[a] 268,464	820	5,554,911	3,539,184	1,073,182	11,456,659	58,000	21,951,220

[a] Includes 61,131 pounds from gold ore and 207,333 pounds from silver ore.

ZINC.

The mine production of recoverable zinc in Montana was 186,259,331 pounds, valued at $18,998,452, in 1917, against 229,259,075 pounds, valued at $30,720,716, in 1916. The bulk of the zinc output was from Silver Bow County, and smaller quantities came from Jefferson, Lincoln, Ravalli, Mineral, Lewis and Clark, Beaverhead, and Broadwater counties. The largest quantity of zinc was contained in the product of the Butte & Superior mine at Butte and amounted to 131,337,299 pounds in concentrate having an average zinc content of 47.36 per cent. All of the zinc concentrate produced in Butte at the Butte & Superior and Elm Orlu mills were shipped to eastern smelting works, but nearly all the zinc ore from the Emma mine and other properties at Butte was concentrated at the Washoe concentrator and the concentrate was shipped and treated at the electrolytic zinc plant at Great Falls. The zinc plants[1] at Washoe and Great Falls treated during the year 326,479.14 tons of ore and other zinciferous material, of which 257,849.93 tons of zinc ore were produced by mines of the company and 68,629.21 tons were purchased from other companies. The plants at Great Falls produced 50,624,524 pounds of electrolytic zinc in 1917, principally from Montana ore but partly from ore from Idaho and Utah.

First in production of zinc in 1917 was the Butte & Superior mine, followed by the Elm Orlu, Anaconda mines, and Emma property, all at Butte.

[1] Anaconda Copper Mining Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

Mine production of recoverable zinc in Montana in 1917, in pounds.

County.	Zinc ore.	Lead-zinc ore.	Copper-lead-zinc ore.	Total.
Beaverhead		15,918		15,918
Broadwater	15,363			15,363
Jefferson	155,664	3,357,556	124,865	3,638,085
Lewis and Clark		31,145		31,145
Lincoln		1,552,867		1,552,867
Mineral		197,595		197,595
Ravalli		491,943		491,943
Silver Bow	33,861,909	146,454,506		180,316,415
	34,032,936	152,101,530	124,865	186,259,371

MINING INDUSTRY.

A systematic campaign to interfere with and prevent the production of metals essential to winning the war was inaugurated in June, 1917, through the activity of the I. W. W. A series of labor disturbances, strikes, and walkouts occurred, which greatly reduced the output of copper ore from the various mines at Butte. This condition lasted through the summer and well into the fall of 1917, automatically closing the concentrators and smelters at Washoe and Great Falls. The smaller operators at Butte, and particularly the zinc producers, the Butte & Superior and the Elm Orlu, were the first to make anything near a normal production of ore. On December 18 the Metal Mine Workers' Union voted to call the labor strikes off and return to work. Wages for miners before the trouble were $4.75 per day and at present are $5.25. Payment is reported[1] to have been based on the sliding scale with a base of $3.50 per day when copper was under 15 cents per pound and advancing 25 cents for every 2 cents increase in the price of copper. This was agreed on by the companies notwithstanding the fact that the price of copper was fixed by the Government in October.

METALLURGIC INDUSTRY.

Various kinds of milling plants, 53 in number, operated in Montana during a part or the whole of the year 1917, some of them only for short periods. Eleven plants used the amalgamation process; 2 used amalgamation and concentration; 1 used concentration and cyanidation; 14 were cyanidation mills; 19 were concentration mills, of which 11 used oil-flotation equipment after table concentration and 2 used the flotation method alone. Included in this total there were 2 copper-leaching plants, 1 electrolytic zinc-leaching plant, and 3 copper-precipitating plants that extracted copper from mine waters. Several small precipitating plants were operated by lessees, whose output was included with that of the lessor. Of the 337,610 tons of ore and old tailings treated at gold and silver mills, 8,925 tons were treated by amalgamation and yielded 2,845.30 ounces of gold and 1,246 ounces of silver, or an average recovery of $6.59 in gold and 0.14 ounce of silver per ton. The ore treated by cyanidation aggregated 318,823 tons, which, with 9,862 tons of old tailings, yielded

[1] Min. and Sci. Press, Jan. 5, 1918, p. 20.

Digitized by Google

64,062 ounces of gold and 233,822 ounces of silver, or an average recovery per ton for ore and old tailings of $4.03 in gold and 0.71 ounce of silver. The total value of the bullion recovered from ore and tailings by both amalgamation and cyanidation was $1,576,793, as against an output in 1916 valued at $1,407,099. During 1917 there were 167 pounds of mercury and 158,215 pounds of sodium cyanide consumed in gold and silver mills. This represented 0.04 pound of mercury per ounce of gold and silver bullion and 0.018 pound per ton of ore treated. The consumption of cyanide was 0.53 pound per ounce of gold and silver bullion and 0.48 pound per ton of ore and tailings treated.

Gold and silver produced at mills in Montana in 1917.

County.	Ore.	Bullion recovered from ore by—				Total value.
		Amalgamation.		Cyanidation.		
		Gold.	Silver.	Gold.	Silver.	
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Fine ounces.*	*Fine ounces.*	
Beaverhead	5,000			1,132.18	6,826	$29,029
Broadwater	[a] 51	189.77	43			3,958
Cascade	9	8.69				180
Deer Lodge	1			.02	17	15
Fergus	[b] 38,133			12,937.42	2,660	269,632
Granite	163	97.60	68			2,074
Jefferson	3	.03	51			43
Lewis and Clark	[c] 61,141	1,136.42	675	[d] 34,038.60	[d] 84,364	797,204
Lincoln	630	562.17	157			11,749
Madison	[e] 2,843	541.06	203	[f] 158.95	[f] 8,548	21,681
Missoula	400	300.00	47			6,241
Park	12	9.56	2			200
Phillips	219,350			[g] 15,703.88	[g] 131,341	432,853
Powell				[h] 83.21	[h] 64	1,772
Silver Bow	12			7.74	2	162
	327,748	2,845.30	1,246	64,062.00	233,822	1,576,793

[a] Also yielded 1 ton of concentrates.
[b] Also yielded 14 tons of concentrates.
[c] Also yielded 11 tons of concentrates.
[d] Includes bullion from 4,962 tons of old tailing.
[e] Also yielded 65 tons of concentrates.
[f] Includes bullion from 500 tons of old tailing.
[g] Includes bullion from 4,000 tons of old tailing.
[h] Bullion from 400 tons of old tailing.

Mills in Montana equipped for the concentration of low-grade ore treated 5,086,706 tons, or about 80 per cent of the total ore mined. The concentrates produced and smelted amounted to 1,793,899 tons, containing 32,675.39 ounces of gold, 10,053,994 ounces of silver, 215,587,957 pounds of copper, 15,550,225 pounds of lead, and 185,851,604 pounds of recoverable zinc, valued in all at $88,109,646, or an average value per ton of $49.12.

Crude ore directly smelted, 503,023 tons, contained 47,631.24 ounces of gold, 2,580,608 ounces of silver, 43,912,757 pounds of copper, 5,877,283 pounds of lead, and 407,727 pounds of zinc, valued in all at $15,646,263, or an average of $31.10 per ton.

Digitized by Google

The following tables give the quantity of material shipped from the concentration mills and of crude ore shipped to the smelters, with the metals produced, by counties, in 1917:

Mine production of metals from Montana concentrates in 1917.

By counties.

County.	Ore to concentrating mills.	Concentrates produced.						Total value of concentrates.
		Quantity.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	
	Short tons.	*Short tons.*	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
Broadwater	4,461	261	7.92	53	152,422			$41,819
Fergus		14	47.93	126	60	2,375		1,315
Jefferson	48,479	14,872	2,070.22	162,039	1,025,144	749,275	3,485,301	876,117
Lewis and Clark	4,839	1,375	455.76	16,614	3,191	414,957	31,145	62,845
Lincoln	61,647	6,083	445.00	89,980		3,927,559	1,552,867	579,506
Madison	9,000	481	1,101.60	3,644	34,848	522		35,334
Mineral	21,033	1,390	27.12	1,561	399,891			111,017
Powell	1,506	195	77.17	2,344	11,371	9,951		7,486
Ravalli		605	96.27	16,155	4,280	32,618	491,943	69,448
Sanders	636	212	2.87	3,083	16,672	65,315		12,768
Silver Bow	4,935,105	1,768,411	28,343.53	9,758,395	213,940,098	10,347,653	180,290,348	86,311,991
	5,086,706	1,793,899	32,675.39	10,053,994	215,587,957	15,550,225	185,851,604	88,109,646

By kinds of concentrates.

Dry or siliceous		429	1,118.35	2,705	7,211	102		$27,325
Copper	1,492,104	22,981.51	7,263,678	213,185,020				64,659,851
Lead		8,818	1,748.36	181,721	28,095	6,279,655		733,600
Zinc		285,621	6,203.06	2,520,460	2,275,544	8,017,658	182,958,601	22,177,608
Copper-lead		515	152.35	12,812	40,414	156,388		38,188
Lead-zinc		6,178	413.76	63,138	26,073	1,038,422	2,768,138	439,351
Copper-lead-zinc		234	58.00	9,480	25,600	58,000	124,865	33,723

Mine production of metals from Montana crude ore shipped to smelters in 1917.

By counties.

County.	Quantity.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
	Short tons	*Fine oz.*	*Fine oz.*	*Pounds.*	*Pounds.*	*Pounds*	
Beaverhead	4,129	569.48	123,795	240,794	1,022,258	15,918	$269,053
Broadwater	6,632	2,436.71	17,215	778,937	328,200	15,363	306,998
Cascade	6,782	211.66	204,178	1,023	1,295,063		284,272
Deer Lodge	52,179	22,087.42	20,800	186,680			524,690
Fergus	11	19.54	193	185	2,220		805
Gallatin	18		3	3,627			992
Granite	20,958	5,500.46	445,562	419,983	57,067		600,411
Jefferson	18,927	3,173.62	160,995	188,771	1,691,049	152,784	410,813
Lewis and Clark	6,717	6,277.26	54,398	25,614	784,911		249,083
Madison	2,131	2,398.63	21,647	42,164	413,054		114,455
Meagher	873	.38	634	80,871	26,994		24,931
Mineral	1,532	82.49	5,554	118,484	60,028	197,595	63,945
Missoula	288	9.21	593	35,286	41,394		13,871
Park	153	102.38	1,001	1,154	38,229		6,543
Powell	239	142.55	6,227	7,488	43,428		13,859
Sanders	368	9.23	8,495	63,443	68,568		30,408
Silver Bow	381,086	4,610.22	1,509,318	41,718,253	4,800	26,067	12,731,134
	503,023	47,631.24	2,580,608	43,912,757	5,877,283	407,727	15,646,263

By kinds of ore.

Dry or siliceous	99,817	39,081.31	713,086	529,440	258,958		$1,562,271
Copper	380,130	4,331.85	1,416,880	43,237,494	920		13,060,962
Lead	20,402	4,116.60	360,124	25,279	4,623,358		786,351
Zinc	475	30.36	4,425	4,283	32,389	194,214	28,040
Copper-lead	1,799	71.12	82,935	116,261	916,794		180,392
Lead-zinc	400		3,158		44,964	213,513	28,247

Digitized by Google

PRODUCTION BY COUNTIES.

GENERAL FEATURES.

The following tables show the mine production of each metal, by counties, with its total value in 1917, the production of ore and its average value per ton by counties in 1916 and 1917, and the statistics of placer mines in 1916 and 1917. They are followed by a review of the mining industry for each county and each producing mining district.

Mine production of gold, silver, copper, lead, and zinc in Montana in 1917.

County.	Gold.					Silver.	
	Placers.		Deep mines.		Total value.	Quantity.	Value.
	Quantity.	Value.	Quantity.	Value.			
	Fine oz.		*Fine oz.*			*Fine oz.*	
Beaverhead	27.82	$575	1,734.09	$35,847	$36,422	139,303	$114,786
Broadwater	238.54	4,931	2,634.40	54,458	59,389	17,352	14,298
Cascade	.....	.....	220.35	4,555	4,555	204,178	168,243
Deer Lodge	.....	.....	22,087.44	456,588	456,588	20,817	17,153
Fergus	.....	.....	13,004.89	268,835	268,835	2,979	2,455
Gallatin	.....	.....	.....	.....	.....	3	2
Granite	634.82	13,123	5,598.06	115,722	128,845	445,806	367,344
Jefferson	35.94	743	5,256.58	108,663	109,406	324,686	267,541
Lewis and Clark	300.55	6,213	41,908.04	866,316	872,529	156,107	128,632
Lincoln	1.11	23	1,007.17	20,820	20,843	90,137	74,273
Madison	20,006.45	413,570	4,215.06	87,133	500,703	37,967	31,285
Meagher	29.95	619	.38	8	627	638	526
Mineral	340.13	7,031	109.61	2,266	9,297	7,125	5,871
Missoula	60.08	1,242	309.21	6,392	7,634	643	530
Park	12.43	257	111.94	2,314	2,571	1,004	827
Phillips	.....	.....	15,703.88	324,628	324,628	131,341	108,225
Powell	686.63	14,194	302.93	6,262	20,456	8,719	7,185
Ravalli	40.20	831	96.27	1,990	2,821	16,159	13,315
Sanders	2.56	53	12.10	250	303	11,578	9,540
Silver Bow	176.96	3,658	33,240.54	687,143	690,801	11,511,600	9,485,558
	22,594.17	467,063	147,552.94	3,050,190	3,517,253	13,128,142	10,817,589

County.	Copper.		Lead.		Recoverable zinc content.		Total value.
	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	
	Pounds.		*Pounds.*		*Pounds.*		
Beaverhead	266,634	$72,791	1,515,521	$130,335	15,918	$1,624	$355,958
Broadwater	931,359	254,261	328,200	28,225	15,363	1,567	357,740
Cascade	1,023	279	1,295,063	111,375	.....	.....	284,452
Deer Lodge	186,680	50,964	.....	.....	.....	.....	524,705
Fergus	245	67	4,595	395	.....	.....	271,752
Gallatin	3,627	990	.....	.....	.....	.....	992
Granite	419,983	114,655	57,087	4,909	.....	.....	615,753
Jefferson	1,215,385	331,800	2,455,350	211,160	3,638,085	371,085	1,290,992
Lewis and Clark	28,805	7,864	1,199,868	103,189	31,145	3,177	1,115,391
Lincoln	.....	.....	3,927,559	337,770	1,552,867	158,392	591,278
Madison	77,012	21,024	428,999	36,894	.....	.....	589,906
Meagher	80,871	22,078	26,994	2,322	.....	.....	25,553
Mineral	518,375	141,516	60,028	5,162	197,595	20,155	182,001
Missoula	35,286	9,633	41,394	3,560	.....	.....	21,357
Park	1,154	315	38,229	3,288	.....	.....	7,001
Phillips	.....	.....	.....	.....	.....	.....	432,853
Powell	18,859	5,149	53,379	4,591	.....	.....	37,381
Ravalli	4,260	1,163	32,618	2,805	491,943	50,178	70,282
Sanders	80,115	21,872	133,883	11,514	.....	.....	43,229
Silver Bow	270,592,901	73,871,862	10,352,453	890,311	180,316,115	18,392,274	103,330,806
	274,462,574	74,928,283	21,951,220	1,887,805	186,259,331	18,998,452	110,149,382

Digitized by Google

Ore sold or treated, mines producing, and average value per ton of ores in Montana in 1916 and 1917.

County.	Ore sold or treated, 1917 (short tons).		Number of deep mines producing.		Average value per ton.[a]		Average value per ton in gold and silver.[a]	
	Quantity.	Increase or decrease.	1916	1917	1916	1917	1916	1917
Beaverhead	11,730	+ 9,070	23	35	$65.54	$30.30	$24.26	$12.84
Broadwater	11,144	+ 3,816	13	37	35.39	31.66	11.43	6.17
Cascade	6,791	+ 4,786	17	34	59.24	41.88	35.63	25.45
Deer Lodge	52,180	— 13,536	13	14	12.34	10.05	11.64	9.08
Fergus	38,144	— 28,091	12	9	6.80	7.12	6.67	7.11
Gallatin	18	— 7	1	2	14.68	55.11	.04	.11
Granite	21,121	— 5,233	31	33	26.38	28.52	21.12	22.86
Jefferson	67,632	+ 13,301	61	75	10.76	19.08	3.82	5.56
Lewis and Clark	77,659	+ 5,217	46	77	11.58	14.28	11.30	12.81
Lincoln	62,277	+ 61,934	4	2	25.70	9.49	23.17	1.53
Madison	14,520	— 9,574	85	97	10.65	11.97	8.35	7.98
Meagher	873	— 1,129	5	7	29.16	28.56	.10	.61
Mineral	22,565	— 22,472	3	6	14.47	7.75	1.12	.36
Missoula	688	— 43	5	8	20.93	29.23	7.02	10.06
Park	165	+ 133	2	6	30.22	40.87	17.09	19.03
Phillips	223,350	— 36,530	3	2	2.03	1.94	2.03	1.94
Powell	2,145	+ 1,279	18	14	37.80	10.78	23.00	6.24
Ravalli	12,100	— 7,900	1	1	4.82	5.74	1.13	1.26
Sanders	1,004	+ 495	7	8	64.54	43.00	11.43	9.75
Silver Bow	5,681,058	— 1,528,777	43	51	17.69	18.19	1.50	1.79
	6,307,164	— 1,553,261	393	518	16.94	17.39	1.87	2.20

[a] Value per ton, placer product excluded.

Number and production of producing placer mines in Montana in 1916 and 1917.

County.	1916						1917					
	Hydraulic, dry, and sluicing.	Dredging.	Drift.	Gold.	Silver.	Total value.	Hydraulic, dry, and sluicing.	Dredging.	Drift.	Gold.	Silver.	Total value.
					Fine ounces.						*Fine ounces.*	
Beaverhead	4	.....	.....	$740	3	$742	2	.....	.....	$575	2	$577
Broadwater	6	.....	.....	3,424	31	3,444	6	.....	.....	4,931	41	4,965
Granite	8	.....	1	4,478	50	4,511	6	.....	.....	13,123	176	13,268
Jefferson	5	.....	.....	970	10	977	9	.....	.....	743	12	753
Lewis and Clark	17	.....	2	6,638	52	6,672	15	.....	2	6,213	56	6,259
Lincoln	5	.....	.....	1,493	6	1,497	1	.....	.....	23	.....	23
Madison	7	1	.....	644,766	4,869	647,970	5	1	.....	413,570	3,136	416,154
Meagher	1	.....	.....	48	.....	48	2	.....	.....	619	4	622
Mineral	15	1	2	12,273	29	12,292	16	.....	.....	7,031	10	7,039
Missoula	10	.....	.....	2,492	5	2,495	5	.....	.....	1,242	3	1,245
Park	.....	.....	1	543	3	545	3	.....	.....	257	1	258
Phillips	1	.....	.....	101	2	102	.....	.....	.....	.....	.....	.....
Powell	18	.....	1	22,738	145	22,834	16	.....	1	14,194	84	14,263
Ravalli	4	.....	1	15,981	46	16,011	3	.....	.....	831	4	834
Sanders	2	.....	.....	212	.....	212	1	.....	.....	53	.....	53
Silver Bow	7	.....	.....	6,262	91	6,322	5	.....	.....	3,658	22	3,676
	110	2	8	723,159	5,342	726,674	95	1	3	467,063	3,551	469,989

Digitized by Google

BEAVERHEAD COUNTY.

Mine production in Beaverhead County, Mont., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead	Recoverable zinc content.	Total value.
		Short tons.		*Fine oz.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	27	2,660	$5,651	90,616	226,132	785,308	.....	$175,091
1917	37	11,730	36,422	139,303	266,634	1,515,521	15,918	355,958
Increase, 1917	.....	9,070	30,771	48,687	40,502	730,213	15,918	180,867

[a] Includes placer production.

Thirty-five deep-mine operators produced 9,070 tons of ore more than was produced by 23 deep-mine operators in 1916. The total average value per ton decreased from $65.54 in 1916 to $30.30 in 1917, and the gold and silver value decreased from $24.26 to $12.84 a ton. About half of the ore mined in 1917 was of shipping grade and contained $11,772 in gold, 123,795 ounces of silver, 240,794 pounds of copper, and 1,022,258 pounds of lead, valued in all at $269,053, or an average of $65.16 a ton. Ore treated at one gold and silver mill yielded considerable bullion. The largest part of the county output, or 5,820 tons, was dry or siliceous ore; 1,025 tons was copper ore, 3,201 tons was lead ore and old slag, and 1,647 tons was copper-lead ore. Placer bullion contained $575 in gold and 2 ounces of silver, against a yield of $740 in gold and 3 ounces of silver in 1916.

Argenta district.—The greater part of the district output was derived from old slag, which contained principally lead with considerable silver and a little copper and gold. The Tilden property was a producer of lead sulphide ore, containing silver, copper, and gold. There was also some copper ore produced from the Jack Rabbit property.

Bannack district.—Five producers reported 5,450 tons of ore, containing $29,250 in gold, 7,895 ounces of silver, 17,416 pounds of copper, and 7,997 pounds of lead, valued in all at $41,198, or an average value per ton of $7.56. The greater part of the output in tonnage and value of gold and silver was from the Bannack property, equipped with a cyanidation plant which was operated intermittently the early part of the year and closed indefinitely in June. According to letters,[1]

> The equipment of the mine is in good condition, and its milling capacity is 150 tons a day. Over $1,500,000 has been taken out of the property in the past. But this has been an irregular production, owing to the loss from time to time of milling and shipping ore and the delays experienced in recovering the veins. The present discontinuance of operations, however, resulted from the encountering of heavy water in the Priscilla winze, where the ore sampled across 8 feet averaged $40 gold per ton in the vein at the contact of granodiorite and lime. This discovery in the bottom of the Priscilla winze is no doubt a renewal of the old ore bodies separated by a leached zone. It was impossible to overcome the water with the existing pumping and power plants, and a shutdown resulted.
>
> Exclusive of the rich showings in the Priscilla winze, I should estimate, gaging the values from the mill run and from the extensive sampling which has been done from time to time, that at least 17,400 tons of $5.20 gold per ton ore is ready for milling in the upper workings and most of this ore has already

[1] Turner, G. D. B., mining engineer, to J. H. McClement, New York. Letter dated Nov. 15, 1917.

Digitized by Google

been broken and filled in stopes ready to withdraw. Under the present condition of labor and material, I should estimate a net profit on the working of this mill of at least $1.13 per ton, or $18,871.

Some oxidized copper ore was shipped from the Excelsior claim of the Original Bannack Mining Co. and three smaller producers.

Beaverhead district.—Eight deep mines produced 164 tons of ore, containing gold, silver, copper, and lead, having a total value of $13,245, or an average value per ton of $80.76. There was a placer output reported by one producer. The principal producers of copper ore were the Baltic, Dark Horse, and Monument properties. The I. X. L. placer was operated about 30 days during the year and won a small quantity of gold bullion by sluicing.

Big Hole district.—The Montana Oreway property, near Briston, produced siliceous silver ore and some oxidized copper-lead ore. Through small operations of the New Discovery placer a small quantity of gold bullion was produced.

Blue Wing district.—Five operators produced 248 tons, the largest output coming from the New Departure property, which yielded principally silver ore containing gold with a little lead and copper. There were smaller productions from the Kent and Cotton Tail properties.

Bryant district.—The output of 1,918 tons of ore, principally from the Cleopatra, Ariadne, True Fissure, Oneida, Alta, Atlantis, Trapper, and Cleve claims, contained $1,473 in gold, 80,891 ounces in silver, 104,791 pounds of copper, 908,830 pounds of lead, and 15,918 pounds of recoverable zinc, valued in all at $176,518, or an average value per ton of $92.03. All this ore, which included that from the Vermont, Avanca, Copper Bottom, and a small tonnage of old slag from the Hecla, was shipped directly to the smelters.

Camp Creek district.—Some copper ore, containing silver and a little gold, was shipped from the Banner property.

Elkhorn district.—This district was the scene of much active development work during 1917. The Boston Montana Development Co. reported the control of about 2,000 acres of mineral land, known as the Central group and other claims, cut by numerous veins, all said to contain a commercial grade of copper ore on the surface. Two of the largest veins are reported to have been cut at a depth of 1,000 feet by the recently completed double-tracked adit 2,070 feet long. Additional development was made by two crosscuts 2,001 feet and 2,500 feet long, respectively. A concentration mill is planned, and a railroad to the mines, starting from Divide on the Oregon Short Line Railroad, is expected to be built in 1918.

Polaris district.—The Silver Fissure mine yielded an important tonnage of siliceous silver ore, containing a little gold, which was shipped to the copper smelter at Anaconda.

Saginaw district.—An estimated production of 290 tons of oxidized copper ore containing a little silver was reported shipped from the Saginaw group.

Utopia district.—The Indian Queen and the Chief & Ida properties were producers of smelting ore containing copper and a little silver.

Vipond district.—Two producers reported oxidized lead ore containing silver. The principal part of the output was shipped from the Gray Jockey claim directly to the smelter.

Digitized by Google

BROADWATER COUNTY.

Mine production in Broadwater County, Mont., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead.	Recoverable zinc content.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	19	7,328	$82,491	7,223	700,542	46,480	.....	$262,784
1917	43	11,144	59,389	17,352	931,359	328,200	15,363	357,740
Increase or decrease, 1917	.....	+3,816	−23,102	+10,129	+230,817	+281,720	+15,363	+94,956

[a] Includes placer production.

The production in 1917 of 11,144 tons of ore by 37 operators of deep mines is 3,816 tons more than was produced by 13 operators in 1916. The total average value per ton decreased from $35.39 in 1916 to $31.66 in 1917, and the gold and silver value in this ore from $11.43 to $6.17. The greater part of the ore, or 6,632 tons, was of shipping grade. There were treated at 2 milling plants 4,512 tons of ore, which yielded 261 tons of concentrate, principally a copper product, and some gold and silver bullion. The total output from deep mines of the county was $54,458 in gold, 17,311 ounces of silver, 931,359 pounds of copper, 328,200 pounds of lead, and 15,363 pounds of recoverable zinc, valued in all at $352,775. The yield of placer bullion amounted to $4,931 in gold and 41 ounces of silver, against $3,424 in gold and 31 ounces of silver in 1916.

Backer district.—The Slim Jim and Humming Bird properties were producers of gold bullion containing a little silver, recovered in milling operations from small but rich veins of gold quartz. Some of the work on the Slim Jim property was performed by lessees. Placer gravel in Confederate Gulch, worked by hydraulicking, also yielded some gold and silver bullion.

Beaver district.—Twelve deep-mine operators and 1 placer operator reported the production of 1,027 tons of ore, containing $9,929 in gold, 10,168 ounces of silver, 554 pounds of copper, 269,556 pounds of lead, and 15,363 pounds of recoverable zinc, valued in all at $43,208. The ore produced averaged $41.49 per ton. The principal producer of lead ore of shipping grade was the Hyantha property. Smaller shipments were made from the Little Olga, Mary V., and Joe Dandy properties. The Indian Creek placer produced a small quantity of gold from hydraulic operations.

Cedar Planes district.—Sixteen deep mines and 1 placer reported the production of 4,251 tons of ore, containing $42,010 in gold, 5,858 ounces of silver, 80,388 pounds of copper, and 45,906 pounds of lead. The total value of this output was $72,731. The ore, all of which was of shipping grade, averaged $16.92 a ton. Owing to litigation, the largest producer in the district was practically inactive, and only a small quantity of iron sulphide ore, containing principally gold and a little copper, was shipped early in 1917. The Copper King & Alaska, Jumbo, Mohave, Mountain View, Ruby Silver, Santa Anita, and Little Giant properties were producers. The Crow Creek placer in Charity Gulch was operated about 75 days, yielding a small quantity of gold bullion.

Digitized by Google

Hellgate district.—The Furnace Creek Oxide Copper Co., operating the Eclipse Argo property, equipped with a 50-ton table concentrator, shipped copper concentrate and copper sulphide ore to the smelter. The ore is mostly chalcopyrite, containing one-tenth of an ounce of silver and a trace of gold per ton.

Park district.—Six deep mines and 3 placers reported an output valued at $2,789 in gold, silver, and lead. The principal producers of lead ore were the Double Standard, Margaret Taylor, Bedford, Boomerang, and Iron Mask properties. Three placers produced $120 in gold and silver bullion. The Metropolitan & Kalamazoo property in the Warm Springs region was also worked.

CASCADE COUNTY.

Mine production in Cascade County, Mont., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc content.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	17	2,005	$6,533	98,651	3,916	635,169	19,106	$118,795
1917	34	6,791	4,555	204,178	1,023	1,295,063	.....	284,452
Increase or decrease, 1917	.....	+4,786	−1,978	+105,527	−2,893	+659,894	−19,106	+165,657

Thirty-four deep mines in 1917 produced 4,786 tons more ore than 17 operators in 1916. The total average value per ton of the ore decreased from $59.24 in 1916 to $41.88 in 1917, and the gold and silver value per ton from $35.63 to $25.45. The total output of the county amounted to $284,452. The greater part of the ore, or 3,665 tons, was dry or siliceous in character, and the remainder, 3,126 tons, was lead ore.

Montana district.—Thirty-one producers reported an output of 6,488 tons of ore, containing $4,555 in gold, 196,426 ounces of silver, 534 pounds of copper, and 1,215,994 pounds of lead, valued in all at $271,131, or an average value per ton of $41.79. All the ore, with the exception of 9 tons which yielded a little gold bullion, was of shipping grade. Over half of the output, consisting of sulphide ore containing principally silver and a low percentage of lead, came from the Galt property. Other producers of importance were the Tom Hendricks, Liberty, Queen of the Hills, Ripple, Silver Belt, B. & M., Equator, Wright & Edwards, Florence, and Broadwater properties.

Running Wolf Creek district.—Three deep-mine producers shipped to the smelters from Stanford, on the Great Northern Railway, 303 tons of ore, containing 7,752 ounces of silver, 489 pounds of copper, and 79,069 pounds of lead, valued in all at $13,321, or an average value per ton of $43.96. Most of this output, consisting of oxidized lead ore, was from the Mountainside property. Ore was also produced from the S. W. Scott, Romer Sunrise, Dry Wolf, and Charles Martin claims.

Digitized by Google

DEER LODGE COUNTY.

Fourteen deep-mine operators reported the production of 52,180 tons of ore in 1917, a decrease of 13,536 tons. The total value per ton decreased from $12.34 in 1916 to $10.05 in 1917, and the gold and silver value per ton from $11.64 to $9.08. The largest part of the ore, or 52,133 tons, was highly oxidized ore of shipping grade, containing principally gold and valuable at the smelters chiefly for fluxing. No placer production was reported in 1917.

Fisher Creek district.—The Little May claim was a producer of sulphide copper ore containing a little silver.

French Gulch district.—The placers and lode mines of the Boston Montana Development Co. were idle. All of the work by this mining company was performed in the Elkhorn district of Beaverhead County.

Georgetown district.—Eleven producers reported 52,085 tons of ore, containing $456,523 in gold, 20,218 ounces of silver, and 178,262 pounds of copper, valued in all at $521,849, or an average value per ton of $10.02. The principal part of the output was from the Southern Cross mine, which produces an oxidized iron ore, containing gold with a little silver and copper. Similar ore was produced from the Holdfast, New Year, and Oro Fino properties.

Oro Fino district.—The Independence mine yielded a small quantity of oxidized copper ore, which was shipped directly to the smelter. There was also a small output of silver ore containing a little gold from the March property.

FERGUS COUNTY.

Mine production in Fergus County, Mont., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	
1916	12	66,235	$432,687	13,920	8,280	93,351	$450,324
1917	9	38,144	268,835	2,979	245	4,595	271,752
Decrease, 1917		28,091	163,852	10,941	8,035	88,756	178,572

Nine producers in 1917, against 12 producers in 1916, reported a large decrease. All the ore, with the exception of 11 tons, was of milling grade and yielded gold and silver bullion and a little lead concentrate. The crude shipping ore contained gold, silver, copper, and lead and was valued at $805, or an average of $73.18 per ton.

Cone Butte district.—The Big Chicago property was a producer of gold ore, which was treated in its 15-ton cyanidation plant.

North Moccasin district.—Owing to the severe weather conditions in the district, open-cut mining was possible for only eight minths during 1917. Gold ore was produced from the North Moccasin and Kendall properties, operated by the Barnes King Development Co., whose annual report[1] gives a yield of 26,790 tons of ore, averaging

[1] Barnes King Development Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

$8.53 per ton in gold and silver, against 33,715 tons averaging $8.65 in 1916. From the Kendall property, which was leased during 1917, the production of ore was 7,923 tons, averaging $2.95 a ton in gold and silver. This output is only a little more than half that of 1916, when 14,918 tons were mined and milled, averaging $2.50 a ton in gold and silver.

Warm Springs district.—From the Maginnis and Cumberland properties some gold ore was treated in cyanidation plants.

GALLATIN COUNTY.

The Leonard mine and one other property in an unorganized mining district produced silver-bearing copper ore, valued at $992 at the smelter.

GRANITE COUNTY.

Mine production in Granite County, Mont., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.[a]	Silver.	Copper.	Lead.	Recoverable zinc content.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	40	26,354	$134,002	649,328	493,349	75,709	89,063	$699,782
1917	39	21,121	128,845	445,806	419,983	57,087	.....	615,753
Decrease, 1917	.....	5,233	5,157	203,522	73,366	18,622	89,063	84,029

[a] Includes placer production.

Thirty-three producers mined 21,121 tons of ore, or 5,233 tons less than was mined by 31 producers in 1916. The total average value per ton increased from $26.38 in 1916 to $28.52 in 1917, and the gold and silver value per ton from $21.12 to $22.86. The crude ore shipped, 20,958 tons, contained gold, silver, copper, and lead and had an average value per ton of $28.65. There were 163 tons of ore which yielded bullion at gold and silver mills. Six placer operators reported the yield of $13,123 in gold and 176 ounces of silver, against $4,478 in gold and 50 ounces of silver from 9 placers in 1916.

Alps district.—Some gold ore from the Rainy Day property treated in a 5-ton amalgamation mill produced a small quantity of gold bullion.

First Chance district.—The Nancy Hanks property, worked by lessees in 1917, produced a considerable quantity of gold ore containing silver and a little copper. The Mountain group was operated during the greater part of the year, yielding copper ore of shipping grade, and the Alabama placer, situated at Summit, 2 miles east of Garnet, yielded a small quantity of gold from sluicing operations.

Flint Creek district.—Eighteen producers reported the output of 16,810 tons of ore, containing $39,759 in gold, 427,623 ounces of silver, 201,064 pounds of copper, and 41,652 pounds of lead, valued in all at $450,593, or an average value per ton of $26.81. All this ore was shipped directly to the smelter, with the exception of 2 tons, which produced a little silver bullion. The principal part of the output was silver ore with a little gold and copper from the

Digitized by Google

Granite-Bimetallic mine. From the Hope mine, operated by the Philipsburg Mining Co., copper ore and some lead ore containing silver and gold was shipped. There were smaller productions from the Hobo group, Londonderry, Swastika, and White Horse claims. Shipments of manganese ore from various properties were made during 1917 to manufacturers of steel in the Eastern States.

Rock Creek district.—The principal work done was on the Basin placers, which were worked by hydraulicking methods and yielded gold and silver bullion.

South Boulder district.—Ten deep mines reported the production of 730 tons of ore, containing $1,327 in gold; 5,511 ounces of silver, 39,257 pounds of copper, and 10,397 pounds of lead, valued in all at $17,479, or an average value per ton of $23.94. The placer output made by 2 producers was valued at $373. Lessees milled some gold ore from the Royal Gold property and produced a small quantity of gold bullion. The Royal Basin, Brooklyn, Kink & Copper Queen, and Bay View properties were producers, principally of copper ore. The Montana placer, on Princeton Creek, and the Lulu placer, in Wilson Gulch, were producers of gold bullion.

JEFFERSON COUNTY.

Mine production in Jefferson County, Mont., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead.	Recoverable zinc content.	Total value.
		Shorttons.		*Fine oz.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	66	54,331	$100,412	164,703	852,857	679,760	893,348	$585,872
1917	84	67,632	109,406	324,686	1,215,385	2,455,350	3,638,085	1,290,992
Increase, 1917		13,301	8,994	159,983	362,528	1,775,590	2,739,737	705,120

[a] Includes placer production.

Seventy-five deep-mine producers in 1917 reported 13,301 tons of ore more than was reported by 61 producers in 1916. The total average value per ton increased from $10.76 in 1916 to $19.08 in 1917, and the gold and silver value per ton in this ore from $3.82 to $5.56. Most of the ore produced, or 48,479 tons, was of milling grade and yielded 14,872 tons of concentrates, which contained $42,795 in gold, 162,039 ounces of silver, 1,025,144 pounds of copper, 749,275 pounds of lead, and 3,485,301 pounds of recoverable zinc, valued in all at $876,117, or an average value per ton of $58.91. There were 18,927 tons of shipping ore, containing gold, silver, copper, lead, and zinc, valued in all at $410,813, or an average value per ton of $21.71. The greater part of the ore output (30,521 tons) was classified as copper ore, and 17,974 tons were lead-zinc ore. The remainder of the output consisted of 5,792 tons of dry or siliceous ore, 10,969 tons of lead ore, 363 tons of zinc ore, 1,001 tons of copper-lead ore, and 1,012 tons of copper-lead-zinc ore. The production of 9 placer operators amounted to $743 in gold and 12 ounces of silver, against a production of $970 in gold and 10 ounces of silver in 1916.

Amazon district.—From the Australian claim a small tonnage of silver ore and some low-grade lead ore was shipped directly to the smelter. There was also a small shipment from the Phoenix property.

Digitized by Google

Boulder district.—Altogether 2,266 tons of ore were produced by 5 deep mines in the district. The total output contained $6,047 in gold, 24,753 ounces of silver, 52,001 pounds of copper, 191,726 pounds of lead, and 124,865 pounds of zinc, valued in all at $69,683, or an average value per ton of $30.83. The larger part of this ore, or 1,921 tons, was milled and produced copper-lead-zinc concentrate. There were also 345 tons of crude shipping ore produced. The Baltimore property was the largest producer, yielding an ore from which a concentrate containing copper, lead, zinc, and silver was saved at the Washoe works near Anaconda. Copper-lead ore from the Bland & Weaver property was treated in its 40-ton concentration plant situated in the district. There was also a small output of gold bullion reported by 2 placer operators.

Cataract district.—Twenty-three deep mines in 1917 produced 22,183 tons of ore, containing $51,153 in gold, 152,977 ounces of silver, 186,043 pounds of copper, 1,063,054 pounds of lead, and 3,509,184 pounds of recoverable zinc, valued in all at $677,356, or an average value per ton of $30.53. The placer output reported by a few producers was small. One property produced most of the ore, which was milled and yielded lead and zinc concentrates. The ore of shipping grade amounted to 4,215 tons. The largest producer was the Comet mine, from which the zinc concentrates were shipped to the electrolytic zinc works at Great Falls and the lead concentrates to the lead plant at East Helena. There were also considerable shipments of crude ore from the West Rumley and the Hope, and smaller lots from the Crystal, John T., Last Chance, Montana, Solar Pearl, Uncle Sam, and Ruby properties. The Aaron placer on Overland Creek, 11 miles from Basin, produced a small quantity of gold.

Colorado district.—Eighteen producers reported 35,945 tons of ore, containing $23,620 in gold, 128,696 ounces of silver, 895,792 pounds of copper, 910,160 pounds of lead, and 4,036 pounds of recoverable zinc, valued in all at $452,903, or an average value per ton of $12.60. Most of this ore, or 28,593 tons, was milled and produced copper concentrate containing silver and gold. The Bertha mine was the principal producer of milling ore. The ore of shipping grade amounted to 7,259 tons, containing 1,043.73 ounces of gold, 78,578 ounces of silver, 20,236 pounds of copper, and 900,336 pounds of lead. Most of this crude ore was shipped from the Angelica property, with smaller quantities from the Alta and the Blue Bird.

Elkhorn district.—There were 5,910 tons of ore and a small quantity of old tailings reported by 8 operators. The total output contained $21,260 in gold, 9,113 ounces of silver, 17,222 pounds of copper, and 105,235 pounds of lead, valued in all at $42,521, or an average value per ton of $7.19. The principal part of the ore shipped was from the Golden Curry mine, which yielded an oxidized iron ore containing a little gold, silver, and copper. Other shipments of importance were made by lessees on the Elkhorn Queen and the Holter claims. The Fortune Teller placer, on Wilson Creek, yielded gold by sluicing.

Homestake district.—The Black Sheep and Homestake properties were reported as small shippers of crude ore to the smelter.

Digitized by Google

Lump Gulch district.—Five producers reported the shipment of 79 tons of ore, valued for its content of gold, silver, copper, and lead at $4,256, or an average value per ton of $53.87. The output of gold bullion from 2 placers was valued at $336. The deep mines operated were the Bell, White Pine, Two Dot, and Capital Consolidated. The Lump Gulch placer, 9 miles from Clancey, yielded a small quantity of gold bullion during the construction of 1,400 feet of sluice boxes.

Whitehall district.—All the ore produced in the district was of shipping grade and amounted to 972 tons, containing $3,979 in gold, 3,595 ounces of silver, 63,301 pounds of copper, and 162,774 pounds of lead, valued in all at $38,220, or an average value per ton of $39.32. Most of the ore was from the property of the Butte Cardwell Mining Co. There were smaller shipments made from the Eighty Acre, Parrot, Golden Sunlight, and Milburn properties.

LEWIS AND CLARK COUNTY.

Mine production in Lewis and Clark County, Mont., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc content.	Total value.
Placers:		*Short tons.*		*Fine oz.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	19	.....	$6,638	52	.....	.....	.....	$6,672
1917	17	.....	6,213	56	.....	.....	.....	6,259
Deep mines:								
1916	46	72,442	751,476	101,533	33,102	92,285	43,318	838,634
1917	77	77,659	866,316	156,051	28,805	1,199,868	31,145	1,109,132
Increase or decrease, 1917	.....	+5,217	+114,415	+54,472	−4,297	+1,107,583	−12,173	+270,085

The output of ore reported by 77 producers was 5,217 tons greater than was produced by 46 operators in 1916. The total average value per ton increased from $11.58 in 1916 to $14.28 in 1917, and the gold and silver value from $11.30 to $12.81. Ores sent to gold and silver mills, aggregating 61,141 tons, were treated principally by cyanidation and yielded bullion containing $727,132 in gold and 85,039 ounces of silver and having an average value per ton of $13.04. In addition to the ores yielding bullion, 4,839 tons of ore produced 1,375 tons of concentrates, containing gold, silver, lead, zinc, and a little copper. Crude shipping ore aggregated 6,717 tons and contained $129,762 in gold, 54,398 ounces of silver, 25,614 pounds of copper, and 784,911 pounds of lead, valued in all at $249,083, or an average value per ton of $37.08. Most of the ore mined (69,848 tons) was dry or siliceous in character. There were also produced 148 tons of copper ore, 7,405 tons of lead ore, and 258 tons of lead-zinc ore. The placer output of 17 producers amounted to $6,213 in gold and 56 ounces of silver, against $6,638 in gold and 52 ounces of silver in 1916.

Bald Butte district.—Three producers shipped gold and silver bullion and some concentrate containing gold and silver, recovered from 161 tons of ore and 4,962 tons of old tailings. The tailings were treated in a cyanidation plant, and the ore was treated by amalgamation. The Albion and Eureka properties were the producers of

Digitized by Google

crude ore, and the tailings were from an old mill situated in the district.

Big Blackfoot district.—The Lockey claim yielded a small quantity of gold bullion from crude ore treated in an arrastre.

Dry Gulch district.—A small shipment of crude lead ore, containing silver, was made from the Lady Alice property. The New York Gulch placer produced some bullion, which, with that from the operations carried on by several Chinamen, yielded gold valued at $2,422 and 19 ounces of silver.

Gladstone district.—The Copper Lode mine was a producer of sulphide copper ore, containing silver.

Gould district.—A small quantity of gold, probably from operations in 1916, was reported from one property in the district.

Greenhorn district.—Crude ore of shipping grade, containing silver, was produced from the Stem Winder and Far West properties, and gold ore with a little lead and silver was produced from the Umatilla and Pipe Line claims. The Evans & Jones placer was operated for four months by drift mining and yielded a small quantity of gold.

Helena district.—Crude ore shipped amounting to 2,045 tons and 4 tons treated by amalgamation were reported by 14 operators. The total output of the district, containing gold, silver, copper, and lead, was valued at $67,145, or an average value per ton of $32.80. The greater part of the ore was produced from the Helena mine, operated by the Helena Mining Bureau, which shipped a sulphide ore of lead and iron containing considerable silver and some gold. The Rock Rose & Looby, Horn Lode, and Copper Queen properties shipped small quantities of ore. Various small operations carried on with rockers and bullion from the Humboldt placer, in Grizzly Gulch, yielded $760 in gold and 6 ounces of silver. The Northwestern Metals zinc plant, which was built in 1915 and proved a failure, was equipped for concentration and operated as a custom plant by the New York Montana Testing & Engineering Co. in 1917. Ore from the Valley Forge dumps at Rimini and manganese ore from Philipsburg and Butte were treated. The mill has a capacity of 50 to 80 tons of ore daily and is equipped with 2 crushers, 2 sets of rolls, 1 Colorado ball mill, 8 Wilfley tables, and 4 Hartz jigs.

Lincoln district.—From the Mike Horse mine some lead ore containing silver and a little copper and gold was shipped to the smelter. The Harvey and Old Billy Williams placers yielded gold by sluicing. It is possible to work these properties only about six months of the year.

Ottawa district.—Fifteen producers reported 56,565 tons of ore, containing $691,160 in gold, 82,694 ounces of silver, 3,287 pounds of copper, and 91,290 pounds of lead, valued in all at $768,048, or an average value per ton of $13.58. The greater part of this output was treated at cyanidation plants. The 400 tons shipped directly to smelters contained 5.42 ounces of gold, 2,818 ounces of silver, 3,287 pounds of copper, and 91,290 pounds of lead. Most of the milling ore was from the Shannon and Piegan-Gloster properties. There was also an important tonnage of ore from the Drumlummon mine treated in the mill belonging to the St. Louis Mining Co.

Digitized by Google

At the Piegan-Gloster mine[1] 20,525 tons of ore were mined and treated by the cyanidation process and yielded bullion containing 8,381.65 ounces of gold and 60,008.86 ounces of silver. According to the report of the company,

> Development work was mostly confined to the ground adjoining the Gloster workings, and production came from ore shoots found west of the old stopes.
>
> The 400 level was driven west 657 feet on veins, and three ore bodies were found. These were short and did not go up far enough to justify the driving of the 360 level west.
>
> The 500 level was driven 560 feet west, but values under the ore shoots found on the 400 level were found too low grade to stope, except for a distance of 40 feet below the 400. There are three short ore shoots still ahead of the 500 face, and it is likely that they will be found as one longer shoot when opened on this level.
>
> At the eastern end of the mine crosscuts and drifts were entirely unproductive, although 250 feet of vein was explored which lines up with the Gloster vein on strike.

The Shannon became the property of the Barnes King Co. in 1917 and produced 32,359 tons of ore, which was treated by the cyanidation process and yielded 23,011.07 ounces of gold and 30,211.72 ounces of silver. The ore from the Piegan-Gloster and Shannon mines was treated at the Gloster mill. The company report continues as follows:

> Sinking from the 400 level to the 500 was begun in February, and drifts started on the latter level in April. In sinking this lift the shaft was in the vein but apparently passed through the ore shoot halfway down, and drifting east on the 500 level has failed to show values. In drifting west the vein was rich, but the shoot was only a little more than 100 feet long and about the width of the drift. Values were approximately $50 per ton. * * *
>
> Sinking of the shaft to the 650 was started in November and 85 feet of the 150 completed by the end of the year.

In Uncle Ben Gulch, 9 miles from Marysville, lessees operated the Sandburn & Goodenough placer by sluicing and hydraulicking.

Owyhee district.—Three producers reported 47 tons of ore, valued at $2,186, or an average value per ton of $46.51 for its content of gold, silver, and copper. The producers were the Grand View, D. & D., and McRea claims.

Poorman district.—A small quantity of bullion was produced from sluicing gravel of one placer.

Scratch Gravel district.—Nine producers reported 3,629 tons of ore, all of which was shipped to the smelters and contained $117,028 in gold, 15,598 ounces of silver, 2,420 pounds of copper, and 109,684 pounds of lead, valued in all at $139,975, or an average value per ton of $38.57. The principal part of the production was from the Franklin mine, and some ore came also from the Scratch Gravel gold mine. Both properties produced a silver-bearing gold ore, which was smelted. There were also large shipments from the Julia and Katie claims.

Springhill district.—The Skelly Gulch and St. Louis placers, situated 9 miles from Austin, yielded a small quantity of gold bullion by drifting and sluicing.

Stemple district.—Eight operators produced 1,544 tons of ore, containing gold, silver, and copper, valued at $16,855. The larger part of the ore was estimated as the output of one property, which pro-

[1] Barnes King Development Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

duced gold bullion recovered by amalgamation. There was also some ore treated by cyanidation. Only 35 tons of crude ore, a part of which was from the Bachelor property, were shipped directly to the smelter. There were smaller shipments from the Klondyke and Rover claims.

Ten Mile district.—The Stanton and Merritt were the only mining claims from which ore was shipped in 1917. The former property yielded milling ore, which was shipped to the concentrating works near Helena, and some zinc ore was shipped to eastern zinc furnaces.

Unionville district.—From a clean-up of the Whitlatch mine and mill, some bullion and crude smelting ore containing gold and silver were shipped.

Vaughn district.—Seven producers reported 6,644 tons of ore, which with bullion from 2 placers contained $16,829 in gold, 15,110 ounces of silver, 1,071 pounds of copper, and 219,413 pounds of lead, valued in all at $48,441. Most of the output was milled and yielded bullion at gold and silver mills and a lead concentrate at a custom milling plant. The principal part of the bullion production came from the Porphyry Dike and San Juan properties, and the milling ore was from the mine dump of the Valley Forge property. There was a small output of shipping ore and milling ore from the R. E. Lee and Caplice Extension properties. The Perseverance and Tucker Gulch placers yielded some gold bullion during a short season of operation.

Wolf Creek district.—The production was 85 tons of ore, containing gold, silver, copper, and lead, with a total average value per ton of $37.21. The producers were the Silver Lode, King Bear, Algoma, Hanks, and Mountain View properties.

LINCOLN COUNTY.

Two deep-mine operators reported 62,277 tons of ore, valued in all at $591,255, or an average value per ton of $9.49. All of this ore was milled, 630 tons yielding gold and silver bullion by amalgamation and the remainder producing concentrates, containing gold, silver, lead, and zinc. Only one placer operator reported production, against 5 placer operators producing $1,493 in gold and 6 ounces of silver in 1916.

Libby district.—Gold and silver bullion and tungsten concentrates were produced from ore treated from the Rose Consolidated property, which is equipped with an amalgamation and concentration plant. Only one placer producer reported a small quantity of gold. In previous years the placer output has been noteworthy, and it is possible that more gold was produced in 1917 than was reported to the Survey.

Troy district.—The Snowstorm Consolidated, operating the Banner & Bangle property, treated a large quantity of ore, yielding lead and zinc concentrates. The mill producing these concentrates is a new one situated on Callahan Creek, 1 mile from Troy, completed and started May 1, 1917. It has an equipment for treating 400 tons of ore daily, consisting of a gyratory crusher, 4 sets of rolls, three 8-foot Hardinge mills, 2 Richards-Janney classifiers, 7 Isbell vanners, and 11 Wilfley and 15 Diester tables. Experimental work with oil flotation is under way.

Digitized by Google

MADISON COUNTY.

Mine production in Madison County, Mont., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc content.	Total value.
Placers:		*Shorttons.*		*Fine oz.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	8	.....	$644,766	4,869	.....	.....	.....	$647,970
1917	6	.....	413,570	3,136	.....	.....	.....	416,154
Deep mines:								
1916	85	24,094	175,464	39,046	116,744	383,557	2,642	256,694
1917	97	14,520	87,133	34,831	77,012	428,999	.....	173,752
Increase or decrease, 1917	.....	−9,574	−319,527	−5,948	−39,732	+45,442	−2,642	−314,758

Ninety-seven deep-mine operators in 1917 reported the production of 14,520 tons of ore, a decided decrease from the output of 1916. The total average value per ton increased from $10.65 in 1916 to $11.97 in 1917, but the gold and silver value per ton decreased from $8.35 to $7.98. The larger part of the ore (9,000 tons) was treated at concentration mills and yielded 481 tons of concentrates containing $22,772 in gold, 3,644 ounces of silver, 34,848 pounds of copper, and 522 pounds of lead, valued in all at $35,334, with an average value per ton of $73.46. There were 2,843 tons of ore treated at gold and silver mills, yielding bullion containing $14,470 in gold and 8,751 ounces of silver and having an average value per ton of $7.63. There were 2,131 tons of ore shipped, containing $49,584 in gold, 21,647 ounces of silver, 42,164 pounds of copper, and 413,054 pounds of lead, valued in all at $114,455, or an average value per ton of $53.71. Of the ore mined, 10,167 tons were classified as dry or siliceous ore, 3,291 tons as copper ore, and 1,062 tons as lead ore. Placer bullion reported by 6 producers amounted to $413,570 in gold and 3,136 ounces of silver, against a placer output by 8 producers of $644,766 in gold and 4,869 ounces of silver in 1916.

Alder Gulch district.—The output of 8 deep mines and 3 placers was valued at $421,393. The ore produced amounted to 267 tons, of which 145 tons were milled, yielding gold and silver bullion, and the remainder of the ore was shipped directly to the smelter. The principal producers were the U. S. Grant, Butte & Virginia, Alameda, Feldspar, Metallic, and Adopted Kid properties. The placer gold came largely from the Conrey property, on which 3 dredges operated during the entire year, yielding a greatly decreased output. During two months of 1917 the Alder Gulch Consolidated placers yielded gold by sluicing.

Havana district.—The Forsythe Development Co., operating the Havana mine, shipped a small quantity of siliceous silver ore containing a little gold. This property is opened by a shaft 300 feet deep. Much of the work in 1917 consisted of cleaning up the old works and dewatering the mine.

Lower Hot Springs district.—The output of 44 tons of ore by 9 producers was valued at $2,875, or an average value per ton of $65.34. The ore contained principally gold and silver, with a small quantity of copper reported from one property. The principal producers were the Badger, Florence, Twin Lake, Josephine, Midnight, and Morning Star.

Digitized by Google

McCarthy district.—The Windy and Mountain View properties were producers of lead ore, containing silver and a little gold and copper.

Mineral Hill district.—Seven operators reported the production of 2,557 tons of ore, containing $13,229 in gold, 951 ounces of silver, 1,335 pounds of copper, and 2,732 pounds of lead, valued in all at $14,612, or an average value per ton of $5.71. Most of the ore was produced from the Indian Gold property and was treated in an amalgamation and concentration plant, yielding gold and silver bullion and concentrate. There were 57 tons of ore shipped directly to the smelter from the Mountain Chief, Pony, White Pine, Horn Silver, and Wilson properties.

Norwegian district.—Four producers reported the output of 83 tons of ore of shipping grade, valued at $2,487, or an average value per ton of $29.96 for the content of gold, silver, copper, and lead. The producers were the Colorado, Gold Hill, O. K., and Rogers properties.

Rabbit district.—Seven mine operators reported a production of 187 tons of ore, containing gold, silver, copper, and lead, valued at $9,871, or an average value per ton of $52.79. Among the claims producing were the Emma, Marshall, Nez Perce, Rambler, Clifton, and Good Friday.

Ramshorn district.—The North Star mine produced a small quantity of gold ore containing a little copper and silver, and some gold ore was shipped from the Betsy Baker and Gold Coin group. In California Gulch the Camp Bird placer was operated and produced some gold bullion.

Sheridan district.—Ten producers reported 416 tons of ore, containing $5,285 in gold, 1,769 ounces of silver, 368 pounds of copper, and 164,118 pounds of lead, valued in all at $20,957, or an average value per ton of $50.38. A large part of this output was from the Deutschland claim, which yielded lead sulphide ore containing silver and gold. Smaller quantities of similar ore were produced by the Ivey, Silver King, Bay State, and Brandon properties, and gold and silver ore by the Ruby and Tamarack properties.

Silver Star district.—Nine operators reported 144 tons of ore, containing gold, silver, copper, and lead, valued at $4,945, or an average value per ton of $34.34. All of this ore, except 2 tons producing gold and silver bullion, was shipped directly to the smelters. The Edgerton, Hudson, King Fisher, Lean, and Turmoil properties were producers.

Summit district.—Seven producers reported 654 tons, containing $5,012 in gold, 10,535 ounces of silver, 3,923 pounds of copper, and 522 pounds of lead, valued in all at $14,809, or an average value per ton of $22.64. The larger part of the ore was shipped directly to the smelters, and 500 tons of tailing and 42 tons of crude ore yielded gold and silver bullion and a small quantity of lead concentrate. The old tailings were from the Easton Pacific property, operated by lessees in 1917. There was also a small quantity of silver ore shipped to the smelter from this property. Shipping ore was also produced from the Elfleda, Homestake, Copper Glance, and Wild Cat properties. The Mountain Flower and Highland Chief properties yielded milling ore producing bullion and a small quantity of con-

Digitized by Google

centrate. A small experimental concentration plant equipped with a crusher and one Isbell vanner was completed in December, 1917. Ores from the Winnetka, St. John, and Moonlight properties will be treated if these ores are found amenable to concentration.

Tidal Wave district.—Ore amounting to 6,973 tons was produced by 25 operators in 1917 and contained $50,546 in gold, 10,026 ounces of silver, 14,633 pounds of copper, and 190,781 pounds of lead, valued in all at $79,209, or an average value per ton of $11.36. The greater part of the ore from the B. & H. property was milled and produced concentrate containing gold, silver, and copper. The remaining part of the output, or 973 tons, was shipped directly to the smelters from the Elenora, Silver Bell, Sunset, Van Meter, Missouri & Texas, Longfellow, Ella, Bay State, High Ridge, and Little Goldie properties.

Upper Hot Springs district.—Three producers reported 49 tons of ore, containing $3,664 in gold, 394 ounces of silver, and 887 pounds of copper, valued in all at $4,230, or an average value per ton of $86.33. The mines producing were the Monitor & Revenue, Galena & Boaz, and Bull Moose.

Washington district.—Gold ore, with a little silver and lead, was shipped from the Lehigh property.

Wilmah district.—Milling ore treated in a 100-ton concentration mill on the Montana-Illinois property yielded copper concentrate containing silver and gold. As the milling plant is driven by water power, it was run only a short time between June and August when there was sufficient water.

MEAGHER COUNTY.

There were 873 tons of ore produced in 1917, which contained copper, silver, lead, and gold, having an average value per ton of $28.56, against an output of 2,002 tons in 1916, having an average value per ton of $29.16. The output of ore in 1917 was made by 7 producers, who reported 830 tons of copper ore and 43 tons of lead ore. The placer production reported by 2 operators amounted to $619 in gold and 4 ounces of silver, against $48 in gold in 1916.

Castle Mountain district.—The Copper Top mine and the Vandor property yielded copper ore containing silver, and the Yellowstone and Skidoo mines a small quantity of silver-lead ore. The total output was shipped directly to the smelters.

Diamond district.—One placer was productive of a small quantity of gold.

Musselshell district.—The principal producer was the Copperopolis mine, yielding silver-bearing copper ore. There was also a small output of similar ore from the Virginia & Southern Cross and the Blue Bird properties. From the operation of one placer, a few ounces of gold was reported.

MINERAL COUNTY.

Six producers in 1917 reported 22,565 tons of ore, containing $2,266 in gold, 7,115 ounces of silver, 518,375 pounds of copper, 60,028 pounds of lead, and 197,595 pounds of zinc, valued in all at $174,962, or an average value per ton of $7.75. This output consisted largely

Digitized by Google

of copper ore (22,076 tons), most of which was concentrated and yielded a concentrate containing copper with some silver and gold. The crude ore shipped aggregated 1,532 tons and contained $1,705 in gold, 5,554 ounces of silver, 118,484 pounds of copper, 60,028 pounds of lead, and 197,595 pounds of recoverable zinc, valued in all at $63,945, or an average value per ton of $41.74. The placer bullion reported by 16 producers amounted to $7,031 in gold and 10 ounces of silver, against a production of $12,273 in gold and 29 ounces of silver reported by 18 producers in 1916.

Cedar Creek district.—Ore produced from the Amador mine, operated by the Intermountain Copper Mining Co., yielded at its milling plant a considerable output of concentrate containing copper, silver, and gold. There was also some copper ore, which was shipped directly to a smelter in British Columbia. The mill is a 120-ton concentrator in which oil flotation was used. From the operations of 16 placers $7,031 in gold and 10 ounces of silver were produced. The principal part of the output was from the Cedar Creek Co.'s placers operated by hydraulic mining. The dredge, which was formerly on this ground, has been moved outside of the county. Other placers producing were the Eddie, Meadow Creek, Mildred, Nip & Tuck, Ohio, Stockholm, C. B. & Q., Windfall, Blue Bird, and Dakota.

Iron Mountain district.—The principal production was from one property, the Iron Mountain Tunnel, and consisted of zinc-lead sulphide ore and lead sulphide ore.

St. Regis district.—Ore of shipping grade, containing copper and gold, was produced from the St. Lawrence property, and some ore was also produced from the Oro Fino claim.

Saltese district.—The Last Chance claim yielded a small quantity of lead ore containing silver.

MISSOULA COUNTY.

Eight deep mines produced 688 tons of ore. The principal part, 400 tons, yielded gold and silver bullion and 288 tons were shipped directly to the smelters. The total output of ore contained $6,392 in gold, 640 ounces of silver, 35,286 pounds of copper, and 41,394 pounds of lead, valued in all at $20,112, or an average value per ton of $29.23. There were five placers yielding gold and silver bullion, containing $1,242 in gold and 3 ounces of silver.

Coloma district.—Gold ore from the Dandy property, which was operated by a lessee, yielded bullion in its amalgamation mill. The gravel of the Elk Creek placer was sluiced and yielded a small quantity of gold bullion.

Copper Cliff district.—Copper ore containing silver was shipped from the Copper Cliff and Mammoth properties.

Nine Mile district.—Through the operations of four placers an output of $570 in gold was reported.

Ravalli district.—A small quantity of copper ore containing silver was produced from the McDonald property.

Wallace district.—Copper ore, containing silver, was shipped to the smelter from the Hidden Treasure property.

Woodman Creek district.—The Lawyer's Combination property, Thanksgiving, and Bunker Hill claims were producers of silver-bearing copper ore, all of which was shipped directly to the smelter.

Digitized by Google

PARK COUNTY.

Emigrant Creek district.—There were two placers producing a small quantity of gold.

Natural Bridge district.—Copper ore containing silver was shipped to the smelter from the Drago property.

New World district.—Silver-lead ore, produced from the St. Elmo, Cuba Consolidated, and Yellowstone properties, was shipped to a lead smelter.

Porcupine district.—A small quantity of gold bullion, probably recovered from ore mined in the district, was reported by one operator.

Sheepeater district.—The Jardine mines, operated principally for the production of tungsten ore, were producers of gold bullion, probably recovered in the course of saving scheelite concentrate.

PHILLIPS COUNTY.

Little Rockies district.—Ore from two properties near Zortman, aggregating 219,350 tons, and 4,000 tons of old tailings re-treated, yielded gold and silver bullion by cyanidation. The bullion output of the county and district was second only to that of Lewis and Clark County in 1917 and had a value in gold and silver of $432,853, or of $1.94 a ton. There was a decided decrease in 1917, due in part to labor troubles. The Ruby Gulch Mining Co. has a 600-ton plant, and the value of the gold in the bullion was about eight times the value of the silver. The August Mining Co. operated a 200-ton plant, and the value of the gold in the bullion was approximately half of the value of the silver. The Beaver Creek mine, formerly a good producer, was idle.

POWELL COUNTY.

Mine production in Powell County, Mont., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	
Placers:							
1916	19	.....	$22,738	145	.....	.....	$22,834
1917	17	.....	14,194	84	.....	.....	14,263
Deep mines:							
1916	18	866	10,981	13,585	27,957	86,083	32,736
1917	14	2,145	6,262	8,635	18,859	53,379	23,118
Increase or decrease, 1917	.....	+1,279	−13,263	−5,011	−9,098	−32,704	−18,189

Fourteen producers reported in 1917 an output of 2,145 tons of ore, which was 1,279 tons more than was produced by 18 operators in 1916. The total value per ton decreased from $37.80 in 1916 to $10.78 in 1917, and the gold and silver value per ton from $23 to $6.24. Most of the ore, or 1,506 tons, was of milling grade, yielding concentrates containing $1,595 in gold, 2,344 ounces of silver, 11,371 pounds of copper, and 9,951 pounds of lead, valued in all at $7,486, or an average value per ton of $38.39. The ore shipped directly to the smelter aggregated 239 tons, containing $2,945 in gold, 6,227 ounces of silver, 7,488 pounds of copper, and 43,428 pounds of lead, valued in all at $13,859, or an average value per ton of $57.97.

Digitized by Google

Seventeen placer producers reported $14,194 in gold and 84 ounces of silver in 1917, against an output of $22,738 in gold and 145 ounces of silver in 1916.

Dunkelberg district.—Lead ore, containing a little silver, was shipped to the smelter by the Dunkelberg Mining Co.

Mary Ann district.—The Gray Rock property yielded about a carload of silver-lead ore, containing a little gold. The Marian and Clara May claims were also producers.

Ontario district.—Silver-lead ore from the Black Jack and Monarch properties and copper ore from the Foolhead group constituted the total production of the district in 1917.

Ophir district.—Three deep mines and seven placers produced ore and bullion valued at $7,414. There were 489 tons of ore, containing gold, silver, and copper, which had an average value per ton of $11.90. Some old tailings from the Victor property, re-treated by cyanidation, yielded gold and silver bullion. The Montana Clinton was a producer of copper ore containing silver and gold. Placer operators on seven properties reported the production of $1,586 in gold and 13 ounces of silver.

Pioneer district.—Seven placer operators reported an output of $11,635 in gold and 69 ounces of silver. As in previous years, the Pioneer placer, operated by hydraulicking and sluicing, was the principal producer. There was also some gold produced from the Friday, Oro Fino, and Upper Gold Creek placers.

Snowshoe district.—The Arnold and Wall Street properties each yielded copper ore, containing some silver and gold, which was shipped to the smelter.

Washington Gulch district.—From the operations of placers a small production of gold was reported.

Zozell district.—An important tonnage of lead concentrate, containing gold and silver, resulted from a short mill run on ore from the Emery property. There was also a small production of lead ore from the Bonanza property.

RAVALLI COUNTY.

Curlew district.—Old tailings re-treated in the concentration plant of the Victor Reduction Co. resulted in the shipment of lead and zinc concentrates containing some silver and copper.

Hughes Creek district.—From the operations of placers $831 in gold and 4 ounces of silver were reported.

SANDERS COUNTY.

Eight deep-mine producers reported the output of 1,004 tons of ore, containing $250 in gold, 11,578 ounces of silver, 80,115 pounds of copper, and 133,883 pounds of lead, valued in all at $43,176, or an average value per ton of $43. Compared with 1916, the ore output was 495 tons greater, but the average value per ton was less. Of the output, 201 tons were classified as copper ore, 116 tons as lead ore, and 687 tons as copper-lead ore.

Perma district.—Copper ore from the Exchange property and lead ore containing silver and copper from the Glancus claim were shipped to the smelter.

Digitized by Google

Revais Creek district.—The Dixon property yielded copper ore containing silver.

Spring Gulch district.—Five producers reported 949 tons of ore, containing $223 in gold, 11,419 ounces of silver, 64,459 pounds of copper, and 132,724 pounds of lead, valued in all at $38,644, or an average value per ton of $40.72. The King & Queen was the principal producer. The milling ore yielded a copper-lead concentrate, and the crude shipping product was copper ore and copper-lead ore. Lead ore of shipping grade containing silver was also produced from the Glen Metals property and the Silver King claim. A lessee shipped a small quantity of copper ore containing silver from the Copper King group.

Trout Creek district.—A small quantity of gold was reported from placers.

SILVER BOW COUNTY.

Mine production in Silver Bow County, Mont., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead.	Recoverable zinc content.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	50	7,209,835	$973,052	14,983,771	349,538,498	9,195,082	224,585,142	$127,547,714
1917	56	5,681,058	690,801	11,511,600	270,592,901	10,352,453	180,316,415	103,330,806
Increase or decrease, 1917		−1,528,777	−282,251	−3,472,171	−78,945,597	+1,157,371	−44,268,727	−24,216,908

[a] Includes placer production.

Fifty-one mine producers in 1917 reported 5,681,058 tons of ore, practically all of which was produced from the mines in the Butte or Summit Valley district. Most of this ore was produced by a few large operators. The remainder of the producers were lessees operating on various properties. The total average value per ton increased from $17.69 in 1916 to $18.19 in 1917, and the gold and silver value per ton in this ore from $1.50 to $1.79. The gold produced from both deep mines and placers decreased in value from $973,052 in 1916 to $690,801 in 1917, the silver from $9,859,321 to $9,485,558, the copper from $85,986,471 to $73,871,862, and the zinc from $30,094,409 to $18,392,274. Owing to the improved production and better price of lead in 1917, the value of the county output increased from $634,461 to $890,311. The total value of all metals decreased from $127,547,714 in 1916 to $103,330,806 in 1917. The larger part of the ore produced, 4,935,105 tons, was concentrated at milling plants situated at Butte, Anaconda, and Great Falls. The product consisted of lead concentrates, zinc concentrates, copper concentrates, and lead-zinc concentrates, aggregating 1,768,411 tons and containing $585,913 in gold, 9,758,395 ounces of silver, 213,940,098 pounds of copper, 10,347,653 pounds of lead, and 180,290,348 pounds of zinc, valued in all at $86,311,991, or an average value per ton of $48.81. The crude smelting ore amounted to 381,086 tons and contained $95,301 in gold, 1,509,318 ounces of silver, 41,718,253 pounds of copper, 4,800 pounds of lead, and 26,067 pounds of zinc, valued in all at $12,731,134, or an

Digitized by Google

average value per ton of $33.41. A small quantity of gold and silver bullion was produced from 12 tons of ore treated at a gold and silver mill. The ores mined were classified as 4,775,213 tons of copper ore, 633,901 tons of lead-zinc ore, 258,461 tons of zinc ore, and 13,483 tons of dry or siliceous ore. The placer output was $3,658 in gold and 22 ounces of silver, as against $6,262 in gold and 91 ounces of silver in 1916.

Divide Creek district.—Nine deep-mine producers reported 188 tons of ore, containing gold, silver, and copper, valued at $8,520, or an average value per ton of $45.32. The producers of copper ore carrying silver were the Gold King, Combination, Red Rose, Columbia, Copper Bell, Copper King, and Copper Ware.

German Gulch district.—This district, situated 20 miles from Butte, is usually the source of some placer bullion. In 1917 an output of $2,441 in gold and 12 ounces of silver was reported. Some of this production was from the Siberia and Central placers, equipped for hydraulicking and sluicing the gravel.

Highland district.—Placer bullion from the Highland placer of the Butte Water Co., and several smaller lots from various sources credited to the district, contained $1,217 in gold and 10 ounces of silver.

Summit Valley or Butte district.—Since the beginning of activities in 1882 to the end of 1917, Silver Bow County, of which this district covers the largest part, has produced gold, silver, copper, lead, and zinc valued at $1,447,637,563, divided as follows: Gold, $29,390,013; silver, $223,249,431; copper, $1,103,082,221; lead, $2,621,177. In 1905 the production of zinc began, and to the end of 1917 the value amounted to $89,294,721. The values given above are for 1,421,741.84 ounces of gold, 324,603,999 ounces of silver, 7,272,510,606 pounds of copper, 44,164,797 pounds of lead, and 910,955,686 pounds of recoverable zinc. A statement of the figures by years to 1913 may be seen in Mineral Resources for that year.

The principal producers of copper ores in 1917 were the Anaconda, North Butte, Pittsmont, Dutton, Bullwhacker, Balaklava, and Duluth. From the Elm Orlu mine copper ore and a large tonnage of zinc ore were mined; the zinc ore was treated in the Timber Butte mill, where zinc concentrate containing gold, silver, and copper and some lead concentrate were recovered. The Butte & Superior was the largest producer of lead-zinc sulphide ore, containing silver, which yielded, after concentration, lead concentrate as well as zinc concentrate.

The high price of silver has stimulated the revival of old silver properties that had been lying dormant for the last 25 or 30 years. Practically all of the present large operators in the district showed interest in local silver properties. The demand for manganese for the steel industry went hand in hand with the silver development, since most of the old silver mines have good surface showings of manganese ore. The Anaconda Co. is reported to be developing the Nettie, Orphan Girl, and Bonanza claims. The Butte & Superior Co. worked a group of claims in the silver district, the most important of which were the Germania, Tzarina, and Humboldt. The Clark Realty Co. worked the Moulton, Anselmo, and Travona properties. The Butte-Detroit Copper & Zinc Co. mined manganese ore

Digitized by Google

from the Britannia claim and concentrated it at the remodeled Ophir mill, situated in the southwestern part of Butte. The Davis-Daly, besides producing copper from the Colorado ores, extensively developed the Hibernia and Mount Moriah claims, both old silver producers. All this work is said to add to Butte's mining area and extends almost 4 miles southwest of its present productive areas.

In 1917 the Anaconda properties[1] produced 4,193,624.13 tons of ore and 10,011.83 tons of precipitate, or a total of 4,203,635.96 tons, against a total in 1916 of 5,589,157.48 tons. The Washoe reduction works, at Anaconda, treated 4,267,854 tons of ore and other cupriferous material; and the Great Falls plant 813,495.53 tons. Of this quantity, 3,906,901 tons of ore were produced from company mines; 449,513 tons of ore were either purchased from or treated for other companies; and 17,130 tons of precipitates and cleanings came from the old works at Anaconda and Butte. This material, treated at Anaconda and Great Falls copper plants, produced 253,508,332 pounds of fine copper, 9,031,025.78 ounces of silver, and 58,545.604 ounces of gold. The electrolytic copper refinery at Great Falls produced during the year 141,517,768 pounds of cathodes, 132,089,914 pounds of which were melted into shape at Great Falls, and 9,427,854 pounds were shipped to the Raritan copper works for melting. The copper-leaching plant at Anaconda treated during the year 598,370.16 tons of tailings, from which there were produced 10,039,340 pounds of cement copper. The zinc plants at Anaconda and Great Falls treated 326,479.14 tons of ore and other zinciferous material in 1917, of which 257,849.93 tons were produced by mines of the company and 68,629.21 tons of ore were purchased from other companies. At Great Falls 50,624,524 pounds of electrolytic zinc were produced in 1917. The company report contains much of interest, part of which follows:

During the year much attention was paid to the treatment of complex residues resulting from the zinc-leaching plant. These residues were stock piled until the month of June, when a bag house was put into commission. After continued experimental effort the desired result was obtained, and a reverberatory furnace, smelting zinc residues, was put into regular operation. By means of the method employed satisfactory recovery was made of the gold, silver, copper, and about 20 per cent of the lead contained in the furnace charge. This matte is converted in the usual way; most of the remaining lead is driven as a fume into the bag house, there collected, and then shipped to the lead plant of the International Smelting Co. for further treatment.

The plant recoveries have been very good and have realized the expectations entertained at the time of the reconstruction and improvement of the old and the construction of the new plants. * * *

The zinc-plant construction was completed during the year, and the bag house for collecting lead fume from the reverberatory furnace for smelting zinc-plant residues was completed. Three additional driers were built for the purpose of drying zinc-plant residues preliminary to smelting.

Four additional roasting furnaces were constructed for roasting zinc concentrates. * * * Work was commenced and has progressed satisfactorily on a rod and wire mill. This plant will be capable of rolling into rods 100 tons of copper per day and drawing into wire 80 tons of copper per day. It will roll copper rods and draw copper wire to market specifications. Completion of this mill, which will be approximately coincidental with the issuing of this report, will mark the entry of the company into the metal-manufacturing business.

[1] Anaconda Copper Mining Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

The North Butte properties [1] produced 304,647 wet tons of copper ore and 31 tons of copper precipitate. Of this, there were treated at the Anaconda smelter 296,750 dry tons of ore and 23 dry tons of precipitate. There were 7,202 dry tons of first-class ore, 263,436 tons of second-class ore, and 26,112 tons of third-class ore. All of the ore treated produced 14,493,452 pounds of fine copper, 662,845.79 ounces of silver, and 958.99 ounces of gold. There were also mined 5,770 dry tons of zinc ore, containing 1,222,482 pounds of zinc and 8,800.67 ounces of silver. Dividends paid in 1917 amounted to $1,075,000, the same as in 1916. The company report says:

Nearly 90 per cent of the entire production of ore for the year was mined prior to June 8, 1917, on which date the mines were thrown out of operation by an unfortunate fire which broke out on the 2,400 level of the Granite Mountain shaft and which burned out the timbering for a length of 1,400 feet and badly caved both the shaft and stations. In repairing the shaft it was decided to use steel and reinforced concrete construction from the 1,600 to the 3,000 levels and also to coat the timbers with cement from the 1,600 level to the surface in order to make the shaft fireproof, this being in line with the policy of the company to make its mines as safe as possible for the workmen. * * *

It was necessary to employ the Speculator shaft to lower supplies for the repair work at the Granite Mountain shaft.

Nearly all of the copper bullion produced at the Pittsmont smelter at Butte is from the ore of the Pittsmont and Dutton mines. Some ore is purchased from other mines producing ore usually desirable for its fluxing qualities. A 1,200-ton milling plant is attached to the smelter, where lower-grade ores are treated by concentration. The company [2] operating the property mined 181,904 dry tons of first-class and second-class copper ore, against a total output in 1916 of 209,805 tons. Of custom ore, there were treated 30,851 dry tons, which, with ore from the company's mine, yielded 20,013,900 pounds of copper, 581,190 ounces of silver, and 1,825 ounces of gold. The gross value of the metals shipped was $5,317,279.49. According to the company report, the average price of 25.46 cents a pound was paid for copper which cost 17.6727 cents to produce, leaving a profit of 7.7876 cents a pound. The following is from the same report:

During the first five months of the year (1917) average monthly production of first-class ore was 4,224 tons, and of second-class 14,100 tons. During the succeeding five months corresponding figures were 2,325 tons first class and 6,580 tons second class. In other words, output of first-class ore was reduced by 45 per cent, and second class by 55 per cent. * * *

Owing to an advance in wages and the cost of materials, combined with decreased efficiency of labor, the cost of mining advanced from $5.46 per ton in 1916 to $8.29 per ton in 1917, or 52 per cent. The cost of smelting has for like reasons increased very materially. In the meantime the higher average assay value of all ore mined, namely, 4.31 per cent as against 3.67 per cent for 1916, has tended to reduce the cost of copper per pound, the net result of the effect of these various factors being an increase of 8 mills per pound in the cost of copper delivered in New York.

From the Tuolumne property [3] 29,930 dry tons of ore were shipped containing an average of 1.47 ounces of silver and 0.0072 ounce of gold per ton and of 2.431 per cent of copper, and from the Main Range mine 10,774 dry tons were shipped, averaging 9.42 ounces of

[1] North Butte Mining Co Ann. Rept. for year ending Dec. 31, 1917.
[2] East Butte Copper Mining Co. Ann. Rept. for year ending Dec. 31, 1917.
[3] Toulumne Copper Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

silver and 0.0078 ounce of gold to the ton and 1.972 per cent of copper. Production of ore in the Tuolumne mine came principally from the 1,200, 1,400, and 2,600 foot levels, and in the Main Range from the 700-foot level. The company report says:

During the month of April it became necessary to suspend operations due to fire in an adjoining mine which filled the Tuolumne workings with gas and seriously threatened the property. Operations were resumed about June 1, and on June 9 another serious fire in a neighboring property necessitated a second suspension. The labor disturbances during the months of June, July, August, and September interrupted operations to a considerable extent and lowered production.

On account of the constantly increasing cost of production it was deemed advisable to suspend operations at the Tuolumne mine on January 1, 1918.

In 1917 the Butte & Superior mine[1] produced 461,953 tons of milling ore, this being a little less than 75 per cent of that milled in 1916. The mill recoveries averaged 91.13 per cent of the zinc content. Mining costs were 65 cents greater, or $5.15 a ton in 1917, and the direct cost of milling the ore was $2.52 a ton. Dividends paid in 1917 amounted to $1,567,057, and capital distribution was $362,747, which, added to the total paid by the company in the past, makes $16,940,257.88, or at the rate of $59.65 per share. The company report says:

On account of the labor troubles which developed in June, and the resultant discontinuance for a time and curtailment thereafter of production from the property, it was considered unnecessary to hoist any ore through the new shafts, although the two new electric hoists were installed and in satisfactory operating condition about the middle of the year.

The No. 3, or new ore shaft, was sunk to a depth of 119 feet below the 1,900-foot level and will be continued to a point 50 feet below the 2,050-foot level, at which depth it will be discontinued for the present and a station cut at the 1,900-foot level. * * *

On practically all of the levels of the mine there was shown by development work a very satisfactory extension of existing ore bodies. Above the 1,200-foot level there was added to ore reserves a total of 111,100 tons, leaving almost as much ore in sight above this level as was included in the records of a year ago and extending the future life of these levels accordingly. A considerable portion of this ore of rather high grade was developed in the Jersey Blue vein and a substantial tonnage of medium or low-grade ore in the Overman claim, where between the 1,000 and 1,300 foot levels there was mined a large tonnage of ore of rather low grade but commercially profitable under conditions existing, especially during the early part of the year. * * * On the 1,400-foot level good ore has been disclosed for a distance of approximately 200 feet in the Deadwood vein, and stoping operations have been commenced. Developments to date on the 1,900-foot level amount to only about 200 feet in length on the vein, this disclosing ore of a fair grade, such as was indicated by the workings immediately above on the 1,800-foot level. * * *

Estimate of ore reserves as of December 31 shows 1,059,200 tons, averaging 17.6 per cent zinc and containing 5.9 ounces of silver per ton. * * *

During the early part of the year approximately 6,140 tons of concentrates were shipped to the plants of the American Zinc, Lead & Smelting Co., and 2,658 tons to the United States Smelting Co., practically all of the balance during that period going to the American Metal Co. under regular contract. Subsequent to February all of the production of concentrates, with the exception of a few thousand tons disposed of by sale to other smelters, was shipped to the American Metal Co.

All residues were disposed of, about 6,900 tons remaining on hand at the plants of the American Zinc, Lead & Smelting Co. being sold for delivery during the first five months of the year 1918. Unsold spelter to the amount of 3,081 tons remained on hand at the plants of the American Zinc, Lead & Smelting Co. and the United States Smelting Co.

[1] Butte & Superior Mining Co. Sixth Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

Crude ore treated and concentrates produced at Butte-Superior mill in 1917.

Ore and product.	Quantity (tons).	Gold.		Silver.	
		Total content.	Average per ton.	Total content.	Average per ton.
		Ounces.	*Per cent.*	*Ounces.*	*Per cent.*
Crude ore, milled	461,953	4,196.128	0.00908	2,679,462.39	5.8003
Zinc concentrate	[a] 138,661	3,842.391	.0277	2,472,985.40	17.8348
Lead concentrate	2,543	75,921	.0296	54,316.82	21.3620

Ore and product.	Copper.		Lead.		Zinc.	
	Total content.	Average per ton.	Total content.	Average per ton.	Total content.	Average per ton.
	Pounds.	*Per cent.*	*Pounds.*	*Per cent.*	*Pounds.*	*Per cent.*
Crude ore, milled	1,586,302	0.1717	10,082,584	1.0913	142,920,807	15.4692
Zinc concentrate	1,304,739	.4705	9,289,683	3.3498	131,337,299	47.3636
Lead concentrate	14,831	.2917	1,808,368	35.5600	699,436	13.7540

[a] Includes concentrates from tailing re-treated.

During 1917 the Emma mine[1] produced 42,248.46 tons of zinc ore, which was treated under contract at the zinc concentrator of the Washoe plant near Anaconda, and the zinc concentrate was shipped and treated by the electrolytic zinc plant at Great Falls. Advantage was taken of the prevailing high prices paid for manganese ore, and toward the end of 1917 test shipments of rhodochrosite, or carbonate of manganese, which has been developed in comparatively large bodies in this mine, were made to eastern steel plants. The results were satisfactory, and this ore, heretofore considered valueless, promises to become the source of income during 1918.

[1] Under lease from the Butte Copper & Zinc Co.; mentioned in Anaconda Copper Mining Co. Ann. Rept. for year ending Dec. 31, 1917, p. 7.

Digitized by Google

QUICKSILVER.

By F. L. RANSOME.

STATISTICAL SUMMARY.

Quicksilver produced in the United States in 1917.

State.	Ore treated (short tons).	Percentage tenor won.	Flasks of 75 pounds.	Value.
California	235,786	0.38	23,938	$2,521,151
Texas	28,242	1.42	10,791	1,136,508
Nevada	3,639	1.02	997	105,004
Oregon	12,732	a.11	388	40,864
Arizona	79	1.90	40	4,213
Idaho	6	3.12	5	526
	280,484	.48	36,159	3,808,266

a Abnormally low, owing to accumulation of unworked soot.

Average price per flask:	
San Francisco	$105.32
New York	$106.30
London	£22 5s. 3d.
Total number of mines producing	51
Total increase of production in 1917 over 1916 ....flasks..	6,227
Total exports from United States .....pounds..	808,336
Total imports into United States .....do....	390,494

INTRODUCTION.

That there was unusual activity in quicksilver mining in the United States in 1917 is shown by the fact that the production rose to 36,159 flasks, a quantity that has not been reached since 1883. The increased output, however, was obtained almost wholly from mines that had been productive in preceding years and not from newly discovered deposits. The high price of quicksilver has not led to as much prospecting, either of new territory or in well-known quicksilver districts, as might have been expected, and at comparatively few places have energetic efforts been made to reopen old mines that were abandoned when prices were from one-third to one-half of those that have prevailed during the past three years. Known resources of ore have been drawn upon heavily in order to take advantage of a good market, but less attention has been given to mine development and to the search for new ore bodies than is requisite if production is to increase or even if it is to be maintained at its present level. The war has not only increased greatly the demands for quicksilver to be used in fulminate, drugs, and marine paint but it has brought about some new and important applications that can not at present be described. Although it is a difficult matter to estimate with accuracy the quantities of quicksilver that are consumed annually in the manufacturing industries of the country, such estimates as have been

Digitized by Google

made indicate that the output for 1917, and so far as can be foreseen the output for 1918, will have to be considerably surpassed if all demands for the metal, including those of the Government, are to be met from domestic sources in 1919. There is every reason to expect that prices will continue high during that year and that some new uses discovered for quicksilver will persist and even increase after peace is declared. The metal is not likely to fall to its prewar price for some years, if at all, and it would seem that both patriotism and self-interest should induce those owning idle mines in which there may still remain bodies of ore, or from which additional exploration might be carried out with no more than the usual chances inseparable from quicksilver mining, to use every effort to place them again in the productive class. The apparent success of the rotary furnace in California and the substitution of wooden for brick condensers promise to be important steps toward lessening the initial cost of equipping a quicksilver mine and in diminishing the amount of capital hitherto locked up in immobile, unsalable brick structures capable of absorbing and retaining thousands of dollars' worth of quicksilver.

It will probably be noted that the present report is longer than its immediate predecessors, owing chiefly to the inclusion of a general review of the more important quicksilver deposits of the world, a section on the mineralogy of quicksilver ores, and an extensive bibliography. It is not intended to repeat these features annually, but the present interest in quicksilver as one of the necessities of modern warfare, not only as a potent means of destruction but also as an essential ingredient of preservative and medicinal compounds, renders this a particularly appropriate time to put into practice the Survey's policy of presenting an occasional summary of more general information concerning the metal than would be comprised in a purely statistical investigation. It is hoped that, with prompt returns from the producers, the briefer reports planned for the next few years may each appear within a very few months after the end of the year to which it pertains.

To Mr. H. D. McCaskey, author of the Survey's statistical reports on quicksilver from 1907 to 1916, and still in charge of the Division of Mineral Resources, I am deeply indebted not only for material turned over to me for use in this report but for friendly advice and suggestions drawn from his long familiarity with the quicksilver industry that have been most helpful to one taking up the statistical phase of the subject for the first time. Special acknowledgments are due also to the quicksilver-mine operators, with most of whom I have been so fortunate as to come into enjoyable personal contact, for their courteous considerations and for the public spirit and patience with which they have responded to inquiries. As a class their patriotism and their frankness in supplying information are unquestionable, and this attitude has been an inspiring feature of the work upon which the present report is based. Finally, attention may appropriately be called to the very careful and painstaking work of Miss I. P. Evans in the preparation of the bibliography appended to the report, which, it is hoped, will be of assistance to those desiring to turn to original sources of information on quicksilver in North America.

Digitized by Google

PRODUCTION.

DOMESTIC.

Including some small prospects that yielded only a flask or two from development work, there were 51 productive quicksilver mines in the United States in 1917, against 66 in 1916 and 39 in 1915. This number includes four sources of metal entirely from old dumps and at least two important mines at which dumps and ground under old reduction works contributed a large part of the total output. Of the productive mines, 34 were in California, 8 in Nevada, 4 in Texas, 2 in Oregon, 2 in Arizona, and 1 in Idaho.

According to confidential returns to the Geological Survey from individual mine operators, the output of quicksilver in the United States in 1917 was 36,159 flasks of 75 pounds each, against 29,932 flasks in 1916 and 21,033 flasks in 1915. This production was the greatest in quantity since 1883, when the output was 46,725 flasks. The notable increase of production during the last three years, while it shows that the industry has been capable of reaction under the stimulus of prevailing prices, can not in itself be accepted as an earnest of continued improvement at a similar rate. The prices obtainable for quicksilver have led to considerable activity in prospecting and to development on a small scale, but only in rare instances have they induced large expenditure in development or equipment with a view to long-continued production. There



FIGURE 3.—Diagram showing quantity and value of quicksilver produced in the United States from 1850 to 1917, inclusive.

Digitized by Google

has been a tendency to exhaust known reserves and enlarge old stopes and to neglect the systematic search for new ore bodies, which is so necessary if a mine is to maintain its productivity. In other words, the effort during the last two or three years has had much of the character of a spurt that can not be indefinitely maintained. The failure, except in one or two instances, of high prices to revive extensive operations at mines once productive but long idle has been distinctly disappointing to those interested in the growth of the quicksilver industry. The known facts indicate that the output for 1918 is not likely to reach 36,000 flasks.

At the average price for the year, $105.32 a flask, based on quotations for domestic quicksilver in San Francisco, published weekly in the Mining and Scientific Press, the value of the output in 1917 was $3,808,266, a sum exceeded only in the year 1875, when the value of the output was $4,228,538. The producers of 33,529 out of the total 36,159 flasks stated on their statistical returns the prices received for their product. These averaged $104.23 a flask, or $1.09 less than the average quotation in San Francisco.

Compared with 1916, the quicksilver yield for 1917 shows an increase of 21 per cent in quantity but of only about 1 per cent in value.

The production of California increased 14 per cent in quantity but decreased 5 per cent in value in 1917 as compared with 1916.

Quicksilver produced in the United States, 1913–1917, in flasks of 75 pounds.

State.	1913		1914		1915		1916		1917	
	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.
Arizona	2,977	$119,765	3,156	$154,801	4,423	$379,493	5	$629	40	$4,213
Oregon [a]							[b] 378	47,587	388	40,864
Texas							6,306	793,862	10,791	1,136,506
California	15,591	627,228	11,303	554,414	14,283	1,225,481	21,045	2,649,355	23,938	2,521,151
Nevada	1,645	66,178	2,089	102,465	2,327	199,657	2,198	276,706	997	105,004
Idaho									5	526
	20,213	813,171	16,548	811,680	21,033	1,804,631	29,932	3,768,139	36,159	3,808,266

[a] Oregon had no output in 1913 and 1914. [b] Includes 75 flasks from Washington.

The following table gives the quantity, average price, and value of the quicksilver produced annually in the United States from the year 1850. Up to 1882 this table is identical with that on page 406, which shows the production of California:

Digitized by Google

Quicksilver produced in the United States, 1850–1917.

[In flasks of 76.5 pounds to June, 1904; subsequently in flasks of 75 pounds.]

Year.	Flasks.	Price per flask.	Value.	Year.	Flasks.	Price per flask.	Value.
1850	7,723	$99.45	$768,052	1885	32,073	$30.75	$986,245
1851	27,779	66.93	1,859,248	1886	29,981	35.50	1,064,325
1852	20,000	58.33	1,166,600	1887	33,825	42.375	1,433,334
1853	22,284	55.45	1,235,648	1888	33,250	42.50	1,370,625
1854	30,004	55.45	1,663,722	1889	26,484	45.00	1,191,780
1855	33,000	53.55	1,767,150	1890	22,926	52.50	1,203,615
1856	30,000	51.65	1,549,500	1891	22,904	45.25	1,036,406
1857	28,204	48.73	1,374,381	1892	27,993	40.71	1,139,595
1858	31,000	47.83	1,482,730	1893	30,164	36.75	1,108,527
1859	13,000	63.13	820,690	1894	30,416	30.70	933,771
1860	10,000	53.55	535,500	1895	36,067	37.04	1,335,922
1861	35,000	42.05	1,471,750	1896	30,765	34.96	1,075,544
1862	42,000	36.35	1,526,700	1897	26,691	37.28	995,040
1863	40,531	42.08	1,705,544	1898	31,092	38.23	1,188,647
1864	47,489	45.90	2,179,745	1899	30,454	47.70	1,452,656
1865	53,000	45.90	2,432,700	1900	28,317	44.94	1,272,566
1866	46,550	53.13	2,473,202	1901	29,727	48.46	1,440,570
1867	47,000	45.90	2,157,300	1902	34,291	43.20	1,481,371
1868	47,728	45.90	2,190,715	1903	35,634	45.29	1,613,864
1869	33,811	45.90	1,551,925	1904	35,315	43.50	1,536,203
1870	30,077	57.38	1,725,818	1905	30,534	36.22	1,105,941
1871	31,686	63.10	1,999,387	1906	26,063	39.50	1,030,279
1872	31,621	65.93	2,084,773	1907	21,564	39.60	853,538
1873	27,642	80.33	2,220,482	1908	19,752	44.17	872,446
1874	27,756	105.18	2,919,376	1909	21,075	45.45	957,859
1875	50,250	84.15	4,228,538	1910	20,601	46.51	958,153
1876	72,716	44.00	3,199,504	1911	21,256	46.01	977,989
1877	79,395	37.30	2,961,434	1912	25,064	42.05	1,053,941
1878	63,880	32.90	2,101,652	1913	20,213	40.23	813,171
1879	73,684	29.85	2,199,467	1914	16,548	49.05	811,680
1880	59,926	31.00	1,857,706	1915	21,033	85.80	1,804,631
1881	60,851	29.83	1,815,185	1916	29,932	125.89	3,768,139
1882	52,732	28.23	1,488,624	1917	36,159	105.32	3,808,266
1883	46,725	28.75	1,343,344				
1884	31,913	30.50	973,347		2,305,130	.....	108,708,078

The quantity and value of the quicksilver produced annually in the United States are also shown graphically in figure 3.

WORLD'S PRODUCTION.

In the following table are given the best figures available for the world's production of quicksilver in recent years. The foreign figures, generally published in metric tons, are calculated to flasks of 75 pounds net by multiplying by the factor 29.395. As far as possible the figures are taken from official statistical publications of the respective countries. Where no trustworthy data are obtainable the output is estimated on such miscellaneous information as could be collected. This expedient unfortunately has been necessary in the case of Austria and Hungary, for which no statistics have been obtainable since the outbreak of the war. The estimate of production for "Mexico and other countries" is admittedly based upon very meager data. The figures given for the years 1908 to 1915 in earlier reports have been thoroughly revised and Government sources substituted, where possible, for unofficial publications previously cited.

Digitized by Google

World's production of quicksilver, 1908–1917, in flasks of 75 pounds.

[1 metric ton=29.395 flasks.]

Country.	1908	1909	1910	1911	1912	1913	1914	1915	1916	1917
United States	19,752	21,075	20,601	21,256	25,064	20,213	16,548	21,033	29,932	36,159
Austria	[a] 16,814	[a] 17,196	[a] 17,725	[a] 20,694	[a] 22,428	[a] 24,104	[b] 25,000	[b] 25,000	[b] 25,000	[b] 25,000
Hungary	[c] 2,289	[c] 2,098	[c] 2,641	[c] 2,339	[c] 2,494	[c] 2,606	[b] 2,500	[c] 2,500	[b] 2,500	[b] 2,500
Italy	[d] 20,106	[d] 22,668	[d] 26,264	[d] 28,072	[d] 29,406	[d] 29,513	[d] 31,541	[d] 28,954	[e] 32,129	[f] 29,300
Russia	[g] 1,389	[h] 206	[h] 118	.....	.....	.....	.....	[i] 800	[i] 1,100	[b] 500
Spain	[f] 31,382	[f] 40,933	[f] 32,892	[f] 43,912	[f] 36,921	[f] 36,619	[f] 28,000	[f] 35,925	[f] 23,369	[f] 25,133
Mexico and other countries	[b] 5,880	[b] 4,500	[b] 4,500	[b] 4,500	[b] 4,500	[b] 4,000	[b] 4,000	[b] 4,000	[b] 4,000	[b] 4,000
	97,612	108,676	104,741	120,773	120,813	117,055	107,589	118,212	118,030	122,592

[a] Statistik des Bergbaues in Österreich, Wien.
[b] Statistics not available. Estimate only.
[c] Ungar. statist. Jahrb., Budapest.
[d] Riv. servizio min., Roma.
[e] Min. Jour., London.
[f] Eng. and Min. Jour., Feb. 16, 1918 ("nearly 1,000 tonnes").
[g] Statistics of the mineral industry of Russia, Petrograd.
[h] Metallgesellschaft, Frankfurt-am-Main.
[i] Statistics not available. Estimate based on oral information from Russian Special Commission to United States in 1917.
[j] Estadística minera de España, Madrid.

QUANTITY AND TENOR OF ORE TREATED.

According to reports from producers there was mined in 1917 about 289,400 short tons of ore, inclusive, however, of considerable material, not separately reported by the mine operators, obtained from dumps and from the wrecking of old furnaces and condensers. There was treated in furnaces 264,691 short tons of ore (including some concentrates), which yielded 32,956 flasks of quicksilver. This is at the rate of 0.46 per cent, or 9.2 pounds of quicksilver to the ton of ore. There was treated in retorts 7,107 tons of ore, which yielded 2,320 flasks. This is at the rate of 1.22 per cent, or 24.4 pounds to the ton. In addition there was retorted about 900 tons of concentrates from old dumps, which yielded 548 flasks. The greater part of this material came from the extensive dumps at Sulphur Bank, Cal. There was also passed through a washer 7,786 tons of earth from the sites of old furnaces, which yielded 335 flasks of quicksilver without further metallurgical treatment.

Quicksilver ore treated and metal won in the United States, 1914–1917.

State.	1914			1915			1916			1917		
	Ore treated (short tons).	Metal won (pounds per ton).	Percentage tenor won.	Ore treated (short tons).	Metal won (pounds per ton).	Percentage tenor won.	Ore treated (short tons).	Metal won (pounds per ton).	Percentage tenor won.	Ore treated (short tons).	Metal won (pounds per ton).	Percentage tenor won.
Arizona							2	.....	.....	79	38.0	1.90
Oregon [a]	7,334	32.3	1.62	7,321	45.3	2.27	[b] 5,802	4.8	0.24	12,732	[c] 2.3	[c].11
Texas							25,945	18.2	.91	28,242	28.4	1.42
California	101,553	8.3	.42	129,521	8.3	.41	205,072	7.6	.38	235,786	7.6	.38
Nevada	14,111	11.1	.56	21,975	7.9	.40	12,911	12.6	.63	3,639	20.4	1.02
Idaho	.....	.....	.....	.....	.....	.....	.....	.....	.....	6	62.4	3.12
	122,998	10.1	.50	158,817	9.9	.50	249,732	9.0	.45	280,484	9.6	.48

[a] Oregon had no output in 1914.
[b] Includes 47 tons from Washington.
[c] These figures abnormally low, owing to accumulation of unworked soot.

Digitized by Google

The table below shows the relative importance of furnaces and retorts in the production of domestic quicksilver. The furnaces are preponderantly fine-ore inclined-tile furnaces of the Hüttner-Scott type, but include some coarse-ore shaft furnaces of simple construction and a few exceptional models. The retorts are chiefly of the cylindrical pipe form, usually arranged in "banks" or "benches" of 12 retorts, but include also a number of the D pattern and a few unusual varieties.

Quicksilver ore treated in furnaces and in retorts in 1917.

State.	Ore treated (short tons).		Quicksilver won (flasks).		Percentage tenor won.	
	Furnaces.	Retorts.	Furnaces.	Retorts.	Furnaces.	Retorts.
California [a]	223,069	[b] 4,931	21,780	1,823	0.37	1.44
Texas	26,802	1,440	10,530	261	1.47	.68
Other States [c]	14,820	1,641	646	784	.16	1.79
	264,691	8,012	32,956	2,868	.46	1.34

[a] This table does not include 7,786 tons of material taken from under old reduction works, which yielded 335 flasks of quicksilver by washing.
[b] Includes the Sulphur Bank product as concentrates, not as the crude dump material sent through the mill.
[c] Includes Arizona, Nevada, Oregon, and Idaho.

METHODS OF TREATMENT.

The metallurgy of quicksilver is now being studied for the United States Bureau of Mines by Dr. L. H. Duschak, superintendent of the Bureau's station at Berkeley, and will probably be discussed also in a bulletin on quicksilver in California prepared for the California State Mining Bureau by Walter W. Bradley and now in press. It is not the purpose of the present report to treat extensively of the metallurgical side of the industry but merely to give to the reader a brief outline of the ways in which quicksilver is being obtained from its ores. Those who wish to pursue the subject further may profitably consult the full bibliography prepared by Miss Evans and appended to this report.

The ores of quicksilver, unlike those of most metals that are won by smelting, are without exception in this country treated at the mines, and the liquid metal is shipped as a finished commercial product. A moderate heat, about 360° C., is sufficient to vaporize and decompose cinnabar, and metallic quicksilver is readily obtained by condensation. In outline the process is exceedingly simple, but in practice it is by no means easy so to control the operation as to obtain practically all of the metal from the ore with the minimum expenditure of labor and fuel.

In general, two classes of reducing plants may be distinguished, namely, furnaces and retorts. In the furnaces, with the exception of the Fitzgerald furnace and the Livingston retort furnace, which are little used, the ore is exposed to the direct action of the flame and the volatile products of combustion, with more or less dust, as well as the mercury vapor, are drawn into the condensing chambers. In retorts, on the other hand, the ore is heated in a closed vessel, out of contact with the flame, and only those volatile constituents that are

Digitized by Google

driven off from the charge pass into the condensers. Furnaces are comparatively expensive but have greater capacity than retorts, cost much less to operate per ton of ore, and, for ores of medium and low grade, are more efficient. Retorts, on the other hand, are comparatively cheap and can be successfully employed in treating small bodies of rich ore, although their use is attended with the ever-present danger of salivation or mercurial poisoning. The relative importance of the two classes of reduction plants may be seen from the table on page 373.

The standard furnace in the United States is the Hüttner-Scott, or, as it is commonly called, the Scott furnace. This is a masonry structure of rectangular shaft form and requires special skill in its construction. The ore is fed at the top and falls over a series of alternating or "staggered" fire-brick shelves inclined at 45°. The rate of passage through the furnace is controlled by drawing off portions of the spent charges at regular intervals from the bottom of the shaft, and the burning is continuous. The flames pass back and forth through the flues formed by the spaces that the ore does not fill under the sloping shelves. The shelves are arranged in one to five vertical compartments, according to the size of the furnace. The fuel is wood or oil and is burned in one or more fire boxes, not mixed with the ore.

At the Oceanic mine in California, where Scott furnaces are successfully used on ore yielding 3.7 pounds of quicksilver to the ton of ore, the consumption of wood is 0.031 cord to the ton. Scott furnaces usually range in capacity from 10 to 80 tons of ore for each 24 hours and, when skillfully handled, are very efficient. They are, however, expensive to build, difficult to repair, rather slow in action, absorb considerable quicksilver, and can not be moved.

These disadvantages, which apply in some degree also to other masonry furnaces, have led to attempts to utilize the tubular, rotating cement kiln as a quicksilver furnace. Recently Mr. H. W. Gould, general superintendent of the New Idria and Sulphur Bank mines in California, undeterred by the unsuccessful attempts of others to adapt these furnaces to the metallurgy of quicksilver, has installed them at Idria and Sulphur Bank. He reports as follows concerning their operation:

> These furnaces as applied to quicksilver reduction are an adaptation of the rotary furnace in general use for cement burning, with such modifications in design and operation as are necessary and with provision made for taking the fumes from the furnace to a suitable condensing system.
>
> The first furnace installed was a tube, 48 inches in diameter by 50 feet in length, made of ⅜-inch boiler plate, with a lining 4 inches thick of segmental fire brick. It is mounted on two sets of riding rings and trunnions, on which it revolves, and is driven through gears at a speed of from one-half to four revolutions per minute. The ore is fed from the ore bin by a crawl feeder to a screw conveyer, which carries the ore through a brick dust chamber and drops it on the floor of the furnace. As the tube has an inclination of one-half inch to the foot, the ore moves down from the feed end to the discharge end as the tube revolves.
>
> The furnaces are fired by oil sprayed directly into the tube, through the discharge end, or by wood burned in a fire box leading into the tube. Rub joints at each end of the tube prevent fume leakage. The fumes are led from the dust chamber through vitrified earthenware pipes 12 to 24 inches in diameter, into which cold air and some water are introduced as a spray under high pressure. From the pipes the vapors and fumes are conducted into large cylindrical wooden tanks from which the uncondensed fumes pass out to a stack.

Digitized by Google

Furnaces have been made in the following sizes:

One 36-inch by 38-foot; capacity 10 to 30 tons.
Three 48-inch by 50 or 56 foot; capacity 40 to 100 tons.
Four 60-inch by 56-foot; capacity 75 to 150 tons.

Some of these are now in operation, and all will be within the next 60 days.

The capacity of the furnace depends upon the character of the ore and the fuel used. Oil fuel is preferable to wood. The larger furnaces are economically more efficient than the smaller ones.

The first furnace erected was a 48-inch by 50-foot tube at Idria. It was placed in use about March 1, 1918, and has been in continuous successful operation since. A few modifications have been made in subsequent installations but no radical changes.

The rotary furnace appears to have the following advantages: Low cost of installation; low fuel consumption per ton of ore roasted; great flexibility in operation, as it can be fired up in a short time and closed down instantly; better metallurgical practice, as it almost eliminates absorption losses; decreased labor costs, as both the charging and drawing are automatic; availability for burning very fine ore or dust if necessary; last, but not least, absence of the possibility of mercurial poisoning or salivation of workmen.[1]

At the Goldbanks mine in Nevada and at the El Senador mine of the New Almaden Co. in California furnaces of the Herreshoff type, with revolving rabbles, have been used for quicksilver ore. Their efficiency for this purpose, however, does not appear to have been fully established.

The condensing systems used with quicksilver furnaces vary greatly, and at no two mines are they identical. The standard, until recently, was a series of rectangular brick chambers, with small holes and a trough along one side at the base to conduct the quicksilver to a collecting reservoir. Present practice in California tends to rectangular chambers or cylindrical tanks of redwood lumber. These cost less than brickwork, have better radiation, are easier to clean, and absorb less mercury. At some mines condensers of vitrified earthenware pipe are successfully employed.

As a rule a considerable part of the quicksilver retained in furnace condensers is in the form known as "soot," a dark-gray to black material containing metallic mercury mixed with exceedingly fine solid particles of various materials including ore dust and unconsumed hydrocarbons. The proportion of soot to free quicksilver varies widely with the character of the ore and the operation of the furnace. In one or two mines practically all of the product is in the undesirable form of soot. A large part of the quicksilver is extracted from the soot by kneading the mass with hoes on iron plates or with a machine for the purpose, when the metal runs out. The residual mass is then recharged into the furnace, or, more commonly, treated in retorts.

As the Johnson-McKay type of retort is so largely used in development of prospects, the following data from a letter to the Survey from the Joshua Hendy Iron Works, San Francisco, makers of this retort, are given as of general interest to the industry:

The Johnson & McKay quicksilver furnace consists of a series of retort pipes set up in brickwork, complete with covers, condenser pipes, etc. The retort pipes are furnished either 10-inch or 12-inch diameter, the larger size being preferable. The usual furnace consists of a battery of twelve 12-inch pipes, but a less number of pipes may be installed, if desired.

With a 12-pipe retort, where the duration of the roasting period for each charge of ore would take 12 hours, the operation of this furnace is continuous, in that one pipe is unloaded and recharged with ore every hour. When the

[1] Letter dated Aug. 22, 1918.

Digitized by Google

pipes are sufficiently heated they are successively charged with ore at hourly intervals, so that at the end of 12 hours the charge in the first pipe will have roasted for that length of time, and the last pipe will have been charged. The first pipe is then ready for unloading and recharging. At the end of the next hour the second pipe is unloaded and recharged, and this operation is continued indefinitely. This cycle of operation is based, however, on a 12-hour roasting period for each charge of ore; but that the length of the roasting period may vary is obvious, this being dependent on the character of the ore, the intensity of heat maintained in the furnace, the experience of the attendant, etc.

It will be understood also that the capacity of these furnaces varies. We will say, however, that the capacity of a twelve 12-inch pipe retort is usually rated at 5 tons per 24 hours, but some users of this same size of furnace have reported a daily capacity of 7 tons. Using wood for fuel, the consumption is about 1¼ to 1½ cords per day.

Concentration by the ordinary wet gravity methods has not proved generally successful with quicksilver ores in competition with the low cost and high efficiency of furnace reduction. The only mill in operation on quicksilver ore throughout 1917 was at New Idria, Cal., and this was continued in use only because the ratio of fine ore to coarse ore exceeded the limit set by the furnace capacity of the plant. In the later part of the year there was also in operation the 400-ton mill at Sulphur Bank, treating dump material, but this will probably be abandoned also when adequate furnaces have been constructed. There were also running for part of the year the 100-ton mill at the January (Harrison) mine and a small mill, since abandoned, at the Bella Union mine. At the Black Butte mine, Oreg., an experimental flotation mill was operated for part of the year and proved so successful that a 40-ton mill was equipped for flotation early in 1918.

COSTS.

The question, "How much does it cost to produce a flask of quicksilver?" has been frequently asked of late and is not easily answered. So many factors enter into the problem that it is difficult, as regards relative efficiency, to arrive at a satisfactory basis of comparison between mine and mine or between one region and another. Under otherwise identical conditions it costs very little more to produce 2 flasks from 2 per cent ore than to produce 1 flask from 1 per cent ore, as in each case the same quantity of ore is mined and treated. Practically the only increased cost in connection with the higher-grade ore is the small one involved in bottling, transporting, and selling the larger output. Conditions, however, are never identical. The higher-grade ore may be less favorably situated, may require more expensive mining, or may demand more careful sorting than the lower-grade ore, and these disadvantages may offset the initial advantage of higher tenor. In many mines the tenor of the ore as mined is, within certain limits, under the control of the operator, who faces the problem of determining the particular relation between quantity of ore mined, tenor, labor, equipment, and capital that will yield him the most profit. With ores which yielded an average of only 0.38 per cent of quicksilver, the average cost, inclusive of operating expenses, development work, and ordinary amortization charges, of producing and selling a flask of the metal in California in 1917 was from $65 to $70. The cost in Texas is undoubtedly higher on ore of the same grade, but Texas ores in 1917 showed

Digitized by Google

the relatively high average tenor of 1.43 per cent.

An attempt has been made to determine the approximate number of flasks produced annually per man employed and the quantity of quicksilver corresponding to each man-day of labor in the two principal quicksilver States. Reliable and complete figures on the average number of men employed and the total number of man-days of work in each State are not available, however, and recourse must be had in part to estimates. Consequently, the figures that follow can be regarded only as rough approximations.

It is estimated that in California in 1917 about 950 men were employed in the mining and metallurgy of quicksilver and that these worked 310,500 man-days. There was treated in the same year in that State 235,786 short tons of ore, which yielded 23,938 flasks of quicksilver, or 0.38 per cent. This corresponds to 248.1 tons handled and 25.1 flasks produced per man annually, or 0.75 ton and 0.077 flask per man-day.

In comparing 8 of the most productive and representative mines at which furnaces were used in California, it is found that in 1917 they treated 203,449 tons of ore, from which were obtained 18,581 flasks of quicksilver. The proportion of quicksilver won from the ore in these eight mines ranged from 0.17 to 1.08 per cent, and the



FIGURE 4.—Diagram showing variations of monthly average market quotations for domestic quicksilver at San Francisco from 1913 to 1917, inclusive.

Digitized by Google

average was 0.336 per cent. As nearly as can be determined these mines employed an average of 715 men, who worked, it is estimated, 233,689 man-days. The quantity of treated ore handled per man during the year ranged from 119.1 to 624.4 short tons at the different mines and averaged for all of them 322.8 tons. The quantity handled per man-day ranged from 0.365 to 1.905 tons, and averaged 0.987 ton. The number of flasks obtained per man for the year ranged from 16.3 to 34.4 and averaged 26. The number of flasks per man-day ranged from 0.050 to 0.105 and averaged 0.079.

A comparison of three mines at which furnace reduction was practiced in Texas in 1917 shows that these mines treated 26,802 tons of ore, from which were won 10,530 flasks of quicksilver. The proportion of metal obtained ranged from 0.55 to 3.88 per cent, and the average was 1.47 per cent. The three mines employed an average of 253 men, who worked 84,795 man-days. The quantity of treated ore handled per man during the year ranged from 73 to 140.2 tons and averaged 105.9 tons. The quantity handled per man-day ranged from 0.233 to 0.384 ton and averaged 0.316 ton. The number of flasks obtained per man for the year ranged from 12.3 to 84.1 and averaged 41.6. The number of flasks per man-day ranged from 0.039 to 0.271 and averaged 0.124.

The data just presented for California and Texas are summarized in the following table, which, owing to the uncertainty attaching to the labor figures, especially to those for man-days, is presented merely as a rough approximation to the truth.

Relations of quicksilver production to labor in California and Texas.

State.	Ore treated (short tons).	Quicksilver produced (flasks).	Tenor won.	Average number of men employed.	Man-days of work.	Quantity of ore treated per man (short tons).	Quantity of ore treated per man-days (short tons).	Quicksilver obtained per man annually (flasks).	Quicksilver obtained per man-day (flasks).
California:									
All mines	235,786	23,938	0.38	950	310,500	248.1	0.75	25.1	0.077
Eight leading mines	203,449	18,581	.34	715	233,689	322.8	.99	26.0	.079
Texas:									
Three mines	26,802	10,530	1.47	253	84,795	105.9	.32	41.6	.124

Foreign costs are particularly difficult to ascertain under present conditions. Prior to the war the cost of producing a flask of quicksilver from the rich ore at Almaden, Spain, which in 1915 yielded an average of 9.04 per cent of quicksilver, was about $12. This at first glance seems very low but is not at all extraordinary when it is considered that this ore is more than twenty-three times as rich as the average ore treated in California and that consequently a flask of quicksilver can be obtained with less than one-twentieth of the labor necessary in that State and with that labor paid for at much lower wages. At Monte Amiata, in Italy, on ores averaging in 1913 0.89 per cent the cost of producing a flask appears to have been about $30. In that district the annual production of metal per man in that year is given as 40.5 flasks for the Abbadia San Salvatore mine and 23.6 flasks for the district as a whole. At Idria, in Austria, the cost, prior to the war, on ore averaging 0.65 per cent, was about $23 a flask.

Digitized by Google

PRICES.

The domestic price of quicksilver remained high enough throughout 1917, owing chiefly to the demand for war uses, to offer considerable profit to those operators fortunate enough to be in ore and to have the equipment for mining and reducing it. The highest price reached in San Francisco was $140 a flask during the latter part of February, and the lowest quotation in the same market was $80 in January. The price of $105 a flask fixed for Government purchases at the Mare Island Navy Yard, Cal., or of $105.75 in New York, became effective at the beginning of April. About 40 per cent of the output of the principal mines was requisitioned at this price, and this action, although it has not directly interfered with the movement of prices in the open market, has doubtless tended to stabilize them.

The prices given in the following table for the United States and the United Kingdom have been obtained by averaging the weekly quotations published in the Mining Journal, for London; the Engineering and Mining Journal, for New York; and the Mining and Scientific Press, for San Francisco, the primary domestic market. As the figures prior to 1913, however, are not complete in the Mining and Scientific Press, they have been taken, for the years 1907–12, inclusive, from the Engineering and Mining Journal. Obviously, the figures given in this table, being annual averages, may differ considerably from the price actually quoted or obtained on a particular date.

Average yearly prices of quicksilver in the United States and the United Kingdom from 1907 to 1917, inclusive.

[Per flask of 75 pounds.]

Year.	San Francisco [a] (domestic).	New York. [b]	London. [c]			Year.	San Francisco [a] (domestic).	New York. [b]	London. [c]		
			£	s.	d.				£	s.	d.
1907	$39.60	$41.50	7	0	6	1913	$40.23	$39.54	7	9	2
1908	44.17	44.84	8	4	8	1914	49.05	48.31	d7	15	0
1909	45.45	46.30	8	12	0	1915	85.80	87.01	14	10	8
1910	46.51	47.06	8	16	0	1916	125.89	125.49	17	2	10
1911	46.01	46.54	8	4	11	1917	105.32	106.30	22	4	3
1912	42.05	42.46	8	2	10						

[a] Min. and Sci. Press, San Francisco.
[b] Eng. and Min. Jour., New York.
[c] Min. Jour. (London).
[d] Metal exchange closed about three months after outbreak of war. Average based on 37 weeks only.

The table below shows average monthly quotations, as published in the Mining and Scientific Press.

Figures 4 and 5 show the variations in prices during the years indicated.

Prices of domestic quicksilver at San Francisco, 1915–17.

[Per flask of 75 pounds.]

Month.	1915	1916	1917	Month.	1915	1916	1917
January	$51.90	$222.00	$81.00	July	$95.00	$81.20	$102.00
February	60.00	295.00	126.25	August	93.75	74.50	115.00
March	78.00	219.00	113.75	September	91.00	75.00	112.00
April	77.50	141.60	114.50	October	92.90	78.20	102.00
May	75.00	90.00	104.00	November	101.50	79.50	102.50
June	90.00	74.70	85.50	December	123.00	80.00	117.42

Digitized by Google



FIGURE 5.—Diagram showing prices of quicksilver in London, New York, and San Francisco in 1917. The Mining Journal, of London, occasionally quotes prices on "Spanish quicksilver." In January and for the first two weeks in February it quoted "Spanish quicksilver" only. In September it gave two quotations on "Spanish quicksilver" in addition to those on "quicksilver." All these quotations are represented in the diagram.

Digitized by Google

Although San Francisco is commonly looked upon as the "primary market" for quicksilver in the United States, from the fact that the greater part of this metal produced in the country comes from the Pacific coast and goes through the hands of San Francisco firms, yet it should be noted that that city is not a market in the same sense as New York. Most of the quicksilver that passes nominally through San Francisco is handled on commission and is sold in New York, which consequently is the great distributing point of quicksilver to the actual consumers.

IMPORTS AND EXPORTS.

The import duty on quicksilver from 1890 to 1895 was 10 cents a pound. From 1895 to 1913 it was 7 cents. The Underwood tariff bill enacted in 1913 and still in force made the duty 10 per cent ad valorem, which at the average price in London for 1917 would be equivalent to an import tax of about 14 cents a pound.

In the following tables[1] are given imports of quicksilver for domestic consumption, total annual exports, and annual exports by countries. In 1917 the imports were less by 33,902 pounds, or about 452 flasks, than in 1916, and the decrease in the total value of the imports was $67,887. The exports increased by 1,898 flasks, with an increase in value of $327,995. About 34.5 per cent of the total exports went to Canada, to be used chiefly in the manufacture of fulminate and glacial acetic acid for war purposes.

Quicksilver imported and entered for consumption in the United States, 1908–1917.

Year.	Quantity (pounds).	Value.	Year.	Quantity (pounds).	Value.
1908	15,113	$8,216	1913	171,653	$75,361
1909	15,968	8,203	1914	614,869	271,984
1910	667	381	1915	421,884	282,752
1911	471,944	251,386	1916	424,396	515,919
1912	82,706	39,920	1917	390,494	448,032

Quicksilver exported from the United States, 1908–1917.

Year.	Quantity (flasks of 75 pounds).	Value.	Year.	Quantity (flasks of 75 pounds).	Value.
1908	2,996	$124,960	1913	1,140	$43,574
1909	6,802	266,243	1914	1,446	70,753
1910	1,923	91,077	1915	3,372	225,509
1911	291	13,995	1916	8,880	670,475
1912	310	13,360	1917	10,778	998,470

[1] Prepared by J. A. Dorsey from records of the Bureau of Foreign and Domestic Commerce, Department of Commerce.

Digitized by Google

Domestic quicksilver exported from the United States, 1916–17, by countries.

Country.	1916		1917	
	Quantity (pounds).	Value.	Quantity (pounds).	Value.
Europe:				
Azores, and Madeira islands			100	$124
Denmark	1,020	$1,595		
England	246,034	216,301	92,314	101,825
France	325	487	9,543	11,040
Netherlands	4,821	5,096	375	400
Norway			9,365	14,993
Russia in Europe	1,512	1,520		
Scotland	15,000	15,300		
Spain	50	34	126	148
Sweden	5,625	7,200		
North America:				
British Honduras	10	48	20	23
Canada	71,759	99,745	279,358	372,759
Mexico	91	159	815	1,059
Newfoundland			175	206
Central America:				
Costa Rica	164	181	292	362
Guatemala	300	420	270	329
Honduras	75	96		
Nicaragua	834	1,298	1,152	1,628
Panama	87	51		
Salvador	75	105	150	265
West Indies:				
British—				
Jamaica			55	69
Cuba	1,422	1,506	1,127	1,287
Dominican Republic	88	90	90	99
Dutch			20	34
French			158	220
South America:				
Argentina	1,636	1,863	1,515	2,397
Brazil	966	872	119	161
Chile	823	1,331	225	329
Colombia	990	1,185	329	406
Ecuador	600	681	675	936
Guiana—				
British			200	230
Dutch	615	630		
French	600	531	3,111	4,521
Peru	2,787	3,933	375	250
Venezuela	2,136	2,364	225	240
Asia:				
China	9,005	9,950		
China, British leased territory			3,750	4,700
Chosen (Korea)	150	150	1,650	2,426
British East Indies			90	100
Dutch East Indies	150	150	1,242	1,288
Hongkong	49,275	55,206	142,850	171,415
Japan	241,025	234,197	178,625	196,952
Russia in Asia	2,700	2,850	5	12
Oceania:				
British—				
Australia	675	635	33,365	42,077
New Zealand			9,525	10,033
Philippines	352	381	455	518
Africa:				
British South Africa	1,050	1,078	34,500	51,600
Portuguese South Africa	1,200	1,256		
	666,027	670,475	808,336	998,470

Manufactured products containing quicksilver imported for consumption in the United States in 1916–17.

	1916		1917	
	Quantity (pounds).	Value.	Quantity (pounds).	Value.
Fulminate:				
For mining				$75,839
For other uses		$229,194		1,848,802
Vermilion reds	58,635	79,411	16,751	24,441
Calomel, corrosive sublimate, and other mercurial chemical preparations		19,874		4,155

Digitized by Google

USES OF QUICKSILVER.

The following are the principal uses of quicksilver under normal conditions, stated in general order of decreasing importance. Quicksilver enters largely into the manufacture of drugs and chemicals, including calomel and corrosive sublimate. Mercuric oxides and mercury salts are also used extensively in the manufacture of certain chemicals, such as glacial acetic acid, phthalic acid, and phthalic anhydride, into which mercury does not itself enter. Mercury fulminate, with the chemical formula $Hg(CNO)_2$, is used as a detonator for high explosives,[1] and to a less extent than formerly in small-arms ammunition. It is made by treating mercury with strong nitric acid and alcohol.

The discovery of mercury fulminate by Howard in 1799 led to the invention of the percussion cap in place of the old flintlock, and fulminate still remains the best-known and most-used detonator for gunpowder and high explosives. It is often combined with other substances, particularly with an abrasive, such as powdered glass, to increase its sensitiveness, and with compounds or mixtures that themselves have the property of detonating, such as sulphide of antimony and chlorate of potassium. Recently a large part of the mercury fulminate in detonators for modern high explosives has been replaced by picric acid, trinitrotoluene, or tetranitromethylamine, whereby a much stronger initial effect is obtained and one part of mercury fulminate is made to detonate a charge that would have required six times as much fulminate used alone. Other substances have been found also which seem likely to replace mercury fulminate entirely for certain uses. One of these is lead azide, a salt of hydronitric acid. Large dry crystals of this salt are so sensitive as to explode when brushed with a feather, but smaller crystals are less sensitive. Other proposed substitutes are lead styphnate, $PbC_6(NO_2)_{12}O_2$; hexamethylamine triperoxidediamine, $(N(CH_2O.OH_2C)_3N)$, said to be four or five times as strong as mercury fulminate; nitrogen tetrasulphide, N_4S_4; diazobenzolnitrate, $C_6H_5N_2(NO_3)$; basic mercury nitromethane; and perchlorate of trimercuraldehyde.[2]

As mercuric sulphide, mercury forms the brilliant red pigment vermilion. The metal is employed extensively in electrical apparatus, including recitifiers for changing alternating into direct current, mercury-vapor lamps,[3] and storage batteries. In the manufacture of felt hats from rabbit's fur, mercuric nitrate is used to roughen the hairs so that they will adhere together, a process technically known as "carroting." Metallic quicksilver is employed in the amalgamation of gold and silver ores, although of late years

[1] Detailed specifications for mercury fulminate for military use have been prepared for the Ordnance Department, U. S. A., by H. C. Pritham, chief chemist, Frankford Arsenal; Dr. C. G. Storm, design section, Ordnance Department; and Capt. Paul McMichael, design section, Ordnance Department.

[2] Most of the statements in this paragraph are taken from a paper by Walter Arthur (Initiation of explosives: Jour. Ind. and Eng. Chemistry, vol. 9, pp. 392–395, 1917). Some of the chemical formulas are too complex to reproduce here.

[3] The light from the mercury-vapor quartz lamp is rich in violet rays, which fact gives the lamp its well-known usefulness in photography. It is also a source of ultra-violet rays, but, as glass is opaque to these rays, the lamp, to be effective, must be inclosed in quartz instead of glass. The ultra-violet rays are destructive to the lower forms of life and advantage is taken of this property by using quartz-inclosed, mercury-vapor lamps to sterilize the water supplied to some of the cities in Europe, particularly Marseille and Luméville in France and Leghorn and Pisa in Italy. A description of the apparatus used and the method followed is given in "Water supply," by W. P. Mason, 4th ed., New York, 1916, pp. 202–206, and in "Water purification plants and their operation," by M. F. Stein, New York, 1916, p. 174. See also Recklinghausen, M. von, Sterilization of water by ultra-violet rays of the mercury-vapor quartz lamp: Am. Inst. Elect. Eng. Proc., vol. 33, pp. 1049–1062, 1914.

Digitized by Google

the wide application of the cyanide process has decreased this use. In the metallic state, also the metal is utilized in the manufacture of instruments, thermostats, gas governors, and other appliances. Mercury enters into the composition of some antifouling marine paints for ship bottoms, a modern and at present a rapidly increasing use. The mercury for this purpose is generally employed as the red mercuric oxide, its efficacy depending upon the gradual conversion of the oxide to the poisonous bichloride by the sodium chloride of salt water. About 12 ounces of mercuric oxide or 11 ounces of metallic mercury is contained in each gallon of paint, which covers 243 square feet. Mercury is also used in certain compounds for preventing boiler scale, in cosmetics, and in dental amalgam. Silver nitrate has to a large extent been substituted for mercury in silvering mirrors. A small quantity of quicksilver, not more than 2 or 3 flasks annually, is used in floating certain types of revolving lights in lighthouses. The quicksilver so used, like that in some instruments and appliances, such as gas governors, is not consumed in the ordinary course of events, and additional quantities are required only when new installations are made. Quicksilver is also used as the cathode in certain electrolytic processes for manufacturing chlorine and caustic soda from common salt. The quicksilver combines with metallic sodium as sodium amalgam, which, in the presence of water, immediately reacts and forms metallic mercury and sodium hydrate. Mercuric oxide parts with oxygen readily and is a useful oxidizing agent in certain chemical processes. An important modern utilization of this property is in the manufacture of glacial acetic acid by the oxidation of acetylene.

Experiments have been carried out on a considerable scale to determine the possible advantage of using mercury vapor as proposed by W. L. R. Emmet [1] in tandem mercury and steam boilers with turbine power generators. These are reported to have been encouraging and a 4,000-kilowatt unit has been built by the General Electric Co. to test further this application. The mercury so used is recoverable, except for incidental losses, but nevertheless if this invention leads in practice to as great an increase of power or economy of fuel, 45 per cent, as the experimental work has indicated, it is likely to result in a large consumption of the metal.

From data collected chiefly by J. P. Dunlop, under the supervision of H. D. McCaskey, both of the Survey, it is estimated that the principal purposes for which quicksilver was used in the United States in 1917 were as follows:

	Flasks of 75 pounds.
Drugs and chemicals	8,500
Fulminate	4,850
Vermilion	3,130
Oxide (for antifouling marine paint)	3,000
Electrical apparatus (batteries, electrolyzers, rectifiers, lamps, etc.)	2,700
Felt manufacture (especially hats)	1,700
Gold and silver amalgamating mills	850
Instruments, thermostats, gas governors, automatic sprinklers, etc	630
Miscellaneous, including boiler compounds and cosmetics	1,000
	26,360

[1] See bibliography.

Digitized by Google

It is estimated that the nonmilitary uses alone, if unrestricted, will require about 23,260 flasks in 1918, and that the Government requirements, partly to be met from abroad, will even exceed this quantity.

CONSUMPTION OF QUICKSILVER IN GOLD AND SILVER MINING.

Quicksilver is utilized to amalgamate with and retain native gold, both in quartz milling and in placer mining. Under ideal conditions the metal so employed would be recoverable and could be used over and over. In practice, however, there is some loss, which, according to Sharwood,[1] who has given this subject careful study, usually ranges from 0.005 to 0.01 pound avoirdupois, or from 0.07 to 0.15 ounce troy, to each ton of low-grade ore treated in modern mills. The following table gives approximately this loss for each State, including probably some quicksilver purchased during the year for new or enlarged milling operations. The figures given for Alaska are the least reliable, as they are based for the most part on statements of the cost of the quicksilver consumed annually in the large mills on Douglas Island with small, arbitrarily assumed additions for the smaller mills in the Territory. In the summer of 1916 amalgamation on Douglas Island was replaced by the cyanide process.

Quicksilver consumed in gold-quartz milling in United States, 1912–1916, in pounds.

State.	1912	1913	1914	1915	1916
Alaska	[a] 7,700	[a] 7,500	[a] 7,500	[a] 5,750	[a] 7,750
Arizona	[b] 1,400	[b] 1,500	[c] 1,802	[c] 547	[c] 645
California	[d] 24,200	[d] 17,000	[d] 17,500	[d] 19,600	[d] 19,300
Colorado	[e] 10,622	[e] 10,834	[e] 6,059	[e] 6,014	[e] 5,237
Idaho	[f] 700	[f] 254	[f] 598	[f] 1,040	[f] 1,183
Montana	[b] 750	[b] 200	[c] 408	[c] 371	[b] 206
Nevada	[b] 1,500	[b] 1,600	[b] 6,826	[c] 4,367	[c] 2,111
New Mexico	[e] 187	[e] 133	[e] 365	[e] 368	[e] 280
Oregon	[b] 280	[b] 350	[b] 400	[d] 1,690	[d] 3,700
South Dakota	[e] 14,095	[e] 12,160	[e] 13,500	[e] 13,900	[e] 12,516
Utah	[b] 40	[b] 30	[b] 20	[c] 30	[c] 15
Washington	[f] 121	[f] 130	[f] 43	[f] 28	[f] 317
	61,575	51,691	55,021	53,705	53,280

[a] Rough estimate based on cost of quicksilver consumed as given in annual reports of Alaska gold-mining companies (F. L. Ransome).
[b] Estimate based on bullion produced by amalgamation (H. D. McCaskey).
[c] Heikes, V. C., U. S. Geol. Survey Mineral Resources, 1912–1916.
[d] Estimate based on bullion produced by amalgamation (F. L. Ransome).
[e] Henderson, C. W., U. S. Geol. Survey Mineral Resources, 1912–1916.
[f] Gerry, C. N., idem.

The quantity of quicksilver used in sluicing, hydraulic mining, and dredging, and the proportion of it lost, vary widely with the character of the gravel and the coarseness of the gold. In modern gold dredging the quantity lost annually by each dredge is very small, and according to William S. Noyes,[2] of the El Oro Dredging Co., averages, roughly, about a flask. An attempt was made to estimate the quantity lost annually in placer mining in each State and to prepare for this branch of the mining industry a table similar to

[1] Sharwood, W. J., Loss of quicksilver in gold mills: Min. and Sci. Press, Apr. 6, 1918, p. 483.
[2] Letter, Aug. 12, 1918.

Digitized by Google

that just given, but the data available proved insufficient for this purpose. Probably from 15,000 to 20,000 pounds, or from 200 to 265 flasks, is lost annually in California in placer mining, including dredging, and possible twice as much in the country as a whole.

GENERAL GEOGRAPHIC AND GEOLOGIC RELATIONS OF QUICKSILVER DEPOSITS.

IN THE WORLD AS A WHOLE.

The ores of quicksilver, like those of most metals, show on the whole a close association with igneous rocks and with zones of fissuring. More commonly than with other metals, with the possible exception of antimony, they are associated with volcanism as opposed to plutonic igneous activity and were deposited comparatively near the surface. It follows that quicksilver deposits as a rule are found in regions of Tertiary and Quaternary volcanic activity which have not been subjected to long and deep erosion, that they are more likely to be in the younger geologic formations than in the older rocks, and that as a class, compared, for example, with the hypogene ores of gold or copper, they do not extend to great depth. It must be noted, however, that there are some conspicuous exceptions to these generalizations. Although California deposits are in a region of late volcanic activity and many of them are closely associated with active hot springs, the ore bodies at present most productive in that State, those at New Idria (Idria post office) and the great deposits which formerly yielded so richly at New Almaden, have no obvious connection with volcanism. The same is true of many smaller deposits in that State. The quicksilver deposits in Arizona, not yet more than nominally productive, are in pre-Cambrian schist and are by no means clearly associated with volcanic activity. The greatest quicksilver mine in the world, that at Almaden, Spain, has no known connection with vulcanicity or massive igneous rocks, has been worked to a depth of 1,150 feet, and the ore bodies have been found to grow larger and richer downward. The deepest quicksilver mine in the world is the New Almaden, in California, worked to a depth of 2,200 feet. The part of the mine below the 800-foot level was abandoned at a time when the price of quicksilver was low, but it is doubtful whether under any conditions that can now be foreseen it will be profitable to reopen and work the deep levels of this mine. The ground at that depth is difficult to hold and mining is interfered with by abundant water and gas.

Although most of the known quicksilver deposits (Pl. II) are in regions of geologically late volcanic eruptions, it is probable that ores of quicksilver were deposited during or closely following epochs of similar igneous activity in the older geologic periods, but that many of them have been removed by erosion. Some of the deposits in the older rocks, which do not appear to be related to Tertiary or later volcanic eruptions, may have had such earlier origin.

The quicksilver deposits of the Adriatic region in Europe, including those at Idria in Austria, Avala in Serbia, and Monte Amiata in Italy, have been shown by De Launay to belong to a single metallo-

Digitized by Google



ON RECORD.

95185°—M R 1917, PT I.

Digitized by Google

Digitized by Google

genetic province characterized by Tertiary eruptions. Similarly, the somewhat scattered occurrences of quicksilver in Alaska, Washington, Idaho, Montana, Oregon, Nevada, Utah, California, Arizona, Mexico, Peru, and Chile coincide in part with the belt of Tertiary and Quaternary volcanic activity along the western sides of the continents of North America and South America. Future work may subdivide this belt into two or more provinces as regards the genesis of the quicksilver deposits, but existing knowledge is insufficient for such distinction. The deposits at Almaden, Spain, in the Donetz Basin, Russia, in Asiatic Turkey, and in China appear to be isolated occurrences that can not at present be assigned to recognizable provinces of eruptive activity and metallization.

The quicksilver deposits themselves are not confined to rocks of any particular kind or of any particular geologic age. At Almaden, in Spain, the ore bodies have been formed by the impregnation and displacement of quartzite beds that lie between clay slates, all of Silurian age. At Oviedo, in the same country, cinnabar, with pyrite, orpiment, and realgar, occurs in brecciated sandstone and shale of Carboniferous age. At Idria, in Austria, the ore consists chiefly of Triassic shale, sandstone, and dolomite impregnated with cinnabar near a zone of overthrust faulting and was deposited in post-Eocene time. In Tuscany, in Italy, the principal ore bodies are in Eocene limestones and shales, close to a contact between them and trachyte. In California most of the deposits are in the sedimentary rocks of the Franciscan group, probably of Jurassic or early Cretaceous age, and in the serpentine associated with the Franciscan. The New Almaden ores, contrary to previously published descriptions, are wholly in serpentine, and the New Idria ores are in sandstone and shale. In Nevada most of the deposits are in Tertiary rhyolite, although some are in Triassic or Jurassic limestone. The only important mine in Oregon is in andesite, presumably of Tertiary age. The Texas ores are in massive Lower Cretaceous limestone and in Upper Cretaceous limestone and shale (Eagle Ford). They are closely associated with small bodies of intrusive rocks of various kinds. Some of the deposits in Mexico appear to be geologically similar to those in Texas. The formerly very important deposits at Huancavelica, in Peru, are in Cretaceous or Jurassic shales, conglomerates, sandstones, and limestones, especially in sandstone, in close proximity to andesitic intrusive rocks.

IN THE UNITED STATES.

It is entirely in accord with the general association of quicksilver ores with volcanic activity that the quicksilver deposits of the United States (Pl. III) are found in the western part of the country, where the products of Tertiary and later volcanism abound, and where numerous hot and thermal springs testify to the comparative recency of much of the igneous activity.

The most abundant and productive deposits are in California. Western Texas comes next in productivity, followed by Nevada. Oregon, Arizona, Washington, Idaho, Montana, Utah, and Wyoming are all known to contain some quicksilver deposits, although Oregon is the only one of these States in which the metal is at present being produced steadily on a commercial scale.

Digitized by Google

In California the principal deposits occur in the Coast Ranges, within a belt about 400 miles long that extends from Santa Barbara on the southeast to Ukiah on the northwest. The maximum width of this belt is about 75 miles. The known occurrences within this area are numerous. About 25 of them are at present productive, while it is estimated that at least three times that number of mines, which were productive in the past, are now idle. A comparatively small number of deposits are prospects, from which no production has yet been recorded. There are a few deposits of quicksilver ore in California outside of the belt mentioned, but these are of comparatively small economic importance.

With a few exceptions, the deposits of the main quicksilver belt in California are in rocks of the Franciscan group, probably of Jurassic age, or in the serpentine, which is such an abundant and characteristic associate of these rocks and which is the alteration product of irruptive rocks of the peridotite group, rich in magnesium and iron. Probably the greater number are in the serpentine. Others are in sandstone, generally near the serpentine, and still others are in thin-bedded siliceous rocks known as radiolarian chert. The most notable exceptions to the occurrence of ore within the serpentine and Franciscan group are the deposits of the Oceanic mine, near Cambria, San Luis Obispo County, and of the Sulphur Bank mine, in Lake County. The ore of the Oceanic occurs in fine-grained sandstone, probably Miocene, that is faulted against the Franciscan, and the ore at Sulphur Bank occurs partly in basalt and accompanying local detrital deposits that lie upon the Franciscan and partly in the Franciscan itself.

Some of the mines, not all at present productive, in which the ore is wholly or partly in serpentine are the Elgin, Wide Awake, Empire, and Central, in Colusa County; the Abbott, Baker, Big Injun, Chicago, Great Western, Helen, Mirabel, and Wall Street, in Lake County; the Aetna, Bella Union, Corona, Knoxville (Redington), La Joya, and Twin Peaks, in Napa County; the Culver-Baer, Great Eastern, and Rattlesnake, in Sonoma County; the January (Harrison) and Reed, in Yolo County; the New Almaden and New Guadalupe, in San Clara County; the Patriquin, in Monterey County; the Alpine, Aurora, Cerro Bonito, Flint (Fourth of July), Los Picachos, and San Carlos (the New Idria Quicksilver Mining Co.), in San Benito County; the Belt (La Libertad), Cambria, Keystone, Little Bonanza, Tartaglia, and Huasna, in San Luis Obispo County; the Acachuma and Los Prietos, in Santa Barbara County; and the Mercy, in Fresno County. In some of these mines the serpentine is present only as narrow dikes or tongues entirely altered to one of the varieties of "quicksilver rock," which to the inexperienced eye may not be recognized as having once been serpentine. Mines in which the ore occurs wholly or partly in sandstone or shale are the Manzanita, in Colusa County; the Sulphur Bank, in Lake County; the Oat Hill, in Napa County; the Eureka and Socrates, in Sonoma County; the New Idria, Wonder, Florence Mac, Cerro Bonito, and Del Mexico, in San Benito County; and the Oceanic, Klau, and Capitola, in San Luis Obispo County. Mines in which the ore occurs wholly or in part in radiolarian chert are the Great Western and Big Chief, in Lake County, and the Cloverdale, in Sonoma County. Mines in which the

Digitized by Google

Digitized by Google

Digitized by Google

ore occurs in unserpentinized dikes or small intrusive masses are the Star and Silver Bow workings of the Aetna mine, in Napa County; the St. Johns, in Solano County; the Cuddeback, in Kern County; and, to a small extent, the New Idria, in San Benito County. Mines in which the ore occurs partly or wholly in lava or tuff are the Sulphur Bank, in Lake County; the Manhattan, in Napa County; and probably the Brownlie and Hastings, in Solano County, although the exact nature of the ore-bearing rock of these two mines is as yet in doubt.

In Oregon cinnabar is widely distributed, but only one deposit, the metallized fissure zone in andesite at Blackbutte, in Lane County, is at present commercially productive.

In Washington cinnabar has been found at a few localities in Chelan, Kittitas, and Lewis counties. None of the deposits has yet proved to be of economic importance.

Nevada contains many widely scattered deposits of quicksilver ore, no one of which has yet been worked on an extensive scale, although a few of them have been fairly productive for short periods. The Nevada quicksilver ores occur in rhyolite of Tertiary age and in various limestones or associated sedimentary beds of Paleozoic and Mesozoic age. The deposits in rhyolite include that in Sheep Canyon, 1½ miles southeast of Ione, in Nye County; those at Ivanhoe Springs, in Elko County, 50 miles northwest of Elko; at Goldbanks, in Humboldt County, 30 miles south of Winnemucca; at Montgomery Mountain, in Mineral County, 5 miles east of Montgomery station on the narrow-gage railway from Mina, Nev., to Keeler, Cal.; and, in part, the deposits on Bare Mountain, 6 miles east of Beatty, in Nye County. This ore in rhyolite is generally very hard and siliceous, although less so near Ione and on Montgomery Mountain than at the other localities mentioned. The quicksilver occurs chiefly in the mineral cinnabar distributed unevenly and in places very erratically through the altered rhyolite.

The deposits occurring in limestone or dolomite, or in sedimentary beds associated with limestone, include that near the head of Shamrock Canyon, near Ione; those in the Humboldt Range east and northeast of Lovelock, in Humboldt County; in part those near Beatty; and those in the Pilot Mountains, 8 miles a little south of east from Mina, in Mineral County.

In Arizona most of the known quicksilver deposits occur in zones of fissuring or shearing in pre-Cambrian schist. Such are the deposits in the Mazatzal Mountains, Maricopa and Gila counties, which have yielded some quicksilver but have not yet been made continuously productive, the deposits 15 miles north of Phoenix now being developed and the lode of the Colonial Mining Co., near Quartzite, in Yuma County, at present unworked, although it has produced some quicksilver. The occurrence of cinnabar in Skull Valley, in Yavapai County, west of Prescott, has been known for many years. The mineral is said to be in a fissure vein in granite. No production is recorded from this locality.

In Texas the principal quicksilver deposits are in the Terlingua district, in Brewster County, about 75 miles south of Alpine. The ore occurs along fissure zones in Cretaceous limestones and shales, generally in proximity to bodies of intrusive rock.

Digitized by Google

MINERALOGY OF QUICKSILVER ORES.

GENERAL CHARACTER OF ORES.

Quicksilver ores as a rule are comparatively simple in mineralogical character. About 25 mercurial minerals are known, but most of them are rare, and to few quicksilver miners does "quicksilver ore" suggest anything but rock containing the brilliant red sulphide cinnabar, with perhaps some native mercury and possibly a little of the black or dark-gray sulphide metacinnabar. These minerals are commonly associated with more or less iron sulphide in the form of pyrite or marcasite. The mercury minerals and associated sulphides may be scattered in small specks through sandstone or other porous rock; they may occur as irregular streaks or bunches in altered rocks of various kinds; or, with calcite, barite, or quartz as gangue minerals, they may form definite veins, although these are rarely of regular form.

A large number of the deposits in California are in serpentine, and in these the cinnabar and accompanying sulphides occur in dark opal or in carbonates of calcium, magnesium, and iron, or in mixtures of opal and carbonates. In Nevada many of the deposits are in rhyolite, which in the vicinity of the cinnabar is generally much altered. In some localities the rhyolite has been changed to a very hard granular rock resembling quartzite, in others it has been converted to white opal, and in others to soft masses of sericite or kaolinite. Various mixtures of these minerals are also common.

In certain localities the sulphide of antimony, stibnite, is fairly abundant with the cinnabar, and most quicksilver deposits, especially in California, contain small quantities of an oily or asphaltic hydrocarbon.

MINERALS CONTAINING MERCURY.[1]

Amalgam.—A variable mixture of mercury and silver (Ag_2Hg_3 to $Ag_{36}Hg$), which crystallizes in the isometric system as dodecahedrons or modified cubes. It is silver-white with brilliant luster and from 3 to 3.5 in hardness.[2]

Amalgam carries from 26.4 to 95.1 per cent of silver. The mineral is rare, but has been found in Europe, Chile, British Columbia, and Colorado.

Lehrbachite.—A selenide of lead and mercury (PbSe with HgSe). Known only from the Harz Mountains in Germany.

Sphalerite.—Some varieties of zinc blende (ZnS) contain mercury, and from the sphaleritic zinc ores mined near Cologne, in Germany, quicksilver is obtained as a by-product.

---

[1] A few doubtful mineral species of which the composition is not accurately known and which may be mixtures, are omitted from this list. Such are "ammiolite" and "barcenite," supposed mercurial antimonates or antimonites.

[2] The Mohs scale, to which the hardness of minerals is commonly referred, is as follows:

1. Talc.
2. Gypsum (can be scratched with finger nail).
3. Calcite (can be cut with knife).
4. Fluorite.
5. Apatite.
6. Feldspar (can barely be scratched with good knife).
7. Quartz.
8. Topaz.
9. Sapphire.
10. Diamond.

Digitized by Google

Metacinnabar.[1]—The black sulphide of mercury (HgS) having the same composition as cinnabar and containing, when pure, 86.2 per cent of quicksilver. It is gray to black, with metallic luster, is brittle, and has a hardness of 3. The streak, or color of the powder, is black. Metacinnabar has been found in Germany, Mexico, and New Zealand, and has been an important source of quicksilver in some California mines. A little of the powdered mineral mixed with sodium carbonate (common soda) and heated in the bottom of a glass tube closed at one end will give a mirror-like ring of metallic quicksilver around the cooler part of the tube.

Guadalcazarite is a variety of metacinnabar containing a little zinc and selenium. It occurs in Guadalcazar, Mexico.

Leviglianite is reported to be another variety which contains iron and is found in Italy.

Tiemannite.—The selenide of mercury (HgSe). It is steel gray to black, with metallic luster, and crystallizes in complexly modified tetrahedrons of the isometric system. Its hardness is 2.5 and its specific gravity 8.19. This is a rare mineral but has been found in Germany and California and was formerly mined as an ore of quicksilver at the Lucky Boy mine in Piute County, Utah, where it is associated with barite, calcite, and manganese oxide.

Onofrite.—The sulphoselenide of mercury with the formula Hg (S, Se). It is dark gray to black, massive, fine granular, brittle, and has a hardness of 2.5. Its specific gravity is 8. The mineral is rare. It occurs with calcite and barite at San Onofre, Mexico, and was mined with tiemannite in Piute County, Utah.

Coloradoite.—The telluride of mercury (HgTe). It is iron black, inclining to gray, with metallic luster, is massive with granular texture, has a hardness of 3 and a specific gravity of 8.6. The mineral is rare. It occurs sparingly with gold-tellurium ores in Colorado and Western Australia.

" Kalgoorlite," a supposed telluride of gold, silver, and mercury from western Australia, has been shown to be probably a mixture of coloradoite and the gold-silver telluride, petzite.

Cinnabar.—The brilliant cochineal red sulphide of mercury (HgS), containing, when pure, 86.2 per cent of quicksilver. It crystallizes, like quartz, in the rhombohedral division of the hexagonal system. The crystals are transparent with adamantine luster, inclining toward metallic luster in some of the darker varieties. They have perfect cleavage parallel to the prism faces. The mineral also occurs as fine-grained aggregates of dull luster, although brilliant color. The crystals exhibit great variety of form from rhombohedral or thick-tabular to needle-like prisms. The hardness is 2 to 2.5 and the specific gravity from 8 to 8.2. The streak is scarlet. The characteristic color is sometimes masked by impurities, such as clay, iron oxide, or organic compounds. Minerals commonly associated with cinnabar are pyrite and marcasite, stibnite, native quicksilver, metacinnabar, sulphur, calcite, iron-magnesium carbonates, silica (as quartz, chalcedony, and opal), barite, and bituminous compounds. Less common associates are realgar (sulphide of arsenic),

[1] Inasmuch as cinnabar is almost universally used instead of cinnabarite there is apparently no good reason why this shorter form should not be employed in place of the more pedantic metacinnabarite.

Digitized by Google

sulphides of copper, native gold, and fluorite. Cinnabar is the principal ore of quicksilver and at the present time is the source of more than 95 per cent of the metal produced in the United States. Its color and general physical properties make its recognition easy as a rule. Where its identity is in doubt the same simple test may be applied as for metacinnabar to establish the presence of mercury. As cinnabar darkens or even turns black on exposure, it may be necessary to break or scratch the mineral to reveal its characteristic red color.

Livingstonite.—A mercury sulphantimonite ($HgSb_4S_7$) which occurs in groups of slender prismatic crystals of bright lead-gray color and metallic luster. Its hardness is 2 and its specific gravity 4.81. The streak is red. It contains theoretically 24.8 per cent of mercury. Livingstonite is a rare mineral which has been reported only from Huitzuco and Guadalcazar, Mexico.

Tetrahedrite (variety schwatzite).—The mercurial tetrahedrite, a copper-mercury sulphantimonite ($4(Cu_2Hg)S,Sb_2S_3$), is dark gray to iron-black, with metallic luster but often dull. Its specific gravity is 5.1. It occurs in Hungary, where it has yielded quicksilver as a by-product in copper smelting, in Italy, and in the Blue Mountains of Oregon in gold ores. Schwatzite is a comparatively rare mineral and has not been recognized in quicksilver deposits, although the observations of Lindgren[1] on the relations of the mercurial tetrahedrite to cinnabar in the Blue Mountains led to his suggestion[2] that the cinnabar of the Plomosa district in Arizona may have been derived from schwatzite. It does not appear, however, that any considerable part of the cinnabar of the productive quicksilver deposits can have had this origin.

Calomel.—The mercurous chloride of mercury (Hg_2Cl_2), also known as horn quicksilver or horn mercury, crystallizes in the tetragonal system in pyramidal, prismatic, and tabular crystals, often complexly faceted. The color is white, gray, yellow, or brown, with adamantine luster. The hardness is between 1 and 2 and the specific gravity 6.48. Calomel is found sparingly in the quicksilver deposits of Europe, Mexico, and Texas. It is probably in all places a secondary mineral due to the action of atmospheric water on cinnabar.

Terlinguaite.[3]—A rare oxychloride (Hg_2ClO) in small monoclinic prismatic crystals with adamantine luster, as crystalline crusts and as yellow powder. The crystals are greenish yellow but turn olive-green on exposure. The mineral is brittle to sectile, with perfect cleavage. It has been described only from the Terlingua district, Tex., where it occurs as a secondary mineral in shallow workings associated with calomel, eglestonite, montroydite, kleinite, and mosesite.

Eglestonite.—The rare mercurous oxychloride (Hg_4Cl_2O) forms minute dodecahedral and octahedral crystals of the isometric system.

---

[1] Lindgren, Waldemar, The gold belt of the Blue Mountains of Oregon: U. S. Geol. Survey Twenty-second Ann. Rept., pt. 2, p. 664, 1901. Also Mineral deposits, p. 801, New York, 1913.

[2] Bancroft, Howland, Notes on the occurrence of cinnabar in central western Arizona: U. S. Geol. Survey Bull. 430, p. 153, 1910.

[3] For full descriptions of this and other minerals occurring at Terlingua see Hillebrand, W. F., and Schaller, W. T The mercury minerals from Terlingua, Tex.: U. S. Geol. Survey Bull. 405, 1909.

Digitized by Google

They are yellow to brown with brilliant adamantine to resinous luster but darken on exposure and finally turn black. The mineral is brittle and has a hardness from 2 to 3 and a specific gravity of 8.3. It is known only in the Terlingua district with terlinguaite and other secondary mercury minerals.

Kleinite.—A rare mercury-ammonium chloride of uncertain formula which crystallizes in the hexagonal system in short yellow to orange crystals that darken on exposure but regain their original color in the dark. Its hardness is 3.5 and its specific gravity 7.9. It is a secondary mineral and occurs with terlinguaite.

Mosesite.—Another mercury-ammonium chloride, which crystallizes in small octahedra of the isometric system and has imperfect cleavage, uneven fracture, hardness slightly above 3, adamantine luster, rich lemon to canary-yellow color, and very pale yellow powder and streak. It occurs with terlinguaite.[1]

Iodyrite (variety tocornalite).—A rare iodide of silver and mercury, found only in Chile. It occurs in granular massive form and is of pale-yellow color, darkening on exposure. Another rather uncertain species originally described as an iodide of mercury but apparently containing chlorine and selenium has been named coccinite. It occurs at Casas Viejas, Mexico, in reddish-brown particles on a selenide of mercury.

Montroydite.—Mercuric oxide (HgO) occurs in long, slender prisms or as equidimensional or distorted crystals, of the orthorhombic system and as velvety crusts, of orange-red color. It is transparent, brittle and has a hardness between 1.5 and 2. It is associated with terlinguaite.

Magnolite.—A doubtful species supposed to be a tellurate of mercury (Hg_2TeO_4). Found as minute white silky crystals on coloradoite, in the Magnolia district, Colo.

TENOR.

The richest quicksilver ores worked on a large scale are those of Almaden, Spain, where the average content won from the ore in 1917 was nearly 7 per cent and where the average of some ore bodies is stated to be as high as 25 per cent. Probably the lowest tenor in ores that are successfully worked is found on the Pacific coast of the United States. The average content won from the California ores during the last two years is 0.38 per cent and the range, in furnace operations, in 1917, was from 0.17 per cent to 1.08 per cent. In Texas, in 1917, the average was 1.42 per cent and the range from 0.55 to 3.88 per cent. The ore at Idria, Austria, according to the latest information available, averages about 0.65 per cent. In the Monte Amiata district, Italy, the ores are reported to range in tenor from 0.25 to 30 per cent, the average for the district in 1913 being 0.89 per cent.

[1] Schaller, W. T., The properties of mosesite: U. S. Geol. Survey Bull. 509, pp. 104–109, 1912.

Digitized by Google

REVIEW OF QUICKSILVER DEPOSITS OF THE WORLD.

EUROPE.

Spain.—In Europe the largest and richest deposit of quicksilver ore known is at Almaden, in central Spain, about 125 miles south-southwest of Madrid and about 46 miles west-southwest of the town of Ciudad Real, in the Province of the same name. There are three nearly parallel ore bodies, trending east and west and standing vertically side by side, each consisting of a portion of a bed of quartzite impregnated with cinnabar. The beds of quartzite are separated by beds of clay slate. Along the south side of the ore bodies and their immediate inclosing rocks is a bed or layer of breccia of peculiar character locally called frailesca. This has been regarded by some geologists as a tuff. The rocks with which the ore is associated are all Silurian. The ore bodies are as much as 200 meters long and 12 meters wide. They have been mined to a depth of 350 meters, and have proved to become longer and wider with increasing depth. The main ore body is said to average from 14 to 15 per cent of quicksilver. The average content won from the ore in 1917 was nearly 7 per cent of quicksilver. The production in 1915 was 35,232 flasks (1,200 metric tons); in 1916, about 23,000 flasks; and in 1917, probably about 24,500 flasks. The mine is said[1] to have ore opened up that insures a future production of at least 40,000 metric tons of quicksilver.

The Almaden mine, whose output is such as in normal times to determine the market for quicksilver, has been owned and worked by the Spanish Government since 1645. The Government, on the basis of competitive proposals, contracts with the successful bidder for the sale of the quicksilver for periods of 10 years. For a number of successive periods the contract has been awarded to the Rothschilds of London, the present one dating from June 1, 1912. The contractors bind themselves to sell in London the greatest possible quantity of quicksilver, which they take f. o. b. at the reduction plant at Almaden, at prices above £7 per flask. They receive (1) a commission of 1¼ per cent of the amount of the sale; (2) 6s. for each flask shipped from Spain to London; and (3) 10 per cent of the amount by which the sales price exceeds £8 2s. per flask. The Spanish Government reserves from the operation of this contract 500 flasks annually for the national requirements of Spain. By this arrangement, although the mine is owned by Spain, the market has been controlled in London. At present the control of the sale of Almaden mercury has been taken over by the Admiralty through Messrs. Rothschild.

As regards the operation of the Almaden mine the following statement appeared in the Mining Journal (London) of August 4, 1917, page 492:

> We learn that the Cortes last year authorized the Spanish Treasury to appoint a committee to control the administration of the Almaden mines. It has been decided to put the working of the mines up for tender for a working period of not more than fifteen years.

[1] Sterner-Rainer, R., Der derzeitige Stand des Quecksilberhüttenwesens in Europa: Oesterr. Zeitschr. Berg- u. Hüttenwesen, vol. 62, p. 531, 1914.

Digitized by Google

Other productive deposits in Spain are those near Oviedo, in the Province of that name, about 20 miles south of the Bay of Biscay. Here the ore is described as occurring in Carboniferous sandstone and shale, particularly along zones of brecciation in these rocks. The principal deposit is described as up to 35 feet wide and several kilometers long. The ore contains cinnabar, pyrite, orpiment, and realgar. It is said to average about 0.3 per cent of quicksilver with arsenic compounds as by-products. According to a report from Vice Consul General H. A. McBride, written in Barcelona in 1911, the principal companies operating in the Oviedo district were the Oviedo Mercury Mines Co. (Ltd.), of London, the Sociedad Fábrica de Mieres, of Oviedo, and the Sociedad Unión Asturiana, of Mieres. The production from the district in 1915 was 608 flasks (20.7 metric tons).

A third group of deposits lies on the south slope of the Sierra Nevada in the Provinces of Granada and Almeria, southern Spain. These are described [1] as occurring in talc slates or schists of Triassic age, the cinnabar being accompanied by tetrahedrite and sulphides of nickel and cobalt. The production from Granada in 1915 was 41 flasks (1.4 metric tons).

Quicksilver has also been produced in a small way in the Province of Castellón, in eastern Spain. Other occurrences of cinnabar of slight or no economic importance are known in eastern Spain near La Creu in Valencia and near Orihuela in the adjoining Province of Alicante.

Portugal.—A small quantity of quicksilver was produced in Portugal in the nineteenth century from a mine near Conna, not far from Lisbon.[2]

France.—Cinnabar occurs at a number of localities in France and also in Corsica, but the deposits are not of economic character.

Germany.—In south Germany, north of Zweibrücken, in the Bavarian Pfalz (the ancient Palatinate), are quicksilver deposits which had considerable importance near the end of the thirteenth century, but the mines had been closed for many years at the beginning of the war. The deposits are described as veins and impregnations in Carboniferous shales and sandstones, in conglomerate, in melaphyre, and in rhyolite porphyry. They are said to have been very rich near the surface but to have become poor at depths less than 200 meters. Cinnabar and other mercurial minerals have been found at various localities in Germany, chiefly in deposits worked for other metals. The sphaleritic zinc ores mined near Bensberg, 15 kilometers east of Cologne, in the province of Rhineland, yield annually about 90 flasks of quicksilver, won as a by-product in zinc smelting.

Austria-Hungary.—In Austria-Hungary the principal deposit, owned by the Government, is at Idria, in the province of Krain, about 28 miles slightly east of north from Trieste, at the head of the Adriatic Sea, and 18 miles in a straight line from Gorizia. The ore bodies, of post-Eocene age, occur as veins, as more or less flat, horizontal masses, and as stocks, chiefly as impregnations of Triassic shale, fine-grained sandstone, and dolomite, and in the interstices of brecciated dolomite in the hanging wall of a great overthrust fault.

[1] De Launay, L., Traité de métallogénie: Gîtes minéraux et métallifères, vol. 3, p. 424.
[2] Calderón, D. S., Los minerales de España, vol. 1, p. 207, 1910.

Digitized by Google

The overthrust beds are complexly folded and rest on Cretaceous limestone. The ore bodies are very irregular in form and trend generally northwest-southeast, whereas the direction of the overthrust is southwest.[1] The ore is mineralogically simple, consisting of cinnabar in minute crystals, metacinnabar, with pyrite, calcite, dolomite, a little quartz, gypsum, and hydrocarbons (anthracite and idrialite). The deepest shaft is only 985 feet (300 meters) deep. In 1914 the Idria mine produced 23,832 flasks (811 metric tons). The output in Austria in 1916, probably all from Idria, is believed from the best information available to have been about 25,000 flasks. Reserves capable of yielding 20,000 metric tons, or 587,733 flasks, are known.

Other deposits in southern Austria (Krain) belonging to the same metallogenetic province as Idria are the Sanct Anna near Neumarkt, about 38 kilometers east of Laibach. These mines were formerly productive but were idle at the beginning of the war.

At Zips, near Iglo, in northern Hungary, quicksilver is obtained as a by-product from iron ore consisting of siderite which carries mercurial tetrahedrite and some cinnabar. The production in 1913 was 2,615 flasks. Cinnabar and other mercury-bearing minerals occur at a few other places in Austria-Hungary but not in economically important quanttiy.

Italy.—To the west of Idria quicksilver deposits belonging to the same general belt of metallization extend into northern Italy. The principal deposit of this belt in Venetia is the Vallalta, near Gosaldo, 95 kilometers north-northwest of Venice, close to the borders of the Tyrol. The deposit is described as occurring at a contact between quartzose porphyry and Triassic sandstone, shale, and conglomerate. The mine produced 9,550 flasks (325 metric tons) between 1856 and 1870 but has long been idle.

The most productive deposits of quicksilver in Italy are those of the Monte Amiata district. These are in Tuscany, in the province of Siena, about halfway between Rome and Florence. Monte Amiata is apparently a post-Pliocene volcano, and traces of recent volcanic activity survive in the issuance of gases and hot water.

The most recent and comprehensive account of these deposits is that of De Castro.[2] According to him, the mass of Monte Amiata consists of a rock termed trachyoligoclasite but commonly referred to as trachyte and locally called peperino, which has been erupted through shales and limestones from early Jurassic to late Tertiary age. The ore bodies of the district are so varied in form and occurrence that it is difficult to summarize their characteristics, but the principal deposits are found mainly as irregular masses and impregnations in Eocene limestones and shales close to the contact with the trachyte and particularly in brecciated and clayey material that has resulted from the crushing and alteration of the Eocene sedimentary beds by the trachytic eruption. There were eight producing mines in 1913, the most productive being the Abbadia-San Salvatore, which yields about 65 per cent of the output of the district. The district in 1916 yielded 32,129 flasks, and in 1917 about 29,300 flasks. Most of the metal before the war was exported to Great Britain and Ger-

[1] Kropáč, Josef, Über die Lagerstättenverhältnisse des Bergbaugebietes Idria: Berg- u. Hüttenmän. Jahrb., vol. 60, pp. 97–146, 1912.

[2] Castro, C. de, Le miniere di mercurio del Monte Amiata: R. Ufficio geologico, Memorie descrittive della Carta geologica d'Italia, vol. 16, pp. 1–209, 1914.

Digitized by Google

many and since the entry of Italy into the war has gone to Great Britain.

The ore is cinnabar accompanied by pyrite, sulphides of arsenic and antimony, gypsum, and celestite. It ranges in tenor from 0.25 to 30 per cent, the average for the district in 1913 being 0.89 per cent. The coarse ore is treated in simple shaft furnaces and the fine ore in Cermak-Spirek furnaces, which are similar to the Scott furnace. The San Salvatore mine has fourteen 24-ton shaft furnaces, and four 24-ton and two 12-ton Cermak-Spirek furnaces. The annual production of metal per man was 1.378 metric tons, or 40.5 flasks, at the San Salvatore mine and 0.803 metric tons, or 23.6 flasks, for the district as a whole.

The most productive of the Monte Amiata mines are understood to have been under German control prior to the entry of Italy into the war but to have been seized by the Italian Government when it entered the conflict.

From Monte Amiata a belt of quicksilver deposits extends northwest between Florence and Pisa into the "Alpes Apuanes," but none of these has yet proved of economic value.

Serbia.—At Mount Avala, 20 kilometers southeast of Belgrade, deposits of quicksilver ore have been known since 1883. The ore, as described by Fischer,[1] occurs in a stocklike mass of quartz, opal, and siderite, which is a thermal alteration product of serpentine. The deposit thus resembles many of those in California. The Avala deposits were worked between 1889 and 1895 but have not fulfilled expectations and apparently have not been productive in late years.

Other occurrences of cinnabar are known in Serbia, Bosnia, and Albania but so far as known are not economically important.

Russia.—The only quicksilver deposits of note in European Russia are those near Nikitovka, in the Donetz coal basin, in the southwestern part of the Government of Woronesh, southern Russia.[2] The ore occurs as a network of small veins and as impregnations in much disturbed Carboniferous shales. The essential mineral is cinnabar accompanied by stibnite and pyrite. The deposits were discovered in 1879; the maximum output, 18,102 flasks (616 metric tons), was reached in 1897; and work was abandoned in 1911 but has been resumed since in a small way, according to reports. The ore mined in 1904 yielded 0.345 per cent of quicksilver; in 1905, 0.378 per cent; and in 1906, 0.276 per cent.

Quicksilver deposits are reported to have been worked in 1912 in the Government of Ekaterinoslaf, in southern Russia, and cinnabar is known to occur, closely associated with gold, about 20 miles from Neviansk on the eastern slope of the Urals in the Government of Perm.

ASIA.

Turkey.—The Konia mine in south central Asia Minor (Anatolia) is in silicified limestone. The quicksilver occurs as cinnabar, and most of the ore carries from 1 to 2.5 per cent of the metal, although portions of the ore body containing stibnite carry as much as 8 per cent. The known reserves were estimated in 1908 at 13,000 metric

[1] Fischer, H., Die Quecksilberlagerstätten am Avalaberge in Serbien: Zeitschr. prakt. Geologie, vol. 14, pp. 245–256, 1906.

[2] The Donetz basin is in what is now (October, 1918) Ukraine.

Digitized by Google

tons of 1 per cent ore.[1] The production in 1911 was only 90 flasks of 75 pounds. This mine reverted to the Turkish Government in 1912.

The Kara-Burnu mine, said to be the only important quicksilver mine in Turkey, is situated near Aidin, 30 kilometers southeast of Smyrna, in a region of Cretaceous limestones and Miocene basalt. The ore is worked by open-cut methods and averaged 0.33 per cent of quicksilver in 1912. In 1906 and 1907 the mine was producing about 3,000 flasks annually, but of late years the production has declined and in 1912 amounted to only 911 flasks (31 metric tons).

Russia.—The Ildekansk quicksilver mine, near Nertschinsk in southeastern Siberia, east of Lake Baikal, has gained ill-founded notoriety from the fact that political exiles were condemned to mine the ore, which occurs in small quantity as cinnabar with calcite and quartz in veins and bunches in limestone. The deposit appears to be of slight economic importance.

In several of the gold districts in Siberia cinnabar has been found in the auriferous gravels, but such occurrences appear to have led to the discovery of cinnabar in place only in the Ekaterinburg district, in the southern Urals.

China.—That quicksilver deposits occur in the Province of Kweichow, south-central China, has long been known, but the locality is remote from ordinary routes of travel and comparatively little is on record concerning their character. According to Brelich[2] the mines are in the prefecture of Toon-Yen and from 1,324 to 1,426 miles from Shanghai, according to the route taken. The ore bodies of the Wan San Chang mines are the most extensively worked. These occur in nearly horizontal magnesian limestone as (1) impregnations of particular beds, (2) along fissures and bedding planes, (3) as isolated bunches, and (4) as irregular disseminations through disturbed portions of the limestone. For several years prior to 1905 the output averaged about 4,000 pounds of quicksilver a month, with a small quantity of cinnabar marketed as such. This would be equivalent to about 640 flasks annually. More recent figures of production are not available.

Japan.[3]—Quicksilver ores occur at several localities in Japan, but the output is small and the Suigin mine at Suii, in Awa, Shikoku, appears to have been the only mine in operation in recent years. Here cinnabar associated with calcite is found along a fault fissure in Mesozoic limestone as veinlets and impregnations.

East Indies.—In Sarawak, Borneo, quicksilver has been produced from irregular deposits in shales and sandstones, the annual output, partly from placer operations, amounting to 1,733 flasks in 1872.[4]

Production is known to have continued until 1880, but no record of subsequent operations has been found. Cinnabar has been reported also from Sumatra and Java.[5]

[1] Monaci, E. P., Le miniere di mercurio in Turchia: Rassegna Min., 1908, p. 138.

[2] Brelich, Henry, Chinese methods of mining quicksilver: Inst. Min. and Met. Trans., vol. 14, pp. 483–496, 1905.

[3] Mining in Japan, past and present, pp. 107–108, Japan Bur. Mines and Dept. Agr. and Commerce, 1909. A list of localities with brief notes on modes of occurrence is given.

[4] Everett, A. H., Notes on the distribution of useful minerals in Sarawak. An undated pamphlet in the library of the United States Geological Survey; apparently written about 1874.

[5] Becker, G. F., Geology of the quicksilver deposits of the Pacific slope: U. S. Geol. Survey Mon. 13, p. 48, 1888. Becker, in the second chapter of this monograph, presents many notes on the foreign occurrences of quicksilver, many of which, however, relate to deposits of no known economic importance.

Digitized by Google

OCEANICA.

Australia.—Deposits containing quicksilver are known to occur along the coastal region of Queensland from Brisbane to Cape York and a few flasks have been produced from the Kilkivan district, near Gympie, in this region. The cinnabar is said to be found in lodes in granite, diorite, schist, altered sandstone and conglomerate, associated in some of the localities with serpentine. The deposits apparently are small and of low grade.[1]

In New South Wales deposits of doubtful economic value occur as lodes at Pulganbar, Yulgilbar, and Ewangar, near Grafton. A furnace was reported to be under construction at Pulganbar in 1913, but the results of its operation are not known. Deposits, also of doubtful value, are reported near Rylstone and Bingara.

New Zealand.—Quicksilver minerals have been found in regions of recent volcanic activity in New Zealand, but no deposits of economic value are known, and the Government is understood to have offered a bonus of 8 cents a pound for the first 100,000 pounds retorted from domestic ore. Prospecting is said to have been in progress in 1917 at Puhi Puhi, on North Island, with encouraging results.

New Caledonia.—Some occurrences of cinnabar have been reported in New Caledonia, but none, so far as known, is worked or is of economic value.

AFRICA.

Occurrences of cinnabar have been reported from the Transvaal, Abyssinia, and Madagascar, but only in Algeria have deposits been worked. These, according to De Launay,[2] occur as complex veins that carry, besides cinnabar, galena, tetrahedrite, sphalerite and stibnite. Deposits of the same general character occur in Tunis.

NORTH AMERICA.

In North America the quicksilver deposits are confined to the Cordilleran region from Alaska to Central America. By far the most productive deposits are in California and western Texas.

Alaska.—In Alaska minerals containing quicksilver have been found in the sluice boxes in a number of the placer-mining districts, but deposits in place have been discovered in the central Kuskokwim region only.[3] At the Parks prospect, 15 miles upstream from Georgetown, the ore occurs as cinnabar accompanied by stibnite, quartz, and a ferruginous dolomite in shattered Cretaceous shale in association with intrusive bodies of diabasic and granitic rock.[4] Development has been hindered by the difficulties of access to the region, and only a few hundred pounds of quicksilver has been produced for local consumption. Another prospect is 5 miles below Kolmakof and about 100 miles downstream from the Parks prospect.[5] Here quartz

[1] Ball, L. C., Mercury in Queensland: Government Min. Jour., vol. 15, pp. 623–629. 1914. Dunstan, B., Queensland mineral deposits, 11. Mercury: Idem, vol. 18, pp. 232–238, 1917.

[2] Launay, L. de, Gîtes minéraux et métallières, vol. 3, p. 445, Paris, 1913.

[3] Smith, P. S., and Maddren, A. G., Quicksilver deposits of the Kuskokwim region: U. S. Geol. Survey Bull. 622, p. 272, 1915.

[4] Smith, P. S., The Lake Clark-Central Kuskokwim region, Alaska: U. S. Geol. Survey Bull. 655, 1917.

[5] Smith, P. S., and Maddren, A. G., op. cit., p. 272.

Digitized by Google

lenses and veinlets containing cinnabar occur in arkosic sandstone, closely associated with a sill of altered "andesite."

Quicksilver ore in place is reported also on the divide between Kuskokwim and George rivers, about 2½ miles northwest of the Parks prospect, and near Iditarod.[1]

Canada.—A small output of quicksilver was recorded in Canada in 1895–1897 from pockety deposits of cinnabar in quartz veins cutting Tertiary volcanic rocks near the west end of Kamloops Lake, British Columbia. Cinnabar and native quicksilver are reported to occur on Groundhog River near the Transcontinental Railroad,[2] but, so far as known, these deposits have never been developed. Some cinnabar, but not in commercial quantity, has been stated to occur in the silver ore of the Nipissing mine of the Cobalt district.

Washington.—In Washington quicksilver ores have been prospected near Orondo, in Chelan County; north of Cle Elum, in Kittitas County; and near Morton, in Lewis County. The production from this State is thus far inconsiderable.

Oregon.—In Oregon there are many widely distributed occurrences of cinnabar, but only one deposit, that at Blackbutte, in Lane County, is at present productive, although occasionally a flask or two is obtained from prospects near Gold Hill, in the southwestern part of the State.[3]

The principal ore body of the Black Butte mine is a metallized fissure zone in andesite. It is about 200 feet long, up to 15 feet wide, and has been worked to a depth of about 400 feet. The ore body has been cut on the 500-foot level, but on the only level below this, the 900-foot, no workable body of ore has yet been found. The ore averages about 0.2 per cent of quicksilver, and the quantity available above the 500-foot level is estimated by the company at about 150,000 tons.

California.—It is not possible in an outline of this brevity to describe all of the deposits in California. Only a few notes can be given on those that are now leading producers or are likely in the near future to attain that rank. Many of the most productive mines of the past—as, for example, the Redington, or Knoxville, Great Western, and Oat Hill—have yielded no quicksilver from underground work for many years.

The most productive mine in California at present is the New Idria, in San Benito County, which in 1917 yielded 11,000 flasks out of a total for the State of 23,938 flasks and for the United States of 36,159 flasks. The New Idria ore comes from two mines, the New Idria proper and the San Carlos, which lies about 1¾ miles southeast of the New Idria. The New Idria has been extensively opened to a depth of about 1,000 feet. The San Carlos is worked principally by open pits, although a level, now abandoned, was run at a depth of 500 feet.

The New Idria ore bodies occur as rudely lenticular or pipelike masses in steeply upturned Franciscan sandstone and shale, the shale being generally indurated and closely laminated with thin layers of sandstone. The San Carlos ore forms very irregular masses in simi-

[1] Smith, P. S., and Maddren, A. G., op. cit., pp. 286–287.
[2] Report from U. S. Consul H. D. Dill, Orillia, Ontario, Dec. 12, 1911.
[3] Since this report was written the Rainier mine, in the Meadows district, near Gold Hill, has become productive.—F. L. R.

Digitized by Google

lar but in general somewhat softer sandstone and shale of the Franciscan, and, to a less extent, in soft crushed serpentine. The two mines contributed nearly equally to the total production in 1917, and the average won tenor of the ore in that year was 0.32 per cent.

The New Almaden mine, situated in Santa Clara County, 12 miles south of San Jose, comprises an extensive system of underground workings to a depth of 2,245 feet. At present, however, all the levels below the 800 foot are under water, and of late years very little ore has been taken from the old mine. Most of the recent production of the New Almaden Co. (Inc.) has come from the Senator (El Senador) mine, about 3 miles northwest of the old mine, and from quicksilver recovered from ground under old furnaces and condensers.

In the New Almaden, in the Senator, and in the neighboring New Guadalupe the ore occurs as irregular, more or less lenticular masses in opalized and otherwise altered serpentine. In 1917 the New Guadalupe ore averaged very nearly 1.1 per cent in won tenor. Close to the mine now being operated by the New Guadalupe Mining Co., and owned by the same company, is the original Guadalupe mine, once highly productive but which has long lain idle. It has recently been pumped out and may soon yield additional quicksilver. The ground both of the New Almaden and New Guadalupe companies has great possibilities, but no estimate can be made at present of the quantity of ore probably available.

The Oceanic mine, situated 4 miles east of Cambria, in San Luis Obispo County, ranked fourth in production in California in 1917. The ore occurs as an impregnation of nearly vertical, fine-grained Tertiary, probably Miocene, sandstone. The ore body is about 600 feet long, 40 feet wide at the surface, and has been worked from the surface to the 300-foot level, where it is said to be about 15 feet wide. The so-called 300-foot level, now under water, is about 555 feet below the highest point at which ore was mined at the surface and 300 feet below the fourth (tunnel) level. Most of the ore at present is coming from ground above the fourth level, which is 255 feet below the highest surface ore. The average won tenor of the ore in 1917 was 0.185 per cent.

Other mines in California which yielded from 500 to 1,000 flasks in 1917 are the Great Eastern, near Guerneville; the Cloverdale, about 8 miles east of Cloverdale; and the Culver-Baer, about 12 miles (20 miles by road) east of the same town, all in Sonoma County. Those whose output was between 400 and 500 flasks are the St. Johns, near Vallejo, Solano County, and the Helen, near Middletown, in Lake County.

Nevada.—The principal mines in Nevada have already been mentioned on page 389. The total yield from this State in 1917 was 997 flasks, nearly half of which came from the Farnham and Drew mine, east of Mina, which closed for lack of ore near the end of the year. The next mine in point of yield, the Goldbanks, is also at present nonproductive.

Idaho.—Only nominal production has been reported from Idaho, but the Fern mine near Yellow Pine, Valley County, is being developed with promising results. The ore occurs as replacement deposits in limestone which is interbedded with quartzite. There are also some prospects in Cassia County, near Black Pine.

Digitized by Google

Montana.—There is an undeveloped deposit of cinnabar near Boulder.

Utah.—Quicksilver was formerly produced as a by-product from cinnabar associated with gold ores of the Mercur district, and from the unusual sulphoselenide ores of mercury near Marysvale.

Arizona.—The deposits of quicksilver ore known in Arizona are at present of so little economic importance that it appears unnecessary in the present brief sketch to describe individual occurrences.

Texas.—The principal mines in the Terlingua district are the Chisos, Mariposa, Big Bend, and Dallas. These all lie nearly on an east-west line, 11 miles long. Another producing mine, the Ellis, is situated about 35 miles east-southeast of Terlingua post office and 6 miles south-southwest of McKinney Springs post office, between the Chisos Mountains and the Rio Grande. The largest and most productive mine is the Chisos, which is opened by three shafts to a depth of 750 feet along a metallized fault zone for a length of about 2,000 feet. The principal source of quicksilver in the ore now mined is cinnabar, but the district is noted for the rare oxychlorides and other secondary mercury minerals formerly abundant in shallow workings. Some of these, so far as known, occur only in this district.

Mexico.—Deposits containing quicksilver are rather widely distributed through Mexico but are not at present very productive, and information concerning the state of the quicksilver-mining industry is difficult to obtain in the existing disturbed condition of the country. The most productive mines are in the State of San Luis Potosi, particularly near Moctezuma, 40 miles north of the city of San Luis Potosi and near Guadalcazar, about 60 miles northeast of the same place. At Guadalcazar the deposits, which prior to the political upheaval in Mexico were yielding from 500 to 700 flasks a year, occur in Cretaceous limestone near porphyry. The principal mines are the Nuevo Potosi and Trinidad. The ores are described as consisting of metacinnabar (guadalcazarite) and cinnabar, with calcite, fluorite, gypsum, and native sulphur.[1]

The ores at Moctezuma are reported to be of fairly high grade and similar in general character to those of the longer-known Guadalcazar district. The output in 1912 was reported to be about 1,200 flasks a year.

The mines near Huitzuco, in the State of Guerrero, have been worked since 1873. The ore occurs as irregular pipelike bodies at enlargements of fissures in middle Cretaceous limestone. These bodies are described by Villarello[2] as from 50 to 80 meters in diameter and up to 250 meters, or possibly more, in depth. The ores consist of livingstonite, pyrite, and free sulphur, with much gypsum and calcite. Occasionally some metacinnabar is found. According to Halse[3] the main shaft of the Santa Cruz mine went through 144

[1] Halse, Edward, Quicksilver mines and reduction works at Huitzuco, Guerrero, Mexico: Fed. Inst. Min. Eng. Trans., vol. 10, pp. 72–88, 1895–1896. Contains notes on Guadalcazar mines.
Rundall, W. H., Mining and treatment of quicksilver ores at Guadalcazar, Mexico: Eng. and Min. Jour., vol. 59, pp. 607–1895.
Mexican quicksilver mining operations: Min. and Eng. World, vol. 37, p. 282, 1912. [Extract from consular report.]

[2] Villarello, J. D., Génesis de los yacimientos de Palomas y Huitzuco en los estados de Durango y Guerrero de la República Mexicana: Soc. cient. "Ant. Alzate" Mem. y. rev., vol. 19. pp. 95–136, 1903.

[3] Halse, Edward, op. cit.

Digitized by Google

feet of gypsum and did not enter wholly unaltered limestone until it attained a depth of 380 feet.

The principal mines at Huitzuco are understood to have belonged to the wife of former President Diaz. Although it is learned that they have not been regularly worked since his overthrow, considerable quantities of mercury are reported to have been brought from Huitzuco to the City of Mexico. This was probably obtained from working the old dumps. A new company, the Cía. minera de Cinabrio, with offices in the city of Mexico, is reported as about to work the Las Negrillas mine, near Huitzuco, with the expectation of producing about 300 flasks a month.

There are at least three quicksilver mines in the State of Zacatecas that have yielded quicksilver, the San Antonio at Ville Garcia, the San Carlos in the municipality of Carro, and the El Puesto at El Puesto. The San Antonio is reported to be well equipped and to be making a small production under the present control of revolutionists. Quicksilver is also recovered in this State near Fresnillo as secondary metal from old patios in which silver ores have been treated by amalgamation.

Quicksilver deposits occur at Palomas, 80 kilometers west of the city of Durango, in the State of that name. They are described by Villarello[1] as irregular, nonpersistent veins in altered rhyolite near intrusive basalt. Cinnabar, a little native quicksilver, and a bituminous mineral are associated with "amorphous silica" (opal?) as gangue. The mean tenor of the ore formerly worked is given as 0.5 per cent.

Occurrences of mercury minerals are known also in the States of Chihuahua, Sonora, Tepic, Jalisco. At San Onofre, in Jalisco, is the type locality of the sulphoselenide of mercury onofrite. Some of the deposits in Chihuahua are understood to belong to the same general group as those in trans-Pecos Texas, but no definite information relating to them has been obtained.

Formerly most of the quicksilver obtained in Mexico was consumed in that country or exported to London. Recently, however, considerable quantities have been sent to the United States.

Central America.—Cinnabar has been reported as occurring in Guatemala, and native quicksilver is found in clay on the Isthmus of Panama.

SOUTH AMERICA.

In South America quicksilver deposits are known in British Guiana, Colombia, Ecuador, Bolivia, Chile, Brazil, Argentina, and Peru, and reported also in Uruguay, Venezuela, and Paraguay. Only those in Peru and Chile appear to be of present economic importance, and the production of Peru in 1916 was only 62 flasks (2.1 metric tons).

The most famous deposits in Peru are those at Huancavelica,[2] particularly those of the Santa Barbara mine. These have been worked since 1566 and are said to have produced 46,500 metric tons (1,366,480 flasks of 75 pounds) before 1790. The production in the nineteenth century has been estimated at 3,500 metric tons (102,865 flasks).

[1] Villarello, J. D., op. cit.
[2] Umlauff, A. F., El cinabrio de Huancavelica: Cuerpo Ing. Minas del Perú Bol. 7, 1904.

Digitized by Google

The ore bodies of the Santa Barbara mine occur on the east flank of the western chain of the Andes in a steeply upturned series of Cretaceous limestones, shales, and sandstones and post-Cretaceous conglomerates. These rocks are cut by andesite and basalt. The ore zone runs north-northwest and has a length of about 50 kilometers. The ore bodies are numerous, irregular, and occur in all of the stratified rocks mentioned, particularly in the sandstone and limestone. The ore is reported to have had a tenor of 2 per cent or more of quicksilver and to have continued to a depth of 190 meters.

In 1915 the greater part of the quicksilver-bearing ground in the Huancavelica district was purchased by Eulogio E. Fernandini, of Lima, and work has already been begun preparatory to a resumption of mining on an extensive scale. The old main tunnel of the Santa Barbara mine had been reopened by the end of 1916 for about 1,150 feet and a new tunnel had been begun about 500 feet below the old tunnel. There was also under construction in that year a hydroelectric plant to supply power to the mine.[1]

At Yauli, in an Andean valley about 120 kilometers east-northeast of Lima, cinnabar and pyrite occur in quartz veins in shales and sandstone in the vicinity of hot sulphur springs.

In Chile, at Punitaqui, in the Province of Coquimbo, quicksilver ores occur in irregular veins closely associated with gold veins and veins carrying copper and tin. The prevailing rocks of the region are syenite and diorite, which are cut and locally metamorphosed by a broad intrusive mass of diabase, in which the quicksilver deposits occur. The quicksilver ores consist of cinnabar, pyrite, chalcopyrite, hematite, chalcocite, and mercurial tetrahedrite in a quartz gangue.[2] These ores, carrying more than 0.4 per cent of quicksilver, were being retorted in 1916 [3] and probably in 1917, although there is no official record of any production of mercury in Chile in 1916, the latest year for which figures are available.

In the same province, near Arqueros, the occurrence of native silver amalgam has long been known [4] and the same mineral is found near Rosilla, in the Province of Atacama. Deposits of sulphide of mercury, presumably cinnabar, are also reported near Petorca, in the Province of Aconcagua.[5]

QUICKSILVER-MINING INDUSTRY BY STATES.

ALASKA.

So far as known, there was no production of quicksilver in Alaska in 1917 and no important activity to record.

ARIZONA.

Arizona produced only 40 flasks in 1917, of which 38 flasks came from the Sunflower district in the Mazatzal Range and 2 flasks from the southern part of the Phoenix Mountains, 9 miles northeast of

[1] Cuerpo Ing. Minas del Perú Bol. 86, p. 127, 1918.
[2] Götting, A., Die Erzgänge zu Punitaqui in Chile, mit besonderer Berücksichtigung der Zinnoberführenden Lagerstätten: Zeitschr. prakt. Geologie, 1894, pp. 224–230.
[3] Lamb, M. R., Flotation for cinnabar: Min. and Sci. Press, vol. 113, p. 6, 1916.
[4] Domeyko, Ignace, Sur les mines d'amalgame natif d'argent d'Aqueros, au Chili: Annales des mines, vol. 20, pp. 255–307, 1841.
[5] Ortúzar, Adolfo, Chile of to-day, New York, 1907.

Digitized by Google

Phoenix. The total production from this State to date has been extremely small, and since 1914, when the furnace of the Cinnabar Development Co., near Quartzsite, Yuma County, was shut down, it has come chiefly from small lots of ore retorted in connection with prospecting.

GILA AND MARICOPA COUNTIES.

In the Mazatzal Range,[1] on both sides of the boundary between Maricopa and Gila counties, prospecting and development has been in operation on a small scale since 1912. In 1917 the claims of the Sunflower Cinnabar Mining Co. were worked for a time under lease to C. N. and M. A. Sears, and the bank of retorts was rebuilt.

Prospecting was in progress in the Phoenix Mountains, Maricopa County, on deposits described by F. C. Schrader[2] as shear zones in schist, carrying cinnabar, metacinnabar, and a little native quicksilver, with quartz, calcite, and iron oxide, the last presumably from pyrite or marcasite. The principal lodes, 3 in number, strike northeast to north-northeast, and the most extensive development work at the close of the year was a shaft 70 feet deep. The deposits are similar in character to those in the Mazatzal Range and have the advantage of greater accessibility.

PIMA COUNTY.

At the Roadside mine in Pima County, Courtney De Kalb, consulting engineer, reported to the Survey in 1915 the presence of cinnabar, native mercury, and mercurial tetrahedrite in copper-silver ore. So far as known, there has been no production of quicksilver from this locality, and the occurrence, like the similar ores described by Lindgren[3] in the Blue Mountains of Oregon, appears to be of scientific rather than economic interest.

YAVAPAI COUNTY.

In Skull Valley, in Yavapai County, the occurrence of cinnabar has long been known[4] and has led to some shallow prospecting. The cinnabar is reported to be associated with quartz in a vein in granite. There appears to have been no activity at this locality in 1917.

YUMA COUNTY.

The mine of the Cinnabar Development Co., near Quartzsite, remained closed.

CALIFORNIA.

PRODUCTION.

Quicksilver mining was actively prosecuted in California in 1917 and yielded 23,938 flasks, valued at $2,521,151. Of this 21,780 flasks

[1] Ransome, F. L., Quicksilver deposits of the Mazatzal Range, Ariz.: U. S. Geol. Survey Bull. 620, pp. 111–128, 1915.
[2] Schrader, F. C., Quicksilver deposits of the Phoenix Mountains, Ariz.: U. S. Geol. Survey Bull. 690–D, pp. 95–109, 1918.
[3] Lindgren, Waldemar, The gold belt of the Blue Mountains of Oregon: U. S. Geol. Survey Twenty-second Ann. Rept., pt. 2, p. 664, 1902.
[4] Blake, W. P., Minerals of Arizona, their occurrence and association: a report to the governor of Arizona, p. 15, Tucson, 1909.

Digitized by Google

was reduced in furnaces, 1,823 flasks in retorts, and 335 flasks was recovered by washing. The output in 1916 was 21,045 flasks, valued at $2,649,355. There was therefore in 1917 a gain of 13.7 per cent in quantity but a loss of 4.8 per cent in value. The output of the State for 1917 was the largest since 1905 and, next to 1916, the record year for high average price, was the greatest in value since 1877. It constituted 66 per cent of the total quicksilver output of the country.

In the following table, which gives the annual yield of quicksilver in California from 1850, when production began, to date, the quantities are recorded in flasks of 76½ pounds to June, 1904, since when they are given as the present standard domestic flasks of 75 pounds.

Quicksilver produced in California, 1850–1917.

Year.	Flasks.	Price per flask.	Value.	Year.	Flasks.	Price per flask.	Value.
1850	7,723	$99.45	$768,052	1885	32,073	$30.75	$986,245
1851	27,779	66.93	1,859,248	1886	29,981	35.50	1,064,325
1852	20,000	58.33	1,166,600	1887	33,760	42.375	1,430,580
1853	22,284	55.45	1,235,648	1888	33,250	42.50	1,370,625
1854	30,004	55.45	1,663,722	1889	26,464	45.00	1,190,880
1855	33,000	53.55	1,767,150	1890	22,926	52.50	1,203,615
1856	30,000	51.65	1,549,500	1891	22,904	45.25	1,036,406
1857	28,204	48.73	1,374,381	1892	27,093	40.71	1,139,595
1858	31,000	47.83	1,482,730	1893	30,164	36.75	1,108,527
1859	13,000	63.13	820,690	1894	30,416	30.70	933,771
1860	10,000	53.55	535,500	1895	36,067	37.04	1,335,922
1861	35,000	42.05	1,471,750	1896	30,765	34.96	1,075,544
1862	42,000	36.35	1,526,700	1897	26,091	37.28	995,040
1863	40,531	42.08	1,705,544	1898	31,092	38.23	1,188,647
1864	47,489	45.90	2,179,745	1899	29,454	47.70	1,404,956
1865	53,000	45.90	2,432,700	1900	26,317	44.94	1,182,686
1866	46,550	53.13	2,473,302	1901	26,720	48.46	1,294,851
1867	47,000	45.90	2,157,300	1902	28,972	43.20	1,251,590
1868	47,728	45.90	2,190,715	1903	30,726	45.29	1,382,523
1869	33,811	45.90	1,551,925	1904	29,217	43.50	1,270,940
1870	30,077	57.38	1,725,818	1905	24,635	36.22	892,280
1871	31,686	63.10	1,999,387	1906	20,310	39.50	802,245
1872	31,621	65.93	2,084,773	1907	17,431	39.60	690,268
1873	27,642	80.33	2,220,482	1908	16,984	44.17	750,183
1874	27,756	105.18	2,919,376	1909	16,078	45.45	730,745
1875	50,250	84.15	4,228,538	1910	17,211	46.51	800,484
1876	72,716	44.00	3,199,504	1911	18,860	46.01	867,749
1877	79,395	37.30	2,961,434	1912	20,524	42.05	863,034
1878	63,880	32.90	2,101,652	1913	15,591	40.23	627,228
1879	73,684	29.85	2,199,467	1914	11,303	49.05	554,414
1880	59,926	31.00	1,857,706	1915	14,283	85.80	1,225,481
1881	60,851	29.83	1,815,185	1916	21,045	125.89	2,649,355
1882	52,682	28.23	1,487,213	1917	23,938	105.32	2,521,151
1883	46,725	28.75	1,343,344				
1884	31,913	30.50	973,347		2,210,852	.....	102,851,913

As usual, San Benito County, in which are situated the New Idria workings, at present the most productive mine in the Western Hemisphere, leads, with nearly half of the total output of the State. It is followed by Santa Clara County, which contains the New Almaden, the largest, deepest, and in total output, the most productive quicksilver mine in California, and the New Guadalupe mine. Third in rank is Sonoma County, with the Cloverdale, Great Eastern, Culver-Baer, and Socrates mines. San Luis Obispo County, in which the Oceanic was the leading mine in 1917, comes fourth, and Lake County, with the Helen, Sulphur Bank, and Big Injun as chief producers but with a number of famous old mines now idle, ranks fifth. Napa County, also containing many old mines that contributed largely to the production of the State in past years, now holds sixth place.

Digitized by Google

Thirty-four operators reported production in California in 1917. Of these, two, the New Almaden Co. (Inc.) and the New Idria Quicksilver Mining Co., were each conducting productive operations at two distinct mines at adjacent localities under one management. At 17 localities the metal was obtained by furnace reduction from mines having considerable development, although at only four of them was the ore hoisted by machinery. At 12 localities it was won by retorts from mines generally but not invariably less developed than those equipped with furnaces. At six localities it was recovered entirely from salvage operations on old dumps or reduction works, usually by gravity concentration and retorting, and at one locality by steam-shovel work on old dumps, followed by gravity concentration and retorting. Altogether, there was mined or handled about 248,000 tons of ore, of which 235,786 tons was treated. About 20,000 tons of this material was moved with a steam shovel at Sulphur Bank, which marks a new departure in quicksilver mining in California. Of the ore treated, 223,069 tons was sent through furnaces and 4,931 tons of new ore and dump concentrates was retorted. At New Almaden 335 flasks of quicksilver was recovered by passing through a washer 7,786 tons of material excavated from the sites of old furnaces.

Quicksilver produced in California, 1917, by counties.

County.	Quantity (flasks of 75 pounds).	Value.	County.	Quantity (flasks of 75 pounds).	Value.
Lake	1,159	$122,066	Solano	515	$54,240
Napa	832	87,626	Sonoma	2,538	267,312
San Benito	11,018	1,160,416	Others [a]	727	76,568
San Luis Obispo	1,366	143,867			
Santa Clara	5,783	609,066		23,938	2,521,151

[a] Includes Colusa, Fresno, Kern, Monterey, Trinity, and Yolo counties, in each of which there was only a single mine productive.

COLUSA COUNTY.

The Manzanita mine, near Wilbur Springs, in the Sulphur Creek district, which has been worked for both gold and quicksilver, was under lease and bond in 1917 to the Cerise Gold Mining Co., but this company's operations were confined to a gold deposit on Cerise Hill a short distance south of the old Manzanita workings and on the opposite side of Sulphur Creek. A little prospecting was done at the old Elgin mine and a few flasks of quicksilver obtained by retorting samples. The Wilbur Hill, Central, Empire, and Wide Awake mines remained idle.

FRESNO COUNTY.

Work at the Mercy mine was resumed in July, but after a three-months' run, during which a small production was made, the furnace was cooled for repairs.

Digitized by Google

KERN COUNTY.

The Cuddeback mine, situated about half a mile northeast of Tehachapi Loop on the Southern Pacific Railroad, near Keene, was productive during the year, the ore being treated in 12 Johnson-McKay retorts.

The deposit in which this mine has been developed is noteworthy as lying outside of the generally recognized quicksilver belt of California and as being, unlike most bodies of quicksilver ore in that State, of recent discovery. In character, also, it is different from all others in the State. The general rock of the vicinity, a rather dark medium-grained granite or granodiorite is cut by a number of rhyolite dikes, of which at least two contain cinnabar. The dike of the Cuddeback mine is about 100 feet wide and at least 500 feet long. It shows nearly vertical, but curved and contorted lamination, and is all more or less altered. The known ore bodies, of irregular form, occur in the dike, near small fissures that are generally nearly parallel with the dike walls. The typical ore is rather soft, altered, chalky rhyolite, colored pink by finely disseminated cinnabar. Cinnabar is stated[1] also to occur as veinlets or seams an eighth of an inch in thickness. The deepest workings, early in 1918, were probably not more than 30 feet below the surface, and ore had been mined at three places within a length of about 500 feet.

KINGS COUNTY.

The Kings Quicksilver Mining Co., working on the Segregation claim, made a very small production in January, with a 20-ton Scott furnace. The mine was closed, however, on February 1, and remained idle for the rest of the year.

LAKE COUNTY.

The Helen, at present the most productive mine in Lake County, was operated successfully throughout the year. During the latter part of 1917 the ore was obtained chiefly from the northwestern part of the mine—in the Santa Maria workings, on the Helen claim—and contained so much pyrite as to cause considerable difficulty in its treatment. The product of the 50-ton Scott furnace was obtained as soot, which necessitated the interruption of furnace operation for periodic clean-ups. The Wall Street mine is about half a mile down the canyon from the Helen, on the road to Middletown, on a lode in serpentine, which is thought by some to be a faulted portion of the Helen lode. There does not appear to be a particle of evidence, however, for this supposed relationship. As usual, the mine, which has a depth of about 90 feet, was worked by the owner unaided and he made a small production from a D retort and a small ingeniously constructed furnace. The Chicago mine, near the Helen, equipped with an unfinished 15-ton Scott furnace of reinforced concrete, remained idle. The Big Injun mine, about 2 miles northwest of the Helen, was active for part of the year and produced some quicksilver with a concentrating table and retorts. About the end of

[1] Gillan, S. L., Cinnabar in the Sierra Nevada: Min. and Sci. Press, vol. 114, p. 79, 1917.

Digitized by Google

the year ore was discovered at the surface about 1 mile northeast of the Big Injun and half a mile south of Anderson Springs. At the date of writing considerable production has already been made from this deposit, now known as the Big Chief. The ore, which, as seen in the initial surface cut, consists of innumerable little stringers of cinnabar in radiolarian chert, has been treated in the Big Injun retorts.

Probably the most interesting development in Lake County during the year was the resumption in June of work on an extensive scale at the famous old Sulphur Bank mine. Here the rock of widespread dumps, estimated to contain at least 800,000 tons of material, consisting chiefly of basalt that has been leached of practically all of its constituents save silica and contains cinnabar and free sulphur, was being handled with a steam shovel, crushed, and subjected to gravity concentration in a 125-ton mill equipped with 4 Deister-Overstrom tables and 2 Risdon-Johnson vanners. The concentrates were being resorted in two benches of twelve 12-inch Johnson-McKay retorts and 4 small D retorts. One or more rotary furnaces have since been added, and concentration will probably be abandoned. The mine is operated under lease by the Sulphur Bank Association and is likely during 1918 to become one of the large producers of the State.

The Mirabel and Great Western mines near Middletown were idle in 1917, with no prospect of a resumption of activity. The Baker mine, 3 miles southeast of Lower Lake, was worked and made a small production from 7 pipe retorts. An inclined shaft was sunk on the vein to a depth of 100 feet. At the Abbott mine, near Wilbur Springs, the 50-ton Scott furnace was operated for a month, and some quicksilver was produced. The mine was idle, however, at the end of the year.

MONTEREY COUNTY.

The Patriquin, near Parkfield, the only productive quicksilver mine in Monterey County, was worked steadily and yielded considerable quicksilver from two benches of 12 pipe retorts, with a total capacity of about 3 tons in 24 hours. The ore occurs in altered serpentine and is mined by very irregular workings to a depth of about 160 feet. No attempt is made to handle rock containing less than 1 per cent of quicksilver, and there has been no systematic underground exploration or development.

NAPA COUNTY.

The old Oat Hill mine, which was worked by the Napa Consolidated Mining Co. from 1867 to 1909 and was one of the larger and more productive mines in the State, was acquired in 1917 under a 20-year lease and bond by Mr. Murray Innes, who immediately began reopening some of the old tunnels and prospecting new ground. The ore in this mine occurs in sandstone[1] of the Franciscan group in

[1] In Becker's well-known monograph on the geology of the quicksilver deposits of the Pacific slope (U. S. Geol. Survey Mon. 13, 1888) the sandstone in the vicinity of the mine is described as covered by a thin sheet of basalt which is represented on the geologic map of Oat Hill by H. W. Turner, published as Plate V of that report. This sheet does not exist, although the surface of the sandstone slopes is littered with loose blocks of basalt that, during the progress of erosion, have rolled or crept down hill from a thick flow of basalt, a remnant of which caps the hill north and west of the mine openings. This flow is the "thick sheet" shown on the edge of the map just mentioned.

Digitized by Google

the immediate vicinity of six or more persistent fissures that strike from west-northwest to north-northwest. A small production was made from the Oat Hill dumps by concentration and retorting. The Knoxville, also known as the Boston and formerly as the Redington, one of the best-known and most productive quicksilver mines in California, remained idle in 1917, although a little metal was retorted from dumps and old furnaces. The Manhattan mine was also unworked.

At the Aetna mine, 12 miles north of St. Helena and about 3 miles southeast of Oat Hill, work was in progress during the second half of the year. Some new buildings were constructed, additional machinery was put in, and the mine was reopened. Production was begun with a 45-ton Scott furnace. At the Twin Peaks mine, between Aetna Springs and Oat Hill, prospecting was in progress on a small scale, but no quicksilver was produced. The Corona mine, between the Twin Peaks and the Oat Hill mines, was idle in 1917. No production was made by the Belle Union mine, near Oakville. The La Joya mine, about 4 miles west of Oakville, was in operation during the year, and yielded considerable quicksilver. The mine is equipped with an old Fitzgerald furnace, with a capacity of about 8 tons, a Livingston patent retort furnace that has not been successfully operated, and 12 Johnson-McKay retorts.

SAN BENITO COUNTY.

As usual, the New Idria and the jointly operated San Carlos mine yielded most of the quicksilver produced in the county, about half of the total quantity coming from each mine. Owing largely to the difficulty of securing trained miners a large part of the ore was obtained by surface and open-cut work.

The ore from the San Carlos is brought to the mill and furnaces at Idria over a Painter aerial tramway 10,000 feet in length, and a similar tramway, 3,500 feet long, to carry ore from above the fifth level of the New Idria mine, was completed at the end of the year. The San Carlos tramway in 1917 was transporting 240 tons a day, but twice this quantity could easily be carried. There were in operation near the end of the year a 200-ton gravity concentrating mill, which was reducing the excess of fine ore to a 12 per cent concentrate, two 88-ton coarse-ore furnaces, and a 60-ton fine-ore Scott furnace. There was under construction a 48-inch by 50-foot rotary furnace with cylindrical redwood-tank condensers, and similar condensers were being gradually substituted for the old brick condensers at the other furnaces. According to the company's published report, the ore treated was a little higher in grade than in 1916.

The Aurora mine, situated a short distance southeast of the New Idria, made an exceedingly small production and was practically idle for most of the year. No production was made by the Alpine, Florence Mac, Hernandez, or Wonder mines, although some prospecting was done at the Alpine.

SAN BERNARDINO COUNTY.

Cinnabar is reported to occur in dikes from 10 to 100 feet in width, near Danby. Shallow prospecting was in progress at the end of the year.

Digitized by Google

SAN LUIS OBISPO COUNTY.

The Oceanic mine, 5 miles east of Cambria, was by far the most productive mine in the county, although the ore is probably the lowest in grade that is worked in California. It was also the only quicksilver mine in operation in the county at the end of 1917. The concentration mill, built at the Oceanic by former lessees, has been abandoned and dismantled by the owner, and all of the ore is now treated in two 50-ton Scott furnaces. The Klau or Karl mine produced some quicksilver early in the year with 2 banks of 12-pipe retorts. No use has been made of the 50-ton Scott furnace since the building inclosing it was destroyed by fire. A small quantity of quicksilver was obtained from the Little Bonanza or Josephine mine. The Huasna mine (Deer Trail claim), situated in Stevens Canyon, 6½ miles east-southeast of Huasna post office, made a small production with 12-pipe retorts from a bunch of good ore in serpentine. At the end of the year no work whatever was in progress at the Klau, Little Bonanza, Belt (Libertad), or Cambria mines.

SANTA BARBARA COUNTY.

In the El Montecito mining district, on Santa Ynez River, north of Santa Barbara, a very small production was made, with retorts, from claims on the Los Prietos lode. The lode has not been examined by any geologist of this Survey, but from all accounts appears to be a persistent and regular zone of metallization between serpentine on the south and sandstone and conglomerate on the north. The deposit is evidently not suited to retort reduction, but might be successfully worked with a furnace. There are five or six groups of claims in the district and three sets of retorts. Work in 1917 was confined chiefly to development and to building roads and trails.

SANTA CLARA COUNTY.

At New Almaden the principal output was from the El Senador or Senator mine, about 4 miles northwest of the famous old workings in Mine Hill. The El Senador ore was reduced in a 45-ton Herreshoff furnace fitted with a Cottrell treater. A 90-ton Scott furnace, however, was under construction, and in June, 1918, use of the older furnace was discontinued, although it is said to have worked fairly well, giving an extraction of about 82 per cent. The ore at the El Senador occurs as lenticular bunches of irregular stringers of cinnabar in altered serpentine, generally near the contact of this rock with sandstone of the Franciscan group. There is much crushing and shearing, and the structure is complex in detail. A notable feature of the ore is the presence of fairly abundant stibnite in fine needles, a mineral not hitherto reported from the quicksilver deposits of Santa Clara County. During the year a new winze was sunk to the 600-foot level and the level was considerably extended.

Some underground work was done in Mine Hill through the Day tunnel (800-foot level), but this had been discontinued at the time of visit, early in 1918. At the old hacienda one small coarse-ore furnace was in operation on miscellaneous lots of ore, but the principal

Digitized by Google

source of quicksilver was material from the site of old furnaces and condensers. The large boulders are picked out and the rest of the material is passed through a revolving screen, whose main function is to loosen the lumps of clay and soil. Oversize and undersize go into the same flume and are delivered to a log washer. Most of the quicksilver settles in the washer and is drawn off. From the washer the tailings go to a pulsating jig, which recovers additional quicksilver and some cinnabar. The jig tailings pass over riffles to the dump.

At the New Guadalupe, whose output of quicksilver was exceeded in California only by the New Idria, production, as in recent years, came from the newer mine on what is known as the Datum vein, a deposit similar in general character and relationships to that of the El Senador. This zone of metallization lies on the northeast side of Capitancillos Creek and runs northwest, or nearly parallel with the creek. The original zone of metallization on which the old Guadalupe mine was opened, lies southwest of the Datum and runs west-northwest, crossing the creek obliquely. In consequence of this fact, the old mine, which has been idle for years, made a great deal of water. The present company completed during the year a large concrete flume to carry off the creek water and early in 1918 had reopened the old mine to the fifth level and had begun to drive a connecting crosscut between the two mines. Some ore is reported to have been found in the course of this work.

There were in use in 1917 one of the two 15-ton coarse-ore furnaces and one of the two originally 24-ton Scott furnaces. All of the furnaces have been modified from their original design and differ from those used elsewhere. The ore, before going to the Scott furnace, passes through a rotary drier in which the temperature is high enough to volatilize some quicksilver, which is conducted into a condensing system common to all of the furnaces.

SISKIYOU COUNTY.

At the Ivanhoe mine near Cinnabar Springs, 10 miles northwest of Gottville, 12 Johnson-McKay retorts were operated for a short time on a few hundred pounds of ore collected in the course of earlier hydraulic washing and on material from prospect dumps, but very little quicksilver was obtained and none was shipped. The deposit consists of landslide material, mainly crushed schist, which is of very low grade as a whole but contains a few stringers of good ore in the schist fragments.

SOLANO COUNTY.

The St. Johns mine continued to make a good record in working low-grade ore, which occurs in dark soft shale, probably Knoxville, at or near the contact with very irregular bodies of light-colored much-altered intrusive rock whose original character has not yet been determined. The original irregularity of the intrusive bodies has been much increased by complex faulting. Close to the ore the shale is generally much harder than elsewhere. The two Neat coarse-ore furnaces were not in use in 1917, all the ore being treated in a Scott furnace with an actual capacity of from 18 to 25 tons. During the

Digitized by Google

year the old brick condensers were replaced by cylindrical redwood tanks horizontally placed.

At the Hastings mine two of the three retorts were in use during the later part of the year, the Neat furnace being idle. The lessees of this mine have since ceased operations.

There appeared to be some possibility that the Brownlie mine between the St. Johns and the Hastings might be reopened.

SONOMA COUNTY.

The Great Eastern, Cloverdale, and Culver-Baer mines were considerable producers in 1917. The United States Mines Development Corporation, operating the Socrates mine, rebuilt the 40-ton Scott furnace, carried out other improvements at the mine, and produced some quicksilver. The company, however, became involved in legal difficulties in connection with the purchase of the property and ceased operations early in 1918.

The ore of the Socrates mine contains a larger proportion of native quicksilver than any other mine now worked in California unless possibly the small deposit at the Rattlesnake. It occurs generally in disturbed sandstone of the Franciscan close to serpentine, which forms the hanging wall.

An inconsiderable production was made by the Rattlesnake mine, which is worked on a small scale. The Eureka mine was idle.

The Great Eastern mine, near Guerneville, had a successful year, a body of good ore having been found in the upper workings. At the beginning of the year the mine was equipped with one 20-ton Scott furnace and one 14-ton Knox-Osborne coarse-ore furnace. The coarse-ore furnace proved unsatisfactory and was replaced by a new 20-ton Scott furnace.

The Cloverdale mine was steadily productive, although the old 25-ton Livermore furnace was evidently permitting considerable loss of quicksilver into the atmosphere. Early in 1918 the control of the Cloverdale mine passed into the hands of Andrew Rocca, well known in California for his long and successful experience in quicksilver mining. The title of the company, however, remains as the Western Mercury Co. The Cloverdale ore consists of cinnabar with a little pyrite or marcasite filling innumerable small fractures in shattered, brittle radiolarian chert of the Franciscan group.

The ore of the Culver-Baer mine was treated in a 14-ton coarse-ore Knox-Osborne furnace, the fine material being saved until enough accumulated to justify a run by the 24-ton Scott furnace. The ore bodies occur in a lodelike mass of ferruginous carbonate rock between walls of sandstone and shale of the Franciscan group. The lode material is altered serpentine.

STANISLAUS COUNTY.

A little development work but no production was reported at the Newhall mine, and there was no activity, so far as could be learned, in the Stayton district.

TRINITY COUNTY.

A very small production was made by lessees from the Altoona mine, near Castella.

Digitized by Google

YOLO COUNTY.

At the January mine, formerly known as the Harrison, considerable development work was carried out, buildings were constructed, machinery installed, a 100-ton gravity-concentration mill built, and four D retorts set up. A small production was made, but operations were limited by shortage of water. The ore occurs in dark opalized serpentine. At the Reed mine a small production was made from old dump material.

IDAHO.

A small production was reported from Idaho in 1917, from the Yellow Pine district in Valley County (formerly parts of Idaho and Boise counties). The following account of deposits in Cassia and Valley counties is based on notes supplied by E. S. Larsen, of this Survey, as the result of a visit made in August, 1918.

CASSIA COUNTY.

The claims of the Valentine Cinnabar Mining Co. are situated in the eastern part of Cassia County, on the eastern slope of the Black Pine Mountains and about 4 miles west of Black Pine post office, which is in Oneida County. The prevailing rock is limestone with some interbedded shale and sandstone. The general dip of the beds is west. No igneous rock occurs near the quicksilver deposit, so far as known.

The deposit, which appears to be parallel to the bedding of the sediments and to lie at the contact between a shaly bed and an overlying limestone layer, has the form of a chimney, lenticular in horizontal section, and only about 10 feet in length along the strike of the sediments. The friable vein material, which is a replacement of the limestone, is made up mostly of barite, with chalcedonic silica and some earthy cinnabar in thin films coating the barite. Small irregular bunches of ore show much more cinnabar than the mass as a whole.

Other prospects in the vicinity were not examined by Mr. Larsen.

VALLEY COUNTY.

In the Yellow Pine mining district, near the heads of Fern and Cinnabar creeks, and about 60 miles east by northeast of Cascade, active prospecting for quicksilver is being carried on by the Fern Quicksilver Mining Co., the Yellow Pine Quicksilver Co., the Monumental Mercury Mines Co. (the old Pringle-Smith prospect), and others. The deposits are in a series of sedimentary rocks made up of alternating limestones and quartzites that strike northwest and have a nearly vertical dip. These sediments have been invaded by a great granitic batholith, and only half a mile west of the prospects and about the same distance to the south the obliquely truncated sediments and the eroded surface of the granite are overlain by a considerable thickness of andesitic lavas. Dikes of quartz latite porphyry cut the sediments. The deposits are irregular replacements in the limestone layers, mostly near their contacts with the quartzites. The cinnabar is crystalline and is closely associated with veinlets of chalcedonic silica but is also present in the adjacent, iron-

Digitized by Google

stained limestone; some pyrite (or marcasite), a very little stibnite, and some copper stains are associated with the cinnabar.

The Fern Quicksilver Mining Co. is working a stockwork of small stringers of chalcedonic silica, and its 12 Johnson-McKay retorts have been treating about 2 tons of ore a day. At the time of visit the retorts had been operated for about two weeks, and the average content of quicksilver won from the ore was a little over 2 per cent.

The principal workings of the Yellow Pine Quicksilver Co. are to the east of the Fern mine and at about the same stratigraphic horizon. Some cinnabar is shown in a few scattered prospect pits, but the main work is being done in a tunnel that is to crosscut a lenslike body of more or less silicified limestone which in outcrop is approximately 250 feet long and 60 feet wide and which shows some cinnabar in a few scattered pits. Below the outcrop the soil yields cinnabar on panning.

The workings of the Monumental Mercury Mines Co. are on Cinnabar Creek, about three-quarters of a mile north of the Fern mine and on a different layer of limestone. This limestone bed is about 150 feet thick, and the lower workings are near its southwest side, while the upper workings, which are about 1,500 feet to the northwest, are near the northeast side. The limestone exposed in the lower workings is brecciated and silicified and shows more or less cinnabar. The upper workings are planned to cut a similar body of silicified limestone about 60 feet by 100 feet on the outcrop. The company is operating 12 screw-top retorts with a capacity of about 14 pounds of ore each, and is preparing to install 52 such retorts, in which it plans to treat about 1 ton of picked ore a day and to operate throughout the winter of 1918–19.

MONTANA.

No quicksilver was produced in Montana in 1917, but a prospect owned by A. G. Lewis and partner about half a mile north of Boulder station, on the Great Northern Railway, and 100 yards from the railway track, was examined by E. S. Larsen. Mr. Larsen states that a coarse-grained granitic rock is traversed by several rudely parallel fissures along which chalcedonic silica has been deposited. A few shallow pits on one of these veins show earthy cinnabar coating fragments of fractured chalcedony, the whole being a foot or so wide.

NEVADA.

The production of quicksilver in Nevada in 1917 was 997 flasks, valued at $105,004, against 2,198 flasks, valued at $276,706, in 1916. Eight operators reported production in 1917, against 10 in 1916. The ore treated amounted to 3,639 tons, and yielded 20.4 pounds to the ton, or 1.02 per cent. The principal factors in bringing about the decreased production in this State were the destruction by fire of the furnace building of the Goldbanks Quicksilver Co. and the exhaustion of the single known ore body of the Nevada Cinnabar Co. near Ione. The Mercury Mining Co., also near Ione, made a much smaller output than in 1916, so that of the only three furnaces in the State one was wholly idle and the other two were operated for only a part of the year. One new deposit was discovered and

Digitized by Google

developed during the year, that on Montgomery Mountain, in Esmeralda County.

Quicksilver produced in Nevada, 1903–1917.

Year.	Quantity (flasks).	Price per flask.	Value.	Year.	Quantity (flasks).	Price per flask.	Value.
1903	65	$45.29	$2,944	1912	2,550	$42.05	$107,228
1904	17	43.50	740	1913	1,645	40.23	66,178
1905	None.	36.22	.....	1914	2,089	49.05	102,465
1906	None.	39.50	.....	1015	2,327	85.80	199,657
1907	None.	39.60	.....	1016	2,198	125.89	276,706
1908	None.	44.17	.....	1917	997	105.32	105,004
1909	316	45.45	14,362				
1910	70	46.51	3,256		12,344	.....	881,761
1911	70	46.01	3,221				

ELKO COUNTY.

The Ivanhoe Cinnabar Co., working at Ivanhoe Springs, about 50 miles in a straight line northwest of Elko and about 90 miles by road, produced a few flasks of quicksilver from shallow workings. The ore was treated in 6 D retorts with sagebrush as fuel. The ore is cinnabar which occurs as irregular stringers and as streaky disseminations in a much-altered, glassy rhyolite flow breccia. The most common kind of alteration is a change of the rhyolite to a cryptocrystalline white rock of flinty texture and splintery fracture. Some of it, however, has been converted to opal, some to fine-grained chalky material of as yet undetermined character, and some to a yellowish siliceous sponge. The cinnabar is widely distributed over an area of 5 or 6 square miles and much of the material is undoubtedly of very low grade, but some of the shallow cuts, particularly one on the Helen No. 1 claim, showed some excellent ore at the time of visit, late in 1917. The impression gained from such work as has been done is that the ore is all comparatively near the surface. Nothing was seen indicative of the persistence of workable deposits to a depth of over 50 feet, although the possible existence of deep ore can not be denied on the slender evidence afforded by the present stage of development. At least three groups of claims besides those of the Ivanhoe Cinnabar Co. were being prospected in 1917.

HUMBOLDT COUNTY.

The Goldbanks mine, 40 miles south of Winnemucca, was worked successfully from the 1st of June until July 10, when the building inclosing the 50-ton Herreshoff furnace was destroyed by a fire supposed to have been of incendiary origin. Prospecting and development were continued throughout the year, but nothing was done to place the furnace again in commission. The typical ore at the Goldbanks is cinnabar, which occurs in small stringers and finely disseminated through an extremely hard light-colored quartzitic rock, which is locally termed quartzite, but which preliminary field examination shows to be almost certainly a silicified rhyolite flow breccia with probably some silicified massive rhyolite. The ore thus far mined constituted an irregular mass about 350 feet long, 100 feet wide, and

Digitized by Google

20 feet thick. This was mined by open-cut methods. The ore, so far as ascertainable at the time of visit late in 1917, probably does not continue as an extensive body below a depth of about 50 feet, but there is still a large quantity of ore exposed in the walls of the pit and the extent of the ore both laterally and downward is far from definitely known.

The only other production reported from Humboldt County was by the Lovelock Quicksilver Mines Co., which operated twelve 12-inch pipe retorts near Antelope Springs, about 22 miles southeast of Lovelock, for a part of the year only. There is a fairly large quantity of low-grade ore in the vicinity of Antelope Springs, of which a considerable part is on land belonging to the Southern Pacific Co. The remainder is divided between three or four owners or groups of owners. The ore occurs mainly as cinnabar dispersed through masses of shattered limestone conglomerate or breccia that rest, as remnants left by erosion, on the crests of ridges and hills of soft shale. It is doubtful whether any of the ore extends to a greater depth than 50 feet, and no indication was seen that any ore occurs in the underlying shale.

MINERAL COUNTY.

About 14 miles east of Mina, in the Pilot Mountains, the Farnham & Drew, or Red Devils mine, worked under lease and bond by the Mina Quicksilver Co., produced a considerable quantity of quicksilver from high-grade ore treated in two D retorts, a bank of 12 pipe retorts being unused. The ore occurs as lenticular bodies in disturbed shale, and some of the best of it is said to contain 1.2 ounces of gold and 44.4 ounces of silver to the ton, with 25 per cent of lead and 18 per cent of quicksilver. Such ore apparently consists mainly of massive rather ocherous cinnabar with carbonate of lead and a yellow powdery mineral that has not yet been studied but which resembles massicot, the yellow oxide of lead. At the time of visit the mine was 150 feet deep on an incline of about 45°. Early in 1918 the lessees exhausted the ore in sight and abandoned operations.

The Lost Steers group, in the same district, was worked in a small way by a lessee who produced some quicksilver from superficial cuts, with a single D retort. The Cinnabar King was idle in 1917, after a total production amounting in all to only about 30 flasks. The general geology of the Pilot Mountains deposits has been described by Knopf.[1]

The Mount Montgomery mine is situated on a spur on the north side of Mount Montgomery, in the White Mountain Range, at an elevation of about 9,100 feet. It is 5 miles by a good mountain road from Mount Montgomery station, on the Carson & Colorado Railroad. The ore occurs in a remnant of a rhyolitic flow, about 250 feet thick, that apparently rests on andesite. The rhyolite, a glassy, brittle variety, has been much fractured and in part altered to a white, pulverulent material. The ore consists largely of a soft, powdery mixture of cinnabar with the altered rhyolite. Work in 1917 consisted chiefly of development and the erection of two D retorts, although a

[1] Knopf, Adolph, Some cinnabar deposits in western Nevada: U. S. Geol. Survey Bull. 620, pp. 59–62, 1916.

Digitized by Google

few tons of ore were retorted at Belleville and yielded some quicksilver.

At Belleville some quicksilver was produced as a by-product in treating tailings for their silver and gold contents.

NYE COUNTY.

No production was reported from the cinnabar deposits east of Beatty, described in 1916 by Knopf.[1] The property of the Denver Bullfrog Cooperative Mining Co., on Meiklejohn Mountain, was sold by the sheriff of Nye County and is now reported to be owned by the Telluride Group Mines Co.

In the Ione district the Nevada Cinnabar Co. made no production. The large ore body in rhyolite, which was worked by open-cut mining, is exhausted, and although some attempts were made in 1917 to find additional ore, these had not been successful at the end of the year.

The Mercury Mining Co., whose mine lies about a mile north of that of the Nevada Cinnabar Co., carried on prospecting during the later part of the year with such success that the 25-ton Scott furnace was started in October and a small production made.

A very brief examination of this mine was made in October, 1917, and the following notes give merely a general characterization of the deposit. The rocks exposed in the vicinity of the mines are impure limestones, hard shales, and a thick bed of very hard siliceous breccia. They are in contact on the west with a broad belt of ancient greenstones and on the east with the Tertiary rhyolites, here faulted down against them. These older rocks are probably of Carboniferous age. The ore occurs near and partly within a neck of coarse agglomerate containing abundant boulders and angular fragments of soft altered rhyolite, the largest 4 or 5 feet in diameter, together with boulders and fragments of the older rocks. This mass of agglomerate probably fills a hole blown through the older rocks by a volcanic explosion at the time of the Tertiary rhyolitic eruptions of the region. The ore in the inclosing rocks is found chiefly as cinnabar in cracks and crevices in shattered limestone, but also to some extent in shale in the limestone. That in the agglomerate generally occurs as an impregnation of the chalky rhyolite boulders with cinnabar.

A very small output of quicksilver was made from a superficial pocket of cinnabar found by prospectors near the crest of the Shoshone Mountains, north of Ione and 12 miles west of Bowler's ranch on Reese River.

OREGON.

Occurrences of cinnabar are widely distributed through Oregon, but only one, that at Blackbutte in Lane County, produced on a considerable scale. Some of the numerous prospects in the southwestern part of the State give promise, however, of becoming productive mines.

DOUGLAS COUNTY.

The Elkhead mine, 6 miles southwest of Blackbutte and the same distance southeast of Yoncalla, near Elkhead post office, lay idle for

[1] Knopf, Adolph, op. cit., pp. 62–67.

Digitized by Google

15 or 16 years, but in 1917 the mine changed hands, the plant was overhauled, and a two months' test run was made with the 20-ton Scott furnace. No production, however, was reported. The ore occurs in soft, bleached, much altered andesitic rock, probably in part at least a tuff, which has been faulted down by a westward-dipping fault so as to be in contact with shale along its eastern boundary. The ore formerly worked formed an irregular flat-lying body about 10 feet thick that extended westward into the hill from the fault and evidently resembled in general character that of the Black Butte mine, presently to be described.

JACKSON COUNTY.

The following note on quicksilver deposits, mostly in Jackson County, is supplied by J. T. Pardee, of this Survey:

Deposits containing quicksilver are reported here and there in a belt 10 or 15 miles wide that extends northward 25 miles or more from a point a few miles northeast of Medford, Oreg. The belt lies from 10 to 20 miles east of the Southern Pacific Railroad and covers part of the western slopes and spurs from the Cascade Mountains in Jackson and Douglas counties. At the north of the area a prospect is reported on Drew Creek, 4 or 5 miles south of Drew post office, Douglas County. It is reached by a road and trail 40 miles long from Riddles and is said to be promising but undeveloped. Another undeveloped prospect is said to lie about a mile south of Rogue River at the mouth of Elk Creek, a point about 30 miles from Medford on the road to Crater Lake. Films and specks of cinnabar are reported by Henry M. Parks, director of the Oregon Bureau of Mines and Geology, as occurring on seams in volcanic tuff at a point about 3 miles southeast of Brownsboro, Jackson County. Within the belt mentioned, however, practically all the deposits that have been developed to any noteworthy extent are in the Meadows mining district north and south of Evans Creek about 20 miles above its mouth at Rogue River on the Southern Pacific Railroad. North of Evans Creek, named in order, are the Little Jean mine owned by Dr. W. P. Chisholm of Gold Hill, the Cinnabar Nos. 1 and 2 claims of B. F. Peart, of Central Point, Oreg., and the Blue Jay, Homestead, Rainier, and other claims of the Rainier Quicksilver Co. The Mountain King mine, owned in Detroit, Mich., is south of the creek on the slope west of Ramsey Canyon and about 2 miles southwest of the Little Jean. In addition, some undeveloped prospects are reported a mile southeast of the Little Jean. The area through which all the different deposits mentioned are distributed is 3 or 4 miles long and a mile or more in width.

The Meadows district is conveniently reached from Gold Hill or Rogue River on the Southern Pacific Railroad by auto roads. The surface is mountainous and moderately rough, the local relief ranging from 500 to 1,500 feet. Streams are fairly numerous and the slopes thickly timbered. There are several farms along Evans Creek.

The prevailing formation is a dark-gray quartz mica schist that grades into shale or argillite on one hand and into sandstone on the other. It is highly inclined and cut by dikes and irregular branching bodies of a moderately fine light-gray porphyry, most of the exposures of which are badly decomposed and rusty with iron oxides. At the Mountain King mine a fine-grained gray granitoid rock is exposed, which is presumably a part of the same body as the porphyry. In places along Evans Creek the schist is also cut by pegmatite dikes.

The main porphyry body extends from a point north of the Homestake claim, where it appears as a dike 100 feet wide, southward a mile or more, where it expands to a width of at least 1,000 feet. A narrower dike several hundred feet long has a general east and west course through the Rainier claim. The Mountain King granite area is irregular, but at least 500 feet wide in places.

The porphyry is severely and the granite moderately sheared and crushed, and so far as they could be observed the predominant shear planes have a general east-west direction.

Along some of the numerous sheared and brecciated zones the porphyry is partly altered to a jaspery quartz that crops out rather prominently. Generally the weathered layer of the crushed porphyry is rich in iron oxides. Here and there small veins and stringers of quartz or of calcite are abundant. Water level appears to be generally within a few feet of the surface.

Digitized by Google

In places the oxidized porphyry breccia shows films and specks of cinnabar on the seams, and some of it in the Rainier lode looks to be fairly rich in quicksilver. Below water level in the Rainier cinnabar, together with much pyrite and some quartz and calcite, fills spaces in the partly silicified breccia. According to reports, a little cinnabar can generally be panned from the surface mantle throughout the area of altered porphyry. As cinnabar was seen at several widely separated places, this statement is probably true.

On the Mountain King, according to Mr. Pardee, there are 8 or 10 tunnels at elevations from 2,400 to 3,000 feet, which are said to have a total length of 2,500 feet. The principal tunnel is on the slope west of Ramsey Creek, at an elevation of 2,550 feet, or 500 feet above that stream. Together with its branches, it has a length of 600 feet and attains a depth of at least 200 feet. Tunnels at points 50 and 150 feet lower aggregate about 400 feet.

The workings examined by Mr. Pardee on the Mountain King showed, in July, 1918, some small veins and stringers of quartz and calcite, some of which are banded with pyrite, and also some rather persistent but narrow zones of breccia. A little cinnabar was seen at one place near the mouth of the tunnel at an elevation of 2,400 feet, and some native quicksilver is said to have been found in this tunnel. No production was reported in 1917.

At the Little Jean mine the 12 Johnson-McKay retorts were reset and a very small production was made. According to H. G. Ferguson, of this Survey, who visited the mine in November, 1917, the Little Jean is about 18 miles north-northwest of Gold Hill, on a branch of Evans Creek, at an elevation of 2,500 feet. The workings are near the top of a rather steep hill and comprise about 300 feet of irregular tunnels with a maximum depth of about 40 feet. The country rock is shale and sandstone, the shale predominating, much sheared and faulted, but generally dipping north to northeast at low angles. The cinnabar, with some native quicksilver, occurs in a gougy fault zone from 3 to 6 inches wide.

No production was reported in 1917 from the Rainier mine, then in possession of the Utah Quicksilver Co. The claims formerly held by this company and some additional ones have since been acquired by the Rainier Quicksilver Co., and active work was in progress in 1918. The following notes are based on information furnished from the field by Mr. Pardee, who visited the mine in July, 1918.

At that time the company was developing the mine on two levels and also preparing to reopen an old shaft on the Homestake claim. The 12 Johnson-McKay retorts were in operation and considerable production had been made.

Workings on the Rainier claim consisted of two short crosscut tunnels, 50 feet apart vertically, with about 200 feet of drifts. The greatest depth reached was about 70 feet. About 1,500 tons of ore, averaging over 1 per cent of quicksilver, of which ore perhaps half would average over 3 per cent, had been blocked out on July 20, 1918, and the outlook for finding large additions to the ore already known seemed good.

LANE COUNTY.

The Black Butte mine, 16 miles south of Cottage Grove, was operated throughout the year on very low grade ore, which was treated in a 36-ton Scott furnace with Dennis patented vitrified pipe condensers. Experiments in flotation were carried out and proved so satisfactory that early in 1918 a flotation mill of about 40

Digitized by Google

tons capacity was added to the plant. The ore occurs as cinnabar, with a little native quicksilver, in a fissure zone in andesite and andesitic breccia, which, near the ore bodies, have been altered to a light-gray to white, rather soft rock with stringers of hard brown material formed by the segregation of iron oxide along cracks. The cinnabar forms small stringers, rarely over an inch in width, and is also distributed as small specks through the altered rock. Marcasite and pyrite are in places associated with the cinnabar and occasionally masses of black, fibrous carbonaceous material, probably carbonized wood, and irregular stringers of stibnite, are found in the workings. The main stope is about 180 feet long, about 15 feet wide, and has been carried from the surface nearly to the 400-foot level. The mine is worked through tunnels, and the ore is carried down to the furnace by an aerial tramway. The total cost of mining and treatment, according to Mr. E. B. Crane, the superintendent, is $2.68 a ton. The furnace consumes from 1½ to 2 cords of wood a day, which costs, delivered, from $2 to $2.50 a cord.

MALHEUR COUNTY.

In the southeast corner of the State, about 11 miles west-northwest of McDermitt, a small town on the Oregon-Nevada line, some prospecting was done on a group of 12 claims over which cinnabar is rather widely distributed. Here a flow of rhyolite, 100 feet or more in thickness, is exposed on the south slope of a basalt-capped ridge and is overlain by hot-spring deposits, patches of leaf-bearing lacustrine shale, with layers of diatomaceous earth, and some sandy tuff beds. The rhyolite is silicified but so far as could be seen from the shallow pits and trenches contains very little cinnabar. The cinnabar occurs chiefly in the porous, siliceous hot-spring sinter and in the lake beds. Not enough work had been done in 1917 to determine whether the deposits have economic value, but they were reported early in 1918 to have been sold, and presumably additional prospecting will be carried on.

TEXAS.

PRODUCTION.

There were 4 producing mines in Texas in 1917, all in Brewster County. The ore treated amounted to 28,242 short tons and yielded 10,791 flasks of quicksilver, valued at $1,136,508. In 1916 25,945 tons yielded 6,306 flasks, valued at $793,862. The production of Texas from the beginning of operations in the Terlingua district to date is given in the following table:

Quicksilver produced in Texas, 1899–1917.

Year.	Quantity (flasks).	Price per flask.	Value.	Year.	Quantity (flasks).	Price per flask.	Value.
1899	1,000	$47.70	$47,700	1910	3,320	$46.51	$154,413
1900	1,800	44.94	80,892	1911	2,326	46.01	107,019
1901	2,932	48.46	142,085	1912	1,990	42.05	83,680
1902	5,319	43.20	229,781	1913	2,750	40.23	110,633
1903	5,029	45.29	227,763	1914	3,144	49.05	154,213
1904	5,336	43.50	232,116	1915	4,417	85.80	378,979
1905	4,723	36.22	171,067	1916	6,306	125.89	793,862
1906	4,761	39.50	188,060	1917	10,791	105.32	1,136,508
1907	3,686	39.60	145,966				
1908	2,382	44.17	105,213		76,200	.....	4,680,295
1909	4,188	45.45	190,345				

Digitized by Google

BREWSTER COUNTY.

The Chisos mine in the Terlingua district continued to be the most productive quicksilver mine in Texas and the second in rank in the United States, being surpassed only by the New Idria in California. It is also the deepest mine in the district.

The Chisos ore bodies occur along a strong curved fault zone with a generally nearly east and west trend. The course of the fault is concave to the north, the dip on the whole nearly vertical, and the downthrow along the main ore-bearing part of the zone apparently nowhere in the mine exceeds 60 feet, although there has evidently been a considerable horizontal component of the movement in the fault plane. The mine has three operating shafts and the workings open the fault zone for a length of about 2,500 feet and to a depth of 750 feet, by levels generally 50 feet apart vertically. The rocks exposed in the mine from the surface downward are the thinly laminated yellowish shales correlated with the Austin chalk, probably not over 50 feet thick at the mine; the thin-bedded, flaggy, more or less sandy shales and limestones known as the Eagle Ford formation, here about 500 feet thick; the Buda limestone, 100 feet thick; the Del Rio clay, 75 to 100 feet thick, and the thick-bedded Edwards limestone. The Austin chalk and Eagle Ford formations are Upper Cretaceous and the Buda limestone, Del Rio clay, and Edwards limestone are Lower Cretaceous. The ore of the Chisos mine occurs chiefly in the Buda limestone, but above the 550-foot level large quantities have been stoped also from the overlying Eagle Ford, and some was found early in 1918 on the 700-foot level in the Edwards limestone, exploration of which at this locality has barely begun, chiefly because it lies below water level. This limestone has supplied most of the ore of the Mariposa and other mines west of the Chisos.

From the surface to the 600-foot level the ore bodies occurred at intervals nearly all along the explored portion of the fault zone, especially where this consists of several fissures or is joined by cross fissures. Below the 600-foot level, however, most of the ore—and the richest that has yet been found in the mine—forms a single remarkable chimney, from 75 to 100 feet in diameter, that extends from a little above the 600-foot level to the 750-foot level and perhaps deeper. Although the 700-foot and 750-foot levels are nearly all in Del Rio clay, the ore chimney is in a mass of shattered Buda limestone, which probably has been faulted down into the clay shale, perhaps as a consequence of the collapse of a solution chamber in the massive Edwards limestone. The ore in this dropped mass is a chaotic breccia consisting chiefly of fragments of Buda limestone with cinnabar, native quicksilver, free sulphur, and marcasite or pyrite, and perhaps other minerals less readily recognizable, as an interstitial filling and as a replacement of some of the smaller limestone fragments. The large output of the Chisos mine during the last three or four years has come almost entirely from this one rich ore body.

The Chisos ore is treated in a skillfully handled 20-ton Scott furnace with brick condensers. A rotary furnace 65 feet long and 54 inches in diameter, with a 12-inch lining of fire brick, was completed some time ago but was reset at a higher angle (7°) early in 1918 and may now be in operation. This furnace has a separate condens-

Digitized by Google

ing system of combined brick chambers with Cermak elliptical vitrified pipes about 12 by 18 inches in section.

At the Mariposa mine (formerly the Marfa and Mariposa) extensive superficial prospecting was carried out, in the course of which considerable quicksilver was produced in one of the two 10-ton Scott furnaces. The mine changed ownership in October, and more extensive work was planned for 1918, including the operation of the 50-ton Scott furnace of the Terlingua Mining Co., whose ground has been leased to the Mariposa Mining Co. All of the ore treated in 1917 was taken from shallow pits and trenches in the Edwards limestone, chiefly on the east side of California Hill, the operations extending over an area about a mile long and half a mile wide. The ore occurs in a broad zone of nearly east-west fissures, some of which are traceable for half a mile or more, although others are much shorter. Many of them, although well defined and accompanied by considerable brecciation near the surface, become very indistinct and carry no ore below a depth of 50 feet or less. A very persistent fissure, that of the Margaret D. vein, lies about 500 yards north of the Mariposa group of fissures, with a curving but generally nearly east and west strike. This shows cinnabar at many places, and was formerly worked at the Colquitt-Tignor mine and, farther west, for a short time by the Mariposa company. The ore shoots are reported to be generally rather narrow and of lower grade than those near California Hill. No underground work was being done in California Hill at the time of visit, in March, 1918, although a large part of the total quicksilver obtained from this mine, said to amount to about 27,000 flasks, was obtained from stopes in this hill, especially from those near the so-called phonolite dike and at or near the contact of the Del Rio clay with the underlying Edwards limestone.

At Study Butte, in the eastern part of the Terlingua district, the Study Butte Mining Co., operating the Big Bend mine, made a fairly large production, exceeded only by that of the Chisos Mining Co., in Texas, and those of the New Idria, New Guadalupe, and New Almaden companies, in California. The ore, after sorting to a little more than half of the material broken, and to a grade slightly above one-half of 1 per cent, was treated in a 50-ton Scott furnace.

At Study Butte the beds of the Eagle Ford formation have been separated by an intrusive sheet, from 400 to 500 feet thick, of light-gray porphyry, whose exact petrographic character has not yet been determined. The porphyry forms the crest of the butte and, with the shales above and below it, dips to the north, apparently at about 60° near the crest of the hill but becoming nearly horizontal at the base of the north slope. The ore occurs on the north side of the butte in and near a series of northwest-southeast fissures, especially for short distances above and below the contact of the porphyry with the overlying shale. The cinnabar in the fissures is generally associated with a calcite gangue.

In the Dallas mine, owned by the Texas Almaden Mining Co. and lying just east of the Big Bend, the ore apparently occurs mainly as a nearly horizontal layer in the Eagle Ford formation, immediately above the porphyry. The Dallas mine, like the Big Bend, is under lease to W. D. Burcham and associates, and preparations were being made early in 1918 to pump it out and resume work.

Digitized by Google

Prospecting for quicksilver was not generally active in the Terlingua district in 1917, but the Rainbow Mining Co., on ground just west of the Chisos mine, was attempting to find an ore shoot in the westward continuation of the Chisos fault zone.

Outside of the Terlingua district the Ellis mine, sometimes called the 34 mine, situated 6 miles south-southwest of McKinney Springs post office, between the Chisos Mountains and the Rio Grande, was opened in June and by the end of the year had made a considerable production with retorts from high-grade ore.

The mine is in the Eagle Ford formation, which in its vicinity contains numerous dikes and intrusive sheets of igneous rocks of various kinds. The ore was discovered at the lower contact of an inclined dike that apparently was intruded along a thrust plane which dips northwest about 35°, or a little more steeply than the beds above and below it. When the ore had been followed down for 50 to 60 feet it was found to turn into a nearly vertical fissure, which in places forms two slightly diverging branches. The ore along this fissure is in places 5 feet wide and continues to the 100-foot level, where another intrusive rock appears in which the fissures are barren. A 50-foot winze from the 100-foot level passes through this rock, and ore was just appearing in a short crosscut under it at the time of visit in March, 1918.

The three retorts in which the ore was being treated in 1917 are of unusual design, consisting of specially cast tubes about 16 inches in diameter and 12 feet long set at an angle of 45°. They are charged at the top, the two end ones every 8 hours and the middle one every 6 hours, and discharge at the bottom. About one-half of the contents are removed before each charging and the total capacity of the three retorts is about 4 tons in 24 hours, with a consumption of 1½ cords of wood. A manifold collects the quicksilver vapor and conducts it into small vitrified pipe condensers. These retorts are said to be satisfactory, and larger ones were to be installed in 1918. They are much more convenient to charge and discharge than the ordinary retorts, but there is probably considerable loss of quicksilver, especially in the operation of charging.

UTAH.

No production of quicksilver was reported in Utah in 1917, although from 1903 to 1907 this State produced 3,338 flasks and the annual production in 1905 rose to 1,133 flasks. Practically all of this came from the Sacramento gold mine in the Mercur district and from the sulphoselenide ores near Marysvale.

WASHINGTON.

There was no output of quicksilver from Washington, and apparently very little prospecting or development work done in that State in 1917.

Digitized by Google

BIBLIOGRAPHY OF QUICKSILVER IN NORTH AMERICA.

Compiled by ISABEL P. EVANS.

This bibliography comprises all references found on the history of the early California quicksilver mines, the occurrence of mercury minerals in North America, the machinery used in handling these minerals, descriptions of mercury lamps, and also articles on the chemistry, physics, and metallurgy of quicksilver. The list of serials comprises only those which have been examined from their beginning to the end of 1917. Reviews have not been included unless they contained original matter.

SERIALS EXAMINED.

Alaska and Northwest Mining Journal. Seattle, Wash.
American Institute of Mining Engineers: Transactions. Philadelphia, Easton, Pa.; New York, N. Y.
American Journal of Science. New York, N. Y.; New Haven, Conn.
Arizona State Bureau of Mines: Annual Report; Bulletin. Tucson, Ariz.
Boston Society of Natural History: Proceedings. Boston, Mass.
British Columbia Mining Record; continued as British Columbia Mining and Engineering Record. Victoria, B. C.
California Academy of Sciences: Proceedings. San Francisco, Cal.
California State Mining Bureau: Annual Report; Bulletin. San Francisco, Cal.
California, University of, Department of Geology: Bulletin. Berkeley, Cal.
Canada, Department of Mines, Mines Branch: Annual Report; Bulletin. Ottawa, Ontario.
Canada Geological Survey: Summary Report. Ottawa, Ontario.
Canadian Mining Institute: Monthly Bulletin; Transactions. Toronto and Ottawa, Ontario.
Canadian Mining Manual. Ottawa and Toronto, Ontario.
Canadian Mining Review; continued as Canadian Mining Journal. Toronto, Ontario.
Colorado Geological Survey: Bulletin. Denver, Colo.
Economic Geology. Lancaster, Pa.
Engineering and Mining Journal. New York, N. Y.
Federated Institution of Mining Engineers: Transactions. *See also* Institution of Mining Engineers. Newcastle upon Tyne, England.
Idaho State Inspector of Mines: Annual Report. Boise, Idaho.
Institution of Mining and Metallurgy: Bulletin; Transactions. London, England.
Institution of Mining Engineers: Transactions. Newcastle upon Tyne, England.
Journal of Industrial and Engineering Chemistry. Easton, Pa.
Manufacturers Record. Baltimore, Md.
Metallgesellschaft: Annual Issue. Frankfort-on-the-Main, Hesse-Nassau, Germany.
Metallurgical and Chemical Engineering. New York, N. Y.
Mexican Mining Journal. Mexico City, D. F.
Mineral Industry. New York and London.
Mines and Minerals or Colliery Engineer. Scranton, Pa. Incorporated with Coal Age, November 6, 1915. New York, N. Y.
Mining American. Denver, Colo.
Mining and Engineering World. Chicago, Ill. Incorporated with Engineering and Mining Journal, January 6, 1917.
Mining and Scientific Press. San Francisco, Cal.
Mining and Statistic Magazine; continued as Mining Magazine and Journal of Geology. New York.
Mining Magazine. London, England.
Mining Magazine. New York, vols. 1–9, 1853–1857; continued as Mining and Statistic Magazine, vol. 10–vol. 11, No. 4, 1858; continued as Mining Magazine and Journal of Geology, etc., 2d ser., vols. 1–2 (whole number, vols. 11–12), November, 1859–January, 1861 [no more published].

Digitized by Google

Mining Magazine. New York, vols. 10–13, 1904–1906; incorporated with Engineering and Mining Journal, Aug. 1, 1906. This magazine is the continuation of the Pacific Coast Miner, which would have begun its tenth volume July 1, 1904, "which explains why the magazine takes this volume and number." (Min. Mag., vol. 10, p. 42, 1904.)
Mining Reporter; continued as Mining Science; continued as Mining American. Denver, Colo.
Mining Science; continued as Mining American. Denver, Colo.
Mining World; continued as Mining and Engineering World. Chicago, Ill. Incorporated with Engineering and Mining Journal January 6, 1917.
Nevada State Mineralogist: Report. Carson, Nev.
Oregon Bureau of Mines and Geology, Mineral Resources of Oregon. Corvallis, Oreg.
Oregon University: Bulletin. Eugene, Oreg.
Salt Lake Mining Review. Salt Lake City, Utah.
Science. New York, N. Y.
Scientific American. New York, N. Y.
Scientific American Supplement. New York, N. Y.
Sociedad científica "Antonio Alzaté": Memorias y Revista. Mexico City, D. F.
Texas Academy of Sciences: Transactions. Austin, Tex.
Texas Geological Survey: Annual Report. Austin, Tex.
Texas Mineral Resources. Austin, Tex.
Texas, University of: Bulletin. Austin, Tex.
United States Geological Survey: Annual Reports; Bulletins; Geological Atlas of the United States, folios; Mineral Resources; Monographs; Professional Papers. Washington, D. C.
Washington (State) Geological Survey: Bulletin. Olympia, Wash.

INDEX TO BIBLIOGRAPHY.[1]

Alaska.
Alaska and Northwest Mining Journal, 1, 2.
Brooks, A. H., 1–8.
Hinckley, F. C., 1.
McCaskey, H. D., 6, 9, 11–13.
Mertie, J. B., jr., and Harrington, G. L., 1.
Mining and Engineering World, 4.
Prindle, L. M., 1.
Smith, P. S., 1.
Smith, P. S., and Maddren, A. G., 1.
Spurr, J. E., and Post, W. S., 1.
Arizona.
Arizona, University of, 1.
Bancroft, H., 1, 2.
Dennis, C. G., 6.
Dennis, C. G., and Bogard, V. E., 1.
Hill J. M., 1.
Horton, F. W., 1.
Joseph, P. E., 1.
McCaskey, H. D., 1, 2, 4–6, 9, 11–13.
Mineral Industry, 6.
Mining and Engineering World, 5.
Mining and Scientific Press, 35.
Ransome, F. L., 6.
Thom, W. T., 3, 4, 6.
Turner, H. W., 5, 6.
Willis, C. F., 1, 2.
British Columbia.
Becker, G. F., 7.
British Columbia Mining Record, 1.
Camsell, C., 1.
British Columbia—Continued.
Dawson, G. M., 1.
Hoffman, G. C., 1–3.
Merritt, W. H., 1.
Mineral Industry, 6.
Monckton, G. F., 1.
Ontario Bureau of Mines, 1.
California.
American Quicksilver Co., 1.
Anonymous, 1, 2.
Arnold, R., and Anderson, R., 1.
Aubury, L. E., 1.
Becker, G. F., 7–10.
Black, G. F., 1, 2.
Blake, W. P., 1–3, 10.
Boalich, E. S., 1–3.
Bradley, W. W., 1–4.
Brown, G. C., 1.
Browne, J. R., 1, 2.
California Senate and Assembly Journal, 1, 2.
California State Mining Bureau, 1–3.
Caslamayomi Rancho, 1.
Castillero, A., 1.
Christy, S. B., 2–4.
Crawford, J. J., 1, 2.
De Kalb, C., 1.
Demaret, L., 1.
Dennis, C. G., 6, 8.
Dennis, C. G., and Bogard, V. E., 1.
Dolbear, S. H., 1.
Eakle, A. S., 2.
Eddy, L. H., 1–8.

[1] The numerals given in this index are the numbers prefixed to the titles of the citations in the bibliography, pp. 432–455. Thus under the heading "Uses" the references to "Becker, G. F., 1" and "Mining and Scientific Press, 26" are, respectively, to the article on quicksilver and fuel by Becker (Min. and Sci. Press, Feb. 13, 1875) and to the article on the Use and care of mercury, published in Min. and Sci. Press for Aug. 17, 1907.

Digitized by Google

California—Continued.
Edwards, C. E., 1.
Egleston, T., 1.
Emmons, W. H., 1.
Engineering and Mining Journal, 1, 3, 5, 9–11, 18, 19, 27.
Fairbanks, H. W., 1.
Forstner, W., 1, 2.
Gillan, S. L., 1.
Goodyear, W. A., 1.
Guadalupe Mining Co., 1.
Hamilton, F., 1–4.
Hanks, H. G., 1–3.
Harper's New Monthly Magazine, 1.
Hart, T. S., 1.
Heberlein, C. A., 1.
Hess, F. L., 1.
Hewett, A. S., 1.
Hill, J. M., 1.
Horton, F. W., 1.
Ingalls, W. R., 1.
Innes, M., 1.
Lake Quicksilver Mining Co., 1.
Lakes, A., 1.
Lake Valley Quicksilver Mining Co., 1.
Landers, W. H., 1, 2.
Lawson, A. C., 1.
LeConte, J., and Rising, W. B., 1.
Lindgren, W., 1.
Lindgren, W., and Turner, H. W., 1, 2.
Lowell, F. L., 1, 2.
Lyman, C. S., 1.
Lytle, J. A., 1.
McCaskey, H. D., 1–7, 9, 11–13.
McGarrahan, W., 1, 2.
McNeely, W. M., 1.
Mason, R. B., 1.
Melville, W. H., 1.
Melville, W. H., and Lindgren, W., 1.
Metallgesellschaft, 1–8.
Mineral Industry, 1–5, 8, 13–14, 16, 18–20.
Mining American, 3.
Mining and Engineering Review, 2.
Mining and Engineering World, 3, 9.
Mining and Scientific Press, 1, 3–13, 15–18, 21–24, 28, 36, 41–42.
Mining and Statistic Magazine, New York, 1–4.
Mining Magazine, New York, 1–5.
Mining Magazine and Journal of Geology, 1.
Mining Science, 2, 5.
New Almaden mine, 1–5.
New Idria Mining Co., 1.
Newcomb, B. M., 1.
Newland, D. H., 1.
Nöggerath, A., 1.
Osmont, V. C., 1.
Panoche Grande Quicksilver Mining Co., 1.
Panoche Grande Rancho, 1.
Parker, E. W., 1–3.
Phillips, J. A., 1.
Phillips, J. A., and Louis, H., 1.

California—Continued.
Place, R. G., 1.
Pošepný, F., 1, 2.
Powell, J. W., 1–4.
Purnell, S., 1.
Quicksilver Mining Co., 1–17.
Randol, J. B., 1–9.
Ransome, F. L., 1.
Rath, G. v., 1.
Raymond, R. W., 1–4, 5–7, 9–10.
Revista Semanal, 1.
Ries, H., 1.
Rogers, A. F., 1, 2.
Rolland, G., 1.
Salt Lake Mining Review, 4.
San Francisco Commercial Herald, 1.
Santa Clara Mining Association, 1.
Shaw, C. P., 1.
Silliman, B., jr., 1.
Skidmore, W. A., 1, 2.
Storms, W. H., 1.
Struthers, J., 1–3.
Thom, W. T., 1–5.
Turner, H. W., and Ransome, F. L., 1.
Tyson, P. T., 1.
Van Wagenen, T. F., 1.
Veatch, J. A., 1.
Vivian, W., 1.
Wagoner, L., 1, 2.
Walcott, C. D., 1–4, 6–7, 9–11.
Watts, W. L., 1–6.
Wells, W. V., 1.
Whitney, J. D., 3–5.
Williams, A., jr., 1, 2, 4, 5, 7.
Yale, C. G., 1–11.
Canada. *See also* British Columbia, Nova Scotia, and Ontario.
Buisson, A., 1.
Colquhoun, A. L., 1.
Hore, R. E., 1.
Hunt, T. S., 1.
McLeish, J., 1–5, 6.
Mineral Industry, 6–11, 15.
Young, G. A., 1.
Chemistry and physics.
Baly, E. C. C., 1.
Becker, G. F., 5, 7–10.
Blagden, Charles, 1.
Broderick, T. M., 1.
Burdick, A. J., 1.
Carson, J. P., 1.
Chemical Society, London, 1.
Chism, R. E., 1.
Clarke, F. W., 1, 2.
Colvin, V., 1.
Davis, H. S., 1.
Dunnicliffe, H. B., 1.
Emmons, W. H., 3.
Engineering, 1.
Engineering and Mining Journal, 2.
Forbes, G. S., and Richter, H. W., 1.
Grout, F. E., 1.
Hanks, H. G., 5.
Horton, F. W., 1.
Hovey, E. O., 1.
Huff, W. B., 1.
Hutchins, T., 1, 2.

Digitized by Google

Chemistry and physics—Continued.
Imperial Institute, London, 1.
Jameson, R., 1.
Jamieson, G. S., 1.
Lake Valley Quicksilver Mining Co., 1.
LeConte, J., and Rising, W. B., 1.
Lindgren, W., 2, 5–7.
McLennan, J. C., 1.
Mallet, J. W., 1.
Mellor, J. W., 1.
Mineral Industry, 5, 11.
Mining and Scientific Press, 43.
Ostwald, W., 1.
Penfield, S. J., 1.
Pošepný, F., 1, 2.
Raymond, R. W., 4.
Rickard, T. A., and Ralston, O. C., 1.
Schaller, W. T., 1.
Schrauf, A., 1.
Scientific American, 2.
Scientific American Supplement, 1–3.
Smith, S. W. J., and Moss, H., 1.
Stillman, M. H., 1.
Tate, J. T., 1.
Wilhelm, R. M., 1.

Colorado.
Emmons, W. H., 1.
Endlich, F. M., 1.
Freeman, H. C., 1.
Mineral Industry, 4.
Smith, J. A., 1.
Williams, A., jr., 2, 7.

Demand.
Engineering and Mining Journal, 15, 16, 26.
McCaskey, H. D., 1–2, 4–6, 9–13.
Manufacturers Record, 1.
Mining and Scientific Press, 4, 26, 29, 40, 42.
Mining Science, 3.
Raymond, R. W., 5, 6.
Smith, G. O., 2.
Yale, C. G., 2–3, 5–10.

Description.
Achiardi, A. d', 1.
Allen, E. T., and Crenshaw, J. L., 1.
Bagley, W. S., 1.
Beck, R., 1.
Becker, G. F., 4, 10.
Browne, J. R., 1.
Butler, G. M., 1.
Egleston, T., 1.
George, R. D., 1, 2.
Hanks, H. G., 4.
Haverstock, R. S., 1.
Joseph, P E., 1.
Lindgren, W., 7.
McCaskey, H. D., 5.
Mining and Scientific Press, 20.
Moses, A. J., and Parsons, C. L. 1.
Penfield, S. J., 1.
Phillips, J. A., 1.
Richardson, C. H., 1.
Ries, H., 1.

Description—Continued.
Spencer, L. J., 1.
Van Wagenen, T. F., 1.
Whitney, J. D., 1.
Young, G. A., 1.

Geology.
Becker, G. F., 2, 3, 6, 7–10.
Blake, W. P., 5.
Broderick, T. M., 1.
Browne, J. R., 1.
Christy, S. B., 1.
Clevenger, G. H., 1.
Durand, F. E., 1, 2.
Emmons, S. F., and Becker, G. F., 1.
Emmons, W. H., 2, 3.
Joseph, P. E., 1.
Kemp, J. F., 2.
King, C., 1.
Krusch, P., 1.
Le Conte, J., 1, 2.
Le Conte, J., and Rising, W. D., 1.
Lindgren, W., 6–8.
McCaskey, H. D., 6–8.
Moore, G. E., 1.
Pardee, J. T., and Hewett, D. F., 1.
Phillips, W. B., 13.
Pošepný, F., 1.
Richardson, C. H., 1.
Schrauf, A., 1.
Turner, H. W., 9.
Udden, J. A., 2, 3.
Van Wagenen, T. F., 1.
Veatch, J. A., 1, 2.
Virlet d'Aoust, P. T., 1.
Wagoner, L., 2.
Weaver, C. E., 1.
Weed, W. H., 1, 2.
Whitney, J. D., 1.

Idaho.
Becker, G. F., 7.
Bell, R. N., 1, 2.
Blake, W. P., 4.
McCaskey, H. D., 6, 9, 11–13.
Williams, A., jr., 7.

Machinery and lamps.
Becker, G. F., 1.
Brown, C. F., 1.
Dennis, C. G., 1.
Desha, L. J., 1.
Egleston, T., 1.
Electrical Review and Western Electrician, 1.
Electrical World, 1.
Emmet, W. L. R., 1, 2.
Engineering and Mining Journal, 21–23.
Fawcett, W., 1.
Geary, J. W., 1.
Hageman, I., 1.
Horton, F. W., 1.
James, G. A., 1.
Knipp, C. T., 1, 2.
Kraus, C. A., 1.
Langmuir, I., 1.

Digitized by Google

Machinery and lamps—Continued.
Metallurgical and Chemical Engineering, 1.
Mineral Industry, 4, 10, 11.
Newman, J., 1.
Patten, H. E., and Mains, G. H., 1.
Purnell, S., 1.
Robertson, M., 1.
Scientific American, 1.
Struthers, J., 2.
Williams, A., jr., 1.

Maps.
Gannett, H., 1.
Geary, J. W., 1.
Hill, R. T., 1.
Map of Alaska, 1.
Topographic map, Brewster County, Tex., 1.
Topographic map, Brewster and Presidio counties, Tex., 2.

Metallurgy.
Aubury, L. E., 2.
Austin, L. S., 1.
Booth, F. J., 1.
Carey, E. E., 1.
Christy, S. B., 2–4.
Clennell, J. E., 1.
Dennis, C. G., 2, 5–7.
Dennis, W. B., 3.
Egleston, T., 1, 2.
Engineering and Mining Journal, 7, 8, 20.
Feust, A., 1.
Geary, J. W., 2.
Hague, A., 1.
Hamilton, E. M., 1.
Hanks, H. G., 3.
Heberlein, C. A., 1.
Hewitt, A. S., 1.
Horton, F. W., 1.
Imperial Institute, London, 1.
Janin, L., jr.
Juretzka, F., 1.
Lamb, M. R., 1.
Landers, W. H., 3.
Lang, H., 1.
McCaskey, H. D., 1, 13.
McNeely, W. M., 1.
Mactear, J., 1.
Mexican Mining Journal, 1, 2.
Mineral Industry, 4, 8, 15–17.
Mining American, 3.
Mining and Engineering Review, 1.
Mining and Engineering World, 7, 8.
Mining and Scientific Press, 2, 14, 19, 24, 25, 34, 39, 45.
Mining Journal, London, 1.
Moore, G. E., 1.
Mosher, D., 1.
Mulholland, C. A., 1–3.
Murray, B. L., 1, 2.
Northey, G. V., 1.
Prather, J. K., 1.
Purnell, S., 1.

Metallurgy—Continued.
Raymond, R. W., 8.
Richardson, C. H., 1.
Scott, R., 1.
Seamon, W. H., 1.
Sharwood, W. J., 1, 2.
Smith, R. O., 1.
Spirek, V., 1.
Stovall, D. H., 3.
Strauss, L. W., 1.
Struthers, J., 2.
Symington, R. B., 1.
Szilard, B., 1.
Thornhill, E. B., 1–4.
Turner, H. W., 4–6, 8.
Watson, R. B., 1.
Whitton, W. W., 1.

Mexico.
Aguilera, J. G., 1.
Babb, P. A., 1.
Barriga, M. D., 1.
Blake, W. P., 9.
Bonney, W. L., 1, 2.
Brush, G. J., and Comstock, W. J., 1.
Capilla, A., 1.
Castillo, A. del., 1, 2.
Collins, H. F., 1.
Encyclopaedia Britannica, 1.
Engineering and Mining Journal, 14.
Flores, T., 1.
Gabb, W. M., 1.
Galeoti, H., 1.
Halse, E., 1, 2.
Hill, R. T., 1.
Hillebrand, W. F., 1.
Hillebrand, W. F., and Schaller, W. T., 1.
Humboldt, A., 1.
Laguerenne, T. L., 1.
McNeely, W. M., 1.
Merrill, F. J. H., 1.
Mineral Industry, 1–13, 15, 16.
Mining and Engineering World, 1.
Mining and Scientific Press, 27, 30.
Mining Reporter, 2.
Newland, D. H., 1.
Nöggerath, A., 1.
Phillips, J. A., and Louis, H., 1.
Ramirez, S., 1, 2.
Rangel, M., 1.
Raymond, R. W., and Ingalls, W. R., 1.
Revista Semanal, 1.
Rundall, W. H., 1.
Sandberger, F., 1.
Sanford, S., and Stone, R. W., 1.
Struthers, J., 2.
Thomas, K., 1.
Van Wagenen, T. F., 1.
Villarello, J. D., 1–3.
Whitney, J. D., 1.

Montana.
Emmons, W. H., 3.
Emmons, W. H., and Calkins, F. C., 1.

Digitized by Google

Nevada.
Becker, G. F., 7.
Blake, W. P., 7.
Burgess, J. A., 1.
Davis, W. C., 1.
Dennis, C. G., 6, 8.
Dennis, C. G., and Bogard, V. E., 1.
Eakle, A. S., 1.
Emmons, W. H., 3.
Engineering and Mining Journal, 11, 17, 24.
Higgins, W. C., 1.
Hill, J. M., 1.
Horton, F. W., 1.
Knopf, A., 1.
Lindgren, W., 5, 8.
McCaskey, H. D., 1–2, 4–6, 8–9, 11–13.
Mineral Industry, 6, 16.
Mining American, 1.
Mining and Scientific Press, 42.
Parker, E. W., 2, 3.
Powell, J. W., 1.
Ransome, F. L., 2–5.
Raymond, R. W., 7, 9.
Salt Lake Mining Review, 2.
Shockley, W. S., 1.
Thom, W. T., 4–6.
Turner, H. W., 6, 7, 9.
Walcott, C. D., 6, 10, 11.
Whitehill, H. R., 1.
Whitney, J. D., 2.
Williams, A., jr., 2, 7.

Nova Scotia.
Becker, G. F., 7.
How, H., 1.

Ontario.
Miller, W. G., 1.
Ontario Bureau of Mines, 2.
Thornhill, E. B., 4.

Oregon.
Butler, G. M., and Mitchell, G. J., 1.
Crane, E. B., 1.
Demaret, L., 1.
Dennis, C. G., and Bogard, V. E., 1.
Dennis, W. B., 1, 2.
Diller, J. S., and Kay, G. F., 1.
Emmons, W. H., 2.
Hill, J. M., 1.
Horton, F. W., 1.
Lindgren, W., 2, 3.
McCaskey, H. D., 1–2, 4–6, 9, 11–13.
Mineral Industry, 16.
Mining and Scientific Press, 37.
Mitchell, G. J., 1.
Newland, D. H., 1.
Oregon Bureau of Mines and Geology, 1.
Pardee, J. T., and Hewett, D. F., 1.
Parks, H. M., 1.
Parks, H. M., and Swartley, A. M., 1.
Raymond, R. W., 9.
Stafford, O. F., 1.
Stovall, D. H., 1, 2, 4.
Struthers, J., 2, 3.

Oregon—Continued.
Thom, W. T., 1, 3, 4.
Todd, A., 1.
Turner, H. W., 5–7.
Walcott, C. D., 3, 7.
Wendeborn, B. A., 1.
Williams, A., jr., 7.
Winchell, A. N., 1.

Prices.
Becker, G. F., 7, 10.
Boutwell, J. M., 1.
Bradley, W. W., 4.
Browne, J. R., 2.
Day, D. T., 1–14, 16–25.
Dennis, C. G., 3, 4–8.
Eddy, L. H., 1–8.
Emmons, S. F., 1.
Emmons, S. F., and Becker, G. F., 1.
Engineering and Mining Journal, 16, 18, 25.
Hanks, H. G., 3.
Horton, F. W., 1.
Imperial Institute, London, 1.
Joseph, P. E., 1.
Kemp, J. F., 1.
Krusch, P., 1.
Lowell, F. L., 1.
McCaskey, H. D., 1–2, 4–6, 9, 11–13.
McLeish, J., 1–5, 6.
Metallgesellschaft, 1–8.
Mining and Scientific Press, 42.
Mining Industry, 1–22.
Pickering, A. H., 1.
Pitaval, R., and Ganet, L., 1.
Powell, J. W., 2–5.
Randol, J. B., 2–9.
Raymond, R. W., 1–3, 5–7, 9–10.
Smith, P. S., 1.
Struthers, J., 2–5.
Thom, W. T., 1–6.
Turner, H. W., 7–9.
Walcott, C. D., 1–11.
Williams, A., jr., 1, 3–6.
Yale, C. G., 1, 3–10.

Santo Domingo.
Courtney, W. S., 1.

Texas.
Blake, W. P., 8.
Burcham, W. D., 1.
Canfield, F. A., Hillebrand, W. F., and Schaller, W. T., 1, 2.
Cummins, W. F., 1.
Davis, L. H., 1.
Day, D. T., 15.
Demaret, L., 1.
Dennis, C. G., 1, 5, 6, 8.
Dennis, C. G., and Bogard, V. E., 1.
Dinsmore, C. A., 1.
Emmons, W. H., 3.
Hill, B. F., 1–3.
Hill, J. M., 1.
Hill, R. T., 1, 2.
Hornaday, W. D., 1.
Horton, F. W., 1.

Digitized by Google

Texas—Continued.
Kirk, M. P., 1.
Kirk, M. P., and Malcolmson, J. W., 1.
Koch, W. E., 1.
McCaskey, H. D., 1–2, 4–6, 9, 11–13.
Mineral Industry, 4, 8, 13, 14, 20.
Mining and Scientific Press, 32, 42, 44.
Mining Reporter, 1.
Moses, A. J., 1, 2.
Newland, D. H., 1.
Parker, E. W., 1–3.
Phillips, W. B., 1–12, 14–23, 24.
Ries, H., 1.
Schaller, W. T., 1.
Simonds, F. W., 1.
Spalding, E. P., 1.
Struthers, J., 1–3.
Texas Mineral Resources, 1.
Thom, W. T., 1–5.
Turner, H. W., 2–3, 5–7, 9.
Udden, J. A., 1–3.
Udden, J. A., and Baker, C. L., 1.
Walcott, C. D., 6, 7, 9–11.

United States.
Becker, G. F., 7, 10.
Boutwell, J. M., 1.
Clark, M. B., 1.
Day, D. T., 1–14, 16–25.
Dennis, C. G., 3–8.
Dennis, C. G., and Bogard, V. E., 1.
Dunlop, J. P., 1.
Eddy, L. H., 1–8.
Emmons, S. F., 1.
Emmons, S. F., and Becker, G. F., 1.
Engineering and Mining Journal, 12, 13, 16.
Horton, F. W., 1.
Imperial Institute, London, 1.
Joseph, P. E., 1.
Kemp, J. F., 1.
Krusch, P., 1.
Lowell, F. L., 1.
McCaskey, H. D., 1–2, 4–6, 9–13.
Metallgesellschaft, 1–8.
Mineral Industry, 1–21.
Mining American, 2.
Mining and Engineering World, 3, 6.
Mining and Scientific Press, 31, 38, 40.
Mining Science, 4.
Newland, D. H., 1.
Nöggerath, A., 1.
Parker, E. W., 1–3.
Phillips, J. A., and Louis, H., 1.
Pickering, A. H., 1.
Powell, J. W., 5.
Randol, J. B., 7.
Raymond, R. W., and Ingalls, W. R., 1.
Ries, H., 1.
Salt Lake Mining Review, 2.
Schrader, F. C., Stone, R. W., and Sanford, S., 1.
Schrauf, A., 1.
Smith, G. O., 2.

United States—Continued.
Struthers, J., 1–5.
Thom, W. T., 1–5.
Turner, H. W., 5–7, 9.
Walcott, C. D., 5, 8, 9.
Whitney, J. D., 1.
Williams, A., jr., 1, 3–6.

Uses.
Becker, G. F., 1, 7, 10.
Bradley, W. W., 4.
Colvin, V., 1.
Dennis, C. G., 8.
George, R. D., 2.
Hanks, H. G., 2.
Horton, F. W., 1.
Imperial Institute, London, 1.
McCaskey, H. D., 1, 2, 6, 7, 9, 11–13
Mining American, 2.
Mining and Scientific Press, 26, 42.
Mining Science, 3.
Pitaval, R., and Ganet, L., 1.
Richardson, C. H., 1.
Ries, H., 1.
Salt Lake Mining Review, 3.
Smith, P. S., 1.
Van Wagenen, T. F., 1.
Williams, A., jr., 4, 5.
Wolf, A. G., 1.

Utah.
Beason, L. H., 1.
Becker, G. F., 7.
Blake, W. P., 6.
Brush, G. J., and Comstock, W. J., 1.
Demaret, L., 1.
Emmons, W. H., 3.
Horton, F. W., 1.
Lindgren, W., 4.
McCaskey, H. D., 1–2, 4–6, 9, 11–13.
Mining Magazine, New York, 1.
Struthers, J., 2.
Thom, W. T., 1, 2.
Williams, A., jr., 7.

Washington.
Dennis, C. G., and Bogard, V. E., 1.
McCaskey, H. D., 4, 6, 9, 11–13.
Mining and Scientific Press, 33.
Smith, G. O., 1.
Weaver, C. E., 1.

World's production.
Becker, G. F., 7, 10.
Boutwell, J. M., 1.
Dennis, C. G., 6–8.
Eddy, L. H., 1–8.
Engineering and Mining Journal, 16.
Horton, F. W., 1.
Imperial Institute, London, 1.
Joseph, P. E., 1.
Krusch, P., 1.
Lindgren, W., 7.
McCaskey, H. D., 1–2, 4–6, 9–13.
Metallgesellschaft, 1–8.
Mineral Industry, 1–21.
Mining and Engineering World, 2, 6.

Digitized by Google

World's production—Continued.
Mining and Scientific Press, 29, 31, 38.
Mining Magazine, New York, 6.
Newland, D. H., 1.
Pickering, A. H., 1.
World's production—Continued.
Pitaval, R., and Ganet, L., 1.
Struthers, J., 1–5.
Turner, H. W., 5–7.
Van Wagenen, T. F., 1.
Williams, A., jr., 1, 4–6.

BIBLIOGRAPHY.

Achiardi, Antonio d'. 1. I metalli loro minerali e minere [mercurio]; vol. 1, pp. 100–110, 120–124, 1883.

Aguilera, J. G. 1. The geographical and geological distribution of the mineral deposits of Mexico [mercury]: Am. Inst. Min. Eng. Trans., vol. 32, pp. 508–509, 1902.

Alaska and Northwest Mining Journal. 1. Quicksilver deposits in Alaska: Vol. 7, No. 4, pp. 73–74, 1 fig., October, 1915.

——— 2. Quicksilver in Jackson County, Oreg.: Vol. 11, No. 1, p. 4, July, 1917.

Allen, E. T., and Crenshaw, J. L. 1. The sulphides of zinc, cadmium, and mercury; their crystalline forms and genetic conditions [metacinnabar]: Am. Jour. Sci., 4th ser., vol. 34, pp. 373–381, 1912.

American Quicksilver Co. of California. 1. Mercury, 29 pp., New York, 1849. Pamphlet.

Anonymous. 1. History of the mineral and allodial titles of the quicksilver mines on the Rancho de los Capitancillos, about 60 miles from San Francisco, in Santa Clara County, Cal., 16 pp., New York, 1858. Pamphlet.

——— 2. Exploits of the Attorney General in California, by an early Californian; dated August 10, 1860, 80 pp., New York, 1860. Gives a brief history of the quicksilver mines of California and the early claimants to them. Pamphlet.

Arizona, University of. 1. Mineralogy of useful minerals in Arizona [cinnabar]: Bull. 41 (Econ. ser. 11), p. 30, 1916–1917.

Arnold, Ralph, and Anderson, Robert. 1. Geology and oil resources of the Coalinga district, Cal. [investigation of quicksilver]: U. S. Geol. Survey Bull. 398, p. 16, 1910.

Aubury, L. E. 1. The quicksilver resources of California: California State Min. Bur. Bull. 27, 273 pp., 50 pls., 94 figs., 8 maps, 1903.

——— 2. Metallurgy of quicksilver: Min. World, vol. 19, pp. 20–22, 8 figs., Dec. 5; pp. 21–22, 9 figs., Dec. 12, 1903.

Austin, L. S. 1. The metallurgy of the common metals [mercury], 2d ed., pp. 126–127, 244, San Francisco, 1909.

Babb, P. A. 1. Dulces Nombres quicksilver deposit, Mexico: Eng. and Min. Jour., vol. 88, pp. 684–686, 4 figs., Oct. 2, 1909.

Bagley, W. S. 1. Descriptive mineralogy: Determinative mineralogy [mercury], pp. 52, 62–63, 489, New York and London, 1917.

Baly, E. C. C. 1. Inorganic chemistry [critical temperature of mercury]: Chem. Soc. Ann. Rept., vol. 12, p. 44, 1916.

Bancroft, Howland 1. Notes on the occurrence of cinnabar in central western Arizona: U. S. Geol. Survey Bull. 430, pp. 151–153, 1910.

——— 2. Reconnaissance of the ore deposits in northern Yuma County, Ariz. [quicksilver and cinnabar]: U. S. Geol. Survey Bull. 451, pp. 44–45, 84, 1911.

Barriga, M. D. 1. Mining in Mexico [cinnabar]: Mining Jour. (London), vol. 77, p. 455, Apr. 29, 1905.

Beason, L. H. 1. Quicksilver from Sacramento mine, Mercur district, Utah: Mineral Industry, vol. 15, p. 357, 1907.

Beck, Richard. 1. The nature of ore deposits, vol. 2, pp. 350–360, 1905. [Trans. by W. H. Weed.]

Becker, G. F. 1. Quicksilver and fuel: Min. and Sci. Press, vol. 30, pp. 98, 102, Feb. 13, 1875.

——— 2. The relations of the mineral belts of the Pacific slope to the great upheavals: Am. Jour. Sci., 3d ser., vol. 28, pp. 209–212, 1884.

——— 3. Geology of quicksilver: U. S. Geol. Survey Fourth Ann. Rept., pp. 40–41, 1884.

——— 4. Statistics and technology of the precious metals; geological sketch of the Pacific division [cinnibar, metacinnabarite, and quicksilver]: Tenth Census of the United States, vol. 13, pp. 10, 15, 16, 23–28, 1885.

Digitized by Google

Becker, G. F. 5. Natural solutions of cinnabar, gold, and associated sulphides: Am. Jour. Sci., 3d ser., vol. 33, pp. 199–210, 1887.
———6. Geology of the quicksilver deposits of the Pacific slope: U. S. Geol. Survey Seventh Ann. Rept., pp. 93–94, 96, 1888.
———7. Geology of the quicksilver deposits of the Pacific slope: U. S. Geol. Survey Mon. 13, 486 pp., 7 pls., and atlas of 14 sheets folio, 1888.
———8. Summary of the geology of the quicksilver deposits of the Pacific slope: U. S. Geol. Survey Eighth Ann. Rept., pt. 2, pp. 961–985, pls. lxii–lxiii, 1889.
———9. Investigations of quicksilver deposits of the Pacific slope: U. S. Geol. Survey Ninth Ann. Rept., pp. 100–101, 1889.
———10. Quicksilver ore deposits: U. S. Geol. Survey Mineral Resources, 1892, pp. 139–168, 1893.
Bell, R. N. 1. Mining industry of Idaho [mercury]: Idaho State Inspect. Mines Fourteenth Ann. Rept., p. 47, 1912.
———2. Quicksilver: Idaho State Inspect. Mines Nineteenth Ann. Rept., pp. 95–96, 1917.
Black, J. S. 1. Report of the Attorney General [on the New Almaden quicksilver mine] to the President on the resolutions of the Legislature of California, 10 pp., Washington, 1860.
———2. The notes on the history of quicksilver in California, in the case of the United States *vs.* Andreas Castillero, decided by the Supreme Court, December term, 1862: U. S. Supreme Court Repts., vol. 67 [vol. 2 of Black series], pp. 42, 84–88, 147–148, 349, 1862 [1863].
Blagden, Charles. History of the congelation of quicksilver: Philos. Trans., vol. 73, pp. 329–397, 1783.
Blake, W. P. 1. Quicksilver mine of [New] Almaden, California (from a letter to J. D. Dana, dated San Francisco, Feb. 14, 1854): Am. Jour. Sci., 2d ser., vol. 17, pp. 438–440, 1854.
———2. Mercury; Santa Clara County, New Almaden; Guadalupe mine; Monterey County: Am. Jour. Sci., 2d ser., vol. 20, p. 80, 1855.
———3. Annotated catalogue of the principal mineral species hitherto recognized in California and the adjoining States and Territories [cinnabar and mercury]: Browne, J. R., Mineral resources of the States and Territories west of the Rocky Mountains [for 1866], pp. 202, 207, 1867.
———4. Mineralogical notices. No. 2; Cinnabar in calcite in Idaho: California Acad. Nat. Sci. Proc., vol. 3, p. 298, 1867.
———5. Note on the occurrence of gold with cinnabar in the Secondary or Tertiary rocks: Boston Soc. Nat. Hist. Proc., vol. 11, pp. 30–31, 1868.
———6. Notes on some points in the mineralogy and geology of Utah: Am. Jour. Sci., 3d ser., vol. 2, p. 216, 1871.
———7. The ore deposits of Eureka district, eastern Nevada: Am. Inst. Min. Eng. Trans., vol. 6, pp. 554–563, 1879.
———8. Cinnabar in Texas: Am. Inst. Min. Eng. Trans., vol. 25, pp. 68–76, 1896.
———9. Notes on the mines and minerals of Guanajuato, Mexico [cinnabar]: Am. Inst. Min. Eng. Trans., vol. 32, pp. 220, 223, 1902.
———10. Minerals of Arizona, their occurrence and association [cinnabar]: a report to the Hon. J. H. Kibbey, governor of Arizona, p. 15, 1909.
Boalich, E. S. 1. Mineral production for 1911 [quicksilver]: California State Min. Bur. Bull. 69, pp. 30–31, 1912.
———2. Mineral production for 1912 [quicksilver]: California State Min. Bur. Bull. 65, pp. 19–20, 1913.
———3. Mineral production for 1913 [quicksilver]: California State Min. Bur. Bull. 68, pp. 23–24, 1914.
Bonney, W. 1. Mineral resources of San Luis Potosi, Mexico [quicksilver mines]: Min. and Eng. World, vol. 38, p. 720, Apr. 12, 1913.
———2. Mineral resources of San Luis Potosi [quicksilver]: Mexican Min. Jour., vol. 16, No. 6, p. 281, June, 1913.
Booth, F. J., The reduction of quicksilver ore: Min. and Sci. Press, vol. 93, pp. 570–572, Nov. 10, 1906.
Boutwell, J. M. 1. Quicksilver: U. S. Geol. Survey Mineral Resources, 1906, pp. 491–499, 1907.
Bradley, W. W. 1. Mines and minerals of Fresno and Kings counties [quicksilver] (chapters of State mineralogist's report, 1913–14), pp. 6, 36–38, 100, 102–104, California State Min. Bur., July, 1915.

Digitized by Google

Bradley, W. W. 2. Mines and mineral resources of the counties of Colusa, Glenn, Lake, Marin, Napa, Solano, Sonoma, Yolo [quicksilver] (chapters of State mineralogist's report, 1913–14), pp. 17, 27, 54–68, 111–120, 139–140, 170–179, 197, California State Min. Bur., illus., July, 1915.
——— 3. California mineral production for 1915 [quicksilver]: California State Min. Bur. Bull. 71, pp. 33–35, August, 1916.
——— 4. California mineral production for 1916 [quicksilver]: California State Min. Bur. Bull. 74, pp. 42–47, August, 1917.
British Columbia Mining Record, Savonas cinnabar properties: Vol. 7, pp. 375–376, October, 1900.
Broderick, T. M. 1. Some experiments bearing on the secondary enrichment of mercury deposits: Econ. Geology, vol. 11, No. 7, pp. 645–651, October-November, 1916.
Brooks, A. H. 1. The mining industry in 1905 [prospecting for cinnabar deposits in Alaska]: U. S. Geol. Survey Bull. 284, p. 9, 1906.
——— 2. Mineral deposits of Alaska [occurrence of cinnabar]: U. S. Geol. Survey Bull. 592, pp. 36–37, 1914.
——— 3. Mining and mineral wealth of Alaska [occurrence of cinnabar], p. 26, Washington, D. C., Judd & Detweiler, 1909.
——— 4. Geologic features of Alaska metalliferous lodes [occurrence of cinnabar]: U. S. Geol. Survey Bull. 480, p. 93, 1911.
——— 5. The Alaskan mining industry in 1914 [quicksilver]: U. S. Geol. Survey Bull. 622, pp. 21, 67, 1915.
——— 6. The Alaskan mining industry in 1915: Iditarod district [antimony-cinnabar lodes]: U. S. Geol. Survey Bull. 642, p. 66, pl. 1 (map, in pocket), 1916.
——— 7. Antimony deposits of Alaska [stibnite-cinnabar lodes]: U. S. Geol. Survey Bull. 649, p. 12, 1916.
——— 8. Alaska's mineral supplies, introduction [quicksilver]: U. S. Geol. Survey Bull. 666–P, p. 9, 1917.
Brown, C. F. 1. Oil-burning mercury retort, furnace, and condenser: Min. Reporter, vol. 55, p. 355, Apr. 18, 1907.
Brown, G. C. 1. Mines and minerals of Shasta, Siskiyou, and Trinity counties, Cal. [quicksilver] (chapters of State mineralogist's report, 1913–14), pp. 126, 131–132, 179–180, California State Min. Bur., July, 1915.
Browne, J. R. 1. Quicksilver mines of California: Mineral resources of the States and Territories west of the Rocky Mountains [for 1866], pp. 170–178, 1867.
——— 2. Quicksilver: Mineral Resources of the States and Territories west of the Rocky Mountains [for 1867], op. 263–264, 636, 1868.
Brush, G. J., and Comstock, W. J. 1. On American sulphoselenides of mercury, with analyses of onofrite from Utah: Am. Jour. Sci., 3d ser., vol. 21, pp. 312–316, 1881.
Buisson, Arthur. 1. The production of copper, gold, lead, nickel, silver, zinc, and other metals [mercury]: Canada Dept. Mines, Mines Branch Ann. Rept. on mineral production 1916, p. 41, 1917. [Advance chapter.]
Burcham, W. D. 1. Quicksilver in Terlingua, Tex.: Eng. and Min. Jour., vol. 103, p. 97, Jan. 13, 1917.
Burdick, A. J. 1. Chemical tests for minerals [native mercury and cinnabar], pp. 55–56, Beaumont, Cal., Gateway Publishing Co., 1917.
Burgess, J. A. 1. The halogen salts of silver and associated minerals at Tonopah, Nev. [cinnabar]: Econ. Geology, vol. 6, No. 1, p. 21, January–February, 1911.
Butler, G. M. 1. A pocket handbook of minerals [cinnabar, mercury]. 1st ed., pp. 55–56, Beaumont, Cal., Gateway Publishing Co., 1917.
Butler, G. M., and Mitchell, G. J. 1. Preliminary survey of the geology and mineral resources of Curry County, Oreg. [mercury and cinnabar]: Oregon Bur. Mines and Geology, Mineral Resources of Oregon, vol. 2, No. 2, p. 72, October, 1916.
California Senate and Assembly Jour. 1. Fifteenth sess., Appendix, vol. 2 [Mining review for 1863, quicksilver, p. 193], 1864.
——— 2. Sixteenth sess., Appendix, vol. 3 [Mining review for 1865, quicksilver, pp. 332–333], 1866.
California State Mining Bureau. 1. California mineral production for 1915 [quicksilver]; Bull. 71, pp. 33–35, August, 1916.
——— 2. California's mineral production for 1915 [quicksilver]; Press Bull. 37, p. 2, Aug. 25, 1916.

Digitized by Google

California State Mining Bureau. 3. Quicksilver in California; its military importance; no commercial substitute yet developed; Press Bull. 40, 1 p., May 15, 1917.
Camsell, Charles. 1. The mineral resources of a part of the Yale district, British Columbia; a descriptive summary [mercury]: Canadian Min. Inst. Quart. Bull. 12, p. 129, October, 1910.
Canfield, F. A., Hillebrand, W. F., and Schaller, W. T. 1. Mosesite, a new mercury mineral from Terlingua, Tex.: Am. Jour. Sci., 4th ser., vol. 30, pp. 202–208, 1910.
——— 2. Mosesit, ein neues Quecksilbermineral von Terlingua, Tex.: Zeitschr. Kryst. Min., Leipzig, vol. 49, pp. 1–8, 1911.
Capilla, Alberto. 1. Breves anotaciones sobre la mina de mercurio "La Guadalupana," San Luis Potosi [Mexico]: Soc. cient. Ant. Alzate, Mem. y Rev., vol. 13, pp. 423–427, 1904.
Carey, E. E. 1. Principles of electrolytic amalgamation: Min. World, vol. 32, pp. 896–897, Apr. 30, 1910.
Carson, J. P. 1. The mineral district of Chiquilistlan [Mexico]: Am. Inst. Min. Eng. Trans., vol. 6, pp. 405–406, 1879.
Caslamayomi Rancho. 1. Sonoma County, Cal., 17 pp., [about 1865]. Pamphlet.
Castillero, Andreas. 1. *See* J. S. Black, U. S. Supreme Court Repts., vol. 67 [vol. 2 of Black], 1862.
Castillo, Antonio del. 1. Resumen de los trabajos que sobre reconocimientos de criaderos y minas de azogue se practicaron el año 1844: La Naturaleza, vol. 2, pp. 39–120, 1871.
——— 2. Quicksilver mining in Mexico: Min. and Sci. Press, vol. 30, p. 41, Jan. 16, 1875.
Chemical Society, London. 1. Inorganic analysis; detection and estimation of mercury: Ann. Rept. 1916, vol. 13, pp. 182–186, 1917.
Chism, R. E. 1. A new assay for mercury: Am. Inst. Min. Eng. Trans., vol. 28, pp. 444–452, 1 fig., 1899.
Christy, S. B. 1. On the genesis of cinnabar deposits: Am. Jour. Sci., 3d ser., vol. 17, pp. 453–463, 1879.
——— 2. Quicksilver reduction at New Almaden, Cal.: Am. Inst. Min. Eng. Trans., vol. 13, pp. 547–584, 6 pls., 1885.
——— 3. Quicksilver reduction at New Almaden [California]: U. S. Geol. Survey Mineral Resources, 1883 and 1884, pp. 503–536, 1885.
——— 4. Quicksilver-condensation at New Almaden [California]: Am. Inst. Min. Eng. Trans., vol. 14, pp. 206–265, 1886.
Clarke, F. W. 1. . . . on the electrolytic estimation of mercury: Am. Jour. Sci., 3d ser., vol. 16, pp. 200–201, 1878.
——— 2. The data of geochemistry [mercury]: U. S. Geol. Survey Bull. 330, pp. 17, 572–577, 1908; 2d ed., Bull. 491, pp. 18, 633–638, 1911; 3d ed., Bull. 616, pp. 18, 664–669, 1916.
Clennell, J. E. 1. Volumetric estimation of mercury: Eng. and Min. Jour., vol. 98, pp. 787–789, Oct. 31, 1914.
Clevenger, G. H. 1. Note upon the occurrence of mercury in cobalt ores: Econ. Geology, vol. 10, pp. 770–773, December, 1915.
Collins, H. F. 1. Quicksilver mining in the district of Guadalcazar, State of San Luis Potosi, Mexico: Inst. Min. and Met., London, vol. 4, pp. 121–150, 1896.
Colquhoun, A. L. 1. Notes on the occurrence of quicksilver in Canada: Canadian Min. Inst. Jour., vol. 1, pp 13–16, 1899; Canadian Min Rev., vol. 18, pp. 41–42, 1899; summary, Min. and Sci. Press, vol. 79, p. 288, Sept. 9, 1899.
Colvin, Verplanck. 1. On certain new phenomena in chemistry; an account of mercury and its amalgams: Albany Inst. Trans., vol. 7, pp. 172–185, 1872.
Courtney, W. S. 1. The gold fields of St. Domingo [" mercury at the head of the River Yaque "], p. 119, New York, 1860.
Crane, E. B. 1. Difficult mine sampling [method employed at Black Butte quicksilver mine, Lane County, Oreg.]: Min. and Sci. Press, vol. 114, p. 539, Apr. 21, 1917.
Crawford, J. J. 1. Report of State mineralogist [quicksilver]: California State Min. Bur., Twelfth Rept., pp. 358–372, 1894.
——— 2. Report of State mineralogist [quicksilver]: California State Min. Bur., Thirteenth Rept., pp. 594–604, 1896.
Cummings, W. F. 1. Mining districts in El Paso County, Tex.: Texas State Geol. and Sci. Assoc. Geol. and Sci. Bull., vol. 1, No. 2 [p. 3], 1888.
Davis, H. S. 1. The rhythmic precipitation of colloidal mercury: Am. Chem. Soc. Jour., vol. 39, pp. 1312–1314, 1 fig., July, 1917.

Digitized by Google

Davis, L. H. 1. West Texas mining notes: Texas Mineral Resources, vol. 1, No. 1, p. 2, November, 1916.
Davis, W. C. 1. Quicksilver in Nevada: Min. and Sci. Press, vol. 99, p. 663, Nov. 13, 1909.
Dawson, G. M. 1. Report on explorations in British Columbia; cinnabar on the Homathco: Canada Geol. Survey Rept. Prog. for 1876–1877, p. 133, 1878.
——— 2. The mineral wealth of British Columbia [occurrence of mercury]: Canada Geol. Survey Ann. Rept., new ser., vol. 3, pt. 2, pp. 105R, 156R, 1889.
——— 3. Report on the area of the Kamloops map sheet, British Columbia [mercury on Copper Creek]: Canada Geol. Survey Ann. Rept., new ser., vol. 7, pp. 340–341, 1896.
Day, D. T. 1. Quicksilver: U. S. Geol. Survey Mineral Resources, 1886, pp. 160–168, 1887.
——— 2. Quicksilver: U. S. Geol. Survey Mineral Resources, 1887, pp. 2, 6, 8, 9, 118–125, 1888.
——— 3. Quicksilver vermilion: U. S. Geol. Survey Mineral Resources, 1887, p. 679, 1888.
——— 4. Statistics of quicksilver: U. S. Geol. Survey Eighth Ann. Rept., pt. 1, p. 196, 1889.
——— 5. Statistics of quicksilver: U. S. Geol. Survey Ninth Ann. Rept., pp. 135, 139, 1889.
——— 6. Statistics of quicksilver: U. S. Geol. Survey Tenth Ann. Rept., pt. 1, p. 183, 1890.
——— 7. Quicksilver: U. S. Geol. Survey Mineral Resources, 1888, pp. 2, 97–107, 1890.
——— 8. Quicksilver vermilion: U. S. Geol. Survey Mineral Resources, 1888, p. 622, 1890.
——— 9. Statistics of quicksilver: U. S. Geol. Survey Twelfth Ann. Rept., pt. 1, pp. 130–131, 1891.
——— 10. Quicksilver: U. S. Geol. Survey Mineral Resources, 1889 and 1890, pp. 2, 6, 94–109, 1892.
——— 11. Quicksilver in 1891: U. S. Geol. Survey Mineral Resources, 1891, pp. 1–2, 117–125, 1893.
——— 12. Summary of production of quicksilver in 1892: U. S. Geol. Survey Mineral Resources, 1892, p. 2, 1893.
——— 13. Quicksilver in 1893: U. S. Geol. Survey Mineral Resources, 1893, pp. 2, 111–118, 1894.
——— 14. Quicksilver in 1893: U. S. Geol. Survey Fifteenth Ann Rept., p. 204, 1895.
——— 15. Quicksilver in 1894; discovery of, in Texas: U. S. Geol. Survey Sixteenth Ann. Rept., pt. 3, pp. 6, 598–604, 1895.
——— 16. Quicksilver in 1895: U. S. Geol. Survey Seventeenth Ann. Rept., pt. 3, pp. 7, 179–184, 1896.
——— 17. Quicksilver; summary of production: U. S. Geol. Survey Eighteenth Ann. Rept., pt. 5, pp. 6, 287–290, 1897.
——— 18. Quicksilver; summary, imports, production since 1850, prices: U. S. Geol. Survey Nineteenth Ann. Rept., pt. 6, pp. 5, 243–248, 1898.
——— 19. Quicksilver; summary, production, imports, and prices: U. S. Geol. Survey Twentieth Ann. Rept., pt. 6, pp. 7, 271–275, 1899.
——— 20. Quicksilver in 1900: U. S. Geol. Survey Mineral Resources, 1900, pp. 15, 235–238, 1901.
——— 21. Quicksilver in 1901: U. S. Geol. Survey Mineral Resources, 1901, p. 18, 1902.
——— 22. Quicksilver in 1902: U. S. Geol. Survey Mineral Resources, 1902, pp. 13–14, 1904.
——— 23. Quicksilver in 1903: U. S. Geol. Survey Mineral Resources, 1903, pp. 13–14, 281–284, 1904.
——— 24. Quicksilver in 1904: U. S. Geol. Survey Mineral Resources, 1904, pp. 12, 295–299, 1905.
——— 25. Quicksilver in 1905 (summary): U. S. Geol. Survey Mineral Resources, 1905, pp. 14–15, 1906.
De Kalb, Courtenay. 1. Guadalupe quicksilver works [California]: Min. and Sci. Press, vol. 100, pp. 446–447, figs., Mar. 26, 1910.
Demaret, Léon. 1. Les principaux gisements des minérais de mercure du monde [United States, California, Oregon, Texas, Utah]: Annales des mines de Belgique, vol. 9, pp. 46–66, 1904.

Digitized by Google

Dennis, C. G. 1. Rare mercury ores [Texas]: Min. and Sci. Press, vol. 95, p. 92, 2 figs., July 20, 1907.
———2. Modern quicksilver reduction: Min. and Sci. Press, vol. 99, p. 761, Dec. 4, 1909.
———3. Quicksilver production and prices: Min. and Sci. Press, vol. 106, pp. 61–62, Jan. 4, 1913.
———4. Quicksilver production and prices: Min. and Sci. Press, vol. 108, pp. 81–82, Jan. 3, 1914.
———5. Quicksilver: Mineral Industry, vol. 22, pp. 651–656, 1914.
———6. Quicksilver in 1914: Min. and Sci. Press, vol. 110, pp. 91–92, Jan. 9, 1915.
———7. Quicksilver: Mineral Industry, vol. 23, pp. 654–659, 1915.
———8. Quicksilver: Mineral Industry, vol. 24, pp. 614–619, 1916.
Dennis, C. G., and Bogard, V. E. 1. Quicksilver: Mineral Industry, 1916, vol. 25, pp. 638–640, 1917.
Dennis, W. B. 1. The quicksilver deposits of Oregon: Eng. and Min. Jour., vol. 76, pp. 539–541, 2 figs., Oct. 10, 1903.
———2. Quicksilver in Oregon: Mineral Industry, vol. 16, pp. 815–816, 1908.
———3. Shortening the roasting period for mercury: Eng. and Min. Jour., vol. 88, pp. 112–116, 6 figs., July 17, 1909.
Desha, L. J. 1. An apparatus for the purification of mercury: Am. Chem. Jour., vol. 41, pp. 152–155, 1 fig., February, 1909.
Diller, J. S. 1. Quicksilver: U. S. Geol. Survey Geol. Atlas, Roseburg folio (No. 49), [p. 4], 1898.
———2. Mineral resources of southwestern Oregon [quicksilver]: U. S. Geol. Survey Bull. 546, p. 129, 1914.
Diller, J. S., and Kay, G. F. 1. Mineral resources of the Grants Pass quadrangle and bordering districts, Oreg. [cinnabar]: U. S. Geol. Survey Bull. 380, p. 79, 1909.
Dinsmore, C. A. 1. Quicksilver deposits of Brewster County, Tex.: Min. World, vol. 31, pp. 877–878, 6 figs., Oct. 30, 1909.
Dolbear, S. H. 1. Chemical resources of California [quicksilver]: Met. and Chem. Eng., vol. 12, No. 11, p. 721, November, 1914.
Dunlop, J. P. 1. Metals and ores in 1914 and 1915 [production of quicksilver]: U. S. Geol. Survey Mineral Resources, 1915, pt. 1, p. 726, 1916.
Dunnicliffe, H. B. 1. A simple method for the purification of mercury: Chem. News, vol. 116, No. 3009, pp. 41–42, 1 fig., July 27, 1917.
Durand, F. E. 1. Note on crystals of quartz of a red color, by the interposition of cinnabar: California Acad. Sci. Proc., vol. 4, p. 211, 1873.
———2. Notes on the crystallization of metacinnabarite: California Acad. Sci. Proc., vol. 4, pp. 219–220, 1873.
Eakle, A. S. 1. The minerals of Tonopah, Nev.: California Univ. Dept. Geology Bull., vol. 7, p. 8, 1912.
———2. Minerals of California [cinnabar, mercury, and metacinnabarite]: California State Min. Bur. Bull. No. 67, pp. 18, 32–36, 201, 204–209, 1914.
Eddy, L. H. 1. Quicksilver in California in 1910: Eng. and Min. Jour., vol. 91, p. 85, Jan. 7, 1911.
———2. Quicksilver in California: Mineral Industry, vol. 19, pp. 592–593, 1911.
———3. Quicksilver in California in 1911: Eng. and Min. Jour., vol. 93, p. 38, Jan. 6, 1912.
———4. Quicksilver in California: Mineral Industry, vol. 20, pp. 651–652, 1912.
———5. Quicksilver in California: Eng. and Min. Jour., vol. 95, p. 78, Jan. 11, 1913; Mineral Industry, vol. 21, pp. 744–745, 1913.
———6. Quicksilver operations in northern California: Eng. and Min. Jour., vol. 96, p. 828, Nov. 1, 1913.
———7. Quicksilver in California in 1913: Eng. and Min. Jour., vol. 97, p. 155, Jan. 10, 1914.
———8. Quicksilver in California in 1914: Eng. and Min. Jour., vol. 99, pp. 68–69, Jan. 9, 1915.
Edwards, C. E. 1. California quicksilver industry: Min. World, vol 24, pp. 270–271, Feb. 24, 1906.
Egleston, Thomas. 1. Notes on the treatment of mercury in north California: Am. Inst. Min. Eng. Trans., vol. 3, pp. 273–307, 1875.
———2. The metallurgy of silver, gold, and mercury in the United States, 2 vols., New York and London, 1887–1890.

Digitized by Google

Electrical Review and Western Electrician. 1. Oldest mercury-vapor lamp still fit for service: Vol. 70, p. 44, 1 fig., Jan. 6, 1917.
Electrical World. 1. Improved mercury-vapor lamps: Vol. 69, p. 145, illus., Jan. 20, 1917.
Emmet, W. L. R. 1. Mercury boiler; a thermodynamic process in tandem with a steam-generating plant for the production of power: Eng. Mag., vol. 47, pp. 265–268, May, 1914.
——— 2. Power from mercury vapor: Am. Inst. Elec. Eng. Proc., vol. 33, pp. 473–489, illus., January, 1914.
Emmons, S. F. 1. Geological distribution of the useful metals in the United States [quicksilver]: Am. Inst. Min. Eng. Trans., vol. 22, pp. 85–86, 1894.
Emmons, S. F., and Becker, G. F. 1. Statistics and technology of the precious metals; placer mines, amalgamating mills [quicksilver]: Tenth Census, vol. 13, pp. 200, 259, 264, Append. I, p. 455, 1885.
Emmons, W. H. 1. The Neglected mine and near-by properties. Durango quadrangle, Colo.: U. S. Geol. Survey Bull. 260, pp. 123–127, 1905.
——— 2. Exploration of metalliferous deposits [mercury]: Min. and Sci. Press, vol. 114, p. 440, Mar. 31, 1917.
——— 3. The enrichment of ore deposits [mercury; small replacement power of, list of principal mercury minerals, analyses, description, occurrence]: U. S. Geol. Survey Bull. 625, pp. 138–139, 392–398, 1917.
Emmons, W. H., and Calkins, F. C. 1. Geology and ore deposits of the Philipsburg quadrangle, Mont.; U. S. Geol. Survey Prof. Paper 78, p. 154, 1913.
Encyclopaedia Britannica. 1. 11th ed., vol. 18, Mexico [Mining], p. 326, 1911.
Endlich, F. M. 1. Catalogue of minerals found in Colorado [mercury]: U. S. Geol. and Geog. Survey Terr. Tenth Ann. Rept., p. 146, 1878.
Engineering. 1. The critical temperature of mercury: Vol. 100, p. 502, Nov. 12, 1915.
Engineering and Mining Journal. 1. . . . quicksilver deposits of California: Vol. 22, p. 118, Aug. 19, 1876.
——— 2. Purification of mercury: Vol. 46, p. 191, Sept. 8, 1888.
——— 3. Quicksilver mining [California]: Vol. 48, pp. 470–471, Nov. 30, 1889.
——— 4. Quicksilver Mining Co. [New Almaden, Santa Clara County, Cal.]: Vol. 78, pp. 676–677, Oct. 27, 1904.
——— 5. Quicksilver production in California: Vol. 79, p. 22, Jan. 5, 1905.
——— 6. Quicksilver, how it comes and how weighed in the form of amalgam: Vol. 80, p. 308, Aug. 19, 1905.
——— 7. How to purify mercury: Vol. 94, p. 640, Oct. 5, 1912.
——— 8. The trend of quicksilver metallurgy: Vol. 94, pp. 545–546, Sept. 21, 1912.
——— 9. California quicksilver in 1912: Vol. 95, p. 967, May 10, 1913.
——— 10. The quicksilver matter: Vol. 95, p. 817, Apr. 19, 1913.
——— 11. Quicksilver near Mina, Nev,; Vol. 96, pp. 93, 809, July 12 and Oct. 25, 1913.
——— 12. The quicksilver market: Vol. 97, pp. 53, 154–155, Jan. 10, 1914.
——— 13. Quicksilver mining in 1913: Vol. 97, p. 154, Jan. 10, 1914.
——— 14. Mercury recovery plant at Fresnillo, Zacatecas, Mexico: Vol. 97, pp. 953–954, illus., May 9, 1914.
——— 15. Some deficiencies in mineral resources: Vol. 98, p. 450, Sept. 5, 1914.
——— 16. Quicksilver market: Vol. 99, pp. 49, 68, 960, Jan. 9, and May 29, 1915.
——— 17. Cinnabar in western Nevada: Vol. 100, p. 668, October 23, 1915.
——— 18. Quicksilver receipts at San Francisco: Vol. 101, p. 418, Feb. 26, 1916.
——— 19. Production of quicksilver in California in 1915: Vol. 101, p. 508, Mar. 18, 1916.
——— 20. Concentrating quicksilver ores: Vol. 101, p. 1033, June 10, 1916.
——— 21. Oceanic quicksilver mill: Vol. 102, pp. 512–513, Sept. 16, 1916.
——— 22. Landers mercury furnace; Vol. 102, p. 634, Oct. 7, 1916.
——— 23. Robbins barrel amalgamator; Vol. 102, p. 712, Oct. 14, 1916.
——— 24. Discovery of cinnabar near Gold Circle district, Nev.; Vol. 102, p. 767, Oct. 21, 1916.
——— 25. Quicksilver; Vol. 103, p. 6, Jan. 6, 1917.
——— 26. Minerals of military importance [mercury]; Vol. 103, pp. 974–975, June 2, 1917.
——— 27. Quicksilver in California; Vol. 103, p. 1023, June 9, 1917.
Fairbanks, H. W. 1. Some remarkable hot springs and associated mineral deposits in Colusa County, Cal.: Science, vol. 23, pp. 120–121, 1894.

Digitized by Google

Fawcett, Waldon. 1. A quicksilver furnace: Am. Inventor, p. 143, November, 1905.
Feust, Arthur. 1. Modern quicksilver reduction: Min. and Sci. Press, vol. 99, p. 795, Dec. 11, 1909.
Flores, T., El mercurio en México: Boletín minero, vol. 1, No. 1, pp. 13–15, Mexico, Jan. 1, 1916.
Forbes, G. S., and Richter, H. W. 1. The measurement of oxidation potentials at mercury electrodes. The chromic-chromous potential: Am. Chem. Soc. Jour., vol. 39, pp. 1140–1148, 4 figs., June, 1917.
Forstner, William. 1. The quicksilver resources of California: California State Min. Bur. Bull. 27, 260 pp., illus., 1903.
——— 2. The quicksilver deposits of California: Eng. and Min. Jour., vol. 78, pp. 385–386, 426–428, illus., Sept. 8 and 15, 1904.
Freeman, H. C. 1, The La Plata Mountains [Colorado]: Am. Inst. Min. Eng. Trans., vol. 13, pp. 681–684, 1885.
Gabb, W. M. 1. Communication on the San Luis Obispo quicksilver fossils: California Acad. Nat. Sci. Proc., vol. 3, pp. 173–174, 1864.
Galeotti, H. 1. Notice sur un gîte de mercure dans le sol tertiaire récent du Gigante au Mexique: Acad. roy. sci. Bruxelles Bull., vol. 5, pp. 196–202, 1838.
Gannett, Henry. 1. Detailed topographic work; maps of the quicksilver mining districts of California: U. S. Geol. Survey Fourth Ann. Rept., pp. 4–6, 1884.
Geary, J. W. 1. A rotary furnace for roasting quicksilver ores: Min. and Sci. Press, vol. 90, p. 22, Jan. 14, 1905.
——— 2. The condensation of quicksilver vapors: California Jour. Tech., vol. 7, pp. 35–36, 47, February, 1906: Min. Reporter, vol. 53, pp. 392–393, Apr. 19, 1906; Min. Mag., New York, vol. 13, p. 421, 1906.
George, R. D. 1. Mercury, quicksilver, and its ores: Colorado State Geol. Survey Bull. 6, pp. 236–238, 1913.
——— 2. Common minerals and rocks, their occurrence and uses [mercury, quicksilver, and its ores], pp. 249–251, Denver, Colo., 1917.
Gillan, S. L. 1. Cinnabar in the Sierra Nevada: Min. and Sci. Press, vol. 114, No. 3, p. 79, Jan. 20, 1917.
Goodyear, W. A. 1. Report on an examination of the quicksilver mines of California (May, 1871): California Geol. Survey, Geology, vol. 2, Appendix, pp. 91–135, 1882.
Grout, F. E. 1. On the behavior of cold acid sulphate solutions of copper, silver, and gold, with alkaline extracts of metallic sulphides [cinnabar]: Econ. Geology, vol. 8, pp. 417, 425, 427, 1913.
Guadalupe Mining Co. of Santa Clara County, Cal. 1. 57 pp., New York, February, 1852. Pamphlet.
Hageman, Ira. 1. Quicksilver apparatus: U. S. Patent No. 970705, Sept. 20, 1910.
Hague, Arnold. 1. Chemistry of the Washoe process; chemical action of mercury and other reagents: U. S. Geol. Expl. 40th Par. Rept., vol. 3, pp. 273–293, 1870.
Halse, Edward. 1. The silver district of Tehuilotepec, State of Guerrero, Mexico: Eng. and Min. Jour., vol. 60, pp. 197–199, Aug. 31, 1895.
——— 2. The quicksilver mines and reduction works at Huitzuco, Guerrero, Mexico: Fed. Inst. Min. Eng. Trans., vol. 10, pp. 72–88, 354, 1896.
Hamilton, E. M. 1. Flotation for cinnabar: Min. and Sci. Press, vol. 112, p. 541, Apr. 15, 1916.
Hamilton, Fletcher. 1. Mines and mineral resources of Del Norte County, etc. [quicksilver] (chapters of State mineralogist's report, 1913–14), p. 20, California State Min. Bur., July, 1915.
——— 2. Mineral production for 1914 [quicksilver]: California State Min. Bur. Bull. 70, pp. 28–30, July, 1915.
——— 3. Production of quicksilver in California in 1915: Eng. and Min. Jour., vol. 101, p. 508, Mar. 18, 1916.
——— 4. Concentration of quicksilver ores in California: Min. and Eng. World, vol. 44, p. 997, May 27, 1916.
Hanks, H. G. 1. Quicksilver: [California] State Mineralogist [First] Ann. Rept., June 1, 1880–Dec. 1, 1880, pp. 26–27, 1881.
——— 2. Quicksilver, receipts at San Francisco, charging sluices with, loss of, retorting: [California] State Mineralogist Second Ann. Rept., Dec. 1, 1880–Oct. 1, 1882, pp. 24, 112, 116, 117, 121, 1882.
——— 3. Quicksilver: California State Min. Bur. Fourth Ann. Rept., pp. 328–344, 1884.

Digitized by Google

Hanks, H. G. 4. Something about quicksilver: Min. and Sci. Press, vol. 59, pp. 22–23, June 13, 1889.
———5. The properties of mercury: Min. and Sci. Press, vol. 59, pp. 142–143, Aug. 24, 1889.
Harper's New Monthly Magazine. 1. Down in the cinnabar mines; a visit to New Almaden in 1865: Vol. 31, pp. 545–560, illus., October, 1865.
Hart, T. S. 1. Notes on the Almaden mine, Cal.: Am. Jour. Sci., 2d ser., vol. 16, pp. 137–139, 1853.
Haverstock, R. S. 1. Quicksilver: Min. and Sci. Press, vol. 84, pp. 4–5, Jan. 4. 1902.
Heberlein, C. A. 1. The mining and reduction of quicksilver ore at the Oceanic mine, Cambria, Cal.: Am. Inst. Min. Eng. Trans., vol. 51, pp. 110–119, 1916.
Hess, F. L. 1. [Occurrence of cinnabar and mercury near Livermore, Cal.]: U. S. Geol. Survey Bull. 285, p. 388, 1906.
Hewitt, A. S. 1. A century of mining and metallurgy in the United States [commencement of mining in New Almaden quicksilver mine, Cal.]: Am. Inst. Min. Eng. Trans., vol. 5, pp. 175–176, 1877.
Higgins, W. C. 1. The Nevada Cinnabar Co.: Salt Lake Min. Rev., vol. 16, p. 21, Sept. 30, 1914.
Hill, B. F. 1. The Terlingua quicksilver deposits, Brewster County, Tex.: Texas Univ. Min. Survey Bull. 4, 74 pp., illus., maps, October, 1902.
———2. The occurrence of the Texas mercury minerals: Am. Jour. Sci., 4th ser., vol. 16, pp. 251–252, 1903.
———3. Das Vorkommen der texanischen Quecksilbermineralien: Zeitschr. Kryst. Min., Bd. 39, pp. 1–2, 1904.
Hill, J. M. 1. The mining districts of the western United States [quicksilver]: U. S. Geol. Survey Bull. 507, pp. 54, 77, 114, 199, 245, 262, 1912.
Hill, R. T. 1. Physical geography of the Texas region [occurrence of cinnabar]: U. S. Geol. Survey Top. Atlas (folio 3), p. 12, 1900.
———2. The cinnabar deposits of the Big Bend province of Texas: Eng. and Min. Jour., vol. 74, pp. 305–307, illus., Sept. 6, 1902.
———3. The geographic and geologic features, and their relation to the mineral products, of Mexico [cinnabar]: Am. Inst. Min. Eng. Trans., vol. 32, p. 173, 1902.
Hillebrand, W. F. 1. Preliminary announcement concerning a new mercury-mineral from Terlingua (Tex.): Science, new ser., vol. 22, p. 844, 1905.
Hillebrand, W. F., and Schaller, W. T. 1. The mercury minerals from Terlingua, Tex.: U. S. Geol. Survey Bull, 405, 174 pp., 6 pls., 1909.
Hinckley, F. C. [in Spurr, J. C.] 1. [Deposits of quicksilver ore near Kolmakof, Alaska]: U. S. Geol. Survey Twentieth Ann. Rept., pt. 7, p. 129, 1900.
Hoffmann, G. C. 1. Chemical contributions to the geology of Canada [occurrence of cinnabar in British Columbia]: Canada Geol. Survey Ann. Rept., 1886, new ser., vol. 2, p. 9 T, 1887.
———2. Chemical contributions to the geology of Canada [occurrence of native mercury in British Columbia]: Canada Geol. Survey Ann. Rept., 1890–1891, new ser., vol. 5, pt. 2, pp. 65–66 R, 1893.
———3. Chemical contributions to the geology of Canada [occurrence of cinnabar in British Columbia]: Canada Geol. Survey Ann. Rept., 1892–1893, new ser., vol. 6, p. 31 R, 1895.
Hore, R. E. 1. Occurrence of minerals in Canada [mercury or quicksilver]: Canadian Min. Manual, p. 117, 1916–1917.
Hornaday, W. D. 1. The cinnabar deposits of Terlingua, Tex.: Min. World, vol. 33, pp. 1133–1134, 5 figs., Dec. 17, 1910.
Horton, F. W. 1. Quicksilver: U. S. Geol. Survey Mineral Resources, 1905, pp. 393–404, 1906.
Hovey, E. O. 1. Ores of economic importance [mercury]: U. S. Geol. Survey Mineral Resources, 1901, p. 971, 1902.
How, Henry. 1. Mineralogy of Nova Scotia [mercury], p. 61, Halifax, N. S., 1869.
Huff, W. B. 1. The spectra of mercury: Astrophys. Jour., vol. 12, pp. 103–109, September, 1900.
Humboldt, Alexander. 1. Essai politique sur le royaume de la Nouvelle Espagne [Mexico] [mercure], vol. 2, p. 585, Paris, 1811.
Hunt, T. S. 1. Mineral species of Canada [quicksilver]: Canada Geol. Survey Fifteenth Rept. Prog., p. 518, 1863.

Digitized by Google

Hutchins, Thomas. 1. An account of the success of some attempts to freeze quicksilver at Albany Fort, in Hudson's Bay, in the year 1775: Philos. Trans., vol. 66, pp. 174–178, 1776.

——— 2. Experiments for ascertaining the point of mercurial congelation: Philos. Trans., vol. 73, pp. 303*–370*, pl. 7, 1783.

Imperial Institute, London. 1. The occurrence, distribution, and uses of mercury: Bull., vol. 11, No. 3, pp. 479–495, July–September, 1913.

Ingalls, W. R. 1. Work was begun at the quicksilver mines of New Almaden, Cal., 1851: Mineral Industry, vol. 1, p. 227, 1893.

Innes, Murray. 1. California quicksilver: Eng. and Min. Jour. vol. 101, p. 68, Jan. 8, 1916.

James, G. A. 1. The James apparatus for quicksilver determination: Eng. and Min. Jour., vol. 90, pp. 800–801, illus., Oct. 22, 1910.

Jameson, Robert. 1. A treatise on the external, chemical, and physical characters of minerals [fluid minerals, mercury], 1st ed., p. 81, Edinburgh, 1805; 3d ed., p. 275, Edinburgh, 1817.

Jamieson, G. S. 1. A new volumetric method for the determination of mercury: Am. Jour. Sci., 4th ser., vol. 33, pp. 349–351, 1912.

Janin, Louis, jr. 1. Mining and metallurgy of quicksilver: In Raymond, Mines and mining in the States and Territories west of the Rocky Mountains, Sixth Ann. Rept. [for 1873], pp. 379–407, 1874.

Joseph, P. E. 1. Mercury-quicksilver: Arizona State. Bur. Mines Bull. 12, 8 pp., 1916.

Juretzka, Franz. 1. Die Verarbeitung quecksilberhaltiger Nebenmaterialien im Zinkhüttenbetriebe [mercury from zinc blende]: Metall u. Erz, vol. 12, pp. 307–310, 5 figs., Aug. 8, 1915.

Kemp, J. F. 1. Ore deposits of the United States [mercury], 1st ed., pp. 267–269, 1893; 2d ed., pp. 309–312, 1895; 3d ed. ("and Canada" added to title), pp. 424–428, 1900.

——— 2. The rôle of the igneous rocks in the formation of veins: Am. Inst. Min. Eng. Trans., vol. 31, pp. 169–198, 1902.

King, Clarence. 1. Mining districts [geological occurrence of quicksilver]: U. S. Geol. Expl. 40th Par., vol. 3, p. 5, 1870.

Kirk, M. P. 1. The Terlingua quicksilver district: Min. Mag., New York, vol. 11, pp. 441–443, May, 1905.

Kirk, M. P., and Malcolmson, J. W. 1. A new quicksilver mining district [Big Bend, Tex.]: Eng. and Min. Jour., vol. 77, pp. 685–686, Apr. 28, 1904.

Knipp, C. T. 1. Efficient and rapid mercury still: Science, new ser., vol. 33, pp. 667–669, Apr. 28, 1911.

——— 2. A simple demonstration tube for exhibiting the mercury hammer, glow by mercury friction, and the vaporization of mercury at reduced pressure: School Sci. and Math., vol. 17, pp. 442–3, May, 1917.

Knopf, Adolph. 1. Some cinnabar deposits in western Nevada: U. S. Geol. Survey Bull. 620, pp. 59–68, Sept. 14, 1915; Min. American, vol. 72, p. 8. Nov. 13, 1915.

Koch, W. E. 1. Quicksilver in Texas: Mineral Industry, vol. 17, p. 745, 1909.

Kraus, C. A. 1. Mercury vapor pumps for operating against high pressure: Am. Chem. Soc. Jour., vol. 39, pp. 2183–2186, 1 fig., October, 1917.

Krusch, P. 1. Vorkommen und Entstehung der Quecksilbererze: Prometheus, Jahrg. 7, No. 340, pp. 437–440; No. 341, pp. 458–461, 1896.

Laguerenne, T. L. 1. Informe que rinde á la Secretaría de Fomento, como resultado de su exploración á los criaderos metalíferos de la Sierra del Estado de Guerrero: Mexico, Ministerio de fomento Anales, vol. 7, pp. 605–687. 1882.

Lakes, A. 1. New Almaden mines of Santa Clara County, Cal.: Mines and Minerals, vol. 19, pp. 346–349, illus., March, 1899.

Lake Quicksilver Mining Co. 1. Bear mining district, Lake County, Cal., Prospectus, 8 pp., New York, 1864. Pamphlet.

Lake Valley Quicksilver Mining Co. 1. Reports by Profs. Spence, Silversmith, Engineer Widmann, and H. Woodleaf, of San Francisco, Cal., with Profs. Adelberg and Raymond's analysis and assay of the ores, 28 pp., New York, 1865. Pamphlet.

Lamb, M. R. 1. Flotation for cinnabar: Min. and Sci. Press, vol. 113, p. 6, July 1, 1916.

Digitized by Google

Landers, W. H. 1. New Almaden quicksilver mine: Eng. and Min. Jour., vol. 100, p. 687, Oct. 23, 1915.
———2. Quicksilver mining in California: Min. and Sci. Press, vol. 112, pp. 282–284, map. Feb. 19, 1916.
———3. The smelting of mercury ores: Eng. and Min. Jour., vol. 102, pp. 630–633, Oct. 7, 1916.
Lang, Herbert. 1. Quicksilver reduction: Min. and Sci. Press, vol 112, pp. 707–714, May 13, 1916.
Langmuir, I. 1. Condensation pump; an improved form of high vacuum pump: Gen. Electric Rev., vol. 19, pp. 1060–71, December, 1916; Franklin Inst. Jour., vol. 182, pp. 719–743, December, 1916. Abstract, Sibley Jour. Eng., vol. 31, pp. 105–6, January, 1917.
Lawson, A. C. 1. Quicksilver: U. S. Geol. Survey Geol. Atlas, San Francisco folio (No. 193), p. 22, 1914.
LeConte, Joseph. 1. On mineral-vein formation now in progress at Steamboat Springs compared with the same at Sulphur Bank: Am. Jour. Sci., 3d ser., vol. 25, pp. 424–428, 1883.
———2. On the genesis of metalliferous veins: Am. Jour. Sci., 3d ser., vol. 26, pp. 1–19, 1883.
LeConte, Joseph, and Rising, W. B. 1. The phenomena of metalliferous-vein formation now in progress at Sulphur Bank, Cal.: Am. Jour. Sci., 3d ser., vol. 24, pp. 23–33, 1882.
Lindgren, Waldemar. 1. The gold-quartz veins of Nevada City and Grass Valley districts, Cal. [occurrence of cinnabar]: U. S. Geol. Survey Seventeenth Ann. Rept., pt. 2, p. 119, 1896.
———2. The gold belt of the Blue Mountains of Oregon [cinnabar, mercurial tetrahedrite, and mercury]: U. S. Geol. Survey Twenty-second Ann. Rept., pt. 2, pp. 604, 642, 683, 708, 1901.
———3. Rare minerals in gold-quartz veins of eastern Oregon [cinnabar and mercurial tetrahedrite]: Min. and Sci. Press, vol 82, p. 252, June 1, 1901.
———4. The Annie Laurie mine, Piute County, Utah [occurrence of mercury]: U. S. Geol. Survey Bull. 285, p. 90, footnote, 1906.
———5. Cinnabar in decomposed granite, Steamboat Springs, Nev.: Am. Inst. Min. Eng. Trans., vol. 36, p. 30, 1906.
———6. The relation of ore deposition to physical conditions [occurrence of cinnabar]: Econ. Geology, vol. 2, pp. 114, 119, 120, 1907.
———7. Mineral deposits [cinnabar, metacinnabarite, and quicksilver], pp. 107, 441, 457–473, 800–801, 812, New York and London, 1913.
———8. Geology and mineral deposits of the National mining district, Nev. [occurrence of cinnabar]: U. S. Geol. Survey Bull. 601, pp. 14, 15, 47, 48, 1915.
Lindgren, Waldemar, and Turner, H. W. 1. Quicksilver deposits: U. S. Geol. Survey Geol. Atlas, Placerville folio (No. 3) [p. 3], 1894.
———2. Quicksilver: U. S. Geol. Survey Geol. Atlas, Smartsville folio (No. 18) [p. 6], 1895.
Lowell, F. L. 1. Quicksilver for 1910: Min. and Sci. Press, vol, 102, p. 62, Jan. 7, 1911.
———2. Mines and minerals of Kern, Kings, Madera, Mariposa, Merced, San Joaquin, Stanislaus counties [quicksilver] (chapters of State mineralogist's report, 1913–14), pp. 176, 206–207, California State Min. Bur., July, 1915.
Lyman, C. S. 1. Mines of cinnabar in upper California: Am. Jour. Sci., 2d ser., vol. 6, pp. 270–271, 1848.
Lytle, J. A. 1. Report on the Altoona quicksilver mine, Trinity County, Cal. [manuscript], 6 pp., dated Sept. 1, 1884.
McCaskey, H. D. 1. Quicksilver: U. S. Geol. Survey Mineral Resources, 1907, pt. 1, pp. 677–692, 1908. [Pages 689–692 contain a bibliography on quicksilver.]
———2. Quicksilver: U. S. Geol. Survey Mineral Resources, 1908, pt. 1, pp. 683–695, 1909.
———3. The New Idria quicksilver mine, Cal.: Min. World, vol. 32, p. 104, Jan. 15, 1910.
———4. Quicksilver: U. S. Geol. Survey Mineral Resources, 1909, pt. 1, pp. 549–559, 1911.
———5. Quicksilver: U. S. Geol. Survey Mineral Resources, 1910, pt. 1, pp. 693–710, 1911.

Digitized by Google

McCaskey, H. D. 6. Quicksilver: U. S. Geol. Survey Mineral Resources, 1911, pt. 1, pp. 889–921, 1912.
———7. Quicksilver deposits: Min. Sci., vol. 66, pp. 41–42, July 18, 1912.
———8. Widespread deposits of cinnabar in Nevada: Min. Sci., vol. 66, pp. 55–57, July 25, 1912.
———9. Quicksilver: U. S. Geol. Survey Mineral Resources, 1912, pt. 1, pp. 931–948, 1913.
———10. The quicksilver situation: Eng. and Min. Jour., vol. 98, p. 647, Oct. 10, 1914.
———11. Quicksilver; U. S. Geol. Survey Mineral Resources, 1913, pt. 1, pp. 197–212, 1914.
———12. Quicksilver: U. S. Geol. Survey Mineral Resources, 1914, pt. 1, pp. *13, *29, 315–332, 1916.
———13. Quicksilver: U. S. Geol. Survey Mineral Resources, 1915, pt. 1, pp. 259–277, 1916.
McGarrahan, William. 1. [*See* Panoche Grande Quicksilver Mining Co. for history of case, 1861, and C. P. Shaw, 1872. *See also* Panoche Grande rancho, Cal., speech of James A. Garfield, February 20, 1871.]
———2. The history of the McGarrahan claim as written by himself, extracts from letters, papers, and documents of said McGarrahan, 411 pp., Washington 1876 (?).
McLeish, John. 1. Mineral production of Canada during the calendar years 1907 and 1908 [mercury]: Canada Dept. Mines, Mines Branch Ann. Rept., p. 146, Ottawa, 1910.
———2. Mineral production of Canada during the calendar year 1909 [mercury]: Canada Dept. Mines, Mines Branch Ann. Rept., p. 138, Ottawa, 1911.
———3. Mineral production of Canada during the calendar year 1911 [mercury]: Canada Dept. Mines, Mines Branch Ann. Rept., p. 151, Ottawa, 1913.
———4. Mineral production of Canada during the calendar year 1912 [mercury]: Canada Dept. Mines, Mines Branch Ann. Rept., p. 161, Ottawa, 1914.
———5. Mineral production of Canada during the calendar year 1913 [mercury]: Canada Dept. Mines, Mines Branch Ann. Rept., p. 149, Ottawa, 1914.
———6. Mineral Production of Canada during the calendar year 1915 [mercury]: Canada Dept. Mines, Mines Branch Ann. Rept., p. 149, 1917.
McLennan, J. C. 1. On the temperature of the mercury arc: Sci. Am. Suppl., vol. 79, p. 107, Feb. 13, 1915.
McNeely, W. M. 1. Notes on quicksilver: Mexican Min. Jour., vol. 8, p. 24, Sept., 1909.
Mactear, James. 1. Mining and metallurgy of quicksilver in Mexico: Inst. Min. and Met., London, vol. 4, pp. 69–120, 1896.
Mallet, J. W. 1. Note on the extent to which mercury volatilizes along with the vapor of water at 100° C.: Am. Jour. Sci., 2d ser., vol. 30, pp. 124–125, 1860.
Manufacturers Record. 1. American quicksilver industry as affected by the war: Vol. 71, p. 61, Jan. 11, 1917.
Map of Alaska. 1. Distribution of mineral deposits [quicksilver]: U. S. Geol. Survey Bull. 642, pl. 1, in pocket, 1916.
Mason, R. B. 1. Letter from Monterey, Cal., dated Aug. 17, 1848: Repts. Secretary of War (H. Doc. 17, 31st Cong., 1st sess.), pp. 528–536, 1850. Gives a description of the quicksilver mines near San Jose.
Mellor, J. W. 1. Modern inorganic chemistry [mercury], new ed., pp. 341–345, London, 1917.
Melville, W. H. 1. Metacinnabarite from New Almaden, Cal.: Am. Jour. Sci., 3d ser., vol. 40, pp. 291–295, 1890: U. S. Geol. Survey Bull. 78, pp. 80–83, 1891.
Melville, W. H., and Lindgren, Waldemar. 1. Contributions to the mineralogy of the Pacific coast [cinnabar crystals]: U. S. Geol. Survey Bull. 61, pp. 11–22, 1890.
Merrill, F. J. H. 1. The mercury deposits of Mexico. Min. World, vol. 24, p. 244, Feb. 17, 1906.
Merritt, W. H. 1. Occurrence of cinnabar in British Columbia: Fed. Inst. Min. Eng. Trans., vol. 13, pp. 592–594, 3 figs., 1898.
Mertie, J. B., jr., and Harrington, G. L. 1. Mineral resources of the Ruby-Kuskokwim region [quicksilver lodes]: U. S. Geol. Survey Bull. 642, pp. 237–238, 258–259, 263, 1916.

Digitized by Google

Metallgesellschaft. 1. Comparative statement of the production of quicksilver: Thirteenth Ann. issue, pp. 19, 102, April, 1907.
———2. Comparative statement of the production of quicksilver: Fourteenth Ann. issue, pp. 19, 102, Mar., 1908.
———3. Comparative statement of the production of quicksilver: Fifteenth Ann. issue, pp. 19, 102, July, 1909.
———4. Comparative statement of the production of quicksilver: Sixteenth Ann. issue, pp. 19, 102, June, 1910.
———5. Comparative statement of the production of quicksilver: Seventeenth Ann. issue, pp. 19, 98, July, 1911.
———6. Comparative statement of the production of quicksilver: Eighteenth Ann. issue, pp. 19, 98, July, 1912.
———7. Comparative statement of the production of quicksilver: Nineteenth Ann. issue, pp. 19, 100, July, 1913.
———8. Comparative statement of the production of quicksilver: Twentieth Ann. issue, pp. 19, 100, July, 1914.
Metallurgical and Chemical Engineering. 1. Roasting furnace with fume condenser [designed to operate on ores containing volatile metals such as quicksilver and zinc]: Vol. 16, p. 706, patent, fig. 3 [diagram], June 15, 1917.
Mexican Mining Journal. 1. Purification of mercury: Vol. 11, pp. 32–33, Sept., 1910.
———2. Assaying mercury ores: Vol. 14, p. 30, Feb., 1912.
Miller, W. G. 1. Notes on the Cobalt area [Ontario] [mercury]: Eng. and Min. Jour., vol. 92, p. 647, Sept. 30, 1911.
Mineral Industry. 1. Quicksilver: Vol. 1, pp. 4–10, 407–410, 1893.
———2. Quicksilver: Vol. 2, pp. 551–554, 793, 799, 803, 1894.
———3. Quicksilver: Vol. 3, pp. 477–481, 1895.
———4. Quicksilver: Vol. 4, pp. 519–523, 1896.
———5. Quicksilver: Vol. 5, pp. 4, 7, 461–465, 828, 1897.
———6. Quicksilver: Vol. 6, pp. 4, 5, 563–565, 800, 831–832, 853, 856, 1898.
———7. Quicksilver: Vol. 7, pp. 3, 5, 577–581, 871, 874, 1899.
———8. Quicksilver: Vol. 8, pp. 3, 5, 8, 487–491, 856, 877, 880, 1900.
———9. Quicksilver: Vol. 9, pp. 3, 563–566, 804, 858, 879, 882, 1901.
———10. Quicksilver: Vol. 10, pp. 3, 555, 557, 784, 826–830, 858, 879, 882, 1902.
———11. Quicksilver: Vol. 11, pp. 3, 5, 776, 800, 831–832, 853, 856, 1903.
———12. Quicksilver: Vol. 12, pp. 3, 4, 305, 309, 311, 1904.
———13. Quicksilver: Vol. 13, pp. 3, 4, 371–375, 543, 1905.
———14. Quicksilver: Vol. 14, pp. 502–503, 1906.
———15. Quicksilver: Vol. 15, pp. 3, 9, 674–675, 676–679, 928, 1907.
———16. Quicksilver: Vol. 16, pp. 813, 816–817, 818–820, 1908.
———17. Quicksilver: Vol. 17, p. 13, 1909.
———18. Quicksilver: Vol. 18, pp. 3, 615–617, 1910.
———19. Quicksilver: Vol. 19, pp. 590–596, 1911.
———20. Quicksilver: Vol. 20, pp. 650–653, 1912.
———21. Quicksilver: Vol. 21, pp. 743–749, 1913.
———22. Quicksilver: Vol. 22, p. 994, 1914.
Mining American. 1. A new cinnabar district [Nevada]: Vol. 73, p. 7, Mar. 18, 1916.
———2. The mercury situation: Vol. 73, p. 5, Mar. 25, 1916.
———3. California's quicksilver: Vol. 75, p. 7, July 28, 1917.
Mining and Engineering Review (San Francisco). 1. Metallurgy of quicksilver: Vol. 20, pp. 7–8, Mar. 4, 1905.
———2. Quicksilver production in California: Vol. 20, p. 5, Jan. 28, 1905.
Mining and Engineering World. 1. Mexican quicksilver mining operations: Vol. 37, p. 282, Aug. 17, 1912.
———2. The world's quicksilver industry in 1912: Vol. 28, pp. 160–161, 904, Jan. 25 and May 10, 1913.
———3. Quicksilver output in 1913; California, largest producer: Vol. 41, p. 254, Aug. 8, 1914.
———4. Quicksilver deposits of the Kuskokwim region, Alaska: Vol. 42, pp. 817–819, May 1, 1915.
———5. Quicksilver deposits on the Mazatzal Range of Arizona: Vol. 44, pp. 81–82, Jan. 8; p. 1,131, June 17, 1916.
———6. The reaction in quicksilver: Vol. 44, p. 794, Apr. 22, 1916.

Digitized by Google

Mining and Engineering World. 7. Concentration methods for the reduction of quicksilver ores: Vol. 45, p. 366, Aug. 26, 1916.
——— 8. Recovering quicksilver from ores: Vol. 45, p. 740, Oct. 28, 1916.
——— 9. Quicksilver mining at Idria, Cal.: Vol. 45, p. 1112, Dec. 30, 1916.
Mining and Scientific Press. 1. Sonoma County quicksilver mines [California]: Vol. 27, p. 166, Sept. 13, 1873.
——— 2. Divisibility of quicksilver, gold, and silver: Vol. 28, p. 22, Jan. 10, 1874.
——— 3. California quicksilver in 1871, 1872, and 1873: Vol. 28, p. 50, Jan. 24, 1874.
——— 4. Why quicksilver is high [contains table of production at New Almaden, Cal., for 21 years]: Vol. 28, p. 184, Mar. 21, 1874.
——— 5. Quicksilver discoveries in California: Vol. 28, pp. 98, 118, 154, 170, 312, 1874.
——— 6. Quicksilver in California: Vol. 28, pp. 186, 198, 214, 258, 290, 294, 310, 314, 316, 322, 326, 337, 358, 362, 370, 402, 410, 1874.
——— 7. The Rattlesnake quicksilver mine [California]: Vol. 29, p. 54, July 25, 1874.
——— 8. Mineral wealth of Colusa County [cinnabar]: Vol. 29, p. 70, Aug. 1, 1874.
——— 9. From the quicksilver mines [California]: Vol. 29, p. 81, Aug. 8, 1874.
——— 10. Quicksilver in San Luis Obispo County (condensed from San Luis Obispo Tribune of Aug. 1, 1874): Vol. 29, p. 102, Aug. 15, 1874.
——— 11. Quicksilver in Sonoma and Napa [condensed from Calistoga Press]: Vol. 29, p. 114, Aug. 22, 1874.
——— 12. The Pine Flat quicksilver mines [California]: Vol. 29, pp. 139, 154, 322, Aug. 29, Sept. 5, and Nov. 21, 1874.
——— 13. Cinnabar, Lake, and Calistoga districts [California]: Vol. 29, p. 218, Oct. 3, 1874.
——— 14. Purifying quicksilver: Vol. 29, p. 289, Nov. 7, 1874.
——— 15. The Colusa quicksilver mines: Vol. 30, pp. 33, 42, 82, Jan. 16 and Feb. 6, 1875.
——— 16. Sonoma County quicksilver mines: Vol. 30, p. 66, Jan. 30, 1875.
——— 17. California [quicksilver and cinnabar]: Vol. 30, pp. 132–133, Feb. 27, 1875.
——— 18. Quicksilver in Solano County: Vol. 30, pp. 146, 346, Mar. 6 and May 29, 1875.
——— 19. Reduction of quicksilver ores—Patera's process: Vol. 30, p. 241, illus., Apr. 10, 1875.
——— 20. Mercurial minerals and their associates: Vol. 59, pp. 298–299, 318–319, Oct. 19 and 26, 1889.
——— 21. California quicksilver mines: Vol. 81, pp. 506–507, Nov. 3, 1900.
——— 22. The Great Eastern quicksilver mine [Sonoma County, Cal.]: Vol. 89, p. 391, 2 figs., Dec. 10, 1904.
——— 23. Cinnabar in San Luis Obispo County, Cal.: Vol. 89, p. 323, 2 figs., Nov. 12, 1904.
——— 24. Reduction of cinnabar at Sulphur Creek, Cal.: Vol. 90, p. 335, May 27, 1905.
——— 25. Reduction of quicksilver: Vol. 95, p. 151, Aug. 3, 1907.
——— 26. The use and care of mercury: Vol. 95, pp. 216–217, Aug. 17, 1907.
——— 27. [Quicksilver near Las Penas, Mexico]: Vol. 95, p. 732, Dec. 14, 1907.
——— 28. Quicksilver in California: Vol. 100, pp. 15–16, map, Jan. 1, 1910.
——— 29. The quicksilver situation: Vol. 100, p. 789, May 28, 1910.
——— 30. Quicksilver in Mexico: Vol. 102, pp. 820–821, June 17, 1911.
——— 31. Quicksilver [editorial]: Vol. 104, pp. 298–299, Feb. 24, 1912.
——— 32. Report from the Terlingua quicksilver district, Tex.: Vol. 105, p. 772, Dec. 14, 1912.
——— 33. Cinnabar in Washington: Vol. 106, p. 796, May 24, 1913.
——— 34. Recovery of quicksilver from ores: Vol. 107, p. 348, Aug. 30, 1913.
——— 35. Discovery of cinnabar in Matzatzal Mountains, Ariz.: Vol. 109, p. 156, July 25, 1914.
——— 36. Notes on quicksilver in California: Vol. 112, p. 353, Mar. 4, 1916.
——— 37. Quicksilver from alluvial deposits, Oregon [editorial]: Vol. 112, p. 497, Apr. 1, 1916.
——— 38. Quicksilver [editorial]: Vol. 112, p. 659, May 6, 1916.
——— 39. Concentration of quicksilver ores: Vol. 112, p. 796, May 27, 1916.

Digitized by Google

Mining and Scientific Press. 40. The demand for quicksilver: Vol. 113, p. 137, July 22, 1916.
——— 41. Mineral production of California in 1915: Vol. 113, p. 361, Sept. 2, 1916.
——— 42. Metal market in 1916 [quicksilver]: Vol. 114, pp. 6–7, Jan. 6, 1917.
——— 43. Freezing point of mercury: Vol. 114, p. 58, Jan. 13, 1917.
——— 44. Large production and extension of operation in Terlingua district, Tex.: Vol. 114, p. 590, Apr. 28, 1917.
——— 45. New metallurgical methods for quicksilver ores: Vol. 114, p. 768, June 2, 1917.
Mining and Statistic Magazine (New York) [continuation of Mining Magazine, New York]. 1. Mercury mines of New Almaden, Cal.: Vol. 10, pp. 142–143, 1858.
——— 2. Quicksilver mines of Monterey County, Cal.: Vol. 10, pp. 246–247, 1858.
——— 3. Santa Clara quicksilver mines [Cal.]: Vol. 10, p. 246, 1858.
——— 4. The quicksilver mine of New Almaden [Cal.]: Vol. 10, pp. 448–449, 1858.
Mining Journal (London). 1. Concentration of quicksilver ores: Vol. 118, pp. 503–504, Aug. 11, 1917.
Mining Magazine (New York). 1. The Almaden [quicksilver] mine, Cal.: Vol. 1, pp. 209–210, 1853.
——— 2. Quicksilver in California: Vol. 2, pp. 116–117, 1854.
——— 3. Quicksilver exported from San Francisco during the year 1853: Vol. 2, pp. 352–353, 1854.
——— 4. Quicksilver: Vol. 7, p. 424, 1856.
——— 5. Shipment of quicksilver from San Francisco: Vol. 8, p. 104, 1857.
——— 6. Quicksilver: Vol. 9, pp. 99–101, 1857.
Mining Magazine (New York) [not a continuation of the previous Mining Magazine of New York]. 1. Quicksilver in Utah [editorial]: Vol. 12, pp. 125–126, 1905.
Mining Magazine and Journal of Geology [continuation of Mining and Statistic Magazine]. 1. New quicksilver mine in California: Second ser., vol. 1, p. 81, November, 1859.
Mining Reporter. 1. Texas quicksilver deposits: Vol. 43, p. 155, 1901.
——— 2. Mercury deposits of Mexico: Vol. 53, pp. 466–467, May 10, 1906.
Mining Science. 1. Methods of quicksilver reduction: Vol. 58, p. 467, Dec. 10, 1908.
——— 2. Quicksilver in California: Vol. 65, p. 349, Apr. 18, 1912.
——— 3. Large quicksilver consumption: Vol. 65, p. 525, June 20, 1912.
——— 4. Prospecting for quicksilver: Vol. 66, pp. 33–34, July 18, 1912.
——— 5. California quicksilver: Vol. 66, p. 35, July 18, 1912.
Mitchell, G. J. 1. Minerals of Oregon (cinnabar): Oregon Univ. Bull., new ser., vol. 13, pp. 20–21, November, 1915.
Monckton, G. F. 1. Cinnabar-bearing rocks of British Columbia: Inst. Min. Eng. [England] Trans., vol. 27, pp. 463–469, 1904.
Moore, G. E. 1. On the occurrence in nature of amorphous mercuric sulphide [names metacinnabar as a new species]: Am. Jour. Sci., 3d ser., vol. 3, pp. 36–43, 1872.
Moses, A. J. 1. Eglestonite, terlinguaite, and montroydite, new mercury minerals from Terlingua, Tex.: Am. Jour. Sci., 4th ser., vol. 16, pp. 253–263, 6 figs., September, 1903.
——— 2. Eglestonit, Terlinguait und Montroydit, neue Quecksilbermineralien von Terlingua in Texas: Zeitschr. Kryst. Min., Bd. 39, pp. 3–13, 6 figs., 1904.
Moses, A. J., and Parsons, C. L. 1. Elements of mineralogy, etc. [mercury or quicksilver minerals], 5th ed., pp. 373–378, New York, D. Van Nostrand Co., 1916.
Mosher, D. 1. Notes on the metallurgy of cinnabar ores: Pacific Miner, February, 1910. [Not seen.]
Mulholland, C. A. 1. Treatment of low-grade cinnabar ores: Australian Min. Standard, vol. 45, p. 565, June 8, 1911.
——— 2. The treatment of low-grade cinnabar ores: Min. and Eng. World, vol. 35, pp. 241–242, Aug. 5, 1911.
——— 3. Wet method of mercury extraction: Min. and Sci. Press, vol. 111, p. 346, Sept. 4, 1915.

Digitized by Google

Murray, B. L. 1. Electrolytic determination of mercury in mercury oleates: Jour. Ind. and Eng. Chemistry, vol. 8, p. 257, March, 1916.
——— 2. Electrolytic determination of mercury in mercury salicylates: Jour. Ind. and Eng. Chemistry, vol. 8, p. 258, March, 1916.
New Almaden [quicksilver] mine [of California]. 1. The discussion reviewed: Press of the Daily National office, 76 pp., San Francisco, 1859. Pamphlet.
——— 2. Further correspondence between the counsel for the proprietors and the Government, 42 pp., Washington, 1859. Pamphlet.
——— 3. Letter of Hon. John A. Collier in reference to the New Almaden quicksilver property, 29 pp., New York, 1859. Pamphlet.
——— 4. Opinion of the Court, delivered by Mr. Justice Clifford in "U. S. vs. Castillero," 53 pp., New York, 1863. Pamphlet.
——— 5. Memorial of the quicksilver miners of California, 32 pp., Washington, 1883. Pamphlet.
New Idria Mining Co., Cal. 1. *See also* McGarrahan, William, 1876, and Shaw, C. P., 1872.
Newcomb, B. M. 1. Quicksilver in California: Mineral Industry, vol. 10, pp. 555–557, 1902.
Newland, D. H. 1. Quicksilver: Mineral Industry, vol. 12, pp. 305–309, 311, 1904.
Newman, John. 1. On a new mercurio-pneumatic apparatus: Jour. Sci. and Arts, vol. 1, pp. 185–187, London, 1816.
Nöggerath, Adalbert. 1. Mittheilungen über die Quecksilbergwerke zu Almadén und Almadenejos in Spanien nebst einem Ueberblick der Vorkommnisse von Quecksilber im Allgemeinen [California, United States, Mexico]: Zeitschr. Berg., Hütten- u. Salinenwesen preuss, St., vol. 10, pp. 380, 390, 1862.
Northey, G. V. 1. Concentration of cinnabar ores: Eng. and Min. Jour., vol. 96, pp. 783–784, Oct. 25, 1913.
Ontario Bureau of Mines. 1. Cinnabar or sulphide of mercury, found in British Columbia, at the Ebenezer mine, Kicking Horse Pass, disseminated through crystalline limestone: Sixth Rept., 1896, p. 211, 1897.
——— 2. Mercury in Cobalt ores: Twenty-sixth Ann. Rept., p. 20, 1917.
Oregon Bureau of Mines and Geology. 1. Minerals and mineral industries of Oregon (quicksilver): Panama-Pacific ed., pp. 24–25, 1915.
Osmont, V. C. 1. A geological section of the Coast Ranges north of the Bay of San Francisco [quicksilver deposits]: California Univ. Dept. Geology Bull., vol. 4, pp. 50–51, Dec. 1, 1904.
Oswald, Wilhelm. 1. The principles of inorganic chemistry [mercury]: Trans. by A. Findlay, pp. 656–672, London, 1902.
Pagliucci, F. D. 1. The quicksilver deposits of Huitzuco [Mexico]: Eng. and Min. Jour., vol. 79, pp. 417–418, 2 figs., Mar. 2, 1905.
Palmer, L. A. 1. Ore occurrence at the Cloverdale mine [Sonoma County, Cal.] [quicksilver]: Min. and Sci. Press, vol. 108, p. 812, 1 fig., May 16, 1914.
Panoche Grande Quicksilver Mining Co. 1. The origin of the grant and the change of title vesting the rancho in said company, 16 pp., 1861. Pamphlet.
Panoche Grande rancho, Cal. 1. Speech of James A. Garfield on the McGarrahan claim, delivered in the House of Representatives, Feb. 20, 1871, 16 pp., 1871. Pamphlet..
Pardee, J. T., and Hewett, D. F. 1. Geology and mineral resources of the Sumpter quadrangle [mercury and cinnabar]: Oregon Bur. Mines and Geology, Mineral Resources of Oregon, vol. 1, pp. 66, 91, October, 1914.
Parker, E. W. 1. Quicksilver; summary, production, prices: U. S. Geol. Survey Twenty-first Ann. Rept., pt. 6, pp. 7, 273–283, 1901.
——— 2. Quicksilver: U. S. Geol. Survey Mineral Resources, 1911, pt. 1, pp. 94, 110, 1912.
——— 3. Quicksilver: U. S. Geol. Survey Mineral Resources, 1912, pt. 1, pp. 117, 136, 1913.
Parks, H. M. 1. Mining increasing in Oregon [quicksilver in southwestern Oregon]: Eng. and Min. Jour., vol. 103, p. 106, Jan. 13, 1917.
Parks, H. M., and Swartley, A. M. 1. Handbook of the mining industry of Oregon [cinnabar deposits]: Oregon Bur. Mines and Geology, Mineral Resources of Oregon, vol. 2, pp. 14, 33, 55–56, 218, 227, December, 1916.
Patten, H. E., and Mains, G. H. 1. An apparatus for the purification of mercury: Jour. Ind. and Eng. Chemistry, vol. 9, pp. 600–603, June, 1917.
Penfield, S. J. 1. Crystallized tiemannite and metacinnabarite: Am. Jour. Sci., 3d ser., vol. 29, pp. 449–454, 1885.

Digitized by Google

Phillips, J. A. 1. A treatise on ore deposits [quicksilver], pp. 69, 558–561, 583, illus., London, 1884.
Phillips, J. A., and Louis, Henry. 1. A treatise on ore deposits [mercury], 2d ed., pp. 116, 117, 135, 142, 746, 791–796, 829, 830, 867, illus., London, 1896.
Phillips, W. B. 1. Sulphur, oil, and quicksilver in Trans-Pecos Texas: Texas Univ. Min. Survey Bull. 2, 42 pp., illus., map, 1902.
——— 2. [Description of the mapping of the quicksilver district in Texas]: Texas Univ. Min. Survey Bull. 7, pp. 8–9, map, 1904.
——— 3. A new quicksilver field in Brewster County, Tex.: Eng. and Min. Jour., vol. 77, pp. 160–161, Jan. 28, 1904.
——— 4. Extension of the quicksilver district in Brewster County, Tex.: Eng. and Min. Jour., vol. 78, p. 212, Aug. 11, 1904.
——— 5. Condition of the quicksilver industry in Brewster County, Tex.: Eng. and Min. Jour., vol. 78, pp. 553–554, Oct. 6, 1904.
——— 6. The quicksilver deposits of Brewster County, Tex.: Econ. Geology, vol. 1, pp. 155–162, 1905.
——— 7. Terlingua quicksilver district, Brewster County, Tex.: Min. World, vol. 23, pp. 39, 63, 95, 198, 259–260, 1905.
——— 8. Condition of the quicksilver industry in Brewster County, Tex.: Mineral Industry, vol. 13, pp. 376–379, 1905.
——— 9. Quicksilver deposits of Terlingua district, Brewster County, Tex.: Am. Min. Cong., Eighth Ann. Sess., pp. 184–193, 1906.
——— 10. The quicksilver deposits of Brewster County, Tex.: Econ. Geology, vol. 1, pp. 155–162, 1906.
——— 11. The quicksilver industry in Brewster County, Tex.: Mineral Industry, vol. 14, pp. 506–511, 1906.
——— 12. Prospects of the quicksilver industry in Texas: Min. World, vol. 25, p. 463, Oct. 13, 1906.
——— 13. Geology of quicksilver deposits: Min. World, vol. 29, p. 131, July 25, 1908.
——— 14. Condition of the quicksilver industry in Texas: Eng. and Min. Jour., vol. 88, pp. 1022–1024, Nov. 20, 1909.
——— 15. The mineral resources of Texas [quicksilver]: Texas Dept. Agr. Bull. 14, pp. 8, 20–21, 1910.
——— 16. The quicksilver industry in Texas: Eng. and Min. Jour., vol. 91, pp. 85–86, 419, Jan. 7 and Feb. 25, 1911.
——— 17. Quicksilver in Texas: Mineral Industry, vol. 19, pp. 593–594, 1911.
——— 18. Quicksilver in Texas: Mineral Industry, vol. 20, pp. 652–653, 1912.
——— 19. Quicksilver in Texas in 1911: Eng. and Min. Jour., vol. 93, pp. 38–39, Jan. 6, 1912.
——— 20. Quicksilver industry of Texas: Eng. and Min. Jour., vol. 95, pp. 78–79, Jan. 11, 1913.
——— 21. Quicksilver in Texas: Mineral Industry, vol. 21, pp. 746–747, 1913.
——— 22. Quicksilver in Texas in 1913: Eng. and Min. Jour., vol. 97, p. 156, Jan. 10, 1914.
——— 23. The mineral resources of Texas [quicksilver]: Texas Univ. Bull. 365 (sci. ser. No. 29), pp. 32–33, Oct. 15, 1914.
——— 24. Quicksilver industry of Texas: Min. and Sci. Press, vol. 115, p. 93, July 21, 1917.
Pickering, A. H. 1. Quicksilver in 1915: Min. Jour. (London), vol. 112, p. 47, Jan. 15, 1916.
Pitaval, R., and Ganet, I. 1. Traité général de commerce des minérais et métaux combustibles, alliages, engrais, etc. [mercure], pp. 568–572, Paris [1917?].
Place, R. G. 1. New Almaden quicksilver mine: Eng. and Min. Jour., vol. 100, p. 465, Sept. 18, 1915.
Pošepný, Franz. 1. The genesis of ore deposits [quicksilver]: Am. Inst. Min. Eng. Trans., vol. 23, pp. 225–226, 257, 1894; discussion, vol. 24, p. 984, 1895.
——— 2. The genesis of ore deposits [quicksilver], reprinted from vols. 23 and 24 of Am. Inst. Min. Eng. Trans., 2d ed., pp. 32–36, 66, 256, New York, 1902.
Powell, J. W. 1. Investigations of quicksilver deposits [in eastern California and western Nevada]: U. S. Geol. Survey Seventh Ann. Rept., pp. 25–26, 1888.

Digitized by Google

Powell, J. W. 2. Value of quicksilver at San Francisco: U. S. Geol. Survey Eighth Ann. Rept., pt. 1, p. 85, 1889.
———3. Value of quicksilver at San Francisco: U. S. Geol. Survey Tenth Ann. Rept., pt. 1, p. 52, 1890.
———4. Value of quicksilver at San Francisco: U. S. Geol. Survey Twelfth Ann. Rept., pt. 1, p. 14, 1891.
———5. Metallic products of the United States in 1893 [quicksilver]: U. S. Geol. Survey Fifteenth Ann. Rept., p. 72, 1895.
Prather, J. K. 1. Mining quicksilver; metallurgy of cinnabar: El Paso Min. Jour., 1 p., October, 1909. [Not seen.]
Prindle, L. M. 1. The Fortymile quadrangle, Yukon-Tanana region, Alaska [cinnabar associated with gold]: U. S. Geol. Survey Bull. 375, p. 32, 1909.
Purnell, Samuel. 1. Remarks on quicksilver: Min. and Sci. Press, vol. 33, pp. 240, 276, 289, 321, 352, Oct. 7, 21, and 28, Nov. 11 and 25, 1876.
Quicksilver Mining Co. [deposits in California]. 1. Charter and by-laws: Ann. Meeting Stockholders (Philadelphia), Rept., 30 pp., Jan. 4, 1864. Pamphlet.
———2. Annual report, 103 pp., Feb. 22, 1865. Pamphlet.
———3. Annual Meeting Stockholders (Philadelphia), Feb. 28, 1866: Ann. Rept., 41 pp., New York, March, 1866. Pamphlet.
———4. Annual report, 30 pp., Feb. 24, 1869. Pamphlet.
———5. Reports and exhibits at Ann. Meeting Stockholders (New York), Feb. 22, 1871. Pamphlet.
———6. Reports and exhibits at Ann. Meeting Stockholders (New York), Feb. 28, 1872. Pamphlet.
———7. Reports and exhibits at Ann. Meeting Stockholders (New York), Feb. 26, 1873. Pamphlet.
———8. Tables and tabular statements submitted at Ann. Meeting Stockholders (New York), Feb. 28, 1877; Ann. Rept. for 1876, 67 pp., New York, 1877. Pamphlet.
———9. Annual report for 1882, 63 pp., New York, 1883. Pamphlet.
———10. Report for 1883 and the four months ending Apr. 30, 1884, 84 pp., New York, 1884. Pamphlet.
———11. Report for year ending Apr. 30, 1885, 36 pp., New York, 1885. Pamphlet.
———12. Report for year ending Apr. 30, 1886, 41 pp., New York, 1886. Pamphlet.
———13. Report for year ending Apr. 30, 1887, 45 pp., New York, 1887, Pamphlet.
———14. Report for year ending Apr. 30, 1888, 51 pp., New York, 1888. Pamphlet.
———15. Report for year ending Apr. 30, 1889, 55 pp., New York, 1889. Pamphlet.
———16. Report for year ending Apr. 30, 1890, 57 pp., New York, 1890. Pamphlet.
———17. Report for year ending Apr. 30, 1891, 53 pp., New York, 1891. Pamphlet.
Ramírez, Santiago. 1. Informe sobre el mineral de Guadalcázar en el Estado de San Luis Potosí [minas de mercurio]: Mexico, Ministerio de fomento, Anales, vol. 3, pp. 395–397, 1877.
———2. Noticia histórica de la riqueza minera de Mexico [mercurio]: pp. 88–98, Mexico, Oficina tipográfica, Sec. Fomento, 1884.
Randol, J. B. 1. Production of quicksilver at New Almaden for twenty-two years and three months: Min. and Sci. Press, vol. 30, p. 72, Jan. 30, 1875.
———2. Quicksilver in California: In Raymond, Mines and mining in the States and Territories west of the Rocky Mountains, Eighth Ann. Rept. [for 1875], pp. 4–21, 1877.
———3. Production and price of quicksilver for thirty-four years, 1850 to 1883, Table, San Francisco, March, 1884. [1 sheet.]
———4. Production of quicksilver in California for the years 1885 and 1886: California State Min. Bur. Sixth Ann. Rept., pt. 1, pp. 72–73, 1886.
———5. California quicksilver, a table showing the production for the past six years, 13 pp., San Francisco, 1890. Pamphlet.
———6. Quicksilver mines and reduction works: California State Min. Bur. Tenth Ann. Rept., pp. 920–929, 1890.
———7. Quicksilver and the tariff in the House of Representatives and elsewhere, 20 pp., San Francisco, 1890. Pamphlet.

Digitized by Google

Randol, J. B. 8. Earnings and expenses of the Quicksilver Mining Co., New Almaden, Cal., for twenty-one years, from Jan. 1, 1871, to Dec. 31, 1891. Pamphlet without place of publication or date.
——— 9. Report on mineral industries in the United States; Quicksilver: Eleventh Census, 1890, pp. 179–245, 1892.
Rangel, Manuel. 1. Apuntes sobre la distribución de minerales en el Estado de Durango [mercurio]: Soc. Geol. Mexicana Bol., t. 7, pt. 2, p. 113, 1911.
Ransome, F. L. 1. Quicksilver [in California]: U. S. Geol. Survey Geol. Atlas, Mother Lode District folio (No. 63), p. 10, 1909.
——— 2. Preliminary account of Goldfield, Bullfrog, and other mining districts in southern Nevada [cinnabar]: U. S. Geol. Survey Bull. 303, p. 36, 1907.
——— 3. Notes on some mining districts in Humboldt County, Nev. [occurrence and character of cinnabar]: U. S. Geol. Survey Bull. 414, pp. 30, 37, 45, 65, 71, 1909.
——— 4. The geology and ore deposits of Goldfield, Nev. [occurrence of cinnabar]: U. S. Geol. Survey Prof. Paper 66, pp. 108, 113, 1909.
——— 5. Notes on some mining districts in Humboldt County, Nev. [occurrence and character of quicksilver-antimony deposits]: U. S. Geol. Survey Bull. 414, p. 71, 1909.
——— 6. Quicksilver deposits of the Mazatzal Range, Ariz.: U. S. Geol. Survey Bull. 620, pp. 111–128, 5 figs., 1915.
Rath, G. vom. 1. Vorträge und Mittheilungen; Bericht über die Umgebungen von San Francisco, Santa Cruz, and New Almaden, Californien: Niederrhenisch. Ges. f. Natur-und Heilkunde in Bonn, Sitzungsb., Naturwiss. Sect., 16 November, pp. 303–317, 1885.
Raymond, Rossiter W. 1. New Almaden quicksilver mines: Mineral resources of the States and Territories west of the Rocky Mountains [for 1868], pp. 9–11, 1869.
——— 2. Production of quicksilver during 1869: Mines and mining in the States and Territories west of the Rocky Mountains [for 1869], p. 759, 1870.
——— 3. Condition of the mining industry [quicksilver in California]: Mines and mining in the States and Territories west of the Rocky Mountains [for 1870], pp. 15, 29, 528, 1872.
——— 4. Chemistry of the Washoe process; chemical action of mercury and other reagents: Mines and mining in the States and Territories west of the Rocky Mountains [for 1870], pp. 404–405, 413, 414, 1872.
——— 5. Quicksilver, production and reports of: Mines and mining in the States and Territories west of the Rocky Mountains, Fourth Ann. Rept. [for 1871], p. 523, 1873.
——— 6. Quicksilver: Mines and mining in the States and Territories west of the Rocky Mountains, Fifth Ann. Rept. [for 1872], pp. 9, 497, 1873.
——— 7. Condition of the mining industry [quicksilver in California and Nevada]: Mines and mining in the States and Territories west of the Rocky Mountains, Sixth Ann. Rept. [for 1873], pp. 27–39, 196–197, 1874.
——— 8. The mining and metallurgy of quicksilver; Mines and mining in the States and Territories west of the Rocky Mountains, Sixth Ann. Rept. [for 1873], pp. 379–407, 1874.
——— 9. Condition of the mining industry [quicksilver in California, Nevada, and Oregon]: Mines and mining in the States and Territories west of the Rocky Mountains, Seventh Ann. Rept. [for 1874], pp. 13, 15, 173, 189, 271, 316, 317, 1875.
——— 10. Condition of the mining industry [quicksilver in California]: Mines and mining in the States and Territories west of the Rocky Mountains, Eighth Ann. Rept. [for 1875], pp. 3–15, 18–21, 1877.
Raymond, R. W., and Ingalls, W. R. 1. The mineral wealth of America [quicksilver]: Am. Inst. Min. Eng. Bull. 27, pp. 251, 255, March, 1909.
Revista Semanal. 1. Azogue [quicksilver in California and Mexico]: No. 6, New York, July 28, 1917.
Richardson, C. H. 1. Economic geology [mercury; its properties, occurrence, and uses], pp. 126–130, New York, McGraw-Hill Book Co., 1913.
Rickard, T. A., and Ralston, O. C. 1. Flotation [cinnabar subject to flotation], p. 71, San Francisco, Min. and Sci. Press, 1917.
Ries, Heinrich. 1. Economic geology [mercury], 4th ed., pp. 771–778, 1916.
Robertson, M. 1. Light that kills bacteria [mercury vapor lamp]: Illus. World, vol. 26, pp. 118–119, diags., September, 1916.

Digitized by Google

Rogers, A. F. 1. Eglestonite from San Mateo County, Cal.: Am. Jour. Sci., 4th ser., vol. 32, pp. 48–50, 1911.
———2. Some notes on the rare minerals of California [metacinnabarite from San Benito County]: Min. and Eng. World, vol. 37, p. 105, July 20, 1912.
Rolland, G. 1. Les gisements de mercure de Californie: Annales des mines, 7th ser., vol. 14, pp. 384–432, 1878.
Rundall, W. H. 1. Mining and treatment of quicksilver ores at Guadalcazar, Mexico: Eng. and Min. Jour., vol. 59, pp. 607–609, illus., June 29, 1895; Sci. Am. Suppl., vol. 40, pp. 16289–16290, July 13, 1895.
Sachs, A. 1. Zinnoberkristalle aus Sonoma County in Kalifornien; Gips und Kalkspatkristalle von Terlingua in Texas: Centralbl. Mineralogie, No. 1, 1907, pp. 17–19, 1907.
Salt Lake Mining Review. 1. Saving gold and cinnabar: Vol. 14, p. 23, May 15, 1912.
———2. Great cinnabar discovery [near Mina, Nev.]: Vol. 15, pp. 17–18, July 15, 1913.
———3. Quicksilver for explosives: Vol. 16, p. 24, Oct. 30, 1914.
———4. Quicksilver in California: Vol. 18, p. 39, Apr. 15, 1916.
Sandberger, F. 1. Ueber merkwürdige Quecksilbererze aus Mexico: K.-bayer. Akad. Wiss. München Sitzungsber., Bd. 5, H. 2, pp. 202–205, July 3, 1875.
Sanford, Samuel, and Stone, R. W. 1. Useful minerals of the United States [cinnabar or quicksilver in California, Colorado, Nevada, Oregon, Texas, and Utah]: U. S. Geol. Survey Bull. 585, pp. 35, 48, 117, 155, 182, 185, and 187, 1914.
San Francisco Commercial Herald. 1. Quicksilver production and trade of California: In Raymond, Mines and mining in the States and Territories west of the Rocky Mountains, Eighth Ann. Rept. [for 1875], pp. 461–462, 1877.
Santa Clara Mining Association of Baltimore. 1. First Ann. Rept., 13 pp., Baltimore, 1857. Pamphlet.
———2. Eighth annual report. 8 pp., Apr. 6, 1863. Pamphlet.
Schaller, W. T. 1. The properties of mosesite [mercury mineral from Terlingua, Tex.]: U. S. Geol. Survey Bull. 509 (Mineralogical notes, ser. 2), pp. 104–109, 1912.
Schrader, F. C., Stone, R. W., and Sanford, Samuel. 1. Useful minerals of the United States (a revision of U. S. Geol. Survey Bull. 585): U. S. Geol. Survey Bull. 624, 412 pp., 1917.
Schrauf, A. 1. Aphorismen über Zinnober: Zeitschr. prakt. Geologie, Bd. 2, pp. 10–18, January, 1894.
Scientific American. 1. A mercury-vapor engine: Vol. 112, p. 494, 1915.
———2. The freezing point of mercury: Vol. 115, pp. 473, 527, Dec. 9, 1916.
Scientific American Supplement. 1. The critical temperature of mercury: Vol. 80, p. 393, Dec. 18, 1915.
———2. The damping of waves and other disturbances in mercury: Vol. 83, No. 2140, p. 5, Jan. 6, 1917.
———3. The freezing point of mercury: Vol. 83, No. 2154, pp. 232 and 405, Apr. 14, 1917.
Scott, Robert. 1. Modern quicksilver reduction: Min. and Sci. Press, vol. 100, p. 164, Jan. 22, 1910.
Seamon, W. H. 1. A volumetric method for the determination of mercury: Eng. and Min. Jour., vol. 87, pp. 1047–1048, May 22, 1909.
Sharwood, W. J. 1. The determination of mercury in cyanide solution and precipitate: Min. and Sci. Press, vol. 111, pp. 663–665, Oct. 30, 1915.
———2. The estimation of gold and silver in mercury and amalgam, and the preparation of pure mercury: Am. Inst. Min. Eng. Trans., vol. 52, pp. 158–161, 1916.
Shaw, C. P. 1. Argument before the U. S. Senate Committee, Forty-second Congress, in support of the claim of William McGarrahan for the Rancho Panoche Grande, Cal., 320 pp., Washington, 1872.
Shockley, W. S. 1. Quicksilver in Nevada: Mineral Industry, vol. 17, p. 745, 1909.
Silliman, B., jr. 1. Notes on the New Almaden quicksilver mines: Am. Jour. Sci., 2d ser., vol. 38, pp. 190–194, 1864.
Simonds, F. W. 1. The minerals and mineral localities of Texas [cinnabar and mercury]: Texas Univ. Min. Survey Bull 5, pp. 20, 55, Dec., 1902.

Digitized by Google

Skidmore, W. A. 1. Quicksilver mining; progress in Napa, Lake, and Sonoma counties, Cal.: Min. and Sci. Press, vol. 27, p. 152, Sept. 6, 1873.
——— 2. Quicksilver in California: In Raymond, Mines and mining in the States and Territories west of the Rocky Mountains, Seventh Ann. Rept. [for 1874], pp. 13, 15, 173, 189, 1875.
Smith, G. O. 1. Quicksilver [cinnabar]: U. S. Geol. Survey Geol. Atlas, Mount Stuart folio (No. 106), p. 9, 1904.
——— 2. Mid-year review of mining industry, 1915; special demand for quicksilver: Min. and Eng. World, vol. 43, p. 59, July 10, 1915.
Smith, J. A. 1. Catalogue of the minerals of Colorado [mercury]: Colorado State Geologist Bienn. Rept., 1880, p. 64, 1881.
Smith, P. S. 1. The Lake Clark-Central Kuskokwim region, Alaska [quicksilver]: U. S. Geol. Survey Bull. 655, pp. 131, 139–150, 1917.
Smith, P. S., and Maddren, A. G. 1. Quicksilver deposits of the Kuskokwim region [Alaska]: U. S. Geol. Survey Bull. 622, pp. 272–291, 1915.
Smith, R. O. 1. The rapid precipitation of lead and mercury in the electrolytic way, 20 pp., Easton, Pa., 1905.
Smith, S. W. J., and Moss, H. 1. Experiments with mercury jets: Roy. Soc. London, Proc., ser. A, vol. 93, pp. 373–393, figs., July 2, 1917.
Spalding, E. P. 1. The quicksilver mines of Brewster County, Tex.: Eng. and Min. Jour., vol. 71, pp. 749–750, June 15, 1901.
Spencer, L. J. 1. The world's minerals [cinnabar], pp. 68–69, pl. 6, figs. 2, 3, 1911; 2d ed., with an appendix by W. D. Hamman, pp. 88–89, pl. 6, figs. 2, 3; pp. 279–282, 1916.
Spirek, Vincente. 1. The metallurgy of quicksilver: Mineral Industry, vol. 8, pp. 493–494, 1900.
Spurr, J. E., and Post, W. S. 1. Report of the Kuskokwim expedition [occurrence of cinnabar]: U. S. Geol. Survey Special Publication, maps and descriptions of routes of exploration in Alaska in 1898, p. 37, 1899.
Stafford, O. F. 1. The mineral resources and mineral industry of Oregon for 1903 [mercury]: Oregon Univ. Bull., new ser., vol. 1, pp. 98–100, 1904.
Stillman, M. H. The damping of waves and other disturbances in mercury: Bur. Standards Bull., vol. 13, pp. 563–568, Mar. 6, 1917. Abstract, Sci. Am., vol. 115, p. 527, Dec. 9, 1916.
Storms, W. H. Quicksilver production of California: Min. and Sci. Press, vol. 104, p. 400, Mar. 16, 1912.
Stovall, D. H. 1. Quicksilver mining in Oregon: Min. World, vol. 22, p. 137, Jan. 28, 1905.
——— 2. Oregon's quicksilver mine: Los Angeles Min. Rev., vol. 17, No. 9, p. 11, Mar. 4, 1905.
——— 3. Quicksilver extraction: Los Angeles Min. Rev., vol. 18, No. 7, p. 7, Aug. 12, 1905.
——— 4. The cinnabar deposits of Oregon: Min. World, vol. 25, p. 205, Aug. 25, 1906.
Strauss, L. W. 1. Modern quicksilver reduction: Min. and Sci. Press, vol. 100, p. 431, Mar. 19, 1910.
Struthers, Joseph. 1. Quicksilver: U. S. Geol. Survey Mineral Resources, 1901, pp. 235–238, 1902.
——— 2. Quicksilver: Mineral Industry, vol. 11, pp. 540–543, 547, 1903.
——— 3. Quicksilver: U. S. Geol. Survey Mineral Resources, 1902, pp. 251–258, 1904.
——— 4. Quicksilver industry in the United States and foreign countries: Min. World, vol. 21, pp. 79–80, July 23, 1904.
——— 5. Quicksilver: U. S. Bur. Census, Spec. Repts., Mines and quarries, 1902, pp. 649–657, 1905.
Symington, R. B. 1. Present practice in the metallurgy of quicksilver in California: Mineral Industry, vol. 7, pp. 582–588, 1899.
Szilard, Béla. 1. Process of separating mercury from poor ores by electrolysis: U. S. Patent No. 980364, Jan. 3, 1911.
Tate, J. T. 1. The passage of low-speed electrons through mercury vapor and the ionizing potential of mercury vapor: Physical Review, 2d ser., vol. 10, pp. 81–83, 1917.
Texas Mineral Resources. 1. Quicksilver deposits of Brewster County, Tex.: Vol. 1, No. 3, p. 7, Jan., 1917.
Thom, W. T. 1. Quicksilver in 1906; U. S. Geol. Survey Mineral Resources, 1906, p. 15, 1907.
——— 2. Quicksilver in 1907: U. S. Geol. Survey Mineral Resources, 1907, pt. 1, p. 9, 1908.

Digitized by Google

Thom, W. T. 3. Quicksilver in 1908: U. S. Geol. Survey Mineral Resources, 1908, pt. 1, pp. 9–10, 1909.
———4. Quicksilver in 1909: U. S. Geol. Survey Mineral Resources, 1909, pt. 1, p. 10, 1911.
———5. Quicksilver in 1910: U. S. Geol. Survey Mineral Resources, 1910, pt. 1. p. 12, 1911.
———6. Quicksilver in 1913: U. S. Geol. Survey Mineral Resources, 1913, pt. 1, pp. cxxx-cxxxi, cxlvii, 1914.
Thomas, Kirby. 1. Quicksilver in Mexico: Mineral Industry, vol. 18, pp. 621–622, 1910.
Thornhill, E. B. 1. Wet method of mercury extraction: Min. and Sci. Press, vol. 110, pp. 873–874, June 5, 1915.
———2. Recovery of mercury from residues of amalgamated cobalt ores: Canadian Min. Inst. Month. Bull. 36, pp. 263–268, April, 1915.
———3. Recovery of mercury from amalgamation tailing: Min. and Sci. Press, vol. 111, pp. 211–212, Aug. 7, 1915.
———4. Recovery of mercury from amalgamation tailing, Buffalo mines, Cobalt [Ontario]: Am. Inst. Min. Eng. Trans., vol. 52, pp. 165–169; discussion, pp. 169–170, 1916.
Todd, Aurelius. 1. The quicksilver mines of Oregon: West Am. Scientist, vol. 4, pp. 65–66, June, 1895.
Topographic map of the Terlingua quicksilver district, Brewster County, Tex. 1. In Texas Univ. Min. Survey Bull. 4, October, 1902.
Topographic map of Terlingua quadrangle, Brewster and Presidio counties, Tex. 1. In Texas Univ. Min. Survey Bull. 7, 1904.
Turner, H. W. 1. Further contributions to the geology of the Sierra Nevada [occurrence of cinnabar]: U. S. Geol. Survey Seventeenth Ann. Rept., pt. 1, pp. 677–678, 1896.
———2. The Terlingua quicksilver mining district, Brewster County, Tex.: Min. and Sci. Press, vol. 81, p. 64, July 21, 1900.
———3. The Terlingua quicksilver deposits: Econ. Geology, vol. 1, pp. 265–281, 3 figs., December–January, 1905–1906.
———4. Modern quicksilver reduction: Min. and Sci. Press, vol. 99, p. 690, Nov. 20, 1909.
———5. Quicksilver in 1908: Eng. and Min. Jour., vol. 87, p. 141, Jan. 9, 1909.
———6. Quicksilver: Mineral Industry, vol. 17, pp. 742–745, 749–750, 1909.
———7. Quicksilver: Mineral Industry, vol. 18, pp. 617–619, 621, 1910.
———8. Modern quicksilver reduction: Min. and Sci. Press, vol. 100, p. 431, Mar. 19, 1910.
———9. Quicksilver in the United States in 1909: Eng. and Min. Jour., vol. 89, p. 82, Jan. 8, 1910.
Turner, H. W., and Ransome, F. L. 1. Quicksilver deposits [cinnabar]: U. S. Geol. Survey Geol. Atlas, Sonora folio (No. 41), p. 7, 1897.
Tyson, P. T. 1. Geology and industrial resources of California [cinnabar and quicksilver]: 31st Cong., 1st sess., Senate Ex. doc. 47, pp. 24, 36–37, 1850.
Udden, J. A. 1. A sketch of the geology of the Chisos country, Brewster County, Tex.: Texas Univ. Bull. 93 (Sci. ser. 11), 101 pp., April 15, 1907.
———2. Structural relations of quicksilver deposits [Texas]: Min. World, vol. 34, pp. 973–975, 6 figs., May 13, 1911.
———3. The geology of Texas quicksilver deposits: Texas Mineral Resources, vol. 1, pp. 1–2, 28–29, 4 figs., map, April, 1917.
———4. Deposits of quicksilver in Texas: Min. American, vol. 75, 1858, pp. 3–5, Sept. 29, 1917.
Udden, J. A., and Baker, C. L. 1. Economic mineral products [of Texas] [quicksilver]: Texas Univ. Bull. 44, pp. 117–118, Aug. 5, 1916.
Van Wagenen, T. F. 1. American metal mining; quicksilver: Min. Reporter, vol. 42, pp. 293–294, 311, 331, 1900.
Veatch, J. A. 1. The mercury deposits of the Pacific coast: Min. and Eng. World, vol. 40, pp. 591–594, sketch map, Mar. 28, 1914.
———2. The genesis of the mercury deposits of the Pacific coast: Am. Inst. Min. Eng. Bull. 86, pp. 209–226, 3 figs. (maps), February, 1914.
Villarello, J. D. 1. Genesis de los yacimientos mercuriales de Palomas (Durango) et Huitzuco (Guerrero): Soc. cient. Ant. Alzate Mem. y Rev., t. 19, pp. 95–136, 1903.
———2. Descripción de los criaderos de mercurio de Chiquilistlán (Jalisco): Soc. cient. Ant. Alzate Mem. y Rev., t. 20, pp. 889–897, 1904.

Digitized by Google

Villarello, J. D. 3. Description des mines "La Bella Union" [État de Guerrero]. Génèse des gisements de mercure: Soc. cient. Ant. Alzate Mem. y Rev., t. 23, pp. 395–411, 1906.
Virlet d'Aoust, Pierre Théodore. 1. De l'âge géologique de quelques filons métalliques et en particulier des filons de mercure (extrait): Compt. Rend., vol. 83, pp. 289–291, 1876.
Vivian, William. 1. Observations on the mining district of Sonora, Tuolumne County, Cal.: Cornwall Roy. Geol. Soc. Trans., vol. 7, pp. 216–219, 1865.
Wagoner, Luther. 1. Report on Guadalupe quicksilver mine, Cal: Eng. and Min. Jour., vol. 34, pp. 185–186, Oct. 7, 1882.
——— 2. The geology of the quicksilver mines of California: Eng. and Min. Jour., vol. 34, p. 334, 1 fig., Dec. 23, 1882.
Walcott, C. D. 1. Statistics of quicksilver: U. S. Geol. Survey Sixteenth Ann. Rept., pt. 1, pp. 51, 59, 1896.
——— 2. Statistics of quicksilver in 1895: U. S. Geol. Survey Seventeenth Ann. Rept., pt. 1, pp. 84, 92, 1896.
——— 3. Statistics of production of quicksilver: U. S. Geol. Survey Eighteenth Ann. Rept.., pt. 1, pp. 84–85, 1897.
——— 4. Statistics concerning quicksilver: U. S. Geol. Survey Nineteenth Ann. Rept., pt. 1, p. 77, 1898.
——— 5. Statistics of production of quicksilver: U. S. Geol. Survey Twentieth Ann. Rept., pt. 1, p. 80, 1899.
——— 6. Publications on deposits of quicksilver; statistics of production: U. S. Geol. Survey Twenty-first Ann. Rept., pt. I, pp. 29, 104, 1900.
——— 7. Production of quicksilver in 1900: U. S. Geol. Survey Twenty-second Ann. Rept., pt. 1, p. 112, 1901.
——— 8. Statistics of quicksilver: U. S. Geol. Survey Twenty-third Ann. Rept., p. 87, 1902.
——— 9. Statistics of quicksilver: U. S. Geol. Survey Twenty-fourth Ann. Rept., pp. 111–112, 1903.
——— 10. Statistics of quicksilver: U. S. Geol. Survey Twenty-fifth Ann. Rept., pp. 88–89, 1904.
——— 11. Statistics of quicksilver: U. S. Geol. Survey Twenty-sixth Ann. Rept., p. 84, 1905.
Watson, R. B. 1. [Discovery of mercury in silver ore]: Eng. and Min. Jour., vol. 94, pp. 1077–1080, Dec. 7, 1912.
Watts, W. L. 1. Alameda County, Cal. [quicksilver]: California State Min. Bur. Eleventh Rept., pp. 121–122, 1893.
——— 2. Colusa County, Cal.; the mines of Sulphur Creek and vicinity: California State Min. Bur. Eleventh Rept., pp. 181–187, 1893.
——— 3. Lake County [Cal.]; the Abbott quicksilver mines: California State Min. Bur. Eleventh Rept., pp. 239–240, 1893.
——— 4. Santa Clara County, Cal. [quicksilver]: California State Min. Bur. Eleventh Rept., p. 374, 1893.
——— 5. Sonoma County, Cal.; quicksilver at the Great Eastern mine and at Pine Flat district: California State Min. Bur. Eleventh Rept., pp. 460–461, 1893.
——— 6. Stanislaus County, Cal.; the Summit quicksilver mine: California State Min. Bur. Eleventh Rept., pp. 464–465, 1893.
Weaver, C. E. 1. Geology and ore deposits of the Blewett mining district (Chelan County, Wash.) [cinnabar] : Washington Geol. Survey Bull. 6, p. 78, 1911.
Weed, W. H. 1. Influence of country-rock on mineral veins: Am. Inst. Min. Eng. Trans., vol. 33, pp. 634–653, 1902.
——— 2. Ore deposition and vein enrichment by ascending hot waters: Am. Inst. Min. Eng. Trans., vol. 33, pp. 747–754, 1903.
Wells, W. V. 1. A visit to the quicksilver mines of New Almaden: Harper's New Monthly Mag., pp. 25–40, illus., June, 1863.
Wendeborn, B. A. 1. Die Quecksilberablagerungen in Oregon: Berg- u. hüttenm. Zeitung, vol. 63, pp. 274–277, 1904.
Whitehill, H. R. 1. Mineral resources of Nevada [cinnabar]: Nevada State Mineralogist Bien. Rept. for 1877 and 1878, p. 6, 1879.
Whitney, J. D. 1. The metallic wealth of the United States [mercury], pp. 186–187, 193–197, 1854.
——— 2. Notice of cinnabar from Nevada Territory: California Acad. Nat. Sci. Proc., vol. 2, p. 161, 1863.

Digitized by Google

Whitney, J. D. 3. Geology of the Coast Ranges [quicksilver and quicksilver rock]; California Geol. Survey Geology, vol. 1, pt. 1, pp. 16, 19, 68, 69, 71, 83, 89, 90, 1865.
——— 4. Geology of the Coast Ranges [occurrence of cinnabar]: California Geol. Survey, Geology, vol. 1, pt. 1, pp. 24, 58, 60, 72, 78, 91, 92, 114, 1865.
——— 5. The geology of the Sierra Nevada [occurrence of cinnabar]: California Geol. Survey, Geology, vol. 1, pt. 2, pp. 230–260, 1865.
Whitton, W. W. 1. The determination of mercury in ores: California Jour. Tech., vol. 4, pp. 35–36. Sept., 1904.
Wilhelm, R. M. 1. Freezing point of mercury: Bur. Standards Sci. Papers, No. 294, pp. 655–661, Oct. 26, 1916; Bull., vol. 13, No. 4, pp. 655–661, Mar. 6, 1917. Abstract, Sci. Am., vol. 115, p. 527, Dec. 9, 1916.
Williams Albert, jr. 1. Quicksilver [California] and vermilion: U. S. Geol. Survey Mineral Resources, 1882, pp. 387, 398, 1883.
——— 2. Useful minerals of the United States; division of the Rocky Mountains [cinnabar in California, Colorado, Nevada, Utah]: U. S. Geol. Survey Mineral Resources, 1882, pp. 753, 767, 768, 772, 774, 1883.
——— 3. Statistics of quicksilver [United States]: U. S. Geol. Survey Fourth Ann. Rept., p. 65, 1884.
——— 4. Quicksilver [California] and vermilion: U. S. Geol. Survey Mineral Resources, 1883 and 1884, pp. 492–503, 1885.
——— 5. Quicksilver [California] and vermilion: U. S. Geol. Survey Mineral Resources, 1885, pp. 284, 296, 1886.
——— 6. Statistics of quicksilver [United States]: U. S. Geol. Survey Seventh Ann. Rept., p. 132, 1888.
——— 7. Useful minerals of the United States [cinnabar in California, Colorado, Idaho, Nevada, Oregon, and Utah]: U. S. Geol. Survey Mineral Resources, 1887, pp. 703, 705, 713, 724, 756, 778, and 796, 1888.
Willis, C. F. 1. Arizona—mercury: Arizona State Bur. Mines Bull. 6 (Econ. ser. 3), p. 15, 1915–16.
——— 2. Mineralogy of useful minerals in Arizona: Arizona Univ. Bur. Mines Bull. 41 (Econ. ser. 11), p. 30, 1916–17.
Winchell, A. N. 1. Petrology and mineral resources of Jackson and Josephine counties, Oreg. [mercury]: Oregon Bur. Mines and Geology Mineral Resources of Oregon, vol. 1, pp. 65, 124, 129, 161, Aug., 1914.
Wolf, A. G., Liberty Bell mercury trap; Min. and Sci. Press, vol. 115, p. 206, 1 fig., 1917.
Yale, C. G. 1. Quicksilver product of California for 1874: In Raymond, Mines and mining in the States and Territories west of the Rocky Mountains, Seventh Ann. Rept. [for 1874], p. 493, 1875.
——— 2. Minor minerals of the Pacific coast: U. S. Geol. Survey Mineral Resources, 1882, pp. 662–663, 1883.
——— 3. California [quicksilver]: Eng. and Min. Jour., vol. 79, p. 21, Jan. 5, 1905.
——— 4. The mining industries of California: Eng. and Min. Jour., vol. 81, pp. 19–20, Jan. 6, 1906.
——— 5. California quicksilver: Eng. and Min. Jour., vol. 81, pp. 46–47, Jan. 6, 1906.
——— 6. Quicksilver mining in California: Mineral Industry, vol. 14, pp. 503–506, 1906.
——— 7. Quicksilver in California: Min. and Sci. Press, vol. 94, p. 22, Jan. 5, 1907.
——— 8. Quicksilver in California: Mineral Industry, vol. 15, pp. 675–676, 1907.
——— 9. Quicksilver in California: Eng. and Min. Jour., vol. 85, p. 89, Jan. 4, 1908.
——— 10. Quicksilver in California: Mineral Industry, vol. 16, p. 814, 1908.
Young, G. A. 1. A descriptive sketch of the geology and economic minerals of Canada [mercury], p. 132, Ottawa, Government Printing Bureau, 1909. [At head of title: Canada Dept. Mines, Geol. Survey Branch. . .]

Digitized by Google

Digitized by Google

GOLD, SILVER, COPPER, LEAD, AND ZINC IN IDAHO.

(MINES REPORT.)

By C. N. GERRY.

PRODUCTION.

GENERAL STATEMENT.

The value of the mine production of gold, silver, copper, lead, and zinc in Idaho in 1917 was $54,845,153, an increase of 12 per cent over the value in 1916. There was a slight decrease in silver, larger decreases in copper and zinc, and a considerable decrease in gold. The output of lead, however, exceeded that of 1916 by nearly 5 per cent, making a record greater than that of any previous year. The total value was augmented by greatly increased prices of silver, copper, and lead. Thus the value of the output was also a record for the State notwithstanding several decreases in quantity of the metals. Dividends for 1917, partly estimated, amounted to $9,900,691.

The production of the State from the discovery of placer gold to the end of 1917 is given in the table below. The total to 1914, inclusive, has been previously given by periods.[1] The complete table shows that the State has been an important producer of the five metals, which have a total value of nearly $618,000,000. Of this total, lead represents $280,011,845, or more than 45 per cent; silver, $152,779,842, or nearly 25 per cent; gold, $130,910,969, or more than 21 per cent; copper, $19,561,431, or more than 3 per cent; and zinc, $34,299,118, or nearly 6 per cent. The value of the mine production in 1917 exceeded the combined total value of zinc and copper from 1863 to the end of 1917.

Mine production of gold, silver, copper, lead, and zinc in Idaho in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	418	2,718,045	$1,115,810	12,300,873	8,478,281	375,081,781	86,505,219	$48,767,783
1917	359	2,758,507	804,809	12,029,338	7,827,574	393,559,521	79,854,136	54,845,153
Increase or decrease, 1917	.....	+40,462	−311,001	−271,535	−650,707	+18,477,740	−6,651,083	+6,077,370
Total, 1863–1917	.....	.....	130,910,969	224,705,955	116,364,929	5,771,348,252	341,218,640	617,563,205

[1] U. S. Geol. Survey Mineral Resources, 1914, pt. 1, p. 598, 1915.

Digitized by Google

The table giving the separation according to source of metals shows a distinct increase in lead from lead ore, but a decrease in zinc from lead-zinc ore, and a decided decrease in the placer output of gold. There was a decrease in the price of zinc, especially during the last months of the year, and the market for a mixed ore was uncertain.

Ore and metals produced in Idaho in 1917.

Source of production.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.
		Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Placers	121	.....	6,541.80	1,194	.....	.....	.....
Dry or siliceous ore	86	69,650	24,929.28	81,514	10,745	48,689	.....
Copper ore	37	103,224	3,960.99	232,840	6,225,488	11,803	.....
Lead ore	107	1,448,285	2,567.41	8,063,768	1,250,215	275,019,571	.....
Zinc ore	14	19,269	.....	29,684	.....	602,096	10,824,568
Copper-lead ore	1	4	.....	803	320	848	.....
Lead-zinc ore	19	1,118,075	933.16	3,619,535	340,808	117,876,514	69,029,568
	.....	2,758,507	38,932.64	12,029,338	7,827,574	393,559,521	79,854,136

ORE.

The quantity of ore sold or treated in Idaho in 1917 increased 40,462 tons, or about 1.5 per cent. Most of the output was lead ore and lead-zinc ore, the former being nearly 53 per cent of the total and the latter 40 per cent. Copper ore represented nearly 4 per cent of the total; siliceous ore, nearly 3 per cent; and zinc ore and copper-lead ore, less than 1 per cent. Much of the lead ore contains zinc that is not saved at a lead smelter, but most of the concentration mills make a separate zinc product, which is shipped to a zinc smelter or an electrolytic plant. The total ore mined and treated had an average value per ton in gold and silver of $19.83. The average values in gold and silver for each kind of ore are shown at the foot of the following table. The siliceous ore sold or treated averaged per ton as follows: Gold, $7.40; silver, 1.17 ounces; with a trace of copper and lead. The siliceous ore included 67,784 tons of gold ore, averaging per ton $7.54 in gold and 0.39 ounce of silver; and 1,866 tons of silver ore, averaging per ton $2.27 in gold, 29.66 ounces of silver, 0.52 pound of copper, and 2.39 pounds of lead. The copper ore averaged per ton 79 cents in gold and 2.26 ounces of silver, and contained 3.02 per cent of copper. Most of the siliceous ore was treated by amalgamation or cyanidation, and most of the copper ore was shipped directly to smelters. The averages of the crude shipping product are given later. Lead ore as mined averaged 3.6 cents in gold and 5.57 ounces of silver per ton, and contained 0.043 per cent of copper and 9.49 per cent of lead. The total zinc ore mined or treated averaged per ton 1.54 ounces of silver, and contained 1.56 per cent of lead and 28.09 per cent of recoverable zinc. Copper-lead ore, only 4 tons, averaged per ton 200.75 ounces of silver, and contained 4 per cent of copper and 10.60 per cent of lead. Lead-zinc ore averaged per ton 1.7 cents in gold and 3.24 ounces of silver, and contained 0.015 per cent of copper, 5.27 per cent of lead, and 3.09 per cent of recoverable zinc. Most of the lead ore and lead-zinc ore was milled, and the results are given within after the table on concentrates.

Digitized by Google

Ore sold or treated in Idaho in 1917, in short tons.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-lead ore.	Lead-zinc ore.	Total.
Ada	20						20
Adams		165					165
Blaine	20		9,992	262		10,456	20,730
Boise	27,571		19				27,590
Bonner	19		762				781
Bonneville		2					2
Boundary	20	4	38,567				38,591
Butte	1	153	5,744				5,898
Camas	985		14				999
Cassia	127			20			147
Custer	1,201	68,832	13,670				83,703
Elmore	25,616						25,616
Fremont		509	216				725
Gem	4						4
Idaho	11,332	19					11,351
Latah		59					59
Lemhi	1,653	867	16,528				19,048
Owyhee	871						871
Shoshone	158	32,614	1,362,745	18,987	4	1,107,619	2,522,127
Valley	52						52
Washington			28				28
	[a] 69,650	103,224	1,448,285	19,269	4	1,118,075	2,758,507
Average value per ton in gold and silver	$8.36	$2.65	$4.62	$1.27	$165.41	$2.68	$3.84

[a] Includes 67,784 tons of gold ore and 1,866 tons of silver ore.

More than 2 per cent of the ore (67,677 tons) was treated in gold and silver mills in 1917, against 69,773 tons in 1916. Bullion from this ore treated by amalgamation and cyanidation was valued at $486,889, or $7.19 per ton. Idaho County led in production of bullion, and Boise County was second. There was a decided decrease in Elmore County, which was first in 1916. Nearly all the gold in bullion was won by amalgamation, only about 5 per cent being recovered by cyanidation. At these mills during 1917 there were 1,035 pounds of mercury and 4,996 pounds of potassium and sodium cyanide consumed. The average consumption of quicksilver was 0.0162 pound per ton of ore amalgamated and 0.032 pound per ounce of gold and silver bullion saved. The cyanide consumption was 1.30 pounds per ton of ore treated and 0.45 pound per ounce of gold and silver bullion recovered.

Gold and silver produced in mills in Idaho in 1917.

County.	Ore.	Bullion recovered from ore by—				Total value.
		Amalgamation.		Cyanidation.		
		Gold.	Silver.	Gold.	Silver.	
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Fine ounces.*	*Fine ounces.*	
Ada	20	15.34	14			$328
Blaine	2			1.24	11	35
Boise	26,251	7,770.52	1,393	704.15	604	176,832
Butte	1	1.58	2			35
Camas	[a] 985	310.02	122			6,509
Custer	[b] 1,201	160.65	502			3,734
Elmore	[c] 25,592	3,376.38	2,330	412.26	5,409	84,695
Gem	4			.85	53	61
Idaho	[d] 11,154	9,594.02	4,687	9.51	1	202,386
Lemhi	1,617	169.98	47			3,553
Owyhee	[e] 801	134.43	1,970	23.87	3,697	7,942
Shoshone	1	.77				16
Valley	48	35.53	35			763
	67,677	21,569.22	11,102	1,151.88	9,775	486,889

[a] Also yielded 19 tons of concentrates.
[b] Also yielded 62 tons of concentrates.
[c] Also yielded 130 tons of concentrates.
[d] Also yielded 3 tons of concentrates.
[e] Also yielded 68 tons of concentrates.

Digitized by Google

More than 86 per cent of the ore, or 2,375,891 tons, was concentrated. Concentrates from this ore, from 28,215 tons of old tailings treated, and from a small quantity of ore treated in gold and silver mills aggregated 419,182 tons, valued at $38,405,236, or $91.62 a ton in 1917, against $90.55 a ton in 1916. The concentrates were largely from the Coeur d'Alene region, and the ratio was 5.7 tons of ore to 1 ton of concentrate. Nearly 77 per cent of the total was lead concentrate, more than 19 per cent lead-zinc concentrate, and less than 4 per cent was zinc concentrate, copper concentrate, and siliceous concentrate. There was good increase in lead concentrate and zinc concentrate, but the lead-zinc concentrate was less. As each year shows a variation from one class to another, the important feature is the fact that the mills made 32,823 tons more concentrate in 1917. Operators in Shoshone County shipped an average of 33,967 tons of concentrates of various kinds per month, against 31,664 tons in 1916. The crude ore shipped, which was 14,943 tons per month, being added gives the Coeur d'Alene region average monthly shipments of 48,910 tons of concentrates and crude ore, against 43,939 tons in 1916.

Mine production of metals from Idaho concentrates in 1917.

By counties.

County.	Ore to concentrating mills.	Concentrates produced.						Total value of concentrates.
		Quantity.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	
	Short tons.	*Short tons.*	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
Blaine	14,874	5,315	472.68	118,684	4,586	1,263,791	1,949,866	$416,390
Boise	1,279	220	176.62	15,836	4,047	34,483	.....	20,771
Bonner	762	127	.08	2,254	159	197,271	.....	18,867
Boundary	37,856	4,732	24.11	109,184	.....	5,850,609	.....	593,619
Butte	2,923	835	.....	12,525	3,120	885,100	.....	87,292
Camas	.....	19	74.07	134	.....	.....	.....	1,641
Custer	.....	62	392.95	2,855	.....	.....	.....	10,475
Elmore	.....	130	711.50	3,545	.....	.....	.....	17,629
Idaho	.....	3	20.14	140	.....	.....	.....	531
Lemhi	248	62	111.29	363	30,072	.....	.....	10,810
Owyhee	.....	68	341.60	8,185	.....	8,407	.....	14,529
Shoshone	2,317,949	407,609	1,684.72	7,770,764	1,290,226	278,132,199	63,756,334	37,212,682
	2,375,891	419,182	4,009.76	8,044,469	1,332,210	286,371,860	65,706,200	38,405,236

By kinds of concentrates.

Dry or siliceous	245	1,303.51	27,829	163	.....	.....	$49,921
Copper	1,361	108.34	29,416	468,347	.....	.....	154,338
Lead	322,340	2,387.91	7,624,987	863,700	275,749,061	.....	30,282,560
Zinc	15,245	.....	46,805	.....	830,640	10,066,224	1,136,758
Lead-zinc	79,991	210.00	315,432	.....	9,792,159	55,639,976	6,781,659

The concentrates had the following average contents: Siliceous concentrates contained $109.98 in gold and 113.59 ounces of silver, or $203.76 per ton. Copper concentrates contained $1.65 in gold and 21.61 ounces of silver per ton, and also 17.21 per cent copper, a total value per ton of $113.40. Lead concentrates averaged 15 cents in gold and 23.66 ounces of silver per ton, and 0.13 per cent of copper and 42.77 per cent of lead, or a total value per ton of $93.94. Zinc concentrates averaged 3.07 ounces of silver per ton, 2.72 per cent of

Digitized by Google

lead and 33.02 per cent of recoverable zinc, or a total value per ton of $74.57. Lead-zinc concentrates averaged per ton slightly more than 5 cents in gold and 3.94 ounces of silver and 6.12 per cent of lead and 34.78 per cent of recoverable zinc, or a total value per ton of $84.78. Averages for concentrates, as well as for shipping ore, from 1911 to 1914 were given in a previous report.[1]

Of the total ore, 284,567 tons, or more than 10 per cent, was shipped crude to smelters. There was a good increase in crude shipping ore from Shoshone County, which ranked first, as in former years. Custer County also increased its shipping product, supplying nearly 29 per cent of the total. In 1916 all of this ore went to plants outside of the State, but in 1917 part of the lead products were smelted at the Bunker Hill smelter, at Kellogg. The total value of the first-class ore was $15,753,519, or $55.36 a ton. There was a decided increase in lead ore and lead-zinc ore shipped, and a slight increase in copper ore. There was no great change in shipments of crude zinc ore. More than 64 per cent of the crude ore shipped was lead ore, nearly 28 per cent was copper ore, more than 4 per cent was zinc ore, and more than 3 per cent lead-zinc ore. The combined value of the concentrates and the crude ore shipped, most of which went to distant smelters, was $54,158,755. The ore smelted was principally sulphide in character. A close separation of oxidized and sulphide portions, with average content per ton, is as follows: Copper ore shipped consisted of 43,346 tons of oxidized and carbonate ore, averaging per ton $1.18 in gold and 1.02 ounces of silver, and 3.97 per cent of copper, or a total value per ton of $23.70, and of 35,183 tons of sulphide ore, averaging per ton 81 cents in gold and 3.77 ounces of silver, and 3.21 per cent of copper, or a total value per ton of $21.44. There was a greater difference in the lead ore, for the oxidized portion (29,012 tons) averaged per ton 42 cents in gold and 8.60 ounces of silver, and 0.23 per cent of copper and 17.35 per cent of lead, or a total value per ton of $38.60, and the sulphide lead ore shipped (154,079 tons) averaged per ton 10 cents in gold and 22.18 ounces of silver, and 0.19 per cent of copper and 30.92 per cent lead, or a total value per ton of $72.61. A small quantity (195 tons) of oxidized zinc ore averaged 31.68 per cent of recoverable zinc, and 12,459 tons of sulphide ore contained per ton 0.92 ounce of silver, and 2.36 per cent lead and 40.20 per cent of recoverable zinc. The lead-zinc ore and copper-lead ore shipped were sulphide.

[1] U. S. Geol. Survey Mineral Resources, 1914, pt. 1, p. 601, 1915.

Digitized by Google

Mine production of metals from Idaho crude ore shipped to smelters in 1917.

By counties.

County.	Quantity.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
Adams	165	.....	152	31,080	.....	.....	$8,610
Blaine	692	13.84	26,915	2,230	302,262	168,509	66,256
Boise	60	14.90	6,493	276	9,338	.....	6,536
Bonner	19	.84	3,085	748	.....	.....	2,764
Bonneville	2	.96	11	595	.....	.....	192
Boundary	735	7.38	12,398	704	663,525	.....	67,624
Butte	2,974	82.40	24,526	28,450	1,674,808	.....	173,712
Camas	14	11.47	469	.....	4,490	.....	1,010
Cassia	147	30.82	1,998	.....	4,161	11,540	3,818
Custer	82,146	2,587.11	202,669	4,404,625	3,061,332	.....	1,686,217
Elmore	24	208.44	445	241	1,333	.....	4,857
Fremont	725	.48	1,008	162,367	122,927	.....	55,739
Idaho	197	75.27	93	7,132	.....	.....	3,580
Latah	59	1.79	51	18,506	.....	.....	5,131
Lemhi	17,183	599.80	159,423	181,570	7,282,166	.....	819,596
Owyhee	70	116.29	15,236	.....	.....	.....	14,959
Shoshone	179,323	1,883.28	3,470,232	1,586,685	93,875,454	13,967,887	12,829,580
Valley	4	.85	720	.....	.....	.....	611
Washington	28	.....	168	.....	30,106	.....	2,727
	284,567	5,635.92	3,926,092	6,425,209	107,031,902	14,147,936	15,753,519

By kinds of ore.

Dry or siliceous	658	448.79	29,911	6,698	5,799	.....	$36,252
Copper	78,529	3,846.61	177,164	5,699,584	124	.....	1,781,496
Lead	183,091	1,326.52	3,667,378	718,607	105,363,081	.....	12,306,746
Zinc	12,654	.....	11,481	.....	587,456	10,141,012	1,094,364
Copper-lead	4	.....	803	320	848	.....	822
Lead-zinc	9,631	14.00	39,355	.....	1,074,594	4,006,924	533,839

The crude ore shipped had the following averages: Siliceous ore averaged per ton $14.10 in gold and 45.46 ounces of silver, and 0.51 per cent of copper and 0.44 per cent lead, or a total value per ton of $55.09; copper ore averaged $1.01 in gold and 2.26 ounces of silver per ton, and 3.63 per cent of copper, or a total value per ton of $22.69; lead ore averaged 15 cents in gold and 20.03 ounces of silver per ton, and 0.20 per cent of copper and 28.77 per cent lead, or a value per ton of $67.22; zinc ore averaged 0.91 ounce of silver, 2.32 per cent lead, and 40.70 per cent of recoverable zinc, or a total value per ton of $86.48; lead-zinc ore averaged per ton 3 cents in gold and 4.09 ounces of silver, and 5.58 per cent lead and 20.80 per cent of recoverable zinc, or a total value per ton of $55.43. Copper-lead ore smelted was small in quantity; the average contents have already been given.

GOLD.

The mine production of gold in Idaho in 1917 was 38,932.64 fine ounces, valued at $804,809, a decrease of $311,001, or nearly 28 per cent. Boise County was the largest producer of gold, but there was such a large decrease in 1917 that the output of Idaho County was nearly as large. Elmore, Shoshone, Custer, and Lemhi counties had large outputs. The gold output of Elmore and Lemhi counties decreased notably, but that of Idaho and Shoshone counties increased. The lode mines, 247 in number, produced gold valued at $669,578; and 112 placers produced gold valued at $135,231, against 162 placers

Digitized by Google

and $449,093 in 1916. Of the placer gold, $59,447 was won by dredges, $52 by drift mines, and $75,732 by hydraulic or sluicing mines. The dredge output in 1917 decreased $268,249 from that of 1916, and gold recovered by sluicing and hydraulicking decreased $45,480. Of the total gold, nearly 17 per cent came from placers, more than 64 per cent from siliceous ore, nearly 7 per cent from lead ore, more than 10 per cent from copper ore, and more than 2 per cent from lead-zinc ore. Siliceous ores contained $7.40 a ton in gold; copper ore, 79 cents; lead ore, 3.6 cents; and lead-zinc ore, 1.7 cents. Snake River in various counties produced only $917 in gold, against $5,824 in 1916. The production of gold from amalgamation and cyanidation mills was slightly more. In 1917 bullion recovered in these mills contained 22,721.08 ounces of gold, or more than 58 per cent of the total, against 22,479.71 ounces in 1916. Amalgamation won 21,569.20 ounces of gold and cyanidation 1,151.88 ounces. Concentrates of all kinds contained only 4,009.76 ounces of gold, or more than 10 per cent of the total gold, and crude ore shipped to smelters contained 5,635.92 ounces of gold, or nearly 15 per cent of the total. Various sulphide shipping ores contained 2,125.87 ounces of gold and oxidized ores contained 3,510.05 ounces. A statement of dredges operated since 1897 and their output by years was given in a former report.[a] A total of $3,781,503 has been recovered by dredges.

In 1917 there were only four mines which had a gold output of more than $50,000 each. In order of their importance these were the Holte mine, in Idaho County; the Gold Hill & Iowa, in Boise County; Boise Rochester, in Elmore County; and Empire Copper Co., in Custer County.

Mine production of gold in Idaho in 1917, in fine ounces.

County.	Placers.	Dry or siliceous ore.	Copper ore.	Lead ore.	Lead-zinc ore.	Total.
Ada	266.64	15.34				281.98
Benewah	153.93					153.93
Bingham	12.58					12.58
Blaine		5.35		197.41	303.00	505.76
Boise	1,854.70	8,652.23		13.96		10,520.89
Bonner		.84		.08		.92
Bonneville	104.64		.96			105.60
Boundary		4.23		27.26		31.49
Butte		1.58	2.49	79.91		83.98
Camas		384.09		11.47		395.56
Cassia		30.82				30.82
Clearwater	839.26					839.26
Custer	84.66	553.59	2,554.87	38.33		3,231.45
Elmore	46.25	4,708.58				4,754.83
Fremont				.48		.48
Gem	.68	.82				1.50
Gooding	1.64					1.64
Idaho	552.88	9,698.94				10,251.82
Latah	13.11		1.79			14.90
Lemhi	2,002.56	212.50	141.03	527.54		2,883.63
Lincoln	4.69					4.69
Nez Perce	.68					.68
Owyhee	.39	616.20				616.59
Power	11.27					11.27
Shoshone	576.15	7.79	1,259.85	1,670.97	630.16	4,144.92
Twin Falls	12.14					12.14
Valley	2.95	36.38				39.33
	6,541.80	[b] 24,929.28	3,960.99	2,567.41	933.16	38,932.64

[a] U. S. Geol. Survey Mineral Resources, 1914, pt. 1, p. 604, 1915.
[b] Includes 24,721.64 ounces from gold ore and 207.64 ounces from silver ore.

Digitized by Google

SILVER.

The mine production of silver decreased from 12,300,873 ounces in 1916 to 12,029,338 ounces in 1917, but the value increased from $8,093,974 to $9,912,175—a decrease of more than 2 per cent in quantity, but an increase of 22 per cent in value. Fair increase was made in Blaine, Boundary, and Custer counties, but large decrease in Shoshone and Lemhi counties. A separation of the silver according to source shows that the largest part of the total silver yield, or 67 per cent, was from lead ore, 30 per cent from lead-zinc ore, nearly 2 per cent from copper ore, and less than 1 per cent from siliceous ore, zinc ore, and copper-lead ore. Shoshone County produced more than 93 per cent of the silver. Concentrates supplied more than 66 per cent of the silver, shipping ore contained nearly 33 per cent, and gold and silver bullion contained only 0.17 per cent. Crude shipping ore averaged 13.80 ounces a ton and concentrates 19.19 ounces a ton. The silver contents of the different kinds of shipping ore have already been given. The Banner mine in Boise County and the Trade Dollar mine in Owyhee County produced ore in which the silver was far more valuable than the gold. Formerly Owyhee County produced much of this class of ore.

Six mines in Idaho produced a total of more than 9,000,000 ounces of silver in 1917; they were the Hercules, Bunker Hill & Sullivan, Hecla, Morning, Caledonia, and Greenhill-Cleveland. Each of these produced more than 800,000 ounces of silver.

Mine production of silver in Idaho in 1917, in fine ounces.

County.	Placers.	Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-lead ore.	Lead-zinc ore.	Total.
Ada	57	14						71
Adams			152					152
Benewah	23							23
Blaine		2,171		110,825			43,060	156,056
Boise	452	23,995		331				24,778
Bonner		3,085		2,254				5,339
Bonneville	3		11					14
Boundary		12	8	121,562				121,582
Butte		2	228	36,823				37,053
Camas		256		469				725
Cassia		1,998						1,998
Clearwater	187							187
Custer	33	3,357	125,610	103,319				232,319
Elmore	16	11,729						11,745
Fremont			219	789				1,008
Gem		53						53
Idaho	129	4,921						5,050
Latah	1		51					52
Lemhi	161	78	862	158,893				159,994
Owyhee		29,088						29,088
Shoshone	130		105,699	7,528,335	29,684	803	3,576,475	11,241,126
Twin Falls	1							1
Valley	1	755						756
Washington				168				168
	1,194	[a] 81,514	232,840	8,063,768	29,684	803	3,619,535	12,029,338

[a] Includes 26,171 ounces from gold ore and 55,343 ounces from silver ore

COPPER.

The mine production of copper decreased from 8,478,281 pounds, valued at $2,085,657, in 1916 to 7,827,574 pounds, valued at $2,136,928, in 1917, a decrease of nearly 8 per cent in quantity but a slight in-

Digitized by Google

crease in value. More than half of the copper came from Custer County, and about 37 per cent from Shoshone County. The Empire property, near Mackay, is still the largest copper producer in the State. In the Coeur d'Alene region the Richmond mine added considerable copper to the State output. Nearly 80 per cent of the total output was from copper ore, nearly 16 per cent from lead ore, and more than 4 per cent from lead-zinc ore. Concentrates contained about 17 per cent of the copper, and crude shipping ore of all kinds 82 per cent. Crude copper ore of shipping grade averages 3.13 per cent of copper, and copper concentrates 17.21 per cent. Smelting sulphide ore contained 3.21 per cent of copper, and oxidized ore 3.97 per cent. The average price of copper increased from 24.6 cents a pound in 1916 to 27.3 cents in 1917.

Mine production of copper in Idaho in 1917, in pounds.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Copper lead ore.	Lead-zinc ore.	Total.
Adams		31,080				31,080
Blaine			19,416			19,416
Boise	4,129		194			4,323
Bonner	748		159			907
Bonneville		595				595
Boundary	57	147	500			704
Butte		21,185	10,385			31,570
Custer		4,419,707	42,473			4,462,180
Elmore	241					241
Fremont		161,454	913			162,367
Idaho	5,570	1,562				7,132
Latah		18,506				18,506
Lemhi		122,571	89,071			211,642
Shoshone		1,448,679	1,087,104	320	340,808	2,876,911
	[a] 10,745	6,225,486	1,250,215	320	340,808	7,827,574

[a] Includes 9,752 pounds from gold ore and 993 pounds from silver ore.

LEAD.

The mine production of lead increased from 375,081,781 pounds, valued at $25,880,643, in 1916 to 393,559,521 pounds, valued at $33,846,119, in 1917. The increase in quantity was nearly 5 per cent and in value nearly 31 per cent. The total establishes a new record for the State, which has increased its output of lead about 70 per cent since 1904. Aside from Shoshone County, which supplied nearly 95 per cent of the total, good production was made by Lemhi, Boundary, Custer, Butte, and Blaine counties. Lead ore supplied nearly 70 per cent of the total and lead-zinc ore nearly 30 per cent. The recoverable lead in lead ores sold or treated averaged 9.49 per cent, and that in lead-zinc are 5.27 per cent. Crude lead ore of shipping grade averaged 28.77 per cent of recoverable lead, and lead concentrates 42.77 per cent. Concentrates of all kinds produced nearly 73 per cent of the total. Lead concentrates had an average value per ton of $93.94. Crude ore shipped was the source of more than 27 per cent of the lead, and the lead ore shipped to smelter had an average value per ton of $67.22. Nearly all the lead in crude ore shipped was from sulphide ores, only 10,073,879 pounds coming from oxidized ores. The average price of lead for 1917 increased 1.7 cents over the price in 1916.

Digitized by Google

Seven mines produced more than 82 per cent of the State output of lead in 1917. These were the Bunker Hill & Sullivan, Hercules, Morning, Hecla, Consolidated Interstate-Callahan, Tamarack & Custer, and Greenhill-Cleveland. Each one produced more than 10,000,000 pounds of lead, and the Last Chance, Caledonia, and Gold Hunter followed closely.

Mine production of lead in Idaho in 1917, in pounds.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-lead ore.	Lead-zinc ore.	Total.
Blaine	71	.....	1,050,562	.....	.....	659,500	1,710,133
Boise	34,717	.....	9,104	.....	.....	.....	43,821
Bonner	.....	.....	197,271	.....	.....	.....	197,271
Boundary	.....	.....	6,514,134	.....	.....	.....	6,514,134
Butte	.....	.....	2,559,908	.....	.....	.....	2,559,908
Camas	.....	.....	4,490	.....	.....	.....	4,490
Cassia	4,161	.....	.....	.....	.....	.....	4,161
Custer	.....	11,803	3,061,208	.....	.....	.....	3,073,011
Elmore	1,333	.....	.....	.....	.....	.....	1,333
Fremont	.....	.....	122,927	.....	.....	.....	122,927
Lemhi	.....	.....	7,282,166	.....	.....	.....	7,282,166
Owyhee	8,407	.....	.....	.....	.....	.....	8,407
Shoshone	.....	.....	254,187,695	602,096	848	117,217,014	372,007,653
Washington	.....	.....	30,106	.....	.....	.....	30,106
	[a] 48,689	11,803	275,019,571	602,096	848	117,876,514	393,559,521

[a] Includes 44,223 pounds from gold ore and 4,466 pounds from silver ore.

ZINC.

The mine production of recoverable zinc decreased from 86,505,219 pounds, valued at $11,591,699, in 1916 to 79,854,136 pounds, valued at $8,145,122, in 1917. This decrease of 6,651,083 pounds in quantity and of $3,446,577 in value came almost entirely from the Coeur d'Alene region. The Consolidated Interstate-Callahan property retained first place among the zinc producers of the State. The zinc output from Blaine County increased decidedly in spite of numerous difficulties. Zinc has become an important product of Idaho, as will be seen from the value, which compares favorably with that of silver in 1917. Lead-zinc ore supplied more than 86 per cent and zinc ore nearly 14 per cent of the zinc. Both the zinc concentrates and the crude zinc ore shipped are sulphide products, except the 195 tons from Blaine and Cassia counties. From concentrates, both zinc and lead-zinc, 65,706,200 pounds of recoverable zinc were won, or 82 per cent of the total; and from crude ore shipped, 14,147,936 pounds were won, or nearly 18 per cent of the total. Flotation has proved an aid in most of the concentration mills, and much of the material is shipped for treatment at electrolytic plants. The average price of metallic zinc was 10.2 cents a pound in 1917, 3.2 cents less than the price in 1916.

Nine mines produced more than 1,000,000 pounds of spelter each in 1917. Named in order of importance, these were the Consolidated Interstate-Callahan, Success, Morning, Rex, Highland Surprise, Douglas, North Star, Greenhill-Cleveland, and Constitution.

Digitized by Google

Mine production of recoverable zinc in Idaho in 1917, in pounds.

County.	Zinc ore.	Lead-zinc ore.	Total.
Blaine	163,509	1,949,866	2,113,375
Cassia	11,540		11,540
Shoshone	10,644,519	67,079,702	77,724,221
	10,824,568	69,029,568	79,854,136

The source of the ore and the actual assay in zinc, without deduction for losses in smelting, are shown below. There were 117,521 tons of zinc ore, zinc concentrates, lead-zinc ore, and lead-zinc concentrates shipped, of which the gross content was 93,964,203 pounds of zinc, or an average of 39.98 per cent. Most of the output came from the Beaver, Hunter, Lelande, Placer Center, Summit, and Yreka districts, in Shoshone County, and the Warm Springs district in Blaine County. In 1916 the shipments were 115,463 tons of zinc ore and concentrates containing 101,738,293 pounds of zinc, or an average of 44.06 per cent.

Zinc ore, lead-zinc ore, and concentrates produced from Idaho mines sold in 1917.

Classification.	County.	Quantity (short tons, dry weight).	Average assay of ore and concentrate (per cent of zinc).[a]
Sulphide zinc ore and concentrates	Blaine and Shoshone	27,704	42.64
Sulphide lead-zinc ore and concentrates	do	89,622	39.15
Carbonate zinc ore	Blaine and Cassia	195	39.88
		117,521	39.98

[a] Actual zinc content.

REDUCTION PLANTS.

In Idaho 69 milling plants of all kinds were in operation in 1917, against 79 active mills in 1916. Of these mills, 40 were concentration plants, 23 of which used flotation machines with other concentrating devices; 3 used flotation alone; 13 used amalgamation alone; 2 used cyanidation; 12 used amalgamation and concentration; and 2 used amalgamation, concentration, and cyanidation. Most of the ore and concentrate was shipped outside the State for smelting, but in July, 1917, the new lead smelter and refinery of the Bunker Hill Co. began to treat material from the Coeur d'Alene region.

MINING INDUSTRY.

Notwithstanding conditions which tended to retard the output of metals in the State, the year 1917 was a success from the standpoint of the value of the output. This total value increased to nearly $55,000,000, and the net profits from the Coeur d'Alene region alone

Digitized by Google

were nearly $13,000,000. There was an increase of about $600,000 in 1917, compared with an increase of $2,360,000 in 1916. Much of the increase was due to the higher prices of silver, copper, and lead. Compared with other States, Idaho was free from labor disturbances, but the mining industry was affected by the higher cost of material and supplies, scarcity of miners, impending law suits, and uncertainty regarding taxation.

In July the Bunker Hill smelter had its initial run, using one furnace. By the end of the year three furnaces and the refinery were in operation. As the suit with the American Smelting & Refining Co. was settled early in 1918 and the Bunker Hill smelter is in full operation, the plant will no doubt treat in 1918 a large percentage of the ore mined in the district. The smelter at Northport, Wash., was active throughout 1917, and nearly all of the material treated was lead ore and concentrates from Idaho. In the Pine Creek section hauling by wagon was still necessary as the branch railroad was not completed. The dredge of the Yukon Gold Co., at Murray, began operations in December, and it is hoped that the output in 1918 will compensate for the idleness of the Boston-Idaho dredge at Idaho City during 1917.

Mine production of gold, silver, copper, lead, and zinc in Idaho in 1917.

County.	Gold.					Silver.	
	Placers.		Deep mines.		Total value.		
	Quantity.	Value.	Quantity.	Value.		Quantity.	Value.
	Fine ounces.		*Fine ounces.*			*Fine ounces.*	
Ada	266.64	$5,512	15.34	$317	$5,829	71	$58
Adams						152	125
Benewah	153.93	3,182			3,182	23	19
Bingham	12.58	260			260		
Blaine			505.76	10,455	10,455	156,056	128,590
Boise	1,854.70	38,340	8,666.19	179,146	217,486	24,778	20,417
Bonner			.92	19	19	5,339	4,399
Bonneville	104.64	2,163	.96	20	2,183	14	12
Boundary			31.49	651	651	121,582	100,184
Butte			83.98	1,736	1,736	37,053	30,532
Camas			395.56	8,177	8,177	725	597
Cassia			30.82	637	637	1,998	1,646
Clearwater	839.26	17,349			17,349	187	154
Custer	84.66	1,750	3,146.79	65,050	66,800	232,319	191,431
Elmore	46.25	956	4,708.58	97,335	98,291	11,745	9,678
Fremont			.48	10	10	1,008	831
Gem	.68	14	.82	17	31	53	44
Gooding	1.64	34			34		
Idaho	522.88	11,429	9,698.94	200,495	211,924	5,050	4,161
Latah	13.11	271	1.79	37	308	52	43
Lemhi	2,002.56	41,397	881.07	18,213	59,610	159,994	131,835
Lincoln	4.69	97			97		
Nez Perce	.68	14			14		
Owyhee	.39	8	616.20	12,738	12,746	29,088	23,969
Power	11.27	233			233		
Shoshone	576.15	11,910	3,568.77	73,773	85,683	11,241,126	9,262,688
Twin Falls	12.14	251			251	1	1
Valley	2.95	61	36.38	752	813	756	623
Washington						168	138
	6,541.80	135,231	32,390.84	669,578	804,809	12,029,338	9,912,175

Digitized by Google

Mine production of gold, silver, copper, lead, and zinc in Idaho in 1917—Contd.

County.	Copper.		Lead.		Recoverable zinc.		Total value.
	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	
	Pounds.		*Pounds.*		*Pounds.*		
Ada							$5,887
Adams	31,080	$8,485					8,610
Benewah							3,201
Bingham							260
Blaine	19,416	5,331	1,710,133	$147,071	2,118,375	$216,074	507,491
Boise	4,323	1,180	43,821	3,769			242,852
Bonner	907	248	197,271	16,965			21,631
Bonneville	595	162					2,357
Boundary	704	192	6,514,134	560,216			661,243
Butte	31,670	8,619	2,559,908	220,152			261,039
Camas			4,490	386			9,160
Cassia			4,161	358	11,540	1,177	3,818
Clearwater							17,503
Custer	4,462,180	1,218,175	3,073,011	264,279			1,740,685
Elmore	241	66	1,333	115			108,150
Fremont	162,367	44,326	122,927	10,572			55,730
Gem							75
Gooding							34
Idaho	7,132	1,947					218,032
Latah	18,506	5,052					5,403
Lemhi	211,642	57,778	7,232,166	626,236			875,489
Lincoln							97
Nez Perce							14
Owyhee			8,407	723			37,438
Power							233
Shoshone	2,876,911	785,397	372,007,653	31,992,658	77,724,221	7,927,871	50,054,297
Twin Falls							252
Valley							1,436
Washington			31,106	2,589			2,727
	7,827,574	2,136,928	393,559,521	33,846,119	79,854,136	8,145,122	54,845,153

Producing placer mines and production of gold and silver in Idaho in 1916 and 1917.

County.	1916						1917					
	Hydraulic.	Dredge.	Drift.	Gold.	Silver.	Total value.	Hydraulic.	Dredge.	Drift.	Gold.	Silver.	Total value.
					Fine ounces.						*Fine ounces.*	
Ada	3	....	....	$2,659	30	$2,679	4	....	....	$5,512	57	$5,559
Benewah	2	....	....	8,105	46	8,135	2	....	....	3,182	23	3,201
Bingham	1	....	....	48	.....	48	1	....	....	260	.....	260
Boise	30	1	1	295,171	3,638	297,565	22	....	....	38,340	452	38,713
Bonneville	2	....	....	5,268	6	5,272	1	....	....	2,163	3	2,165
Canyon	4	....	....	1,708	15	1,718	.....	.....	.....	.....	.....	.....
Clearwater	15	1	....	26,112	268	26,288	8	1	....	17,349	187	17,503
Custer	7	....	....	4,121	86	4,177	6	....	....	1,750	33	1,777
Elmore	10	....	....	4,934	29	4,953	5	....	....	956	16	969
Gem	2	....	....	116	3	118	1	....	....	14	.....	14
Gooding	4	....	....	243	.....	243	1	....	....	34	.....	34
Idaho	45	....	....	21,373	266	21,549	32	....	....	11,429	129	11,535
Latah	4	....	....	744	2	745	2	....	....	271	1	272
Lemhi	9	2	....	73,957	295	74,151	5	2	1	41,397	161	41,530
Lincoln	.....	.....	.....	.....	.....	.....	2	....	....	97	.....	97
Nez Perce	1	....	1	41	.....	41	1	....	....	14	.....	14
Owyhee	4	....	....	185	5	188	1	....	....	8	.....	8
Power	2	....	....	1,620	5	1,623	3	....	....	233	.....	233
Shoshone	7	....	....	2,170	18	2,182	5	1	....	11,910	130	12,017
Twin Falls	4	....	....	518	.....	518	3	....	....	251	1	252
Valley	.....	.....	.....	.....	.....	.....	2	....	....	61	1	62
	156	4	2	449,093	4,712	452,193	107	4	1	135,231	1,194	136,215

Digitized by Google

Ores sold or treated, deep mines producing, and average value of ores in Idaho.

County.	Ore sold or treated in 1917.		Number of deep mines producing.		Average total value per ton.[a]		Average value per ton in gold and silver.[a]	
	Quantity.	Increase or decrease.	1916	1917	1916	1917	1916	1917
	Short tons.	*Short tons.*						
Ada	20	+ 20	.....	2	.....	$16.40	.....	$16.40
Adams	165	− 711	6	3	$42.55	52.18	$5.30	.76
Bannock	.....	− 57	3	.....	40.67	.....	2.12	.....
Bear Lake	.....	− 62	3	.....	22.64	.....	.06	.....
Blaine	20,730	+11,617	44	31	18.54	24.48	7.11	6.71
Boise	27,590	+ 9,119	17	11	10.82	7.40	10.16	7.22
Bonner	781	− 949	8	2	22.18	27.70	13.66	5.66
Bonneville	2	+ 2	.....	1	.....	96.00	.....	15.00
Boundary	38,591	+28,339	2	4	19.39	17.13	3.07	2.61
Butte	5,898	+ 5,898	.....	8	.....	44.26	.....	5.47
Camas	999	+ 999	.....	3	.....	9.17	.....	8.78
Cassia	147	− 5	3	2	60.58	25.97	22.49	15.53
Clearwater	.....	− 15	1	.....	11.13	.....	11.13	.....
Custer	83,703	+ 5,376	21	27	20.33	20.77	2.29	3.06
Elmore	25,616	−13,669	5	8	5.08	4.18	5.08	4.18
Fremont	725	−10,949	8	3	24.22	76.88	2.06	1.16
Gem	4	− 353	4	1	7.85	15.25	7.72	15.25
Idaho	11,351	+ 4,603	27	24	16.25	18.19	16.22	18.02
Latah	59	+ 59	.....	1	.....	86.97	.....	1.34
Lemhi	19,048	− 4,997	31	34	42.77	43.78	8.39	7.87
Owyhee	871	+ 315	17	17	37.82	42.97	37.82	42.14
Shoshone	2,522,127	+ 5,802	56	60	17.65	19.84	3.06	3.70
Valley	52	+ 52	.....	4	.....	26.42	.....	26.42
Washington	28	+ 28	.....	1	.....	97.39	.....	4.93
	2,758,507	+40,462	256	247	17.78	19.83	3.22	3.84

[a] Value per ton, placer product excluded.

Classifying the deep mines according to the metals produced in 1917 shows that there were 5 mines producing gold only; 1 silver only; 70 gold and silver; 5 copper only; 20 gold, silver, and copper; 54 gold, silver, copper, and lead; 2 gold, silver, copper, lead, and zinc; 14 gold, silver, and lead; 8 gold, copper, and lead; 27 silver and lead; 13 silver and copper; 15 silver, lead, and zinc; 7 gold, silver, lead, and zinc; 4 zinc alone; 1 lead and zinc; and 1 silver, copper, lead, and zinc.

REVIEW BY COUNTIES.

ADA COUNTY.

The Highland and Black Hornet districts produced $5.887 in gold and silver. This is largely represented by placer gold from the Monitor placer on Boise River.

ADAMS COUNTY.

Three deep mines produced 165 tons of ore, containing 152 ounces of silver and 31,080 pounds of copper, valued in all at $8,610. The ore had a total value per ton of $52.18 and was all copper ore.

Seven Devils district.—The production mentioned above came from the Seven Devils, River Queen, and Salzer Ford mines. This is a small production compared with former years.

Digitized by Google

BENEWAH COUNTY.

Two placer properties in Camas Cove district produced $3,182 in gold and 23 ounces of silver. Operations of the Cedar Creek property were stopped by litigation in July.

BINGHAM COUNTY.

Several miles east of Pingree, on Snake River, the Gold Point placer made a small production. Gold from the various Snake River districts was considerably less in 1917 than in 1916.

BLAINE COUNTY.

Mine production in Blaine County, Idaho, in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	44	9,113	$18,582	70,283	42,517	875,196	248,379	$168,958
1917	31	20,730	10,455	156,056	19,416	1,710,133	2,118,375	507,491
Increase or decrease, 1917		+11,617	−8,127	+85,773	−23,101	+834,937	+1,869,996	+338,533
Total, 1880–1917			2,465,858	15,574,163	209,801	181,576,964	6,508,007	24,907,429

There was a good increase in the county in the production of ore and of silver, lead, and zinc, but the output of gold and copper was less than in 1916. Thirty-one deep mines produced 20,730 tons of ore, which had a total value per ton of $24.48 and a value per ton in gold and silver of $6.71. The ore was divided into 10,456 tons of lead-zinc ore, 9,992 tons of lead ore, 262 tons of zinc ore, and 20 tons of siliceous ore. The majority of the ore, 14,874 tons, was concentrated, making 5,315 tons of concentrates valued at $416,390, or $78.34 per ton. There were 692 tons of crude ore shipped valued at $66,256, or $95.75 a ton. From 1880 to 1917 this county has produced $2,465,858 in gold, $14,078,177 in silver, $38,048 in copper, $7,812,303 in lead, and $513,043 in zinc, a total of $24,907,429. The output of the county by years to 1914 was published in this report[1] for that year. The boundary lines of Blaine County were considerably changed in 1917. The eastern section went to make up part of the newly established Butte County and part of the western section formed Camas County. The main producing area, including the Mineral Hill and Warm Springs districts, remains in Blaine County.

Galena district.—A small shipment of sulphide lead ore was made from the Timberline property, northwest of Ketchum.

Mineral Hill district.—Sixteen deep mines produced 1,261 tons of ore, $351 in gold, 22,389 ounces of silver, 2,232 pounds of copper, 258,724 pounds of lead, and 28,055 pounds of zinc, valued at $14,520, or $35.31 per ton. Part of the ore mined, 929 tons, was concentrated, and 330 tons were shipped directly to smelters. Numerous mines contributed small shipments; the most important came from the

[1] U. S. Geol. Survey Mineral Resources, 1914, pt. 1, p. 613, 1915.

Digitized by Google

Eureka mine and the Red Elephant property. A 50-ton concentration mill on the latter property was active for a short time.

Vienna district.—A shipment of rich silver ore was made from the Vienna mine.

Warm Springs district.—Thirteen deep mines produced 19,444 tons of ore, containing $10,027 in gold, 131,006 ounces of silver, 17,135 pounds of copper, 1,443,726 pounds of lead, and 2,090,320 pounds of recoverable zinc, valued at $460,027, or $23.66 per ton. The production in 1916 was 6,547 tons of ore valued at $113,303. Most of the ore, or 13,945 tons, was concentrated, making 5,255 tons of concentrates. The material included 5,162 tons of slag and old tailings and 337 tons of ore shipped directly to smelters. The distinct increase in the district output was due to the North Star Triumph property, operated by the Federal Mining & Smelting Co. Lead-zinc ore and tailings were treated to make a lead concentrate and a lead-zinc concentrate. The recovery of concentrates has not been regular because the mill has been rearranged several times on account of the extreme complexity of the ore. The plant has a capacity of 120 tons and uses concentration on Wilfley tables followed by oil flotation. Considerable money has been spent in development and for the equipment of the property, the operating expense for 1917 alone being $98,652. Work was interrupted in February by a snowslide, which resulted in the death of 11 men.

A considerable production of lead resulted from the treatment of ore from the Independence mine. Concentrates from the 100-ton mill went to the United States smelter at Midvale, Utah. The product was rich in both lead and silver and contained about 20 per cent of iron. Toward the end of the year the property was leased and bonded by the Federal Mining & Smelting Co. A few shipments of carbonate zinc ore were made from the Lake Creek mines, operated by the Kusa Spelter Co. A considerable quantity of old slag was shipped from the Ketchum slag dump by the Big Four Exploration Co., of Salt Lake City, Utah.

BOISE COUNTY.

Mine production in Boise County, Idaho, in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	
1916	49	18,471	$470,060	23,161	23,260	92,356	$497,395
1917	33	27,590	217,486	24,778	4,323	43,821	242,852
Increase or decrease, 1917		+9,119	−252,574	+1,617	−18,937	−48,535	−254,543

[a] Includes placer production.

There was a very decided decrease, amounting to more than 50 per cent, in the output of gold in the county in 1917. Eleven deep mines produced 27,590 tons of ore, containing $179,146 in gold, 24,326 ounces of silver, 4,323 pounds of copper, and 43,821 pounds of lead, valued in all at $204,139, or $7.40 per ton. Of the ore, 26,251 tons were treated in gold and silver mills, and only 60 tons were shipped to smelters. Bullion in the ore milled was valued at $176,832, or $6.74 per ton in gold and silver. All of the output was siliceous, except 19

Digitized by Google

tons, which was lead ore. In 1917 there were 22 placer operators, who produced only $38,340 in gold and 452 ounces of silver, having a total value of $38,713. The large dredge of the Boston Idaho Co. was idle during 1917, which accounts for the decided decrease in the output of placer gold. In 1916 there were 32 placer mines, producing $295,171 in gold and 3,638 ounces of silver.

The production of gold and silver in the county, exclusive of copper and lead, from 1863 to the end of 1917 was $52,102,339 in gold and 2,151,866 ounces of silver, or a total value of $54,380,893. The output by years to 1914 was given in the report[1] for that year.

Banner district.—A 30-ton concentration mill, equipped with two Wilfley tables and a flotation plant, was put in operation in September, 1917, on siliceous silver ore from the Banner mine. Several shipments of rich concentrate and crude ore were made. It is planned to increase the capacity of the mill and to add a cyanide plant.

Boise Basin district.—Nineteen placers and 10 deep mines produced 26,270 tons of ore, $215,489 in gold, 4,700 ounces of silver, 4,078 pounds of copper, and 43,587 pounds of lead, valued in all at $224,224. Most of the ore was treated in gold and silver mills. This is a large decrease from the production of 1916, which was valued at $492,721. By far the most important producer was the Gold Hill & Iowa property. Ore was treated in a 75-ton plant using amalgamation and concentration, and the concentrates were cyanided. In 1917 this was the second largest gold producer in the State, the Holte mine in Idaho County being first. The National Mining & Development Co. treated considerable ore by cyanidation, and the Golden Age and Lucky Boy properties had some ore amalgamated. At the latter mine an electric power and light plant was installed and also a Marathon mill. Initial treatment, however, was not particularly successful. The Diana Mines Co., which did considerable development and advertising in 1915 and 1916, was in the hands of a receiver in 1917. Some bullion and concentrate were marketed in the early part of the year. At the Hay Fork mine, near Idaho City, a 25-ton Marathon mill was installed, which will be ready for operation in 1918. From the Mammoth property some ore was milled by amalgamation, and from the Mohawk mine a shipment of lead ore containing considerable gold was made. The most important of the 19 placer operators were the Boise Basin Improvement Co., the Granite Creek Ditch Co. or the Leary & Brogan ground, the Centerville Mining Co., and the Missouri Mining Co. The Pittsburg Idaho Hydraulic Mining Co. installed a hydraulic elevator in 1916, but the ground was so heavy that the equipment was replaced by a dry land dredge in 1917.

BONNER COUNTY.

Except in output of lead, there was a decided decrease in production in Bonner County in 1917. All of the production came from the Pend Oreille district and was that of the Lawrence Mining & Milling Co. and the B. F. & H. mine. The former produced lead ore, which was concentrated, and the latter a siliceous silver ore. Impor-

[1] U. S. Geol. Survey Mineral Resources, 1914, pt. 1, p. 616, 1915.

Digitized by Google

tant development work was continued at the Keystone mine by the Armstead Mines (Inc.). A long adit was driven in record time and a large tonnage of silver milling ore opened. At the end of January, 1918, the vein was cut 3,565 feet from the portal at a depth of 1,600 feet, and ore was said to assay 25 ounces of silver per ton.

BONNEVILLE COUNTY.

One deep mine and 1 placer produced gold, silver, and copper valued at $2,357. The placer production came from the hydraulic operations of the Idaho Mining & Dredging Co., at Gray, Idaho.

BOUNDARY COUNTY.

Four deep mines produced 38,591 tons of ore, containing $651 in gold, 121,582 ounces of silver, 704 pounds of copper, and 6,514.134 pounds of lead, valued in all at $661,243. Most of the ore, 37,856 tons, was concentrated and the remainder, 735 tons, was shipped directly to smelters. The ore had a total value per ton of $17.13 and a gold and silver value of $2.61. Practically all of it was lead ore.

Lenia district.—The Eureka mine, near Lenia, close to the Idaho-Montana boundary line, made a test shipment of sulphide lead ore.

Moyie Yahk district.—A small output of gold ore was shipped to the smelter by the Bethlehem Gold Mines (Ltd.), and preparations for extensive hydraulic work were said to be under way by the Idaho Gold & Ruby Mining Co.

Priest Lake district.—The greater part of the county output came from the Idaho Continental mine, west of Porthill. This important lead mine was operated for eleven months during the year and shipped several thousand tons of crude lead ore and concentrate. The 300-ton mill is equipped with crusher, rolls, jigs, classifier, Hardinge mill, Wilfley tables, and Frue vanners.

BUTTE COUNTY.

This county was formed during the year, principally from the northeastern part of Blaine County. It also includes parts of western Bingham County and Jefferson County. Eight deep mines produced 5,898 tons of ore, valued at $261,039. The total ore was classified as 5,744 tons of lead ore, 153 tons of copper ore, and 1 ton of siliceous ore. The ore had a total value of $44.46 per ton, of which the gold and silver value was $5.47.

Antelope district.—The Weiler group, under lease and bond, produced considerable oxidized lead ore.

Dome district.—The Wilbert Mining Co. operated a 100-ton concentration mill intermittently and made shipments of crude lead ore and concentrates of good grade. Though shipments were less in 1917 than in 1916 $50,000 in dividends were paid in 1917. This property was mentioned under Fremont County in this report for 1916. As the ore contains very little silver, the decrease in the price of lead had a serious effect on ore shipments, which have to be hauled 40 miles to railroad. The fiscal report[1] for the company mentions the increased costs and continues as follows:

[1] Wilbert Mining Co. (Ltd.) Ann. Rept. for year ending May 15, 1918.

Digitized by Google

It early became apparent to the present management that, in order to eliminate the increasing costs of handling the mine products by hoisting and transportation through various levels until the surface bins were reached, it would be necessary to sink a new shaft from the surface which would connect directly with and form an upward extension of the 200-foot winze sunk from the 600 level during the previous and present (fiscal) years * * *. At the present time the shaft is down 429 feet, at an angle of 21 degrees. An additional depth of 135 feet will connect it with an old stope below the 500 level and about 80 feet of this stope will have to be straightened to the angle of inclination above. The company will then have a straight incline shaft to a depth of 830 feet from which the ore body on the 800-foot level, and below, can be developed * * *.

To operate the drills necessary to sink this shaft a 50-horsepower Chicago pneumatic oil-driven compressor was installed together with a 6 by 8 inch hoisting engine, drills, etc. This installation was well suited for the purpose, though after the flow of water was developed on the 800 level it became apparent that still additional machinery would be necessary to carry on the development at greater depth. This machinery * * * has been ordered, some of it being now on the ground and in process of installation * * *.

The immediate object in the erection of this plant and the driving of a new shaft is, of course, the further development of the ore shoot which has been productive from the surface. * * *

During the year 44 lots of ore were settled for. Of this, 1,021 tons were direct shipping ore, while 3,125 tons of mill ore produced 893 tons of concentrates. This ore returned the company $69.77 per ton or a total of $133,477.31.

With the present price of lead and with cheaper methods of ore extraction available by reason of the new shaft and hoisting machinery, the ore on the 800-foot level, which can readily be blocked out as soon as the new improvements are perfected, should show a substantial profit. From present progress it is probable that shipping will be resumed by the middle or latter part of July.

Hamilton district.—Three deep mines produced 1,032 tons of ore, $1,158 in gold, 2,482 ounces of silver, 11,827 pounds of copper, and 204,365 pounds of lead, valued in all at $24,008, or $23.26 per ton. A shipment of copper ore came from the Copper & Uranium property, and lead ore from the Frank mine and the Metta property.

CAMAS COUNTY.

The western part of Blaine County, including the locality around Soldier, was formed into Camas County in 1917. Three deep mines produced 999 tons of ore, $8,177 in gold, 725 ounces of silver, and 4,490 pounds of lead, valued in all at $9,160. A small production of sulphide lead ore came from the Square Deal property in the Rosetta district. Nearly all the remainder of the ore came from the El Oro Mines (Ltd.), which operated a 10-stamp amalgamation and concentration mill a little over a month. Considerable bullion and rich gold concentrate were shipped. The mill at the Cannon Ball mines in Little Smoky district was improved by adding rolls and jigs, and a K. & K. flotation machine will be installed.

CASSIA COUNTY.

In the Black Pine district, the Hazel Pine mine produced a few shipments of ore containing gold, silver, and lead, the greatest value being for the silver. A shipment of carbonate zinc ore came from the Deer Ridge property. At the Melcher mine, in the Stokes district, a 100-ton concentration plant was under construction.

Digitized by Google

CLEARWATER COUNTY.

Nine placers produced $17,349 in gold and 187 ounces of silver, valued in all at $17,503. The output in 1916 was valued at $26,455.

Burnt Creek district.—Placer gold and silver valued at $442 came principally from the Sweepstake placer.

Pierce district.—The placer output had a value of $17,061, against an output valued at $25,437 in 1916. The majority of the output came from the operation of the dredging plant of the Pierce Co. (Ltd.).

CUSTER COUNTY.

Twenty-seven deep mines produced 83,703 tons of ore, an increase of 5,376 tons. The production of the county, including the output of 6 placers, was $66,800 in gold, 232,319 ounces of silver, 4,462,180 pounds of copper, and 3,073,011 pounds of lead, in all valued at $1,740,685. Other than Shoshone County, this is the only county in the State that produced metals valued at more than a million dollars, although the output of Lemhi County was close to this amount. The county output in 1916 was valued at $1,596,789. The ore was divided into 68,832 tons of copper ore, 13,670 tons of lead ore, and 1,201 tons of siliceous ore. Most of the product was crude ore shipped to the smelters, 82,146 tons, valued at $1,686,217, or $20.53 per ton. No ore was directly concentrated, but 1,201 tons of ore were treated in gold and silver mills making bullion and 62 tons of rich gold concentrate.

Alder Creek district.—This is the most important producing area in the county. There were 14 deep mines producing 80,886 tons of ore, containing $53,428 in gold, 152,308 ounces of silver, 4,386,575 pounds of copper, and 2,356,785 pounds of lead, valued in all at $1,579,148, or $19.54 per ton. All of the product was crude shipping ore. In 1916 twelve mines in the district produced 77,288 tons of ore valued at $1,563,744. The Empire Copper Co., the largest producer, continued to ship copper ore at the rate of more than 5,000 tons a month. This mine alone produced more than half the copper in the State. Dividends declared in 1917 amounted to $200,000. The lower or Cossack tunnel was being connected with the Alberta tunnel above, and a tramway 3 miles long, planned to carry 50 tons per hour, was being installed. Shipments, however, were curtailed, as the Salt Lake smelters were unable to take care of the increased quantity of ore shipped from various districts.

Shipments of copper ore were also made by the Copper Basin Mining Co., but the quantity was much less than in 1916. The company was said to be working on a large body of low-grade sulphide ore newly discovered. There were two other important mines in the district, the Horseshoe property and the Homestake & Copper Queen mine, both producing lead carbonate ore. The latter property averaged nearly 1,000 tons a month during 1917. In the early part of 1918 it was bonded by the United States Smelting Co., of Salt Lake City, Utah.

The geology of this region is described in a recent Survey publication.[1]

[1] Umpleby, J. B., Geology and ore deposits of the Mackay region, Idaho: U. S. Geol Survey Prof. Paper 97, 1917.

Digitized by Google

Bay Horse district.—Nine deep mines produced 1,613 tons of ore, $178 in gold, 76,449 ounces of silver, 75,605 pounds of copper, and 712,717 pounds of lead, valued in all at $145,106, or $89.96 per ton. The output in 1916 was valued at $12,666. The largest production came from the operations of a lease on the Red Bird property belonging to the Clayton Mining & Smelting Co. Several hundred tons of oxidized lead ore were shipped. Shipments of lead ore were also made from the Riverview mine, belonging to the Aetna Mining & Investment Co. The Ramshorn mine, operated by the same interests, produced copper sulphide ore and some old smelter material containing principally silver and copper.

Stanley Basin district.—The output of the district was comparatively low. Only 4 placers produced $1,164 in gold and 30 ounces of silver. The Challis & Sturkey property was operated about six weeks.

Yankee Fork district.—Two deep mines and 2 small placers produced 1,201 tons of ore, $12,030 in gold, and 3,360 ounces of silver, both valued at $14,798. The only important producer was the Old Montana group, belonging to the Custer Consolidated Mining & Development Co. Several hundred tons of ore were treated by amalgamation and concentration.

ELMORE COUNTY.

Eight deep mines produced 25,616 tons of ore, a decrease of 13,669 tons. The value of the ore per ton decreased from $5.08 in 1916 to $4.18 in 1917. The total output of the county, including that of five placers, was $98,291 in gold, 11,745 ounces of silver, 241 pounds of copper, and 1,333 pounds of lead, valued in all at $108,150. The placer output was $956 in gold and 16 ounces of silver.

Bear Creek district.—From 1 small placer and 2 deep mines the district produced gold and silver valued at $396.

Highland district.—A small placer production came from the Last Chance property, near Barber.

Middle Boise district.—Two placers and 4 deep mines produced 25,590 tons of ore, $97,202 in gold and 11,593 ounces of silver, valued in all at $106,755. This represents a decrease from 38,558 tons of ore and a total value of $194,384 in 1916. All of the ore but 10 tons was treated in gold and silver mills. The greater part of the production came from the Boise Rochester mine, where a 40-stamp mill using amalgamation and concentration was operated. A Callow flotation cell was used after the Wilfley tables. The plant was operated from January to the end of September, 1917, when the property was optioned to the new owners. The Atlanta Mines Co. treated several thousand tons of low-grade ore by amalgamation and cyanidation. The property is equipped with five 5-foot Huntington mills and uses plate amalgamation, table concentration, and roasting and cyaniding of concentrates.

Pinegrove district.—An output of gold ore was marketed from the property of the Daily Consolidated Mining Co.

FREMONT COUNTY.

The production of this county is small because part of its mineral area went to make up Butte County in 1917. Three deep mines pro-

Digitized by Google

duced 725 tons of ore. The total value per ton was $76.88, and the gold and silver value $1.16. There were 509 tons of copper ore and 216 tons of lead ore.

Skull Canyon district.—The Skull Canyon mines produced several hundred tons of oxidized copper ore, smelted near Salt Lake City, Utah.

GEM COUNTY.

West View district.—The production from a small shipment of gold ore and a little placer bullion was valued at $75. The district produced metals valued at $2,921 in 1916, and was an important producer several years ago.

IDAHO COUNTY.

Mine production in Idaho County, Idaho, in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.[a]	Silver.[a]	Copper.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	
1916	72	6,748	$129,322	2,572	739	$131,197
1917	56	11,351	211,924	5,000	7,132	218,032
Increase, 1917	.....	4,603	82,602	2,478	6,393	86,835

[a] Includes placer production.

Twenty-four deep-mine operators produced 11,351 tons of ore, an increase of 4,603 tons. The value per ton of the output increased from $16.25 in 1916 to $18.19 per ton in 1917, nearly all of which was for gold and silver. The total output of the county, including that of 32 placers, was valued at $218,032. The placer output was $11,429 in gold and 129 ounces of silver, valued in all at $11,535. Nearly all of the ore, or 11,154 tons, was treated in gold and silver mines, resulting in bullion valued at $202,386, or $18.14 per ton. The remainder of the ore, 197 tons, was shipped directly to smelters.

Camp Howard district.—Three small placers produced $1,090 in gold and eight ounces of silver. The Cape Horn property was the main producer.

Clearwater district.—Aside from a small placer production, the principal operations were on the Cunningham property, from which several shipments of siliceous gold ore, containing some copper, were made.

Dixie district.—A small placer output came from the Moore property, and some gold ore was treated by amalgamation from the Powelson mine.

Elk City district.—Five placers and 9 deep mines produced 839 tons of ore, $9,961 in gold and 130 ounces of silver, having a total value of $10,068. These totals represent a decrease from 1,433 tons of ore and an output valued at $23,778 in 1916. The placer product was valued at $3,453. Bullion from ore amalgamated was marketed from the Mineral Zone, Black Pine, Grangeville, Hope, and Spiked Horse properties. The principal producing placer was the Golden Rule property.

Marshall Lake district.—The production came from the Sherman & Corporal property, known as the Holte mine, and the Lake Creek

Digitized by Google

placer, both near Burgdorf. As the Holte property is the most important gold mine in Idaho, judged by the output in 1917, it is unfortunate that the management publishes no report concerning its operations. Several thousand tons of ore were treated in a 30-ton amalgamation plant equipped with a Lane mill and Deister tables. In October, bullion valued at $24,000 was shipped, and this was said to be a month's clean-up. Late in the year a cyanide plant was being installed. In the same district it was reported that development at the Mount Marshall mine had opened ore at a depth of 1,600 feet.

Newsome district.—Two placers and 2 deep mines produced $557 in gold and 4 ounces of silver. The Moose Creek placer was operated for a short time.

Orogrande district.—The Oro Grande Gold Mining Co. completed a 240-ton cyanide plant on the Crooked River property, but practically no bullion was recovered during the year. A large but low-grade deposit of gold ore is opened by adits and crosscuts.

Ten Mile district.—Six placers and 4 deep mines produced 473 tons of ore, $8,141 in gold, and 135 ounces of silver, total value being $8,252. The output in 1916 was valued at $24,395. Operations continued at the New York mine, but on a smaller scale, and also at the Lone Yellow Pine property. Fair productions came from the Crescent, Little Leggett, Phoenix, and Tippie placers.

Warren district.—Eight placers and 4 deep mines produced 1,038 tons of ore, $12,441 in gold, and 431 ounces of silver, having a total value of $12,796. The output in 1916 was valued at $34,749. The principal producer was the Idaho Standard Mines Co., but the bullion shipped was less than it was during each of the last three years. There were no important placer operations in the district.

Unorganized district.—The Fisher placers produced some gold by hydraulic methods from the South Fork of Clearwater River, near the mouth of Meadow Creek.

KOOTENAI COUNTY.

No production was reported, but development was progressing at the Commonwealth property, near Hayden Lake. Considerable milling ore, containing silver, copper, and lead, is opened.

LATAH COUNTY.

One deep mine and 2 small placers produced gold, silver, and copper, valued at $5,403. Several shipments of copper ore came from the Merger property, operated by the Cottonwood Mining Co.

LEMHI COUNTY.

Mine production in Lemhi County, Idaho, in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	
1916	42	24,045	$113,070	247,571	216,333	11,208,985	$1,102,610
1917	42	19,048	59,610	159,994	211,642	7,282,166	875,489
Decrease, 1917		4,997	53,460	87,577	4,691	3,926,819	227,121

[a] Includes placer production.

Digitized by Google

There was a general decrease in this county in 1917. Thirty-four deep mines produced 19,048 tons of ore, a decrease of 4,997 tons. The total value of the ore was $43.78 per ton, and $7.87 for the gold and silver content. Eight placers produced gold valued at $41,397 and 161 ounces of silver, valued in all at $41,530. The placer output in 1916 was valued at $74,151. Two dredges were operated during the year, but the shipments of bullion were less than in 1916. Most of the ore, or 17,183 tons, was shipped directly to the smelters, and had a total value of $819,596, or $47.70 per ton. There were 1,617 tons of ore treated in gold and silver mills valued at $3,553, and 248 tons were concentrated, making 62 tons of concentrates, valued at $10,810. The ore was classified as 16,528 tons of lead ore, 1,653 tons of siliceous ore, and 867 tons of copper ore.

Eldorado district.—One placer and 7 deep mines produced 612 tons of ore, $5,408 in gold, 475 ounces of silver, and 85,571 pounds of copper, valued in all at $29,161. The dredge of the Bohannon Co. was not operated, but some gold was won from the deposit by hydraulic mining. Small shipments of copper ore were made from several new properties in the district. The largest producer was the Harmony Mines Co., which made good shipments of sulphide copper ore. An oxidized ore was shipped from the Pope Shenon mine. Other producers were the Ranger, Ruby, and Gold Point properties.

Eureka district.—The Mullen dredge on Moose Creek and Daly Creek was operated for about four months during the year. A little ore from the Wickham mine was treated by amalgamation.

Indian Creek district.—The Kittie Burton property, formerly an important producer, made only a few shipments of gold bullion during 1917. The property is equipped with an old 15-stamp amalgamation plant, but only 5 stamps were used intermittently during the year.

Junction district.—A good quantity of sulphide lead ore was shipped from the Sunset property, formerly called the Junction mines. One shipment of copper ore was made by the Greenback Copper Co.

Kirtley Creek district.—The Kirtley Creek Gold Dredging Co. operated its plant during 10 months of the year, and treated 740,587 cubic yards of material. As the Boston-Idaho dredge at Idaho City was idle, this was the most important dredge operation of the year.

Mackinaw district.—Three placers in this district produced $2,192 in gold and 8 ounces of silver. The Hockensmith placer on Arnett Creek was the largest producer.

McDevitt district.—A few shipments of copper concentrates were made from the Copper Queen property, operated by the Idaho-Seattle Mining Co. A small concentration plant was active only during a short period. Some crude ore was also shipped from the Blue Bird claim.

Mineral Hill district.—Four deep mines produced 771 tons of ore, $1,954 in gold, and 58 ounces of silver, having a total value of $2,002. The output in 1916 was valued at $3,899. Most of the ore came from the Kentuck property, on which the mill is equipped for amalgamation and concentration, but the concentrates were not marketed.

Pratt Creek district.—A small quantity of ore from the Climax property was treated by amalgamation. The mill was improved by the addition of a Dorr classifier, a Card table, and a Wilfley table.

Digitized by Google

Spring Mountain district.—Eight deep mines produced 640 tons of ore, $876 in gold, 5,698 ounces of silver, 5,615 pounds of copper, and 305,306 pounds of lead, valued in all at $33,360, or $52.13 per ton. In 1916 the output was valued at $31,933. The entire output was an oxidized lead ore smelted in Utah. The principal part of it came from the Winnie mine, owned by the Excelsior Mining Co.

Texas district.—Eight deep mines produced 13,995 tons of ore, $10,015 in gold, 138,105 ounces of silver, 83,456 pounds of copper, and 6,516,418 pounds of lead, valued in all at $707,008, or $50.52 per ton. The entire product was oxidized lead ore shipped without treatment. In 1916 eight deep mines produced 20,384 tons of ore valued at $953,722. The largest producer was the Pittsburg-Idaho Co., followed by the Latest Out Mining Co., and the Gilmore Mining Co. Shipments were also made from the Mountain Boy mine. The Pittsburg-Idaho mine shipped about 500 tons per month in 1917, against 1,000 tons per month in 1916. Dividends of $65,524 were paid from previous earnings remaining at the close of 1916, but the mine was said to be closed at the end of 1917. The loss in 1917 was due to transportation difficulties, water in the mine, and delay in the delivery of power machinery. Shipments from the Latest Out mine were at the rate of 300 tons per month, practically the same as in 1916, and the Gilmore Mining Co. shipped approximately 250 tons per month.

OWYHEE COUNTY.

Mine production in Owyhee County, Idaho, in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.[a]	Silver.[a]	Lead.	Total value.
		Short tons.		*Fine ozs.*	*Pounds.*	
1916	21	556	$10,344	16,513	.....	$21,209
1917	18	871	12,746	29,088	8,407	37,438
Increase, 1917	.....	315	2,402	12,575	8,407	16,229

[a] Includes placer production.

Seventeen deep mines produced 871 tons of ore, an increase of 315 tons. The ore had a total value per ton of $42.97 and a gold and silved value of $42.14. The entire product was siliceous. The production of gold and silver from the discovery of gold in 1863 to and including that of 1917 was $21,643,604 in gold and 24,379,782 ounces of silver, having a total value of $40,424,125. There was only one small placer operated in 1917.

Carson district.—Nearly all the county output came from this district. The gold was valued at $12,738, which with 29,088 ounces of silver and 8,407 pounds of lead, gave a total value of $37,430, or $42.97 per ton. The most important part of the production came from the Sunnyside mine, operated by the Bergh Mining Co. Amalgamation and concentration were used in the mill, which was operated for a short time. The Trade Dollar property, owned by the Florida Mountains Mines Co., produced some gold and silver as a result of ore milled and some rich crude ore and concentrates shipped. At the Silver City property several hundred tons of siliceous silver

Digitized by Google

ore were treated by cyanidation. A small clean-up was made from the old De Lamar mine.

Steele district.—In the Steele district, the Demming Mines Co. erected a 100-ton flotation plant on Boulder Creek, 40 miles southwest of Murphy, Idaho. It consists of crusher, tube mill, classifier, flotation machines, and filter, to treat ore containing gold and silver. Machinery is also on the ground to increase the capacity to 200 tons per day.

POWER COUNTY.

A small placer production came from the banks of Snake River near Aberdeen, American Falls, and Neeley.

SHOSHONE COUNTY.

Mine production in Shoshone County, Idaho, in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	63	2,516,325	$46,459	11,639,841	2,370,610	356,233,926	86,238,283	$44,424,716
1917	66	2,522,127	85,683	11,241,126	2,876,911	372,007,653	77,724,221	50,054,297
Increase or decrease, 1917		+5,802	+39,224	−398,715	+506,301	+15,773,727	−8,514,062	+5,629,581

[a] Includes placer production.

Shoshone County is usually referred to as the Coeur d'Alene region, which is the most important mining center of the State. It comprises several mining districts, the production of each of which is given separately. Sixty deep mines in the county produced 2,522,127 tons of ore, an increase of 5,802 tons over the output of 1916, when 56 deep mines produced. The total value per ton of the ore as mined was $19.84 and the value per ton in gold and silver was $3.70. The corresponding values in 1916 were $17.65 and $3.06. The value of the county output increased nearly 13 per cent and represented more than 91 per cent of the total value of the State output. There was a good increase in the production of lead, and small increase in both copper and gold, but the production of zinc and silver decreased. The output of lead ore ranked first with 1,362,745 tons, and lead-zinc ore followed closely with 1,107,619 tons. There were also 32,614 tons of copper ore, 18,987 tons of zinc ore, and 158 tons of siliceous ore. More than 84 per cent of the total ore of the State (2,317,949 tons) and 24,854 tons of old tailings were concentrated and reduced to 407,609 tons of concentrates, containing $34,826 in gold, 7,770,764 ounces of silver, 1,290,226 pounds of copper, 278,132,199 pounds of lead, and 63,756,334 pounds of recoverable zinc, in all valued at $37,212,682, or $91.05 per ton. These concentrates were separated into 1,308 tons of copper concentrates, containing 39.57 ounces of gold, 29,084 ounces of silver, and 438,275 pounds of copper; 182,922 tons of lead concentrates, containing 1,029.01 ounces of gold, 4,186,357 ounces of silver, 511,143 pounds of copper, and 161,975,139 pounds of lead; 15,245 tons of zinc concentrates, containing

Digitized by Google

46,805 ounces of silver, 830,640 pounds of lead, and 10,066,224 pounds of recoverable zinc; and 76,554 tons of lead-zinc concentrates, containing 47 ounces of gold, 288,282 ounces of silver, 9,448,459 pounds of lead, and 53,690,110 pounds of recoverable zinc. In 1917 only a few tons of ore were treated by amalgamation or cyanidation, but there were 32 milling plants having a combined daily capacity of approximately 10,372 tons, which were active nearly all of the year. These mills were concentration plants, and 24 of them used flotation machines. Of the county ores treated or shipped 179,323 tons were first-class crude ore containing $38,931 in gold, 3,470,232 ounces of silver, 1,586,685 pounds of copper, 93,875,454 pounds of lead, and 13,967,887 pounds of recoverable zinc, in all valued at $12,829,580, or $71.54 per ton. The crude ore smelted included 157 tons of siliceous ore, 8,487 tons of copper ore, containing 1,220.33 ounces of gold, 76,615 ounces of silver, and 1,010,404 pounds of copper; 148,672 tons of lead ore, containing 641.95 ounces of gold, 3,341,978 ounces of silver, 575,961 pounds of copper, and 92,212,556 pounds of lead; 12,372 tons of zinc ore, containing 11,481 ounces of silver, 587,456 pounds of lead, and 9,960,963 pounds of zinc; and 9,631 tons of lead-zinc ore, containing 14 ounces of gold, 39,355 ounces of silver, 1,074,594 pounds of lead, and 4,006,924 pounds of zinc. Six placer mines in the county produced $11,910 in gold and 130 ounces of silver.

Some recent articles referring to the region are noted below.

Easton, S. J., The Coeur d'Alene district: Eng. and Min. Jour., Jan. 12, 1918, p. 64.

Bell, R. N., Mining industry of Idaho for 1917; Idaho Geol. Survey Nineteenth Ann. Rept., 1918.

Soper, E. K., Mining districts of northern Idaho; Min. and Sci. Press, Jan. 26, 1918, p. 121.

American Smelting v. Bunker Hill: Min. and Sci. Press, Dec. 1, 1917, p. 779.

Mine production in the Coeur d'Alene region, Shoshone County, Idaho, 1884–1917.

Year.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
		Fine ounces.	*Pounds.*	*Short tons.*	*Pounds.*	
1916	46,459	11,639,841	2,370,610	178,117	86,238,283	$44,424,716
1917	85,683	11,241,126	2,876,911	186,004	77,724,221	50,054,297
1884–1917	5,608,399	165,103,762	68,054,429	2,647,377	334,651,441	409,935,329

Since the beginning of mining in 1884 the Coeur d'Alene region has produced gold, silver, copper, lead, and zinc valued at $409,935,329—gold, $5,608,399; silver, $102,424,182; copper, $10,935,462; lead, $257,188,290; and recoverable zinc, $33,778,996. The production of this region by years, from 1884 to 1913, was given in the report for 1913.[1] From 1904 to 1917 the operators in the region mined, shipped or treated 26,710,555 tons of ore.

Beaver district.—Four deep mines and 4 placers had a total production of 151,941 tons of ore, $1,314 in gold, 284,967 ounces of silver, 1,129 pounds of copper, 15,383,920 pounds of lead, and 44,796,575 pounds of recoverable zinc, valued in all at $6,128,703. In

[1] U. S. Geol. Survey Mineral Resources, 1913, pt. 1, p. 780, 1914.

Digitized by Google

1916 the mines produced 146,407 tons of ore, which, with the placer output, had a total value of $8,261,950. Of the total quantity, 138,004 tons were milled, making 54,350 tons of concentrates, and 13,937 tons were shipped directly to smelters. Lead ore was milled from the Idora and the Tuscumbia mines, and lead-zinc ore from the Ray Jefferson mine was treated in a new 400-ton concentration plant. As usual, the greater part of the district output was from the property of the Consolidated Interstate-Callahan Mining Co., the largest zinc producer in the State. The printed report of the company,[1] made for 18 months so as to change to the calendar year, contains the following paragraphs:

During the period covered by this report we have completed the 3-compartment shaft to what is known as the No. 8 level, a distance of 850 feet below the main working tunnel, or the No. 4 level. We have developed and have been mining from a fine body of ore on the No. 7 level, and have encountered the same high-grade ore on the No. 8 level, which is just opened up, proving that the ore is continuing with depth. The shaft is being continued to what will be known as the No. 9 level, which will give the mine a depth of 1,050 feet below the main workings of the property. * * *

During the last 18 months several important additions to our milling equipment have been installed. These improvements consist of a 400-ton flotation plant, a Sauerman slack-line cableway, and the enlargement of our grinding, thickening, and flotation departments to meet the demands of an increasing tonnage. * * *

Our company has acquired a controlling interest in the Blue Grouse Mining Co. and also a controlling interest in the Silver State Mining Co., which properties adjoin the Interstate property on the north. We have also acquired full ownership of the Nipsic property, which adjoins the Silver State property. These three additional properties increase the acreage of the Consolidated Interstate-Callahan Mining Co. by approximately 342 acres, giving our company a total acreage at this time of 1,250 acres. A crosscut is now being run from the Interstate No. 6 level, across the Silver State property and into the Nipsic property, which will open up the Nipsic vein about 1,000 feet below the ore body indicated in the upper levels of the Nipsic mine, and will also develop the Silver State property.

During the year our title to the Amazon-Manhattan property, which was acquired by the company some years ago, was questioned by adverse claimants, and the matter went to the State courts of Idaho for adjustment, which resulted in the courts directing that the adverse claimant be awarded the property, upon the return to the company of the full amount paid for the Amazon-Manhattan—that is, $160,000. * * *

Conditions at the mine and in the mill are first-class, and when the new flotation plant is thoroughly adjusted we expect to make a much higher recovery of metal values in the ore. * * *

Notwithstanding the unsettled labor conditions with which other sections of the country have had to contend, so far we have had no labor troubles of any kind in the Coeur d'Alene district.

A summary of the quarterly reports gave 161,455 tons of ore mined, of which 130,724 tons were milled. The crude ore and concentrates shipped amounted to 67,008 tons. The lead in lead ore and lead concentrate was 8,956,100 pounds, and the gross zinc in crude zinc ore and concentrate was 52,045,288 pounds. There was also silver recovered from both the lead and the zinc products and some lead from the zinc products. According to the statement to the county assessor the product had a gross value of $3,250,835. The cost of extraction was $1,080,698; freight and treatment, $747,375; betterment and repairs, $188,699; and net profit, $1,234,063. Dividends declared in 1917 amounted to $929,980, making $6,509,860 to date.

[1] Consolidated Interstate-Callahan Mining Co. Rept. for 18 months ending Dec. 31, 1917.

Digitized by Google

A small placer production from the district was valued at $1,231, partly from the Lock & Erwin property on Trail Creek.

Coeur d'Alene district.—On Prichard Creek, near Murray, stream gravel was treated by the dredge of the Yukon Gold Co. This plant was brought from Alaska and operated about one month toward the close of the year. It is of steel construction, electrically driven, and will treat about 5,000 cubic yards of gravel per day. In 1918 it will probably add much gold to the State output.

Eagle district.—A considerable quantity of lead sulphide ore of good grade was shipped from the Jack Waite property to the lead plant at International, Utah. In November shipments ceased as floods had made the roads impassable.

Evolution district.—Six deep mines produced 4,456 tons of ore, $766 in gold, 163,037 ounces of silver, 26,275 pounds of copper, and 735,431 pounds of lead, valued in all at $205,529, or $46.12 per ton. The output in 1916 was valued at $38,353. Several properties were operated, including the Old Charles Dickens, Nellie, Polaris, and Silverado. The best part of the ore came from the Yankee Boy mine, operated by the Big Creek Leasing Co. A considerable quantity of ore high in silver but rather low in lead was shipped to the East Helena smelter. Dividends of $10,000 were paid in 1917.

Hunter district.—Nine deep mines produced 585,903 tons of ore, $10,348 in gold, 1,766,441 ounces of silver, 361,234 pounds of copper, 70,448,635 pounds of lead, and 7,145,620 pounds of recoverable zinc, valued in all at $8,351,948, or $14.25 per ton. In 1916 seven deep mines had an output valued at $6,793,627. Most of the ore, or 508,674 tons, together with 8,390 tons of old tailings, was milled and made 56,700 tons of concentrates, containing 205.57 ounces of gold, 1,055,459 ounces of silver, 308,383 pounds of copper, 39,291,048 pounds of lead, and 7,123,180 pounds of recoverable zinc. The remainder was crude ore shipped to smelters—68,839 tons—containing 295 ounces of gold, 710,982 ounces of silver, 52,851 pounds of copper, 31,157,587 pounds of lead, and 22,440 pounds of recoverable zinc. The largest producer was the Morning mine, owned by the Federal Mining & Smelting Co., which was operated 11 months during the year. According to the statement to the county assessor, the mine produced 469,079 tons of ore extracted, having a gross value of $4,620,345. The cost of extraction was $1,668,772; freight and treatment, $1,463,366; betterment and repairs, $168,248; and net profit, $1,319,962. The printed annual report[1] of the company, which deals with the Morning mine and mines in other districts, contains the following notes:

> The amount of ore shipped during the year, while slightly less than that shipped during the preceding year, is greatly in excess of that shipped in 1915: Total shipments 1917, 130,097 tons; 1916, 137,390 tons; 1915, 75,449 tons.
>
> During the year, the profitable mines of the company yielded the following profits: Wardner, $54,884; Morning, $1,319,892; Mace, $272,162. * * *
>
> *Mace mines.*—The profitable ore in both Green Hill and Federal territory was exhausted in December, 1917, and the property is now shut down. The pumps have been brought to the surface and stored, and the other machinery dismantled. * * *
>
> *Wardner mine.*—This mine is practically exhausted and will probably be finally closed down within the year. It will not thereafter be a producer, as title to the property will then finally vest in the Bunker Hill & Sullivan Mining & Concentrating Co. under the terms of the settlement of 1910.

[1] Federal Mining & Smelting Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

Morning mine.—Developments during last year were very satisfactory. The 2,000 level has been sunk and has disclosed much additional ore. The mine seems to grow better with depth.

Due to a shifting or swelling of the side walls, the Morning shaft became badly in need of repairs, necessitating the closing down of the mine from early in December until the middle of February, when operations were resumed. During the period of shutdown many of the crew sought employment elsewhere, but it is expected that in a short time the mine will again be running to its full capacity. * * *

The total ore mined by the company was 728.359 tons, but this total included 50,500 tons from the Greenhill mine and 7,360 tons from the North Star in Blaine County. Ore reserves January 1, 1918, at the Wardner, Morning, and Mace mines were 637,870 tons of milling ore and 89,595 tons of first-class ore.

The average number of employees at all plants, exclusive of the Wallace office, was 1,064, at an average wage of $4.98 per shift. * * *

The efficiency of labor measured in tons of ore per man per shift is only 75 per cent of that of normal times, say 1914. Wages have increased 32.4 per cent over normal. The increased cost of labor to us is, therefore, 76.6 per cent.

The costs of materials and supplies have also continued to increase all along the line, especially powder and steel. * * *

The company's operations are now substantially confined to the Morning mine, which contains a large body of complex ore. Our milling and metallurgical processes have been greatly improved in the last year or two. Nevertheless, with advancing costs of labor and supplies and a fixed maximum to the price of lead, profits become uncertain and difficult to forecast. * * *

During the year a suit was brought by the Star Mining Co. against the Federal Co. for an injunction and accounting in regard to the Morning vein lying west of the west-end line of the Morning. A temporary injunction was granted, which suspended operations during the year in the ground in dispute, and considerably curtailed the activity of the Morning mine. In addition, the necessity for doing a large amount of development work to prove our case in court resulted in a material decrease in the development of the Morning mine proper. However, this litigation work resulted in the disclosure of a much larger amount of ore in the ground in dispute than we had previously estimated, and resulted, as a whole, in a material addition to our ore reserves of the Morning mine. The estimated tonnage in this ground is about 654,000 tons.

The Star case was tried the latter part of the year 1917, and a decision has just been rendered in favor of the contention of this company.

The Gold Hunter Mining & Smelting Co. operated its mine and mill throughout the year. The plant has a capacity of 400 tons per day, and is equipped with ball mill, Dorr thickener, and three flotation cells. Concentrates which were shipped to Colorado contained slightly more lead but less silver than in the output of 1916. According to the statement to the assessor 116,562 tons were extracted, having a gross value of $994,408. The cost of extraction was $525,494; freight and treatment, $293,202; betterment and repairs, $44,893; and net profit, $130,812. No dividends were paid.

At the National property several thousand tons of ore were treated in the 500-ton concentrator. Shipments of copper concentrates were made to Tacoma. The management has had considerable difficulty with a low-grade ore in a very hard gangue, but shipments are continuing in spite of adverse conditions. According to the county assessor there were 13,374 tons of ore extracted, having a gross value of $72,742. The cost of extraction was $41,835; freight and treatment, $15,720; and betterment and repairs, $50,000.

A few shipments of copper ore were made from the Snowstorm property, east of Mullan, formerly the largest producer of copper in the State.

The North Idaho Metals Corporation treated old tailings and separated and shipped lead concentrate and lead-zinc concentrate. Small

Digitized by Google

shipments were made from the Alice, Carney, and Midnight properties.

Lelande district.—Nine deep mines produced 802,479 tons of ore, containing $15,610 in gold, 5,170,490 ounces of silver, 552,180 pounds of copper, 142,601,428 pounds of lead, and 3,535,684 pounds of recoverable zinc, valued in all at $17,051,202, or $21.25 per ton. The output had a value greater than that of any district in the State, though the output of Yreka district was nearly as large. The production of lead was considerably greater than in any other district in the State. In 1916 the output of the district was valued at $15,512,333. Of the ore, 747,734 tons, with 733 tons of old tailings, were concentrated, making 123,090 tons of concentrates, containing 535.14 ounces of gold, 3,500,260 ounces of silver, 309,308 pounds of copper, 98,651,367 pounds of lead, and 2,747,335 pounds of recoverable zinc. The crude ore shipped was 54,012 tons, containing 220 ounces of gold, 1,670,230 ounces of silver, 242,872 pounds of copper, 43,950,051 pounds of lead, and 788,349 pounds of recoverable zinc. As in former years, the main producer of the district was the Hercules mine, from which more than 2,000 tons of first-class crude ore were shipped per month. In addition to these shipments, the mill at Wallace treated more than 900 tons per day throughout most of the year. The product is mainly a lead sulphide crude ore and concentrate shipped to the Northport Smelting Co., at Northport, Wash. There is, however, some zinc ore shipped and some zinc concentrate saved at the mill. Details concerning the mining and milling operations of the company are not published. According to the statement to the assessor, 108,052 tons of crude ore and concentrate were shipped, having a total value of $9,880,979. The cost of extraction was $2,140,053; freight and treatment, $3,765,025; betterment and repairs, $285,500; and net profit, $3,690,400. Dividends were paid, but the amount paid was not published. An estimate in the Wallace Miner was $3,000,000 for the year. As a result of a lawsuit in 1917, the following information concerning past production was published from the court proceedings:

From 1901 to October 28, 1916, the ore mined was 1,650,087 tons, of which 165,984 tons were crude shipping ore having an average content of 59.93 ounces of silver and 54.16 per cent of lead. From 1906 to 1916 there were 1,484,103 tons milled, averaging 8.60 ounces of silver per ton and 9.85 per cent of lead. Concentrates from this mill product totaled 258,604 tons and averaged 44.49 ounces of silver per ton and 52.33 per cent of lead. Receipts for the period were $20,972,610; profits, $11,915,878; and dividends, $9,981,227. The table by years is given by Weed.[1] For 16 years, not including the year 1917 and part of 1916, the mine produced about 21,454,000 ounces of silver and 450,000,000 pounds of lead. In the early part of 1918 the opening of the ore body below the No. 5 level at a depth of 2,000 feet was most encouraging.

The Hecla Mining Co. continued to make shipments of lead ore and concentrate. There was also a good output of zinc concentrate marketed during the year. A large part of the production went to the new plant of the Bunker Hill Co., at Sweeney, Idaho. The mill at Gem, which is equipped with jigs, tables, and flotation cells, was increased to a capacity of 750 tons daily. According to the statement

[1] Weed, H. W., The mines handbook, vol. 13, p. 775, 1918.

Digitized by Google

to the county assessor, there were 374,213 tons of ore extracted, which had a gross value of $4,462,030. The cost of extraction was $1,506,639; freight and treatment, $798,165; betterment and repairs, $262,161; and net profit, $1,895,065, from which dividends of $1,600,000 were paid in 1917. Dividends paid to date amount to $6,905,000. Considerable information regarding this mine, including the report for 1917, was recently published.[1] Extracts follow:

During the year 12,386 feet of development was accomplished—3,473 feet on the Ore-Or-No-Go vein and 8,913 feet on Hecla vein. Main shaft was sunk 210 feet and a new level is to be opened at the 2,000-foot, a point which it is believed the workings have nearly reached. A raise from the 900-foot level, in ore, to the No. 3 adit level, is in progress, and should be completed in June. Ore reserves are estimated at 1,326,399 tons, including 70,000 tons above water level on the Ore-Or-No-Go vein—sufficient supply for four years and one month at the production rate maintained last year. * * * From both veins 374,213 tons were raised, of which 292,726 tons were milled in Gem and Black Cloud mills, 14,474 tons shipped crude, and 67,013 tons classified as waste. Combined mining costs reached $3.493 and milling costs $0.686. Per ton gross receipts were $9.811 and gross expenses $4.029, leaving net per ton profit of $5.782. Total production was 1,366,960 ounces silver, 44,363,559 pounds lead, and 507,888 pounds zinc.

Production for 14 years was 335,053 tons of crude ore and concentrate shipped, containing 9,625,014 ounces of silver and 325,786,612 pounds of lead.

From the Greenhill Cleveland property, controlled by the Federal Mining & Smelting Co., shipments of lead ore, lead concentrate, and lead-zinc concentrate were made at the rate of more than 1,500 tons per month. The ore on this property, however, is said to be practically exhausted at the beginning of 1918. According to the statement to the assessor the mine produced 18,012 tons of crude ore and concentrate, valued at $1,341,331. The cost of extraction was $654,856; freight and treatment, $290,311; betterment and repairs, $258,841; and net profit, $137,323. A 500-ton concentration mill near Wallace, which is equipped for gravity concentration and flotation, was used to treat this ore.

Good shipments of crude lead ore and zinc ore were made from the Frisco property without treatment, as the mill formerly used on the ore of the Frisco mine was sold to the Tamarack & Custer Consolidated Mining Co. at the end of 1916. The statement to the assessor gives 1,260 tons of ore extracted, valued at $62,480. Cost of extraction was $36,107; freight and treatment, $19,650; and net profit, $6,723.

The Marsh property, at Burke, produced milling ore, which was treated at the company's Black Cloud mill north of Wallace. Shipments of lead concentrate and lead-zinc concentrate were made until the property was closed the latter part of the year. The mill was leased to the Hecla Mining Co., and Hecla ore was treated there as well as at the mill at Gem.

There were also shipments made by lessees from the Mace & Burke mine of the Federal Mining & Smelting Co., and several shipments of concentrate from the treatment of creek tailings.

Placer Center district.—Seven deep mines in 1917 produced 159,696 tons of ore, containing $1,757 in gold, 540,748 ounces of silver, 50,159 pounds of copper, 16,450,681 pounds of lead, and 14,363,730 pounds of recoverable zinc, valued in all at $3,340,886, or $20.92 per

[1] Norman, S., Northwest mines handbook, vol. 1, p. 78, 1918.

Digitized by Google

ton. The ore was divided into 5,629 tons of crude ore shipped to smelters, 151,119 tons of ore concentrated, with 2,948 tons of old tailings re-treated, resulting in 35,257 tons of concentrates. In 1916 the output of ore was 130,076 tons valued at $2,547,727. The Tamarack & Custer Consolidated Mining Co. operated a 500-ton concentration mill equipped with flotation machines and shipped crude lead ore and concentrate to the Northport smelter. There was a slight increase in the output, though the mill was not operated until the middle of the year. According to the statement to the assessor, there were 16,916 tons of crude ore and concentrate marketed having a gross value of $1,338,322. The cost of extraction was $518,799; freight and treatment, $141,020; betterment and repairs, $27,645; and net profit, $350,858. Dividends were paid amounting to $124,340.

At the Success mine a 250-ton concentration and flotation mill was operated most of the year, and shipments of zinc concentrate were made at the rate of more than 1,000 tons a month. There was also some silver-lead concentrate separated. The property was operated at a loss of $102,091, due, it is said, to an unfavorable smelting contract. According to the statement to the assessor, the ore extracted was 57,297 tons. The amount received from sales of ore was $350,105; the cost of extraction was $335,553; and freight and treatment, $116,643. As expenses were high in 1917 and the management gave no detailed information to stockholders, there was much dissatisfaction, which led to a lawsuit and a change of management.

Shipments of a good grade of zinc concentrate were also made from tailings on Ninemile Creek, near Sunset.

St. Joe district.—The Richmond property became an important shipper of oxidized copper ore, containing about 20 per cent of iron and 30 per cent of silica. The production was nearly a million pounds of copper with some gold. During the year a tramway 8,800 feet long was completed and a compressor installed. The greatest depth attained was 370 feet through a crosscut tunnel 600 feet long, at which point the ore was said to be changed to a sulphide. Dividends were published as $83,200. According to a short printed statement, 7,766 tons, assaying 6.17 per cent copper and 0.156 ounce of gold, were shipped during the year. Receipts were $292,117, and net profit, $97,235.

Summit district.—From the operations of 1 small placer and 4 deep mines, the district had an output of 792 tons of ore, $143 in gold, 2,378 ounces of silver, 275 pounds of copper, 346,548 pounds of lead, and 172,679 pounds of recoverable zinc, valued in all at $49,595. The ore had a value per ton of $62.49. In 1916 the district produced 5,309 tons of ore and had an output valued at $70,285. Shipments of lead ore were made by the Fidelity Co. and by the Henrietta Exploration Co., operating the Bear Top mine. The Murray Hill Mining Co. milled a few hundred tons of ore, which resulted in a zinc concentrate. The best product of the district was high-grade sulphide lead ore and sulphide zinc ore from the Terrible Edith mine. The lead ore is steel galena, and some of it in carload lots assayed 63 per cent of lead.

Yreka district.—Eighteen deep mines produced 807,450 tons of ore, containing $19,484 in gold, 3,303,244 ounces of silver, 926,938

Digitized by Google

pounds of copper, 124,684,064 pounds of lead, and 7,709,933 pounds of recoverable zinc, valued in all at $14,503,653, or $17.96 per ton. Most of the ore, or 770,376 tons, with 12,783 tons of old tailings, was concentrated, making 137,873 tons of concentrates. In 1916 this district produced 857,066 tons of ore, valued at $11,169,005. The Bunker Hill & Sullivan property was the largest lead producer of the State, though in silver output it was exceeded by that from the Hercules mine, at Burke. Two concentration mills were in operation the entire year, which treated an average of 1,650 tons a day. According to the statement to the county assessor, the company extracted 493,030 tons of ore, valued at $9,584,963. The cost of extraction was $1,473,480; freight and treatment, $4,641,181; betterment and repairs, $1,056,619; and net profit of $2,447,285, which included royalties amounting to $33,602. Dividends for 1917 amounted to $2,043,750, and dividends to date are $20,533,500. Extracts from the annual report[1] follow:

The mine yielded in 1917 a larger tonnage of ore than during any former year. Besides, we recovered and sold a substantially larger amount of lead and silver than during any year in the history of the property, although our operations were more or less hampered by scarceness of labor and materials and by the same difficulties which have hampered most of the industries of the country. Not only was this record production made, but the sinking of our main shaft to the No. 15 level was completed, the No. 15 shaft and pump stations were excavated, and the No. 15 crosscut was well advanced. The above-mentioned operating difficulties have resulted in higher costs per ton than the average of former years, but because of increased output, as well as the introduction of improved ore-handling methods in our newer work, the costs per ton did not exceed those of 1916. * * *

The development during the year on Bunker Hill No. 14 level has been most satisfactory. Although we have not yet cut the ore on the No. 15 level, it is believed that the lateral extensions made to the known ore on No. 14, and other levels, will make available an ore tonnage in excess of the quantity extracted during the year. It is confidently expected that within a few weeks the No. 15 crosscut will penetrate the ore, when a very substantial addition will be made to our ore reserves.

We have 3,457,419 tons of ore blocked out to date. * * *

The mine was in operation for the full period of 12 months and produced 492,617 tons of concentrating ore and 413 tons from exploration at a cost of $1,176,074.56; * * * 1,524 feet of drifts, raises, crosscuts, and shaft work were driven at a cost of $30,579.80. * * *

The concentrators were in operation for the full year. * * *

During the year 493,030 tons of ore were concentrated, making the average work of the concentrators 1,351 tons per day, or say 1,385 tons per 24 hours of actual operation, at a cost of $295,964.61. * * *

The company shipped 102,911.51 tons concentrates, at a cost of $23,402.

The ore milled—493,030 tons—assayed 10.65 per cent lead and 4.32 ounces of silver. From this ore, 103,982 tons of concentrates were produced, containing 93,992,898 pounds of lead and 1,692,765 ounces of silver. The loss in tailing was 10.49 per cent of the lead and 20.40 per cent of the silver in ore milled, or a total of 11.88 per cent. The total cost per pound of lead was 6.64 cents, a considerable increase. From 1886 to 1917 the company has mined 7,886,886 tons of ore having a gross value of $80,247,373. Net smelter returns were $46,975,409, and operating profit $26,261,032.

The Bunker Hill smelter and refinery were completed in 1917, and three furnaces, having a combined capacity of 1,000 tons per

[1] Bunker Hill & Sullivan Mining & Concentrating Co. Thirtieth Ann. Rept., for year ending Dec. 31, 1917.

Digitized by Google

day were in operation by the end of the year. The products from custom ore treated were desilverized lead, fine silver, and gold. The Bunker Hill & Sullivan Mining & Concentrating Co. had a contract with the American Smelting & Refining Co. to treat the output of the mine. When the Bunker Hill smelter was put in operation the American Smelting & Refining Co. protested against a diversion of the ores and applied for an injunction against the Bunker Hill Co. Later the matter was settled out of court, and a new contract was signed, by which half the mine product is to be treated at Kellogg and half at the various plants of the American Smelting & Refining Co.

The Caledonia Mining Co. continued to ship ore and concentrate at the rate of about 1,500 tons per month. This ore is rather low in lead compared with other properties, but it contains considerable silver. According to the statement to the assessor, there were 38,577 tons extracted having a gross value of $1,849,255. The cost of extraction was $137,111; freight and treatment, $484,989; and net profit, $1,227,155. Dividends of $937,800 were paid for the year, and $2,901,606 to date. According to the printed report[1] of the company, the output of the Caledonia in 1917 was 27,122 tons milled and 17,983 dry tons crude ore and concentrate shipped. These shipments produced 1,068,700 ounces of silver, 544,802 pounds of copper, and 9,434,900 pounds of lead. The totals are slightly less than those of 1916.

During the year many hundred feet of development work was done, trying to find new ore, or the downward extension of the old ore bodies. In this we were unsuccessful. The amount of war tax we will have to pay is unknown, but it will be a large sum. We intend to continue the present dividend rate as long as it is policy to do so.

The Last Chance mine, of the Federal Mining & Smelting Co., was practically exhausted in the upper levels, and the property was turned over to the Bunker Hill Co. according to previous arrangements. During the year considerable lead concentrate and crude lead ore were marketed. According to the statement to the assessor, this property at Wardner produced 147,347 tons of ore, having a gross value of $626,686. The cost of extraction was $401,344; freight and treatment, $170,458; and net profit, $54,884. Notes of the operating company are given under Hunter district.

The Stewart Mining Co., operating the Stewart mine and the Crown Point mine of the Coeur d'Alene Development Co., produced about 2,000 tons of milling ore per month, which resulted in lead concentrate. A 200-ton plant using Hardinge mill, jigs, Wilfley tables, and flotation, was active.

The Hypotheek property produced nearly 40,000 tons of ore, which was considerably oxidized and principally of milling grade. A 200-ton concentration mill was operated and the product shipped to the United States smelter at Salt Lake City, Utah. There were several other properties shipping crude lead ore or concentrate, including the Ontario, Sierra Nevada, and Hays Co., working on tailings, and the Alhambra property, using a 35-ton flotation mill. The Big Creek Mining Co. made shipments of sulphide copper ore containing considerable silver. Low-grade copper ore was concentrated at the

[1] Caledonia Mining Co. Ann. Statement for year ending Dec. 31, 1917.

Digitized by Google

Horst-Powell property, north of Kellogg. The mine, however, was closed in the latter part of 1917.

One of the largest zinc producers in the district was the Highland Surprise Co., which operated a mill and shipped zinc concentrate to various smelters in the East, but especially to the Anaconda zinc plant at Great Falls, Mont. The Anaconda Copper Co. leased and operated the Douglas mine, and lead-zinc ore was shipped for leaching. The mine was operated continuously in 1917, though shipments were irregular owing to impassable wagon roads. According to the statement to the assessor, there were 7,799 tons extracted, having a gross value of $346,718. Cost of extraction was $179,286; freight and treatment, $143,595, and net profit, $23,477. Dividends of $17,050 were paid by the Douglas Co. from royalty.

The Constitution mine was also a considerable shipper of sulphide lead-zinc ore and concentrate, which contained more than a million pounds of recoverable zinc. A 100-ton concentration and flotation plant was in active operation. The Black Hawk mine, belonging to the Federal Mining & Smelting Co., was operated through lessees. A large production of lead concentrate and lead-zinc concentrate was marketed. According to the figures to the assessor, there were 15,600 tons of ore extracted, having a gross value of $117,126. The cost of extraction was $66,948; freight and treatment, $46,305; and net profit, $3,873.

The Nabob property produced some lead-zinc shipping ore and lead concentrate of a good grade, and a few tons of lead concentrate came from the Wyoming property.

TWIN FALLS COUNTY.

Three small placers produced $251 in gold and 1 ounce of silver from along Snake River.

VALLEY COUNTY.

From the southern part of Idaho County and the northern extension of Boise County, a new county was formed during 1917 known as Valley County. The production of six small mines had a total value of $1,436 in gold and silver. In the Big Creek district the Snowshoe mine produced some ore which was treated in a 1-stamp mill using amalgamation. In the Payette River district, near Emmett, the Three Sisters property made a test shipment of siliceous silver ore.

WASHINGTON COUNTY.

One shipment of lead ore was made from the Galena Silver mine, near Council, Idaho, in the Heath district.

Digitized by Google

GOLD, SILVER, COPPER, LEAD, AND ZINC IN WASHINGTON.

(MINES REPORT.)

By C. N. Gerry.

PRODUCTION.

GENERAL STATEMENT.

The value of the mine production of gold, silver, copper, lead, and zinc in Washington in 1917 was $2,289,285, an increase of 12 per cent over that of 1916. There was a moderate increase in the quantity of ore mined, and a decided increase in the production of lead, but the output of gold, silver, copper, and zinc were less in quantity than in 1916. The output of lead and the total value of the metals were records for the State, being greater than any previous yearly figures. Dividends paid by four companies in 1917 amounted to $344,823. During 57 years the State has produced gold, silver, copper, lead, and zinc valued at $36,486,666, of which more than 75 per cent was for gold.

Mine production of gold, silver, copper, lead, and zinc in Washington in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	113	164,998	$577,655	335,121	2,645,022	5,399,274	1,693,734	$2,048,350
1917	136	172,119	492,324	282,320	2,199,518	9,789,687	1,195,567	2,289,285
Increase or decrease, 1917	.....	+7,121	−85,331	−52,801	−445,504	+4,390,413	−498,167	+240,935
Total, 1860–1917	.....	.....	27,448,692	7,053,440	10,922,800	27,257,104	3,154,797	36,486,666

ORE.

The quantity of ore sold or treated increased from 164,998 tons in 1916 to 172,119 tons in 1917, or more than 4 per cent. There was an increase of 13,228 tons in Stevens County, but a decrease of 5,787 tons in Ferry County. The total value per ton of the ore increased from $12.36 in 1916 to $13.27 in 1917, but the value per ton in gold and silver decreased from $4.79 to $4.18. Of the total output of ore, more than 38 per cent was dry or siliceous ore, more than 43 per cent copper ore, 9 per cent lead ore, and nearly 9 per cent lead-zinc ore. The siliceous ore averaged per ton $8.83 in gold and silver;

Digitized by Google

the copper ore, $1.78; the lead ore, 28 cents; and the lead-zinc ore, 8 cents. The siliceous ore was composed of 65,058 tons of gold ore, averaging per ton $7.36 in gold, 1.54 ounces of silver, and 0.76 pound of copper; 533 tons of silver ore, averaging per ton $1.67 in gold, 36.11 ounces of silver, 4.16 pounds of copper, and 2.36 pounds of lead; and 48 tons of gold and silver ore, averaging per ton $13.29 in gold, 23 ounces of silver, and 51.14 pounds of lead. The gold ore includes 4,966 tons of sulphide iron ore, containing 102.33 ounces of gold, 467 ounces of silver, and 19,837 pounds of copper. This class of ore amounted to 10,956 tons in 1916. The siliceous ore, with the iron ore, averaged per ton $7.31 in gold, 1.84 ounces of silver, with a trace of copper and lead. Copper ore as mined averaged 8 cents in gold and 2.06 ounces of silver per ton and 1.43 per cent of copper, or a total value of $9.59. Lead ore averaged 0.34 ounce of silver per ton and 29.68 per cent of lead, or a total value of $51.34. Zinc ore, all of which was of shipping grade, contained 18.93 per cent of recoverable zinc, or a value of $38.61 per ton, and lead-zinc ore, which was all milled, averaged 0.15 per cent lead and 3.85 per cent recoverable zinc, and had a total value per ton of $8.22. Nearly all of the lead ore and most of the siliceous ore was shipped without treatment, but all of the lead-zinc ore and most of the copper ore was concentrated.

Ore and metals produced in Washington in 1917.

Source of production.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.
		Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Placers	17	.....	283.86	86	.....	.....	.....
Dry or siliceous ore	56	65,639	23,240.61	120,510	51,391	4,483	.....
Copper ore	43	75,006	281.93	154,747	2,147,102	.....	.....
Lead ore	18	16,407	1.55	5,630	535	9,739,302	.....
Zinc ore	2	114	.....	.....	.....	.....	43,149
Lead-zinc ore	2	14,953	8.22	1,347	490	45,902	1,152,418
	.....	172,119	23,816.17	282,320	2,199,518	9,789,687	1,195,567

Ore sold or treated from Washington in 1917, in short tons.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Lead-zinc ore.	Total.
Chelan	21	.....	.....	.....	.....	21
Ferry	53,197	5,933	1	.....	.....	59,131
King	180	.....	.....	.....	.....	180
Kittitas	12	37	.....	.....	.....	49
Okanogan	658	1,167	.....	.....	.....	1,825
Pend Oreille	.....	.....	107	36	14,953	15,096
Pierce	.....	18	.....	.....	.....	18
Skagit	14	.....	.....	.....	.....	14
Snohomish	1	2,837	.....	.....	.....	2,838
Stevens	657	65,009	16,299	78	.....	82,043
Whatcom	10,897	.....	.....	.....	.....	10,897
Yakima	2	5	.....	.....	.....	7
	[a] 65,639	75,006	16,407	114	14,953	172,119
Average value per ton in gold and silver	$8.83	$1.78	$0.28	.....	$0.08	$4.18

[a] Includes 65,058 tons of gold ore, 48 tons of gold and silver ore, and 533 tons of silver ore.

Six milling plants were active in 1917, of which 3 used amalgamation, 2 used concentration, and 1 was equipped for amalgamation and concentration. The United Copper mill at Chewelah continued

Digitized by Google

the use of flotation with table concentration, and a considerable quantity of ore was amalgamated at the Boundary Red Mountain property, in Whatcom County. The cyanide mill at Republic was idle, as all of the ore was shipped directly to smelters.

Gold and silver mills treated more than 6 per cent of the total quantity of ore and tailings, or 10,986 tons, in 1917, against 12,702 tons in 1916.

Most of the ore treated came from Whatcom County, near Sumas. No cyanide was consumed, but 185 pounds of mercury was used in 4 milling plants. The average consumption of mercury was 0.0168 pound per ton of ore amalgamated and 0.026 pound per ounce of gold and silver bullion saved.

Gold and silver produced at mills in Washington in 1917.

County.	Ore.	Bullion recovered from ore by—				Total value.
		Amalgamation.		Cyanidation.		
		Gold.	Silver.	Gold.	Silver.	
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Fine ounces.*	*Fine ounces.*	
Chelan	17	11.84	2	.....	.....	$246
Ferry	10	.....	.....	12.84	50	307
Kittitas	12	9.19	3	.....	.....	192
Okanogan	a 90	72.72	34	.....	.....	1,531
Whatcom	10,855	6,625.63	372	.....	.....	137,271
Yakima	2	1.50	.....	.....	.....	31
	10,986	6,720.88	411	12.84	50	139,578

a Also yielded 2 tons of concentrates.

Nearly 43 per cent of the output of ore, or 73,673 tons, was concentrated, an increase from 53,635 tons in 1916. Concentrates increased from 4,130 tons to 6,076 tons. The greater part was a copper concentrate from the Chewelah district, in Stevens County, and most of the remainder was zinc concentrates together with a small quantity of lead concentrates from the Metaline district, in Pend Oreille County. Copper concentrates averaged 21 cents in gold and 26.96 ounces of silver per ton and 10.33 per cent of copper and had an average value per ton of $78.02. Lead concentrates averaged $3.54 in gold and 28.06 ounces of silver per ton and 47.81 per cent of lead and had a value per ton of $111.70. Zinc concentrates averaged 42.43 per cent of recoverable zinc and had a value per ton of $86.56.

Mine production of metals from Washington concentrates in 1917.[a]

County.	Ore to concentrating mills.	Concentrates.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value of concentrates.
	Short tons.	*Short tons.*	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
Okanogan	.....	2	6.22	15	.....	.....	.....	$141
Pend Oreille	14,953	1,406	8.22	1,347	490	45,902	1,152,418	122,908
Stevens	58,720	4,668	46.98	121,194	964,750	.....	.....	364,213
	73,673	6,076	61.42	122,556	965,240	45,902	1,152,418	487,262

a The concentrates from Chelan County were gold concentrates in 1917, those from Stevens County were all classified as copper concentrates, and those from Pend Oreille were mostly zinc, except two shipments of lead concentrates.

Digitized by Google

Nearly 51 per cent of the ore, or 87,416 tons, was mined and shipped directly to smelters. The greatest quantity of ore come from Ferry County, but a more valuable product came from Stevens County. Of the first-class or shipping ore, more than 62 per cent was siliceous, more than 18 per cent copper ore, nearly 19 per cent lead ore, and less than 1 per cent zinc ore. The siliceous ore shipped to smelters averaged per ton $6.23 in gold, 2.20 ounces of silver, and 0.94 pound of copper, and was valued at $8.30. Copper ore shipped averaged 30 cents in gold and 2.06 ounces of silver per ton and 3.63 per cent of copper and was valued at $21.82 per ton. First-class lead ore shipped had an average assay of 0.34 ounce of silver per ton and 29.68 per cent of lead and was valued at $51.34 per ton. Crude zinc ore shipped averaged 18.93 per cent of recoverable zinc and had a value of $38.61 per ton. Most of the copper ore shipped, or 16,143 tons, was sulphide, containing 233.83 ounces of gold, 33,429 ounces of silver, and 1,163,581 pounds of copper. The sulphide lead ore shipped was 2,575 tons, containing 0.58 ounce of gold, 4,150 ounces of silver, 535 pounds of copper, and 2,968,168 pounds of lead. Of the zinc ore shipped, 78 tons was sulphide, containing 18,852 pounds of recoverable zinc. The oxidized copper ore—143 tons—averaged 6.56 per cent of copper, and the oxidized or carbonate lead ore—13,832 tons—averaged 24.48 per cent of lead.

Mine production of metals from Washington crude ore shipped to smelters in 1917.

By counties.

County.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
Chelan	4	16.94	8				$356
Ferry	59,121	16,051.09	98,030	273,624	1,395		487,401
King	180	277.77	2,706	4,870			9,301
Kittitas	37		15	4,002			1,104
Okanogan	1,735	214.90	14,566	83,524	2,455		39,457
Pend Oreille	143		205		84,422	24,297	9,908
Pierce	18		47	3,084			881
Skagit	14	.58	508				431
Snohomish	2,838	20.76	1,151	180,948			50,777
Stevens	23,279	101.76	39,776	682,740	9,654,746	18,852	1,053,498
Whatcom	42	20.42	2,128				2,171
Yakima	5	.15	34	1,486			437
	87,416	16,704.17	159,174	1,234,278	9,743,018	43,149	1,655,720

By kinds of ore.

Dry or siliceous	54,609	16,467.67	119,991	51,391	3,716		$453,636
Copper	16,286	234.92	33,553	1,182,352			355,286
Lead	16,407	1.58	5,630	535	9,739,302		842,397
Zinc	114					43,149	4,401

GOLD.

The mine production of gold was valued at $492,324, against $577,655 in 1916, a decrease of nearly 15 per cent. Of this total more than 70 per cent came from ores shipped directly to smelters, 28 per cent came from ores treated by amalgamation or cyanidation, more than 1 per cent was from placers, and less than 1 per cent was from

Digitized by Google

concentrates. The table below shows that siliceous ore supplied most of the gold, or nearly 98 per cent, and that copper ore contained 1 per cent of the total. There was decided decrease in gold recovered from siliceous ores.

Mine production of gold in Washington in 1917, in fine ounces.

County.	Placers.	Dry or siliceous ore.	Copper ore.	Lead ore.	Lead-zinc ore.	Total.
Chelan	4.26	28.78	.....	.....	.....	33.04
Clallam	30.19	.....	.....	.....	.....	30.19
Ferry	.....	15,930.46	133.47	.....	.....	16,063.93
King	.....	277.77	.....	.....	.....	277.77
Kittitas	225.38	9.19	.....	.....	.....	234.52
Okanogan	15.91	264.94	28.90	.....	.....	309.75
Pend Oreille	.....	.....	.....	.....	8.22	8.22
Skagit	.....	.58	.....	.....	.....	.58
Snohomish	4.30	1.20	19.56	.....	.....	25.06
Stevens	.....	80.34	99.85	1.55	.....	181.74
Wahkiakum	3.87	.....	.....	.....	.....	3.87
Whatcom	.....	6,645.85	.....	.....	.....	6,645.85
Yakima	.....	1.50	.15	.....	.....	1.65
	283.86	a 23,240.61	281.93	1.55	8.22	23,816.17

a Includes 23,166.31 ounces from gold ore, 30.89 ounces from gold and silver ore, and 43.41 ounces from silver ore.

SILVER.

The mine production of silver decreased from 335,121 ounces, valued at $220,510, in 1916 to 282,320 ounces, valued at $232,632, in 1917, a decrease of nearly 16 per cent in quantity but an increase in value. Stevens and Ferry counties had the largest production. Crude ore shipped to smelters supplied more than 56 per cent of the total, concentrates more than 43 per cent, and placers and mill bullion less than 1 per cent. Siliceous ore contained nearly 43 per cent, copper ore nearly 55 per cent, and lead ore 2 per cent. Silver usually accompanies the lead ore in the Western States, but there is practically no silver in the ore of the Electric Point mine near Northport.

Mine production of silver in Washington in 1917, in fine ounces.

County.	Placers.	Dry or siliceous ore.	Copper ore.	Lead ore.	Lead-zinc ore.	Total.
Chelan	.....	10	.....	.....	.....	10
Clallam	5	.....	.....	.....	.....	5
Ferry	.....	96,854	1,204	22	.....	98,080
King	.....	2,706	.....	.....	.....	2,706
Kittitas	79	3	15	.....	.....	97
Okanogan	2	12,884	1,731	.....	.....	14,617
Pend Oreille	.....	.....	.....	205	1,347	1,552
Pierce	.....	.....	47	.....	.....	47
Skagit	.....	508	.....	.....	.....	508
Snohomish	.....	.....	1,151	.....	.....	1,151
Stevens	.....	5,045	150,565	5,403	.....	161,013
Whatcom	.....	2,500	.....	.....	.....	2,500
Yakima	.....	.....	34	.....	.....	34
	86	a 120,510	154,747	5,630	1,347	282,320

a Includes 100,158 ounces from gold ore, 1,104 ounces from gold and silver ore, and 19,248 ounces from silver ore.

Digitized by Google

COPPER.

The mine production of copper decreased from 2,645,022 pounds, valued at $650,675, in 1916 to 2,199,518 pounds, valued at $600,468, in 1917. The production increased slightly in Stevens and Okanogan counties, but decreased considerably in Ferry County. Crude ore produced more than 56 per cent of the copper and concentrates nearly 44 per cent. Most of the metal came from copper ore and only a little more than 2 per cent from siliceous ore.

Mine production of copper in Washington in 1917, in dry pounds.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Lead-zinc ore.	Total.
Ferry	41,935	231,689	.....	.....	273,624
King	4,870	.....	.....	.....	4,870
Kittitas	.....	4,002	.....	.....	4,002
Okanogan	2,527	80,997	.....	.....	83,524
Pend Oreille	.....	.....	.....	490	490
Pierce	.....	3,084	.....	.....	3,084
Snohomish	.....	180,948	.....	.....	180,948
Stevens	2,059	1,644,896	535	.....	1,647,490
Yakima	.....	1,486	.....	.....	1,486
	[a] 51,391	2,147,102	535	490	2,199,518

[a] Includes 49,172 pounds from gold ore and 2,219 pounds from silver ore.

LEAD.

There was a record mine production of lead in the State in 1917, as well as in 1916; the output increased from 5,399,274 pounds, valued at $372,550, in 1916 to 9,789,687 pounds, valued at $841,913, in 1917. This total represents an increase of more than 81 per cent in the production, which came principally from the mines of the Northport district of Stevens County, where encouraging development of galena and carbonate ore continues. Less than 1 per cent of the lead came from concentrates. Of the lead ore shipped, 13,832 tons were carbonate containing 6,771,134 pounds of lead and 2,575 tons were sulphide containing 2,968,168 pounds of lead.

ZINC.

The mine production of recoverable zinc was 1,195,567 pounds, valued at $121,948, against 1,693,734 pounds, valued at $226,960, in 1916. Zinc and lead-zinc ores were mined in the Metaline and Bossburg districts. Crude ore supplied 43,149 pounds and concentrates 1,152,418 pounds. The closing of the Great Western and Last Chance mines in the Northport district reduced the State output of zinc.

MINING INDUSTRY.

Mining conditions in Washington during 1917 were in many respects similar to those of other Western States. Metal prices for silver, copper, and lead were higher during the first part of the year, and fluctuated until the Government fixed the price of copper and zinc. The cost of labor and supplies was abnormally high, and men

Digitized by Google

were scarce, owing to the draft for the Army. Smelting conditions in Washington and British Columbia were also unfavorable to greater production. The smelter at Trail, British Columbia, which receives siliceous ore, copper ore, and lead ore from Washington, suffered from shortage of coke and from labor strikes, so that mines in the eastern part of the State were forced to ship ore to the Tacoma smelter in the western section, where they had no smelting contract. A strike at Republic interfered with production, and the ore shipped was of lower grade. Notwithstanding these adverse conditions, the lead output of the State was considerably increased. The output of zinc, however, fell short of the former production, owing partly to depletion of ore bodies. The increased value of silver and copper and a record output of lead overbalanced the decrease in the quantity of gold, silver, copper, and zinc, so that the total value of the five metals was greater than that in any previous year. More dividends were paid in 1917, though the total is not large compared with other States.

Mine production of gold, silver, copper, lead, and zinc in Washington in 1917.

County.	Ore.	Gold.		Silver.	
		Quantity.	Value.	Quantity.	Value.
	Short tons.	*Fine oz.*		*Fine oz.*	
Chelan	21	33.04	$683	10	$8
Clallam		30.19	624	5	4
Ferry	59,131	16,063.93	332,071	98,080	80,818
King	180	277.77	5,742	2,706	2,230
Kittitas	49	234.52	4,848	97	80
Okanogan	1,825	309.75	6,403	14,617	12,044
Pend Oreille	15,096	8.22	170	1,552	1,279
Pierce	18			47	39
Skagit	14	.58	12	508	419
Snohomish	2,838	25.06	518	1,151	948
Stevens	82,043	181.74	3,757	161,013	132,675
Wahkiakum		3.87	80		
Whatcom	10,897	6,645.85	137,382	2,500	2,060
Yakima	7	1.65	34	34	28
	172,119	23,816.17	492,324	282,320	232,632

County.	Copper.		Lead.		Recoverable zinc.		Total value.
	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	
	Pounds.		*Pounds.*		*Pounds.*		
Chelan							$691
Clallam							628
Ferry	273,624	$74,699	1,395	$120			487,708
King	4,870	1,329					9,301
Kittitas	4,002	1,092					6,020
Okanogan	83,524	22,802	2,455	211			41,460
Pend Oreille	490	134	130,324	11,208	1,176,715	$120,025	132,816
Pierce	3,084	842					881
Skagit							431
Snohomish	180,948	49,399					50,865
Stevens	1,647,490	449,765	9,655,513	830,374	18,852	1,923	1,418,494
Wahkiakum							80
Whatcom							139,442
Yakima	1,486	406					468
	2,199,518	600,468	9,789,687	841,913	1,195,567	121,948	2,289,285

Digitized by Google

Ore sold or treated, deep mines producing, and average value of ores in Washington, in 1916 and 1917.

County.	Ore sold or treated, 1917.		Number of deep mines producing.		Average total value per ton.[a]		Average value per ton in gold and silver.[a]	
	Quantity.	Increase or decrease.	1916	1917	1916	1917	1916	1917
	Short tons.	*Short tons.*						
Asotin		− 1	1		$55.00		$28.00	
Chelan	21	− 1,288	5	4	6.55	$28.71	6.55	$28.71
Ferry	59,131	− 5,787	23	20	10.69	8.25	7.55	6.98
King	180	+ 131	1	1	35.02	51.67	35.02	44.29
Kittitas	49	+ 44	2	6	22.40	26.47	22.40	4.18
Okanogan	1,825	− 141	18	25	19.43	22.54	15.48	9.93
Pend Oreille	15,096	− 49	1	7	7.80	8.80		.09
Pierce	18	− 116	1	1	20.22	48.94	1.16	2.17
Skagit	14	+ 14		2		30.78		30.78
Skamania		− 8	1		49.25		9.88	
Snohomish	2,838	+ 740	4	7	35.33	17.89	.69	.48
Stevens	82,043	+13,228	30	39	14.08	17.29	1.80	1.66
Whatcom	10,897	+ 347	3	5	12.65	12.80	12.65	12.80
Yakima	7	+ 7		2		66.86		8.86
	172,119	+ 7,121	90	119	12.36	13.27	4.79	4.18

[a] Placer product excluded.

There were 17 active placer mines, of which 15 were worked by hydraulic and sluicing methods and 2 by drifting. Of the 119 deep mines, 8 produced gold; 35, gold and silver; 5, copper; 46, gold, silver, and copper; 2, silver; 3, gold, silver, and lead; 1, zinc; 15, silver and lead; 2, gold, silver, copper, and lead; 1, silver, lead, and zinc; and 1 gold, silver, copper, lead, and zinc.

REVIEW BY COUNTIES.

CHELAN COUNTY.

From 4 deep mines and 1 placer the county output was 21 tons of ore, $683 in gold, and 10 ounces of silver. This represents a decrease of $7,999 in gold and 167 ounces of silver. Information concerning the mining companies operating in this and other counties of the State is given in a recently published reference book,[1] which also gives short articles on the important mining districts.

Blewett district.—A small output of gold bullion came from the Ivanhoe property, principally from development work.

Entiat district.—A small shipment of siliceous gold ore was made, but the Rex mine, formerly a good producer, was idle.

CLALLAM COUNTY.

Placer gold valued at $624, with 5 ounces of silver, was produced near Ozette, Clallam County.

[1] Norman, Sidney, Northwest mines handbook, 1918.

Digitized by Google

FERRY COUNTY.

Mine production in Ferry County, Wash., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Total value.
		Short tons.		*Fine oz.*	*Pounds.*	*Pounds.*	
1916	25	64,918	$399,376	138,293	828,264	3,646	$694,378
1917	20	59,131	332,071	98,080	273,624	1,395	487,708
Decrease, 1917		5,787	67,305	40,213	554,640	2,251	206,670

There was a decided decrease in the quantity of ore mined and metals produced in Ferry County in 1917. Twenty deep-mine operators produced 59,131 tons of ore, a decrease of nearly 9 per cent from 1916. The value of the ore also decreased considerably, from $10.69 to $8.25 per ton. Only 10 tons was treated in gold and silver mills, and the remainder, 59,121 tons, having a value of $487,402, or $8.24 per ton, was shipped directly to smelters. Of the total output, 53,197 tons were siliceous ore, 5,933 tons were copper ore, and 1 ton was lead ore. Ferry County produced more than 67 per cent of the gold of the State, nearly 35 per cent of the silver, and 12 per cent of the copper.

Belcher district.—The Belcher mine was operated for a short time in 1917 and shipments of sulphide iron ore were made to Canadian smelters. The Laurier Mining Co. made a few shipments of sulphide copper ore. Formerly the output of both these properties was greater.

Curlew district.—Some old dump material, containing gold and silver, was shipped from the California property, and the Boston & New York group produced a small shipment of siliceous silver ore and one of copper ore.

Danville district.—Three deep mines produced 7,337 tons of ore, containing $22,263 in gold, 2,174 ounces of silver, and 242,942 pounds of copper, valued in all at $90,377, or an average value per ton of $12.32. In 1916 the district produced 18,436 tons of ore, valued at $198,199. All the ore was shipped without treatment and consisted of a copper sulphide ore from the Lone Star & Washington property and a siliceous gold ore from the Lucile Dreyfus mine, operated by the Virginia Mining Co.

Republic district.—Eleven deep mines produced 46,785 tons of ore, containing gold valued at $305,331 and 94,718 ounces of silver. The value of this ore was $383,379, or $8.19 per ton. Fourteen deep mines in 1916 produced 45,313 tons of ore, valued at $467,791. There was, therefore, a slight increase in the ore output, but a decided decrease in the value of the product. As this ore is used at the smelters primarily for its silica, some of it is shipped regardless of its low content of gold. With the exception of 10 tons milled, the entire output was shipped to various smelting plants. From 1896 to the end of 1917 the Republic district produced 469,043 tons of ore, yielding $6,421,686 in gold and 1,875,744 ounces of silver, valued together at $7,483,666. The largest producer of the district was, as formerly, the Lone Pine-Surprise-Pearl property, operated by the Northport

Digitized by Google

Smelting & Refining Co. In fact, more than half of the district output came from this property. The ore of the Knob Hill mine is of a much better grade, and though only about 6,000 tons of ore were shipped from the property, the content of gold was the largest production from the district. The company reported receipts of $102,143, from which dividends amounting to $34,784 were paid. The Last Chance mine, developed by a vertical shaft 530 feet deep, was an important producer. The ore was shipped to Tacoma. Development proceeded in a thorough manner at these mines, though work was affected by a shortage of labor. Other shippers were the Black Tail, Tom Thumb, Quilp, and Old Republic mines. The San Poil, formerly a considerable producer, shipped less than 1,000 tons. On November 15, 1917, a strike was called at the Trail smelter, and the plant was idle until late in December. Earlier in the year there were difficulties on account of a shortage of coke. Washington mines, and especially those at Republic, Chewelah, and Northport, are served by the following smelters: Canada Copper Corporation, Greenwood, British Columbia, copper plant, capacity 2,500 tons; Granby Consolidated Mining, Smelting & Power Co., Grand Forks, British Columbia, copper plant, 4,400 tons; Granby Consolidated Mining, Smelting & Power Co., Anyox, British Columbia, copper plant, 2,000 tons; Tacoma Smelting Co., Tacoma, Wash., copper plant, 2,500 tons; Northport Smelting Co., Northport, Wash., lead plant, 1,000 tons; Consolidated Mining & Smelting Co., Trail, British Columbia, lead plant, 350 tons, and copper plant, 1,800 tons; Ladysmith Smelting Corporation (Ltd.), Ladysmith, British Columbia, copper plant, 300 tons.

KING COUNTY.

Several shipments of arsenical pyrite, containing gold, silver, and copper, were made from the Apex mine, near Berlin. The ore also contained some lead, which was lost in a copper smelter.

KITTITAS COUNTY.

Six deep mines and 8 placers produced 49 tons of ore, $4,848 in gold, 97 ounces of silver, and 4,002 pounds of copper, valued in all at $6,020.

Cle Elum district.—The Mineral Creek Copper Co. and the Bonanza Copper Co. made shipments of sulphide copper ore.

Swauk district.—Three small deep mines and 8 placers had an output valued at $4,915. The 8 placers produced $4,658 in gold and 79 ounces of silver. The Ford placer and the Golden Rule group were the largest producers.

OKANOGAN COUNTY.

Twenty-five deep mines and 4 placers produced 1,825 tons of ore, $6,403 in gold, 14,617 ounces of silver, 83,524 pounds of copper, and 2,455 pounds of lead, valued in all at $41,460. There was a decrease in the quantity of ore treated and in the production of gold and silver. The total value of the ore increased from $19.43 per ton in 1916 to $22.54 in 1917, but the gold and silver value per ton decreased from

Digitized by Google

$15.48 to $9.93. Most of the ore, 1,735 tons, was shipped directly to the smelters and contained $4,442 in gold, 14,566 ounces of silver, 83,524 pounds of copper, and 2,455 pounds of lead, valued in all at $39,457, or $22.74 per ton. There were also 90 tons treated in gold and silver mills. The ore was classified as 1,167 tons of copper ore and 658 tons of siliceous ore.

Cascade district.—A shipment of rich silver ore was made from the Phil Sheridan property, operated by the Carey Mining & Milling Co., but only a small clean-up was made from the Bodie mine, formerly a fair producer.

Conconully district.—Production from the Arlington mine was small, only one shipment of siliceous silver ore having been made to Tacoma.

Meyers Creek district.—Eight deep mines and 1 placer produced 406 tons of ore, $2,951 in gold, 549 ounces of silver, and 11,378 pounds of copper, having a total value of $6,509. The production in 1916 was valued at $21,958. Nearly all the ore was shipped to smelting plants. The Eagle and the Reco properties produced a rich gold ore, and the Neutral and the Caribou properties copper ore.

Okanogan district.—There were four small producers in the district, but the Spokane mine, operated by the Morgan Mines Co., was the only one of importance. Two shipments of siliceous gold and silver ore were made during the year.

Palmer Mountain district.—Ten deep mines produced 1,225 tons of ore, containing $1,591 in gold, 5,690 ounces of silver, 69,619 pounds of copper, having a total value of $25,285, or $20.64 per ton. A new and considerable production of copper ore came from the Copper World Extension mine, near Loomis, and a better grade of ore, containing some gold and silver, came from the O. K. Copper property at Oroville. The Pyrargyritic Mining Co. produced several shipments of rich silver ore. Other producers were the 49th Parallel, Golden Chariot, and Pinnacle properties. A custom concentration plant, designed to treat 100 tons per day, was being constructed by the Bender Metals Milling Co. at Nighthawk.

PEND OREILLE COUNTY.

Metaline district.—Six deep mines produced 15,093 tons of ore, containing $170 in gold, 1,504 ounces of silver, 490 pounds of copper, 129,639 pounds of lead, and 1,176,715 pounds of recoverable zinc, valued in all at $132,717, or $8.79 per ton. Nearly all of this ore was milled, only 140 tons being shipped directly to the smelters. Most of the output came from the Josephine mine of the Lead Zinc Co., which operated a 175-ton concentration plant using tables and flotation. The main product was a zinc concentrate shipped to eastern smelters and to the electrolytic plant at Trail, British Columbia. Early in 1918 the company was in financial difficulties and all machinery was sold. Small shipments of lead ore were made from the Belle of May, Lead King, Metaline Consolidated, and Lead Queen mines. A test shipment of lead-zinc ore came from the Metaline Oriole property.

Newport district.—A small shipment of lead ore, containing considerable silver, was shipped from the Eagle mine.

Digitized by Google

PIERCE COUNTY.

Glacier Basin district.—The Mount Rainier Mining Co. made a shipment of sulphide copper ore.

Copper smelting and refining at the Tacoma plant were uninterrupted throughout the year. Custom ore from Washington mines is treated, but most of the ore comes from Alaska, South America, British Columbia, and the Western States.

SKAGIT COUNTY.

Small shipments of siliceous silver ore came from the Jackman Creek district, near Rockport.

SNOHOMISH COUNTY.

Seven deep mines and 1 placer produced 2,838 tons of ore, $518 in gold, 1,151 ounces of silver, and 180,948 pounds of copper, valued in all at $50,865. This production represents a general decrease. The ore which was shipped directly to smelters, had a value of $17.89 per ton, and was practically all copper ore.

Index district.—Four mines in this district produced almost all of the county output. The main producer was the Sunset property at Index, which was operated the entire year, and shipped sulphide copper ore. A 150-ton concentrator was being installed in the fall of 1917, but is not yet complete. A shipment of high-grade copper ore was made from the Bush & Curry mine.

Sultan district.—Aside from a small placer production, the principal producer was the Florence Rae Copper Co., which made one shipment of sulphide copper ore containing some silver.

STEVENS COUNTY.

Mine production in Stevens County, Wash., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc.	Total value.
		Short tons.		*Fine oz.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	30	68,815	$8,972	174,612	1,478,357	5,356,229	832,412	$968,666
1917	39	82,043	3,757	161,013	1,647,490	9,655,513	18,852	1,418,494
Increase or decrease, 1917	.....	+13,228	−5,215	−13,599	+169,133	+4,299,284	−813,560	+449,828

The output of ore and the quantity of copper and lead produced during the year increased, but the production of gold, silver, and zinc decreased. Thirty-nine deep mines produced 82,043 tons of ore, an increase of 13,228 tons. The value per ton increased from $14.08 in 1916 to $17.29 in 1917, but the gold and silver value decreased from $1.80 to $1.66 per ton. Most of the ore, or 58,720 tons, was milled and yielded 4,668 tons of concentrates valued at $364,213, or $78.02 per ton. The remainder, 23,279 tons, was shipped directly to

Digitized by Google

the smelters and had a total value of $1,053,497, or $45.25 per ton. Of the total output, 65,009 tons were copper ore, 16,299 tons lead ore, 657 tons siliceous ore, and 78 tons zinc ore.

Bossburg district.—The Young America mine, near Bossburg, made a shipment of low-grade zinc ore to the leaching plant at Great Falls, Mont. The Bonanza mine continued to make shipments of lead ore, which was mined by lessees.

Cedar Canyon district.—Four deep mines produced 913 tons of ore, $326 in gold, 5,098 ounces of silver, and 121,372 pounds of copper, valued in all at $37,662, or $41.25 per ton. Shipments of copper ore came from the Turk mine, operated by the High Grade Mining Co., and several shipments of silver ore came from the Silver Queen property.

Chewelah district.—From 1901 to the end of 1917 this district has produced 203,187 tons of ore, yielding $62,330 in gold, 952,679 ounces of silver, 5,816,437 pounds of copper, and 265,139 pounds of lead, having a total value of $1,834,159. Ten deep mines in 1917 produced 62,436 tons of ore, containing $1,508 in gold, 150,137 ounces of silver, and 1,212,608 pounds of copper, valued in all at $456,263, or $7.31 per ton. Of the ore, 58,720 tons were concentrated and 3,716 tons were shipped to various smelters. The crude ore shipped contained 25.95 ounces of gold, 28,943 ounces of silver, and 247,858 pounds of copper. The United Copper Co. remained the most important producer in the district. Shipments were also made from the Amazon, B. & B., Browns Lake, and Copper King mines. The following notes regarding the United Copper and Copper King mines are taken from the printed report.[1]

The year 1917 was a very trying one for the United Copper Mining Co., owing to fluctuating metal prices, labor strikes, increased operating costs, and the heavy loss we sustained through being compelled to ship our product to the Tacoma smelter through a greater part of the year. * * *

A labor strike in the British Columbia coal fields in March compelled the Trail smelter to discontinue smelting copper ore on account of failure of coke supply. From March 15 to September 15 our shipments went to the Tacoma smelter, but the settlement basis was not as favorable as our contract at Trail, resulting in a heavy loss to our company during this period.

In July our mine employees called a strike for higher wages, which we could not afford to pay, and it was several weeks before we were able to secure full crews again. In September we renewed our shipments to the Trail smelter, but on November 14 their smelter employees walked out on strike and our shipments were again diverted to the Tacoma smelter. * * *

But with all the handicaps, we are able to report most encouraging progress for the year. The 2-compartment shaft which was started at the close of 1916 has been sunk to the 1,300 level, that is, 300 feet below the 1,000 level, where a big hoisting station has been cut out. Drifts and raises have been run on each 100-foot level as the shaft was sunk, and very good ore is found at all points.

The Copper King mine, adjoining the United Copper on the north, has been acquired on a working bond at a price and on terms that will permit of making all payments from the earnings from the King ores, and will require no money to be diverted from the United Copper earnings. * * *

To meet the imperative demands on our milling capacity to handle a much greater tonnage of our low-grade ores it was found necessary to install additional equipment, and our two mills can now handle from 350 to 400 tons daily throughout the coming year.

A summary of the available ore gives 293,985 tons for the United Copper mine and 100,000 tons for the Copper King mine, from which

[1] United Copper Mining Co. Twelfth Ann. Rept., for year ending Dec. 31, 1917.

Digitized by Google

the estimated yield is 714,190 ounces of silver and 10,101,320 pounds of copper. The mine produced 1,147,014 pounds of copper and 147,573 ounces of silver, and the gross smelter returns were $354,372. Mining and milling cost $198,756; freight, $23,490; and treatment, $18,453. Dividends paid in 1917 amounted to $100,000, but the indebtedness at the end of the year was $61,577.

Clugston Creek district.—A test shipment of lead ore from the Neglected group was made to the Northport smelter.

Colville district.—A small output of slag was shipped from the Old Dominion smelter dump.

Loon Lake district.—Shipments of a good grade of copper ore were continued from the Loon Lake property in 1917. The operations were somewhat hampered by the labor troubles at the Canadian smelters. The shaft was sunk from the 200-foot to the 500-foot level and about 700 feet of drifts were run. Dividends in 1917 amounted to $43,352. Early in 1918 the company planned a concentration mill.

Marcus district.—The Napoleon mine, formerly an important producer, made only a few shipments of iron sulphide ore, to be used as a flux at the plant of the Canada Copper Co., at Greenwood, B. C. There was a decrease of several thousand tons of ore from the shipments made in 1916.

Northport district.—Ten deep mines produced 15,789 tons of ore, $74 in gold, 3,248 ounces of silver, 535 pounds of copper, and 9,465,046 pounds of lead, valued in all at $816,890, or $51.74 per ton. This was a decided increase from 10,223 tons of ore, valued at $45.16 per ton, in 1916. Several prospects in the district developed into shipping mines during the year. The largest production and the main increase came from the Electric Point mine, but a good production also came from the Gladstone property. Smaller shipments were made from the Coyote, W. J. Bryan, Iroquois, Lead Trust, and United Treasure mines. The Great Western and Last Chance mines, formerly operated by the Norman Mines Co., on lease, were idle during 1917. This accounts for the decrease in shipments of lead-zinc ore from the county. The Electric Point mine was operated at a loss in 1916, but in 1917 the company received $553,523 from the sale of ore. Dividends paid amounted to $166,687, including $86,558 paid from capital. The following paragraphs are taken from the printed statement.[1]

> Our engineers estimate that on December 31, 1917, we had 15,000 tons of ore blocked out. Since December 31, 1917, we have reached the 700-foot level and opened up a fine body of ore.
>
> We are expecting to build a tramway as soon as possible, to cost not to exceed $50,000.
>
> We have not paid any dividends since September 30, 1917, and have not shipped any ore since November 1, 1917, as we were behind with our development work and may have to use the surplus to provide transportation facilities.

Most of the ore is oxidized, though shipments of high-grade galena were also made. The mine is opened by shaft to the 700-foot level.

The Northport Smelting & Refining Co. operated three blast furnaces on lead ore, treating material from the Hercules mine at Burke, Idaho, and the Tamarack and Custer mines at Sunset, Idaho, and siliceous ore from Republic and custom ore from other mines. The plant is credited with a production of 45,000 tons of lead bullion

[1] Electric Point Mining Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

in 1917, and a charge of 400,000 tons for the year. To reduce the loss of metals in the fumes a Cottrell precipitating plant was installed during the year.

Orient district.—A small shipment of rich gold ore was made from the F. H. C. mine and of lead ore from the Old Tenderfoot property.

Spokane Indian Reservation district.—Initial shipments of copper ore were made from the O-Lo-Lim copper mine near Miles, Wash. The property was operated about seven months and is opened by a 100-foot shaft.

Springdale district.—The Copper Butte property made a few test shipments of very low-grade copper ore. Small shipments were also made from the Golden Seal and Rambler properties.

Valley district.—A shipment of sulphide copper ore was made from the Admiral property and an oxidized copper ore from the Edna mine, operated by the Valley Mining Co.

WAHKIAKUM COUNTY.

Some placer gold was shipped from the vicinity of Grays River.

WHATCOM COUNTY.

Five deep mines produced 10,897 tons of siliceous ore, containing $137,382 in gold and 2,500 ounces of silver, having a total value of $139,442. Compared with 1916, this was a slight increase in both the quantity of ore treated and the amount of gold recovered. Most of the ore was treated by amalgamation, only 42 tons having been shipped directly to the smelters.

Mount Baker district.—The entire county production came from this district. The Boundary Red Mountain Mining Co. continued to treat gold ore at its 10-stamp mill equipped from amalgamation. The mine is opened by two adits, one 500 feet and the other 1,300 feet long. The Lone Jack mine of the Boundary Gold Co. also treated several hundred tons of ore by amalgamation.

YAKIMA COUNTY.

A small test shipment of copper ore was made from the Red Bird mine in Bumping Lake district.

Digitized by Google

Digitized by Google

GOLD, SILVER, COPPER, LEAD, AND ZINC IN ARIZONA.[1]

(MINES REPORT.)

By V. C. HEIKES.

PRODUCTION.

GENERAL STATEMENT.

The mines of Arizona produced in 1917 gold, silver, copper, lead, and recoverable zinc contained in bullion, ore of shipping grade, and concentrates and valued at $209,393,802. The value of the output, compared with that of 1916, increased $18,587,632, or 9.74 per cent. There were 452 producers from deep mines and 32 producers from placers, as against 504 deep-mine and 23 placer producers in 1916. The increase in the value of the metal output in 1917 was principally in copper; there was also an increase in the value of gold, silver, and lead. Dividends were paid in 1917 by 18 companies and amounted to $47,216,611. This does not include dividends from the Copper Queen mine, which were included in the combined dividends, amounting to $10,800,000, of the Phelps-Dodge Corporation, operating in Arizona, Mexico, and New Mexico.

Mine production of gold, silver, copper, lead, and recoverable zinc in Arizona in 1916 and 1917.

Year.	Number of producers	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead.	Recoverable zinc content.	Total value.
		Short tons.		*Fine oz.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	527	17,033,810	$3,985,559	7,212,039	721,833,169	27,062,087	19,677,949	$190,806,170
1917	484	15,770,193	5,068,193	6,983,913	712,166,891	23,465,445	20,894,860	209,393,802
Increase or decrease, 1917..	−43	−1,263,617	+1,082,634	−228,126	−9,666,278	−3,596,642	+1,216,911	+18,587,632

[a] Includes placer production.

ORE.

The production of 15,770,193 short tons of ore in 1917 was 1,263,617 tons less than the output in 1916. The total average value per ton increased from $11.20 in 1916 to $13.28 in 1917, and the gold and silver value per ton increased from 51 cents to 69 cents. The dry or siliceous ores decreased from 336,304 tons in 1916 to 317,716 tons in 1917. This classification includes 236,585 tons of siliceous gold ore, averaging $11.25 in gold, 1.27 ounces of silver, 2.6 pounds of cop-

[1] The statistical tables in this report were compiled by Bessie N. Patchell, of the United States Geological Survey.

Digitized by Google

per, and 1.14 pounds of lead to the ton. These ores were principally from Mohave, Yavapai, and Cochise counties. There was only 1 ton of siliceous material classified as gold and silver ore. The siliceous silver ores produced in 1917 aggregated 80,817 tons, averaging per ton 82 cents in gold, 6.75 ounces of silver, 2.75 pounds of copper, and 0.49 pound of lead. These ores were produced chiefly in the Turquoise and Tombstone districts of Cochise County.

The copper ore mined by 258 producers aggregated 15,245,297 tons, against 16,491,971 tons mined by 272 producers in 1916. The larger part of the copper ore mined, or 9,976,461 tons, was from low-grade disseminated deposits near Globe, Ray, and Ajo, where most of the ore was treated. The richer siliceous ore or that valuable as converter lining was shipped to various smelters. There was also similar disseminated ore, 1,213,197 tons in quantity, mined and milled from the low-grade copper deposits in the Clifton and Morenci camps of Greenlee County. Altogether the output of disseminated ores aggregated 11,189,658 tons and yielded 284,100,353 pounds of copper, or nearly 40 per cent of the total output of the State. There were mined and smelted directly (without previous concentration) 3,679,576 tons of crude copper ores, averaging 46 cents in gold and 1.17 ounces of silver per ton and 5.58 per cent of copper, with an average value of $31.86 a ton, against 3,701,716 tons in 1916, with an average value of $26.86 a ton. Of the copper ores smelted directly, 2,771,597 tons were sulphides, averaging 57 cents in gold and 1.36 ounces of silver per ton and 6.13 per cent of copper and having an average value of $35,18 a ton. The oxidized copper ore smelted, 907,979 tons in quantity, contained 12 cents in gold and 0.59 ounce of silver per ton and 3.87 per cent of copper and was valued at $21.74 a ton. There was a decrease in the quantity of lead ores smelted, which amounted to 45,940 tons in 1917, against 46,930 tons in 1916. The larger part, or 40,566 tons, was oxidized, and 5,374 tons was sulphide ore. The oxidized ores contained $2.41 in gold and 11.25 ounces of silver per ton, 0.76 per cent of copper, and 16.96 per cent of lead and had a total average value of $45 a ton. The sulphide lead ores contained $1.89 in gold and 15.85 ounces of silver per ton, 0.98 per cent of copper, and 18.42 per cent of lead. The quantity of zinc ores mined increased from 52,652 tons in 1916 to 62,839 tons in 1917. Of this ore, 5,190 tons, mainly sulphide ores, were shipped crude to smelters. The remainder of the zinc ore was concentrated and yielded 11,627 tons of concentrate. The lead-zinc ore amounted to 49,071 tons, of which 2,051 tons, mostly sulphide crude ore, was shipped to smelters, and 47,020 tons of ore were concentrated and yielded 13,145 tons of zinc concentrate, 9,300 tons of lead concentrate, and 382 tons of lead-zinc concentrate. The copper-lead ore, all of which was shipped to the smelter, amounted to 1,610 tons in quantity. The larger part (965 tons) was sulphide, there being only 645 tons classified as oxidized. The sulphide ores contained 46 cents in gold and 20.70 ounces of silver per ton, 4.66 per cent of copper, and 11.54 per cent of lead and had an average value of $62.53 a ton. There were 6,832 tons of copper-zinc ore and 4,543 tons of old tailings concentrated, which yielded 1,523 tons of copper concentrate, 524 tons of copper-zinc concentrate, and 740 tons of zinc concentrate.

Digitized by Google

Ore and metals produced in Arizona in 1917.

Source of production.	Number of producers	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc content.
		Short tons.	*Fine oz.*	*Fine oz.*	*Pounds.*	*Pounds.*	*Pounds.*
Placers	32	.....	832.73	227	.....	.....	.....
Dry or siliceous ore	121	317,716	131,997.57	848,500	829,737	309,219	.....
Copper ore	258	15,245,297	98,530.97	5,214,411	710,067,644	60,287	.....
Lead ore	86	82,285	5,739.02	553,544	728,779	16,239,714	.....
Zinc ore	8	62,839	4,078.35	116,179	143.193	181,420	10,618,248
Copper-lead ore	12	1,610	54.76	33,647	141.130	432,484	.....
Lead-zinc ore	8	49,071	2,352.86	190,033	58,057	6,161,811	9,476,718
Copper-zinc ore	2	11,375	1,587.57	27,372	200,351	30,510	799,894
	.....	15,770,193	245.173.83	6,983,913	712,166,891	23,465,445	20,894,860

Ore sold or treated in Arizona in 1917, in short tons.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-lead ore.	Lead-zinc ore.	Copper-zinc. ore.	Total.
Cochise	95,248	1,784,050	34,071	.....	29	1,535	.....	1,914,933
Coconino	.....	1,511	.....	.....	.....	.....	.....	1,511
Gila	147	6,048,653	688	52	4	.....	.....	6,049,544
Graham	36	10,745	1,766	.....	27	.....	.....	12,574
Greenlee	57	1,431,061	.....	.....	.....	.....	.....	1,431,118
Maricopa	615	916	21	.....	.....	.....	.....	1,552
Mohave	168,376	3,162	2,084	58,163	.....	43,780	.....	275,565
Pima	851	992,422	1,619	44	457	516	.....	995,909
Pinal	4,489	3,761,484	32,531	18	209	.....	.....	3,798,731
Santa Cruz	128	47,708	3,843	4,027	876	3,240	5,057	64,879
Yavapai	47,363	1,120,448	1,980	535	.....	.....	6,318	1,176,644
Yuma	406	43,137	3,682	.....	8	.....	.....	47,233
Value per ton in gold and silver	[a]317,716 $10.79	15,245,297 $0.41	82,285 $6.98	62,839 $2.86	1,610 $17.92	49,071 $4.18	11,375 $4.87	15,770,193 $0.68

[a] Includes 236,585 tons of gold ore, 1 ton of gold and silver ore, 80,817 tons of silver ore, and 313 tons of iron ore.

GOLD.

In 1917 Arizona ores, placer dust, and bullion yielded 245,173.83 ounces of gold, valued at $5,068,193. Of this value, $17,214, against $14,281 in 1916, came from placers; $2,728,632, against $1,517,616 in 1916, came from dry or siliceous ore; and $2,036,816, against $2,180,211 in 1916, came from copper ores. The mines of Mohave County produced the largest output of gold—$2,463,178 in 1917, against $1,038,814 in 1916. Cochise County was second, with a production of $1,149,782, against $1,514,811 in 1916. The United Eastern and Tom Reed mines were the largest contributors in Mohave County, the Calumet & Arizona and Copper Queen in Cochise County, and the United Verde and Copper Chief in Yavapai County. Gold recovered from ores treated in gold and silver mills represented about 49 per cent of the total production, and crude ores shipped to smelters about 39 per cent. From ores treated in mills by amalgamation the gold recovered amounted to $38,759, and that from ores treated by cyanidation to $2,455,019. Concentrates contained $542,446, as against $405,500 in 1916, and ores shipped directly to smelters contained $2,003,570, against $2,129,500 in 1916. The chief producing districts in 1917 were the San Francisco district in Mohave County, where siliceous gold ores were pro-

Digitized by Google

duced; the Warren district in Cochise County, where copper ores were produced, and the Verde district in Yavapai County, producing both siliceous and copper ore.

Of the mines producing gold in 1917 the United Eastern, at Oatman, was first, with 86,629.41 ounces from siliceous ore. The United Verde Copper mine was second, followed by the Calumet & Arizona, at Bisbee, the Tom Reed, at Oatman, the Copper Queen, at Bisbee, the Blue Bell, in Yavapai County, and the Magma, in Pinal County. Altogether these seven properties yielded about 80 per cent of the total gold.

Mine production of gold in Arizona in 1917, in fine ounces.

County.	Placers.	Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-lead ore.	Lead-zinc ore.	Copper-zinc ore.	Total.
Cochise	.....	4,085.48	48,550.97	2,984.45	.....	.....	.....	.....	55,620.70
Coconino	.....	.....	1.11	.....	.....	.....	.....	.....	1.11
Gila	.....	63.14	5,669.66	402.69	.....	.....	.....	.....	6,135.49
Graham	.....	26.30	13.56	12.95	.....	2.00	.....	.....	54.81
Greenlee	.....	23.02	2,527.99	.....	.....	.....	.....	.....	2,551.01
Maricopa	149.38	1,136.66	256.99	3.28	.....	.....	.....	.....	1,546.31
Mohave	.....	112,251.83	45.78	599.34	4,073.00	.....	2,186.29	.....	119,156.24
Pima	231.14	54.29	55.01	3.68	.....	21.26	.....	.....	365.38
Pinal	.....	92.09	7,235.12	580.96	.....	4.00	.....	.....	7,912.17
Santa Cruz	.....	9.67	33.95	14.00	.....	27.50	166.57	.....	251.69
Yavapai	181.99	13,698.53	32,899.37	1,137.26	5.35	.....	.....	1,587.57	49,510.07
Yuma	270.22	556.56	1,241.56	.41	.....	.....	.....	.....	2,068.85
	832.73	[a]131,997.57	98,530.97	5,739.02	4,078.35	54.76	2,352.86	1,587.57	245,173.83

[a] Includes 128,801.16 ounces from gold ore, 3.62 ounces from gold and silver ore, and 3,192.79 ounces from silver ore.

SILVER.

Silver produced from mines in Arizona decreased from 7,212,039 ounces in 1916 to 6,983,913 ounces in 1917. The value, however, increased from $4,745,522 to $5,754,744 on account of the increased price of the metal. Of this output, 5,214,411 ounces came from copper ore, 848,500 ounces from dry or siliceous ore, 553,544 ounces from lead ore, 190,033 ounces from lead-zinc ore, and smaller quantities from zinc, copper-lead, and copper-zinc ores. The greatest increase of silver was in Yavapai, Santa Cruz, Pinal, and Mohave counties, principally from copper ores. Bullion recovered from gold and silver ores, principally by cyanidation (252,652 ounces), yielded 254,353 ounces of silver in 1917. Concentrates contained 1,271,890 ounces, and crude ore shipped to smelters contained 5,312,292 ounces, representing more than 76 per cent of the total output. Cochise County mines led in output of silver, producing 2,707,220 ounces of silver in 1917, against 3,709,225 ounces in 1916, 3,034,714 ounces in 1915, 2,753,953 ounces in 1914, and 2,127,171 ounces in 1913. Yavapai County produced 2,207,583 ounces of silver in 1917, against 1,735,302 ounces in 1916.

Nearly half of the total silver came from the ore of four important copper properties. The United Verde was first in 1917, followed by the Calumet & Arizona and the Copper Queen, both at Bisbee, and the Magma, in Pinal County.

Digitized by Google

Mine production of silver in Arizona in 1917, in fine ounces.

County.	Placers.	Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-lead ore.	Lead-zinc ore.	Copper-zinc ore.	Total.
Cochise	.....	522,668	1,806,240	378,263	.....	29	.....	.....	2,707,220
Coconino	.....	.....	4,576	.....	.....	.....	.....	.....	4,576
Gila	.....	19,092	476,816	5,147	.....	865	.....	.....	501,920
Graham	.....	1,212	3,031	28,886	.....	195	.....	.....	33,324
Greenlee	.....	704	82,754	.....	.....	.....	.....	.....	83,458
Maricopa	24	490	2,198	42	.....	.....	.....	.....	2,754
Mohave	.....	75,363	4,770	26,773	90,104	.....	173,084	.....	370,094
Pima	120	358	145,801	13,863	.....	7,492	.....	.....	167,634
Pinal	.....	532	665,436	4,900	.....	9,071	.....	.....	679,939
Santa Cruz	.....	8,572	111,500	35,380	23,507	15,446	16,949	7,429	218,783
Yavapai	22	218,971	1,909,194	56,885	2,568	.....	.....	19,943	2,207,583
Yuma	61	518	2,095	3,405	.....	549	.....	.....	[a] 6,628
	227	[a]848,500	5,214,411	553,544	116,179	33,647	190,033	27,372	6,983,913

[a] Includes 302,808 ounces from gold ore, 114 ounces from gold and silver ore, and 545,578 ounces from silver ore.

COPPER.

The production of copper from Arizona mines amounted to 712,166,891 pounds, valued at $194,421,561, in 1917, against 721,833,169 pounds, valued at $177,570,960, in 1916. There was, therefore, a decrease of 9,666,278 pounds in quantity and an increase of $16,850,601 in value. Crude ore shipped directly to the smelters yielded 412,030,793 pounds, or nearly 58 per cent of the total quantity, against 385,569,908 pounds in 1916. Of the output from crude ore smelted in 1917, Cochise County produced about 43 per cent. Yavapai, Gila, Pima, Greenlee, and Pinal counties also produced large quantities. The copper in concentrates produced at milling plants decreased from 331,133,062 pounds in 1916 to 282,146,701 pounds in 1917. This decrease was due principally to labor strikes in Gila and Cochise counties. Gila County, including the Globe and Miami districts, produced altogether 141,554,598 pounds in concentrates, against 189,299,027 pounds in 1916, 77,085,710 pounds in 1915, 73,488,162 pounds in 1914, 71,609,847 pounds in 1913, 63,969,423 pounds in 1912, and 49,226,341 pounds in 1911. The low-grade disseminated ores in Pima, Pinal, and Gila counties yielded 146,547,980 pounds of copper, against 244,675,654 pounds in 1916, 124,264,911 pounds in 1915, 95,485,293 pounds in 1914, 87,073,406 pounds in 1913, 68,753,553 pounds in 1912, and 30,666,515 pounds in 1911. Similar low-grade copper deposits exist in Greenlee County, whose output added made the total production from the disseminated deposits in Arizona 284,100,353 pounds, or nearly 40 per cent of the aggregate output in 1917. In 1916 these ores altogether produced 299,704,303 pounds of copper.

Thirteen properties produced about 88 per cent of the total quantity of copper, each of them yielding over 10,000,000 pounds. The Copper Queen, at Bisbee, was first, with 93,618,409 pounds, followed by the Ray Consolidated, in Pinal County, with 88,582,649 pounds; Inspiration, at Globe, with 80,566,982 pounds; and United Verde, in Yavapai County. Those closely following were the United Verde Extension, Calumet & Arizona, Miami Copper, Arizona Copper, Old Dominion, New Cornelia, Detroit Copper, Shattuck, and Magma.

Digitized by Google

Mine production of copper in Arizona in 1917, in dry pounds.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-lead ore.	Lead-zinc ore.	Copper-zinc ore.	Total.
Cochise	216,409	176,093,792	502,938	.....	1,842	.....	.....	176,814,981
Coconino	.....	346,538	.....	.....	.....	.....	.....	346,538
Gila	.....	175,380,380	2,099	.....	1,147	.....	.....	175,383,626
Graham	283	420,660	66,903	.....	1,418	.....	.....	489,264
Greenlee	143	53,072,187	.....	.....	.....	.....	.....	53,072,330
Maricopa	188	81,090	127	.....	.....	.....	.....	81,405
Mohave	2,321	828,211	12,141	.....	.....	55,300	.....	897,973
Pima	.....	34,782,224	56,963	.....	38,256	.....	.....	34,877,443
Pinal	.....	102,877,626	2,600	.....	32,166	.....	.....	102,912,392
Santa Cruz	2,746	3,693,677	81,266	137.843	65,756	2,757	117,131	4,101,176
Yavapai	602,738	158,919,096	1,742	5,350	.....	.....	83,220	159,612,146
Yuma	4,909	3,572,163	.....	.....	545	.....	.....	3,577,617
	a829,737	710,067,644	726,779	143,193	141,130	58,057	200,351	712,166,891

a Includes 604,040 pounds from gold ore, 222,566 pounds from silver ore, and 3,131 pounds from iron ore.

LEAD.

The mine production of lead in Arizona in 1917 was 23,465,445 pounds, valued at $2,018,028, against 27,062,087 pounds, valued at $1,867,284, in 1916, a decided decrease in quantity but an increase in value. Cochise County, principally the Warren or Bisbee district, although responsible for the decrease in quantity, had the largest yield of lead, or 11,262,440 pounds, valued at $968,570, as against 15,902,137 pounds, valued at $1,097,247, in 1916. Mohave County followed with 6,141,246 pounds, Santa Cruz County with 1,839,390 pounds, and Graham County with 1,488,711 pounds. Concentrates derived from low-grade ores produced 6,751,858 pounds of lead, and crude ores shipped directly to smelters produced 16,713,587 pounds.

Five properties produced about seven-tenths of the lead, the Copper Queen, at Bisbee, leading with 6,870,128 pounds, followed closely by the Tennessee, at Chloride, and by lesser quantities from the Shattuck-Arizona, at Bisbee, the Grand Reef, in Graham County, and the Bunker Hill, at Tombstone.

Mine production of lead in Arizona in 1917, in dry pounds.

County.	Dry or siliceous ore.	Copper ore.	Lead ore.	Zinc ore.	Copper-lead ore.	Lead-zinc ore.	Copper-zinc ore.	Total.
Cochise	260,609	903	10,795,424	.....	4,433	201,071	.....	11,262,440
Gila	1,176	418	184,804	.....	817	.....	.....	187,215
Graham	.....	.....	1,473,075	.....	15,636	.....	.....	1,488,711
Maricopa	1,715	31,907	12,110	.....	.....	.....	.....	45,732
Mohave	11,303	.....	770,079	.....	.....	5,359,864	.....	6,141,246
Pima	.....	.....	518,191	.....	117,064	51,764	.....	687,019
Pinal	.....	26,212	822,690	.....	76,579	.....	.....	925,481
Santa Cruz	9,991	207	888,874	160,020	217,176	549,112	14,010	1,839,390
Yavapai	24,425	640	623,909	21,400	.....	.....	16,500	686,874
Yuma	.....	.....	200,558	.....	779	.....	.....	201,337
	a309,219	60,287	16,289,714	181,420	432,484	6,161,811	30,510	23,465,445

a Includes 269,441 pounds from gold ore and 39,778 pounds from silver ore.

Digitized by Google

ZINC.

The mine output of recoverable zinc from Arizona zinc-bearing ores in 1917 amounted to 20,894,860 pounds, valued at $2,131,276, against 19,677,949 pounds, valued at $2,636,845, in 1916. There was an increase of more than 6 per cent in quantity but a decrease in the value of the output on account of the lower price of zinc. Most of the zinc ore and lead-zinc ore was mined in Mohave County at Union Pass and Chloride. Santa Cruz and Yavapai counties contributed zinc from both zinc ore and copper-zinc ore. Ores milled yielded 17,817,501 pounds of zinc from concentrates, the remainder being from first-class or shipping ore. Smaller quantities of ore containing zinc were mined in Cochise, Pima, Pinal, and Gila counties.

The three large producers of zinc in Arizona were the Golconda and Tennessee mines, in Mohave County, and the Duquesne mine, in Santa Cruz County. These properties yielded nearly 87 per cent of the total in 1917.

Mine production of recoverable zinc in Arizona, in 1917, in dry pounds.

County.	Zinc ore.	Lead-zinc ore.	Copper-zinc ore.	Total.
Cochise		608,443		608,443
Gila	35,333			35,333
Mohave	8,664,101	8,485,099		17,149,200
Pima	19,171	175,440		194,611
Pinal	11,322			11,322
Santa Cruz	1,465,919	207,736	271,534	1,945,189
Yavapai	422,402		528,360	950,762
	10,618,248	9,476,718	799,894	20,894,860

Zinc ore and concentrate from Arizona mines and mills sold in 1917.

Classification.	County.	Quantity.	Average assay of ore and concentrate.[a]
		Short tons.	*Per cent of zinc.*
Sulphide zinc ore	Mohave, Santa Cruz, and Yavapai	4,898	25.38
Sulphide lead-zinc ore	Cochise	1,473	23.04
Oxidized zinc ore	Gila, Pima, Pinal, and Santa Cruz	292	36.35
Oxidized lead-zinc ore	Cochise and Pima	578	21.07
Zinc concentrates	Mohave and Yavapai	25,512	39.90
Lead-zinc concentrates	Mohave and Santa Cruz	382	37.05
Copper-zinc concentrates	Santa Cruz	524	30.48
		33,659	36.51

[a] Actual assay content.

MINING INDUSTRY.

Miners working in the copper mines of Arizona demanded higher pay, making their first request in November, 1916, of the New Cornelia Copper Co., at Ajo, which had not started its newly erected electrolytic copper plant. This labor strike was settled in January,

Digitized by Google

1917, and was followed the last of May by similar trouble at Jerome. Further agitation was started at Bisbee in June and in the Globe-Miami district in July, causing the mines in the latter district to close for seven weeks. By this closing of the mines in the Globe-Miami district, there was a decrease in copper output of more than 15,000,000 pounds a month and in other districts a curtailment of production that greatly affected the total output of the metal. However, much of this decrease in copper was offset by the New Cornelia Co., which began to produce heavily in June and continued for the next six months with an average of about 3,000,000 pounds of copper a month. To this amount was added the increased copper output of the Imperial mine, at Silver Bell, the Magma mine, at Superior, and the important new producers at Stoddard, in Yavapai County. These activities prevented a greater decrease in copper.

There were 11 copper-smelting plants in operation in 1917, as follows: Copper Queen and Calumet & Arizona, at Douglas; Sasco smelter, near Silver Bell; American Smelting & Refining Co., at Hayden; Consolidated Arizona, at Humboldt; International, at Miami; Old Dominion, at Globe; Detroit, at Morenci; Arizona Copper and Shannon, at Clifton; and United Verde, at Clarkdale. The United Verde Extension has designed a smelting plant equipped with blast furnaces and converters for the treatment of its ore. This plant was completed in 1918.

REDUCTION MILLS.

Forty-nine milling plants of various kinds were in operation in Arizona in 1917, but only a few continuously. Two mills used straight amalgamation; 4, amalgamation and concentration; 1, amalgamation and cyanidation; 7, only cyanidation; 2, amalgamation, concentration, and cyanidation; 28, concentration, of which 8 were equipped for table concentration only, 18 for table and flotation concentration, and 2 for straight flotation only. In addition there were 2 leaching plants and 3 precipitating plants recovering copper from solutions. A list giving all the mills in commission, including many new plants under construction in 1911 and 1912, was published in Mineral Resources for 1911, Part I, page 426.

The ore treated in 1917 by amalgamation amounted to 21,100 tons and produced 1,874.99 ounces of gold and 1,701 ounces of silver, an average recovery per ton of $1.84 in gold and 0.08 ounce in silver. Ores treated by cyanidation amounted to 222,669 tons, which, with 22,709 tons of old tailings, produced 118,761.54 ounces of gold and 252,652 ounces of silver, or an average recovery per ton from ore and tailings of $10 in gold and 1.03 ounces of silver. The total value of the bullion recovered from ore and tailings was $2,703,365, as against $1,858,983 in 1916. During 1917 there were 205 pounds of quicksilver and 157,961 pounds of sodium cyanide consumed at milling plants. This corresponds to 0.057 pound of mercury per ounce of gold and silver and 0.01 pound of mercury per ton of ore treated. The consumption of cyanide was 0.43 pound per ounce of gold and silver and 0.64 pound per ton of ore and tailings treated.

Digitized by Google

Gold and silver produced at mills in Arizona in 1917.

County.	Ore.	Bullion recovered from ore by—				Total value.
		Amalgamation.		Cyanidation.		
		Gold.	Silver.	Gold.	Silver.	
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Fine ounces.*	*Fine ounces.*	
Cochise	[a] 53,758	437.41	880	1,568.55	141,952	$159,161
Gila	37	55.61	90			1,224
Graham	8	4.30	2			91
Greenlee	27	19.02	6			398
Maricopa	428	474.43	315			10,067
Mohave	[b] 167,518	167.66	99	[c] 112,015.11	[c] 57,378	2,366,385
Pima	70	46.50	22			979
Pinal	2	[d] 91.14	[d] 135			1,995
Santa Cruz	6	4.10	5			89
Yavapai	[e] 21,886	551.67	133	[f] 5,177.88	[f] 53,322	162,487
Yuma	29	23.15	14			489
	243,769	1,874.99	1,701	118,761.54	252,652	2,703,365

[a] Also yielded 1,739 tons of concentrate.
[b] Also yielded 1 ton of concentrate.
[c] Includes bullion from 499 tons of old tailings.
[d] Includes bullion from 4,480 tons of old tailings.
[e] Also yielded 57 tons of concentrate.
[f] Includes bullion from 17,730 tons of old tailings.

Concentration plants reduced 10,943,997 tons of ore to 783,832 tons of concentrates, which were shipped to smelters and produced $542,446 in gold, 1,271,890 ounces of silver, 282,146,701 pounds of copper (or nearly 40 per cent of the total output of copper in the State), 6,751,858 pounds of lead, and 17,817,501 pounds of recoverable zinc, valued in all at $81,014,577, a total average value per ton of $103.35. Copper concentrates amounting to 745,123 tons comprised more than 95 per cent of the total concentrates produced.

Mine production of metals from Arizona concentrates in 1917.

By counties.

County.	Ore to concentrating mills.	Concentrates produced.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc content.	Total value of concentrates.
	Short tons.	*Short tons.*	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
Cochise	6,102	2,261	559.29	52,260	65,493	356,520		$103,163
Gila	5,730,268	277,910	3,431.65	232,993	141,554,598			38,907,329
Graham	9,024	564	1.01	340	246,298			67,540
Greenlee	1,268,783	164,371	2,041.70	65,629	40,067,614			11,040,208
Mohave	76,397	33,801	6,243.92	265,622	55,542	5,454,404	16,809,871	2,546,795
Pima	779	58		220				181
Pinal	3,685,395	261,987	6,268.18	462,974	91,011,649	58,442		25,362,272
Santa Cruz	21,299	2,729	174.57	25,892	468,482	707,442	479,270	262,565
Yavapai	143,811	39,996	7,520.51	163,957	8,657,025	28,465	528,360	2,710,273
Yuma	2,139	155		2,003		146,585		14,256
	10,943,997	783,832	26,240.83	1,271,890	282,146,701	6,751,858	17,817,501	81,014,577

By kinds of concentrates.

Dry or siliceous	102	58.48	906	284				$2,032
Copper	745,123	18,646.92	922,052	282,020,820				78,136,921
Lead	12,189	2,629.76	201,406	64,117	6,676,631			812,014
Zinc	25,512	4,880.80	138,802	30,100	16,500	17,305,375		1,990,052
Copper-zinc	524		3,932	31,380	14,010	271,534		40,709
Lead-zinc	382	24.87	4,792		44,717	240,592		32,849

Digitized by Google

Of the material smelted, the crude ore was the largest part—3,782,494 tons. It contained the following quantities of recoverable metals: 96,922.70 ounces, or $2,003,570, in gold; 5,312,292 ounces of silver; 412,030,793 pounds of copper; 16,713,587 pounds of lead; and 3,077,359 pounds of zinc, valued in all at $120,616,563, or an average value per ton of $31.89. The copper ores constituted the largest part of the crude ores smelted, aggregating 3,679,576 tons, of which the Warren or Bisbee district, in Cochise County, produced more than 48 per cent. The dry or siliceous ores formed the next largest quantity—48,127 tons, followed by lead ores—45,940 tons, the latter being produced largely in the Warren district of Cochise County.

Mine production of metals from Arizona crude ore shipped to smelters in 1917.

By counties.

County.	Crude ore to smelter.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc content.	Total value.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
Cochise	1,832,073	52,514.41	2,367,105	175,716,928	10,905,920	608,443	$52,006,755
Coconino	1,511	1.11	4,576	346,538	.....	.....	98,399
Gila	318,539	2,648.23	268,709	33,754,742	187,215	35,333	9,510,908
Graham	3,542	49.50	32,982	242,966	1,488,711	.....	222,559
Greenlee	153,064	490.29	17,823	12,840,937	.....	.....	3,530,397
Maricopa	1,124	922.50	2,415	81,405	45,732	.....	47,216
Mohave	5,395	729.55	46,905	836,431	686,842	330,329	375,831
Pima	264,849	87.74	167,272	18,796,312	687,019	194,611	5,349,972
Pinal	108,854	1,552.85	216,830	11,900,743	867,039	11,322	3,535,391
Santa Cruz	41,671	73.02	192,886	3,632,694	1,131,948	1,465,919	1,399,044
Yavapai	1,008,307	36,078.02	1,990,149	150,303,490	658,409	422,402	43,518,311
Yuma	43,565	1,775.48	4,550	3,577,617	54,752	.....	1,021,850
	3,782,494	96,922.70	5,312,292	412,030,793	16,713,587	3,077,359	120,616,563

By kinds of ore.

Dry or siliceous	48,127	10,082.72	399,846	740,079	42,669	.....	$743,612
Copper	3,679,576	81,488.69	4,306,674	410,285,672	60,287	.....	117,248,041
Lead	45,940	5,221.98	541,540	720,719	15,743,892	.....	2,104,908
Zinc	5,190	74.55	28,585	143,193	181,420	2,293,476	313,724
Copper-lead	1,610	54.76	33,647	141,130	432,484	.....	104,578
Lead-zinc	2,051	.....	.....	.....	252,835	783,883	101,700

PRODUCTION BY COUNTIES.

GENERAL STATEMENT.

The following tables show the State output by counties in 1917, the production of each metal, and the total value; also the production of ore and the average value per ton, by counties, in 1916 and 1917. The tables are followed by a review of the mining industry of each county and each producing mining district.

Digitized by Google

Ore sold or treated, number of deep mines producing, and average value of ore per ton in Arizona in 1916 and 1917.

County.	Ore sold or treated, 1917.		Number of deep mines producing.		Average total value per ton.[a]		Average value per ton in gold and silver.[a]	
	Quantity.	Increase or decrease.	1916	1917	1916	1917	1916	1917
	Short tons.	*Short tons.*						
Cochise	1,914,933	− 415,638	67	53	$23.67	$27.51	$1.70	$1.77
Coconino	1,511	+ 1,373	3	6	76.80	65.12	2.26	2.51
Gila	6,049,544	−1,718,146	58	50	7.19	8.01	.06	.09
Graham	12,574	+ 6,048	17	13	37.22	23.08	2.02	2.27
Greenlee	1,431,118	− 580,764	18	17	9.35	10.21	.06	.08
Maricopa	1,552	− 17,119	22	14	3.82	36.91	3.00	20.06
Mohave	275,565	+ 68,029	45	59	20.32	19.20	5.86	10.05
Pima	995,909	+ 521,924	62	61	19.74	9.78	.69	.14
Pinal	3,796,731	+ 334,724	45	26	6.28	7.61	.15	.19
Santa Cruz	64,879	+ 34,492	34	26	28.12	25.61	1.73	2.86
Yavapai	1,176,644	+ 209,086	88	75	30.19	39.58	2.25	2.41
Yuma	47,233	− 7,626	45	52	21.58	21.95	1.25	.90
	15,770,193	−1,263,617	504	452	11.20	13.28	.51	.69

[a] Placer product excluded.

Mine production of gold, silver, copper, lead, and zinc in Arizona in 1917.

County.	Gold.					Silver.	
	Placers.		Deep mines.		Total value.		
	Quantity.	Value.	Quantity.	Value.		Quantity.	Value.
	Fine ounces.		*Fine ounces.*			*Fine ounces.*	
Cochise			55,620.70	$1,149,782	$1,149,782	2,707,220	$2,280,749
Coconino			1.11	23	23	4,576	3,771
Gila			6,135.49	126,832	126,832	501,920	413,582
Graham			54.81	1,133	1,133	33,324	27,459
Greenlee			2,551.01	52,734	52,734	83,458	68,769
Maricopa	149.38	$3,088	1,396.93	28,877	31,965	2,754	2,269
Mohave			119,156.24	2,463,178	2,463,178	370,094	304,958
Pima	231.14	4,778	134.24	2,775	7,553	167,634	138,130
Pinal			7,912.17	163,559	163,559	679,939	560,270
Santa Cruz			251.69	5,203	5,203	218,783	180,277
Yavapai	181.99	3,762	49,328.08	1,019,702	1,023,464	2,207,583	1,819,048
Yuma	270.22	5,586	1,798.63	37,181	42,767	6,628	5,462
	832.73	17,214	244,341.10	5,050,979	5,068,193	6,983,913	5,754,744

County.	Copper.		Lead.		Recoverable zinc content.		Total value.
	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	
	Pounds.		*Pounds.*		*Pounds.*		
Cochise	176,814,981	$48,270,490	11,262,440	$968,570	608,443	$62,061	$52,681,852
Coconino	346,538	94,605					98,399
Gila	175,383,626	47,879,730	187,215	16,100	35,333	3,604	48,439,848
Graham	489,264	133,569	1,488,711	128,029			290,190
Greenlee	53,072,330	14,488,746					14,610,249
Maricopa	81,406	22,223	45,732	3,933			60,390
Mohave	897,973	245,147	6,141,246	528,147	17,149,200	1,749,219	5,290,649
Pima	34,877,443	9,521,542	687,019	59,084	194,611	19,850	9,746,159
Pinal	102,912,392	28,095,063	925,481	79,591	11,322	1,155	28,899,658
Santa Cruz	4,101,176	1,119,621	1,839,390	158,188	1,945,189	198,409	1,661,698
Yavapai	159,612,146	43,574,116	686,874	59,071	950,762	96,978	46,572,677
Yuma	3,577,617	976,689	201,337	17,315			1,042,233
	712,166,891	194,421,561	23,465,445	2,018,028	20,894,860	2,131,276	209,393,902

Digitized by Google

COCHISE COUNTY.

Mine production in Cochise County, Ariz., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc content.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	69	2,330,571	[a] $1,514,811	[a] 3,709,225	203,651,911	15,902,137	72,703	$55,160,840
1917	53	1,914,933	1,149,782	2,707,220	176,814,981	11,262,440	608,443	52,681,652
Increase or decrease, 1917		−415,638	−365,029	−1,002,005	−26,836,930	−4,639,697	+535,740	−2,479,188

[a] Includes placer production.

The total average value per ton of the ore increased from $23.67 in 1916 to $27.51 in 1917, and the gold and silver value in this ore increased from $1.70 to $1.77. All the metals, with the exception of zinc, decreased in quantity and value. Gold decreased from $1,514,811 in 1916 to $1,149,782 in 1917; silver, from $2,440,670 in 1916 to $2,230,749 in 1917; copper, from $50,098,370 to $48,270,490; lead, from $1,097,247 to $968,570. Recoverable zinc, valued at $9,742 in 1916, increased to $62,061 in 1917. Ores of smelting grade, of which there were 1,832,073 tons, predominated and contained $1,085,569 in gold, 2,367,105 ounces of silver, 175,716,928 pounds of copper, 10,905,920 pounds of lead, and 608,443 pounds of zinc, valued in all at $52,006,755, or an average value per ton of $28.39. The 33,241 tons of lead ores shipped to plants outside of the State contained 2,963.45 ounces of gold, 374,325 ounces of silver, 502,048 pounds of copper, and 10,693,489 pounds of lead. Of the copper ores smelted, it was estimated that 318,108 tons were oxidized ores and 1,457,403 tons were sulphide ores. No production of placer gold was reported in 1917.

California district.—Four producers reported the output of 194 tons of ore, nearly all of which was shipped directly to the smelters, containing 334 ounces of silver, 17,410 pounds of copper, 29,057 pounds of lead, and 31,556 pounds of recoverable zinc, valued in all at $10,746, or an average value per ton of $55.39. The Cochise & Bullion property yielded a copper-lead ore and some concentrate from milling tests made on the low-grade ore dumps. It is reported that a 125-ton concentration mill for the treatment of this ore is under construction. There were small shipments also from the Horace, Gardner, and Willie Rose properties.

Cochise or Johnson district.—Nineteen producers reported the output in 1917 of 57,167 tons of ore, containing $691 in gold, 47,106 ounces of silver, 4,180,646 pounds of copper, and 15,975 pounds of lead, valued in all at $1,182,196, or an average value per ton of $20.68. All the ore except 161 tons was shipped directly to smelters, and was milled and produced some bullion and concentrate. The largest part of the output came from the Republic mines and yielded copper sulphide ore containing a little silver. The other producers of more than 500 tons of ore were the Peabody and Dragon Mountain mines.

Digitized by Google

There was also some production from the Middlemarch property, which is included in this district. The company operating the property has erected a 100-ton oil-flotation plant and shipped its first copper concentrate in 1917.

Dos Cabezas district.—The greatest part of the output of 4 producers reporting in 1917 came from the Mascot property. This ore is largely a low-grade copper sulphide containing a little silver. The Leroy and Casey properties were also producers.

Hartford or Huachuca district.—Two producers reported the output of 392 tons of ore, containing principally lead and silver, with a little copper and gold. The total value of the output was $11,490. The district is also a producer of some tungsten ore, of which no account is taken in this report.

Tombstone district.—The output of 57,474 tons of ore made by 5 producers in 1917 contained $69,721 in gold, 444,139 ounces of silver, 229,488 pounds of copper, and 1,278,754 pounds of lead, valued in all at $608,315, or an average value per ton of $10.58. The larger part of the ore, 26,762 tons, was shipped directly to the smelters, and 16,075 tons yielded gold and silver bullion and some lead concentrate. There was also 14,637 tons of old tailings shipped to the smelter, yielding principally silver, some copper, and a little gold. A considerable production came from the Bunker Hill Mines Co., operating the Tombstone group, which also produced considerable manganese ore and concentrate used at the smelter at Douglas and at metallurgic plants in the East. There were also small productions of silver ore from the Randolph, Silver Bar, and Solstice properties.

Turquoise district.—Nine producers reported a yield of 93,847 tons of ore, containing $62,372 in gold, 228,960 ounces of silver, 3,526,880 pounds of copper, and 127,887 pounds of lead, valued in all at $1,224,871, or an average value per ton of $13.05. Part of the district output of ore was milled, and 51,093 tons were shipped directly to the smelters. There were also 5,096 tons of old tailings, containing a small quantity of gold and silver, sold to the smelters as converter lining. The Commonwealth mine was the producer of the milling ore and old tailing. The Great Western Copper Co. shipped its oxidized copper ore directly to the smelter at Douglas. There were also shipments from the Leonard property, of heavy sulphide ore low in copper, which is valuable fluxing ore for the Shannon works at Clifton. The Tejon and Black Tail properties both produced ore of smelting grade.

Warren or Bisbee district.—From 10 properties in the district there was produced 1,687,112 tons of ore, containing $1,014,930 in gold, 1,966,165 ounces of silver, 167,599,046 pounds of copper, 9,725,771 pounds of lead, and 576,887 pounds of recoverable zinc, valued in all at $49,284,848, or an average value per ton of $29.21. All the ore, with the exception of 2,947 tons, was of smelting grade. There were also shipped to the smelters 3,267 tons of old slag, containing copper and silver. Most of the ore, containing copper, was treated at the two smelters at Douglas, and the lead ore was shipped to the smelter at El Paso, Tex.

Digitized by Google

The Copper Queen mines,[1] according to the annual report of the company, produced 796,502 tons of various kinds of ore, divided as follows:

Ore and metals produced at Copper Queen mines, Ariz., 1917.

Kind of material and destination.	Ore.	Gold.	Silver.	Copper.	Lead.
	Short tons.	*Ounces.*	*Ounces.*	*Pounds.*	*Pounds.*
Shipped to Douglas:					
Company ore	737,729	18,339	563,493	89,235,586	.....
Lease ore	35,986	59	36,533	2,932,820	.....
Sacramento Hill ore	237	3	177	15,120	.....
Shipped to El Paso:					
Silver-lead ore	14,658	614	209,969	428,705	6,023,858
Lease ore	2,571	117	14,178	18,909	745,248
To experimental concentrator:					
Copper ore	2,124	.....	.....	.....	.....
Lead ore	818	.....	.....	.....	.....
To Chicago:					
Manganese ore	2,379	.....	.....	.....	.....
	796,502	.....	.....	.....	.....
Miscellaneous:					
Precipitates	816	.....	57	793,433	.....
Old dump slag	3,267	.....	205	152,121	.....
	800,585	.....	.....	.....	.....
Concentrates:					
Copper to Douglas	265	3	116	40,825	.....
Lead to El Paso	120	21	3,937	890	101,022
	.....	19,156	828,665	93,618,409	6,870,128
Total, 1916	.....	24,030	1,096,136	102,685,722	9,421,562

At the Copper Queen mine[2] the removal of Sacramento Mountain, to expose for steam shoveling a large body of low-grade disseminated ore, was commenced in 1917. This operation involves the removal and transportation to rather remote points of 8,000,000 cubic yards of overburden in order to make an estimated tonnage of 6,000,000 tons of ore available for open-pit mining. A concentrator having a capacity of 3,000 tons daily will be built at a point about 3 miles distant, in which the direct-flotation method will be followed.

From the Calumet & Arizona mines[3] 747,456 dry tons of ore were mined and shipped to various smelters, but the bulk, 721,328 tons of copper ore, was smelted at the Douglas plant. Ores high in sulphur content, 50,572 tons in quantity, were in demand at Sasco, Globe, and Miami; 3,259 tons of manganese ore went to steel manufacturers at Chicago and Birmingham; 1,607 tons of lead-zinc sulphides to Kansas paint makers; and 1,458 tons of lead ore to the smelter at El Paso. At Douglas the company smelted, in addition to its own ores, 295,286 tons of custom ore from New Mexico and Arizona mines. There was produced from the company ore sold or treated 59,131,512 pounds of refined copper, 906,038 ounces of silver, and 27,947.83 ounces of gold. Dividends paid in 1917 amounted to $7,067,241, including a distribution from capital. Altogether since 1903, including 1917, there have been paid by this company dividends amounting to $35,992,761.75. The following paragraphs were taken from the company's annual report:

Precious metals per ton of refined copper from our own ores amounted to $43. * * *

[1] Phelps Dodge Corp. Ann. Rept. for year ending Dec. 31, 1917.
[2] Eng. and Min. Jour., Jan. 12, 1918, p. 58.
[3] Calumet & Arizona Mining Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

The wages of the men have been based on a sliding scale dependent upon the price of copper, but when the Government price of 23½ cents per pound was fixed for a certain term, it was agreed that the wages established during the month of August by the price of copper for July should remain in force during the term in spite of the reduction of the selling price. During the last four months, therefore, miners' wages have been $5.35 a day and unskilled underground labor has been 25 cents less. * * *

The new reverberatory furnace was started up and is in operation. We have not sufficient waste-heat boilers for four reverberatories and have accordingly ordered two more 713-horsepower Stirling boilers similar to those now installed. The constant decrease in the amount of oxidized ores and increase in the tonnage of sulphide ores tends to the production of lower-grade mattes and greatly embarrasses us in our converter department. * * *

The steam produced from our waste-heat boilers is far more than is necessary to generate power for the entire smelting plant. Accordingly a high-tension transmission line was constructed from the smelter to the mines at Bisbee, a distance of about 24 miles. At the present time we are only sending up about 500 kilowatts of current, but as soon as the new electric pump in the Junction mine is in operation power will be furnished for it from the same source.

The Shattuck-Arizona mine[1] yielded 130,583 dry tons of copper ore shipped to Douglas and 7,992 tons of lead ore treated at El Paso. These ores contained 11,935,317 pounds of copper, 154,344 ounces of silver, 1,542 ounces of gold, and 2,010,145 pounds of lead. Dividends have been paid since July 20, 1910, amounting to $6,562,500, of which $1,575,000 was paid in 1917. The company's report contains the following paragraphs:

Every effort is being made to increase mine output, but progress has been slow owing to lower average grade of ore mined and inability to obtain satisfactory results from the small amount of development work performed. Copper ore reserves have been depleted during the last seven months of the year, due largely to the decrease in the amount of development work and negative results from the work actually accomplished. Promising leached-ore territory has been opened up, but without finding commercial ores, although the showings of leached ground are sufficient to justify the expectation of opening up good ore-bearing ground during the coming year.

Good progress has been made in exposing additional tonnages of lead-silver siliceous ores in the upper levels of the mine, especially at the 100-foot level. With the siliceous lead-silver ores we have found tonnages of high-grade copper ores, which will become available as soon as milling operations of the lead ores are started.

The increase in cost per pound of copper was due to a great extent to the decrease in labor efficiency on account of strike troubles, less metal recovery due to our mining of lower-grade ores, and in a lesser degree to the greater cost of supplies.

A very promising ore deposit was opened up during the past year on the 100-foot level. The lens of ore is high-grade copper ore associated with lead-silver values of sufficient grade to prevent mining the copper at this time without sacrificing the lead-silver values. * * *

Shipments of high-grade lead ores have been made at the rate of 150 tons per week. A much larger tonnage could have been shipped had the custom smelter at El Paso been able to treat and market these ores. The embargo has been a handicap to our operations in the lead-bearing section of the property. Important additions have been made to the low-grade siliceous lead-silver ores, and a method has been developed for realizing a good profit from the treatment devised for these ores. During the year 1916 laboratory experiments had been conducted and indicated a substantial profit could be made by concentration and flotation. During the months of February and March, 1917, actual milling tests at the rate of 50 tons daily were carried out in the Copper Queen experimental mill. This work resulted in showing that 92 per cent of the lead and 80 per cent of the silver values could be recovered at a profit of at least $4 per ton of ore treated under normal prices for lead and silver.

[1] Shattuck-Arizona Cooper Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

Plans and specifications for a milling plant capable of treating 400 tons per day were prepared during the year, and the building of this plant is now progressing very rapidly. Machinery has been ordered and if delivered promptly on agreed dates the plant should be ready for operation May 1, 1918.

COCONINO COUNTY.

Francis district.—All the ore shipped by 4 producers was of smelting grade, valued at $11,181, or an average value per ton of $29.74, principally for its copper content. The H. P. & Royal claims and the May Queen property were the largest producers; both marketed low-grade copper ore. There was also some ore shipped by lessees from other properties.

Grand Canyon district.—Lessees on the Grand Canyon Copper mine shipped two cars of copper ore of good grade during 1917.

White Mesa district.—The Navajo Copper Co. in 1917 purchased machinery for a mill, which had not been completed at the end of the year. Considerable copper ore was shipped for treatment to the smelters at El Paso, Tex., and Tacoma, Wash.

GILA COUNTY.

Mine production in Gila County, Ariz., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc content.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	58	7,767,690	$113,614	508,576	225,110,898	232,602	59,646	$55,849,581
1917	50	6,049,544	126,832	501,920	175,383,626	187,215	35,333	48,439,848
Increase or decrease, 1917	.....	−1,718,146	+13,218	−6,656	−49,727,272	−45,387	−24,313	−7,409,733

The total average value per ton of the ore sold or treated in Gila County increased from $7.19 in 1916 to $8.01 in 1917, and the gold and silver value from 6 cents to 9 cents a ton. The output of gold, valued at $113,614 in 1916, increased to $126,832 in 1917; silver increased in value from $334,643 to $413,582; copper decreased from $55,377,281 to $47,879,730; and lead increased from $16,050 to $16,100. There was also a production of zinc in 1917 valued at $3,604. Of the ores produced, 5,730,268 tons were of concentrating grade and produced 277,910 tons of concentrate, containing 3,431.65 ounces of gold, 232,993 ounces of silver, and 141,554,598 pounds of copper. The crude ores, mostly copper ore, shipped directly to the smelters amounted to 318,539 tons, against 351,021 tons in 1916. The crude ores in 1917 contained 2,648.23 ounces of gold, 268,709 ounces of silver, 33,754,742 pounds of copper, 187,215 pounds of lead, and 35,333 pounds of zinc. There were also 700 tons of old copper slag smelted. Nearly all of the ore produced was treated in the district, with the exception of lead ores and some copper ores, which were shipped to plants outside of the county. Of the copper ores smelted, 93,817 tons were oxidized and 223,868 tons were sulphides. The smelting ores shipped were valued at $9,510,908, or an average value per ton of $29.86, and the concentrates, chiefly copper, were valued at $38,907,329, or an average value per ton of $139.99.

Digitized by Google

Banner district.—Eight properties were producers of 101,728 tons of ore, containing $21,334 in gold, 28,788 ounces of silver, 5,888,057 pounds of copper, 113,496 pounds of lead, and 35,333 pounds of recoverable zinc, valued in all at $1,665,860, or an average value per ton of $16.38. All of this ore was of smelting grade with the exception of 20 tons, which yielded a small quantity of gold bullion. The Christmas property was the principal producer of copper ore treated at the Hayden smelter. This property is opened by a vertical shaft 850 feet deep. The Gila Canyon property was next in importance as a shipper of copper ore. From the Lavell mine considerable oxidized lead ore was shipped to El Paso. The London-Arizona yielded copper ore and a small quantity of oxidized zinc ore.

Brown district.—A small quantity of oxidized copper ore was shipped from the Bell Copper prospect to the Globe smelter.

Dripping Springs district.—The Cow Boy property yielded a small quantity of gold bullion from milling operations and one lot of oxidized lead ore, which was shipped to a smelter.

Globe-Miami district.—Thirty-six properties produced 5,947,681 tons of ore, the larger part of which (5,730,268 tons) was of milling grade and yielded 277,910 tons of concentrate containing 3,431.65 ounces of gold, 232,993 ounces of silver, and 141,554,598 pounds of copper. The smelting ore amounted to 216,713 tons, containing 1,635.17 ounces of gold, 221,210 ounces of silver, 27,862,512 pounds of copper, and 65,010 pounds of lead. In addition to this ore, there were 700 tons of old slag smelted, which contained copper and silver.

Recent developments reported[1] in the district are of importance.

The development of high-grade copper ore on the 1,000-foot level at Iron Cap indicates an exceptionally important strike for the Globe district and lends much encouragement to the exploration that Old Dominion, Commercial, and Superior-Boston have been carrying on at depth, with attendance of good results. The outlook is also improved for New Dominion and several other developing properties. Iron Cap ore is in bornite and on the 1,000-foot level averages 12.5 per cent copper with about 10 ounces silver. On the 800-foot level the ore has an average width of 8 feet and on the 900-foot of 12 feet and carries 10 per cent copper. Sinking from the 1,000 to 1,100-foot has been started. Arizona Commercial is opening new stopes between the 1,500 and 1,400 foot levels and pushing development vigorously with good results on the 800, 1,000, 1,200, and 1,500 foot levels. The water area has been lowered between the 1,200 and 1,500 foot levels. Porphyry Copper Co. is to block out ore, preparations being under way to cut stations at 530 feet and 630 feet in the shaft and start driving.

The Old Dominion mine[2] and the United Globe mines, combined in 1917 under one company, produced 199,888 dry tons of ore, averaging 4.97 per cent of copper. This included 81,728 tons of smelting ore averaging 6.92 per cent of copper, 114,217 tons of concentrating ore averaging 3.62 per cent of copper, 3,904 tons of siliceous ore averaging 3.29 per cent of copper, and 39 tons of iron ore averaging 2.21 per cent of copper. The total production of metal in 1917, including that from custom ores, was 32,365,795 pounds of refined copper, 165,703 ounces of silver, and 3,897.60 ounces of gold. The mining costs per ton in 1917 were $8.08, against $6.48 in 1916, and milling costs were $1.25, against $1.14. The metal extraction for 1917 was 88.01 per cent, as compared with 86.63 per cent in 1916. Of the total ex-

[1] Min. and Sci. Press, Jan. 26, 1918, p. 136.
[2] Old Dominion Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

traction, 30.54 per cent was made by flotation, 69 per cent by water concentration, and 0.46 per cent from overflow slimes sent to the smelter. Dividends have been paid since 1905 by the companies operating these properties amounting to $13,216,976, of which $2,376,262 was paid in 1917.

In 1917 the Inspiration mine[1] produced 3,914,742 tons of ore, against 5,353,880 tons mined in 1916. Of the ore mined, 3,891,075 tons were concentrated and yielded 0.0359 ton of concentrate per ton of ore treated. There were 23,677 tons of oxidized ore shipped to the smelter. The total production of copper was 80,566,982 pounds, against 120,772,637 pounds in 1916. The total cost of copper derived from concentrating ores was 10.43 cents a pound and the total cost per ton of ore was $2.01. The dividends paid in 1917 amounted to $9,751,227.75. The company's annual report says:

> The production of the company for the first half of the year was 12.9 per cent above the average for a like number of months in the previous year. The operations during the later part of the year were interrupted by a strike brought about simultaneously in the first days of July by agents of the I. W. W. and the International Union of Miners, Mill, and Smelter Workers. Work was resumed in the mine on August 23, and the mill started on September 1. On October 20 the strike was declared off, we having at that date 968 men in our employ, most of the draft men and the other Americans having previously returned to work. * * *
>
> The local increase in the cost of producing copper for the year as against the previous one has been due to the interruption of the strike, the increased prices paid for labor and material, the increased State and county taxes, and the decreased yield from the ore treated. The ore yielded 22.46 pounds per ton in 1916, and 20.39 pounds in 1917. This result was mainly due to the active working of a new stope, which was not in commission in 1916, yielding ore of a satisfactory margin at present prices of copper but of a lower grade than the average. The percentage of copper recovered from the ore by the concentrator was practically the same as last year, which indicates slightly better work in view of the lower grade of ore treated.

The Miami property[2] produced 1,640,206 tons of ore, which yielded 53,639 tons of concentrates containing 46,172,322 pounds of copper, or an average of 860.8 pounds a ton, representing a mill recovery of 69.25 per cent. The smelter returned 43,863,699 pounds, or 95 per cent of the total content, as merchantable copper. The total cost of handling the ore in 1917 was $2.28 a ton, divided into mining, $1.267; milling, $0.691; and general expense, $0.325, or a total average per pound of copper of $0.125. The total dividends paid by this company since 1912 amounted to $16,233,030.75, of which $6,537,247.50 were paid in 1917. The following extracts are from the company's report:

> During the first six months of the year production continued on the scale reached by the end of 1916 at the rate of about 6,000 tons of ore per day and a monthly output of 5,000,000 pounds of refined copper. For the last few months of this period labor unrest was evident, and it culminated in a strike on July 2, as a result of which operations were very much hampered for the balance of the year. The property was closed down for seven weeks, when work was resumed and continued on a gradually increasing scale until by the end of the year normal conditions were again reached. * * *
>
> An important step affecting the mine was taken by the decision to sink a new working shaft known as shaft No. 5. Up to the present time shaft No. 4 has been the only outlet for ore from the mine, and the crushing plant at this point has been barely able to handle the output under continuous op-

[1] Inspiration Consolidated Copper Co. Ann. Rept. for the year ending Dec. 31, 1917.
[2] Miami Copper Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

eration. The new shaft will be lined with concrete in place of timber and thus be fireproof, and complete hoisting equipment and a second crushing plant will be installed. * * * The new shaft will have a total depth of 830 feet and will be connected with the ore-producing portion of the mine at the 570 and 720 foot levels, where underground ore pockets will be located. * * *

Underground development work done during the year amounted to 25,476 feet, consisting of 10,457 feet of drifts. 14,993 feet of raises, and 26 feet for the new working shaft. * * *

No additional tonnage of high-grade ore has been developed, and at the end of the year the reserves of this class stand at 14,760,000 tons (2.40 per cent of copper).

In the area containing the low-grade ore body 12 additional churn-drill holes were put down, aggregating 8,407 feet. This drill work was not undertaken with the idea of increasing the tonnage, but of more clearly defining the limits of the ore body. No revision of the estimate has therefore been made, and the reserves of this grade stand at 28,000,000 tons with an average of 1.06 per cent copper.

In addition to the above, there is the body of mixed oxide and sulphide ore partially developed, estimated to contain 6,000,000 tons averaging about 2 per cent copper.

At the Copper Hill property[1] 12,687 tons of smelting ore, containing an average of 9.64 per cent of copper, and 27,016 tons of concentrating ore, containing 4.52 per cent of copper, were mined and shipped to the Old Dominion smelter and concentrator. Dividends paid since October 31, 1916, amount to $556,500, including $424,000 paid in 1917. The company's report says:

Mining operations were suspended during the year from July 2 until August 18 on account of the strike. * * *

The most important ore developments for the year were on the eighth and tenth levels east of the Budget fault, on the ore which was first discovered in 1915 on the twelfth level and in 1916 on the tenth level. * * *

The ore on the eighth level has been developed for a distance of 300 feet farther east than the end of the tenth level. The average grade of the ore developed on the eighth and tenth levels is considerably higher than that heretofore developed in the mine. It is not, however, as desirable as smelting ore on account of its low content of sulphur and iron and its large amount of silica. * * * A noticeable characteristic of this ore shoot is the occurrence of small rich lenses of ore at intervals along both the foot and hanging walls, separated by siliceous ore of concentrating grade. These shoots do not seem to be regular but change from one wall to the other, it not being unusual to find rich ore on both the foot and hanging walls in the same portion of the vein. * * *

On the twelfth level little was accomplished toward developing new ore on account of the large flow of water coming from east of the Budget fault. * * *

On both the thirteenth and fourteenth levels, near the fault, there is still a considerable tonnage of sulphide ore of smelting grade which has not been extracted on account of the water from the fault. * * *

The fifteenth level had been advanced for about 100 feet at the time of the strike. Work was not resumed on the fifteenth level until the latter part of October, and no ore had been developed on the level at the end of the year. A raise from the fifteenth to the fourteenth encountered ore 35 feet below the fourteenth. Nothing was done on the sixteenth level after work was discontinued on the station.

From the Iron Cap property[2] in 1917 there were shipped 20,989 tons of ore to the El Paso smelter and 10,631 tons of concentrating ore to the Old Dominion mill. The production from both milling and shipping ore was 145,788 ounces of silver and 4,584,000 pounds

[1] Arizona Commercial Mining Co. Ann. Rept. for year ending Dec. 31, 1917.
[2] Iron Cap Copper Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

of copper. According to the company's annual report, the development was as follows:

> The Williams shaft has been sunk 128 feet to a total depth of 1,083 feet. A station is being cut on the eleventh level. * * *
> The Iron Cap shaft has been sunk 130 feet and is now 15 feet below the tenth level. * * * The 900-foot level was opened during the year by crosscutting from the shaft to the vein and drifting east and west on the vein about 700 feet. Stopes have been opened for a distance of 327 feet. The vein has increased in width as well as in the value of the ore over the level above.

At Miami during 1917 the International smelting plant[1] treated 242,936 tons of copper concentrates and 26,839 tons of purchased ores, or a total of 269,775 tons, from which there were produced 138,762,411 pounds of fine copper, 201,859 ounces of silver, and 2,953.64 ounces of gold.

Green Valley district.—The Pittsburg & Tonto property yielded a little sulphide copper ore, which was shipped to Globe in 1917.

Richmond Basin district.—A small quantity of silver ore was shipped to San Francisco and to Deming, N. Mex., from the Jumbo property.

GRAHAM COUNTY.

From 13 producers in the county there were reported 12,574 tons of ore containing gold, silver, copper, and lead, valued at $290,190. Most of this ore, 9,024 tons in quantity, was of milling grade and produced copper concentrate from ores mined in the Bunker Hill district. The Bunker Hill, Aravaipa, Ashpeak, Lone Star, and Stanley Butte districts produced altogether 1,721 tons of smelting ore.

Aravaipa district.—Three producers yielded 1,595 tons of ore, containing $289 in gold, 28,098 ounces of silver, 67,557 pounds of copper, and 1,351,277 pounds of lead, valued in all at $158,095, or an average value per ton of $99.12. The Laurel Canyon Mining Co. operated the Grand Reef property, which is said to have produced ore carrying 41 per cent of lead and 5 to 10 ounces of silver per ton. This, with the production of two other operators, makes the total output an important one.

Bunker Hill district.—The Copper State, New York, California, and Table Mountain properties were the only producers in 1917 and shipped some concentrate and crude ore containing copper. Some lead was contained in the ore shipped from the last-named property.

Lone Star district.—Three producers shipped directly to the smelters 1,588 tons of ore, containing $28 in gold, 663 ounces of silver, 134,403 pounds of copper, and 46,319 pounds of lead, valued in all at $41,249, or an average value per ton of $25.98. The Atlas Copper, Mono, and Ten Strike were the producers.

Stanley Butte district.—The Copper Reef and Friend properties each shipped oxidized copper ore to the Globe and Miami smelters.

[1] Anaconda Copper Mining Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

GREENLEE COUNTY.

Mine production in Greenlee County, Ariz., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	
1916	19	2,011,882	$50,594	90,759	75,976,831	8,540	$18,801,202
1917	17	1,431,118	52,734	83,458	53,072,330	.....	14,610,249
Increase or decrease, 1917	.....	−580,764	+2,140	−7,301	−22,904,501	−8,540	−4,190,953

In 1917 there were 17 producers of ore in Greenlee County. The quantity of ore mined was 580,764 tons less than was reported by 18 deep-mine producers in 1916. The ore sold or treated averaged $10.21 a ton in 1917, against $9.35 a ton in 1916. The gold and silver reported as being recovered from the refining of copper bullion amounted to only 8 cents a ton. The concentrating ores aggregated 1,268,783 tons and produced 164,371 tons of concentrates, which contained $42,206 in gold, 65,629 ounces of silver, and 40,087,614 pounds of copper, valued in all at $11,040,203, or an average value per ton of $67.17. The ore smelted was 153,064 tons, all of which was copper ore except 30 tons of siliceous ore. Of the copper ore, 101,527 tons were estimated to be oxidized and 51,507 tons were sulphide. No placer production was reported in 1917.

Ashpeak district.—The Ashpeak mine, placed under option in March to a Nevada company,[1] is mentioned in its annual report as follows:

> The vein, a silver-bearing quartz-filled fissure of unusual persistence, had been developed to a depth of 500 feet. No ore of importance was exposed, but a favorable rock change, accompanied by gradually increasing values, was indicated as taking place with depth. Development work is now being carried on to determine whether these favorable conditions continue until ore in payable quantities will result.

Copper Mountain and Greenlee districts.—The combined production of these two districts is represented in the table giving the production of Greenlee County.

In 1917 the Detroit mine[2] produced 310,743 tons of concentrating ore assaying 2.34 per cent of copper, which yielded 1.62 per cent of fine copper. There were 16,594 tons of smelting ore treated assaying 8.73 per cent of copper, from which was recovered 8.32 per cent of fine copper. From this output and 904 tons of old slag and tailing and 5,022 tons of siliceous copper ore to converters, there was produced altogether 13,202,201 pounds of fine copper. A distribution of the tonnage of ore from the various mines into different classes is taken from the annual report of Phelps Dodge Corporation, as follows:

Mine.	Total.	Second class.	Sulphide.	Oxide.	Quartz.	First class.	Precipitates.
Ryerson	135,670	132,456	615	.....	.....	2,596	2.4
Yankie	81,304	76,039	904	.....	2,924	1,438	.1
Copper Mountain	56,643	53,731	392	2,521	.....	.....	.....
Arizona Central	50,899	50,530	368	.....	.....	.....	.....
	324,516	312,756	2,279	2,521	2,924	4,034	2.5

[1] Goldfield Consolidated Mines Co. Eleventh Ann. Rept., for year ending Dec. 31, 1917.
[2] Phelps Dodge Corp. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

A labor strike completely stopped the production of copper for four months and caused a very much reduced output for November and December.

The Arizona Copper Co.'s report[1] for the fiscal year gives the following information:

During the year our production of copper amounted to 42,480,000 pounds, which compared with 34,144,840 pounds for the previous year.

The total ore mined from the company's properties amounted to 1,178,087 tons, as compared with 905,486 tons the previous year, and the yield, as indicated by the smelter returns from ores treated, was 36.6 pounds of copper per ton of ore, which compares with a yield of 36.06 pounds per ton treated during the previous year.

The period under review may be characterized as a period of severe stress from an operating standpoint, on account of the peculiarly difficult labor situation which has existed in this State for some time past. * * *

The daily output of ores from the mines was 4,808 tons, as compared with 4,006 tons the previous year, and represents what may be considered the maximum output which can be conveniently handled with present facilities, all departments operating at full capacity.

The grade of smelting ore treated was 5.714 per cent copper, while the grade of concentrating ore treated was 2.435 per cent copper. * * *

The total ore treated by concentrators during the year was 1,127,054 dry tons.

No. 6 concentrator treated 996,699 dry tons of an average grade of 2.44 per cent copper, containing 0.34 per cent in the oxidized form. A total extraction of 73.02 per cent was made, or an increase of 3 per cent over that of the previous period. * * *

No. 4 concentrator, at Clifton, treated 130,355 dry tons of ore during the period, and the grade of this ore was very low, being only 2.26 per cent, of which 0.36 per cent was in the oxidized form. The average extraction here was 71.33 per cent, or slightly better than that made during the previous year.

Additional flotation cells have been added to this plant, and the old vanners have been removed and are being replaced with Deister tables with the expectation of making a better recovery. * * *

The smelter was operated on a two-furnace basis throughout the year, except when impossible on account of strikes.

The average amount of new material smelted daily was 812 dry tons. * * *

The work of excavating the slag from the old Clifton smelter site has proceeded continuously throughout the year, the total tonnage of this material recovered at the end of September being 20,849 dry tons, assaying 3.82 per cent copper, which has been resmelted, and considerable tonnage still remains.

The Shannon property[2] was operated under many difficulties in 1917, resulting from the labor strike and high prices of materials. The company recently purchased the Yaeger Canyon property in Yavapai County and paid dividends in 1917 amounting to $525,000, most of which were from profits in 1916 and accumulated surplus. The company's report contains additional information as follows:

The company mined and treated during the period of operation 157,000 tons of ore from its own properties and 13,800 tons custom ore, or a total of 171,000 tons, from which was produced 6,138,219 pounds of copper, 1,096.2132 ounces of gold, and 51,771.35 ounces of silver. * * *

Aside from the small production and the large expenses incurred during the year incidental to the five months' shutdown, the other elements that entered into making the cost of producing copper unusually high this year were the lower copper contents of our Metcalf ores and the constant increase in the cost of labor, fuel, and supplies. Wages are to-day 120 per cent higher than they were before the war. Fuel oil, which the company uses in its power plant, advanced from 37½ cents per barrel in 1916 to $1.35 per barrel. Coke, for which we paid $3.75 per ton before the war, is now $8.60 per ton. Lumber

[1] Arizona Copper Co. Ann. Rept. for year ending Sept. 30, 1917.
[2] Shannon Copper Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

advanced from $24 per thousand, the pre-war price, to $34 per thousand. And so on through the list of everything used in the operation of our property.

It should be pointed out here that the principal ores produced from the Shannon mines are semioxidized, direct-smelting ores and are not susceptible to treatment by concentration. This makes the cost at Shannon higher than at other western mines producing low-grade sulphide ores, susceptible to mechanical concentration, which is a much cheaper process than treating by direct smelting.

For many years it has been expected and assumed that the oxidized ore deposits of the Shannon mines were nearing their end. Lateral developments, however, continued to uncover from time to time additional ores, and enabled us to maintain our normal production of copper. Recently, however, these ores, aside from being more scarce, have also become too low in grade to be smelted at a profit under existing high cost of labor, fuel, and supplies.

It is intended, therefore, to eliminate gradually the mining of these low-grade semioxidized ores and to mine and treat only concentrating ores and such other ores as will show a profit on the present price of copper. * * *

Foreseeing the possibility of the exhaustion of the Metcalf mines, your directors caused the investigation of various mining properties with a view of purchase. * * *

The other mines which were acquired by your company a few years ago, known as the Leonard group, are also showing encouraging developments and offer the possibility of becoming larger and more profitable producers than in the past. There is reason to hope, therefore, that when these two outside mines are brought to a greater state of development their production will offset the loss of production through the exhaustion of the Metcalf mines. Despite the five-month shutdown and the expense it entailed, and despite the distribution of $525,000 in dividends and the investment in connection with the exploration and purchase of the Yaeger Canyon property, your company is free from any floating debts.

MARICOPA COUNTY.

The output of 1,552 tons of ore in 1917, reported by 14 producers, was 17,119 tons less than was reported by 22 producers in 1916. The total average value per ton increased from $3.82 in 1916 to $36.91 in 1917, and the gold and silver value of this ore from $3 to $20.06. The milling ores aggregated 428 tons, producing gold and silver bullion, a decrease from 764 tons in 1916. The higher average value was due to shipments of picked ore (1,124 tons) selected to bear the cost of treatment and transportation to the smelter. The total value of all the ore milled and shipped amounted to $57,282, a decrease of $11,282 from 1916. The reports of 4 placer operators show the recovery of $3,088 in gold and 24 ounces of silver, against an output of $412 in gold and 2 ounces of silver in 1916.

Cave Creek district.—The Mormon Girl property yielded oxidized copper ore, valuable in gold and containing some silver. All this ore was shipped to the Hayden smelter in 1917.

Prosperity district.—The Gun Boat property yielded a small tonnage of lead-sulphide ore, containing gold and silver. This was shipped to San Francisco.

Salt River district.—The Delta property yielded a small quantity of gold ore, containing some silver and copper, shipped to the Douglas smelter.

Sunset district.—The Black Bird property is reported to have yielded gold bullion recovered by the amalgamation process.

Vulture district.—The principal part of the district ore output, consisting of 237 tons of ore, was treated in the milling plant of the Vulture Co. This is the smallest production reported from the district in recent years. Some gold and silver bullion was recovered from the ore milled, and some ore was shipped directly to the smelter.

Digitized by Google

Wickenburg district.—There were 583 tons of ore produced from various prospects in the district, though some of it may have come from adjoining districts. This ore contained $3,054 in gold, 1,194 ounces of silver, 52,669 pounds of copper, and 31,907 pounds of lead, valued in all at $21,161, or an average value per ton of $36.30. Most of this ore was received in small lots at the Arizona Smelting & Reduction Co.'s sampling and concentrating works, where it was mixed for reshipment or brought up to shipping grade by concentration and shipped to the smelters. The company also purchased ores from properties in Maricopa, Yuma, and Yavapai counties and dealt in ores of rare metals.

MOHAVE COUNTY.

Mine production in Mohave County, Ariz., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.	Silver.	Copper.	Lead.	Recoverable zinc content.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	45	207,536	$1,038,814	270,193	1,270,051	5,849,842	17,047,117	$4,216,987
1917	59	275,565	2,463,178	370,094	897,973	6,141,246	17,149,200	5,290,649
Increase or decrease, 1917	.....	+68,029	+1,424,364	+99,901	−372,078	+291,404	+102,083	+1,073,662

The total average value per ton of the ore produced by 59 mine operators decreased from $20.32 to $19.20, but the gold and silver value increased from $5.86 to $10.05 per ton. The total gold increased in value from $1,038,814 in 1916 to $2,463,178 in 1917; the silver from $177,787 to $304,958; and the lead from $403,639 to $528,147. The value of the copper decreased from $312,433 in 1916 to $245,147 in 1917; and that of zinc from $2,284,314 to $1,749,219. Most of the ore produced in the county is of milling grade and yields bullion or concentrates. There were 167,518 tons of ore treated by amalgamation or cyanidation, which produced $2,319,024 in gold and 57,477 ounces of silver, with a total value of $2,366,385, or an average value per ton of $14.13. The concentrating ores aggregated 76,397 tons and produced 33,801 tons of concentrates, against 100,363 tons of ore and 34,086 tons of concentrates in 1916. The concentrates in 1917 contained $129,073 in gold, 265,622 ounces of silver, 55,542 pounds of copper, 5,454,404 pounds of lead, and 16,809,871 pounds of zinc, having a total value of $2,546,795, or an average value per ton of $75.35. Crude ore shipped to smelters amounted to 5,395 tons, against 5,400 tons in 1916. In 1917 shipping ore contained $15,081 in gold, 46,995 ounces of silver, 836,431 pounds of copper, 686,842 pounds of lead, and 339,329 pounds of zinc, and had a total value of $375,831, or an average value per ton of $69.66.

Bentley district.—All of the ore produced in the district required hauling a great distance by truck and wagon to the railroad, most of it as far as St. Thomas and Moapa and some of it to Lund, a station in Utah on the Salt Lake Route. The larger part of the production came from the Grand Gulch and Savanic properties. The Cop-

Digitized by Google

per Mountain mine was also a producer. Altogether there were 2,939 tons of ore produced, containing 1,405 ounces of silver and 813,531 pounds of copper, valued in all at $223,252, or an average value per ton of $75.96.

Cedar Valley district.—There were four producers reporting the production of ore. Various products came from the Diamond Joe, San Francisco, and the Leviathan properties. The last-named property produced sulphide ore containing chalcopyrite and molybdenite, which carries a small amount of gold and silver. The mill on the property makes a sulphide concentrate, which, during 1917, was shipped to Los Angeles.

Indian Secret district.—The White Hills property yielded a small test shipment of silver ore, which went to San Francisco in 1917.

Hackberry district.—Lessees working on the Old Hackberry mine produced a lead-zinc ore, which was concentrated at Needles, and a crude ore, carrying lead and silver, which was shipped directly to the smelter near San Francisco.

Salt Springs district.—The Arizona & Clipper group was prospected, and a little gold bullion was recovered from ore treated in a neighboring mill. The property is situated 65 miles northeast of Chloride.

San Francisco district.—There were 167,258 tons of ore mined in the district, from which were recovered $2,310,270 in gold and 57,353 ounces of silver, valued in all at $2,357,529, or an average value per ton of $14.10. One small lot of ore containing gold and silver was shipped directly to the smelter, and 499 tons of sweepings were treated at milling plants. The principal production of ore came from the United Eastern and Tom Reed mines, each producing about the same quantity of ore, which was treated by the cyanidation process.

Work at the Gold Road mine[1] was confined entirely to exploration. No stoping was done, and the mill was not operated. Work was continued on the narrow vein of ore of good grade discovered in 1916. A fair tonnage of this ore has been opened up.

The Tom Reed mine[2] yielded at its cyanidation plant gold bullion valued at $620,178.74 from 81,114 tons of ore and $6,432.56 from 770 tons of tailing treated within the fiscal year ending March 31, 1918. During the previous year 46,170 tons of ore were milled, yielding $486,677.98. No dividends were paid during the company's fiscal year. The following paragraphs are from the company's report:

> During the month of April and up to May 26, 1917, the old 20-stamp mill was in commission, which, together with the two tube mills, handled 7,940 tons of ore. * * * On May 26, 1917, the newly installed mill equipment, consisting of the three Allis-Chalmers ball mills, the four new 12 by 40 foot Dorr agitators, and one 12 by 40 foot Dorr thickener, were put in operation, since which time the new plant has treated 73,830 tons of ore and 459 tons of scrapings from the tailings pond, making a total of 74,289 tons treated prior to the close of the fiscal year.
>
> The average value of the ore heads for the year was $7.59 per ton, with an average gross tailings loss per ton of 44.6 cents, to which should be credited the net recovery from the tailings treated, which leaves a net tailings loss of 36.7 cents per ton for the year, or an extraction of 95.14 per cent. * * *

[1] United States Smelting, Refining & Mining Co. Twelfth Ann. Rept., for year ending Dec. 31, 1917.

[2] Tom Reed Gold Mines Co. Tenth Ann. Rept., for year ending April 1, 1918.

Digitized by Google

During the year 81,884 tons of ore were milled at a cost of $2.6261 per ton, including overhead and all indirect charges, as compared with a cost per ton of $2.7556 for the preceding year. Mining costs were $2.6265 per ton; including all overhead charges, compared with $3.1271 for 1916. The total cost per ton for mining and milling, inclusive of administration, taxes, and depreciation, was $5.2526 per ton, a showing of unusual economy in operation, which resulted in lowering the unit costs of the year 1917, which had established a new record for low mining and reduction costs in the district. This may be considered a distinct accomplishment if the rising cost of material and labor is considered. The only deduction that can be gained from these figures is the fact that the percentage of metallic content in the ore mined and treated during the year 1917–1918 was much lower than in any previous year, the average value for the current year being $7.59 per ton as compared with $11.03 for the year previous. Consequently, although aggregate expenses of operations were greater, unit costs were somewhat lower for this year than last.

At the end of 1916 the United Eastern mine[1] and mill were both ready for active work, and regular mining and milling operations began on January 4, 1917. The total production for the year was 84,548 tons of ore, from which were recovered 86,629.411 ounces of gold, valued at $1,790,785.50, and 44,353.17 ounces of silver, valued at $36,885, or a total value of $1,827,670.50, and an average per ton of ore of $21.74. The loss in the tailing was 3,245.454 ounces of gold and 1,256.14 ounces of silver, valued in all at $68,134.82, or an average of 68 cents a ton. Dividends paid in 1917 amounted to $408,900. The company report continued with the following detail:

Stoping is done by the cut and fill method. Square-sets are used on the levels, two sets high, and above them the stope is kept filled with waste rock to within working distance of the backs. The ore is broken down on plank floors. It was at first planned to use a variation of the cut and fill method of stoping, known as the "rill system," but the nature of the ore and walls was such that this proved to be impracticable, so the backs are now kept horizontal and are carried forward by steps.

Development work was done to the extent of 2,066 feet of drifting, crosscutting, and raising, and the No. 2 shaft was sunk an additional depth of 297.5 feet to the total depth of 1,163.5 feet. As a result of the development work, substantial additions were made to the ore reserves above the 665-foot level, and the shaft sinking is in preparation for the development of ore on the lower levels. * * *

At the Big Jim mine, after its acquisition by this company in April, 1917, 854 feet of drifting and crosscutting was done with favorable results, but development work was stopped in August on account of the unusually high cost of labor and supplies. * * *

The mill operates on the continuous counter-current decantation process of cyanide treatment. As it was originally designed, the crushing and grinding department had a capacity of 400 tons per day, and the department for cyanide treatment had a capacity of 200 tons per day. The limit of 200 tons was considerably exceeded after the first two months of operation, and by making some additions and changes, the daily capacity was increased until the monthly average is now close to 270 tons per day. * * *

The ore has proved readily amenable to cyanide treatment. The gold is free, and there are practically no minerals in the ore that interfere with the process. Very fine grinding is necessary on account of the minute subdivision of the gold. Eighty per cent of the ore is ground to pass through a 200-mesh screen. The solution in the agitators is kept at a strength of 2.6 pounds of cyanide per ton of solution, and the consumption of cyanide is 0.722 pound per ton of ore. That the process is well adapted to the ore is proved by the satisfactory rate of extraction of 96.33 per cent, which represents the average for the year.

The cost of mining and milling has been very moderate considering the extraordinarily high prices of labor and materials that have prevailed during the year. The average operating costs were: Mining, $4.181 per ton; milling, $2.159

[1] United Eastern Mining Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

per ton; marketing costs, $0.123 per ton; indirect costs, $0.65 per ton; and total operating costs, $7.113 per ton.

These figures include development work and all taxes, except Federal income taxes, but do not include shaft sinking. They will compare favorably with the costs of similar work elsewhere under like conditions.

Wallapai district.—Twenty-nine producers reported 104,362 tons of ore, containing $144,959 in gold, 294,197 ounces of silver, 84,394 pounds of copper, 6,087,742 pounds of lead, and 17,127,596 pounds of recoverable zinc, valued in all at $2,680,978, or an average value per ton of $25.69. Of this ore, the largest part, or 76,250 tons, was milled and produced 33,751 tons of concentrate containing gold, silver, copper, lead, and zinc. This concentrate, with 2,238 tons of ore, was shipped directly to the smelters. There were 25,756 tons of old tailings reconcentrated and 100 tons of oxidized copper ore leached with sulphuric acid and the copper precipitated by electrolysis. This test was made on ore from the Emerald Isle property. The principal producers were the Golconda and Tennessee mines. The former yielded ore from which zinc concentrate containing gold and silver was saved. All of the ore from the Tennessee mine was shipped to Needles for treatment, the resulting zinc concentrate going to Checotah, Okla. According to the report[1] of the company operating the Tennessee mine, the decrease in the price of spelter and lead made the extraction of ore unprofitable and caused the discontinuance of the lease under which the company was operating. Simultaneously the mill for the treatment of this ore at Needles, Cal., was shut down.

The Schuylkill mine adjoins the Tennessee mine on the north, and like many others in the district it is an old mine reopened. The 700-foot level has been reached, and it is reported that sinking will be continued to the 1,000-foot level. The Elkhart, lying north of the Schuylkill, is another old mine of the district. It was unwatered the latter part of 1916 by the American Smelting & Refining Co. for examination. Some mill ore was shipped from the property in 1917, which yielded concentrates containing gold, silver, lead, and a little copper. The Stockton Hill section, lying on the east side of the Cerbat Range and about east of the old town of Cerbat, shared in general activity by the work of the Arizona-Butte property. A 150-ton concentrator equipped with rolls and tables was operated in this section and treated the ore of the Banner and several other mines in 1917. The concentrate and crude ore shipped contained gold, silver, and lead. A lot of lead-zinc concentrate was also shipped.

From the Payroll claim a considerable quantity of lead-zinc ore was shipped to the Needles mill. The Middle Golconda property was also a producer of zinc ore, which was shipped directly to the smelter.

PIMA COUNTY.

Sixty-one operators of deep mines produced 995,909 tons of ore in Pima County in 1917, against 173,985 tons and 62 producers in 1916. The output from deep mines in 1917 included $2,775 in gold, 167,514 ounces of silver, 34,877,443 pounds of copper, 687,019 pounds of lead,

[1] United States Smelting, Refining & Mining Co. Twelfth Ann. Rept., for year ending Dec. 31, 1917.

Digitized by Google

and 194,611 pounds of zinc, valued in all at $9,741,282, or an average value per ton of $9.78. The placer output was $4,778 in gold and 120 ounces of silver. The most notable increase was in the output of copper from the low-grade disseminated ores produced in the Ajo district.

Ajo district.—There were 11 ore producers reporting the output of 801,026 tons of ore, from which was recovered $852 in gold, 6,754 ounces of silver, and 20,201,645 pounds of copper, valued in all at $5,521,466, or an average value per ton of $6.89. Of this output, 70,800 tons were shipped directly to the smelter, most of it for converter lining, and the remaining ore was leached in the plant of the New Cornelia Copper Co., which, in 1917, was the principal producer in the district. Crushing of the ore was begun at the New Cornelia[1] plant in April, and on May 1 the first work of spreading ores in the leaching tanks was commenced, and then gradually each part of the plant was put in operation successfully. The first shipment of electrolytic copper was made from Ajo on June 18. The company's report says:

In addition to the ore mined and treated at the plant 60,561 tons of richer ore was sent to Douglas under an advantageous contract. At first we mined rather lean ores from the original New Cornelia property, but since the absorption of the Ajo Consolidated property we are now shipping from a compact body in that property containing 425,000 tons of ore that according to the drilling and shipments contains better than 4 per cent copper. The total production for the year was 19,482,191 pounds, separated as follows: Electrolytic copper, 12,764,848 pounds; copper in cement copper shipped, 3,316,283 pounds; and copper in ore shipped, 3,401,060 pounds.

In addition to this there is 3,456,584 pounds of recoverable copper locked up in the process. This figure includes starting sheets of which we have a large stock, unfinished cathodes, copper in solution, and cement copper in launders. Of course, a corresponding amount will remain as in process of manufacture as long as the works are operated, but it must be remembered that all this has been partially manufactured during the current year. * * *

While the amount of cement copper produced was about 25 per cent of the total copper resulting from leaching operations and the electrolytic copper produced was about 75 per cent, we are finding out that this proportion of cement copper may be largely decreased. More electrolytic copper will be made in proportion to cement copper, because refined copper from the latter costs about 2 cents a pound more than our electrolytic copper and suffers a deduction of 3 per cent for smelting loss besides.

During the year the New Cornelia Copper Co. absorbed the property of the Ajo Consolidated Copper Co., and the combined properties now have the following ore developed:

	Quantity (short tons).	Copper (per cent).
Oxidized ores	12,800,569	1.568
Sulphides	40,302,457	1.587
Total	53,103,026	1.582
Less ore mined	840,424	1.803
Total	52,262,602	1.579

Included in the above estimate of oxidized and carbonate ores there is one body containing about 400,000 tons of ore estimated to contain a little over 4 per cent of copper which will be mined and shipped to the Calumet & Arizona smelter at Douglas.

[1] New Cornelia Copper Co. Ann. Rept. for year ending Dec. 31, 1917. The early history and present developments are interestingly described by Courtenay De Kalb in the Mining and Scientific Press for Jan. 26, 1918, p. 115, and Feb. 2, 1918, p. 153.

Digitized by Google

Amole district.—The Mile Wide property yielded sulphide copper ore carrying a little silver, which was shipped to Sasco. This property is opened by an inclined shaft 400 feet deep and has about 2,800 feet of drifts.

Arivaca district.—Some gold and silver bullion was recovered from ore produced in this district in 1917.

Baboquivari district.—The Papago Chief property is equipped with a small mill in which there is one concentrating table. It is reported that there was a small shipment of gold and silver ore from the property in 1917.

Cababi district.—Three properties were credited with the production of small quantities of ore mined and shipped, part of which was gold ore and the rest a copper-lead ore.

Empire district.—Five producers reported the production of 1,528 tons of ore, containing $76 in gold, 9,015 ounces of silver, 1,323 pounds of copper, and 326,799 pounds of lead, valued in all at $35,970, or an average value per ton of $23.54. About half of the ore was shipped directly to the smelter, and the remainder, 779 tons, was milled near Tucson. The principal production of oxidized lead ore of smelting grade was from the Forty-nine mine, the ore being shipped to El Paso, Tex., and Deming, N. Mex. The Total Wreck was also a producer of milling ore. The concentrate, carrying a large percentage of molybdate of lead, was all treated by the Arizona Rare Metals Co. of Tucson.

Helvetia district.—Ten producers reported the production of 18,499 tons of ore, containing $269 in gold, 24,525 ounces of silver, 2,615,613 pounds of copper, and 19,171 pounds of recoverable zinc, valued in all at $736,496, or an average value per ton of $39.81. The Narragansett was the principal producer, shipping oxidized copper ore containing some silver. Numerous operators on the property of the Rosemont Copper Co. shipped, in addition to oxidized copper ore, a small quantity of zinc ore. Other known producers were the Sweet Bye and Bye, Bulldozer, and Pickwick properties.

Old Baldy district.—Two carloads of copper ores were reported to have been shipped from the Gray Jackson property in 1917.

Pima district.—There were 18 producers reporting 45,299 tons of ore, containing $145 in gold, 57,639 ounces of silver, 4,440,864 pounds of copper, 263,872 pounds of lead, and 175,440 pounds of recoverable zinc, valued in all at $1,300,584, or an average value per ton of $28.71. All the ore produced was of shipping grade and came principally from the Glance, Mineral Hill Consolidated, Plumed Knight, San Xavier, Morgan, and Vulcan properties.

Roskruge district.—A small quantity of gold bullion was recovered from ore treated from the Roadside property.

Santa Catalina district.—Copper sulphide ore, carrying some silver, was shipped from the Pontotoc property.

Santa Rosa district.—Oxidized copper ore shipped to the smelters at Douglas was reported from the Aeolian property in 1917. This ore carried about 40 per cent of silica and 7 per cent of iron, besides its copper.

Silver Bell district.—The operation of the smelter at Sasco created considerable activity in the district, and there was an increased tonnage treated from the Imperial mine, as well as from the Oxide

Digitized by Google

and El Tiro properties. The total output of the district aggregated 125,124 tons of ore from 6 producers. The smelting company, besides treating ore from the Imperial and other mines in the district, handled a large quantity of ore from other districts of Arizona. The operator of the smelter was the American Smelting & Refining Co., which is reported to have purchased the mine at Silver Bell and the smelter at Sasco. A large quantity of ore was carried by the Arizona Southern Railroad from Red Rock, where connection is made with the Southern Pacific Railroad.

PINAL COUNTY.

Twenty-six mine operators produced 3,798,731 tons of ore, the principal part of which was from the Ray mines. The ore output was greater by 334,724 tons than the production of 45 operators in 1916. The total average value per ton increased from $6.28 in 1916 to $7.61 in 1917, and the gold and silver in this ore from 15 cents to 19 cents a ton. Nearly all of the ore, or 3,685,395 tons, was of concentrating grade and produced 261,987 tons of concentrate, most of which contained copper, there being only a small quantity of lead concentrate recovered at one property. The ores of smelting grade, shipped directly to smelters, aggregated 108,854 tons and contained 1,552.85 ounces of gold, 216,830 ounces of silver, 11,900,743 pounds of copper, 867,039 pounds of lead, and 11,322 pounds of zinc, valued in all at $3,535,391, or an average value per ton of $32.48. In 1916 the shipments of ore aggregated 53,746 tons, valued at $1,997,613, or an average value per ton of $37.17. At gold and silver mills 2 tons of ore were treated, which produced 91.14 ounces of gold and 135 ounces of silver. No placer bullion was reported in 1917.

Casa Grande district.—Nine producers reported the output of 1,533 tons of ore, containing $145 in gold, 7,493 ounces of silver, 172,326 pounds of copper, 33,014 pounds of lead, and 11,322 pounds of recoverable zinc, valued in all at $57,358, or an average value per ton of $37.42. All of this ore was of smelting grade, the largest part of it being oxidized copper ore from the Lake Shore property treated at Sasco. There were also important shipments from the property of the House Mines Copper Co. Shipments of similar ore came from the Copperosity, Republic & Reward, Vekol, and Security properties.

Mineral Creek or Ray district.—The greater part of the district ore output was from the Ray Consolidated property. There were, however, considerable shipments of crude ore from the Copper Butte mine, the Arizona-Hercules mine, and the Ray Silver Lead property.

In 1917 the Ray Consolidated mine[1] produced 92,207,356 pounds of copper, from which smelter deductions were made, leaving a net production of 88,582,649 pounds. The annual report contains the following paragraphs:

During the year 3,560,704 tons of ore were mined, leaving the ore reserves of 89,812,522 tons, averaging 2.048 per cent copper. As there was no recalculation of the entire ore body made this year, these results are obtained by difference. At regular periods, however, during the balance of the life of the property, new calculations of the ore reserves will be made whenever develop-

[1] Ray Consolidated Copper Co. Ninth Ann. Rept., for year ending Dec. 31, 1917.

Digitized by Google

ment work indicates that this should be done, in order to state the ore reserves correctly. * * *

The total amount of ore mined from all sources during the year and shipped to the reduction works at Hayden was 3,621,233 tons, an average of 9,921 tons per day, containing 1.681 per cent copper. This is an increase of 7.7 per cent over the year 1916, when the total production was 3,363,466 tons, or an average of 9,190 tons per day. Of the ore received at the mill for 1917, 3,558,080 tons, equivalent to 9,748 tons per day, and averaging 1.635 per cent copper, was milling ore; the remainder, 63,153 tons, averaging 4.28 per cent copper, was sorted or selected ore which was diverted to the smelter for direct smelting.

The mining costs for the year were $1.09, of which $0.0466 per ton was due to coarse crushing and loading, leaving the net mining cost $1.04. The tonnage produced from the No. 3 shaft was not obtained by the regular caving system used at the balance of the property, but was extracted through the use of the square-set system of mining, which is approximately four times as expensive as the regular method. Eliminating this tonnage, the average mining cost was $0.99. These costs are higher than those for the previous year, when the mining cost was 69.12 cents, the difference being largely occasioned by the advance in the cost of supplies, which shows an increase of 32 per cent, and an even greater increase in wages paid, amounting to 51.7 per cent over those prevailing during normal times. During the coming year costs will undoubtedly be still higher, as supplies are becoming more expensive.

The most extensive improvement was the development of an entirely new method in treating the finer or slime products of milling operation. This department is now giving final treatment to approximately 75 per cent of the total tonnage. Work has also been started on the installation of additional fine grinding machinery which will further tend to improve metallurgical results, as particles of mineral now remaining encased in the waste portions of the ore will be liberated and made amenable to recovery. * * *

The total ore milled for the year was 3,560,900 dry tons, corresponding to a daily average of 9,756 tons, as compared with 9,105 tons during 1916. The total tonnage of ore milled since the beginning of operations and to the end of 1917 was 16,782,600 tons, averaging 1.678 per cent copper. The average grade of the ore milled for 1917 was 1.635 per cent copper; the average recovery for the year 74.53 per cent of the entire copper content, equivalent to 24.37 pounds of copper per ton.

The concentrate production for the year was 229,197 tons containing an average of 18.935 per cent copper. * * *

The recovery of copper occurring in the form of sulphides was 83.32 per cent, while that existing as oxides and carbonates, which are not readily amenable to concentration, yielded only 33.48 per cent. Experiments are now being conducted, with encouraging results, with a view to improving oxide and carbonate recoveries.

The cost of milling for the year was 82.86 cents per ton, as compared with 55.35 cents for the last year; the same conditions affecting the increased cost at the mine were apparent at the mill, except that there was a greater proportionate increase in the cost of supplies, which at the mill amounted to 51 per cent in excess of that applying in normal periods.

The gross production of copper from all sources was 92,207,356 pounds. This represents an increase of 18 per cent over the gross production of 77,856,713 pounds for 1916. There was produced from the ores delivered without concentrating direct to the smelter a total of 5,409,770 pounds. * * *

The average cost per pound of net copper produced from milling ores, after making allowances for smelting and refining deductions and crediting dividends from the Ray & Gila Valley Railroad and other miscellaneous income as a reduction of operating costs, was 12.141 cents per pound. The combined cost per pound of net copper produced from milling ore and direct shipping ore for the year was 12.229 cents, as compared with 10.267 cents per pound for the previous year. These costs include all operating and general charges, as well as 12.5 cents per ton of ore milled which is applied to the redemption of mine-development costs.

The Ray Hercules property,[1] consisting of 207 acres, is surrounded by the holdings of the Ray Consolidated Co. In 1917, during the construction of the 1,500-ton concentration mill, there was shipped

[1] Ray Hercules Copper Co. Rept. from beginning of operations to Oct. 31, 1917.

Digitized by Google

to the smelters considerable copper ore. As to the quantity of developed ore, the company says in its annual report:

On 13.37 acres of the southwestern portion of the company's ground there was, when the original report was made, estimated to be developed and partially developed 3,428,774 tons of ore having an average assay value of 2.36 per cent copper. This ore was estimated as a result of 16,137 feet of drilling, which had been done prior to September, 1915. Between September, 1915, and February, 1917, 25,864 feet of additional drilling was done. As a result of this drilling and the original drilling, amounting to a total of 42,001 feet, the area is estimated to contain 9,500,000 tons of developed ore having an average assay value of 1.77 per cent copper. Only straight sulphide ore enters into this estimate, and no ore has been taken into consideration beyond the exterior boundaries of lines connecting the drill holes. Nor has any ore been included in my estimate where the drill holes are more than 200 feet apart. The main haulage drift connecting No. 1 shaft and No. 2 shaft and the laterals now being driven therefrom are under the ore body thus far developed by drilling. In the progress of this work more ore is being encountered showing a higher assay value than the average assay value of the ore developed by the drilling.

Old Hat district.—At the Mammoth-Collins mine a 200-ton concentration mill was operated on lead ore, resulting in a concentrate containing wulfenite with some gold. Quite a quantity of tailing was also treated by amalgamation. This property has a vertical shaft on the Mammoth 720 feet deep and an incline shaft 800 feet deep on the Collins. The 200-ton ball mill and concentrating plant was enlarged by the addition of a flotation unit in 1917. The Pearl and the Sunset properties were also producers of oxidized copper and lead ore.

Pioneer district.—Three producers reported production in 1917, the largest one being the Magma mine. The output aggregated 110,572 tons of ore, the larger part of which, 93,975 tons, was milled and produced 32,285 tons of copper concentrate carrying gold and silver. There were also 16,597 tons of crude ore containing copper, gold, and silver, shipped directly to the smelters. The total value of the district production was $3,468,030, or an average value per ton of $31.36.

At the Magma mine[1] 107,529 tons of ore were mined in 1917. This included 13,554 tons of hand-sorted crude copper sulphide ore shipped directly to the smelter, averaging 14.76 per cent of copper and 15.29 ounces of silver and 0.10 ounce of gold to the ton, and 93,975 tons of mill ore averaging 4.02 per cent of copper, 4.38 ounces of silver, and 0.05 ounce of gold. From this mill ore, 16,092 tons of concentrate were produced, containing an average of 10.64 per cent of copper, 11.15 ounces of silver, and 0.14 ounce of gold. The net production from all products, after deducting concentrating, smelting, and refining losses, was 10,148,632 pounds of copper, 537,994.84 ounces of silver, and 5,978.70 ounces of gold. The Magma is opened by a vertical shaft 1,800 feet deep and has a 300-ton mill using gravity concentration followed by flotation. Paragraphs taken from the company's annual report follow:

The net cost of producing copper, including depreciation and all other charges and deducting the revenue from silver and gold, was 16.01 cents per pound and the average selling price was 26.423 cents per pound. The corresponding costs and average selling price for the preceding year were 11.77 cents and 25.433 cents respectively. * * *

[1] Magma Copper Co. Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

During 1917 the No. 2 shaft was sunk from 34 feet below the 1,500 level to 38 feet below the 1,800 level. A station was cut on the 1,600 level, and the main copper ore shoot was partially developed on this level by four crosscuts located an average distance of 60 feet apart. These crosscuts show the vein averages 14.7 feet in width and assays 9.36 per cent copper, 3.82 ounces silver, and 0.03 ounce gold.

During the year diamond-drill holes 15 and 16 were put down from a point in the main crosscut on the 1,500-foot level about 180 feet south of the vein. Drill hole 15 was put down on an angle 60° from the horizontal and pointed due north. This hole passed through the vein at elevations corresponding to the 1,700 and 1,750 foot levels, where commercial ore was indicated.

Drill hole 16 was put down vertically from the same location as 15. It encountered the vein at elevations corresponding to the 2,200 and 2,250 foot levels. As this hole was a deep one, and considerable trouble was experienced due to caving, it had to be abandoned before complete information was secured. Core samples showed copper values in the form of chalcopyrite.

Riverside district.—Three producers reported 132 tons of ore, valued at $4,171, or an average value per ton of $31.60, most of which represents the copper content. The producers were the Prosperity, Sultana, and Troy-Arizona.

Saddle Mountain district.—The Little Treasure property yielded a small quantity of silver ore, which was shipped directly to the smelter.

SANTA CRUZ COUNTY.

Twenty-six producers reported 64,879 tons of ore in 1917, or 34,492 tons more than was reported by 34 producers in 1916. The total value of this ore, containing gold, silver, copper, lead, and zinc, was $1,661,698 in 1917, against $854,605 in 1916. In 1917 the ore sold or treated contained $5,203 in gold, 218,783 ounces of silver, 4,101,176 pounds of copper, 1,839,390 pounds of lead, and 1,945,189 pounds of zinc, valued in all at $1,661,698, or an average value per ton of $25.61. Ore of shipping grade amounted to 41,671 tons and contained most of the copper and some of the lead. The ores produced were classified as copper ore, 47,708 tons; copper-zinc ore, 5,057 tons; lead ore, 3,843 tons; zinc ore, 4,027 tons; lead-zinc ore, 3,240 tons; copper-lead ore, 876 tons; and siliceous ore, 128 tons.

Harshaw district.—Six producers reported 1,314 tons of ore containing $157 in gold, 17,867 ounces of silver, 9,659 pounds of copper, and 426,932 pounds of lead, valued in all at $54,232, or an average value per ton of $41.27. All this ore was of shipping grade, forwarded directly to the smelters. The Flux mine was the principal producer of oxidized lead ore, and smaller quantities were shipped from the Horseshoe, Sunnyside, and World's Fair properties.

Nogales district.—A small production of ore was reported from the Arizona-European property. This was shipped directly to the smelter and contained copper, silver, and gold.

Oro Blanco district.—The most important producer was the Montana property, which was under lease to the Goldfield Consolidated Co. of Nevada. During its investigation considerable lead-zinc ore was produced, which was concentrated in a mill erected especially for its treatment. The property was closed and the lease given up in February, 1918. The operating company[1] reports as follows:

During February an option was taken on the property, and at that time something in excess of 30,000 tons of ore assaying 12 per cent zinc, 6 per cent

[1] Goldfield Consolidated Mines Co. Eleventh Ann. Rept., for year ending Dec. 31, 1917.

Digitized by Google

lead, and 6 ounces silver were considered developed and a small concentrating mill was being erected. It was realized the ore developed was not sufficient to warrant the construction of a mill, but owing to the chance for profit on account of the then high price of base metals and the opportunity that would be afforded for fully determining proper working methods in case the subsequent mine developments should expose additional ore bodies, the mill with accessory construction was completed and is now in operation. The mine development being carried on shows the vein weakening with depth and, while not yet conclusive, indicates future ore reserves will not be of sufficient value to warrant its purchase. At the present time it is apparent the profits from mill operation will not be sufficient to return the amount spent in construction and mine development and a material loss will be incurred.

Palmetto district.—The largest part of 20,311 tons of ore produced in the Palmetto district by 3 operators was from the Three R property, which yielded copper sulphide ore shipped directly to the smelter.

Patagonia district.—Four operators reported a production of 38,563 tons of ore, containing $21 in gold, 173,429 ounces of silver, 3,059,619 pounds of copper, 626,099 pounds of lead, and 1,622,843 pounds of recoverable zinc, valued in all at $1,197,576, or an average value per ton of $31.06. The greater part of the ore, 33,506 tons, was shipped directly to the smelters, and 3,154 tons were milled at concentration plants, yielding 426 tons of copper concentrates and 524 tons of copper-zinc concentrates. The largest producer was the Duquesne property.

Tyndall district.—Five operators reported 989 tons of ore containing $744 in gold, 4,525 ounces of silver, 25,770 pounds of copper, and 225,925 pounds of lead, valued in all at $30,938, or an average value per ton of $31.28. There were 257 tons of ore shipped directly to the smelters and 732 tons were milled, producing 183 tons of lead concentrate, carrying principally silver. A large part of the output came from the Wandering Jew property and consisted of concentrating ore containing lead, silver, and a little copper. The other producers were the Burro, Royal Blue, and Santa Cruz.

Wrightson district.—The American Boy, yielding an oxidized copper ore, was the only producer from which a report was received in 1917.

YAVAPAI COUNTY.

Mine production in Yavapai County, Ariz., in 1916 and 1917.

Year.	Number of producers.	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead.	Recoverable zinc content.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	95	967,558	$1,035,351	1,735,302	109,525,718	265,023	583,741	$29,217,015
1917	88	1,176,644	1,023,464	2,207,583	159,612,146	686,874	950,762	46,572,677
Increase or decrease, 1917	.....	+209,086	−11,887	+472,281	+50,086,428	+421,851	+367,021	+17,355,662

[a] Includes placer production.

Seventy-five deep mines and 13 placers reported a total metal output valued at $46,572,677 in 1917, against $29,217,015 in 1916, when 95 operators of deep mines and placers reported. The total average

Digitized by Google

value per ton of the ore increased from $30.19 in 1916 to $39.58 in 1917, and the gold and silver value in this ore from $2.25 to $2.41. Of the total value of the metals reported, $1,023,464 was for gold, $1,819,048 was for silver, $43,574,116 for copper, $59,071 for lead, and $96,978 for zinc. Compared with that of 1916 the output of each metal shows a substantial increase, with the exception of gold, which was $11,887 less. Ores of smelting grade shipped to various smelters aggregated 1,008,307 tons. Most of this shipment was first-class copper ore (980,644 tons in quantity), of which much the larger part was sulphide ore (954,433 tons) and the remainder was oxidized copper ore (26,211 tons). The total value of the smelting ores was $43,518,241, or an average value per ton of $43.16. There were produced 47,363 tons of dry or siliceous ore, mostly gold ore, the larger part of which was treated at gold and silver mills. Concentrates, amounting to 39,996 tons, derived from 143,811 tons of ore, were smelted and contained $155.463 in gold, 163,957 ounces of silver, 8,657,025 pounds of copper, 28,465 pounds of lead, and 528,360 pounds of zinc, valued in all at $2,710,273, or an average value per ton of $67.76. The placer output amounted to $3,762 in gold and 22 ounces of silver, as against a production of $3,580 in gold and 44 ounces of silver in 1916.

At the concentrating mill and smelter of the Consolidated Arizona Smelting Co., situated at Humboldt, about 1,800,000 pounds of copper is produced monthly from the treatment of about 800 tons of ore daily. Approximately half of the copper production in 1917 was from the ores of the company's mines, the Blue Bell and De Soto, and the remainder from custom material. The concentrator has a capacity of 500 tons of ore per day and treats exclusively the more siliceous ore from the Blue Bell and De Soto mines. No custom ore is milled, and the oxidized domestic ore and basic domestic ore are likewise sent direct to the furnaces. The De Soto ore is all very siliceous, containing 65 to 75 per cent insoluble matter, and is sent to the concentrator, but much of the Blue Bell ore is very basic, and it is more profitable to smelt the ore directly when the percentage of insoluble matter runs below 50 per cent, particularly as the precious-metal content is greater in the more basic ore, and the recovery of it is better in direct smelting than in concentration followed by smelting.[1]

Agua Fria district.—Three producers reported 39,853 tons of ore, nearly all of which was of milling grade, producing copper concentrate carrying silver and a little gold. In addition to the 5,875 tons of concentrate recovered from the milling ore, there were 1,142 tons of ore, containing copper, shipped directly to the smelters. The Binghampton was the largest producer of milling ore, which was treated in its flotation mill, which has recently been increased to a capacity of 250 tons of ore daily. The Copper Queen property, situated near by, also had treated at this mill some of the ore taken out during development work. The Binghampton property is opened by a 1,000-foot adit and a 600-foot shaft, with about 4,000 feet of workings. The ore is chalcopyrite with some iron pyrite and tetrahedrite disseminated in the Yavapai schist. 9 recent article,[2] describing the

[1] Milnes, P. R., Concentration and smelting at Humboldt, Ariz.: Min. American, Apr. 15, 1918, pp. 3–5.
[2] Min. and Sci. Press, Aug. 4, 1917, p. 174.

Digitized by Google

new flotation mill and the mine, states that the ore stopes are 20 feet wide and from 100 to 200 feet long. One-fifth of the output of the mine is coming from the 600-foot level from new development work.

Big Bug district.—The reports of 18 operators gave a production of 109,736 tons of ore, containing $146,400 in gold, 191,870 ounces of silver, 6,774,730 pounds of copper, and 256,194 pounds of lead, valued in all at $2,176,035, or an average value per ton of $19.83. The greater part, or 61,355 tons, was milled with a recovery of 19,557 tons of concentrates, containing 3,465.58 ounces of gold, 80,630 ounces of silver, and 3,739,510 pounds of copper. The ore treated in gold and silver mills aggregated 606 tons and yielded bullion containing 380.50 ounces of gold and 465 ounces of silver. Some of this ore was reported to have produced concentrate, which is included in the figures above. The Blue Bell mine was the largest producer of ores of milling and smelting grade, containing copper, silver, and a little gold. All of the ore from this mine was hauled by railroad from Mayer to Humboldt, where the more basic ore and oxidized ore are smelted and the remainder reduced to concentrate, which is smelted. The Blue Bell ore deposit is the result of replacement in schist by chalcopyrite and pyrite, accompanied by secondary silicification. Six ore bodies have persisted with practically the same dimensions on each level from the surface to the deepest workings at 1,200 feet. These ore bodies range in length from 100 to 400 feet and in width from 5 to 25 feet. Two systems of mining are in use—"cut and fill" and overhead stoping on ore or "shrinkage stoping." The latter method predominates and the former is employed only where the stope walls are bad, by reason of severe faulting. The ore is hoisted to the surface in skips through a 3-compartment shaft and dumped into bins, from which it is drawn for the buckets of the aerial tramway, to be carried 3 miles to the railroad. There it is loaded in 40-ton cars for the 12-mile haul to Humboldt over the Crown King branch of the Santa Fe system. The Blue Bell mine's present production is 10,000 tons of ore a month, and the mining cost, including development, is $2.75 to $3 per ton f. o. b. cars Bluebell siding.[1]

For a short time the Big Ledge Copper Co., operating the Henrietta and Butternut mines, smelted its ores in the furnaces situated at Mayer, owned by the Great Western Smelting Co. This plant was closed down for an indefinite period after a short operation in 1917. Lead ore was produced from the Arizona National property, and several small shipments were made from prospects in the district. Some gold bullion and concentrate were recovered from ores mined from the Union property, operated by a new company in 1917.

Black Canyon district.—Two producers reported ore containing gold, silver, copper, and lead valued at $420.

Black Hills district.—A small quantity of ore, containing copper and a little silver, came from the cleaning up of the old works of the Yaeger Canyon property, recently taken under control by the Shannon Copper Co., of Clifton. During the first part of 1918 considerable development work was being done, and the mine will probably produce within that year.

[1] Milnes, P. R., Concentration and smelting at Humboldt, Ariz.: Min. American, Apr. 15, 1918.

Digitized by Google

Black Rock district.—A small quantity of ore, mined from two properties in the district, was reported to have been shipped to the sampling works at Wickenburg, where it was sold for its copper and silver content.

Castle Creek district.—Some ore was shipped to the Wickenburg sampler from the Empress Copper property, the only producer in the district.

Copper Basin district.—The most important operations were carried on at the Copper Basin and Senator properties. All of the ore contains copper and is of shipping grade. The mines are operated by the Phelps-Dodge Corporation,[1] whose annual report gives details as follows:

> There were shipped from the Copper Basin mine 17,299 dry tons of ore containing 934,781 pounds of copper, yielding us $166,090. Of the above tonnage, 762 tons, containing 42,286 pounds of copper, were shipped during the month of December, 1916, and settled for in January, 1917, returning $10,207.57. Also there are approximately 2,700 tons of ore in transit to the smelter unsettled for, which were shipped during the month of December, 1917, and which are not included in the above tonnage for the year. Of the 17,299 tons of ore shipped, 11,658 tons went to the United Verde Copper Co. smelter at Jerome, 4,253 tons to the Copper Queen smelter at Douglas, and 1,388 tons to the Consolidated Arizona smelter at Humboldt, Ariz.
>
> Development and prospecting work totaled 1,250 feet, and ore reserves in sight at the end of the year compare favorably with those of the beginning of the period.
>
> On the Senator group there was driven about 600 feet of new openings, and 800 feet of the Snoozer tunnel was cleaned out and repaired, preparatory to mining the known ore body in the Snoozer vein. Only one carload of ore was shipped during the year, containing 35 tons, the values being largely in gold and silver.

Eureka district.—The development of the Copper King mine and the building of a road connecting this property with the railroad 29 miles distant were carried on during 1917. During this time shipments of zinc sulphide ore were made to a smelter in Arkansas. Work at the surface exposed an important deposit of low-grade oxidized copper and zinc ores, which led to prospecting the deposit in the hope of finding a copper ore body, but instead a very large zinc deposit was opened to a depth of about 200 feet by an incline shaft. The oxidized zinc ore was replaced by sulphides 50 feet from the surface.

Hassayampa district.—Eleven producers reported the output of ore and 2 placer operators reported bullion in 1917. From the deep mines 2,294 tons of ore were produced, of which 614 tons were shipped directly to the smelters, yielding principally lead, a little copper, gold, and silver. At the milling plants 1,680 tons of ore were treated, yielding gold and silver bullion and a small tonnage of lead concentrate. The total output of the district, including that of the placers, amounted to $10,094 in gold, 13,873 ounces of silver, 12,786 pounds of copper, and 163,780 pounds of lead, valued in all at $39,101. The Big Pine, Davis, Crook, Surprise, and Holden properties were the largest producers.

Humbug district.—Production was reported from two properties, the Golden Central and the Marietta, each of which shipped ore containing copper.

[1] Phelps-Dodge Corporation Ann. Rept. for year ending Dec. 31, 1917.

Digitized by Google

Peck district.—Low-grade copper ore mined from the De Soto property and shipped to Humboldt for concentration and smelting formed the principal part of the district output. There was also a small shipment of lead ore from the Swastika property.

The ore deposit of the De Soto mine is due to a replacement in schist by chalcopyrite and pyrite, accompanied by secondary silicification. There are six ore bodies which have persisted with practically the same dimensions from the surface to the deepest workings. The mine is worked through the 2,000-foot adit, which corresponds to the 600-foot level of the mine. Five levels have been opened above the adit and two below it. The mine's production of 150 tons per day is hauled by mules from ore pockets on the adit level to bins on the upper terminal of the aerial tram, a distance of 2,300 feet. The tram line is 4,000 feet long and operates by gravity, there being a difference in elevation of 1,000 feet between the two terminals. The De Soto ore bodies range in length from 50 to 120 feet and in width from 5 to 40 feet. The walls stand firmly, and "shrinkage" stoping is the only method employed. The mining cost,[1] including development, sorting, and tramming, is $2.55 per ton, and freight to Humboldt (25 miles distant) is 70 cents, making the ore cost $3.25 per ton f. o. b. Humboldt.

Pine Grove district.—Ore produced from the Wildflower mine and tailings from the old Crown King mine were treated in the Bradshaw reduction works, a concentration plant which was reconstructed with modern equipment and first operated in 1916.

Silver Mountain district.—The Rose Mary group yielded some bullion from ores treated in a neighboring stamp mill, and a small parcel of very rich gold ore was shipped to the smelter.

Tiger district.—The old mill of the Tiger Gold mine was put in operation by the Bradshaw Reduction Co. and was used in re-treating mill tailings from the former Tiger operations. The Cougar and Nelson properties also produced.

Turkey Creek district.—Four producers in 1917 reported 46 tons of ore, which yielded gold, silver, copper, and a little lead, valued at $1,878.

Verde district.—In 1917 six producers reported the output of 949,094 tons of ore, containing $753,314 in gold, 1,884,673 ounces of silver, 145,983,703 pounds of copper, and 205,817 pounds of lead, valued in all at $42,177,535, or an average value per ton of $44.44. All of the ore produced, with the exception of 15,881 tons, which was milled and produced gold and silver bullion, was of smelting grade and was treated at the smelters at Clarkdale, Douglas, Globe, and Humboldt. The producers were the Copper Chief, Dundee, Jerome Verde, United Verde, and United Verde Extension.

Copper sulphide ore shipped to custom works from the United Verde Extension mine[2] aggregated 115,064 dry tons, containing 63,242,784 pounds of copper, 1,656 ounces of gold, and 332,536 ounces of silver. These figures represent 95 per cent of the metallic content. The construction of a smelter was commenced during 1917. An adit connecting the 1,300-foot level of the mine has been completed for

[1] Milnes, P. R., Concentration and smelting at Humboldt, Ariz.: Min. Am., Apr. 15, 1918.

[2] United Verde Extension Mining Co. Directors' report for year ending Dec. 31, 1917. The story of the United Verde Extension mine and the district is interestingly written by T. A. Rickard (Min. and Sci. Press, Jan. 5, 1918, p. 9).

Digitized by Google

4,133 feet. A standard-gage railroad 3.2 miles long was completed between the smelter site and the portal of the adit.

Important interests have been prospecting ground adjoining the larger producers, but so far without disclosing any large ore body. Some of these developments are mentioned in a recent article[1] as follows:

Dundee was closed down pending completion of arrangement by which it will use the new Verde Extension traffic tunnel to gain entrance and make a raise from around the 900-foot level to the shaft it has been sinking. Costs of pumping and hoisting will be dispensed with under this plan. Jerome Victor Extension is expecting to recover the 1,200-foot level from the water and resume development there at an early date. The 1,200-foot has been opened slightly; the showing there is promising for the small extent that it has been possible to follow it. Water increases, pump troubles, and machinery breakdowns have interfered at several times. The Verde Extension new blower has greatly improved conditions underground. The fire area has about been disposed of. Progress with the smelter of this company is going on well. The Verde Combination ore find on the 600-foot is near the Gadsden line and is encouraging, although more depth is considered requisite to establish individual value for the strike. The Calumet Jerome is in the same situation, requiring more depth to enable deductions of value. The Del Monte closing-down is apparently for an indefinite period, although additional equipment was received and in course of installation when the closing order came, while a year's stock of general supplies is on hand at the camp and there is an abundant sum of money in the treasury for another year's work. Labor is plentiful in the district, a surplus having been on hand for some time. The demand for an increase of $1 per day both above and below ground will probably be adjusted by Administrator Meyers. The I. W. W. disturbing elements are held to be responsible for the demands. Costs of living in the district are asserted at this time to be no higher than when the present wage scale was agreed upon in June. The administrator is now investigating the costs of living, upon alleged increase in which the demand for higher pay is based. The present wage is $5.15 per day.

Walker district.—Including the production of four deep mines and six placers, the output of the district aggregated $7,723. The ore produced, 132 tons, containing principally gold and silver with a little copper, was shipped directly to the smelters. The placers alone yielded $2,412 in gold and 15 ounces of silver, against a production in 1916 of $1,366 in gold and 9 ounces of silver.

Walnut Grove district.—The McMahon group reported the shipments of some oxidized copper ore containing gold, which was shipped to the Humboldt smelter.

Weaver district.—The Monica property was the principal producer of ore in 1917 and treated about 3,500 tons in its amalgamation and cyanide mill. The output of this property combined with the production reported by three placers aggregated $13,375 in gold and silver.

YUMA COUNTY.

Fifty-two deep-mine operators in Yuma County in 1917 reported the output of 47,233 tons of ore, which was 7,626 tons less than was reported by 45 producers in 1916. The total average value per ton of this ore increased from $21.58 in 1916 to $21.95 in 1917, but the gold and silver value decreased from $1.25 to 90 cents. The total value of the gold, silver, copper, and lead produced in the county was $1,042,233, as against an output valued at $1,190,362 in 1916. The placer production amounted to $5,586 in gold and 61 ounces of silver,

[1] Min. and Sci. Press, p. 135.

Digitized by Google

against a recovery of $6,249 in gold and 61 ounces of silver in 1916. Ore of shipping grade aggregated 43,565 tons, containing 1,775.48 ounces of gold, 4,550 ounces of silver, 3,577,617 pounds of copper, and 54,752 pounds of lead. At gold and silver mills there were 29 tons of ore treated, which produced 23.15 ounces of gold and 14 ounces of silver.

Castle Dome district.—Eight deep mines and three placers reported the production of ore and bullion valued at $21,955, of which $20,133 was from 3,688 tons of ore containing gold, silver, and lead and $1,822 represented the placer production. The Hull mine was the principal producer, and smaller yields were made by the Big Eye, Lady Edith, Ophir, Sonora, and Silver Dollar properties.

Cienega district.—Four deep-mine producers reported 1,783 tons of ore of shipping grade containing $11,699 in gold, 1,297 ounces of silver, 307,592 pounds of copper, and 288 pounds of lead, valued in all at $96,766, or an average value per ton of $54.27. The Empire-Arizona was the largest shipper of oxidized copper ore. This property is opened by a 300-foot shaft on the Carnation claim and by a 240-foot two-compartment shaft on the Eagle's Nest claim. These claims are said to show three large veins occurring at the contact of porphyry with limestone and schist. Outcrops of iron oxide carry copper. Several shipments were made from the Billy Mack mine, which was sold to the Illinois Arizona Copper Co. in September. A carload of oxidized copper ore was also shipped from the Nellie property, and various prospects produced ore which was shipped to the sampling works at Wickenburg.

Ellsworth district.—Seventeen deep-mine producers and 2 placers reported an output valued at $85,600. There were 925 tons of ore produced in the district containing $12,517 in gold, 304 ounces of silver, and 259,653 pounds of copper, with an average value per ton of $90.44. The placer yield was $1,919 in gold and 34 ounces of silver. The Critic property was the principal producer, yielding a sulphide copper ore, which was shipped directly to the smelter. There were smaller productions from the Black Reef, Copper Bell, Jerome Wenden, Bullard, Cracker Jack, True Blue, Vindicator, Wenden Copper, and Verde properties.

Kofa district.—One small lot of gold ore was shipped from the district in 1917, probably from one of the old mines.

Planet district.—The output of five deep mines aggregated 40,196 tons of smelting ore, containing $710 in gold, 612 ounces of silver, 2,974,923 pounds of copper, and 779 pounds of lead, valued in all at $813,434, or an average value per ton of $20.24. The principal part of the ore came from the Swansea lease on the Clara copper property at Swansea and was shipped to Humboldt and Sasco. The New Planet mine was also a producer of copper sulphide ore. This property is opened by a vertical shaft 668 feet deep.

Plomosa district.—The output of 11 deep mines and 5 placers in 1917 was valued at $22,522. There were 635 tons of ore produced, containing $11,232 in gold, 534 ounces of silver, and 35,449 pounds of copper and having a total average value per ton of $33.62. The placer output amounted to $1,162 in gold and 12 ounces of silver. The Dutchman was the largest producer, yielding gold ore of shipping grade. There was also some ore shipped from the Desert, Excelsior, Gold Hills, Little Butte, and Cosmos properties.

Digitized by Google

REDUCTION PLANTS IN ARIZONA.

A list of reduction plants in Arizona was published in Mineral Resources for 1911 (Part I, pp. 427–430). The following list has been revised from that list to the extent of adding the names of new plants and their equipment and of noting changes in the equipment of old mills that now use modern methods. The names of some plants that appeared in the former list have been omitted, as they are reported to be partly or entirely dismantled:

Reduction mills in Arizona in 1917.

[A, active; B, idle; C, under construction.]

Name.	District.	Process.	Equipment.	Approximate maximum daily capacity.
				Short tons.
Cochise County:				
King Copper Co. (C).	California	Concentration	In course of construction	125
Paradise (custom) (A).	do	do	1 crusher, rolls, 1 Huntington mill, 1 classifier, 2 Deister tables.	75
Middlemarch (A).	Cochise	Flotation	Telsmith gyratory crusher, ball mill 6 by 6, Akins classifier, flotation machines.	100
Grand Central (for tailings). (C).	do	Roasting and amalgamation.	Roaster and pans	100
Huachuca (B)	Hartford	Concentration	Crusher, tables	6
Reef (A)	Huachuca	do	Blake crusher, rolls, Allen cone classifiers, 1 Deister and 1 Wilfley table.	70
Tombstone (A)	Tombstone	Concentration, flotation, and cyanidation.	2 Blake crushers, 40 stamps, rolls, 1 tube mill, 2 Dorr classifiers, 12 Wilfley tables, K. & K. flotation machine (experimental), 5 Parral tanks, 2 percolation tanks, 1 Oliver filter.	300
Commonwealth (A).	Turquoise	Cyanidation	40 stamps, 3 tube mills, Dorr classifier, 2 Pachuca tanks, 7 agitation tanks, 4 Oliver filters (partly dismantled in 1917).	300
Copper Queen (A)	Warren	Concentration and flotation.	Telsmith No. 5 crusher, rolls, Hardinge mill, 2 drag and 1 hydraulic classifier, 2 Senn pan motion vanners, 3 Butchart tables, flotation machines.	100
Shattuck-Arizona (C).	do	Gravity concentration, sulphidizing, and flotation.	1 gyratory crusher, Traylor rolls, 2 Marcy mills, 1 tube mill, 5 Allen cone classifiers, 5 coarse and 3 fine Butchart tables, K. & K. and Park flotation machines.	400
Coconino County:				
Bridal Veil (A)	Cataract Canyon	Concentration	1 set of rolls (9 by 12 inches), jigs.	10
Gila County:				
Dripping Spring (A).	Dripping Springs.	Amalgamation and concentration.	Gardner grinder, jigs	5
Inspiration (A)[a]	Globe	Flotation followed by gravity concentration.	Crushers (at mine), 40 Marcy ball mills, 40 Dorr and 19 drag classifiers, 220 double-deck Deister tables, pneumatic flotation, machines 8 Oliver filters.	18,000

[a] Gahl, Rudolf, History of the flotation process at Inspiration: Am. Inst. Mech. Eng. Trans., vol. 55, pp. 576–647, 1917.

Digitized by Google

Reduction mills in Arizona in 1917—Continued.

Name.	District.	Process.	Equipment.	Approximate maximum daily capacity.
				Short tons.
Gila County—Continued.				
Miami (A)	Globe	Concentration and flotation.	2 gyratory crushers, 17 Hardinge mills, 9 Dorr, 24 Deister and 28 Richards classifiers, 132 Deister slime and 40 Deister sand tables, pneumatic flotation machines, 3 Oliver filters.	6,000
Old Dominion (A)	do	Concentration and flotation (two mills).	2 Traylor rolls, 1 Marathon and 5 Hardinge tube mills, 18 Deister classifiers, 18 Deister tables, 4 Senn vanners, 2 Overstrom tables, flotation machines, 2 Oliver filters.	400 (old mill), 800 (new mill).
Yo Tambien (Pinto Creek) (B).	do	Concentration	2 jaw crushers, 3 Allis Chalmers rolls, 3 classifiers, 1 Hancock jig, 2 Standard and 2 Wilfley tables.	100
Kellner (Yellow Metal) (B).	Lost Gulch	Concentration and cyanidation.	Gates crusher, 10 stamps, 2 Wilfley tables, 2 vanners, tanks.	20
Ray Consolidated (A).	At Hayden	Concentration	16 Garfield rolls, 24 6-foot Chilean mills, 89 Richards Janney classifiers, 550 Isbell vanners, Harz jigs, 100 Wilfley tables, 176 special Garfield tables.	10,000
Graham County:				
Copper Glance (A).	Bunker Hill	Concentration and flotation.	Blake crusher, Marcy mill, Dorr classifier, 6 Wilfley tables, Callow flotation machines.	140
Graham Consolidated (B).	Clark	Amalgamation and concentration.	1 crusher, 2 Tremain stamps, 1 Wilfley table.	16
Lost Mexican (A)	Unorganized (5 miles east of Bonita).	Amalgamation	Crusher, 1 Wilfley table	5
Greenlee County:				
Detroit Copper (A).	Copper Mountain	Concentration and flotation.	3 Symons crushers, 6 Colorado rolls, 5 Marathon tube mills, 4 Dorr Franz classifiers, 38 Frue and 1 Senn vanner, 25 Wilfley and 6 Overstrom tables, Mineral Separation flotation machines, 2 Oliver filters.	1,500
Gold Belt (B)	do	Amalgamation and concentration.	Crusher, 5 stamps, 1 Frue vanner.	5
Buzzard Shadow (B).	do	Amalgamation	Crusher, 4 Nissen stamps, copper plates.	8
Arizona Copper (A).	Greenlee	Gravity concentration and flotation (two mills).	Morenci mill: 1 McCully gyratory and 2 Symons crushers, 2 Superior and 13 Arizona rolls, 12 Hardinge and 2 other tube mills, 12 Dorr classifiers, 79 Frue and 24 Isbell vanners, 108 National tables, 63 Callow roughing cells, 18 Callow cleaning cells, 2 Oliver filters.	4,000
			Clifton mill: 2 Marcy mills, 8 National tables, 12 Callow roughing cells, 4 Callow cleaning cells, 16 double-deck Deister slime tables, 2 Hardinge mills, 2 drag belt classifiers.	500
Shannon (Custom) (A)	do	Concentration and experimental flotation.	2 crushers, 2 roller mills, 1 tube mill, Allen cones, Janney classifiers, 20 vanners, 12 Wilfley tables, flotation machines.	500
Smart (B)	do	Amalgamation and concentration.	Blake crusher, 1 Nissen stamp, 1 Wilfley table.	10
Maricopa County:				
Relief (B)	Agua Fria	Amalgamation and cyanidation.	Crusher, 1 Lane mill, Allis Chalmers rolls, 4 50-ton tanks.	25

Digitized by Google

Reduction mills in Arizona in 1917—Continued.

Name.	District.	Process.	Equipment.	Approximate maximum daily capacity.
Maricopa County—Continued.				*Short tons.*
Fort Worth (B)..	Cave Creek.....	Amalgamation and concentration.	5 stamps, 1 table.....	15
Vulture (A).....	Vulture.....	Amalgamation, concentration and cyandiation.	Gates No. 5 crusher, 20 stamps, 3 5-foot Australian grinding pans, 1 Dorr classifier, 3 Wilfley (No. 5) and 6 Deister slime tables, 200-ton cyanide mill, 4 Dorr 30-foot agitation tanks.	100
Arizona Vermont (B).	White Picacho...	Amalgamation and concentration.	Sampson crusher, Ellspass mill, 1 plate, Wilfley table.	15
Sturdy (B).....	Winafred.....	.....do.....	Stamps, tables.....	25
Mohave County:				
Doyle (B).....	Aubrey.....	Amalgamation and cyanidation.	2 percolation tanks.....	1
Graystone (B)...	.....do.....	Cyanidation.....	5 stamps, 1 tank.....	3
Copperville (B)...	Cedar Valley.....	Concentration.....	2 Symons disk grinders, 2 Webb City rolls, Overstrom classifier 14, Overstrom tables.	100
Leviathan (A)...	.....do.....	Concentration and flotation (of molybdenum).	Crusher, rolls, 1 Akins classifier, Mineral Separation flotation.	50
San Francisco (B)	.....do.....	Amalgamation and concentration.	Blake crusher, 10 stamps, hydraulic classifier, 1 Frue vanner.	30
Yucca Tungsten (A).	.....do.....	Concentration.....	2 Universal crushers, 2 hydraulic and 1 Bunker Hill classifiers, 3 Card and 4 Wilfley tables, 3 Harz jigs.	50
Walkover (B)....	Cottonwood.....	Amalgamation and concentration.	1 crusher, 14 stamps, 1 Gates table.	20
Cyclopic (B).....	Gold Basin.....	Cyanidation.....	Dodge crusher, 1 set of Dodge rolls, 5 50-ton Wood tanks.	100
Golden Burro (B)	Greenwood.....	Amalgamation.....	2 stamps, plate.....	5
Nevada Arizona (A).	Hackberry.....	Amalgamation, concentration, and cyanidation.	Dodge crusher, 1 6-foot Allis Chalmers Chilean mill, 1 Isbell table, 10 agitation tanks.	50
Gold Flats (B)..	Maynard.....	Amalgamation and concentration.	Dodge crusher, 3 stamps, Wilfley table.	12
Arizona & Eastern (B, C).	.....do.....	Amalgamation and cyanidation.	Blake crusher, 2 stamps (cyanide plant under construction).	10
Moyle (B).....	.....do.....	.....do.....	Crusher, 1 stamp, 3 tanks, 1 filter.	4
Frisco (B).....	San Francisco....	Cyanidation.....	Blake crusher, 3 rolls, 2 tube mills, 2 Dorr classifiers, 2 Dorr thickeners, 6 300-ton Pachuca tanks (agitation), 2 Kelly filter presses.	100
Gold Road (B)...	.....do.....	.....do.....	Gates No. 5 crusher, 40 stamps, 4 tube mills, 6 Dorr duplex classifiers, 16 ore tanks, 3 Pachuca agitation tanks, 2 Dahne slime presses, Butter filter.	300
Secret Pass (B)..	.....do.....	Amalgamation.....	5 stamps, plates.....	20
Pioneer (B).....	.....do.....	Amalgamation and cyanidation.	Blake crusher, 10 stamps, 7 30-ton tanks.	35
Ruth-Kattan (B)	.....do.....	Cyanidation.....	Gates crusher, 8 stamps, 1 Allis Chalmers tube mill, 3 agitation tanks.	60
Tom Reed (A, C).	.....do.....	.....do.....	Austin gyratory crusher, 20 stamps, 3 Allis Chalmers ball mills (1 primary grinder and 2 regrinders), 5 Dorr classifiers, 4 Dorr agitators, 9 Dorr thickeners, 2 Merrill filters.	300

Digitized by Google

Reduction mills in Arizona in 1917—Continued.

Name.	District.	Process.	Equipment.	Approximate maximum daily capacity.
				Short tons.
Mohave County—Continued.				
United Eastern (A, C).	San Francisco	Cyanidation	Telsmith No. 6 gyratory crusher, 2 Marcy mills, 3 Allis-Chalmers concave tube mills, 2 Simplex and 3 Duplex Dorr classifiers, 7 Dorr agitators, 7 Dorr thickeners.	275
Vivian (B)	do	Amalgamation	10 stamps, plates	40
Bi-Metal (B)	Wallapai	do	Blake crusher, 10 stamps, 1 Huntington mill.	35
Arizona Butte (A).	do	Concentration	Crusher, 2 Davis rolls, 1 Delano classifier, 6 Butchart and 1 Wilfley tables (plan jigs and flotation).	150
Emerald Isle) (A, C).	do	Sulphuric-acid leaching and electrolytic precipitation.	1 Dodge crusher, 4 leaching tanks with filter bottoms, 16 cells with lead anodes.	40
Flores (B)	do	Amalgamation	Blake crusher, 5 stamps, ore feeder plates, Gilpin and canvas tables.	15
Washington Arizona (C).	do	Flotation	Fields flotation machines	300
Gem (A)	do	Amalgamation and concentration.	Crusher, 4 Nissen stamps, 3 Standard tables.	30
Keystone (A)	do	Concentration and flotation.	1 Blake crusher, 1 ball mill, 1 Akins classifier, 3 Wilfley tables, Mineral Separation flotation, 1 Dorr thickener.	150
Midnight (B)	do	Amalgamation	10 stamps, plates	30
Minnesota (B)	do	Concentration	1 Dodge and 1 Blake crusher, Chilean mill, 3 Frue vanners, 10 Wilfley tables.	150
Oro Plata (B)	do	do	1 crusher, 2 Nissen stamps, 3 vanners.	15
Union Basin (A).	do	Concentration and flotation.	Crusher, rolls, tables, flotation machines (destroyed by fire October, 1917).	200
Tennessee (custom) (A).	At Needles, Cal.	do	Jaw crusher, 3 rolls, 1 tube mill, 3 classifiers, 3 Johnson and 1 Isbell vanners, 3 Wilfley and 3 Deister tables, flotation machines, 2 Portland filters.	240
Utah-Arizona (A)	Weaver	Amalgamation and concentration.	1 Blake crusher, 5 stamps, plates, 1 Lane mill, 2 Wilfley tables.	50
Pima County:				
New Cornelia (A)	Ajo	Sulphuric-acid leaching and electrolytic precipitation.	5 Gates gyratory crushers, 12 Symons vertical disk pulverizers, 12 leaching tanks 88 by 88 by 15 feet, 5 solution tanks 60 by 90 by 11 feet, 152 electrolytic tanks and lead anodes.	5,000
Old Yuma (B)	Amole	Concentration	Gyratory crusher, 3 rolls, 2 tables.	250
International Tungsten (A).	Arivaca	do	2 crushers, 10 stamps, 8 Wilfley tables, Johnson vanner.	100
Wedge (B)	Pima	do	1 crusher, 1 set of rolls, Lane mill, 1 classifier, 5 tables, jigs.	100
Welden (A)	Quijotoa	Amalgamation and concentration.	Gates crusher, 5 stamps, 3 Standard tables.	25
Isabelle (B)	Saltwell	Amalgamation	Lane mill	40
El Tiro (B)	Silver Bell	Concentration	Huntington mill, Richards classifier, 3 tables.	100
Pinal County:				
Copper State (A).	Bunker Hill	Concentration and flotation.	1 Marcy mill, Dorr duplex classifier, 7 Wilfley tables, 5 Callow cells, 1 Oliver filter.	150
Silver Reef (B)	Casa Grande	Cyanidation	Crusher, 20 stamps, 1 12-foot tube mill, 10 tanks.	50
Vekol (B)	do	Concentration	10 stamps, tables	50
Bulldog (B)	Goldfields	Amalgamation and cyanidation.	2 stamps, 3 percolation tanks	5
Mammoth or Goldfield (B).	do	do	Gates crusher, 20 stamps, 3 50-ton percolation tanks.	50

Digitized by Google

Reduction mills in Arizona in 1917—Continued.

Name.	District.	Process.	Equipment.	Approximate maximum daily capacity.
				Short tons.
Pinal County—Con.				
Ray Hercules (C).	Mineral Creek....	Concentration and flotation.	2 Gates crushers (at mine), 2 Traylor rolls, 6 Hardinge and 3 Marcy mills, 9 Dorr classifiers, 15 Overstrom tables, 42 flotation cells, 3 Oliver filters.	1,500
Campo Bonita (B)	Old Hat.....	Amalgamation and concentration.	5 stamps, tables.....	15
Mammoth Collins (A).	.....do.....	Concentration.....	McCully No. 3 crusher, 1 Marcy mill, 1 Senn pan vanner, 7 Wilfley and 2 Card tables.	175
Superstition Cons. (B).	Pioneer.....	Concentration and flotation.	Crusher, tables, flotation machines.	50
Magma (A).....	.....do.....	.....do.....	2 crushers, 4 tube and ball mills, drag classifier, 13 Wilfley and 4 Deister tables, flotation cells.	350
Silver King (C)..	.....do.....	Concentration and flotation experiments, 1917.	Crusher, Butchart table, K. & K. flotation (plan 50-ton Marcy mill).	100
Superstition Mountain (B).	.....do.....	Concentration.....	Crusher, Huntington mill, 1 double-deck Wilfley table.	20
Kelvin - Sultana (B).	Riverside.....	.....do.....	Gates gyratory crusher, Symons disk pulverizer, rolls, 1 8-foot Hardinge mill, 1 Richards-Janney mill, 5 Wilfley, and 5 Deister tables.	250
Santa Cruz County:				
Montana (A).....	Oro Blanco.....	Concentration and flotation.	Crusher, tables, flotation cells. cells.	100
Duquesne (A)....	Patagonia.....	Flotation and concentration.	Crusher, Marcy ball mill, 2 drag classifiers, 3 Callow cells, 2 Oliver filters.	100
Wandering Jew (A).	Tyndall.....	Concentration.....	Crusher, rolls, 1 classifier, 1 vanner, 1 Wilfley table.	75
Lower California Metals Co. (custom) (C).	Near Nogales.....	Concentration and flotation.	1 Blake crusher, 2 ball mills, 1 Knapp classifier, 2 Wilfley tables, flotation cells.	100
Yavapai County:				
Binghamton (A).	Agua Fria.....	.....do.....	Crusher, Dorr classifier, 3 Deister and 1 Butchart table, Inspiration flotation, 3 Oliver filters.	250
Consolidated Arizona (A)....	Big Bug (at Humboldt).	.....do.....	1 Blake and 1 Symons crusher, 3 Hardinge and 1 Allis Chalmers tube mills, 1 Caldecott classifier, 2 Buchart and 2 Wilfley tables, Mineral Separation flotation, 1 Portland filter.	500
Henrietta (B)....	Big Bug.....	Amalgamation, concentration, and cyanidation.	1 crusher, 20 stamps, 3 Wilfley tables, 12 percolation tanks (old).	60
Fortune (B).....	.....do.....	Amalgamation and concentration.	Jaw crusher, 10 stamps, 3 Wilfley tables.	30
Jones (A).....	.....do.....	.....do.....	Austin No. 2 gyratory crusher, 10 stamps, 2 Wilfley tables, 4 25-ton tanks.	18
Lelan (B).....	.....do.....	.....do.....	Blake crusher, 10 stamps, 2 Wilfley tables.	40
Dividend (B)....	.....do.....	.....do.....	1 crusher, 10 stamps, 1 Wilfley table.	20
Oriental (B).....	.....do.....	.. Concentration.....	2 crushers, 1 Ellspass mill, 1 hydraulic classifier, 2 Standard and 2 Bartlett tables.	40
Poland (B).....	.....do.....	Amalgamation, concentration.	Crusher, 20 stamps, card tables.	100
McCabe - Gladstone (B).	.....do.....	Concentration.....	1 Gyratory crusher, 10 stamps, 3 Standard and 1 Wilfley tables.	65
Golden Belt (B)..	Black Canyon....	Amalgamation, concentration.	1 Dodge crusher, 2 Tremain steam stamps, 1 Wilfley table (plan cyanide mill in 1918).	12

Digitized by Google

Reduction mills in Arizona in 1917—Continued.

Name.	District.	Process.	Equipment.	Approximate maximum daily capacity.
Yavapai County—Continued.				*Short tons.*
Parker (B)	do	do	1 Dodge crusher, 5 stamps, 1 Standard table.	24
Big Blue (B)	Black Rock	Concentration	Bryan mill, 1 Deister and 1 Wilfley table, Deister slimer.	40
Oro Grande (B)	do	Amalgamation	1 Dodge crusher, 10 stamps	60
Dark Horse (B)	do	Amalgamation, concentration, and cyanidation	Crusher, 20 stamps, plates, 6 vanners, 6 percolation tanks.	80
Ventura (B)	Castle Creek	Concentration	1 crusher, 1 modified Lane mill.	5
Gold Lode (B)	Cherry Creek	Amalgamation and concentration.	Blake crusher, 10 stamps, 2 Frue vanners.	40
Federal (B)	do	Amalgamation, concentration, and cyanidation.	Blake crusher, 1 Dorr classifier, 2 Wilfley tables, 6 agitation tanks.	75
Golden Idol (B)	do	Amalgamation and concentration.	1 Blake crusher, 3 stamps, 1 Wilfley table.	10
Statehood (B)	do	Amalgamation, concentration, and cyanidation.	1 crusher, 5 stamps, 1 Standard table, 2 percolation tanks.	15
Verde Inspiration (B).	do	Amalgamation and concentration.	2 crushers, 3 stamps, classifiers, 2 vanners, 2 tables.	21
Arizona Mines & Reduction Co. (custom mill and sampler) (A).	At Wickenburg	Concentration and flotation.	Ball mills, classifiers, 3 Wilfley tables, special flotation (also 200-ton sampler).	50
Hub (B)	Copper Basin	Amalgamation	3 stamps, plates	10
Belle (Miller) (B).	Eureka	do	1 Dodge crusher, 1 Chilean mill.	10
Hillside (B)	do	Concentration	Crusher, 5 stamps, 1 Wilfley table, 1 slimer.	15
Nieman (A)	do	Amalgamation and cyanidation.	Crusher, 10 stamps, 1 agitation tank.	10
Big Pine (A)	Hassayampa	Cyanidation	1 Blake crusher, 1 tube mill, 1 ball mill, 2 classifiers, 3 agitation tanks, Oliver filter (partly destroyed by fire December, 1917).	80
Cash (Y. P.) (B).	do	Amalgamation and concentration.	Blake crusher, 10 stamps, 1 Huntington mill, 1 Monell classifier, 4 Wilfley and 3 Monell tables, 1 Monell slimer.	30
Climax (B)	do	do	Blake crusher, 10 stamps, 2 Wilfley tables.	25
Emporia (B)	do	do	1 Blake crusher, 5 stamps, 2 Wilfley tables.	15
Independence (B)	do	Cyanidation	Jaw crusher, Lane mill, 8 tanks (4 agitation).	20
Juanita (B)	do	Amalgamation	2 stamps, plates	7
Midnight Test (B)	do	Amalgamation and concentration.	1 Blake crusher, 6 Nissen stamps, 1 Frue vanner, 2 new Standard tables.	40
Dunkirk (Castle) (B).	do	Concentration and flotation.	4 Nissen stamps, 3 Wilfley tables, flotation cells.	40
Mount Union (B)	do	Amalgamation and concentration.	Crusher, Huntington mills, plates, tables.	60
Sundance (B)	do	Concentration	1 crusher, 5 stamps, 3 rolls, 1 Standard table.	20
Sunnyside (B)	do	Amalgamation and concentration.	Crusher, Huntington mills, plates, tables.	25
Venezia (B)	do	do	2 crushers, 20 stamps, 2 Wilfley tables.	100
Empire (B)	do	Concentration	Crusher, 10 stamps, 1 table	40
Acquisition (B)	Humbug	Amalgamation and concentration.	1 Austin crusher, 10 stamps, 2 classifiers, 1 Allis Chalmers vanner, 2 Wilfley tables.	20
American Gold (B).	do	Amalgamation, concentration, and cyanidation.	Blake crusher, 10 stamps, 2 Wilfley tables, 40-ton cyanide plant (4 percolation tanks).	20
Congress (B)	Martinez	Concentration and cyanidation.	4 Blake crushers, 40 stamps, 10 Standard tables, 6 Frue vanners, 9 ore tanks.	200
Alaska (B)	do	do	4 Nissen stamps, tables, agitation tanks.	30

Digitized by Google

Reduction mills in Arizona in 1917—Continued.

Name.	District.	Process.	Equipment.	Approximate maximum daily capacity.
Santa Cruz County—Continued.				*Short tons.*
Buster (B)	Pine Grove	Amalgamation and concentration.	8 stamps, tables	20
Old Tiger (B, C)	do	Concentration and flotation.	Blake crusher, ball mill, drag classifier, Callow flotation cells.	100
Derby (Madezille) (B).	Thumb Butte	Amalgamation and concentration.	Crusher, 5 stamps, 1 Frue vanner.	10
Crown King (A, C).	Tiger	Concentration and flotation.	1 Dodge crusher, 1 Allis Chalmers ball mill, 1 Dorr classifier, 6 Wilfley tables, Callow flotation.	75
Lincoln (B)	do	Amalgamation and concentration.	Hendrie & Bolthof crusher, 15 stamps, 2 Allis Chalmers vanners, 3 Wilfley tables.	45
Tiger or Oro Belle (A).	do	do	Jaw crusher, 20 stamps, 2 Wilfley tables.	70
Cumberland (B)	Turkey Creek	do	Crusher, 10 stamps, 2 Wilfley tables.	25
Copper Chief (A)	Verde	Cyanidation	Blake crusher, 1 Stearns Roger ball mill, 1 tube mill, 1 Dorr classifier, 3 Dorr thickeners, 4 Dorr agitation tanks, 2 Oliver filters (contemplate changing process to chloridizing roast).	100
El Toro (B)	Walker	Amalgamation	3 stamps (will add crusher and table).	7
Homestead (B)	do	do	5 stamps, plates	15
Pine Mountain (B).	do	Amalgamation and concentration.	Blake crusher, 10 stamps, 2 Wilfley tables.	20
Mudhole (B)	do	do	Crusher, 3 Huntington mills, 4 Wilfley tables.	100
Malapai (B)	Walnut Grove	do	Crusher, 1 stamp, 1 Standard table.	16
Isabella (Old Spaniard) (B).	do	Amalgamation	Dodge crusher, 1 3½-foot Huntington mill.	12
Rochester (B)	do	Amalgamation, concentration, and cyanidation.	10 stamps, tables, tanks	30
Alvarado (B)	Weaver	Cyanidation	Crusher, 20 stamps, 2 tube mills, cone classifiers, 2 Hendryx & Butters agitation tanks, Butters filters (60 frame).	150
Yarnell (B)	do	Amalgamation and cyanidation.	Blake crusher, 20 stamps, plates, tanks, filter press.	60
Mayflower (B)	do	Amalgamation and concentration.	Crusher, 10 stamps, 2 Wilfley tables.	35
Monica (A)	do	Amalgamation and cyanidation.	20 stamps, plates, tanks	60
Octave (B)	do	Amalgamation, concentration, and cyanidation.	2 Blake crushers, 40 stamps, 6 Wilfley tables, 8 ore tanks (old; will be remodeled).	100
Gold King (B)	do	Amalgamation and concentration.	1 crusher, 2 stamps, 1 Frue vanner.	12
Monarch (B)	White Picacho	Concentration	Crusher, stamps, tables	100
Producer (B)	do		1 180-pound stamp, capacity about 200 pounds of ore in 24 hours, used for sampling.	
Yuma County:				
Big Eye (B)	Castle Dome	Amalgamation and cyanidation.	Blake crusher, 5 stamps, 3 Trent agitation tanks.	10
Hull No. 1 (A)	do	Concentration	Crusher, 2 rolls, 1 Delano classifier, 2 Wilfley tables, and 1 Deister table.	100
Henneys (C)	do	do	Joshua Hendy crusher, 1 Stebbins table.	50
Bonanza & Golden Eagle (B).	Ellsworth	Amalgamation	40 stamps, plates	120
Copper Belt (B)	do	do	10 stamps, plates	40
Socorro (B)	do	Amalgamation, concentration, and cyanidation.	20 stamps, tables, tanks	60
Fortuna (B)	Fortuna	Amalgamation	20 stamps (1,400 pounds), plates.	70

Digitized by Google

Reduction mills in Arizona in 1917—Continued.

Name.	District.	Process.	Equipment.	Approximate maximum daily capacity.
Yuma County—Continued.				*Short tons.*
King of Arizona (B).	Kofa	Cyanidation	Crusher, rolls, tube mills, agitation tanks.	200
Scott (B)	Plomosa	Amalgamation and concentration.	Blake crusher, 1 stamp, 1 Standard table.	7
Stafford (B)	do	Amalgamation	Blake crusher, Lane slow-speed mill.	20
Red Cloud Consolidated (C).	Silver	Concentration	Crusher, 2 sets of rolls, Eggleston ball mill, 3 Stebbins dry tables (burned in 1918).	300

Digitized by Google

IRON ORE, PIG IRON, AND STEEL.[1]

By ERNEST F. BURCHARD.

INTRODUCTION.

Throughout 1917 war-time activity continued to prevail in the iron industry. The phenomenal records of shipments of iron ore and production and shipments of pig iron made in 1916 were not quite reached, owing to unfavorable weather and to shortage of labor, boats, and other transportation facilities, and of coal and coke. Cooperation between furnace men, transportation companies, and ore producers resulted in the successful movement and equitable distribution of ore, without which the production of pig iron would have suffered much more serious handicaps. Government control of prices, supplies, and products also aided in preventing an acute shortage of ore and metal needed for war purposes. The quantity of iron ore mined showed a small increase, contributed by southern and eastern districts.

The American iron and steel industry is the bulwark upon which not only the United States but her allies have depended for munitions, armaments, and ships, and the patriotic response of this industry as a whole to the call for increased production of steel has won grateful public acknowledgment from those in high command.

Extraordinary economic conditions prevailed in 1917. Demand for iron and steel was world-wide and at all times greatly exceeded supply. During the first half of the year, in the absence of regulations and restrictions, prices rose to unprecedented levels and would have gone still higher had the fundamental relations between supply and demand been allowed free sway. In the second half of the year the United States Government became a large purchaser and Federal regulation of prices and distribution of products were put into effect. Production was in nowise curtailed, however, as the war needs of the United States and the allied governments far exceeded the iron and steel making capacity.

Estimates by the Geological Survey of the production, shipments, and stocks of iron ore in 1917 were released on January 24, 1918, and comparison of these figures with the final ones published in this report indicate that the estimates of production and shipments were respectively only 0.05 per cent and 0.1 per cent high, and that stocks was 0.65 per cent low.

[1] The statistics of iron ore, pig iron, and steel were compiled by J. H. Winchell and H. W. Davis, those of ferroalloys by Miss M. B. Clark, and the imports and exports by J. A. Dorsey.

Digitized by Google

IRON ORE.

IRON ORE MINED AND SHIPPED IN 1917.

The iron ore mined in the United States in 1917, exclusive of that containing 5 per cent or more of manganese,[1] amounted to 75,288,851 gross tons, as compared with 75,167,672 gross tons mined in 1916, an increase of 121,179 gross tons, or 0.16 per cent. Beneficiated ore, instead of crude ore mined, is included in these figures, if the ore is treated in any way. The quantity of iron ore shipped from the mines in the United States in 1917 amounted to 75,573,207 gross tons, valued at $238,260,444, as compared with 77,870,553 gross tons, valued at $181,902,277, shipped in 1916. This represents a decrease in quantity of 2,297,346 gross tons, or 2.95 per cent, and an increase in value of $56,358,167, or 30.98 per cent, as compared with shipments in 1916. The average price of ore per ton at the mines for all grades of ore for the whole country in 1917 was $3.15, as compared with $2.34 in 1916. These quantities of ore, both mined and shipped, include the iron ore used for fluxing other metallic ores at smelters in the Western States, but the shipments do not include the iron ore sold for the manufacture of paint. The quantity of iron ore sold for the manufacture of paint in 1917 amounted to 18,656 tons, valued at $56,859, or $3.05 per ton, compared with 16,968 gross tons, valued at $45,256, or $2.67 per ton in 1916.

The ore reported as sold for fluxing other than in the manufacture of pig iron amounted to 107,793 gross tons, valued at $374,441, in 1917, as compared with 88,601 gross tons, valued at $288,089, in 1916. The domestic iron ore actually sold for the manufacture of pig iron amounted in 1917 to 75,465,414 gross tons, valued at $237,886,003, as compared with 77,781,952 gross tons, valued at $181,614,188, in 1916.

A graphic comparison of the annual production of iron ore and its derived metals since 1870 is afforded by the curves shown in figure 6. It must be borne in mind, however, that the figures for the three products are not strictly comparable, because considerable foreign iron ore and also some cinder, scale, and scrap enter into the production of pig iron, and considerable quantities of scrap iron and steel, as well as cinder and scale, enter into the production of new steel.

IRON ORE MINED AND SHIPPED, BY STATES.

Iron ore was mined in 25 States in 1917, as compared with 24 States in 1916, Ohio having dropped out and Arkansas and Montana having been added as producers in 1917. Of these States, California, Montana, and Nevada produced iron ores for metallurgic flux only; part of the production of Colorado, New Mexico, and Utah was used for smelter flux and part for pig iron and ferroalloys; the remaining States produced iron ore mainly for use in blast furnaces, except small quantities used for paint from Georgia, Michigan, New York, Pennsylvania, and Wisconsin. The output in the three States producing

[1] The production of manganiferous iron ore is stated in the chapter on manganese and manganiferous ores in Mineral Resources for 1917.

Digitized by Google

the largest quantity of iron ore—Minnesota, Michigan, Alabama—was about the same as in 1916, and New York and Wisconsin, in addition, each produced more than 1,000,000 tons of ore. The Min-



FIGURE 6.—Curves showing annual production of iron ore, pig iron, and steel in the United States, 1870 to 1917.

nesota iron ranges are producing more iron ore than all the rest of the States together, having furnished nearly 60 per cent of the total for the United States in recent years.

Digitized by Google

IRON-ORE SHIPMENTS.

The following table, showing the iron ore shipped from the mines in 1916 and 1917, by States, is given precedence over the table showing the quantity mined because the table of shipments is the only one in which values are recorded:

Iron ore shipped from mines in the United States, 1916 and 1917, by States.

State.	1916		1917		Increase or decrease in 1917.		Percentage or increase or decrease in 1917.	
	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.	Quantity.	Value.
Alabama	6,801,839	$10,843,231	7,101,586	$13,049,535	+ 299,747	+$2,206,304	+ 4.4	+ 20.3
California	2,970	11,880	2,207	8,828	— 763	— 3,052	— 25.7	— 25.7
Georgia	252,143	413,259	211,501	324,175	— 40,642	+ 110,916	— 16.1	+ 26.8
Maryland	(a)	(a)	10,730	40,423	(b)	(c)	(b)	(c)
Michigan	18,995,797	49,054,340	17,712,916	62,833,624	—1,282,881	+13,779,284	— 6.8	+ 28.1
Minnesota	45,869,251	106,628,784	44,962,127	142,901,148	— 907,124	+36,272,364	— 2.0	+ 34.0
Missouri	34,914	116,484	38,770	134,906	+ 3,856	+ 18,422	+11.0	+ 15.8
New Jersey	528,084	1,877,056	474,708	2,341,160	— 53,376	+ 464,104	— 10.1	+ 24.7
New Mexico	157,779	168,157	231,604	381,275	+ 73,825	+ 213,118	+46.8	+126.7
New York	1,464,917	5,571,429	1,356,011	7,381,333	— 108,906	+ 1,809,904	— 7.4	+ 32.5
North Carolina	(a)	(a)	90,957	445,898	(b)	(c)	(b)	(c)
Ohio	(a)	(a)	0	0	(b)	(c)	(b)	(c)
Pennsylvania	558,556	702,633	548,674	873,320	— 9,882	+ 170,687	— 1.8	+ 24.3
Tennessee	467,741	736,397	520,460	1,235,718	+ 52,719	+ 499,321	+11.3	+ 67.8
Virginia	486,798	1,000,118	472,337	1,182,449	— 14,461	+ 182,331	— 3.0	+ 18.2
Wisconsin	1,529,459	3,644,542	1,179,709	3,913,437	— 349,750	+ 268,895	—22.9	+ 7.4
Other States [d]	720,305	1,133,967	658,910	1,013,215	+ [b] 40,292	+ [c] 365,569	+[b]5.6	+[c]32.2
	77,870,553	181,902,277	75,573,207	238,260,444	—2,297,346	+56,358,167	— 2.95	+ 30.98

[a] Less than three shippers in Maryland, North Carolina, and Ohio, in 1916, and permission not granted to publish State totals. Figures for these States, therefore, included in "Other States."

[b] Increase for North Carolina and decrease for Maryland and Ohio included with those for "Other States."

[c] Increase for Maryland and North Carolina and decrease for Ohio included with those for "Other States."

[d] 1916: Colorado, Connecticut, Iowa, Maryland, Massachusetts, Nevada, North Carolina, Ohio, Utah, West Virginia, and Wyoming. 1917: Arkansas, Colorado, Connecticut, Iowa, Massachusetts, Montana, Nevada, Utah, West Virginia, and Wyoming.

IRON ORE MINED, BY VARIETIES, BY STATES, AND BY MINING DISTRICTS.

Iron minerals comprise sulphides, oxides, carbonates, silicates, and phosphates, of which only the oxides and the carbonates are used in the iron and steel industry, except a small quantity of oxide by-products from sulphide ores used in the manufacture of sulphuric acid. The ores of iron are generally classed under the four heads, hematite, brown ore, magnetite, and carbonate.[1]

Hematite has always been predominant as an ore of iron, and in 1917 it constituted nearly 94 per cent of the iron ore mined in the United States. Brown ore and magnetite are far below it in importance, having together furnished in 1917 a little more than 6 per cent of the total production of iron ore. The production of iron carbonate is insignificant in comparison with that of the other ores; in 1916 it constituted only about 0.002 per cent of the total, and in 1917 none was reported to have been mined.

[1] Notes concerning the composition of these types of ores are given in U. S. Geol. Survey Mineral Resources, 1916, pt. 1, pp. 537–541, 1918.

Digitized by Google

Iron ore mined in the United States in 1916 and 1917, by States and varieties, in gross tons, with percentage of increase or decrease in 1917.

State.	Hematite.	Brown ore.	Magnetite.	Carbonate.	Total quantity.	Percentage of increase or decrease in 1917.
1916.						
Alabama	5,672,005	1,075,896			6,747,901	
California			3,000		3,000	
Georgia	110,647	146,302			256,949	
Iowa		11,351			11,351	
Maryland		4,455			4,455	
Michigan	18,071,016				18,071,016	
Minnesota	44,585,422				44,585,422	
Missouri	27,568	7,346			34,914	
Nevada		9,910			9,910	
New Jersey			493,004		493,004	
New Mexico			157,779		157,779	
New York	74,723	(a)	a1,267,784		1,342,507	
North Carolina		4,263	60,043		64,306	
Ohio				1,800	1,800	
Pennsylvania		16,031	543,400		559,431	
Tennessee	256,093	192,541	7,200		455,834	
Utah		45,514			45,514	
Virginia	80,258	b 360,234	(b)		440,492	
West Virginia		3,605			3,605	
Wisconsin	1,304,518				1,304,518	
Wyoming	545,774				545,774	
Other States c		28,190			28,190	
	70,728,024	1,904,484	2,533,364	1,800	75,167,672	
1917.						
Alabama	5,949,096	1,088,611			7,037,707	+ 4.29
Arkansas	40				40	
California			2,207		2,207	− 26.43
Georgia	101,895	124,735			226,630	− 11.80
Iowa		22,612			22,612	+ 99.2
Maryland	d 11,830	(d)			11,830	+165.54
Massachusetts		10,000			10,000	(e)
Michigan	17,868,601				17,868,601	− 1.12
Minnesota	44,595,232				44,595,232	+ 0.02
Missouri	26,866	12,042			38,908	+ 11.44
Nevada		1,010			1,010	− 89.79
New Jersey			489,943		489,943	− 0.62
New Mexico	25,471		211,750		237,221	+ 50.35
New York	f 53,514	(f)	1,250,803		1,304,317	− 2.84
North Carolina		35,644	55,353		90,997	+ 41.50
Pennsylvania		4,927	541,773		546,700	− 2.28
Tennessee	260,038	247,340	1,151		508,529	+ 11.56
Utah		48,058			48,058	+ 5.59
Virginia	109,166	360,711	26		469,903	+ 6.68
West Virginia		4,632			4,632	+ 28.48
Wisconsin	1,202,235				1,202,235	− 7.84
Wyoming	543,846				543,846	− 0.35
Other States g		27,693			27,693	+e33.71
	70,743,513	1,992,332	2,553,006		75,288,851	+ 0.16

a Brown ore included in magnetite.
b Magnetite included in brown ore.
c Colorado, Connecticut, and Massachusetts, in 1916.
d Brown ore included in hematite.
e Less than three producers in Massachusetts in 1916, and permission not granted to publish State total. Increase in 1917, therefore, included in "Other States."
f Brown ore included in hematite.
g Colorado, Connecticut, and Montana, in 1917.

The principal iron-mining districts in the United States, except the Adirondack and Birmingham districts, are interstate and the different varieties of ore are to a large extent locally segregated, so that statistics of production by districts are of more general interest and importance than statistics by States. The Lake Superior district, comprising all the mines in Minnesota and Michigan and those in northern Wisconsin, mined 63,481,321 gross tons in 1917, nearly all hematite, compared with 63,735,088 gross tons in 1916, a decrease of 0.39 per cent. This district mined nearly 85 per cent of the total ore in 1916 and 1917. The Birmingham district, in north

Digitized by Google

central Alabama, mined 6,187,073 gross tons of ore, including both hematite and brown ore, in 1917, compared with 5,976,018 tons in 1916, an increase of 3.53 per cent. This district therefore mined about 8 per cent of the total, or a little less than one-tenth as much as the Lake district. The Adirondack district, New York, mined 1,100,001 gross tons of magnetite in 1917, compared with 1,077,638 tons in 1916, an increase of 2.07 per cent. None of the other individual districts mined as much as 1,000,000 tons. The production in 1917 of the several districts was not greatly different from their production in 1916, and is an indication that about the maximum capacity under the prevailing conditions of shortage in labor and cars had been reached.

Iron ore[a] *mined in the United States, by mining districts and varieties, in 1916 and 1917, in gross tons.*

1916.

District.	Hematite.	Brown ore.	Magnetite.	Carbonate.	Total.
Lake Superior[b]	63,735,088				63,735,088
Birmingham	5,461,444	514,574			5,976,018
Chattanooga	540,405	296,218			836,623
Adirondack			1,077,638		1,077,638
Northern New Jersey and southeastern New York		(c)	[c] 683,150		683,150
Other districts	991,087	1,093,346	772,922	1,800	2,859,155
	70,728,024	1,904,484	2,533,364	1,800	75,167,672

1917.

District.	Hematite.	Brown ore.	Magnetite.	Carbonate.	Total.	Percentage of change in 1917.
Lake Superior[b]	63,481,321				63,481,321	−0.39
Birmingham	5,728,862	458,211			6,187,073	+3.53
Chattanooga	524,787	296,698			821,485	−1.81
Adirondack			1,100,001		1,100,001	+2.07
Northern New Jersey and southeastern New York		(c)	[c] 642,232		642,232	−5.99
Other districts	1,008,543	1,235,936	812,260		3,056,739	+6.91
	70,743,513	1,992,332	2,553,006		75,288,851	+0.16

[a] Exclusive of ore containing 5 per cent or more of manganese.
[b] Includes only those mines in Wisconsin which are in the true Lake Superior district.
[c] A small quantity of brown ore included in magnetite.

These tables show that the greater part of the hematite comes from the Lake Superior district (Michigan, Minnesota, and Wisconsin) and Alabama, the bulk of the brown ore from the southern Appalachian districts, and the magnetite from New York, Pennsylvania, and New Jersey. The iron carbonate is mined in Ohio; (none was mined in 1917. On a later page is given the production of the principal ranges in the Lake Superior district. The bulk of the Lake Superior hematite is more or less hydrated and many deposits include masses of brown ore having varying percentages of combined water. There is, however, a complete gradation from anhydrous hematite to limonite, and as there is no sharp dividing line and as also the greater part of the ore is nearer the anhydrous than the completely hydrated condition, the production of the hydrated ores is included in the production of hematite. Certain mines in northern Michigan produce an ore which is locally termed magnetite. It is a coarsely crystalline anhydrous ore, consisting dominantly of hematite, but

Digitized by Google

having sufficient quantities of magnetite distributed through it to render the ore strongly magnetic. This magnetic ore is also included with hematite in the tables of production, both because it is not a true magnetite and because the quantity is not of sufficient importance to warrant making additional tables for magnetic ores.

The Birmingham and Adirondack districts were the only large iron-ore producing districts that showed increase in output, as compared with 1916.

TOTAL OUTPUT OF IRON ORE.

The following table shows the production of various types of iron ore in the United States as far as it has been recorded or estimated. The statistics from 1889 to the present were collected by the United States Geological Survey; those for 1880 were collected for the census report of that year; those for 1881 were estimated by I. L. Bell;[a] and those from 1882 to 1888, inclusive, were estimated by James M. Swank[b] from the pig iron produced. Figures are not available for the production of various classes of iron ores prior to 1889, except for the census year 1880. The figures for the years prior to 1880 were calculated from the pig iron produced, which included imported ore as well as domestic ore used.

Iron ore mined in the United States, 1810–1917, in gross tons.

Year.	Hematite.	Brown ore.	Magnetite.	Carbonate.	Total.
1810–1869					49,656,000
1870 c–1879					44,570,527
1880	2,243,993	1,918,622	2,134,216	823,471	7,120,302
1881					7,119,643
1882					8,700,000
1883					8,800,000
1884					7,718,129
1885					7,600,000
1886					10,000,000
1887					11,300,000
1888					12,062,530
1889	9,056,288	2,523,087	2,506,415	422,251	14,518,041
1890	10,527,650	2,559,938	2,570,838	377,617	16,036,043
1891	9,327,398	2,757,564	2,317,108	189,108	14,591,178
1892	11,646,619	2,485,101	1,971,965	192,981	16,296,666
1893	8,272,037	1,849,272	1,330,886	134,834	11,587,629
1894	9,347,434	1,472,748	972,219	87,278	11,879,679
1895	12,513,995	2,102,358	1,268,222	73,039	15,957,614
1896	12,576,288	2,126,212	1,211,926	91,423	16,005,449
1897	14,413,318	1,961,954	1,059,479	83,295	17,518,046
1898	16,150,684	1,989,681	1,237,978	55,373	19,433,716
1899	20,004,399	2,869,785	1,727,430	81,559	24,683,173
1900	22,708,274	3,231,089	1,537,551	76,247	27,553,161
1901	24,006,025	3,016,715	1,813,076	51,663	28,887,479
1902	30,532,149	3,305,484	1,688,860	27,642	35,554,135
1903	30,328,654	3,080,399	1,575,422	34,833	35,019,308
1904	23,839,477	2,146,795	1,638,846	19,212	27,644,330
1905	37,567,055	2,546,662	2,390,417	21,999	42,526,133
1906	42,481,375	2,781,063	2,469,294	17,996	47,749,728
1907	46,060,486	2,957,477	2,679,067	23,589	51,720,619
1908	31,788,564	d 2,620,390	d 1,547,797	26,585	35,983,336
1909	46,208,640	d 2,839,265	d 2,229,839	16,527	51,294,271
1910	51,367,607	d 2,993,744	d 2,631,835	22,320	57,014,906
1911	39,626,224	2,032,094	2,202,527	15,707	43,876,552
1912	51,345,782	1,614,486	2,179,533	10,346	55,150,147
1913	57,933,251	1,682,063	2,357,274	7,849	61,980,437
1914	38,286,670	1,537,750	1,610,303	5,138	41,439,761
1915	52,227,324	1,488,709	1,807,002	3,455	55,526,490
1916	70,728,624	1,904,484	2,533,364	1,800	75,167,672
1917	70,743,513	1,992,332	2,553,006		75,288,851
					1,202,531,741

[a] Principles of the manufacture of iron and steel, p. 451, 1884.
[b] U. S. Geol. Survey Mineral Resources, 1882 to 1888.
[c] Includes ore produced by owners of blast furnaces, estimated by census at 800,000 tons.
[d] Some brown ore included in magnetite.

Digitized by Google

PRINCIPAL IRON-ORE MINES.

In 1917 there were 452 iron-ore mines active, compared with 405 in 1916, and 240 mines in 1917 produced more than 50,000 gross tons of iron ore each, compared with 222 mines in 1916. The total ore produced by the mines whose output was more than 50,000 gross tons each was 72,822,173 gross tons, or more than 96 per cent of the entire production of the United States in 1917. Of these 240 mines, 11 (1 less than in 1916) produced more than 1,000,000 tons of iron ore each in 1917. First place in 1917 was held by the Hull-Rust mine, at Hibbing, Minn.; second place by the Red Mountain group, near Bessemer, Ala.; third place by the Mahoning, at Hibbing, Minn.; and fourth place by the Fayal, at Eveleth, Minn. The production of these mines in 1917 was, respectively, 6,468,483 tons, 2,955,022 tons, 2,525,145 tons, and 2,022,816 tons, compared with 7,658,201 tons, 2,899,588 tons, 2,215,788 tons, and 2,252,008 tons, respectively, in 1916. Eight of the 11 mines producing more than 1,000,000 tons in 1917 are in Minnesota. The largest producer in Michigan in 1917 was the Norrie group, which reported having mined 1,384,002 gross tons of hematite, a slight decrease from the production in 1916. Permission has been granted to the Survey by the owners and operators of 212 of these large mines to publish their production, and these statistics are given in the following table:

Iron-ore mines of the United States that produced more than 50,000 gross tons each in 1917.

Rank.	Name of mine.	State.	Nearest town.	Variety of ore.	Quantity mined.
1	Hull-Rust	Minnesota	Hibbing	Hematite	6,468,483
2	Red Mountain group	Alabama	Bessemer	do	2,955,022
3	Mahoning	Minnesota	Hibbing	do	2,525,145
4	Fayal	do	Eveleth	do	2,022,816
5	Canisteo	do	Coleraine	do	1,643,226
6	Morris	do	Hibbing	do	1,606,701
7	Kerr	do	do	do	1,586,409
8	Sellers	do	do	do	1,575,057
9	Adams	do	Eveleth	do	1,549,658
10	Norrie group	Michigan	Ironwood	do	1,384,002
11	Wakefield	do	Wakefield	do	1,061,721
12	Newport and Bonnie	do	Ironwood	do	986,853
13	Woodward 1, 2, and 3	Alabama	Lipscomb	do	877,637
14	Holman	Minnesota	Taconite	do	835,464
15	Bennett	do	Keewatin	do	791,545
16	Leonidas	do	Eveleth	do	782,343
17	Witherbee, Sherman & Co. (Inc.).	New York	Mineville	Magnetite	780,131
18	Dean	Minnesota	Buhl	Hematite	773,666
19	Hawkins	do	Nashwauk	do	720,646
20	Chapin	Michigan	Iron Mountain	do	715,001
21	Shenango	Minnesota	Chisholm	do	699,539
22	Burt	do	Hibbing	do	695,663
23	Plymouth	Michigan	Verona	do	658,207
24	Susquehanna	Minnesota	Hibbing	do	622,051
25	Sauntry-Alpena	do	Virginia	do	606,223
26	Sunrise	Wyoming	Sunrise	do	520,114
27	Palms	Michigan	Bessemer	do	508,723
28	Cornwall	Pennsylvania	Miners Village	Magnetite	491,427
29	Albany	Minnesota	Hibbing	Hematite	460,505
30	Glen	do	Chisholm	do	443,446
31	Montreal	Wisconsin	Montreal	do	441,802
32	Leetonia	Minnesota	Hibbing	do	406,603
33	Commodore	do	Virginia	do	406,369
34	Caspian	Michigan	Palatka	do	404,025
35	Penn group	do	Vulcan and Norway	do	388,771
36	Ordean	Minnesota	Virginia	do	383,968
37	Dunwoody	do	Hibbing	do	372,139
38	Spruce	do	Eveleth	do	369,117
39	Zenith	do	Ely	do	368,453
40	Chisholm	do	Chisholm	do	367,725
41	Corsica	do	Gilbert	do	355,685
42	Chester	do	Chisholm	do	354,979
43	Colby	Michigan	Bessemer	do	344,441

Digitized by Google

Iron-ore mines of the United States that produced more than 50,000 gross tons each in 1917—Continued.

Rank.	Name of mine.	State.	Nearest town.	Variety of ore.	Quantity mined.
44	Biwabik	Minnesota	Biwabik	Hematite	342,570
45	Stevenson	do	Hibbing	do	342,392
46	Pioneer	do	Ely	do	332,182
47	North Harrison	do	Nashwauk	do	330,777
48	La Rue	do	do	do	319,210
49	Carpenter	Michigan	Crystal Falls	do	318,712
50	Arcturus	Minnesota	Marble	do	314,073
51	Armour No. 2	do	Crosby	do	311,291
52	Hartley-Burt	do	Chisholm	do	310,264
53	Aragon	Michigan	Norway	do	301,934
54	Lake Superior	do	Ishpeming	do	294,449
55	Tobin	do	Crystal Falls	do	293,300
56	Miller	Minnesota	Aurora	do	293,133
57	Lincoln	do	Virginia	do	287,751
58	Songo	Alabama	Songo	do	283,362
59	Clark	Minnesota	Chisholm	do	268,087
60	Woodbridge	do	Buhl	do	267,397
61	Balkan	Michigan	Alpha	do	262,803
62	Pettit	Minnesota	Gilbert	do	262,514
63	Helmer	do	Kinney	do	259,362
64	Webb	do	Hibbing	do	253,802
65	Mohawk	do	Aurora	do	253,609
66	Utica	do	Hibbing	do	251,996
67	Mace No. 2	do	Nashwauk	do	251,280
68	Hill Annex	do	Calumet	do	250,902
69	Cary	Wisconsin	Hurley	do	250,297
70	Aurora	Michigan	Ironwood	do	249,501
71	Smith	Minnesota	Hibbing	do	249,417
72	Puritan	Michigan	Ironwood	do	248,146
73	Tully	do	Stambaugh	do	239,999
74	Graham	Minnesota	Mesaba	do	238,904
75	Ironton	Michigan	Bessemer	do	236,708
76	Philbin	Minnesota	Hibbing	do	230,572
77	Union	do	Virginia	do	221,821
78	Chatham	Michigan	Stambaugh	do	221,378
79	Belgrade	Minnesota	Biwabik	do	219,447
80	Spaulding	Alabama	Birmingham	do	213,965
81	Ottawa	Wisconsin	Montreal	do	211,657
82	Fierro Group	New Mexico	Fierro	Magnetite	208,253
83	Odgers	Michigan	Crystal Falls	Hematite	204,500
84	Section 30	Minnesota	Ely	do	204,497
85	Raimund No. 1	Alabama	Bessemer	do	201,665
86	Bengal	Michigan	Palatka	do	200,572
87	Itasca	Minnesota	Buhl	do	197,481
88	Mahnomen	do	Ironton	do	196,000
89	Sibley	do	Ely	do	193,834
90	Shiras	do	Buhl	do	193,592
91	Kennedy	do	Cuyuna	do	193,409
92	Thompson	do	Crosby	do	191,472
93	Eureka	Michigan	Ramsay	do	191,162
94	Laura	Minnesota	Hibbing	do	190,761
95	Homer	Michigan	Iron River	do	189,872
96	Sunday Lake	do	Wakefield	do	189,212
97	Wanless	Minnesota	Buhl	do	186,721
98	Pewabic	Michigan	Iron Mountain	do	183,414
99	Kinney	Minnesota	Kinney	do	183,314
100	Leonard	do	Chisholm	do	182,336
101	Baltic (Inc. Fogarty)	Michigan	Palatka	do	181,199
102	Cambria	do	Negaunee	do	180,373
103	Genoa	Minnesota	Gilbert	do	171,504
104	Sliver	do	Virginia	do	171,028
105	Mary Charlotte No. 1 and 2	Michigan	Negaunee	do	168,924
106	Hillcrest	Minnesota	Ironton	do	166,350
107	Pennington	do	do	do	165,895
108	North Eddy	do	Hibbing	do	163,974
109	Osana-Wauseca	Michigan	Iron River	do	162,404
110	Bristol	do	Crystal Falls	do	161,000
111	Meacham	Minnesota	Crosby	do	160,108
112	Steinman	Alabama	Steinman	do	159,342
113	St. James	Minnesota	Aurora	do	157,200
114	Brown Mining Co	Tennessee	Cardiff	do	156,924
115	Rowe	Minnesota	Riverton	do	155,874
116	Bangor	do	Biwabik	do	154,379
117	Brunt	do	Mountain Iron	do	151,553
118	Croft	Michigan	Crosby	do	149,898
119	Richmond	do	Palmer	do	149,217
120	Zimmerman	do	Gaastra	do	147,552
121	Loretto	do	Loretto	do	146,687
122	Hiawatha	do	Iron River	do	145,580
123	Soudan	Minnesota	Soudan	do	145,338
124	Mount Hope	New Jersey	Mount Hope	Magnetite	142,799

Digitized by Google

Iron-ore mines of the United States that produced more than 50,000 gross tons each in 1917—Continued.

Rank.	Name of mine.	State.	Nearest town.	Variety of ore.	Quantity mined.
125	American-Boston	Michigan	Diorite	Hematite	132,422
126	Attalla	Alabama	Attalla	do	128,029
127	North Anvil	Michigan	Bessemer	do	127,937
128	Breitung-Hematite No. 1	do	Negaunee	do	127,588
129	Frantz	Minnesota	Buhl	do	127,245
130	Norman	do	Virginia	do	126,121
131	Hanna A	do	Mountain Iron	do	125,318
132	Washington	New Jersey	Oxford	Magnetite	124,535
133	Geneva	Michigan	Ironwood	Hematite	122,193
134	Tilden	do	Bessemer	do	120,486
135	Mace No. 1	Minnesota	Hibbing	do	119,085
136	Greeley	Alabama	Greeley	Brown ore	119,070
137	South Chandler	Minnesota	Ely	Hematite	117,322
138	Judson	Michigan	Alpha	do	116,523
139	Chandler	Minnesota	Ely	do	116,375
140	Amasa Porter	Michigan	Amasa	do	115,358
141	Agnew	Minnesota	Hibbing	do	115,255
142	Hammond	Alabama	Hammond	do	114,713
143	Bates	Michigan	Iron River	do	113,292
144	Clifford	do	Iron Mountain	do	113,234
145	Midget	Minnesota	Hibbing	do	113,008
146	Majorca	do	Calumet	do	112,394
147	Deacon	do	Buhl	do	111,866
148	Davidson No. 1	Michigan	Iron River	do	110,221
149	Mayville	Wisconsin	Mayville	do	104,212
150	Elba	Minnesota	Gilbert	do	103,068
151	Ohio	Michigan	Michigamme	do	102,665
152	Brotherton	do	Wakefield	do	101,859
153	Hanna B	Minnesota	Mountain Iron	do	101,136
154	Adams	Michigan	Ishpeming	do	99,744
155	Rolling Mill	do	Negaunee	do	96,141
156	Patrick	Minnesota	Nashwauk	do	95,888
157	Asteroid	Michigan	Ramsay	do	91,135
158	Warren	Minnesota	Hibbing	do	94,029
159	Hudson	do	Aurora	do	93,369
160	Grace	do	Hibbing	do	93,022
161	Davidson No. 2	Michigan	Iron River	do	92,048
162	Chicagon	do	do	do	91,445
163	Tioga	Minnesota	Chisholm	do	89,177
164	Bray	do	Keewatin	do	88,843
165	Himrod	Michigan	Negaunee	do	88,447
166	Morrow	Minnesota	Eveleth	do	88,284
167	Richards	Michigan	Crystal Falls	do	86,500
168	Ironaton	Alabama	Ironaton	Brown ore	84,771
169	Ernst	Wisconsin	Commonwealth	Hematite	82,892
170	Rogers	Michigan	Iron River	do	81,958
171	State Lease 40	Minnesota	Crosby	do	81,489
172	Perkins	do	Aurora	do	80,929
173	Oriskany	Virginia	Oriskany	Brown ore	80,791
174	Victoria	Minnesota	Virginia	Hematite	80,710
175	Weed	do	Mesaba	do	80,639
176	Cahoon	Wisconsin	Baraboo	do	80,535
177	Vaney	Alabama	Russellville	Brown ore	78,693
178	Armour No. 1	Minnesota	Crosby	Hematite	77,883
179	Breitung-Hematite No. 2	Michigan	Negaunee	do	77,828
180	Warner	do	Amasa	do	77,592
181	Cuyuna-Duluth	Minnesota	Ironton	do	76,939
182	Jean	do	Eveleth	do	76,663
183	Yale	Michigan	Bessemer	do	73,789
184	Wacootah	Minnesota	Mountain Iron	do	71,807
185	Berkshire	Michigan	Stambaugh	do	71,300
186	Empire	do	Palmer	do	70,931
187	South Uno (N. P.)	Minnesota	Hibbing	do	70,258
188	Thorne	do	Buhl	do	68,962
189	Raimund No. 2	Alabama	Bessemer	do	68,520
190	Isabella	Michigan	Palmer	do	67,341
191	La Belle	Minnesota	Gilbert	do	67,314
192	Queen Group	Michigan	Negaunee	do	67,242
193	North Uno (N. P.)	Minnesota	Hibbing	do	65,151
194	Castile	Michigan	Wakefield	do	64,351
195	Tannehill	Alabama	Goethite	Brown ore	63,786
196	Missabe Mountain	Minnesota	Virginia	Hematite	62,931
197	Friedman	Alabama	Woodstock	Brown ore	61,795
198	Omaha	Minnesota	Brainerd	Hematite	60,000
199	Julia	do	Virginia	do	59,441
200	York	do	Nashwauk	do	58,800
201	Houston	Alabama	Rickey	Brown ore	57,151
202	Anvil	Michigan	Bessemer	Hematite	55,490
203	Cranberry	North Carolina	Cranberry	Magnetite	55,353
204	Wilson, Hyde & Hurst	Alabama	Russellville	Brown ore	54,029
205	Franklin	Minnesota	Virginia	Hematite	53,000

Digitized by Google

Iron-ore mines of the United States that produced more than 50,000 gross tons each in 1917—Continued.

Rank.	Name of mine.	State.	Nearest town.	Variety of ore.	Quantity mined.
206	Champion	Alabama	Oneonta	Brown ore	51,906
207	Keewanee	do	Birmingham	Hematite	51,532
208	Asd	Minnesota	Eveleth	do	50,889
209	Raimund No. 3	Alabama	Bessemer	do	50,422
210	French Creek	Pennsylvania	St. Peters	Magnetite	50,346
211	Judd	Minnesota	Taconite	Hematite	50,278
212	Madrid	do	Virginia	do	50,000
	Total (212 mines)				67,703,451
	Unspecified (28 mines)[a]				5,028,722
	Output from mines producing more than 50,000 gross tons each				72,822,173
	Output from mines producing less than 50,000 gross tons each				2,466,678
	Grand total of United States				75,288,851

[a] Includes the product of 28 mines producing more than 50,000 gross tons each and operated by 12 companies which do not permit the publication of individual figures.

STOCK OF IRON ORE AT MINES.

According to the reports of producers, a few of which have been revised since the report for 1916 was published, the total quantity of iron ore in stock at the mines at the close of 1917 amounted to 10,628,908 gross tons, compared with 10,835,224 tons at the close of 1916, a decrease of less than 2 per cent. As the quantity of ore in stock piles is necessarily partly estimated, there are variations in the mine reports from year to year which prevent an absolute balance between the quantity mined and the quantity sold and stocks on hand.

Stock of iron ore at mines, by States, Dec. 31, 1916 and 1917, in gross tons.

State.	1916	1917	State.	1916	1917
Alabama	684,199	619,976	New Mexico		7,700
California	30	14	New York	129,986	61,647
Georgia	10,443	20,654	North Carolina		40
Iowa	1,200	1,200	Ohio	3,388	3,388
Maryland	1,050	2,130	Pennsylvania	36,450	34,961
Massachusetts	4,000	2,950	Tennessee	15,371	128
Michigan	4,671,456	4,840,665	Virginia	41,402	35,931
Minnesota	4,794,561	4,529,733	Wisconsin	289,548	310,557
Missouri	2,913	2,320			
New Jersey	149,227	154,914	Total	10,835,224	10,628,908

PRICES OF IRON ORE PER TON.

In the following table the average selling price per ton at the mines of the different classes of iron ore in 1916 and 1917 is given for each of the producing States or groups of States, except where there were less than three producers or shippers of a certain variety of ore, and permission was not given to publish in a State whose total may be published. The average prices per gross ton (the whole United States considered) in 1917 were: Hematite, $3.12; brown ore, $2.95; and magnetite, $4.29; as compared with prices, respectively, of $2.32, $2.03, and $3.11, in 1916. These figures are taken directly from statements of the producers and probably represent only approximately the actual selling prices. The element of inaccuracy lies in the fact that by far the greater bulk of the iron ore produced in the United States is mined by iron and steel producers for their own furnaces and that the value placed on such ore is therefore largely a

Digitized by Google

matter of accounting. Some of the reports made to the Survey evidently include merely actual mining costs; others contain, in addition, the cost of selling and insuring the ore; in others an allowance for sinking fund is included; and in still others the figures given are the prices used in charging costs against the blast furnaces. At any rate, they include no freight costs. The selling prices of Lake Superior iron ore at lower Lake ports are given on pages 575–576.

The general average price per gross ton of all kinds of iron ore in the United States was $3.15 in 1917, compared with $2.34 in 1916, an increase of 81 cents a ton, or nearly 35 per cent.

Average price per gross ton of iron ore in 1916 and 1917.

State.	Hematite.		Brown ore.		Magnetite.		Carbonate.	
	1916	1917	1916	1917	1916	1917	1916	1917
Alabama	1.52	1.61	1.97	3.08				
California					4.00	4.00		
Georgia	1.32	2.36	1.87	2.58				
Maryland		(a)	(a)	2.56				
Michigan	2.58	3.55						
Minnesota	2.32	3.18						
Missouri	3.58	3.98	2.41	2.27				
New Jersey					3.55	4.98		
New Mexico		2.27			1.07	1.57		
New York	2.09	(a)	(a)	(a)	3.88	5.53		
North Carolina			(a)	2.42	(a)	(a)		
Ohio							b 3.00	
Pennsylvania			3.05	4.20	(a)	(a)		
Tennessee	1.42	1.76	1.76	3.01	(a)	(a)		
Virginia	2.06	2.54	2.05	2.49	(a)	(a)		
Wisconsin	2.38	3.32						
Other States c	1.00	1.11	3.15	3.54				
Total average	2.32	3.12	2.03	2.95	3.11	4.29	3.00	

a Less than three producers or shippers, and permission to publish not given; therefore price may not be shown.
b Estimated.
c 1916: Colorado, Connecticut, Iowa, Massachusetts, Nevada, Utah, West Virginia, and Wyoming; 1917: Arkansas, Colorado, Connecticut, Iowa, Massachusetts, Montana, Nevada, Utah, West Virginia, and Wyoming.

Average price per gross ton of iron ore in the United States, 1889 and 1892 to 1917.

Year.	Hematite.	Brown ore.	Magnetite.	Carbonate.	General average.
1889					$2.30
1892					2.04
1893					1.66
1894					1.14
1895					1.14
1896					1.42
1897					1.08
1898					1.14
1899					1.42
1900					2.42
1901					1.71
1902					1.84
1903					1.89
1904					1.56
1905					1.77
1906	$2.13	$1.78	$2.05	$1.75	2.11
1907	2.03	1.81	2.03	1.74	2.55
1908	2.32	1.70	2.40	1.38	2.27
1909	2.17	1.68	2.40	1.73	2.15
1910	2.52	1.76	2.36	1.61	2.47
1911	2.12	1.72	2.29	1.83	2.11
1912	1.87	1.79	2.18	1.96	1.88
1913	2.21	1.88	2.07	2.06	2.19
1914	1.79	1.72	2.39	2.44	1.81
1915	1.80	1.80	2.50	2.44	1.83
1916	2.32	2.03	3.11	3.00	2.34
1917	3.12	2.95	4.29		3.15

Digitized by Google

APPARENT CONSUMPTION OF IRON ORE COMPARED WITH PRODUCTION OF PIG IRON.

The following table includes data on certain items from which an approximate estimate of the annual consumption of iron ore in the United States is deduced. The result is, of course, merely an approximaton, for no data are available on certain items, such as stocks at furnaces, which should enter into the final result. The items considered in the table and in the annual estimates for all years preceding 1911 are (1) domestic iron ore mined; (2) stocks of ore at mines; (3) stocks of ore at lower Lake ports; (4) production of zinc residuum; (5) imports of ore; (6) exports of ore. Beginning with 1911 data on the shipments of ore became available, and these figures, together with zinc residuum and imports of ore, constitute the available supply which, less the exports, gives the apparent domestic consumption, without consideration of the stocks at mines and at Lake ports. This apparent consumption includes small quantities of ore not used in the manfacture of pig iron, such as ore consumed in the open-hearth steel furnaces and in smelting gold, silver, and copper; but it does not include ore used in the manufacture of paint.

In the same table is given the production of pig iron, including ferromanganese, spiegeleisen, ferrosilicon, and other ferroalloys, for corresponding years and the ratio of pig iron and ferroalloys produced to iron ore consumed. On later pages of the report will be found detailed statistics on the production and shipments of pig iron.

The ratio of pig iron manufactured to iron ore consumed was 51.11 per cent in 1917, as compared with 50.42 per cent in 1916.

The actual figures of consumption of ore as reported directly to the Survey by the manufacturers of iron are of interest in comparison with the figures in this table. Prior to 1915 such data have not been sufficiently complete for publication, but in connection with the statistics of value of pig iron, which are collected only by the United States Geological Survey, it has been found necessary to gather related data, some of which are now sufficiently complete for publication. For instance, the quantity of domestic ore consumed in the manufacture of pig iron in 1917, according to reports to the Survey from blast furnaces, was 69,108,181 gross tons; the total consumption of iron ore in 1917, including imported ore and 5,647,723 tons of mill cinder, scale, scrap, etc., was 75,505,078 gross tons, from which were produced 37,924,490 gross tons of pig iron, exclusive of ferroalloys—a ratio of pig iron produced to ore consumed of 50.22 per cent. The quantity of pig iron made in 1917 from domestic ore was 37,364,033 gross tons and from foreign ore 560,457 gross tons. In 1916 the domestic ore consumed was 70,769,337 gross tons, and the total consumption of iron ore, including imported ore and 4,036,022 tons of mill cinder, scale, and scrap, was 76,100,877 gross tons, from which were produced 38,701,963 gross tons of pig iron, exclusive of ferroalloys—a ratio of pig iron produced to ore consumed of 50.86 per cent.

Digitized by Google

Apparent consumption of iron ore compared with production of pig iron in the United States, 1889–1917, in gross tons.

Year.	Domestic iron ore produced.[a]	Stocks of ore at mines.	Stocks of ore at lower Lake ports Dec. 1.	Zinc residuum.	Imports.	Exports.	Apparent consumption.	Pig iron produced.[b]	Percentage ratio of pig iron to iron ore.
1889	14,518,041	2,256,973	2,607,106	43,648	853,573	.....	14,366,562	7,603,642	52.93
1890	16,036,043	2,000,000	3,893,487	48,560	1,246,830	.....	16,332,025	9,202,703	56.45
1891	14,591,178	2,450,279	3,508,489	38,228	912,864	.....	15,476,989	8,279,870	53.50
1892	16,296,666	2,911,740	4,149,451	31,859	806,585	.....	16,032,687	9,157,000	57.11
1893	11,587,629	3,526,161	4,070,710	37,512	526,951	.....	11,616,412	7,124,502	61.33
1894	11,879,679	3,236,198	4,834,247	26,981	167,307	.....	11,600,393	6,657,388	57.39
1895	15,957,614	2,976,494	4,415,712	43,249	524,153	.....	17,203,255	9,446,308	54.91
1896	16,005,449	3,405,302	4,954,984	44,953	682,806	.....	15,765,128	8,623,127	54.70
1897	17,518,046	3,098,287	5,923,755	33,924	489,970	.....	17,380,184	9,652,680	55.54
1898	19,433,716	2,846,457	5,136,407	48,502	187,208	.....	20,708,604	11,773,934	56.86
1899	24,683,178	2,320,278	5,530,283	65,010	674,082	40,665	25,513,903	13,620,703	53.39
1900	27,553,161	3,709,950	5,904,670	87,110	897,831	51,460	26,722,583	13,789,242	51.60
1901	28,887,479	4,239,823	5,859,663	52,311	966,950	64,703	29,357,171	15,878,354	54.09
1902	35,554,135	3,834,717	7,074,254	65,246	1,165,470	88,445	35,886,921	17,821,307	49.66
1903	35,019,308	6,297,888	6,371,085	73,264	980,440	80,611	34,232,399	18,009,252	52.61
1904	27,644,330	4,666,931	5,763,399	68,189	487,613	213,865	30,224,910	16,497,033	54.58
1905	42,526,133	3,812,281	6,438,967	90,289	845,651	208,017	43,433,138	22,992,380	52.94
1906	47,749,728	3,281,789	6,252,455	93,461	1,060,390	265,240	49,355,343	25,307,191	51.28
1907	51,720,619	3,033,110	7,385,728	93,413	1,229,168	278,608	51,879,998	25,781,361	49.69
1908	35,983,336	6,065,397	8,441,533	110,225	776,898	309,099	32,473,268	15,936,018	49.74
1909	51,294,271	6,135,271	8,965,789	141,264	1,694,957	455,934	52,080,428	25,795,471	49.53
1910	57,014,906	9,422,285	9,426,881	137,173	2,591,031	748,875	55,246,129	27,303,567	49.42
1911	41,092,447	.....	.....	109,296	1,811,732	768,386	42,245,089	23,649,547	55.98
1912	57,017,614	.....	.....	104,670	2,104,576	1,195,742	58,031,118	29,726,937	51.23
1913	59,643,098	.....	.....	102,239	2,594,770	1,042,151	61,297,956	30,966,152	50.52
1914	39,714,280	.....	.....	100,198	1,350,588	551,618	40,613,448	23,332,244	57.45
1915	55,493,100	.....	.....	159,318	1,341,281	707,641	56,286,058	29,916,213	53.15
1916	77,870,553	.....	.....	198,817	1,325,736	1,183,952	78,211,154	39,434,797	50.42
1917	75,573,207	.....	.....	155,332	971,663	1,132,313	75,567,889	38,621,216	51.11

[a] Beginning with 1910, iron ore sold for paint excluded from production and included in metallic paint. Beginning with 1911, figures represent shipments.

[b] From annual reports of the American Iron and Steel Association prior to 1912, and including ferroalloys produced in blast furnaces; beginning with 1912, according to American Iron and Steel Institute, and also including ferroalloys.

Digitized by Google

IRON-ORE INDUSTRY IN THE LAKE SUPERIOR DISTRICT.

PRODUCTION.

The ranges in the United States portion of the Lake Superior district which produced ore in 1917 were the Marquette, Menominee, Gogebic, Vermilion, Mesabi, and Cuyuna, besides the Baraboo and Iron Ridge areas. Only two of the ranges in the Lake Superior district mined a larger quantity of iron ore in 1917 than in 1916—the Cuyuna and Gogebic ranges—27.7 and 2.3 per cent, respectively. The output of the Cuyuna range approached 2,000,000 tons and for the first time the Cuyuna production surpassed that of the Vermilion range, advancing from sixth to fifth place among the Lake Superior ranges.

The total quantity of ore mined from the Lake Superior district, excluding the Baraboo and Iron Ridge areas, in 1917 was 63,481,321 gross tons, compared with 63,735,088 gross tons in 1916, a decrease of 253,767 tons, or about 0.4 per cent. The output in 1917 excludes all ore containing more than 5 per cent manganese. The Mesabi range mined 41,127,323 tons, compared with 41,325,341 tons in 1916, a decrease of less than 0.5 per cent; the Menominee range, 6,366,483 tons, compared with 6,649,578 tons in 1916, a decrease of 4.3 per cent; the Gogebic range, 7,881,232 tons, compared with 7,707,101 tons in 1916, an increase of 2.3 per cent; the Marquette range, 4,638,374 tons, compared with 4,792,987 tons in 1916, a decrease of 3.2 per cent; the Vermilion range, 1,481,301 tons, compared with 1,704,440 tons in 1916, a decrease of 13.1 per cent; and the Cuyuna range, which in 1917 entered upon its seventh year as a shipper of ore, 1,986,608 tons, compared with 1,555,641 tons in 1916, an increase of 27.7 per cent. The production of maganiferous iron ore from the Cuyuna range is reported in the chapter on manganese and manganiferous ores elsewhere in Mineral Resources for 1917. The Mesabi range produced 64.8 per cent of the entire output of the Lake Superior district and 54.6 per cent of the entire production of the United States.

Iron ore mined in the Lake Superior district,[a] 1916 and 1917, in gross tons.

Range.	1916	1917	Change in 1917.	Per centage of change, 1917.	Percentage of total output, 1917.	
					Lake Superior district.	United States.
Marquette (Michigan)	4,792,987	4,638,374	−154,613	− 3.2	7.3	6.2
Menominee (Michigan and Wisconsin)	6,649,578	6,366,483	−283,095	− 4.3	10.0	8.5
Gogebic (Michigan and Wisconsin)	7,707,101	7,881,232	+174,131	+ 2.3	12.4	10.5
Vermilion (Minnesota)	1,704,440	1,481,301	−223,139	−13.1	2.4	2.0
Mesabi (Minnesota)	41,325,341	41,127,323	−198,018	− .5	64.8	54.6
Cuyuna (Minnesota)	1,555,641	1,986,608	+430,967	+27.7	3.1	2.6
	63,735,088	63,481,321	−253,767	− .4	100.0	84.4

[a] Includes only such Wisconsin mines as are in the true Lake Superior district.

Digitized by Google

The following table shows the total production of the Lake Superior district, by ranges. The figures prior to 1872 were collected by A. P. Swineford, editor Marquette Mining Journal [1]; those for 1872 to 1877, inclusive, are from the Michigan Mineral Statistics; those for 1878 to 1888, inclusive, were collected by W. J. Stevens [2]; and the later figures were collected by the United States Geological Survey.

Iron ore produced in the Lake Superior district, 1854–1917, in gross tons.

Year.	Marquette.	Menominee.	Gogebic.	Vermilion.	Mesabi.	Cuyuna.	Total.
1854–1869	3,112,209						3,112,209
1870	859,507						859,507
1871	813,984						813,984
1872	948,553						948,553
1873	1,195,234						1,195,234
1874	899,934						899,934
1875	881,166						881,166
1876	993,311						993,311
1877	1,014,754	10,375					1,025,129
1878	1,033,082	78,028					1,111,110
1879	1,130,019	245,672					1,375,691
1880	1,384,010	524,735					1,908,745
1881	1,579,834	726,671					2,306,505
1882	1,829,394	1,136,018					2,965,412
1883	1,305,364	1,047,863					2,353,227
1884	1,559,912	895,634	1,022	62,122			2,518,690
1885	1,430,862	690,435	119,590	227,075			2,467,962
1886	1,627,383	880,006	756,237	307,948			3,571,574
1887	1,851,717	1,199,343	1,285,265	394,910			4,731,235
1888	1,918,672	1,191,097	1,433,689	511,953			5,055,411
1889	2,631,026	1,876,157	2,147,923	864,508			7,519,614
1890	2,863,848	2,274,192	2,914,081	891,910			8,944,031
1891	2,778,482	1,856,124	2,041,754	945,105			7,621,465
1892	2,848,552	2,402,195	3,058,176	1,226,220	29,245		49,564,388
1893	2,064,827	1,563,049	1,466,815	815,735	684,194		6,594,620
1894	1,935,379	1,255,255	1,523,451	1,055,229	1,913,234		7,682,548
1895	1,982,080	1,794,970	2,625,475	1,027,103	2,839,350		10,268,978
1896	2,418,846	1,763,235	2,100,398	1,200,007	3,082,973		10,566,359
1897	2,673,785	1,767,220	2,163,088	1,381,278	4,220,151		12,205,522
1898	2,987,930	2,275,664	2,552,205	1,125,538	4,837,971		13,779,308
1899	3,634,596	3,281,422	2,725,648	1,643,984	6,517,305		17,802,955
1900	3,945,068	3,680,738	3,104,033	1,675,949	8,158,450		20,564,238
1901	3,597,089	3,697,408	3,041,869	1,805,996	9,303,541		21,445,903
1902	3,734,712	4,421,250	3,683,792	2,057,532	13,080,118		26,977,404
1903	3,686,214	4,093,320	3,422,341	1,918,584	13,452,812		26,573,271
1904	2,465,448	2,871,130	2,132,988	1,056,430	11,672,405		20,198,311
1905	3,772,645	4,472,630	3,344,551	1,578,626	20,156,566		33,325,018
1906	4,070,914	4,962,357	3,484,023	1,794,186	23,564,891		37,876,371
1907	4,167,810	4,779,592	3,609,519	1,724,217	27,245,441		41,526,579
1908	3,309,917	2,904,011	3,241,931	927,206	17,725,014		28,108,079
1909	4,291,957	4,789,352	3,807,157	1,097,444	27,877,705		41,863,635
1910	4,631,427	4,983,729	4,746,818	1,390,360	30,576,409		46,328,743
1911	3,743,145	4,062,778	3,099,197	1,336,938	23,126,943	181,224	35,550,225
1912	3,545,012	4,465,486	3,926,632	1,457,273	32,604,756	369,739	46,368,878
1913	3,977,806	4,997,246	4,743,515	1,536,115	36,378,671	744,007	52,377,362
1914	3,320,783	3,671,499	4,601,240	1,352,416	19,808,434	776,051	33,540,403
1915	3,817,892	4,665,455	4,996,237	1,541,645	30,802,409	1,120,606	46,944,254
1916	4,792,937	6,649,578	7,707,101	1,704,440	41,325,341	1,555,641	63,735,088
1917	4,638,374	6,366,453	7,881,232	1,481,301	41,127,323	1,986,608	63,481,321
	125,697,444	111,269,402	103,488,903	41,128,183	452,111,652	6,733,876	840,429,460

SHIPMENTS AND RECEIPTS.

According to the Iron Trade Review, 64,437,003 gross tons of iron ore were shipped in 1917 from the Lake Superior district, including the Iron Ridge and Baraboo areas in Wisconsin, compared with 66,658,466 tons in 1916. Of the total in 1917, there were 62,498,901 gross tons shipped by boat and 1,938,102 tons by rail, compared

[1] U. S. Geol. Survey Mineral Resources, 1882, p. 116, 1883. [2] Idem, 1891, pp. 39–41, 1893.

Digitized by Google

with 64,734,198 tons shipped by boat and 1,924,268 tons by rail in 1916. The shipments from the Lake Superior iron-ore ranges and the Baraboo and Iron Ridge areas as reported to the Survey in 1917 amounted to 63,854,752 gross tons, exclusive of manganiferous iron ore containing 5 per cent or more of manganese.

Iron ore shipped from the Lake Superior district, 1913–1917, by ports, in gross tons.[a]

Shipping port.	1913	1914	1915	1916	1917
Escanaba, Mich.	5,399,444	3,664,451	5,649,289	7,457,444	7,156,854
Marquette, Mich.	3,137,617	1,755,726	3,099,589	3,858,092	3,207,145
Ashland, Wis.	4,338,230	3,363,419	5,146,772	8,057,814	7,597,841
Two Harbors, Minn.	10,075,718	5,610,262	8,642,942	10,735,853	9,990,901
Superior, Wis.	13,788,343	11,309,748	8,342,793	12,787,046	13,978,741
Duluth, Minn.	12,331,126	6,318,291	15,437,419	21,837,949	20,567,419
Total by lake.	49,070,478	32,021,897	46,318,804	64,734,198	62,498,901
Total by rail.	876,638	707,829	953,947	1,924,268	1,938,102
	49,947,116	32,729,726	47,272,751	66,658,466	64,437,003

[a] Iron Trade Review.

Iron ore shipped from the Lake Superior district, 1913–1917, by months, in gross tons.[a]

Month.	1913	1914	1915	1916	1917
April.	866,387	269,686	503,832	1,658,411	211,532
May.	7,284,212	3,832,063	5,012,359	8,449,580	6,263,612
June.	7,974,444	5,502,367	6,005,091	9,507,576	9,639,991
July.	8,204,416	5,784,514	7,204,020	9,750,157	10,241,633
August.	7,684,285	5,869,477	8,081,117	9,850,140	10,146,786
September.	7,259,662	5,431,307	7,863,146	9,600,786	9,536,152
October.	6,526,103	4,242,392	7,146,873	9,116,196	8,193,892
November.	3,270,958	1,068,681	4,445,129	5,715,452	7,333,828
December.	18,545	1,411	57,236	1,085,900	911,475
Total by lake [b].	49,070,478	32,021,897	46,318,804	64,734,198	62,498,901
Total by rail.	876,638	707,829	953,947	1,924,268	1,938,102
	49,947,116	32,729,726	47,272,751	66,658,466	64,437,003

[a] Iron Trade Review.
[b] Totals by seasons will be found to vary slightly from the sums of the monthly movements because of corrections.

Iron ore received at Lake Erie ports, 1913–1917, in gross tons.[a]

Port.	1913	1914	1915	1916	1917
Toledo.	1,084,215	773,711	1,158,374	2,035,160	2,445,602
Huron.	687,485	617,363	695,865	1,324,112	1,631,395
Lorain.	3,709,213	1,677,988	3,517,258	4,613,929	3,831,244
Cleveland.	8,812,583	5,519,698	7,504,697	10,669,745	9,077,161
Fairport.	2,037,126	1,558,134	2,001,103	2,580,647	2,311,179
Ashtabula.	8,336,126	5,318,788	7,813,101	11,474,268	10,251,304
Conneaut.	7,849,303	6,263,420	8,573,509	9,588,341	8,729,754
Erie.	713,904	260,991	707,875	1,525,031	2,079,227
Buffalo.	5,506,691	2,913,273	5,339,724	7,432,220	7,843,215
Detroit.	363,001	332,564	459,877	425,579	418,151
Port Colborne, Ontario, Canada.	.....	166,665	196,077	138,240	194,627
	39,099,647	25,402,655	37,967,460	51,807,272	48,812,859

[a] Iron Trade Review.

Digitized by Google

The difference between the shipments of Lake Superior ore and the receipts of Lake Erie ports is accounted for in large part by the quantity of ore delivered at Lake Michigan ports, South Chicago, Ill., Gary and Indiana Harbor, Ind., and Milwaukee, Wis., the receipts at those ports and at smaller places being shown in the table following. It is understood that there is also a loss, probably less than 1 per cent, in handling ore between mines and lower Lake ports.

Iron ore received at Lake Michigan ports, 1913–1917, in gross tons.[a]

Port.	1913	1914	1915	1916	1917
Elk Rapids, Mich		28,437			
East Jordan, Mich	28,444	38,158	37,658	38,573	35,792
Milwaukee, Wis	234,591	93,121	187,286	239,219	224,570
Gary, Ind	2,365,551	1,631,564	2,421,924	2,718,185	3,883,082
Indiana Harbor, Ind	455,252	661,054	689,226	793,215	900,692
South Chicago, Ill	5,572,866	3,606,587	4,195,976	7,740,877	7,030,174
Boyne City, Mich	45,028	50,098	40,401	43,788	44,437
	8,701,732	6,109,019	7,572,471	11,573,857	12,118,747

[a] Iron Trade Review.

The following table shows the total quantity of iron ore shipped from the Lake Superior district since 1854, the date of the opening of the Marquette range, the oldest of the Lake Superior ranges. This table gives the shipments as published by the Iron Trade Review and is inserted for comparison with the table giving the total production of the Lake Superior district, without regard to shipments.

Iron ore shipped from the Lake Superior district, 1854–1917, in gross tons.[a]

Year.	Quantity.	Year.	Quantity.	Year.	Quantity.
1854	3,000	1876	992,764	1898	14,024,673
1855	1,449	1877	1,015,087	1899	18,251,804
1856	36,343	1878	1,111,110	1900	19,059,393
1857	25,646	1879	1,375,091	1901	20,589,237
1858	15,876	1880	1,908,745	1902	27,571,121
1859	68,832	1881	2,306,805	1903	24,289,878
1860	114,401	1882	2,965,412	1904	21,822,839
1861	49,909	1883	2,353,288	1905	34,384,116
1862	124,169	1884	2,518,092	1906	38,565,762
1863	203,055	1885	2,466,372	1907	42,266,668
1864	243,127	1886	3,568,022	1908	26,014,987
1865	236,208	1887	4,730,577	1909	42,586,869
1866	278,796	1888	5,063,093	1910	43,442,397
1867	473,567	1889	7,292,754	1911	32,793,130
1868	491,449	1890	9,012,379	1912	48,221,546
1869	617,444	1891	7,062,233	1913	49,947,116
1870	830,940	1892	9,069,556	1914	32,729,726
1871	779,607	1893	6,060,492	1915	47,272,751
1872	900,901	1894	7,748,932	1916	66,658,466
1873	1,162,458	1895	10,429,037	1917	64,437,003
1874	919,557	1896	9,934,828		
1875	891,257	1897	12,469,638		834,853,280

[a] Iron Trade Review.

Digitized by Google

STOCKS OF IRON ORE AT LAKE ERIE PORTS.

Stocks of iron ore at Lake Erie ports, Dec. 1, 1913–1917, in gross tons.[a]

Port.	At close of navigation, Dec. 1—				
	1913	1914	1915	1916	1917
Toledo, Ohio	349,047	580,600	311,799	394,869	399,479
Sandusky, Ohio	2,472	2,471	1,871	.....	.....
Huron, Ohio	441,541	483,769	558,692	590,743	556,765
Lorain, Ohio	694,704	548,097	824,968	1,076,105	978,108
Cleveland, Ohio	1,930,720	1,757,543	1,795,962	1,936,906	1,914,071
Fairport, Ohio	478,014	406,124	413,994	474,930	536,580
Ashtabula, Ohio	3,20[illegible],807	2,749,315	2,870,204	3,266,752	3,435,624
Conneaut, Ohio	1,245,032	1,160,639	1,216,686	1,363,550	1,544,706
Erie, Pa	594,613	484,467	589,355	625,193	519,698
Buffalo, N. Y	319,726	234,880	326,800	438,712	441,318
	9,261,676	8,407,905	8,910,351	10,167,760	10,326,349

[a] Iron Trade Review.

Stocks of iron ore at Lake Erie ports May 1, 1914–1918, in gross tons.[a]

Port.	At opening of navigation, May 1—				
	1914	1915	1916	1917	1918
Toledo, Ohio	215,534	255,343	164,637	257,030	230,797
Sandusky, Ohio	2,741	2,471	.....	.....	.....
Huron, Ohio	308,478	462,917	286,054	333,124	387,042
Lorain, Ohio	245,057	377,550	173,771	508,618	475,137
Cleveland, Ohio	1,487,292	1,592,783	772,721	970,973	933,687
Fairport, Ohio	245,038	283,591	198,636	237,645	329,528
Ashtabula, Ohio	2,187,622	1,963,233	1,176,142	1,660,818	1,744,448
Conneaut, Ohio	495,153	564,077	41,080	183,255	344,447
Erie, Pa	461,750	412,186	342,866	406,078	363,008
Buffalo, N. Y	271,492	178,152	187,498	219,691	313,925
	5,920,157	6,092,303	3,343,405	4,772,232	5,622,019

[a] Marine Review.

PRICES OF LAKE SUPERIOR IRON ORE.

Beginning with the season of 1907 the base for the old range and Mesabi Bessemer ore has been a metallic iron content of 55 per cent natural, and that of the old range and Mesabi non-Bessemer ore has been a metallic iron content of 51.5 per cent natural. For the years preceding 1907 the guaranty of Bessemer ores was 55.70 per cent iron natural, and for the non-Bessemer ores it was 52.80 per cent, except Mesabi non-Bessemer for 1905 and 1906, when the natural iron content was 53 per cent.

At Lake Erie ports for the season of 1917 and the first half of 1918 Mesabi Bessemer was listed at $5.70 a gross ton and Mesabi non-Bessemer at $5.05 a ton, compared with $4.20 and $3.55 a ton, respectively, for 1916; old range Bessemer was listed at $5.95 and old range non-Bessemer at $5.20 a ton for 1917, compared with $4.45 and $3.70 a ton, respectively, for 1916. These prices represent advances of $1.50 a ton on all grades of ore, or from 34 per cent to 42 per cent. These advances, though considerable, are not proportionate to the advances in the prices of pig iron during the corresponding period

Digitized by Google

(which averaged at the furnaces nearly 61 per cent), and iron ore producers succeeded in obtaining Government approval of an increase of 45 cents a ton on all grades of ore on July 1, 1918, and of 25 cents more, effective October 1, 1918.

Selling prices of iron ore per gross tons at lower Lake ports at date of buying movement, 1890–1918.[a]

Season.	Date of buying movement.	Season iron-ore prices.			
		Old range Bessemer.	Mesabi Bessemer.	Old range non-Bessemer.	Mesabi non-Bessemer.
1890	Dec. 15, 1889	$5.50	No sale.	$5.25	No sale.
1891	June 1, 1891	4.50	No sale.	4.25	No sale.
1892	Jan. 31, 1892	4.50	No sale.	3.65	No sale.
1893	Mar. 15, 1893	3.85	$3.00	3.20	No sale.
1894	Mar. 1, 1894	2.75	2.35	2.50	No sale.
1895	Apr. 1, 1895	2.90	2.15	2.25	$1.90
1896	May 1, 1896	4.00	3.50	2.70	2.25
1897	May 20, 1897	2.60	2.25	2.15	1.90
1898	Mar. 20, 1898	2.75	2.25	1.85	1.75
1899	Feb. 1, 1899	3.00	2.40	2.15	2.00
1900	Dec. 15, 1899	5.50	4.50	4.25	4.00
1901	Apr. 15, 1901	4.25	3.25	3.00	2.75
1902	Feb. 1, 1902	4.25	3.25	3.25	2.75
1903	Mar. 20, 1903	4.50	4.00	3.60	3.20
1904	Apr. 15, 1904	3.25	3.00	2.75	2.50
1905	Feb. 1, 1905	3.75	3.50	3.20	3.00
1906	Dec. 5, 1905	4.25	4.00	3.70	3.50
1907	Nov. 5, 1906	5.00	4.75	4.20	4.00
1908	June 15, 1908	4.50	4.25	3.70	3.50
1909	May 10, 1909	4.50	4.25	3.70	3.50
1910	Dec. 24, 1909	5.00	4.75	4.20	4.00
1911	Apr. 21, 1911	4.50	4.25	3.70	3.50
1912	Mar. 20, 1912	3.75	3.50	3.00	2.85
1913	Nov. 19, 1912	4.40	4.15	3.60	3.40
1914	May 1, 1914	3.75	3.50	3.00	2.85
1915	Apr. 19, 1915	3.75	3.45	3.00	2.80
1916	Dec. 7, 1915	4.45	4.20	3.70	3.55
1917	Nov. 22, 1916	5.95	5.70	5.20	5.05
1918[b]	Apr. 1, 1918	5.95	5.70	5.20	5.05
	July 1, 1918	6.40	6.15	5.65	5.50
	Oct. 1, 1918	6.65	6.40	5.90	5.75

[a] Iron Trade Review.
[b] Prices approved by the Government Apr. 1, were advanced 45 cents for all grades on July 1, and 25 cents more on Oct. 1.

MINING DEVELOPMENTS.

In a comprehensive review of the mining developments and conditions in the Lake Superior district, particularly the Minnesota ranges, for the year 1917, by Sawhill,[1] it is indicated that exploration and development work in this district has uncovered sufficient ore nearly to match the record shipments of this and the preceding year. In this article it is pointed out that no public campaign was necessary in order to stimulate the production of iron ore to meet the war demand and that there was every reason to believe that the Lake Superior district would be able to continue to meet that demand, should it be necessary, throughout 1918. Transportation agencies were handicapped to a greater degree in 1917 than in the preceding year by inclement weather, ice, and shortage of boats, but, as indicated on page 573, the Lake shipments fell off only about 2,235,000 tons.

[1] Sawhill, R. V., How ore districts meet war demand: Iron Trade Rev., Jan. 3, 1918, pp. 85–94, 108.

Digitized by Google

Shipments of iron ore from mines to furnaces entirely by rail, notwithstanding prophesies to the contrary, showed only a small increase—less than 14,000 tons—and amounted to less than 2,000,000 gross tons in all. Some of this ore was shipped to blast furnaces at St. Louis, Mo. An interesting development in this connection is the transportation in 1917 of about 3,000 tons of ore by barge down Mississippi River from St. Paul, Minn., to St. Louis, Mo. Such navigation is possible from March to November, inclusive, and it is expected that the quantity of ore so carried will increase and that it will also include ore mined at Waukon, Iowa.

Development of labor-saving equipment has become an important feature of iron-ore mining in the Lake Superior district, and has been stimulated by the shortage of labor coupled with the necessity of getting out extraordinary quantities of ore in 1916 and 1917. Mammoth steam shovels are increasing in number; pneumatically operated 20-ton steel ore cars are being substituted for hand-operated 7-ton wooden cars, and heavier locomotives also are used; dirt spreaders and track layers dispense with gangs of laborers; drag-line excavators are coming into use as well as skip hoists; ore loaders for underground mines are being developed; and mining equipment is being electrified.

Ore concentration, especially of the lean ores of the western part of the Mesabi range, continued to make progress. Three new washing plants are reported to have been completed in 1917; three more were under construction, besides six plants already in operation. Screens especially developed for rock separation were installed at three mines.

At the beginning of 1917 there was considerable uncertainty as to whether labor conditions might be such as to interfere seriously with mining and shipment of the required quantity of iron ore, because in 1916 there had been considerable unrest and some strikes due to agitation by outside influences. During 1917, however, the unrest subsided to a great extent, the high wages contributing in no small measure to this result. Two wage increases were made during 1917, one on May 1 and another on October 1, so that common labor received at the close of the year $3.45 per day and contract miners earned in many instances in excess of $4.75 per day. The following table [1] indicates the advance in wages during the last two years:

Wages in iron mines of Lake Superior district, 1915–1917.

Kind of labor.	Daily wages.				
	1915 (Dec. 1).	1916		1917	
		Dec. 1.	Dec. 15.	May 1.	Oct. 1.
Common labor	$2.25	$2.60	$2.85	$3.15	$3.45
Common labor (company account)	2.60	2.90–3.00	3.20–3.30	3.40–3.50	3.70–4.00
Miners (contract)	2.75–2.85	3.50	3.85	4.25	4.70–4.75

[1] Iron Trade Rev., Jan. 3, 1918, p. 92.

Digitized by Google

Notwithstanding these very liberal wages labor is generally considered to be less efficient than in the days of greater competition and more moderate wages.

The shortage of labor was accented to some extent by the Nation's call to war service, for there was a patriotic response in the way of enlistments and many men were drafted, but the inroads upon the mining organizations were not as great proportionately as in many other industries on account of the large alien population in the iron-ore districts.

IRON-ORE RESERVES.

In view of the heavy draft on ore reserves since the beginning of the European war a comparison of tonnage estimates at different periods is of interest. Data are available for the reserves in Minnesota and in Michigan, but not for Wisconsin. The ore reserves of Wisconsin are, however, much smaller than those of the other two States. The estimates of ore reserves in Minnesota were prepared by the Minnesota Tax Commission, and those for Michigan by R. C. Allen, State geologist. The figures given in the following tables include developed and prospective ore in the ground and ore in stock piles.

Iron-ore reserves in Minnesota May 1, 1915, 1916, and 1917, in gross tons.

Range.	1915.	1916.	1917.
Mesabi	1,389,003,652	1,384,635,891	1,381,674,246
Vermilion	11,011,974	13,058,280	11,961,684
Cuyuna	72,403,065	77,926,062	69,915,118
	1,472,418,691	1,475,620,233	1,463,551,048

Iron-ore reserves in Michigan Jan. 1, 1916, 1917, and 1918, in gross tons.

Range.	1916.	1917.	1918.
Gogebic	45,932,974	47,317,323	55,813,661
Marquette	82,562,079	95,751,559	78,175,301
Menominee (including Iron River and Crystal Falls districts)	70,525,437	69,708,894	66,154,547
	199,020,490	212,777,776	200,143,509

The data for Minnesota and Michigan are not based on the same dates and are therefore not strictly comparable, but they show the trend of the balance between production and ore believed to be in reserve. In Minnesota the blocking out of new ore reserves during the year ending May 1, 1916, apparently more than kept pace with the depletion of the supplies, but during the next year there was an apparent falling off of more than 12,000,000 tons. This decrease, however, was largely due to revisions of earlier estimates of reserves on the Cuyuna range. In Michigan during the year ending January 1, 1917, exploration kept ahead of production, but on January 1, 1918, there appears to have been a decrease in the reserves of more than 12,600,000 gross tons, or about 70 per cent of the quantity mined in that State in 1917.

Digitized by Google

FOREIGN TRADE IN IRON ORE.

IMPORTS.

The quantity of iron ore imported into the United States in 1917 was 971,663 gross tons, valued at $3,655,392, or $3.76 a ton. This represents a decrease in quantity of 354,073 tons, or nearly 27 per cent, and in value of $911,122, or nearly 20 per cent, as compared with the imports during 1916, which were 1,325,736 gross tons, valued at $4,566,514, or $3.44 a ton. As to the source of the imports in 1917, Cuba produced more than 56 per cent of the ore, Canada 20 per cent, Spain 16 per cent, Sweden 6 per cent, and minor quantities came from French Africa and the United Kingdom. Supplies from Canada have increased since 1914, largely from the Canadian ranges in the Lake Superior region. The diagram (fig. 7), indicates the source and destination of the iron ore imported into the United States.



FIGURE 7.—Source and destination of iron ore imported into the United States in 1917.

The statistics of imports of iron ore are compiled from the records of the Bureau of Foreign and Domestic Commerce, Department of Commerce.

Iron ore imported into the United States, 1914–1917.

Country.	1914		1915		1916		1917	
	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.
Cuba	815,017	$2,288,102	831,618	$2,450,163	715,571	$2,195,409	546,069	$1,728,437
Spain	66,982	233,287	42,092	165,827	161,422	582,691	152,713	582,644
French Africa	46,175	114,781	21,825	47,272	38,004	95,342	8,860	22,212
Greece			738	2,895				
Newfoundland and Labrador	38,515	57,681						
United Kingdom	2,663	52,814			140	2,019	4,717	133,004
Germany	2,256	9,222						
Canada	52,514	153,415	84,124	245,092	136,835	509,572	195,588	850,153
Belgium								
Sweden	280,887	1,481,747	204,632	1,061,624	212,063	1,108,216	63,715	338,936
Chile	35,180	41,760	153,600	181,271	71,701	73,265		
Other countries	[a] 10,399	[a] 51,023	[b] 2,652	[b] 27,501			[c] 1	6
	1,350,588	4,483,832	1,341,281	4,181,645	1,325,736	4,566,514	971,663	3,655,392

[a] Of this, 2,400 tons, valued at $3,600, was from Venezuela, and 6,050 tons, valued at $40,039, was from French Oceania.
[b] Of this, 2,638 tons, valued at $27,280, was from Egypt.
[c] Norway.

Digitized by Google

In the following table are shown the annual imports of iron ore into the United States as far as recorded. Iron ore was imported from Europe in large quantities for the first time in 1879, most of the imports prior to that date coming from Canada.

Iron ore imported into the United States, 1872–1917, in gross tons.

Year.	Quantity.	Year.	Quantity.	Year.	Quantity.
1872	23,733	1888	587,470	1905	845,651
1873	45,981	1889	853,573	1906	1,060,390
1874	57,987	1890	1,246,830	1907	1,229,168
1875	56,655	1891	912,864	1908	776,898
1876	17,284	1892	806,585	1909	1,694,957
1877	30,669	1893	526,951	1910	2,591,031
1878	28,212	1894	167,307	1911	1,811,732
1879[a]	150,197	1895	524,153	1912	2,104,576
1879[b]	284,141	1896	682,806	1913	2,594,770
1880	493,408	1897	489,970	1914	1,350,588
1881	782,887	1898	187,208	1915	1,341,281
1882	589,655	1899	674,082	1916	1,325,736
1883	490,875	1900	897,831	1917	971,663
1884	487,820	1901	966,950		
1885	390,786	1902	1,165,470		38,020,568
1886	1,039,433	1903	980,440		
1887	1,194,301	1904	487,613		

[a] Fiscal years end. [b] Calendar years begin.

EXPORTS.

The quantity of iron ore exported from the United States in 1917 amounted to 1,132,313 gross tons, valued at $4,464,111, or $3.94 a ton, as compared with 1,183,952 gross tons, valued at $3,702,496, or $3.13 a ton, in 1916. This represents a decrease in quantity of 51,639 tons, or 4 per cent, and an increase in value of $761,615, or 20 per cent. The greater part of the ore was exported to Canada, it is understood, for the manufacture of iron and steel at plants in Ontario. More ore was exported to Canada in 1917 than was imported into the United States from all sources.

The data regarding exports are compiled from the records of the Bureau of Foreign and Domestic Commerce, Department of Commerce.

Iron ore exported from the United States, 1916–1917.

Country	1916		1917	
	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.
England	5	$300	45	$1,359
Canada	1,183,679	3,699,727	1,129,390	4,451,240
Brazil	100	605	.....	.....
Chile	168	1,864	.....	.....
Mexico	.....	.....	2,878	11,512
	1,183,952	3,702,496	1,132,313	4,464,111

Digitized by Google

Iron ore exported from the United States, 1899–1917, in gross tons.

Year.	Quantity.	Year.	Quantity.
1899	40,665	1909	455,934
1900	51,460	1910	748,875
1901	64,703	1911	768,386
1902	88,445	1912	1,195,742
1903	80,611	1913	1,042,151
1904	213,865	1914	551,618
1905	208,017	1915	707,641
1906	265,240	1916	1,183,952
1907	278,608	1917	1,132,313
1908	309,099		9,387,325

IRON-ORE INDUSTRY OF CUBA.

The iron ore shipped from Cuba to the United States in 1917 amounted to 553,485 gross tons, valued at $2,793,113, compared with 712,716 gross tons, valued at $2,196,327, in 1916, a decrease in quantity of 159,231 tons, or 22 per cent, and an increase in value of $596,786, or 27 per cent. The average selling price of the ore was apparently $5.05 a ton in 1917, compared with $3.08 in 1916. The shipments in 1917 consisted of 48 per cent of hematite, including a little magnetite, from the Daiquiri, Juragua, and Cuero mines on the southern coast, and 52 per cent of brown ore from the Mayari mines, near the northern coast. In 1916 the iron content of the hematite, dried at 212° F., ranged from 57 per cent to 60.03 per cent, and the brown ore carried 35.22 per cent (natural) and 52.44 per cent (nodulized), and in 1917, hematite (natural) ranged from 55.67 per cent to 58.61 per cent, with one report of dried ore that carried 58.81 per cent, and the brown ore carried 35.05 per cent (natural) and 54.23 per cent (nodulized). The product of the Cuero mines is noted as a low-phosphorus ore. The total stock of ore reported as on hand at the close of 1917 was 1,166,934 gross tons, compared with 628,120 tons at the close of 1916. This included both natural and nodulized ore.

The following table shows the shipments of iron ore from Cuba since the opening of the mines in 1884. The curtailment of iron-ore production in Cuba as a result of the war in Europe is shown by these statistics. The sudden depression in the iron industry in 1914 reduced the Cuban ore output about 48 per cent as compared with 1913. In 1915 the output was about the same as in 1914, but in 1916 and 1917 the output was further restricted by the shortage of ships, notwithstanding the great need for these excellent and easily accessible ores at iron and steel plants on the eastern seaboard of the United States. The statistics of the Cuban iron-ore shipments are collected by the United States Geological Survey.

Digitized by Google

Iron ore shipped from mines in the Province of Oriente, Cuba, 1884–1917, in gross tons.

Year.	Juragua Iron Co. (Ltd.) (hematite and magnetite).	Sigua Iron Co. (hematite).	Spanish-American Iron Co.		Cuban Steel Ore Co. (hematite).	Ponupo Manganese Co., El Cuero iron mines (hematite).	Total.
			Daiquiri mines (hematite and a little magnetite).	Mayari mines (brown ore).			
1884	25,295						25,295
1885	80,716						80,716
1886	112,074						112,074
1887	94,240						94,240
1888	206,061						206,061
1889	260,291						260,291
1890	363,842						363,842
1891	264,262						264,262
1892	335,236	6,418					341,654
1893	337,155	14,020					351,175
1894	156,826						156,826
1895	307,503		74,991				382,494
1896	298,885		114,110				412,995
1897	[a] 248,256		[b] 206,029				454,285
1898	83,696		80,225				163,921
1899	161,783		211,442				373,225
1900	154,871		293,195				448,066
1901	199,764		[c] 334,974		17,651		552,389
1902	221,039		455,105		23,590		699,734
1903	155,898		467,629				623,527
1904	31,162		356,111				387,273
1905	139,828		421,331				561,159
1906	133,379		507,195				640,574
1907	181,063		469,111				650,174
1908	366,580		254,256				620,836
1909	356,659		519,752			59,721	936,132
1910	318,814		670,976	307,700		165,008	1,462,498
1911	355,132		252,717	387,791		168,074	1,163,714
1912	360,094		463,533	446,176		127,994	1,397,797
1913	369,213		591,322	491,713		130,183	1,582,431
1914	267,641		284,507	228,949		40,013	821,110
1915	215,032		245,590	300,896		65,930	827,448
1916	212,013		181,602	258,451		60,650	712,716
1917	39,784		181,028	287,904		44,769	553,485
	7,414,067	20,438	7,636,731	2,709,580	41,241	862,342	18,684,419

[a] Of this quantity, 5,932 tons were sent to Pictou, Nova Scotia.
[b] Of this quantity, 51,537 tons were sent to foreign ports.
[c] Of this quantity, 12,691 tons were sent to foreign ports.

PRODUCTION OF IRON ORE IN PRINCIPAL COUNTRIES.

Since the beginning of the war in Europe authentic statistics of iron ore output from most of the principal producing foreign countries have not been available, and in the chapter on iron ore in mineral resources for 1916 no table of production in principal countries was given. The greater importance that has become attached to foreign statistics and their interpretation since the United States became involved in the war has made it especially desirable to present once more as many of these figures as possible. The following table has been prepared from many more sources of information than were formerly utilized; consequently the data are not so uniform and in all probability are not so reliable as those obtained in times of peace directly from the governments concerned. Though the statistics are far from complete, and many of the figures are subject to revision, it is believed that the table will serve a useful purpose.

Digitized by Google

Iron ore produced in some principal countries, 1913-1917, in gross tons.

Country.	1913	1914	1915	1916	1917	Source of data.[a]
North America:						
Canada [b]	274,673	218,620	355,457	245,693	192,210	1913–1917, 1.
Cuba [b]	1,582,431	821,110	827,448	712,716	553,485	1913–1917, 2.
Newfoundland [b]	1,433,858	566,000	775,403	903,625	788,820	1913–1917, 1.
United States	61,980,437	41,439,761	55,526,490	75,167,672	75,288,851	1913–1917, 2.
South America:						
Chile [c]	13,877	62,484	153,600	61,701	.....	1913–14, 3; 1915–16, 4.
Venezuela [d]	57,225	2,400	(e)	(e)	(e)	1913–14, 4.
Europe:						
Austria-Hungary	5,233,055	3,939,248	/1,213,367	(e)	(e)	1913–1915, 5.
Belgium	147,048	(e)	(e)	(e)	(e)	1913, 5.
France	21,572,835	(e)	(e)	(e)	(e)	1913, 4.
Germany	26,771,593	(e)	(e)	(e)	(e)	1913, 4.
Greece	305,095	294,476	154,900	83,619	(e)	1913–1915, 5; 1916, 3.
Italy	593,618	695,124	669,042	927,101	g 516,070	1913–14, 4; 1915–16, 5; 1917, 6.
Luxemburg	7,215,514	4,926,980	6,040,765	6,643,689	4,436,682	1913–1917, 5.
Norway	77,667	641,700	706,379	865,700	(e)	1913–1916, 5.
Portugal	48,392	6,532	(e)	(e)	(e)	1913–14, 5.
Russia	7,947,191	(e)	(e)	(e)	(e)	1913, 5.
Spain	9,703,177	6,710,357	5,527,552	5,762,733	5,461,857	1913–1916,5; 1917, 7.
Sweden	7,355,428	6,480,773	6,772,683	6,874,018	(e)	1913–1916, 5.
United Kingdom	15,997,328	14,867,582	14,235,012	13,494,658	15,180,000	1913–1916, 8; 1917, 5.
Asia:						
China	h 416,342	h 488,258	537,047	274,078	299,465	1913–14, 9; 1915–1917, 5.
Chosen (Korea)	139,730	179,062	206,510	241,412	(e)	1913–1916, 10.
India	370,845	441,674	390,270	411,758	(e)	1913–1916, 5.
Japan	168,397	134,193	133,933	156,263	(e)	1913–1916, 10.
Philippine Islands	546	392	(e)	(e)	(e)	1913–14, 11.
Africa:						
Algeria	1,327,320	1,097,101	805,547	923,598	(e)	1913–1916, 5.
Morocco	.....	.....	186,149	(e)	(e)	1915, 5.
Tunis	584,649	244,528	281,304	361,593	596,261	1913–1917, 5.
Australia	i 90,712	177,938	370,887	390,108	j 328,310	1913, 4; 1914–1916, 5; 1917, 3.

[a] 1, Canada Department of Mines, Mines Branch; 2, United States Geological Survey; 3, Mineral Industry; 4, United States Geological Survey Mineral Resources; 5, Iron, Steel and Allied Trades Federation (London) Statistical Report 3; 6, La Metallurgia Italiana, Sept. 1, 1917; 7, Engineering and Mining Journal, Nov. 9, 1918, p. 840; 8, Mines and Quarries (London); 9, Iron Trade Review, July 26, 1917; 10, Bureau of Foreign and Domestic Commerce, Department of Commerce; 11, Bureau of Mines, Manila, P. I.

[b] Shipments.
[c] Exports.
[d] Exports to United States.
[e] Statistics not available.
[f] For Hungary only.
[g] 6 months only.
[h] From Tayeh deposits only.
[i] For South Australia and Queensland.
[j] For South Australia only.

BENEFICIATED IRON ORE.

Statistics of beneficiated iron ore have been gathered by the Survey for the years beginning with 1914 and, although complete returns were not at first received from every producer who subjects his ore to any form of beneficiation, the responses to the special inquiries have been, on the whole, satisfactory and interesting and have shown continued improvement.

The following processes were reported as employed to improve the quality of the ore at various mines: Crushing and screening, drying by direct heat and by steam, hand picking on tables and on belts, washing by means of hydraulic jets and logs, jigging, electromagnetic cobbing, other concentration and separation, calcining, nodulizing, and desulphurization by sintering. Some of the operations combined two or more of these processes. Iron ores were reported as beneficiated at 94 mines in 16 States in 1917 and at 83 mines in 14 States

Digitized by Google

in 1916, and in addition at the brown-ore mines of the Spanish-American Iron Co. in the Mayari district, Cuba.

In addition to these processes some iron ore is recovered in the form of blast-furnace ore dust, but no statistics have been gathered on this subject. Ore so recovered has been originally accounted for in the statistics of shipments from the mines. Operations which involve sintering of the ore dust have been carried on by the Sintered Ore Co., at Buffalo, N. Y., and the American Sintering Co., at Youngstown, Ohio.

In Alabama the ore treated was principally brown ore, and the usual processes to which it was subjected were log washing, screening, and picking belt. A total of 1,159,624 gross tons of beneficiated ore, valued at $3,324,715, was marketed from 19 mines in Alabama in 1917, compared with 996,344 tons, valued at $1,969,706, from 12 mines in 1916. Of this quantity 242,742 tons were hematite run over a picking belt.

One mine in Connecticut, 10 in Georgia, 1 in Iowa, 1 in Maryland, 1 in Massachusetts, and 1 in Missouri reported the concentration of brown ore in 1917.

Red hematite was beneficiated at 2 mines in Michigan and at 18 mines in Minnesota in 1917. Washing and drying were the principal processes employed, and 1 mine reported crushing and picking also in 1917.

Five mines reported magnetic concentration of magnetite in New Jersey, and at 2 of them dry tables were employed in addition; 2 mines reported hand cobbing. At 1 mine in North Carolina, which produces magnetite, the ore was subjected to a rough concentration consisting of electromagnetic cobbing, and 2 mines reported washing of brown ore in 1917.

In New York beneficiation of ore was reported by 10 mines. One mine crushed washed brown ore; and the rest produced magnetite. The magnetite was mainly concentrated magnetically, although at one mine only crushing and hand picking on slow-moving belt were reported. The total shipments of beneficiated brown ore and magnetite in New York amounted to 958,979 gross tons, valued at $5,446,881, in 1917, compared with 1,042,823 tons, valued at $4,104,398, in 1916. At the Waukon, Iowa, brown-ore mine there was a large increase in production, the shipments of beneficiated ore having amounted in 1917 to 22,612 gross tons compared with 10,151 gross tons in 1916, an increase of more than 122 per cent. The product was shipped to the furnace of the Mississippi Valley Iron Co. at St. Louis, the owner of the mine.

In Pennsylvania 2 mines reported washing brown ore; at 1 mine the Grondal concentrating process was employed; 1 magnetite mine reported desulphurization by sintering. The shipments of beneficiated ore from this State amounted to 215,380 gross tons, valued at $1,031,296, in 1917, compared with 208,351 tons, valued at $776,830, in 1916.

In Tennessee red hematite from the mines of the Rockwood-Cardiff area was improved by breaking and hand picking, and brown ore from 7 mines in the west-central belt was beneficiated. At six of these brown-ore mines washing was reported as the only method;

Digitized by Google

the other reported hand picking, washing, and jigging. In all probability, however, hand picking is employed to a greater or less extent at nearly all brown-ore mines where the ore occurs with gravel. Calcining of brown ore is practiced at one cold-blast furnace. The total beneficiated iron ore shipped from mines in Tennessee in 1917 was 334,254 gross tons, valued at $739,505, compared with 331,499 tons, valued at $533,266, in 1916. One magnetite mine reported hand picking.

Six mines reported beneficiation of brown ore in Virginia in 1917, compared with seven in 1916. The total shipments of treated ore in 1917 amounted to 134,215 gross tons, valued at $350,203, compared with 155,436 tons, valued at $307,653, in 1916. A small quantity of magnetite was also treated at one of these mines. Washing, screening, and jigging were the methods employed in treating the brown ore.

The brown ores of the Mayari mines, Cuba, have been nodulized for many years at an extensive plant at Felton, on Nipe Bay. The total quantity of this ore reported as shipped in 1917 amounted to 285,724 gross tons, compared with 257,605 tons in 1916.

The total beneficiated ore reported as shipped from mines in the United States in 1917 amounted to 8,166,564 gross tons, valued at $27,733,036, compared with 8,105,011 tons, valued at $21,037,364, in 1916. This represents an increase in quantity of 61,553 tons, or about 0.76 per cent. From such figures as are available, showing the relation between crude ore treated and beneficiated ore recovered, it is apparent that in washing brown ore the ratios, by weight, of crude ore washed to resultant concentrates range from 7:1 to 1.24:1; in concentrating red hematite, the ratios range from 1.69:1 to 1.056:1; and in magnetite they range from 3.89:1 to 1.041:1.

Beneficiated iron ore shipped from mines in the United States, 1916 and 1917.

State.	Variety.	1916		1917	
		Quantity (gross tons).	Value.	Quantity (gross tons).	Value.
Alabama	Red hematite, brown ore	996,344	$1,969,706	1,159,624	$3,324,715
Georgia	Brown ore	104,583	196,771	88,156	223,171
Minnesota	Red hematite	4,576,249	10,801,034	4,576,626	13,471,608
New Jersey	Magnetite	528,084	1,877,056	471,253	2,325,723
New York	Red hematite, brown ore, magnetite	1,042,823	4,104,398	958,979	5,446,881
North Carolina	Brown ore, magnetite	(a)	(a)	38,163	216,929
Pennsylvania	Brown ore, magnetite	208,351	776,830	215,380	1,031,296
Tennessee	Red hematite, brown ore, magnetite	331,499	533,266	334,254	739,505
Virginia	Brown ore, magnetite	155,436	307,653	134,215	350,203
Other States [b]	Red hematite, brown ore, magnetite	161,642	470,650	189,914	603,005
		8,105,011	21,037,364	8,166,564	27,733,036

[a] Included in "Other States."
[b] 1916: Connecticut, Iowa, Maryland, Massachusetts, Michigan, Missouri, and North Carolina. 1917: Connecticut, Iowa, Maryland, Massachusetts, Michigan, Missouri, and New Mexico.

Digitized by Google

IRON AND STEEL.

The records of the production and sales of iron and steel for 1917 in comparison with former years are shown in the following pages, the data being derived from several authoritative sources, such as the American Iron and Steel Institute, Metal Statistics, the Iron Age, the Iron Trade Review, the Bureau of Foreign and Domestic Commerce, and especially from the producers who report directly to the United States Geological Survey.

PIG IRON.

PRODUCTION, SHIPMENTS, AND VALUE, BY STATES.

The bureau of statistics of the American Iron and Steel Institute reports the production in 1917 of all kinds of pig iron, including such ferroalloys as spiegeleisen, ferromanganese, ferrosilicon, and ferrophosphorus, produced in blast furnaces as well as some that were electrically produced, as amounting to 38,621,216 gross tons, compared with 39,434,797 tons produced in 1916, a decrease of 813,581 tons, or about 2 per cent.

Pig iron, including some ferroalloys, manufactured in the United States in 1916 and 1917, in gross tons.[a]

	1916	1917		1916	1917
Pennsylvania	16,506,284	15,539,728	Virginia	399,885	520,311
Ohio	8,602,895	8,518,603	Missouri		
Illinois	3,922,512	3,456,915	Iowa [b]		
Alabama	2,762,885	2,953,705	Colorado	437,633	453,742
Indiana			Washington		
Michigan	2,221,708	2,657,503	California		
New York			Maryland	501,452	422,212
New Jersey	2,352,535	2,417,527	Tennessee	355,374	369,951
Wisconsin			Connecticut		
Minnesota	811,325	738,541	Massachusetts	5,719	10,527
West Virginia					
Georgia	554,590	561,951		39,434,797	38,621,216
Kentucky					

[a] Bureau of statistics of the American Iron and Steel Institute.
[b] Ferrosilicon produced in electric furnace for first time in 1916.

According to reports to the United States Geological Survey by the manufacturers, the shipments of pig iron, exclusive of ferroalloys, in 1917 amounted to 38,612,546 gross tons, valued f. o. b. at the furnaces at $1,053,785,975, as compared with 39,126,324 tons, valued at $663,478,118, in 1916, a decrease in quantity of 513,778 tons, or 1.3 per cent, and an increase in gross value of $390,307,857, or nearly 59 per cent. These values represent the approximate amounts received for the iron f. o. b. at the furnaces, and eliminate freight costs, selling commissions, and other items which are included in some of the market prices of pig iron as published in the trade journals.

The pig iron shipped includes the metal produced from foreign as well as from domestic ore. The quantity and value of pig iron derived from ore imported from Africa, Canada, Cuba, Spain, and Sweden, although it constitutes a very small percentage of the total production, is considerable, as it is calculated that the shipments derived from foreign ore in 1917 amounted to 505,216 gross tons, valued at $14,381,196, as compared with 764,850 tons, valued at

Digitized by Google

$15,996,756, in 1916. In the manufacture in 1917 of 486,561 gross tons of pig iron, 912,630 gross tons of foreign iron ore were reported to have been used, thus indicating an average pig-iron yield of 53.31 per cent, as compared with the quantity of imported ore. Domestic ore including 5,484,267 tons of cinder, scale, scrap, etc., and amounting to 74,592,448 gross tons, was reported in 1917 as used in the manufacture of 37,437,929 tons of pig iron, thus indicating a yield of 50.19 per cent in pig iron from the domestic materials. The total production in 1917 of pig iron, exclusive of ferroalloys, reported to the Survey was 37,924,490 gross tons.

Pig iron shipped from blast furnaces in the United States in 1916 and 1917.

State.	1916		1917		Change in 1917.		Percentage of change, 1917.	
	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.	Quantity.	Value.
Alabama	2,672,498	38,994,660	2,971,626	$64,309,714	+ 299,128	+$25,315,054	+ 11	+ 65
Illinois	3,857,391	67,764,309	3,458,126	91,094,541	− 399,265	+ 23,330,232	− 10	+ 35
Kentucky	144,444	2,595,600	192,204	5,532,367	+ 47,760	+ 2,936,767	+ 33	+113
Michigan	506,646	8,851,361	611,446	18,300,501	+ 105,800	+ 9,449,140	+ 21	+107
New Jersey	(a)	(a)	187,753	6,618,536	(b)	(b)	(b)	(b)
New York	2,289,608	40,537,240	2,276,367	52,318,661	− 13,241	+ 11,781,421	− .6	+ 29
Ohio	8,689,030	136,855,228	8,469,052	231,165,093	− 219,978	+ 94,309,865	− 3	+ 69
Pennsylvania	16,351,131	293,437,782	15,423,262	460,677,474	− 927,869	+167,239,692	− 6	+ 57
Tennessee	329,342	4,981,538	346,338	9,102,441	+ 17,296	+ 4,120,903	+ 5	+ 83
Virginia	444,491	7,140,002	562,299	15,703,295	+ 117,808	+ 8,563,293	+ 26	+120
Wisconsin	423,973	7,534,327	402,732	11,052,274	− 21,241	+ 3,497,947	− 5	+ 46
Other states c	3,418,770	54,786,071	3,711,041	87,981,078	+b480,024	+b39,763,543	+b14	+b73
	39,126,324	663,478,118	38,612,546	1,053,785,975	− 513,778	+390,307,857	− 1.3	+ 59

a Included with "Other States."
b Increase in New Jersey included in "Other States."
c 1916: California, Colorado, Connecticut, Indiana, Maryland, Massachusetts, Minnesota, Missouri, New Jersey, and West Virginia. 1917: Colorado, Connecticut, Georgia, Indiana, Maryland, Massachusetts, Minnesota, Missouri, Washington, and West Virginia.

AVERAGE PRICES.

The average price per gross ton of all kinds of pig iron, by States, from 1912 to 1917, given in the following table is based on reports of the manufacturers to the Survey. These figures represent the approximate prices f. o. b. at the blast furnaces and do not include the prices of ferroalloys.

The general average prices for 1916 and 1917 appear low for such active years in the iron industry. At the close of 1916 market prices of pig iron were between 45 and 68 per cent higher than at the beginning of the year, but this increase was confined almost entirely to the last two or three months of the year (see fig. 8), so that the average increase in price was only 28 per cent as compared with 1915. In 1917, however, the course of prices was very different, for at the beginning and end of the year prices were more nearly the same with the high levels at the middle of the year. The curve (fig. 8) of market prices of basic iron at Valley furnaces reflects this unusual condition. The general average price for all grades of pig iron at the furnaces, exclusive of ferroalloys, for the year 1917 was $27.29, as compared with $16.96 in 1916, an increase of $10.33 a ton, or nearly 61 per cent. The States in which the average selling price of pig iron was more than $30 a ton were Connecticut, Georgia, Massachusetts, Missouri, New Jersey, and Washington.

Average price per gross ton of pig iron in the United States, 1912 to 1917.

State.	1912	1913	1914	1915	1916	1917
Alabama	$10.75	$12.08	$10.82	$10.24	$14.59	$21.64
Illinois	15.26	15.83	13.59	13.93	17.57	26.34
Kentucky	15.74	16.09	12.24	13.44	17.97	28.78
Michigan	14.30	14.69	13.78	13.63	17.51	29.93
New Jersey	(a)	(a)	(a)	(a)	(a)	35.25
New York	14.22	15.35	14.26	14.02	17.70	22.98
Ohio	13.07	15.02	13.46	12.96	15.75	27.30
Pennsylvania	14.60	15.36	13.78	13.69	17.95	29.87
Tennessee	12.29	13.22	12.05	12.09	15.13	26.26
Virginia	13.27	13.96	12.53	12.83	16.06	27.93
Wisconsin	14.33	15.13	13.35	13.20	17.77	27.39
Other States [b]	14.07	15.50	13.55	12.96	16.03	24.25
Average for United States	13.93	15.08	13.42	13.21	16.96	27.29

[a] Included in "Other States."

[b] 1912 and 1913: California, Colorado, Connecticut, Indiana, Maryland, Massachusetts, Minnesota, Missouri, New Jersey, and West Virginia; 1914: California, Colorado, Connecticut, Indiana, Maryland, Massachusetts, Minnesota, Mississippi, Missouri, New Jersey, and West Virginia; 1915: Colorado, Connecticut, Indiana, Maryland, Massachusetts, Minnesota, Missouri, New Jersey, and West Virginia; 1916: California, Colorado, Connecticut, Indiana, Maryland, Massachusetts, Minnesota, Missouri, New Jersey, and West Virginia; 1917: Colorado, Connecticut, Georgia, Indiana, Maryland, Massachusetts, Minnesota, Missouri, Washington, and West Virginia.

In the following summary of the annual average price per gross ton of pig iron in the United States for the years 1889 to 1917, the prices prior to 1907 include the cost of transportation of some pig iron from blast furnaces to markets. Prior to 1910 the values of blast-furnace ferroalloys are included. Since 1910 the prices represent, as closely as can be ascertained, the average price paid for pig iron at the blast furnaces. The extreme range in prices is from $9.76 in 1894 to $27.29 in 1917. The lowest prices were in the years 1894 to 1898, and the highest (except for 1917) were in the years 1902 to 1907.

Average price per gross ton of pig iron in the United States, 1889–1917.

1889	$15.78	1899	$18.00	1909	$16.25
1890	16.43	1900	18.85	1910	15.45
1891	15.50	1901	15.25	1911	14.07
1892	14.32	1902	20.92	1912	13.93
1893	11.90	1903	19.12	1913	15.08
1894	9.76	1904	14.13	1914	13.42
1895	11.14	1905	16.63	1915	13.21
1896	10.47	1906	19.98	1916	16.96
1897	9.85	1907	20.56	1917	27.29
1898	9.90	1908	15.96		

MARKET PRICES.

The average monthly prices of the principal grades of pig iron either at the blast furnaces or at the nearest market for 1916 and 1917, according to published market quotations, are of interest in comparison with the general average prices per ton of pig iron in the United States ($16.96 and $27.29) reported to the Survey by blast-furnace operators. The accompanying diagram (fig. 8) graphically shows the price curve of basic pig iron at the blast furnaces in the Mahoning and Shenango valleys, Ohio and Pennsylvania, 1912 to 1917, inclusive. Beginning at $30 a ton in 1917 the price rose almost steadily from February to July, when it reached $52.50 per

Digitized by Google



FIGURE 8.—Curve showing prices of basic pig iron at blast furnaces in Mahoning and Shenango valleys, Ohio and western Pennsylvania, 1912 to 1917, by months. Statistics from the Iron Age, Jan. 3, 1918, p. 68.

Digitized by Google

ton, according to the Iron Age (and $53.52, according to Metal Statistics). These figures are among the top prices paid for this grade of pig iron since the Civil War. The effect of Government price regulation brought it down precipitately so that from October until the end of the year it was stationary at $33 a ton.

The following comment on pig iron prices in 1917 indicates the extremes reached before they were controlled by the Government.[1]

Pig iron accomplished the seemingly impossible in the year and basic, Bessemer, and foundry grades were sold freely at above $50, furnace. What they would have brought had the Government bar not been on prices during the latter part of the year when coke shortages produced a veritable famine of metal is an open question. Belief has been expressed by close students of the market that $75 to $100 would not have been beyond reason under the economic situation that then obtained. Bessemer in July sold at the top figure of $57, Valley, and the average for that month was $57.95, Pittsburgh. This represented an advance of $22 over the average for December, 1916. Basic rose from $30, Valley, in December of the previous year to $52.25 in July. Foundry iron got up to $55, Valley, in July, but failed to reach the figure it commanded in 1864, which was over $73, furnace. Nor did it equal its performance of the same year when prices in the Lehigh Valley between May and December ranged from $59.50 to $70.25 per ton. The high price for eastern Pennsylvania No. 2X in 1917 was $52.50, furnace. Low phosphorus iron experienced a most spectacular flight. In the first half of the year it advanced from $53.50 to $92.50, Philadelphia. These astounding values for pig iron symbolize the unexampled demand that existed for every form of blast furnace product. One of the effects of these very profitable prices for the maker was the reclaiming to production of many isolated and high-cost furnaces which long had been carried on the country's inactive list and were regarded as unlikely to resume.

Average monthly prices per ton of principal grades of pig iron, 1916 and 1917.[a]

Month.	1916				1917			
	Foundry pig iron at Valley furnaces.	Foundry pig iron at Birmingham, Ala., furnaces.	Bessemer pig iron at Valley furnaces.	Basic pig iron at Valley furnaces.	Foundry pig iron at Valley furnaces.	Foundry pig iron at Birmingham, Ala., furnaces.	Bessemer pig iron at Valley furnaces.	Basic pig iron at Valley furnaces.
January	$18.50	$14.92	$21.00	$18.00	$30.00	$24.27	$35.00	$30.00
February	18.50	14.64	20.50	17.88	30.00	24.13	35.00	30.00
March	18.50	15.00	20.67	18.48	34.96	29.67	36.70	31.93
April	18.50	15.00	21.00	18.48	39.16	33.76	41.36	38.52
May	18.44	15.00	21.00	18.21	42.65	36.62	44.12	41.46
June	18.39	14.63	21.00	18.25	49.19	40.92	53.50	49.23
July	18.25	14.00	21.00	18.00	53.00	45.36	55.56	53.52
August	18.27	14.00	21.00	18.00	53.00	45.00	54.26	51.70
September	18.58	14.38	21.33	18.27	47.68	42.60	47.58	43.80
October	20.56	15.35	23.81	20.17	33.00	33.00	36.30	33.00
November	25.60	19.72	29.40	24.80	33.00	33.00	36.30	33.00
December	29.84	23.38	34.84	29.84	33.00	33.00	36.30	33.00
Average	20.16	15.84	23.05	19.87	39.89	35.11	42.67	39.10

[a] Metal Statistics, 1918.

BLAST FURNACES.

The number of furnaces in blast on June 30 and December 31 and the total number of stacks recorded for the years 1916 and 1917, not including any electric reduction furnaces, as published by the bureau of statistics of the American Iron and Steel Institute, are as follows:

[1] Iron Trade Rev., Jan. 3, 1918, pp. 16–17.

Digitized by Google

Blast furnaces in the United States, 1916 and 1917.

State.	Furnaces in blast June 30, 1916.	Dec. 31, 1916.			Furnaces in blast June 30, 1917.	Dec. 31, 1917.		
		In.	Out.	Total.		In.	Out.	Total.
Pennsylvania	132	127	30	157	136	122	41	163
Ohio	67	65	12	77	72	64	15	79
Illinois	23	24	0	24	22	18	7	25
Alabama	31	29	18	47	34	34	13	47
New York	20	18	9	27	21	21	4	25
Virginia	9	9	13	22	12	15	4	19
Tennessee	12	11	7	18	12	10	6	16
Colorado	4	3	3	6	4	3	3	6
Missouri	1	2	0	2	2	2	0	2
Oregon	0	0	1	1	0	0	1	1
Washington					0	0	1	1
California	0	0	0	0	0	0	1	1
Maryland	4	4	1	5	4	2	3	5
New Jersey	1	1	4	5	4	5	0	5
Wisconsin	6	5	3	8	6	5	3	8
Minnesota	3	3	0	3	3	3	0	3
Indiana	10	10	0	10	12	13	1	14
Michigan	12	12	2	14	12	12	2	14
West Virginia	4	4	0	4	4	3	1	4
Kentucky	4	4	2	6	4	4	3	7
Georgia	0	0	4	4	0	1	3	4
Texas	0	0	2	2	0	0	2	2
Mississippi	0	0	1	1	0	0	1	1
Connecticut	0	1	2	3	2	2	1	3
Massachusetts	1	1	1	2	1	1	1	2
	344	333	115	448	367	340	117	457

MONTHLY PRODUCTION OF PIG IRON.

The accompanying diagram (fig. 9) illustrates the course of the manufacture of pig iron by months during the last six years. The rising production of 1912 and early 1913, the decline from the middle of 1913 to the close of 1914 broken by feeble rallies in March and August, 1914, the rapid rise in production from month to month throughout 1915 broken only slightly in November, the high level maintained continuously above 3,000,000 tons throughout 1916, culminating in the record production in October of 3,508,849 gross tons, and the generally high level maintained in 1917 broken only by decreases to below 3,000,000 tons in February and December, are graphically indicated.

PRODUCTION OF PIG IRON, BY GRADES.

The statistics of production of the principal grades of pig iron have been published by the American Iron and Steel Institute for 1913 to 1917, as follows:

Pig iron manufactured in the United States, 1913–1917, by grades, in gross tons.

Grade.	1913	1914	1915	1916	1917
Bessmer and low phosphorus	11,590,113	7,859,127	10,523,306	14,422,457	13,714,732
Basic (mineral fuel)	[a] 12,536,693	[a] 9,670,687	[a] 13,093,214	17,684,087	17,671,662
Forge pig iron	324,407	361,651	316,214	348,344	345,707
Foundry and ferrosilicon	5,220,343	4,533,254	4,864,348	5,553,644	5,328,258
Malleable	993,736	671,771	829,921	921,486	1,015,579
Spiegeleisen	110,338	79,935	97,885	194,002	192,985
Ferromanganese	119,495	106,083	129,072	221,532	260,125
White, mottled, direct castings, etc	71,027	49,736	62,253	89,245	92,168
	30,966,152	23,332,244	29,916,213	39,434,797	38,621,216

[a] Includes a small quantity of basic iron made with charcoal.

Digitized by Google



FIGURE 9.—Curve showing production of coke and anthracite pig iron in the United States, 1912–1917, by months. Statistics from the Iron Age, Jan. 10, 1918.

Digitized by Google

PRODUCTION OF PIG IRON ACCORDING TO FUEL USED.

In the following table are given the statistics of the American Iron and Steel Institute showing the production of pig iron, according to the fuel used, from 1913 to 1917. The charcoal figures include small quantities of pig iron made with charcoal and electricity. The totals for each of the five years also include small quantities of ferroalloys made with electricity and with coke and electricity.

Pig iron manufactured in the United States, 1913–1917, by fuel used, in gross tons.

Fuel used.	1913	1914	1915	1916	1917
Bituminous, chiefly coke	30,326,130	22,976,856	29,535,308	38,844,598	37,863,643
Anthracite and coke	277,595	89,569	84,753	217,788	381,048
Anthracite alone	22,446	1,895			
Charcoal	339,981	263,924	296,152	372,411	376,525
	30,966,152	23,332,244	29,916,213	39,434,797	38,621,216

TOTAL PRODUCTION OF PIG IRON.

The next table shows the production in the United States of pig iron, including the commoner ferroalloys, as far as has been recorded. The statistics for 1912 to 1917 are those of the American Iron and Steel Institute; those for the years from 1854 to 1911 were collected by the American Iron and Steel Association; those for 1810, 1840, and 1850 are census figures; those for the other years are largely estimates by early statisticians.

Pig iron manufactured in the United States, 1810–1917, in gross tons.

Year.	Quantity.	Year.	Quantity.	Year.	Quantity.
1810	53,908	1866	1,205,963	1893	7,124,502
1820	20,000	1867	1,305,923	1894	6,657,388
1828	130,000	1868	1,431,250	1895	9,446,308
1829	142,000	1869	1,711,287	1896	8,623,127
1830	165,000	1870	1,665,179	1897	9,652,680
1831	191,000	1871	1,706,793	1898	11,773,934
1832	200,000	1872	2,548,713	1899	13,620,703
1840	286,903	1873	2,560,963	1900	13,789,242
1842	215,000	1874	2,401,262	1901	15,878,354
1846	765,000	1875	2,023,733	1902	17,821,307
1847	800,000	1876	1,868,961	1903	18,009,252
1848	800,000	1877	2,066,594	1904	16,497,033
1849	650,000	1878	2,301,215	1905	22,992,380
1850	563,755	1879	2,741,853	1906	25,307,191
1852	500,000	1880	3,835,191	1907	25,781,361
1854	657,337	1881	4,144,254	1908	15,936,018
1855	700,150	1882	4,623,323	1909	25,795,471
1856	788,515	1883	4,595,510	1910	27,303,567
1857	712,640	1884	4,097,868	1911	23,649,547
1858	629,548	1885	4,044,526	1912	29,726,937
1859	750,560	1886	5,683,329	1913	30,966,152
1860	821,223	1887	6,417,148	1914	23,332,244
1861	653,164	1888	6,489,738	1915	29,916,213
1862	703,270	1889	7,603,642	1916	39,434,797
1863	846,075	1890	9,202,703	1917	38,621,216
1864	1,014,282	1891	8,279,870		
1865	831,770	1892	9,157,000		627,960,624

Digitized by Google

FOREIGN TRADE IN PIG IRON.

IMPORTS.

The quantity of pig iron and ferroalloys, the principal of which were ferromanganese and ferrosilicon, imported into the United States in 1917 was 76,786 gross tons, compared with 135,349 tons imported in 1916, a decrease of 58,563 tons, or 43 per cent. Separate statistics of imports of ferroalloys given on page 599 indicate that the imports of pig iron alone (by difference) were 21,023 gross tons in 1917 compared with 37,533 tons in 1916, a decrease of 16,510 tons, or nearly 44 per cent. The United Kingdom furnished the largest quantity of these products in both years; Canada and China followed in order of importance in 1917.

The statistics of imports of iron are compiled from the records of the Bureau of Foreign and Domestic Commerce, Department of Commerce, and the following table gives the imports from the various countries from 1913 to 1917:

Pig iron, including kentledge, ferromanganese, ferrosilicon, and spiegeleisen, imported into the United States, 1913–1917, in gross tons.

Country.	1913	1914	1915	1916	1917
North America:					
Canada	4,609	25,968	21,166	33,716	21,143
Newfoundland and Labrador	.....	200	.....	.....	.....
West Indies	72	.....	.....	.....	83
South America	.....	250	.....	.....	.....
Europe:					
Austria-Hungary	340	899	.....	.....	.....
Belgium	256	500	.....	.....	.....
France	179	40	20	.....	.....
Germany	8,358	10,609	600	341	.....
Italy	.....	550	.....	.....	20
Netherlands	460	2,539	.....	.....	.....
Norway	117	225	.....	.....	.....
Sweden	2,002	2,329	1,392	792	.....
Switzerland	1,680	.....	.....	.....	.....
United Kingdom (England	131,340	90,627	59,105	89,764	51,384
United Kingdom (Scotland	1,581	1,012	792	.....	250
Asia:					
British India	2,439	1,310	2,382	1,313	.....
China	3,017	200	3,430	8,861	3,503
China, leased territory (British)	.....	1,285	.....	.....	.....
Hongkong	.....	200	.....	.....	.....
Japan	.....	70	250	562	85
Oceania	.....	90	.....	.....	.....
Other countries	.....	.....	699	.....	318
	156,450	138,903	89,836	135,349	76,786

EXPORTS.

The quantity of pig iron exported from the United States in 1917 was 656,220 gross tons, compared with 607,236 tons in 1916, an increase of 48,984 tons, or 8 per cent. The increase in value, from $15,381,431 in 1916 to $24,037,051 in 1917, represented more than 56 per cent. The largest quantity was shipped in 1916 and 1917 to Italy, and considerable quantities were shipped also to Canada, England, and France, and Japan became a larger purchaser in 1917, but exports to Denmark and the Netherlands decreased notably. Several European countries were added to the list in 1916, and the exports to Switzerland, Denmark, Netherlands, Spain, Norway, and Sweden at this time were due to war conditions in Europe.

Digitized by Google

The following table has been compiled from records of the Bureau of Foreign and Domestic Commerce:

Pig iron exported from the United States to foreign countries, 1913–1917, in gross tons.

Country.	1913	1914	1915	1916	1917
North America:					
Canada	193,396	57,852	60,197	101,277	153,745
Costa Rica	310	18	50	68	26
Mexico	85	454	684	676	920
Panama	3,921	1,056	2,316	1,968	1,816
West Indies:					
Cuba	646	593	844	5,338	4,243
South America:					
Argentina	792	1,042	912	380	2,580
Brazil	1,305	575	304	1,176	1,483
Chile	690	1,875	2,716	6,500	8,888
Peru	172	200	286	682	578
Europe:					
Austria-Hungary	4,601	1,150	.....	.....	.....
Belgium	4,715	1,219	.....	.....	.....
Denmark	48	.....	.....	17,380	1,836
France	752	397	9,414	71,226	65,618
Germany	1,723	749	.....	.....	.....
Greece	.....	.....	.....	50	.....
Italy	24,551	14,288	81,792	234,213	184,763
Netherlands	1,516	1,467	1,993	22,464	2,124
Norway	.....	.....	.....	11,267	12,986
Russia in Europe	.....	.....	.....	926	6,017
Spain	.....	.....	.....	8,464	5,891
Sweden	.....	.....	.....	20,707	17,799
Switzerland	.....	.....	.....	3,671	1,404
United Kingdom—					
England	20,972	18,013	57,368	88,315	138,196
Scotland	396	148	.....	2,249	7,874
Ireland	26	.....	.....	357	1,610
Asia:					
Japan	2,293	2,938	1,811	5,033	30,809
Oceania:					
Australia	14,354	10,099	2,008	433	257
New Zealand	85	.....	.....	260	760
All other countries	299	290	1,814	2,156	3,997
	277,648	114,423	224,509	607,236	656,220
Value	$4,026,306	$1,638,102	$3,667,167	$15,381,431	$24,037,051

PRODUCTION OF PIG IRON IN PRINCIPAL COUNTRIES.

The following table is taken from Metal Statistics, 1918. The grand totals are regarded as representing the world's production of pig iron:

Pig iron manufactured in principal countries in 1850, 1890, 1900, 1910, 1913, 1915, and 1916, in gross tons.[a]

Country.	1850	1890	1900	1910	1913	1915[b]	1916[c]
United States	563,755	9,202,703	13,789,242	27,303,567	30,966,152	29,916,213	39,434,797
Germany	350,000	4,584,882	8,381,373	14,559,509	19,004,022	11,603,874	13,000,000
Great Britain	2,300,000	7,904,214	8,959,691	10,217,022	10,481,917	8,793,659	9,047,983
France	405,653	1,931,188	2,669,966	3,974,478	5,227,378	4,000,000	5,000,000
Russia	227,555	912,561	2,889,789	2,992,058	4,474,757	3,638,000	4,300,000
Austria-Hungary	250,000	910,685	1,472,695	2,153,788	2,335,170	1,929,000	2,000,000
Belgium	144,452	775,385	1,001,872	1,822,821	2,318,767	500,000	1,000,000
Canada	.....	19,439	86,090	740,310	1,015,118	825,420	1,069,541
Sweden	150,000	483,155	518,263	594,385	728,103	755,000	750,000
Spain	.....	176,598	289,315	367,423	418,061	421,000	440,000
Italy	.....	14,094	23,569	347,657	420,011	389,000	454,923
Other countries	10,000	80,000	100,000	400,000	500,000	500,000	500,000
	4,401,415	26,994,904	40,181,865	65,472,918	77,889,856	63,271,166	77,000,000

[a] Metal Statistics, 1918, p. 49.
[b] Partly estimated.
[c] Largely estimated. Production in Belgium wholly, and in France largely, by Germans.

Digitized by Google

FERROALLOYS.[1]

The activity in the domestic ferroalloy industry that developed in 1916 continued unabated during 1917. The general situation has been reviewed by Anderson[2] and Johnson[3] and the ferromanganese and spiegeleisen situation by Cone[4] and Stone.[5] Thus far the Survey has obtained more or less incomplete statistics of production and value for the alloys of iron with manganese, silicon, phosphorus, tungsten, molybdenum, chromium, vanadium, titanium, uranium, and cerium, but there are small quantities of alloys with many other metals, and elements, among which might be mentioned aluminum, boron, cobalt, nickel, tantalum, zinc, and zirconium, upon which no data have been obtained.

SHIPMENTS AND VALUE.

The quantity of ferroalloys of all classes reported as shipped or used and which the Survey is at liberty to publish amounted to only about 1.64 per cent of the total marketed production of pig iron during 1917, but the value per ton is so much greater as to have an important influence on the apparent average value of the pig iron, if included with it, and would make it $28.98 a ton, instead of $27.29. The quantity reported falls short of the actual production of the United States, as the output of certain electrically produced ferroalloys is not available for publication by the Geological Survey.

There is a sufficient number of producers of the commoner ferroalloys, such as ferromanganese, spiegeleisen, and ferrosilicon, to enable the Survey to publish the reported production of these three types of alloys separately; but the production of the rarer alloys, among which are ferrochrome, ferromolybdenum, ferrovanadium, and ferrouranium, must be grouped together, and as there are less than three reporting producers of ferrophosphorus the value of this alloy is grouped with that of ferrosilicon, although permission to show quantity was given for 1916.

The shipments of ferroalloys of all classes in 1917, as reported to the United States Geological Survey, were 634,021 gross tons, valued at $83,731,724, as compared with 589,738 gross tons, valued at $50,281,692, in 1916, an increase in quantity of 44,283 tons, or 7.5 per cent, and in value of $33,450,032, or 66.5 per cent, in 1917. Of the shipments in 1917, it is calculated that 267,667 gross tons, valued at $56,186,626, were made from imported ores derived from Bolivia, Brazil, China, Costa Rica, Cuba, India, Japan, Mexico, Nova Scotia, Panama, Peru, Porto Rico, and Quebec. The ferrovanadium, ferromolybdenum, ferromanganese, spiegeleisen, ferrotungsten, and ferrocarbontitanium were made in part or wholly from imported ore.

The sales of ferromanganese and spiegeleisen of domestic manufacture in 1917 amounted to 449,466 gross tons, valued at $63,687,007, compared with 406,940 gross tons, valued at $36,281,695, sold

[1] Notes on ores used in manganese ferroalloys are given also in the chapter on the production of manganese and manganiferous ores in Mineral Resources for 1917, and notes on ores for certain other ferroalloys in the chapters on chrome ore and ores of other rare metals.

[2] Anderson, R. J., Metallurgical ferroalloys in 1917: Eng. and Min. Jour., Jan. 26, 1918, pp. 191–193.

[3] Johnson, J. E., jr., Phases of iron and steel metallurgy in 1917: Iron Age, Jan. 3, 1918, pp. 77–82, and 128.

[4] Cone, E. F., Spiegeleisen in place of ferromanganese: Iron Age, Jan. 3, 1918, pp. 40–41, and 129.

[5] Stone, G. C., Ferromanganese and spiegeleisen: Idem, Jan. 12, 1918, pp. 75–76.

Digitized by Google

in 1916. The figures for ferromanganese and spiegeleisen, which may be shown separately for the last two years, are as follows: For 1917 ferromanganese 260,225 gross tons, valued at $53,930,771, or an average of $207.25 a ton; spiegeleisen, 189,241 gross tons, valued at $9,756,236, or an average of $51.55 a ton; for 1916, ferromanganese, 224,103 gross tons, valued at $30,123,493, or an average of $134.42 a ton; spiegeleisen, 182,837 gross tons, valued at $6,158,202, or $33.68 a ton. The continued increases in value are noteworthy. The sales of ferrosilicon and ferrophosphorus in 1917 amounted to 175,079 gross tons, valued at $8,562,182 an average value of $48.90 a ton, compared with 179,274 tons, valued at $5,273,088, or $29.41 a ton, in 1916. The sales of alloys of iron with the rarer metals—chromium, cerium, molybdenum, tungsten, titanium, uranium, and vanadium—as reported to the Survey, amounted in 1917 to 9,476 gross tons, valued at $11,482,535, compared with 3,524 gross tons, valued at $8,726,909, in 1916, an increase in quantity of 5,952 tons and in value of $2,755,626. These alloys were therefore valued at an average price of nearly $1,212 a ton in 1917, compared with $2,476 a ton in 1916. Ferrotungsten shipments in 1917 were 1,258 gross tons, valued at $4,225,070, or an average of $3,359 a ton.[1]

The following table gives an incomplete outline of the sales of ferroalloys in the United States in 1915, 1916, and 1917:

Ferroalloys of domestic manufacture shipped in 1915, 1916, and 1917.

Variety of alloy.	1915		1916		1917	
	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.
Ferromanganese	144,260	$9,253,443	224,103	$30,123,493	260,225	$53,930,771
Spiegeleisen	114,556	2,403,550	182,837	6,158,202	189,241	9,756,236
Ferrosilicon	128,263	2,595,265	166,308	5,273,088	175,079	8,562,182
Ferrophosphorus			12,966			
Ferrotungsten (50 per cent or more tungsten)	(a)	(a)	(a)	(a)	1,258	4,225,070
Other varieties[b]	1,565	3,198,127	3,524	8,726,909	8,218	7,257,465
	388,644	17,450,385	589,738	50,281,692	634,021	83,731,724

[a] Included with "Other varieties."
[b] 1915: Ferromolybdenum, ferrotungsten, and ferrovanadium; 1916: Ferrochrome, ferromolybdenum, ferrotungsten, and ferrovanadium; 1917: Ferrocerium, ferrochrome, ferromolybdenum, ferrocarbontitanium, ferrouranium, and ferrovanadium.

In 1917 ferromanganese was reported to have been made at 23 localities in the United States, spiegeleisen at 18 places, ferrosilicon at 17 places, ferrophosphorus at 1 place, ferrocerium at 1 place, ferrochrome at 4 places, ferromolybdenum at 3 places, ferrocarbontitanium at 1 place, ferrotungsten at 8 places, ferrouranium at 1 place, and ferrovanadium at 4 places.

The following table shows the number of localities by States at which the principal ferroalloys were manufactured in 1916 and 1917, but these operations do not include all those at which ferroalloys

[1] Quotations of market prices of ferroalloys and of the ores of the rare metals entering into the same may be found in current issues of Metallurgical and Chemical Engineering.

Digitized by Google

are manufactured electrically. In all there were reported 81 localities at which ferroalloys were made in 1917; compared with 46 localities in 1916.

Number of places, by States, at which ferroalloys were manufactured in 1916 and 1917.

State and alloy.	1916	1917	State and alloy.	1916	1917
Alabama:			New York:		
Ferromanganese	2	3	Ferromanganese	0	1
Spiegeleisen	2	3	Ferrosilicon	1	5
California:			Ferrocarbontitanium	0	1
Ferromanganese	1	1	Ferrotungsten	0	1
Ferrosilicon	0	1	Ohio:		
Ferrochrome	1	1	Ferrosilicon	4	4
Ferromolybdenum	0	1	Oregon:		
Ferrotungsten	0	1	Ferromanganese	0	1
Colorado:			Pennsylvania:		
Spiegeleisen	1	1	Ferromanganese	8	9
Ferrosilicon	0	1	Spiegeleisen	7	9
Ferrochrome	0	1	Ferrosilicon	1	1
Ferromolybdenum	0	1	Ferrocerium	0	1
Ferrotungsten	0	2	Ferrochrome	0	1
Illinois:			Ferromolybdenum	1	1
Ferromanganese	2	2	Ferrotungsten	3	3
Spiegeleisen	1	2	Ferrouranium	0	1
Ferrosilicon	1	0	Ferrovanadium	3	4
Iowa:			Tennessee:		
Ferrosilicon	1	1	Ferrosilicon	0	2
Kentucky:			Ferrophosphorus	2	1
Ferrosilicon	1	1	Virginia:		
Maryland:			Ferromanganese	0	2
Ferromanganese	1	1	Spiegeleisen	0	3
Ferrosilicon	1	1	Washington:		
Ferrotungsten	0	1	Ferromanganese	0	2
Spiegeleisen	1	0	Ferrochrome	0	1
New Jersey:				46	81
Ferromanganese	0	1			

The following records of average contract prices of 80 per cent ferromanganese at eastern seaboard and 20 per cent spiegeleisen by months for the last three years are of interest:

Prices per ton of ferromanganese and spiegeleisen, 1915, 1916, and 1917.

Month.	Ferromanganese.			Spiegeleisen.		
	1915[a]	1916[a]	1917[b]	1915[a]	1916[a]	1917[b]
January	$68.00	$110.00	$175.00	$26.00	$32.50	$57.50
February	100.00	140.00	192.50	25.50	42.50	66.25
March	100.00	175.00	212.50	26.00	55.00	77.50
April	100.00	175.00	250.00	26.00	60.00	76.75
May	100.00	175.00	375.00	26.00	60.00	78.00
June	105.00	175.00	400.00	26.00	55.00	83.00
July	103.00	175.00	400.00	26.00	47.50	85.00
August	105.00	170.00	387.50	26.00	47.50	81.25
September	110.00	164.00	380.00	29.00	45.00	80.50
October	105.00	160.00	300.00	30.00	40.00	73.50
November	100.00	155.00	247.50	30.00	45.00	63.25
December	100.00	162.50	250.00	30.00	50.00	60.30

[a] Iron Trade Review, Jan. 4, 1917, p. 25. [b] Idem, Jan. 3, 1918, p. 25.

IMPORTS.

According to the reports of the Bureau of Foreign and Domestic Commerce, the imports for consumption of all classes of ferroalloys into the United States in 1917 were 55,763 gross tons, valued at $6,703,330, compared with 97,816 tons, valued at $9,792,747, in

Digitized by Google

1916. The imports of ferromanganese were 41,969 gross tons, valued at $5,710,988, or $136.08 a ton, as compared with 90,928 gross tons, valued at $9,240,528, or $101.62 a ton, in 1916. The imports of spiegeleisen in 1917 amounted to 3,968 gross tons, valued at $291,594, or $73.48 a ton, as contrasted with no imports of this alloy in 1916. The imports of the alloys of the rarer metals are not all reported separately. For instance, the imports of ferrochrome are combined with those of chromium, those of ferromolybdenum are combined with those of the metal molybdenum, and those of ferrotungsten are included with those of tungsten. For the sake of comparison, however, such statistics as are available are presented in the following two tables:

Ferroalloys imported for consumption in the United States in 1915, 1916, and 1917.

Variety of alloy.	1915		1916		1917	
	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.
Chrome or chromium and ferrochrome	32	$1,662	10	$1,998		
Ferrophosphorus	12	617			85	$5,458
Ferrosilicon	5,128	311,219	6,740	384,384	9,740	691,684
Molybdenum and ferromolybdenum		203				
Titanium and ferrotitanium			100	8,126		
Tungsten and ferrotungsten	7	9,588	38	157,711	1	3,606
Ferromanganese	55,263	3,333,699	90,928	9,240,528	41,969	5,710,988
Spiegeleisen	200	5,110			3,968	291,594
	60,642	3,662,098	97,816	9,792,747	55,763	6,703,330

Ferromanganese and ferrosilicon imported into the United States in 1915, 1916, and 1917.

[General imports.]

Country.	Alloy.	1915		1916		1917	
		Quantity (gross tons).	Value.	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.
British India	Ferromanganese			[a] 1,313	$190,649		
Canada	Ferrosilicon	4,887	$274,059	6,691	379,133	9,729	$689,902
England	Ferromanganese			[a] 41,832	4,626,509	46,059	6,054,188
	Ferrosilicon	319	33,165	49	5,251		
Scotland	Ferromanganese					250	38,932
France	Ferrosilicon	20	2,906				
Japan	Ferromanganese					72	14,259
	Ferrosilicon					11	1,782

[a] Included in "All other pig iron" prior to July, 1916.

PRODUCTION OF STEEL, BY STATES AND KINDS.

The following tables showing the production of steel were compiled by the bureau of statistics of the American Iron and Steel Institute. No data whatever are available on the value of the steel output.

Digitized by Google

Bessemer steel ingots and castings manufactured in the United States, 1913–1917, in gross tons.

State.	1913	1914	1915	1916	1917
Ohio	4,024,662	2,862,700	3,929,665	4,711,784	4,256,337
Pennsylvania	2,954,818	2,014,526	2,507,243	3,444,163	3,537,094
Illinois	1,475,274	871,110	1,270,502	1,958,259	1,683,960
Other States	1,090,952	472,510	579,803	944,833	1,002,569
	9,545,706	6,220,846	8,287,213	11,059,039	10,479,960

Open-hearth steel ingots and castings manufactured in the United States, 1913–1917, in gross tons.

State.	1913	1914	1915	1916	1917
New England States	195,419	137,962	191,582	278,768	332,597
New York and New Jersey	996,312	719,227	1,266,017	1,872,258	2,110,846
Pennsylvania	12,522,227	9,854,038	13,245,393	16,030,251	16,284,102
Ohio	2,726,219	2,592,778	3,521,404	5,057,751	6,074,857
Indiana	2,180,106	1,628,840	2,504,427	3,243,961	3,722,931
Illinois	1,264,854	896,610	1,169,657	1,812,169	1,966,296
Other States	1,714,794	1,345,229	1,780,622	3,120,269	3,657,264
	21,599,931	17,174,684	23,679,102	31,415,427	34,148,893

According to these tables there was a decrease of 5 per cent in the production of Bessemer steel in 1917 compared with that of 1916, and an increase of 9 per cent in open-hearth steel. In the total production of steel in 1917 there was an increase of 5 per cent compared with 1916. Of the total output in 1917, 76 per cent was represented by open-hearth steel, 23 per cent by Bessemer steel, and less than 1 per cent by all other classes of steel.

PRODUCTION OF ELECTRIC STEEL.

The production of steel by the electric process in 1917 amounted to 304,543 gross tons, as compared with 168,918 tons in 1916, an increase of 135,625 tons, or more than 80 per cent. The following table gives the production of electric steel ingots and castings since 1909. In 1908 there were 55 tons of electric steel produced, but this quantity was included with open-hearth steel for that year.

Steel electrically manufactured in the United States, 1909 to 1917, in gross tons.

Year.	Ingots.	Castings.	Total.
1909	13,456	306	13,762
1910	50,821	1,320	52,141
1911	27,227	1,878	29,105
1912	14,147	4,162	18,309
1913	20,973	9,207	30,180
1914	15,458	8,551	24,009
1915	46,348	23,064	69,412
1916	126,048	42,870	168,918
1917	239,632	64,911	304,543

In the total production of electric steel in 1915 are included 27,944 tons of steel ingots and castings which were treated with ferrovanadium, ferrotitanium, ferrochrome, and other alloys, of which 27,848

Digitized by Google

tons were ingots and 96 tons were castings. In 1916 the production of similarly treated steel amounted to about 71,129 tons—70,203 tons of ingots and 926 tons of castings—and in 1917 it amounted to 130,578 tons—129,282 tons of ingots and 1,296 tons of castings.

On December 31, 1917, the number of completed plants which were equipped for the manufacture of steel by the electric process was 89, as compared with 57 plants at the close of 1916, a gain of 32 plants. The statistics of electric steel have been furnished by the American Iron and Steel Institute.

TOTAL DOMESTIC PRODUCTION OF STEEL.

Steel produced in the United States, 1810–1917, in gross tons.

Year.	Bessemer.	Open-hearth.	Crucible.	Other Steel.	Total.
1810	.....	.....	917		917
1860	.....	.....	11,838		11,838
1863	.....	.....	8,075		8,075
1864	.....	.....	9,258		9,258
1865	.....	.....	13,627		13,627
1866	.....	.....	16,940		16,940
1867	2,679	.....	16,964		19,643
1868	7,589	.....	19,197		26,786
1869	10,714	893	19,643		31,250
1870	37,500	1,339	29,911		68,750
1871	40,179	1,785	31,250		73,214
1872	107,239	2,679	26,125	6,911	142,954
1873	152,308	3,125	31,059	12,244	198,796
1874	171,309	6,250	32,436	5,672	215,727
1875	335,283	8,080	35,180	11,256	389,799
1876	469,639	19,187	35,163	9,202	533,191
1877	500,524	22,349	36,098	10,647	569,618
1878	653,773	32,255	38,309	7,640	731,977
1879	829,439	50,259	50,696	4,879	935,273
1880	1,074,202	100,851	64,664	7,558	1,247,335
1881	1,374,247	131,202	80,145	2,720	1,588,314
1882	1,514,687	143,341	75,973	2,691	1,736,692
1883	1,477,345	119,356	71,835	4,999	1,673,535
1884	1,375,531	117,515	53,270	4,563	1,550,879
1885	1,519,430	133,376	57,599	1,515	1,711,920
1886	2,269,190	218,973	71,973	2,367	2,562,503
1887	2,986,033	322,069	75,375	5,594	3,339,071
1888	2,511,161	314,318	70,279	3,682	2,899,440
1889	2,930,204	374,543	75,865	5,120	3,385,732
1890	3,688,871	513,232	71,175	3,793	4,277,071
1891	3,247,417	579,753	72,586	4,484	3,904,240
1892	4,168,435	669,889	84,700	4,548	4,927,581
1893	3,215,686	737,890	63,613	2,806	4,019,995
1894	3,571,313	784,936	51,702	4,081	4,412,032
1895	4,909,128	1,137,182	67,666	858	6,114,834
1896	3,919,906	1,298,700	60,689	2,394	5,281,689
1897	5,475,315	1,608,671	69,959	3,012	7,156,957
1898	6,609,017	2,230,292	89,747	3,801	8,932,857
1899	7,586,354	2,947,316	101,213	4,974	10,639,857
1900	6,684,770	3,398,135	100,562	4,862	10,188,329
1901	8,713,302	4,656,309	98,513	5,471	13,473,595
1902	9,138,303	5,687,729	112,772	8,386	14,947,250
1903	8,592,829	5,829,911	102,434	9,804	14,534,978
1904	7,859,140	5,908,166	83,391	9,190	13,859,887
1905	10,941,375	8,971,376	102,233	8,963	20,023,947
1906	12,275,830	10,980,413	127,513	14,380	23,398,136
1907	11,667,549	11,549,736	131,234	14,075	23,362,594
1908	6,116,755	7,836,729	63,631	6,132	14,023,247
1909	9,330,783	14,493,936	107,355	22,947	23,955,021
1910	9,412,772	16,504,509	122,303	55,335	26,094,919
1911	7,947,854	15,598,650	97,653	31,949	23,676,106
1912	10,327,901	20,780,723	121,517	21,162	31,251,303
1913	9,545,706	21,599,931	121,226	34,011	31,300,874
1914	6,220,846	17,174,681	89,869	27,631	23,513,030
1915	8,287,213	23,679,102	113,782	70,939	32,151,036
1916	11,059,039	31,415,427	129,692	169,522	42,773,680
1917	10,479,960	34,148,893	126,716	305,038	45,060,607

Digitized by Google

FOREIGN TRADE IN STEEL.

The extraordinary development of the export trade in steel in the United States since the beginning of the war in Europe is indicated in the table of exports which shows, by classes, the exports of manufactured iron and steel from this country in 1915, 1916, and 1917. For comparison the imports are tabulated also. The figures were compiled from records of the Bureau of Foreign and Domestic Commerce.

In 1915, 1916, and 1917 the quantity of iron and steel exports (so far as recorded) increased 149 per cent, 66 per cent and 5 per cent, respectively, but the total values increased 133 per cent, 136 per cent, and 57 per cent, respectively.

Iron and steel imported into the United States, 1915, 1916, and 1917.

Article.	1915		1916		1917	
	Quantity (gross tons.)	Value.	Quantity (gross tons.)	Value.	Quantity (gross tons.)	Value.
Scrap iron and steel	79,982	$761,719	116,039	$1,140,704	180,034	$2,437,423
Bar iron	8,474	417,491	7,701	647,393	2,240	193,831
Ingots, blooms, slabs, etc., not elsewhere specified	4,412	187,623	11,487	430,323	35,861	1,635,323
Ingots, blooms, and slabs, billets and bars of steel, and steel in forms, not elsewhere specified	10,586	1,753,978	17,792	2,809,319	8,337	2,313,613
Hoop or band iron or steel for baling	.....	28	.....	.....	.....	.....
Rails for railway	78,525	2,088,532	26,299	740,109	9,263	307,139
Sheets and plates	1,420	218,954	1,938	345,622	1,747	526,788
Tin and terne plates	2,350	196,328	1,129	214,574	124	31,453
Wire rods	5,317	331,724	4,625	509,559	1,060	221,184
	191,066	5,956,377	187,010	6,837,603	238,666	7,666,754
Wire and articles made from wire	.....	640,521	.....	652,889	.....	348,876
All other manufactures—free	.....	200,763	.....	105,896	.....	82,993
All other manufactures—dutiable	.....	2,324,447	.....	3,503,219	.....	4,072,935
	.....	3,165,731	.....	4,261,004	.....	4,504,804
Grand total	.....	9,122,108	.....	11,098,607	.....	12,171,558

Digitized by Google

Iron and steel exported from the United States, 1915, 1916, and 1917.

Article.	1915		1916		1917	
	Quantity (gross tons.)	Value.	Quantity (gross tons.)	Value.	Quantity (gross tons.)	Value.
Scrap and old, fit only for manufacture	79,361	$1,111,254	212,765	$3,689,675	145,574	$3,362,562
Bar iron	39,740	1,471,466	74,069	3,913,849	56,332	5,046,727
Bars or rods (of steel), wire rods	165,015	4,713,109	158,284	8,109,111	181,941	15,356,275
All other	425,678	16,412,440	774,455	47,670,408	626,465	59,708,761
Billets, ingots, and blooms, not elsewhere specified	560,704	14,176,528	1,504,562	90,095,601	2,017,113	161,391,007
Bolts and nuts	23,536	1,806,842	29,227	3,132,897	32,261	5,259,622
Hoop and bands	29,249	1,433,879	43,208	3,251,882	58,769	7,330,301
Horseshoes	15,863	2,741,724	7,806	1,007,198	8,403	1,594,962
Cut nails	4,236	190,667	4,752	312,195	4,525	434,726
Railroad spikes	13,256	591,752	22,852	1,489,091	21,188	2,009,808
Wire nails	91,564	4,371,072	150,173	10,794,418	114,912	12,068,147
All other (including tacks)	9,251	1,065,416	12,353	1,637,051	19,351	3,867,605
Cast-iron pipes and fittings	47,022	2,128,025	70,223	3,988,293	77,528	7,483,216
Wrought-iron pipes and fittings	129,966	8,081,416	158,350	13,195,696	127,191	16,659,553
Radiators and cast-iron house-heating boilers	2,291	183,523	2,424	232,845	5,201	672,331
Rails for railways, of steel	391,379	12,095,170	540,828	20,417,582	512,669	24,023,090
Galvanized iron and steel plates	75,905	5,381,303	85,304	8,350,005	86,487	13,207,827
Iron sheets and plates, all other	25,543	1,221,699	46,499	3,136,262	62,238	7,540,780
Steel plates	223,806	8,037,551	276,084	16,499,757	525,660	65,888,695
Steel sheets	94,349	3,726,933	107,721	6,546,814	157,354	18,654,553
Structural iron and steel	232,139	8,960,411	300,594	17,541,862	294,150	24,437,289
Tin and terne plates	154,641	11,501,995	227,391	21,352,177	232,797	41,883,415
Barbed wire	248,611	13,933,234	418,882	31,230,905	193,471	19,775,784
All other wire	224,972	11,900,373	264,142	20,994,035	201,472	22,541,224
	3,308,097	137,347,782	5,493,898	338,589,607	5,763,052	540,218,263
Axes	.....	588,443	.....	722,520	.....	1,023,184
Hammers and hatchets	.....	509,824	.....	366,161	.....	568,892
Railway-track material, switches, frogs, fishplates, splices, bars, etc	.....	4,857,047	.....	6,540,187	.....	8,194,270
Saws	.....	1,294,447	.....	2,923,055	.....	5,113,514
Shovels and spades	.....	352,727	.....	666,407	.....	509,559
All other tools	.....	8,676,483	.....	12,716,778	.....	14,696,939
	.....	16,278,971	.....	23,935,108	.....	29,506,358
Grand total	.....	153,626,753	.....	362,524,715	.....	569,724,621

Digitized by Google

Digitized by Google

GOLD AND SILVER.

(GENERAL REPORT.)

By H. D. McCaskey and J. P. Dunlop.

ACKNOWLEDGMENTS.

To those engaged in the mining and metallurgic industries, to merchants, bankers, and transportation officials of the United States and Alaska, to the Bureau of the Mint, the Post Office Department, and the Bureau of Foreign and Domestic Commerce of the Department of Commerce, and to other officials, public and private, who have cooperated with the United States Geological Survey by furnishing information on the production of gold and silver, acknowledgment is gratefully made. To the authors of the Survey mines reports on the production of gold, silver, copper, lead, and zinc in the Eastern, Central, and Western States, and in Alaska, Messrs. B. S. Butler, C. N. Gerry, V. C. Heikes, Charles W. Henderson, James M. Hill, G. C. Martin, and Charles G. Yale, the writers are especially indebted.

PRODUCTION.

DOMESTIC PRODUCTION.

Approximate distribution, by producing States and Territories, of the production of gold and silver in the United States for 1917.[a]

State or Territory.	Gold.		Silver.	
	Quantity (fine ounces).	Value.	Quantity (fine ounces).	Commercial value.
Alabama	106	$2,200		
Alaska	709,729	14,671,400	1,207,164	$994,100
Arizona	250,613	5,180,600	6,962,257	5,733,400
California	1,012,461	20,929,400	2,107,107	1,735,200
Colorado	772,766	15,974,500	7,291,495	6,004,500
Georgia	314	6,500		
Idaho	36.511	754,800	11,402,542	9,390,080
Illinois			7,116	5,900
Maryland			538	400
Michigan			684,225	563,400
Missouri	15	300	63,344	52,200
Montana	177,690	3,673,200	14,555,034	11,986,100
Nevada	335,361	6,932,500	11,217,654	9,237,700
New Mexico	52,505	1,085,400	1,535,807	1,264,700
North Carolina	524	10,800	590	500
Oregon	81,624	1,687,300	172,152	141,800
Philippine Islands	69,953	1,446,100	12,715	10,500
Porto Rico	5	100		
South Carolina	82	1,700		
South Dakota	356,662	7,372,900	190,382	156,800
Tennessee	267	5,500	106,975	88,100
Texas	5	100	587,945	484,200
Utah	170,383	3,522,100	13,360,905	11,002,700
Vermont	5	100	403	300
Virginia	63	1,300	4,500	3,700
Washington	23,617	488,200	266,112	219,100
Wyoming	179	3,700	3,400	2,800
	4,051,440	83,750,700	71,740,362	59,078,100

[a] Gold value $20.67+ per fine ounce. Average commercial (dealers') buying price of silver 0.999 fine in 1917, 82.4 cents per fine ounce.

Digitized by Google

The figures in this table result from cooperation of the United States Bureau of the Mint and the United States Geological Survey and are agreed upon after conference and adjustment between the two bureaus. They are, therefore, final for both.

The totals are based on bullion deposits in the United States mints and assay offices and on returns to the Bureau of the Mint from the smelting and refining companies. The distribution is adjusted by information collected by the United States Geological Survey directly from the producing mines and tabulated for the mines reports later discussed. The data giving the total production, and in part the distribution, are obtained from records of (1) the unrefined domestic gold and silver deposited in United States mints and assay offices, (2) the domestic gold and silver in fine bars reported by private refineries, and (3) the unrefined domestic gold and silver contained in ores and matte exported for reduction. The last item is of small relative importance.

Increase or decrease in production of gold and silver in the United States in 1917.

State or Territory.	Gold.		Silver.	
	Quantity (fine ounces).	Value.	Quantity (fine ounces).	Commercial value.
Alabama	− 252	− $5,200		
Alaska	− 70,308	−1,453,400	− 59,153	+ $161,100
Arizona	+ 52,624	+1,087,800	+ 282,005	+ 1,338,800
California	− 50,841	−1,051,000	+ 170,197	+ 461,000
Colorado	−155,309	−3,210,500	− 260,266	+ 1,038,600
Georgia	− 673	− 13,900		
Idaho	− 14,684	− 303,500	− 167,857	+ 1,778,500
Illinois			+ 1,334	+ 2,100
Maryland			+ 335	+ 300
Michigan			− 74,843	+ 64,100
Missouri	+ 15	+ 300	− 65,516	− 32,600
Montana	− 31,696	− 655,200	+ 508,980	+ 2,746,000
New Hampshire			− 935	− 600
Nevada	−103,144	−2,132,200	−2,464,413	+ 237,100
New Mexico	− 12,301	− 264,600	− 194,110	+ 126,700
North Carolina	− 589	− 12,200	− 1,143	− 600
Oklahoma			− 606	− 400
Oregon	− 10,361	− 214,200	− 49,735	− 4,200
Philippine Islands	− 3,296	− 68,100	− 4,928	− 1,100
Porto Rico	− 24	− 500		
South Carolina	+ 67	+ 1,400		
South Dakota	− 4,782	− 98,800	− 19,718	+ 18,600
Tennessee	− 9	− 200	+ 13,138	+ 26,400
Texas	− 19	− 400	− 76,374	+ 47,200
Utah	− 16,296	− 336,900	− 184,807	+ 2,091,700
Vermont	− 9	− 200	− 1,561	− 1,000
Virginia	+ 39	+ 800	+ 3,992	+ 3,400
Washington	− 4,470	− 92,400	− 28,404	+ 25,400
Wyoming	− 798	− 16,500	− 7	+ 600
Increase or decrease	−427,616	−8,839,600	−2,674,440	+10,125,100

In addition to the production of gold and silver by domestic smelters and refiners from domestic sources in 1917, amounting to 4,051,440 fine ounces of gold and 71,740,362 fine ounces of silver, these plants produced 769,171 fine ounces of gold and 50,106,811 fine ounces of silver from foreign ores. These figures represent a decrease of 31,634 ounces of gold and an increase of 3,855,794 ounces of silver compared with the corresponding figures for 1916. The foreign ores producing this bullion were mainly from Mexico and Canada.

The value of the new gold used in the arts and industries in the United States in 1917 was $34,803,445, and the quantity of silver used for such purposes in 1917 was 15,998,807 fine ounces.

Digitized by Google

PRICES OF SILVER.

The average official monthly prices of fine bar silver in New York in 1917 were as follows:

Price of silver per fine ounce in 1917, by months.[1]

January	$0.7598	August	$0.86125
February	.7771	September	1.05026
March	.74023	October	.87692
April	.7400	November	.86672
May	.74875	December	.88015
June	.77447		
July	.80845	Yearly average	.8235

The average annual price of silver per fine ounce from 1865 to 1917, inclusive, has been as follows:

Price of silver per fine ounce, 1865–1917.[2]

1865	$1.337	1883	$1.11	1901	$0.60
1866	1.339	1884	1.11	1902	.53
1867	1.33	1885	1.07	1903	.54
1868	1.326	1886	.99	1904	.58
1869	1.325	1887	.98	1905	.61
1870	1.328	1888	.94	1906	.68
1871	1.325	1889	.94	1907	.66
1872	1.322	1890	1.05	1908	.53
1873	1.297	1891	.99	1909	.52
1874	1.278	1892	.87	1910	.54
1875	1.24	1893	.78	1911	.53
1876	1.16	1894	.63	1912	.615
1877	1.20	1895	.65	1913	.604
1878	1.15	1896	.68	1914	.553
1879	1.12	1897	.60	1915	.519
1880	1.15	1898	.59	1916	.658
1881	1.13	1899	.60	1917	.824
1882	1.14	1900	.62		

PRODUCTION OF GOLD AND SILVER SINCE 1792.

According to tables published by the Director of the Mint the total production of gold and silver in the United States is as follows:

Gold and silver produced in the United States, 1792–1917.

[The estimate for 1792–1872 is by R. W. Raymond, commissioner, and for the period since 1872 by the Director of the Mint.]

Period.	Gold.		Silver.	
	Quantity (fine ounces).	Value.	Quantity (fine ounces).	Commercial value.
1792–1847	1,187,170	$24,537,000	309,500	$404,500
1848–1872	58,279,778	1,204,750,000	118,568,200	157,749,900
1873–1917	129,810,577	2,683,420,900	2,260,659,739	1,736,859,300
	189,277,525	3,912,707,900	2,379,537,439	1,895,013,700

[1] This represents average official quotations for sale by the Mint and is above dealers' prices for silver 0.999 fine.

[2] Based on London price of bar silver 1.000 fine and taken at average price and par of exchange.

Digitized by Google

These figures show a total production of gold for the United States, from the earliest mining to the end of 1917, of 189,277,525 ounces, valued at nearly $3,913,000,000, and an output of silver of nearly 2,380,000,000 ounces, valued at more than $1,895,000,000. Although the production of gold was less than one-twelfth the output of silver in quantity, its value was more than twice that of the silver.

The average commercial value per fine ounce of silver for the 125 years contributing to the total domestic production was a little less than $0.80. Fluctuations in value of silver per fine ounce are shown in the curve on figure 10. It is of interest to note that the average value for the total output of silver was reached in 1893. For the years shown (1871 to 1917, inclusive) the average annual value was above $0.80 before 1893, and has been below that figure every year since until 1917, when the average value was $0.8235, or 2.35 cents more than the average value 1871–1916.

Gold and silver produced in the United States, 1880–1917.

Year.	Gold.		Silver.	
	Quantity (fine ounces).	Value.	Quantity (fine ounces).	Commercial value.
1880	1,741,500	$36,000,000	30,318,700	$34,717,000
1881	1,678,612	34,700,000	33,257,900	37,657,500
1882	1,572,157	32,500,000	36,196,900	41,105,900
1883	1,451,250	30,000,000	35,732,900	39,618,400
1884	1,489,050	30,800,000	37,743,900	41,921,300
1885	1,538,373	31,801,000	39,909,400	42,503,500
1886	1,686,788	34,869,000	39,684,000	39,482,400
1887	1,603,049	33,136,000	41,721,900	40,887,200
1888	1,604,478	33,167,500	45,792,700	43,045,100
1889	1,594,775	32,967,000	50,094,500	46,838,400
1890	1,588,877	32,845,000	54,516,300	57,242,100
1891	1,604,840	33,175,000	58,330,000	57,630,000
1892	1,597,698	33,015,000	63,500,000	55,662,500
1893	1,739,323	35,955,000	60,000,000	46,800,000
1894	1,910,813	39,500,000	49,500,000	31,422,100
1895	2,254,760	46,610,000	55,727,000	36,445,500
1896	2,568,132	53,088,000	58,834,300	39,654,600
1897	2,774,935	57,363,000	53,860,000	32,316,000
1898	3,118,398	64,463,000	54,438,000	32,118,400
1899	3,437,210	71,053,400	54,764,500	32,858,700
1900	3,829,897	79,171,000	57,647,000	35,741,100
1901	3,805,500	78,666,700	55,214,000	33,128,400
1902	3,870,000	80,000,000	55,500,000	29,415,000
1903	3,560,000	73,591,700	54,300,000	29,322,000
1904	3,892,480	80,464,700	57,682,900	33,456,000
1905	4,265,742	88,180,700	56,101,900	34,222,000
1906	4,565,333	94,373,800	56,517,900	38,256,400
1907	4,374,827	90,435,700	56,514,700	37,299,700
1908	4,574,340	94,560,000	52,440,900	28,050,600
1909	4,821,701	99,673,400	54,721,900	28,455,200
1910	4,657,018	96,269,100	57,137,900	30,854,500
1911	4,687,053	96,890,000	60,399,400	32,615,700
1912	4,520,717	93,451,500	65,766,900	39,197,500
1913	4,299,783	88,884,400	66,801,500	40,348,100
1914	4,372,976	94,531,800	72,455,100	40,067,700
1915	4,887,602	101,035,700	74,961,075	37,397,300
1916	4,479,056	92,590,300	74,414,802	48,953,000
1917	4,051,440	83,750,700	71,740,362	59,078,100
	116,270,813	2,403,529,100	2,052,250,039	1,485,784,900

Digitized by Google



FIGURE 10.—Curves showing production and value of gold and silver and price per fine ounce of silver in the United States, 1871–1917.

Digitized by Google

IMPORTS AND EXPORTS.

Value of gold and silver imported and exported, 1917.

[Figures furnished by the Bureau of Foreign and Domestic Commerce, Department of Commerce.]

Metal.	Imports.	Exports.	Excess of—	
			Imports.	Exports.
GOLD.				
Contained in domestic ore and base bullion		$251,963		$251,963
Contained in foreign ore and base bullion	$15,508,581		$15,508,581	
Domestic bullion refined		90,212,645		90,212,645
Foreign bullion refined	401,687,827	31,470	401,656,357	
United States coin	62,312,573	274,036,206		211,723,633
Foreign coin	72,945,393	7,351,600	65,593,793	
	552,454,374	371,883,884	482,758,731	302,188,241
Excess			180,570,490	
SILVER.				
Contained in domestic ore and base bullion		167,326		167,326
Contained in foreign ore and base bullion	37,668,562		37,668,562	
Domestic bullion refined		76,555,369		76,555,369
Foreign bullion refined	9,497,753	3,214,819	6,282,934	
United States coin	1,162,009	1,003,379	158,630	
Foreign coin	5,012,153	3,189,983	1,822,170	
	53,340,477	84,130,876	45,932,296	76,722,695
Excess				30,790,399

DOMESTIC SUPPLY.

The remarkable gain in domestic supply of gold indicated by the great excess of $530,200,000 in imports over exports for 1916, or $76,000,000 more than the world's total output of new gold for the year, was due to the fact that this country has been a creditor nation since the last great movements of its gold abroad. This movement was much less conspicuous in 1917, though the excess of imports of gold in ore bullion and coin amounted to more than $180,000,000, due largely to the imports of foreign refined bullion. The continuation of large exports of silver to the Far East, and especially to the entente nations in Europe, was due largely to demand for exchange and for the coinage of silver money to pay troops in the field. The quantity of refined domestic silver bullion exported was more than double the silver contained in imported foreign ore and base bullion.

The domestic supply of new gold comes chiefly from dry or siliceous gold ores, treated in gold mills by amalgamation or cyanidation, or both, and from placer gravels largely by dredging. As shown on page 645 these ores and placer gravels supplied 25.8 per cent of the yield of gold in 1917. Examples of gold-milling ores are those of the Homestake mines of South Dakota, the Goldfield mines in Nevada, the Grass Valley and Mother Lode mines of California, the Alaska mines of the Juneau district, and the Cripple Creek and upper San Miguel County mines in Colorado. The great gold-dredging fields of California, especially of the Marysville district, are examples of the placer gravels worked on a large scale. A considerable output of gold is also now recovered from the refining of copper bullion from copper ores, especially of the West Mountain or Bingham district, Utah, the Robinson or Ely district, Nev., and the Summit Valley or Butte

Digitized by Google

district, Mont. In 1917 the copper ores of the United States produced more than 8.7 per cent of the total gold, against 9 per cent in 1916. The natural tendency is for the proportionate output from gold ores to decrease, with declining yield from some of the principal gold camps, and for that from copper ores to increase, with a general net falling off of total yield of gold owing to the preponderant output from gold and gold-silver ores.

The principal domestic supply of new silver comes from dry or siliceous silver and silver-gold ores, from copper ores, from lead ores, and from lead-zinc ores—in the proportion of 30.4, 28.8, 27, and 12.2 per cent, respectively, in 1917, against 31.2, 31.1, 24.4, and 10.9 per cent, respectively, in 1916. The dry or siliceous silver-gold ores have come chiefly from four large mines of the Tonopah district, Nev., and declining output from this camp more than offsets gains from such ores elsewhere. The bulk of the silver ores of this class are milled and cyanided at or near the mines, although a small quantity of richer ores is shipped to copper and lead smelters. The largest single producer of silver in 1917 from domestic mines was the Anaconda Copper Co., of Montana, producing from copper ores; the second largest was the Hercules Mining Co., of Idaho, producing from lead ores; and the third largest was the Tonopah Belmont Mining Co., of Nevada, producing from siliceous ores. Of the 25 mines or groups of mines producing silver on the largest scale, 8 were silver-gold and silver mines, 6 were copper mines, 10 were lead mines, and 1 was a zinc-lead mine. With large recent increase in output of argentiferous copper, lead, and zinc-lead ores, the domestic silver output has been fairly well maintained against decline from silver-gold and (the rare) silver ores. The silver obtained as a by-product from copper, lead, and zinc ores is derived from refining the copper and lead bullion produced in smelting those and other ores.

WORLD'S PRODUCTION OF GOLD.

Value of gold produced in the world, 1860–1917.

[The annual production from 1860 to 1872 is obtained from statistics for 5-year periods compiled by Dr. Adolph Soetbeer. Since 1872 the estimates are those of the Bureau of the Mint.]

Calendar year.	Value.	Calendar year.	Value.	Calendar year.	Value.	Calendar year.	Value.
1860.....	$134,083,000	1875.....	$97,500,000	1890.....	$118,848,700	1905.....	$380,288,700
1861.....	122,989,000	1876.....	103,700,000	1891.....	130,650,000	1906.....	402,503,000
1862.....	122,989,000	1877.....	113,947,200	1892.....	146,651,500	1907.....	412,966,600
1863.....	122,989,000	1878.....	119,092,800	1893.....	157,494,800	1908.....	442,476,900
1864.....	122,989,000	1879.....	108,778,800	1894.....	181,175,600	1909.....	454,059,100
1865.....	122,989,000	1880.....	106,436,800	1895.....	198,763,600	1910.....	455,239,100
1866.....	129,614,000	1881.....	103,023,100	1896.....	202,251,600	1911.....	461,939,700
1867.....	129,614,000	1882.....	101,996,600	1897.....	236,083,700	1912.....	466,136,100
1868.....	129,614,000	1883.....	95,392,000	1898.....	286,879,700	1913.....	460,497,204
1869.....	129,614,000	1884.....	101,729,600	1899.....	306,724,100	1914.....	439,029,702
1870.....	129,614,000	1885.....	108,435,600	1900.....	254,576,300	1915.....	468,724,918
1871.....	115,577,000	1886.....	106,163,900	1901.....	260,992,900	1916.....	454,176,500
1872.....	115,577,000	1887.....	105,774,900	1902.....	296,737,600	1917.....	423,590,200
1873.....	96,200,000	1888.....	110,196,900	1903.....	327,702,700		
1874.....	90,750,000	1889.....	123,489,200	1904.....	347,377,200		12,595,397,124

The peak of the world's production of gold was reached in 1915 (see Pl. IV), when most of the great gold fields were contributing maximum outputs. In 1916 declines in the United States, Russia (and Siberia), and Australasia more than offset an increase in Africa.

Digitized by Google

In 1917 the estimated total production of gold in the world decreased more than $30,000,000. The production of the United States decreased nearly $9,000,000, Canada $4,000,000, Africa $8,000,000, Australasia $4,500,000, and Russia $4,500,000.

The high-water mark of silver output was reached in 1911, when Mexico, Canada, and Australasia were all producing at or near the maximum. Increased output from the United States has not offset large falling off in the above-named countries, especially Mexico, in the last six years,

A valuable paper on "Gold and silver deposits in North and South America" was read by Waldemar Lindgren at the Second Pan American Scientific Congress and has been republished in the Transactions of the American Institute of Mining Engineers, volume 55, pages 883–909, 1917.

In the following table is shown the output of gold, by countries, as given by the Bureau of the Mint:

World's production of gold, 1904–1917.

Country.	1904	1905	1906	1907	1908	1909	1910
North America:							
United States	$80,464,700	$88,180,700	$94,373,800	$90,435,700	$94,560,000	$99,673,400	$96,269,100
Canada	16,462,500	14,610,400	12,023,900	8,382,800	9,482,100	9,382,200	10,205,900
Mexico	12,605,300	16,107,100	18,534,700	18,681,100	22,371,200	23,842,900	24,910,600
Africa	85,913,900	113,254,700	135,358,000	151,984,100	166,520,500	170,988,600	175,189,900
Australasia	87,767,300	85,926,500	82,391,400	75,677,700	73,327,300	71,007,900	65,470,600
Europe:							
Russia and Finland	24,808,200	22,292,200	19,496,500	26,684,300	28,052,200	32,381,300	35,579,600
Austria-Hungary	2,117,300	2,457,400	2,615,400	2,484,900	2,469,300	1,942,000	2,172,600
Germany	64,700	66,700	80,400	66,600	64,300	69,200	62,900
Norway							1,400
Sweden	40,200	36,700	13,300	18,700	14,500	10,100	2,000
Italy	44,000	44,000	41,200	39,600	46,500	24,200	29,600
Spain and Portugal						2,900	2,800
Turkey	29,000	6,000	6,000	4,500	2,200	500	500
France			502,400	835,400	1,147,400	1,400,600	1,707,100
Great Britain	359,800	112,700	29,200	29,200	16,000	21,500	39,600
Serbia			59,800	59,800	59,800	150,300	
South America:							
Argentina	9,200	5,500	5,500	103,000	161,300	189,900	173,100
Bolivia	21,900	18,800	754,600	1,267,400	346,300	492,400	463,600
Chile	636,900	948,500					
Colombia	1,947,400	2,584,000	2,190,800	3,255,600	3,427,300	3,179,900	3,370,000
Ecuador	132,900	188,500	294,200	267,100	350,300	274,400	249,200
Brazil	2,043,500	2,044,600	2,403,000	2,020,700	2,196,600	2,252,900	1,954,700
Venezuela	300,000	171,400	25,300	22,400	24,500	280,600	340,500
Guiana:							
British	1,608,800	1,690,700	1,607,700	1,304,400	1,408,100	1,192,700	1,192,700
Dutch	441,600	632,500	689,200	640,000	663,000	621,000	792,600
French	1,806,400	1,859,700	1,858,900	2,360,800	2,135,500	2,143,800	2,229,100
Peru	1,329,200	516,100	829,000	514,500	514,500	514,500	455,900
Uruguay	25,000	50,000	31,700	51,900	91,600	91,600	91,600
Central America	1,252,500	1,513,400	1,910,700	2,107,800	3,018,800	2,630,100	4,657,400
Asia:							
Japan	2,948,200	3,072,400	2,748,900	2,773,000	3,321,600	3,616,900	3,903,600
China	4,500,000	4,500,000	4,500,000	4,500,000	8,647,300	9,352,100	3,658,100
Indo-China				31,800	65,600	65,600	55,000
Chosen (Korea)	3,000,000	2,593,000	2,283,000	2,170,800	3,047,500	1,993,600	4,399,100
Siam	51,800	48,600	53,200	166,200	327,600	327,600	56,500
India, British	11,722,900	11,950,200	12,067,700	10,383,600	10,598,500	10,358,600	10,718,400
East Indies, British	1,485,300	1,391,000	1,448,700	1,561,300	1,400,900	1,436,900	1,446,800
East Indies, Dutch	1,414,500	1,414,500	1,254,900	2,079,900	2,596,300	2,146,400	3,387,100
	347,377,200	380,288,700	402,503,000	412,966,600	442,476,900	454,059,100	455,239,100

Digitized by Google



Digitized by Google

Digitized by Google

World's production of gold, 1904–1917—Continued.

Country.	1911	1912	1913	1914	1915	1916	1917
North America:							
United States	$96,890,000	$93,451,500	$88,884,400	$94,531,800	$101,035,700	$92,590,300	$83,750,700
Canada	9,762,100	12,648,800	16,598,900	15,983,004	18,977,901	19,235,000	15,200,000
Mexico	24,880,100	24,500,000	19,308,800	4,788,175	6,559,275	7,690,700	9,000,000
Cuba	20,000						
Africa	191,538,400	211,850,600	207,326,500	201,996,796	217,851,898	222,948,900	214,614,000
Australasia	60,184,200	54,509,400	53,113,200	47,569,023	48,988,177	40,475,800	35,945,500
Europe:							
Russia, Finland and Siberia	32,151,600	22,199,000	26,508,700	28,586,392	26,322,746	22,500,000	18,000,000
Austria-Hungary	2,185,100	2,048,200	2,179,300	200,744	1,392,465	1,000,000	1,000,000
Germany	78,100	78,100	135,600	.....	.....	.....	.....
Norway	.....	.....	.....	.....	.....	.....	.....
Sweden	2,000	20,300	17,600	54,304	25,323	12,200	10,000
Italy	44,800	11,000	17,200	32,145	2,295	2,000	2,000
Spain and Portugal	2,400	2,300	2,300	2,336	661	.....	.....
Turkey	500	500	500	475	475	.....	.....
France	1,812,100	1,812,100	2,127,400	1,400,000	1,400,000	1,000,000	700,000
Great Britain	39,600	27,800	17,900	20,238	19,266	5,700	5,000
Serbia	251,100	251,100	328,000	116,000	.....	.....	.....
South America:							
Argentina	$289,000	$107,300	$2,600	.....	.....	$15,300	$4,600
Bolivia and Chile	362,500	175,000	336,884	$202,770	$814,418	301,000	315,000
Colombia	3,167,800	2,971,700	2,971,700	4,678,587	5,453,148	6,173,900	6,200,000
Ecuador	276,800	406,500	406,500	346,853	545,674	560,000	710,000
Brazil	3,834,500	3,570,600	2,254,700	2,139,803	2,424,515	2,890,000	2,958,000
Venezuela	364,800	623,500	419,040	564,220	1,395,349	1,269,900	637,000
Guiana:							
British	892,000	879,800	1,353,500	1,126,500	923,892	660,700	600,000
Dutch	523,400	407,300	470,400	503,400	449,054	438,200	400,000
French	2,229,100	3,050,600	3,050,600	1,959,793	1,959,793	1,600,000	1,500,000
Peru	492,300	492,200	912,280	1,022,125	1,109,891	1,267,400	1,300,000
Uruguay	70,600	111,000	29,900	15,276	11,836	12,000	10,000
Central America	3,360,400	3,030,400	2,721,700	2,393,190	2,970,271	3,517,600	3,122,000
Asia:							
Japan	4,118,600	4,467,000	3,614,400	4,679,358	5,386,066	5,185,600	4,562,200
China	3,314,600	3,658,900	3,658,900	3,658,900	2,804,692	3,100,700	3,600,100
Indo-China	74,700	74,700	74,700	66,419	43,659	65,600	50,000
Chosen (Korea)	2,889,400	2,852,600	3,582,500	3,309,870	3,739,477	4,122,400	4,444,000
Siam	56,500	56,500	56,500	.....	.....	.....	.....
India, British	11,054,100	11,055,700	12,178,000	11,378,400	11,522,457	11,206,500	10,756,800
East Indies, British	1,339,400	1,352,000	1,352,000	4,480,853	3,100,000	3,000,000	2,818,000
East Indies, Dutch	3,387,100	3,387,100	3,387,100				
Federated Malay States	.....	.....	282,400	269,147	351,527	327,900	342,300
Formosa	.....	.....	814,600	952,806	1,143,017	1,001,200	1,033,000
	461,939,700	466,136,100	460,497,204	439,029,702	468,724,918	454,176,500	423,590,200

For some foreign countries, owing to the difficulty of obtaining accurate statistics since the beginning of the European war, estimates have been made for 1914, 1915, 1916, and 1917; for a few other countries, because of lack of basis for estimates, the figures for preceding years have been repeated.

The figures given for the years 1904 to 1912, inclusive, are taken from the reports of the Director of the Mint. The statistics for 1913 to 1917, inclusive, were mainly adjusted in conference between the Mint and the Geological Survey.

The notable increase of total world's output of gold culminated in a new record of $468,724,918 in 1915.

The estimated world's production of gold in 1916 was $454,176,500, or about $14,500,000 less than in 1915, and it is estimated that the production in 1917 was $45,000,000 less than in 1915.

Digitized by Google

The present tendency, in the absence of discovery and development of new gold fields on a large scale, is toward a declining world's output of new gold, and this tendency is accentuated by the high cost of labor and supplies, which makes the operation of many gold mines unprofitable.

WORLD'S PRODUCTION OF SILVER.

Production of silver in the world, 1860–1917.

[The annual production from 1860 to 1872 is obtained from statistics for 5-year periods compiled by Dr. Adolph Soetbeer. For the period since 1872 the estimates are those of the Bureau of the Mint.]

Year.	Quantity (fine ounces).	Commercial value.	Year.	Quantity (fine ounces).	Commercial value.
1860	29,095,428	$39,337,000	1890	126,095,062	$131,937,000
1861	35,401,972	46,191,000	1891	137,170,000	135,500,200
1862	35,401,972	47,651,000	1892	153,151,762	133,404,400
1863	35,401,972	47,616,000	1893	165,472,621	129,119,900
1864	35,401,972	47,616,000	1894	164,610,394	104,493,000
1865	35,401,972	47,368,000	1895	167,500,960	109,545,600
1866	43,051,583	57,646,000	1896	157,061,370	105,859,300
1867	43,051,583	57,173,000	1897	160,421,082	96,252,700
1868	43,051,583	57,098,000	1898	169,055,253	99,742,600
1869	43,051,583	57,043,000	1899	168,337,452	101,002,600
1870	43,051,583	57,173,000	1900	173,591,364	107,626,400
1871	63,317,014	83,958,000	1901	173,011,283	103,806,700
1872	63,317,014	83,705,000	1902	162,763,483	86,264,700
1873	63,267,187	82,120,800	1903	167,689,322	90,552,200
1874	55,300,781	70,674,400	1904	164,195,266	95,233,300
1875	62,261,719	77,578,100	1905	172,317,688	105,113,700
1876	67,753,125	78,322,600	1906	165,054,497	111,721,100
1877	62,679,916	75,278,600	1907	184,206,984	121,577,100
1878	73,385,451	84,540,000	1908	203,131,404	108,655,100
1879	74,383,495	83,532,700	1909	212,149,023	110,364,400
1880	74,795,273	85,640,600	1910	221,715,673	119,727,000
1881	79,020,872	89,925,700	1911	226,192,923	122,143,800
1882	86,472,091	98,232,300	1912	224,310,654	137,883,300
1883	89,175,023	98,984,300	1913	225,410,085	136,153,700
1884	81,567,801	90,785,000	1914	160,626,019	88,845,500
1885	91,609,959	97,518,800	1915	178,850,500	92,809,100
1886	93,297,290	92,793,500	1916	161,177,900	106,022,800
1887	96,123,586	94,031,000	1917	163,992,700	135,048,000
1888	108,827,906	102,185,900			
1889	120,213,611	112,414,100		6,837,394,741	5,370,527,100

The figures for the world's production of silver in 1917 show that the United States and Canada produced about 94,000,000 ounces, or 57 per cent, and that Mexico, Central America, and South America yielded more than 49,000,000 ounces, or 30 per cent, so that approximately only 21,000,000 ounces of silver came from all other countries, mainly from Japan, Spain, and Australasia.

There was a considerable increase in the quantity of silver produced in Mexico in 1917, but the production from mines in the United States decreased about 2,700,000 ounces and that from Canada 3,300,000 ounces.

Digitized by Google

World's production of silver, 1905–1917, in fine ounces.
[Figures supplied by U. S. Bureau of the Mint.]

Country.	1905	1906	1907	1908	1909	1910	1911	1912	1913	1914	1915	1916	1917
North America:													
United States	56,101,600	56,517,900	58,514,700	52,440,800	54,721,500	57,137,900	60,399,400	63,766,800	66,801,500	72,455,100	74,961,075	74,414,800	71,740,400
Canada	5,994,292	8,568,665	12,779,800	22,106,238	27,529,473	32,869,264	32,740,748	31,625,451	31,524,708	28,406,711	26,625,960	25,459,700	22,151,000
Mexico	65,040,865	55,225,268	61,147,203	73,664,027	73,942,432	71,372,194	79,032,440	74,640,300	70,703,828	27,546,752	39,570,151	22,838,400	31,214,000
Central American States	1,361,449	1,670,159	1,892,896	1,460,809	2,294,272	2,026,885	1,211,747	2,845,954	2,135,641	2,754,868	2,920,496	2,602,500	2,369,500
South America:													
Bolivia and Chile	3,494,851	3,149,395	5,222,358	5,806,117	5,548,154	6,490,163	4,555,043	4,049,856	3,932,594	789,685	3,870,065	4,402,100	4,107,400
Argentina	150,149	14,440	25,178	127,108	265,106	263,255	203,111	81,996	35,271	.....	.....	21,300	29,000
Brazil	.....	.....	.....	.....	.....	.....	47,222	40,610	28,364	76,685	21,523	22,000	25,000
Colombia	679,245	763,335	1,048,719	1,375,039	431,204	866,093	817,431	587,683	587,683	351,271	351,271	309,400	325,000
Ecuador	.....	13,592	2,456	22,642	22,642	22,642	22,642	22,642	22,642	16,726	24,655	30,000	45,000
Peru	6,156,044	7,404,238	9,566,118	9,566,118	9,566,118	6,626,930	8,351,563	8,351,563	9,971,067	9,214,190	9,419,950	10,787,000	11,000,000
Guiana and Uruguay	.....	.....	.....	.....	.....	.....	.....	724,235	51,111	.....	.....	8,500	8,000
Venezuela	.....	.....	.....	104,626	204,958	208,043	436,903	122,303	.....	.....	.....	.....	3,300
Europe:													
Austria-Hungary	1,860,169	1,806,322	1,744,233	1,770,457	999,184	1,540,808	1,538,772	1,840,297	2,104,107	1,572,746	1,772,699	1,500,000	1,500,000
Germany	5,820,947	5,696,433	5,088,086	4,971,544	5,332,901	5,597,026	4,984,677	4,984,677	4,984,677	.....	.....	.....	.....
France	890,555	719,453	794,973	592,042	629,848	713,028	429,831	429,831	520,766	.....	.....	.....	.....
Great Britain	167,479	137,216	137,216	135,255	141,943	136,370	136,370	113,769	128,543	135,458	96,450	86,500	86,000
Greece	829,025	829,025	829,025	829,025	829,025	881,539	803,750	803,750	803,750	591,464	591,464	350,000	350,000
Italy	757,777	672,449	737,843	674,848	786,620	468,566	998,576	447,761	423,888	510,365	493,856	486,500	450,000
Norway	242,805	175,475	201,516	226,175	213,122	229,989	292,075	247,988	247,988	440,917	413,867	439,100	282,000
Spain and Portugal	4,000,000	4,064,532	4,097,035	4,175,674	4,767,091	4,546,430	4,270,324	5,358,448	4,437,637	4,434,417	4,567,454	4,517,800	4,500,000
Russia	204,960	166,183	132,122	132,122	132,122	140,632	477,140	200,094	.....	.....	638,403	550,000	500,000
Serbia	.....	.....	.....	.....	11,226	.....	24,132	24,132	28,758	12,014	.....	10,000	20,000
Sweden	24,765	32,375	29,761	35,728	29,373	19,823	19,823	32,202	58,969	33,511	24,230	37,900	35,000
Turkey	37,874	37,874	67,351	7,971	1,717,896	1,717,896	1,717,896	1,509,133	1,509,133	1,509,133	1,509,133	500,000	400,000
Australasia	15,035,486	13,909,371	17,949,099	17,175,099	16,359,284	21,545,828	16,578,421	14,737,944	18,128,577	3,573,077	4,295,755	4,068,300	4,070,800
Asia:													
British India	.....	.....	.....	.....	.....	44,772	104,323	93,649	.....	236,440	284,875	628,700	600,000
China	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....	18,230	30,000	63,400
Chosen (Korea)	.....	.....	.....	.....	.....	164,844	9,446	12,224	15,048	16,864	21,897	25,000	28,000
Dutch East Indies	182,889	248,240	335,454	571,953	465,980	465,980	465,980	465,980	465,980	.....	.....	.....	.....
Indo-China	.....	.....	.....	.....	.....	.....	.....	.....	.....	1,767	1,056	1,000	1,000
Formosa	.....	.....	.....	.....	.....	.....	.....	.....	51,763	51,080	47,653	47,700	50,000
Japan	2,664,842	2,530,093	3,073,411	3,887,397	4,130,972	4,581,613	4,459,087	4,932,852	4,649,910	4,836,228	5,120,293	5,805,700	6,844,500
Africa	619,620	702,464	790,431	1,272,595	1,076,577	1,037,160	1,064,050	.....	.....	.....	.....	.....	.....
Belgian Kongo	.....	.....	.....	.....	.....	.....	.....	.....	1,454	4,770	4,770	11,000	10,300
Egypt	.....	.....	.....	.....	.....	.....	.....	.....	.....	1,223	1,657	1,200	900
French East Africa	.....	.....	.....	.....	.....	.....	.....	73,286	.....	.....	.....	20,000	20,000
Madagascar	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
Rhodesia	.....	.....	.....	.....	.....	.....	.....	158,572	121,537	150,794	185,238	200,700	212,000
Transvaal, Cape Colony, Natal	.....	.....	.....	.....	.....	.....	.....	984,672	933,191	901,763	996,379	968,900	950,000
Portuguese East Africa	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....	1,200	1,200
	172,317,688	165,054,497	184,206,984	203,131,404	212,149,023	221,715,673	226,192,923	224,310,654	225,410,085	160,626,019	178,850,500	161,177,900	163,992,700

Digitized by Google

GOLD AND SILVER AND THE WAR.

The vast issues of bonds floated by most of the belligerent countries in the last three years have brought under consideration the desirability of larger production of gold and silver in order to sustain national credits, but this has not been possible under war conditions. It is not surprising that the world's production of gold decreased about $30,600,000 in 1917 nor that the output of silver was less by 61,500,000 ounces in 1917 than in 1913. It is astonishing that the decline was not more pronounced.

The full effects of the shortage of labor, the inefficiency of much of the labor available, lack and increased cost of transportation, and high costs of material did not reach a climax until 1918. The world's production of gold will undoubtedly be much less in 1918 than in 1917. The production of silver probably will not show so large a decline, for the larger output of silver from copper and lead ores in the United States, and from copper, silver, and lead mines in Mexico and South America, will partly offset decrease from siliceous ores in the United States and Canada.

War demands for silver, because of continued imperative needs in the Orient and because of the large increase in silver coinage to relieve gold currency and to pay armies and workers, have steadily increased. Commercial uses of silver in the arts and most industries have likely decreased but the use of silver nitrate has increased enormously. In order to stabilize the market for silver the maximum domestic price was fixed at 101½ cents per ounce, and under the Pittman Act passed by Congress in April, 1918, 350,000,000 silver dollars held in the United States Treasury were made available for remelting into bars and are being utilized by the United States and allied nations to settle trade balances in India, China, and other large silver-using countries. The quantity of silver required for this purpose was in excess of the total output of silver in the world in 1917, and it is stated that more than 75,000,000 silver dollars have been remelted up to October 1, 1918.

It is certain that the production of gold in South Africa, the United States, Russia, India, and Canada will materially decrease in 1918, and although there may be increase in Mexico and some South American countries such increase will be comparatively small and will not offset the loss in the principal gold-producing countries.

Many operators of gold mines produce ore of such grade that the margin of profit is very small and that margin depends entirely on the continuous supply and economical treatment of large quantities of ore. The difficulty in obtaining supplies and the decreased efficiency of the miners that could be obtained prevented the usual development in 1917. In consequence much of the ore milled in 1917 and in 1918 was that already broken in the mines and kept as a reserve. Prospecting and development of new mines and opening of new ore bodies in working properties have been retarded or altogether suspended. Moreover some properties have previously successfully mined and treated quantities of low-grade ore by mixing it with ore of higher grade. The higher cost of mining has in many cases rendered this course impossible lately, and the higher-grade ore was treated alone. This may result in leaving large quantities of ore which it will not be possible to hoist and mill at a profit in the future.

Digitized by Google

The gold-mining districts most affected by labor conditions were those adjacent to districts in which base metals were mined, as the products of the base-metal mines were sold at prices which enabled higher wages to be paid than owners of gold mines could afford to pay. Many gold mines have closed down and at others the best ore bodies are being exhausted at little or no profit.

The conditions at present hampering the mining of gold and the remedies for such conditions were investigated by organizations of mine owners such as the American Gold Conference, organized at Reno, Nev., in August, 1918, and the International Gold Conference, organized at Spokane, Wash., in September, 1918. It has been generally realized that it has not yet proved feasible to increase the price of gold or to change the quantity of gold in the coinage, but the operators of gold mines suggest that the gold industry can be aided by less revolutionary methods, which will not meet the same opposition. A report on the causes of the decrease in the production of gold and the future outlook of the industry has been made to the Secretary of the Interior by a joint committee from the Bureau of Mines and the Geological Survey under the chairmanship of Mr. Hennen Jennings.

In November, 1918, a committee, which includes the Director of the Mint, the Governor of Nevada, representatives of the War Trade Board and the War Industries Board, and prominent economists, was appointed to consider legislation to meet the problems which have tended seriously to impair the supply of gold from United States mines.

It is apparent that conditions imposed by the world war are responsible for much of the decrease in gold production, but in the United States there have been contributing causes which are more fully discussed in the separate State chapters of Mineral Resources for 1917 which relate to gold, silver, copper, lead, and zinc. Briefly stated, some of these minor causes are as follows:

In Alaska a decrease of about $1,300,000 of the total decrease of $2,580,000 in 1917 was due to the flooding of the Treadwell mines and to the lower gold content of the siliceous ore mined, which fell from an average per ton of $1.66 in gold in 1916 to $1.34 in 1917. Much of the decrease in yield of gold in Nevada in 1917 was due to the exhaustion of high-grade gold ore at Goldfield and of silver-gold ore at Tonopah. The quantity of ore treated in these two districts was 809,610 tons, only 28,986 tons less than in 1916, but the gold recovered decreased $1,153,000. Nearly all the decrease in yield of gold from Idaho was due to the exhaustion of gravels worked by dredging, and part of the decrease in Montana was due to the same cause and also to the strike at Butte, which reduced the quantity of gold-bearing copper ore mined and treated. California and Colorado were the two States most affected by the shortage of labor and the high cost of supplies, and much of the decrease in the production of gold in those States was caused by the smaller quantity of siliceous ores and old tailings treated by cyanidation. In Colorado the decrease in yield of gold was partly due to the smaller quantity of high-grade gold ores available for milling at Cripple Creek, Camp Bird, and other camps, and to the partial exhaustion of the high-grade deposits of gravel. It is difficult to make a correct division of the decrease of gold in the United States in 1917 between that caused by the war and that resulting from other causes. It is probable that at least $4,500,000 of the decrease of more than $10,000,000 was the result of conditions apart from the war.

Digitized by Google

MINES REPORT.

METHOD OF COLLECTING STATISTICS.

The first table in this report presents the final official figures of the production of gold and silver in the United States in 1917 as agreed upon by the Bureau of the Mint and the United States Geological Survey. With the comparatively unimportant exceptions of domestic gold and silver contained in ores and mattes exported for reduction during the year, these figures record the actual production of gold and silver bullion from domestic ores in marketable form as metals, either refined or unrefined.

Owing to the difficulty of tracing this total gold and silver production back to its origin by States, counties, and mining districts, however, the Geological Survey attacks this problem of distribution by systematic investigation of the mine production of ores containing gold and silver during the calendar year and of the output of the placer mines. In this way the state of the mining industry is studied in detail, and classification of output by methods of production and by kinds of ore, as well as by mining districts, is obtained. The resulting figures form the basis of the mines report.

Of the two plans outlined for ascertaining the gold and silver production of the United States it may be said that the one is a measure of the mining industry and the other a measure of the metallurgical industry; that the one reports the production and recoverable content of mine output and the other the metal actually recovered in marketable form. The two methods will not produce exactly corresponding results, nor should they be expected to do so.

The figures of the reports of the Mint and of the mines reports for a period of years sufficiently long to compensate for overlap or lag should agree within allowable limits of error due to the complex problem involved.

For the last 13 years in which complete statistics have been gathered by both methods the final figures have been as follows:

Production of gold and silver in the United States, 1905–1917, according to mint and to mine returns.

Year.	Mint.		Mine.	
	Gold.	Silver.	Gold.	Silver.
		Ounces.		*Ounces.*
1905	$88,180,700	56,101,000	$88,159,881	56,272,496
1906	94,373,800	56,517,900	97,219,645	57,362,455
1907	90,435,700	56,514,700	87,471,136	52,500,101
1908	94,560,000	52,440,800	91,914,891	50,878,140
1909	99,673,400	54,721,700	99,438,144	57,315,677
1910	96,269,100	57,137,900	94,933,778	57,598,509
1911	90,890,000	60,399,400	97,054,791	61,108,791
1912	93,451,500	63,766,800	92,880,467	66,041,506
1913	88,884,400	66,801,500	89,987,888	71,200,237
1914	91,531,800	72,455,100	92,703,757	69,633,769
1915	101,035,700	74,961,075	99,605,314	72,368,878
1916	92,590,300	74,414,802	92,822,430	78,875,176
1917	83,750,700	71,740,362	82,032,745	70,665,531
	1,214,627,100	817,973,439	1,206,224,867	821,821,269

These figures show, according to Mint reports, a total excess of gold for the 13 years of $8,402,233, or a difference of not quite 0.7 per cent, and a total deficit of silver of only 3,847,830 ounces, or a difference less than 0.47 per cent. The figures for Alaska placers are

Digitized by Google

not considered to be so closely approximate as the above agreement for gold, hence the differences for the United States proper are probably even lower. It is thought that those small differences are fully accounted for in the detailed discussions of the subject in previous reports of this series. For figures of any one year an excess of mining over smelting and refining is indicated by larger returns in the mines reports for gold or silver or both and opposite relations or excess of smelting and refining and drawing upon stocks are indicated by larger returns in the Mint report.

UNITS OF MEASUREMENT.

In measurement of ores and concentrates the short ton of 2,000 pounds is used throughout. The price of gold is fixed by law at $20.67+ per fine ounce. The annual average prices for silver from 1865 to 1917, inclusive, based on the equivalent New York value of a fine ounce with exchange at par, are given elsewhere in this report. (See p. 607.) The average commercial prices (or dealers' prices) for silver 0.999 fine at New York are those quoted from day to day on the market and run uniformly somewhat below the prices as given elsewhere by years.

PRODUCTION OF GOLD AND SILVER REPORTED FROM THE MINES.

The following table gives the quantity and value of the output of recoverable gold and silver (mine production) by States reported from the producing mines in 1917 to the United States Geological Survey. The increase or decrease of production shows results by comparison with the corresponding Survey mine figures for 1916.

Mine production of gold and silver in the United States in 1917.

State or Territory.	Gold.		Silver.		Increase or decrease.	
	Quantity (fine ounces).	Value.	Quantity (fine ounces).	Value.	Gold.	Silver (fine ounces).
Alabama	109.42	$2,262	11	$9	− $6,388	− 42
Alaska	709,049.45	14,657,353	1,239,150	1,021,060	− 2,584,360	− 140,021
Arizona	245,173.83	5,068,193	6,963,913	5,754,744	+ 1,082,634	− 228,126
California	971,733.00	20,087,504	1,775,431	1,462,955	− 1,323,237	− 788,923
Colorado	760,901.22	15,729,224	7,304,353	6,018,787	− 3,424,597	− 352,191
Georgia	333.26	6,889	46	37	− 15,650	− 28
Idaho	38,932.64	804,809	12,029,338	9,912,175	− 311,001	− 271,535
Illinois	.....	.....	7,186	5,921	.....	+ 1,502
Maryland, New Hampshire, Pennsylvania and Vermont	6.62	137	1,709	1,409	+ 137	− 2,312
Michigan	.....	.....	688,551	567,366	.....	− 28,089
Missouri	.....	.....	61,586	50,747	.....	− 67,864
Montana	170,147.11	3,517,253	13,128,142	10,817,589	− 1,033,241	− 3,366,224
Nevada	336,664.26	6,959,468	11,269,969	9,286,454	− 1,906,769	− 2,567,556
New Mexico	51,478.64	1,064,158	1,394,365	1,148,957	− 318,322	− 371,909
North Carolina	589.55	12,187	1,110	915	− 14,050	+ 447
Oklahoma	.....	.....	.....	.....	.....	− 606
Oregon	72,165.73	1,491,798	125,656	103,541	− 410,381	− 105,686
Philippine Islands	68,119.81	1,408,161	4,019	3,312	− 106,039	− 13,624
Porto Rico	4.84	100	.....	.....	− 500	.....
South Carolina	52.39	1,083	3	2	+ 763	− 25
South Dakota	356,244.77	7,364,233	186,765	153,894	− 96,411	− 28,440
Tennessee	257.65	5,326	99,053	81,619	− 413	+ 4,352
Texas	1.06	22	595,789	490,930	− 392	− 57,666
Utah	162,305.67	3,355,156	13,479,133	11,106,806	− 219,791	+ 226,096
Virginia	64.97	1,343	4,518	3,723	+ 458	+ 3,735
Washington	23,816.17	492,324	282,320	232,632	− 85,331	− 52,801
Wyoming	181.98	3,762	3,415	2,814	− 16,804	− 2,109
	3,968,334.04	82,032,745	70,665,531	58,228,398	−10,789,685	− 8,209,645
Increase or decrease in value	.....	.....	.....	.....	−10,789,685	+$6,228,532

Digitized by Google

A decrease in production of gold from mines of the United States of $10,789,685 is shown for 1917, following a decrease of $6,782,884 in 1916. A decrease of 8,209,645 ounces of silver is shown, following an increase of 6,506,298 ounces in 1916.

The principal gold-producing States ranked as follows in 1917: California, Colorado, Alaska, South Dakota, Nevada, and Arizona, and these six States together made nearly 85 per cent of the total output. The only notable increase was Arizona, which produced about $1,080,000 more in 1917 than in 1916. The most notable decrease in gold was $3,424,597 in Colorado, $2,584,360 in Alaska, $1,906,769 in Nevada, $1,323,237 in California, and $1,033,241 in Montana. Every State that yielded more than $50,000 in gold, with the exception of Arizona, had a decreased output in 1917.

The principal silver-producing States in 1917 in order of output were Utah, Montana, Idaho, Nevada, Colorado, and Arizona, and these six States together produced 90 per cent of the total for the United States. There was no large increase in 1917 and only five States had an increased output, of which Utah had the largest—226,000 ounces. There was large decrease in output of silver—2,567,556 ounces in Nevada, 3,366,224 ounces in Montana, 788,923 ounces in California, and 352,191 ounces in Colorado.

About $35,400,000, or 43 per cent, of the entire output of gold in the United States in 1917 was produced by 25 companies. The largest producer was the celebrated Homestake mine in South Dakota. Seventeen of the larger properties produced the gold from dry or siliceous ores, 3 produced it from gravels by dredging, 4 recovered the gold in the treatment of copper ores, and 1 from lead ores. Deducting the output of gold of the large producing operators, it is shown that about $46,800,000 came from the operation of about 5,000 placer and deep mines, many of which produced between $100,000 and $600,000 each. Hundreds of mines, especially placer properties in California, Oregon, Idaho, Alaska, Arizona, and the Applachian States, yielded very small quantities of gold.

Larger producers of gold in the United States in 1917, in order of output.

Operator.	State.	Mining district.	Source of gold.
Homestake Mining Co	South Dakota	Whitewood	Dry or siliceous ores
Yuba Consolidated Goldfields	California	Marysville	Dredging gravels.
Cresson Consolidated Mining Co	Colorado	Cripple Creek	Dry or siliceous ores
Portland Gold Mining Co	do	do	Do.
Alaska Gastineau Mining Co	Alaska	Juneau	Do.
Empire Mines	California	Grass Valley	Do.
United Eastern Mining Co	Arizona	Oatman	Do.
Vindicator Consolidated Gold Mining Co	Colorado	Cripple Creek	Do.
Goldfield Consolidated Mines Co	Nevada	Goldfield	Do.
North Star Mines	California	Grass Valley	Do.
Yukon Gold Co	Alaska	Ruby and Iditarod	Dredging gravels.
Utah Copper Co	Utah	West Mountain	Copper ores.
Argonaut Mining Co	California	Grass Valley	Dry or siliceous ores
Tomboy Gold Mines Co	Colorado	Upper San Miguel	Do.
Liberty Bell Gold Mining Co	do	do	Do.
Marysville Dredge Co	California	Marysville	Dredging gravels.
Plymouth Consolidated Mining Co	do	Mother Lode	Dry or siliceous ores
Kennedy Mining Co	do	Jackson	Do.
Barnes King Mining Co	Montana	Ottawa	Do.
Alaska United Mining Co	Alaska	Juneau	Do.
United Verde Copper Co	Arizona	Verde	Copper ores.
Calumet & Arizona Mining Co	do	Turquoise	Do.
United States Mining Co	Utah	West Mountain	Lead ores.
Anaconda Copper Mining Co	Montana	Summit Valley	Copper ores.
Tom Reed Gold Mines Co	Arizona	Oatman	Dry or siliceous ores

Digitized by Google

The largest output of silver was that of the Anaconda Copper Co. from copper ores. The Hercules Mining Co., of Idaho, which had the second largest output of silver, and the Bunker Hill & Sullivan Mining Co., the fourth largest producer, derived the silver from lead ores. The Tonopah Belmont Development Co., which held third place, was the largest producer from siliceous ores. Six of the 25 mines enumerated recovered silver from copper ore, 10 from lead ore, 8 from dry or siliceous ore, and 1 from zinc-lead ore. Several mines yielded more silver than the Presidio mine, in Texas, but it was the largest producer of silver from ore that contained no appreciable quantity of any other metal. The approximate output of the 25 properties was 35,410,000 ounces, or about 50 per cent of the total production of silver in the United States in 1917.

Larger producers of silver in the United States in 1917, in order of output.

Operator.	State.	Mining district.	Source of silver.
Anaconda Copper Mining Co.	Montana	Summit Valley	Copper ores.
Hercules Mining Co.	Idaho	Leland	Lead ores.
Tonopah-Belmont Development Co.	Nevada	Tonopah	Dry or siliceous ores.
Bunker Hill & Sullivan Mining Co.	Idaho	Yreka	Lead ores.
Butte & Superior Mining Co.	Montana	Summit Valley	Lead-zinc ores.
Chief Consolidated Mining Co.	Utah	Tintic	Lead ores.
United Verde Copper Co.	Arizona	Verde	Copper ores.
Tonopah Mining Co.	Nevada	Tonopah	Dry or siliceous ores.
Hecla Mining Co.	Idaho	Leland	Lead ores.
Tonopah Extension Mining Co.	Nevada	Tonopah	Dry or siliceous ores.
Federal Mining & Smelting Co.	Idaho	Hunter	Lead ores.
Caledonia Mining Co.	do	Yreka	Do.
Calumet & Arizona Mining Co.	Arizona	Warren	Copper ores.
Silver King Coalition Mining Co.	Utah	Uintah	Lead ores.
Kennecott Copper Co.	Alaska	Chitina	Copper ores.
Jim Butler Tonopah Mining Co.	Nevada	Tonopah	Dry or siliceous ores.
Copper Queen Consolidated Mining Co.	Arizona	Warren	Copper ores.
Nevada Wonder Mining Co.	Nevada	Wonder	Dry or siliceous ores.
Green Hill Cleveland Mining Co.	Idaho	Leland	Lead ores.
North Butte Mining Co.	Montana	Summit Valley	Copper ores.
Iron Blossom Consolidated Mining Co.	Utah	Tintic	Lead ores.
United States Mining Co.	do	West Mountain	Do.
West End Consolidated Mining Co.	Nevada	Tonopah	Dry or siliceous ores
Smuggler Union Mining Co.	Colorado	Upper San Miguel	Do.
Presidio Mining Co.	Texas	Shafter	Siliceous (silver) ores.

MINE PRODUCTION OF GOLD AND SILVER, BY STATES.

ALASKA.

It is estimated that the total production of gold in Alaska from earliest mining, in 1880, to the end of 1917 has been $292,758,000, of which $207,142,992 has come from placers. The total production of silver has been 7,541,600 fine ounces, of which 4,607,493 ounces was recovered from copper ores and 1,703,323 ounces from the refining of placer gold.[1]

Gold.—The mine production of gold in Alaska in 1917 was $14,657,353, or about $2,580,000 less than that of 1916. The yield from siliceous ores decreased from $5,912,736 in 1916 to $4,581,453 in 1917; the yield from copper ores increased from $188,977 in 1916 to $265,900 in 1917; the placer output in 1917 was $9,810,000 against $11,140,000 in 1916. Thirty-six dredges produced $2,500,000 of the placer gold, which was $179,000 less than the yield from dredging in 1916.

[1] U. S. Geol. Survey Mineral Resources, 1917, pt. 1, pp. 131–136, 1918.

Digitized by Google

Of the productive gold lode mines, 10 were in southeastern Alaska, 3 on Prince William Sound, 4 in Kenai Peninsula, 5 in Willow Creek district, and 9 in Fairbanks district. The 10 deep gold mines in southeastern Alaska yielded more than 92 per cent of the gold derived from siliceous ores.

The 3,414,664 tons of siliceous ores treated in 1917 yielded an average of $1.37 in gold and silver a ton, and the 659,951 tons of copper ore contained $1.70 in gold and silver a ton and had a copper content of 6.4 per cent.

More than 31 per cent of the total output of gold in Alaska came from gold lode mines in 1917, against 34 per cent in 1916, 36 per cent in 1915, 31 per cent in 1914, 31 per cent in 1913, and 29 per cent in 1912. The 610 placers operated in 1917 yielded approximately 5,900,000 cubic yards of auriferous gravel, of which the dredges handled about 3,700,000 cubic yards and made an average recovery of 67.5 cents a yard in 1917, against 69 cents a yard in 1916, 51 cents a yard in 1915, and 52 cents a yard in 1914. The estimated total recovery of gold by dredging for the period 1903–1917, inclusive, is $17,610,000.

The only new placer-bearing areas reported in 1917 were in the Kuskokwim and Goodnews Bay districts.

Silver.—The mine production of silver in Alaska in 1917 was 1,239,150 fine ounces, against 1,379,171 ounces in 1916. The copper mines produced 1,041,153 ounces, a decrease of 165,968 ounces. The siliceous ores yielded 133,587 ounces in 1917, against 110,050 ounces in 1916 and 91,341 ounces in 1915, and the placers yielded 64,410 ounces in 1917, against 62,000 ounces in 1916.

ARIZONA.

Gold.—The mine production of gold in Arizona in 1917 was $5,068,193, which was $1,082,634, or 27 per cent, more than in 1916. Placers contributed only $17,214, which came from small mines in Yuma, Pima, Maricopa, and Yavapai counties. The deep mines produced $5,050,979, of which 53 per cent came from dry or siliceous ores mined chiefly in Mohave, Yavapai, and Cochise counties, and 40 per cent was contained in copper ores mined chiefly in Cochise and Yavapai counties. Mohave County had a gold output of $2,463,178, an increase of more than $1,400,000; Cochise County produced $1,149,782 and Yavapai County $1,023,464. The gold recovered from ores treated at gold and silver mills represented 49 per cent of the total output, against 36 per cent in 1916, and crude ores shipped to smelters contained nearly 39 per cent. The crude copper ores mined and smelted directly (without previous concentration) contained an average gold content of 46 cents a ton.

Silver.—The mine production of silver decreased from 7,212,039 fine ounces in 1916 to 6,983,913 ounces in 1917. Of this production 5,214,411 ounces came from copper ores, 848,500 ounces from dry or siliceous ores, 553,544 ounces from lead ores, 190,033 ounces from lead-zinc ores, and smaller quantities from zinc, copper-zinc, and copper-lead ores. Cochise County produced 2,707,220 ounces in 1917, of which 1,806,040 ounces came from copper ores and 522,688 ounces from siliceous ores. The silver output of Yavapai County, which increased from 1,735,302 ounces in 1916 to 2,207,583 ounces in 1917,

Digitized by Google

was mainly derived from copper ores. Bullion recovered from gold and silver ores, almost all by cyanidation, yielded 254,353 ounces of silver. Concentrates contained 1,271,890 ounces and crude ore shipped to smelters contained 5,312,292 ounces, or 76 per cent of the total output of silver.

CALIFORNIA.

Gold.—The mine production of gold in California in 1917 was $20,087,504. The decrease of $1,082,634 was due to a smaller production from deep-mine operations.

In 1917 the deep mines produced $11,013,474 (a decrease of $1,821,610), of which gold-quartz ores yielded 93 per cent and copper ores 6.1 per cent. California placers in 1917 produced $9,074,030 in gold, or $498,373 more than in 1916. Of the placer production $8,313,527 was recovered by dredging. The total dredge production from 1896 to the end of 1917 has been $95,193,985 and the yield of gold by dredges was equal to 41 per cent of the total yield of gold for 1917. The Yuba County dredges, 12 in number, made the largest output of gold, the value being $3,659,211, an increase of $519,061. Sacramento County, with 12 dredges working, made an output of $1,913,504, an increase of $84,026. In Butte County (including Oroville and other districts) 11 dredges produced $898,141 in gold, or $312,733 less than in 1916. Dredges were also operated in Calaveras, Eldorado, Merced, Stanislaus, Placer, Shasta, Siskiyou, and Trinity counties.

Five of the 26 counties in California which reported mine production of gold had a yield of more than $1,000,000 in 1917, as follows: Nevada, $3,682,947; Amador, $3,664,164; Yuba, $3,677,673; Sacramento, $1,919,581; Calaveras, $1,471,442. Of these Yuba and Sacramento counties obtained most of their yield by dredging, Amador and Calaveras are on the Mother Lode, and Nevada County produced mainly from siliceous ores of the Grass Valley district. The five Mother Lode counties—Amador, Calaveras, Eldorado, Mariposa, and Tuolumne—whose output is mainly gold milling ores, produced $3,202,212 in gold from mill bullion and $1,888,961 from concentrates in 1917, against a recovery of $3,719,649 from mill bullion and $2,092,169 from concentrates in 1916.

Silver.—The mine production of silver in California in 1917 was 1,775,431 fine ounces, a decrease of 788,923 ounces. More than 36 per cent of the output, or 625,000 ounces, came from the copper ores of Shasta County. Copper ores yielded 882,480 ounces. Siliceous ores yielded 139,492 ounces, silver-lead ores, silver ores, and lead ores 726,174 ounces, and placers the remainder. The only counties producing more than 100,000 ounces of silver in 1917 were Shasta, Inyo, Calaveras, and San Bernardino. About 85 per cent of all the silver was recovered from crude ores sent to smelters.

COLORADO.

Gold.—The total mine production of gold in Colorado in 1917 was $15,729,224, a decrease of $3,424,597. The Cripple Creek district, with a decrease of $1,724,703, produced $10,394,847 in gold, which was 66 per cent of the State output of gold from all sources. During

Digitized by Google

1917 the Roosevelt tunnel was driven 1,746 feet. The total length of the tunnel from portal to breast at the end of 1917 was 24,000 feet.

The San Juan region, in Dolores, La Plata, Ouray, San Juan, and San Miguel counties, produced $2,451,292, a decrease of $589,988. Lake County yielded $1,175,219, a decrease of $545,221, and there were also decreases in Boulder, Clear Creek, Gunnison, Gilpin, La Plata, Ouray, Chaffee, and San Juan counties. Siliceous and dry ores, which amounted to 74 per cent of all the ore sold or treated, yielded 74 per cent of the total output of gold. Slightly less than 3 per cent came from lead ore, 4 per cent from placers, about 1 per cent from copper ore, and the remainder from other classes of ore. The placer production in 1917 was $661,028, a decrease of $51,896. Summit County produced nearly 82 per cent and Lake County 17 per cent of the placer gold. Dredges in these two counties recovered more than 98 per cent of the placer gold.

Silver.—The mine production of silver in Colorado in 1917 was 7,304,353 fine ounces, a decrease of 352,191 ounces. Lake County, principally Leadville, produced 2,184,000 ounces, a decrease of 463,560 ounces. San Miguel County produced 779,364 ounces, a decrease of 32,677 ounces. There was a considerably larger production of silver from Ouray, San Juan, Clear Creek, Chaffee, and Pitkin counties and decreased output from Gilpin and La Plata counties. Siliceous and dry ores yielded 66.6 per cent of the silver recovered, lead ores 16 per cent, lead-zinc ores 12.7 per cent, and copper ores 2.5 per cent. The remainder came from placers, zinc ores, and copper-lead ores.

IDAHO.

Gold.—The mine production of gold in Idaho in 1917 was $804,809, a decrease of $311,001. The total production of gold from Idaho from the discovery of placer gold in 1863 to the end of 1917 is estimated at $130,910,969 by C. N. Gerry.[1]

Boise and Idaho counties were the largest producers of gold and yielded about 53 per cent of the total output. The lode mines produced gold valued at $669,578. The placer mines produced $135,231 in gold in 1917, of which $59,447 was won by dredging. The total output of gold recovered by dredges from 1897 to the end of 1917 has been $3,781,503. Of the total gold in 1917 about 17 per cent came from placers, 64 per cent from siliceous ores, 7 per cent from copper ores, and the remainder from lead and lead-zinc ores.

Silver.—The mine production of silver in Idaho in 1917 was 12,029,338 fine ounces, or 271,535 ounces less than in 1916. The total yield of silver from Idaho for the period 1863 to 1917, inclusive, is 224,706,000 fine ounces.[1]

There was a decrease of 3 per cent in the output of silver from Shoshone County, which yielded 93.4 per cent of the total quantity of silver in 1917, 95 per cent in 1916 and 1915, and 98 per cent in 1914. Lead ores contained 67 per cent of the output of silver and lead-zinc ores 30 per cent. Crude ore shipped, which averaged 13.80 ounces of silver a ton, supplied nearly 33 per cent of the silver, and concentrates, which averaged 19.19 ounces of silver a ton, contained nearly 67 per cent of the total silver. Inability to handle and smelt all the ores mined had the effect of curtailing the production of silver.

[1] U. S. Geol. Survey Mineral Resources, 1917, pt. 1, p. 457, 1918.

Digitized by Google

MARYLAND, PENNSYLVANIA, NEW HAMPSHIRE, AND VERMONT.

A small production of gold and silver was reported by copper mines in Frederick County, Md., in 1917, although work was also done on prospects in Montgomery County, Md. A small quantity of gold and about 500 ounces of silver were obtained from copper ores and old slag shipped from mines in Orange County, Vt.

MICHIGAN.

Silver.—The copper mines of Michigan produced 688,551 fine ounces of silver in 1917, against 716,640 ounces in 1916. The silver was mainly derived from the electrolytic treatment of 70,329,000 pounds of copper. The average recovery of silver per ton of "rock" treated was 0.21 ounce a ton. Of the total output of silver 558,465 ounces came from mines in Houghton County.

MISSOURI, OKLAHOMA, ILLINOIS, AND KENTUCKY.

Silver.—The lead and zinc mines of the Central States produce no gold and only a comparatively small quantity of silver. Nearly all the silver is a by-product from the refining of lead from concentrates of lead ores mined in southeastern Missouri. The total yield of silver from Missouri in 1917 was 61,586 fine ounces, which, with the exception of a few ounces recovered from copper ore, was derived from lead recovered from 76,222 tons of galena concentrates. The average recovery was slightly less than 0.81 ounce of silver per ton of concentrate smelted.

The lead-zinc fluorspar deposits of the Kentucky-Illinois field carry silver, and from the lead concentrates shipped from Illinois in 1917 a recovery of 7,186 ounces was recorded, against 5,684 ounces in 1916. The average silver content per ton recovered from lead concentrates from Illinois in 1917 was 5.80 ounces. No silver ore was shipped from the Criswell mine, near Byars, McClain County, Okla., in 1917.

MONTANA.

Gold.—The mine production of gold in Montana decreased from $4,550,494 in 1916 to $3,517,253 in 1917. The placer yield was $467,063, a decrease of $256,096. Lewis and Clark County had the largest total output, $872,529. Most of the placer gold was recovered by one company, which operated three dredges in Alder Gulch, in Madison County. Deer Lodge County produced $456,588, chiefly from siliceous ores, and Silver Bow County $690,801, chiefly from copper ores. At amalgamation and cyanidation plants $1,383,097 in gold was produced, or an average recovery of $4.10 per ton of ore and tailings treated. Ore treated at concentration mills yielded concentrates containing $675,560, or 37 cents a ton, and crude ore shipped to smelters contained $982,558 in gold, or an average of $1.95 a ton.

Silver.—Montana mines produced 13,128,142 fine ounces of silver in 1917, a production nearly 20 per cent less than in 1916. The copper ores yielded 8,911,389 ounces (an average of 1.84 ounces per ton), of which Silver Bow County (Butte) supplied 8,791,855 ounces. The lead-zinc ores produced 2,386,824 ounces, of which Silver Bow

Digitized by Google

County supplied 2,183,662 ounces. The dry or siliceous ores produced 954,477 ounces, of which Granite County supplied 394,586 ounces. Nearly all the silver from zinc ore, 378,239 ounces, came from Silver Bow County.

NEVADA.

Gold.—The mine production of gold in Nevada in 1917 was $6,959,468, against $8,866,237 in 1916. The production in 1917 from mines in Esmeralda County was $1,986,001, a decrease of nearly $700,000. The Goldfield district yielded $1,900,082 in gold in 1917, against $2,651,158 in 1916. Nye County produced $2,007,234, of which Tonopah yielded $1,539,529. The counties having a substantial increase in gold were White Pine and Lincoln. Sixty-six per cent of the decrease in output of gold was due to smaller yield from Goldfield and Tonopah.

Silver.—There was a decrease in the mine production of silver in Nevada in 1917, the total being 11,269,969 fine ounces, against 13,837,525 ounces in 1916. Nye County (almost wholly from the Tonopah district) again led in output with 7,172,642 ounces, which was about 1,700,000 ounces less than in 1916. Churchill County, with 887,765 ounces, Humboldt County, with 859,837 ounces, and Lincoln County, with 523,399 ounces, were the other counties which had an output exceeding 500,000 ounces. Dry or siliceous ores yielded all but 1,093,252 ounces of the output of silver and 90 per cent of this yield was recovered by cyanidation.

NEW MEXICO.

Gold.—The mine production of gold in New Mexico in 1917 was $1,064,158, against $1,382,480 in 1916 and $1,461,105 in 1915. Mills in the Mogollon district, Socorro County, produced $258,620; Grant County, $404,446; and Colfax County, $348,733.

Copper ores, chiefly from Grant County, contained $224,829, and dry and siliceous ores yielded $816,469. The output from other kinds of ore was very small, and the placer output was only $12,179.

Silver.—The mine production of silver in New Mexico decreased from 1,766,274 fine ounces in 1916 to 1,394,365 ounces in 1917. Socorro County produced 859,892 fine ounces, or about 62 per cent, chiefly from siliceous ores from the Mogollon district, the remainder from mixed ores of the Magdalena district. The output of silver from Grant County decreased from 549,907 fine ounces in 1916 to 487,558 ounces in 1917, and most of this yield came from the Lordsburg district. Dry and siliceous gold and silver ores, chiefly from Grant, Sandoval, and Socorro counties, yielded 69.3 per cent of the total; copper ores, chiefly from Grant, Socorro, and Santa Fe counties, yielded 23 per cent. The remainder of the production was from lead, lead-zinc, and copper-lead ores, mainly from the Central and Magdalena districts.

OREGON.

Gold.—The mine production of gold from Oregon decreased more than 21 per cent, being $1,491,798 in 1917, against $1,902,179 in 1916. The output in 1916 was the largest recorded by the Survey for 13 years. The decrease in 1917 was mainly due to the deep mines, which yielded only $764,432, or $265,230 less in 1917 than in 1916.

Digitized by Google

The output from deep mines was almost entirely from siliceous ores. The placer mines of the State produced $727,366, a decrease of $145,151. The three dredges in the Cracker Creek district in Baker County and one dredge in Grant County produced $618,922, and a few drift mines, hydraulic and surface placers in Baker, Jackson, Crook, Josephine, and Malheur counties produced the remainder of the placer gold. Baker County, with a yield of $1,228,199, and Grant County with a yield of $137,720, were the only counties which produced more than $100,000 in gold.

Silver.—The mine production of silver in Oregon in 1917 was 125,656 fine ounces, a decrease of 105,686 ounces. Of the total production 87,121 ounces came from siliceous ores, 31,375 ounces from copper ores, and 7,160 ounces from placer bullion.

SOUTH DAKOTA.

The total value of the production of gold in South Dakota from 1876 to the end of 1917 is given by Charles W. Henderson, of the United States Geological Survey, as $207,518,800, and the total output of silver for the same period as 6,434,500 fine ounces.[1]

Gold.—The mine production of gold in South Dakota in 1917 was $7,364,233, against $7,460,644 in 1916. The output was almost wholly from siliceous milling ores of low grade, of which about 64 per cent was recovered by amalgamation and the remainder by cyanidation. The Homestake mines and mills were operated continuously and produced $6,619,573 in bullion from 1,677,623 tons of ore treated. The Golden Reward, Mogul, and Trojan mills were also operated steadily. The small yield of placer gold came from Lawrence and Pennington counties.

Silver.—The mine output of silver, derived mainly from refining the gold bullion produced, was 186,765 fine ounces, or 28,440 ounces less than in 1916.

SOUTHERN APPALACHIAN STATES.

The total production of gold from 1799 to the end of 1917 in the southern Appalachian States, as shown from data compiled by the Bureau of the Mint and the United States Geological Survey, has been $51,007,344. The figures credit Alabama with $765,539, Georgia with $17,817,876, Maryland with $71,405, North Carolina with $23,626,782, South Carolina with $5,181,429, Tennessee with $248,144, and Virginia with $3,296,169.

Gold.—The combined mine production of gold in the southern Appalachian States in 1917 was $29,156, against $64,370 in 1916. North Carolina led with $12,187; Georgia was next with $6,889; Tennessee, $5,326; Alabama, $2,262; Virginia, $1,343; South Carolina, $1,083; and Maryland, $66. The gold produced in Tennessee was from copper ores of the Ducktown district. The production of gold from 29 placers amounted to $6,954. Copper ores, mainly from Maryland, North Carolina, and Tennessee, yielded about 430 ounces of gold, and siliceous ores from Alabama, Georgia, North Carolina, and South Carolina yielded only 574 ounces in 1917, against 1,985 ounces from these States and Virginia in 1916.

[1] U. S. Geol. Survey Mineral Resources, 1917, pt. 1, p. 154, 1918.

Digitized by Google

TEXAS.

Gold.—The total output of gold from Texas mines from 1885 to the end of 1917 is given by Charles W. Henderson as $43,500.[1]

The yield of gold has been very small and has been mainly a by-product. The output of gold decreased from $414 in 1916 to $22 in 1917.

Silver.—The total production of silver in Texas from 1885 to 1917, inclusive, has been 13,677,100 ounces, according to Henderson.[1]

The mine production for 1917 was 595,789 fine ounces, against 653,455 ounces in 1916. The greater part of the silver continued to come from the Presidio silver mine and cyanidation mill in the Shafter district, Presidio County. The silver contained in copper ores shipped in 1917 amounted to 1,699 ounces and that in lead ores to 962 ounces.

UTAH.

Gold.—The total output of gold in Utah from 1864 to 1917, inclusive, is given by V. C. Heikes, of the United States Geological Survey, as $93,119,333.[2]

The mine production of gold decreased from $3,574,947 in 1916 to $3,355,156 in 1917. The largest part of the gold was contained in ores produced in Salt Lake County, and amounted to $2,268,684. Juab County ranked next with $843,609, against $856,474 in 1916. The Bingham district, with its large output of copper and other ores, produced $2,241,152 in gold in 1917, and the Tintic district, partly in Juab County and partly in Utah County, produced $868,547. The production of placer gold in 1917 was only $112, and the output recovered by cyanidation and amalgamation was about $2,900. The greater part of the Utah gold (58.5 per cent) was derived from copper ores mainly mined in Salt Lake and Juab counties; lead and lead-zinc ores contained 29 per cent.

Silver.—The total output of silver in Utah from 1864 to 1917, inclusive, has been 366,020,500 fine ounces, according to Heikes.[2]

The mine production of silver in Utah in 1917 was 13,479,133 ounces, an increase of 226,096 ounces. The largest production was from Juab County, credited with 4,988,005 ounces (mainly from lead ores), against 4,892,439 ounces in 1916. Salt Lake County had the next largest output, 3,769,884 ounces (from copper, lead, and lead-zinc ores), against 3,863,264 ounces in 1916. Of the Salt Lake County output of silver, the Bingham district produced 74 per cent. The Tintic district, in Juab and Utah counties, yielded 5,558,763 ounces (mainly from lead ores); and the Park City region, in Summit and Wasatch counties, produced 2,937,438 ounces, mainly from lead and lead-zinc ores. Altogether the lead ores of Utah yielded 7,490,650 ounces of silver in 1917, the copper ores 2,225,119 ounces, the lead-zinc ores 1,329,531 ounces, and the dry or siliceous ores 2,340,537 ounces. The crude ore smelted in 1917 contained 10,498,129 ounces and concentrates contained 2,469,804 ounces.

[1] U. S. Geol. Survey Mineral Resources, 1917, pt. 1, 1918.
[2] Idem, p. 167.

Digitized by Google

WASHINGTON.

The total production of gold in Washington from earliest mining to the end of 1917 is given by C. N. Gerry, of the United States Geological Survey, as $27,448,700, and the total production of silver as 7,053,400 fine ounces.[1]

Gold.—The mine production of gold in Washington in 1917 was $492,324, against $577,655 in 1916. Of the production in 1917 more than 70 per cent was derived from ores shipped directly to smelters, 28 per cent came from ores treated by amalgamation or cyanidation, and less than 1 per cent came from placers. Siliceous ores supplied about 97 per cent of all gold recovered and copper ores about 1 per cent. Ferry County alone produced $332,071 in 1917, against $399,376 in 1916. Nearly all the yield from Ferry County was, as usual, from the Republic district.

Silver.—The mine production of silver in Washington decreased from 335,121 ounces in 1916 to 282,320 ounces in 1917, of which Ferry County produced 98,080 ounces, mainly from siliceous ores, and Stevens County 161,013 ounces, mainly from copper ores.

WYOMING.

The total production of gold in Wyoming from 1867 to the end of 1917 is given by Charles W. Henderson as $1,235,100 and the output of silver for the same period as 68,575 ounces.[2]

The mine production of gold in Wyoming in 1917 was $3,762, against $20,566 in 1916, and that of silver 3,415 ounces in 1917, against 5,524 ounces in 1916. The Copper Mountain district, in Fremont County, produced most of the gold mainly from copper ores shipped to smelters. Copper ores shipped from mines in Albany, Lincoln, and Platte counties contained nearly all the remainder of the gold and silver reported in 1917.

PHILIPPINE ISLANDS.

The output of gold in the Philippine Islands from 1907 to 1917, inclusive, has been $7,759,522. The mine production of gold for 1917 was $1,408,161, against $1,514,200 in 1916, $1,320,900 in 1915, $1,371,514 in 1914, $868,362 in 1913, and $570,212 in 1912. The mine production of silver in the Philippine Islands in 1917 was 4,019 ounces and was recovered entirely from gold bullion refined.

NUMBER OF PRODUCING MINES.

The following table indicates the number of mines producing gold and silver in 1917 divided into placers and deep or lode mines. The placers are those in which the gold and the silver in natural alloy with the gold and, in a few placers, found also with platinum are recovered from gravels and sands, whether by hand washing, sluicing, hydraulicking, drifting (in frozen ground or ancient buried river channels), or by dredging. The deep mines are those producing gold and silver (from ores as distinguished from gravels) mainly from underground workings, including those whose ores are valuable chiefly for copper,

[1] U. S. Geol. Survey Mineral Resources, 1917, pt. 1, p. 493, 1918.
[2] Idem, p. 161.

Digitized by Google

lead, or zinc, but which contribute precious metals as by-products. In addition to producing mines here enumerated, many properties were being prospected and developed (though prospecting and development were less active than usual) without making any output in 1917, and many other mining claims were being held by assessment work only.

The enumeration of placer mines is less satisfactory than that of deep mines, because some of the operations are only temporary and individually small and because the production is frequently by transitory miners not regularly working placer ground. The unit, so far as possible is, however, as for deep mines, not the operator, but the mining claim or group of claims.

Number of producing gold and silver mines in 1917.[a]

State or Territory.	Number of mines.			State or Territory.	Number of mines.		
	Placer.	Deep.	Total.		Placer.	Deep.	Total.
Alabama		1	1	North Carolina	14	7	21
Alaska	810	40	850	Oregon	53	23	76
Arizona	32	452	484	South Carolina	2	1	3
California	249	241	490	South Dakota	7	23	30
Colorado	33	715	748	Tennessee[c]		7	7
Georgia	13	6	19	Texas		9	9
Idaho	112	247	359	Utah	3	331	334
Illinois[b]		2	2	Vermont and New Hampshire		3	3
Maryland and Pennsylvania		3	3	Virginia[c]		5	5
Michigan[b]		10	10	Washington	17	119	136
Missouri		4	4	Wyoming	1	16	17
Montana	99	518	617		1,552	3,811	5,363
Nevada	91	852	943				
New Mexico	16	176	192				

[a] Philippine Islands and Porto Rico not included.
[b] Number of mines contributing to production of silver.
[c] Number of mines contributing to production of gold and silver.

The table shows the number and distribution of mines producing gold and silver in the United States and Alaska. With the exception of (1) some of the Michigan copper mines, (2) all zinc mines in the Eastern and Central States and a few in the far West, and (3) all lead mines of the Central States (except a few in Illinois and southeastern Missouri), practically all mines producing copper, lead, and zinc in the United States and Alaska produce gold and silver also. The table, therefore, with these exceptions, is a table of mines producing these five metals. It also includes certain mines producing oxidized manganese iron fluxing ores of Colorado, Utah, and elsewhere, whose ores contain small quantities of precious metals, especially silver, and are smelted as flux.

Number of mines producing gold and silver, 1906–1917.

Year.	Placer.	Deep.	Total.	Year.	Placer.	Deep.	Total.
1906	2,316	2,114	4,430	1913	1,774	3,502	5,276
1907	2,586	2,604	5,190	1914	1,815	3,158	4,973
1908	2,599	2,864	5,463	1915	1,720	3,597	5,317
1909	2,187	3,183	5,370	1916	1,530	3,765	5,295
1910	2,026	3,299	5,325	1917	1,552	3,811	5,363
1911	2,146	3,553	5,699				
1912	2,044	3,567	5,611	Average	2,025	3,251	5,276

Digitized by Google

Comparison of the figures for 1917 shows a net total increase of 68 producing mines, following decrease in 1912, 1913, 1914, and 1916, and an increase of 344 mines in 1915. The total number of properties operated in 1917 was 87 in excess of the average for the last 12 years. The number of placer properties worked in 1917 showed an increase of 22, but the total was nearly 800 less than the number operated in 1906. This is a natural result due to the exhaustion of the rich gravels and to the acquisition of large areas of placer ground by dredge mining companies. The number of deep mines operated increased from 3,765 in 1916 to 3,811 in 1917, or 560 more than the average for 12 years. High prices for copper, lead, and zinc in 1917 resulted in more deep mines being operated than in any year for which data are available by the Survey.

In total number of operating mines Nevada ranked first with 943, followed in order by Alaska with 850, Colorado with 748, Montana with 617, California with 490, Arizona with 484, and Idaho with 359. In number of placers Alaska led with 810, followed by California with 249, and Idaho with 112; and in deep mines Nevada led with 852, followed by Colorado with 715, Montana with 518, Arizona with 452, Utah with 331, Idaho with 247, and California with 241.

ORE PRODUCTION, CLASSIFICATION, AND AVERAGE VALUE.

The best index of deep mining is, of course, the quantity, metallic content, and value of ore mined, rather than the number of mines or of operators. In the next following table are given the production of ore by classes of ore and by States and Territories from mines producing gold and silver and the average extraction value of precious metals per ton.

The classification adopted is necessarily arbitrary in part. An ore is generally understood to be worked at a profit for one or more metals. The complex nature of western ores, especially, and the gradations from one well-recognized class to another render essential some fixed measures for the terminology used. The dry or siliceous ores comprise gold and silver ores proper, as well as fluxing ores carrying considerable quantities of iron and manganese oxides and very small quantities of gold and silver, and precious metal bearing ores carrying copper, lead, or zinc in quantities too low to classify them as copper, lead, zinc, or mixed ores. The distinction beween gold and silver ores is not here made. The total number of silver mines and the total production of true silver ores are both very small. The copper ores include those containing 2.5 per cent or more of copper, or less than this percentage in the cases of the great disseminated copper deposits of the West and of the Lake Superior ores; in general, the lead ores are those containing 4.5 per cent or more of lead, and the zinc ores are those containing 25 per cent or more of zinc, both irrespective of their precious-metal content; but ores of lower grades in lead and especially in zinc are treated profitably in some places, and of course they are then classified as lead or zinc ores, as the case may be. The mixed ores are combinations of those enumerated.

Digitized by Google

Ore produced and average extraction value of gold and silver per ton in 1917.[a]

State or Territory.	Dry or siliceous ores.		Copper ores.		Lead ores.	
	Quantity (short tons).	Average value.	Quantity (short tons).	Average value.	Quantity (short tons).	Average value.
Alabama and Georgia	19,320	$0.33	39,290			
Alaska	3,414,664	1.37	659,951	$1.70		
Arizona	317,716	10.79	15,245,297	.41	82,285	$6.98
California	2,018,003	5.13	892,579	1.57	92,533	7.54
Colorado	1,996,590	9.13	33,233	9.17	103,081	13.18
Idaho	69,650	8.36	103,224	2.65	1,448,285	4.62
Maryland and Virginia [b]			15,490	.06		
Michigan [b]			3,240,000	.18		
Montana	444,232	6.76	4,844,537	1.63	28,923	14.42
Nevada	1,413,929	9.86	4,945,482	.26	66,614	8.10
New Hampshire and Vermont			5,851	.08		
New Mexico	221,662	7.27	4,188,027	.11	17,426	3.75
North Carolina and South Carolina	1,303	4.30	832	5.11	32	5.03
Oregon	99,397	7.90	43,041	1.76		
South Dakota	1,867,859	4.02	82	1.52	369	12.03
Tennessee			589,004	.15		
Texas	51,966	9.40	298	4.48	51	15.94
Utah	164,057	14.33	14,121,671	.27	638,071	10.55
Washington	65,639	8.83	75,006	1.78	16,407	.28
Wyoming	49	39.49	6,286	.73		
Total, 1917	12,166,026	5.56	49,049,181	.49	2,494,077	6.88
Percentage of tonnage	18.11		73.02		3.71	
Total, 1916	12,921,268	5.73	47,478,127	.51	2,373,579	5.95
Percentage of tonnage	19.46		71.52		3.58	

	Zinc ores.		Copper-lead and copper-lead-zinc ores.		Lead-zinc ores.		Total (short tons).
	Quantity (short tons).	Average value.	Quantity (short tons).	Average value.	Quantity (short tons).	Average value.	
Alabama and Georgia							58,610
Alaska			42	$133.33			4,074,657
Arizona	62,839	$2.86	12,985	6.42	49,071	$4.18	15,770,193
California	135	.17					3,003,250
Colorado	140,445	.19	2,976	45.47	412,371	2.25	2,688,706
Idaho	19,269	1.27	4	165.41	1,118,075	2.68	2,758,507
Maryland and Virginia [b]					9,317	.54	24,807
Michigan [b]							3,240,000
Montana	258,846	1.32	4,356	21.24	726,280	2.89	6,307,164
Nevada	18,393	.13	1,158	20.34	27,943	5.40	6,473,519
New Hampshire and Vermont					3,000	.03	8,851
New Mexico	135,129	.02	3,684	7.12	10,899	.82	4,576,827
North Carolina							2,167
Oregon							142,438
South Dakota							1,868,310
Tennessee [c]							589,004
Texas	40		27	2.34			52,382
Utah	6,535		6,443	12.23	421,704	3.57	15,358,481
Washington	114				14,953	.08	172,119
Wyoming							6,335
Total, 1917	641,755	.90	31,675	14.58	2,793,613	2.82	67,176,327
Percentage of tonnage	.95		.05		4.16		
Total, 1916	833,345	1.21	79,992	5.54	2,702,091	2.31	66,388,402
Percentage of tonnage	1.25		.12		4.07		

[a] Illinois, Missouri, the Philippine Islands, and Porto Rico not included; quantity of crude ore containing precious metals not known.
[b] Includes only copper ore yielding precious metals.
[c] Lead and zinc ores yielded no precious metals.

The total quantity of ore sold or treated from which gold or silver was produced increased from 66,388,402 short tons in 1916, the largest production recorded, to 67,176,327 short tons in 1917. The

Digitized by Google

total of such ores has increased more than 16,600,000 tons in two years. In 1917 the quantity of copper ores sold or treated increased more than 1,500,000 tons, and lead-zinc ore more than 91,000 tons; dry or siliceous ores decreased more than 750,000 tons; zinc ores, nearly 200,000 tons; copper-lead ores, 48,000 tons. Arizona, Utah, Nevada, and Montana led in quantity of ore, owing to the largely increased output from copper mines, the ore from Arizona and Utah being mainly from low-grade disseminated ores and that from Montana mainly from the Butte vein deposits. Nevada ore was mainly from Ely copper ores, but also from siliceous ores from Goldfield, Tonopah, and other districts. Alaska, New Mexico, California, Idaho, and Colorado come next, with an output mainly of dry or siliceous ores from many districts in Alaska, California, and Colorado, and of copper ores from the low-grade ore bodies in New Mexico.

The large production of lead and lead-zinc ores in Idaho ranked that State before South Dakota, which produced ores that were mainly dry or siliceous in character.

The average extraction values in gold and silver were comparatively high for the siliceous ores of Colorado, New Mexico, Nevada, Montana, Oregon, Utah, Idaho, Texas, and Washington, and low for the larger ore bodies of California, South Dakota, and Alaska. Some of the States produced comparatively small quantities of copper ore carrying high extraction values in gold and silver, but the copper ores of the important copper-producing States showed low extraction values. The average recovery in gold and silver from the copper ores of Arizona was $0.41 a ton, that of Tennessee $0.15 a ton, that of Montana $1.63 a ton, that of Nevada $0.26, that of New Mexico $0.11, that of Utah $0.27, that of California $1.57, and that of Michigan $0.18. The lead ores of Utah showed an average recovery in gold and silver of $10.55 a ton, and the lead ores of Idaho only $4.62 a ton. Idaho produced the largest quantity of gold and silver bearing lead ores, and also of lead-zinc ores. Utah yielded the next largest quantity of lead ore, but the gold and silver content of such ore was less than that of Montana ore of similar character. About 18.1 per cent of the output of ore considered as producing gold and silver was dry or siliceous ore, against 19.5 per cent in 1916; 73 per cent was copper ore, against 71.5 per cent in 1916; 3.71 per cent was lead ore; 4.16 per cent was lead-zinc ore; 0.95 per cent was zinc ore, and 0.05 per cent was copper-lead ore. The average precious-metal extraction value per ton of siliceous ores of the United States decreased from $5.73 to $5.56, that of zinc ores from $1.21 to $0.90, and that of copper-lead ores increased from $5.54 to $14.58. The average gold and silver value of copper ores per ton was 51 cents in 1916 and 49 cents in 1917, and that of lead-zinc ores increased from $2.31 to $2.82.

DISTRIBUTION OF MINE PRODUCTION OF GOLD IN 1917, BY SOURCES.

As shown by the following table, the great bulk of the domestic output of gold is obtained from dry or siliceous ore—normally gold quartz and gold-silver quartzose ores—and from placers, more than 38 per cent of the total production of gold coming from these sources alone. The total contribution of gold derived from the great copper,

Digitized by Google

lead, and zinc mines of the country is therefore relatively small, notwithstanding their recent enormous development and production of ore.

It is interesting to note, however, that the placer mines and dry or siliceous ores yielded 2 per cent less of the total gold than they did in 1915 and that the output of gold from placer mines, which had advanced from nearly 24 per cent of the total gold in 1910 to more than 25 per cent in 1914 and had declined to less than 23 per cent in 1915, increased to 25 per cent in 1916, and 26.3 per cent in 1917. This increase in percentage was due, however, not so much to increased output from placers as to smaller production from deep mines. The contribution of gold from dry or siliceous ores, which had gradually declined from about 69 per cent in 1910 to about 66 per cent in 1914 and had increased to nearly 68 per cent in 1915, decreased more than 4 per cent in 1916 and was only 62 per cent in 1917. The yield of gold from copper ores, which had increased from 6 per cent in 1914 to 7 per cent in 1915 and to 9 per cent in 1916, decreased to less than 9 per cent in 1917.

Mine production of gold in 1917, in fine ounces.[a]

State or Territory.	Placers.	Dry or siliceous ores.	Copper ores.	Lead ores.	Zinc ores.	Copper-lead and copper-lead-zinc ores.	Lead-zinc ores.	Total.
Alabama and Georgia	135.99	306.69						442.68
Alaska	474,558.75	221,505.73	12,830.16			154.81		709,049.45
Arizona	832.73	131,997.57	98,530.97	5,739.02	4,078.35	2,352.86	1,642.33	245,173.83
California	438,956.20	495,581.36	32,408.98	4,786.46				971,733.00
Colorado	31,977.24	692,605.90	7,455.00	19,220.70	522.63	1,239.89	7,879.86	760,901.22
Idaho	6,541.80	24,929.28	3,960.99	2,567.41			933.16	38,932.64
Maryland, New Hampshire, and Vermont			6.62					6.62
Montana	22,504.17	107,172.83	27,561.58	4,688.65	1,475.24	281.45	6,373.21	170,147.11
Nevada	14,153.75	268,671.85	49,419.80	3,939.81	8.22	263.74	207.09	336,664.26
New Mexico	589.16	39,496.75	10,876.11	367.20	.43	88.74	60.25	51,478.64
North Carolina	192.48	222.68	108.86	5.53				589.55
Oregon	35,186.33	34,554.41	2,424.99					72,165.73
South Carolina	7.94	44.45						52.39
South Dakota	44.70	356,168.17	.85	1.05				356,244.77
Tennessee			257.65					257.65
Texas			.06	1.00				1.06
Utah	5.42	20,394.61	94,844.85	27,115.49		92.25	19,853.05	162,305.67
Virginia							64.97	64.97
Washington	283.86	23,240.61	281.93	1.55			8.22	23,816.17
Wyoming	1.64	92.30	88.04					181.98
Total, 1917	1,026,062.16	2,416,985.19	341,117.42	68,463.87	6,084.87	4,473.74	37,022.14	3,900,209.39
Value	$21,210,587	$49,963,518	$7,051,523	$1,415,274	$125,786	$92,480	$765,316	$80,624,484
Percentage of total	26.31	61.97	8.75	1.75	0.16	0.11	0.95	
Total, 1916	1,106,900.45	2,796,041.63	400,849.30	71,921.71	8,302.30	4,452.36	28,538.82	4,417,006.57
Value	$22,881,663	$57,799,310	$8,286,290	$1,486,754	$171,624	$92,039	$589,950	$91,307,630
Percentage of total	25.06	63.30	9.07	1.03	.19	.10	.65	

[a] Philippine Islands and Porto Rico not included.

PLACERS.

GENERAL.

The total value of the production of gold from placers was $21,210,587 in 1917, against $22,881,663 in 1916. The placer production increased in California by 24,109 ounces in 1917, but decreased in Alaska, Oregon, Colorado, Nevada, Idaho, and Montana.

Digitized by Google

The placer production is derived chiefly from dredging, from drift mining (which is of decreasing importance in Alaska in frozen ground at no great depth, but of continued importance in California in ancient buried river channels, often at considerable depth), and from hydraulic and sluicing placers. In California, especially, hydraulic mining was of much importance in the past and had become a special branch of the industry in itself, but restrictive laws relative to the débris and to disturbance of navigable streams have in recent years greatly confined mining activity of this kind. Finally, there is a small annual output of gold from dry placers in the Southwest and also a production of gold and platinum from ocean-beach mining in California and Oregon.

Some interesting notes on beach mining in California and Oregon and on dry placers in California, by Charles G. Yale, and on dry placers in Arizona, Nevada, and New Mexico, by V. C. Heikes, were published in the Survey report on gold and silver for 1912, copies of which can still be had on application to the Director, United States Geological Survey, Washington, D. C.

DREDGING.

The production of gold by dredging in the United States and Alaska from the commercial beginning of the industry in 1896 to the end of 1917 has amounted in value according to best available data to $132,653,700, of which $95,193,985 came from California, $17,609,894 from Alaska, $8,509,188 from Montana, $4,750,919 from Colorado, and $3,691,502 from Idaho. Oregon produced more gold from dredging in 1916 and 1917 than Montana or Idaho and nearly as much as Colorado, and the total production from dredges in Oregon has been more than $2,500,000.

Brief details of dredging operations have been given in Mineral Resources in the mines reports on gold, silver, copper, lead, and zinc of the Western States and also in earlier reports of the Director of the Mint. A brief history of gold dredging in the United States was given in the gold and silver (general) report for the year 1914, and the production of gold obtained by dredging in the United States and Alaska from 1896 to the end of 1914 and the number of dredges operated was given by States for each year. Further information is to be found in reports of geological surveys or mining officials of different States. A comprehensive and very useful report is contained in Bulletin 57 of the California State Mining Bureau, "Gold dredging in California," by W. B. Winston and Charles Janin. Other valuable treatises are "Dredging for gold in California," by D'Arcy Weatherbe, published by the Mining and Scientific Press; and "The history and development of gold dredging in Montana," by Hennen Jennings, with a chapter on placer mining methods and costs, by Charles Janin, published as Bulletin 121 of the Bureau of Mines. The most recent valuable contribution is "Gold dredging in the United States," by Charles Janin, published as Bulletin 127 of the Bureau of Mines.

The gold recovered in the United States and Alaska by 109 gold dredges in 1917 was $12,550,425, against $12,786,614 by 113 dredges in 1916. Of the output in 1917, California produced $8,313,527 from 55 dredges, Alaska $2,500,000 from 36 dredges, Montana

Digitized by Google

$409,455 from 3 dredges, Colorado $647,270 from 6 dredges, and Idaho $59,446 from 4 dredges. Four dredges operating in Oregon produced $618,922.

Gold produced in the United States by dredges, 1896–1917.

Year.	Dredges.	California.	Alaska.	All other States.[a]	Total.
1896	2	$2,000	.....	$42,000	$44,000
1897	6	5,000	.....	113,556	118,556
1898	8	18,887	.....	168,813	187,700
1899	18	206,302	.....	227,876	434,178
1900	27	200,929	.....	319,108	520,037
1901	34	471,762	.....	268,251	740,013
1902	48	867,665	.....	501,857	1,369,522
1903	45	1,475,749	$20,000	420,315	1,916,064
1904	61	2,187,038	25,000	511,679	2,723,717
1905	68	3,276,141	40,000	371,235	3,687,376
1906	76	5,098,359	120,000	503,035	5,721,394
1907	79	5,065,437	250,000	340,265	5,655,702
1908	88	6,536,189	170,901	646,481	7,353,571
1909	96	7,382,950	424,993	975,656	8,783,599
1910	115	7,550,254	800,000	942,786	9,293,040
1911	119	7,666,461	1,500,000	1,159,908	10,326,369
1912	124	7,429,955	2,200,000	1,588,956	11,218,911
1913	116	8,090,394	2,200,000	1,936,642	12,226,936
1914	120	7,783,394	2,350,000	2,379,389	12,512,783
1915	114	7,796,465	2,330,000	2,356,660	12,483,125
1916	113	7,769,227	2,679,000	2,338,487	12,786,614
1917	109	8,313,527	2,500,000	1,736,898	12,550,425
	.....	95,193,985	17,609,894	19,849,853	132,653,732

[a] Other States that have produced gold by dredges are Colorado, which yielded, 1901–1917, $4,750,919 Idaho, 1897–1917, $3,691,502; Montana, 1896–1917, $8,509,188; and Oregon, New Mexico, Nevada, South Dakota, Wyoming, Alabama, Georgia, and North Carolina, a combined yield, 1902–1917, of $2,898,244.

DRY AND SILICEOUS ORES.

In 1917 dry and siliceous ores, including true gold, gold-silver, and silver ores, and precious metal ores not classed primarily as copper, lead, zinc, or mixed ores, produced $49,963,518 in gold, against $57,799,310 in 1916. The largest producers from this class of ore are in order of rank: Colorado, California, South Dakota, Nevada, and Alaska.

The siliceous ores are in part free-milling (amalgamating), as in Alaska, California, and Oregon; both amalgamating and concentrating, as in many States; simply concentrating ores, as in parts of Colorado and Arizona; all-sliming and cyaniding ores; and finally smelting ores. Tailings both from old dumps and from present millings are largely reworked by concentration and subsequent cyanidation.

The loss in tailings from gold mills is being constantly cut down, and the most serious loss remains in tailings from concentrating plants. The chlorination process is of decreasing relative importance, having been used in only a few plants in California in 1917. Smelting is mainly of concentrates and of siliceous and pyritic ores, which are also valuable as fluxes. Exact figures of relative output by methods will appear in detail by States in another table.

As most of the production of gold in the United States is derived from placer gravels and dry or siliceous ores, including true gold, gold-silver, and silver ores, the following table for certain States, prepared by V. C. Heikes, of the United States Geological Survey, is of special interest. The table shows the quantity of each class of ore treated and the average content in gold per ton for the period

Digitized by Google

1913 to 1917, inclusive, for Arizona, Idaho, Montana, Nevada, Utah, and Washington. None of the States have a large yield of gold from gold-silver ores, and Nevada, with a yield much less in 1917 than in 1913, was the only State that produced a large quantity of gold from silver ores. Arizona shows an increase both in quantity of gold ore treated and of gold recovered, though the average content per ton in 1917 was slightly less than in 1913. In Idaho the quantity of gold ore treated in 1917 was nearly double that in 1913, but the average recovery decreased from 0.410 ounce per ton in 1913 to 0.365 ounce per ton in 1917. In Montana nearly 180,000 tons more of gold ore was treated in 1917 than in 1913 and the average yield per ton of ore decreased from 0.369 ounce in 1913 to 0.252 ounce in 1917. In Nevada the quantity of gold ore treated in 1917 was 183,000 tons less than in 1913 and the average recovery of gold per ton decreased from 0.438 ounce to 0.292 ounce.

The yield of gold from gold ores in Utah has been comparatively small in recent years and although there was an increased quantity of gold recovered from such ores in 1917 compared with 1916, the yield was less than $100,000, which is less than one-half that for the year 1913. The quantity of gold ores treated in Washington in 1917 was larger than in 1913, but the average recovery per ton declined from 0.570 ounce in 1913 to 0.356 ounce in 1917.

Gold produced in six Western States during 1913–1917—total quantity of ore mined and gold produced, compared with quantity and content of gold ore, gold-silver ore, silver ore, and ounces of placer gold, and with number of producers in each class.

Year.	Total number of producers.	Total quantity of ore mined.	Total gold.[a]	Gold ore.			
				Number of producers.	Quantity.	Gold.	Average content.
Arizona:		*Short tons.*	*Fine ounces.*		*Short tons.*	*Fine ounces.*	
1913	438	7,931,862	194,656.69	116	210,228	120,351.91	0.572
1914	395	8,009,927	202,166.62	121	263,895	136,558.47	.517
1915	517	9,612,559	201,531.46	139	182,251	92,771.19	.509
1916	527	17,033,810	192,801.41	105	164,918	63,562.20	.385
1917	484	15,770,193	245,173.83	86	236,585	128,801.16	.544
Idaho:							
1913	384	2,451,592	65,043.04	76	36,729	15,074.89	.410
1914	384	2,235,349	55,743.24	84	37,098	13,407.04	.361
1915	412	2,408,846	57,069.49	102	51,786	21,681.77	.419
1916	418	2,718,045	53,977.30	75	69,443	25,068.38	.361
1917	359	2,758,507	38,932.64	70	67,784	24,721.63	.365
Montana:							
1913	558	5,960,118	168,994.77	182	229,520	84,748.32	.369
1914	505	5,128,956	199,203.94	183	315,804	116,964.96	.370
1915	643	6,129,924	242,077.93	225	466,818	150,169.29	.322
1916	513	7,860,425	220,130.15	150	498,082	131,175.61	.263
1917	617	6,307,164	170,147.11	137	411,118	103,835.48	.252
Nevada:							
1913	786	5,367,211	570,589.41	323	772,749	338,770.66	.438
1914	731	4,522,022	555,402.47	310	837,699	334,137.48	.399
1915	799	5,118,620	551,683.01	206	959,304	333,907.39	.348
1916	779	5,941,165	428,904.21	308	817,100	232,699.56	.285
1917	943	6,473,519	336,664.26	287	589,228	171,815.15	.292
Utah:							
1913	217	10,202,566	172,467.95	5	68,408	11,974.24	.175
1914	211	8,544,014	157,961.16	5	1,987	856.32	.430
1915	234	10,451,445	174,590.65	7	13,883	3,226.24	.232
1916	318	13,920,643	172,938.06	10	1,308	663.82	.508
1917	334	15,358,481	162,305.67	6	14,728	4,678.60	.318
Washington:							
1913	57	15,685	33,682.30	26	56,008	31,943.93	.570
1914	67	95,947	26,953.24	22	73,618	26,184.86	.356
1915	104	86,677	18,934.90	46	41,412	18,223.36	.440
1916	113	164,998	27,944.06	38	70,048	26,932.84	.384
1917	136	172,119	23,816.17	23	65,058	23,166.31	.356

Digitized by Google

Gold produced in six Western States during 1913–1917—Continued.

Year.	Gold-silver ore.		Silver ore.		Placers.	
	Quantity.	Gold.	Quantity.	Gold.	Number of producers.	Gold.
Arizona:	*Short tons.*	*Fine ounces.*	*Short tons.*	*Fine ounces.*		*Fine ounces.*
1913	1,261	406.82	32,216	1,858.40	36	1,484.67
1914	58	46.78	128,759	8,230.65	57	1,458.02
1915	14,349	2,338.97	144,198	9,189.84	49	1,705.12
1916	1,470	994.00	169,916	8,858.47	23	660.84
1917	1	3.62	80,817	3,192.79	32	832.73
Idaho:						
1913	23,890	7,238.56	206	27.82	235	33,574.81
1914	44	92.42	1,100	176.56	208	33,884.46
1915	119	90.81	397	162.87	186	28,294.06
1916	447	227.19	1,793	201.15	162	21,724.87
1917	.....	.....	1,866	207.64	112	6,541.80
Montana:						
1913	13,586	3,763.07	41,382	4,237.81	152	38,748.47
1914	427	451.46	25,854	4,182.65	147	45,579.75
1915	1,025	125.64	25,657	4,760.58	161	45,219.87
1916	999	176.45	24,761	4,075.20	120	34,982.82
1917	7	2.20	33,097	3,335.15	99	22,594.17
Nevada:						
1913	72,909	27,115.32	697,775	144,961.52	64	14,775.75
1914	6,878	3,929.80	676,573	146,181.17	111	18,250.05
1915	16,558	5,372.05	721,753	127,079.12	103	19,123.55
1916	13,330	2,681.38	721,211	116,039.39	65	17,139.89
1917	17,614	3,099.45	807,087	93,757.16	91	14,153.75
Utah:						
1913	82,165	16,425.10	73,294	4,172.90	7	92.88
1914	77,653	11,901.80	69,379	5,508.11	7	59.55
1915	11,135	1,534.16	36,958	4,488.27	6	46.34
1916	4,337	1,130.41	83,718	7,328.18	8	60.47
1917	25,318	4,864.68	124,011	10,851.33	3	5.42
Washington:						
1913	4	58.00	120	23.00	12	200.00
1914	.....	.....	274	269.00	17	278.45
1915	.....	.....	748	54.36	31	346.00
1916	.....	.....	428	46.19	23	400.40
1917	48	30.89	533	43.41	17	283.86

[a] Includes placer production given in last column.

Nearly all the siliceous ore in three of the largest gold-producing States—Alaska, California, and South Dakota—yields only small values in silver and is classed as gold ore. The siliceous ores from Colorado include some silver and gold-silver ores, but the great bulk of the siliceous ore is purely gold ore. The quantity of siliceous ore treated each year in these States and the average recovery in gold per ton is as follows:

Siliceous ore treated and gold recovered per ton of ore treated in 1913–1917.

Year.	Alaska.		California.		South Dakota.		Colorado.	
	Ore treated.	Recovery per ton.	Ore treated.	Recovery per ton.	Ore treated.	Recovery per ton.	Ore treated.	Recovery per ton.
	Short tons.	*Ounces.*	*Short tons.*	*Ounces.*	*Short tons.*	*Ounces.*	*Short tons.*	*Ounces.*
1913	1,614,506	0.144	2,031,429	0.267	1,899,139	0.187	2,161,458	0.378
1914	1,738,127	.135	2,050,797	.264	2,019,255	.175	2,157,762	.414
1915	3,020,607	.097	2,368,352	.272	1,889,970	.189	2,183,431	.464
1916	3,548,798	.081	2,192,078	.262	1,870,721	.193	2,057,452	.412
1917	3,414,664	.065	2,018,003	.246	1,867,859	.191	1,996,590	.347

COPPER ORES.

The production of gold as a by-product of the smelting of copper ores sold or treated in 1917 was $7,051,523, against $8,286,290 in 1916, a decrease from 9.07 per cent of the total gold yield in 1916 to 8.75 per cent in 1917. The largest production was in Arizona, followed by Utah, Nevada, California, and Montana, in the order given. The

Digitized by Google

largest decrease was in Montana and California, caused by a smaller output of copper in those States. It is probable that the increase in the production of copper in Montana and Arizona in 1918 will result in a recovery of gold from copper ores equal to the output from that source in 1916.

LEAD ORES.

The production of gold in lead ores sold or treated in 1917, chiefly from Utah and Colorado, was $1,415,274, against $1,486,754 in 1916, or 1.75 per cent of the total domestic output of gold in 1917.

LEAD-ZINC, ZINC, AND OTHER ORES.

The production of gold from lead-zinc ores was $765,316 in 1917, against $589,950 in 1916; from zinc ores $125,786 in 1917, against $171,624 in 1916; and from copper-lead and copper-lead-zinc ores $92,480 in 1917, against $92,039 in 1916.

DISTRIBUTION OF MINE PRODUCTION OF SILVER IN 1917, BY SOURCES.

The mine production of silver from the three most important sources of silver—dry or siliceous ores, copper ores, and lead ores—was 86.18 per cent of the total output in 1917. The output from dry and siliceous ores decreased 0.77 per cent in 1917, following a decrease of 4.35 per cent in 1916; that from lead ores increased 2.65 per cent; that from lead-zinc ores increased about 1.35 per cent; and that from copper ores decreased 2.37 per cent. The combined output from placers, zinc ores, copper-lead ores, and copper-lead-zinc ores was about 1.6 per cent of the total production of silver.

Mine production of silver in 1917, in fine ounces.[a]

State or territory.	Placers.	Dry or siliceous ores.	Copper ores.	Lead ores.	Zinc ores.	Copper-lead and copper-lead-zinc ores.	Lead-zinc ores.	Total.
Alabama and Georgia	9	48	.....	.....	.....	.....	.....	57
Alaska	64,410	131,631	1,040,185	.....	.....	2,924	.....	1,239,150
Arizona	227	848,500	5,214,411	553,544	116,179	61,019	190,033	6,983,913
California	27,257	139,492	882,480	726,174	28	.....	(b)	1,775,431
Colorado	8,302	4,867,628	182,791	1,167,167	19,525	133,128	925,812	7,304,353
Idaho	1,194	81,514	232,840	8,063,768	29,684	803	3,619,535	12,029,338
Illinois c	.....	.....	.....	7,186	.....	.....	.....	7,186
Maryland, New Hampshire and Vermont	.....	.....	1,589	.....	.....	.....	120	1,709
Michigan	.....	.....	688,551	.....	.....	.....	.....	688,551
Missouri	.....	.....	20	61,566	.....	.....	.....	61,586
Montana	3,551	954,477	8,911,389	388,435	378,239	105,227	2,386,824	13,128,142
Nevada	6,278	10,176,717	327,751	556,706	2,620	21,967	177,930	11,269,969
New Mexico	92	966,006	315,877	70,021	3,381	29,600	9,388	1,394,365
North Carolina	34	97	922	57	.....	.....	.....	1,110
Oregon	7,160	87,121	31,375	.....	.....	.....	.....	125,656
South Carolina	.....	3	.....	.....	.....	.....	.....	3
South Dakota	4	182,023	130	4,608	.....	.....	.....	186,765
Tennessee	.....	.....	99,053	.....	.....	.....	.....	99,053
Texas	.....	593,128	1,621	962	.....	78	.....	595,789
Utah	.....	2,340,537	2,225,119	7,490,650	.....	93,296	1,329,531	13,479,133
Virginia	.....	.....	.....	.....	.....	.....	4,518	4,518
Washington	86	120,510	154,747	5,630	.....	.....	1,347	282,320
Wyoming	.....	33	3,382	.....	.....	.....	.....	3,415
Total, 1917	118,604	21,489,465	20,314,233	19,096,474	549,656	448,042	8,645,038	70,661,512
Value	$97,730	$17,707,319	$16,738,928	$15,735,495	$452,916	$369,187	$7,123,511	$58,225,086
Percentage of total	0.17	30.41	28.75	27.02	0.78	0.64	12.23	100.00
Total, 1916	126,351	24,593,659	24,541,234	19,216,586	1,274,292	533,273	8,572,141	78,857,583
Value	$83,139	$16,182,625	$16,148,132	$12,644,514	$838,484	$350,894	$5,640,469	$51,888,257
Percentage of total	0.16	31.18	31.12	24.37	1.61	0.68	10.88	100

[a] Philippine Islands and Porto Rico not included. [b] Included with lead ores. [c] Fluorspar-lead ore.

Digitized by Google

PLACERS.

The output of silver from the refining of placer gold was 118,604 fine ounces in 1917, against 126,351 ounces in 1916. Seventy-eight per cent of the production was from Alaska and California.

DRY AND SILICEOUS ORES.

The mine production of silver from dry and siliceous ores in 1917 was 21,489,465 fine ounces, against 24,593,656 ounces in 1916. About 48 per cent of this was from Nevada (chiefly from Tonopah district) and 23 per cent was from Colorado (mainly from the Leadville, Upper San Miguel, and Sneffels districts). The quantity of silver from siliceous ores mined in Utah increased from 1,153,993 ounces in 1916 to 2,340,537 ounces in 1917. There were decreases in all the other States, especially in Nevada, where the production in 1917 was 2,575,194 ounces less than in 1916. New Mexico and Montana also each produced more than 900,000 ounces of silver from this source, and Arizona nearly 850,000 ounces. Ninety-nine per cent of the silver produced in Texas was from siliceous silver ores.

A large part of the silver from gold-silver siliceous ores is obtained with the gold by amalgamation and cyanidation in the mills, and the silver is recovered by refining the mill bullion. The remainder is produced by smelting the richer ores and refining the copper or lead bullion produced.

COPPER ORES.

The mine production of silver from domestic copper ores in 1917 was 20,314,233 fine ounces, against 24,541,234 ounces in 1916, a decrease of about 12 per cent. The decrease in production of silver from copper ores mined in Alaska was 167,000 ounces; Arizona, 130,000 ounces; Utah, 408,000 ounces; Montana, 2,300,000 ounces; and California, 1,000,000 ounces. None of the larger copper-producing States had any increase in silver recovered from copper ores.

The production of silver from copper ores is from the electrolytic refining of Lake and blister copper produced by smelting. The copper ores are mainly sulphides (except the Lake ores of Michigan, which are native metal in amygdaloid and conglomerate matrix), and a greater tonnage contains chalcocite than chalcopyrite or cupriferous pyrite. The great disseminated copper deposits of Utah, Arizona, and New Mexico are of increasing importance and the lode deposits of Butte, Mont., have long been famous. The silver tenor of the extensive disseminated deposits of the Santa Rita district, N. Mex., and of Ely, Nev., are notably low, but similar deposits elsewhere add large quantities of silver.

In Michigan 3,240,000 tons of copper ore yielded 688,551 ounces of silver, or slightly more than 0.2 ounce per ton.

In output of silver from copper ores Montana continued to lead with 8,911,389 ounces in 1917, against 11,226,034 ounces in 1916; Arizona followed with 5,214,411 ounces in 1917, against 5,347,893 ounces in 1916; Utah ranked third with 2,225,119 ounces in 1917, against 2,633,402 ounces in 1916; and California produced 882,480 ounces in 1917, against 1,969,783 ounces in 1916. The production of Montana is mainly from Butte, that of Arizona has been chiefly from Bisbee and Jerome, that of Utah from Tintic and Bingham, and that of California from Shasta and Calaveras counties. Of these dis-

Digitized by Google

tricts Bisbee well represents the disseminated type; Bingham produces from both lode and disseminated deposits; and the remainder produce silver chiefly from copper ore mined from deep lodes.

LEAD ORES.

The mine production of silver from argentiferous lead ores in 1917 was 19,096,474 fine ounces, against 19,216,586 ounces in 1916. The output from Idaho decreased from 8,227,936 ounces in 1916 to 8,063,768 ounces in 1917, that of Utah decreased from 8,118,264 ounces to 7,490,650 ounces, and that of Colorado was about the same as in 1917. The yield in Idaho is mainly from the silver-lead ores of the Coeur d'Alene, that in Utah is chiefly from the Park City and Tintic districts, and that in Colorado from Aspen and Leadville. There was an increase in the production of silver from lead ores in California from 325,468 ounces in 1916 to 726,174 ounces in 1917. There was also a small increase in both Nevada and Arizona. Most of the output is from the desilverization of lead bullion from smelting of western ores and concentrates.

ZINC, LEAD-ZINC, AND MIXED ORES.

Argentiferous zinc ores produced 549,656 ounces of silver in 1917, against 1,274,292 ounces in 1916, mainly as refinery by-products from the smelting of zinc concentrates from Montana, Idaho, California, and Arizona.

Lead-zinc ores produced 8,645,038 fine ounces of silver in 1917, against 8,572,141 ounces in 1916, chiefly from concentrates from the Coeur d'Alene in Idaho, the Butte district in Montana, and the Park City region in Utah. The output from Idaho decreased from 3,718,529 ounces in 1916 to 3,619,535 ounces in 1917.

Copper-lead and copper-lead-zinc ores produced 448,042 ounces of silver in 1917, against 533,273 ounces in 1916. The output was mainly from Utah, Montana, Colorado, and Arizona.

SILVER PRODUCTION, BY SOURCES, 1905–1917.

Production of silver in the United States, by sources, as reported by mines, 1905–1917, in fine ounces.[a]

Year.	Placers.	Dry or siliceous ores.	Copper ores.	Lead ores.	Zinc ores.	Copper-lead and copper-lead-zinc ores.	Lead-zinc ores.	Total.
1905.....	112,826	17,187,899	15,762,947	16,070,203	939,252	5,416,723	782,656	56,272,496
1906.....	171,058	16,792,799	15,880,870	15,328,653	98,423	6,815,078	2,274,972	57,362,453
1907.....	126,808	19,038,042	13,955,436	17,318,811	93,419	489,825	1,474,725	52,497,066
1908.....	159,285	19,862,038	14,945,189	14,049,481	37,605	1,099,283	722,906	50,875,787
1909.....	152,040	19,826,890	18,300,705	17,027,737	313,948	549,923	1,141,434	57,312,677
1910.....	159,381	23,125,042	16,024,543	15,028,076	755,369	535,987	1,968,311	57,596,709
1911.....	170,064	25,205,749	16,759,638	15,596,638	630,573	285,006	2,460,152	61,107,840
1912.....	163,955	26,363,436	18,744,661	16,632,377	664,421	654,396	2,810,939	66,034,385
1913.....	123,739	28,010,875	18,250,253	18,629,246	86,432	752,563	5,334,120	71,187,228
1914.....	152,128	27,812,335	14,829,828	19,302,081	145,264	248,856	7,132,747	69,623,249
1915.....	154,968	25,709,505	18,781,365	19,828,533	1,136,220	234,047	6,509,092	72,353,730
1916.....	126,351	24,593,656	24,541,234	19,216,586	1,274,292	533,273	8,572,141	78,857,533
1917.....	118,604	21,489,455	20,314,233	19,096,474	549,656	448,042	8,645,038	70,661,512
	1,891,227	295,017,721	227,090,902	223,124,896	6,724,874	18,063,812	49,829,233	821,742,665

[a] Philippine Islands excluded.

This table shows that the production of silver as reported by the mines has increased from 50,875,787 fine ounces in 1908 to 70,661,512

Digitized by Google

ounces in 1917. The production from siliceous, copper, lead, zinc, and lead-zinc ores all show an increase. The recoveries from dry or siliceous ores reached its apex in 1913 when the yield from Tonopah mines was at its zenith, and the production in 1917 was about 6,500,000 ounces less than it was in 1913. The yield of silver from copper ores has increased from 13,955,436 ounces in 1907 to 20,314,233 ounces in 1917, or about 46 per cent. The total yield of silver from zinc ores has been comparatively small, though the output from that kind of ore increased from 37,605 ounces in 1908 to nearly 550,000 ounces in 1917. The combined production of silver from lead and lead-zinc ore increased from 14,772,387 ounces in 1908 to 27,788,727, or 88 per cent.

The production of silver from siliceous ores will probably continue to decrease in 1918 and that from copper ores and lead ores may equal that of 1916. It is not expected that the production of silver in the United States in 1918 will show any increase, but the gain from copper and lead ores may nearly equal the loss in the recoveries from siliceous ores and zinc and zinc-lead ores.

DISTRIBUTION OF PRODUCTION OF GOLD AND SILVER BY METHODS OF TREATMENT.

SUMMARY OF DISTRIBUTION.

In the following table is given a summary of the distribution of the production of gold and silver in the United States in 1917, showing (1) total crude ore, tailings, and slags sold or treated; (2) crude ore treated in gold and silver mills; (3) crude ore concentrated and resulting concentrates; (4) crude ore shipped to smelters; (5) old tailings and slags treated. The last four items include recoverable gold and silver content in fine ounces.

Distribution of gold and silver produced in 1917, by States.[a]

State or Territory.	Total quantity of ore, tailings, and slag treated or sold in 1917.	Ore to gold and silver mills.			Crude ore—			
		Quantity.	Gold in bullion.	Silver in bullion.	To concentrating mills.	Concentrates produced from all sources.		
					Quantity.	Quantity.	Gold.	Silver.
	Short tons.	*Short tons.*	*Fine ounces.*	*Fine ounces.*	*Short tons.*	*Short tons.*	*Fine ounces.*	*Fine ounces.*
Alaska	4,074,657	3,101,131	117,689	29,290	769,776	75,156	103,813	574,976
Arizona	15,770,193	243,769	120,636	254,353	10,943,997	783,532	26,241	1,271,890
California	3,003,250	1,809,017	376,089	83,142	422,169	74,409	97,211	111,561
Colorado	2,688,706	1,486,384	553,554	400,109	700,014	280,563	87,650	2,600,743
Idaho	2,758,507	67,677	22,721	20,877	2,375,891	419,182	4,010	8,044,469
Montana	6,307,164	327,748	66,908	235,068	5,086,706	1,793,899	32,675	10,053,994
Nevada	6,473,519	1,125,255	248,057	9,241,543	4,524,310	627,416	50,466	713,459
New Mexico	4,576,827	123,824	26,271	657,437	4,215,988	360,614	10,168	196,713
Oregon	142,438	93,433	32,719	57,269	41,276	7,755	2,256	53,790
South Dakota	1,868,310	1,867,583	355,578	181,051				
Texas	52,382	51,966		593,128				
Utah	15,358,481	190	141	26	13,718,660	813,287	73,674	2,469,804
Washington	172,119	10,986	6,734	461	73,673	6,076	61	122,556
Wyoming	6,335	20	15	6				
Eastern or Appalachian States[b]	682,994	20,214	416	67	33,347	2,770	72	5,976
Total	63,935,882	10,329,197	1,927,528	11,753,827	42,905,807	5,244,959	488,297	26,219,931
Total, 1916	64,409,377	11,249,436	2,118,252	14,724,426	43,371,329	5,496,226	547,172	29,566,150

[a] Exclusive of small quantity of silver from copper ores in Michigan and Missouri and from lead ores in Illinois and Missouri, and of gold and silver from the Philippine Islands and Porto Rico.

[b] Copper, zinc, and zinc-lead ores containing no silver excluded.

Digitized by Google

Distribution of gold and silver produced in 1917, by States—Continued.

State or Territory.	Crude ore to smelters.			Old tailings and slag treated.		
	Quantity.	Gold.	Silver.	Quantity	Gold.	Silver.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Short tons.*	*Fine ounces.*	*Fine ounces.*
Alaska	203,750	12,989	570,474			
Arizona	3,782,494	96,928	5,312,292	799,933	[a] 541	[a] 145,151
California	566,069	39,653	1,524,109	205,995	19,824	29,362
Colorado	502,308	87,720	4,295,199			
Idaho	284,567	5,636	3,926,092	30,372	24	36,706
Montana	503,023	47,631	2,580,608	389,687	[b] 339	[b] 254,921
Nevada	658,447	23,105	1,238,946	165,607	883	69,743
New Mexico	237,015	14,451	540,123			
Oregon	6,720	1,746	2,457	1,009	258	4,980
South Dakota	727	622	5,710			
Texas	416	1	2,661			
Utah	1,178,002	87,030	10,498,129	461,629	1,455	511,174
Washington	87,416	16,704	159,174	44	33	43
Wyoming	6,315	165	3,409			
Eastern or Appalachian States	628,600	367	99,369	833	222	995
Total, 1916	8,645,869	434,743	30,758,752	2,055,009	23,579	1,053,075
	8,894,609	634,366	33,161,551	894,030	10,305	427,291

[a] Gold and silver from 22,709 tons of old tailings, cyanided included, under recoveries at gold and silver mills.
[b] Gold and silver from 9,862 tons of old tailings, cyanided included, under recoveries at gold and silver mills.

The first item consists of all classes of ores, tailings, and slag from which gold and silver were produced in 1917. The grand total is 63,935,882 short tons in 1917, against 64,409,377 tons in 1916. This takes no account of placer gravel but represents output of mines producing ore only. The greatest output was from Arizona, Utah, Montana, Nevada, and Alaska, all notable for large yield of copper ores.

In reference to the second item many gold and silver mills employ concentrating apparatus, and the concentrates obtained are combined in the table with those from straight concentrating mills under the heading "Concentrates produced." The gold and silver recovery under this item is mainly by amalgamation and cyanidation, as is shown in detail in the last table of this report. The total quantity of crude ore treated in gold and silver mills in 1917 was 10,329,197 short tons, against 11,249,436 tons in 1916. The greatest quantities milled were in Alaska, California, South Dakota, Colorado, and Nevada. The total recovery of gold from the mills was 1,927,528 fine ounces in 1917, against 2,118,252 ounces in 1916, and the production was, as usual, chiefly from Colorado, California, South Dakota, and Nevada, in the order named. The total silver recovery in mills was 11,753,827 fine ounces, against 14,724,426 ounces in 1916, and came very largely from Nevada (from Tonopah and Goldfield chiefly), but also in considerable part from New Mexico, Texas, Arizona, and Colorado.

Under the third item is given the quantity of ore treated by concentration only, including the large quantities of copper, lead, zinc, and mixed ores, whose concentrates are smelted primarily for these metals, the gold and silver being recovered in refining the copper and lead bullion and smelting the zinc residues. Examples are the copper ores of the disseminated deposits of Bingham, Utah, and of New Mexico and Nevada; the copper ores of Butte, Mont., and the lead and lead-zinc ores of Coeur d'Alene, Idaho, Butte, Mont.,

Digitized by Google

and Leadville, Colo. The quantity of concentrates produced and the recoverable gold and silver content, however, as already stated, represent not only the concentrates from these straight concentrating mills but also those from gold and silver mills, which form, however, a very small part of the total quantity of concentrates and are mainly derived from Alaska, California, and Colorado ores. These concentrates are mainly smelted but are also treated in gold and silver mills by the processes named.

The ore treated in straight concentration mills decreased from 43,371,329 short tons in 1916 to 42,905,807 tons in 1917, mainly because of less activity at copper mines in Montana and Arizona. Utah ranked first in quantity of ore concentrated, followed by Arizona, Montana, Nevada, New Mexico, and Idaho. These quantities, with the exception of those of Montana and Idaho, represent largely low-grade disseminated copper ores milled. The total quantity of gold and silver bearing concentrates from all classes of milling ore decreased from 5,496,226 short tons in 1916 to 5,244,959 tons in 1917. Montana mills produced the largest quantity of concentrates, or 34 per cent, followed by those of Utah, Arizona, Nevada, and Idaho. The total recoverable gold content of all concentrates was 488,297 ounces in 1917, against 547,172 ounces in 1916, and came mainly from Alaska, California, Colorado, Utah, and Nevada, in the order named. The total recoverable silver from concentrates produced was 26,219,931 fine ounces in 1917, against 29,566,150 ounces in 1916, and came chiefly from Montana, Idaho, Colorado, Utah, and Arizona. The large decrease was due to the decrease in the silver in concentrates derived from ores mined in Montana and Nevada.

The fourth item covers the quantity and the recoverable precious-metal content of crude ores shipped from the mines direct to the smelters, and in general includes the richer gold, silver, copper, lead, and mixed ores from which the gold and silver is eventually recovered by refining the copper or lead bullion that collects the precious metals in the smelting. The total quantity shipped of this class of ore decreased from 8,894,609 short tons in 1916 to 8,645,869 tons in 1917. The output was notably from Arizona, followed by Utah, Nevada, California, Eastern or Appalachian States, Montana, and Colorado, in the order named. The total yield of gold from crude ores smelted decreased from 634,366 fine ounces in 1916 to 434,743 ounces in 1917, and came chiefly from Arizona, Colorado, Utah, Montana, California, and Nevada, in the order given. The total recoverable silver output decreased from 33,161,551 fine ounces in 1916 to 30,758,752 ounces in 1917, and was notably from Utah, Arizona, Colorado, Idaho, Montana, California, and New Mexico.

Under the fifth item is given the quantity of old materials, principally tailings and slags, retreated, and their recoverable contents. These are partly smelted, often for their fluxing as well as their metal value; but considerable quantities of old tailings are now concentrated and cyanided, and impounding of mill tailings for future treatment as well as because of legal requirements has now become a general practice. The total quantity of all old material treated as shown in the table increased from 894,030 short tons in 1916 to 2,055,009 tons in 1917. The increase in quantity of old

Digitized by Google

material treated was due mainly to the high prices of copper and lead. Most of the gold and silver derived from old tailings is included under recoveries by amalgamation and cyanidation at gold and silver mills.

From this table the output of ore from the Central States, producing small quantities of silver and no gold, has been omitted. The output of zinc ore from the Eastern States is also omitted, as this zinc ore is reported to produce neither silver nor gold.

PERCENTAGE OF OUTPUT OF GOLD AND SILVER PRODUCED BY DIFFERENT PROCESSES.

Percentage of output of gold and silver produced by different processes, 1912–1917.

Process.	Percentage of total output.											
	Gold.						Silver.					
	1912	1913	1914	1915	1916	1917	1912	1913	1914	1915	1916	1917
Placers	24.8	24.9	25.2	22.7	25.0	25.8	0.2	0.2	0.2	0.2	0.2	0.2
Gold and silver mills:												
By amalgamation	22.3	21.5	20.9	22.8	21.5	20.9	1.2	.6	.4	.4	.4	.4
By cyanidation	30.9	31.2	31.4	30.4	28.1	29.5	17.8	19.7	22.1	22.1	18.3	16.3
By chlorination	.4	.3	.4	.5	.5	.2	.....	.....	.....	.....	.....	.....
Total milling	53.6	53.0	52.7	53.7	50.1	50.6	19.0	20.3	22.5	22.5	18.7	16.7
Smelting [a]	21.6	22.1	22.1	23.6	24.9	23.6	80.8	79.5	77.3	77.3	81.1	83.1
Total [b]	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0

[a] Both crude ore and concentrates. [b] Philippine Islands and Porto Rico excluded.

The placers produced about 25.8 per cent of the total output of gold, an increase of 0.8 per cent. The dredges produced 1.8 per cent less gold in 1917 than in 1916, and the combined placer yield from hydraulic, drift, and other surface methods was $1,300,000 less than in 1916. The decrease from placers was largely due to a smaller output from Alaska and Idaho. The percentage of output of silver credited to the placers is insignificant.

In the mills the amalgamation process showed a loss of 0.6 per cent of the total recovery of gold in 1917. This was due to the decrease in mining and milling in Colorado, California, and Nevada, which produce ores more amenable to treatment by amalgamation. The gold recovered by cyanidation showed an increase of 1.3 per cent following a decrease of 2.3 per cent in 1916. The chlorination process was used in only a few mills in California and the output of gold was only 0.2 per cent of the total recovery of gold, compared with 0.5 per cent in 1916. None of the Colorado plants used chlorination in 1917, and the total recovery of gold by that process in California mills amounted to $188,129.

GOLD AND SILVER PRODUCED AT MILLS, BY STATES.

Large quantities of concentrates from sulphide ores are now smelted and the increased application of the flotation process has resulted in decreased yield of gold and silver from cyanidation. Part

Digitized by Google

of the flotation concentrates are cyanided and not shipped to smelters. This method was adopted by the Goldfield Consolidated Mines Co., which had retained part of the cyanide plant for treatment of tailings and the flotation concentrates.

It is stated in the annual report of the Goldfield Consolidated Mines Co. for 1917 that the treatment by cyanidation of concentrates recovered by flotation was not profitable in that such flotation concentrates must be subjected to a chloridizing roast prior to the treatment by cyanide. The flotation concentrates are now shipped to smelters.

The smelters, which had for three years been producing each year a slightly greater proportion of gold and a smaller proportion of silver, are to be credited in 1917 with about 23.6 per cent of the total output of gold and 83.1 per cent of the silver. The decrease in the per cent of gold in 1917 was due to the smaller quantity of gold recovered from crude ore smelted.

The bulk of the production of gold remains mainly from the gold mills, but in decreasing proportion. As shown by the table above the proportion of gold recovered by amalgamation, cyanidation, and chlorination has decreased from 53.6 per cent in 1912 to 50.6 per cent in 1917.

The following table shows in greater detail the ore treated and the output of gold and silver mills, by States, in 1917:

Gold and silver produced at mills in 1917, by States.[a]

State.	Ore and tailings treated.	Bullion recovered.				Percentage of gold and silver from all sources.			
		Amalgamation.		Cyanidation.		Amalgamation.		Cyanidation.	
		Gold.	Silver.	Gold.	Silver.	Gold.	Silver.	Gold.	Silver.
	Short tons.	*Fine oz.*	*Fine oz.*	*Fine oz.*	*Fine oz.*				
Alaska	3,414,654	115,341	29,296	47,315	4,640	16.3	2.3	6.7	0.3
Arizona	266,478	1,875	1,701	118,762	252,652	.8	.....	48.4	3.6
California[b]	2,015,012	376,089	83,142	22,650	29,937	38.7	4.7	2.3	1.7
Colorado	1,493,257	29,107	19,457	524,447	380,652	3.8	.3	68.4	5.2
Idaho	67,677	21,569	11,102	1,152	9,775	55.4	.1	3.0	.1
Montana	337,610	2,845	1,246	64,062	233,822	1.7	.....	37.6	.5
Nevada	1,271,022	21,740	21,191	226,317	9,220,352	6.4	.2	67.2	81.8
New Mexico	123,824	14,867	2,256	11,404	655,181	28.8	.1	22.1	3.8
Oregon	135,718	10,039	57,160	25,194	36,237	13.9	45.5	34.9	28.8
South Dakota	[c]1,867,583	228,018	61,759	127,560	119,292	64.0	33.1	35.8	63.3
Texas	51,966	.....	.....	.....	593,128	.....	.....	.....	99.5
Utah	190	141	26	.....	.....	.....	.....	.....	.....
Washington	10,986	6,721	411	13	50	28.2	.2	.....	.....
Wyoming	20	15	6	.....	.....	8.2	.2	.....	.....
Appalachian States	20,214	314	38	102	29	22.2	.....	7.2	.....
Total, 1917	11,076,211	828,681	288,791	1,169,478	11,535,747	20.9	.4	29.4	16.3
Value	.....	$17,130,357	$237,976	$24,175,256	$9,505,455	.....	.....	.....	.....
Total, 1916	11,393,838	964,589	348,177	1,260,172	14,432,378	21.5	.4	28.1	18.3
Value	.....	$19,939,824	$229,097	$26,050,067	$9,496,505	.....	.....	.....	.....

[a] Porto Rico and Philippine Islands excluded.

[b] Recovered by chlorination, 9,100.74 ounces of gold and 283 ounces of silver in California. Value of gold recovered by chlorination was $188,129; that of silver, $233.

[c] Part of ore amalgamated followed by cyanidation of new tailings. Total ore and new tailings cyanided, 1,809,417 tons.

Digitized by Google

Figures corresponding to those in this table were collected and compiled for the entire United States by the Survey for the first time in 1911, and comparison for seven years can therefore now be made.

The total quantity of crude ore treated and old tailings re-treated in gold and silver mills was 11,076,211 short tons in 1917 against 11,393,838 tons in 1916, 11,878,287 tons in 1915, 9,849,085 tons in 1914, 9,401,856 tons in 1913, 9,677,360 tons in 1912, and 9,670,483 tons in 1911. In 1917 ores from Alaska and California treated at gold and silver mills amounted to about 50 per cent of the total quantity.

The great bulk of the ore treated, as shown, was milled in Alaska, California, South Dakota, Nevada, and Colorado, in the order named, and here the famous mills of the Homestake, Mother Lode, Grass Valley, Treadwell, Cripple Creek, Tonopah, and Goldfield mines are especially in evidence. Large numbers of smaller mills, however, mark the wide distribution of gold mining in these regions and in many other scattered districts.

The total yield of gold by amalgamation in the United States in 1917 was 828,681 fine ounces, valued at $17,130,357, against 964,589 ounces, valued at $19,939,824, in 1916. The output in 1917 was 376,089 ounces in California, 228,018 ounces in South Dakota, 115,341 ounces in Alaska, 29,107 ounces in Colorado, and 21,740 ounces in Nevada. Idaho showed the only increase, 3,000 ounces, in gold recovered by amalgamation.

The total yield of silver by amalgamation in 1917 was only 288,791 fine ounces, valued at $237,976, against 348,177 ounces, valued at $229,097, in 1916. The output came mainly from California, South Dakota, Oregon, Alaska, Nevada, and Colorado, in the order given, and consisted chiefly of silver alloyed with gold.

The total output of gold by cyanidation in 1917 was 1,169,478 fine ounces, valued at $24,175,256, against 1,260,172 ounces, valued at $26,050,067, in 1916. The output was 524,447 ounces in Colorado, 226,317 ounces in Nevada, 127,560 ounces in South Dakota, 47,815 ounces in Alaska, 118,762 ounces in Arizona, and 22,650 ounces in California in 1917. The only important increase in 1917 was that of Arizona, amounting to 55,318 ounces. The more important decrease was in Alaska, 32,522 ounces; California, 34,324 ounces; Nevada, 67,308 ounces.

The total yield of silver by cyanidation in 1917 was 11,535,747 fine ounces, valued at $9,505,455, against 14,432,378 ounces, valued at $9,496,505, in 1916. Nevada led, with the bulk of the output—9,220,352 ounces—and was followed by New Mexico with 655,181 ounces, Texas with 593,128 ounces, and Colorado with 380,652 ounces. The most notable losses were in Arizona, 395,730 ounces; New Mexico, 184,289 ounces; Colorado, 130,339 ounces; and Nevada, 2,081,509 ounces.

The quantity of gold recovered from ore treated by amalgamation decreased about 136,000 ounces in 1917 and that recovered from ores cyanided decreased about 90,000 ounces.

Of the gold-producing States, whose chief output is from milling ores, Alaska, California, and South Dakota still yield more gold by amalgamation than by cyanidation, whereas the latter process produces more gold than amalgamation in Colorado, Arizona, Nevada,

Digitized by Google

Oregon, and Montana, and it produces much more silver in Arizona, Colorado, Montana, Nevada, New Mexico, South Dakota, and Texas. Oregon, Alaska, and California were the only States in which the recovery of silver by amalgamation exceeded that by cyanidation. Altogether amalgamation produced gold and silver valued at $17,368,107 from milling ores in 1917, against $33,680,711 produced by cyanidation from such ores in that year.

Of the total output of gold from all sources in 1917, amalgamation produced 16.3 per cent in Alaska, 38.7 per cent in California, and 64 per cent in South Dakota, and cyanidation produced 48.4 per cent in Arizona, 68.4 per cent in Colorado, 67.2 per cent in Nevada, 22.1 per cent in New Mexico, 35.8 per cent in South Dakota, and 37.6 per cent in Montana.

Of the total output of silver from all sources in 1917, amalgamation produced 33.1 per cent in South Dakota and 45.5 per cent in Oregon, and cyanidation produced 81.8 per cent in Nevada, 63.3 per cent in South Dakota, and 99.5 per cent in Texas.

QUICKSILVER AND POTASSIUM AND SODIUM CYANIDE CONSUMED IN CERTAIN STATES.

For details of the consumption of quicksilver in the amalgamation milling process and of potassium cyanide and sodium cyanide in the cyanidation process the reader is referred to the mines reports of the several Western States named in the prefatory note. Data as to consumption of these supplies are not yet furnished by a sufficient number of mining and milling companies to justify tabulation for the entire United States. It has been estimated by H. D. McCaskey that the consumption of quicksilver in the amalgamation process in the United States (including Alaska) for the period 1911 to 1917, inclusive, has varied between 90,000 and 100,000 pounds annually. The consumption at mills treating ore and by dredging and other methods of placer mining are given in the separate chapter entitled "Quicksilver in 1917," prepared by F. L. Ransome and published elsewhere in Mineral Resources for 1917.

In the following tables, compiled by V. C. Heikes, of the United States Geological Survey, some details are given for the consumption of quicksilver and of cyanide in the recovery of gold and silver in six Western States from 1911 to 1917, inclusive.

Digitized by Google

Quicksilver consumed in certain Western States, 1911–1917.

State and year.	Number of mills using quicksilver.	Ore and tailings treated.	Total quicksilver.[a]	Quicksilver consumed (average per ounce of gold and silver bullion).
Arizona:		*Short tons.*	*Pounds.*	*Pounds.*
1911	26	46,833	1,362.00	0.086
1912	40	28,028	1,414.30	.098
1913	18	36,338	2,912.68	.158
1914	22	44,808	1,802.00	.116
1915	32	34,360	547.00	.063
1916	13	17,568	645.00	.040
1917	9	21,100	205.00	.057
Idaho:				
1911	35	72,210	1,648.00	.057
1912	43	34,609	700.00	.020
1913	40	28,258	254.00	.019
1914	29	25,877	598.00	.042
1915	36	46,423	1,040.00	.027
1916	36	66,304	1,183.00	.039
1917	27	63,884	1,035.00	.032
Montana:				
1911	24	61,767	898.00	.031
1912	17	48,837	783.59	.047
1913	23	14,508	289.57	.077
1914	18	29,983	408.00	.074
1915	24	28,504	371.00	.051
1916	18	18,959	206.00	.026
1917	13	8,925	167.00	.040
Nevada:				
1911	56	781,463	4,753.00	.012
1912	49	368,714	6,636.73	.044
1913	39	360,579	5,054.73	.051
1914	42	250,408	6,826.00	.063
1915	47	211,729	4,367.00	.038
1916	36	131,891	2,111.00	.034
1917	32	67,359	839.00	.020
Utah:				
1911	6	5,020	105.00	.058
1912	4	588	27.70	.145
1913	3	1,157	71.81	.107
1914	2	533	20.00	.108
1915	3	1,399	30.00	.020
1916	4	703	15.00	.039
1917	2	190	5.00	.030
Washington:				
1911	5	11,846	526.00	.197
1912	9	4,609	121.00	.043
1913	9	768	43.82	.038
1914	5	2,146	43.00	.039
1915	3	1,286	28.00	.031
1916	5	11,495	317.00	.027
1917	4	10,976	185.00	.026

State.	1911	1912	1913	1914	1915	1916	1917
	Pounds.	*Pounds.*	*Pounds.*	*Pounds.*	*Pounds.*	*Pounds.*	*Pounds.*
Arizona	1,362.00	1,414.30	2,912.68	1,802.00	547.00	645.00	205.00
Idaho	1,648.00	700.00	254.00	598.00	1,040.00	1,183.00	1,035.00
Montana	898.00	783.59	289.57	408.00	371.00	206.00	167.00
Nevada	4,753.00	6,636.73	5,054.73	6,826.00	4,367.00	2,111.00	839.00
Utah	105.00	27.70	71.81	20.00	30.00	15.00	5.00
Washington	526.00	121.00	43.82	43.00	28.00	317.00	185.00
	9,292.00	9,683.32	8,626.61	9,697.00	6,383.00	4,477.00	2,436.00

[a] Partly estimated.

Quicksilver consumed in Colorado in 1917 amounted to 3,800 pounds, in New Mexico to 175 pounds, and in South Dakota to 13,199 pounds.

Digitized by Google

Potassium and sodium cyanides consumed in certain Western States, 1913–1917, in pounds.

State.	Potassium cyanide.					Sodium cyanide.				
	1913	1914	1915	1916	1917	1913	1914	1915	1916	1917
Arizona	.....	.....	715	.....	580	.....	.....	226,427	216,841	157,381
Colorado	659,374	35,800	39,600	22,200	135,680	260,589	935,589	1,088,592	1,082,617	746,428
Idaho	.....	.....	2,894	3,431	1,268	.....	.....	3,725	700	3,728
Montana	.....	.....	1,003	13,305	.....	.....	.....	162,377	190,249	158,215
Nevada	.....	.....	13,514	140,328	130	.....	.....	3,050,092	2,179,995	1,925,038
New Mexico	1,415	.....	29,000	.....	.....	190,190	237,511	216,709	176,525	123,500
South Dakota	113,727	89,649	11,477	5,300	.....	388,961	425,397	458,300	419,210	384,938
Utah	.....	.....	36	1,200	.....	.....	.....	5,320	.....	37,000
Washington	.....	.....	1,200	.....	.....	.....	.....	3,400	2,380	.....
	774,516	125,449	99,439	185,764	137,658	839,740	1,598,497	5,214,942	4,268,517	[a]3,536,228

[a] Mines in Texas used 37,000 pounds of sodium cyanide in 1917.

Potassium and sodium cyanides consumed in certain Western States, 1911–1917.

State and year.	Number of mills using cyanidation process.	Ore and tailing treated.	Total consumption of cyanide.[a]	Cyanide consumed.	
				Average per ton of ore and tailing.	Average per ounce of gold and silver.
Arizona:		*Short tons.*	*Pounds.*	*Pounds.*	*Pounds.*
1911	9	152,815	115,877	0.758	0.919
1912	9	202,285	129,987	.642	.973
1913	11	208,591	189,291	.907	1.138
1914	13	294,827	264,969	.900	.369
1915	17	267,639	227,142	.850	.275
1916	9	276,623	216,841	.780	.300
1917	10	227,648	157,961	.69	.430
Idaho:					
1911	10	64,510	181,808	2.818	4.300
1912	5	54,477	161,156	2.958	3.300
1913	6	37,303	94,475	2.533	3.400
1914	10	12,094	32,529	1.800	2.530
1915	10	4,676	6,619	1.410	.440
1916	8	3,469	4,631	1.33	.38
1917	4	3,793	4,996	1.30	.45
Montana:					
1911	27	203,912	91,657	.449	.610
1912	21	184,487	93,344	.506	.913
1913	24	170,348	116,422	.683	.958
1914	13	192,235	151,738	.789	.921
1915	18	330,140	163,380	.494	.449
1916	18	381,560	203,554	.53	.69
1917	15	328,685	158,215	.48	.53
Nevada:					
1911	41	1,083,883	2,352,961	2.170	.313
1912	37	1,179,365	2,618,424	2.220	.252
1913	29	1,326,793	2,798,224	2.109	.228
1914	36	1,240,337	3,217,886	2.365	.258
1915	37	1,479,898	3,063,606	2.070	.239
1916	33	1,367,249	2,320,328	1.70	.20
1917	32	1,203,665	1,925,168	1.60	.20
Utah:					
1911	6	268,691	205,041	.763	1.450
1912	6	170,809	203,721	1.193	2.380
1913	6	81,940	70,238	.857	.956
1914	4	17,113	7,396	.432	.607
1915	3	12,064	5,356	.440	.830
1916	2	720	1,200	1.67	4.48
1917	.....	.....	.....	.....	.....
Washington:					
1911	3	17,381	9,700	.544	2.605
1912	4	16,703	36,517	2.186	.993
1913	2	20,410	32,090	1.572	.993
1914	2	22,387	48,820	2.180	.999
1915	4	1,746	4,600	2.600	.916
1916	1	1,207	2,380	1.97	3.12
1917	.....	.....	.....	.....	.....

Digitized by Google

Potassium and sodium cyanides consumed in certain Western States, 1911–1917—Contd.

State.	1911	1912	1913	1914	1915	1916	1917
	Pounds.	*Pounds.*	*Pounds.*	*Pounds.*	*Pounds.*	*Pounds.*	*Pounds.*
Arizona	115,877	129,987	189,291	264,969	227,142	216,841	157,961
Idaho	181,808	161,156	94,475	32,529	6,619	4,631	4,996
Montana	91,657	93,344	116,422	151,738	163,380	203,554	158,215
Nevada	2,352,961	2,618,424	2,798,224	3,217,886	3,063,606	2,320,328	1,925,168
Utah	205,041	203,721	70,238	7,396	5,356	1,200	.....
Washington	9,700	36,517	32,090	48,820	4,600	2,380	.....
	2,957,044	3,243,149	3,300,740	3,723,338	3,470,703	2,748,934	2,246,340

[a] Partly estimated.

It has not been possible to obtain a complete report showing the total consumption of potassium cyanide and sodium cyanide used in the recovery of gold and silver in the United States in 1917. If the quantity used in California, Alaska, and Oregon is added to the 3,710,886 pounds reported to have been used in other Western States the estimated total consumption was probably several hundred tons less than the estimated quantity, 2,600 tons, consumed in 1916.

The figures given indicate the elimination of the use of potassium cyanide in the recovery of gold and silver, for only about 69 tons were used in 1917 and this was probably from old stocks at mines. The growing scarcity of potassium cyanide necessarily increased the use of sodium cyanide. The domestic supply of sodium cyanide was sufficient to supply the domestic consumption. As the quantity of bullion recovered was less in 1917 than in 1916, however, the quantities of quicksilver and of cyanide used were less. The quantity of cyanide used per ton of ore or tailings treated and the quantity of gold and silver recovered per pound of cyanide show considerable variations. These variations are doubtless due in part to greater efficiency in large milling plants in some of the States but are mainly caused by the difference in the character and varying metal content of the ores treated.

Digitized by Google

Digitized by Google

ANTIMONY.

By EDSON S. BASTIN.

THE ANTIMONY SITUATION.

The United States is dependent upon three classes of material as sources of antimony or its alloys or compounds. (1) Antimony ore is imported from China (direct or via Japan), Bolivia (via Chile and Peru), and Mexico, and small quantities of ore are produced in the western United States. (2) Liquated antimony sulphide, also known as "crude antimony," "needle antimony," and antimony matte, is imported in small quantity from China. This material is produced by submitting the ores of the natural antimony sulphide, stibnite, to a red heat sufficient to melt but not to decompose it, and the metallic sulphide is then run into molds and allowed to cool. (3) Metallic antimony, known as antimony regulus, is imported from China, Japan, and Mexico and is produced in small quantity in the United States from both foreign and domestic ores. The metallic antimony imported from Japan is derived mainly from the refining of Chinese ore or "crude." A fourth class of material which should also be mentioned is antimonial lead, carrying from 12 to 18 per cent of antimony. Any of the three classes of materials noted above may enter into this product, but it is derived mainly from lead ores, most of them of the antimonial variety.

The United States has always been dependent mainly on foreign sources for its supplies of antimony. China and Japan have been the principal contributors, although Mexico and Bolivia have also made considerable contributions. This dependence is a reflection of the higher wage scale in this country as compared with certain foreign countries, particularly China, but it is due also to our comparative poverty in antimony resources, although little information of a quantitative nature has been collected concerning these resources, and they may be greater than has generally been assumed.

For many years prior to the European war the New York prices of the ordinary grades of metallic antimony ranged from 6 to 8 cents a pound; the imports, calculated as antimony metal, ranged from about 4,000 to 7,500 short tons; and the production from ores mined in this country was negligible. With the outbreak of the war the price of antimony began to rise rapidly because of the need of the metal in the manufacture of shrapnel bullets, and as uncertainty was felt as to the continuance of supplies from abroad, numerous mines in the Western States and several in Alaska were put into operation. By the end of 1915 the New York price had reached 40 cents a pound, and by March, 1916, it attained its maximum, for ordinary grades, of about 44 cents. These high prices drew out in the United States in

Digitized by Google

1915 a production of ore carrying about 2,100 short tons of antimony and in 1916 ore containing about 1,770 short tons of antimony. The high prices also greatly stimulated imports, as is shown in Plate V, and this forced down the prices of ordinary grades to 11 or 12 cents late in 1916 and made it impossible for most of the new domestic mines to operate at a profit. By the end of 1916 many of these mines had closed and others were in a precarious condition.

In anticipation of the entrance of the United States into the war there was a notable recovery in prices, ordinary grades reaching about 33 cents in April, 1917. This increase again stimulated imports (see Pl. V), which proved to be far in excess of the demands and not only forced a rapid decline in price to a fairly constant level of about 14 cents during the last half of 1917 but also built up large stocks in bonded warehouses (see fig. 11) and in the hands of dealers



FIGURE 11.—Diagram showing stocks of metallic antimony in bonded warehouse at end of each month in 1917 and 1918, as reported by the Bureau of Foreign and Domestic Commerce.

and consumers. Stocks in bonded warehouses alone, which were negligible early in 1917, amounted to more than 10,000,000 pounds at the end of the year. The decline in prices in 1917 dealt a final blow to domestic antimony mining, which during the year produced ore carrying only about 390 short tons of metallic antimony. Before the end of the year nearly all domestic mines had ceased operation. The experience of some of the larger operators seems to have indicated that mining and treatment of domestic ores could not be profitably conducted in 1917 unless the market price for ordinary grades of antimony was at least 20 cents.

In view of the large differential between the cost of production of antimony here and in China a return to an almost complete dependence upon foreign supplies is to be expected with the return of normal conditions. The fostering of a domestic antimony industry through protective tariff legislation involves grave considerations of public policy, including a careful weighing of the interests of domestic

Digitized by Google



DIAGRAM SHOWING ARY GRADES OF ANTIMONY METAL IN NEW YORK

Digitized by Google

Digitized by Google

consumers as well as producers and of the commercial and political importance of our foreign trade relations.

USES.

Peace uses.—Metallic antimony unalloyed has few industrial uses. In the form of fine powder, known as "iron black," it is used for producing the appearance of polished steel on articles made of papier-mâché or pottery. For these purposes it is precipitated by the action of metallic zinc on an acid solution of antimony salts. Antimony alloys readily with most heavy metals, and the alloy is harder than the two pure metals. Most of these alloys possess the property of slight expansion on solidifying. Type metal is an alloy of antimony, lead, and tin; babbitt, antifriction, or bearing metal is usually an alloy of antimony, tin, and copper. Britannia metal, also known as "white metal," is an alloy of antimony, tin, and copper, with some zinc and, rarely, small quantities of other metals. It is used in making cheap domestic tableware, teapots, and spoons. Antimony alloys find minor utilization in battery plates, toys, cable coverings, and siphon tops. Small quantities of antimony enter into certain brasses and aluminum alloys. Lead-antimony alloy, or "hard lead," is used in making acid-resisting valves.

White antimony oxide, mainly the tetraoxide (Sb_2O_4), is used for making opaque white enamel and other sanitary ware. In this use antimony oxides compete with tin oxide. Antimony oxide, mainly trioxide, is used as a coloring agent in the manufacture of glass, as it is more readily fusible than tetraoxide and does not impart opacity to the glass. Antimony oxides are further used as paint pigments.

The red sulphides of antimony are used in vulcanizing and coloring red rubber and also as paint pigments. The natural antimony trisulphide, stibnite, enters into the composition of safety matches or of the compound which is put on the match box.

Antimonate of lead, containing an excess of lead oxide, known as "Naples yellow," is used in oil paints and in the glass and ceramic industries. Tartar emetic (double tartrate of antimony and potassium) and antimony fluoride are employed as mordants in dyeing. Tartar emetic and antimony trioxide are employed medicinally.

War uses.—Antimonial lead carrying 12 to 13 per cent of antimony is employed in the manufacture of shrapnel bullets. Antimony sulphide is almost universally used as a constituent of primers in shells and cartridges, a utilization which is of the utmost importance but requires only very small amounts of material, not more than a few hundred tons being so used in the United States during 1918. Specifications for antimony sulphide for these purposes have been unnecessarily exacting, for recent investigations[1] have demonstrated that most of the material that has been successfully used in primers has contained from 80 to 85 per cent of antimony sulphide (Sb_2S_3), 2 to 3 per cent of siliceous material insoluble in sulphuric acid, and as much as 18 per cent of antimony combined with oxygen either as an oxide or as an oxysulphide. The presence of lead and iron as impurities is probably not deleterious, as was formerly supposed, for excellent primers have been prepared by substituting lead sulphide or iron sulphide for antimony sulphide. These

[1] Cushman, A. S., Antimony sulphide as a constituent in military and sporting arms primers: Jour. Ind. and Eng. Chemistry, May, 1918, pp. 376–383.

Digitized by Google

investigations relieve any apprehension as to an adequte supply of antimony material suitable for primers. They show that readily obtainable commercial grades of antimony sulphide are adequate for this purpose and that probably other sulphides could, if necessary, be substituted for antimony sulphide.

Antimony sulphide as a powder is used in the charges of some shells to produce on explosion a dense white smoke, which is of service in range finding.

SUPPLY OF ANTIMONY.

In estimating the supplies of antimonial materials available for domestic use in 1917 ores are excluded from consideration in order to avoid confusion and duplication, inasmuch as the recoverable antimony content of both foreign and domestic ores eventually appears in the records of production of metal, alloys, or compounds.

Antimony metal available in 1917.[1]

		Short tons.
Stocks in bonded warehouses Dec. 31, 1916		1,155
Production from domestic ores		258
Production from foreign ores		2,182
Imports (general)		17,824
		21,419
Stocks in bonded warehouses Dec. 31, 1917	5,201	
Exports	495	
		5,696
Antimony metal available for private stocks or consumption in 1917		15,723

Antimony alloys, mainly antimonial lead, available in 1917.

	Gross weight (short tons).	Antimony content (short tons).
Production of by-product antimonial lead [a]	18,646	2,759
Production of antimonial lead from antimony ores and lead ores or scrap lead	2,283	348
Recovery from secondary metals and drosses [b]	.....	4,961
Imports of type metal for consumption	None.	None.

[a] Produced from lead skimmings as by-product of lead smelting.
[b] Recovered mainly as purified alloys, not as antimony metal. Gross weight not reported.

The domestic production of antimony oxide and other compounds in 1917 has not been reported; the imports for consumption amounted to 10 short tons, gross weight.

MINE PRODUCTION OF ANTIMONY ORES.

The production of antimony ores in the United States in 1917 was confined to the Western States and Alaska. Nevada led, with a production of about 870 short tons, and was followed by Alaska, with less than 100 tons, and by California, Idaho, and Utah, with less than 50 tons each. The total reported for the United States was about 1,060 short tons having an average tenor of about 37 per cent

[1] Antimony regulus or metal and very small quantities of antimony sulphide or "crude" antimony.

Digitized by Google

metallic antimony. The total antimony content was about 390 short tons, of which perhaps 80 per cent, or 312 short tons, was recoverable.

The mine production in 1917 was less than one-fourth of that in 1916 (4,500 short tons, with a metallic antimony content of 1,770 short tons). The decline was due to the downward trend in prices, which began early in April, as is shown in Plate V.

Alaska.—Only one property in Alaska produced antimony ore in 1917; this was the Scrafford, in the Fairbanks district. The ore, most of which assayed 45 to 55 per cent of antimony oxide, was shipped to Seattle. It was recovered by sluicing old dumps, no new mining being undertaken.

Arkansas.—At the mine of the American Star Antimony Co. near Gillham, in Sevier County, Ark., some ore was mined in 1917, but not sold. Late in the year the plant was closed down.

California.—Less than 50 tons was reported as produced in California in 1917, from the Lone Tree mine, near Hollister, San Benito County, and from a prospect in Kern County.

Idaho.—Three properties in Shoshone County, Idaho, reported operations in 1917, but their aggregate output of ore was less than 50 tons. The Coeur d'Alene Antimony Mining Co., whose office is at Kellogg, operated a mine in the valley of Pine Creek, in the Yreka district. In February, 1918, this company reported that a concentrating plant was in course of erection and that it was planned to recover the metal from the concentrates by electrolytic treatment. The Star Antimony Mining Co., with office at Kellogg, also mined a few tons of ore in the same district. Ore from this district was shipped exclusively to the Magnolia Metal Co. at Matawan, N. J.

In 1917 a reduction plant was in erection at the mine of the Idaho Antimony Mining Co. in the Yellow Pine district, Idaho County, but no antimony was marketed during the year.

Development work was done at the Orlando Leasing Co.'s property in the Lelande district, and also on a property operated by Charles A. Pearsons, of Beeler, both in Shoshone County. The Hougland mine, 8 miles from Burke, formerly a large producer, was idle during 1917. The deposits are said to be flat-lying or "blanket" veins worked by tunnels. At one time an oxide plant was operated at this mine.

Nevada.—Nevada produced about 870 tons of antimony ore in 1917 out of the total of 1,060 tons reported for the entire United States. The production came mainly from Humboldt and Lander counties, although small quantities were mined in White Pine County. As in previous years the Sutherland mine, 5 or 6 miles from Lovelock, Humboldt County, was one of the principal producing properties, but it was worked by lessees. The ore was shipped mainly to the Nichols-Layng Chemical Co., of San Francisco.

The National Antimony Co. stated in February, 1918, that it was erecting a plant for the production of antimony oxides at Mill City. Some ore was mined at its property in the Star district, Humboldt County, during the year.

In Lander County the mines of Antonio Borrego, Joseph Bray, and J. F. Murphy, in the Reese River district, Toyabe Range, were operated, and the output was shipped to Matawan, N. J. The Antimony King mine, in the same district, was operated by the Nichols-Layng Chemical Co., and the output was shipped to the works of this company at San Francisco.

Digitized by Google

Utah.—The Stibnite Mining Co., with office at Ogden, produced a small quantity of high-grade ore (assaying 60 to 66 per cent Sb_2O_3) from its mine in Bill Lewis Canyon, 3½ miles from Brigham City, Box Elder County. The ore was shipped to the Magnolia Metal Co., Matawan, N. J.

SMELTER PRODUCTION OF METALLIC ANTIMONY.

The production of metallic antimony in the United States in 1917, at the four plants mentioned below, amounted to 258 short tons from domestic ores and 2,182 short tons from imported ores, a total of 2,440 short tons. This is the first year for which figures of smelter production of metallic antimony have been obtained. The value of this antimony, computed on the basis of an average price of 20.7 cents a pound, or $414 a short ton, in New York City, for ordinary grades, is $1,010,160.

Smelters engaged in the production of metallic antimony in the United States in 1917 were the following:

Magnolia Metal Co., office at 113 Bank Street, New York City; plant at Matawan, N. J. This company has been a large user of domestic as well as foreign ores.

The Antimony & Compounds Co. of America, Highland Park, New Brunswick, N. J. This company, which is closely associated with the Société des mines de La Lucette et Le Genest, the principal French producer of antimony, established a plant at Piscataway, N. J., early in 1917. The plant has depended mainly on foreign ores.

Nichols-Layng Chemical Co., San Francisco, Calif.; treats only domestic ores.

Western Metals Co., Los Angeles, Calif. Plant at San Pedro, near Los Angeles. The plant treated mainly Bolivian and Mexican ores.

SMELTER PRODUCTION OF ANTIMONIAL LEAD.

The production of antimonial lead from lead skimmings as a by-product of the lead-smelting industry is tabulated for recent years in the chapter dealing with lead from figures collected by C. E. Siebenthal, of the United States Geological Survey. In 1916 and 1917 this production was as follows:

By-product antimonial lead produced in the United States from both foreign and domestic ores, 1916–17.

	Gross weight (short tons).	Antimony content (short tons).	Value of antimony content.[a]
1916	24,038	3,496	$1,775,968
1917	18,646	2,759	1,142,226

[a] Calculated on basis of average yearly price of 25.4 cents a pound, or $508 a short ton, in 1916, and of 20.7 cents a pound, or $414 a short ton, in 1917 for ordinary grades in the New York market.

In addition to the production recorded above 2,283 short tons of antimonial lead, valued at $144,072 and containing 348 tons of antimony, was produced from the smelting of foreign and domestic antimony ores with lead ores or scrap lead.

Digitized by Google

In obtaining this product there were used 345 short tons of antimony ores from Mexico and South America and 563 tons from Alaska and the western United States.

RECOVERY OF SECONDARY ANTIMONY.

During 1917 4,961 short tons of antimony was recovered from old alloys, scrap, and dross. Practically all of this was recovered in the form of alloys, not as metallic antimony. (See p. 656.)

Antimony content of secondary alloys recovered from old alloys, scrap, and dross, 1913–17.

Year.	Quantity (short tons).	Value.[a]
1913	2,705	$401,963
1914	2,646	444,844
1915	3,102	1,811,568
1916	4,480	2,270,016
1917	4,961	2,061,700

[a] Values calculated at average yearly price for ordinary brands of antimony as published by the American Metal Market.

IMPORTS.

The accompanying statistics of imports are taken from the reports of the Bureau of Foreign and Domestic Commerce, United States Department of Commerce, long tons being recalculated to short tons. The imports are reported as (1) imports for consumption, including merchandise entered for immediate consumption or withdrawn from bonded warehouses for consumption, and (2) total imports. Only total imports are listed by countries of origin.

In contrast to the small domestic production of 1,060 short tons of antimony ore in 1917, the imports were nearly ten times as great, amounting to 10,370 short tons. Furthermore, the imported ore averaged 57 per cent antimony, as against 37 per cent for the domestic ore.

Total imports[a] of antimony into the United States in 1917.

Country.	Antimony ore.			Antimony metal.[b]	
	Quantity (short tons).	Antimony content.		Quantity (pounds).	Value.
		Quantity (pounds).	Value.		
Canada	126	105,077	$15,762	190,000	$24,879
Newfoundland and Labrador	22	30,136	1,985	.....	.....
Mexico	2,116	1,434,403	76,712	4,126,659	416,866
Argentina [c]	596	632,662	55,514	.....	.....
Chile [c]	4,098	5,131,569	507,463	.....	.....
Peru	44	27,570	3,636	.....	.....
Colombia	2	2,356	255	.....	.....
Honduras	3	4,785	1,563	.....	.....
China	2,949	4,060,353	331,504	11,324,846	1,333,541
Hongkong [d]	.....	.....	.....	859,835	101,568
Japan	.....	.....	.....	18,677,597	2,333,745
England	.....	.....	.....	470,176	87,081
Portugal	302	390,282	27,870	.....	.....
Portuguese Africa	112	101,250	9,734	.....	.....
	10,370	11,920,443	1,031,998	35,649,113	4,297,680

[a] Includes large quantities of antimony metal that went into bonded warehouse and that are not included in the table of imports for consumption.

[b] Includes small quantities of liquated antimony sulphide, known in the trade as "crude antimony," "antimony matte," or "needle antimony."

[c] Imports credited to Chile originated mainly in Bolivia; those credited to Argentina may also be Bolivian.

[d] Nearly all the imports of antimony ore and metal from Hongkong and Japan are of Chinese origin. Some of the material credited to other countries is possibly also of Chinese origin, having been transshipped in a foreign port.

Digitized by Google

The total imports show a notable increase in 1917 over 1916, when the ore imports amounted to 7,764 short tons, having an antimony content of 9,485,423 pounds, and the metal imports aggregated 19,749,830 pounds.

It is noteworthy that ore imports from Mexico were considerably larger in 1917 than in 1916 (1,339 short tons) and that ore imports from China also increased (1,048 short tons in 1916). Metal imports from China and Hongkong combined were about the same as in 1916, but metal imports from Japan were nearly three times those in 1916 (6,869,293 pounds). Noteworthy imports of metal also came from Mexico in 1917, although in 1916 none were brought in.

As shown in Plate V, the imports suddenly increased just after the entrance of the United States into the war, reached a maximum in August, and declined rapidly during the remainder of the year.

Antimony imported and entered for consumption, 1913–1917.

Year.	Antimony ore.[a]			Liquated antimony sulphide.[b]		Metallic antimony.[c]		Antimony oxide and other compounds.[d]	
	Quantity (short tons).	Antimony content (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.
1913	2,860	2,007	137,361	3	419	6,240	798,581	984	$117,169
1914	1,791	1,254	71,341	49	4,004	6,555	736,420	1,372	315,001
1915	2,494	1,544	332,125	.....	.....	7,354	2,660,830	423	132,193
1916	7,840	4,622	1,072,340	.....	.....	7,064	3,542,507	243	109,832
1917	9,003	5,831	1,006,884	796	128,660	11,285	2,829,159	10	5,368

[a] Classified in tariff classification as "Antimony ore and stibnite containing antimony."
[b] Classified in tariff classification as "Antimony matte, containing not more than 10 per cent of lead."
[c] Classified in tariff classification as "Antimony regulus or metal."
[d] Classified in tariff classification as "Antimony, oxide, salts, and compounds of."

For years large quantities of antimonial lead were imported into the United States as type metal, for which it is largely used, but since 1911 these imports have declined. The following table is compiled from the records of the Bureau of Foreign and Domestic Commerce:

Type metal imported and entered for consumption, 1906–1917.

Year.	Type metal.		Assumed antimony content.		Year.	Type metal.		Assumed antimony content.	
	Quantity (short tons).	Value.	Quantity (short tons).	Percentage.		Quantity (short tons).	Value.	Quantity (short tons).	Percentage.
1906	9,801	$900,608	1,853	18.9	1912	291	$18,668	52	17.2
1907	7,416	932,027	1,369	18.5	1913	284	20,098	50	17.6
1908	2,055	156,847	422	20.5	1914	755	45,373	94	12.4
1909	6,997	532,108	1,327	19.0	1915	1,384	107,607	172	12.4
1910	6,697	485,493	1,109	16.6	1916	581	83,816	119	20.5
1911	4,195	310,658	727	17.3	1917	None.	.....	None.	.....

The customs returns give only the lead content of imported type metal, and the figures given above are based on the assumption that the remainder is practically all antimony, but this assumption is

Digitized by Google

wholly arbitrary, for imported type metal contains as much as 2 per cent of impurities, such as iron, arsenic, and copper. The antimony content is therefore probably too large by some quantity less than or approximately equal to 2 per cent of the total quantity of type metal, and the correct percentage is correspondingly lower.

EXPORTS.

Exports of metallic antimony[1] as recorded under "Exports of foreign merchandise" in the reports of the Bureau of Foreign and Domestic Commerce amounted to 989,477 pounds, valued at $169,260, in 1917, as against 3,018,251 pounds, valued at $761,045, in 1916. The exports in both years went mainly to Canada. No exports of antimony ore were recorded in 1917.

STOCKS.

Stocks of metallic antimony in bonded warehouses as reported by the Bureau of Foreign and Domestic Commerce were small during the first half of 1917, amounting on June 30 to only 322,811 pounds. During the last half of the year, as shown in figure 11, they increased very rapidly because of low prices and market stagnation, and on December 31 they amounted to 10,401,682 pounds.

PRICES.

The average New York prices for the highest grades of metallic antimony for the last 23 years, in cents per pound, are given by the Engineering and Mining Journal as follows:

1895	7.56	1903	6.00	1911	7.54
1896	6.65	1904	6.37	1912	7.76
1897	6.75	1905	10.25	1913	7.52
1898	8.69	1906	21.73	1914	8.76
1899	9.43	1907	14.84	1915	30.28
1900	9.50	1908	8.00	1916	25.37
1901	8.25	1909	7.47	1917	20.69
1902	6.12	1910	7.39		

For the ordinary grades of metallic antimony the fluctuations in average monthly prices during the five years 1914 to 1918 are shown in Plate V.

FOREIGN SOURCES.

CHINA.

The following statement in regard to the Chinese antimony industry is quoted from a report from the United States commercial attaché at Peking dated September, 1918:[2]

China at present supplies the greater part of the world's demand. Sixty-two per cent of the American imports of antimony in 1916 came from China. It is produced in Hunan, Kwangtung, and southwestern China, 95 per cent coming from Hunan, which possesses the purest ores, practically free from arsenic and carrying from 20 to 64 per cent of antimony. Smelting is done at Changsha, Hankow, and Wuchang. The Wah Chang Co. (Chinese) owns the French patent rights for Hunan for the Herrenschmidt process for the treatment of low-grade sulphide ores and also has a Chinese Government monopoly for a limited term of years for producing regulus in Hunan Province. Antimony crude (concentrated antimony sulphide containing between 65 and 70 per cent of antimony metal) is the usual form in which antimony is marketed in China. The regulus assays at 98 to 99.8 per cent pure. In 1917 China

[1] "Matte, regulus, or metal," in Bureau of Foreign and Domestic Commerce classification.
[2] Commerce Repts., Nov. 27, 1918, p. 787.

Digitized by Google

exported 15,000 long tons of regulus, 20,000 tons of crude, and 4,000 tons of ore. The ports of export are Hankow, Shanghai, and Hongkong. The regulus is shipped in boxes, 13½ pounds to a box.

The conditions of the antimony industry in Hunan, the principal producing Province, during 1917 are described at some length in a report from the United States consul at Changsha,[1] from which the following extracts are quoted:

While antimony continued to be the most important product of the mines of Hunan in the business of the Province during the year 1917, the production fell off and exports decreased by reason of the return to a more or less normal condition in the price. The customs statistics for 1917 give the following total exports from the port of Changsha to all countries: Antimony, crude, 42,665,733 pounds, valued at $2,252,807; antimony ore, 201,600 pounds, valued at $9,394; and antimony regulus, 29,608,267 pounds, valued at $3,258,712.

With the fall in the price of antimony, smelters shut down and many of the mines that had been operating as speculations were closed.

This report gives also a detailed description of the operations of the Wah Chang Mining & Smelting Co., the principal antimony producer of the district.

JAPAN.

Since the beginning of the European war Japan has done a large business in Chinese antimony, and in 1917 the United States received more antimony from Japan than from any other single source. Japan has some antimony resources of her own, the development of which began in 1876 and for a number of years grew rapidly, the value of the production fluctuating from $50,000 to $120,000 annually. On account of growing scarcity of good ores and the low price of antimony domestic mining then declined, and it received its final blow in 1897, when the rich mines in Hunan Province, in China, were opened. Since then the Japanese have been unable to compete with the Chinese in antimony mining but have smelted some Chinese ore and matte.

With the beginning of the European war Japan began to import large quantities of antimony ore, matte, and metal from China and to make greatly increased exports, mainly as refined metal but to some extent in munitions. Her total exports of metallic and "crude" antimony increased from about 440 short tons in 1912 to about 4,750 short tons in 1914 and 15,700 short tons in 1917.[2]

Japan's smelting and transportation capacities have greatly facilitated the supplying of the Allies with their antimony requirements during the war, but the Chinese have during the same period greatly enlarged and extended their facilities for treating their antimony ores and may now be in a position to supply direct most of the normal peace needs of their foreign customers.

MEXICO.

United States imports of antimony ore and metal from Mexico in 1917 are shown in the table on page 659. These figures indicate a notable increase over 1916, when no imports of metal were recorded and when the imports of ore were 1,339 short tons (2,678,000 pounds), having an antimony content of 1,048,387 pounds.

At Catorce, on the National Railway of Mexico, in the State of San Luis Potosi, and at Charcas, a few miles farther south in the same

[1] Commerce Repts., May 21, 1918, pp. 699–703.
[2] From statistical returns of the Department of Finance of the Empire of Japan.

Digitized by Google

State, are the deposits of the Republican Mining Co. (Cookson interests), an English concern. The ore is smelted at Wadley, near Catorce.

Another antimony mine in the State of San Luis Potosi,[1] 8 miles east of Maroma station on the National Railway of Mexico, was operated during 1917 by William Dingwall, of San Antonio, Tex. Operation was somewhat irregular, owing to disturbance by bandits. The ore mined in 1917 was mainly oxide ore carrying an antimony content varying from 25 to 40 per cent. It is transported on pack mules to Maroma station and shipped by rail to the Metals Refining Co. at Hammond, Ind., where it is used in the production of antimonial lead.

In the State of Sonora[2] antimony ores were mined during 1917 by Miller & Thompson, 617 Pacific Building, San Francisco. The mine is in the Alter district, close to the Gulf of California and near a locality known as Antimonio. The ore occurs over wide areas as float and also in small veins and lenses. The ore thus far shipped is an oxide said to carry less than 0.5 per cent of other metals. Car lots averaged 46 to 52 per cent antimony. The ore was hauled by wagons 90 miles to Santa Ana, the nearest railroad point, and from there shipped to the smelter of the Western Metals Co., at Harbor City, near Los Angeles, Calif. The maximum monthly capacity of the mine is said to be about 400 tons of ore. Shipments during the year were much delayed because of the uncertain political and market conditions. Freight charges from Santa Ana to Harbor City were $8.75 a ton, and Mexican export duties and charges aggregated about $5 a ton.

BOLIVIA.

According to the United States Bureau of Foreign and Domestic Commerce,[3] the exports of antimony ore from Bolivia in 1917 were valued at $6,630,000, as against $6,591,000 in 1916.

FRANCE.

The following statement in regard to the French antimony industry is quoted from the American Metal Market and Daily Iron and Steel Report for July 8, 1918:

> The Société des mines de La Lucette et Le Genest, in France, is practically the only works in that country producing antimony on a considerable scale and has been showing considerable activity for some time past in extending its operations both at home and abroad. As regards refinery operations, it has been largely dependent upon oxide ores imported from Algeria, but developments at the La Lucette mine, which was originally worked unsuccessfully as a gold proposition, has resulted in the discovery that the entire area carries veins of stibnite interspersed with small gold-bearing stringers. This, it is thought, may have important effects upon the company's activities, in so far as French ore supplies are concerned, for the company is in a very good position to make use of gold-bearing stibnite. By means of the imported oxide ores the La Lucette Co. is able to produce about 300 tons a month of regulus of antimony and has thus been the mainstay of France so far as this particular metal is concerned during a very critical period.

AUSTRALIA.

According to the United States consul at Sydney,[4] the value of antimony ores exported from Australia for the fiscal years ending June 30, 1916 and 1917, was $530,410 and $378,808, respectively.

---

[1] Letter from William Dingwall, May, 1918.
[2] Letter from C. N. Miller, May 4, 1918.
[3] Commerce Repts., Oct. 24, 1918, p. 328.
[4] Supplement to Commerce Repts., No. 60b, Nov. 8, 1918, p. 5.

Digitized by Google

Digitized by Google

MANGANESE AND MANGANIFEROUS ORES.

By D. F. HEWETT.

INTRODUCTION.

As manganese ore is one of the few mineral commodities for the supply of which the United States is largely dependent on foreign countries, the events of the war, particularly their effect upon marine trade, continued to determine the trend of the domestic industry. The production of steel from American furnaces had risen from 32,151,036 tons in 1915 to 42,773,680 tons in 1916, and the entry of the United States into the war in April, 1917, made it clear that the best efforts of the country would be given to maintain the maximum rate of production of iron and steel. As a result of these efforts, the production of steel for the year rose to 45,060,607 tons, and as small quantities of manganese alloys are essential in making almost all steel, there was a similar increase in the demand for manganese ores.

As it was widely thought and stated that the domestic supply of manganese ores was inadequate to meet increasing needs, it was natural that efforts should be made by consumers to procure as much foreign material as could be obtained under existing shipping conditions. Imports for the year rose, therefore, to the maximum record of 629,972 tons, of which 80 per cent came from Brazil. The hazard of moving materials through the submarine zone around Great Britain, which had been the source of nearly half this country's supply of manganese in the form of ferromanganese, reduced the imports of that alloy to 41,969 tons, the lowest since 1904. The increase in price of manganese alloys and ores caused by the shortage induced many persons to search for and exploit domestic deposits of the ores. The shipments of high-grade manganese ore during 1917 rose to 129,405 tons, or more than four times those of 1916 (31,474 tons). Likewise the shipments of low-grade material rose from 544,326 tons in 1916 to 860,944 tons in 1917.

The realization that the war might continue several years and that during a part of that period the submarine menace might greatly curtail the imports of raw materials led the United States Geological Survey, in cooperation with several State organizations, to make a careful survey of the location and extent of domestic manganese deposits and the classes of material they were capable of yielding. A similar study had been made by Harder[1] in 1909, but since then many new deposits had been discovered and the well-known districts had been further explored. Field work was begun in April, 1917,

[1] Harder, E. C., Manganese deposits of the United States, with sections on foreign deposits, chemistry, and uses: U. S. Geol. Survey Bull. 427, 1910.

Digitized by Google

and the most important districts were examined during the summer. Although plans provided for continuing and practically completing this work during 1918, the work of the season of 1917 yielded data which permitted estimates of the probable production during 1918 that were nearly twice the actual production during 1917. It was therefore apparent early in the year that the domestic contribution of high-grade as well as low-grade ore would be an appreciable part of the country's needs.

The important geologic conclusions arising out of the field work were published as soon as possible after the work was finished.[1]

Manganese alloys and ore produced in the United States and imported from important foreign sources, 1890–1917, in gross tons.

Year.	Steel.	Ferromanganese.		Spiegeleisen.		Manganese ore.				
	Production.	Production.	Imports.	Production.	Imports.	Production.	Total imports.	Imports from—		
								Russia.	India.	Brazil.
1890	4,277,071	.....	.....	.....	.....	19,287	34,154	.....	.....	.....
1891	3,904,240	.....	.....	.....	.....	22,452	28,825	.....	.....	.....
1892	4,927,331	.....	.....	.....	.....	13,613	58,572	.....	.....	.....
1893	4,019,995	.....	.....	.....	.....	7,718	68,113	[a] 36,070	[b]	.....
1894	4,412,032	.....	.....	.....	.....	6,308	44,655	[a] 28,300	.....	[c]
1895	6,114,334	.....	.....	.....	.....	9,547	86,111	[a] 55,987	.....	.....
1896	5,281,089	.....	.....	.....	.....	10,088	31,489	[a] 3,600	.....	.....
1897	7,156,957	.....	.....	.....	.....	11,108	119,961	88,910	17,400	12,083
1898	8,932,857	.....	.....	.....	.....	15,957	114,885	46,396	5,944	17,031
1899	10,639,857	.....	.....	.....	.....	9,935	188,349	73,397	17,950	28,115
1900	10,188,329	[d]	[e]	[d]	[e]	11,771	256,252	132,121	10,650	54,451
1901	13,473,595	59,639	20,750	231,822	26,827	11,995	165,722	32,600	11,000	48,029
1902	14,947,250	44,526	50,388	168,408	68,813	7,477	235,576	3,338	64,170	102,550
1903	14,534,978	35,061	41,519	156,700	122,015	2,825	146,056	5,576	35,960	76,910
1904	13,859,887	57,076	21,813	162,470	4,623	3,146	108,519	11,959	10,200	66,875
1905	20,023,947	62,186	52,841	227,797	55,457	4,118	257,033	24,650	101,030	114,670
1906	23,398,136	55,520	84,359	244,980	103,268	6,921	221,260	13,805	154,180	30,260
1907	23,362,994	55,918	87,400	283,430	48,994	5,604	209,021	1,000	95,300	52,922
1908	14,023,247	40,642	44,624	111,376	4,579	6,144	178,203	250	143,813	17,150
1909	23,955,021	82,209	88,934	142,831	16,921	1,544	212,765	14,486	145,140	35,600
1910	26,094,019	71,376	114,228	153,055	25,383	[f] 2,258	242,348	33,120	140,965	53,750
1911	23,676,106	[f] 74,002	80,263	[f] 104,013	20,970	[f] 2,457	176,852	19,103	103,580	41,600
1912	31,251,103	[f] 125,378	99,137	[f] 102,961	1,015	[f] 1,664	300,661	83,334	128,645	81,580
1913	31,300,874	[f] 219,495	128,070	[f] 106,980	77	[f] 4,048	345,090	124,337	141,587	70,200
1914	23,513,080	[f] 100,731	82,997	[f] 76,625	2,870	[f] 2,635	283,294	52,681	103,583	113,924
1915	32,151,036	[f] 144,260	55,263	[f] 114,556	200	[f] 9,613	320,778	.....	36,450	275,579
1916	42,773,080	[f] 224,103	90,928	[f] 182,937	.....	[f] 31,474	576,321	.....	51,960	471,837
1917	45,060,007	[f] 260,225	41,969	[f] 189,241	3,968	[f] 129,405	629,972	.....	48,975	512,517

[a] Drake, Frank, The manganese ore industry of the Caucasus: Am. Inst. Min. Eng. Trans., vol. 28, p. 191, 1898.
[b] First shipment made from India.
[c] First shipments made from Brazil.
[d] Figures for ferromanganese and spiegeleisen combined prior to 1901.
[e] Figures for fiscal years only available prior to 1901.
[f] Marketed production.

SOURCES OF MANGANESE.

MANGANESE MINERALS.

Though manganese forms a part of about one hundred minerals and is a relatively widespread element, practically all the manganese in commercial use is derived from material containing one or more of the first seven of the minerals named in the following table:

[1] For brief summaries, refer to the discussion by States (pp. 682–686); also to bibliography (pp. 691–696).

Digitized by Google

Principal manganese minerals.

Mineral	Composition.	Percentage of manganese.
Polianite	MnO_2	63.2
Pyrolusite	$MnO_2.nH_2O$	60-63
Psilomelane	$MnO_2.(MnKBa)O.nH_2O$	45-60
Wad	Hydrous impure mixture of manganese oxides	5-50
Manganite	$Mn_2O_3.H_2O$	62.4
Braunite	$3Mn_2O_3.MnO.SiO_2$	69
Franklinite	$(FeZnMn)O.(FeMn)_2O_3$	10-19
Rhodochrosite	$MnO.CO_2$	47.56
Rhodonite (manganese pyroxene)	$MnO.SiO_2$	41.9
Tephroite (manganese olivine)	$2MnO.SiO_2$	54.3
Spessartite (manganese garnet)	$3MnO.Al_2O_3.3SiO_2$	33.3

MANGANESE ORES.

In the report on manganese ores in 1916 [1] a new classification of the manganese-bearing raw materials of the United States was adopted. It was the purpose of the new classification to group the raw materials according to manganese content so that the quantities of material capable of certain specific uses would be indicated. Thus, in restricting the term "manganese ore" to material containing more than 40 per cent of manganese it was the intention to indicate that practically all material in this class was capable of being smelted to ferromanganese containing 80 per cent of manganese, the product which is made from a large part of such ore. The war brought about changes in practice in the making and use of manganese alloys, so that early in 1918 it seemed desirable to change the limits previously placed in the classification of the ores. The action that led to this change was the recommendation in April, 1918, by the American Iron and Steel Institute to its members, who include the officials of practically every steel company in the United States, that ferromanganese containing 70 per cent of manganese be used as far as practicable in place of the 80 per cent alloy and that spiegeleisen containing 16 per cent of manganese be used in place of 20 per cent alloy, and therefore that alloys of the lower grades be accepted on contracts for the higher grades. The purpose of lowering the grade of ferromanganese from 80 to 70 per cent of manganese was to permit the wider use of domestic ores in making the alloy. Actually, the grade of alloy which may be made from an ore depends largely upon the percentages of manganese, iron, and silica that are present. If a classification were to indicate truly the use to which the material could be put, it should properly be based upon assigned limits to each of these ingredients. In the United States, however, there are few large deposits of manganiferous materials of any grade which appear to be capable of shipping regularly over long periods material exhibiting the narrow ranges in composition that much foreign material shows. The actual work required in classifying the shipments from individual mines according to a system based upon the percentages of manganese, iron, and silica is too great to permit the ready adoption of such a system by the domestic producers. In spite of certain obvious objections, therefore, the adopted classification is based upon the manganese content alone.

[1] Hewett, D. F., U. S. Geol. Survey Mineral Resources, 1916, pt. 1, pp. 733-734, 1918.

Digitized by Google

The new classification aims to group materials that are capable of being used to make the grades of alloys adopted as a war expedient. It remains to be determined whether the steel industry will continue to make and use the new grades of alloys or whether when the supply of high-grade foreign ores is not hindered the industry will demand the old grades. Probably many steel makers will return to the use of the old grades of alloys, but as some makers appear to be satisfied with new grades, it will serve a purpose to continue the classification of ore adopted during the war.

Material containing more than 35 per cent of manganese will be considered manganese ore. If the manganese in such material is present as one of the common oxides, it is possible for other substance to make up about 45 per cent of the total. On the other hand, if the manganese is present as carbonate, only 27 per cent of other substances may be present. During 1917 large quantities of oxide material were marketed from Arizona, California, and Montana which contained more than 16 per cent of silica, and some mines reported shipments with as much as 27 per cent of silica. The iron content of manganese ores from most of the States is low—generally from 2 to 5 per cent—but material from several districts, especially Bisbee, Ariz., and Lake Valley, N. Mex., ranges from 3 to 11 per cent, and the average is close to 9 per cent. The average composition of the entire output during 1917—129,405 tons—as reported by the shippers, was manganese, about 42.5 per cent; iron, 2.8 per cent; silica, 14 per cent; natural basis, but moisture not reported.

Material containing 10 to 35 per cent of manganese will be considered ferruginous manganese ore. In the report for 1916 the range for material under this class was 15 to 40 per cent of manganese. It should be stated that there is no natural basis for choosing the percentage that marks the distinction between manganese ore and ferruginous manganese ore. Any such percentage must be arbitrarily chosen on the basis of the use to which the material is to be put. Although large quantities of both oxide and carbonate materials containing from 35 to 40 per cent of manganese were shipped from a number of States during 1917, relatively little material containing 25 to 35 per cent of manganese has been produced from domestic deposits. Most of the material that is classified as ferruginous manganese ore, produced largely in Minnesota, Michigan, Nevada, and Colorado, contains from 14 to 25 per cent of manganese, 25 to 35 per cent of iron, and 8 to 20 per cent of silica.

The objection has been made that in some districts such material has long been known as manganiferous iron ore and that it will be confusing to restrict the name to material containing 5 to 10 per cent of manganese which was not widely mined and used until recently, and to apply a new name to material that was formerly known by the old name. In reply to this objection it may be stated that there is need for two terms and that the material containing more than 10 per cent of manganese has more interest and commonly derives more value from its manganese than from its iron content. Spiegeleisen containing 16 per cent of manganese may be made from most of the material that is produced in the United States at present, although less than one-third was so used in 1917.

Material containing 5 to 10 per cent of manganese is classified as manganiferous iron ore. The market for such material lies mainly

Digitized by Google

with the makers of basic pig iron, so called because it is especially adapted to making steel by the basic open-hearth process. There is no record that any of this material is used for making spiegeleisen.

Manganiferous silver ore is applied to those materials, either oxides or carbonates, that contain more than 5 per cent of manganese and sufficient silver to make them more valuable as a source of silver than of manganese. Such materials commonly contain from 5 to 45 per cent of iron, several per cent of silica and lead, and a little gold and copper, and are shipped to lead or copper smelters where the silver, gold, lead, and copper are recovered and the manganese aids in making a more fusible and fluid slag.

Manganiferous zinc residuum is a product that commonly contains 14 to 15 per cent of manganese and is obtained by roasting franklinite, a mineral found only in several deposits near Franklin Furnace, N. J.

MANGANESE AND MANGANIFEROUS ORES.

SHIPMENTS AND PRODUCTION.

Manganese and manganiferous ore shipped in 1915.

State.	Ore containing 35 per cent of manganese or more.			Ore containing 10 to 35 per cent of manganese.			Ore containing 5 to 10 per cent of manganese.		
	Number of shippers.	Quantity (gross tons).	Value.	Number of shippers.	Quantity (gross tons).	Value.	Number of shippers.	Quantity (gross tons).	Value.
Alabama	1	200	(a)						
Arizona:									
Used for fluxing				1	1,452	(a)			
Used for other purposes	1	339	(a)						
Arkansas	7	1,288	$13,135	3	2,655	$8,742			
California	6	2,563	29,004						
Colorado:									
Used for fluxing				13	10,799	16,946	8	b 4,166	$2,656
Used for other purposes	1	150	(a)	4	15,956	41,527			
Georgia	4	3,168	33,927	1	676	(a)			
Minnesota				3	42,973	187,971			
Nevada:									
Used for fluxing				1	104,498	(a)			
Tennessee	1	150	(a)						
Texas	1	(a)	(a)						
Utah:									
Used for fluxing	1	55	(a)						
Used for other purposes	1	(a)	(a)						
Virginia	7	1,620	17,988	6	1,944	6,708			
Wisconsin							1	10,616	(a)
Undistributed		80	19,057			535,087			17,517
	31	9,613	113,111	32	180,953	796,981	9	b 14,782	20,173

a Included under "Undistributed." Survey not at liberty to publish.
b Includes 796 gross tons of ore containing less than 5 per cent manganese.

Digitized by Google

Manganese and manganiferous ore shipped in 1916.

State.	Ore containing 35 per cent of manganese or more.			Ore containing 10 to 35 per cent of manganese.			Ore containing 5 to 10 per cent of manganese.		
	Number of shippers.	Quantity (gross tons).	Value.	Number of shippers.	Quantity (gross tons).	Value.	Number of shippers.	Quantity (gross tons).	Value.
Alabama	1	(a)	(a)						
Arizona:									
Used for fluxing				1	7,392	$39,904			
Used for other purposes	5	3,060	$113,060						
Arkansas	10	6,318	180,722	6	3,632	22,665			
California	6	6,136	122,592	1	139	(a)			
Colorado:									
Used for fluxing				15	7,405	17,986	10	b 3,858	$1,029
Used for other purposes	3	110	1,670	(c)	90,850	299,012			
Georgia	1	(a)	(a)	2	(a)	(a)			
Minnesota				5	193,257	685,875	3	47,146	104,887
Montana	6	6,418	37,978						
Nevada:									
Used for fluxing				1	122,429	(a)			
Used for other purposes	2	(a)	(a)						
New Mexico	1	(a)	(a)	2	16,068	(a)			
Pennsylvania				1	451	(a)			
Tennessee	3	429	8,380						
Texas	1	(a)	(a)						
Utah:									
Used for fluxing				1	(a)	(a)			
Used for other purposes	6	1,282	22,597	1	(a)	(a)			
Virginia	15	4,417	118,342	7	7,213	28,079	2	(a)	(a)
Washington	1	(a)	(a)	1	(a)	(a)			
Wisconsin							1	3,982	6,570
Undistributed		3,304	50,937		4,967	693,908		30,487	76,715
	61	31,474	656,278	d 44	453,853	1,787,429	16	b 90,473	189,201

a Included under "Undistributed." Survey not at liberty to publish.
b Includes 1,026 gross tons of ore containing less than 5 per cent manganese.
c Not ascertained.
d Number of shippers of ore in Colorado for purposes other than fluxing not ascertained; therefore, not included in this total.

Digitized by Google

Manganese and manganiferous ore shipped in 1917:

State.	Ore containing 35 per cent of manganese or more.			Ore containing 10 to 35 per cent of manganese.			Ore containing 5 to 10 per cent of manganese.		
	Number of shippers.	Quantity (gross tons).	Value.	Number of shippers.	Quantity (gross tons).	Value.	Number of shippers.	Quantity (gross tons).	Value.
Alabama	3	264	$10,538	.....	.....	.....	.....	.....	.....
Arizona:									
Used for fluxing	.....	.....	.....	2	17,015	(a)	1	15,396	(a)
Used for other purposes	22	14,802	479,971	2	2,040	(a)	.....	.....	.....
Arkansas	13	10,140	448,511	11	9,100	263,227	.....	.....	.....
California	40	14,196	228,501	4	152	1,760	.....	.....	.....
Colorado:									
Used for fluxing	1	54	(a)	17	14,166	23,799	14	b6,380	$10,719
Used for other purposes	1	60	(a)	14	104,315	269,284	.....	.....	.....
Georgia	13	3,614	89,888	10	13,281	118,368	.....	.....	.....
Michigan	.....	.....	.....	1	52,198	(a)	.....	.....	.....
Minnesota	.....	.....	.....	8	359,573	1,826,835	2	91,590	(a)
Montana	28	61,109	1,797,842	2	1,568	(a)	.....	.....	.....
Nevada:									
Used for fluxing	.....	.....	.....	1	122,872	142,543	.....	.....	.....
Used for other purposes	6	3,450	91,907	.....	.....	.....	.....	.....	.....
New Mexico	6	2,603	54,143	1	15,900	(a)	.....	.....	.....
North Carolina	2	102	(a)	.....	.....	.....	.....	.....	.....
South Carolina	1	405	(a)	1	650	(a)	.....	.....	.....
Tennessee	13	1,996	75,066	2	83	(a)	.....	.....	.....
Texas	1	25	(a)	1	135	(a)	.....	.....	.....
Utah:									
Used for fluxing	.....	.....	.....	1	100	(a)	.....	.....	.....
Used for other purposes	6	4,195	118,927	1	36	(a)	.....	.....	.....
Virginia	18	12,360	588,806	12	17,577	131,197	3	16,819	54,771
Wisconsin	.....	.....	.....	.....	.....	.....	c1	c200,327	(a)
Wyoming	1	30	(a)	.....	.....	.....	.....	.....	.....
Undistributed	.....	.....	25,622	.....	.....	439,279	.....	.....	602,083
	175	129,405	4,109,722	91	730,759	3,036,292	c20	bc130,185	c369,769

a Included under "Undistributed." Survey not at liberty to publish.
b Includes 141 gross tons of ore containing less than 5 per cent manganese.
c Manganiferous iron ore from Wisconsin, containing approximately 5 per cent of manganese, not included in totals.

Digitized by Google

Manganese and manganiferous ore produced in the United States, 1838 to 1917, in gross tons.[a]

Year.	Ore containing 35 per cent of manganese or more.	Ore containing 10 to 35 per cent of manganese.	Ore containing 5 to 10 per cent of manganese.	Year.	Ore containing 35 per cent of manganese or more.	Ore containing 10 to 35 per cent of manganese.	Ore containing 5 to 10 per cent of manganese.
1838–1879	43,860	.....	.....	1899	9,935	(b)	
1880	5,761	.....	.....	1900	11,771	(b)	
1881	4,895	.....	.....	1901	11,995	(b)	
1882	4,532	.....	.....	1902	7,477	(b)	
1883	6,155	.....	.....	1903	2,825	(b)	
1884	10,180	.....	.....	1904	3,146	(b)	
1885	23,258		(b)	1905	4,118	(b)	
1886	30,193		(b)	1906	6,921	41,300	
1887	34,524		(b)	1907	5,604	103,844	
1888	29,198		(b)	1908	6,144	55,894	
1889	24,197		(b)	1909	1,544	68,654	
1890	19,287		(b)	1910	2,258	41,260	19,841
1891	22,452		(b)	1911	2,457	37,584	6,853
1892	13,613		(b)	1912	1,664	40,803	10,654
1893	7,718		(b)	1913	4,048	51,512	7,891
1894	6,308		(b)	1914	2,635	91,666	6,599
1895	9,547		(b)	1915	9,613	180,953	[c]14,782
1896	10,088		(b)	1916	31,474	453,853	[d]90,473
1897	11,108		(b)	1917	129,405	730,759	[e]130,185
1898	15,957		(b)		587,865	.....	.....

[a] Beginning with 1910, the figures represent ore marketed (or shipments).
[b] Manganiferous ore included in iron ore figures.
[c] Includes 796 tons of ore containing less than 5 per cent of manganese.
[d] Includes 1,026 tons of ore containing less than 5 per cent of manganese.
[e] Includes 141 tons of ore containing less than 5 per cent of manganese.

MANGANESE ORE.

PRODUCTION.

The activity in the manganese ore industry during 1917 is shown by the great increase in the number of shippers, which rose from 61 to 175, and by a greater increase in shipments, which rose from 31,474 to 129,405 tons. Although the increase in the number of shippers was greatest in California, from 6 to 40, most of the shipments represent the results of a brief campaign of prospecting the deposits in that State, of which there are known to be many. Other States that showed great increases in the number of shippers include Arizona, Georgia, Montana, and Tennessee.

Shipments of ore showed the greatest increase in Montana, the 61,109 tons shipped during 1917 being the most thus far recorded in any State for one year. More than three-fourths of the total shipments for the year were derived from districts in States west of the eastern boundary of Colorado, and a large part of this quantity came from deposits that were not recorded before the war aroused interest in manganese deposits. Further, the shipments during 1917 from this region were more than six times those during 1916. By contrast, the shipments from the well-known eastern districts in Arkansas, Georgia, Tennessee, and Virginia, with which the name "manganese" has been particularly identified for many years, contributed scarcely one-fifth of the total shipments during 1917 and only two and one-half times those from the same districts during 1916. The explanation of this inability of the eastern districts to respond quickly to the increasing demand and higher prices appears to lie in the nature of the deposits rather than in their number and size. The

Digitized by Google

material that is shipped from practically all the eastern deposits is the product of washing or concentration, and the output is therefore determined by the capacity of existing mills, and even though the mills are not complicated structures considerable time must elapse before the number can be greatly increased. On the other hand, with one exception, the western deposits yielded during 1917 material that was shipped with no more preparation than rough sorting.

The grade of the eastern material is rather better than that of the western. Although it is not possible to make an accurate calculation of the average composition of the shipments from each district in 1917, available data indicate that the eastern ores contain 2 or 3 per cent more manganese, 5 or 6 per cent less silica, and about 0.1 per cent more phosphorus than the western ores.

IMPORTS.

The following table was compiled from the records of the Bureau of Foreign and Domestic Commerce, Department of Commerce:

Manganese ore imported into the United States, 1914–1917.

	1914		1915		1916		1917	
	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.
Argentina							6,600	$40,023
Australia					488	$19,313		
Belgium	450	$5,913						
Brazil	113,924	736,769	275,579	$2,240,837	471,837	7,139,821	512,517	8,578,296
British India	103,583	504,981	36,450	194,626	51,960	401,779	48,975	362,582
Canada	64	1,357	325	12,989	756	72,496	883	40,534
Chile						18	202	6,330
Costa Rica					1,244	38,703	7,163	211,601
Cuba			5,141	69,453	30,563	514,184	44,511	612,413
France	5	1,580						
Germany	1,713	92,273	258	23,590		16		
Greece					3,000	24,318		
Japan	40	1,320	2,810	106,434	5,196	163,491	2,745	85,538
Mexico					390	7,093	345	9,790
Netherlands	2,505	52,213	50	1,792				
Panama					10,498	265,772	5,202	163,120
Portugal					289	11,997		
Russia	52,681	490,331						
United Kingdom	8,321	136,206	49	4,730	100	7,178	805	152,084
All other	8	1,177	116	1,529			[a] 24	[a] 618
	283,294	2,024,120	320,778	2,655,980	576,321	8,666,179	629,972	10,262,929

[a] Includes 4 tons, valued at $180, from British South Africa and 20 tons, valued at $438, from China.

PRODUCTION IN PRINCIPAL PRODUCING COUNTRIES.

The following table gives the latest available statistics with regard to American and foreign production of manganese ore.

So far as possible the figures are taken from the official publication of the country concerned, which is the case with Canada, Belgium, France, German Empire, India, Italy, and Spain; otherwise, Mines and Quarries, London, is used. The Geological Survey receives assistance in its foreign statistics from Mineral Industry, New York.

Digitized by Google

Manganese ore produced in principal producing countries, 1913–1917, in gross tons.

Country.	Percentage of manganese.	1913	1914	1915	1916	1917
North America:						
Canada	(?)	.....	25	180	855	131
Costa Rica	37–48	.....	.....	.....	[a] 1,244	[a] 7,163
Cuba	36–44	.....	.....	[b] 9,000	[b] 33,120	[b] 41,651
Mexico	40+	.....	.....	.....	[a] 390	[a] 345
Panama	50±	.....	.....	.....	[a] 10,498	[a] 5,202
Porto Rico	40+	.....	.....	.....	[a] 738	[a] 1,189
United States	35+	4,048	2,635	9,613	31,474	129,405
South America:						
Argentina	(?)	.....	.....	.....	.....	[a] 6,600
Brazil	38–50	120,368	180,738	284,111	495,172	524,436
Chile	40–48	.....	.....	.....	.....	[d] 202
Europe:						
Austria	(?)	16,280	[c]	[c]	[c]	[c]
Bosnia and Herzegovina	(?)	5,709	4,055	[c]	[c]	[c]
France	30+	7,610	[c]	[c]	[c]	[c]
Germany	30+	748	[c]	[c]	[c]	[c]
Greece	(?)	549	[c]	[c]	[c]	[c]
Hungary	(?)	18,706	[c]	[c]	[c]	[c]
Italy	18–45	1,596	1,623	12,379	17,960	[c]
Russia	41–48	1,289,370	[d] 703,762	[d] 8,705	[d] 8,722	[c]
Spain	29+	21,254	12,947	14,102	13,954	56,556
Sweden	(?)	3,938	3,585	7,487	3,585	[c]
United Kingdom	30+	5,393	3,437	4,640	5,140	9,942
Africa:						
Gold Coast	(?)	.....	.....	.....	[e]	[e]
Tunis	(?)	.....	.....	1,437	1,995	5,708
Union of South Africa	(?)	.....	.....	.....	.....	123
Asia:						
India	47–52	815,047	682,898	450,416	654,204	590,813
Japan	50+	18,016	16,807	25,400	7,749	[c]
Oceania:						
Australia	40+	27	6	200	488	.....

[a] Imports into United States. Production and exports not available.
[b] Figures collected by United States Geological Survey.
[c] Statistics not available.
[d] Exports.
[e] Shipments July, 1916, to November, 1917, 28,465 tons.

FERRUGINOUS MANGANESE ORES.

Although the number of shippers as well as the shipments of ferruginous manganese ore increased in most of the States during 1917, Minnesota and Michigan contributed three-fourths of the increase in total shipments. Several western districts, especially Leadville, Colo., and Silver City, N. Mex., were capable of greatly increased shipments, but their remoteness from the principal consuming centers of the Eastern States hindered marketing, and shipments from Leadville during 1917 were only 20 per cent more than in 1916, whereas shipments from Silver City were less than in 1916. All the shipments from Minnesota were derived from mines on the Cuyuna Range, and those from Michigan from the Bengal mine, Iron County.

Digitized by Google

Manganiferous silver ore shipped, 1907–1917, in gross tons.

Year.	Arizona.	Colorado.		Nevada.	Utah.
		For fluxing.	For other purposes.		
1907	.....	32,197	67,514	.....	.....
1908	.....	35,581	15,973	.....	.....
1909	.....	52,119	12,905	.....	.....
1910	.....	55,770	.....	.....	.....
1911	.....	41,753	.....	.....	.....
1912	.....	48,618	.....	.....	.....
1913	.....	49,758	.....	.....	.....
1914	.....	37,781	2,100	.....	.....
1915	[a] 1,452	14,965	15,956	104,498	55
1916	[a] 7,392	16,263	90,600	122,429	27
1917	[a] 32,009	20,546	104,169	122,872	100

[a] Ore containing more than 35 per cent of manganese sent to makers of manganese alloys not included.

Ferruginous manganese and manganiferous iron ores shipped from the Cuyuna district, Minn., 1913–1917, in gross tons.

Mine.	Ore containing 10 to 35 per cent of manganese.					Ore containing 5 to 10 per cent of manganese.					Total.
	1913	1914	1915	1916	1917	1913	1914	1915	1916	1917	
Algoma (Hoch)	.....	192	7,600	23,000	[a]84,125	.....	.....	.....	.....	.....	[a]114,917
Cuyuna Mille Lacs	[b]26,200	55,000	35,221	90,000	112,554	.....	.....	.....	.....	.....	318,975
Ferro	.....	.....	.....	14,710	([a])	.....	.....	.....	.....	.....	[a]14,710
Hillcrest	.....	.....	.....	.....	.....	.....	.....	.....	2,712	9,590	12,302
Joan, Nos. 1 and 4	.....	.....	.....	.....	8,375	.....	.....	.....	.....	.....	8,375
Mahnomen	.....	.....	.....	([c])	4,000	.....	.....	.....	[c]43,000	82,000	129,000
Mangan, Nos. 1 and 2	.....	.....	.....	30,329	52,290	.....	.....	.....	.....	.....	82,619
Merritt, No. 1	.....	.....	.....	.....	33,180	.....	.....	.....	.....	.....	33,180
Sultana	.....	.....	152	35,218	65,018	.....	.....	.....	.....	.....	100,388
	26,200	55,192	42,973	193,257	359,542	.....	.....	.....	45,712	91,590	814,466

[a] Shipments from Ferro mine included with Algoma mine for 1917. Not reported separately to the Geological Survey.
[b] Percentage of manganese not stated.
[c] Shipments from Mahnomen mine in 1916 averaged 5 to 14 per cent of manganese. Not reported in greater detail to the Geological Survey.

VALUE OF MANGANESE ORES.

In general the value of materials that contain manganese depends on the composition, the minerals present, and the condition or state of aggregation of the material. The value depends largely, of course, on the content of metallic manganese but incidentally on the absence of such substances as phosphorus, silica, copper, cobalt, and iron. For certain purposes, other things being equal, it depends on the amount of oxygen which will be liberated under certain conditions, and this is different for the several oxide minerals. If the material is to be used in the manufacture of manganese alloys in the blast furnace, it should be in coherent lumps, as fine sand and powder can not be treated to advantage. On the other hand, if the material is to be used to make dry batteries or flint glass and is not already in finely divided condition, it is crushed and pulverized.

The price offered for ore to be used to make ferromanganese is normally determined by the condition of the steel industry, and in the United States this price corresponds closely to that on the

Digitized by Google

English, French, Belgian, and German markets when allowance is made for the difference in freight rates between the mines and the place of delivery. This is true because the furnaces of these countries derive most of their ore from the same countries that supply the United States.

During 1917, however, several conditions brought about uncommon variations as well as disparities between the prices of ores and of alloys. The announcement of unrestricted submarine warfare in a zone surrounding Great Britain and France by Germany in February made the import of manganese ore to English furnaces and the export of ferromanganese exceedingly hazardous. As a result the price of ferromanganese rose rapidly, from $175 a ton in February to a maximum of $400 in July. This was followed by advances in the prices offered for ores. As shown in figure 12 (p. 681) during 1915 and 1916 the advance in the price of manganese ore followed rather slowly the advances in the price of ferromanganese. The extraordinary profit in smelting ferromanganese, in part indicated by the intervals elapsing between an advance in the price of ferromanganese and that in the price of ore, stimulated a number of new smelters in the United States to enter the field. Some of these depended solely on imported ore, but a few that were advantageously situated were led to compete for the existing supply of domestic ore, with the result that during 1917 the prices offered for domestic ore advanced rapidly, closely following advances in price of alloys, and the prices offered in several localities, notably Chicago, were appreciably higher than those in other parts of the country.

The schedule of prices announced by the Carnegie Steel Co. on May 2, 1917, is given below. These prices are about 20 cents a unit higher than those offered March 9, 1917, and 45 cents a unit higher than those offered August 25, 1916.

Schedules of prices paid per ton of 2,240 pounds for domestic manganese ore delivered at Pittsburgh, Etna, Pa., and South Chicago, Ill.

Prices are based on ores containing not more than 8 per cent silica or 0.20 per cent phosphorus and are subject to deductions as follows: For each 1 per cent in excess of 8 per cent silica there shall be a deduction of 15 cents per ton; fractions in proportion.

For each 0.02 per cent, or fraction thereof, in excess of 0.20 per cent phosphorus there shall be a deduction of 2 cents per unit of manganese per ton; fractions in proportion.

Ores containing less than 40 per cent manganese or more than 12 per cent silica or 0.225 per cent phosphorus are subject to acceptance or refusal at the buyer's option.

Settlements are based on analysis of sample dried at 212° F., the percentage of moisture in the sample as taken being deducted from the weight.

Percentage of metallic manganese in ore.	Price per unit of manganese, in cents.
Over 49	100
46 to 49	98
43 to 46	95
40 to 43	90

According to these specifications the price paid for ores ranged from $36 for 40 per ore to $50 for 50 per cent ore. In the fall of 1917 this schedule was withdrawn, and subsequently purchases were based upon specific bids for each lot, or upon special contracts.

Digitized by Google

In July, 1917, the Miami Metals Co., Chicago, Ill., offered the following schedule of prices for ore purchased during that month:

For manganese ore of normal physical structure the following prices per gross ton (2240 pounds) f. o. b. Chicago:

	Cents per unit.
35 to 37 per cent	74
37 to 39 per cent	80
39 to 41 per cent	86
41 to 43 per cent	92
43 to 45 per cent	96
45 to 47 per cent	100
47 to 49 per cent	104
49 per cent or more	108

There will be a penalty of 50 cents per ton for each per cent of silica over 10 per cent, and a bonus of 50 cents per ton for each per cent of silica under 10 per cent, also a penalty of 15 cents a ton for each 0.01 per cent phosphorus over 0.15 per cent. Material with more than 20 per cent silica and 0.25 per cent phosphorus will be subject to rejection.

In December, 1917, it was reported[1] that high-grade Indian ore had recently been sold for $1.30 per unit and similar Brazilian ore at $1.10 to $1.20 per unit, at seaboard. The following prices were also offered for domestic material by a dealer: 38 to 42 per cent of manganese, 90 cents per unit; 42 to 46 per cent, $1.00 per unit; 46 to 50 per cent, $1.10 per unit, and 50 per cent or more, $1.20 per unit.

The value of an ore adapted to use as an oxidizer in dry batteries and flint glass varies with its content of manganese dioxide and, in contradistinction to those used in metallurgic industries, does not depend, except indirectly, on its content of metallic manganese. As much of the ore of the Caucasus region, Russia, contains from 85 to 92 per cent of manganese dioxide and less than 1 per cent of iron and is therefore admirably adapted to these uses, most specifications for ores to be put to these uses before the war were such as could be met by ore from the Caucasus region but only rarely by ores from other regions. According to one manufacturer of dry batteries, as long as Caucasian ore was available there was little experimentation to determine the suitability of the several manganese minerals and the limits beyond which other elements than manganese may be present. As a result of recent experiments, it has been shown that copper, nickel, and cobalt are the most harmful elements in the ordinary dry battery and should not be present in even minute quantities. A few tenths of 1 per cent of any of these elements renders an ore unfit for this use. On the other hand, it is stated that 2 or 3 per cent of iron as oxide does not necessarily greatly affect the efficiency of a battery and that the 1 per cent limit is arbitrary. In the absence of an established schedule, such as exists in the steel industry, most of the ore is supplied to the dry-battery makers by brokers in lots ranging from 5 to 100 tons under guaranteed specifications. On account of the temporary elimination of Caucasian ore prices have risen, and it is reported that during 1917 prices ranged from $75 to $160 a ton. Few of the known deposits of the United States are capable of producing more than a small quantity of ore that contains less than 1 per cent iron and a trace of copper, nickel, and cobalt. Early in 1917 ore containing no more than 70 per cent of manganese

[1] Iron Age, vol. 100, p. 1359, Dec. 6, 1917.

Digitized by Google

dioxide was marketable for these uses. It is estimated that the present demand for manganese ore for dry batteries and flint glass is about 25,000 tons a year.

The value of ferruginous manganese ores, manganiferous iron ores, and manganiferous silver ores depends on local conditions in the metallurgic industries that consume them, as the manganese content is used only indirectly. In both Minnesota and Colorado it is customary to pay a flat rate for ore having a certain percentage of manganese, iron, silica, moisture, and phosphorus. For each additional per cent of manganese a premium is paid, and for each additional per cent of silica or mositure a penalty is charged.

Ferruginous manganese ores containing 15 to 35 per cent of manganese, less than 15 per cent of silica, and the remainder chiefly iron were sold at the mines in 1917 at prices that ranged from $4.50 to $18 a ton.

Manganiferous zinc residuum is not sold in the open market but is smelted to spiegeleisen by the only company that produces it.

MANGANIFEROUS ZINC RESIDUUM.

Unique deposits of zinc ore containing franklinite, willemite, zincite, calcite, and minor silicate and other minerals occur near Franklin Furnace, N. J. By mechanical and electromagnetic processess of separation three products are obtained from these ores, one containing the greater part of the franklinite and the remaining two the other zinc minerals. The franklinite product is first roasted with anthracite to eliminate the zinc, which is recovered as zinc oxide, and the residue, containing from 14 to 15 per cent of manganese and 40 per cent of iron, is smelted to spiegeleisen, containing 19 to 20 per cent of manganese.

Manganiferous residuum produced from zinc roasting in the United States, 1889–1917.

	Gross tons.		Gross tons.		Gross tons
1889	43,648	1900	87,110	1910	137,173
1890	48,560	1901	52,311	1911	109,296
1891	38,228	1902	65,246	1912	104,670
1892	31,859	1903	73,264	1913	102,239
1893	37,512	1904	68,189	1914	100,198
1894	26,981	1905	90,289	1915	159,318
1895	43,249	1906	93,461	1916	198,817
1896	44,953	1907	93,413	1917	155,332
1897	33,924	1908	110,225		
1898	48,502	1909	141,264		2,404,241
1899	65,010				

NOTE.—The manufacture of spiegeleisen from manganiferous residuum was begun in 1870, but there is no record of the quantity of raw material used prior to 1889.

FERROMANGANESE AND SPIEGELEISEN.

In 1917 the number of plants engaged in making ferromanganese increased to 23, and the marketed output of the alloy increased to 260,225 tons, the highest on record. At the same time the imports of ferromanganese declined to 41,969 tons, the lowest since 1904. The available supply of ferromanganese was therefore 302,194 tons.

The number of plants engaged in making spiegeleisen also increased to 17 in 1917, and the marketed output was 189,241 tons. This, with the 3,968 tons imported indicates an available supply of 193,209 tons for the year.

Digitized by Google

A list of the plants where ferromanganese and spiegeleisen were made in 1917 follows (f indicates ferromanganese; s, spiegeleisen):

s American Manganese Manufacturing Co., Dunbar, Pa.
fs Berkshire Iron Works, Sheridan, Pa.
fs Bethlehem Steel Co., Lebanon, Pa.
f Bethlehem Steel Co., Sparrows Point, Md.
f Bilrowe Alloys Co., Tacoma, Wash.
s Colorado Fuel & Iron Co., Pueblo, Colo.
f Donner Steel Co., Tonawanda, N. Y.
s T. B. Guernsey & Co. (Inc.), Graham, W. Va.
fs Juniata Furnace & Foundry Co., Newport, Pa.
f Lackawanna Iron & Steel Co., Lebanon, Pa.
fs E. J. Lavino & Co., Marietta, Pa.
fs Lebanon Blast Furnace Co., Labanon, Pa.
f E. E. Marshall, Harrisburg, Pa.
fs Miami Metals Co., South Chicago, Ill.
s New Jersey Zinc Co., Palmerton, Pa.
f Noble Electric Steel Co., Heroult, Calif.
fs Oriskany Ore & Iron Corporation, Reusens, Va.
fs Seaboard Steel & Manganese Corporation, Temple, Pa.
f Seattle Smelting Co., Seattle, Wash.
fs Southeastern Iron Corporation, Goshen, Va.
fs Southern Manganese Corporation, Anniston, Ala.
fs Tennessee Coal, Iron & Railroad Co., Bessemer and Birmingham, Ala.
fs United States Steel Corporation, Chicago, Ill., and Pittsburgh, Pa.
f Western Reduction Co., Portland, Oreg.
f Wharton Steel Co., Wharton, N. J.

Ferromanganese and spiegeleisen produced[a] in the United States, 1901–1917.

Year.	Ferromanganese.		Spiegeleisen.	
	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.
1901	59,639	(b)	231,822	(b)
1902	44,526	(b)	168,408	(b)
1903	35,961	(b)	156,700	(b)
1904	57,076	(b)	162,370	(b)
1905	62,186	(b)	227,797	(b)
1906	55,520	(b)	244,980	(b)
1907	55,918	(b)	283,430	(b)
1908	40,642	(b)	111,376	(b)
1909	82,209	(b)	142,831	(b)
1910	71,376	(b)	158,065	(b)
1911	74,602	c$4,746,541	104,013	(c)
1912	125,378	c8,282,006	102,561	(c)
1913	119,495	c9,272,269	106,980	(c)
1914	100,731	4,440,253	76,625	$1,586,139
1915	144,260	9,253,443	114,556	2,403,550
1916	224,103	30,123,493	182,837	6,158,202
1917	260,225	53,930,771	189,241	9,756,236

[a] Beginning with 1911 the figures represent product marketed (or shipped).
[b] Figures not available.
[c] Value for spiegeleisen included with that for ferromanganese.

Digitized by Google

Ferromanganese and spiegeleisen imported for consumption in the United States, 1903–1917.

Year.	Ferromanganese.		Spiegeleisen.		Total.	
	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.	Quantity (gross tons).	Value.
1903	41,519	$1,699,666	122,015	$2,709,317	163,534	$4,408,983
1904	21,813	707,037	4,623	132,461	26,436	839,498
1905	52,841	1,884,651	55,457	1,336,104	108,298	3,220,755
1906	84,359	4,953,644	103,268	2,942,940	187,627	7,896,584
1907	87,400	5,354,656	48,994	1,399,381	136,394	6,754,037
1908	44,624	1,860,664	4,579	125,054	49,203	1,985,718
1909	88,934	3,396,381	16,921	356,447	105,855	3,752,828
1910	114,228	4,341,071	25,383	489,049	139,611	4,830,120
1911	80,263	3,015,062	20,970	405,444	101,233	3,420,506
1912	99,137	3,906,920	1,015	28,094	100,152	3,935,014
1913	128,070	5,682,915	77	2,173	128,147	5,685,088
1914	82,997	3,619,607	2,870	71,147	85,867	3,690,754
1915	55,263	3,333,699	200	5,110	55,463	3,338,809
1916	90,928	9,240,528			90,928	9,240,528
1917	41,969	5,710,988	3,968	291,594	45,937	6,002,582
	1,114,345	58,707,489	410,340	10,294,315	1,524,685	69,001,804

Ferromanganese and spiegeleisen are essentially alloys of manganese, iron, and carbon, although in the ordinary process of manufacture it is impossible to prevent the presence of small quantities of silicon and phosphorus. Their use depends upon the effects produced by the addition of small quantities of manganese and carbon to molten steel. It is commonly stated that a part of the manganese combines with any oxygen in the molten steel, that the remainder increases the tensile strength of the steel, and that the carbon raises the percentage of that element to the desired proportion. The name spiegeleisen (German, mirror iron) was given on account of the highly brilliant plates that develop when the alloy with 15 to 20 per cent of manganese crystallizes. It commonly contains manganese, 20 per cent; iron, 75 per cent; and carbon, 5 per cent. The ratio of manganese to carbon is therefore 4 to 1. Ferromanganese commonly contains manganese, 78 to 82 per cent; iron, 12 per cent; and carbon, 7 per cent. The ratio of manganese to carbon is therefore about 12 to 1. There appears to be no natural division between the manganese content of spiegeleisen and ferromanganese, but 40 per cent is commonly accepted by the steel trade.

Spiegeleisen was the first alloy to be developed, and it was added to all steel made by the Bessemer and open-hearth processes until about 1875, when ferromanganese became a commercial product. For many years thereafter spiegeleisen was used only in making so-called "medium" and "high-carbon" steels (those containing more than 0.25 per cent of carbon) by the Bessemer process, whereas ferromanganese was used in making "low-carbon" steel (that containing less than 0.25 per cent of carbon). It can readily be understood that for a given quantity of manganese in the form of alloys added to the molten steel, three times as much carbon is added if spiegeleisen is used as if ferromanganese is used. During recent years many makers of steel have experimented with the use of alloys having a manganese content intermediate between that in spiegeleisen and that in ferromanganese, as well as with other alloys, such as silicomanganese. The use of several of the alloys for special purposes has been fairly

Digitized by Google

established, and although a few makers of steel have contended that in spite of the low ratio of manganese to carbon alloys containing 15 to 35 per cent of manganese could be used to make steel containing 0.10 to 0.25 per cent of carbon the practice has not come into wide use.

The foregoing summary is given to show that although a certain quantity of manganese is apparently needed in making steel by the



FIGURE 12.—Diagram showing contract prices of feromanganese, spegeleisen, and manganese ore, 1912–1917.

Bessemer and open-hearth processes, the quantity of each alloy that is needed appears to depend largely on the desired carbon content of the steel that is made but possibly may be slightly changed by local experimentation. So far as the writer is aware, there are no accurate statistical data available concerning the carbon content of different varieties of steel made in the United States and the manganese alloys used in making them. The following table has been prepared on the assumption that only ferromanganese has been used recently in making open-hearth steel and that only spiegeleisen has been used in making Bessemer steel. Even though this assumption is not

Digitized by Google

strictly true, it probably yields dependable conclusions with regard to the consumption of manganese alloys. The table disregards the small quantities of alloys exported and the difference between stocks at the beginning and end of each year.

Apparent domestic consumption of ferromanganese and spiegeleisen per ton of steel, 1901–1917.

Period.	Open-hearth steel.	Ferromanganese.		Bessemer steel.	Spiegeleisen.	
		Production and imports.	Consumed per ton of steel.		Production and imports.	Consumed per ton of steel.
	Gross tons.	*Gross tons.*	*Pounds.*	*Gross tons.*	*Gross tons.*	*Pounds.*
1901–1905	31,053,491	446,699	32.2	45,245,009	1,224,832	60.6
1906–1910	61,365,323	725,210	26.5	48,803,689	1,134,817	52.1
1911–1915	98,833,090	1,010,196	22.9	42,329,520	529,867	28.0
1916	31,415,427	315,031	22.5	11,059,039	182,837	37.0
1917	34,148,893	302,194	19.8	10,479,960	193,209	41.3

It is thought that the large increase in apparent consumption of spiegeleisen per ton of Bessemer steel since 1915 and the slight decrease in the apparent consumption of ferromanganese per ton of open-hearth steel indicate an actual increase in the use of spiegeloisen in place of ferromanganese, probably in making steel by both processes.

The diagram on page 681 showing the prices of ferromanganese and spiegeleisen is based upon quotations published by the Iron Trade Review.[1] For comparison the prices offered for manganese ore by the Carnegie Steel Co., Pittsburgh, Pa., are presented. It will be observed that the announcement of a war zone around Great Britain and France and the prospect of a declaration of war by the United States caused a spectacular rise in the prices of the alloys to the highest recorded in more than 30 years.

DOMESTIC MANGANESE DEPOSITS.

ALABAMA.

Three operators in Etowah County, Ala., reported shipments of high-grade manganese ore to furnaces in the Birmingham district in 1917.

ARIZONA.

The Bunker Hill Mines Co., Tombstone, Cochise County, Ariz., continued to produce ore, a part of which was shipped raw, and a part was treated in concentrating mills before shipping. The principal source of production in Arizona, however, was the Bisbee district, Cochise County, where the Calumet & Arizona Mining Co. and Thomas Higgins maintained regular shipments from several properties.

There was much prospecting in several other counties, notably in the Aguila district, Maricopa County, as well as in Mohave, Yavapai, Pinal, Gila, Greenlee, and Santa Cruz counties. E. L. Jones, jr., examined a number of these deposits in 1917, and a preliminary report based on his work was issued as a press bulletin. A more detailed report is in preparation.

[1] Iron Trade Review, vol. 62, p. 25, 1918.

Digitized by Google

ARKANSAS.

With the exception of several small shipments from Pike County, in western Arkansas, the output of manganese in Arkansas in 1917 came from the Batesville district in Independence and Izard counties, where there was much more activity than in 1916. Although only a few deposits in the district yielded more than several hundred tons of high-grade product, the great number that are opened and the ease with which they may be exploited permit the aggregate output to compare favorably with that of other States.

CALIFORNIA.

Manganese deposits are widespread throughout California, and in 1917 shipments were reported from 57 deposits in 21 counties. The Ladd deposit, in San Joaquin County, contributed the largest quantity, but shipments from the Tolbard mine, Imperial County, and the Braito mine, Plumas County, were also noteworthy. The counties in which there was the greatest activity, as measured by number of shipping mines, were in order, Mendocino, Alameda, Santa Clara, Plumas, Imperial, San Bernardino, San Joaquin, followed by 14 others.

Although many deposits have long been known in the first four counties, as well as others, the deposits of Imperial and San Bernardino counties that yielded considerable ore were not discovered until 1916 and 1917, when the shortage of manganese ore in the United States aroused interest in prospecting.

COLORADO.

Although there were a few attempts to mine and ship high-grade manganese ore in several counties in Colorado, including Fremont and Custer, interest in manganese in this State is particularly attached to the deposits of the Leadville district. Of 124,915 tons shipped from the district in 1917, 104,315 tons was shipped to makers of manganese alloys, and for the first time the material was sent to furnaces at Chicago, Ill., and Pittsburgh and Temple, Pa.

Umpleby[1] examined the low-grade deposits of the Leadville and Red Cliff districts in August, 1917.

GEORGIA.

Almost the entire output of manganese ore from Georgia during 1917 came from mines of the Cartersville district, Bartow County, but several deposits in Fannin, Haralson, Murray, and Paulding counties also contributed. The largest shipments came from several deposits operated by the Georgia Iron & Coal Co.

MICHIGAN.

The Bengal mine, in Iron County, Mich., continued to ship during 1917 material which contained manganese, 16.83 per cent; iron, 37.01 per cent; and silica, 5.48 per cent (dry basis).

[1] Umpleby, J. B., Leadville manganese resources: Min. and Sci. Press, vol. 115, p. 758, 1917; Manganiferous iron ore occurrences at Red Cliff, Colo.: Eng. and Min. Jour., vol. 104, p. 1140, 1917.

Digitized by Google

MINNESOTA.[1]

When the shortage of ferromanganese and high-grade ore became serious late in 1917, the larger market for spiegeleisen and low-grade ore created a greater demand for the ores of the Cuyuna range, Minn., than had been known before. The district underwent further intensive exploration, and several new mines, including the Joan Nos. 1 and 4 and Merritt No. 1, capable of shipping material containing 15 to 30 per cent of manganese, were brought to the producing stage.

MISSOURI.

Explorations in the vicinity of Cornwall, Madison County, Mo.,[2] yielded about 100 tons of material containing 40 per cent of manganese, 5 per cent of iron, and 15 per cent of silica.

MONTANA.

The active search for and exploration of manganese deposits in the Philipsburg district, Mont., begun in 1916, continued throughout 1917. In comparison with the four operators who shipped 6,380 tons from six deposits in 1916, 19 operators shipped 59,327 tons of material containing more than 35 per cent of manganese from 27 deposits in 1917. Early in 1917 it was widely recognized that the district contained the largest deposits of readily available high-grade material in the United States. The deposits were examined and described by Umpleby.[3]

It has long been known that the surficial zone of many silver and zinc-bearing lodes of the Butte district contained oxides of manganese and that the deeper zone contained rhodochrosite, carbonate of manganese, and rhodonite, silicate of manganese. Although oxidized ores had been mined as a source of silver from time to time, the first efforts were made in 1917 to mine and ship these materials as a source of manganese. The oxidized zones of several lodes, especially the Ancient, yielded small quantities of oxides, but large bodies of rhodochrosite were developed in the Emma mine, and the first shipments, containing manganese, 38.1 per cent; iron, 1.8 per cent, and silica, 6.2 per cent were made. The deposits have been described by Pardee.[4]

Other deposits near Cherry and Wigwam creeks,[5] near Renova, Madison County,[5] and near Melrose, Beaverhead County, were explored during 1917.

NEVADA.

There was a widespread search for manganese deposits in Nevada in 1917, and a number of new deposits were reported. The most noteworthy was that of the Three Kids mine, 14 miles west of Las Vegas, Clark County, although others were reported in Humboldt and White Pine counties. Shipments were made from the Three

[1] Harder, E. C., and Johnston, A. W., Notes on the geology of the iron ores of the Cuyuna district, Minn.: U. S. Geol. Survey Bull. 660, pp. 1–26, 1917. Harder, E. C., Manganiferous iron ores of the Cuyuna district, Minn.: Am. Inst. Min. Eng. Trans., vol. 58, pp. 453–484, 1918.

[2] Reported by G. L. Barnes, Cornwall, Mo.

[3] Umpleby, J. B., The manganese deposits of Philipsburg, Mont.: Min. and Sci. Press, vol. 115, p. 725, 1917.

[4] Pardee, J. T., Manganese at Butte, Mont.: U. S. Geol. Survey Bull. 690, pp. 111–130, 1918.

[5] Pardee, J. T., Some manganese deposits in Madison County, Mont.: U. S. Geol. Survey Bull. 690, pp. 131–143, 1918.

Digitized by Google

Kids deposit, as well as from those near Shafter, Elko County, and near Ely, White Pine County, previously recorded. The Prince Consolidated Mining & Smelting Co. continued to ship silver-bearing low-grade ore from its mines near Pioche.[1]

NEW MEXICO.

The Lake Valley mine, near Lake Valley, Sierra County, N. Mex., yielded a large part of the shipments of high-grade manganese ore from New Mexico during 1917. A new deposit near Water Canyon, Socorro County, also yielded considerable ore, a representative carload of which contained manganese 42.34 per cent; iron, 1.20 per cent; silica, 9.48 per cent; phosphorus, 0.027 per cent; water, 19.04 per cent. Other deposits near Rincon, Dona Ana County, and near Silver City, Grant County, shipped high-grade ore.

The low-grade deposits near Silver City[2] yielded approximately the same quantity of material as in 1916.

SOUTH CAROLINA.

Shipments of manganese ore from South Carolina in 1917 were derived from the deposits near McCormick, Abbeville County, operated by the Atlantic Mining Co.

TENNESSEE.

The manganese deposits of Tennessee attracted considerable interest during 1917, and the number of areas within which deposits are known to exist was greatly increased. Shipments were made from deposits in Bradley, Carter, Cocke, Johnson, and Loudon counties.

TEXAS.

High-grade manganese ore was shipped from the Spiller mine in Mason County, Tex., and trial shipments of low-grade material were made from recently discovered deposits near Shumla, Val Verde County.[3]

UTAH.

Several groups of claims in the Little Grand district, Grand County, Utah, were the source of regular shipments of high-grade manganese ore in 1917. Similar material was shipped from several deposits in the Tintic district, Juab and Tooele counties, and near Marysvale, Piute County.

VIRGINIA.

The great increase in the quantity of high-grade manganese ore shipped from Virginia in 1917, as compared with 1916, is due largely to the discovery and exploitation of the Miller mine, near Suiter, Bland County, which stimulated great interest in prospecting for manganese in Bland and adjoining counties.

---

[1] Umpleby, J. B., Manganese fluxing ore at Pioche, Nev.: Eng. and Min. Jour., vol. 104, p. 760, 1917.
[2] Umpleby, J. B., Manganiferous iron deposits at Silver City, N. Mex.: Eng. and Min. Jour., vol. 104, p. 921, 1917.
[3] Umpleby, J. B., Some western manganese deposits (preliminary report): U. S. Geol. Survey press bulletin, 1917.

Digitized by Google

The Kennedy mine, near Stuarts Draft; and the Crimora mine, near Crimora, Augusta County; several new deposits opened by the United States Manganese Co., near Elkton, Rockingham County; and the Powell Fort mine of the Stockwood Realty Co., Shenandoah County, shipped regularly throughout the year. A number of old deposits were reopened in many parts of the State.

Systematic studies of the manganese deposits of the Valley of Virginia were undertaken by the United States Geological Survey in cooperation with the Virginia Geological Survey. On the basis of this work, a preliminary report[1] was issued in which the location and features of six tracts which have not been exploited but which appear to contain deposits of manganese are set forth.

WYOMING.

A recently discovered deposit of manganese ore 38 miles northeast of Medicine Bow, Albany County, Wyo., was the source of a shipment of uncommonly high-grade material adapted to use in dry batteries.

FOREIGN MANGANESE DEPOSITS.

AFRICA.

GOLD COAST COLONY, WEST AFRICA.

S. H. Ford[2] describes some manganese deposits that were discovered by A. E. Kitson, a Government geologist, in 1914, at Dagwin, near Taquah. As the material was greatly needed in England, the deposits were vigorously explored and a spur from the Seccondle Railway, 200 yards distant, was built. From June, 1916, to November 7, 1917, 28,465 tons of high-grade material was shipped. The rocks near by are deeply weathered, and the associations of the manganese minerals are obscure.

TUNIS.

According to Consul E. C. Kemp,[3] 5,800 tons (metric?) of manganese ore was produced in Tunis in 1917. The exact source of the material is not stated.

ASIA.

SOUTHERN CHINA.

Consul General George E. Anderson[4] states that the conditions under which metallic minerals are sampled and purchased in southern China are not conducive to maximum production. He says that managanese ore is purchased but does not give the source of the material.

---

[1] Hewett, D. F., Stose, G. W., Katz, F. J., and Miser, H. D., Possibilities for manganese in certain undeveloped tracts in Shenandoah Valley, Va.: U. S. Geol. Survey Bull. 660, pp. 271–296, 1918.
[2] Ford, S. H., Manganese in West Africa; Min. Mag., vol. 17, p. 271, 1917.
[3] Commerce Reports, Apr. 16, 1918.
[4] Idem, June 22, 1917.

Digitized by Google

INDIA.

Consul Lucien Memminger [1] submits a statement showing the cost of mining and transporting manganese ore derived from the surface laterite deposits in the Shimoga district, State of Mysore, India. The cost of mining, transportation to the port of Marmagoa, and port charges is 26 rupees, 10 annas ($8.60) a ton.

The Iron Age [2] presents a table showing the analyses of a number of cargoes of Indian manganese ore received in the United States in 1915, 1916, and 1917. Twenty-three cargoes received in 1917 showed the following range in composition: Manganese, 50.0 to 53.1 per cent; silica, 4.98 to 7.97 per cent; phosphorus, 0.063 to 0.114 per cent; moisture, 0.335 to 1.265 per cent.

RUSSIA.[3]

According to the British consul at Batum there was a remarkable revival in the Caucasus manganese industry in 1916. The Russian [iron] works, which formerly drew most of their supplies from the Nikopol mines in south Russia, were unable to obtain sufficient ore from that source in 1916, and therefore supplies from the Caucasus deposits were in greater demand. During the 10 years preceding the war these works obtained, through the ports of Poti and Mariupol, an annual average quantity of about 2,000,000 poods [32,770 metric tons]. In 1916, however, their demands amounted to 12,000,000 poods [196,618 metric tons]. The actual quantity of ore dispatched from Tchiaturi during 1916 was 15,755,250 poods [258,146 metric tons], of which 9,650,750 poods [158,125 metric tons] were sent inland by rail via Baku and the remainder went to Poti. Of the latter quantity rather less than half was for shipment by the Black Sea route to south Russia; the remainer was added to the stocks that were in Poti at the outbreak of hostilities with Turkey and that at the end of 1916 amounted to nearly 8,000,000 poods [131,076 metric tons]. According to official figures the stock of ore at Tchiaturi at the end of 1916 was 45,000,000 poods [737,302 metric tons], and 3,000,000 poods [49,153 metric tons] was calculated to be in stock at Batum. Thus the total stock of manganese ore in the Caucasus at the end of 1916 was 56,000,000 poods [917,532 metric tons], and it would therefore appear that the production of ore in 1916 more than kept pace with the demand from the Russian market.

Notwithstanding the fact that the existing washing plants at Tchiaturi are capable of producing 45,000,000 poods [737,302 metric tons] of washed ore and that the installation of new plants at present is costly, preparations for an extension of washing plants were proceeded with during the year and several new ones were installed.

A large number of exploration certificates were issued by the Mining Department of the Caucasus in 1916 for prospecting work on petroliferous plots in many parts of Transcaucasia and the northern Caucasus, and also for similar work on manganese ore bearing lands in the district of Sharopan in the Government of Kutais.

SOUTH AMERICA.

BRAZIL.

Consul General A. L. M. Gottschalk [4] reports the exports of manganese ore from Brazil during the first six months of each year from 1913 to 1917. Later [5] he reports the monthly shipment of man-

[1] Idem, Dec. 28, 1917.
[2] Iron Age, vol. 101, p. 287, 1918.
[3] Quoted from British Board of Trade Jour., July 19, 1918. Reprinted in Commerce Reports, Aug. 8, 1917.
[4] Commerce Repts., Dec. 11, 1917.
[5] Idem, Dec. 26, 1917.

Digitized by Google

ganese ore over the Central Railroad of Brazil from the mines to Rio de Janeiro. The table follows:

Manganese ore shipped over Central Railroad of Brazil to Rio de Janeiro, 1914–1917, in tons.

Month.	1914	1915	1916	1917
January	26,468	26,735	36,025	39,843
February	17,510	22,915	32,780	37,505
March	20,510	24,587	31,441	40,700
April	16,172	24,690	34,675	46,659
May	21,058	25,138	29,400	38,747
June	26,785	20,295	37,040	51,037
July	22,720	19,060	40,394	39,158
August	14,960	21,100	40,639	58,758
September	12,450	28,330	36,338	45,059
October	21,075	30,370	40,099	60,188
November	19,620	30,635	35,940	.....
December	25,857	36,025	37,654	.....
	245,185	309,880	432,425	457,654

He also reports [1] that an American company has recently purchased four mines in the State of Bahia, the largest in the municipality of Bom-Fim, northwest of Bahia, but not well explored. Three other deposits are near the town of Nazareth, southwest of Bahia. The rate of shipment from these deposits is hindered by lack of railway facilities.

Ambassador E. V. Morgan,[2] at Rio de Janeiro, reports that the State of Minas Geraes has increased the existing export duty on manganese ore. The duty includes an ad valorem tax as well as a special tax, also based on the value. The first duty ranges from 4 per cent where the official valuation is less than 40 milreis per ton to 8 per cent where it is more than 50 milreis per ton. The special tax ranges from 1 to 3 francs per metric ton in addition for similar grades. On the basis of the proposed valuation of 120 milreis per ton, these duties equal 11.700 milreis or about $3 per metric ton.

Consul A. L. M. Gottschalk reports [3] the following destination of exports of manganese ore from Brazil in 1914, 1915, and 1916:

Manganese ore exported from Brazil, 1914, 1915, and 1916.

	1914		1915		1916	
	Quantity (metric tons).	Value.	Quantity (metric tons).	Value.	Quantity (metric tons).	Value.
United States	87,630	$713,380	266,871	$2,457,488	503,120	$7,080,809
Great Britain	23,500	154,248	10,100	73,192	.....	.....
Belgium	10,600	69,575	.....	.....	.....	.....
France	11,400	74,836	.....	.....	.....	.....
Other countries	50,500	268,414	11,700	101,747	10	145
	183,630	1,280,453	288,671	2,632,427	503,130	7,080,954

[1] Idem, July 21, 1917, p. 262. [2] Idem, Nov. 3, 1917. [3] Idem, Dec. 27, 1917.

Digitized by Google

COSTA RICA.

Yonge [1] describes the recently exploited manganese deposits on the Nicoya Peninsula, Guanacaste Province, Costa Rica. The deposits have been known for several years, but the inaccessibility of the region and the climate prevented systematic explorations until 1916. Oxides of manganese are widespread, and float is found in many stream beds, but existing explorations do not permit detailed descriptions of the associations of the deposits.

The ore is mined from surface openings, is carried by a system of tramways to two temporary piers, loaded on large lighters, and towed to steamers in the open roadstead. Rules for the maintenance of healthy conditions in a camp in a malarial region are given in detail.

Consul B. F. Chase,[2] of San Jose, Costa Rica, reports that between 300 and 400 men are engaged in mining manganese ore in Guanacaste. Deposits are found in many parts of Guanacaste. Exports of ore from Costa Rica in 1916 were 1,305 tons, and in 1917, 8,191 tons.

CUBA.

Consul H. M. Walcott [3] makes the following report concerning the manganese mining situation in eastern Cuba:

While several hundred manganese mining claims have been filed during the past year at the mining bureau of this Province, in only a small number has it been demonstrated that they may be operated at a profit, even with the present abnormally high prices paid for the ore. The lack of proper transportation facilities and of good roads is the great drawback to the development of the industry here. With three exceptions the mines have to haul their ore to the railroad in ox carts and mule carts, or by pack mules, for a distance of 3 to 15 miles, and at a cost of $3.50 to $10 a ton.

As most of the ores are of low grade and practically none come up to the standard of 48 per cent metallic manganese, it is difficult to operate at a profit under the conditions that exist. The roads that are available during the few months of the dry season become practically impassable in the season of abundant rainfall which usually occurs from April to November. Some of the American mine operators are now introducing motor trucks and tractors for transportation of the ore, and it is hoped that by this means some of the present difficulties may be overcome.

The manganese mines or claims of this Province may be divided into nine groups—Cristo, Ponupo, San Nicolas, Palmarito, Los Negros, Santa Rita, Guisa, Sabanilla, and South Coast—the most important of which are the Ponupo and Cristo.

The Ponupo group produces at present about 5,000 tons of ore a month. It is chiefly low grade, averaging from 38 to 40 per cent metallic manganese, and is rather low in silica and iron. As this group is near the line of the railroad, the ore is mined and shipped at a profit under present prices.

The Cristo group consists of several small claims which at present produce approximately 4,000 tons of ore monthly. The mineral runs slightly higher in metallic manganese and about the same in silica and iron as the Ponupo ore, but the greater part of it requires washing.

The Palmarito and Los Negros groups produce each about 1,000 tons monthly. The ore from them is high grade and very low in silica and iron.

Considerable modern machinery has recently been installed at the San Nicolas mines, and it is expected that several thousand tons monthly will soon be produced from this group.

The remaining four groups have a combined monthly production at present estimated at 1,000 tons, making the total for the Province approximately 12,000 tons monthly, all of which is exported to the United States through the ports of Santiago and Nipe.

The declared exports of manganese ore from the Province of Oriente in 1917 were valued at $567,849, of which a large proportion was shipped through the port of Santiago de Cuba, and the remainder from Antilla (Nipe).

---

[1] Yonge, A. M., Manganese deposits in Costa Rica: Eng. and Min. Jour., vol. 104, pp. 739-741, 1917.
[2] Commerce Repts., Nov. 19, 1918.
[3] Idem, Mar. 26, 1918, p. 1146.

Digitized by Google

HONDURAS.

Consul W. F. Boyle, Puerto Cortes, Honduras, reports [1] that residents of that district advise him that they have discovered a deposit of manganese ore within 2 miles of the Honduras National Railroad. It is stated that graphite, gold, and silver accompany the manganese.

PORTO RICO.

According to George Troutmann,[2] of Ponce, Porto Rico, manganese deposits were exploited during 1917 and 1918 near the town of Juana Diaz, 14 miles east of Ponce. Here manganese oxides occur in pockets in weathered marble, but their extent can not be determined in advance of mining. The analysis of a representative shipment of 2,000 sacks follows: Manganese dioxide, 86.52 per cent (manganese 56.75 per cent); iron, 0.34 per cent; copper, 0.10 per cent; sulphur, 0.04 per cent; phosphorus, 0.037 per cent; silica, 2.26 per cent; moisture, 5.53 per cent. The deposits occur at an elevation of about 950 feet, and the product is carried by pack animals 2 miles to a good wagon road by which the distance to Ponce is 12 miles.

The collector of customs of San Juan reports that 738 long tons of manganese ore was shipped from the island in 1916 and 1,189 long tons in 1917.

OCEANIA.

NEW ZEALAND.

Consul General A. A. Winslow, of Auckland, New Zealand, has forwarded [3] to the Bureau of Foreign and Domestic Commerce at Washington, correspondence with P. E. Cheal, of Cameron Road, Remuera, Auckland, in which a manganese deposit in the Otau district is described. The deposit lies 3 miles from Otau, and 35 miles south of Auckland, but if the deposit were to be exploited, it would be best to construct a tramway to Hauraki Gulf. The deposit appears to be a vertical lode, at least 10 feet thick, which crops out conspicuously along a ridge 1,400 feet above sea level. It is estimated that 16,000 to 18,000 tons of unusually high-grade material may be readily mined above the lowest workings, 76 feet below the outcrop.

UNION OF SOUTH AFRICA.

A. B. Welch [4] describes manganese deposits at seven localities in South Africa that lie at distances of 12 to 150 miles from Cape Town. Two of the three most valuable deposits are lodes of oxides in sandstone that range from 3 to 8 feet in width and are estimated to contain respectively about 2,000 and 8,000 tons of material that carries more than 35 per cent of manganese. The third deposit covers an area of about 600 by 900 feet on the crest of a hill of sandstone, from which a hot spring issues. Explorations show that in this deposit manganese oxides persist to a depth of at least 20 feet and indicate that 500,000 tons of material containing 30 per cent of manganese and 18 per cent of iron may be present. The origin of this deposit is obscure.

---

[1] Commerce Repts., Aug. 28, 1918.
[2] Letter dated Apr. 7, 1918.
[3] Letter dated Mar. 6, 1917.
[4] Manganese deposits of the southwest districts of the Cape Province, 10 pp., Dept. Mines and Industries, 1917.

Digitized by Google

BIBLIOGRAPHY OF MANGANESE DEPOSITS.

The following bibliography includes most of the authoritative and comprehensive reports that describe manganese deposits in the United States, as well as most foreign countries. It can not be considered complete. In preparing it the aim has been to present such references as would permit one who wished to become familiar with the present state of knowledge concerning manganese deposits, as well as their distribution, to do so in the minimum length of time. This scope necessarily eliminates many short articles that are essentially progress reports concerning a single mine or minor district as well as a few reports that are not readily accessible.

GENERAL.

BEYSCHLAG, F., KRUSCH, P., and VOGT, J. H. L., Die Lagerstätten der nutzbaren Mineralien und Gesteine, 3 vols., 1910.

DEMORET, L., Les principaux gisements des minérais de manganèse du monde: Annales des mines de Belgique, pp. 809–901, 1905.

EMMONS, W. H., The principles of economic geology, pp. 508–511, 1918.

FACH, E., Le minéral de manganèse, 44 pp. Paris, H. Dunod & E. Pinat, 1914.

FERMER, L. L., The manganese deposits of India: India Geol. Survey Mem., vol. 37, 4 parts, 1909.

HARDER, E. C., Manganese deposits of the United States; U. S. Geol. Survey Bull. 427, 1910.

LINDGREN, WALDEMAR, Mineral deposits, pp. 251–253, 315–321, 1913.

PENROSE, R. A. F., jr., Manganese, its uses, ores, and deposits: Arkansas Geol. Survey Ann. Rept. for 1890, vol. 1, 1893.

STELZNER, A. W., and BERGEAT, A., Die Erzlagerstätten, 1904–1906.

NORTH AMERICA.

CANADA.

NEWFOUNDLAND.

DALE, N. C., Manganese deposits of Conception and Trinity bays (Newfoundland): Geol. Soc. America Bull., vol. 25, pp. 73–74, 1914.

——— The Cambrian manganese deposits of Conception and Trinity bays (Newfoundland): Am. Philos. Soc. Proc., vol. 54, pp. 371–456, 1915.

NOVA SCOTIA.

KRAMM, H. E., The occurrence of manganese at New Ross, Nova Scotia: Canadian Min. Jour., vol. 33, p. 660, 1913.

UNITED STATES.

ALABAMA.

GIBSON, A. M., Report on the structure of the Murphrees Valley, Ala.: Alabama Geol. Survey Rept., 1893, pp. 112–119.

ARIZONA.

ALLEN, M. A., and BUTLER, G. M., Manganese: Arizona Bur. Mines Bull. 91, pp. 32, 1918.

JONES, E. L., JR., Some manganese deposits in western Arizona (preliminary report): U. S. Geol. Survey press bulletin, 1917.

ARKANSAS.

JOSLIN, G. A., Manganese in west-central Arkansas: Min. and Sci. Press, vol. 113, pp. 947–948, 1916.

MISER, H. D., Manganese deposits of the Caddo Gap and De Queen quadrangles, Ark.: U. S. Geol. Survey Bull. 660, pp. 59–122, 1917.

PENROSE, R. A. F., jr., Manganese, its uses, ores, and deposits; Arkansas Geol. Survey Ann. Rept. for 1890, vol. 1, 1893.

Digitized by Google

CALIFORNIA.

DOLBEAR, S. H., The Ladd manganese mine: Min. and Sci. Press, vol. 110, p. 258, 1915.

——— The manganese industry in California: Min. and Sci. Press, vol. 110, p. 172, 1915.

——— Manganese and chromium in California: California State Min. Bur. Bull. 76, pp. 9–100, 1918.

COLORADO.

ARGALL, P., Siderite and sulphides in Leadville ore deposits: Min. and Sci. Press, vol. 104, pp. 50–54, 128–134, 1914.

EMMONS, S. F., Geology and mining industry of Leadville, Lake County, Colo.: U. S. Geol. Survey Second Ann. Rept., pp. 201–290, 1882.

EMMONS, S. F., and IRVING, J. D., The Downtown district of Leadville, Colo.: U. S. Geol Survey Bull. 320, p. 21, 1907.

MEANS, A. H., Geology and ore deposits of Red Cliff, Colo.: Econ. Geology, vol. 10, pp. 1–27, 1915.

UMPLEBY, J. B., Leadville manganese resources: Min. and Sci. Press, vol. 115, p. 758, 1917.

——— Manganiferous iron ore occurrences at Red Cliff, Colo.: Eng. and Min. Trans., vol. 104, pp. 1140–1141, 1917.

GEORGIA.

BREWER, W. M., The manganese ores of Georgia: Alabama Indust. and Sci. Soc. Proc., vol. 4, pt. 2, p. 72, 1894.

HAYES, C. W., Manganese ores of the Cartersville district, Ga.: U. S. Geol. Survey Bull. 213, p. 232, 1903.

LAFORGE, LAURENCE, Manganese ore in the Cartersville district, Ga. (preliminary report): U. S. Geol. Survey press bulletin, 1918.

WATSON, T. L., Geological relations of the manganese ore deposits of Georgia: Am. Inst. Min. Eng. Trans., vol. 34, p. 207, 1904.

——— Preliminary report on the manganese deposits of Georgia: Georgia Geol. Survey Bull. 14, 1908.

KANSAS.

WHITAKER, W. A., and TWENHOFEL, W. H., Manganese in the Dakota sandstone of central Kansas: Econ. Geology, vol. 12, pp. 473–475, 1917.

MARYLAND.

HEWETT, D. F., Some manganese deposits in Virginia and Maryland: U. S. Geol. Survey Bull. 640, pp. 37–71, 1916.

SINGEWALD, J. T., jr., Manganese in Maryland: Maryland Geol. Survey, vol. 9, pp. 325–327, 1911.

MINNESOTA.

HARDER, E. C., Notes on the geology and iron ores of the Cuyuna district, Minn.: U. S. Geol. Survey Bull. 660, p. 1–26, 1917.

——— Manganiferous iron ores of the Cuyuna district, Minn.: Am. Inst. Min. Eng. Bull., September, 1917, pp. 1313–1344.

MCCARTHY, E. P., Manganiferous iron ores of the Cuyuna range: Eng. and Min. Jour., vol. 100, p. 400–402, 1915.

NEWTON, E., Manganiferous iron ores of the Cuyuna district, Minn.: Minneapolis School of Mines Exper. Sta. Bull. 95, pp. 1–126, 1918.

VAN HISE, C. R., and LEITH, C. K., The geology of the Lake Superior region: U. S. Geol. Survey Mon. 52, pp. 211–216, 488, 604–605, 1911.

MONTANA.

EMMONS, W. H., and CALKINS, F. C., Geology and ore deposits of the Philipsburg quadrangle, Mont.: U. S. Geol. Survey Prof. Paper 78, pp. 209–212, 1913.

PARDEE, J. T., Manganese at Butte, Mont.: U. S. Geol. Survey Bull. 690, pp. 111–130, 1918.

——— Some manganese deposits in Madison County, Mont.: U. S. Geol. Survey Bull. 690, p. 131–143, 1918.

UMPLEBY, J. B., The manganese deposits of Philipsburg, Mont.: Min. and Sci. Press, vol. 115, p. 725, 1917.

WEED, W. H., Geology and ore deposits of the Butte district, Mont.: U. S. Geol. Survey Prof. Paper 74, pp. 69, 79, 1912.

Digitized by Google

NEVADA.

HALE, F. A., jr., Manganese deposits of Clark County, Nev.: Eng. and Min. Jour., vol. 105, pp. 775–777, 1918.
PENROSE, R. A. F., jr., A Pleistocene manganese deposit near Golconda, Nev.: Jour. Geology, vol. 1, p. 275, 1893.
UMPLEBY, J. B., Manganese fluxing ore at Pioche, Nev.: Eng. and Min. Jour., vol. 104, p. 760, 1917.

NEW JERSEY.

SPENCER, A. C., U. S. Geol. Survey Geol. Atlas, Franklin Furnace folio (No. 161), p. 24, 1908.
WOLFF, J. E., Zinc and manganese deposits of Franklin Furnace, N. J.: U. S. Geol. Survey Bull. 213, p. 214, 1903.

NEW MEXICO.

UMPLEBY, J. B., Manganiferous iron deposits at Silver City, N. Mex.: Eng. and Min. Jour., vol 104, p. 931, 1917.
WELLS, E. H., Manganese in New Mexico: New Mexico State School of Mines Bull. 2, pp. 1–85, 1918.

NORTH CAROLINA.

PRATT, J. H., Manganese mining industry in North Carolina, 1905: North Carolina Geol. Survey Econ. Paper 6, pp. 29–32, 1902.

OKLAHOMA.

HEWETT, D. F., Manganese and manganiferous ores in 1912: U. S. Geol. Survey Mineral Resources, 1912, pt. 1, p. 219, 1913.
REEDS, C. A., Geology and mineral resources of the Arbuckle Mountains, Okla.: Oklahoma Geol. Survey Bull. 3, pp. 54–59, 1910.

OREGON.

PARDEE, J. T., Manganiferous ore in Lake Creek district, Jackson County, Oreg. (preliminary report): U. S. Geol. Survey press bulletin, 1918.

SOUTH CAROLINA.

HAFER, C., Manganese in South Carolina: Eng. and Min. Jour., vol. 98, p. 1135, 1914.
PETRE, R. W., Manganese in South Carolina: Eng. and Min. Jour., vol. 101, p. 1019, 1916.

TENNESSEE.

NELSON, W. A., A new manganese deposit in Tennessee: Resources of Tennessee; vol. 1, pp. 220–228, Tennessee Geol. Survey, 1911.
PURDUE, A. H., Manganese deposits of Bradley County, Tenn.: Resources of Tennessee, vol. 8, pp. 46–47, Tennessee Geol. Survey, 1918.
STOSE, G. W., and SCHRADER, F. C., Manganese deposits of East Tennessee: Resources of Tennessee, vol. 8, pp. 153–207, 231–324, Tennessee Geol. Survey, 1918.
WATKINS, J. H., Manganese in Tennessee: Eng. and Min. Jour., vol. 102, p. 545, 1916.

TEXAS.

PAIGE, SIDNEY, Mineral resources of the Llano-Burnet region, Tex.: U. S. Geol. Survey Bull. 450, pp. 82–83, 1911.
ROBERTS, J. R., and NASH, J. P., The geology of Valverde County: Texas Univ. Bull. 1803, 1918.

UTAH.

PARDEE, J. T., Manganese in the Green River district, Utah (preliminary report): U. S. Geol. Survey press bulletin, 1918.
——— Manganese ore in the Tintic district, Utah (preliminary report): U. S. Geol. Survey press bulletin, 1918.

VERMONT.

JONES, R. V., Manganese deposits of South Wallingford, Vt.: Eng. and Min. Jour., vol. 105, p. 779, 1918.

Digitized by Google

VIRGINIA.

BALL, S. M., Manganese deposits of Virginia: Eng. and Min. Jour., vol. 87, p. 1056, 1909.

HALL, C. E., Geological notes on the manganese ore deposits of Crimora, Va.: Am. Inst. Min. Eng. Trans., vol. 20, p. 46, 1892.

HEWETT, D. F., Some manganese mines in Virginia and Maryland: U. S. Geol. Survey Bull. 640, pp. 37–71, 1916.

HEWETT, D. F., STOSE, G. W., KATZ, F. J., and MISER, H. D., Possibilities for manganese ore in certain undeveloped tracts in Shenandoah Valley, Va.: U. S. Geol. Survey Bull. 660, pp. 271–296, 1918.

JUDD, E. K., The Crimora manganese mine: Eng. and Min. Jour., vol. 83, p. 478, 1907.

WATSON, T. L., Mineral resources of Virginia, pp. 235–258, Virginia-Jamestown Exposition Commission, 1907.

ANONYMOUS, Mining of manganese ore in Virginia: Iron Age, vol. 97, p. 776, 1916.

WASHINGTON.

JENKINS, O. P., Two manganese deposits in northern Washington: Eng. and Min. Jour., vol. 105, p. 1082, 1918.

PARDEE, J. T., Manganese in the Olympic region, Wash. (preliminary report): U. S. Geol. Survey press bulletin, 1918.

WYOMING.

JONES, E. L., jr., Manganese ore in Wyoming (preliminary report): U. S. Geol. Survey press bulletin, 1918.

MEXICO.

BIDDLE, C., Notes on Magdalena Bay, Mexico: Eng. and Min. Jour., vol. 82, p. 361, 1906.

WALLACE, H. V., Deposits of manganese in Lower California: Min. and Eng. World, vol. 35, pp. 103–104, 1911; Min. and Sci. Press, vol. 103, pp. 201–202, 1911.

WEST INDIES AND CENTRAL AMERICA.

COSTA RICA.

YONGE, A. M., Manganese deposits in Costa Rica: Eng. and Min. Jour., vol. 104, pp. 739–741, 1917.

CUBA.

BROWN, H. C., Mineral resources of Cuba in 1901, p. 24.

HAYES, C. W., VAUGHAN, T. W., and SPENCER, A. C., A geological reconnaissance of Cuba, p. 62, 1901.

SOUDER, HARRISON, Mineral deposits of Santiago, Cuba: Am. Inst. Min. Eng. Trans., vol. 35, p. 308, 1904.

SPENCER, A. C., Manganese deposits of Santiago, Cuba: U. S. Geol. Survey Bull. 213, p. 251, 1903.

——— Manganese deposits of Santiago Province, Cuba: Eng. and Min. Jour., vol. 74, p. 247, 1902.

DOMINICAN REPUBLIC.

DE GARSTON, E. M., Board of Trade Jour. (London), vol. 61, pp. 450–452, 1907.

PANAMA.

CHIBIAS, E. J., Manganese deposits of the Department of Panama, Republic of Colombia: Am. Inst. Min. Eng. Trans., vol. 27, p. 63, 1897.

WILLIAMS, E. G., The manganese industry of the Department of Panama, Republic of Colombia: Am. Inst. Min. Eng. Trans., vol. 33, pp. 197–234, 1902.

ST. MARTIN.

Daily Cons. and Trade Reports, May 23, 1912.

Digitized by Google

SOUTH AMERICA.

BRAZIL.

BRANNER, J. C., The manganese deposits of Bahia and Minas, Brazil: Am. Inst. Min. Eng. Trans., vol. 29, p. 756, 1899.
DERBY, O. A., On the manganese deposits of the Queluz (Lafayette) district, Minas Geraes: Am. Jour. Sci., 4th ser., vol. 12, p. 18, 1901.
——— On the original type of manganese ore deposits of the Queluz district, Brazil: Am. Jour. Sci., 4th ser., vol. 25, p. 213, 1908.
FRAZER, R., Bahia, Brazil: Daily Cons. and Trade Reports., 1914, p. 476.
HARDER, E. C., The geology of central Minas Geraes, Brazil: Jour. Geology, vol. 23, pp. 404–406, 1915.
——— Manganese ores of Russia, India, Brazil, and Chile: Am. Inst. Min. Eng. Trans., vol. 56, pp. 31–68, 1916.
LUSTOSA, JOAQUIN, and BRANNER, J. C., Manganese deposits of Morro da Mina, Brazil: Eng. and Min. Jour., vol. 86, pp. 496–497, 1908.
SCOTT, H. K., The manganese ores of Brazil: Iron and Steel Inst. Jour., vol. 1, p. 179, 1900.
SINGEWALD, J. T., and MILLER, B. L., Manganese ores of the Layette district, Minas Geraes, Brazil: Am. Inst. Min. Eng. Trans., vol. 56, pp. 7–30, 1916.
——— High-grade manganese ores of Brazil: Iron Age, vol. 97, p. 417, 1916.

CHILE.

HARDER, E. C., Manganese ores of Russia, India, Brazil, and Chile: Am. Inst. Min. Eng. Trans., vol. 56, pp. 31–68, 1916.

EUROPE.

AUSTRIA.

NASKE, T., Manganese ore in Austria: Stahl und Eisen, vol. 28, pp. 543–547, 1907.
SCOTT, H. K., Manganese ores of the Bukowina: Iron and Steel Inst. Jour., vol. 94, pp. 288–355, 1916.

BULGARIA.

SCOTT, H. K., Notes on some Bulgarian mineral deposits: Inst. Min. and Met. Bull. 103, 1913.

GERMANY.

KERN, J., Zur Frage der Mangan-versorgung Deutschlands: Bergwirtschaftliche Mitteilungen, Jahrg. 4, pp. 49–59, 1913.
SCHEFFER, ——, The importance of manganese and manganiferous ores in German industry: Glückauf, vol. 49, pp. 2056, 2111, 2151, 1913.

RUMANIA.

BUTUREANV, V. C., The ores of manganese and iron of the crystalline massif of Broskeni, Rumania: Soc. franç. min. Bull., vol. 40, pp. 164–177, 1917.

RUSSIA.

DRAKE, FRANK, The manganese industry of the Caucasus: Am. Inst. Min. Eng. Trans., vol. 28, p. 191, 1898.
CAULDWELL, F. W., Batum, Russia: Daily Cons. and Trade Reports, May 7, 1912.
DE HAUPTICK, E., Russia in 1912: Min. Jour. (London), vol. 100, p. 6, 1912.
SCOTT, H. K., Discussion of paper by E. C. Harder: Am. Inst. Min. Eng. Trans., vol. 56, pp. 68–74, 1916.

SPAIN.

HOYER, ——, Contributions to the knowledge of the manganese deposits of the Province of Huelva: Zeitschr. prakt. Geologie, vol. 19, pp. 407–438, 1911.

Digitized by Google

AFRICA.

BELGIAN CONGO.

GUILLEMAIN, C., On the knowledge of the ore deposits in the Province of Katanga, Belgian Congo Colony: Zeitschr. prakt. Geologie, vol. 21, p. 333, 1913.

TUNIS.

Manganese ore in Tunis: Iron and Steel Inst. Jour., vol. 3, p. 497, 1908 (quoted from Rassegna mineraria, vol. 28, pp. 233–236).

WEST AFRICA.

FORD, S. H., Manganese in West Africa: Min. Mag., vol. 17, p. 271, 1917.

ASIA.

BORNEO.

Manganese ore in Borneo: Iron and Steel Inst. Jour., vol. 3, p. 329, 1907. Abstracted from Board of Trade Jour., London, vol. 58, p. 228.

INDIA.

FERMOR, L. L., The manganese deposits of India: India Geol. Survey Mem., vol. 37, pts. I, II, III, IV, 1909.
CARTER, H. A., Manganese mining in British India: Min. and Sci. Press, vol. 103, pp.834–835, 1911.
Quinquennial review of the mineral production of India: India Geol. Survey Rec., vol. 46, pp. 135–139, 1915.

JAPAN.

SNODGRASS, J. H., Manganese mining in Japan: Min. World, vol. 30, p. 790, 1909.

PHILIPPINES.

SMITH, W. D., The asbestos and manganese deposits of Ilocos Norte: Philippine Jour. Sci., vol. 2, No. 3, p. 145, 1907.
FANNING, P. R., Manganese deposits of the Philippine Islands: Mineral Resources Philippine Islands, pp. 42–47, 1911.

Digitized by Google

GOLD, SILVER, COPPER, LEAD, AND ZINC IN NEW MEXICO.[1]

(MINES REPORT.)

By CHARLES W. HENDERSON.

PRODUCTION.

The total value of the gold, silver, copper, lead, and zinc produced in New Mexico from ores and gravels in 1917 amounted to $34,896,936, as compared with $30,827,767 in 1916, an increase of $4,069,169, or 13 per cent. There were 192 producing mines, of which 177 were deep and 15 were placer, a decrease of 14 deep mines and of 4 placers. The output of gold was 51,478.64 fine ounces, valued at $1,064,158, a decrease of 15,398.83 fine ounces in quantity and of $318,322 in value. The output of silver was 1,394,365 fine ounces, valued at $1,148,957, a decrease of 371,909 fine ounces in quantity and of $13,251 in value. The output of copper was 105,568,000 pounds, an increase of 12,820,711 pounds; the output of lead (calculated as lead in lead bullion and lead in leaded zinc oxide) was 9,108,804 pounds, an increase of 894,615 pounds; and the output of zinc (calculated as spelter and as zinc in leaded zinc oxide) was 30,200,000 pounds, a decrease of 6,370,649 pounds.

Mine production of gold, silver, copper, lead, and zinc in New Mexico, 1904–1917.

Year.	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead.	Zinc.	Total value.
	Short tons.		*Fine oz.*	*Pounds.*	*Pounds.*	*Pounds.*	
1904	102,339	$381,930	214,553	4,972,170	3,122,872	13,403,835	$1,961,390
1905	145,629	317,510	369,192	6,126,025	1,510,209	15,142,254	2,460,535
1906	207,691	298,019	491,127	7,028,670	2,987,369	17,292,655	3,203,739
1907	219,992	329,982	705,544	10,990,015	3,809,881	750,085	3,239,823
1908	135,434	298,757	406,044	6,112,610	873,763	3,576,516	1,525,091
1909	164,156	239,491	397,783	5,393,146	5,029,767	13,085,945	2,070,368
1910	191,865	482,424	843,987	4,614,396	4,320,841	18,088,129	2,691,090
1911	232,699	762,808	1,354,540	4,057,040	2,966,222	10,237,176	2,704,843
1912	1,352,286	784,446	1,536,701	34,030,964	5,494,018	13,566,637	8,527,955
1913	2,217,660	881,926	1,631,273	56,308,706	3,946,304	16,523,161	11,694,002
1914	2,232,853	1,171,696	1,777,445	59,307,925	1,763,641	18,403,392	11,049,982
1915	2,797,072	1,461,105	2,006,531	76,788,366	4,542,361	25,404,064	19,279,468
1916	3,870,950	1,382,480	1,766,274	92,747,289	8,214,189	36,570,649	30,827,767
1917	4,576,827	1,064,158	1,394,365	105,568,000	9,108,804	30,200,000	34,896,936
Increase or decrease, 1917.	+705,877	−318,322	−371,909	+12,820,711	+894,615	−6,370,649	+4,069,169

[a] Includes placer production.

[1] For discussion of the geology of the districts mentioned in the following pages the reader is referred to the bibliography appended to the report for 1912 in Mineral Resources for 1912, pt. 1, p. 819, 1913; to U. S. Geol. Survey Bull. 507 (the mining districts of the western United States, by J. M. Hill, with a geologic introduction by Waldemar Lindgren), 1912; and to U. S. Geol. Survey Prof. Paper 68 (The ore deposits of New Mexico, by Waldemar Lindgren), 1910.

Digitized by Google

GOLD.

The gold produced from New Mexico ores and gravels in 1917 amounted to 51,478.64 fine ounces, valued at $1,064,158, as against 66,877.47 fine ounces, valued at $1,382,480, in 1916, a decrease of 15,398.83 fine ounces in quantity and of $318,322 in value. Colfax and Lincoln counties produced 17,268.67 fine ounces, valued at $356,975, or nearly 34 per cent of the total output of the State; Grant County produced 19,565.08 fine ounces, valued at $404,446, or 38 per cent; and Socorro County produced (chiefly from the siliceous mines at Mogollon) 12,616.49 fine ounces, valued at $260,806, or nearly 25 per cent of the total. Dry and siliceous ores yielded 39,496.71 ounces, valued at $816,469, or 77 per cent of the total. Copper ores contained 10,876.11 fine ounces, valued at $224,829, or 21 per cent of the total, chiefly from Central and Lordsburg districts, Grant County. Lead ores furnished 367.20 fine ounces, valued at $7,591, chiefly from the Victorio district, Luna County, and the Magdalena district, Socorro County. Coppper-lead ores furnished a small quantity of gold. The production of placer gold amounted to 589.16 fine ounces, valued at $12,179.

SILVER.

The silver produced from New Mexico ores and gravels in 1917 amounted to 1,394,365 fine ounces, valued at $1,148,957, as compared with 1,766,274 fine ounces, valued at $1,162,208, in 1916, a decrease of 371,909 fine ounces in quantity and of $13,251 in value. Of the total quantity Socorro County contributed 859,892 fine ounces, or 62 per cent, most of it from siliceous ore from the Mogollon district and the remainder from mixed ores of the Magdalena district. Grant County contributed 487,558 fine ounces, or 35 per cent of the total, chiefly from the Lordsburg district, though a considerable quantity came from the Central district. The output of silver from Grant and Socorro counties combined was 97 per cent of the total.

Dry and siliceous gold and silver ore, chiefly from Socorro and Grant counties, produced 966,006 fine ounces of silver, or 70 per cent of the total; copper ores chiefly from Grant and Socorro counties produced 315,877 ounces, or 23 per cent; lead ores, chiefly from the Central district, Grant County, the Victorio district, Luna County, and the Magdalena district, Socorro County, produced 70,021 ounces, or 5 per cent; copper-lead ores, chiefly from the Central district, Grant County, produced 29,600 ounces, or 2 per cent.

COPPER.

In 1917 the copper produced in New Mexico amounted to 105,568,000 pounds, valued at $28,820,064, an increase of 12,820,711 pounds and $6,004,231, as compared with the output in 1916. Grant County produced 101,373,641 pounds, or 96 per cent of the total, most of it the output of the Chino Copper Co., at Santa Rita, and of the Lordsburg and Burro Mountain districts. The increase for the year in Grant County was 13,589,096 pounds, which included an increase of 7,971,815 pounds in the Central district, and an increase of 6,245,026 in the Burro Mountain district. There was a

Digitized by Google

decrease of 493,223 pounds in the Lordsburg district. The output of Otero County decreased 352,236 pounds and that of Santa Fe County decreased 1,753,467 pounds; but that of Socorro County increased 1,686,483 pounds.

Copper ores, chiefly from Grant, Otero, Santa Fe, Socorro, and Torrance counties, yielded 101,280,755 pounds, or 96 per cent of the total; dry and siliceous gold and silver ore, chiefly from the dry ore of Otero County and from the siliceous ore of Lordsburg district, Grant County, yielded 3,566,170 pounds, or 3 per cent; lead ores, chiefly from the Magdalena district, Socorro County, yielded 195,950 pounds; and copper-lead ores, chiefly from the Central district, Grant County, 482,372 pounds.

LEAD.

In 1917 the lead produced amounted to 9,108,804 pounds, valued at $783,357, an increase of 894,615 pounds in quantity and of $216,578 in value.

The principal lead-producing districts were the Central district, Grant County; the Magdalena district, Socorro County; the Cooks Peak and Victorio districts, Luna County. Socorro County produced 4,886,803 pounds; Grant County, 3,224,477 pounds; and Luna County, 721,177 pounds. Lead ores produced 5,635,818 pounds; zinc and lead-zinc ores, 2,479,132 pounds; and copper-lead ores, 690,320 pounds—the combined content of these classes of ores representing 97 per cent of the total.

ZINC.

The total zinc, whether marketed as spelter or as oxide, recoverable from crude ore and concentrates shipped from New Mexico in 1917, calculated in terms of spelter and zinc in the various forms of zinc oxide, was 30,200,000 pounds, valued (in terms of the Survey's average price of zinc for the year) at $3,080,400.

Mines producing zinc in New Mexico in 1917 were at Kelly, Socorro County; in the Central and Pinos Altos districts, Grant County; Cooks Peak, Florida Mountains, and Tres Hermanas districts, Luna County; and Cerillos district, Santa Fe County.

Zinc ore and concentrates marketed in New Mexico, 1916–17, and average assay of zinc.

Year.	Quantity.	Average assay.
	Short tons.	*Per cent.*
1916	74,944	29.16
1917	62,573	29.84
Decrease	12,371	.....

Digitized by Google

OUTPUT OF ORE AND METAL CONTENT.

Ore and metals produced in New Mexico in 1917.

Source.	Quantity.	Gold.	Silver.	Copper.	Lead.	Zinc.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Copper ore	4,188,027	10,876.11	315,877	101,280,755	92,673	.....
Dry ore	221,662	39,496.71	966,006	3,566,170	210,861	.....
Lead ore	17,426	367.20	70,021	195,950	5,635,818	.....
Lead-copper ore	3,684	88.74	29,600	482,372	690,320	.....
Zinc ore	135,129	.47	3,381	436	1,395,066	28,811,431
Lead-zinc	10,899	60.25	9,388	42,317	1,084,066	1,388,569
Total ores	4,576,827	50,889.48	1,394,273	105,568,000	9,108,804	30,200,000
Placers	.....	589.16	92	.....	.....	.....
	4,576,827	51,478.64	1,394,365	105,568,000	9,108,804	30,200,000

PLACER OUTPUT.

Placer output in New Mexico in 1917.

County.	Gold.		Silver.		Total value.
	Quantity.	Value.	Quantity.	Value.	
	Fine ounces.		*Fine ounces.*		
Colfax	277.62	$5,739	34	$28	$5,767
Grant	152.53	3,153	47	39	3,192
Lincoln	3.10	64	.....	.....	64
Otero	35.65	737	3	2	739
Santa Fe	104.25	2,155	6	5	2,160
Sierra	16.01	331	2	2	333
Total 1917	589.16	12,179	92	76	12,255
Total 1916	537.74	11,116	72	47	11,163
Increase	51.42	1,063	20	29	1,092

CONTENT OF ORES.

Content of copper ores sold or treated in New Mexico in 1917.

County.	Ore.	Gold.	Silver.	Copper.	Lead.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*
Colfax	21	.....	4	3,882	.....
Dona Ana	66	.....	126	7,660	.....
Grant	4,132,671	10,266.94	211,353	97,640,974	58,538
Guadalupe	74	.....	40	4,022	.....
Lincoln	113	.....	74	13,172	.....
Mora	37	.....	40	6,315	.....
Otero	8,943	258.28	2,200	476,124	11,994
Rio Arriba	27	.10	392	2,802	.....
Sandoval	20	.....	153	12,901	.....
Santa Fe	7,062	338.29	6,763	400,143	.....
Sierra	47	4.00	50	9,678	.....
Socorro	36,725	1.01	93,069	2,495,708	21,761
Taos	52	6.04	301	6,748	54
Torrance	2,169	1.45	1,312	200,626	326
	4,188,027	10,876.11	315,877	101,280,755	92,673

Digitized by Google

Content of dry and siliceous gold and silver ores sold or treated in New Mexico in 1917.

County.	Ore.	Gold.	Silver.	Copper.	Lead.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*
Colfax, Lincoln, and Otero	20,849	17,866.95	5,236	339,514	930
Dona Ana		1.74			
Grant	83,847	9,020.39	228,470	3,215,629	48,000
Santa Fe		6.69	1		
Sierra	45	7.00	4,168	43	
Socorro	116,612	12,540.29	726,460	10,889	161,601
Taos	309	53.65	1,671	95	330
	221,662	39,496.71	966,006	3,566,170	210,861

Content of lead ores sold or treated in New Mexico in 1917.

County.	Ore.	Gold.	Silver.	Copper.	Lead.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*
Dona Ana	351	3.00	4,579	8,461	162,965
Grant	4,325	45.23	16,777	4,862	1,688,538
Luna	1,785	252.08	12,305	319	547,778
Otero	5	.02	4		1,913
Santa Fe	30	1.00	122		5,379
Sierra	502	1.11	695	168	75,500
Socorro	10,428	64.76	35,539	182,140	3,153,745
	17,426	367.20	70,021	195,950	5,635,818

Content of lead-zinc ores sold or treated in New Mexico in 1917.

County.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Grant	7,449	60.25	9,388	42,317	739,066	394,969
Socorro	3,450				345,000	993,600
	10,899	60.25	9,388	42,317	1,084,066	1,388,569

Content of lead-copper ores sold or treated in New Mexico in 1917.

County.	Ore.	Gold.	Silver.	Copper.	Lead.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*
Grant	3,534	19.74	21,523	469,859	661,389
Sierra	25	59.00	3,797	1,939	4,616
Socorro	125	10.00	4,280	10,574	24,315
	3,684	88.74	29,600	482,372	690,320

Content of zinc ores sold or treated in New Mexico in 1917.

County.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Grant	83,515				28,946	12,940,158
Luna	3,158		2,837		173,339	1,635,500
Santa Fe	3,067				12,400	512,628
Socorro	45,389	0.47	544	436	1,180,381	13,723,145
	135,129	.47	3,381	436	1,395,066	28,811,431

Digitized by Google

SMELTERS.

Three smelters were in operation in New Mexico in 1917: The Santa Fe Gold & Copper Co.'s 125-ton matting plant at San Pedro, which was operated on copper ore from its own mines for three months; the Empire Smelting & Refining Co.'s lead plant at Deming, which was operated on lead ores from Arizona and southern New Mexico mines; and the Grubnau, Bryant & Grubnau zinc oxide plant, at Waldo (near Cerrillos), which treated zinc carbonate ores from Arizona, New Mexico, and old Mexico.

The bulk of the copper ore and concentrates mined and produced in New Mexico continued to be shipped to the smelter at El Paso, Tex. Lead ores and concentrates were shipped to Pueblo, Colo. Shipments were also made to the Copper Queen and Calumet smelters, at Douglas, Ariz., and to the smelter at Sasco, Ariz. Zinc ore and concentrates were shipped to smelters and zinc oxide plants in New Mexico, Colorado, Kansas, Oklahoma, Wisconsin, and the Eastern States.

MINING INDUSTRY.

The Mogollon district, Socorro County, remained the most productive silver-mining district, despite a decrease in output, but continued to take second place to the Elizabethtown district, Colfax County, in production of gold. The Elizabethtown (Baldy) district continued to produce much high-grade metallic gold, gold bullion, and concentrates from the Aztec mine, at Baldy, as well as small quantities of placer gold from near Elizabethtown. The Lordsburg and Pinos Altos districts, Grant County, made a decreased output of both gold and silver, as did the Orogrande district, Otero County, and the San Pedro district, Santa Fe County. No production was made in the silver-gold Cochiti (Bland) district, Sandoval County. The amalgamation mill at the Homestake mine, Whiteoaks, Lincoln County, continued to be operated, and the new Parsons amalgamation mill, at Nogal, Lincoln County, was in operation for a period.

Copper continued to be the principal product of New Mexico mines in 1917 when it made the largest output on record. The Chino Copper Co., which since 1910 has been mining with steam shovels large low-grade copper deposits at Santa Rita, reports that during the year 1917 there were treated in the large milling plant at Hurley a total of 3,608,100 tons of ore, equivalent to 9,885 tons a day. The Burro Mountain 1,000-ton mill (first set in operation in April, 1916) produced in 1917 a greatly increased quantity of copper concentrates. The production of copper decreased in the Lordsburg, Orogrande, Organ Mountains, and San Pedro districts, but the high prices for copper resulted in continued scattered shipments from the deposits in the "Red Beds" of New Mexico.

The output of lead increased 894,615 pounds. Large quantities of lead carbonate and of lead-zinc sulphide ores were shipped from the Magdalena district, Socorro County; lead ores were shipped from the Cooks Peak, Florida Mountains, and Victorio districts, Luna County; from the Central and San Simon districts, Grant County; from the Caballos Mountains, Sierra County; and from the Organ Mountains, Dona Ana County.

The output of zinc decreased 6,370,649 pounds. At Kelly the new Graphic mill, built to replace the one destroyed by fire in 1916,

Digitized by Google

was operated from March throughout the year, and the Kelly mill was also operated. At Hanover and Cleveland both mills were in operation throughout the year. The Tom Payne mill, near Cerrillos, was also in operation. Zinc carbonate ores shipped from Kelly, Cooks Peak, Hanover, Florida Mountains, and Tres Hermanas, were much less than in 1916.

Mine production of gold, silver, copper, lead, and zinc in New Mexico in 1917.

County.	Number of mines producing.	Ore.	Gold.[a]		Silver.[a]	
			Quantity.	Value.	Quantity.	Value.
		Short tons.	*Fine ounces.*		*Fine ounces.*	
Colfax and Lincoln	11	11,940	17,268.67	$356,975	2,705	$2,229
Dona Ana	5	417	4.74	98	4,705	3,877
Grant	68	4,315,341	19,565.08	404,446	487,558	401,748
Guadalupe	3	74			40	33
Luna	10	4,943	252.08	5,211	15,142	12,477
Mora	1	37			40	33
Otero	19	17,991	1,172.95	24,247	4,850	3,996
Rio Arriba	4	27	.14	3	392	323
Sandoval	1	20			153	126
Santa Fe	12	10,159	450.23	9,307	6,892	5,679
Sierra	13	619	87.12	1,801	8,712	7,179
Socorro	28	212,729	12,616.49	260,806	859,892	708,551
Taos	3	361	59.69	1,234	1,972	1,625
Torrance	14	2,169	1.45	30	1,312	1,081
Total, 1917	192	4,576,827	51,478.64	1,064,158	1,394,365	1,148,957
Total, 1916	210	3,870,950	66,877.47	1,382,480	1,766,274	1,162,208
Increase or decrease, 1917		+705,877	−15,398.83	−318,322	−371,909	−13,251

[a] Includes placer production.

County.	Copper.		Lead.		Zinc.		Total value.
	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	
	Pounds.		*Pounds.*		*Pounds.*		
Colfax and Lincoln	17,956	$4,902	980	$80			$364,186
Dona Ana	16,121	4,401	162,955	14,015			22,391
Grant	101,373,641	27,675,004	3,224,477	277,305	13,335,127	$1,360,183	30,118,686
Guadalupe	4,022	1,098					1,131
Luna	319	87	721,117	62,016	1,635,500	166,821	246,612
Mora	6,315	1,724					1,757
Otero	814,736	222,423	13,907	1,196			251,862
Rio Arriba	2,802	765					1,091
Sandoval	12,901	3,522					3,648
Santa Fe	400,143	109,239	17,779	1,529	512,628	52,288	178,042
Sierra	11,828	3,229	80,116	6,890			19,099
Socorro	2,699,747	737,031	4,886,803	420,265	14,716,745	1,501,108	3,627,761
Taos	6,843	1,868	384	33			4,760
Torrance	200,626	54,771	326	28			55,910
Total, 1917	105,568,000	28,820,064	9,108,804	783,357	30,200,000	3,080,400	34,896,036
Total, 1916	92,747,289	22,815,833	8,214,189	566,779	36,570,649	4,900,467	30,827,767
Increase or decrease, 1917	+12,820,711	+6,004,231	+894,615	+216,578	−6,370,649	−1,820,067	+4,069,169

Digitized by Google

Gold and silver produced at mills in New Mexico, 1909–1917.

Year.	Ore to gold and silver mills.	Gold in bullion.	Silver in bullion.	Ore to concentrating mills.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Short tons.*
1909	32,830	6,725.84	169,650	78,782
1910	67,148	14,220.94	412,272	61,379
1911	109,113	21,894.14	771,014	59,622
1912	106,208	20,342.58	842,018	1,142,002
1913	124,536	24,891.37	1,024,363	1,987,896
1914	156,913	29,780.64	1,161,455	1,955,881
1915	149,650	40,474.37	1,129,701	2,428,344
1916	135,267	34,332.33	841,865	3,442,681
1917	123,824	26,270.55	657,437	4,215,988
Increase or decrease, 1917	−11,443	−8,061.78	−184,428	+773,307

Mine production of metals from New Mexico concentrates, 1909–1917.

Year.	Concentrates produced.					
	Quantity.	Gold.	Silver.	Copper.	Lead.	Zinc.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
1909	7,554	1,598.31	112,639	2,015,118	436,558	821,766
1910	18,298	4,536.03	255,060	1,050,238	2,701,843	6,882,175
1911	16,243	7,938.70	333,654	1,125,927	1,562,768	5,304,000
1912	81,811	7,190.63	290,081	28,760,908	1,984,435	6,404,768
1913	198,243	7,913.39	294,948	51,723,923	1,076,848	8,594,183
1914	161,003	12,754.17	312,734	53,398,611	637	8,541,261
1915	174,074	12,876.72	323,402	66,326,554	75,580	11,179,266
1916	311,726	13,125.69	336,472	80,235,404	727,888	16,625,663
1917	360,614	10,167.96	196,713	92,990,700	2,108,154	21,130,965
Increase or decrease, 1917	+48,888	−2,957.73	−139,759	+12,755,296	+1,380,266	+4,505,302

Mine production of metals from New Mexico crude ore shipped to smelters, 1909–1917.

By years.

Year.	Crude ore.	Gold.	Silver.	Copper.	Lead.	Zinc.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
1909	52,544	2,196.50	115,332	3,378,028	4,593,209	12,264,179
1910	63,338	3,317.99	176,281	3,564,148	1,618,998	11,205,954
1911	63,964	6,162.71	249,710	2,931,113	1,403,454	4,933,176
1912	104,076	9,595.57	404,402	5,270,056	3,509,583	7,161,869
1913	105,228	9,478.13	311,872	4,584,783	2,869,516	7,928,978
1914	120,059	12,785.76	302,926	5,909,314	1,763,004	9,862,131
1915	219,078	16,882.78	552,373	10,461,812	4,466,781	14,224,798
1916	293,002	18,881.71	587,865	12,514,885	7,486,301	19,944,986
1917	237,015	14,450.93	540.123	12,577,300	7,000,650	9,069,035
Increase or decrease, 1917	−55,987	−4,430.78	−47,742	+62,415	−485,651	−10,875,951

By kind of ores (in 1917).

Dry and siliceous	91,838	9,919.90	238,122	3,559,076	9,167	.....
Copper	104,509	4,075.09	199,543	8,339,902	92,673	.....
Lead	17,426	367.20	70,021	195,950	5,635,818	.....
Copper-lead	3,684	88.74	29,600	482,372	690,320	.....
Zinc	15,963	.....	2,837	.....	210,585	8,015,397
Zinc-lead	3,595	.....	.....	.....	362,087	1,053,638

Digitized by Google

Mine production of metals from New Mexico crude ore shipped to smelters, 1917.

County.	Crude ore.	Gold.	Silver.	Copper.	Lead.	Zinc.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Colfax	21	.....	4	3,882	.....	.....
Dona Ana	417	3.00	4,705	16,121	162,965	.....
Grant	145,144	12,528.98	361,867	8,425,314	2,454,498	1,829,242
Guadalupe	74	.....	40	4,022	.....	.....
Lincoln	114	9.91	90	13,172	.....	.....
Luna	4,943	252.08	15,142	319	721,117	1,635,500
Mora	37	.....	40	6,315	.....	.....
Otero	16,016	1,137.30	4,752	779,893	13,907	.....
Rio Arriba	27	.10	392	2,802	.....	.....
Sandoval	20	.....	153	12,901	.....	.....
Santa Fe	7,162	339.29	6,885	400,143	10,179	26,884
Sierra	619	71.11	8,710	11,828	80,116	.....
Socorro	60,191	78.10	134,993	2,693,119	3,557,158	5,577,409
Taos	61	29.61	1,038	6,843	384	.....
Torrance	2,169	1.45	1,312	200,626	326	.....
	237,015	14,450.93	540,123	12,577,300	7,000,650	9,069,035

Gold and silver contained in bullion produced at mills in New Mexico, 1917.

Process.	Quantity.	Gold in bullion.	Silver in bullion.
	Short tons.	*Fine ounces.*	*Fine ounces.*
Amalgamation	11,890	14,866.81	2,256
Cyanidation	111,934	11,403.74	655,181
	123,824	26,270.55	657,437

The quicksilver consumed in New Mexico in 1917 amounted to 175 pounds, representing 1 pound for every 85 ounces of gold, and the sodium cyanide to 123,500 pounds, representing 1 pound for every 0.09 ounce of gold and 1 pound for every 5.30 ounces of silver.

REDUCTION MILLS.

Mineral Resources for 1912, Part 1, pages 832–835, contained a complete list of the reduction mills in New Mexico in 1912 and descriptions of equipment and process. Changes in this list for 1913–1917 have been noted in the text for the several counties for each year, and reference should be made to the 1912 report for details of equipment.

REVIEW BY COUNTIES.[1]

BERNALILLO COUNTY.

Assessment and development work only was done in the Coyote, Hell Canyon, and Soda Springs districts.

COLFAX COUNTY.

Elizabethtown district (including Baldy).—The Aztec mine[2] at Baldy continued to ship gold bullion and concentrates carrying a high content of gold from the 10-stamp amalgamation-concentration mill on

[1] For discussion of geology of the districts mentioned in the following pages the reader is referred to Hill, J. M., The mining districts of the western United States: U. S. Geol. Survey Bull. 507, 1912; and Lindgren, Waldemar, The ore deposits of New Mexico: U. S. Geol. Survey Prof. Paper 68, 1910.

[2] Lee, W. T., The Aztec gold mine, Baldy, N. Mex.: U. S. Geol. Survey Bull. 620, pp. 325–330, 1916.

Digitized by Google

the property. Several placer mines were operated during the year at Elizabethtown. The following table shows the production of Elizabethtown and Baldy districts (which is the output for Colfax County) from 1904 to 1916, inclusive:

Mine production in Elizabethtown district, Colfax County, N. Mex., 1904–1917.

Year.	Ore.	Gold.		Silver.	Copper.	Lead.	Total value.
		Placer.	Deep.				
	Short tons.			*Fine ounces.*	*Pounds.*	*Pounds.*	
1904	380	$90,639	$3,638	67	.....	.....	$94,316
1905	13	31,994	445	157	.....	.....	31,749
1906	.....	14,492	.....	93	.....	.....	14,554
1907	.....	11,914	.....	33	.....	.....	11,969
1908	.....	11,274	.....	66	.....	.....	11,309
1909	83	16,037	1,705	127	.....	.....	17,808
1910	93	9,588	3,433	261	.....	2,182	13,258
1911	2,306	9,860	31,547	1,254	5,587	.....	42,770
1912	3,025	8,385	27,316	634	6,243	.....	37,121
1913	3,222	4,550	15,588	254	1,147	134	20,475
1914	2,860	4,930	63,129	577	11,083	154	69,358
1915	2,673	2,631	350,745	2,483	14,092	787	357,138
1916	6,064	5,039	417,258	2,803	447	.....	424,251
1917 [a]	.....	.....	.....	.....	.....	.....	.....

[a] Combined with Lincoln County.

DONA ANA COUNTY.

Mine production in Dona Ana County, N. Mex., 1904–1917.

Year.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
	Short tons.		*Fine oz.*	*Pounds.*	*Pounds.*	*Pounds.*	
1904	5,580	.....	24,101	40,000	1,581,488	.....	$87,145
1905	6,566	$6,710	21,776	96,058	327,707	30,000	52,020
1906	16,220	.....	34,051	434,000	1,207,193	.....	175,386
1907	6,084	6	25,612	776,125	675,189	.....	207,920
1908	3,090	.....	9,283	21,150	379,697	.....	23,660
1909	2,816	248	16,975	10,600	772,028	.....	43,650
1910	2	.....	15	.....	705	.....	39
1911	5	.....	111	363	1,561	.....	173
1912	78	17	1,790	6,685	26,139	.....	3,397
1913	155	30	1,232	10,189	9,557	.....	2,774
1914	451	927	3,564	78,180	29,897	.....	14,462
1915	1,599	2,426	8,335	241,749	19,170	.....	49,859
1916	2,615	503	7,948	206,187	34,696	106,679	73,144
1917	417	98	4,705	16,121	162,965	.....	22,391
Increase or decrease, 1917.	−2,198	−405	−3,243	−190,066	+128,269	−106,679	−50,753

Organ Mountains district.—The only large producers were the mines of the Stephenson-Bennett group, under lease to the American Smelting & Refining Co. During November and December, 1917, this company shipped lead ore to the El Paso smelter and lead-zinc ore to Coffeyville, Kans. The Phelps Dodge Co., which had an option on this mine and others during 1916, relinquished the option early in 1917 and made no shipments of ore in 1917. Other mines from which small shipments were made in 1917 were the Modoc and Excelsior.

Digitized by Google

GRANT COUNTY.

Mine production in Grant County, N. Mex., 1904–1917.

Year.	Ore.	Gold.		Silver.	Copper.	Lead.	Zinc.	Total value.
		Placer.	Deep.					
	Short tons.			*Fine ozs.*	*Pounds.*	*Pounds.*	*Pounds.*	
1904	47,032	$8,081	$60,347	74,793	4,428,508	179,142	.....	$695,099
1905	81,160	10,943	35,064	86,629	5,291,222	321,035	257,203	954,026
1906	127,800	2,290	97,519	163,987	6,388,830	710,895	144,656	1,492,069
1907	146,746	3,782	109,260	224,279	8,046,315	1,394,390	73,729	1,948,582
1908	75,254	3,514	42,168	95,477	5,242,767	244,589	251,070	810,403
1909	89,576	3,584	34,242	74,198	5,176,585	215,070	203,278	760,690
1910	70,862	2,641	63,291	156,557	4,404,394	257,953	1,285,500	790,598
1911	93,770	4,043	112,241	221,882	3,918,928	694,247	306,895	772,481
1912	1,200,691	2,551	163,645	356,057	32,952,133	2,309,732	3,135,000	6,142,526
1913	1,984,304	1,646	102,971	206,215	53,436,177	446,805	2,553,322	8,674,423
1914	1,986,921	21,560	319,300	304,679	58,259,113	570,513	3,734,768	8,448,810
1915	2,523,275	1,979	363,104	508,552	72,487,200	2,251,383	6,083,580	14,168,358
1916	3,577,868	2,009	417,666	549,907	87,784,545	2,561,638	14,084,843	24,440,634
1917	4,315,341	3,153	401,293	487,558	101,373,641	3,224,477	13,335,127	30,118,686
Increase or decrease, 1917	+737,473	+1,144	−16,373	−62,349	+13,589,096	+662,839	−749,716	+5,678,052

Apache No. 2 (Anderson) district.[1]—Shipments of silver-copper ore were continued throughout the year from the Apache mine, southeast of Hachita.

Black Hawk district.—At the Black Hawk mine, reopened in 1916 after many years of idleness, the year 1917 was spent in pumping, timbering, sampling, and drifting. This property is opened by a 720-foot incline shaft, and 4,880 feet of drifts.

Burro Mountain district.[2]—The annual report (dated Feb. 11, 1918) of Phelps-Dodge Corporation, for the calendar year 1917, says of the Burro Mountain Branch mines and the 1,500-ton water and flotation concentrating mill:

The net production of copper and silver, based on smelter returns from shipments of concentrates, precipitates, and lease ore, was as follows:

	Quantity.	Copper.		Silver.
	Dry tons.	*Per cent.*	*Pounds.*	*Ounces.*
Concentrates	45,681	14.775	12,823,641	39,403.57
Precipitates	303	54.855	315,412	.....
	45,984	.....	13,139,053	39,403.57
Lease ore	12,485	4.4626	1,114,338	.....
	58,469	.....	14,253,391	39,403.57

The ore mined for delivery to the concentrator was 473,443 tons, having an assay value of 1.972 per cent. The cost of mining a ton of ore shows a reduction as compared with the previous year, but this improvement is more than counterbalanced by a drop in the grade of the ore from 2.117 per cent in 1916. Much of the necessary expense of placing the stopes in economical condition to extract ore has been absorbed in the past costs of mining, and a marked improvement in costs should be experienced in this respect in the future.

[1] As distinguished from Apache (Chloride) district, Sierra County.

[2] Paige, Sidney, Metalliferous ore deposits near the Burro Mountains, Grant County, N. Mex.: U. S. Geol. Survey Bull. 470, pp. 131–150, 1911: also U. S. Geol. Survey Geol. Atlas, Silver City folio (No. 199), 1916. Weed, W. H., The copper mines of the United States in 1905: U. S. Geol. Survey Bull. 285, p. 118, 1906. Somers, R. E., Geology of the Burro Mountains: Am. Inst. Min. Eng. Bull. 101, pp. 967–996, 1915. Bush. F. V., Burro Mountain porphyry copper developments: Min. and Sci. Press, Feb. 6, 1915, pp. 222–224.

Digitized by Google

The ore reserves have been substantially increased and the stopes themselves have been put into condition for more economical operation.

The results of concentrator operations for the year are shown below:

Ore milled, 473,443 tons dry weight, assaying 1.972 per cent copper.
Moisture of general heads, 3.329 per cent.
Copper in ore milled, 9,334.948 tons.
Concentrates produced, 45,681 tons dry weight, assaying 14.775 per cent copper.
Tailings produced, 427,762 tons dry weight, assaying 0.606 per cent copper.
Saving (average of four methods of figuring), 72.256 per cent.
Yield, 1.426 per cent.
Ratio of concentration, 10.364.
Tons of ore milled per day, actual running time, 1,485.218.
Gallons fresh water used per ton ore milled, 748.101.
Kilowatt hours per ton of ore milled, 9.222.

Churn drilling operations continued at a reduced rate throughout the year, and satisfactory ore discoveries were made at several points of the property. On the Michigan and Manana claims ore was cut by two holes placed within the general trend of the mineralized zone, and by these discoveries the possibility of continuous ore between No. 11 stope and the Mohawk ore body, 1,800 feet to the northeast, is materially strengthened.

Systematic drilling has been started on the properties of the Azure Mining Co., which is held under option, but without, as yet, very encouraging results.

A total of 30,542 feet was drilled during the year, 52 holes having been sunk an average depth of 587.4 feet.

The leaching operations on the old ore dump at No. 2 shaft yielded about 280,090 pounds of copper, or about 25 per cent of its original content. Exhaustive experiments will be undertaken during the year to determine whether it will be practical to leach on a large scale the very considerable tonnage of ore below milling grade which exists in these properties. With the hope of further information as to the possibilities of the process, plans are now under way for a new series of ore heaps of varying size and depth to be located in the flat below the mill. Facilities will be provided for the proper make-up and control of leaching solutions and efforts made to determine the suitable chemical and physical operating conditions for the best results.

The Phelps Dodge Corporation also maintains and controls the town site, upon which it has built a model town. The only other producing property of importance was the Austin-Amazon group, from which a considerable quantity of copper-silver ore was shipped.

Central district.[1]—The Central district, embracing the towns of Bayard, Fierro, Georgetown, Hanover, and Santa Rita, not only makes the most valuable output of ore in New Mexico, but produces the most interesting variety of ores. Besides the Chino Copper Co.'s mines at Santa Rita, the Empire Zinc Co.'s mines at Hanover, and the Hanover-Bessemer Iron and Copper Co.'s mines at Fierro, there were 24 other producing mines in the district in 1917. From the dumps of the Hanover and Modoc mines a considerable quantity of oxidized ore, low in copper but high in iron, was shipped as iron fluxing ore for the Copper Queen smelter, at Douglas, Ariz. Zinc carbonate ore was shipped from the Hanover mines of the Empire Zinc Co., the Hanover Copper Co.'s group, the Belle, the Mountain Home group, and from others. Both oxidized and sulphide copper was shipped from the Dewey and Schley mines; copper ore from the Copper Rose, Edmonson, Philadelphia, and San Jose mines; copper and lead-copper ore from the Groundhog and the Ivanhoe; and lead oxidized ore of good grade and in considerable quantity from the Lucky Hill mine. Iron ore to the steel mill at Pueblo, Colo., and to the lead smelters at Deming was shipped by the Republic Mining

[1] Paige, Sidney, U. S. Geol. Survey Geol. Atlas, Silver City folio (199), 1916: The Hanover iron-ore deposits, New Mexico: U. S. Geol. Survey Bull. 380, pp. 199–214, 1909. Birkinbine, John, Iron ores of the United States: U. S. Geol. Survey Eighteenth Ann. Rept. pt. 5 pp. 48–50, 1897.

Digitized by Google

& Milling Co. This company also developed a large body of zinc sulphide ore.

The Hanover-Bessemer Iron & Copper Co., owner of the iron mines at Fierro, for many years leased to the Colorado Fuel & Iron Co., of Pueblo, Colo., built an electrostatic separation mill in 1917 for the treatment of the iron ores, with a resultant separation of copper products as well.

The Empire Zinc Co. also operated steadily its magnetic separating mill [1] at Hanover on zinc sulphide ores from its mines.

The Gold Gulch concentration mill, built in 1916, on Santa Rita Creek, near Bayard, was operated in 1917 on lead-zinc ore from the Booth, Gold Gulch, and Jack Mining Co.'s mines.

The Chino Copper Co. is mining a low-grade copper deposit at Santa Rita by steam shovels. The ore is concentrated at Hurley, where the company's wet-concentration-flotation mill is located. Concentrates and occasional cars of ore are shipped principally to the El Paso smelter. The eighth annual report of the Chino Copper Co., dated March 5, 1918, covering the year ended December 31, 1917, says:

The gross production for the year of copper in concentrates and direct shipments, including a small amount of precipitates, was 83,339,782 pounds. After making smelter deductions the net production was 79,636,235 pounds. There was also produced gold and silver valued at $56,160. These net figures were the result of handling during the year 3,608,100 tons through the mill and 3,757 tons of direct shipping ore.

The net cost of producing copper for the year * * * was 11.39 cents per pound as compared with 8.7 cents for 1916. This was after deducting precious metal values and miscellaneous earnings for the year, which amounted to 0.46 cent per pound, from the cost of producing copper. Taxes accrued and included in operating expenses during the year were insufficient by $830,996 to cover the total of $2,033,439 for all 1917 taxes as now estimated and returned to the proper officials. The total cost, including, as usual, all taxes as last stated and also including the adjustment to income from stripping account noted below, was 12.79 cents per pound. Higher prices for labor and supplies and increases in taxes in 1917 are responsible for this considerable advance in cost of production. * * *

The net income from operations was $9,826,616. Miscellaneous income, dividends, rentals, etc., amounted to $310,436, or a total income from all sources of $10,137,052. There was a direct charge to income for plant alterations, replacements, and abandonments and depreciation adjustment of $336,077; also an amount of $288,121 for adjustment of charges to stripping account. * * * The total income, therefore, applicable to dividends or other capital purposes aggregated $9,512,854, or $10.93 per share, as compared with $14.76 per share for the year 1916. Disbursements to stockholders were made during the first three quarters at the quarterly rate of $2.50 per share and for the last quarter at $2 per share; in addition a Red Cross dividend of 40 cents per share was paid, making total disbursements to stockholders during the year of $9.90 per share. The total amount distributed to stockholders during the year was $8,612,802. An amount for depreciation of plants of 5 per cent of their total cost was set aside and included in operating expenses. The entire operations outlined above resulted in passing $900,052 to the "earned surplus" and "depletion" account, which at the end of the year aggregated $14,863,926. The total disbursements to stockholders down to and including December 31, 1917, were $22,488,132. * * *

Churn drilling was continued throughout the year, the three drills operating in the Northwest and Southwest ore bodies. Extensions of the ore bodies were demonstrated. The total driling for the year was 22,425 feet, and since the beginning of operations there has been a total of 249,728 feet drilled. * * *

The prospect drilling for this year has shown additional commercial ore in excess of the tonnages removed. A considerable proportion of this new ore lies within the pit slopes as heretofore laid out. Revised calculations of total ore reserves were not made because the time and expense of doing so did not seem warranted, and it can only be stated, therefore, that the remaining reserves at the end of 1917 exceed those at

[1] For description see Met. and Chem. Eng., Oct. 10, 1916, pp. 481–482.

Digitized by Google

the end of 1916, which were reported at that time to be 95,555,843 tons, averaging 1.656 per cent copper.

During the month of May, 1917, the second unit of the primary crushing plant at the mine was finished and placed in successful operation. In order to provide equipment for moving the additional ore tonnages to this plant, 16 automatic air dump cars of 20-yard capacity were ordered early in the year and are received as required. * * *

During the year the three upper stripping benches of the Hearst pit were completed back to the point to allow ample slope for the recovery of the steamshovel ore. This work was also completed on the upper benches of the Northwest and North ore bodies. The shovels thus released were moved to the Southwest ore body and work on the top benches of that ore body started.

The total amount of ore and waste removed by the steam shovels during the year was 5,583,016 cubic yards of material in place. Of this amount 3,712,414 cubic yards was stripping, the remainder being equivalent to 3,607,825 tons of ore. Of the ore that was removed, 3,604,068 tons were sent to the mill, and 3,757 tons were shipped direct to the smelter, these direct shipments averaging 18.27 per cent copper. During the year there was no ore sent to the ore dumps; on the other hand, there were 3,271 tons taken from the ore dumps and sent to the mill for experimental purposes, so that the total shipments to the mill were 3,607,339 tons. The ore remaining on the ore dumps at the mine at the close of the year was 1,061,636 tons.

From the beginning of steam shovel operations on September 23, 1910, when the first shovel was erected, there was removed a total of 28,378,348 cubic yards of material in place, of which 20,599,199 cubic yards were stripping, the remainder being equivalent to 15,194,517 tons of ore. Of this ore 1,061,636 tons remain stored in the stock piles at the mine, 14,109,194 tons were shipped to the mill, the balance, 23,687 tons, having been shipped directly to the smelter. * * *

Following the plans made and approved in 1916 covering additions to and alterations in the original five-section mill and the addition of two sections, work was continued on these improvements throughout the year. The alterations and additions to the original mill were completed and the concentrating machinery put completely in service for all five sections during the latter part of May. The power plant additions were completed and the turbo-generator set placed in service at practically the same time. The completion of these improvements, as well as the putting in service of the second unit of the primary crushing plant at Santa Rita, resulted immediately in the treating of additional tonnages, amounting to an increase of over 11 per cent for the balance of the year. Construction work on sections 6 and 7 was pushed as fast as the machinery and material could be obtained, with the result that in the latter part of December the fine crushing machinery and part of the concentrating machinery were in operation in section 6, though the full benefit of this section can not be felt until about the 1st of February, 1918. As a result of the work with the 100-ton experimental plant it was possible to outline a flow sheet for section 7 in handling the oxidized and partly oxidized ores. The necessary apparatus has been ordered and the installation will be completed as quickly as such material as is not on hand is received. A part of the floor space of section 7 will be devoted to the regular milling operations and the other part will be equipped with the special apparatus which has been decided on, in order that further work on at least a 500-ton basis may be carried on. The tailings retreatment plant construction was not continued to completion, as, owing to developments in the experimental plant, it was deemed wise to await the result of the new line of work which had been indicated by larger scale investigations. During the year the canal was completed to take care of the overflow of flood waters from the tailings and water storage dam and the railroad track for handling the material to and from the tailings mill was in service. * * *

For the year 1917 there was treated in the mill at Hurley a total of 3,608,100 tons of ore, equivalent to an average of 9,885 tons per day. Previous to June 1 the average per day was 9,285 tons. Subsequent to June 1 the average per day was 10,308 tons. The average treated per day for 1916 was 8,455 tons, so that there was an average increase for 1917 over 1916 of 1,430 tons per day, or 16.9 per cent. The average content of the ore treated for the year was 1.64 per cent copper, or 0.19 per cent lower than for 1916. The total production of concentrates was 264,765 tons, which averaged 15.47 per cent copper. The total amount of copper contained in concentrates was 81,925,809 pounds, being an increase of 8.44 per cent over 1916 and corresponding to a recovery of 22.706 pounds of copper per ton of ore, equivalent to an extraction of 69.32 per cent, which was 2.73 per cent better than for the year 1916, notwithstanding the increased tonnage and lower grade ore. The average cost of milling was $1.03 per ton, as against a cost for 1916 of 64 cents per ton. Mill supplies show an increase of 42.2 per cent in cost per ton. Power costs increased 47.3 per cent, due principally to the advance in prices paid for fuel.

Digitized by Google

During the year there were shipped from the mine direct to the smelter 3,757 dry tons of ore and 48.5 dry tons of precipitates containing 1,413,973 gross pounds of copper.

The production of copper contained in the concentrates and other shipping products for the year 1917, by quarters, was as follows:

	Pounds.
First quarter	19,240,577
Second quarter	21,944,094
Third quarter	21,887,390
Fourth quarter	20,267,721
	83,339,782

The average cost of net copper produced for the year, after making deductions for smelter allowances and crediting precious metal values and miscellaneous income, was 11.39 cents per pound, as compared with 8.7 cents per pound for the previous year. The credit for precious metals amounted to 0.07 cent per pound and that of miscellaneous income to 0.39 cent per pound, a total of 0.46 cent per pound. The per pound cost stated includes depreciation and reserves for taxes set up during the year, the latter being, however, insufficient to meet actual requirements and therefore subject to adjustment against income.

Mine production in Central district, Grant County, N. Mex., 1904–1917.

Year.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
	Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1904	21,048	$5,582	282	3,264,208	11,977	.....	$430,607
1905	17,115	.....	.....	2,704,233	.....	.....	421,860
1906	39,155	4	1,524	3,075,001	235,070	99,656	614,648
1907	57,079	5,559	36,813	4,994,575	855,358	73,729	1,078,555
1908	41,852	777	296	3,994,502	29,122	251,070	541,231
1909	41,456	816	1,380	3,348,808	23,256	203,278	448,856
1910	37,008	.....	404	2,679,630	155	1,285,500	409,955
1911	45,584	104	8,673	1,413,189	605,978	290,122	325,156
1912	1,136,290	996	29,596	29,512,812	2,172,676	2,205,824	5,138,779
1913	1,948,471	9,697	12,500	51,695,656	331,440	2,187,266	8,167,144
1914	1,984,020	102,971	42,971	55,222,874	365,079	3,669,513	7,672,759
1915	2,395,795	102,379	73,267	66,581,366	1,542,234	5,628,870	12,561,729
1916	3,134,791	133,962	116,953	74,228,606	2,122,797	7,278,575	19,592,956
1917	3,668,289	138,873	121,386	82,200,421	2,250,337	7,398,853	23,627,822
Increase, 1917	533,498	4,911	4,433	7,971,815	127,540	120,278	4,034,866

Chloride Flat district (near Silver City).—No silver ores were shipped from this formerly producing district, but iron-manganese ores[1] in considerable quantity were shipped during the year.

Eureka district (including Sylvanite).—One car of zinc carbonate ore was shipped from the Sheridan mine and one car of lead-silver ore from the Natches mine.

Fremont district.[2]—One car of zinc-lead carbonate was shipped from the Doyle prospect.

Gold Hill district.—The Cline two-stamp amalgamation mill was operated for two months and produced gold-silver bullion.

Lordsburg district (including Pyramid and Virginia or Shakespeare districts).—The production of this district in 1917 was a little less than in 1916, the record year in the history of the district. All the ore was shipped direct to smelters. The average assay for the district in 1917 was gold 0.1194 ounce and silver 2.97 ounces per ton, and copper 2.14 per cent. The principal producing property was the group operated by the Eighty-five Co. This company in 1917 was also

[1] See Eng. and Min. Jour., Nov. 24, 1917, p. 931.
[2] Darton, N. H., Geology and underground water of Luna County, N. Mex.: U. S. Geol. Survey Bul. 618, pp. 106–107, 1916.

Digitized by Google

engaged in building a 500-ton gravity and oil flotation mill, to be completed in 1918. Increased shipments of copper were made from the Bonney mine. Other producing mines were the Atwood and Nellie Bly.

Mine production in Lordsburg district, Grant County, N. Mex., 1904–1917.

Year.	Ore.	Gold.	Silver.	Copper.	Lead.	Total value.
	Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	
1904	250	$1,184	2,580	18,200	12,000	$5,5[illegible]
1905	366	10	7,584	48,000	.....	12,07[illegible]
1906	1,743	5,168	27,261	212,601	.....	64,46[illegible]
1907	5,645	8,761	31,303	463,335	10,522	122,4[illegible]
1908	7,532	10,617	9,889	259,079	11,363	50,55[illegible]
1909	10,090	25,983	50,154	589,969	8,802	129,19[illegible]
1910	29,220	59,798	130,321	1,627,591	19,662	337,7[illegible]
1911	46,139	106,648	182,448	2,455,336	2,157	510,35[illegible]
1912	55,340	144,859	275,251	3,155,585	4,562	835,0[illegible]
1913	31,284	55,234	154,779	1,601,461	14,572	397,5[illegible]
1914	38,964	101,080	232,647	2,614,674	30,049	578,65[illegible]
1915	92,093	222,848	374,325	3,890,365	28,723	1,094,7[illegible]
1916	119,906	267,148	373,074	4,755,179	30,478	1,664,5[illegible]
1917	99,532	245,607	295,443	4,261,956	41,442	1,656,1[illegible]
Increase or decrease, 1917...	−19,434	−21,541	−77,631	−493,223	+10,964	−28,3[illegible]

Pinos Altos district.[1]—The only important decrease in the production for 1917 was for copper. Placer gold production increased.

The Cleveland zinc mine and magnetic separation mill was operated steadily, the product being entirely zinc concentrate. Lead and zinc ore was shipped from the Lead Hill mine, and a car of lead-zinc ore from the Calumet mine. A considerable quantity of silver ore was shipped from the Manhattan mine. Lessees on the Mina Grande, Pacific, and Atlantic groups shipped some silver-copper ore.

Mine production in Pinos Altos district, Grant County, N. Mex., 1904–1917.

Year.	Ore.	Gold.		Silver.	Copper.	Lead.	Zinc.	Total value.
		Placer.	Deep.					
	Short tons.			*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1904	4,719	$7,750	$49,660	37,229	104,069	2,653	.....	$92,5[illegible]
1905	6,848	10,943	31,442	39,585	103,469	.....	160,779	$2,41[illegible]
1906	14,074	2,290	89,674	83,566	328,788	.....	.....	211,4[illegible]
1907	14,841	3,782	78,723	65,862	322,195	.....	.....	190,4[illegible]
1908	1,451	1,479	8,548	8,941	34,514	3,953	.....	2,5[illegible]
1909	38	3,584	2,083	1,377	6,200	418	.....	7,3[illegible]
1910	20	2,494	1,372	223	269	2,226	.....	4,11[illegible]
1911	855	4,043	1,406	5,616	3,232	4,063	16,773	9,9[illegible]
1912	6,169	2,551	7,973	15,864	96,507	50,269	929,176	102,3[illegible]
1913	3,643	1,646	29,162	28,276	100,555	83,067	366,056	87,[illegible]
1914	3,686	a 21,650	114,181	23,256	129,587	29,994	48,840	169,4[illegible]
1915	7,024	1,979	31,823	19,856	377,463	130,638	454,710	172,4[illegible]
1916	46,471	2,009	11,775	17,816	122,716	152,696	6,741,925	967,8[illegible]
1917	45,993	3,153	7,731	10,803	49,945	80,989	5,556,882	607,1[illegible]
Increase or decrease, 1917...	−478	+1,144	−4,044	−7,013	−72,771	−71,707	−1,185,033	−360,4[illegible]

a Placer and surface lode mines combined. Only small quantity recovered by actual placer methods. Fineness so similar separation not practicable.

[1] Paige, Sidney, The ore deposits near Pinos Altos, N. Mex.: U. S. Geol. Survey Bull. 470, pp. 109–125, 1911; U. S. Geol. Survey Geol. Atlas Silver City, folio (No. 199), 1916.

Digitized by Google

San Simon (Granite Gap) district (Steins).—Several cars of ore were shipped from this district in 1917—lead ore from the Granite Gap mine, lead-zinc ore from the Silver Hill, copper ore from the Johnny Bull, and copper ore from the Hamilton group.

Steeplerock district.—From the 500-foot level of the Carlisle mine (unwatered and opened in 1916 after a long idleness) was mined and milled several thousand tons of lead-zinc ore, the product being lead-zinc and lead concentrates, both of which also contained silver and some copper. Several cars of copper ore were shipped from the Delmire group and a car of silver ore from the Jim Crow group.

Swarts (Carpenter or Camp Monarch) district.—During three months the Monarch mill (built in 1906) was operated on lead-zinc ore from open-cut mining at the Grand Central mine. This mine is also opened by an incline shaft.

GUADALUPE COUNTY.

Several cars of copper-silver ore were shipped from the Pintada district. The plans for leaching the ores of this district seem to have been abandoned.

LINCOLN COUNTY.

Mine production in Lincoln County, N. Mex., 1904–1917.

Year.	Ore.	Gold.		Silver.	Copper.	Lead.	Total value.
		Placer.	Deep.				
	Short tons.			*Fine ounces.*	*Pounds.*	*Pounds.*	
1904	820	$20,100	$3,496	2,576	.....	2,261	$30,183
1905	3,060	2,260	5,215	757	14,404	7,511	10,582
1906	6,380	.....	16,463	1,946	.....	.....	17,767
1907	5,767	.....	41,417	721	.....	.....	41,893
1908	4,399	816	26,896	5,472	1,195	.....	32,770
1909	3,633	472	23,391	388	700	7,977	24,499
1910	10,727	1,400	53,876	559	189	5,614	55,849
1911	1,578	1,629	30,305	184	555	6,620	32,399
1912	2,003	1,008	21,408	1,005	9,988	103,911	29,358
1913	5,589	1,027	41,469	1,100	7,068	94,010	48,392
1914	13,540	908	62,499	961	15,068	10,641	66,360
1915	8,550	1,308	44,068	493	5,091	13,277	47,141
1916	1,490	651	7,093	953	28,045	.....	15,270
1917	(a)	(a)	(a)	(a)	(a)	.....	(a)

a Combined with Colfax County.

Estey district (Oscuro Mountains).—Several cars of copper were shipped from the Walter Mayfield group.

Jicarilla district.—There was a small production of placer gold in this district.

Nogal district.—The 250-ton amalgamation mill, completed early in 1917 to treat the ores of the Hopeful mine, was operated for a period. The Vera Cruz amalgamation mill (built in 1902), 4 miles south of Nogal, was rebuilt during the year, with plans for operating in 1918. The rebuilt mill will have a capacity of 50 tons a day, and the equipment consists of one Blake crusher, one Ellis ball Chilean mill, one Senn amalgamator, and 10 tanks for dewatering and for proposed future treatment of tailings by cyanidation.

Whiteoaks district.—During the later half of the year the Homestake 20-stamp amalgamation mill was operated on ore from the North Homestake and South Homestake mines.

Digitized by Google

LUNA COUNTY.

Mine production in Luna County, N. Mex., 1904–1917.

Year.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
	Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1904	1,576	$1,695	8,549	16,000	671,772	.....	$37,605
1905	1,346	.....	5,199	.....	463,956	225,000	38,221
1906	1,994	413	11,265	.....	831,193	103,836	61,673
1907	2,048	13,741	8,633	.....	1,022,773	.....	73,646
1908	288	3	1,077	5,934	127,535	.....	6,713
1909	1,163	3,208	6,916	1,115	682,906	.....	36,314
1910	525	26	2,484	47	298,112	.....	14,490
1911	229	104	1,278	1,814	98,888	.....	5,458
1912	3,090	5,687	24,265	.....	827,556	458,594	89,493
1913	5,185	11,085	41,664	1,453	1,158,682	702,028	126,771
1914	2,127	220	2,975	2,181	416,923	793,588	58,694
1915	2,082	491	2,795	4,080	148,766	861,218	116,405
1916	7,630	3,535	18,077	2,663	868,724	2,725,582	441,255
1917	4,943	5,211	15,142	319	721,117	1,635,500	246,612
Increase or decrease, 1917	−2,687	+1,676	−2,935	−2,344	−147,607	−1,090,082	−194,643

Cooks Peak district.[1]—The greater part of the shipments from this district was zinc carbonate ore, the remainder consisting of associated lead carbonate ore. The Consolidated Kansas City smelter group, consisting of the Desdemona, Othello, and Monte Christo claims, was the largest shipper. Other producing mines were the Summit, Contention, and Faywood.

Florida Mountains district.[2]—A large quantity of zinc carbonate ore was shipped from the Lucky John mine.

Fremont district.—A car of lead ore was shipped from the International prospect.

Tres Hermanas district.[3]—From the Homestead mine a very considerable quantity of zinc carbonate ore of very good average of zinc was shipped.

Victorio (Gage) district.[4]—The revival of mining began in this district in 1916 continued throughout 1917. Lead-silver ores were shipped to smelters from the Rambler and the Chance groups.

MORA COUNTY.

A car of copper ore was shipped from the Coyote district, 12 miles north of Mora, N. Mex. The ore is found in a bituminous shale.

[1] Darton, N. H., Geology and underground water of Luna County, N. Mex.; U. S. Geol. Survey Bull. 618, pp. 102–103, 1916.
[2] Darton, N. H., op. cit., pp. 107–108.
[3] Lindgren, Waldemar, The Tres Hermanas mining district, N. Mex.; U. S. Geol. Survey Bull. 380, pp. 123–128, 1909. Darton, N. H., op. cit., pp. 105–106.
[4] Darton, N. H., op. cit., pp. 103–104.

Digitized by Google

OTERO COUNTY.

Mine production in Otero County, N. Mex., 1904-1917.

Year.	Ore.	Gold.		Silver.	Copper.	Lead.	Total value.
		Placer.	Deep.				
	Short tons.			*Fine ounces.*	*Pounds.*	*Pounds.*	
1904	170	$1,050	$1,569	164	14,400	.....	$4,586
1905	117	1,036	41	93	53,602	.....	9,495
1906	268	195	228	533	133,166	.....	26,481
1907	12,203	100	14,711	2,135	679,480	.....	152,116
1908	22,418	1,475	34,215	4,351	723,907	.....	133,552
1909	143	100	157	29	6,354	.....	1,098
1910	2,545	6,022	2,559	2,046	49,874	6,046	16,286
1911	1,096	.....	6,718	715	22,730	739	9,971
1912	3,792	2,084	11,005	1,107	146,588	.....	37,907
1913	25,582	42	49,830	7,088	760,914	1,911	172,179
1914	11,176	.....	38,515	5,761	418,316	2,027	97,416
1915	16,628	.....	54,979	6,255	872,748	.....	210,881
1916	21,838	305	39,525	7,928	1,166,972	17,392	333,321
1917	17,991	737	23,510	4,850	814,736	13,907	251,862
Increase or decrease, 1917	−3,847	+432	−16,015	−3,078	−352,236	−3,485	−81,459

Highrolls (Sacramento) district.—The continuing high price of copper seems to have been the reason for an increase in copper ore shipments from this district, which until 1917 had made its largest yield in 1916. The producing mines were the Alvarado, Alamo, Copper Bell, Nelson, and Old Reliable.

Jarilla (Orogrande, Silver Hill) district.—Lode mines in this district in 1917 produced 15,558 tons of ore, yielding $23,504 in gold, 4,511 ounces of silver, and 731,894 pounds of copper, with a total value of $227,028. This production, in point of gross value, is the largest on record for the district, except that for the year 1916. There was also some production of placer gold from the Little Joe placer, the gravel of which was worked by jigs, trommels, and shaking riffles. Producing deep mines were the By Chance, Delusion, Garnet, Gem, Iron Mask, Mexican, Nannie Baird, Providence, Turquoise, and Verde. In addition, considerable magnetite iron ore was shipped to the Colorado Fuel & Iron Co.'s steel mill at Pueblo, Colo.

Tularosa district.—The Tularosa Copper Co.'s 100-ton wet concentration mill was operated on low-grade copper ore from the Virginia mine for six months, until compelled to close by the high cost of labor and supplies. Several cars of merchantable copper concentrates were produced.

RIO ARRIBA COUNTY.

Several small lots of silver-copper ore were shipped from Espanola, Tres Piedras, and El Vada.

SANDOVAL COUNTY.

Cochiti (Bland) district.—The Cossak 100-ton continuous countercurrent decantation-cyanidation mill, closed in October, 1916, was not operated in 1917.

Nacimiento Mountains district.—A car of silver-copper ore was shipped from the Copper Glance mine, near Senorita, in the "Red Beds."

Digitized by Google

SAN MIGUEL COUNTY.

The Pecos Mines Co. did extensive development work on its patented claims, in the Copper district, at the junction of Willow Creek and Pecos River, 15 miles from Valley Ranch post office.

SANTA FE COUNTY.

Mine production in Santa Fe County, N. Mex., 1904–1917.

Year.	Ore.	Gold.		Silver.	Copper.	Lead.	Zinc.	Total value.
		Placer.	Deep.					
	Short tons.			*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1904	170	$4,135	$1,292	.....	2,308	.....	.....	$5,727
1905	180	4,002	2,241	42	.....	.....	.....	2,266
1906	128	6,737	7,143	53	.....	.....	.....	13,916
1907	21,338	1,231	16,748	17,635	1,231,260	.....	.....	275,870
1908	7	1,789	242	6	.....	.....	.....	2,034
1909	2,831	1,817	871	2,295	1,093	213,558	4,426	13,445
1910	4,739	4,262	3,877	3,359	5,150	262,023	74,759	26,173
1911	120	2,359	1,325	2,632	16,644	11,178	.....	7,663
1912	15,335	1,302	10,216	14,178	810,563	12,511	10,565	155,272
1913	29,800	129	26,076	22,076	1,798,769	794	.....	319,053
1914	23,584	1,312	9,040	5,723	293,360	52,948	89,860	59,182
1915	27,713	1,567	42,100	24,371	1,704,857	50,638	14,556	358,558
1916	42,683	3,112	66,254	31,871	2,153,610	166,304	334,321	676,399
1917	10,159	2,155	7,152	6,892	400,143	17,779	512,628	178,042
Increase or decrease, 1917	−32,524	−957	−59,102	−24,979	−1,753,467	−148,525	+178,307	−498,357

Cerillos district.—A car of zinc ore was shipped from the Grand Central mine and a car of copper ore from the Bonanza mine. The 100-ton concentrating plant of the Tom Payne mine was operated during part of the year, the product being a zinc concentrate.

In July, 1917, the Grubnau, Bryant & Grubnau zinc oxide furnaces were started in operation at Waldo, near Cerrillos. This plant used zinc carbonate ores from New Mexico, Arizona, and Colorado. No doubt this plant was built at this place because of the proximity of the Cerrillos coal fields, where an anthracite coal, necessary for the burning of zinc oxide, is found.

Montezuma district.—A test of copper ore was shipped from the Taggart group, in Dalton Canon, 12 miles east of Santa Fe.

De Vargas district.—A test car of low-grade silver-copper ore was shipped from a prospect on the De Vargas Grant.

New Placers and San Pedro districts.—The mines and 125-ton matting blast furnace of the Santa Fe Gold & Copper Co., at San Pedro, were operated only the first three months of the year. Development work was continued through July. Several cars of copper ore from prospects in the San Pedro district were shipped to smelters.

The Santa Fe Dredging Co. continued testing the gravels of the Golden placer, near Golden, with a traction dredge. In 1918 this company started the construction of a floating chain-bucket dredge. Various small lots of placer gold from this district were marketed during the year.

Digitized by Google

SIERRA COUNTY.

Mine production in Sierra County, N. Mex., 1904–1917.

Year.	Ore.	Gold.		Silver.	Copper.	Lead.	Zinc.	Total value
		Placer.	Deep.					
	Short tons.			*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1904	1,295	$22,979	$51,617	17,055	16,700	.....	.....	$96,632
1905	3,516	47,878	51,164	8,700	46,664	.....	.....	11,613
1906	3,246	1,509	16,539	8,102	5,995	.....	.....	24,633
1907	700	595	7,629	2,250	5,425	9,548	.....	11,300
1908	680	1,979	16,039	8,589	12,874	6,075	.....	24,524
1909	4,294	.....	10,450	25,698	25,838	49,023	.....	29,280
1910	8,306	584	11,113	15,778	2,448	11,274	.....	21,024
1911	5,036	823	26,962	16,487	5,374	28,088	.....	38,459
1912	252	1,546	2,597	11,236	8,988	21,001	.....	13,481
1913	269	423	434	2,529	2,568	32,685	.....	4,221
1914	98	442	1,305	3,982	14,436	5,743	.....	6,093
1915	438	1,757	1,079	316	2,228	24,617	7,492	5,472
1916	935	.....	1,468	2,138	14,427	126,609	7,045	16,104
1917	619	331	1,470	8,712	11,828	80,116	.....	19,099
Increase or decrease, 1917	−316	+331	+2	+6,574	−2,599	−46,493	−7,045	+2,995

Caballos Mountain district.[1]—Lessees operating the Marion and Gladys mines shipped a considerable quantity of lead ore to El Paso.

Chloride (Apache, Cuchillo Negro) district.—Development work only was done in this district.

Hermosa district.—Small lots of lead ore were shipped from the Antelope and from the Woolford mine.

Hillsboro (Las Animas) district.—Several small lots of copper ore were shipped from this district.

Kingston (Black Range) district.—A car of silver ore was shipped from the Lady Franklin mine, which is opened by an adit 1,700 feet long. Development work was done at the Empire Zinc Co.'s property.

Lake Valley district.[2]—The demand for manganese resulted in a very considerable output of ore, averaging 37 per cent manganese, from this district, once an important silver-producing district.

Tierra Blanca district.—A car of silver-lead ore was shipped from the Roper group to the smelter at Deming.

[1] Hess, F. L., Vanadium in the Sierra de los Caballos, N. Mex.: U. S. Geol. Survey Bull. 530, pp. 157–160, 1912.

[2] Clark, Ellis, The silver mines of Lake Valley, N. Mex.: Am. Inst. Min. Eng. Trans., vol. 24, pp. 138–167, 1894.

Digitized by Google

SOCORRO COUNTY.

Mine production in Socorro County, N. Mex., 1911–1917.

Year.	Gold.		Silver.	
	Quantity.	Value.	Quantity.	Value.
	Fine ounces.		*Fine ounces.*	
1911	25,844.49	$534,253	1,109,945	$568,271
1912	25,427.30	525,629	1,126,439	692,754
1913	30,179.04	623,856	1,347,160	813,685
1914	30,542.38	631,367	1,424,763	787,993
1915	24,654.47	509,653	1,358,000	688,506
1916	18,146.67	375,125	1,061,711	711,766
1917	12,616.49	260,806	859,892	708,551
Decrease, 1917	5,530.18	114,319	221,819	3,215

Year.	Copper.		Lead.		Zinc.		Total value.
	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	
	Pounds.		*Pounds.*		*Pounds.*		
1911	79,321	$9,915	2,124,901	$95,621	9,930,281	$566,026	$1,794,086
1912	89,776	14,813	2,193,178	98,693	9,962,478	687,411	2,019,300
1913	289,566	44,883	2,199,247	96,767	13,267,811	742,997	2,322,188
1914	214,722	28,588	674,795	26,317	13,785,176	703,044	2,177,179
1915	1,416,098	247,817	2,033,723	95,585	18,437,218	2,286,215	3,827,776
1916	1,013,264	249,263	4,424,522	305,292	19,312,179	2,587,832	4,229,278
1917	2,699,747	737,031	4,886,803	420,265	14,716,745	1,501,108	3,627,761
Increase or decrease, 1917	+1,686,483	+487,768	+462,281	+114,973	−4,595,434	−1,086,724	−601,517

Magdalena (Kelly) district.—The Magdalena district has been best known as a zinc carbonate and zinc sulphide district, and for 1917 the production of zinc was 14,716,745 pounds, valued at $1,501,108, as against 19,312,179 pounds, valued at $2,587,832 in 1916. The production of lead increased from 4,421,290 pounds in 1916 to 4,885,210 pounds in 1917, and of copper increased from 993,199 pounds to 2,690,381 pounds. The production of silver increased from 72,877 ounces to 137,114 ounces.

The Graphic mill, destroyed by fire on August 10, 1916, was completely reconstructed by March 1, 1917, and milling operations were continued from that date throughout the year on zinc sulphide ore from the Graphic and Waldo mines, with product of zinc concentrate. In addition, regular shipments of copper sulphide, zinc carbonate, lead carbonate, and zinc-lead carbonate ores were continued. The new mill has the following equipment: Blake crusher, rolls, Chilean mill, tube mill, Janney flotation machines, Ovoca classifiers, Oliver filters.

The Kelly magnetic separation mill was operated on zinc sulphide ores from the Kelly mine. In addition, a large quantity of zinc carbonate ore and lead carbonate ore was shipped from this mine to smelters.

The Black Cloud mill was idle in 1917, having been in operation only for several months after its completion in September, 1916.

Lead and lead-copper ores were shipped from the Germany mine, lead carbonate and zinc carbonate from the Juanita, and copper, lead, and zinc ores from the Hardscrabble.

Digitized by Google

Mine production in Magdalena district, Socorro County, N. Mex., 1904–1917.

Year.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
	Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1904	27,998	$154	5,024	3,200	688,209	17,991,780	$932,658
1905	30,411	.....	4,800	320,000	390,000	14,630,051	934,322
1906	35,478	.....	2,515	64,560	238,088	17,044,163	1,067,410
1907	3,630	13	4,406	24,045	707,981	676,356	85,158
1908	6,319	72	460	2,605	16,073	3,325,446	157,631
1909	30,724	435	17,925	170,792	3,085,279	12,878,241	860,051
1910	42,232	408	65,800	152,181	3,451,228	16,727,870	1,110,529
1911	25,840	352	42,773	77,448	2,123,039	9,930,281	694,266
1912	22,500	746	32,792	69,532	2,192,792	9,962,478	818,473
1913	47,647	3,942	40,212	278,252	2,198,030	13,267,811	911,069
1914	51,595	2,265	14,436	214,722	674,205	13,785,176	768,144
1915	75,401	488	56,897	1,406,789	2,031,297	18,437,218	2,657,209
1916	78,669	2,036	72,877	993,199	4,421,290	19,312,179	3,187,217
1917	100,709	2,186	137,114	2,690,381	4,885,210	14,716,745	2,770,878
Increase or decrease, 1917	+22,040	+150	+64,237	+1,607,182	+463,920	−4,595,434	−416,339

Mogollon (Cooney) district.—This district maintained its position as the most productive silver-mining district in New Mexico, its silver output representing 52 per cent of that of the State. The gold output from this district represented only 24 per cent of the total output of the gold produced in the State.

The Mogollon Mines Co.'s cyanidation and concentration mill was operated continuously on company ore and on custom ore from the Oaks Co. The Socorro Mining & Milling Co.'s cyanidation mill was operated on company ore and custom ore until October 26, 1917, when fire destroyed the greater part of the plant. The producing mines operated by the Oaks Co. included the Clifton, Deep Down, Eberle, and Maud S.

Mine production in Mogollon or Cooney district, Socorro County, N. Mex., 1904–1917.

Year.	Ore.	Gold.	Silver.	Copper.	Lead.	Total value.
	Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	
1904	11,276	$61,880	79,014	422,308	.....	$162,484
1905	15,534	97,158	240,943	295,175	.....	288,735
1906	16,076	127,907	268,567	.....	.....	307,847
1907	20,698	105,413	418,338	150,000	.....	411,516
1908	19,546	116,418	278,939	.....	.....	264,256
1909	23,945	111,464	249,413	46	49	241,167
1910	50,514	304,210	595,669	.....	.....	625,871
1911	102,219	531,358	1,067,038	1,873	1,862	1,097,206
1912	101,361	524,858	1,093,158	184	386	1,197,197
1913	115,739	619,886	1,306,766	4,418	1,217	1,409,912
1914	136,124	629,102	1,410,327	.....	590	1,409,035
1915	119,710	509,165	1,301,059	.....	2,426	1,168,916
1916	118,257	373,068	1,008,483	858	3,232	1,037,084
1917	111,934	258,620	722,642	414	1,593	854,327
Decrease, 1917	6,323	114,448	285,841	444	1,639	182,757

Oscuro Mountains.—Several carloads and other small lots of copper ore were shipped from the Oscuro Mountains, northwest of Oscuro, in Lincoln County.

Carthage (Headquarters district).—Tests of the new mill at the Rim Rock mine yielded several cars of lead concentrates. The mill is a dry crushing plant, consisting of a Blake crusher, rolls, and Plumb jigs. Several small lots of copper ore were also shipped from this district.

Digitized by Google

TAOS COUNTY.

Copper Mountain (Picuris) district.—The 25-ton concentration mill of the Champion mine was operated for a short time and the product, a small quantity of copper concentrate, with some crude ore from the mine, was shipped to El Paso. A car of copper ore was also shipped from the Isabella mine.

Red River district.—The June Bug mill (built in 1898) was rebuilt as an oil flotation mill in 1916 by the Memphis-Red River Co., and in 1917 treated several hundred tons of gold-silver ore. Development work was done at several other properties in this district.

Rio Hondo district.—No work was done at the copper prospects, near Twining.

TORRANCE COUNTY.

Carocito district.[1]—Shipments begun in 1916 from several prospects north of Scholle and west of Mountainair, on the Atchison, Topeka & Santa Fe Railway, continued in 1917. The output for 1917 was 2,169 tons of copper ore carrying $30 in gold, 1,312 ounces of silver, and 200,626 pounds of copper, as against 3,172 tons carrying 2,600 ounces of silver and 331,475 pounds of copper in 1916. According to Charles T. Kirk, State geologist of New Mexico, the ores are mainly of the bedded type and occur in the "Red Beds." The ore lies nearly altogether in limestone and shaly limestone and the minerals are chalcocite, malachite, and azurite.

[1] See Min. and Sci. Press, Sept. 2, 1916, p. 366.

Digitized by Google

GOLD, SILVER, COPPER, LEAD, AND ZINC IN TEXAS.[1]

(MINES REPORT.)

By CHARLES W. HENDERSON.

PRODUCTION.

The total value of the gold, silver, copper, lead, and zinc produced in Texas in 1917 was $499,794, the largest since the beginning of the mining industry of the State, in 1884. The output of silver, the principal metal produced, showed a considerable decrease, but the total value of the silver at the increased average value was considerably greater than in 1916. The Presidio silver mine, at Shafter, equipped with a large cyanidation mill, continued to produce at approximately its regular annual rate, and its output continued to represent the greater part of the State total. A car of zinc ore was also shipped from the Shafter district.

From Van Horn, Culberson County, was shipped a car of copper ore and one of silver ore; a car of copper ore was shipped from Crowell, Foard County; a car of copper ore from Chillicothe, Hardeman County; and copper and silver ore was shipped from the Allamoore-Sierra Blanca district, Hudspeth County.

Mine production of gold, silver, copper, lead, and zinc in Texas, 1885–1917.[a]

Period.	Gold.	Silver.		Copper.		Lead.		Zinc.		Total value (commercial).
		Quantity.	Commercial value.	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	
		Fine oz.		*Pounds.*		*Pounds.*		*Pounds.*		
1885–1890	$6,906	1,670,720	$1,652,225							$1,659,131
1891–1900	30,682	4,332,214	2,979,288	42,000	$5,376	7,385	$318			3,015,664
1901–1910	3,372	3,950,644	2,266,537	35,383	4,647	295,018	13,611	95,957	$5,262	2,293,429
1911	21	424,394	224,929			122,800	5,526			230,476
1912	63	406,067	249,731	721	119	65,311	2,939	238,000	16,422	269,274
1913	340	427,553	258,242	34,665	5,373	225,227	9,910	652,607	36,546	310,411
1914	234	530,817	295,542	23,760	3,160	149,027	5,812	216,451	11,039	313,787
1915	1,503	675,473	342,465	42,491	7,436	219,298	10,307	80,395	3,769	365,480
1916	414	653,455	429,973	99,569	24,494	49,927	3,445	282,388	31,140	489,466
1917	22	595,789	490,930	23,132	6,315	2,490	214	22,676	2,313	499,794
	43,557	13,667,126	9,187,862	301,721	56,920	1,136,483	52,082	1,488,474	106,491	9,446,912
Increase or decrease, 1917	− 392	− 57,666	+ 60,957	−76,437	−18,179	− 47,437	− 3,231	−209,712	−28,827	+ 10,328

[a] For yearly output and authority for each, see U. S. Geol. Survey Mineral Resources, 1914, pt. 1, p. 236, 1915.

REDUCTION MILLS.

A complete list of the reduction mills in Texas in 1912, with description of equipment and process, was given in Mineral Resources for 1912, part 1, page 879. Any changes in this list for 1913–1917 have been noted in the text for the several counties for each year.

[1] For discussion of the geology of the districts mentioned in the following pages the reader is directed to the bibliography in Mineral Resources, 1912, pt. 1, pp. 876–877, 1913; to Survey Bulletin 507 (The mining districts of the western United States, by J. M. Hill), with a geologic introduction by Waldemar Lindgren, 1912; and to Mineral Resources, 1908, pt. 1, pp. 539–540, 1909.

Digitized by Google

REVIEW BY COUNTIES.[1]

BREWSTER COUNTY.

There were no shipments of ore from the Alpine district, but some development work was done at the Bird mine, from which, in the past, some silver-bearing galena ore has been shipped to the El Paso smelter.[2]

BURNET COUNTY.[3]

No work was done on the Copper prospects northwest of Burnet.

COLEMAN COUNTY.

Some prospecting and development by shallow holes was done at the Lee Baker farm, near Santa Ana.

CULBERSON COUNTY.[3]

The mining districts of Culberson County were included in El Paso County before 1911. In 1917 a car each of ore was shipped from the Hazel and from the Pecos mine. The ore of the Hazel mine occurs in pre-Cambrian sandstone.[4]

EL PASO COUNTY.

(See Culberson and Hudspeth counties.)

FOARD AND KNOX COUNTIES.

A car of copper ore was shipped from the Foard County Copper Co.'s prospect, near Crowell, from the blue clays of the Permian beds.[5]

Some development work was done by the Brazos Wichita Copper Co., on prospects near Benjamin.

HUDSPETH COUNTY.

Prior to 1917, the mining districts now in Hudspeth County were in El Paso County. A car of silver-copper ore was shipped by the Texas Mining Co., at Allamore. A car of silver ore was shipped from the Tama mine, at Sierra Blanca. A car of ore was mined from the Little Lightning mine, at Sierra Blanca, but not shipped until 1918.

PRESIDIO COUNTY.

Shafter district.[6]—Operations were continuous at the Presidio mine, from which the greater part of the silver output of the State has come since 1884. The ore, chiefly silver chloride (horn silver), is treated in a 125-ton cyanidation mill.

---

[1] In this section references to discussions of the geology of the several districts are given in the footnotes.

[2] Phillips, W. B., Lead ore in Burnet County, Tex.: Eng. and Min. Jour., vol. 77, p. 364, 1904.

[3] Richardson, G. B., U. S. Geol. Survey Geol. Atlas, Van Horn folio (No. 194), 1913.

[4] Richardson, G. B., Reconnaissance of trans-Pecos Texas: Texas Univ. Mineral Survey Bull. 9, pp. 24–25, 1904. Von Streeruwitz, W. H., Report on the Geology and mineral resources of trans-Pecos Texas: Texas Geol. Survey third Ann. Rept., p. 699, 1891, Trans-Pecos Texas; Texas Geol. Survey Third Ann. Rept., pp. 387–389, 1892.

[5] Cummins, W. F., Notes on the Geology of northwest Texas: Texas Geol. Survey Fourth Ann. Rept., pp. 232–238, 1893. Phillips, W. B., Texas Geol. Survey Second Ann. Rept., p. 450, 1890. Phillips, W. B. The Permian copper ores in Texas: Eng. and Min. Jour., Dec. 16, 1911, pp. 1181–1182.

[6] Phillips, W. B., Shafter silver district, Presidio County, Tex.: Eng. and Min. Jour.; p. 1303, Dec. 31, 1910. Udden, J. A., The geology of the Shafter silver mine district, Presidio County, Tex.: Texas Univ. Mineral Survey Bull. 8, p. 54, 1904.

Digitized by Google

COPPER.

By B. S. Butler.

INTRODUCTION.

In the production of metallic copper suitable for commercial purposes at least three distinct processes are usually required, namely, mining, smelting, and refining. The Lake Superior native-copper district is the only important producing region where these three processes are not entirely distinct. It is possible, therefore, to ascertain the copper output of the country by collecting statistics from the mines, from the smelters, and from the refineries, and each of these sets of figures has its advantages. The mine figures have the advantage of giving the most accurate distribution of the production but are less accurate in total quantity of copper recovered; the smelter figures permit reasonably accurate distribution and also furnish the actual recovery of copper from the ores treated during the year; the refinery figures furnish the best measures of the copper made available for commercial uses during the year, but at this stage of manufacture the accurate distribution to the State of origin, or even the separation of copper derived from domestic and from foreign sources, is uncertain.

Statistics for 1917 showing the production of each of these stages of manufacture have been collected by the United States Geological Survey and are presented in the following report.

As the same material passes through the three processes of manufacture at successive periods, usually requiring two to three months from the time it is taken from the mine before it reaches the stage of refined copper, the year's production as recorded for the different stages does not represent the same materials—that is, the refinery production for the calendar year 1917 represents the mine production from about October 1, 1916, to October 1, 1917. The three sets of figures representing the successive stages of manufacture do not, therefore, necessarily agree, although they should not differ greatly if the condition of the industry is normal. The mine figures and the smelter figures will differ by the difference in the quantity of ore, matte, and other materials in stock at the beginning and at the end of the year and by the difference in the quantity of copper reported by the mines and that recovered by the smelters. The latter differ-

Digitized by Google

ence is due to the fact that considerable copper is recovered from sulphur, lead, zinc, and siliceous ores carrying so little copper that the mines do not receive pay for and frequently do not report the copper content of the ore, although it is eventually recovered by the smelters. The smelter and refinery figures will differ by the increase or decrease in stock of blister and other unrefined forms of copper at the beginning and at the end of the year and by the loss in refining.

As the smelter production permits reasonably accurate distribution as to the source by States and also gives the actual output of copper, it is adopted in this report as the production of the country. It is made up of the production of blister copper and of furnace-refined or ingot copper of the Lake district.

SUMMARY OF STATISTICS.

Summary of statistics of the copper industry in the United States in 1912, 1913, 1914, 1915, 1916, and 1917.

	1912	1913	1914
Production of copper:			
Smelter output.....pounds..	1,243,268,720	1,224,484,098	1,150,137,192
Mine production.....do....	1,249,094,891	1,235,569,727	1,148,431,437
Refinery production of new copper:			
Electrolytic.....do....	914,935,871	1,022,497,601	991,573,073
Lake.....do....	231,112,228	155,715,286	158,009,748
Casting and pig.....do....	57,629,296	58,611,026	60,840,368
Total domestic.....do....	1,203,676,895	1,236,823,913	1,210,423,189
Total domestic and foreign.....do....	1,568,104,478	1,615,067,782	1,533,781,394
Total new and old copper.....do....	1,843,000,000	1,888,000,000	1,790,000,000
Total ore produced.....short tons..	35,671,028	36,361,101	35,187,118
Copper ore produced.....do....	35,656,414	36,336,682	35,175,541
Average yield of copper.....per cent..	1.71	1.67	1.60
Average price per pound.....cents..	16.5	15.5	13.3
Imports (unmanufactured).....pounds..	410,241,295	408,778,954	306,350,827
Exports of metallic copper [a].....do....	775,000,658	926,241,092	840,080,922
Consumption:			
Total new copper.....do....	775,978,332	812,268,639	610,445,373
Total new and old copper.....do....	1,051,000,000	1,085,000,000	866,000,000
World's production.....do....	2,237,576,000	2,168,361,000	2,052,917,000
Value of production in the United States.....	$205,139,338	$189,795,035	$152,968,000

	1915	1916	1917
Production of copper:			
Smelter output.....pounds..	1,388,009,527	1,927,850,548	1,886,120,721
Mine production.....do....	1,488,071,528	2,005,875,312	1,895,434,349
Refinery production of new copper:			
Electrolytic.....do....	1,114,345,342	1,579,620,513	1,452,744,593
Lake.....do....	236,757,062	269,794,531	268,508,091
Casting and pig.....do....	36,603,119	39,337,155	152,293,487
Total domestic.....do....	1,387,705,523	1,888,752,199	1,873,546,171
Total domestic and foreign.....do....	1,634,204,448	2,259,387,315	2,428,546,171
Total new and old copper.....do....	2,027,000,000	2,959,000,000	3,195,000,000
Total ore produced.....short tons..	43,415,133	57,953,357	58,514,325
Copper ore produced.....do....	43,404,182	57,863,365	58,482,694
Average yield of copper.....per cent..	1.66	1.70	1.60
Average price per pound.....cents..	17.5	24.6	27.3
Imports (unmanufactured).....pounds..	315,698,449	462,335,980	556,420,297
Exports of metallic copper [a].....do....	681,917,955	784,006,486	1,125,647,336
Consumption:			
Total new copper.....do....	1,043,497,328	1,429,755,266	1,315,670,803
Total new and old copper.....do....	1,435,000,000	2,130,000,000	2,063,000,000
World's production.....do....	2,381,169,000	3,037,163,000	3,205,828,000
Value of production in the United States.....	$242,902,000	$474,288,000	$514,911,000

[a] Total exports of copper exclusive of ore, concentrates, and composition metal.

Digitized by Google

Copper produced in the United States, 1913–1917.

[Smelter output, in pounds fine.]

	1913	1914	1915	1916	1917
Alaska	23,423,670	24,985,847	70,695,286	113,823,064	84,759,086
Arizona	404,278 809	382,449,922	432 467,690	694,8a7,307	719,035,514
California	32,492,265	29,784,173	37 658 444	43,400,876	44,933,846
Colorado	9,052,104	7,316,066	7,272,178	9,536,193	10,054,951
Georgia				803,699	930,691
Idaho	8,711,490	5,875,205	6,217,728	7,248,794	6,446,224
Maine					34,872
Maryland		12,248	15 426	126,965	291,501
Michigan	155,715,286	158,009,748	238,956,410	269,794,531	268,508,091
Missouri	576,204	53,519	306,406	377,575	407 141
Montana	285,724,467	236,805,845	268,263,040	352,139,768	276,225,977
Nevada	85,209,536	60,122,904	67,757,322	100,816,724	115,028,161
New Jersey				4,115	
New Mexico	50,196,881	64,204,703	62,817,234	79,863,439	107,593,615
North Carolina	180	19,712	33,353	5,961	125,004
Oregon	77,812	5,599	797,471	2,433,567	1,105,097
Pennsylvania	245,337	422,741		904	115,000
South Carolina					210,000
Tennessee	19,489,654	18,661,112	18,205,308	14,556,278	16,093,757
Texas	39,008	34,272	38,971	86,463	2,061,129
Utah	148,057,450	160,589,660	175,177,695	232,335,950	227,840,447
Vermont	5,771		23,995	324,400	102,522
Virginia	46,961	17,753	50,008	1,066,143	146,912
Washington	732,742	683,602	903,661	2,473,481	2,051,416
Wyoming	362,235	17,082	351,871	1,78a,351	2,019,767
Undistributed	46,836	65,479			
	1,224,484,098	1,150,137,192	1,388,009,527	1,927,850,548	1,886,120,721

World's production of copper (smelter output), 1908–1917, in metric tons.[a]

Country.	1908	1909	1910	1911	1912
Germany	20,500	22,800	25,100	22,400	25,600
England	5,441	3,717	4,178	3,262	1,933
Italy	2,825	2,535	1,7o6	1,666	2,319
Norway	1,591	1,545	1,8i4	1,565	2,130
Austria-Hungary	[b] 1,700	[b] 1,700	[b] 2,300	[b] 2,600	[b] 4,000
Russia	17,133	17,801	22,686	25,9a6	33,972
Sweden	2,808	2,375	3,111	3,221	3,957
Spain	45,063	44,892	48,532	49,211	61,018
Turkey	[b] 1,100	[b] 800	[b] 600	[b] 1,000	[b] 500
Serbia	[b] 2,200	[b] 4,600	[b] 4,900	[b] 7,000	[b] 7,400
Portugal	[c] 8,000	[c] 8,000	[c] 7,000	[c] 7,500	[c] 6,500
Total Europe	108,351	110,765	121,987	125,371	149,329
Canada	28,895	23,811	25,262	25,242	35,304
Mexico	30,413	43,598	52,723	59,421	55,068
Cuba	[b] 3,000	[b] 3,000	[b] 3,500	[b] 3,800	[b] 4,400
Newfoundland	[b] 1,500	[b] 1,400	[b] 1,100	[b] 1,200	[b] 500
United States	427,547	495,760	489,9o7	497,702	563,943
Total North America	491,355	567,569	572,542	587,365	659,215
Argentina	[b] 200	[b] 600	[b] 300	[b] 1,000	[b] 300
Bolivia	[d] 2,540	[d] 2,032	[d] 2,b20	[d] 1,829	[d] 1,880
Chile	42,997	42,726	38,2o2	36,420	41,647
Peru	19,854	20,068	27,374	27,735	26,969
Venezuela				[c] 725	[c] 851
Total Central and South America	65,591	65,426	68,446	67,709	71,647
Union of South Africa	1,073	1,643	2,647	20,954	16,847
Southern Rhodesia	85	88	39		
Other Africa	[c] 2,400	[c] 10,800	[c] 10,900	[b] 10,814	[b] 11,231
Total Africa	3,558	12,531	13,586	31,768	28,078
Japan	40,653	45,841	49,324	53,402	62,423
Australia	[e] 38,930	[e] 37,103	40,028	44,473	44,266
Grand total	748,438	839,235	865,913	910,088	1,014,958

[a] Figures unaccompanied by footnote references are taken from official publications. The official figures for countries where ore or matte was exported for smelting have been converted to quantities showing copper recoverable by the smelters.

[b] Figures compiled by Henry Merton & Co. (Ltd.)

[c] Estimated by U. S. Geological Survey.

[d] Figures taken from Chilean official publication.

[e] Nearly completely official. A small part estimated by the U. S. Geological Survey.

Digitized by Google

World's production of copper (smelter output), 1908–1917, in metric tons [a]—Con.

Country.	1913	1914	1915	1916	1917
Germany	25,300	[b] 30,000	[b] 35,000	[b] 35,000	[b] 45,000
England	2,732	2,558	822	1,028	1,159
Italy	2,091	1,839	940	1,867	1,331
Norway	2,741	2,860	2,828	1,614	[b] 2,000
Austria-Hungary	[c] 4,100	[b] 3,300	.....	.....	.....
Russia	33,694	32,334	25,962	[b] 13,380	[b] 17,000
Sweden	4,215	4,692	4,561	3,181	4,423
Spain	31,248	25,706	34,699	32,880	33,526
Turkey	[c] 500	.....	.....	.....	.....
Serbia	[c] 6,400	.....	.....	.....	.....
Portugal	[b] 5,800	[b] 4,570	[b] 4,290	[b] 4,308	[b] 4,300
Total Europe	118,821	107,859	109,102	93,258	113,739
Canada	34,916	34,354	45,716	53,139	49,545
Mexico	[b] 52,800	[b] 36,337	20,598	28,411	50,986
Cuba	[c] 3,400	[b] 6,300	[b] 8,900	[b] 9,500	[b] 10,700
Newfoundland	.....	.....	.....	.....	.....
United States	555,422	521,699	629,597	874,467	855,539
Total North America	646,538	598,690	704,811	965,517	966,770
Argentina	[c] 100	[b] 300	[b] 300	[b] 300	[b] 300
Bolivia	4,029	8,667	23,813	29,011	37,444
Chile	42,263	44,665	52,341	71,288	102,527
Peru	27,776	27,090	34,728	43,078	45,176
Venezuela	[b] 720	[b] 720	[b] 750	[b] 840	[b] 862
Total Central and South America	74,888	81,442	111,932	144,517	186,309
Union of South Africa	16,677	26,604	26,281	20,722	18,263
Southern Rhodesia	.....	917	3,191	3,194	3,548
Other Africa	[c] 14,803	[c] 6,524	[b] 10,000	[b] 10,000	[b] 14,477
Total Africa	31,480	34,045	39,472	33,916	36,288
Japan	66,501	70,463	75,416	100,636	111,188
Australia	45,334	38,698	39,358	39,804	39,860
Grand total	983,562	931,197	1,080,091	1,377,648	1,454,154

[a] Figures unaccompanied by footnote references are taken from official publications. The official figures for countries where ore or matte was exported for smelting have been converted to quantities showing copper recoverable by the smelters.
[b] Estimated by U. S. Geological Survey.
[c] Figures compiled by Henry Merton & Co. (Ltd.).

GENERAL CONDITION OF THE INDUSTRY.

WORLD'S PRODUCTION AND CONSUMPTION.

The production and consumption of copper in the world during any period are essentially the same; they differ only by the relatively small changes in stocks. Since the beginning of the war there has been a large increase in the production and consumption, as shown in the accompanying diagram (fig. 13). The increase in production has come mainly from the United States, Canada, Chile, Peru, Japan, Africa, and Germany. Mexico and Russia have produced less copper than before the war. (See fig. 14.) The consumption of copper by the different countries since the beginning of the war is not accurately known, first, because statistics have not been given out by some of the countries, and, second, because the copper that has entered war uses has been so distributed among the nations allied in the war that it can not easily be credited to the country that used it. A quantity equivalent to the entire increase over the pre-war period, and considerably more, has been used on the battle fields of Europe.

Digitized by Google



FIGURE 13.—Curves showing the principal features of the copper industry, 1907–1918.

Digitized by Google



	Metric tons 1913	1917
United States	565,422	855,539
Japan	66,501	111,188
Chile	42,263	102,527
Canada	34,916	49,545
Mexico	52,800	50,986
Peru	27,776	45,176
Germany	25,300	45,000
Spain and Portugal	37,048	42,826
Australia	45,334	39,860
Africa	31,480	36,288
Norway	2,741	2,000
Russia	33,694	17,000
Other countries	28,287	56,219
World	983,562	1,454,154

FIGURE 14.—Production of copper by countries, 1913 and 1917.

The following table gives the consumption by the more important manufacturing countries in 1913. This represented peace consumption:

Copper consumed in 1913.

[From Metallgesellschaft, 1913.]

Europe:	Metric tons.
Germany	259,300
England	140,300
France	103,600
Austria-Hungary	39,200
Russia	40,200
Italy	31,200
Belgium	15,000
Netherlands	1,000
Other Europe	13,300
Total Europe	643,100

America:	Metric tons.
United States	348,100
Other America	3,000
Total America	351,100
Asia, Australia, and Africa	50,300
World's consumption	1,044,500

The accompanying diagram (Pl. VI) shows the position of the principal producing centers of the world.

Digitized by Google



Digitized by Google

Digitized by Google

It is evident that the United States is by far the largest single factor in nearly every phase of the industry. At present it is not only the largest producer and consumer, but excels in both imports and exports. There was a considerable increase in 1916 and 1917 in the copper imported into the United States in various stages of manufacture. This was due in part to increase of production of copper that would have naturally been refined in the United States, and in part to shipping conditions that made it advantageous to ship



FIGURE 15.—Relative production, consumption, imports, and exports, of copper by the principal copper producing and consuming countries in 1913.

to the United States copper that had previously gone direct to European countries. With the shortage of labor that was developing in the United States during 1917 and that continued to increase in 1918 it was evident that a large importation of copper was desirable, as this would utilize labor in some neutral countries that would not otherwise contribute directly to the prosecution of the war. The shortage of shipping which had been increasing during the war became acute when the transportation of the American Army began.

Digitized by Google

The full utilization of labor and the shortage of shipping favored the importation of copper in an advanced state of manufacture and in a highly concentrated form. These conditions resulted in the issuance of an order July 12, 1918, cutting off importation into the United States of copper ore except from Canada, Mexico, and Cuba, and of concentrates containing less than 60 per cent of copper. The order concerning concentrates was modified September 8, 1918, to include concentrates containing 50 per cent copper. Even with the elimination of the ore shipments it was not always found feasible to furnish sufficient shipping to transport the needed supplies to the South American mining companies or to bring their copper to the United States.

DOMESTIC CONDITIONS.

Principal features of copper industry in the United States, 1907–1917.

Year.	Production.			Imports (unmanufactured).
	Refined copper, primary.	Secondary copper.	Smelter production, domestic ores.	
	Pounds.	*Pounds.*	*Pounds.*	*Pounds.*
1907	1,332,500,000	.....	888,900,000	252,600,000
1908	1,137,900,000	.....	942,500,000	218,700,000
1909	1,391,000,000	.....	1,092,900,000	321,800,000
1910	1,422,000,000	.....	1,080,000,000	344,000,000
1911	1,433,800,000	214,000,000	1,097,000,000	334,600,000
1912	1,568,100,000	275,000,000	1,243,000,000	410,000,000
1913	1,615,000,000	273,000,000	1,224,000,000	408,700,000
1914	1,533,700,000	255,800,000	1,150,000,000	306,000,000
1915	1,634,200,000	392,400,000	1,388,600,000	315,600,000
1916	2,259,000,000	700,000,000	1,928,000,000	462,000,000
1917	2,428,000,000	767,000,000	1,886,000,000	556,000,000

Year.	Exports of metallic copper.	Domestic consumption (new copper).	Average yearly price per pound.	World's production.
	Pounds.	*Pounds.*		*Pounds.*
1907	508,900,000	487,700,000	$0.200	1,589,000,000
1908	661,800,000	479,900,000	.132	1,650,000,000
1909	682,800,000	688,500,000	.130	1,850,000,000
1910	708,000,000	732,000,000	.127	1,909,000,000
1911	786,500,000	681,700,000	.125	2,006,000,000
1912	775,000,000	775,900,000	.165	2,238,000,000
1913	926,000,000	812,000,000	.155	2,168,000,000
1914	840,000,000	610,000,000	.133	2,053,000,000
1915	681,900,000	1,043,000,000	.175	2,381,000,000
1916	784,000,000	1,430,000,000	.246	3,037,000,000
1917	1,126,000,000	1,316,000,000	.273	3,206,000,000

In the United States at the beginning of 1917 the producing capacity was the largest in the history of the copper industry and was almost wholly utilized. In 1916 the refineries that had not kept pace with the increased production of raw copper had been enlarged to care for all production. In the early months of 1917 there were few serious interruptions to production, which went on at a record rate. Before the middle of the year, however, labor troubles in the West seriously interfered with production in several of the larger districts. The labor difficulty was further increased by demands for men in the Army and in some district for other war industries.

Digitized by Google

Before a settlement of the labor troubles had been effected the transportation situation had become acute. The industry was hampered by inability to procure supplies or to ship the raw copper. Large quantities of copper on the way to eastern refineries were caught in the transportation jams and but for the importations by water the situation might have been most serious. As it was, the refineries were unable to operate at their full capacity for lack of raw copper. The net result of conditions in 1917 was a slight decrease in the production of copper in the United States, but a considerable increase in the quantity imported, so that there was more copper available for consumption and export than in 1916. Before transportation conditions had improved in the spring of 1918 the labor supply at the refineries had become so short that operation at full capacity was impossible. This condition prevailed until the signing of the armistice caused the demand for copper to decrease greatly.

The cost of production steadily increased throughout 1917, because of increases in nearly all the items that entered into costs. Many of the more skilled laborers entered the Army, so that there was not only an increase in the cost of labor but a decrease in the efficiency. In the Lake Superior district, where there was no disturbance on account of strikes, the average cost of production for the companies reporting that item was 11.17 cents per pound in 1916 and 12.80 cents in 1917, an increase of 1.73 cents. The average increase for all districts was probably somewhat higher.

The average price received for all copper delivered in 1916 was 24.6 cents a pound; in 1917 it was 27.3 cents a pound, an increase of 2.7 cents a pound. The increase in the selling price was doubtless fully as much as the increase in costs, so that the average profit per pound equaled or exceeded that of the previous year. On September 21 a maximum price of 23.5 cents a pound was fixed by agreement between the Government and the copper producers. This price, however, did not apply to a very large proportion of the copper delivered in 1917. A further discussion of costs and prices will be found on pages 783–785.

The average recovery decreased from 1.70 per cent, or 34 pounds per ton of ore in 1916 to 1.60 per cent or 32 pounds per ton of ore in 1917. In several plants the recovery for the year was low as the result of operating plants above their capacity for best metallurgic results, and a decided improvement in this respect may be expected.

By the end of 1916 many of the contracts for munitions for the allied governments had been completed and arrangements had been made to manufacture a much larger output of munitions in Europe. There was, therefore, a larger demand for unmanufactured copper, which resulted in largely increased exports.

The added requirements of our Army and Navy incident to our active participation in the war did not offset the reduction of foreign contracts for munitions, and domestic consumption showed a slight decrease.

Digitized by Google

PRODUCTION.

MINE PRODUCTION AND LABOR EFFICIENCY.

In the copper report for 1916 statistics were presented showing the relative importance of the large and small producers in the copper industry, and the suggestion was offered that with a limited supply of labor available to the industry an increase in the price of copper would not necessarily result in an increase in production. It was believed that an increase in the price would probably result in the employment of much labor in prospecting and in inefficient mining that could advantageously be used in the more efficient mines during the war crisis. Further studies of the subject were made after that report was published and will be summarized in this report. The acute necessity for using our labor to the best advantage is happily past, but it is nevertheless desirable to know how efficient labor is and what effect the change in price had on efficiency. The accompanying table shows the production by different classes of mines for 1913, 1916, and 1917. The average price per pound of copper in 1913 was 15.5 cents, in 1916 24.6 cents, and in 1917 27.3 cents.

Copper output of the United States 1913, 1916, and 1917, classified by mines in which copper was the most important constituent and by those in which it was a by-product, and the production of the copper mines classified according to their contribution to the total output.

Year.	Production from copper mines producing—							
	Less than 1,000,000 pounds.		1,000,000 and less than 5,000,000 pounds.		5,000,000 and less than 10,000,000 pounds.		10,000,000 pounds or more.	
	Number of mines.	Quantity (pounds).	Number of mines.	Quantity (pounds).	Number of mines.	Quantity (pounds).	Number of mines.	Quantity (pounds).
1913	492	22,960,797	36	93,068,952	11	78,178,256	24	1,004,634,383
1916	914	51,497,875	55	131,708,061	12	92,125,118	30	1,703,393,730
1917	1,006	50,641,988	58	130,596,600	16	106,458,988	32	1,579,590,348

Year.	Total.		Copper by-product.		Grand total.		Average price of copper (cents per pound).
	Number of mines.	Quantity (pounds).	Number of mines.	Quantity (pounds).	Number of mines.	Quantity (pounds).	
1913	563	1,198,862,388	883	36,707,339	1,446	1,235,569,727	15.5
1916	1,011	1,977,724,784	837	28,150,528	1,848	2,005,875,312	24.6
1917	1,112	1,867,287,924	813	28,146,425	1,925	1,895,434,349	27.3

The most striking feature of this table is the large increase in the number of small mines from 1913 to 1916 and 1917 without a correspondingly large increase in the copper produced. On the other hand, the large mines showed but a moderate increase in number, but from 1913 to 1916 a very large increase in the production of copper. The effect of the high price of copper, combined with the shortage of labor in the years 1916 and 1917 is worthy of note.

Digitized by Google

There was a considerable increase in the number of small mines operated in 1917 and a proportionate increase in the labor employed, but not a proportionate increase in production. On the other hand, the large mines showed an actual decrease in production. The actual decrease would doubtless be more than accounted for by the loss of production due to strikes in several of the large mines, but it is also true that many of the large mines were short of labor.

It may be said, in general, that metal is won with less labor from the larger than from the smaller mines, but there are many exceptions, and it is of interest to get some approximate idea of the labor efficiency in the mining of copper. This is shown in the accompanying table and figure, which, however, represent only the labor employed in actual mining. A large amount of labor is required for the production of the metal after it has been mined—for some ore as much or more labor than is required for the mining. This varies with the character of the ore. Some comes from the mine a high-grade product ready for smelting, but some must be concentrated before smelting. Many of the mines of the Lake Superior district require a relatively large amount of labor for mining, but the metallurgy is simple, and hence for commercial copper their labor item may compare favorably with that of other mines that require less labor for mining. Moreover, in this table only copper is considered—a treatment which is permissible if copper is of chief interest—but in any adequate study of labor efficiency the by-products of varying importance, as gold and silver, sulphuric acid, and other materials, would necessarily be included. Under these limitations the table shows that a considerable amount of labor was employed at a very low rate of efficiency, and would seem to support the idea that in a time of labor shortage like that during the war the inefficient producer should not be greatly encouraged if maximum production is to be realized.

Classification of copper mines according to efficiency of labor in mining.

Mine production (pounds per man per day).	Percentage of total labor employed.		Percentage of total copper produced by mines.		Average production per man per day.	
	1916	1917	1916	1917	1916	1917
					Pounds.	*Pounds.*
Above 300	6.2	6.4	22.5	22.5	416.1	371.8
200 to 300	7.2	7.7	14.2	16.5	230.0	227.9
100 to 200	14.2	15.6	16.2	17.7	133.3	129.5
75 to 100	39.0	6.5	26.6	5.5	78.9	90.5
50 to 75	18.4	48.2	9.5	30.1	59.6	65.1
Less than 50	15.0	15.5	5.0	4.4	38.5	30.1
	.....	.....	94.0	96.7	108.9	102.2
By-product and labor efficiency unknown	.....	.....	6.0	3.3	.....	.....
	.....	.....	100.0	100.0	.....	.....

The accompanying diagram (fig. 16) shows the relative amount of labor employed in the different classes of mines and the relative efficiency in the production of copper.

Digitized by Google

In the least efficient group in 1917 a total of 2,773,000 days' labor yielded 83,500,000 pounds of copper; in the most efficient group 1,146,000 days' labor yielded 426,000,000 pounds of copper. There seems little question as to which of these groups should have first call



FIGURE 16.—Labor employed and copper produced in different classes of copper mines, 1916 and 1917.

on labor in a time of national crisis. There is likewise little question as to which will survive in normal times. Of course, the prospect must precede the mine, nevertheless in war time, with ample mines to employ all available labor, we are primarily interested in getting out the metal, not in developing mines for future production.

Digitized by Google

SMELTER PRODUCTION.

Copper produced in the United States from 1845 to 1917, inclusive.

[Values rounded.]

Year.	Quantity.	Increase.	Value.	Year.	Quantity.	Increase.	Value.
	Pounds.	*Pounds.*			*Pounds.*	*Pounds.*	
1845	224,000		$45,000	1883	115,526,053	24,879,821	$19,062,000
1846	336,000	112,000	57,000	1884	144,946,653	29,420,600	18,842,000
1847	672,000	336,000	124,000	1885	165,875,483	20,928,830	17,915,000
1848	1,120,000	448,000	218,000	1886	157,763,043	a 8,112,440	17,512,000
1849	1,568,000	448,000	349,000	1887	181,477,331	23,714,288	25,044,000
1850	1,456,000	a 112,000	320,000	1888	226,381,466	45,440,942	38,029,000
1951	2,016,000	560,000	334,000	1889	226,775,962	414,496	30,615,000
1852	2,464,000	448,000	542,000	1890	259,763,092	32,987,130	40,523,000
1853	4,480,000	2,016,000	985,000	1891	284,121,764	24,358,672	36,368,000
1854	5,040,000	560,000	1,108,000	1892	344,998,679	60,876,915	40,020,000
1855	6,720,000	1,680,000	1,814,000	1893	329,354,398	a 15,644,281	35,570,000
1856	8,960,000	2,240,000	2,419,000	1894	354,188,374	24,833,976	33,648,000
1857	10,752,000	1,792,000	2,688,000	1895	380,613,404	26,425,030	40,726,000
1858	12,320,000	1,568,000	2,833,000	1896	460,061,430	79,448,026	49,687,000
1859	14,112,000	1,792,000	3,104,000	1897	494,078,274	34,016,844	59,289,000
1860	16,128,000	2,016,000	3,709,000	1898	526,512,987	32,434,713	65,288,000
1861	16,800,000	672,000	3,696,000	1899	568,666,921	42,153,934	97,242,000
1862	21,160,000	4,360,000	4,655,000	1900	606,117,166	37,450,245	100,615,000
1863	19,040,000	a 2,120,000	6,473,000	1901	602,072,519	a 4,044,647	100,546,000
1864	17,920,000	a 1,120,000	8,422,000	1902	659,508,644	57,436,125	80,460,000
1865	19,040,000	1,120,000	7,473,000	1903	698,044,517	38,535,873	95,632,000
1866	19,936,000	896,000	6,828,000	1904	812,537,267	114,492,750	104,005,000
1867	22,400,000	2,464,000	5,682,000	1905	888,784,267	76,247,000	138,650,000
1868	25,984,000	3,584,000	5,976,000	1906	917,805,682	29,021,415	177,136,000
1869	28,000,000	2,016,000	6,790,000	1907	868,996,491	a 48,809,191	173,799,000
1870	28,224,000	224,000	5,977,000	1908	942,570,721	73,574,230	124,419,000
1871	29,120,000	896,000	7,023,000	1909	1,092,951,924	150,380,903	142,084,000
1872	28,000,000	a 1,120,000	9,956,000	1910	1,080,159,502	a 12,792,115	137,180,000
1873	34,720,000	6,720,000	9,721,000	1911	1,097,232,749	17,073,240	137,154,000
1874	39,200,000	4,480,000	8,624,000	1912	1,243,268,720	146,035,971	205,139,000
1875	40,320,000	1,120,000	9,152,000	1913	1,224,484,098	a 18,784,622	189,795,000
1876	42,560,000	2,240,000	8,937,000	1914	1,150,137,192	a 74,346,905	132,938,000
1877	47,040,000	4,480,000	8,937,000	1915	1,388,009,527	237,872,335	242,902,000
1878	48,160,000	1,120,000	7,994,000	1916	1,927,850,518	539,841,021	474,288,000
1879	51,520,000	3,360,000	9,582,000	1917	1,886,120,721	a 41,729,827	514,911,000
1880	60,480,000	8,960,000	12,943,000				
1881	71,680,000	11,200,000	13,046,000		25,198,055,508		4,162,913,000
1882	90,646,232	18,966,232	17,313,000				

a Decrease.

The figures in this table, except those for 1917, are taken from the volumes of Mineral Resources of the United States. Statistics for 1882 to 1917, inclusive, are based on the returns to the United States Geological Survey by the copper-producing companies. Figures for the years prior to 1882 were compiled by the Survey from the best sources available. Reliable figures for years previous to 1845 are not obtainable. The year 1845, however, marks the entrance of the Lake Superior district into the ranks of producers and is really the beginning of important production of copper in this country. The industry has shown a steady and, since 1880, when Arizona and Montana became large producers, a very rapid growth.

Only eight times since 1880 has the annual production shown a decrease from that of the preceding year, and every time the decrease has been slight and, except that of 1913, has been more than recovered in the following year. The years showing a decrease are 1886, 1893, 1901, 1907, 1910, 1913, 1914, and 1917. In several other years the increase has been slight. In most years in which there has been a decrease it may be attributed to a general condition of financial and business depression which has resulted in a decrease in the demand for copper and other materials necessary to the expansion

Digitized by Google

of industries. In three years a slight decrease appears to have been due to the fact that the producing capacity of the country had been increased out of proportion to the demand for domestic consumption and export, and a temporary curtailment in production became necessary to permit the absorption of accumulated stocks. This, coupled with attempts at artificial control of prices, appears to have been the case in 1886 and also in 1901, and the decrease in production in 1910 may be attributed to a similar cause. The large increase in 1912 was due to the output from the mines that reached the producing stage during 1912 or had previously made but relatively small production.

The total decrease in 1913 was really less than that of Michigan alone in that year, which was due to labor troubles. The decrease in 1914 can be attributed entirely to the European war, and the increase in 1915 and 1916, which in 1916 was greater than the total production of any year before 1899, is to be accounted for in the same manner. The slight decrease in 1917 was due to labor troubles in several of the western districts.

The figures of smelter production in 1917 are based on returns made confidentially to the United States Geological Survey by all known smelting companies handling copper-bearing materials from the United States. To all companies and officials who have aided in furnishing this information and have given valuable time to answering inquiries concerning distribution of the output sincere thanks are extended. The following list gives the name of the owning or operating company, the location, and the final copper product of each smelting and refining plant treating material from the United States during 1917. It does not include lead and zinc plants that recovered copper as a by-product from mixed ores. Lists of lead and zinc smelters may be found in the reports on those metals.

Copper reduction plants that treated materials from the United States in 1917.

Location.	Company.	Final copper product.
Arizona:		
Ajo	New Cornelia Copper Co	Electrolytic.
Clifton	Arizona Copper Co	Blister.
Do	Shannon Copper Co	Do.
Douglas	Calumet & Arizona Mining Co	Do.
Do	Phelps Dodge Corporation	Do.
Globe	Old Dominion Copper Mining & Smelting Co	Do.
Hayden	American Smelting & Refining Co	Do.
Humboldt	Consolidated Arizona Smelting Co	Do.
Clarkdale	United Verde Copper Co	Do.
Mayer	Great Western Smelters Corporation	Matte.
Miami	International Smelting & Refining Co	Blister.
Morenci	Phelps Dodge Corporation	Do.
Sasco	American Smelting & Refining Co	Do.
California:		
Campo Seco	Penn Mining Co	Do.
Kennett	Mammoth Copper Mining Co	Do.
Martinez	Mountain Copper Co	Do.
Colorado:		
Salida	Ohio & Colorado Smelting & Refining Co	Do.
Maryland:		
Baltimore	Baltimore Copper Smelting & Rolling Co	Electrolytic.
Michigan:		
Hancock	Lake Superior Smelting Co	Anodes and Lake.
Do	Quincy Mining Co	Do.
Houghton	Michigan Smelting Co	Do.
Hubbell	Calumet & Hecla Mining Co	Do.
Montana:		
Anaconda	Anaconda Copper Mining Co	Blister.
Butte	East Butte Copper Mining Co	Do.
Great Falls	Anaconda Copper Mining Co	Blister and electrolytic.

Digitized by Google

Copper reduction plants, etc.—Continued.

Location.	Company.	Final copper product.
Nebraska:		
Omaha	American Smelting & Refining Co	Blister.
Nevada:		
McGill	Nevada Consolidated Copper Co	Do.
Thompson	Mason Valley Mines Co	Do.
New Jersey:[a]		
Chrome	United States Metals Refining Co	Electrolytic and casting.
Maurer	American Smelting & Refining Co	Electrolytic.
Newark	Balbach Smelting & Refining Co	Electrolytic and casting.
Perth Amboy	Raritan Copper Works	Electrolytic.
New Mexico:		
San Pedro	Santa Fe Gold & Copper Mining Co	Matte.
New York:		
Laurel Hill	Nichols Copper Co	Electrolytic and casting.
Tennessee:		
Copperhill	Tennessee Copper Co	Blister.
Isabella	Ducktown Sulphur, Copper & Iron Co. (Ltd.)	Matte.
Texas:		
El Paso	American Smelting & Refining Co	Blister.
Utah:		
Garfield	Garfield Smelting Co	Do.
International	International Smelting & Refining Co	Do.
Virginia:		
West Norfolk	Norfolk Smelting Co	Do.
Washington:		
Tacoma	Tacoma Smelting Co	Blister and electrolytic.
British Columbia:		
Anyox	Granby Consolidated Mining, Smelting & Power Co.	Blister.
Grand Forks	do	Do.
Do	do	Do.
Greenwood	British Columbia Copper Co, (Ltd.)	Do.
Trail	Consolidated Mining & Smelting Co. of Canada	Matte.

[a] This list does not include a smelter in New Jersey and one in Pennsylvania, both of which make blister from material solely of foreign origin.

During the year 46 copper smelting and refining plants treated material from the United States; of these, 41 were domestic plants and 5 were foreign.

The figures of production represent the actual smelter recovery. For Michigan it is the sum of furnace-refined copper and copper cast into anodes for electrolytic refining. As to blister copper, the figures represent the fine copper content. Some casting and electrolytic copper is produced direct from ore or matte, and this is included in the smelter production.

MINE RETURNS.

The figures of mine production are based on reports furnished to the United States Geological Survey by all mines producing copper in 1917. These mines reported 1,895,434,349 pounds of copper, or 9,300,000 pounds more than the smelters. The mines and smelters of several of the large copper producers are under the same management and their production is reported on the same basis. In the case of mines that ship to custom smelters or have only matting furnaces and ship their matte for conversion there is likely to be considerable discrepancy, as the mines may report a considerable quantity that has not reached the stage of blister by the close of the year and is consequently not included in the smelter production, or material that was reported by the mines in one year may be treated by the smelters the following year. This discrepancy is more pronounced if a marked curtailment of production occurs at the beginning or end of the year, so that there is not the balance of over-

Digitized by Google

lap that occurs if the industry is in normal condition throughout the year. Considerable copper is recovered by the smelters from ores that are treated primarily for other metals, the copper content being so low that it is not paid for and consequently is not always reported by the mines.

Copper produced in the United States in 1916 and 1917, according to smelter and mine returns, in pounds.

State.	1917				1916	
	Rank (smelter).	Percentage of total (smelter).	Smelter returns.	Mine returns.	Smelter returns.	Mine returns.
Alaska	7	4.49	84,759,086	88,793,400	113,823,064	119,854,839
Arizona	1	38.12	719,035,514	712,166,891	694,847,307	721,833,169
California	8	2.38	44,933,846	48,153,139	43,400,876	55,897,118
Colorado	10	.53	10,054,951	8,122,004	9,536,193	8,624,081
Georgia	16	.05	930,691	930,691	803,699	803,699
Idaho	11	.34	6,446,224	7,827,574	7,248,794	8,478,281
Maine	22	.....	34,872	30,406	.....	.....
Michigan	3	14.24	268,508,091	255,710,128	269,794,531	273,692,525
Missouri	18	.02	407,141	365,013	377,575	386,200
Montana	2	14.65	276,225,977	274,462,574	352,139,768	352,928,373
Nevada	5	6.10	115,028,161	122,794,704	100,816,724	105,116,813
New Jersey	.....	.....	.....	.....	4,115	.....
New Mexico	6	5.70	107,593,615	105,568,000	79,863,439	92,747,289
North Carolina	20	.....	125,004	124,991	5,961	9,800
Oregon	15	.06	1,105,097	2,474,487	2,433,567	3,581,886
Pennsylvania, Maryland, and Virginia	17	.03	553,413	787,331	1,194,012	1,337,580
South Carolina	19	.01	210,000	.....	.....	.....
South Dakota	.....	.....	.....	10,707	.....	.....
Tennessee	9	.85	16,093,757	16,033,749	14,556,278	14,679,794
Texas	12	.11	2,061,129	23,132	86,463	99,569
Utah	4	12.08	227,840,447	246,674,153	232,335,950	240,275,222
Vermont	21	.....	102,522	153,900	324,400	273,430
Washington	13	.11	2,051,416	2,199,518	2,473,481	2,645,022
Wyoming	14	.11	2,019,767	2,027,857	1,784,351	2,610,622
	.....	.....	1,886,120,721	1,895,434,349	1,927,850,548	2,005,875,312

Copper produced from domestic ores as reported by mines, smelters, and refineries, 1906–1917, in pounds.

Year.	Mine.	Smelter.	Refinery.
1906	916,971,387	917,805,382	897,382,387
1907	847,151,015	868,990,491	826,622,390
1908	956,840,578	942,570,721	919,111,414
1909	1,126,521,126	1,092,951,624	1,065,564,921
1910	1,088,237,432	1,080,159,509	1,071,894,876
1911	1,114,764,197	1,097,232,749	1,101,270,803
1912	1,249,094,891	1,243,268,720	1,203,676,895
1913	1,235,569,227	1,224,484,098	1,236,823,913
1914	1,148,431,437	1,150,137,192	1,210,423,189
1915	1,488,071,528	1,388,009,527	1,387,705,523
1916	2,005,875,312	1,927,850,548	1,888,752,199
1917	1,895,434,349	1,886,120,721	1,873,546,171

The difference between the smelter and the refinery production is accounted for entirely by an increase in the stocks of blister copper plus the copper content of bluestone produced and the loss in refining.

It appears that although theoretically the output reported by the mines should be considerably in excess of that reported by the smelters, this difference in the last 11 years has been nearly balanced by copper recovered from lead, zinc, gold, silver, and sulphur ores, which carry so little copper that it is not paid for, and consequently has not usually been reported by the mines.

Digitized by Google

PRODUCTION BY STATES.

Twenty-four States and Territories contributed to the production of copper in 1917. The table on page 738 shows the mine and the smelter output of individual States for 1916 and 1917.

According to smelter returns, the four leading States—Arizona, Montana, Michigan, and Utah—produced 79 per cent of the total output in 1917, as compared with 80 per cent in 1916; and the eight leading States, including Nevada, New Mexico, Alaska, and California produced 97.76 per cent of the total output in 1917.

In the distribution of the blister output of the States of origin it is necessary to have reports not only from blister producers, but also from matte smelters, as the matte is credited by the smelter that converts it to the State from which it was received, although the matte smelter may have received its ores from several States. In the adjustment of the products of these matte smelters slight errors in the distribution of the blister production are probably introduced. Likewise, the distribution of copper derived from zinc residues is subject to some error.

The following table shows the production from 1908 to 1917. The report for 1915 contains a table showing the production of copper by the different States from 1845.

Copper produced (smelter output) in the United States, 1908–1917, in pounds.

State.	1908	1909	1910	1911	1912
Alaska	4,438,336	4,057,142	4,311,026	22,314,989	31,926,209
Arizona	289,523,367	291,110,298	297,250,538	303,202,532	359,322,096
California	39,643,335	53,568,708	45,760,200	35,835,651	31,516,471
Colorado	13,943,878	11,485,431	9,307,497	9,791,361	7,963,520
Idaho	7,256,086	7,096,132	6,877,515	4,514,116	7,182,185
Michigan	222,289,584	227,005,923	221,462,984	218,185,236	231,112,228
Montana	252,509,122	314,900,279	283,078,516	271,816,098	308,794,483
Nevada	12,241,372	53,849,231	64,494,640	65,561,015	83,413,900
New Mexico	4,991,351	5,031,136	3,784,609	2,860,400	29,170,400
Oregon	271,191	245,403	22,022	125,943	311,860
Utah	71,370,370	101,241,114	125,185,455	142,340,215	132,150,052
Washington	162,201	120,611	65,021	195,503	1,069,938
Wyoming	2,416,197	433,672	217,127	130,499	25,080
Other States and unapportioned	21,513,431	22,806,294	18,342,359	20,358,791	19,310,298
	942,570,721	1,092,951,624	1,080,159,509	1,097,232,749	1,243,268,720

State.	1913	1914	1915	1916	1917
Alaska	23,423,070	24,985,847	70,695,286	113,825,064	84,759,086
Arizona	404,278,809	382,449,922	432,467,690	694,847,307	719,035,514
California	32,492,265	29,784,173	37,658,444	43,400,876	44,933,846
Colorado	9,052,104	7,316,066	7,272,178	9,536,193	10,054,951
Idaho	8,711,490	5,875,205	6,217,728	7,248,794	6,446,224
Michigan	155,715,286	158,009,748	238,956,410	269,794,531	268,508,091
Montana	285,724,467	236,805,845	268,263,040	352,139,768	276,225,977
Nevada	85,209,536	60,122,904	67,757,322	100,816,724	115,028,161
New Mexico	50,196,881	64,204,703	62,817,234	70,863,439	107,593,615
Oregon	77,812	5,599	797,471	2,433,567	1,105,097
Utah	148,057,450	160,589,660	175,177,695	232,335,950	227,840,447
Washington	732,742	683,602	903,661	2,473,481	2,051,416
Wyoming	362,235	17,082	351,871	1,784,351	2,019,767
Other States and unapportioned	20,449,951	19,288,836	18,673,497	17,352,503	20,518,529
	1,224,484,098	1,150,137,192	1,388,009,527	1,927,850,548	1,886,120,721

Digitized by Google

Copper produced in the United States, 1845–1917.

State.	Quantity (pounds).	Percentage.	Rank.
Alaska	408,738,006	1.62	9
Arizona	6,486,734,449	25.74	2
California	700,756,683	2.78	6
Colorado	267,245,844	1.06	10
Idaho	100,753,426	.40	11
Michigan	6,298,285,858	24.99	3
Montana	7,331,462,884	29.10	1
Nevada	715,848,659	2.84	5
New Mexico	489,029,835	1.95	7
Oregon	7,307,133	.03	14
Utah	1,877,572,042	7.45	4
Washington	10,088,124	.04	13
Wyoming	30,534,285	.12	12
Other States and unapportioned	473,697,380	1.88	8
	25,198,055,508	100.00	.....

The figures in the first column of the preceding table show the copper output of each important copper-producing State, except those on the Atlantic coast, since the beginning of the industry. Some copper was produced in New Mexico in the early years of the last century, but the exact quantity is not known, though it was not large as measured by the present production of the metal. Prior to 1845 also a little copper was produced in Michigan and a considerable quantity in the Eastern States.

Under "Eastern States and unapportioned" is included some copper classed as "lead desilverizers" in the earlier reports of the Survey. This should properly be credited to some of the Western States. The output of the Central States, except Michigan, is also included under this head. Statistics for the individual Eastern States have not been compiled, but it may be stated that about 336,000,000 pounds has been derived from Tennessee. To the remainder Vermont and Virginia have made the largest contributions, and some copper has been produced by practically all the Appalachian States.

Montana, Arizona, and Michigan stand out as the three chief copper-producing States. Montana ranks first, with more than 29 per cent of the entire output of the country; Arizona ranks second, with more than 25 per cent; and Michigan ranks third, with nearly 25 per cent. The three leading States have produced 80 per cent of the total. Utah, ranking next in order, has produced about 7 per cent of the total output.

As will be noted by reference to the table showing the output for 1917, these three States still maintain their preeminence, having produced 81 per cent of the total output in 1908, 76 per cent in 1909, 74 per cent in 1910, 72 per cent in 1911 and 1912, 69 per cent in 1913, 68 per cent in 1914, 1915, and 1916, and 67 per cent in 1917.

Digitized by Google

Mine production of copper in the principal districts in 1917.

District or region.	State.	Mine output (pounds).	Percentage of total production.	Rank.
Butte	Montana	270,500,000	14.27	1
Lake Superior	Michigan	255,710,128	13.49	2
Bingham	Utah	225,400,000	11.89	3
Globe-Miami	Arizona	169,490,000	8.94	4
Bisbee (Warren)	do	167,600,000	8.84	5
Jerome	do	145,900,000	7.70	6
Ely (Robinson)	Nevada	93,620,000	4.94	7
Ray (Mineral Creek)	Arizona	92,000,000	4.85	8
Santa Rita (Central)	New Mexico	82,200,000	4.34	9
Copper River	Alaska	70,500,000	3.72	10
Morenci-Metcalf	Arizona	53,000,000	2.80	11
Shasta County	California	26,650,000	1.41	12
Ajo	Arizona	20,200,000	1.07	13
Yerington	Nevada	19,400,000	1.02	14
Ducktown	Tennessee	16,093,000	.85	15
Prince William Sound	Alaska	15,500,000	.82	16
Burro Mountain	New Mexico	14,574,000	.77	17
Pioneer	Arizona	10,600,000	.56	18
Tintic	Utah	9,045,000	.48	19
Foothills Belt	California	8,000,000	.42	20
Plumas County	do	7,400,000	.39	21
Silver Bell	Arizona	7,200,000	.38	22
Big Bug	do	6,770,000	.36	23
Banner	do	5,880,000	.31	24
Pima	do	4,440,000	.23	25
Alder Creek	Idaho	4,380,000	.23	26
Lordsburg	New Mexico	4,261,000	.23	27
Cochise	Arizona	4,180,000	.22	28
Courtland (Turquois)	do	3,526,000	.19	29
Patagonia	do	3,050,000	.16	30
Planet	do	2,975,000	.16	31
Coeur d'Alene region	Idaho	2,875,000	.15	32
San Juan-Ouray region	Colorado	2,765,000	.15	33
Peck	Arizona	2,700,000	.15	34
Magdalena	New Mexico	2,690,000	.14	35
Helvetia	Arizona	2,600,000	.14	36
Ketchikan	Alaska	2,600,000	.14	37
Santa Fe	Nevada	2,590,000	.14	38
Aqua Fria	Arizona	2,580,000	.14	39
Ophir	Utah	2,230,000	.12	40
Leadville	Colorado	2,171,000	.11	41
San Francisco	Utah	2,130,000	.11	42
Clifton	do	1,890,000	.10	43
Platte Canyon	Wyoming	1,880,000	.10	44
Baker County	Oregon	1,386,000	.07	45
Copper Basin	Arizona	1,380,000	.07	46
Lucin	Utah	1,350,000	.07	47
Rocky	do	1,300,000	.07	48
Trinity	California	1,300,000	.07	49
Dos Cabezos	Arizona	1,260,000	.06	50
Chewelah	Washington	1,200,000	.06	51
Josephine County	Oregon	1,087,000	.06	52
Total		1,862,008,128		
All others		32,991,872	1.74	
Grand total		1,895,000,000		

Blister copper produced in the principal districts to the end of 1917.

District.	State.	Date production began.	Quantity (pounds).	Percentage of total production.	Rank.
Butte	Montana	1868	7,300,500,000	28.97	1
Lake Superior	Michigan	1845	6,285,487,364	24.94	2
Bisbee	Arizona	1880	2,387,156,000	9.47	3
Bingham	Utah	1896	1,598,519,000	6.34	4
Morenci-Metcalf	Arizona	1873	1,350,196,000	5.35	5
Globe-Miami	do	1881	1,072,690,000	4.26	6
Jerome	do	1883	1,001,340,000	3.97	7
Ely (Robinson)	Nevada	1908	627,744,000	2.49	8
Shasta County	California	1897	540,650,000	2.15	9
Santa Rita (Central)	New Mexico	1800	455,339,000	1.81	10
Ray (Mineral Creek)	Arizona	1911	388,678,000	1.54	11
Ducktown	Tennessee	1850	336,059,000	1.33	12
Foothills Belt	California	1862	143,860,000	.57	13
Tintic	Utah	1880	140,630,000	.56	14

Digitized by Google

Fourteen districts in eight States have each contributed in excess of 100,000,000 pounds to the copper output of the country. Five of these districts are in Arizona, two each in California and Utah, and one each in Montana, Michigan, Nevada, New Mexico, and Tennessee. Two districts stand out prominently. They are the Butte district, Mont., which has contributed nearly one-third of the output of the country, and the Lake Superior district, Mich., which has produced nearly 25 per cent of the total output. Bisbee, ranking third, has yielded 9.47 per cent of the total. The 14 districts have yielded 94 per cent of the total output of the United States since 1845.

It is noteworthy that not a single one of the leading copper districts of the United States, several of which have been active producers for a period of 30 years or more, has been worked out or has shown a decrease in its ability to produce copper.

QUANTITY AND YIELD OF COPPER ORES.

COPPER-BEARING ORES PRODUCED.

The following tables show the quantity and the yield in copper of the ore produced by the mines of the United States in 1917. The figures are taken from the mines reports that form a part of the annual volume Mineral Resources. The close agreement between the output as reported by the mines and the actual recovery of metal as reported by the smelters indicates that the tenor of the ores as reported by the mines is very close to the actual recovery. The classification of some of the complex western ores is difficult and more or less arbitrary. Under copper ores are classed those which contain 2.5 per cent or more of copper, as well as those which contain less than this percentage, provided their principal value is in copper. Under copper-lead and copper-zinc ores are classed complex ores in which copper is a valuable constituent. Considerable copper was reported by the mines from ores mined primarily for other metals, including siliceous gold and silver ores, lead ores, zinc ores, pyritic sulphur ores, and ores concentrated for values in other metals. No attempt has been made to compile tables showing the quantity and yield of this group of copper-bearing ores, but together with old slags and other material they have yielded a total of 27,623,002 pounds of copper.

Copper produced in the United States in 1917 from ores in which copper constitutes the principal value.

State.	Copper ore.	Copper in ore.		Gold in ore.	Silver in ore.	Value in gold and silver per ton.
		Quantity.	Percentage.			
	Short tons.	*Pounds.*		*Fine ounces.*	*Fine ounces.*	
Alaska	659,957	88,793,400	6.73	12,830.16	1,040,185	$1.70
Arizona	15,245,297	708,387,623	2.32	98,530.97	5,214,411	.41
California	892,579	48,153,139	2.70	32,408.98	882,480	1.57
Colorado	83,233	3,133,437	4.71	7,455.00	182,791	9.17
Georgia	39,290	930,691	1.18			
Idaho	103,224	6,225,486	3.02	3,960.99	232,840	2.65
Maine	1,942	30,406	.78			
Michigan	12,400,723	255,719,128	.99		688,551	.18
Missouri					20	
Montana	4,844,537	271,331,853	2.80	27,561.56	8,911,389	1.63
Nevada	4,945,482	122,422,830	1.24	49,419.80	327,751	.26
New Mexico	4,188,027	101,280,755	1.21	10,876.11	315,877	.11
North Carolina	832	124,991	7.51	168.86	922	5.11

Digitized by Google

Copper produced in the United States in 1917, etc.—Continued.

State.	Copper ore.	Copper in ore.		Gold in ore.	Silver in ore.	Value in gold and silver per ton.
		Quantity.	Percentage.			
	Short tons.	*Pounds.*		*Fine ounces.*	*Fine ounces.*	
Oregon	43,041	2,474,487	2.87	2,424.99	31,375	$1.76
Pennsylvania, Maryland, and Virginia	286,332	787,331	.14	3.19	1,092	.....
South Dakota	82	9,971	6.08	.85	130	1.52
Tennessee	589,004	16,033,749	1.37	257.65	99,053	.15
Texas	298	20,158	3.38	.06	1,621	4.48
Utah	14,121,671	235,899,850	.84	94,844.85	2,225,119	.27
Vermont	5,851	153,900	1.32	3.43	497	.....
Washington	75,006	2,147,102	1.43	281.93	154,747	1.78
Wyoming	6,286	2,027,857	16.13	88.04	3,382	.73
Total and average	58,482,694	1,866,079,144	1.60	341,117.42	20,314,233	.49

Copper ores concentrated and smelted and copper produced from each class of ore in the United States in 1917.

State.	Ore concentrated.				Ore smelted.		
	Quantity.	Concentrates produced.	Copper in concentrates.	Percentage of copper from ore.	Quantity.	Copper produced.	Percentage of copper from ore.
	Short tons.	*Short tons.*	*Pounds.*		*Short tons.*	*Pounds.*	
Alaska	456,253	59,559	41,286,800	4.52	203,704	47,506,600	11.67
Arizona	10,835,510	745,123	282,020,820	1.30	[a] 4,409,787	[a] 426,366,803	4.83
California	422,169	52,099	13,464,000	1.59	470,410	34,689,139	3.69
Colorado	.....	.....	.....	.....	33,233	3,133,437	4.71
Georgia	.....	.....	.....	.....	39,290	930,691	1.18
Idaho	24,695	1,361	525,902	1.06	78,529	5,699,584	3.63
Maine	1,942	240	30,406	.78	.....	.....	.....
Michigan	12,400,723	205,131	255,710,128	.99	.....	.....	.....
Missouri	.....	.....	.....	.....	.....	.....	.....
Montana	4,464,407	1,492,104	228,094,359	2.55	380,130	43,237,494	5.69
Nevada	4,475,976	600,357	87,194,581	1.06	469,506	35,228,249	3.75
New Mexico	4,083,518	316,194	92,939,853	1.26	104,509	8,340,902	3.99
North Carolina	.....	.....	.....	.....	832	124,991	7.51
Oregon	36,676	7,522	1,372,000	1.87	6,365	1,102,487	8.66
Pennsylvania, Maryland, and Virginia	273,982	7,508	751,021	.14	12,350	36,311	.15
South Dakota	.....	.....	.....	.....	82	9,971	6.08
Tennessee	.....	.....	.....	.....	589,004	16,033,749	1.36
Texas	.....	.....	.....	.....	298	20,158	3.38
Utah	13,504,515	655,259	207,616,977	.77	617,156	28,282,873	2.29
Vermont	5,540	651	125,770	1.14	311	28,130	4.52
Washington	58,720	4,668	964,750	.82	16,286	1,182,352	3.63
Wyoming	.....	.....	.....	.....	6,286	2,027,857	16.13
Total and average	51,044,626	4,148,276	1,212,097,367	1.19	7,438,068	653,981,778	4.39

[a] Includes ore leached.

Copper produced from copper-lead and copper-zinc ores in the United States in 1917.

State.	Copper-lead and copper-zinc ores.	Copper in ore.	Percentage of copper.
	Short tons.	*Pounds.*	
Arizona	12,987	341,481	1.3
Colorado	2,976	204,563	3.4
Idaho	1	320	16.0
Montana	4,356	182,275	2.1
Nevada	1,158	127,459	5.5
New Mexico	3,684	482,372	6.6
Texas	27	2,974	5.5
Utah	6,443	393,079	3.1
Total and average	31,632	1,734,523	2.7

Digitized by Google

Copper derived from ore classed as copper bearing (copper, copper-lead, and copper-zinc ores), and total production of copper from all sources in the United States in 1917.

State.	Ore treated.	Copper recovered.	Percentage of copper.	Copper from all sources including old slags, smelter cleanings and precipitates.
	Short tons.	*Pounds.*		*Pounds.*
Alaska	659,957	88,793,400	6.73	88,793,400
Arizona [a]	15,258,284	708,729,104	2.32	712,166,891
California	892,579	48,153,139	2.70	48,153,139
Colorado [b]	36,209	3,338,000	4.61	8,122,004
Georgia	39,290	930,691	1.18	930,691
Idaho	103,224	6,225,486	3.02	7,827,574
Maine	1,942	30,406	.78	30,406
Michigan	12,400,723	255,710,128	.99	255,710,128
Missouri				[c] 365,013
Montana [d]	4,848,893	271,512,128	2.80	274,462,574
Nevada	4,946,640	122,550,289	1.24	122,794,704
New Mexico [e]	4,191,711	101,763,127	1.21	105,568,000
North Carolina	832	124,991	7.51	124,991
Oregon	43,041	2,474,487	2.87	2,474,487
Pennsylvania, Maryland, and Virginia	286,332	787,331	.14	787,331
South Dakota	82	9,971	6.08	10,707
Tennessee	589,004	16,033,749	1.37	16,033,749
Texas	325	23,132	3.57	23,132
Utah	14,128,114	236,292,929	.84	246,674,153
Vermont	5,851	153,900	1.32	153,900
Washington	75,006	2,147,102	1.43	2,199,518
Wyoming	6,286	2,027,857	16.13	2,027,857
Total and average	58,514,325	1,867,811,347	1.60	1,895,434,349

[a] Considerable copper was recovered from old slags and ores not classed as copper ores.
[b] Most of the copper from Colorado is derived from ores classed as siliceous ores and lead ores.
[c] Mainly recovered in dressing lead ores.
[d] Considerable copper was recovered as precipitates from mine waters and from ores not classed as copper ores.
[e] A large quantity of copper was derived from ores classed as lead ores, lead-zinc ores, and siliceous ores.

Copper ores produced in the United States, 1906–1917, and average yield in copper, gold, and silver.

Year.	Copper ores.	Yield in copper.	Yield per ton in gold.	Yield per ton in silver.	Value per ton in gold and silver.
	Short tons.	*Per cent.*	*Ounces.*	*Ounces.*	
1906	18,000,000	2.50	0.0150	0.882	$0.856
1907	20,253,000	2.11	.0135	.609	.622
1908	[a] 22,290,886	2.07	.0104	.666	.560
1909	27,932,618	1.98	.0097	.655	.540
1910	28,497,238	1.88	.0093	.562	.495
1911	29,988,235	1.82	.0089	.555	.492
1912	35,656,414	1.71	.0073	.517	.468
1913	36,336,682	1.67	.0057	.502	.420
1914	[b] 35,175,541	1.60	.0075	.422	.39
1915	43,404,182	1.66	.0078	.428	.38
1916	57,863,365	1.70	.0069	.424	.42
1917	58,482,694	1.60	.0058	.347	.49

[a] Includes 143,675 tons of slag smelted.
[b] Includes 99,816 tons of slag smelted and ore leached.

Digitized by Google

Copper ores produced in the United States, 1906–1917, classified as smelting and concentrating ores, and average yield in copper.

Year.	Smelting ores.		Concentrating ores.	
	Quantity.	Yield in copper.	Quantity.	Yield in copper.
	Short tons.	*Per cent.*	*Short tons.*	*Per cent.*
1906	3,278,000	.....	14,722,000	.....
1907	3,957,500	4.05	16,295,500	1.41
1908	4,386,689	4.27	17,760,522	1.485
1909	5,267,707	4.15	22,664,911	1.47
1910	5,001,394	4.14	23,495,844	1.40
1911	4,355,650	4.66	25,632,585	1.34
1912	5,014,018	4.45	30,642,396	1.26
1913	5,290,310	4.22	31,046,372	1.22
1914	4,597,398	4.23	30,478,327	1.20
1915	5,433,907	4.60	37,970,275	1.26
1916	6,928,010	4.72	50,935,355	1.28
1917	7,438,068	4.39	51,044,626	1.19

The output of copper-bearing ores in 1917 showed a slight increase over that of any preceding year. For the last 12 years there has been a steady increase in the production of these ores except in 1914, when there was a slight decrease. Arizona is the largest producer of copper ore, followed in order by Utah, Michigan, Nevada, Montana, New Mexico, California, Alaska, and Tennessee. In the output of smelting ore Arizona is first, followed by Utah, Tennessee, California, Nevada, Montana, Alaska, and New Mexico. In the output of concentrating ore Utah is first, followed by Michigan, Arizona, Nevada, Montana, New Mexico, and Alaska.

YIELD OF COPPER FROM ORES.

The average yield of copper from copper ore in 1917 was 1.60 per cent. There was a steady decrease in the average yield of copper ores from about 2.50 per cent in 1906 to 1.60 per cent in 1914, but the yield in 1915 and 1916 each show an increase, but was less again in 1917. The decrease from 1906 to 1914 may be taken as a general measure of the improvement in metallurgic practice that has made possible the treatment of lower-grade material. The increase in 1915 and 1916 is doubtless due mainly to the increase in the recovery of copper resulting from the introduction of improved methods, notably the flotation process.

Since 1906 the average yield from direct smelting ores has increased from 4.05 per cent to 4.39 per cent; that from concentrating ores has decreased from 1.48 per cent in 1908 to 1.20 per cent in 1914, since which year it has increased to 1.28 per cent in 1916, owing to improved metallurgical processes, but decreased to 1.19 per cent in 1917.

Of the important copper-producing States, Alaska produced the highest grade of copper ore in 1917, followed in order by Montana, California, Arizona, Tennessee, Nevada, New Mexico, Michigan, and Utah. Of the States producing smelting ore in large quantity, Alaska had the highest yield, followed by Montana, Arizona, Nevada, California, New Mexico, Utah, and Tennessee. Of the States producing concentrating ores in large quantity, Alaska had the highest grade, followed by Montana, California, Arizona, New Mexico, Michigan, Nevada, and Utah.

Digitized by Google

The average recovery of gold and silver from copper ores shows a variation about in proportion to that of copper. In 1906 copper ores averaged 85.6 cents per ton in gold and silver; in 1917 the average yield was 49 cents per ton. Among the principal copper-producing States, Alaska was first in the average yield of gold and silver per ton of ore, followed by Montana, California, Arizona, Utah, Nevada, Michigan, Tennessee, and New Mexico.

REVIEW BY STATES.

SCOPE OF DISCUSSION.

In the following pages a brief statement of the conditions affecting production in the principal copper districts of the country is presented and the tenor of ore from each district is given so far as it does not disclose the production of those individual companies whose figures of output have not already been published in their annual reports or elsewhere. Those who desire more detailed information on the mining operations of the districts are referred to the reports on mine production in the several States, which form other chapters of Mineral Resources, as set forth in the prefatory note.

Figures of metal output, ore reserves, metal content, and recovery in treatment of individual companies given in this report, unless otherwise stated, are quoted from the official reports of the companies.

The report for 1915 contains a map showing the location of the copper-producing districts and the metallurgic plants and also a brief discussion of the geologic occurrence of the ores in the different districts. Copies of that report may be obtained on application to the Director of the United States Geological Survey.

ALASKA.

The production of blister copper from Alaska in 1917 was 84,759,086 pounds, as compared with 113,823,064 pounds in 1916. The mine production of copper in 1917 was 88,793,400 pounds.

Alaska began to produce copper in notable quantity about 1903, and since that time it has been a steady contributor. Its total production of blister copper to the end of 1917 is 408,738,906 pounds. The output in 1917 came from the Ketchikan, Prince William Sound, and Copper River districts.

Ketchikan district.—Copper mining in the Ketchikan district was active in 1917. The mines yielded 41,060 tons of ore, from which 2,646,553 pounds of copper were produced.

The It mine, at Kasaan Bay, was operated by the Granby Consolidated Mining Co. For the fiscal year ending June 30, 1917, 14,881 tons of ore was produced, having an average assay content of 4.09 per cent of copper and $1.68 per ton in gold and silver.

Reserves as of June 30, 1917, were reported as 7,500 tons averaging 3.3 per cent of copper and $1.36 per ton in gold and silver.

Prince William Sound district.—Copper mining in the Prince William Sound district in 1917 was active, and the output was one of the largest made by this district. The ores of the district were

Digitized by Google

shipped to the Tacoma and Anyox smelters. The largest producer was the Beatson Bonanza mine, but much ore was taken from the Ellamar mine. Other copper properties were being developed and made small outputs.

There was mined from the Beatson mine of the Kennecott Copper Corporation 273,523 tons of ore, averaging 2.44 per cent of copper. The ore milled during the year amounted to 253,805 tons, averaging 2.06 per cent copper. Concentrates amounted to 29,423 tons, averaging 14.20 per cent of copper. The average recovery was 80.28 per cent. Direct shipping ore amounting to 49,141 tons and averaging 11.48 per cent copper was produced.

The enlargement of the concentrating plant from 700 to 1,500 tons daily capacity was not completed during the year owing to inability to obtain delivery of equipment, but completion was expected early in 1918.

There was shipped from the Midas mine, operated by the Granby Consolidated Mining Co., for the fiscal year ending June 30, 1917, 21,019 tons of ore, averaging 4.12 per cent of copper and $1.55 in gold and silver per ton. Ore in sight at this mine, as of June 30, 1917, was 44,487 tons, averaging 4 per cent of copper and $1.53 in gold and silver per ton.

Copper River district.—The Bonanza and Jumbo mines of the Kennecott Copper Corporation were the largest producers in the Copper River district. The Mother Lode Copper Mines Co., of the Chitina district, also produced in 1917.

During the year there was mined from the Bonanza and Jumbo mines 265,579 tons of ore, averaging 13.78 per cent of copper; 206,253 tons of ore milled averaged 8.92 per cent of copper. Concentrates amounted to 29,559 tons, averaging 53.52 per cent. The average recovery was 85.98 per cent. The ammonia-leaching plant treated 98,075 tons of tailings, averaging 0.90 per cent of copper, with a recovery of 1,244,200 pounds of copper. The total average milling recovery for the year, including leaching-plant operations, was 89.4 per cent. Plans have been adopted for increasing the leaching plant from 300 tons daily capacity to 700 tons.

Smelting ore was shipped to the amount of 89,799 tons, averaging 38.57 per cent of copper.

The total recovery from the Copper River and Beatson output was 78,211,429 pounds of refined copper and 933,573 ounces silver.

Profit on metals delivered by the Kennecott Copper Corporation amounted to $11,826,212, and total profits, including dividends on stock held by the company, amounted to $17,964,902.

Dividends were paid to the amount of $16,731,147.

Developments were continued by the Mother Lode Copper Mines Co., and a small production was made. In a report dated August 1, 1917, Mr. W. B. Hancock, superintendent, gave the amount of ore developed as 113,930 tons, containing 17,523 tons of copper. A controlling interest in the Mother Lode Mines Co. was acquired by the Kennecott Copper Corporation in 1918, and the mine will probably be operated with the mines of that group and the necessity for the construction of a new mill obviated.

Digitized by Google

ARIZONA.

In 1917 Arizona produced 719,035,514 pounds of blister copper, compared with 694,847,307 pounds in 1916.

The steady output of copper from Arizona began about 1875, though there had been intermittent production since 1862. Since 1880 the growth of the industry has been steady and rapid, and to the end of 1917 Arizona had a recorded production of 6,486,734,449 pounds of copper, or 25.74 per cent of the total output of the country, thus ranking second among the States. In 1917 Arizona produced 38.12 per cent of the total output. The greater part of the production came from five districts. Thirteen copper-smelting plants were operated within the State during the year.

The production of copper for the year was greatly curtailed by labor troubles during the summer, which reduced the production of several of the camps to a greater or less extent for most of the last half of the year.

Bisbee district.—Most of the ore occurs as irregular replacement bodies in limestone without any definite arrangement, and the cost of prospecting is consequently rather high. The irregular character of the ore deposits and the heavy ground, especially in the oxidized ore bodies, have resulted in relatively high cost of extraction.

In recent years large bodies of disseminated ore have been developed in the altered granite porphyry of Sacramento Hill.

Copper produced in Bisbee district, Ariz., 1906–1917.

Year.	Quantity.	Average yield in copper.	Value in gold and silver per ton.	Year	Quantity.	Average yield in copper.	Value in gold and silver per ton.
	Pounds.	*Per cent.*			*Pounds.*	*Per cent.*	
1906	131,000,000	6+	.....	1912	140,000,000	5.6	$1.41
1907	110,000,000	6+	.....	1913	155,100,000	5.6	1.16
1908	129,000,000	6+	.....	1914	151,600,000	5.4	1.35
1909	130,000,000	6+	.....	1915	164,600,000	5.0	1.66
1910	142,500,000	5.4	$1.07	1916	193,600,000	4.9	1.51
1911	130,200,000	5.9	1.42	1917	167,600,000	5.0	1.56

The production of the Copper Queen branch of Phelps Dodge Corporation, as summarized in the company's report, is as follows:

Metals produced by Copper Queen branch of Phelps Dodge Corporation, 1917.

Production of mines.

	Ore, dry weight.	Gold.	Silver.	Copper.	Lead.
	Short tons.	*Ounces.*	*Ounces.*	*Pounds.*	*Pounds.*
Shipped to Douglas	773,952	18,401	600,203	92,183,526	.....
Shipped to El Paso	17,229	731	224,147	447,614	6,769,106
Shipped to experimental concentrator	2,942	.....	.....	.....	.....
Shipped to Chicago	2,379	.....	.....	.....	.....
Precipitates	816	.....	57	793,433	.....
Old dump slag	3,267	.....	205	152,121	.....
Concentrates shipped	385	24	4,053	41,715	101,022
	809,970	19,156	828,665	93,618,409	6,870,128

Digitized by Google

Metals produced by Copper Queen branch of Phelps Dodge Corporation—Continued.

Production of reduction works.

	Ore, dry weight.	Gold.	Silver.	Copper.
	Short tons.	*Ounces.*	*Ounces.*	*Pounds.*
Copper Queen branch	794,904	19,171	550,156	87,831,317
Burro Mountain branch	45,868	293	36,799	13,342,508
Moctezuma Copper Co.	167,381	1,910	508,387	38,499,781
All other	268,664	10,957	946,921	51,907,525
	1,276,817	32,331	2,042,263	191,581,131

Metals produced by Copper Queen Consolidated Mining Co., 1911–1917.

Year.	Ore.	Copper.	Silver.	Gold.	Lead.	Earnings.	Dividends.
	Short tons.	*Pounds.*	*Ounces.*	*Ounces.*	*Pounds.*		
1911	619,132	74,489,728	1,227,453	16,895	5,658,930	$4,155,010	$5,200,000
1912	786,368	88,280,908	1,027,130	18,023	2,953,685	6,977,378	5,707,351
1913	867,481	97,181,725	919,138	16,213	5,701,628	6,916,900	5,700,000
1914	732,829	86,066,143	1,036,672	15,769	8,889,175	6,042,001	4,500,000
1915	833,107	88,551,180	943,368	18,974	9,388,418	.....	.....
1916	951,978	102,685,722	1,096,136	24,030	9,421,562	.....	.....
1917	800,970	93,618,409	828,665	19,156	6,870,128	.....	.....

Work of removing the overburden to permit the mining of the disseminated deposits of Sacramento Hill by steam shovel was in process during the year. The plans for a 3,000-ton mill to treat the ores have been determined on.

Phelps Dodge Corporation reports that the known ore reserves in all the mines of the company were materially increased during the year.

The production of the Calumet & Arizona Mining Co. is shown in the following table:

Metals produced by Calumet & Arizona Mining Co., including the Superior & Pittsburg Co. before the consolidation of the two, 1911–1917.

Year.	Company.	Ore smelted.	Copper produced.	Copper recovered.	Gold.	Silver.	Dividends.
		Short tons.	*Pounds.*	*Per cent.*	*Ounces.*	*Ounces.*	
1911	Calumet & Arizona	231,135	21,476,739	4.457	9,329	216,987	$1,989,059
	Superior & Pittsburg	230,620	28,469,166	6.1859	8,785	236,960	1,739,758
1912	Calumet & Arizona	169,287	16,490,229	4.34	9,066	233,092	2,542,781
	Superior & Pittsburg	318,418	36,618,399	5.762	13,815	361,227	1,919,733
1913	Calumet & Arizona	111,541	52,621,651	4.485	15,890	540,214	3,059,208
	Superior & Pittsburg	376,568		5.785			
1914	Calumet & Arizona	540,468	49,992,909	4.62	19,744	573,606	1,851,008
1915	.....do.....	729,677	63,126,931	4.33	26,212	947,129	2,006,557
1916	.....do.....	845,286	70,702,028	4.17	31,673	1,267,734	5,777,296
1917	.....do.....	.....	59,131,512	.....	27,947	906,038	6,424,762

At the reduction works at Douglas 1,016,613 tons of ore were treated. The sulphuric-acid plant was completed and started in March and operated for the rest of the year. From October 1 the plant produced an average of 223 tons of 50° B. acid per day.

Net income for the year was $6,628,500. Regular dividends for the year amounted to $6,424,762, and Special No. 1 (distribution of capital) amounted to $642,479. Total dividends to the close of 1917 amounted to $35,992,761.

Digitized by Google

The following table shows the results of operations of the Shattuck Arizona Copper Co.:

Metals produced by Shattuck Arizona Copper Co., 1911–1917.

Year.	Copper.	Silver.	Gold.	Lead.	Copper recovered.	Dividends.
	Pounds.	*Ounces.*	*Ounces.*	*Pounds.*	*Per cent.*	
1911 [a]	4,111,000					
1912 [b]	1,253,305	21,008	13		7.13	
1912 [c]	1,746,493	15,165	16		6.67	
1913	13,219,756	236,000	2,033	1,483,956	6.67	$525,000
1914	10,846,918	198,419	2,445	14,065	5.79	525,000
1915	11,154,211	201,869	3,151	2,345,342	5.89	875,000
1916	18,161,763	314,918	4,721	3,413,445	5.38	1,662,500
1917	11,935,317	154,344	1,542	2,010,145	4.57	[d] 612,500

[a] Year ending August, 1911.
[b] Year ending August, 1912.
[c] Aug. 1 to Dec. 31, 1912, inclusive.
[d] Capital distribution to the amount of $1,137,500.

Mine and smelter production of Shattuck Arizona Copper Co., 1917.

	Copper ore.		Special ores.	
	Wet.	Dry.	Wet.	Dry.
Tons ore stoped	136,586	126,554	6,291	6,065
Tons ore developed	4,370	4,049	706	678
Tons ore from dumps, etc	45	42	62	61
Tons ore mined	141,001	130,645	7,059	6,804
Tons ore shipped	141,143	130,774	7,044	6,789
Tons ore smelted	140,936	130,583	8,312	7,992

Copper recovered	pounds	11,935,317
Gold recovered	ounces	1,542
Silver recovered	do	154,344
Lead recovered	pounds	2,010,145

Cost per pound of refined copper.

Gross operating cost	cents	15.638
Less operating credits	do	2.396
Net operating cost		13.242

Globe-Miami district.—Production of copper began in the Globe district in 1881; the camp was well known as a silver producer before that date. For several years the production was intermittent, but since 1888, and especially since 1898, when the railroad reached the camp, the district has ranked among the large copper producers of the country. To the end of 1917 it has produced 1,072,690,000 pounds of copper, or 4.26 per cent of the output of the country since 1845. In total production the district ranks sixth in the country and third in the State; for 1917 it ranked fourth in the country and first in the State. The Miami part of the district made its first notable output in 1911.

Copper produced in Globe-Miami district, Ariz., 1906–1917.

Year.	Copper.	Yield of ore in copper.	Year.	Copper.	Yield of ore in copper.
	Pounds.	*Per cent.*		*Pounds.*	*Per cent.*
1906	27,000,000	3.4	1912	61,600,000	2.21
1907	35,000,000	4	1913	71,000,000	2.38
1908	36,000,000	4.5	1914	72,000,000	2.41
1909	33,000,000	4.43	1915	98,500,000	2
1910	27,600,000	5	1916	220,000,000	1.43
1911	44,600,000	3.35	1917	169,490,000	1.42

Digitized by Google

Ore produced by Old Dominion Co., 1917.

	Quantity (short tons).	Percentage of copper.
Smelting ore	81,728	6.92
Concentrating ore	114,217	3.62
Silica ore	3,904	3.29
Iron ore	39	2.21
	199,888	4.97

Metals produced by Old Dominion Co., 1911–1917.

Year.	Ore.	Copper.	Gold.	Silver.	Average yield in copper.	Cost per pound of copper.	Dividends.
	Short tons.	*Pounds.*	*Ounces.*	*Ounces.*	*Per cent.*	*Cents.*	
1911	174,246	19,195,181	936	42,050	5.84	9.5	$486,000
1912	201,181	16,533,993	583	42,750	4.67	10.34	729,000
1913	169,961	18,945,153	419	51,316	5.88	9.7	810,000
1914	129,813	17,816,284	603	33,311	7.44	8.22	445,500
1915	115,459	13,771,681	620	40,632	6.56	8.90	1,053,000
1916	152,059	17,654,643	1,240	60,688	5.88	11.69	1,944,000
1917[a]	199,888	32,365,795	3,897	165,703	4.97	.....	2,376,262

[a] Includes custom ores.

During the year the Old Dominion Copper Mining & Smelting Co. and the United Globe mines were combined as the Old Dominion Co.

Metals produced by United Globe mines, 1911–1916.

Year.	Ore.	Copper.	Silver.	Gold.	Yield in copper.	Dividends.
	Short tons.	*Pounds.*	*Ounces.*	*Ounces.*	*Per cent.*	
1911	110,578	8,525,433	111,459	876	3.85	.....
1912	188,254	12,252,073	124,362	789	3.25	$460,000
1913	167,919	11,348,100	119,588	1,537	3.38	690,000
1914	155,205	11,086,674	91,582	1,580	3.57	425,500
1915	141,240	11,536,021	105,109	1,508	4.08	621,000
1916	206,163	14,852,399	128,066	1,543	3.60	1,679,000

Dividends paid by the Old Dominion Co. to December 31, 1917, amounted to $13,216,976.

Total dividends paid by the United Globe mines to the end of 1916 amounted to $4,255,000.

The smelters of the Old Dominion Co. at Globe and of the International Smelting & Refining Co. at Miami were operated throughout the year.

The district is served by the Arizona Eastern Railroad.

The Arizona Commercial Mining Co. produced 39,702 tons of ore, averaging 6.153 per cent of copper. The metal output was 3,860,949 pounds of copper, 5,208 ounces of silver, and 374 ounces of gold. The net earnings for the year were $464,750. A dividend of $424,000 was paid during the year.

Digitized by Google

The following tables show the operations of the Miami Copper Co.:

Copper produced by Miami Copper Co., 1911–1917.

Year.	Ore.	Copper content.	Mill extraction.	Refined copper.	Cost of copper per pound.	Dividends.
	Short tons.	*Per cent.*	*Per cent.*	*Pounds.*	*Cents.*	
1911	445,036	2.48	73.37	15,385,783	9.103	.....
1912	1,040,744	2.393	69.39	32,832,609	9.5884	$1,100,112
1913	1,058,784	2.30	71.06	32,867,666	10.6086	1,491,989
1914	1,096,633	2.28	69.93	33,296,010	9.2045	1,120,375
1915	1,348,122	2.17	75.17	41,832,059	8.76	1,681,004
1916	1,842,017	2.07	73.88	53,518,331	9.52	4,295,935
1917	1,640,206	2.03	69.25	43,863,699	12.51	6,537,247

Milling operations of Miami Copper Co., 1917.

Ore milled	short tons	1,640,206
Copper in ore	per cent	2.032
Concentrates produced	short tons	53,639
Copper in concentrates	per cent	43.040
Copper in concentrates	pounds	46,172,322
Copper recovered per ton of ore	do	28.15
Mill extraction	per cent	69.25

Cost of copper in concentrates f. o. b. cars at Miami, Ariz., 1917.

	Per ton of ore.	Per pound of copper.
Mining	$1.267789	$0.047407
Milling	.691498	.025857
General	.325261	.012163
	2.284543	.085427

Ore reserves of Miami Copper Co., January 1, 1918.

	Quantity (short tons).	Percentage of copper.
High-grade sulphide ore	14,760,000	2.40
Low-grade sulphide ore	25,000,000	1.06
Mixed sulphide and oxide ore	6,000,000	2.00
	48,760,000	.....

The production of refined copper by the Inspiration Consolidated Copper Co. for 1917 was 80,566,982 pounds. A total of 3,914,742 tons of ore was mined, of which 3,891,075 tons was concentrating ore and 23,667 tons of oxidized ore was shipped direct to the smelter.

The average grade of ore treated was 1.388 per cent copper and the average extraction 20.39 pounds per ton.

Digitized by Google

Cost of copper derived from concentrating ores of the Inspiration Consolidated Copper Co., 1917.

	Cost per pound.	Cost per ton of ore.
	Cents.	
Mining	3.572	$0.7239
Coarse crushing	.163	.0329
Ore hauling	.101	.0206
Concentrating and royalty	2.931	.5941
Concentrates hauling	.007	.0015
Smelting, freight, refining, marketing, etc.	3.665	.6369
	10.439	2.0099

Mill statistics, Inspiration Consolidated Copper Co., 1917.

Total ore milled, dry tons	3,891,075
Ore milled per day, do	12,884.4
Average number of sections running	13.756
Average output per section, tons	936.7
Assay mill feed, per cent of copper	1.388
Screen analysis of feed (on 48 mesh), per cent	3.3
Copper in feed, oxidized, do	.279
Copper assay of general tailings, do	.355
Copper in general tailings, oxidized, do	.237
Copper in general concentrates, smelter assay, per cent	29.27
Copper in flotation concentrates, do	35.57
Copper in table concentrates, do	13.93
Moisture in general concentrates, do	17.2
Concentrates produced per ton of ore, tons	.0359
Recovery of copper calculated from (smelter assays):	
Assays only, per cent	75.34
Assays and weights of concentrates and feed, per cent	75.78
Assays and weights of concentrates and tails, per cent	75.46
Assays and weights of feed and tails, do	75.36
Recovery of copper sulphides, do	89.73
Water used per ton of ore, gallons	348
Water consumed per ton of ore (first six months of years):	
Reclaimed in tanks at foot of mill, gallons	356
Reclaimed from ponds, do	475
New water from Kiser pump station, do	277
Power used per ton of ore (first six months of year):	
Coarse crushing, kilowatt hours	.43
Fine grinding and concentrating, do	10.87
Blowers for flotation air, do	2.42
Filter and reclaiming water, do	2.01
Lights, do	.07
Steel balls consumed per ton of ore milled, pounds	1.82
Flotation oil consumed per ton of ore milled:	
Coal tar, pounds	1.21
Other oils, do	.11

No new ore was developed during the year. The reserves December 31, 1917, were calculated as 87,864,378 tons.

Net profits for the year were $11,080,731.94, out of which $9,751,227.75 was paid in dividends.

Morenci-Metcalf district.—The Morenci-Metcalf district is one of the oldest copper-producing districts in the State. Production began

Digitized by Google

here in 1873 and since 1880 the district has been a large contributor to the copper output of the country. To the end of 1917 it has produced 1,350,196,000 pounds of copper, or 5.35 per cent of the output of the country since 1845. In total production it ranks fifth among the copper districts of the country. In the output for 1917 it ranks eleventh. All the mines of the district were closed for several months, owing to the labor troubles.

Copper produced in Morenci-Metcalf district, 1906–1917.

Year.	Quantity.	Average yield of copper from ore.	Year.	Quantity.	Average yield of copper from ore.
	Pounds.	*Per cent.*		*Pounds.*	*Per cent.*
1906	56,000,000	.....	1912	79,900,000	2.21
1907	63,000,000	.....	1913	70,100,000	2.00
1908	77,000,000	.....	1914	66,000,000	1.95
1909	72,000,000	2.29	1915	51,096,000	2.01
1910	73,154,000	2.35	1916	75,977,000	1.89
1911	71,500,000	2.29	1917	53,000,000	1.85

In 1917 of the mine production of copper 40,087,000 pounds was derived from concentrating ores and 12,840,000 pounds from smelting ores. The mines of the district produced 1,268,783 pounds of concentrating ores and 153,064 tons of smelting ore.

The ores in general carry little gold and silver, and, as much of the copper is of sufficient purity for commercial purposes, it is not refined electrolytically, and consequently the precious-metal content is not separated from the copper.

Copper produced by Morenci branch of Phelps Dodge Corporation, 1911–1917.

Year.	Ore treated (short tons).	Copper produced.		Dividends.
		Quantity (pounds).	Percentage.	
1911	517,087	22,704,398	2.29	$900,000
1912	520,272	24,802,789	2.38	1,464,610
1913	537,324	22,255,130	2.07	780,000
1914	477,581	20,272,607	2.12	280,000
1915	376,604	15,333,976	2.03	.....
1916	474,808	17,541,258	1.85	.....
1917	333,263	13,202,201	1.98	.....

Copper produced by Morenci branch of Phelps Dodge Corporation, 1917, by kinds of ore.

	Ore treated.	Copper produced.	Assay of original ore.	Yield.
	Short tons.	*Pounds.*	*Per cent.*	*Per cent.*
Concentrating ore	310,743	9,696,107	2.34	1.560
Smelting ore	16,594	2,761,392	8.73	8.320
Old slag and tailings	904	60,434	3.50	3.340
Siliceous ore to converters	5,022	684,268	7.00	6.810
	333,263	13,202,201	2.73	1.981
Purchased scrap	1	1,200	75.00	75.000
	333,264	13,203,401	2.73	1.981

Digitized by Google

Result of concentration operations by the Morenci branch of Phelps Dodge Corporation, 1917.

	Quantity (short tons).	Average assay (per cent of copper).
Ore concentrated	312,224.5	2.333
Concentrates produced	46,047.1	11.201
Tailings produced	.....	.648

Saving	per cent	70.78
Ratio of concentration		6.780
Proportion of actual running time to total time	per cent	54.06

Result of smelting and converting operations of Morenci branch of Phelps Dodge Corporation, 1917.

Concentrates	short tons	46,049	
Ore	do	16,473.5	
Old tailings	do	3.9	
Precipitates	do	120.6	
			62,647
Secondaries:			
Converter slag and cleanings	do	18,584.5	
Furnace cleanings	do	335.5	
Flue dust	do	21,378.5	
			40,298.5
Flux:			
Limestone	do		15,650.3
			118,595.8

Copper produced by Arizona Copper Co., 1911–1917.

Year ending Sept. 30.	Ore treated.	Copper produced.	Average yield.	Year ending Sept. 30.	Ore treated.	Copper produced.	Average yield.
	Short tons.	*Pounds.*	*Per cent.*		*Short tons.*	*Pounds.*	*Per cent*
1911	744,746	34,584,000	2.32	1914	1,079,950	38,756,000	1.808
1912	927,116	38,132,000	2.057	1915	968,566	37,330,000	1.961
1913	936,903	34,226,000	1.938	1916	905,486	34,100,000	1.803
				1917	1,178,087	42,482,000	1.830

No. 6 concentrator treated 996,699 tons of ore with an average copper content of 2.44 per cent. The average extraction was 73.02 per cent. The No. 4 concentrator treated 130,355 dry tons of ore averaging 2.26 per cent of copper. The average extraction was 71.33 per cent.

The company reports that as much new ore was placed in sight during the fiscal year as was extracted for the preceding two years.

Metals produced by Shannon Copper Co., 1911–1917.

Year.	Ore treated.	Copper produced.	Average yield in copper.	Gold.	Silver.	Dividends.
	Short tons.	*Pounds.*	*Per cent.*	*Ounces.*	*Ounces.*	
Year ending August, 1911	263,975	15,168,102	2.845	1,690	91,955	.....
Year ending August, 1912	285,210	16,406,336	2.876	2,615	170,690	$150,000
August to December 31, 1912	95,235	5,149,805	2.704	1,012	54,394	.....
1913	434,307	18,793,724	2.163	3,412	169,197	150,000
1914	193,297	9,003,169	2.33	1,295	60,603	.....
1915	.....	6,017,642	.....	690	35,449	.....
1916	.....	9,364,968	.....	1,527	62,935	150,000
1917	.....	6,138,219	.....	1,096	51,771	525,000

Digitized by Google

Jerome district.—The production of copper in the Jerome district began about 1883, though it had yielded gold and silver prior to that time. Since 1888 it has been a steady and important producer. To the end of 1917 it has produced 1,001,340,000 pounds of copper, or 3.97 per cent of the total output of the country since 1845. In total output it stands seventh among the copper districts of the country, and in output for 1917 it ranks sixth.

Copper produced in Jerome district, Ariz., 1911–17.

	Pounds.		Pounds.		Pounds.
1906	38,500,000	1910	38,600,000	1914	30,000,000
1907	33,000,000	1911	33,200,000	1915	53,260,000
1908	36,000,000	1912	31,680,000	1916	102,000,000
1909	36,700,000	1913	35,300,000	1917	145,900,000

The United Verde Copper Co. was the largest producer in the district.

The United Verde Extension Mining Co. shipped 115,064 tons of ore containing 1,656 ounces of gold, 332,536 ounces of silver, and 63,242,784 pounds of copper, an average of 0.0144 ounce of gold, 2.89 ounces of silver, and 549.6 pounds of copper per ton.

Net earnings for the year amounted to $8,256,117. Dividends were paid to the amount of $2,922,500.

Construction of the smelter and railroad and driving of the extraction tunnel was in progress during the year.

Prospecting was active in the district during the year.

Ray or Mineral Creek district.—Notable production in the Ray or Mineral Creek district began in 1911, and the total production to the end of 1917 has been 388,678,000 pounds. The Ray Consolidated Mining Co. has been the only important producer in the district.

Copper produced by Ray Consolidated Mining Co., 1911–17.

Year.	Ore milled.	Copper content.	Mill recovery.	Refined copper.	Cost per pound.	Dividends.
	Short tons.	*Per cent.*	*Per cent.*	*Pounds.*	*Cents.*	
1911	681,519	1.83	63.1	14,935,047	10.75	.....
1912	1,565,875	1.677	68.278	34,674,275	9.828	.....
1913	2,365,296	1.719	66.09	52,341,029	9.783	$1,631,504
1914	2,427,700	1.76	67.88	57,004,281	8.839	1,089,322
1915	2,848,969	1.673	64.11	60,338,936	9.497	1,872,319
1916	3,332,340	1.607	70.20	74,983,540	10.267	4,337,955
1917	3,560,900	1.635	74.53	88,582,649	12.229	6,634,151

Ore reserves at the end of the year were estimated at 89,812,522 tons, averaging 2.048 per cent copper. The concentrates are treated at the Hayden plant of the American Smelting & Refining Co.

Net profits for the year amounted to $9,701,169.74.

Development of the ore body and construction of the mill of the Ray Hercules Copper Co. was in progress during the year. The developed ore is reported as 9,500,000 tons, averaging 1.77 per cent copper. The first unit of the mill, with a capacity of 1,500 tons per day, will be ready for operation in 1918.

Ajo district.—The Ajo district is in Pima County, about 45 miles from Gila Bend, which is on the Southern Pacific Railroad and with which it is connected by the Tucson, Cornelia & Gila Bend Railroad.

Digitized by Google

The leaching plant of the New Cornelia Copper Co. was placed in operation on May 1, 1917, and has met the estimates and expectations of the designers with far less difficulties and readjustments than would have been expected in starting a new plant and a new process of treatment. The success of this operation is a source of satisfaction not only to those directly interested but to other companies who have low-grade oxidized ores to treat and to the industry in general as adding to our supply of copper ores much oxidized material that it had not previously been possible to treat profitably.

During the year 780,211 tons of ore was mined, electrolytic copper was produced to the amount of 12,764,848 pounds; copper in cement copper, 3,316,283 pounds; and copper in ore shipped to smelters, 3,401,191 pounds, or a total of 19,482,322 pounds.

It is reported that when the plant was operating under normal conditions an extraction of 80 per cent of the copper was realized.

With additions to the plant that were made and in progress during the year it is expected that a capacity of 4,000,000 to 4,500,000 pounds monthly will be attained.

Pioneer district.—The Pioneer district, Pinal County, produced 10,600,000 pounds of copper in 1917, as compared with 9,145,000 pounds in 1916.

The Magma Copper Co., of the Pioneer district, produced 10,148,632 pounds of copper in 1917, at an average cost of 16.01 cents a pound, the operating profits being $1,067,986.13.

Dividends were paid to the amount of $504,000.

Copper ore mined and treated and milling results of the Magma Copper Co., 1917.

	Ore.	Copper.	Silver.	Gold.
	Short tons.	*Per cent.*	*Ounces.*	*Ounces.*
Copper-sulphide ore	107,529	5.375	5.752	0.0563
Hand-sorted crude sulphide shipped direct to smelter	13,554	14.763	15.293	.1002
Mill heads	93,975	4.025	4.376	.05
Concentrates produced	32,184,948	10.637	11.153	.1435

The average assay of mill tailings was 0.5809 per cent of copper and 0.63 ounce of silver.

The mill recovery was 90.511 per cent of the total copper in the mill heads. The total copper recovery, including ore obtained by hand sorting, was 93.7906 per cent of the copper contents of the mine-run ore.

The net production, after deducting all smelting and refining losses, was 10,148,632 pounds of copper, 537,994.84 ounces of silver, and 5,978.699 ounces of gold.

Copper shipments of Magma Copper Co., from beginning of operations to end of 1917.

	Ore.	Copper.	Silver.	Gold.
	Short tons.	*Per cent.*	*Ounces.*	*Ounces.*
Copper concentrates	70,772.7781	13.0272	14.208	0.1250
Crude sulphides	36,406.1720	16.4759	18.330	.0917
Crude carbonate	4,368.4250	8.0742	5.345	.0558
	111,547.3751	13.9588	15.206	.1114

Digitized by Google

Estimated ore reserves of Magma Copper Co. at end of 1917

	Ore.	Gold per ton.	Silver per ton.	Copper.	Lead.	Zinc.
	Short tons.	*Ounces.*	*Ounces.*	*Per cent.*	*Per cent.*	*Per cent.*
Reasonably assured copper sulphide ore.	130,000	0.05	5.75	6.0	.....	.....
Reasonably assured lead-zinc ore.....	20,000	.....	12.0	.....	2.0	12.5
Probable silver sulphide ore.....	8,000	.05	24.0	0.3	1.0	7.0

Silverbell district.—The Silverbell district, in Pima County, showed renewed activity in 1917. Since 1904, when important production of copper in the district began, it has yielded about 49,000,000 pounds of copper. The production in 1917 was 7,200,000 pounds. The Silver Bell mine, operated by the American Smelting & Refining Co., was the principal producer. The ores are treated at the smelter at Sasco.

Other districts that made important production in 1917 are the Cochise district, Cochise County, 4,180,000 pounds; the Banner district, Gila County, 5,880,000 pounds; the Helvetia and Pima districts, Pima County, 2,600,000 and 4,440,000 pounds, respectively; the Patagonia and Big Bug districts, Santa Cruz County, 3,050,000 and 6,770,000 pounds, respectively; and the Copper Basin, Peck, and Planet districts, Yuma County, 1,380,000, 2,700,000, and 2,975,000 pounds, respectively; Aqua Fria district, Yavapai County, 2,580,000 pounds.

CALIFORNIA.

In 1917 California produced 44,933,846 pounds of blister copper, compared with 43,400,876 pounds in 1916.

California was among the earliest of the Western States to make a considerable output of copper. Production began in the "foothill" belt about 1862, and for several years California was second only to Michigan in output of copper. Later, however, the industry declined, and California did not again attain high rank as a copper producer until 1897, when production from the Shasta County district began. Since that time the State's output has been steady and large. The production for the early years has been ascertained from the best sources available, and when to this output the known production since 1882 is added it is found that to the end of 1917 California has produced about 700,756,683 pounds of copper, or 2.78 per cent of the output of the country since 1845. In 1917 the output was 2.38 per cent of the total production of the United States. In total output the State ranks sixth among the copper producers of the country and for 1917 it ranked eighth. Three smelting plants in the State treated copper ores in 1917.

Most of the copper has come from two districts, though numerous other districts have made production, especially in the last few years, and copper minerals are widely distributed over the State. The largest producer has been the Shasta County district.

Shasta County district.—The Shasta County copper belt lies in the Klamath Mountains, at the head of the Sacramento Valley, a few miles north of Redding. Sacramento River crosses the belt, separating it into an eastern and a western portion. The eastern portion

Digitized by Google

contains the Bully Hill and Afterthought districts and the western the Iron Mountain and Little Backbone districts. Placer mining was carried on in the county in the early days of mining in the State, and later considerable silver was produced from the gossan outcrop of the copper deposits. Copper minerals had been long known in the county, but not until 1897, when the Mountain Copper Co. (Ltd.) began production at Iron Mountain, did it become an important contributor of copper.

Copper produced in Shasta County district, Calif., 1906–1917.

Year.	Quantity (pounds).	Average yield of copper (per ct.).	Gold and silver per ton.	Year.	Quantity (pounds).	Average yield of copper (per ct.).	Gold and silver per ton.
1906	21,000,000	3.6	$3.75	1912	26,000,000	3.58	$1.84
1907	28,000,000	3.0	2.70	1913	26,800,000	3.50	1.70
1908	32,000,000	3.2	2.85	1914	25,100,000	3.56	1.28
1909	48,000,000	3.4	2.02	1915	30,500,000	3.29	2.67
1910	36,000,000	3.0	2.14	1916	39,700,000	2.62	2.59
1911	29,900,000	3.7	1.80	1917	26,650,000	2.75	1.00

The total production to the end of 1917 has been about 540,650,000 pounds, or 2.15 per cent of the total output of the country. In 1917 the district produced 1.41 per cent of the total output. In total output the district ranks ninth, and in the production for 1917 it was twelfth among the copper districts of the country.

The principal producing companies in 1917 were the Mountain Copper Co., Mammoth Copper Co., and Balaklala Copper Co. The ores of the Mammoth Co. were smelted at its plant at Kennett, and the Mountain Co.'s ores were smelted at its plant at Martinez, on San Francisco Bay. The Balaklala ores were shipped to the Mammoth plant.

The Mammoth Copper Mining Co. produced 164,540 tons of copper ore and a small tonnage of zinc ore.

Exploration in the Friday Lowden tunnel opened ore of high grade but undetermined extent, which is regarded as demonstrating that the Mammoth ore-bearing area extends to the Friday Lowden tunnel level.

Exploration in section 29 developed a small high-grade ore body and a larger ore body of average grade.

From the Stowell mine 18,497 tons of ore were shipped to the Mammoth smelter, which practically exhausted the known reserves of the mine.

The Mammoth smelter treated 345,990 tons of ore during the year, a large tonnage coming from the Balaklala mine.

The Trinity mine also began shipment to the smelter late in the year.

The Mountain Copper Co. treated 124,446 tons of ore and concentrates, derived as follows: Iron Mountain mine, 13,096 tons; No. 8 mine, 38,107 tons of ore and 11,766 tons of concentrates; Hornet mine, 53,200 tons; purchased ore, 8,277 tons. The output of copper was 3,940 tons.

A plan for treating the "filling" of the old mine was worked out and construction of a plant begun during the year. It is estimated that there are 500,000 tons of this material, though it is not expected that it will be profitable to treat all of it.

Digitized by Google

Reserves at the close of the year were estimated as follows:

Estimated ore reserves of Mountain Copper Co. at end of 1917.

	Ore.	Copper.	Probable ore.
	Short tons.	*Per cent.*	*Short tons.*
Complex vein	73,450	2.16	22,500
West Vein No. 8 mine	62,600	2.55	63,000
St. Patrick vein	17,650	2.13	10,000
Miscellaneous	17,400	1.9	.....
	171,100	2.33	95,500

Available reserves of ore in the Hornet mine are now estimated at 1,400,000 tons.

There were some shipments of ore from the Bully Hill and Afterthought districts.

Electric power is used almost exclusively at both mines and reduction plants.

The Shasta County belt is served by the Southern Pacific Railroad, which has short branches extending to the smelters. The Iron Mountain district is connected with the main line by a narrow-gage railroad operated by the Mountain Copper Co., and the mines of the Mammoth Co. are connected with the smelter by a combined electric railroad, gravity tram, and steam railroad. The ores of the Balaklala and Trinity mines are delivered to the railroad over a cable tramway. The Bully Hill district is served by a standard-gage branch of the Southern Pacific Railroad. The nearest railroad point to the Afterthought district is Bellavista, on the Anderson & Bellavista Railroad, at a distance of about 15 miles.

"*Foothill district.*"—The "foothill belt" is a rather extensive area of copper deposits which has its best development in Calaveras County. This belt furnished practically the entire copper production from California in the sixties. Subsequent to that period the district was inactive for many years, but from 1887 to 1892 the mines again made some production. The present period of activity began about 1901, and for some years the district has made considerable contributions to the copper output of the State.

There is no accurate record of the output of this district in the early days, but from the records of the production of the State it is estimated that to the end of 1917 it has yielded approximately 143,860,000 pounds of copper.

Copper produced in "foothill district," Calif., 1907–1917.

Year.	Quantity.	Average yield.	Year.	Quantity.	Average yield.
	Pounds.	*Per cent.*		*Pounds.*	*Per cent.*
1907	4,500,000	5+	1913	5,800,000	4.5
1908	4,500,000	4	1914	4,400,000	5.0
1909	5,400,000	4.6	1915	3,700,000	5.44
1910	8,000,000	5.2	1916	6,460,000	3.07
1911	5,500,000	4.7	1917	8,000,000	4.18
1912	6,000,000	5.1			

In total output the district ranks thirteenth and in production for 1917 it ranked twentieth among the copper districts of the country.

Digitized by Google

The Penn Mining Co. and the Calaveras Copper Co. were the largest producers.

Plumas County.—In 1917 Plumas County produced 7,471,000 pounds of copper. The principal producers were the Engels Copper Mining Co. and the Walker Mining Co.

Other counties.—San Bernardino County produced 1,572,000 pounds in 1917, and Placer and other counties made smaller production.

COLORADO.

In 1917, Colorado produced 10,054,951 pounds of blister copper compared with 9,536,193 pounds in 1916. Although the State has no important producing district in which copper is the principal metal, yet it ranked tenth among the copper-producing States in 1917. The total recorded output for the State from the beginning of the industry has been 267,245,844 pounds, or 1.06 per cent of the total for the United States since 1845.

The copper has been derived mainly from the treatment of mixed ores in which copper was a minor constituent, including lead-silver ores and pyritic ores rich in gold and silver. In 1917 the largest production came from Lake County and from San Juan, Ouray, San Miguel, Clear Creek, Chaffee, Dolores, Gilpin, and Fremont counties. Leadville and the San Juan-Ouray region have been the greatest producers of copper. Much of the output is recovered as matte in lead furnaces.

IDAHO.

During 1917 Idaho produced 6,446,224 pounds of blister copper, compared with 7,248,794 pounds in 1916. The State has made a small and irregular output of copper since 1884, but only since 1903 has it been a steady producer. To the end of 1917 it had a recorded output of 100,753,426 pounds.

Coeur d'Alene region.—The Coeur d'Alene region has been the most productive copper area in the State, though it is not the most productive at the present time. Complete figures for the copper output of the district are not on record, but the total production has been approximately 63,775,000 pounds. The Snowstorm mine has been the largest copper producer in the district.

Alder Creek district.—There has been intermittent production from the Alder Creek or Mackay district since 1900. In 1917 the mines of the district produced 4,380,000 pounds of copper. The largest producer was the Empire Copper Co.

There are other districts in Idaho, notably that of the Seven Devils region, which contain copper deposits, but owing to lack of transportation facilities they have made but small production.

MICHIGAN.

The production of refined copper in Michigan in 1917 was 268,508,091 pounds, compared with 269,794,531 pounds in 1916.

The mining of copper in Michigan antedates the earliest visits of European explorers to the region. The production on a commercial scale, however, dates from 1845, and since that time the State has been a steady producer and an important factor in the copper industry of the world. To the end of 1917 Michigan has produced

Digitized by Google

6,298,285,858 pounds of copper, or 24.99 per cent of the output from the United States since 1845. For many years subsequent to 1845 Michigan was the most important copper-producing State, and in total output it is second only to Montana and Arizona. The entire output comes from the Keweenaw or Lake Superior district.

Although the district has been an active producer for 70 years, many of the older mines still have large reserves of ore, new mines are being opened, and much territory remains to be prospected. Moreover, large quantities of the mill tailings produced when milling methods were less efficient than at present are being re-treated at a profit.

The Lake Superior region is unique in being the only district in which a large output is derived from native copper.

Production in 1917 was hampered by a shortage of labor supply. Extension of electrical tramming and other means of saving labor tend to relieve the shortage, but it will doubtless continue during the war.

Copper ore produced in Lake Superior district, Mich., 1906–1917.

Year.	Quantity.	Yield of copper.	Year.	Quantity.	Yield of copper.
	Short tons.	*Per cent.*		*Short tons.*	*Per cent.*
1906	8,904,127	1.26	1912	11,411,941	0.96
1907	9,892,214	1.1	1913	7,016,370	.97
1908	10,531,271	1.06	1914	9,269,413	.89
1909	11,429,394	1.02	1915	12,334,700	1.07
1910	10,869,561	1.02	1916	12,364,114	1.08
1911	10,978,827	1.00	1917	12,400,723	.99

The statistics in the following tables are compiled from the annual reports to the stockholders of the individual companies:

Ore milled and copper derived therefrom by Michigan companies in 1915, 1916, and 1917, compiled from the annual reports of the producing companies.

Company.	1915		1916		1917	
	Quantity.	Yield per ton.	Quantity.	Yield per ton.	Quantity.	Yield per ton.
	Short tons.	*Pounds.*	*Short tons.*	*Pounds.*	*Short tons.*	*Pounds.*
Ahmeek	948,874	23.0	1,164,010	20.7	1,271,275	22.0
Allouez	534,705	18.78	566,960	18.02	566,674	15.69
Baltic	378,443	31.79	369,287	33.65	325,342	34.47
Calumet & Hecla	1,739,984	29.74	1,727,794	29.97	1,751,621	28.78
Centennial	150,191	15.63	150,617	15.72	148,332	13.50
Champion	923,743	36.17	936,656	35.87	776,036	35.50
Franklin	122,018	.....	267,286	.....	303,625	.....
Hancock	.....	.....	208,112	.....	302,725	13.22
Houghton	14,657	10.69	19,444	10.55	15,628	11.45
Isle Royale	680,270	13.7	925,419	13.4	922,160	14.6
Keweenaw	.....	.....	6,915	9.96	41,148	9.248
La Salle	80,959	9.67	144,829	9.53	185,014	10.38
Mass	323,335	14.35	287,900	16.51	244,671	16.29
Michigan	.....	.....	.....	.....	2,091	.....
Mohawk	829,789	19.15	664,547	20.82	605,202	20.35
New Arcadian	.....	.....	.....	.....	4,900	.....
Osceola	1,361,089	14.5	1,284,681	15.2	1,237,805	13.0
Quincy	.....	.....	1,204,026	17.5	1,280,837	17.33
South Lake	.....	.....	.....	.....	[a] 68,388	11.03
Superior	212,051	18.23	185,315	16.38	129,587	16.99
Tamarack	217,027	17.9	.....	.....	.....	.....
Trimountain	349,684	23.75	349,504	24.94	264,655	23.72
Victoria	133,984	.....	146,690	.....	137,286	.....
White Pine	[b] 114,039	24.76	188,890	22.27	212,889	19.11
Winona	102,594	16.79	161,828	13.39	112,082	13.33
Wolverine	397,614	18.23	388,898	17.07	352,845	16.60

[a] Includes May, 1916, to Dec. 31, 1917.

[b] Last eight months of 1915.

Digitized by Google

Copper produced by Michigan mines in 1916 and 1917, compiled from the annual reports of the producing companies.

Company.	Quantity (pounds).		Cost per pound.	Price received per pound.	Profit per pound.
	1916	1917			
			Cents.	*Cents.*	*Cents.*
Ahmeek	24,142,158	27,919,312	9.42	26.84	17.42
Allouez	10,219,290	8,892,915	13.84	27.95	14.11
Baltic	12,425,804	11,214,961	13.77	28.73	14.96
Calumet & Hecla	71,349,591	68,419,826	13.01	28.39	15.38
Centennial	2,367,400	2,002,857	18.67	26.96	8.29
Champion	33,601,136	27,550,343	10.40	28.73	18.33
Franklin	3,116,566	3,155,574	.....	26.74	.....
Hancock	2,824,934	4,047,053	.....	28.229	.....
Houghton	204,274	179,012	.....	28.14	.....
Isle Royale	12,412,111	13,480,021	15.74	26.87	11.13
Keweenaw	68,880	380,536	.....	.....	.....
La Salle	1,380,352	1,919,775	20.14	28.45	8.31
Mass	4,752,588	3,984,616	19.81	26.23	6.42
Michigan	.....	35,400	.....	.....	.....
Mohawk	13,834,034	12,313,887	12.06	27.94	15.88
New Arcadian	.....	53,278	.....	.....	.....
Osceola	19,586,501	16,081,958	13.86	27.89	14.03
Quincy	21,065,612	22,195,577	.....	28.60	.....
South Lake	.....	754,433	.....	.....	.....
Superior	3,034,656	2,201,672	16.88	29.39	12.51
Trimountain	8,720,558	6,278,097	15.22	28.73	13.51
Victoria	1,661,832	1,612,640	.....	.....	.....
White Pine	4,207,449	4,067,529	14.99	28.30	13.31
Winona	2,167,255	1,494,472	.....	29.05	.....
Wolverine	6,641,492	5,856,389	11.62	29.15	17.53
	.....	.....	12.80	28.09	15.29

The regrinding and leaching plants that have recently been introduced in the mills of the district have effected a notable increase in the extraction of copper and a further saving is expected by the introduction of the flotation process for the treatment of certain products of the mills.

The district is well located for cheap working of the mines. The Great Lakes furnish cheap transportation for both coal and copper, and the Lake steamers reach the heart of the district by Portage Lake and the Houghton Ship Canal. The district is served by the Mineral Range, Copper Range, and Keweenaw Central railroads and is connected with the main lines of traffic by the Chicago, Milwaukee & St. Paul and Duluth, South Shore & Atlantic railways.

MONTANA.

The output of blister copper from Montana in 1917 was 276,225,977 pounds, compared with 352,139,768 pounds in 1916.

The first record of production of copper from Montana was in 1868, but the State did not become a large contributor of this metal until 1880. Since that time the increase in its output of copper has been steady and rapid. To the end of 1916 the State has produced 7,331,462,884 pounds, or 29.10 per cent of the total output of the United States since 1845. In total production the State ranks first, and in the output for 1917 it ranked second. The Butte district has furnished nearly the entire output.

Three copper-smelting plants were operated in Montana in 1917—that of the East Butte Mining Co. at Butte, and those of the Anaconda Copper Co. at Anaconda and at Great Falls.

Digitized by Google

Butte district.—The presence of copper minerals in the Butte district has been known since the discovery of gold there in 1864, and attempts were made to treat the copper ores as early as 1866; but it was not until the late seventies that Butte began to attract attention as a copper camp, and large production did not begin until a railroad reached the district in 1881. To the end of 1917 Butte has produced about 7,300,500,000 pounds of copper, or 28.97 per cent of the total output of the country since 1845. Both in total production and in the output in 1917 it ranks first among the copper-producing districts of the United States.

Copper and associated metals produced in Butte district, Mont., 1906–1917.

Year.	Copper.	Average yield in copper.	Gold.	Silver.	Year.	Copper.	Average yield in copper.	Gold.	Silver.
	Pounds.	*Per cent.*	*Ounces per ton.*	*Ounces per ton.*		*Pounds.*	*Per cent.*	*Ounces per ton.*	*Ounces per ton.*
1906.....	294,000,000	3.15	0.01	2.0	1912.....	308,000,000	3.02	0.0005	2.09
1907.....	222,000,000	2.75	.014	2.3	1913.....	283,000,000	2.70	.0058	1.92
1908.....	252,500,000	3.3	.0075	2.16	1914.....	235,700,000	2.66	.0059	1.83
1909.....	314,000,000	3.08	.0076	2.07	1915.....	267,000,000	2.66	.0066	1.82
1910.....	282,500,000	3.13	.0068	2.02	1916.....	319,500,000	2.81	.0059	1.79
1911.....	271,200,000	3.17	.0071	2.20	1917.....	270,500,000	2.81	.0056	1.84

Copper, gold, and silver produced by Anaconda Copper Mining Co. from company ores, 1913–1917.

Year.	Ore treated.	Copper.	Silver.	Gold.	Dividends.
	Short tons.	*Pounds.*	*Ounces.*	*Ounces.*	
1913.....	4,566,451	241,983,323	8,719,132	64,898	$12,997,500
1914.....	3,768,640	205,298,531	7,221,815	99,651	9,077,500
1915.....	4,258,129	235,076,289	8,064,986	106,702	9,325,000
1916.....	5,273,066	307,395,092	10,790,705	92,099	17,484,375
1917.....	3,906,901	239,014,880	8,368,180	58,545	19,815,625

On account of interruption of operations and scarcity of labor, it was decided by the Anaconda Copper Mining Co. to curtail development as far as practicable and only 34.61 miles were accomplished as compared with 42.06 miles in 1916. The results of development work were satisfactory.

The annual report of the company states that—

The mines of the company produced during the year 4,193,624.13 tons of ore and 10,011.83 tons of precipitates, a total of 4,203,635.96 tons.

The copper reduction works treated for all companies during the year 4,267,854 tons of ore and other cupriferous material at Anaconda, and 105,690 tons of ore and other cupriferous material at Great Falls. Of this amount 3,906,901 tons of ore were produced by company mines; 449,513 tons of ore were either purchased from or treated for other companies; 17,130 tons of precipitates and cleanings from the old works at Anaconda and Butte were treated.

At Anaconda there were produced 238,413,031 pounds of fine copper, 8,502,070.23 ounces of silver, and 54,396.071 ounces of gold.

At Great Falls there were produced 15,095,301 pounds of fine copper, 528,955.55 ounces of silver, and 4,149.533 ounces of gold.

Or a total production at both Anaconda and Great Falls copper plants of 253,508,332 pounds of fine copper, 9,031,025.78 ounces of silver, and 58,545.604 ounces of gold.

Of the total production at these plants, 239,014,880 pounds of fine copper, 8,368,179.99 ounces of silver, and 58,545.604 ounces of gold were produced from the mines of the company.

The electrolytic copper refinery at Great Falls produced during the year 141,517,768 pounds of cathodes, 132,089,914 pounds of which were melted into

Digitized by Google

shapes at Great Falls and 9,427,854 pounds were shipped to Raritan Copper Works for melting.

The copper leaching plant at Anaconda treated during the year 598,370.16 tons of tailings, from which there were produced 5,019.67 tons of cement copper.

The zinc plants at Anaconda and Great Falls treated during the year 326,479.14 tons of ore and other zinciferous material, of which amount 257,849.93 tons of ore were produced by mines of the company, and 68,629.21 tons of ore were purchased from other companies.

At Great Falls there were produced during the year 50,624,524 pounds of electrolytic zinc.

During the year much attention was paid to the treatment of complex residues resulting from the zinc leaching plant. These residues were stock piled until the month of June, when a bag house was put into commission. After continued experimental effort the desired result was obtained, and a reverberatory furnace, smelting zinc residues, was put into regular operation. By means of the method employed satisfactory recovery was made of the gold, silver, copper, and about 20 per cent of the lead contained in the furnace charge. This matte is converted in the usual way; most of the remaining lead is driven as a fume to the bag house, there collected, and shipped to the lead plant of the International Smelting Co. for further treatment.

Copper, silver, and gold produced by North Butte Mining Co., 1912–1917.

Year.	Copper ore and precipitates treated.	Copper.	Silver.	Gold.	Dividends.
	Short tons.	*Pounds.*	*Ounces.*	*Ounces.*	
1912	425,297	26,480,123	1,377,408	1,367	$697,000
1913	455,029	28,318,321	1,602,163	1,567	820,000
1914	337,415	18,421,761	1,092,300	1,107	635,000
1915	378,161	19,235,285	940,631	1,121	387,000
1916	544,456	24,498,181	1,047,063	1,712	1,075,000
1917	296,773	14,493,452	662,845	959	1,075,000

The production from the North Butte mines for the year was largely made before June 8. On that date a disastrous fire occurred in the Granite Mountain shaft. The repair of the damage together with the general labor disturbance of the district prevented large production for the remainder of the year.

The company acquired additional ground in the "East Side mineral area," and prospecting in this area continued through the year.

Concerning production, the company report states that

During the year there were shipped 304,647 wet tons of ore and 31 wet tons of precipitates, and there were treated at the smelter 296,750 dry tons of ore and 23 dry tons of precipitates. Of this ore, 7,202 dry tons, or 2.4 per cent, were first class; 263,436 dry tons, or 88.8 per cent, were second class; and 26,112 dry tons, or 8.8 per cent, were third class. This ore produced 14,493.452 pounds of fine copper, 662,845.79 ounces of silver, and 958,993 ounces of gold. There were also mined 5,872 wet tons of zinc ore and there were treated 5,770 dry tons, which produced 1,222,482 pounds of zinc and 8,800.67 ounces of silver.

Copper produced by East Butte Copper Mining Co., 1912–1917.

Year.	Ore mined.	Average copper content.	Copper produced by smelter.	Average cost per pound of copper.
	Short tons.	*Per cent.*	*Pounds.*	*Cents.*
1912	99,458	5.78	14,709,460	9.698
1913	105,071	5.16	14,401,108	11.040
1914	72,853	4.72	9,175,578	11.110
1915	150,911	4.28	12,542,058	11.353
1916	253,899	3.67	18,840,713	16.887
1917	189,473	4.31	20,013,900	17.672

Digitized by Google

Operations of East Butte Copper Mining Co. for 1917.

Ore mined (wet weight)—short tons		189,473
Average assay value—per cent		4.31
Cost of mining per ton, including development		$8.29
Company ore treated (dry weight)—short tons		181,904
Custom ore treated (dry weight)—do		30,851
Total ore treated—do		212,755
Copper produced—pounds		20,013,900
Silver produced—ounces		581,190
Gold produced—do		1,825
Gross value of metals shipped		$5,317,279.49
Other income		$80,588.65
Gross income from operations		$5,397,868.14
Cost of mining, treatment, freight, selling, refining, and cost of custom ore purchased	$4,007,014.46	
Miscellaneous operations	82,695.64	
		$4,089,710.10
		$1,308,158.04
Less depreciation	5,921.99	
Ore depletion	163,635.60	
		$169,557.59
		$1,138,600.45
Less exploration and development		$116,639.62
Net surplus on operations		$1,021,960.83
Copper produced—pounds		20,013,900
Price per pound received, New York—cents		25.4603
Cost of production per pound—do		17.6727
Profit per pound—do		7.7876
Average price per ounce received for silver, New York—cents		82.707
Price per ounce received for gold, New York		$20.00

During the year there was shipped from the Tuolumne mine 30,972 wet tons of ore averaging 2.43 per cent of copper, and 1.471 ounces of silver and 0.0072 ounce of gold per ton. There was mined from the Main Range mine 10,967 tons of ore averaging 1.972 per cent of copper, 9.422 ounces of silver and 0.0078 ounce of gold per ton.

The Davis-Daly Copper Co. was a contributor to the copper output of the year and promises an increased production for 1918, the copper output for the first quarter of 1918 being 2,688,000 pounds.

NEVADA.

The production of blister copper in Nevada in 1917 was 115,028,161 pounds, compared with 100,816,724 pounds in 1916.

The earliest record production of copper in Nevada was in 1873, but the State did not become an important factor in the copper industry until 1908, when production from the Ely district began. To the end of 1917 Nevada has a recorded production of 715,848,659 pounds, or 2.84 per cent of the output of the country since 1845. In total production and in the output for 1917 Nevada ranks fifth among the copper-producing States.

Digitized by Google

A large part of the output has come from two districts, the Ely district, in White Pine County, and the Yerington district, in Lyon County.

Ely district.—The Ely district, White Pine County, had the largest production of copper in Nevada in 1917. Although it had long been known that the district contained copper deposits, production did not begin until 1908, when the Steptoe Valley smelting and concentrating plant was completed.

To the end of 1917 the output has been about 627,744,000 pounds. The district has yielded 2.49 per cent of the total output of the country since 1845, and it produced 4.94 per cent of the output in 1917. In total production it ranks eighth and in the production for 1917 it ranked seventh among the copper districts of the country.

Smelter production of metals in Ely (Robinson) district, Nev., 1908–1917.

Year.	Ore.	Copper produced.	Average yield in copper.	Gold and silver per ton of ore.
	Short tons.	*Pounds.*	*Per cent.*	*Cents.*
1908	429,925	14,776,363	1.72	24
1909	1,671,225	51,700,000	1.72	24
1910	2,346,354	62,332,419	1.30	21
1911	2,745,524	65,262,796	1.19	17
1912	2,985,217	64,932,446	1.09	17
1913	3,419,178	69,950,850	1.02	13.4
1914	2,749,913	51,089,921	.98	16
1915	3,204,374	64,638,158	1.01	19
1916	4,053,526	93,037,587	1.14	20
1917	4,466,017	93,615,335	1.05	18

Metals produced by Nevada Consolidated Copper Co., 1909–1917.

Year.	Ore treated.	Average assay of copper.	Average extraction of copper.	Gold and silver recovered per ton.	Refined copper produced.	Average cost of copper per pound.	Dividends.
	Short tons.	*Per cent.*	*Per cent.*	*Cents.*	*Pounds.*	*Cents.*	
1909	1,065,385	2.34	70.73	23.12	34,527,823	7.14	.....
1910	2,237,028	2.06	69.59	21.14	60,513,009	7.37	$2,982,644
1911	3,338,242	1.80	67.59	17.35	78,541,370	7.17	3,746,895
1912	2,852,515	1.692	68.25	16.48	63,063,361	8.86	2,999,137
1913	3,139,137	1.599	68.52	12.32	64,972,829	9.99	2,999,185
1914	2,640,294	1.483	68.48	13.45	49,244,056	10.16	2,249,389
1915	3,081,520	1.54	70.18	18.56	62,726,651	8.67	2,999,185
1916	3,922,634	1.632	73.87	20.44	90,735,287	10.17	7,497,963
1917	4,064,095	1.462	73.08	.....	82,040,508	12.45	8,297,746

Ore reserves of the Nevada Consolidated Copper Co. at the end of 1917 were calculated as follows: Ruth mine, 13,901,862 tons, averaging 2.24 per cent of copper; Copper Flat mine, 56,123,460 tons, averaging 1.415 per cent of copper, or a total in the two principal areas of 70,025,322 tons, averaging 1.58 per cent of copper.

In addition there is developed in the Kimberly mine 664,439 tons of ore, averaging 2.02 per cent of copper; in the Wedge, 43,960 tons, averaging 3.12 per cent of copper; and in the Veteran, 155,800 tons, averaging 3.89 per cent of copper. Net profits for the year amounted to $9,408,892.72.

The old Kimberly mill of the Consolidated Coppermines Co. was remodeled during the year and one section put in operation; a second section was put in operation in 1918.

Digitized by Google

Development of the replacement bodies in the limestone from the Alpha shaft was very encouraging, and considerable smelting ore was shipped from this deposit.

Ore mined, grade of ore, and metal produced by the Consolidated Coppermines Co. in 1917.

Mine.	Ore, dry weight.	Copper recovered.	Copper produced.	Lead produced.	Gold produced.	Silver produced.
	Short tons.	*Per cent.*	*Pounds.*	*Pounds.*	*Ounces.*	*Ounces.*
Morris-Brooks	144,204	1.69	3,320,727	.....	1,505.440	3,257.29
Alpha	22,958	8.62	3,753,662	.....	59.030	985.88
Liberty Pit	175,958	1.36	2,726,863	.....	980.783	2,758.19
Lessees	257	.....	5,646	65,309	11.848	4,947.71
	343,377	.....	9,806,898	65,309	2,557.101	11,987.08

Concentrating results at Kimberly mill of Consolidated Coppermines Co.

Ore milled	short tons	145,466
Concentrates produced	do	11,883
Ratio of concentration, 12.2 into 1.		
Grade of ore	per cent of copper	1.69
Grade of concentrates	do	15.07
Recovery	per cent	73

Concentrating results at Steptoe mill of Nevada Consolidated Copper Co. on Consolidated Coppermines Co.'s ores treated.

Ore milled	short tons	174,056
Concentrates produced	do	17,199
Ratio of concentration, 10.12 into 1.		
Grade of ore	per cent of copper	1.36
Grade of concentrates	do	8.21
Recovery	per cent	59.86

Concentrating sulphide ores are estimated at 20,092,800 tons, averaging 1.31 per cent copper. In addition there is considerable direct smelting ore.

Yerington district.—The Yerington or Mason district is in Lyon County, 50 miles southeast of Reno. It includes the productive portion of the Singatse Range, a low desert range lying between Mason Valley on the east and Smith Valley on the west.

The district did not commence to produce on a large scale prior to 1912.

Copper produced in Yerington district, Nevada, 1912–1917.

	Pounds.		Pounds.
1912	14,700,000	1915	700,000
1913	14,400,000	1916	3,491,000
1914	7,480,000	1917	19,396,000

The smelting plant of the Mason Valley Mines Co., at Thompson, renewed operations February 13, 1917, after being closed since after the beginning of the war.

During the year 294,958 tons of ore and 13,390 tons of low-grade flux were treated, of which 114,273 tons were from the company's mines and 194,075 tons from outside sources. A total of 7,038 tons of blister copper was produced, containing 1,036 ounces of gold, 47,257 ounces of silver, and 13,914,764 pounds of copper. Net gains for the year ending December 31, 1917, were $358,277.67.

Digitized by Google

The Nevada Douglas Copper Co. operated its mines throughout the year.

Ores from the Bluestone mine were shipped to the Mason Valley smelter for treatment.

Other districts.—Copper was produced in the Santa Fe district, Mineral County; Goldfield, Railroad, and Contact districts, Elko County; Jack Rabbit district, Lincoln County; Battle Mountain district, Humboldt County; Yellow Pine district; and smaller production from many other districts.

NEW MEXICO.

The production of blister copper from New Mexico in 1917 was 107,593,615 pounds, compared with 79,863,439 pounds in 1916.

Production of copper from New Mexico began in the last years of the eighteenth century, native copper from the mines of Grant County being carried to Mexico City and coined into money. During the nineteenth century, however, there was but small output. A little copper was reported for the year 1858, but New Mexico did not have a steady output until after 1880, and did not become a large producer until 1912.

From 1845 to 1917 New Mexico had a recorded output of 489,029,835 pounds of copper, or 1.95 per cent of the total output of the country. The principal producing districts are those of Grant County.

Santa Rita district.—The Santa Rita district was probably the first district in the West in which there was any notable production of copper; the output began in the closing years of the eighteenth century, and the metal went to Mexico for coinage. There are no accurate records of the production for this early period of operation.

From the best sources available it is estimated that the total production of copper to the end of 1917 has been 455,339,000 pounds.

Copper produced in Santa Rita district, N. Mex., 1906–1917.

	Pounds.		Pounds.		Pounds.
1906	3,075,000	1910	2,670,000	1914	54,000,000
1907	5,000,000	1911	1,400,000	1915	65,000,000
1908	4,000,000	1912	25,000,000	1916	74,228,000
1909	3,000,000	1913	50,511,000	1917	82,200,000

Since 1909 the Chino Copper Co. has been actively developing the main mineralized area by means of churn drills, and production by this company began late in 1911.

Metals produced by Chino Copper Co., 1911–1917.

Year.	Ore milled.	Copper content.	Mill recovery.	Production of refined copper.	Gold and silver per ton.	Cost of copper per pound.	Dividends.
	Short tons.	*Per cent.*	*Per cent.*	*Pounds.*	*Cents.*	*Cents.*	
1911	.....	.....	.....	986,375	.....	.....	.....
1912	1,120,375	2.077	61.63	27,776,083	.....	7.69	.....
1913	1,942,700	2.033	67.31	50,511,661	.....	8.78	$1,919,070
1914	1,907,300	2.115	67.858	53,999,028	2.71	7.60	2,169,065
1915	2,379,800	2.155	66.588	64,887,788	3.35	7.12	2,609,880
1916	3,094,400	1.83	66.59	72,319,508	2.60	8.70	7,177,335
1917	3,608,100	1.64	69.32	79,636,235	1.59	11.39	8,612,802

Digitized by Google

Two additional units to the mill were in process of construction and operation of the sixth section began late in the year. The seventh section is designed for the treatment of oxidized and partly oxidized ores. Ore reserves are reported at the close of the year as exceeding those at the close of 1916, which were given as 95,555,843 tons averaging 1.656 per cent of copper. Total income for 1917 amounted to $10,137,051.97.

Burro Mountain district.—The Burro Mountain district, southwest of Silver City, produced about 14,574,000 pounds of copper in 1917. The total production from the district has probably been about 34,366,000 pounds.

The gross production of copper from the mines of the Burro Mountain Copper Co. was 14,253,391 pounds.

Operations of the concentrator of the Burro Mountain Copper Co., 1917.

	Quantity (short tons, dry weight).	Average assay (per cent of copper).
Ore milled	451,398	2.387
Concentrates produced	63,595	12.074
Tailings produced	.....	.729
Saving	.....	71.25

Leaching operations on the old dump at No. 2 shaft yielded 280,090 pounds of copper, or about 25 per cent of the original content. Experiments were planned to determine the practicability of leaching ores below milling grade.

Lordsburg district.—The Lordsburg district, in central Grant County, has been a steady producer of copper for several years.

The Eighty Five Mining Co. was the largest producer.

Copper produced (mines report) in Lordsburg district, N. Mex., 1906–1917.

	Pounds.		Pounds.		Pounds.
1906	213,000	1910	1,628,000	1914	2,615,000
1907	463,000	1911	2,455,000	1915	3,890,000
1908	259,000	1912	3,156,000	1916	4,755,000
1909	590,000	1913	1,601,000	1917	4,262,000

Other districts that made notable production in 1916 were the Oro Grande and the Magdalena.

TENNESSEE.

The production of blister copper in Tennessee in 1917 was 16,093,757 pounds, compared with 14,556,278 pounds in 1916.

The entire output came from the Ducktown district, in the extreme southeastern part of the State, in Polk County. The district was one of the earliest large producers in the country. Operations began about 1850, and from that date till the end of the Civil War there was a large production from the "black copper" ores. With the exhaustion of the rich secondary deposits attempts were made to work the lean original sulphides. These efforts met with only indifferent success, and in the late seventies the smelters shut down, thus

Digitized by Google

ending the first period of activity in this district. The present period of activity began in 1890, when the Ducktown Sulphur, Copper & Iron Co. began operations. Since that time the district has been a steady producer from the primary sulphide ores. To the end of 1917 the total output of the district has been 336,059,000 pounds.

Metals produced (smelter figures) in Ducktown district, Tenn., 1906–1917.

Year.	Ore treated.	Copper produced.	Average yield of copper.	Gold and silver per ton of ore.
	Short tons.	*Pounds.*	*Per cent.*	*Cents.*
1906	538,141	17,909,442	1.7	8
1907	558,487	19,475,119	1.77	7
1908	618,806	19,710,108	1.55	5
1909	576,680	19,207,747	1.66	6
1910	552,796	16,691,777	1.52	8
1911	581,974	18,965,143	1.62	11.7
1912	603,229	18,396,256	1.53	10.5
1913	652,253	19,489,654	1.476	11.2
1914	653,621	18,661,112	1.435	9
1915	623,534	18,205,308	1.45	9
1916	482,495	14,556,978	1.52	14
1917	589,004	16,093,757	1.37	15

A part of the copper has been marketed without refining and without recovering the gold and silver contained. This accounts in large part for the variation in the gold and silver recovered per ton of ore treated.

The fact that the ores can be extracted with little timbering, the cheap supply of coke and coal from Tennessee and West Virginia, and the comparatively low cost of labor have made it possible to mine and treat these low-grade ores at a profit.

The pyritic process of smelting is practiced successfully by both the Ducktown Sulphur, Copper & Iron Co. and the Tennessee Copper Co. The low-grade matte produced by the first smelting is resmelted and brought to a proper grade for conversion.

Sulphuric acid plants were operated by both companies. The successful operation of these plants has not only helped to solve the troublesome smelter-smoke problem but has added very materially to the revenue of the companies.

The companies of the district are limited in their output of copper by the fact that some sulphur fumes necessarily escape into the air and the volume that may be permitted to escape is limited by order of the courts.

Copper and acid produced by Tennessee Copper Co., 1911–1917.

Year.	Ore smelted.	Copper.	Sulphuric acid, 60° Baumé.	Cost of copper per pound.	Dividends.
	Short tons.	*Pounds.*	*Short tons.*	*Cents.*	
1911	436,285	13,808,940	.....	10.88	$300,000
1912	444,289	13,252,634	192,084	11.00	500,000
1913	470,135	13,493,140	197,712	11.34	750,000
1914	485,051	12,871,113	210,163	11.84	600,000
1915	475,301	12,750,418	210,666	10.53	600,000
1916	385,188	9,404,295	181,637	14.36	150,000
1917	457,902	10,547,708	262,857	14.90	.....

Digitized by Google

The company's reserves of ore in the Burra Burra, London, and Polk County mines at the end of 1916 were estimated at 3,485,713 tons.

Copper and acid produced by Ducktown Sulphur, Copper & Iron Co., 1913–1915.

Year.	Ore treated.	Copper.	Sulphuric acid, 60° Baumé.
	Short tons.	*Pounds.*	*Short tons.*
1913	182,000	5,992,000	.....
1914	169,000	5,863,000	45,770
1915	150,400	5,370,000	41,295

The Ducktown Co. estimated at the close of 1915 that its ore reserves at the Mary mine amounted to 1,000,000 tons, averaging not less than 2 per cent of copper and 17 per cent of sulphur. The East Tennessee mine was reported as capable of producing 30,000 tons of ore, averaging in excess of 2½ per cent of copper and 8 per cent of sulphur. The Isabella mine had reserves of 2,500,000 tons, averaging 29 per cent of sulphur and 0.8 per cent of copper.

The district is served by a branch line of the Louisville & Nashville Railroad, with which the mines and smelters of the companies are connected by private line.

UTAH.

In 1917 Utah produced 227,840,447 pounds of blister copper, compared with 232,335,950 pounds in 1916.

The first recorded production of copper from Utah was in 1870, but the State did not become a large copper producer until about 1900. Since that time the growth of the industry has been steady and rapid. The total recorded output from the State to the end of 1917 is 1,877,572,042 pounds, or 7.45 per cent of the output of the United States since 1845. In 1917 Utah produced 12.08 per cent of the output. In total output and in the production for 1917 it ranks fourth among the copper-producing States.

Two copper-smelting plants were operated in the State during 1917, the Garfield smelter, at Garfield, and the International smelter, at Tooele.

Bingham district.—The presence of copper minerals in the Bingham district has been known since the early days of mining in the district, but for many years operations were confined to the production of lead, silver, and gold, and not until 1896 did the mining of copper ore become of commercial importance. To the end of 1917 the district has produced approximately 1,598,500,000 pounds of copper, or 6.34 per cent of the output of the country since 1845. For 1917 the district yielded 11.89 per cent of the total production. In total output the district ranks fourth among those of the country and in the production for 1917 it ranks third.

Copper produced (mines report) in Bingham district, Utah, 1906–1917.

	Pounds.		Pounds.		Pounds.
1906	39,424,000	1910	113,726,000	1914	141,925,000
1907	45,432,000	1911	129,996,000	1915	176,593,000
1908	71,156,000	1912	116,622,000	1916	223,620,000
1909	92,560,000	1913	144,920,000	1917	225,412,000

Digitized by Google

The concentrating ore of the district is treated at the mills at Garfield and Lark. The ores and concentrates are smelted at the Garfield and International smelters.

Metals produced by Utah Copper Co., 1911–1917.

Year.	Ore milled.	Copper content.	Mill recovery.	Refined copper.	Gold and silver per pound of copper.	Cost per pound of copper.	Dividends.
	Short tons.	*Per cent.*	*Per cent.*	*Pounds.*	*Cents.*	*Cents.*	
1911	4,680,801	1.51	69.53	93,514,419	1.07	7.865	$4,703,022
1912	5,315,321	1.36	66.32	91,366,337	.95	9.024	4,729,747
1913	7,519,392	1.25	63.95	113,942,834	.64	9.498	4,747,710
1914	6,470,166	1.42	66.04	115,690,445	.75	8.131	4,827,885
1915	8,494,300	1.43	64.13	148,397,006	.62	6.61	6,904,082
1916	10,944,000	1.43	62.34	187,531,824	.65	6.95	19,493,880
1917	12,542,000	1.337	61.10	195,837,111	.70	10.95	23,555,105

Costs of mining and milling copper ore by Utah Copper Co., 1910–1917.

Year.	Ore.	Cost per ton.			
		Mining.	Transportation.	Milling.	Total.
	Short tons.				
1910	4,340,345	$0.4097	$0.2978	$0.4663	$1.1738
1911	4,680,801	.4479	.3078	.4168	1.1725
1912	5,315,321	.4233	.2848	.4158	1.1239
1913	7,519,392	.3288	.2797	.3676	.9761
1914	6,470,166	.3232	.2782	.3536	.9550
1915	8,494,300	.2441	.2781	.3402	.8624
1916	10,994,000	.2781	.2792	.3782	.9355
1917	12,542,000	.4446	.2794	.6930	1.4170

The leaching plant began operation late in the year.

The mills at Garfield treated an average of 34,362 tons of ore daily.

At the end of 1917 development had been carried on over an area of 226.3 acres, and ore estimated at 438,972,700 tons and carrying an average copper content of 1.46 per cent had been developed and partly developed. Of this ore 67,220,700 tons, carrying an average copper content of 1.428 per cent had been extracted prior to January 1, 1918, leaving ore reserves at that date of 371,752,000 tons, averaging 1.39 per cent copper.

Net income and proceeds of depletion for the year amounted to $28,695,495.80.

Copper, gold, and silver produced by Utah Consolidated Mining Co., 1911–1917.

Year.	Ore.	Copper content.	Gold per ton.	Silver per ton.	Copper.[a]	Dividends.
	Short tons.	*Per cent.*	*Ounce.*	*Ounce.*	*Pounds.*	
1911	162,522	2.891	0.0936	0.9815	9,162,023	$150,000
1912	159,143	2.146	.077	.828	6,506,814	450,000
1913	181,077	1.987	.056	.705	7,710,668	450,000
1914	153,345	2.509	.085	.996	7,584,391	600,000
1915	207,119	2.22	.075	1.02	8,936,092	600,000
1916	360,034	1.734	.052	.796	12,211,118	1,125,000
1917	226,536	1.797	.050	.764	7,968,165	1,050,000

[a] Includes copper derived from lead ores.

Digitized by Google

In recent years the Utah Consolidated Co. has been a large producer of lead ores, the yield in 1917 being 13,014,841 pounds. At the end of the year there was "in sight" in the mine 141,000 tons of copper ore, carrying 1.76 per cent of copper and averaging 0.05 ounce of gold and 0.65 ounce of silver per ton. The ore was shipped by aerial train to the International smelter.

The mines and mill of the Ohio Copper Co. were operated throughout the year.

Several other mines in the district yielded considerable quantities of copper and copper-lead ores, notably the Old Jordan mine of the United States Mining Co., the Yampa mine, the Bingham-New Haven mine, the Utah Apex, and other mines.

The district is served by a branch of the Denver & Rio Grande Railroad and by the Bingham & Garfield Railway, controlled by Utah Copper Co. interests, which connects the mines at Bingham with the mills at Garfield. Cable tramways are employed to considerable extent; the ores from the Utah Consolidated mines are delivered to the International smelter in this manner, and ores from other mines are delivered to the railroad over cable tramways.

Tintic district.—The production of copper from the Tintic district is largely incidental to the production of other metals. The quantity of ore in which copper is the most valuable metal constituent is relatively small. There has been a small output of copper from the district for many years, but no accurate statistics of the early output are available. It is estimated that to the end of 1917 the district has yielded 140,630,000 pounds of copper.

Copper produced (mines report) in Tintic district, Utah, 1906–1917.

	Pounds.		Pounds.		Pounds.
1906	7,322,000	1910	8,994,000	1914	5,290,000
1907	7,756,000	1911	10,922,000	1915	5,358,000
1908	5,708,000	1912	13,339,000	1916	7,107,000
1909	5,916,000	1913	9,262,000	1917	9,118,000

Beaver County.—The first notable production of copper from Beaver County came from the Horn Silver mine in 1889, and since that time copper has been produced from lead-silver ores and from small copper mines. The importance of the district as a copper camp dates from the starting of the mill in 1905 to treat ores of the Cactus mine. To the end of 1917 the district has yielded about 45,902,000 pounds of copper.

Copper produced (mines report) in Beaver County, Utah, 1906–1917.

	Pounds.		Pounds.		Pounds.
1906	5,406,000	1910	1,128,000	1914	1,512,000
1907	5,640,000	1911	3,739,000	1915	429,000
1908	5,706,000	1912	3,040,000	1916	3,204,000
1909	1,246,000	1913	3,137,000	1917	3,702,000

The largest output in recent years has been from the Cactus mine; other producers are the Horn Silver, O K, Old Hickory, Milford Copper, and other mines.

Tailings from the old Cactus mill were treated by a flotation plant in 1917.

Digitized by Google

Clifton district.—In the early part of the year the railroad was completed from Wendover to Gold Hill, in the Clifton district. The largest producer of this district was the Western Utah Copper Co., which shipped 32,023 tons of ore, of which 28,718 tons was copper ore and 3,305 tons was lead ore. The copper ore averaged 2.98 per cent of copper and 4.33 ounces of silver per ton. The lead ore averaged 5.62 per cent of lead and 7.98 ounces of silver per ton. A total of 70 ounces of gold, 150,767 ounces of silver, 371,418 pounds of lead, and 1,710,984 pounds of copper was produced. Other mines made small shipments.

Other districts.—Considerable copper has been produced in the Park City, Big Cottonwood, Little Cottonwood, Ophir, and Rush Valley districts, where the metals of chief value are lead and silver.

OTHER STATES.

Georgia.—In 1917 Georgia produced 930,691 pounds of copper. The productive area is adjacent to the Ducktown (Tenn.) copper district.

Oregon.—Oregon produced 1,105,097 pounds of blister copper in 1917, compared with 2,433,567 pounds in 1916. To the end of 1917 the State has a recorded output of 7,307,133 pounds of copper.

Vermont.—Vermont produced 102,522 pounds of blister copper, the largest production for several years.

Virginia.—Virginia produced 146,912 pounds of blister copper, principally from the Virgilina district.

Washington.—Washington produced 2,051,416 pounds of blister copper, as compared with 2,473,481 pounds in 1916.

Wyoming.—The production from Wyoming amounted to 2,019,767 pounds of blister copper, as compared with 1,784,351 pounds in 1916.

REFINERY PRODUCTION.

The refinery output of copper in the United States in 1917 was made by 13 plants, 9 of which employed the electrolytic method and 5 employed the furnace process on Lake Superior copper, the Calumet & Hecla plant employing both methods. Six of the large electrolytic refineries are on the Atlantic tidewater, and 5 Lake refineries are on the Great Lakes. Only 2 plants are located west of the Great Lakes—1 at Great Falls, Mont., and 1 at Tacoma, Wash. In addition to these refineries there are numerous plants in different parts of the country that make a considerable output from old copper, brass, and other alloys of copper. The output of the regular refining plants is in the form of casting, Lake, and electrolytic copper.

CASTING AND PIG COPPER.

Blister copper that is low in precious metals and sufficiently free from impurities for certain uses is refined by the furnace process and ordinarily cast into ingots. This copper is usually unfit for uses requiring a high-grade copper, such as electric transmission, brass manufacture, and rolling, but is suitable for copper castings, and a large part of it is put to that use. Lake copper excepted, a comparatively small percentage of the copper output carries so small a

Digitized by Google

content of precious metals that, together with the added value of electrolytic copper, it will not more than pay for the electrolytic refining of the copper; consequently the output of casting copper is small. Some blister or pig copper low in precious metals has been exported without further treatment and is probably consumed without electrolytic refining. A large percentage of the pig and casting copper shown in the table is from Arizona. Some of the districts produce a rather high grade of blister copper carrying a small amount of precious metals, and it is found profitable to market some of it without electrolytic refining. During 1917 the production of furnace-refined new casting copper amounted to 69,916,911 pounds and of unrefined pig and best select copper to 82,376,576 pounds.

LAKE COPPER.

By Lake copper, as the term is used in this report, is meant the output of the Lake smelters. A considerable portion of this output is refined electrolytically, but most of the electrolytically refined Lake copper is mixed with furnace-refined copper or is sold as some brand of Lake copper. Of the 268,508,091 pounds of copper produced by the Lake smelters, about 70,329,385 pounds were refined electrolytically, either to free the copper from impurities or to recover the silver content.

ELECTROLYTIC COPPER.

Under electrolytic copper, as shown in the accompanying table (p. 778), is included all new copper that was refined electrolytically, except that from the Lake district that was marketed as Lake copper. In 1917 the production of electrolytic copper from primary materials of domestic origin amounted to approximately 1,452,744,593 pounds, and from materials of foreign origin to 555,000,000 pounds, and in addition 66,337,771 pounds was produced from secondary sources—a total electrolytic production of 2,074,082,364 pounds for the year.

SECONDARY COPPER.

Under secondary copper is considered material recovered from remelting old copper, copper scraps, and copper recovered from the treatment of copper alloys or alloys that are treated without the separation of the copper. A canvass of plants producing secondary copper has been made by J. P. Dunlop, of the United States Geological Survey. Concerning the output of secondary copper[1] Dunlop says:

> The total quantity of secondary copper recovered in 1917, on the assumption that the brass remelted had an average copper content of 70 per cent, was 383,400 short tons, of which 39,558 tons (12,654 tons less than in 1916) was recovered by plants refining primary metals and the remainder by plants treating only secondary materials. The copper produced by smelters of the latter class includes 88,426 tons of pig copper, 31,340 tons of copper in alloys other than brass, and 224,000 tons of copper in remelted brass. These figures indicate an increase for 1917 of about 14,300 tons of pig copper, 14,400 tons of copper in brass, and about 17,800 tons in alloys other than brass. At least 188,500 tons was recovered from clean scrap made in the course of manufacture

[1] Dunlop, J. P., Secondary metals: U. S. Geol. Survey Mineral Resources, 1917, pt. 1, pp. 312–313, 1918.

Digitized by Google

of copper and brass ware, so that less than 195,000 tons was obtained from ashes, cinders, and scrap, or from material that had actually been used and discarded. From the reports received it is quite evident that there was an increase in the quantity of old scrap brass and copper smelted, and that there was a very large proportionate increase in the quantity of clean new scrap remelted. The reports from munition factories show enormous increase in the quantity of clean scrap remelted, and apparently there was a decrease in the quantity of scrap brass from other users. The quantity of scrap brass used amounted to 320,000 tons, and of this at least 205,000 tons was clean new punchings, filings, and clippings.

The value of the copper, both as metal and in alloys, is computed at the average yearly price of 27.3 cents, the average sales price of all marketable grades of new metal. This average sales price for 1917 includes the price for the latter part of the year, when a fixed price supplanted open market quotations.

According to the Bureau of Foreign and Domestic Commerce the exports for the calendar year 1917 of scrap brass and copper, fit only for remanufacture, were 4,149 tons of scrap brass and 535 tons of scrap copper, and the imports of scrap copper were 8,934 and of scrap brass 28,035 tons. Many railways sell or turn in the larger portion of their brass and copper scrap and other metal waste to dealers in part payment for new material, but the reports received show that the railways utilized in their own shops and foundries more than 18,820 tons of brass, in addition to 950 tons of copper and 1,120 tons of copper in alloys other than brass. The railway reports, however, frequently include alloys, termed brass, which should more properly be designated as bronze. There was only a very small increase in the quantity of copper alloys used by railways in 1917.

The production of copper from secondary sources in 1917 was equal to about 31 per cent of the refinery output of primary copper in the United States from all sources, or about 41 per cent of the primary copper smelted from domestic ore.

Secondary copper recovered in 1917.

	Short tons.
Copper from scrap, drosses, etc	88,442
Copper produced from alloys other than brass	31,400
	119,842
From new scrap	45,000
From old scrap	74,842
	119,842
Brass scrap melted:	
New clean scrap	205,000
Old scrap	115,000
	320,000
Copper content of brass scrap (averaging about 70 per cent copper):	
New scrap	143,500
Old scrap	80,500
	224,000
Total copper produced at secondary plants:	
From new scrap	188,500
From old scrap	155,342
	343,842

Digitized by Google

REFINED COPPER.

The total production of new refined copper in 1917 was 2,428,000,000 pounds, an increase of 169,000,000 pounds over that of 1916.

Primary and secondary copper produced by regular refining plants and imported in 1913, 1914, 1915, 1916, and 1917, in pounds.

	1913	1914	1915	1916	1917
Primary:					
Domestic—					
Electrolytic	[a]1,922,497,601	[a] 991,573,073	[a]1,114,345,342	[a]1,579,620,513	[a]1,452,744,593
Lake	155,715,286	158,009,748	[b] 236,757,062	269,794,531	268,503,091
Casting	22,603,040	21,506,325	21,555,129	12,469,050	69,916,911
Pig and best select	36,004,986	39,334,043	15,047,990	26,868,105	82,376,576
	[a]1,236,823,913	[a]1,210,423,189	[a]1,387,705,523	[a]1,888,752,199	[a]1,873,546,171
Foreign (electrolytic)	[a] 378,243,869	[a] 323,358,205	[a] 246,498,925	[a] 370,635,116	[a][c]555,000,000
	1,615,067,782	1,533,781,394	1,634,204,448	2,259,387,315	2,428,546,171
Secondary:					
Electrolytic	14,862,577	27,702,928	38,156,789	78,585,296	66,337,771
Casting	22,360,182	4,224,052	21,417,901	25,838,511	12,779,125
	37,222,759	31,926,980	59,574,690	104,423,807	79,116,896
Total output	1,652,290,541	1,565,708,374	1,693,779,138	2,363,811,122	2,507,663,067

[a] The separation of refined copper into metal of domestic and foreign origin is only approximate, as an accurate separation at this stage of manufacture is not possible.
[b] Some Lake copper was refined at seaboard plants and doubtless marketed under some brand other than Lake. This has been excluded from the Lake copper.
[c] Includes refined copper imported.

In addition to the secondary material treated by the regular refining companies, plants that treated secondary material exclusively produced a total of about 687,684,000 pounds of copper as copper and in brass and other alloys of copper, a total production of 766,800,000 pounds from secondary sources. Of this total at least 377,000,000 pounds was produced by remelting clean scrap produced in the manufacture of copper and brass articles.

If the output of plants treating purely secondary material is added to the production of the regular refining companies, the contribution from plants in the United States to the world's supply of copper for 1917 is found to be 3,195,000,000.

Refined copper produced in the United States, 1906–1917, in pounds.

Year.	From primary sources (domestic and foreign).				From secondary sources (copper and copper in alloys).
	Electrolytic.	Lake.	Casting and pig.	Total.	
1906	839,984,614	205,608,382	33,459,413	1,079,052,409	.....
1907	837,389,422	178,534,141	16,592,684	1,032,516,247	.....
1908	848,109,132	222,289,584	67,563,692	1,137,962,408	.....
1909	1,101,894,864	227,005,923	62,120,667	1,391,021,454	.....
1910	1,128,304,725	221,462,984	72,271,426	1,422,039,135	.....
1911	1,156,111,987	218,185,236	59,577,803	1,433,875,026	214,000,000
1912	1,274,935,371	231,112,228	62,056,879	1,568,104,478	275,000,000
1913	1,400,741,470	155,715,296	58,611,026	1,615,067,782	273,000,000
1914	1,314,931,278	158,009,748	60,840,368	1,533,781,394	255,764,000
1915	1,360,844,267	236,757,062	36,603,119	1,634,204,448	392,374,000
1916	1,950,255,629	269,794,531	39,337,155	2,259,387,315	700,000,000
1917	2,007,744,593	268,508,091	152,293,487	2,428,546,171	766,800,000

Digitized by Google

COPPER SULPHATE.

The production of hydrous copper sulphate or bluestone by the copper refineries of the United States in 1917 was 50,412,325 pounds, having a copper content of 12,731,000 pounds, compared with 55,622,345 pounds of bluestone, having a copper content of 14,043,315 pounds, in 1916.

STOCKS.

Stocks of copper January 1, 1906–1918, in pounds.

Year.	Refined copper.	Blister and material in process of refining.	Year.	Refined copper.	Blister and material in process of refining.
1906	118,224,028	110,000,144	1913	105,497,683	274,072,084
1907	46,497,181	135,310,239	1914	90,385,402	247,789,811
1908	125,745,796	175,254,659	1915	173,640,501	203,067,571
1909	121,876,759	234,013,843	1916	82,429,666	274,000,000
1910	141,486,244	266,754,808	1917	128,055,229	424,000,000
1911	122,803,656	245,218,530	1918	114,000,000	411,000,000
1912	88,372,195	219,864,749			

IMPORTS.

The quantity of copper in unmanufactured form imported into the United States in 1917 was 556,420,297 pounds, according to the records of the Bureau of Foreign and Domestic Commerce. The imports in 1916 were 462,335,980 pounds.

Copper imported into the United States in 1916 and 1917, in pounds.

1916.

Country.	Ore (copper content).	Concentrates (copper content).	Matte and regulus (copper content).	Unrefined black copper and copper in bars, pigs, or other forms.	Refined, in bars, plates, rods, or other forms.	Old and clippings for remanufacture.	Composition metal copper chief value.
United Kingdom	463	.....	567,134	1,554,649	1,937,184	203,072	37,560
Germany	.....	.....	.....	.....	.....	.....	.....
Spain	2,619,025	.....	40,186	550,290	.....	.....	.....
Canada	33,964,545	35,200	3,345,009	47,951,823	.....	5,542,454	271,379
Mexico	3,464,522	29,314,152	746,885	61,756,726	9,359	590,948	34,090
Chile	34,806,620	336	9,701,366	70,762,349	5,789,764	220,464	62,082
Cuba	38,400,758	2,131,480	308,902	.....	.....	1,071,902	215,780
Peru	3,301,624	.....	1,478,275	72,827,909	.....	37,685	27,275
Japan	60,002	.....	.....	9,192,410	336,047	.....	.....
Australia and Tasmania	500	.....	.....	.....	.....	.....	.....
Other countries	8,260,846	1,272,706	1,067,318	4,331,159	338,876	1,784,863	110,027
	124,878,905	32,753,874	17,155,075	268,927,315	8,411,230	9,451,388	758,193

1917.

United Kingdom	75,591	.....	174,546	.....	225	5,550	109,131
Germany	.....	.....	.....	.....	.....	.....	.....
Spain	371,902	.....	.....	.....	.....	.....	.....
Canada	31,126,511	33,951	.....	40,571,284	765,980	15,321,755	9,801
Mexico	4,929,250	31,592,982	3,736,059	40,213,831	425,532	215,350	4,339
Chile	28,447,728	169,142	15,289,999	162,227,104	4,074,784	158,468	34,659
Cuba	40,100,956	4,913,440	328,966	.....	8,590	650,282	186,934
Peru	4,644,455	472,232	768,898	100,302,275	.....	90,574	54,465
Japan	.....	607,554	.....	6,393,524	1,101,776	110	.....
Australia and Tasmania	.....	.....	.....	.....	.....	.....	.....
Other countries	6,804,139	493,231	750,475	5,890,018	375,071	1,451,505	29,873
	116,500,532	38,197,532	21,048,943	355,598,036	6,751,958	17,893,594	429,702

Digitized by Google

Copper (unmanufactured) imported into the United States, 1906–1917.

	Pounds.		Pounds.		Pounds.
1906	225, 593, 281	1910	344, 435, 771	1914	306, 350, 827
1907	252, 620, 054	1911	334, 607, 538	1915	315, 698, 449
1908	218, 705, 487	1912	410, 241, 295	1916	462, 335, 980
1909	321, 801, 114	1913	408, 778, 954	1917	556, 420, 297

EXPORTS.

The exports of metallic copper from the United States in 1917 amounted to 1,125,647,000 pounds, according to the Bureau of Foreign and Domestic Commerce. In addition the copper content of 67,721 long tons of ore, matte, and regulus was exported in 1917, compared with the content of 105,847 long tons in 1916. Exports of copper sulphate were 13,938,919 pounds in 1915, 19,469,565 pounds in 1916, and 29,068,748 pounds in 1917.

Domestic copper (ingots, bars, pipes and tubes, plates, and old) exported from the United States in 1913, 1914, 1915, 1916, and 1917, in pounds.

Country.	1913	1914	1915	1916	1917
United Kingdom	133,679,641	198,382,459	201,218,655	184,564,740	406,229,308
Austria-Hungary	34,648,205	26,989,548	.....	.....	.....
Belgium	7,102,120	5,429,717	.....	.....	.....
France	160,000,345	150,839,897	236,236,135	336,829,464	379,174,229
Germany	307,150,761	176,698,948	.....	.....	.....
Italy	41,568,713	67,415,944	107,101,156	113,764,478	180,931,526
Netherlands	178,940,289	126,001,150	4,018,841	5,853,306	2,046,982
Russia in Europe	7,907,672	8,731,272	37,430,402	49,658,437	71,659,157
Other Europe	14,357,014	45,634,229	56,013,517	30,700,473	13,937,302
Canada	35,982,207	24,221,498	24,128,098	45,850,582	53,554,632
Other countries	4,904,125	9,736,260	15,771,151	16,785,006	18,114,200
	[a] 926,241,092	840,080,922	[b] 681,917,955	[c] 784,006,486	[d] 1,125,647,336

[a] Includes sheets, rods, wires, etc.
[b] Does not include copper content of 311,442 pounds in concentrates and 1,556,186 pounds in ore.
[c] Does not include copper content of 965,940 pounds in concentrates and 4,818,828 pounds in ore.
[d] Does not include copper content of 821,477 pounds in concentrates, 5,135,818 pounds in ore, and 1,228,032 pounds in composition metal.

Copper exported from the United States, 1916–17.

	1916	1917
	Pounds.	*Pounds.*
Ore (copper content)	4,818,828	5,135,818
Concentrates (copper content)	965,940	821,477
Unrefined black blister and converter copper (bars, pigs, and other forms)	18,263,118	16,992,357
Refined in ingots, bars, rods, or other forms	716,616,763	1,030,779,328
Composition metal, copper chief value	.....	1,228,032
Old and scrap	815,825	1,070,389
Pipes and tubes	.....	[a] 7,260,833
Plates and sheets	24,843,435	42,664,931
Wire	23,467,345	26,879,498
	789,791,254	1,132,832,663

[a] Figures cover period beginning July 1.

Digitized by Google

Brass exported from the United States in 1917.

	Quantity (pounds).	Value.
Scrap and old	8,298,969	$1,758,384
Bars, plates, sheets, etc	328,346,666	101,521,426
Cartridge shells, empty		[a] 3,533,834
Pipes and fittings	[a] 916,895	[a] 402,167
Wire	[a] 1,804,741	[a] 729,768
All other manufactures of		131,945,530
	339,367,291	239,891,109

[a] For six months beginning July 1, 1917.

Sulphate of copper (blue vitriol) exported from the United States, 1913–1917.

Year.	Quantity (pounds).	Value.
1913	4,168,675	$211,753
1914	7,387,226	327,967
1915	13,938,819	680,966
1916	19,469,565	2,803,833
1917	29,068,748	3,038,380

The value of the copper exported is stated by the Bureau of Foreign and Domestic Commerce as $146,377,621 in 1913, $117,633,145 in 1914, $117,703,941 in 1915, $206,163,241 in 1916, and $338,723,756 in 1917.

Metallic copper exported from the United States, 1906–1917.

	Pounds.		Pounds.		Pounds.
1906	454,752,018	1910	708,316,543	1914	840,080,922
1907	508,929,401	1911	786,553,208	1915	681,917,955
1908	661,876,127	1912	775,000,658	1916	784,006,486
1909	682,846,726	1913	926,241,092	1917	1,125,647,336

Unmanufactured brass exported from the United States, 1913–1917.

Year.	Brass in bars, plates, sheets, etc.	
	Quantity (pounds).	Value.
1913	6,111,463	$933,949
1914	7,115,807	909,153
1915	66,272,144	12,435,782
1916	244,531,706	72,663,626
1917	328,346,666	101,521,426

CONSUMPTION.

The apparent consumption of refined new copper in the United States in 1917 was 1,316,000,000 pounds. In 1916 it was 1,430,000,000 pounds. The method employed in determining the quantity of

Digitized by Google

copper retained for domestic consumption is shown in the following table, which does not include stocks of copper held by consumers:

Apparent domestic consumption of refined new copper in 1913, 1914, 1915, 1916, and 1917, in pounds.

	1913	1914	1915	1916	1917
Total supply of new copper	1,615,067,782	1,533,781,394	1,634,204,448	2,259,387,315	2,428,546,171
Stock at beginning of year	105,497,683	90,385,402	173,640,501	82,429,666	128,000,000
Total available supply	1,720,565,465	1,624,166,796	1,807,844,949	2,341,816,981	2,556,546,171
Copper exported	a817,911,424	a840,080,922	a681,917,955	a784,006,486	a1,126,875,368
Stocks at end of year	90,385,402	173,640,501	82,429,666	128,055,229	114,000,000
Total withdrawn from supply	908,296,826	1,013,721,423	764,347,621	912,061,715	1,240,875,368
Apparent consumption	812,268,639	610,445,373	1,043,497,328	1,429,755,266	1,315,670,803

a Exports of pigs, ingots, bars, rods, pipes, tubes, plates, sheets, and wire, etc., reported by the Bureau of Foreign and Domestic Commerce.

If to the 1,316,000,000 pounds of new refined copper is added the 767,000,000 pounds of secondary copper and copper in alloys produced during the year, it is found that a total of about 2,083,000,000 pounds of new and old copper was available for domestic consumption.

Domestic consumption of new copper, 1906–1917.

	Pounds.		Pounds.		Pounds.
1906	677,434,937	1910	732,405,180	1914	610,445,373
1907	487,771,625	1911	681,753,279	1915	1,043,497,328
1908	479,955,318	1912	775,978,332	1916	1,429,755,266
1909	688,565,243	1913	812,268,639	1917	1,315,670,803

The figures as indicated above do not closely represent the copper that was manufactured in this country for domestic use. The actual domestic consumption for domestic use did not increase in 1915 and 1916 to the extent indicated but represents copper in munitions and other manufactured articles exported. In 1917 the manufacture of munitions for the allied armies was less but the consumption for our own military needs had greatly increased.

USES.

There are no data available showing the quantity of copper which entered the different industries, and the great changes due to the war render any estimate more uncertain than usual.

The following table shows the copper cast in different form in 1918. It will be noted that the total is not the same as the production of refined copper:

Copper cast in different forms in 1917.

Form.	Quantity (pounds).	Percentage.
Wire bars	934,826,000	39
Ingots	953,456,000	40
Cakes	204,493,000	9
Cathodes	123,455,000	5
Other forms	172,244,000	7
	2,388,474,000	100

Digitized by Google

A canvass of all the large users and many of the smaller users of copper in the United States was made to ascertain the quantity used in 1917 and the form in which it was first manufactured. This indicated that 722,524,000 pounds of copper were manufactured into 1,072,504,000 pounds of brass and bronze, and 753,047,000 pounds were used as copper, a total of 1,475,571,000 pounds of copper consumed, divided approximately equally between that used in alloys, mainly brass, and that used as copper.

The following tables show the form of first manufacture of the brass and copper:

First manufactured forms of brass and bronze produced in the United States in 1917.

Form of product.	Brass (pounds).	Copper content (pounds).
Sheets	476,186,000	318,649,000
Rods	279,374,000	177,584,000
Tubing	70,408,000	46,381,000
Castings	120,262,000	90,821,000
Wire	50,690,000	34,671,000
Other forms	75,584,000	54,418,000
	1,072,504,000	722,524,000

First manufactured product of copper produced in the United States in 1917.

Form of product.	Copper (pounds).	Form of product.	Copper (pounds).
Sheets and plates	153,162,000	Castings	3,236,000
Rods	178,322,000	Other forms	31,197,000
Tubing	43,006,000		
Copper and copper clad wire	344,124,000		753,047,000

PRICES AND COSTS.

The average price received for copper delivered by the producers in 1917 as reported by them to the United States Geological Survey and the price used by the Geological Survey in calculating the value of the copper output was 27.3 cents a pound. The average received by selling agencies for 2,584,000,000 pounds, as reported to the Geological Survey by selling agencies, was 27.3027 cents a pound.

The following table shows the average quoted price of copper at New York, as reported by the American Metal Market Co. and by the Engineering and Mining Journal:

Average monthly prices at New York per pound of electrolytic copper in 1913, 1914, 1915, 1916, and 1917, in cents, as reported by the American Metal Market Co.

Month.	1913	1914	1915	1916	1917	Month.	1913	1914	1915	1916	1917
January	16.755	14.45	13.71	24.10	30.26	August	15.68	12.415	17.22	27.36	27.13
February	15.27	14.67	14.57	27.46	35.23	September	16.55	12.085	17.70	28.26	25.45
March	14.925	14.335	14.96	27.44	35.74	October	16.54	11.40	17.86	28.64	23.50
April	15.48	14.34	17.09	29.31	32.19	November	15.47	11.74	18.83	32.22	23.50
May	15.63	14.13	18.60	29.81	32.32	December	14.47	12.93	20.35	33.84	23.50
June	14.85	13.81	19.71	27.49	32.57						
July	14.57	13.49	19.08	25.60	28.90	Average	15.52	13.315	17.47	28.46	29.19

Digitized by Google

Average monthly prices at New York per pound of electrolytic copper in 1913, 1914, 1915, 1916, and 1917, as reported by the Engineering and Mining Journal.

Month.	1913	1914	1915	1916	1917	Month.	1913	1914	1915	1916	1917
January	16.488	14.223	13.641	24.008	28.673	August	15.400	(a)	16.941	26.120	25.350
February	14.971	14.491	14.304	26.440	31.750	September	16.328	(a)	17.502	26.858	25.073
March	14.713	14.131	14.787	26.310	31.481	October	16.337	(a)	17.698	27.193	23.500
April	15.291	14.211	16.811	27.895	27.935	November	15.182	11.739	18.627	30.625	23.500
May	15.436	13.996	18.506	28.625	28.788	December	14.224	12.801	20.133	31.800	23.500
June	14.672	13.603	19.477	26.601	29.962						
July	14.190	13.223	18.796	23.865	26.620	Average	15.269	13.602	17.275	27.202	27.180

a Price not quoted.

At the beginning of the year copper was in the midst of an upward movement that had started about the middle of 1916, and with temporary recessions continued into March, 1917; an opposite movement then set in which with temporary recoveries continued until the price was fixed on September 21, 1917, by agreement between the copper producers and the War Industries Board. The maximum price of 23½ cents a pound f. o. b. New York was fixed for a period of four months.

The agreement was subject to the following conditions: First, that the producers of copper will not reduce the wages now being paid; second, that they will sell to the United States Government, to the public in the United States, and to the Allied governments at not above the maximum price; third, that they will take the necessary measures, under the direction of the War Industries Board, for the distribution of copper to prevent it from falling into the hands of speculators, who might increase the price to the public; fourth, that they will pledge themselves to exert every effort necessary to keep up the production of copper so as to insure an adequate supply so long as the war lasts.

This price and agreement was in force until July 2, 1918, when the price was advanced to 26 cents a pound. On March 21, 1917, the copper producers agreed to furnish to the Government for delivery over a period of 12 months 45,000,000 pounds of copper at an average price of 16⅝ cents a pound. As this transaction was represented through the press, it appears to have gained the general impression that all the needs of the Government were to be supplied at the same rate. When it was found that such was not the intention, the profuse praise that had been given to the copper producers changed in many instances to a very different tone. The adverse criticism to which the producers were subjected appears to have been entirely undeserved, as they evidently never intended to supply all the requirements of the Government at the price named, and indeed it would have been impossible for them to do so if they had so desired and intended.

In this connection it is of interest to note to what extent the price of copper had advanced over that of commodities in general during the period of the war. For this purpose a general index prepared by the United States Department of Labor is presented and compared with copper. The base is the average of the five-year period 1910 to 1914.

Digitized by Google

Year.	General index number.	Price per pound of copper calculated from general index.	Average actual price per pound received for copper.
1910	99	13.95	12.7
1911	97	13.67	12.5
1912	101	14.24	16.5
1913	102	14.38	15.5
1914	101	14.24	13.3
1915	102	14.38	17.5
1916	125	17.63	24.6
1917	178	25.10	27.3

It is apparent that during the period 1915 to 1917 the price of copper was high relative to the general advance in commodities. It is also apparent that the price agreed upon between the copper producers and the Government was considerably below the figure that is indicated by the general advance in commodities.

The average cost of producing copper in the United States for the years immediately preceding the war was probably 9 to 10 cents a pound, and the average selling price for the five-year period 1909 to 1913 was about 14 cents a pound. The average profit was therefore 4 to 5 cents a pound, or 40 to 50 per cent of the cost of production.

Shortly after the beginning of the war both costs and selling price advanced greatly, but the advance in the latter was much greater than in the former, resulting in very large profits. At the time that the maximum price was fixed at 23.5 cents a pound, September 21, 1917, the cost in several districts was exceptionally high owing to the labor troubles of the summer of 1917. Statistics of the cost at that time are not available, at least not to the writer, but it is safe to say that they did not exceed 15 to 16 cents a pound. This would mean that the average profit was 7.5 to 8.5 cents a pound, or considerably more than the pre-war profits a pound. Profits were also 50 per cent or more of the cost of production, which also compared favorably with pre-war profits.

REVIEW OF FOREIGN PRODUCTION.

The following brief notes on the production of copper from the principal sources outside the United States is intended to give a general view of the copper industry from a world standpoint.

NORTH AMERICA.

CANADA.

According to the report of the Department of Mines of Canada, the copper production of Canada for 1917 amounted to 109,227,332 pounds (49,545 metric tons) as compared with 117,150,028 pounds (53,139 metric tons) in 1916. Production in Canada, as in the United States, was affected by labor troubles and shortage of fuel and other supplies.

Digitized by Google

The production from Quebec, which is recovered from pyrite ores, was 5,013,000 pounds (2,273 metric tons) in 1917 and 5,703,000 pounds (2,586 metric tons) in 1916.

The production from Ontario in 1917 was 42,796,000 pounds (19,412 metric tons), and in 1916 it was 44,997,000 pounds (20,410 metric tons). The main production was from the nickel-copper ores of the Sudbury district, including a small output from the Alexo mine in Dundonald Township.

The Sudbury district contains large reserves of nickel-copper ore. In testimony before the Royal Ontario Nickel Commission in 1917, it was estimated that developed ore reserves amounted to perhaps 70,000,000 tons and this quantity has been largely augmented since.

The ores are reduced to matte in the district. The matte has been shipped to the United States and Wales for further treatment. The International Nickel Co. has recently constructed a refinery at Port Colborne and the British-American Nickel Corporation (Ltd.) has constructed a smelting and refining plant in the district.

The principal producing companies of the district are the Canadian Copper Co., a subsidiary of the International Nickel Co., the Mond Nickel Co. (Ltd.), and the British-American Nickel Corporation (Ltd.).

The British Columbia production was 59,007,565 pounds (26,762 metric tons) in 1917, compared with 65,379,364 pounds (29,655 metric tons) in 1916.

The district or division proportions of the output of copper in 1917 were as follows: Skeena division (Hidden Creek), 27,978,015 pounds (12,690 metric tons); Coast (Southern) district, 17,256,534 pounds (7,827 metric tons); Boundary-Yale district, 11,117,290 pounds (5,042 metric tons); Trail Creek (Rossland) division, 1,730,088 pounds (784 metric tons); Omenica division, 852,373 pounds (386 metric tons); and all others, 73,265 pounds (33 metric tons).

The Granby Consolidated Mining, Smelting & Power Co. produced from its Phoenix mine for the year ending June 30, 1917, 677,292 short tons (614,435 metric tons) of ore, from which there was removed an average of 13.52 pounds of copper, 0.177 ounce of silver, and 0.027 ounce of gold to the short ton. The cost of copper sold in 1917 produced from the Phoenix mine averaged 20.8 cents a pound.

Ore reserves at the end of the year were estimated at 3,274,996 short tons (2,971,056 metric tons), containing 17 pounds of recoverable copper and 75 cents in gold and silver to the ton. In addition there is estimated to be 300,000 short tons (272,158 metric tons), containing 9 pounds of recoverable copper and 60 cents in gold and silver to the ton.

The Grand Forks smelter produced 9,038,010 pounds (4,099 metric tons) of copper from Phoenix ores, 389,301 pounds (176 metric tons) from foreign ores, and 8,122,142 pounds (3,684 metric tons) from Anyox matte, a total of 17,549,453 pounds (7,960 metric tons) for the year ending June 30, 1917.

The Canada Copper Corporation (Ltd.) produced during 1917 from its Mother Lode mine 181,189 short tons (164,373 metric tons) of ore averaging 0.917 per cent of copper, 0.17 ounce of silver, and 0.038 ounce of gold to the ton.

Digitized by Google

The Greenwood smelter treated 203,478 short tons (184,594 metric tons) of material during the year, yielding 4,247,316 pounds (1,926 metric tons) of copper, 46,356 ounces of silver, and 9,592 ounces of gold.

Development of the Copper Mountain mine was continued and erection of a mill was begun, but it is not expected to be in operation before 1919. The estimates of ore developed at the mine are 10,000,000 short tons (9,071,940 metric tons) of assured ore and 2,000,000 tons (1,844,388 metric tons) of probable ore, averaging 1.74 per cent of copper and 20 cents in recoverable gold and silver to the ton.

The copper production of the Consolidated Mining & Smelting Co. of Canada (Ltd.) was greatly curtailed from inability to obtain a regular and adequate coke supply.

For the year ending September 30, 1917, the following production of gold-copper ore was made:

	Short tons.	Metric tons.
Center Star-War Eagle	47,896	43,451
White Bear	724	656
Le Roy	57,405	52,077
Emma	40,523	36,745

The capacity of the electrolytic copper refinery has been increased from the original capacity of 10 tons a day to 20 tons a day.

The Britannia Mining & Smelting Co. (Ltd.), operating at Howe Sound, is reported to have produced 18,000,000 pounds (8,164 metric tons) of copper in 1917. The new mill of this company has a much larger capacity than the old equipment. Ore reserves at the beginning of 1917 were reported as 6,462,000 short tons (5,861,034 metric tons) of developed ore, 6,752,000 short tons (6,125,414 metric tons) of probable ore, 4,616,000 short tons (4,187,635 metric tons) of possible ore, a total of 17,830,000 short tons (16,174,000 metric tons), with an estimated average yield of 1.97 per cent of copper.

The Hidden Creek mine of the Granby Consolidated Mining, Smelting & Power Co. produced 760,791 tons (690,189 metric tons) of ore averaging 2.08 per cent of copper, from which there was recovered an average of 33.62 pounds of copper per ton yielding a total of 25,580,630 pounds (11,603 metric tons) of copper, 269,231 ounces of silver, and 4,320 ounces of gold. The average cost of copper sold from this mine during 1917 was 11.5 cents a pound.

The total ore developed during the year ending June 30, 1917, was 11,756,000 short tons (10,665,043 metric tons) of high grade averaging 2.31 per cent of copper, 8,371,000 short tons (7,594,171 metric tons) of low grade averaging 0.65 per cent of copper, a total of 20,128,000 short tons (18,260,121 metric tons) averaging 1.61 per cent of copper. The quantity remaining June 30, 1917, was 9,882,000 short tons (8,964,950 metric tons) of high grade and 8,257,000 short tons (7,490,750 metric tons) of low grade, a total of 18,139,000 short tons (16,455,700 metric tons).

The Whitehorse district in southern Yukon produced 2,182,000 pounds (989 metric tons) of copper in 1917.

Manitoba contributed to the copper production in 1917 for the first time. The output of 3,388 short tons (3,073 metric tons) of ore was by the Mandy Mining Co., at Schist Lake, northwest of The Pas. Developments here and at Flim Flam Lake, a short distance farther

Digitized by Google

north, have indicated large bodies of ore, and with adequate transportation facilities this promises to become an important copper-producing area. Lack of transportation will prevent any very large production for some time.

MEXICO.

The production of copper in Mexico in 1917 was 112,403,736 pounds[1] (50,986 metric tons), an increase of 49,768,845 pounds (22,575 metric tons) over the output in 1916. The production was mainly from Sonora and Lower California. Conditions in the interior of the country were not favorable to production, though the American Smelting & Refining Co. started its smelters at Matehuala and Aguas Calientes; these smelters were operated at only partial capacity.

In Sonora the largest producers were the Cananea Consolidated Copper Co., at Cananea, and the Moctezuma Copper Co., at Nacozari.

The Moctezuma Copper Co. made a net production based on smelter returns of 38,186,451 pounds (17,321 metric tons) of copper, 2,677 ounces gold, 511,738 ounces silver, and 35,630 pounds (16 metric tons) of molybdenum. This was the largest production in the history of the company.

The concentrator treated 750,897 short tons (681,213 metric tons) of ore averaging 3.179 per cent of copper. The ratio of concentration was 4.811 into 1 and the recovery of copper was 81.19 per cent and gave a yield of 2.56 per cent. Plans are under way for extending the flotation plant and experiments in fine grinding were in process looking to a higher recovery from sand tailings.

Ore and concentrates are shipped to the Copper Queen smelter at Douglas for treatment.

The mines and smelter of the Cananea Consolidated Copper Co., at Cananea, operated till June when they were closed on account of difficulties with the Mexican Government and remained closed till December and did not resume full operations till early in 1918. This company when operating under normal conditions is capable of producing 60,000,000 pounds (27,215 metric tons) of copper annually and has large resources in copper ore.

The Compañía del Boleo, with mine and a smelter near Santa Rosalia, Lower California, operated throughout the year. In fact, operations of this company have suffered comparatively slightly throughout the revolutionary period. The company is capable of producing about 30,000,000 pounds (13,607 metric tons) annually. The final product of the plant is black copper and matte, which has been shipped to France and Great Britain for further treatment. In 1918, however, shipment of this material to the United States was begun.

CUBA.

The production of copper in Cuba in 1917, amounting to 23,589,220 pounds (10,700 metric tons), was derived mainly from two districts, the Santiago, near the east end of Cuba, and the Matahambre, near the west end.

[1] Report of Francisco Valdes, Director of Mexico Mint, Oct. 2, 1919.

Digitized by Google

The Santiago district was one of the first in America to produce copper, and the El Cobre mines of the Cuba Copper Co. had been extensively developed before the works were destroyed and the mines allowed to fill with water during the revolts in the seventies. The mine remained idle till after the Spanish-American War. It was finally unwatered in 1916 and vigorously developed. The shipping product is high-grade ore and concentrate, which is sent to the United States for treatment. The mine yields about 600,000 pounds (272 metric tons) of copper monthly.

The Matahambre mine, in the Province of Pinar del Rio, a few miles from the port of Santa Lucia, was discovered in 1913 and has been vigorously developed since that time. High-grade ore has been shipped from the port of Santa Lucia to the United States, and during 1917 a concentrator was under construction for treatment of the low-grade ore. The mine can produce approximately 2,000,000 pounds (907 metric tons) of copper monthly.

SOUTH AMERICA.

For more than a century the west coast of South America has been an important source of the world's copper supply, and from the fifties to the eighties in the last century it was the largest source. Following this period there was a decline in relative and actual production due to the exhaustion of the easily mined high-grade ores. The great advance in metallurgy in recent years has made it profitable to treat low-grade ores, and very large bodies of copper ore have been developed. There has been actually shown to be present in the ore body of the Chile Copper Co. more copper than is known to exist in any other single deposit in the world, and South America is second only to North America in its possibilities of producing copper.

CHILE.

Next to the United States, Chile was the largest producer of copper of the countries of the Western Continent. The production of copper in 1917 was 226,031,024 pounds (102,527 metric tons)—a record output. The production of copper in Chili dates back through the last century, for the third quarter of which it was the world's largest source of supply. For a time it declined in output, but in recent years has again become a very important source.

The two largest producing companies in 1917 were the Chile Copper Co. and the Braden Copper Co.

The Chile Copper Co. in 1917 produced 88,370,188 pounds (40,084 metric tons) of copper.

The average cost of production for 1917 was 19.92 cents a pound.

Digitized by Google

Summary of Chile Copper Co.'s operations, 1915–1917.

	Ore treated.		Percentage of copper in ore treated.	Percentage of net copper saving.	Copper produced (tons).
	Quantity (dry tons).	Daily average (dry tons).			
1915, 7½ months	[a] 567,367 [b] 625,394	[a] 2,488 [b] 2,743	1.71	66.87	[a] 4,964 [b] 5,472
1916, 12 months	[a] 1,581,020 [b] 1,742,748	[a] 4,320 [b] 4,762	1.74	77.15	[a] 18,736 [b] 20,653
1917:					
First quarter	[a] 534,231 [b] 588,879	[a] 5,935 [b] 6,543	1.88	83.32	[a] 10,217 [b] 11,263
Second quarter	[a] 672,571 [b] 741,371	[a] 7,390 [b] 8,147	1.68	82.90	[a] 10,212 [b] 11,257
Third quarter	[a] 660,578 [b] 728,151	[a] 7,180 [b] 7,915	1.72	76.46	[a] 7,946 [b] 8,759
Fourth quarter	[a] 768,176 [b] 846,755	[a] 8,349 [b] 9,204	1.77	83.50	[a] 11,708 [b] 12,906
Total, 1917	[a] 2,635,556 [b] 2,905,156	[a] 7,220 [b] 7,959	1.76	81.81	[a] 40,083 [b] 44,185

[a] Metric tons. [b] Short tons (2,000 pounds).

Summary of Chile Copper Co.'s operations, 1915–1917.

	Short tons.	Metric tons.	Average grade (per cent of copper).
Positive ore:			
Oxidized ore	232,900,000	211,286,280	1.89
Mixed ore	73,100,000	66,316,320	2.98
Sulphide ore	48,700,000	44,180,640	2.36
	354,700,000	321,783,840	2.18
Positive and probable ore:			
Oxidized ore	339,000,000	307,540,800	1.91
Mixed ore	151,000,000	136,987,200	2.98
Sulphide ore	210,000,000	190,512,000	1.84
	700,000,000	635,040,000	2.12

Mainly oxidized ores are now being treated. Mining is done by steam shovel and the copper is extracted by leaching with sulphuric acid solution and electrolytic precipitation. The electrolytic copper is refined and cast into commercial shapes before shipping. Electric power is generated at the coast, oil being used as fuel and the power transmitted to the mine and metallurgical plant.

Operations were considerably curtailed during September and October by a lack of oil due to the shortage of shipping. The present plant has a daily capacity of 10,000 short tons (9,072 metric tons) of ore. It was planned to enlarge this to 27,000 short tons (24,494 metric tons) capacity, but the difficulty of securing material has caused a temporary modification of the plan to 15,000 short tons (13,608 metric tons) daily, or an increase of 50 per cent.

Net surplus from operations in 1917 was $2,598,411.

The Braden Copper Co. produced 63,774,000 pounds (28,927 metric tons) of blister copper in 1917.

Digitized by Google

Summary of Braden Copper Co.'s operations in 1917.

Period.	Blister copper produced (tons).	Ore treated.		Percentage of copper in ore treated.	Concentrates produced (dry tons).	Percentage of net copper saving.
		Quantity (dry tons).	Daily (dry tons).			
First quarter	[a] 6,435 [b] 7,094	[a] 379,582 [b] 418,411	[a] 4,217 [b] 4,649	2.308	[a] 32,870 [b] 36,233	77.26
Second quarter	[a] 7,644 [b] 8,427	[a] 407,457 [b] 449,137	[a] 4,477 [b] 4,936	2.417	[a] 37,568 [b] 41,412	78.08
Third quarter	[a] 7,217 [b] 7,956	[a] 397,897 [b] 438,599	[a] 4,324 [b] 4,767	2.260	[a] 35,239 [b] 38,844	77.08
Fourth quarter	[a] 7,629 [b] 8,410	[a] 447,745 [b] 493,547	[a] 4,867 [a] 5,365	2.291	[a] 38,390 [b] 42,318	74.24
	[a] 28,925 [b] 31,887	[a] 1,632,681 [b] 1,799,694	[a] 4,473 [b] 4,931	2.319	[a] 144,067 [b] 158,807	76.61

[a] Metric tons. [b] Short tons (2,000 pounds).

Braden Copper Co.'s ore reserves as estimated by the company, 1917.

	Short tons.	Metric tons.	Average grade (per cent of copper).
Positive ore	149,192,000	135,346,982	2.42
Probable ore	90,000,000	81,648,000	1.88
	239,192,000	216,994,982	2.21

The net surplus from operations in 1917 amounted to $2,863,111.

The Andes Copper Mining Co., a subsidiary of the Anaconda Copper Mining Co., continued exploration of its properties in Chile. On account of war conditions it was not planned by the company to put them on a producing basis immediately. During 1917 drilling at the Potrerillos property developed 5,434,081 short tons (4,930,342 metric tons) of ore, averaging 1.54 per cent of copper, in addition to that previously developed reported as in excess of 100,000,000 short tons (90,720,000 metric tons) of profitable grade. Construction of the railroad to the property was in progress during the year.

The Santiago Mining Co., also a subsidiary of the Anaconda Copper Mining Co., continued development of the Lo Aquierre mines, situated about 20 kilometers from Santiago. By the summer of 1917 there had been developed 6,000,000 short tons (5,443,800 metric tons) of mixed sulphide and oxidized ore, averaging approximately 2.44 per cent of copper. It is believed that the ore body contains much more ore than has been developed, and it has been estimated as containing probably 16,000,000 short tons (14,516,800 metric tons).

The Anaconda Co. also has under option the Africana mine, which has some high-grade sulphide ore developed.

In addition to the larger operations mentioned, there are many smaller mines that make an important contribution to the total output of the country. Among the more important are the Central Chile Copper Co., with mines and smelters at Panulcillo, Ovalle, Coquimbo; the Poderosa Mining Co., with mines at Collahuasi, Tara-

Digitized by Google

paca, Chile; the Société des mines de cuivre de Catemou, at Estacion Chagres, Aconcagua; the Société des mines de cuivre de Naltagua, at El Monte; and numerous mines tributary to Valparaiso, Coquimbo, Guyacon, Antofagasta, Caldera, and Carrizal.

PERU.

Peru, like Chile, has long contributed to the copper production of the world and in recent years has been a large producer. The output for 1917 was 99,595,009 pounds (45,176 metric tons). The important districts are the Cerro de Pasco and the Morococha. At present the output comes mainly from two companies. The Cerro de Pasco Mining Co., operating at Cerro de Pasco, is the largest producer. The mine was one of the early large silver mines, and in recent years has been a large copper producer, yielding 61,000,000 pounds (27,669 metric tons) in 1915, 71,400,000 pounds (32,387 metric tons) in 1916, and 72,900,000 pounds (33,067 metric tons) in 1917. The mine is located at an elevation of more than 14,000 feet, which has rendered exploitation difficult and expensive. In 1917 ore reserves were estimated by the company as 3,000,000 tons (2,721,600 metric tons), containing 253,452,000 pounds (114,965 metric tons) of copper and 21,745,000 ounces of silver. The company owns coal mines that furnish fuel and coke for operating the plants.

The Morococha Mining Co., operating in the Morococha district, is a subsidiary of the Cerro de Pasco Co., and its ore is treated at the plant of the latter company.

The Sociedad minera Backus y Johnston del Perú has mines in the Morococha and Casapalca districts and mill and smelter at Casapalca, on the Peruvian Central Railroad. The production is about 2,000,000 pounds (907 metric tons) blister copper monthly.

In 1918 the Société des mines de cuivre de Huaron completed a smelter in the Cerro de Pasco district and began production.

In addition to the output of these companies, ore was shipped from Callao and other ports.

EUROPE.

SPAIN AND PORTUGAL.

The copper district of southern Spain, which extends into Portugal, has been an important source of the world's copper supply for many centuries, as far back as Phenician times. It is one of the world's largest deposits, and in spite of the fact that it has been productive for perhaps 3,000 years, the present rate of production can be maintained for many years to come. The ore is pyritic and valuable as a source of sulphur as well as copper. Some of the ore is smelted, some is leached of part of its copper content and shipped as sulphur ore, and pyrite containing some copper is shipped.

Digitized by Google

NORWAY.

Norway makes a relatively small production of copper, chiefly from pyritic ores which are exported for the manufacture of sulphuric acid. Some copper ore is smelted locally, the yield for 1913 to 1916 being about 2,740 short tons (2,485 metric tons) annually. The largest production is from the Sulijema deposits in the northern part of Norway.

GERMANY.

The production of copper from Germany is mainly derived from the copper-bearing shales that underlie a large area in central Germany. This has been an important source of copper for more than six centuries. Before the war, production was confined mainly to the Mansfeld district, where an important chemical industry was based on the mining of this ore. The ores mined averaged about 2½ per cent of copper. It is reported that since the war, the grade of ore mined has been greatly reduced and that material containing as little as 0.7 per cent of copper is being treated. Prior to the war the sulphur content of the ore was recovered and employed in the chemical industry. It is reported that under the stress of war conditions blast furnaces were installed and much of the low-grade material on the old dumps was treated. Before the war, the Mansfeld deposit yielded about 20,000 metric tons of copper annually, but the production has probably since been increased and very likely mines have been reopened that could not be profitably operated before the war.

Other mines of Germany before the war yielded from 2,000 to 3,000 metric tons of copper, mainly from Rammelsberg.

The present production of Germany is not known but has been estimated as high as 45,000 metric tons for 1917.

AUSTRIA-HUNGARY.

Austria-Hungary makes a small production of copper, which before the war amounted to 3,000 to 4,000 metric tons annually. The principal deposits are in northern Bohemia and in the Tyrol in Austria, though there are numerous deposits in Hungary that have yielded small quantities of copper.

ITALY.

Italy makes a small production of copper annually, varying in recent years from 1,000 to 2,500 metric tons. The largest production comes from northern Tuscany.

SERBIA.

The most important copper mines in the Balkans are in northern Serbia near Bor, in the Department of Timok. Before the war there were two smelting plants in northern Serbia, one near Bor and a small plant near Majdenspek. The production of Serbia was 7,000

Digitized by Google

to 8,000 metric tons annually. It is reported that when the Serbs were driven out of the district in 1915, they destroyed the works and flooded the mines. The Austrians reopened the mines, and the acute need of copper by the Central Powers has possibly resulted in a production in excess of that before the war.

RUSSIA.

Russia has long been a producer of copper, and for several years preceding the war the increase in annual output was rapid, though production did not equal the needs of the country. With the opening of the war there was a falling off in copper production due to labor shortage, and the Caucasus region, being in the zone of military operations, was seriously affected. Since the revolution the copper industry has of course suffered in common with others through the general disorganization, though the remoteness of the district from the great political centers was favorable to the industry. The recovery of the industry, of course, depends on the general restoration of organization in the country.

The output has come mainly from the Ural region, from the Caucasus region, and from the Spassky region in western Siberia. The production of the several regions as given by Hutchins[1] is shown in the following table:

Copper produced in Russia 1907–1916, by regions, in metric tons and long tons.

	Ural.	Caucasus.	Siberia.	Chemical and refining works.	Total.
1907	[a] 8,160	[a] 5,504	[a] 1,174	[a] 1,133	[a] 15,971
	[b] 7,418	[b] 5,004	[b] 1,067	[b] 1,030	[b] 14,519
1908	[a] 9,272	[a] 5,303	[a] 2,659	[a] 969	[a] 18,203
	[b] 8,429	[b] 4,821	[b] 2,417	[b] 881	[b] 16,548
1909	[a] 9,276	[a] 7,141	[a] 2,672	[a] 694	[a] 19,783
	[b] 8,433	[b] 6,492	[b] 2,429	[b] 631	[b] 17,985
1910	[a] 11,582	[a] 8,362	[a] 3,482	[a] 985	[a] 22,411
	[b] 10,529	[b] 7,602	[b] 3,165	[b] 895	[b] 22,191
1911	[a] 13,926	[a] 8,752	[a] 4,057	[a] 983	[a] 27,718
	[b] 12,660	[b] 7,956	[b] 3,688	[b] 894	[b] 25,198
1912	[a] 19,196	[a] 10,557	[a] 5,216	[a] 1,324	[a] 36,293
	[b] 17,451	[b] 9,597	[b] 4,742	[b] 1,204	[b] 32,994
1913	[a] 17,641	[a] 10,989	[a] 6,151	[a] 1,508	[a] 36,289
	[b] 16,037	[b] 9,990	[b] 5,592	[b] 1,371	[b] 32,990
1914	[a] 18,216	[a] 9,181	[a] 5,998	[a] 1,533	[a] 34,283
	[b] 16,560	[b] 8,346	[b] 5,453	[b] 1,394	[b] 31,753
1915	[a] 18,512	[a] 4,013	[a] 4,602	[a] 969	[a] 28,096
	[b] 16,829	[b] 3,648	[b] 4,184	[b] 881	[b] 25,472
1916	[a] 16,731	[a] 4,320	[a] 1,042	[a] 520	[a] 22,613
	[b] 15,210	[b] 3,927	[b] 947	[b] 473	[b] 20,557

[a] Metric tons. [b] Long tons (2,240 pounds).

The large producing companies in the Ural and Caucasus regions have both smelting and refining plants. The operations are largely financed by foreign capital. The developed ore reserves in the principal districts are not large as compared with the world's great copper districts but are sufficient to insure their productiveness for some years.

[1] Hutchins, J. P., Russia in 1917: Eng. and Min. Jour., vol. 105, p. 126, 1918. See also Ball and Low, A review of mining in Russia: Eng. and Min. Jour., vol. 103, pp. 404–418, 1917.

Digitized by Google

ASIA.

JAPAN.

Japan has long made considerable production of copper, but the output has rapidly increased in the last few years and it now stands second only to the United States in output. The production for 1917, including remelted, was 111,188 metric tons. Imports amounted to about 14,220 metric tons. Of the available supply, about 62,408 metric tons was exported and 63,000 metric tons consumed in the country. During the first years of the war more than half of the export was to Russia, but in 1917 Great Britain and France received most of the export, while smaller quantities were exported to China, British India, Russia, the United States, and other countries.

The entire output is smelted and refined in the country.

Kenzo Ikeda[1] gives the following list of smelting plants and their production:

Copper smelters in Japan.

Smelter and company.	Production of copper.	Annual capacity of blast furnace.	Smelter and company.	Production of copper.	Annual capacity of blast furnace.
Hitachi, Kuhara	[a] 15,422 [b] 17,000	[a] 362,880 [b] 400,000	Ikuno	[a] 3,175 [b] 3,500	.....
Ashio, Furukawa	[a] 14,515 [b] 16,000	[a] 108,640 [b] 120,000	Osaruzawa	[a] 2,722 [b] 3,000	.....
Besshi, Sumitomo	[a] 9,979 [b] 11,000	[a] 226,800 [b] 250,000	Ogoya	[a] 2,268 [b] 2,500	.....
Kosaka, Fujita	[a] 9,072 [b] 10,000	[a] 362,880 [b] 400,000	Others	[a] 9,072 [b] 10,000	.....
Inujima, Fujita	[a] 3,629 [b] 4,000	[a] 90,720 [b] 100,000		[a] 73,483	.....
Abeshiro	[a] 3,629 [b] 4,000	.....			

[a] Metric tons. [b] Long tons (2,240 pounds).

AUSTRALIA.

The production of copper in Australia during the war has not equaled that immediately preceding the war. This has been due to reorganization necessitated by war conditions. The industry before the war was largely under the control of German interests, which were eliminated. Before the war copper had been exported in various stages of manufacture. The shortage of shipping made it necessary to reduce the tonnage, and now practically all the copper is refined before exportation and many of the manufactured products of copper and brass, previously imported, are manufactured.

[1] Japanese copper production: Min. and Sci. Press, Oct. 27, 1917, p. 618.

Digitized by Google

Australia produced 39,860 metric tons of copper in 1917, divided as follows:

Copper produced in Australia in 1917, by States.

	Metric tons.
Queensland	19,367
South Australia	7,329
Tasmania	5,939
New South Wales	6,681
West Australia and Papua	544

AFRICA.

The production of copper in Africa in 1917 is estimated at about 36,288 metric tons. There has been a steady increase for several years due to the increased production from the Katanga region. The principal producing regions are the Katanga, Cape Colony, and Namaqua. The Kongo region produced about 29,700 tons of copper in 1917.[1] Operations in the Katanga region, the largest producing district, are described by the British vice consul at Elizabethville[2] as follows:

The blast-furnace process of extraction has been employed since 1911. The central smelting plant is at Lubumbashi, near Elizabethville, and at present consists of five blast furnaces, of which four are in continuous operation. Two additional furnaces are in course of construction, and will be ready for use soon. The completed plant will have a daily capacity of 100 tons of copper. The output of the furnaces during the first nine months of 1917 was 19,766 metric tons, as compared with 21,273 tons in the calendar year 1916 and 13,483 tons in 1915. It is estimated that the output for the year 1918 will be 40,000 tons.

Enormous quantities of ore have been proved of a lower grade than is possible to treat economically by smelting; and, after exhaustive experiments, a plant is in course of preparation for the treatment of these ores by leaching and the electrical deposition of the copper. This plant is to have a yearly capacity of 50,000 tons of copper. The program of expansion and development up to the year 1921 provides for an expenditure of £3,000,000.

From 1911 until the outbreak of war, the whole of the company's output was sold to Germany. Since the beginning of hostilities it has been sent to the United Kingdom. The company employs 450 Europeans and 7,000 natives. The scarcity of labor during 1917 was serious.

[1] Iron Monger Metal Market Year Book, London, 1918.
[2] Eng. and Min. Jour., August, 1918, p. 308.

Digitized by Google

GOLD, SILVER, COPPER, LEAD, AND ZINC IN COLORADO.[1]

(MINES REPORT.)

By CHARLES W. HENDERSON.

PRODUCTION.

GENERAL STATEMENT.

The total value of the gold, silver, copper, lead, and zinc produced in Colorado in 1917 was $42,084,668, a decrease of 14 per cent as compared with the yield in 1916. Of this total value, gold represented 37 per cent, with an output of $15,729,224, a decrease of $3,424,597, following a decrease of $3,261,123 in 1916. The value of the zinc output represented 29 per cent of the total, there being a decrease of 13,969,688 pounds in quantity and of $5,722,043 in value. The decrease in silver was 352,191 ounces in quantity, but an increase of $980,781 in value. The production of copper, which is mostly incidental to the recovery of other metals, was 8,122,004 pounds, a decrease of 502,077 pounds, but an increase of $95,783 in value. Lead decreased 2,924,075 pounds in quantity but increased $954,069 in value.

The number of mines producing metals in Colorado in 1917 was 715 deep and 33 placer mines, as compared with 825 deep and 27 placer mines in 1916. This decrease of 104 producing mines was chiefly in Boulder, Clear Creek, Gilpin, and La Plata counties.

ORE.

The output of ore sold or treated from Colorado mines decreased only 8,537 short tons in 1917, as compared with 1916.

During 1917 there were treated at amalgamating and cyaniding mills, with or without concentration equipment (including all the custom mills of the State), 1,487,304 short tons of ore, which had an average recovery of 0.372 ounce of gold and 0.269 ounce of silver per ton. From 1,487,304 tons of ore treated at amalgamation and cyanidation mills and from 699,094 tons sent to concentration and separation mills, a total to both classes of mills of 2,186,398 tons (81 per cent of the total quantity treated, as against 79 per cent in 1916) was produced 280,563 tons of concentrates—ratio, 7.79 to 1.

Crude ore shipped to lead and copper smelters amounted to 377,753 tons, averaging 0.23 ounce of gold and 11.25 ounces of silver per ton, and 0.73 per cent copper and 3.15 per cent lead. Crude ore to smelting and zinc oxide plants amounted to 124,555 tons, averaging 22.15 per cent zinc (original assay).

All classes of concentrates to lead and copper plants amounted to 163,171 tons, averaging 0.52 ounce of gold and 14.49 ounces of silver per ton, and 0.71 per cent copper and 11.65 per cent lead. Zinc and

[1] For discussion of the geology of the districts mentioned in the following pages the reader is directed to the bibliography given in Mineral Resources, 1912, pt. 1, pp. 704–705, 1913, and to U. S. Geol. Survey Bull. 507, The mining districts of the western United States, by J. M. Hill, with a geologic introduction by Waldemar Lindgren, 1912.

Digitized by Google

zinc-lead concentrates shipped to zinc and zinc-oxide plants amounted to 117,392 tons, averaging 40.69 per cent zinc. Crude ore and concentrates combined shipped to lead and copper plants therefore amounted to 540,924 tons, averaging 0.32 ounce of gold and 12.23 ounces of silver per ton, and 0.71 per cent copper and 5.72 per cent lead. Crude ore and concentrates combined shipped to smelting and zinc-oxide plants amounting to 241,947 tons carrying 31.08 per cent of zinc (original assay).

In 1917 there were 33 productive placers in Colorado, which yielded $661,028 in gold and 8,302 fine ounces of silver, valued at $6,841, a total of $667,869, as compared with $718,970 in 1916.

Mine production of gold, silver, copper, lead, and zinc in Colorado in 1916 and 1917.[a]

	Number of producing mines.	Ore.	Gold.		Silver.[b]	Copper.	Lead.	Zinc.	Total value.
			Placer.	Deep.					
		Short tons.			*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	852	2,697,243	$712,924	$18,440,807	7,656,544	8,624,081	70,914,087	134,285,463	$49,200,675
1917	748	2,688,706	661,028	15,068,196	7,304,353	8,122,004	67,990,012	120,815,775	42,084,668
Decrease, 1917	104	8,537	51,896	3,372,701	352,191	502,077	2,924,075	13,469,688	7,116,007

[a] A revised table showing the production of gold, silver, copper, lead, and zinc from the beginning of mining in Colorado to 1917 will be included in a separate chapter of Mineral Resources, "The history of Colorado mine production" (now in preparation).
[b] Includes placer production.

GOLD.

The total production of gold in Colorado in 1917 was 760,901.22 fine ounces, valued at $15,729,224, a decrease of 165,664.87 fine ounces and $3,424,597 in value, following a decrease in 1916 of $3,261,123.

The Cripple Creek district, with a decrease of $1,724,703, produced $10,394,847 in gold, a little less than in 1907, 1911, and 1913. The production from the Cripple Creek district represented 66 per cent of the State yield in 1917.

The San Juan region of Dolores, La Plata, Ouray, San Juan, and San Miguel counties, yielded $2,451,292, a decrease for the region of $589,983, following a decrease of $813,246 in 1916, a decrease of $115,336 in 1915 and a decrease of $101,826 in 1914. Lake County yielded $1,175,219, a decrease of $545,221, following a decrease of $525,712 in 1916. There were decreases of $52,458 in Boulder, $51,426 in Chaffee, $124,947 in Clear Creek, $56,172 in Gilpin, $24,918 in Gunnison, $21,023 in Mineral, $398,344 in Ouray, $116,941 in Park, $120,622 in San Juan, and $62,432 in San Miguel.

Siliceous and dry ore, which was 74 per cent of all the ore sold or treated, yielded 91 per cent of all the gold produced. Nearly 3 per cent came from lead ores, more than 4 per cent from placers, nearly 1 per cent from copper ores, and 1 per cent from lead-zinc ores.

The output of placer gold from 33 placers in 1917 was $661,028, a decrease of $51,896. Summit County, with 4 dredges and 8 hydraulic and sluice mines, produced 82 per cent; and 1 dredge and 1 sluice mine in Lake County produced 17 per cent of the placer yield. The greater part of the remainder came from hydraulicking in Park

Digitized by Google

County. There were also small placer yields in Chaffee, Clear Creek, Eagle, Gunnison, Moffat, and Montrose counties.

SILVER.

The yield of silver in Colorado in 1917 was 7,304,353 fine ounces, valued at $6,018,787, a decrease of 352,191 fine ounces in quantity, but an increase of $980,781 in value, following an increase of 628,572 fine ounces in 1916, a decrease of 1,768,093 fine ounces in 1915, and a decrease of 529,190 fine ounces in 1914.

Chaffee County for 1917 showed an increase of 45,786 ounces, Ouray an increase of 64,636 ounces, Pitkin an increase of 84,182 ounces, Saguache an increase of 27,057 ounces, San Juan an increase of 155,919 ounces, Summit an increase of 55,492 ounces, and there were also increases in Boulder, Gunnison, and Park. Lake County showed a decrease of 747,281 ounces, Gilpin a decrease of 13,968 ounces, La Plata a decrease of 13,863 ounces, Mineral a decrease of 12,439 ounces, and San Miguel a decrease of 32,677 ounces.

Siliceous and dry ores yielded 67 per cent of the total; lead ores, 16 per cent; lead-zinc ores, 13 per cent; copper ores, more than 2 per cent; copper-lead ores, nearly 2 per cent.

COPPER.

The output of copper in 1917 was 8,122,004 pounds, valued at $2,217,307, a decrease of 502,077 pounds, but an increase of $95,783 in value. Although copper is widespread in the ores of the State, there are strictly no producing copper mines in the State and the output for each year is mainly a valuable by-product of other ores.

Lake County was the leading producer of copper and yielded 27 per cent of the output; San Juan County was second, with 21 per cent; San Miguel was third, with 11 per cent; Chaffee was fourth, with 10 per cent; Clear Creek, Gilpin, and Dolores followed in order.

Siliceous and dry ores furnished 45 per cent of the output of copper; copper ores, 39 per cent; lead ores, 10 per cent; copper-lead ores, 2 per cent; and lead-zinc ores, 4 per cent.

LEAD.

The production of lead (in terms of lead in lead bullion and in leaded-zinc oxide) in Colorado in 1917 was 67,990,012 pounds, valued at $5,847,141, a decrease of 2,924,075 pounds in quantity but an increase of $954,069 in value.

Pitkin and Lake counties are the principal lead-producing districts in Colorado. In 1917 there were heavy decreases in Lake, Pitkin, Mineral, Chaffee, and Summit, and also decreases in Boulder and Ouray counties. San Juan County showed the most notable increase, and there were large increases in Dolores, Eagle, Clear Creek, and Gunnison.

In rank, Lake County was first, Pitkin was second, San Juan third, San Miguel fourth, Clear Creek fifth, and Eagle, Chaffee, Ouray, Dolores, Mineral, Summit, Gilpin, Gunnison, and Boulder followed in order. There was a notable decrease in quantity of lead ores produced and in the lead content, but a heavy increase of lead-zinc ores and a very appreciable increase of lead contained therein;

Digitized by Google

there was a decrease in quantity of dry ores and a corresponding decrease in lead content.

Lead-zinc ores furnished 39 per cent of the output of lead; lead ores, 30 per cent; dry and siliceous ores, 27 per cent; zinc ores, more than 1 per cent; copper ores, nearly 1 per cent; and copper-lead ores, nearly 1 per cent.

ZINC.

In 1917 the marketed zinc ores from Colorado contained 120,315,775 pounds of recoverable zinc (as zinc and oxide), valued at $12,272,209, a decrease of 13,969,688 pounds in quantity and of $5,722,043 in value.

Lead-zinc ores furnished 58 per cent of the total yield of zinc; zinc ores, 39 per cent; and dry and siliceous ores, 3 per cent.

Lake County, with a decrease of 16,531,234 pounds, produced 60,254,333 pounds, representing only 50 per cent of the output of zinc in the State in 1917, as compared with 57 per cent in 1916, with 69 per cent in 1915, and with 81 per cent in 1914. Leadville shipments of zinc carbonate ore were 69,238 tons carrying 19.84 per cent of zinc, and the lead-zinc and zinc sulphide ores sold or treated in Leadville amounted to 148,945 tons carrying 21.91 per cent of zinc.

The production of zinc in Eagle County was 23,715,412 pounds and in Summit County 19,868,814 pounds. The largest decreases were in Chaffee, Eagle, Lake, and San Juan counties. The largest increase was in Summit County, with also large increases in Dolores and Gunnison counties. Other notable increases were in Clear Creek, Ouray, Pitkin, and San Miguel counties.

Zinc and lead-zinc ore and concentrates as marketed in 1917 at the mine [a] or mine mill [a] in Colorado.

County and district.	Classification.	Quantity.	Estimated recoverable zinc.	Content of zinc.	Average assay of zinc.
		Short tons.	*Pounds.*	*Pounds.*	*Per cent.*
Chaffee (ore and concentrates), Gunnison (ore and concentrates), Hinsdale (ore), Pitkin (ore and concentrates).	Smelting ore and concentrates.	11,019	5,812,833	7,281,121	33.04
Lake	Concentrating and smelting zinc-lead sulphide ore and concentrates.	131,254	39,137,607	58,984,777	22.47
	Zinc carbonate ore	69,238	21,116,726	27,474,626	19.84
Clear Creek and Gilpin	Concentrating and smelting ore and concentrates.	4,796	3,294,520	3,893,449	40.59
Eagle and Summit	do	86,063	43,584,226	57,217,185	33.24
San Juan region: Dolores (ore), Mineral (concentrates), Ouray (ore), San Juan (concentrates), San Miguel (concentrates).	Smelting ore and concentrates.	15,575	7,369,863	9,151,143	29.38
		317,945	120,315,775	164,002,301	25.79
SUMMARY.					
Lake	Ore and concentrates	200,492	60,254,333	86,459,403	21.56
All other counties	do	117,453	60,061,442	77,542,898	33.01
		317,945	120,315,775	164,002,301	
Total carbonate ore	Crude ore	79,847	25,837,786	33,324,031	20.87
Total sulphide ore	Ore and concentrates	238,098	94,477,989	130,678,270	27.44

[a] The actual product shipped from the mine or mill in mining centers, and the ore purchased by (not the product made at) custom mills at Canon City, Pueblo, and Denver. For that ore concentrated at the mine, it was impossible to get the grade of ore into the mill, but the content of products was obtainable. This table illustrates what material an ore buyer for custom mills and smelters would have found in the various districts.

Digitized by Google

OUTPUT OF ORE AND METAL CONTENT.

Ore and metals produced in Colorado in 1917.

Source of production.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Placers		31,977.24	8,302			
Dry and siliceous ore	1,996,590	692,605.92	4,867,628	3,630,445	18,673,295	3,098,598
Copper ore	33,233	7,455.00	182,791	3,133,437	455,698	
Lead ore	103,081	19,220.68	1,167,167	784,684	20,688,207	
Zinc ore	140,455	522.63	19,525	20,496	1,000,413	47,582,031
Copper-lead ore	2,976	1,239.89	133,128	204,563	428,115	
Lead-zinc	412,371	7,879.86	925,812	348,379	26,744,284	69,635,146
Total 1917	2,688,706	760,901.22	7,304,353	8,122,004	67,990,012	120,315,775
Total 1916	2,697,243	926,566.09	7,656,544	8,624,081	70,914,087	134,285,463
Decrease	8,537	165,664.87	352,191	502,077	2,924,075	13,969,688

Placer output in Colorado in 1917.

County.	Sluice and hydraulic.		Dredges.		Total.	
	Gold.	Silver.	Gold.	Silver.	Gold.	Silver.
	Fine ounces.	*Fine ounces.*	*Fine ounces.*	*Fine ounces.*	*Fine ounces.*	*Fine ounces.*
Chaffee	8.85	1			8.85	1
Clear Creek	21.05	5			21.05	5
Eagle	2.56				2.56	
Gunnison	15.82	4			15.82	4
Lake	8.02	2	5,328.95	1,606	5,336.97	1,608
Moffat	114.12	5			114.12	5
Montrose	45.67	13			45.67	13
Park	263.69	30			263.69	30
Summit	275.75	69	25,892.76	6,567	26,168.51	6,636
Total, 1917	755.53	129	31,221.71	8,173	31,977.24	8,302
Total, 1916	854.26	147	33,633.44	9,042	34,487.70	9,189
Decrease	98.73	18	2,411.73	869	2,510.46	887

Content of dry and siliceous gold and silver ores sold or treated in Colorado in 1917.

County.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Boulder	14,102	3,056.70	97,329	14,071	72,066	
Chaffee	35,629	4,516.63	33,682	67,080	1,047,545	1,111,863
Clear Creek	54,741	11,758.96	253,365	403,501	2,042,736	35,000
Custer	5,603	325.04	82,252	79,006	175,949	
Dolores	188	.94	1,849	7,874	293	
Eagle	5,970	959.83	83,943	20,252	63,609	
Fremont	28		30	1,271		
Garfield	18	34.88	17			
Gilpin	31,761	15,075.43	69,781	199,968	454,519	141,490
Gunnison	1,378	58.98	8,319	15,266	12,199	
Hinsdale	66	19.19	3,371	365	6,872	
Lake	172,817	42,158.41	1,663,546	1,221,652	3,479,752	
La Plata	1,393	1,222.45	14,933	2,753	3,745	
Larimer	50	9.00	11			
Mineral	18,420	166.23	355,266	15,438	549,379	
Montezuma	124	129.21	188	2,538		
Ouray	82,668	4,301.40	773,193	62,882	1,523,869	
Park	1,190	163.36	5,348	781	34,697	
Pitkin	31,572	1.52	315,920	17,454	1,277,665	
Rio Grande						
Routt	60	51.08	1,313			
Saguache	2,222	74.24	27,931	68,866	47,316	
San Juan	48,511	7,050.50	137,505	499,484	1,535,644	
San Miguel	388,915	96,902.98	766,463	909,159	6,139,387	1,810,245
Summit	14,508	1,718.24	102,505	20,784	206,053	
Teller	1,084,656	502,850.72	64,568			
Total, 1917	1,996,590	692,605.92	4,867,628	3,630,445	18,673,295	3,098,598
Total, 1916	2,057,452	847,876.76	5,562,217	4,943,797	23,335,444	7,399,120
Decrease	60,862	155,270.84	694,589	1,313,352	4,662,149	4,300,522

Digitized by Google

Content of copper ores sold or treated in Colorado in 1917.[a]

County.	Ore.	Gold.	Silver.	Copper.	Lead.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*
Baca	9	0.14	57	6,806	----------
Boulder	11	4.02	149	1,157	----------
Chaffee	8,492	33.03	6,639	679,580	2,535
Clear Creek	534	755.87	6,754	43,771	7,127
Custer	101	6.56	1,352	8,126	46
Dolores	5,965	127.33	40,454	469,135	21,069
Eagle	166	264.14	1,549	17,012	155
Fremont	401	28.54	634	58,586	----------
Gilpin	2,158	2,784.03	19,377	322,332	793
Gunnison	2,448	116.04	8,045	160,458	78,362
Hinsdale	23	1.44	291	3,183	492
Jackson	229	19.40	591	23,725	----------
Lake	7,888	2,491.08	32,265	855,952	201,648
La Plata	255	.52	391	23,042	----------
Moffat	15	----------	23	4,326	----------
Montrose	64	----------	653	21,275	----------
Ouray	1,219	106.53	8,564	105,537	35,211
Park	7	.05	6	1,205	----------
Saguache	786	91.68	27,437	43,408	29,742
San Juan	2,343	572.40	24,705	276,549	74,779
San Miguel	119	62.20	2,855	8,272	3,739
Total, 1917	33,233	7,455.00	182,791	3,133,437	455,698
Total, 1916	34,429	15,220.87	199,824	2,977,285	718,569
Increase or decrease	−1,196	−7,765.87	−17,033	+156,152	−262,871

[a] All smelting ore.

Content of copper-lead ores sold or treated in Colorado in 1917.[a]

County.	Ore.	Gold.	Silver.	Copper.	Lead.
	Short tons.	*Fine oz.*	*Fine oz.*	*Pounds.*	*Pounds.*
Clear Creek	650	826.82	14,747	61,660	119,752
Dolores	361	10.35	2,305	22,262	40,233
Gunnison	10	.29	282	851	1,091
Saguache	3	.32	132	204	583
San Juan	1,952	402.11	115,662	119,586	266,451
Total, 1917	2,976	1,239.89	133,128	204,563	428,115
Total, 1916	3,129	1,724.04	110,531	299,239	449,961
Increase or decrease	−153	−484.15	+22,597	−94,676	−21,846

[a] All smelting ore.

Content of lead ores sold or treated in Colorado in 1917.[a]

County.	Ore.	Gold.	Silver.	Copper.	Lead.
	Short tons.	*Fine oz.*	*Fine oz.*	*Pounds.*	*Pounds.*
Boulder	2,722	172.71	196,897	14,285	503,516
Chaffee	9,063	1,903.39	104,657	61,223	1,068,358
Clear Creek	3,019	1,106.77	77,993	61,159	964,665
Custer	177	10.22	5,083	1,084	52,306
Dolores	2,096	101.13	40,482	17,222	752,581
Eagle	2,502	144.66	11,194	989	550,783
Gilpin	1,370	1,349.62	23,427	22,348	360,594
Gunnison	384	70.62	10,388	1,836	185,084
Hinsdale	414	31.89	3,895	2,477	199,932
Lake	19,498	3,224.78	135,093	57,140	2,449,221
Ouray	1,537	81.29	85,729	10,513	463,333
Park	1,496	5,250.09	9,321	10,538	244,012
Pitkin	22,708	----------	163,285	2,058	5,767,314
Rio Grande	16	1.16	52	----------	1,930
Saguache	1,213	334.45	20,516	32,500	233,040
San Juan	31,985	4,258.26	246,467	483,750	5,272,169
San Miguel	259	266.68	10,046	2,994	62,200
Summit	2,602	912.96	22,642	2,268	567,167
Total, 1917	103,081	19,220.68	1,167,167	784,684	20,688,207
Total, 1916	159,247	22,687.40	1,159,615	356,620	27,427,529
Increase or decrease	−56,166	−3,466.72	+7,552	+428,064	−6,739,322

[a] Nearly all smelting ore.

Digitized by Google

Content of zinc ores sold or treated in Colorado in 1917.[a]

County.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Chaffee	2,304					1,013,079
Clear Creek	15		41			8,891
Eagle	39,282		352			12,539,191
Gunnison	5,100					2,631,712
Lake	86,768	522.57	18,584	20,313	996,399	26,867,505
Ouray	879					516,129
Pitkin	169					73,800
Summit	5,938	.06	148	183	4,014	4,031,724
Total, 1917	140,455	522.63	19,525	20,496	1,000,413	47,582,031
Total, 1916	151,497	330.62	58,722	6,349	589,991	52,873,099
Increase or decrease	−11,042	+192.01	−39,197	+14,147	+410,422	−5,291,068

[a] Nearly all smelting ore.

Content of lead-zinc ores sold or treated in Colorado in 1917.[a]

County.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Chaffee	144	2.16	1,556		32,085	56,990
Clear Creek	25,490	235.76	173,8[illegible]5		1,712,337	3,109,139
Dolores	5,416	12.43	3,132	3,423	958,0[illegible]5	1,701,353
Eagle	52,955	631.23	38,585	14,883	1,812,441	11,176,221
Gunnison	3,351	59.22	13,234	1,710	474,264	523,278
Hinsdale	14	2.43	164	74	2,320	4,117
Lake	135,457	3,117.41	327,904	27,566	10,174,782	33,386,828
Mineral	14,335	322.41	6,251	3,859	756,365	54,971
Ouray	220	1.48	611	621	9,308	16,665
Pitkin	70,375	3.56	182,840	7,891	7,307,544	497,994
San Juan	60,894	3,100.27	133,922	286,554	3,366,492	3,270,500
Summit	43,720	391.50	43,768	1,798	138,301	15,837,090
Total, 1917	412,371	7,879.86	925,812	348,379	26,744,284	69,635,146
Total, 1916	291,489	4,238.70	556,446	40,791	18,392,593	74,013,244
Increase or decrease	+120,882	+3,641.16	+369,366	+307,588	+8,351,691	−4,378,098

[a] Nearly all concentrating ore.

REDUCTION MILLS.

Mineral Resources for 1912, Part I, pages 650–664, contains a complete list of reduction mills in Colorado in 1912, with description of equipment and process. Changes of equipment have been noted in the volumes of Mineral Resources for each year since 1912 in the text relating to the several counties, and reference should be made to the report for 1912 and those following for complete information in regard to any particular mill.

Gold and silver produced at mills in Colorado, 1917.

County.	Ore to gold and silver mills.	Gold in bullion.	Silver in bullion.	Ore to concentrating mills.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Short tons.*
Boulder	2,671	1,010.53	746	9,375
Chaffee		67.10	28	36,081
Clear Creek	7,115	372.41	210	69,734
Custer		4.96	6	500
Dolores				604
Eagle		3.93	1	85,888
Gilpin	5,912	996.55	308	22,824
Gunnison				4,650

Digitized by Google

Gold and silver produced at mills in Colorado, 1917—Continued.

County.	Ore to gold and silver mills.	Gold in bullion.	Silver in bullion.	Ore to concentrating mills.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Short tons.*
Lake		1,179.17	562	123,597
Larimer	50	9.00	11	
Mineral				14,335
Ouray	47,480	600.05	560	31,624
Park	500	33.21	13	400
Pitkin			56	75,399
Routt	50	34.22	9	
San Juan	2,000	1,195.48	366	132,438
San Miguel	341,793	61,664.47	344,273	46,922
Summit	1,310	299.46	143	44,778
Teller	1,078,423	486,083.05	52,817	
Total, 1917	1,487,304	553,553.59	400,109	699,094
Total, 1916	1,442,139	581,177.76	536,753	702,200
Increase or decrease	+45,165	−27,624.17	−136,644	−3,106
Average content per ton		0.3722	0.2690	

Mine production of metals from Colorado concentrates in 1917.

By counties.

	Concentrates.	Gold.	Silver.	Copper.	Lead.	Zinc.
	Short tons.	*Fine oz.*	*Fine oz.*	*Pounds.*	*Pounds.*	*Pounds.*
Boulder	435	118.39	25,322	7,719	37,673	
Chaffee	3,669	4,444.85	33,522	66,779	1,047,488	1,202,060
Clear Creek	16,372	9,711.08	382,549	372,041	3,768,205	3,144,139
Custer	206	11.36	3,378	2,049	10,633	
Dolores	295	11.43	2,732	3,423	138,085	38,840
Eagle	44,235	631.23	38,585	14,883	1,812,441	20,793,848
Gilpin	5,943	10,942.04	43,303	126,496	385,745	141,490
Gunnison	2,027	103.89	20,898	16,092	483,961	523,278
Lake	85,109	2,820.86	309,960	27,566	9,102,787	29,347,782
Mineral	1,230	322.41	6,251	3,859	756,365	54,971
Ouray	7,290	3,508.59	677,237	45,518	1,232,726	10,270
Park	70	55.42	2,463	444	19,638	
Pitkin	25,133	2.24	208,953	7,891	7,464,954	281,280
Routt	7	5.49	229			
San Juan	22,682	11,584.63	377,028	1,090,936	8,576,936	3,270,500
San Miguel	29,527	35,156.18	416,756	899,627	6,121,542	1,810,245
Summit	30,229	427.22	46,069	1,223	163,274	15,763,287
Teller	6,054	7,793.10	5,508			
Total, 1917	280,563	87,650.41	2,600,743	2,686,546	41,122,473	76,381,990
Total, 1916	288,211	106,596.20	2,409,006	2,348,220	43,939,994	78,731,912
Increase or decrease	−7,648	−18,945.79	+191,737	+338,326	−2,817,521	−2,349,922

By kinds of concentrates.

Dry and siliceous	55,358	26,005.63	708,559	240,468	1,815,562	
Copper	1,021	882.45	18,021	125,236	55,261	
Lead	98,990	52,347.40	1,434,477	1,256,925	32,018,882	
Lead-copper	7,802	5,701.31	203,183	694,314	4,142,907	
Total to lead and copper plants	163,171	84,936.79	2,364,240	2,316,943	38,032,612	
Zinc	115,475	1,907.01	219,800	343,167	2,892,701	75,217,310
Lead-zinc	1,917	806.61	16,703	26,436	197,160	1,164,680
Total zinc and lead-zinc plants	117,392	[a] 2,713.62	[a] 236,503	[a] 369,603	[b] 3,089,861	[c] 76,381,990
	280,563	87,650.41	2,600,743	2,686,546	41,122,473	76,381,990

[a] Gold and silver recovered in zinc residues.
[b] Lead recovered in zinc residues and in leaded zinc oxide.
[c] Zinc recovered as metal and zinc in zinc oxide.

Digitized by Google

Mine production of metals from Colorado crude ore shipped to smelters in 1917.

By counties.

	Crude ore.	Gold.	Silver.	Copper.	Lead.	Zinc.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Baca	9	0.14	57	6,906	.....	.....
Boulder	4,789	2,104.51	268,307	21,794	537,909	.....
Chaffee	19,621	1,943.26	112,984	741,104	1,103,035	979,872
Clear Creek	7,600	4,600.69	143,986	198,050	1,068,412	8,891
Custer	5,381	325.50	85,303	86,167	217,670	.....
Dolores	13,422	240.75	85,490	516,493	1,634,136	1,662,513
Eagle	14,992	1,354.70	97,437	38,253	614,547	2,921,564
Fremont	429	28.54	664	59,857	.....	.....
Garfield	18	34.88	17	.....	.....	.....
Gilpin	6,553	7,270.49	68,974	418,152	430,161	.....
Gunnison	8,021	201.26	19,370	164,029	267,019	2,531,712
Hinsdale	517	54.95	7,721	6,099	209,616	4,117
Jackson	229	19.40	591	23,725	.....	.....
Lake	298,831	47,514.22	1,871,870	2,155,057	9,199,015	30,906,551
La Plata	1,648	1,222.97	15,324	25,795	3,745	.....
Mineral	18,420	166.23	355,266	15,438	549,379	.....
Moffat	15	.....	23	4,326	.....	.....
Montezuma	124	129.21	188	2,538	.....	.....
Montrose	64	.....	653	21,275	.....	.....
Ouray	7,419	382.06	190,300	134,035	798,995	522,524
Park	1,793	5,324.87	12,199	12,380	259,071	.....
Pitkin	49,425	2.84	453,036	19,512	6,887,569	290,514
Rio Grande	16	1.16	52	.....	1,930	.....
Routt	10	11.37	1,075	.....	.....	.....
Saguache	4,224	500.69	76,016	144,978	310,686	.....
San Juan	11,247	2,603.43	280,867	574,987	1,938,599	.....
San Miguel	578	411.21	18,335	20,798	83,784	.....
Summit	20,680	2,296.08	122,851	23,810	752,261	4,105,527
Teller	6,233	8,974.57	6,243	.....	.....	.....
Total, 1917	502,308	87,719.98	4,295,199	5,435,458	26,867,539	43,933,785
Total, 1916	552,904	204,304.43	4,701,596	6,275,861	26,974,093	55,553,551
Decrease	50,596	116,584.45	406,397	840,403	106,554	11,619,766

By kinds of ore.

Dry and siliceous	264,975	62,433.47	2,890,280	1,628,060	6,231,170	.....
Copper	33,233	7,455.00	182,791	3,133,437	455,698	.....
Lead	76,569	15,762.58	1,045,069	447,918	16,719,893	.....
Lead-copper	2,976	1,239.89	133,128	204,563	428,115	.....
Total to lead and copper plants	377,753	86,890.94	4,251,268	5,413,978	23,834,876	.....
Zinc	107,112	522.63	19,525	20,496	1,000,413	37,874,207
Lead-zinc	17,443	306.41	24,406	984	2,032,250	6,059,578
Total to zinc smelters and zinc oxide plants	124,555	[a] 859.04	[a] 43,931	[a] 21,480	[b] 3,032,663	[c] 43,933,785
	502,308	87,719.98	4,295,199	5,435,458	26,867,539	43,933,785

[a] Gold and silver recovered in zinc residues.
[b] Lead recovered in zinc residues and in leaded zinc oxide.
[c] Zinc recovered as metal and zinc in zinc oxide.

In 1917 Colorado mills consumed 3,800 pounds of quicksilver, 1 pound for every 74 tons of ore, or 1 pound for every 7.66 ounces of gold and 5.12 ounces of silver; also 135,680 pounds of potassium cyanide and 746,428 pounds of sodium cyanide. The cyanides combined were used at the ratio of 0.66 pound per ton of ore and tailings treated, and for every pound used there were recovered 0.59 ounce of gold and 0.43 ounce of silver.

Digitized by Google

Ore, concentrates, and tailings sent to amalgamation and cyanidation mills and gold and silver contained in bullion and precipitates in Colorado in 1917.

Process.	Quantity.	Gold in bullion.	Silver in bullion.	Quicksilver used.	Potassium cyanide used.	Sodium cyanide used.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	
Amalgamation	[a] 280,710	29,106.59	19,457	3,800		
Cyanidation	[b] 1,335,680	524,447.00	380,652		135,680	746,428
		553,553.59	400,109			

[a] Represents original crude ore; amalgamation in many cases followed by concentration.
[b] Represents original crude ore, concentrates, and tailings or slimes first treated by amalgamation and concentration. In the case of the Golden Cycle mill, where ore is crushed in cyanide solution and the greater part of the product is in the form of cyanide precipitates, a very considerable quantity of the gold is recovered on blanket tables by use of mercury; the amalgamation bullion is credited to cyanidation.

MINING INDUSTRY.

Despite the difficulties of high costs of labor and material, the lack of labor, and the constantly lowering content of ore, Colorado gold, silver, copper, lead, and zinc mines produced in 1917 metals valued at $42,084,668, a decrease of only 14 per cent as compared with the yield in 1916. There was decrease in quantity of all the metals produced, but the increased price for silver, lead, and copper was sufficient to show increase in gross value for these three metals. The year was the most disastrous ever encountered by the gold industry, the decrease for that metal being 18 per cent.

The Globe, Leadville, Pueblo, Durango, and Salida lead smelters were operated at reduced capacity on ore from Canada, Colorado, Idaho, New Mexico, and South Dakota and zinc residues from zinc retort smelters in Kansas and Oklahoma.

The United States Zinc Co.'s zinc retort smelter at Pueblo was continuously operated on zinc-lead-silver-gold ores from Arizona, Colorado, Idaho, Montana, and Nevada; and the wet-concentration, magnetic separation mill was also operated on low-grade zinc-lead ore and concentrates from Leadville, Red Cliff, and Telluride, Colo. The residues and lead and iron concentrates from this plant were treated at the Pueblo lead smelter. The Western Chemical Co.'s sulphuric acid, magnetic-separation, wet-concentration plant[1] at Denver was operated steadily, as was the Empire Zinc Co's 200-ton magnetic separation plant[2] at Canon City, both treated chiefly Leadville and Red Cliff zinc and zinc-lead sulphide ores. The Western Zinc Construction Co.'s zinc oxide plant[3] at Leadville was operated steadily throughout the year. The River Smelting & Refining Co. continued operations and experiments at Florence, in the treatment of low-grade lead-zinc-copper ores. Colorado mines also shipped cyanide precipitates and copper ore to the Omaha smelter and refinery, and copper ore was shipped to Utah plants. Lead bullion and copper matte from lead plants in Colorado were sent to the Omaha refinery and to refineries in the Eastern States. Zinc ores and concentrates were sent to Kansas, Oklahoma, Illinois, and Pennsylvania zinc-retort and zinc-oxide plants.

[1] For description see Colorado State Bur. Mines Thirteenth Bienn. Rept., for 1913–14, pp. 150–151, 1914.
[2] For description see Livingston, A. R., Colorado State Bur. Mines Thirteenth Bienn. Rept., for 1913–14, pp. 100–101, 1914.
[3] For description see Leslie, E. H., Zinc pigments and Leadville works: Min. and Sci. Press, Mar. 20, 1915, pp. 433–438; Met. and Chem. Eng., Sept. 15, 1915, pp. 631–633.

Digitized by Google

Smelting plants in Colorado in 1917.

City.	Plant.	Owner.	Class of ore.	Product.	Total furnaces.[a]
Denver	Globe	American Smelting & Refining Co.	Lead base[b]	Lead bullion and copper matte.	7.
Pueblo	Pueblo	do	do	do	7.
Leadville	Arkansas Valley.	do	do	do	10.
Durango	Durango	do	do	do	4.
Salida	Salida[c]	Ohio & Colorado Smelting & Refining Co.	do	do	4.
Pueblo	United States Zinc Co.	American Smelting & Refining Co.	Zinc, lead, copper, gold, silver.	Zinc and zinc dust.	1,944 retorts.
Ouray	Crawford[d]	Ouray Smelting & Refining Co.	Pyritic copper	Copper matte	2.
Florence	Florence (Old Rocky Mountain)[e]	River Smelting & Refining Co.	Zinc, lead, copper, gold, silver.	Zinc oxide, lead sulphate, matte.	Undergoing changes.
Leadville		Western Zinc Concentrating Co.	Zinc carbonate	Zinc oxide	14 fire boxes.
Vulcan	Vulcan[d]	Vulcan Mines & Smelting Co.	Copper	Copper matte	1.

[a] Not all used.
[b] Copper ores and copper in other ores are handled by occasionally turning a lead furnace into a copper furnace.
[c] Weeks, F. D., The Salida smelter: Am. Inst. Min. Eng. Bull. 104, pp. 1691-1695, 1915.
[d] Idle.
[e] Intermediate plant of River Smelting & Refining Co., Keokuk, Iowa, for production of electrolytic spelter.

The operations of the gold mines at Cripple Creek were increasingly difficult throughout the year, and many of the smaller mines closed. The large properties had to face the most difficult operating expenses, but they continued to operate. The Golden Cycle and Portland cyanidation mills, at Colorado Springs, which treated the bulk of the high-grade ore from the Cripple Creek district, were operated steadily, notwithstanding the increased costs of labor and supplies. The Portland-Victor cyanide plant was operated steadily on low-grade ore, and the Portland-Independence cyanide mill was remodeled and completed about the middle of the year and continued in successful operation treating an increasing quantity each month, with an average of 37,500 tons of low-grade material for the last three months. The production of gold from the Cripple Creek district decreased from $12,119,550, in 1916, to $10,394,847, in 1917.

Lake County (Leadville and outlying districts) produced gold, silver, copper, lead, and zinc having a gross value of $11,290,588, as compared with $16,082,059, in 1916. The Arkansas Valley lead smelter, the Western zinc oxide plant, and the Pingrey concentration-flotation plant, all at Leadville, were operated throughout the year. Smelting ores were also shipped to the lead smelters at Salida and Pueblo. The Empire Zinc Co.'s concentration magnetic-separation mill, at Canon City, was operated on Leadville zinc sulphide ores, as was the Western Chemical Co.'s wet concentration magnetic-separation sulphuric acid plant at Denver. Heavy shipments of all grades of ore were made from the Penrose shaft, unwatered in 1916, and various classes of ore were shipped from the unwatered Fryer Hill district. Zinc carbonate shipments were much less in quantity, but the quantity of zinc-lead sulphide ores were about the same as in

Digitized by Google

1916. The year saw the end of operations at the Tucson and Moyer mines drawing near, but the rehabilitation of the Mikado shaft and the Greenback mine. Operations were continuous at the Yak Tunnel properties, but Breece Hill mines did not yield the usual quota of gold-bearing ores. The dredge below Malta was operated during the dredging season, and gold ores were shipped from the Lackawanna Gulch district and zinc-lead and silver ores from the St. Kevin district.

Operations were continuous at Red Cliff (Eagle County), but the yield of zinc was not equal to the record in 1916.

The yield of placer gold from Summit County dredges and placers was not equal to the output in 1916, and the gold from lode mines decreased, but the quantity of silver increased appreciably and the quantity of zinc increased heavily, with a consequent gross value for the county for all metals in excess of the record production made in 1916.

Park County's production of gold decreased, but there was considerable new development work done, which may result in increased production in 1918.

The output in Pitkin County (Aspen) showed a small increase in quantity of silver, a decrease for lead, an increase for zinc, and an increase in gross value of all metals.

The output in Gunnison County continued to show increase for all metals except gold.

Chaffee County's various districts yielded an increased quantity of silver, but decreased quantities of all the other metals, and decreasing ore reserves point to a further decrease for 1918.

Custer County's shipments of silver ore in 1917 were more than twice those made in 1916.

Mining in the Bonanza district, Saguache County, resulted in an increase in the quantity of ores shipped to smelters.

In the San Juan region the Telluride district of San Miguel County and the Silverton district of San Juan County both maintained a steady and increased output, although the output of gold in both counties decreased. The revived Red Mountain district, Ouray County, made a small increase in the value of the metals produced, but the Sneffels district (with Camp Bird mill closed) did not make an output equal to that of 1916. The production of the Uncompaghre district, Ouray County, was almost the same as in 1916.

La Plata County's producing mines decreased in number from 30 to 21, and the yield for 1917 was even less than the yield in 1916. The quantity of copper and lead-zinc ores shipped from Rico (Dolores County) was more than twice that for 1916. Mineral County (Creede) showed decreases in gold, silver, and lead, and a small decrease in gross value of output.

Boulder County's production of gold decreased heavily, but the silver output was maintained at the same rate as in 1916.

Clear Creek County mines showed a heavy decrease in gold, but very appreciable increases in silver, lead, and zinc. Owing to the increased value of the metals and the increases in quantity of the lead and zinc produced, Gilpin County, notwithstanding decreases for gold and silver, showed a small increase in total gross value of production.

Digitized by Google

Mine production of metals in Colorado in 1917.

County.	Producing mines.	Ore sold or treated.	Gold.		Silver.	
			Quantity.	Value.	Quantity.	Value.
		Short tons.	*Fine ounces.*		*Fine ounces.*	
Baca	1	9	0.14	$3	57	$47
Boulder	60	16,835	3,233.43	66,841	294,375	242,565
Chaffee	29	55,652	6,464.06	133,624	146,535	120,745
Clear Creek	80	84,449	14,705.23	303,984	526,750	434,042
Custer	14	5,881	341.82	7,066	88,687	73,078
Dolores	8	14,026	252.18	5,213	88,222	72,695
Eagle	22	100,875	1,992.42	41,187	136,023	112,083
Fremont	7	429	28.54	590	664	547
Garfield	1	18	34.88	721	17	14
Gilpin	60	35,289	19,209.08	397,087	112,585	92,770
Gunnison	25	12,671	320.97	6,635	40,272	33,184
Hinsdale	13	517	54.95	1,136	7,721	6,362
Jackson	1	229	19.40	401	591	487
Lake	88	422,428	56,851.22	1,175,219	2,184,000	1,799,616
La Plata	21	1,648	1,222.97	25,281	15,324	12,627
Larimer	3	50	9.00	186	11	9
Mineral	12	32,755	488.64	10,101	361,517	297,890
Moffat	5	15	114.12	2,359	28	23
Montezuma	3	124	129.21	2,671	188	155
Montrose	4	64	45.67	944	666	549
Ouray	52	86,523	4,490.70	92,831	868,097	715,312
Park	20	2,693	5,677.19	117,358	14,705	12,117
Pitkin	11	124,824	5.08	105	662,045	545,525
Rio Grande	1	16	1.16	24	52	43
Routt	1	60	51.08	1,056	1,313	1,082
Saguache	26	4,224	500.69	10,350	76,016	62,637
San Juan	46	145,685	15,383.54	318,006	658,261	542,407
San Miguel	20	389,293	97,231.86	2,009,961	779,364	642,196
Summit	51	66,768	29,191.27	603,437	175,699	144,776
Teller	63	1,084,656	502,850.72	10,394,847	64,568	53,204
Total, 1917	748	2,688,706	760,901.22	15,729,224	7,304,353	6,018,787
Total, 1916	852	2,697,243	926,566.09	19,153,821	7,656,544	5,038,006
Increase or decrease	−104	−8,537	−165,664.87	−3,424,597	−352,191	+980,781

County.	Copper.		Lead.		Zinc.		Total value.
	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	
	Pounds.		*Pounds.*		*Pounds.*		
Baca	6,806	$1,858					$1,908
Boulder	29,513	8,057	575,582	$49,500			366,963
Chaffee	807,883	220,552	2,150,523	184,945	2,181,932	$222,567	882,423
Clear Creek	570,091	155,635	4,836,617	415,949	3,153,030	321,609	1,631,219
Custer	88,216	24,083	228,303	19,634			123,861
Dolores	519,916	141,937	1,772,221	152,411	1,701,353	173,538	545,794
Eagle	53,136	14,506	2,426,988	208,721	23,715,412	2,418,972	2,795,469
Fremont	59,857	16,341					17,478
Garfield							735
Gilpin	544,648	148,689	815,906	70,168	141,490	14,432	723,146
Gunnison	180,121	49,173	751,000	64,586	3,054,990	311,609	465,187
Hinsdale	6,099	1,665	209,616	18,027	4,117	420	27,610
Jackson	23,725	6,477					7,365
Lake	2,182,623	595,856	18,301,802	1,573,955	60,254,333	6,145,942	11,290,588
La Plata	25,795	7,042	3,745	322			45,272
Larimer							195
Mineral	19,297	5,268	1,305,744	112,294	54,971	5,607	431,160
Moffat	4,326	1,181					3,563
Montezuma	2,538	693					3,519
Montrose	21,275	5,808					7,301
Ouray	179,553	49,018	2,031,721	174,728	532,794	54,345	1,086,234
Park	12,824	3,501	278,709	23,969			156,945
Pitkin	27,403	7,481	14,352,523	1,234,317	571,794	58,323	1,845,751
Rio Grande			1,930	166			233
Routt							2,138
Saguache	144,978	39,579	310,686	26,719			139,285
San Juan	1,665,923	454,797	10,515,535	904,336	3,270,500	333,891	2,553,137
San Miguel	920,425	251,276	6,205,326	533,658	1,810,245	184,645	3,621,736
Summit	25,033	6,834	915,535	78,736	19,868,814	2,026,619	2,860,402
Teller							10,448,051
Total, 1917	8,122,004	2,217,307	67,990,012	5,847,141	120,315,775	12,272,209	42,084,668
Total, 1916	8,624,081	2,121,524	70,914,087	4,893,072	134,285,463	17,994,252	49,200,675
Increase or decrease	−502,077	+95,783	−2,924,075	+954,069	−13,969,688	−5,722,043	−7,116,007

Digitized by Google

REVIEW BY COUNTIES.

BACA COUNTY.

A carload of silver-copper ore was shipped from the Carrizo Creek district in the southwest corner of Baca County.

BOULDER COUNTY.

Mine production in Boulder County, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.	Silver.	Copper.	Lead.	Total Value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	
1916	81	33,011	$119,299	292,824	64,707	864,333	$387,534
1917	60	16,835	66,841	294,375	29,513	575,582	366,963
Increase or decrease, 1917	−21	−16,176	−52,458	+1,551	−35,194	−288,751	−20,571

Central district.—The production of the Central district (near Jamestown) was 1,401 tons of ore, carrying $4,934 in gold, 14,085 ounces of silver, 20,912 pounds of copper, and 170,896 pounds of lead, with a total value of $36,946, as compared with $48,395 in 1916. The only operations of importance were those on the Alice and Argo mines, where mining for fluorspar opened occasional pockets of lead-silver ore, some of which was shipped direct to smelters, and some was concentrated. Other mines from which production was made were the Copper Blush, Gladiator, Gold Nugget, New Rival, Rip Van Dam, Smuggler, Standard, Stanislaus, and Wano.

Gold Hill district.—The production of the Gold Hill district was 4,239 tons of ore, carrying $21,207 in gold, 5,318 ounces of silver, 608 pounds of copper, and 7,790 pounds of lead, with a total value of $26,425, as compared with $19,165 in 1916. For seven months the 50-ton Slide concentration mill was operated on dump ores from the Slide mine. Other producing mines were the Big Horn, Bonanza, Boulder Valley, Fairfax, Gillespie, Hoodoo, Nil Desperandum, Poorman, Scotia, Snowbound, and Victoria.

Grand Island (Cardinal, Caribou, Eldon) district.—The Grand Island district, revived in 1914, and the principal producing district in Boulder County in 1915, continued to produce in 1916 and 1917 at a reduced rate, the yield for 1917 being 4,892 tons, carrying $3,478 in gold, 33,997 ounces of silver, 1,579 pounds of copper, and 39,756 pounds of lead, with a total value of $35,325, as compared with $78,850 in 1916. The 100-ton concentration mill on the Caribou property was operated only two and one-half months and yielded a silver-lead concentrate. The shaft was completed from 980 feet to 1,040 feet. Other producing mines were the Beamer, Comstock, Congo Chief, Eureka group, Grant County, Monitor, Potosi, and Wigwam, at Caribou, and the Mogul Tunnel mine, at Eldora.

Digitized by Google

Magnolia district[1].—The Magnolia district in 1917 produced 85 tons of ore, carrying $1,890 in gold, and 46 ounces of silver, with a total value of $1,928, against $8,408 in 1916. Producing mines were the Graphic, Ke Ke Onga, Keystone, and Mountain Lion.

Sugar Loaf district.—The production of the Sugar Loaf district in 1917 was 3,883 tons, carrying $31,260 in gold, 63,085 ounces of silver, 5,850 pounds of copper, and 34,082 pounds of lead, with a total value of $87,770, as compared with $101,736 in 1916. The 150-ton cyanide plant of the United States Gold Corporation was operated for five months on company ore, and on custom ore from the Alpine Horn, and from the Herald mine. Some gold bullion from free-milling specimens, and smelting ore carrying a very good content of gold was shipped from the Logan mine. Shipments of silver-lead ore continued throughout the year from the Yellow Pine mine. Other producing mines were the Copper Glance, Doss, and Snowy Range.

Ward district.—The Ward district in 1917 continued to be the principal producing district in the county, with an output of 2,335 tons of ore, carrying $4,072 in gold, 177,864 ounces of silver, 564 pounds of copper, and 323,058 pounds of lead, with a gross value of $178,569, as compared with $130,722 in 1916. The principal producing mine was the White Raven, from which a large quantity of silver-lead ore was shipped. Other producing mines were the Celestial Extension, Golden Queen, Nelson, Sans Souci, and Sullivan No. 5.

CHAFFEE COUNTY.

Mine production in Chaffee County, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.[a]	Silver.[a]	Copper.	Lead.	Zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	35	69,358	$185,050	100,749	1,001,455	3,016,899	4,744,985	$1,341,695
1917	29	55,652	133,624	146,535	807,883	2,150,523	2,181,932	882,423
Increase or decrease, 1917.	− 6	−13,706	−51,426	+45,786	−193,572	−866,376	−2,563,053	−459,272

[a] Includes placer production.

Buena Vista district.—A small quantity of placer gold was recovered from gravels of Arkansas River, near Buena Vista.

Chalk Creek district.—The production from the Chalk Creek district, the most important in the county, comes almost entirely from one mine, the Mary Murphy.

The annual report of the general manager of the Mary Murphy Gold Mine Co. for the year ending December 31, 1917, says:

The year was a disastrous one for this company. Increased costs of operation, decreased tonnage, and lower value of product, all contributed to a result

[1] George, R. D., and Crawford, R. D., The main tungsten area of Boulder County, Colo.: Colorado Geol. Survey First Ann. Rept., pp. 7–105, 1909. (Reprint with additions, pp. 1–122, 1916.)

Digitized by Google

which has repeatedly been foreshadowed in former reports; but I must confess that the complete realization of these forebodings has surprised even myself; for I had always hoped that the unforeseen, in the form of new ore discoveries of importance, would step in to relieve the situation. It has not done so, and as a result I have to submit a balance sheet which shows a very heavy loss.

The mill was operated throughout the year at an average tonnage of a little more than 100 tons daily. Most of the time the ore supply permitted of operation on a two-shift basis only, which conduces neither to economy in operation nor to maximum saving.

The ore averaged extremely low in grade; and the zinc products marketed, owing to the continued fall in the price of spelter, were worth considerably less. Spelter is still higher in price than before the war; but because of the great increase in costs everywhere the present price is unremunerative.

In connection with the flotation department we have had to reconcile ourselves to a rather poor saving in order to maintain a high grade of product. It pays better to market a concentrate running 40 per cent zinc or better, and lose 2 per cent in the tailing, than to improve the extraction at the cost of a low-grade product. In this direction we have found that the pneumatic type of machine has a decided advantage.

The concentrating mill, power plant, and electrostatic separating plant are all in good condition and well supplied with spare parts and material. As heretofore, repairs and renewals have been charged to operating, and the cost of additions written off as depreciation * * *.

The quantity of development work performed during 1917 was less than in former years, and, speaking generally, the results were extremely disappointing.

Shortage of labor was very marked, especially during the summer; one of the results of this condition being that development plans had to be based less on the mining requirements than on the men available.

The costs of mining for the year showed further large increase. The average cost, compared with 1914, has increased 58 per cent, in spite of strenuous endeavors to hold it down. Even this does not tell the entire story, for the fall in grade of material supplied to the mill was undoubtedly contributed to by the poor quality of mine labor available, and the fact that attention was compulsorily concentrated on keeping the mill supplied, which always tends to react on the care exerted to mine the ore clean.

For the same reason—lack of efficient miners—we were unable to make any production of crude shipping ore mined on company account. This work requires careful and skillful hand-miners; a class of men which has ceased to exist in Colorado, excepting in small numbers in the older districts * * *.

Development in the Iron Chest leased property was disappointing, especially as to the lower levels. I regard this vein as evidencing impoverishment with depth in even more marked degree than is the case with the other veins of the Mary Murphy system.

Toward the end of the year we purchased, for the sum of $7,500, the Portland, Independence, and K. & P. claims, which cover the southerly extension of the Mary Murphy vein, between the Andy Crawford and the Stanley group. Work of extending south 1,400 adit level into this territory was immediately commenced, and some ore was developed. Unfortunately, it proved to be highly faulted and difficult to follow—at all events above the adit level. Below the latter it presents better probabilities than does most of the Mary Murphy vein at corresponding depth.

For a number of years past we have directed attention to the Pioneer and Mollie claims, owned by the Lady Murphy Mining Co., which adjoin the Mary Murphy claim on the north, and cover the extension of the vein in that direction. These claims had been leased to an association of miners and others at St. Elmo, who have spent a considerable sum in the attempt to make them productive, but without success. * * *

Finally, following the shipment of some of the ore to a new custom milling plant at St. Elmo, with results which completely disheartened the lessees, an opportunity has presented itself, since the first of the year, to lease the Lady Murphy property for a term of 10 years on an attractive basis. Some milling ore, which had long been exposed above the level of our No. 7 adit, is being mined, and we are extending north 1,400 adit through the Pioneer claim. So far, however, it has encountered no ore of workable grade, excepting for a few feet beyond our end-line.

Digitized by Google

This company, therefore, now owns or controls the entire known length of the Mary Murphy vein, for a length of a mile and a quarter, or, in other words, all the territory on Murphy Mountain which seems to merit the expenditure of capital for development.

The ore and mill products shipped during 1917, together with the corresponding figures for the period 1913 to 1916, were as follows:

	1913.		1914.		1915.		1916.		1917.	
	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity. (short tons).	Value.
Into concentration mill	34,271	.....	48,526	.....	55,880	.....	51,116	.....	35,566	.....
Lead concentrates	.....	.....	.....	.....	1,925	$168,484	1,587	$171,788	950	$113,025
Iron-copper concentrates	.....	.....	.....	.....	1,741	43,470	1,635	58,323	756	29,597
Zinc concentrates	.....	.....	.....	.....	4,700	327,570	3,971	227,459	1,754	73,956
Company concentrates	4,069	$160,126	6,137	$211,217	8,366	$539,524	7,193	$457,570	3,460	$216,578
Company bullion (ounces)	477	5,636	425	5,289	50	614	.....	.....	.....	189
Company crude ore	1,694	62,538	3,298	83,653	2,642	61,076	149	2,651	.....	.....
Tributers' crude ore	5,904	168,287	3,744	99,850	1,830	38,931	622	17,470	1,040	25,934

The enormous increase in cost of all supplies and provisions, together with the fact that it has been impossible to collect an increased charge for board from employees, has resulted in a serious and growing loss in operation of company boarding houses.

The operating costs, apart from work performed by lessees, are as follows:

Operating costs at Mary Murphy mine, Romley, Colo., 1913–1917, per ton.

	1913	1914	1915	1916	1917
Mining	$3.45	$3.08	$3.20	$4.11	$4.86
Milling	2.04	1.96	1.99	2.18	2.46
Tramways	.24	.13	.12	.16	.18
General expenses	.30	.21	.25	.34	.49
	6.03	5.38	5.56	6.79	7.99

The annual report of the general manager of the Mary Murphy Gold Mining Co. for the year ending December 31, 1917, says of the purchase of the Red Mountain mines:

After nearly two years spent in the search for new property, we finally decided on the acquisition of leases on an important group of old mines in the Red Mountain district, between Ouray and Silverton; including the Yankee Girl, Robinson, and Genesee-Vanderbilt. * * *

The mines named were old-time silver bonanzas in the period prior to 1894. The Yankee Girl, in particular, produced some of the richest silver ore ever mined in Colorado.

The ore occurs in vertical chimneys, the silver contents of which diminished when followed down to great depths. The areas explored are, however, a very small portion of the total. The chimneys heretofore worked are those which happened to outcrop at surface; and as at least three-fourths of the latter is covered with landslide material, the chances of finding further ore bodies of high-grade ore, especially in the neighborhood of the Yankee Girl and Robinson, are, in my opinion, excellent.

Some of the chimneys contain principally copper, others principally lead and zinc, in each case with silver and a little gold; while others again carry all

Digitized by Google

these metals in a complex mixture. A considerable tonnage of low-grade ore is already exposed; in fact, if this property were situated close to the Mary Murphy, the problem of ore-supply, which at the latter property is so difficult and insistent, would readily solve itself. While the nature of the ore bodies, and the method of working necessarily adopted, do not permit of ore being blocked out in advance, I believe that a sufficient number of such chimneys are exposed to permit an output of 75 tons of milling ore daily; mostly of such a nature that it requires the same complicated treatment as does the ore of the Mary Murphy. The mill under construction at the Genesee, however, will have a capacity of not to exceed 50 tons daily, and is of a simpler type. This may be overcome in part by shipping the more complex ore, or a zinc middling product from concentration to Romley for treatment if a sufficiently low freight rate can be obtained.

The Red Mountain mines are situated at an altitude of 10,700 feet, in a region where the winter snowfall is very great, so that considerable difficulties have to be faced. A narrow-gage railroad connects both the Joker and Genesee tunnels with the Denver & Rio Grande at Silverton; but on account of snow it is usually operated for only about six months each year.

The mines are wet, and the water acid and corrosive, so that in former times their operation was very expensive. This trouble has largely been removed by the driving of the Joker and Genesee tunnels, for while the Yankee Girl and Robinson have been drained for only a little more than one-half of their total depth, the water flow in the lower portion of the mine was relatively small. The value of silver is now higher, and that paid by the smelters for lead and copper double and four times, respectively, as compared with the time when the mines were closed down. Smelting and freight charges are less; and convenient and fairly cheap electric power is now available on the spot; so that, notwithstanding higher wages and lessened efficiency of labor, the economic conditions are now more favorable.

Small shipments were made from the Allie Bell and from the Flora Belle mine.

Cleora district.—The mines in the Cleora district were idle in 1917.

Cottonwood Creek district.—Small lots of ore were shipped from the Catalpa and from the Eureka Mountain mine.

Granite district.—A small car of silver-lead ore was shipped from the Yankee Blade mine. A small quantity of placer gold was sluiced from gravels along Arkansas River.

Monarch district.—From 12 mines 10,201 tons were shipped, carrying $19,061 in gold, 90,187 ounces of silver, 97,161 pounds of copper, 924,907 pounds of lead, and 979,872 pounds of zinc, with a total value of $299,389, as compared with $286,917 in 1916. The chief producing mine was the Madonna, from which a greatly increased quantity of lead oxidized ore was shipped, but a decreased quantity of zinc carbonate ore. Considerable zinc carbonate ore was shipped from the Giant-Eclipse mine. Other producing properties were the Bear and Half Moon group, Christmas, Clemo, Evening Star, Florence, Hawkeye, Jewel group, Silent Friend, and Wilson.

Riverside district.—A small lot of silver ore was shipped from the Hoffman mine and a car of lead-silver ore from the Harvard Tunnel mine.

Turret district (including Sedalia).—Lessees on the Independence mine shipped a considerable quantity of copper ore, and a large quantity of copper ore was shipped to smelter as well as considerable zinc ore to the custom flotation plant at Leadville from the Sedalia mine.

Digitized by Google

Mine production in Clear Creek County,[a] Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	100	94,220	[b]$428,931	[b]462,141	621,732	4,295,725	2,572,575	$1,527,096
1917	80	84,449	[b]303,984	[b]526,750	570,091	4,836,617	3,153,030	1,631,219
Increase or decrease, 1917.	−20	−9,771	−124,947	+64,609	−51,641	+540,892	+580,455	+104,123

[a] For discussion of geology see Spurr, J. E., and Garrey, G. H., Preliminary report on the ore deposits of the Georgetown mining district, Colorado: U. S. Geol. Survey Bull. 285, pp. 35-40, 1906; Economic geology of the Georgetown quadrangle (together with the Empire district), Colorado, with general geology by S. H. Ball; U. S. Geol. Survey Prof. Paper 63, 422 pp., 1906; Bastin, E. S., and Hill, J. M., Economic geology of Gilpin County and adjacent parts of Clear Creek and Boulder counties, Colo.: U. S. Geol. Survey Prof. Paper 94, 1917.

[b] Includes small placer production.

Alice (Yankee) district.—The Alice district in 1917 produced 240 tons of ore, carrying $1,562 in gold, 165 ounces of silver, 502 pounds of copper, and 6,116 pounds of lead, with a total value of $2,361, as compared with $1,333 in 1916. A small lot of gold ore from the Champion mine was treated in the Reynolds mill. Some ore from the Yukon property was milled at various custom plants in the district and at Idaho Springs, and a small lot of gold ore from the Gold Anchor mine was milled in the district.

Argentine district.—The Argentine district produced from four mines 3,504 tons of ore, carrying $18,052 in gold, 27,483 ounces of silver, 83,656 pounds of copper, and 412,791 pounds of lead, with a total value of $99,036, as compared with $112,302 in 1916, the only increase in quantity being for lead. Lessees on the Waldorf mill remodeled the mill on the property into a gravity-flotation-concentration mill, and most of the ore mined during the year was milled. A considerable quantity of lead, copper, and lead-copper ore was shipped from the Santiago mine direct to the smelter. Several cars of lead ore were shipped from the Josephine mine and a small lot of lead ore from the Kittie Owsley mine.

Empire (Upper Union) district.—The Empire district in 1917 from 5 mines produced 849 tons of ore, carrying $5,198 in gold, 8,830 ounces of silver, 1,432 pounds of copper, 58,931 pounds of lead, and 3,030 pounds of zinc, with a total value of $18,242, as compared with $13,396 in 1916.

The Bellevue-Hudson Co. shipped lead ore from the Anamosa and other properties to smelters and to the Argo mill, at Idaho Springs. The Golden Empire concentration mill, at Empire, was used to treat ore from the General Harrison and also from the Victor-Americus. From the Silver Mountain mine ore was shipped to the Argo mill. A small lot of lead ore was shipped to the Globe smelter from the Vera Cruz mine, in the Daily district, and in the same district a car of lead-concentrating ore was shipped from the property of the Grand & Clear Creek Co.

Geneva Creek (Collier Mountain) district.—A test lot of silver ore was shipped from the Silver Queen mine.

Digitized by Google

Georgetown (Griffith, Silver Plume) district.—The Georgetown district in 1917 produced from 22 mines 29,057 tons of ore, yielding $18,052 in gold, 212,500 ounces of silver, 17,879 pounds of copper, 2,127,523 pounds of lead, and 3,118,030 pounds of zinc, with a total value of $699,039, as compared with $592,955 in 1916.

The Capital Co., at Georgetown, operated its amalgamation and concentration mill for only a short period during the year, and lessees shipped several cars of lead and lead-copper ore to smelters. The Onondaga Mines Co., operating the Ruler and Comet mines through the Capital adit, shipped various lots of ore to several of the custom mills in the county. The Colorado Mining Co., controlling by bond and lease several properties long idle, including several large dumps at the mouths of the Equator tunnel, Marshall tunnel, and Ocean Wave tunnel, was occupied in building a 200-ton concentration and flotation mill, near Leavenworth Mountain, to be completed in 1918, and to be used first for the treatment of the dumps and later for any ores found or developed in the mines when reopened. The Midland Chief mill, at Georgetown, was operated for a short period. Several cars of silver-lead ore from the Kelly mine were shipped to the Hudson mill, at Idaho Springs, and several cars of ore from the St. George mine were shipped to the Argo mill, at Idaho Springs. Several cars of ore were also shipped from the Sceptre mine.

At Silver Plume there was a decided revival of mining and increased production. The Wasatch-Colorado concentration mill was actively operated on lead-zinc ores from the Mendota, Diamond, Phoenix, Mammoth, Dives-Pelican-Seven Thirty, and others. Lead-zinc-silver ore in quantity from the Smuggler mine was also treated at the Wasatch-Colorado mill for the first four months of the year, when the capacity of this custom mill become too small for the ores from its own mining operations and other ores offered, so that the Smuggler ore for the last eight months of the year was shipped to the Newton concentration mill at Idaho Springs. The Denbigh Silver-Lead Mining Co. opened up the Terrible mine and shipped some lead-zinc ore to one of the custom concentration plants.

Idaho Springs district.—In the Idaho Springs district are included the mines about Idaho Springs, including Banner, Cascade, Coral, Jackson, Lower Fall River, Payne's Bar, Spanish Bar, and Virginia Canyon subdistricts.

In 1917 the Idaho Springs district produced 40,839 tons of ore, as compared with 51,044 tons in 1916. Including $435 in placer gold and 5 ounces of placer silver, the production of metals in 1917 was $221,475 in gold, 260,346 ounces of silver, 424,186 pounds of copper, 1,979,360 pounds of lead, and 26,666 pounds of zinc, with a total value of $724,309, as compared with $698,604 in 1916. In 1917, of the 40,839 tons mined, only 1,030 tons were treated at amalgamation mills (having also concentration equipment) yielding only 68.58 fine ounces of gold and 37 fine ounces of silver in amalgamation bullion, and 34,457 tons were treated at mills for concentration only, a total to both classes of mills of 35,487 tons, yielding 8,518 tons of concentrates, carrying 7,903.68 fine ounces of gold, 185,625 ounces of silver, 336,086 pounds of copper, 1,548,378 pounds of lead, and 26,666

Digitized by Google

pounds of zinc. Crude ore direct to smelters amounted to 5,352 tons of ore, carrying 2,720.55 fine ounces of gold, 74,679 fine ounces of silver, 88,100 pounds of copper, and 430,982 pounds of lead.

At the mouth of the Argo tunnel, the Argo 20-stamp flotation custom mill was operated steadily on ores from both Gilpin and Clear Creek counties, both from mines worked through the tunnel and from the surface, and also on other custom from the Big Five tunnel, from Dumont, Lawson, Empire, and Georgetown. The Newton mill was operated steadily on custom ores. Other custom mills were the Hudson and the Jackson. Private mills operating were the Little Mattie and the Standard.

In Gilson Gulch, the Franklin mine continued operations by lessees, and several cars were shipped from the French Flag mine. Through the Argo (Newhouse) tunnel, the Gem Consolidated mines continued to be the principal producing property. Production from the Golden Edge mine also continued, and a small lot of ore was shipped from the Sun & Moon group. From mines in Gilpin County, operated from the Argo tunnel, an increased quantity of ore was milled at the Argo mill and at other mills in the district. The mines were the Tremont (formerly called Gunnell), Concrete, Ophir-Burroughs, and Pozo-Dyke. In the Virginia Canyon the producing mines were the Bald Eagle, Bellevue-Champion, Bismarck, Calvin, Comstock, Treasure Vault, and Windsor Castle. The Specie Payment mine, opened through the Two Brothers adit, in Virginia Canyon, was also operated. Through the Big Five tunnel, lessees operating the Edgar, Dove's Nest, and Lake shipped a large quantity of ore to various mills. On the south side of Clear Creek the Little Mattie mine and amalgamation mill continued to be operated, the Lord Byron mine was reopened and operated, and lessees shipped some ore from the Stanley mine. Up Fall River, the Standard mine and amalgamation-concentration mill were operated for a period, and several lots of ore were shipped from the Almaden mine. Up Chicago Creek, some production was made from the Chicago Mountain and from the Beaver mine.

A small quantity of placer gold was sluiced from the gravels of Clear Creek, near Idaho Springs.

Montana (Lawson Dumont) district.—The Montana district in 1917 from 9 mines produced 1,902 tons of ore, yielding $19,949 in gold, 9,938 ounces of silver, 30,518 pounds of copper, and 42,500 pounds of lead, with a total value of $40,123, as compared with $31,732 in 1916. A considerable quantity of gold-silver ore from the Albro mine was sent to an amalgamation-concentration mill at Idaho Springs, with product of gold-silver bullion and copper concentrates, and an appreciable quantity of gold-silver-copper ore was shipped direct to smelters. The 30-stamp (15 used) amalgamation-concentration Dumont mill was operated on ore from the Syndicate, Senator, and Cymric mines. Other producing mines were the Big Chance, Blue Bird, Drummond, Jo Reynolds, and Murray. At Lawson, near the mouth of the Commodore tunnel, the Little Giant Co. built during 1917 a wet concentration and flotation mill and made a test run.

Trail Creek (Lamartine and Freeland) district.—The Trail Creek district in 1917 from 6 mines produced 8,053 tons of ore, yielding

Digitized by Google

$19,692 in gold, 7,352 ounces of silver, 11,916 pounds of copper, 209,396 pounds of lead, and 5,304 pounds of zinc, with a total value of $47,552, as compared with $76,774 in 1916.

Lessees on the Lamartine mine operated the 50-ton amalgamation-concentration mill on the property. The New Era concentration mill was also operated, yielding gold-silver-lead concentrates. Lessees shipped various classes of ore from the Freeland, Toledo, and Turner mines. Concentrating and smelting ore was shipped from the Gum Tree mine. A care of ore was shipped from the Rochford tunnel mine.

CONEJOS AND RIO GRANDE COUNTIES.

Platoro-Gilmore-Summitville district.[1]—A small shipment of lead ore was made by lessees from the Guadalupe mine, near Jasper, Rio Grande County. On this property there was built a small mill, mainly used for experimentation.

In Conejos County, only development work was done in the Platoro district.

COSTILLA COUNTY.

Grayback district.[2]—The Grayback district has been idle for several years.

CUSTER COUNTY.[3]

Mine production in Custer County, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	14	2,245	$6,309	36,971	44,004	123,536	10,970	$51,455
1917	14	5,881	7,066	88,687	88,216	228,303	.....	123,861
Increase or decrease, 1917	.....	+3,636	+757	+51,716	+44,212	+104,767	−10,970	+72,406

The principal producing mine in Custer County was the Passiflora, near Silver Cliff. Most of the ore from this mine was shipped direct to smelters, the remainder being shipped as a concentrate product from experimentation in milling the ore. Other producing mines

[1] For discussion of the geology of the district see Hills, R. C., Ore deposits of the Summit district, Rio Grande County, Colo.: Colorado Sci. Soc. Proc., vol. 1, pp. 20–36, 1883. Raymond, R. W., Mines and mining west of the Rocky Mountains, vol. 10, p. 329, 1875. Emmons, W. H., The enrichment of sulphide ores: U. S. Geol. Survey Bull. 529, p. 226, 1913.

[2] For discussion of geology see Patton, Smith, Butler, and Hoskins, Geology of the Grayback mining district, Costilla County, Colo.: Colorado State Geol. Bull. for 1909. No. 2, 1910.

[3] For discussion of geology see Cross, Whitman, Geology of Silver Cliff and the Rosita Hills, Colo.: U. S. Geol. Survey Seventeenth Ann. Rept., pt. 2, pp. 263–403, 1896; and Emmons, S. F., The mines of Custer County: Idem, pp. 405–472.

Digitized by Google

were the Black Friday, Bismuth, King of the Carbonates, Lady Franklin, Last Quarter, Maverick, and Quartz King.

DOLORES COUNTY.

Mine production in Dolores County, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	13	6,398	$7,426	77,280	419,500	588,333	182,306	$226,497
1917	8	14,026	5,213	88,222	519,916	1,772,221	1,701,353	545,794
Increase or decrease, 1917	−5	+7,628	−2,213	+10,942	+100,416	+1,183,888	+1,519,047	+319,297

Lone Cone (Dunton) district.—The Emma mine in this district was idle.

Pioneer (Rico) district.[1]—All the production from Dolores County in 1917 came from this district. The ores shipped were chiefly copper ore, zinc-lead ore, and lead ore, in order of quantity. The copper ores were shipped both to Durango, Colo., and to smelters in Utah. The zinc-lead ore was shipped to Coffeyville, Kans. Some iron sulphide ore (for its iron content only) was shipped to Vanadium, Colo., for use in the treatment of vanadium ores.[2]

The company and lessees on the Rico-Argentine property shipped large quantities of copper ore and also a considerable quantity of zinc-lead ore. The net smelter returns from ore shipped in 1917 from this property amounted to $47,576 for company shipments and $41,261 for lessees' shipments.[3] From the Rico-Wellington property was shipped 424 tons of copper sulphide, 1,687 tons lead-silver sulphide, 1,826 tons zinc-lead sulphide, and 709 tons pyritic ore. The net value of these shipments was $105,589. Reserves of pyrite ore carrying 45 per cent sulphur are said to be extensive.[4] Other producing mines were the Duncan, Iron group, Lillian D., Lucky Boy, and Swansea-Newman.

DOUGLAS COUNTY.

There have been heretofore desultory attempts to recover gold by sluicing the gravels and conglomerates in Newlins Gulch, near Parker, and at other localities on Cherry Creek, in Douglas County, and nominal quantities have been recovered from time to time, but in 1917 no work was done.

[1] For discussion of geology see Cross, Whitman, and Spencer, A. C., Geology of the Rico Mountains, Colo.: U. S. Geol. Survey Twenty-first Ann. Rept., pt. 2, pp. 7–165, 1900; and Ransome, F. L., The ore deposits of the Rico Mountains, Colo.; U. S. Geol. Survey Twenty-second Ann. Rept., pt. 2, pp. 229–398, 1901.

[2] For discussion of treatment of vanadium ores see Moore, R. B., and Kithil, K. L., A preliminary report on uranium and vanadium: U. S. Bur. Mines Bull. 70, p. 74, 1914.

[3] See Salt Lake Min. Rev., Feb. 15, 1918, p. 39.

[4] Min. and Sci. Press, June 1, 1918, p. 769.

Digitized by Google

EAGLE COUNTY.

Mine production in Eagle County, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	32	105,149	a396,036	222,126	112,610	1,517,362	28,438,052	$4,185,294
1917	22	100,875	a41,187	136,023	53,136	2,426,988	23,715,412	2,795,469
Increase or decrease, 1917	−10	−4,274	−54,849	−86,103	−59,474	+909,626	−4,722,640	−1,389,825

a Includes small placer production.

There are only two mining districts of any consequence in Eagle County, one, the Brush Creek, a small silver district, from which very little ore was shipped in 1917, and the other, the Battle Mountain (or Red Cliff) district, from which the greater part of the production of ore has come. The Red Cliff district is now and has been for some time of importance, principally as a producer of zinc ores (both sulphide and carbonate), with, however, considerable quantities of associated lead, copper, iron, and manganese ores, carrying silver and some gold. The zinc output in 1917 was valued at $2,418,972, as compared with $3,810,699 in 1916.

Battle Mountain (Red Cliff)[1] *district.*—The Iron Mask separation mill was continuously operated on lead-zinc ores from the Iron Mask mine, with product in zinc, lead, and iron manganese concentrates. Zinc carbonate ores were also shipped from the Iron Mask, Black Iron, and other mines. A large quantity of lead-zinc ores from this district was shipped to various concentrating plants and smelters. Other producing mines of importance were the Ground Hog, Pursey Chester, and Wyoming Valley.

Eagle or Brush Creek district.—Several cars of high-grade silver ore were shipped from the Lady Belle and North Dakota mines.

McDonald district.—Sluicing operations on the Grand River, near Burns, yielded a small quantity of placer gold.

Groves Creek.—Placer operations near Minturn yielded a small quantity of placer gold.

EL PASO COUNTY.

At Colorado Springs are located the Golden Cycle and the Portland cyanidation mills, which treat almost exclusively the ores of the Cripple Creek district, Teller County.

Blair Athol district.—The copper deposits in sandstone at Blair Athol, 6 miles north of Colorado City, from which shipments were made in 1913 and 1914 only, have been abandoned.

[1] For discussion of geology see Means, A. H., Geology and ore deposits of Red Cliff, Colo.: Econ. Geology, vol. 10, No. 1, pp. 1–27, January, 1915; also Argall, Philip, Siderite and sulphides in Leadville ore deposits: Min. and Sci. Press, July 11, 1914, p. 52 (siderite at Red Cliff.)

Digitized by Google

FREMONT COUNTY.

From 7 mines in Fremont County in 1917 there were sold or treated 429 tons of ore, yielding $590 in gold, 664 ounces of silver, and 59,857 pounds of copper, with a total value of $17,478, as compared with $30,810 in 1916.

Several cars of copper are were shipped from the Badger Creek district, near Howard, from the Arizona, Badger Creek, Calumet, and Minor mines. From Parkdale, several cars of copper ore were shipped from the Green Mountain mine, and several small lots of copper ore from the Copper Girl and Copper Jack mines, all in the Texas Creek district.

GARFIELD COUNTY.

A car of gold ore was shipped from the Gray Eagle mine, near New Castle.

GILPIN COUNTY.[a]

Mine production in Gilpin County, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	87	38,913	$453,259	126,553	557,317	521,334	.....	$709,603
1917	60	35,289	397,087	112,585	544,648	815,906	141,490	723,146
Increase or decrease, 1917	−27	−3,624	−56,172	−13,968	−12,669	+294,572	+141,490	+13,543

[a] Bastin, E. S., Economic geology of Gilpin County and adjacent parts of Clear Creek and Boulder counties, Colo.; U. S. Geol. Survey Prof. Paper 94, 1916.

Owing to the increased value of metals and increases in quantity of lead and zinc produced, the total value of the production from Gilpin County in 1917 showed a small increase as compared with that of 1916, notwithstanding a decrease of $56,172 in gold.

The quantity of milling ore to amalgamating mills decreased one-half but there was an increase of ore to concentrating mills and a resultant small increase in quantity of concentrates produced. There was also a small decrease in the quantity of crude smelting ore, the content of which in gold and silver showed a considerable decrease.

Operating mills in Gilpin County in 1917 were the American Metals Producing Co. (old Rocky Mountain concentrator), Carr, Eureka, Iron City, Pittsburg, Polar Star, Saratoga, and Two-Forty. The Eureka and Iron City were the only mills steadily operated, the others being operated only for short periods.

A large part of the output of Gilpin County was mined from the Argo tunnel and the ore was treated at Idaho Springs mills.

Southern districts (Central City, Black Hawk, Nevadaville, Russell Gulch).—The old subdivisions by districts of the main area of Gilpin County are so indefinite and have so long since lost their

Digitized by Google

corporate identity that separation of output by districts has been abandoned.

In the near vicinity of Central City producing mines were the Corydon and Troublesome.

Producing mines in the Enterprise district were the Brack Hollow, Bryan tunnel, Little Kingdom, and Two Lassies.

Producing mines in the district embracing Gunnell Hill and Eureka and Prosser gulches were the Boodle, Concrete, Eureka, and Gunnell. All the ore from the Concrete and Gunnell was trammed through the Argo tunnel to Idaho Springs. The Eureka ore was milled in the amalgamation-concentration mill on the property.

Producing mines in the district embracing the town of Black Hawk, and Gregory, Bobtail, and Bates hill, were the Bates, Centennial, Colorado-Carr, Hamlet, Homer, Lucky No. 2, Running Lode, and Senator.

Producing mines in the district embracing Illinois and Leavenworth gulches and the east portion of Quartz hill were the Barnes, Ethan Allen, German, Ingalls, and Wood.

Producing mines in the Lake Gulch district were the Pittsburg, Pittsburg Extension, Star of the West, Vivian Notoway, and West Notoway. The Pittsburg mine has long been one of the important gold mines of the county, but in 1918 there was very little ore shipped direct to the smelter. The 50-ton concentration and flotation mill built at this property was operated for a period, the product being a gold concentrate which in no way equaled the "first class" ore formerly shipped.

In the vicinity of Nevadaville the producing mines were the Belden, Ophir-Burroughs, and Pozo-Dyke. The Ophir-Burroughs and Dyke were worked from the Argo tunnel level and the ore was shipped to Idaho Springs, but the contents were credited to Gilpin County.

In the Quartz Valley district producing mines were the Castle Rock, Gold Cup, Hayseed tunnel, and Spur Daisy.

In the Russell Gulch district among producing mines were the Chase, Bosom Plume, Druid, East Notoway, Federal, Frontenac, Hampton, Iron, Old Town, Powers, Richardson, Saratoga, Silver Dollar, Subtreasury, Togo, and Two-Forty. A concentration mill was built to treat the dump ores of the Saratoga.

Northern districts.—The outlying districts in Gilpin County are the Vermilion district, 4 miles northwest of Central City; the Pine district, 7 miles north of Central City, embracing Perigo and Rollinsville, Lump Gulch, and Moon Gulch sections; the Phoenix district, along the north edge of the county, near the Boulder County line; the Silver Lake district, 5 miles north of Central City; and the Hawkeye district, 7 miles north of Central City and 4 miles east of Apex.

At Apex, the Evergreen Mining Co. added a Marcy mill and flotation cells to its plant, and shipped several cars of high-grade copper concentrates, and also several cars of copper ore direct to the smelter. A car of lead ore was shipped from the Philadelphia mine. Development work was done at the Pennsylvania-Colorado property. The Pioneer mill was operated for a period.

Digitized by Google

On Silver Creek, near Apex, the Cornucopia Mining Co. was occupied in steady development of the Reform property and in testing of ores in the amalgamation-concentration mill on the property.

In the Hawkeye district two small lots of lead-silver ore were shipped from the Alaska and Peru mines.

In the Independence district several small lots of bullion and ore were shipped from a "clean-up" of the Perigo mill, and a car of gold ore was shipped from the Providence-Newport mine.

The Smuggler mine and amalgamation-concentration mill were operated part of the year, and then closed.

GRAND COUNTY.

There were no shipments from Grand County in 1917, and very little development work was done.

GUNNISON COUNTY.

Mine production in Gunnison County, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
		Short tons.	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	18	10,419	a$31,553	a$29,023	84,679	313,217	1,964,873	$356,386
1917	25	12,671	a6,635	a40,272	180,121	751,000	3,054,990	465,187
Increase or decrease, 1917	+7	+2,252	−24,918	+11,249	+95,442	+437,783	+1,090,117	+108,801

a Includes placer production.

Box Canyon district (*Waunita Hot Springs*).[1]—A car of silver ore was shipped from the Mullinger mine.

Cebolla district (*Vulcan, Domingo*).[2]—A large quantity of copper ore was shipped from the Anaconda mine, and a car of copper ore from the Vulcan.

Cochetopa district (*Sillsville*)[3]—No work was done in the Cochetopa district.

Elk Mountain district (*Gothic and Crested Butte*).[4]—A large quantity of zinc carbonate ore was shipped from the Doctor mine, on Spring Creek. This mine is opened by an adit 650 feet long. Operations were continuous throughout 1917. A car of lead-silver ore was shipped from the Cascara-Yankee Blade mine.

Gold Brick district (*Ohio City*).[5]—The amalgamation-concentration mill at the Belzora-Bassick mine was operated for a period on ore taken out in development work. Several cars of zinc carbon-

[1] For discussion of geology see Hill, J. M., Notes on the economic geology of southeastern Gunnison County, Colo.: U. S. Geol. Survey Bull. 380, pp. 21–40, 1909.

[2] Harder, E. C., Manganese deposits of the United States: U. S. Geol. Survey Bull. 380, p. 273, 1909; U. S. Geol. Survey Bull. 427, p. 150, 1910. Leith, C. K., Iron ores of the western United States and British Columbia; U. S. Geol. Survey Bull. 285, p. 197, 1906.

[3] See Hill, J. M., op. cit.

[4] Harder, E. C., op. cit., pp. 188–198, Emmons, S. F., Cross, Whitman, and Eldridge, G. H., U. S. Geol. Survey Geol. Atlas, Anthracite-Crested Butte folio (No. 9), 1894.

[5] See Hill, J. M., op. cit.

Digitized by Google

ate ore were shipped from the Carbonate King mine. A small lot of lead ore was shipped from the Carter property. Other producing mines were the Chicago-Climax, Hill Top, Little Dora, Lucas, and Queen.

Quartz Creek district (Pitkin).[1]—From development work at the Bon Ton mine, several lots of silver ore were shipped. This property is being developed also for molybdenum ores. A considerable quantity of amorphous graphite was shipped from this district.

Rock Creek Marble district.[2]—A small quantity of lead-silver ore was shipped from the Black Queen and Evening Star mines, on Sheep Mountain. The Buckeye Mining & Milling Co., operating the Sheep Mountain tunnel, continued development, completed a concentration mill, and shipped one car of ore. At the Lead King property, which is opened by a 600-foot adit and 1,000 feet of raises and drifts, no work was done in the mine, but the 20-ton concentration plant was operated during the summer months.

Tin Cup district.[1]—The Forest Hill mine, on Trail Creek, 26 miles northeast of Almont, shipped a car each of lead and zinc concentrates from operations in 1916 of its 60-ton concentration mill (built in 1900 by the Gunnison Mining Co.). This mine is opened by a 365-foot shaft and 5,000 feet of drifts. From the Star-Independent mine, opened by a 145-foot vertical shaft and a 200-foot incline shaft, was shipped a considerable quantity of lead-silver ore. The dredge on the Tin Cup placer, on Willow Creek, was idle.

Tomichi (Whitepine) district.[3]—The Akron Mines Co., operating the May, May Mazeppa, Ensign, North Star, and Erie mines, operated for a period the Akron 50-ton concentration mill on lead-zinc ores and shipped lead and lead-zinc concentrates. In addition, considerable lead-zinc ore was shipped to the Western Chemical & Manufacturing Co.'s mill at Denver, and copper ore to the Salida smelter. The Akron Co. also leased the Morning Glim, Parole, and Spar Copper group, from which a car of copper-silver ore was shipped to the smelter, and a considerable quantity of ore carrying silver and a low content of copper was shipped and treated at the Akron mill. A car of silver-lead ore was shipped from the Eureka mine, once a heavy producer. Silver ore, lead ore, and zinc carbonate ore in small quantities were shipped from the Victor mine.

HINSDALE COUNTY.[4]

Hinsdale County produced in 1917 from 13 mines, 517 tons of ore, yielding $1,136 in gold; 7,721 ounces of silver, valued at $6,362; 6,099 pounds of copper, valued at $1,665; 209,616 pounds of lead, valued at

[1] See Hill, J. M., op. cit.

[2] Emmons, S. F., Cross, Whitman, and Eldridge, G. H., U. S. Geol. Survey Geol. Atlas, Anthracite-Crested Butte folio (No. 9), 1894. Covers merely extreme source of Rock Creek, and geology discussed only in general way.

[3] For discussion of geology see Crawford, R. D., Geology and ore deposits of the Monarch and Tomichi districts, Colo.: Colorado Geol. Survey Bull. 4, 1913. Hill, J. M., op. cit.; Harder, E. C., op. cit.; Leith, C. K., op. cit.

[4] For discussion of geology see Irving, J. D., Ore deposits in the vicinity of Lake City, Colo.: U. S. Geol. Survey Bull. 260, pp. 78–84, 1905; Ore deposits of the Ouray district, Colo.; U. S. Geol. Survey Bull. 260, pp. 50–77, 1905. Irving, J. D., and Bancroft, Howland, Geology and ore deposits near Lake City, Colo.: U. S. Geol. Survey Bull. 478, 128 pp., 1911. Larsen, E. S., The economic geology of Carson Camp, Hinsdale County, Colo.: U. S. Geol. Survey Bull. 470; pp. 30–38, 1911. Woolsey, L. H., Lake Fork extension of the Silverton mining area, Colo.: U. S. Geol. Survey Bull. 315, pp. 26–30, 1907.

Digitized by Google

$18,027; and 4,117 pounds of zinc, valued at $420—a total of $27,610, as against $18,847 in 1916.

Galena district.—Several cars of lead-silver ore were shipped from the Highland Chief mine. The Hidden Treasure mill was operated for a short period, with output of lead concentrates. Small lots of ore were shipped from the Frank Hough and from the Varden Belle mine.

Lake district.—Small lots of ore were shipped from the California, Golden Fleece, Grove, Monte Queen, Mountain Chief, Pelican, and Pearl and Ruby mines.

JACKSON COUNTY.

Pearl district.[1]—Shipments of copper ore were continued from the Wolverine mine during 1917.

LAKE COUNTY.

Mine production in Lake County, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.		Silver.	Copper.	Lead.	Zinc.	Total value.
			Placer.	Deep.					
		Short tons.			*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	90	477,240	$119,169	$1,601,271	a2,931,281	2,621,675	21,719,392	76,785,567	$16,082,059
1917	88	422,428	110,325	1,064,894	a2,184,000	2,182,623	18,301,802	60,254,333	11,290,588
Decrease, 1917	2	54,812	8,844	536,377	747,281	439,052	3,417,590	16,531,234	4,791,471

a Includes placer production.

The total value of the production of gold, silver, copper, lead, and zinc in Lake County decreased from $16,082,059 in 1916, to $11,290,588 in 1917, but the decrease was partly met by an increase in shipments of manganese ores for use in the steel industry both at Pueblo, Colo., and at plants in the Eastern States. The manganese output and value is covered by the general manganese report, and no credit for this metal is given in this report, the manganese in manganese-iron-silver fluxing ores to lead smelting plants being considered as unrecovered metal in the slag.

The quantity of ore mined in Lake County in 1917 was 54,812 tons less than in 1916, the greatest decrease showing in the output of pyritic smelting ores, notwithstanding the fact that an increased quantity of pyrite ores were used in the manufacture of sulphuric acid, the residues containing gold, silver, copper, and lead being sold to lead smelters, and credit given in this report for such ores and contents under the classification of smelting ores, with the use in these tables of the original weight as it went to the roasting furnaces, not the weight as it finally arrived at the lead plants, after the sulphur had been removed.

This county continued to rank first in the production of silver, copper, lead, and zinc; in the production of gold it again ranked third, following after Teller and San Miguel. Of the State total, Lake County produced 7 per cent of the gold, 30 per cent of the

[1] Spencer, A. C., Reconnaissance examination of the copper deposits at Pearl, Colo.: U. S. Geol. Survey Bull. 213, pp. 163–169, 1903.

Digitized by Google

silver, 27 per cent of the copper, 27 per cent of the lead, and 50 per cent of the zinc.

The Derry Ranch dredge, on Arkansas River, 12 miles below Leadville, which was operated for the first time in 1915, continued operations during the year 1917. This placer operation is the first revival of that industry since the early sluicing and hydraulic operations in California Gulch immediately following the discovery of gold in that district.

Lake County includes the Leadville, St. Kevin, Sugar Loaf, Twin Lakes, Lackawanna Gulch, Big English Gulch, Weston Pass, Wortman, and Arkansas River placer districts.

LEADVILLE DISTRICT.[1]

GENERAL FEATURES.

Of a total of 422,428 tons of ore mined in 1917 in this county, 411,803 tons were from the Leadville district. The yield was $1,000,116 in gold, 1,940,983 ounces of silver, 2,171,242 pounds of copper, 17,844,500 pounds of lead, and 59,669,068 pounds of zinc, with a total value of $10,813,107, out of a county production of $11,290,588. In 1916 the yield was $1,470,557 in gold, 2,783,570 ounces of silver, 2,610,394 pounds of copper, 21,510,682 pounds of lead, and 76,008,276 pounds of zinc, with a total value of $15,613,649.

The output of zinc carbonate ores decreased from 85,513 tons of 21.52 per cent zinc in 1916 to 69,238 tons of 19.84 per cent zinc in 1917. The zinc sulphide ores shipped from Leadville were 148,945 tons carrying 20 per cent of zinc, as compared with 147,295 tons of 21.69 per cent in 1916. The production of iron pyrites decreased from 161,096 tons in 1916 to 128,533 tons in 1917, and the average assay per ton for this class of ore dropped from 0.339 ounce of gold to 0.277 ounce, and from 12.66 ounces of silver to 9.71 ounces. The quantity of lead oxidized, copper oxidized, and siliceous oxidized ores all decreased, but there was an increase in quantity of iron fluxing ore and iron-manganese fluxing ore. (In addition there was a heavy increase in quantity of iron-manganese ores for use at steel plants.)

Classification of Leadville ores in 1917.

Character.	Quantity.	Percentage.
Sulphide:	*Short tons.*	
Zinc-iron-lead (zinc blende: pyrite and galena)	148,945	36
Iron (pyrite with gold, silver, copper, and lead; and some zinc blende) [a]	128,533	.....
Iron (pyrite with gold, silver, copper, and lead over 4½ per cent dry lead; with some zinc blende) [a]	3,053	32
Iron (pyrite with gold, silver, lead, and copper over 2½ per cent dry copper, with some zinc blende) [a]	364	.....
Total sulphide	280,895	68

[a] The greater part of the iron pyrite carries iron in excess of silica and also high silver but low gold content; a large quantity of iron pyrite carries silica in great mass over iron and high gold but low silver content. Some of the iron pyrite approaches the zinc-iron-lead classification (when zinc market gives higher returns or sale as lead-zinc sulphide than as lead sulphide to lead smelters) and vice versa.

[1] For discussion of geology see Emmons, S. F., Geology and mining industry of Leadville, Colo.: U. S. Geol. Survey Mon. 12, 1886; Emmons, S. F., and Irving, J. D., The Downtown district of Leadville, Colo.: U. S. Geol. Survey Bull. 320, 1907. Argall, Philip, Siderite and sulphides in Leadville ore deposits: Min. and Sci. Press, July 11, and 25, 1914, pp. 50–54, 128–135. Harder, E. C., Manganese deposits of the United States: U. S. Geol. Survey Bull. 380, p. 273, 1909; U. S. Geol. Survey Bull. 427, pp. 137–143, 1910.

Digitized by Google

Classification of Leadville ores in 1917—Continued.

Character.	Quantity.	Percentage.
Oxide:	*Short tons.*	
Lead	16,416	4
Copper	7,524	2
Iron flux	6,050	1
Iron-manganese-silver flux	21,447	5
Siliceous [a]	10,233	3
Zinc	69,238	17
Total oxide	130,908	32
Grand total	411,803	100

[a] All the siliceous oxide ore contains lead under 4½ per cent and copper under 2½ per cent, therefore called "dry." The greater part of the siliceous oxide ore carries a heavy excess of silica over iron; a small part carries iron and silica in equal quantities.

Character.	Quantity.	Recovered contents.				
		Gold.	Silver.	Copper.	Lead.	Zinc.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Sulphide:						
Zinc-iron-lead	148,945	[a] 3,510.02	[a] 343,277	[a] 47,715	[a] 10,884,497	[b]
Iron pyrites [c]	128,533	35,570.98	1,247,574	1,143,659	2,610,052	.....
Lead sulphide	3,053	975.61	31,546	14,932	586,760	.....
Copper sulphide	364	83.08	6,800	28,982	2,170	.....
Oxide:						
Lead	16,416	2,242.04	101,266	42,208	2,858,848	.....
Copper	7,524	2,408.00	25,465	826,970	199,478	.....
Iron flux	6,050	300.33	24,373	6,919	49,161	.....
Iron-manganese flux	21,447	291.17	114,094	2,666	515,970	.....
Siliceous	10,233	1,830.37	46,030	57,191	137,564	.....
Zinc	69,238	.....	.....	.....	.....	[b]
Metallics (sulphide and oxide) [d]	.....	1,169.01	558	.....	.....	.....
	411,803	48,380.61	1,940,983	2,171,242	17,844,500	59,669,068

[a] Recovered as lead and iron concentrates and in zinc residues.
[b] Zinc in terms of recovered zinc (spelter) and recovered zinc in zinc oxide.
[c] Includes both ore to lead plants and that used for making sulphuric acid from which residues were returned to lead plants.
[d] May include some Cripple Creek and Park County metallics.

Character.	Quantity.	Recovered contents.				
		Gold.	Silver.	Copper.	Lead.	Zinc.
	Short tons.	*Fine ounces.*	*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*
Dry, iron, and siliceous ores [a]	166,263	39,161.86	1,432,629	1,210,435	3,312,747	.....
Copper ores [b]	7,888	2,491.08	32,265	855,952	201,648	.....
Lead ores [c]	19,469	3,217.65	132,312	57,140	3,445,608	.....
Zinc ores [d]	83,510	415.85	15,823	20,313	730,176	26,303,043
Lead-zinc ores [e]	134,673	3,094.17	327,454	27,402	10,154,321	33,366,025
	411,803	48,380.61	1,940,983	2,171,242	17,844,500	59,669,068

[a] Includes siliceous oxide, iron oxide, iron-manganese oxide and iron pyrite, also metallics. All smelting ores.
[b] Sulphide and oxide ores. Smelting ores.
[c] Sulphide and oxide lead ores. Smelting ores.
[d] Sulphide and zinc carbonate ores. Smelting ores.
[e] Sulphides. Greater part to concentration mills.

Digitized by Google

Classification of Leadville ores in 1917—Continued.

Character.	Average recovered contents.				
	Gold.	Silver.	Copper.	Lead.	Zinc.
	Ounces per ton.	*Ounces per ton.*	*Per cent.*	*Per cent.*	*Per cent.*
Sulphide:					
Zinc-iron-lead	[a] 0.033	[a] 4.83	(a)	[a] 7.79	[a] 20.00
Iron pyrites	0.277	9.71	0.44	1.02	.....
Lead sulphide	0.320	10.33	0.24	9.61	.....
Copper sulphide	0.228	18.68	3.98	.....	.....
Oxide:					
Lead	0.137	6.17	0.13	8.71	.....
Copper	0.320	3.38	5.50	1.33	.....
Iron flux	0.050	4.03	0.06	0.41	.....
Iron-manganese flux	0.014	5.32	.....	1.20	.....
Siliceous	0.179	4.50	0.28	0.67	.....
Zinc	.....	.....	.....	.....	[b] 19.84
Metallics (sulphide and oxide)	.....	.....	.....	.....	.....

[a] Average assay of greater part of original ore for which data were available. (Lead "wet" assay.)
[b] Average assay of original content; no deductions for loss in smelting. All to zinc plants.

The course of treatment of Leadville ores from mine mouth to market was shown graphically in Mineral Resources for 1911, Part I, page 547, figure 1. With the exception of the quantity of ore, the flow sheet for 1911 applies for 1917 in nearly all the details.

During 1917 the zinc-oxide plant was continuously operated on low-grade zinc carbonate ores. The Leadville district concentration-flotation mill was operated on low-grade zinc ores from the Resurrection dump, on lead-zinc ores from the Leadville Unit, and on lead-zinc ores from Kokomo (Summit County) and from the Sedalia mine in Chaffee County. The A. V. smelter of the American Smelting & Refining Co. was operated steadily on Leadville ores and ores from other parts of Colorado as well as on imported ores from Idaho and elsewhere.

The success attained in 916 in the unwatering of the Downtown mines and the Fryer Hill mines resulted in 1917 in a production of a zinc carbonate, lead carbonate, and iron-manganese ores from the Downtown district, and of zinc carbonate and iron sulphide ores from the Fryer Hill district. During 1917 the Greenback and Mikado shafts were also unwatered and shipping from these properties commenced.

MINES REVIEW.

California Gulch, Iron Hill, and Breece Hill mines as opened by the Yak tunnel.—The Yak tunnel starts in California Gulch and unwaters and develops a great number of mines along its course through Iron and Breece hills toward the Mosquito Range. Of the mines operated by the Yak Co. itself, much of the ore comes from the Cord winze below the tunnel level. Besides the operations of the Yak Co. and its auxiliary company, the Leadville Exploration & Mining Co., there were shipments of ore by lessees from other mines controlled and developed by the Yak Co. Other important mines from which ore was shipped were the Comstock, Dolly B., Fortune, Resurrection, Rubie, Sierra Nevada, South Cord, Vinnie, and White Cap. The bulk of the ore was iron sulphide, which was shipped to lead smelters in Colorado. Much iron pyrite, chiefly valuable for its

Digitized by Google

sulphur content but also carrying considerable silver and some lead and zinc, was shipped to plants for the manufacture of sulphuric acid, the roasted residue finally reaching lead plants. Considerable quantities of zinc carbonate ores were also shipped. The magnetic separation plant at the mouth of the Yak tunnel was dismantled.

California Gulch.—From the Emmett No. 5 mine iron-manganese ore was shipped to the steel plant at Pueblo.

Iron Hill.—From the Tucson, Moyer, and Marian mines, and from leases on the property of the Iron Silver Mining Co., were shipped large quantities of various classes of ore (principally zinc-lead sulphide, zinc sulphide, and iron sulphide) containing 689 ounces of gold, 163,493 ounces of silver, 1,893,020 pounds of lead, 26,914 pounds of copper, 13,342,256 pounds of zinc, and 5,956,671 pounds of combined iron and manganese. The report of the Iron Silver Mining Co. for the year ending December 31, 1917 (dated Feb. 23, 1918), says:

Mining during the past year accomplished a rapid depletion of the ore bodies in the older mines and development consistently failed to reveal the presence of any additional deposits. The Moyer mine has been practically exhausted of commercial ore and the Tucson mine is apparently approaching that condition. A failing ore supply and a lower grade production, accompanied by increasing mining costs, were all responsible for a considerable decrease in earnings for 1917. * * * The purchase of the new Marian group was completed early in 1916 and the work of opening, exploring, and exploiting the claims immediately followed * * * with the result that an initial production of ore was secured in June, 1917. Shipments were necessarily limited at first but were soon increased to the extent that a satisfactory operating profit was realized for the last quarter of the year. Present indications are that the Marian will eventually develop a production and an earning capacity fully up to expectations.

[On the Moyer mine] * * * a satisfactory production was maintained during the first half of the year but, thereafter, it was found that such low-grade ore as still remained in the mine could not, under the existing conditions, be profitably extracted owing to the very substantial and constantly growing increase in the cost of mining, resulting from the payment of higher wages and the material advance in the price of mining supplies. In order to reduce expense it was decided to stop pumping after it had been decided that the water would not, in all probabilities, rise to such a point as would endanger ore extraction at the horizon being mined. The pumps which had been in constant operation at the bottom of the Moyer mine for almost 20 years were shut down and pulled out just prior to the labor strike * * *. Operations were promptly resumed after the strike but were carried on at a steadily increasing loss until the company reluctantly decided to cease work on the Moyer and closed down the mine on October 13, 1917. * * *

The mine still contains considerable quantities of iron pyrites so barren of precious metal content that this material can not be shipped profitably on standard smelter schedules. It has been anticipated that war conditions and expediencies would render these pyrite deposits valuable for sulphur content, but so far, no price has been offered for a sufficiently regular tonnage that would make it worth while to attempt to exploit them. Should such a market eventually present itself the company is in position to reenter the mine and proceed with the extraction of the iron pyrites deposit.

[In the Tucson mine] * * * with the exception of a short period when work was suspended owing to labor troubles, * * * operations were continued throughout the year. * * * There remains but a limited area of what may be considered the mineralized zone of the Tucson mine to be still prospected and unless the work now under way for that purpose is successful the end of profitable operations on this mine is near.

The last annual report fully described the progress that had been made at that date toward equipping and repairing the Mikado shaft for the purpose of gaining access to and eventually mining the deep-seated ore measures of the Marian group of claims. * * * At the beginning of 1917 the surface plant had been completed and the shaft retimbered to the water level. * * * The pumps were received early in the year and immediately installed. * * *

Digitized by Google

The bottom of the shaft was finally reached and its depth from the surface found to be 1,135 feet. Working stations were then cut at the 1,000-foot, 1,075-foot, and 1,125-foot levels. * * *

The 1,000-foot level was driven into the R. A. M. claim, where a large body of medium-grade zinc sulphide ore was opened along the Mikado fault and from which all the ore shipments of the past year were obtained. This deposit underlies a very thick sheet of white porphyry which dips strongly to the southwest, carrying the ore-bearing measures to greater depth. * * * An extension of this level along the underside of the porphyry contact served to indicate the existence of considerable zinc sulphide ore below.

The opportunities afforded by the rehabilitation of the Mikado shaft for establishing a successful mining enterprise were farther augmented, during the year, through negotiation of a five-year lease on the property of the Alleghany Mining Co. This property consists of a group of claims, comprising about 19 acres of ground, adjoining our holdings on the north and advantageously located along the trend of the Mikado fault. On securing this lease the 1,075-foot level was extended into the leased premises where a promising-looking body of zinc sulphide has already been opened. * * *

Lead-zinc sulphide and lead-iron oxidized ores were shipped from the A. Y. & Minnie mine, and lead-iron sulphide and lead-zinc sulphide from the Louisville mine. Iron sulphide ores were shipped from the Adelaide and from the Humboldt mines on North Iron Hill.

Ball Mountain.—Several cars of lead oxidized and sulphide silver-gold ores were shipped from the Sunday mine.

Breece Hill.—Breece Hill and South Evans Gulch embrace the chief gold mines of the district. Lessees on the property of the Ibex Mining Co. continued to ship large quantities of all the various grades of ore, including some metallic gold. Large quantities of iron-sulphide ore were shipped by the Garbutt Leasing Co. from the Garbutt and Nonie mines. Copper siliceous oxide ore was shipped from the Robert Burns; siliceous oxidized and hematite fluxing ore from the Breece mine; lead siliceous oxidized ore from the Eliza and the Elk; siliceous and iron oxidized ores from the President; sulphide ore from the Fanny Rawlings; and siliceous sulphide silver ore from the St. Louis tunnel.

South Evans Gulch and Little Ellen Hill.—The ores of this vicinity carry an appreciable content of gold and silver. From the New Monarch mines there were shipped lead siliceous oxidized, lead siliceous sulphide, and siliceous sulphide and lead-zinc sulphide ores. Siliceous oxidized and siliceous sulphide ores were shipped from the Valley mine.

Carbonate Hill.—The bulk of the zinc carbonate shipments from Leadville continued to come from mines on Carbonate Hill. Large shipments were made from the Big Chief, Castle View, Maid of Erin, Wolftone, and other mines of the Western Mining Co., through the Wolftone shaft, and from the Star Consolidated Mines Co. Iron-manganese ore for fluxing purposes continued to be shipped from the Star mines and also a greatly increased quantity to the steel plant at Pueblo for the manufacture of spiegeleisen. Iron-manganese for fluxing ore and also for the manufacture of spiegeleisen was shipped from the carbonate mine of the Leadville Consolidated Mining Co. There were also large quantities of iron-manganese ores to steel plants from the Catalpa, Crescent, and Yankee Doodle mines. Large quantities of lead-zinc sulphide ore from the Mahala mine and other mines of the Western Mining Co. were shipped to the milling plant and also to the zinc plant of the U. S. Zinc Co., at Pueblo.

Digitized by Google

Fryer Hill.—Iron-manganese ores both for fluxing and to steel plants were shipped from the Fairview (or All Right); iron-manganese fluxing ores from the Dunkin, Matchless, Seneca, and other mines; iron-manganese fluxing, lead oxidized, and zinc carbonate ores from the Little Chief; lead and zinc carbonate from the May Queen; and iron-manganese fluxing, iron and siliceous silver oxidized ores, from the Little Sliver. Lead-zinc sulphide ores were shipped from the Result and Forest City mines through the McCormick shaft up to the time of closing after the labor strike; zinc corbonate was shipped from the Chrysolite mine; and zinc carbonate and iron manganese ores from the Robert E. Lee mine. From the various claims of the Leadville Unit of the United States Smelting, Refining & Mining Co., unwatered and retimbered in 1916, was shipped a variety of ores, including iron sulphide, pyritic ore, zinc sulphide, iron oxidized, and low-grade zinc oxidized ore. Among the claims operated by the Leadville Unit were the Bangkok, Cora Belle, El Paso, Forepaugh, Harvard, Quadrilateral, and Tip Top.

Printer Boy Hill.—Siliceous ozidized, lead oxidized, and zinc carbonate ores were shipped from the Lilian mine, and iron oxidized ore from the Reveille.

Rock Hill.—Lead oxidized ore and iron manganese ore, both for fluxing purposes and to steel plants, were shipped from the Nisi Prius mine, and iron manganese fluxing ore and lead siliceous oxidized ore from the La Plata group.

Iowa Gulch.—Several cars of lead sulphide ore were shipped from the First National mine, and lead oxidized and sulphide from the Ontario-Green Mountain mine.

Downtown district.—Large quantities of iron-manganese fluxing ore, zinc carbonate, zinc-lead sulphide, and lead oxidized ores were shipped from the various properties under control of the Down Town Mines Co., all operated through the Penrose shaft. The C. J. Dold Co. reopened the "Northern" property and shipped iron-manganese ores both for fluxing purposes and to steel plants.

OTHER DISTRICTS.

St. Kevin, Sugar Loaf, and Independence districts.—From the early days of mining in Lake County there has been production from the district lying along the base of the Sawatch Range, including St. Kevin and Sugar Loaf mountains. In 1917 siliceous oxidized and sulphide silver ores were shipped from the Dinero, silver-lead ore from the Bartlett Tunnel property (Prince of Wales), and siliceous oxidized silver ore from the Sugar Loaf Consolidated Co. From the Griffin mine was shipped iron sulphide, siliceous oxidized, and siliceous sulphide ores carrying much silver and some gold, and also a lead-zinc sulphide ore.

Twin Lakes and Lackawanna Gulch districts.—From the Ozark group, the Mount Champion Mining Co. shipped direct to smelters a considerable quantity of sulphide ore carrying a high content of gold. The Mount Champion 100-ton amalgamation and concentration mill[1] was not operated.

[1] For description see Becker, J. A., Colorado State Bur. Mines Thirteenth Bienn. Rept., 1913–14, p. 95, 1914.

Digitized by Google

Weston Pass district.—No shipments of ore were made from the zinc and lead carbonate deposits at the head of Weston Gulch.

Wortman (or Alicante) district.—The Denver Mining & Milling Co. operated its concentration mill on lead-zinc ores from the Burma (or John Reed) group.

Arkansas Valley dredge district.—At the mouth of Rock Creek, 12 miles from Leadville, the Derry Ranch 5-cubic foot bucket dredge, installed during the summer of 1915 and operated 70 days during 1915 and more than 7 months in 1916, was operated 7½ months in 1917. According to the printed report,[1] this dredge up to October 1, 1917, has produced $278,301, and the ground has averaged $0.28 a yard. The property has a life of five more years. Dividends to October 1, 1917, have amounted to 100 per cent. At the close of the 1917 season on December 15, the 1917 report[2] says the gravels dredged in 1917 averaged $0.20 a yard. The property covers 1,800 acres. Dividends in 1917 were $50,000 on a capitalization of $100,000.

Granite district.—A small button of gold bullion was shipped from operations at the Belle of Granite mine, in Lake County, just over the Chaffee-Lake County line, near Granite.

Big English Gulch.—No work was done on the Anderson adit (1,000 feet long) planned to cut Prospect Mountain.

LA PLATA COUNTY.

Mine production in La Plata County, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.	Silver.	Copper.	Lead.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	
1916	36	1,602	$31,653	29,187	12,024	6,551	$54,268
1917	21	1,648	25,281	15,324	25,795	3,745	45,272
Increase or decrease, 1917	−15	+46	−6,372	−13,863	+13,771	−2,806	−8,996

All the ore produced in this county was shipped direct to smelters.

La Plata (California) district.[3]—The mines of this district are located in the La Plata Mountains, in the drainage basin of La Plata River, centering around the town of La Plata, 10 miles from Hesperus, the shipping point on the Rio Grande Southern Railroad.

The May Day mine was idle. The principal producing mines were the Copper Hill, yielding copper-silver ore, and the Valley View, yielding gold-silver ore. Other producing mines were the Bay City, Eagle Pass, Great Western, Incas, Jumbo, Kenebeck, Little Mona, Mountain Meadow, Puzzle, and Ten Broeck.

In Montezuma County, but in La Plata district, on the west slope of the La Plata Mountains, several cars of ore were shipped from the Gold Dollar and from the Tenderfoot mine.

[1] Min. and Sci. Press, Oct. 27, 1917, p. 625.
[2] Eng. and Min. Jour., Feb. 16, 1918, p. 355.
[3] For discussion of geology see Cross, Whitman, and others, U. S. Geol. Survey Geol. Atlas, La Plata folio (No. 60), 1899. Emmons, W. H., The Neglected mine and near-by properties, Durango quadrangle, Colo.: U. S. Geol. Survey Bull. 260, pp. 121–127, 1906.

Digitized by Google

Needle Mountains district.—A small lot of lead-silver ore was shipped from the Eureka mine.

Cave Basin district.—The Cave Basin district, from which there was a small output in 1913, is located in the San Juan National Forest, about 20 miles north and east of Bayfield, in La Plata County, near the La Plata-Hinsdale County line, between Vallecito and Pine rivers. Development work only was done in this district in 1917.

LARIMER COUNTY.

At Masonville the Buckhorn Gold Mining Co., operating the Daisy group, shipped a small bar of gold-silver bullion, the product of the amalgamation mill on the property. There was a small car of copper ore shipped from the Christ Mountain district.

MESA COUNTY.

No production was made in the Unaweep[1] district in 1918.

MINERAL COUNTY.

Mine production in Mineral County, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	9	38,103	$31,124	373,956	13,138	2,295,087	240,575	$471,017
1917	12	32,755	10,101	361,517	19,297	1,305,744	54,971	431,160
Increase or decrease, 1917	+3	−5,348	−21,023	−12,439	+6,159	−989,343	−185,604	−39,857

Creede district.[2]—The Creede district embraces the most important deposits of Mineral County, and in 1917 the yield of the county was entirely from this district.

The Humphrey concentration-flotation mill continued to be operated on ore from the Park Regent group and also from the Last Chance-Volunteer group, and to produce lead and zinc concentrates. Smelting ore shipped from this district decreased from 19,677 tons in 1916 to 18,420 tons in 1917.

The producing mines at Creede were the Alpha, Bachelor, Commodore, Corsair, Equity-Creede, Holy Moses, Solomon, Mollie S., New York-Last Chance-Volunteer, Park-Regent, Silver King, and Monon group.

MOFFAT COUNTY.[3]

Craig district.—No placer gold was recovered in this district in 1917.

[1] For discussion of geology see Butler, B. S., Notes on the Unaweep copper district, Colo.: U. S. Geol. Survey Bull. 580, pp. 19–23, 1914; Emmons, S. F., Copper in the "Red Beds" of the Colorado Plateau region: U. S. Geol. Survey Bull. 260, p. 227, 1905.

[2] For discussion of the geology of the district see Emmons, W. H., and Larsen, E. S., A preliminary report on the geology and ore deposits of Creede, Colo.: U. S. Geol. Survey Bull. 530, pp. 42–65, 1913.

[3] White, C. A., On the geology and physiography of a portion of northwestern Colorado and adjacent parts of Utah and Wyoming: U. S. Geol. Survey Ninth Ann. Rept., p. 691, 1889; Gale, H. S., Gold placers near Lay, Routt County, Colo.: U. S. Geol. Survey Bull. 340, pp. 84–85, 1908; Carnotite and associated minerals in western Routt County, Colo.: idem, pp. 257–262.

Digitized by Google

Douglas Mountain district.—From the Bromide mine was shipped one car of silver-copper ore.

Fourmile district[1] *(near Baggs, Wyo.).*—Producing placer mines in this district were the Buckeye and Hawkeye, Homestake, and Timberlake.

Lay district.—Only assessment work was done on the placer prospects in this district.

MONTEZUMA COUNTY.[2]

Several cars of gold-silver ore were shipped from the Gold Dollar and Tenderfoot mines, in the La Plata district, but on the west slope of the west ridge of the La Plata Mountains, in Montezuma County.

MONTROSE COUNTY.[3]

Several cars of copper-silver ore were shipped from the Cliff Dwellers mine, near Paradox.

A considerable quantity of placer gold was sluiced from the gravels of San Miguel River near Naturita.

OURAY COUNTY.[4]

Mine production in Ouray County, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	52	111,192	$491,175	803,461	444,081	2,339,029	69,015	$1,299,737
1917	52	86,523	92,831	868,097	179,553	2,031,721	532,794	1,066,234
Increase or decrease, 1917	.....	−24,669	−398,344	+64,636	−264,528	−307,308	+463,779	−213,503

Red Mountain district.—The Red Mountain district in 1917 from 19 mines produced 5,690 tons of ore, yielding $5,472 in gold, 21,292 ounces of silver, 126,747 pounds of copper, 13,069 pounds of lead, and $32,794 pounds of zinc, with a total value of $123,318, as compared with $91,459 in 1916, and with $53,200 in 1915.

The revival of mining in this district begun in 1916 continued into 1917. The Mary Murphy Gold Mining Co., of Romley, Chaffee County, which in view of the exhaustion of ore reserves at the Mary

[1] Hoover, H. C., Geology of Fourmile Placer, Colo.: Eng. and Min. Jour., vol. 63, p. 510, 1897.

[2] See La Plata County.

[3] Boutwell, J. M., Vanadium and uranium in Utah: U. S. Geol. Survey Bull. 260, pp. 202–203, 1905. Hillebrand, W. F., and Ransome, F. L., On carnotite and associated vanadiferous minerals in western Colorado: U. S. Geol. Survey Bull. 262, pp. 14–16, 1905. Emmons, W. H., The Cashin mine, Montrose County, Colo.: U. S. Geol. Survey Bull. 285, pp. 125–128, 1906.

[4] For discussion of geology see Cross, Whitman, and Howe, Ernest, U. S. Geol. Survey Geol. Atlas, Ouray folio (No. 153), 1907; Silverton folio (120), 1905; Irving, J. D., Ore deposits of the Ouray district, Colo.: U. S. Geol. Survey Bull. 260, pp. 50–77, 1905. Ransome, F. L., A report on the economic geology of the Silverton quadrangle, Colo.: U. S. Geol. Survey Bull. 182, pp. 1–165, 1901

Digitized by Google

Murphy mine has been scouting for new property, took over in 1917 the Yankee Girl, Robinson, and Genesee-Vanderbilt miles, prominent producers of silver prior to 1894. The construction of a 50-ton concentration mill was begun at the Genesee mine. Smelting ore only was shipped from this group during 1917.

Lesses on the Barstow mine shipped ore both to the custom milling plant at Silverton and to the Durango smelter, and also operated the Barstow concentration mill. A large quantity of zinc sulphide ore was shipped direct to zinc retort plants from the Mountain King mine. The 150-ton gravity concentration and flotation mill at the Keno-Indiana-Guadalupe group was operated for a short period. The Vernon concentration mill was operated for a short period.

Other mines shipping either to the custom mill at Silverton or to the Durango smelter or to both were the Alexandria, Carbonate King, Guston, Hero, Iron City, Jumbo, Kentucky, Lookout, Saratoga, and Snowflake.

Sneffels district.—Although the Camp Bird mill remained idle during 1917, this district continued to be the principal producing district in Ouray County. In 1917 from five mines were sold or treated 75,125 tons of ore, from which were recovered $79,475 in gold, 709,432 ounces in silver, 26,751 pounds of copper, and 1,404,152 pounds of lead, with a total value of $792,107, as compared with $1,044,262 in 1916, and $1,259,367 in 1915. This district produced $2,162,198 in 1911, and from that year on a yearly output of little more than $1,000,000.

The Atlas 100-ton, 20-stamp, Hardinge ball mill, gravity concentration and flotation plant[1] was operated steadily. The Smuggler Union Mining Co., with properties in San Miguel County, continued to extract ore from the Humboldt mine in Ouray County through the extension of the Smuggler Union workings, and to treat the ore at the Smuggler Union mill in San Miguel County. Fortunately, this company keeps a separate record of the bullion and concentrates derived from the Ouray property, so Ouray County is credited with a very appreciable output of silver and gold produced by San Miguel County mills. Another specimen of rich gold was shipped from the pocket of gold discovered in 1916 in the Governor mine. The concentration mill (built underground) of the Mountain Top mine was completed and operated during 1917, the product being a lead-silver concentrate. Lead ore direct to smelter was also shipped from this mine. Lead ore direct to smelter was shipped from the Cumberland-Revenue mine. The driving of the new 10,700-foot low-level adit (commenced December, 1916), to cut the Camp Bird vein 450 feet below the present deepest workings, was continued throughout 1917, advancing to 7,278 feet by October 1, 1917. All work was confined to driving this adit; no ore was shipped, and the mill was idle. In driving the adit several veins were passed through, varying in width from a few inches to 6 feet. No drifting was done on these veins.

[1] For description of mill see Carroll, F., Colorado Bur. Mines Thirteenth Bienn. Rept. for 1913–14, p. 71, 1914; Min. and Sci. Press, June 24, 1916, pp. 953–954.

Digitized by Google

Uncompahgre district.—The Uncompahgre district produced in 1917 from 28 mines, 5,708 tons of ore, yielding $7,884 in gold, 137,273 ounces of silver, 26,055 pounds of copper, and 496,500 pounds of lead, with a total value of $170,809, as compared with $164,016 in 1916.

The copper matting plant at Ouray was idle. The American Nettie amalgamation-concentration mill, consisting of a 3½-foot Huntington mill, amalgamation plates, and Wilfley table, was operated during part of the year. Operations were continued at the Bachelor, from which silver-lead ore was shipped; silver-lead ore from the Black Girl, Calliope, and El Mahdi; and silver ore from the Newsboy, Pony Express, and Wedge. The Gold Crown 100-ton gravity concentration and flotation mill was completed and operated for a short trial run. Other mines from which some production was made were the Benack, Float, Gem, Mickey Breen, Mineral Farm, Portland, Raven, Rose, and Senorita.

PARK COUNTY.[1]

Mine production in Park County, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.		Silver.[a]	Copper.	Lead.	Zinc.	Total value.
			Placer.	Deep.					
		Short tons.			*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	15	3,005	$10,421	$223,878	13,231	22,598	330,609	47,560	$277,749
1917	20	2,693	5,451	111,907	14,705	12,824	278,709	.....	156,945
Increase or decrease, 1917	+5	−312	−4,970	−111,971	+1,474	−9,774	−51,900	−47,560	−120,804

There were 16 producing deep mines and 4 placers in Park County in 1917, an increase of 4 deep mines and of 1 placer. The placer yield was $5,451 in gold as compared with $10,421 in 1916.

Beaver Creek district.—The placer mines in this district were idle.

Buckskin district.—Development work at the Paris mine was continuous, a new adit being driven 300 feet, at a level 110 feet below the old workings. The amalgamation mill on this property was operated for a few weeks only. Several small lots of smelting ore were shipped from other properties in this district.

Consolidated Montgomery district.—A small lot of gold ore was shipped from the Centennial and from the Kansas, and a small lot of gold-silver ore from the Wheeler mine. Development work was done at the Weber group. Development work at the mine and experimental work at the mill was done at the Magnolia and Lee Goss groups by the Commonwealth Mining Co. At the Dolly Varden mine, a 200-ton concentration and flotation mill and an 11,600-foot tram were under construction and machinery was installed in prepa-

[1] For discussion of geology see Patton, H. B., Hoskin, A. J., and Butler, G. M., Geology and ore deposits of the Alma district, Park County, Colo.: Colorado Geol. Survey Bull. 3, 1912.

[a] Includes placer production.

Digitized by Google

ration for development of the mine. It is planned to mill the old dump ore while the mine is being developed.

Freshwater district (Guffey).—From the Mill Gulch mine, opened by a 220-foot shaft and 150 feet of drifts, a small lot of copper oxidized ore was shipped.

Hall Valley district.—Development work was continued at the Whale mine and a car of lead-silver ore was shipped.

Horseshoe district.—Several cars of silver ore were shipped from the Hill Top mine.

Lake George (Pulver) district.—During the summer of 1917 the Great Western property, opened by a 210-foot vertical shaft and 750 feet of drifts, was unwatered and some development work done. At the Apex property, plans were drawn and some progress made toward the erection of a 50-ton flotation mill.

Mosquito district.—At the Hock Hocking mine, the 40-ton gravity concentration mill built during 1916–1917 was operated for one month and produced several cars of silver-lead ore. From this mine, also several cars of smelting silver-lead ore were shipped. The London[1] mine, at the head of Mosquito Creek, on the ridge between Alma and Leadville, continued to be a large producer of lead ore carrying a high content of gold. A car of lead-silver ore was shipped from the Shelby mine.

Tarryall district.—During the summer months the Fortune placers, 4 miles from Como, on Tarryall Creek, were operated by hydraulicking, with an appreciable production of gold-silver bullion, averaging 0.887 fineness gold and 0.101 fineness silver.

PITKIN COUNTY.[2]

Mine production in Pitkin County, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	12	114,330	.....	577,863	28,931	17,519,275	162,574	$1,617,966
1917	11	124,824	$105	662,045	27,403	14,352,523	571,794	1,845,751
Increase or decrease, 1917...	−1	+10,494	+105	+84,182	−1,528	−3,166,752	+409,220	+227,785

Aspen (Roaring Fork) district.—At Aspen are located all the principal producing mines in Pitkin County, nearly all of which, in 1917, were operated by the Smuggler Leasing Co. The Smuggler 360-ton concentration mill[3] was operated on the low-grade silver-lead-zinc ores of the district and produced a large quantity of lead-silver concentrates and an appreciable quantity of lead-zinc concentrates. Much silver ore carrying a low content of lead and some lead-

[1] For discussion of geology see Moore, C. J., The London mine, Mosquito district, Colo.: Am. Inst. Min. Eng. Bull. 75, pp. 415–427, March, 1913.

[2] For discussion of geology see Spurr, J. E., Geology of the Aspen mining district, Colo., with atlas: U. S. Geol. Survey Mon. 31, 260 pp., 1898.

[3] For description of mill see Anderson, C. E., Colorado Bur. Mines Thirteenth Bienn. Rept. for 1913–14, pp. 104–105, 1914.

Digitized by Google

zinc and zinc ores were shipped direct to smelters. Producing mines under lease to the Smuggler Leasing Co., were the Aspen Fraction, Della S, Durant, Bushwhacker, Millinee, Mineral Farm, Mollie Gibson, and Smuggler. The Hunter Creek Mining & Leasing Co. also operated during the year and shipped its ore to the Smuggler mill for concentration. The Newman Mining & Leasing Co. leased a large acreage and operating through the Newman adit shipped a considerable quantity of silver ore. The Hope Mining & Leasing Co., a local corporation continued to drive its crosscut adit to cut the Little Annie and other mines at depth. This adit at the end of 1917 was 6,000 feet in length, of which 1,047 feet were driven in 1917. Development work was continued by the Hurricane Mining & Milling Co., operating through the Wilmington adit 550 feet long. The Park Tunnel Mining & Milling Co. was organized to drive an adit 3,000 feet in length to reopen by this adit some long idle properties in Tourtelotte Park, which, when last worked some 25 years ago, were opened by shafts.

Ashcroft (Columbia) district.—No production has been made in this district for many years.

RIO GRANDE COUNTY.

(See also Conejos County.)

Platoro-Summitville[1] *district.*—A small lot of low-grade lead-silver-gold ore was shipped by lessees operating the Guadalupe mine. This leasing company also erected a small concentration mill. No work on other prospects nor on any of the old properties was done.

ROUTT COUNTY.[2]

Hahns Peak district.—Development work at the Royal Flush group was continuous throughout the year, with a total development at the end of the year of 2½ miles of adits, drifts, and upraises. The 100-ton (per 8-hour shift) concentration mill was operated for a short period and yielded a small quantity of gold-silver concentrates. A small lot of gold-silver ore was shipped direct to the Globe smelter at Denver. Gold specimens were also sold to the Denver Mint. During the latter half of the year the mill was under reconstruction, the equipment consisting of Ball mills, 7 concentrating tables, 2 classifiers, and oil flotation machines.

No placer production was made in this district.

Slater district.—Assessment work only was done in the Slater district.

Yarmony district.—During 1916, the leaching plant built at the Copper King property was operated for a short period, the electrolytic copper produced not being finally marketed until 1917. No work was done at the property or the mill during 1917. The ore is a low-grade copper carbonate in sandstone.

[1] Patton, Horace B., Geology and ore deposits of the Platoro-Summitville mining district, Colo.: Colorado Geol. Survey Bull. 13, 1917.

[2] For discussion of geology see George, R. D., and Crawford, R. D., The Hahns Peak Region, Routt County, Colo.: Colorado Geol. Survey First Rept. for 1908, pp. 189–229, 1909; Gale, H. S., The Hahns Peak gold field: U. S. Geol. Survey Bull. 285, pp. 28–34, 1906; White, C. A., On the geology and physiography of a portion of northwestern Colorado and adjacent parts of Utah and Wyoming: U. S. Geol. Survey Ninth Ann. Rept., p. 691, 1889.

Digitized by Google

SAGUACHE COUNTY.

Mine production in Saguache County, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.	Silver.	Copper.	Lead.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	
1916	20	3,338	$8,024	48,959	92,581	255,449	$80,640
1917	26	4,224	10,350	76,016	144,978	310,686	139,285
Increase, 1917	6	886	2,326	27,057	52,397	55,237	58,645

Baca Grant (Crestone) district.—A small test lot of gold-silver ore was shipped from the Annie L. prospect. Assessment work was done at several properties in the district.

Baca Grant (Music or Liberty) district.—Some development work was done in this district.

Blake district.—A small lot of silver-lead ore was shipped from the Clara mine.

Cochetopa district.—A car of silver-copper ore was shipped from the Alaska-Columbine mine.

Crystal Hill district.—Several cars of silver ore were shipped from the Esperanza mine.

Embargo district.—A car of silver-lead ore was shipped from the Last Relief mine.

Kerber Creek (Bonanza) district.—This district yielded nearly all the output of the county. There was a considerable increase in the yield for 1917. From the Cocomongo mine a large quantity of silver-copper ore was shipped and also a large quantity of silver ore from the Rawley mine. The Rawley mine is opened by a 6,235-foot adit, a 658-foot upraise, 1,641 feet of drifts. During 1917 the three-compartment upraise was completed, a new compressor and motor haulage was also completed, and in addition a power line from Pagosa to the mine. A 7-mile tram to a proposed mill at Shirley, on the railroad, is contemplated. Other producing mines were the Antoro, Cornucopia-Exchequer, Cuba, Eagle, Erie, Foster group, Golden Wave, Jupiter, Legal Tender, Little Johnny, Memphis, Paragon-Michigan, St. Louis, Shawmut, Vienna, and Wheel of Fortune. The Kapi Mining Co. was occupied in driving the May Bell adit and shipped several cars of silver ore from the Shawmut mine.

SAN JUAN COUNTY.[1]

Mine production in San Juan County, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	46	146,128	$438,628	502,342	1,615,167	7,285,304	4,014,408	$2,207,116
1917	46	145,685	318,006	658,261	1,665,923	10,515,535	3,270,500	2,553,137
Increase or decrease, 1917	.....	−443	−120,622	+155,919	+50,756	+3,230,231	−743,908	+346,021

[1] For discussion of geology, see Cross, Whitman, Howe, Ernest, and Ransome, F. L., U. S. Geol. Survey Geol. Atlas, Silverton folio (No. 120), 1905. Emmons, W. H., Ore deposits of Bear Creek, near Silverton, Colo., U. S. Geol. Survey Bull. 285, pp. 25-27, 1906. Ransome, F. L., A report on the economic geology of the Silverton quadrangle, Colo.: U. S. Geol. Survey Bull. 182, pp. 1-265, 1901.

Digitized by Google

Animas district (including the mines in the vicinity of Silverton and south and east of Animas River from Silverton to Middleton).—The Animas district in 1917 produced 76,481 tons of ore, yielding $213,142 in gold, 514,153 ounces of silver, 1,101,432 pounds of copper, 7,181,233 pounds of lead, and 179,686 pounds of zinc, with a total value of $1,573,409, as compared with $881,884 in 1916 and with $568,640 in 1915.

There were 35 producing mines in the district in 1917, an increase of 8 mines. The Iowa-Tiger group and the Silver Lake mines were the principal producers. The Iowa-Tiger mill was operated steadily, with an increased production, particularly a large increase for lead. The Iowa-Tiger mill was also used as a custom plant. The Silver Lake mill was operated as a custom plant on ores from Red Mountain district, Eureka district, and Animas district. The quantity of smelting ore from the Silver Lake mines decreased heavily, but the quantity of milling ore continued about the same as 1916. The Mears-Wilfley 500-ton flotation plant continued to treat old tailing from the Silver Lake mill. The North Star mill and the Green Mountain (Pride of the West Co.) mill were both operated as custom plants and made a large addition to the quantity of ore milled in the district. The Hercules mill was idle, but the Intersection mill was operated for a short period. The Hamlet 150-ton concentration mill was operated for seven and one-half months, but was shut down in August to make changes to the mill. The Kittimac mill was operated on lead-zinc ores for a short period. A considerable quantity of ore from the Mayflower mine was treated at the Iowa-Tiger mill. Lead ore was shipped to the smelter from the Dives mine, and milling and smelting ore was shipped from the Highland Mary.

Other producing mines were the Aspen, Big Giant, Big Three, Champion No. 1, Champion No. 2, Emerald, Fairview, Frank Waller, Kansas City, Lackawanna, Little Nation, Shenandoah, and Silver Pitcher.

Eureka district (north of Silverton, including Chattanooga, Gladstone, Animas Forks, Eureka, and Red Mountain).—The Eureka district in 1917 produced 69,204 tons of ore, yielding $104,864 in gold, 144,108 ounces of silver, 564,491 pounds of copper, 3,334,302 pounds of lead, and 3,090,814 pounds of zinc, with a total value of $979,728, as compared with $1,324,811 in 1916. The Sunnyside 40-stamp gravity and oil flotation mill was operated steadily, yielding lead and zinc concentrates. A new 500-ton gravity and oil flotation plant was under construction. The Gold King mine and 150-ton gravity and oil flotation mill was operated throughout the year. The product from this property was gold-silver concentrates. Lead and zinc concentrates were the product of the Ledge concentration mill, operated on ores from the Silver Ledge mine. From the Congress mine copper smelting ore was shipped and milling ore was shipped to the Silver Lake custom mill. Lead-copper ore was shipped from the St. Paul mine and lead-silver ore from the Carbon Lake mine. Small lots of ore were shipped from the Ben Butler, Galena Queen, Galty Boy, Joe and John, Silver King, and Venus mines.

Digitized by Google

SAN MIGUEL COUNTY.[1]

Mine production in San Miguel County, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.	Silver.	Copper.	Lead.	Zinc.	Total value.
		Short tons.		*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	20	428,651	$2,072,393	812,041	581,427	6,126,551	1,098,485	$3,319,676
1917	20	389,293	2,009,961	779,364	920,425	6,205,326	1,810,245	3,621,736
Increase or decrease, 1917		−39,358	−62,432	−32,677	+338,998	+78,775	+711,760	+302,060

Upper San Miguel district.—The Upper San Miguel district in 1917 produced 387,458 tons of ore, yielding $1,997,950 in gold, 764,091 ounces of silver, 900,784 pounds of copper, 6,142,710 pounds of lead, and 1,810,245 pounds of zinc, with a total value of $3,586,393, as compared with $3,294,393 in 1916.

The three large companies, the Liberty Bell, the Smuggler Union, and the Tomboy, continued to furnish the greater part of the total output, which also includes a large quantity of ore treated at the Smuggler Union mill from the Black Bear mine. The Smuggler Union mill also treated a large quantity of ore from the Humboldt mines (in Ouray County), credit for which is given to Ouray County not to San Miguel County. The Wagner Development & Mining Co. continued to operate its 30-stamp concentration mill on ores from the Alta mines from January to September, when the property was taken over by the Belmont Wagner Mining Co., which made no production during 1917, but did much development work at the mine and reconstructed the mill to adapt it to the flotation process.

The annual report of the Liberty Bell Gold Mining Co. for the year ended September 30, 1917 (dated Jan. 5, 1918), says:

> The operations of the past year show a continued reduction in the tonnages mined and milled, a continued increase in operating costs per ton and, in compensation, a continued increase in gross and net receipts and in recovery per ton. To this may be added a substantial increase in ore reserves.
>
> The ore mined was about 12 per cent less than the preceding year, and the costs per ton were nearly 60 cents greater. The reasons for these changes were, in general terms, the scarcity, poorer quality, and higher cost of labor, the very material increase in cost of supplies, and the further fact that, during this period, mining operations were being transferred from the old part of the mine to a new part in the extreme eastern end, involving large outlays for salvage in one part and for new development and equipment in the other. * * *
>
> The increase of ore reserves * * * is most gratifying. It makes probable a 2-year extension of life, and assays during development work justify expectations of an excellent recovery. Uncertainty as to labor conditions and availability of supplies are our principal concern for the immediate future.
>
> The net profits for the year are seen to be $201,517. To this may be added the allowance of $33,925 for depreciation. During the year $227,037 were paid in dividends, or 34 per cent, of which 15 per cent was in completion of the return of capital.

[1] For discussion of geology, see Purington, C. W., Preliminary report on the mining industries of the Telluride quadrangle, Colo.: U. S. Geol. Survey Eighteenth Ann. Rept., pt. 3, pp. 745–850, 1898. Cross, Whitman, and Purington, C. W., U. S. Geol. Survey Geol. Atlas, Telluride folio (No. 57), 1899. Hess, F. L., Notes on the vanadium deposits near Placerville, Colo.: U. S. Geol. Survey Bull. 530, pp. 142–156, 1912.

Digitized by Google

Summary of operating receipts and expenses.

		Total.	Rate per ton.		
			1917	1916	1899–1917
RECEIPTS.					
Ore proceeds (143,100 tons)		$347,359.66	$5.92	$4.79	$6.28
Stamp bullion					2.74
Cyanide products	$789,543.96		5.52	4.42	2.84
Concentrates	57,815.70		.40	.37	.65
Concentrates cyanide bullion					.04
Slag					.01
Tram receipts	$3,676.75				
Rental receipts	3,328.50				
Commissary profit	2,406.54				
Interest, less loss from investments	17,454.84				
		26,866.63			
Less loss on boarding house		6,223.52			
		20,643.11	.14	.19	.17
Total receipts		868,002.77			
Average receipts per ton milled			6.06	4.98	6.45
EXPENSES.					
General expenses (143,100) tons		59,062.85	0.41	0.33	0.61
Mining (142,900 tons)		311,997.58	2.18	1.91	2.22
Operating	272,066.97		1.90	1.62	
Development work (4,676 feet)	39,930.61		.28	.29	
Tramming (142,900 tons)		23,746.22	.17	.14	.24
Milling (143,100 tons)		239,212.65	1.67	1.49	1.56
Treatment and shipping costs		32,465.80	.23	.20	.26
Stamp bullion				.18	
Concentrates (3,409 tons)	27,706.26		[a]8.13	[a]8.03	
Cyanide bullion (274,359 ounces)	4,759.54		.02	[b].02	
Total operating expenses		666,485.10			
Average cost per ton milled			4.66	4.07	4.91
Balance profit		201,517.67			
Profit per ton milled			1.40	.91	1.54

[a] Per ton of concentrates. [b] Per ounce of bullion.

Of greatest interest this year is the tonnage estimate, in that it shows a marked increase in ore reserves from the previous report notwithstanding the 143,000 tons mined during the year. On the other hand, the decrease in tonnage produced to the lowest point in six years is striking. Operating cost was more than correspondingly high but fortunately was offset by a big increase in the grade of the ore treated and in the price received for silver.

Again country-wide conditions in labor and supply markets outweighed the efforts of the mine staff in holding down costs of operations. Labor was scarce, and new wage scales established at Leadville and Silverton were necessarily followed at Telluride; but they were in effect only for the last three months of the fiscal year. At the end of the year the average wage was $1 higher than it was two years before, an increase of about 27 per cent. The advances in the silver market were sufficient to meet the advances in wages and to pay a part of the advances in supplies, the former being 17 cents and the latter approximately 30 cents a ton. The average price of silver for the year was 77 cents, a gain of 16 cents an ounce and 29 cents a ton over the previous year. * * *

Mining expense was necessarily higher per ton. Increases by labor alone added 11 cents as compared with the two years before. Development in the new ground was higher by $1.15 per foot than the standard of the previous year. At that, the work was not sufficiently remunerative to contractors to get the rapid progress desired. * * *

In the boarding house, the cost of provisions per man for the year increased $52 ($172 in 1916 to $224 in 1917), which is accountable for the greater part of the loss in operating. * * *

The ore reserve of 175,000 tons would seem to offer at least one year of life

Digitized by Google

at full capacity; but, as the new ore being opened is harder and is heavier with iron than that mined heretofore, the maximum capacity of the mill can scarcely exceed 140,000 tons for the next year. Further, there is great doubt whether the labor for even this tonnage will be available. As compared with the previous year, the present ore reserve shows almost double the area per ton of ore; or, in other words, the ore in reserve is of half thickness. The new development of the the year to the east has added greatly to the length of the already long ore body, but reference to the map sheet will show that the proximity of the junction with the Smuggler-Union vein marks a definite limit in that direction. * * *

The table of ore milled shows a gratifying gain of 2 per cent in gold extraction and of 4 per cent in silver. This gain for the whole year was made in the last four months. Mr. A. J. Weinig, superintendent of the mill, then found that the addition of minute quantities of mercury to the ore in process of treatment caused a marked gain in extraction. Subsequently the small tonnage being milled made further advantageous changes in treatment possible.

In the table of principal supplies, it is to be noted that zinc alone of the whole list decreased in price. Power alone was stationary in cost. At the mine, the big charges for mechanical plant represent a part of the cost of new pipe lines, new electric lines, and additional locomotives, hoists, and cars to reach and equip the new workings in the east end. * * *

The Liberty Bell mill has a capacity of from 400 to 500 tons a day, according to the character of the ore, and the process used is concentration, with cyanidation of concentrates and tailing. Mill extraction during the time covered by the annual report was 92 per cent of the gold and 81 per cent of the silver, with a recovery in terms of dollars of 89 per cent. The recovery in terms of dollars for the years 1899 to 1917 has been 83 per cent. During the calendar year 1917 the recovery for gold was slightly better than for the fiscal year, and in February, 1918, a still greater recovery was made.

The annual report of the Tomboy Gold Mines Co. (Ltd.) for the year ended June 30, 1917, shows

That 148,939 tons of ore (from the Argentine and Montana groups) were sent to the mill, where bullion worth $314,822 was obtained by amalgamation and $160,114 by cyanide, together with concentrates selling for $675,674. The total yield was equal to $7.73 per ton milled. Other small items brought the revenue to $1,169,231. The working cost was $811,966, or $5.45 per ton. * * * At the Argentine group developments at depth show that the ore body has increased in size and content of mixed sulphides, thus giving encouragement to open additional levels. The ore here averages $2 to $2.50 in gold and silver, 4 to 5 per cent lead, 5 to 10 per cent zinc, and 1 to 2 per cent copper. The reserve is estimated at 150,000 tons, of which 120,000 tons is ore broken in the stopes. This figure compares with 175,000 tons in 1916. At the Montana group, the reserve has been well maintained at 390,000 tons. In addition, ore has been disclosed in the Sydney-White Cloud property, recently acquired. Experiments are being made with selective flotation with a view to improving the extraction of sulphides. It is also hoped by this means to be able to treat ore not now included in the reserves.[1]

The Tomboy mill is a 60-stamp amalgamation and concentration mill, with a 400-ton cyanidation plant.

The Smuggler Union 450-ton amalgamation, gravity concentration, and flotation mill was operated steadily, the cyanidation plant having been abandoned and the flotation plant installed.

Other producing mines were the Ballard, Modena, and Wild Boy.

Iron Springs (Ames and Ophir) district.—The Iron Springs district in 1917 produced 1,835 tons of ore, yielding $12,011 in gold, 15,273 ounces of silver, 19,641 pounds of copper, and 62,616 pounds

[1] Min. Mag. (London), November, 1917, p. 250.

Digitized by Google

of lead, with a total value of $35,343, as compared with $25,283 in 1916. The principal producing mine was the Butterfly-Terrible, operated by lessees during part of the year. The product was chiefly amalgamation gold-silver bullion from the mill on the property and one car of concentrates. Several cars of silver ore were shipped from the Carbonero. At this mine, the year 1917 was devoted to completion of a working adit 2,500 feet long. Several hundred tons of silver ore from the Carribeau mine was milled. Some lead-silver ore from the Favorite mine was shipped direct to the smelter, and several hundred tons of milling ore was sent to the Suffolk mill. Other small producing mines were the Belisle & Sankey, Duffy, Oregon, San Bernardo, and Santa Cruz.

Lower San Miguel (Sawpit and Placerville).—No ore was mined in this district. Operations were discontinued at the Lizzie G. mine, from which in 1916 some iron pyrite, shipped for its iron and sulphur content only, was shipped to Vanadium for use in the treatment of vanadium ores.

Mount Wilson district.—Some assessment work was done in this district.

SUMMIT COUNTY.

Mine production in Summit County, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.		Silver.[a]	Copper.	Lead.	Zinc.	Total value.
			Placer.	Deep.					
		Short tons.			*Fine ounces.*	*Pounds.*	*Pounds.*	*Pounds.*	
1916	55	65,117	$579,050	$94,841	120,207	14,581	1,688,637	13,940,948	$2,741,177
1917	51	66,768	540,951	62,486	175,699	25,033	915,535	19,868,814	2,860,402
Increase or decrease, 1917	−4	+1,651	−38,099	−32,355	+55,492	+10,452	−773,102	+5,927,866	+119,225

[a] Includes placer production.

The value of the production of Summit County in 1917 was the largest in its history. Dredges[1] and hydraulicking and sluicing operations yielded $540,951 in gold and 6,636 fine ounces of silver, as against $579,050 in gold and 7,292 ounces of silver in 1916 and $607,195 in gold and 7,487 ounces of silver in 1915.

The principal placer-producing district in Colorado is near Breckenridge, Summit County. This county is also one of the three principal zinc-producing counties, being exceeded only by Lake and Eagle.

Breckenridge district.[2]—The Breckenridge district includes the Bevan, Minnesota, and Union districts and contains the mines (near Breckenridge) on French Gulch and on Blue and Swan rivers and all the producing placers in the county. The value of the total output of gold, silver, copper, lead, and zinc from both deep and placer

[1] See Revett, B. S., Gold dredging: Colorado Bur. Mines Thirteenth Bienn. Rept., for 1913–14, pp. 128–131, 1914.

[2] For discussion of the geology of the district see Ransome, F. L., Geology and ore deposits of the Breckenridge district, Colo.: U. S. Geol. Survey Prof. Paper 75, 1911.

Digitized by Google

mines was $2,623,594, or 92 per cent of the county yield, an increase in 1917 of $66,787, following an increase in 1916 of $760,170 and an increase in 1915 of $814,308. The Wellington mine continued to be the principal producing property in the district. The 125-ton wet-concentration mill, with rolls, jigs, and tables, and 100-ton magnetic separation plant,[1] with rolls, roasters, and magnetic separation machines, were operated steadily and produced zinc and lead concentrates. In addition, much high-grade zinc ore was shipped direct to smelters. Other operating mills were the Jessie 100-ton amalgamation mill, operated for two months only, and the Pioneer 20-stamp amalgamation-concentration mill, operated for several months. Other production was in the form of small shipments direct to smelters. Several cars of high-grade lead-gold ore were shipped from the Dunkin, but none of the high-grade pocket gold for which this mine is known was found in 1917. Lead-silver ore was shipped from the Carbonate, Carpenter, Ella-Minnie, Hancock, June Bug, Puzzle-Gold Dust, and Washington; lead-zinc ore from the New York; lead-silver ore and pyrites ore from the Iron Mask; and copper-silver ore, containing some bismuth, from the Mollie B.

All four of the dredges were operated in 1917, but with a decreased output as compared with 1916. The three dredges of the Tonopah Placers Co. were operated during the season as follows: No. 1, April 1, 1917, to February 2, 1918; No. 2, April 2, 1917, to January 3, 1918; No. 3 from March 14, 1917, to January 14, 1918. Only one-half of the net earnings of dredge No. 2 accrued to the company as it was operating on the ground of the Farncomb Hill Gold Dredging Co. Dredge No. 1 was operated at a loss during the year, as it was cutting through ground containing very low contents, in order to reach another part of the property, and it will probably take about two months' operations in the season of 1918 to reach the desired ground. Two of the dredges are of the Bucyrus open-connected type, with buckets of a capacity of 9½ cubic feet; the other dredge is of the double-lift, open-connected type, with buckets of a capacity of 9 cubic feet. The French Gulch Dredging Co.'s dredge, of the Bucyrus type, with buckets of a capacity of 5 cubic feet, was operated from March 20, 1917, to January 3, 1918.

The report of the Tonopah Placers Co. for the year ending December 31, 1917, appears in the sixteenth annual report of the Tonopah Mining Co. of Nevada:

Production and income statement of Tonopah Placers Co. for year ending December 31, 1917.

Gross value of bullion shipped to Mint	$451,743.20	
Cost of operations	285,104.75	
		$166,638.45
Miscellaneous earnings:		
Electric lighting	859.72	
Interest on bank balances	610.70	
		1,470.42
		168,108.87

[1] For description of magnetic plant see Parmalee, H. C., Zinc ore dressing in Colorado: Met. and Chem. Eng., September, 1912, pp. 525–528. Also for description of mills see Henderson, R. M., Colorado Bur. Mines Thirteenth Bienn. Rept., for 1913–14, pp. 106–110, 1914.

Digitized by Google

Production and income statement of Tonopah Placers Co. for year ending December 31, 1917—Continued.

Deductions from earnings of Dredge No. 2, under terms of contract with Farncomb Hill Gold Dredging Co	79,644.62
Net earnings for year 1917	88,464.25
Charges against profit-and-loss account: Depreciation of ore—5 per cent on cost of property, and 10 per cent on plant and equipment for year 1917	108,218.27
Net loss for year 1917	19,754.02
Surplus, December 31, 1916	239,279.48
Surplus, December 31, 1917	219,525.46
Cubic yards dredged	3,351,821
Gold produced, ounces	21,745.65
Silver produced, ounces	5,210.23
Value per yard	$0.1344
Profit per yard	0.0584

Bullion from the Tonopah Co.'s dredges averaged 0.793 gold and 0.194 silver, and that from the French Gulch Co.'s dredge 0.757 gold and 0.226 silver.

Hydraulicking was done on the Ada and Sisler placers in French Gulch. Other producing placers in the vicinity of Breckenridge were the Banner, Engel, and Washington. South of Dillon, on Blue River, a small quantity of placer gold was recovered by sluicing.

Consolidated Tenmile district (Frisco, Kokomo, and Robinson).[1]—This district, in 1917, from 12 mines, produced 14,915 tons of ore, yielding $38,620 in gold, 111,676 ounces of silver, 17,487 pounds of copper, 513,977 pounds of lead, and 298,696 pounds of zinc, with a total value of $210,084, as compared with $80,880 in 1916. From the Michigan mine was shipped direct to smelters a large quantity of lead-silver ore and pyritic silver-gold ore. In this mine are reported considerable bodies of barren pyrite ores. From the Golden Queen mine a large quantity of silver ore was shipped to smelters. From the Raven and Eagle mines silver ore was shipped. From the Wilfley property, the Elk Mountain Co. shipped lead-silver ore to smelters and lead-zinc ore to the Western Chemical & Manufacturing Co. Small shipments of ore were made from the Columbine, Four-Most, F. W. E., Hyman tunnel, King Solomon, Little Rock, Robinson, and Queen of the West mines.

Montezuma district.[2]—This district in 1917, from 11 mines, produced 1,479 tons, yielding $289 in gold, 8,097 ounces of silver, 2,242 pounds of copper, 142,291 pounds of lead, and 67,785 pounds of zinc, with a total value of $26,724, as compared with $103,490 in 1916. The St. John 100-ton mill, with crushers, tube mills, classifiers, jigs, Wilfley tables, and flotation machines, was operated at half capacity during December only. Operations at the mine were confined to

[1] For discussion of geology see Emmons, S. F., U. S. Geol. Survey Geol. Atlas, Tenmile district folio (No. 48), 1898.

[2] For discussion of geology see Patton, H. R., The Montezuma mining district of Summit County, Colo.: Colorado Geol. Survey First Rept. 1908, pp. 104–144, 1909.

Digitized by Google

retimbering during October, November, and December. The mine is opened by an adit 1,800 feet long, a 600-foot vertical shaft, and 5,000 feet of drifts. Lead ore was shipped from the Clarion, Morgan, Paymaster, Rainbow, Silver Wave, and Vanderbilt mines; lead-zinc ore from the Jumbo and More Work mines. The mill on the Silver Wave group has been abandoned.

TELLER COUNTY.

CRIPPLE CREEK DISTRICT.[1]

Mine production of Cripple Creek district, Colo., in 1916 and 1917.

Year.	Number of producing mines.	Ore.	Gold.	Silver.		Total value.
				Quantity.	Value.	
		Short tons.		*Fine ounces.*		
1916	64	945,820	$12,119,550	79,804	$52,511	$12,172,061
1917	63	1,084,656	10,394,847	64,568	53,204	10,448,051
Increase or decrease, 1917	−1	+138,836	−1,724,703	−15,236	+693	−1,724,010

In 1917 there were recovered in the Cripple Creek district by mills and smelters from crude ore and dump ore, from slags, slimes, and "clean-ups" of mills, from stolen bullion and ore, 502,850.72 fine ounces of gold, valued at $10,394,847.

CRIPPLE CREEK DRAINAGE OR ROOSEVELT TUNNEL.

The adit was driven 1,746 feet during 1917, making a total length of 24,000 feet. The total discharge of water at the portal was 8,500 gallons per minute on January 1, 1917, and steadily diminished to 4,000 gallons at the end of 1917. This drainage adit has lowered the general underground water level of the district 700 feet.

MILLS AT COLORADO SPRINGS.

The active valley mills adjoining Colorado Springs were the Golden Cycle, a roast-cyanide (with subsidiary amalgamation) plant[2] of 1,200 tons daily capacity, and the Portland, a 400-ton roast-cyanide concentration mill. These two mills, with the Portland Victor mill and Portland Independence mill, in the Cripple Creek district treated the bulk of the Cripple Creek ore, the quality of ore sent direct to smelters being only 6,233 tons and the concentrates to smelters being only 6,054 tons.

MILLS IN THE CRIPPLE CREEK DISTRICT.

On June 30, 1915, the Portland Gold Mining Co. purchased the Stratton's Independence, and during the rest of 1915 more attention

[1] For discussion of geology see Lindgren, Waldemar, and Ransome, F. L., Geology and ore deposits of the Cripple Creek district, Colo.: U. S. Geol. Survey Prof. Paper 54, 1906.
[2] For description see Milliken, J. T., Colorado Bur. Mines Thirteenth Bienn. Rept., 1913–14, pp. 72–74, 1914.

Digitized by Google

was paid to the proposed changes and enlargements in this mill than to the treatment of ores. During 1916 the work of remodeling and enlarging the Independence mill was delayed by the difficulty in securing machinery and building material, and to a less extent by reason of a change in plans concerning the methods of treatment to be used. The experiments showed that the nonoxidized ores could be treated with marked success by the oil flotation process, and it was contemplated using this process. Further investigation demonstrated that this process does not give satisfactory results when applied to oxidized ores. As oxidized ores predominate in the upper workings of the mine and as these ores will be the most accessible to the Independence mill for the next five or six years, it was decided to continue the use of the cyanide method. By the reconstruction of the mill the capacity was increased from 350 tons to 1,400 tons daily. The combined capacity of this plant and the adjacent Victor mill was therefore 2,000 tons every 24 hours.

The annual report of the Portland Gold Mining Co. for the calendar year 1917 (dated Feb. 18, 1918), says regarding the Victor and Independence mills:

It is a well-known fact that most gold-mining properties, wherever located, have been operated during the past year under very difficult and discouraging conditions, and operations at the Portland mine and mills have not been exceptions to the rule. All of the principal metals, except gold, our only product, have increased in value sufficiently to more than compensate for the increased cost of the material and supplies used in mining and milling, while gold has speedily decreased in purchasing power ever since war conditions began. The ever-increasing cost of fuel, explosives, timbers, steel, chemicals, and other mining and milling supplies, without increase in value of the gold produced to compensate, and the scarcity of efficient labor, even at an increased wage, had the effect of lessening the net earnings of your company for the year, although, notwithstanding all these obstacles and discouraging conditions, a fairly satisfactory net earning was made. * * *

The impossibility of securing prompt delivery of the building material already contracted for, and the high price of that not previously purchased, added largely to the cost of the Independence mill and delayed its completion. However, the mill was virtually completed about the middle of the year, and has been in successful operation since that time, treating an increasing tonnage each month, the average during the last three months having been about 37,500 tons. We expect the tonnage to be increased to 42,000 tons per month when the minor changes and adjustments, such as are incident to all new mills, shall be completed, which will be within the next month or two. Aside from the greatly increased cost of labor and milling supplies, the only other discouraging feature that has developed in connection with the operation of the Independence mill, is the uneven grade of the ore being taken from the dumps at present accessible. However, this adverse condition is now being overcome by bringing, when needed, a better grade from other places in the dumps and upper workings of the mine.

The expense of treating low-grade ore at the Independence mill under the present high cost of labor, cyanide, steel, and other supplies is slightly above our original estimate, but if labor and supplies were obtainable at the prices that existed 18 months ago when construction began the cost of treatment would be materially less than we expected, and a further gratifying feature is that the percentage of extraction is within our original estimate. The successful operation of the last few months proves the mill to be even better in every way than we expected, and there is no question of its great earning capacity when conditions have again become normal.

In the Independence mill your company now has a modern, up-to-date reduction plant, admirably located on the railway at the foot of the hill on which the Portland mine is situated. The plant has a coarse crushing and sampling capacity of 3,000 tons of ore daily and a fine crushing capacity of 1,250 tons a day, which will be increased to 1,400 tons within the next 60 days. The mill

Digitized by Google

is connected with Portland shaft No. 1, 1,667 feet distant, by a large transportation tunnel, which starts at the mill ore bins and runs on a level to the shaft, connecting with it at a depth of 248 feet below the surface. Branches from this tunnel run to chutes under the various surface dumps. The tunnel will be continued without delay to shaft No. 2, 769 feet farther on, and at that point will be 407 feet below the surface. The ore is transported through this tunnel by an electric train consisting of an 8-ton electric motor and ten 4-ton automatic dump cars, which runs over a well-ballasted track laid with 56-pound rails. The cars are loaded at slight expense from chutes over the track and are dumped automatically as they run over the ore bins. A round trip from the chutes under the dumps to the mill can be made every 10 minutes, the cost for the delivery of the ore to the mill bins by this method being less than 9 cents a ton.

Besides the large surface dumps of low-grade ore from which the Independence mill is now being supplied, it is estimated that there are 3,000,000 tons of low-grade ore in place in the mine, above and adjacent to the transportation tunnel, that can be broken and transported through the tunnel to the mill at a total cost of 30 cents or less per ton. This ore is of a higher grade than that in the dumps and can easily bear the additional cost of delivery at the mill. * * *

It may seem strange to those not familiar with the situation that we should build a third mill when we already had two in operation. The explanation is that the Colorado Springs plant was built to treat high-grade ores only and will be useless when the high-grade ores of the district have been exhausted. It would not represent a loss to the company even if it were junked, as its net earnings to date amount to several times the original cost of the plant. The Victor mill was intended to treat such ores as were too low grade to bear the cost of transportation, and for that reason was built at the mine on an unfavorable location, which, however, was the best that could be obtained at that time. At first the mill was largely experimental, but with the improvements that were added its operation proved that in the main the process and methods used in the extraction of the gold were correct, and this is more than confirmed by the fact that the net profits earned by the plant during the seven and a half years of its operation have been more than double its original cost. The Independence is a better plant in many respects than the Victor mill.

An average of 18,000 tons per month of dump and other low-grade ore was treated by the Victor mill during the past year at a fair profit to the company. By the 1st of April we expect the combined tonnage being treated by these mills will be in excess of 60,000 tons of ore monthly.

During the past year there has been a material decrease in the tonnage of high-grade ore shipped to the Colorado Springs mill owing to a lessened production in the Cripple Creek district, doubtless the result of a shortage of efficient labor and of the high cost of fuel, powder, timber, and other necessary supplies. Your board of directors foresaw this possible reduction of the output of high-grade ores, and in the construction of the Independence mill provision was made for the treatment of high-grade ore when it became necessary. Unless there is a material increase in the output of custom ores in the district it may become necessary at no distant day to close our Colorado Springs mill and treat at our Independence mill all of our own high-grade ore as well as the custom ore under contract to us. It is apparent that in the interest of economy all of the milling operations of your company should be combined at the Independence plant at the earliest opportune time. And I wish to call attention to the fact that the acquisition of the Stratton's Independence property made possible a combination of our milling operations at the most favorable and accessible point in the Cripple Creek district so far as the Portland mine is concerned.

The Vindicator Consolidated Gold Mining Co., in its annual report, dated January 31, 1918, for the year ended December 31, 1917, says, regarding its sizing, washing, and flotation mill:

In January, 1917, we requested the Minerals Separation Syndicate to send us one of their engineers to check our work and make such improvements in our milling practice as were possible. Their representative arrived on February 1, taking charge of the mill on that date and conducting operations for the next three months. This experimental work indicated that our process was as successful as anything the Minerals Separation Syndicate could suggest. In order, however, to handle profitably the low-grade ores it appeared necessary to increase the tonnage to the mill without overloading the flotation cells

Digitized by Google

and to improve the grade of the ore going to the flotation cells without commercial loss in the tailings. This has been accomplished by a combined sizing, washing, and flotation treatment, whereby the crude ores are separated into such products as can be profitably marketed direct, those which can be profitably treated by flotation and those which can be rejected from the mill without economic loss.

To accomplish this an electric surface tram was installed to transport at a low cost the reject from the Vindicator concentrating mill to the flotation mill.

This process has so increased the output of flotation concentrates as to necessitate the installation of additional equipment for drying, as the apparatus in use was totally inadequate to dry the concentrates. A drier is now in operation which is able to take care of the entire production of concentrates and which enables us to make prompt shipment of the concentrates produced, which was not possible heretofore.

Satisfactory results are being obtained from this process of combined washing, sizing, and flotation on the ore which is being drawn from the caved slopes of the upper levels of the Golden Cycle shaft. The addition of ore from this source is increasing the crude tonnage treated, and it is expected that it will reach a thousand tons a day within a short time.

Other operating mills in the district were the Isabella 100-ton cyanide leaching plant, operated until June, 1917; the Reed-Dante (or Big Toad) 80-ton coarse-crushing leaching plant, operated for a short period; the Jerry Johnson 100-ton cyanide mill, operated for a short time only; the Rex 100-ton cyanide leaching plant, operated for a short time only; and the Rubie 30-ton cyanide mill, operated for a short period. The Colburn Ajax 300-ton concentration and cyanide mill[1] was idle during 1917 and was remodeled into table and flotation-concentration mill, but not operated. The Free Coinage 60-ton cyanide and concentration mill was idle up to the time of dismantling; the Blue Flag 125-ton continuous agitation cyanide mill and the Wild Horse 50-ton coarse-crushing cyanide leaching plant were idle.

MINES REVIEW.

Poverty Gulch.—The Abe Lincoln and Gold King mines were producers.

Tenderfoot Hill.—Production continued from the Queen Bess property, operated through the Mollie Kathleen shaft. A small quantity of ore was shipped from the Ella W.

Globe Hill.—Stratton Estate mines on Globe Hill continued to produce.

Hoosier Pass.—There was no production from the Hoosier mine.

North slope of Ironclad Hill.—Producing mines were the Forest Queen, Jerry Johnson, W. P. H., and Damon.

Gold Hills.—Producing mines were the Anchoria-Leland, Conundrum, and Midget.

Raven and Guyot Hills.—Producing mines were the Cresson, Doctor-Jack Pot, Elkton, Jo Dandy, and Mary McKinney. A large quantity of low-grade material was shipped from the old Economic mill dump.

The Cresson property continued to be one of the principal producing mines in the district. The Elkton has ceased to be a large producing mine.

The report of the Mary McKinney Co. for the calendar year 1917 shows that there was produced on company account 2,962 tons of

[1] For description see Bryan, R. R., Colorado Bur. Mines Thirteenth Bienn. Rept., 1913–14, pp. 75–76.

Digitized by Google

ore, having a gross value of $40,560, and by lessees 4,960 tons having a gross value of $66,591. The development of the north end of this property proved disappointing.

Beacon Hill.—Producing mines were the Banner, Raaler (C. K. & N.), El Paso, Gold Dollar, Mabel M., and Prince Albert.

Bull Hill.—Producing mines were the Blue Bird, Dante, Dexter, Gold Sovereign, Modoc, Stratton Estate mines (American Eagles, Orpha May, Specimen, War Eagle, etc.), and United Gold Mines Co. group.

Mines between Altman and Goldfield.—Producing mines were the Burns, Golden Cycle, Isabella, Mountain Beauty, Pharmacist, Victor, and Vindicator.

The annual report of the Isabella Mines Co. for the calendar year 1917 says:

During the year ending December 31, 1917, your property was operated at a loss. The causes of this are twofold, namely, a lack of ore in payable quantities and adverse operating conditions due to the war. The production from your property during 1917 was as follows:

	Short tons.	Gross value.	Average value.
Company ore	817	$21,886	$27.69
Lessee's ore	8,334	144,129	17.29
Ore from dumps	361	4,568	12.62
Ore from mill development	297	4,778	16.11
Mill bullion	.....	17,562	.....
	9,809	192,923	.....

The mill was operated continuously from the first of the year to June 10, 1917, milling 8,210 tons of approximately $3 per ton. The mill was closed down on account of a scarcity of ore that could be milled at a profit at the increased cost of supplies and labor.

The Vindicator Consolidated Gold Mining Co. in its annual report for the year ended Dec. 31, 1917 (dated Jan. 31, 1918), says, regarding its mine operations:

During the year 1917, the management of your company has been called upon to face the most difficult operating conditions in its history. These were a gradual reduction in the average grade of ore mined and increased costs of supplies and labor, occasioned by the exceptional conditions incident to the war. * * *

The earnings during the first three-quarters of the year were sufficient to meet the quarterly dividends of 3 per cent each and to pay the taxes due on the production of the previous year, which latter item amounted to more than $51,000. The earnings of the fourth quarter were disappointing, due largely to a reduction in the grade of ore coming from the stopes during that period. A considerable tonnage of concentrates from the flotation mill also remains unshipped, due to a lack of drying facilities, which have only recently been supplied.

Due to the above conditions and to the cost of the installation of changes in ore house methods and the practice at the flotation mill, your board of directors was not warranted in declaring the dividend usually paid on January 25, and this was accordingly passed. * * *

There has been mined by the company during the past year 205,691 tons of crude ore, which has produced 39,799 tons of shipping ore. The gross value of shipping ore was $973,537, and after deducting freight and treatment the net amount from the sale of ore amounted to $742,939. During the year lessees shipped 47,119 tons, of an average gold content of $15.21 per ton, and the gross value of $716,804. After deducting freight and treatment charges,

Digitized by Google

the net results amount to $467,246. The net royalties to the company amount to $153,683 from all its lessees' operations.

During the year 1917 a continuous prospecting campaign has been carried on by the Vindicator Co. This has been principally directed to the 20th level of the Cycle shaft and the 19th level of the Vindicator shaft. The plan followed has been to crosscut the regions showing the heaviest fissuring in the levels above and then to drift on any veins having a promising structure. The result of some 2,600 feet of work of this character has been disappointing. Long stretches on veins favorable in appearance have been driven without developing any ore bodies of importance. Further possibilities still exist which should be definitely investigated before abandoning these deeper levels.

The company ore production for the year has been derived almost entirely from previously opened ore reserves which have been depleted accordingly. The measurable ore of payable grade now blocked out amounts to 255,500 tons, 114,370 tons of which is broken and 141,210 tons is solid ore in place. In addition to this measurable reserve there is a large section of caved stopes in the upper portion of the Golden Cycle shaft, from which a really substantial production can be drawn and which will yield a good profit when handled by the present washing and milling system. About 100 tons daily has recently been drawn from this source with very satisfactory results, and although definite measurement of tonnage can not be made, it is certain that a considerably higher rate of production can be maintained for a long period.

The washing and milling system is the result of systematic research into the distribution of values in your ores, which has been carried on in a thorough manner during the past year by your staff at the mine. Briefly stated, the change in practice results in the elimination from shipped products of certain material too low in grade to pay marketing cost and, by a system of sorting and sizing, selects from this material a product which is treatable in the flotation plant at a very good profit. The benefit of this modified practice promises to amount to about 75 cents per ton more than formerly.

The cost of flotation treatment has proved higher than originally expected, and the mill has not paid expenses until recently.

Battle Mountain.—Producing mines were the Ajax, Carbonate Queen, Coriolanus, Dead Pine, Granite, Gold Coin, Portland, Independence, and Strong.

The twenty-fourth annual report of the Portland Gold Mining Co. for the year ended December 31, 1917 (dated Feb. 18, 1918), says, regarding the mine operations:

During the year shaft No. 2 was sunk an additional 100 feet and the 20th, or water level, was opened up. The ore in the various veins on this level is fully as high grade, if not better than on the 19th level. Ore shoots 717 feet in length have been opened up on the 20th level without the end of such shoots having yet been reached, and the indications are that the tonnage of ore from this level will be fully equal to that of the 19th level.

The showing in the bottom of the 20th level is fully equal to that in the three preceding ones above, and there is little doubt that the ore bodies will continue on down to considerable additional depth, as there is no indication of weakening in the length, width, or value of the ore shoots as disclosed on this level.

The Roosevelt drainage tunnel has reached the Portland property line, and a branch tunnel is now being run from the main tunnel to shaft No. 2. When the tunnel connection with the shaft has been completed, doubtless an arrangement will be made to install a moderate sized electric pumping plant on that level, which will make possible the opening up of several levels below, along the main vein, as the lifting of the limited amount of water found at this depth, to the branch tunnel, will not be excessively expensive, even if continued 500 or 600 feet below the level of the drainage tunnel.

The branch tunnel from the Roosevelt drainage tunnel will take the place of a development drift in that portion of the mine through which it runs. Aside from this, the board of directors has no extensive development or construction work planned for the coming year. * * *

The report of the treasurer shows that during the year 1917, your company made a net earning, not taking into account depreciation and depletion, of $663,254. Dividends amounting to $360,000 were paid during the year, in

Digitized by Google

addition to $393,156 paid on account of the Independence mill construction, leaving a cash balance in the treasury December 31, 1917, of $278,383. The Portland Gold Mining Co. owes nothing, the entire cost of the Independence mill to date having been paid in full. * * *

The accompanying table shows the tonnage, value, and distribution to the different reduction plants, with the average value of the total product treated for the year 1917.

Classification.	Short tons.	Value per ton.	Total value.
Company ore shipped to Colorado Springs plant	56,272	$22.244	$1,251,723.27
Lessee ore shipped to Colorado Springs plant	19,270	18.97	365,683.35
No. 1 Reject to Victor mill	27,721	2.247	62,289.09
No. 2 Reject to Victor Mill	82,141	2.247	184,570.82
Mill dirt from stopes to Victor mill	12,564	2.247	28,231.30
Mill dirt from development to Victor mill	11,837	2.247	26,597.74
No. 2 Dump ore to Victor mill	88,569	2.247	199.014 54
No. 1 Reject to Independence mill	21,327	1.762	37,578 17
No. 1 Dump ore to Independence mill	215,588	1.762	379,866 06
	535,289	4.737	2,535,554.34
Waste to stopes	57,706	.....	.....
	592,995	.....	2,535,554.34

While the showing made the past year has not borne out the predictions made at that time, it must be remembered that we have been and are now operating under the most adverse conditions the gold-mining industry has ever known. Early in the year the effects of the war were noticeable in the labor situation, our best miners quietly leaving the district and going to other camps where special inducements were offered for skilled men. This condition has continued, notwithstanding a wage increase that was asked for and granted early in the summer. Supplies of all kinds have advanced until during the last half of the year the cost of production had increased at least 50 per cent. These conditions are in a measure responsible for the lessened production and the small amount of development work accomplished during the year, and are further reflected in the greater cost per ton of rock handled.

The advisability of sending out of the district to the farming sections for labor was tried with indifferent success. What few men were induced to come were inexperienced and did not take kindly to underground work. So far, the new year does not indicate that the supply of labor or price of supplies will show any decided improvement over the past year.

Digitized by Google

Digitized by Google

ZINC.

(GENERAL REPORT.)

By C. E. Siebenthal.

SUMMARY.

Zinc produced and consumed in the United States, 1911–1917, in short tons.

	1911	1912	1913	1914	1915	1916	1917
Production of primary zinc: [a]							
From domestic ore	271,621	323,907	337,252	343,418	458,135	563,451	584,597
From foreign ore	14,905	14,899	9,424	9,631	31,384	104,005	84,976
	286,526	338,806	346,676	353,049	489,519	667,456	669,573
Production of secondary zinc: [a]							
Redistilled	14,043	26,064	25,991	20,545	29,764	29,663	16,835
Remelted	26,470	26,187	24,014	22,424	23,136	21,037	14,565
	327,039	391,057	396,681	396,018	542,419	718,156	700,973
Apparent consumption of primary zinc.	280,059	340,341	295,370	299,125	364,632	458,428	413,643

[a] "Primary zinc," which is produced directly from ore, is here distinguished from "secondary zinc," which is obtained by refining zinc ashes, skimmings, drosses, and old metals. The statistics of secondary zinc are given on page 860. Wherever in this report the word "zinc" is used without qualification it means primary zinc.

The production of primary zinc from domestic ores in 1917 was 584,597 short tons, valued at $119,258,000, based on the average selling price, as compared with 563,451 short tons, valued at $151,005,000, based on the average selling price, in 1916—an increase of 21,146 tons, or about 4 per cent, in quantity and a decrease of $31,747,000, or about 21 per cent, in value.

INTRODUCTION.

Though the publication of this final report has been so greatly delayed by the press of work growing out of the war that it has value mainly as a statistical record, the essential figures were made available to the public early in 1918.

The statistics of production in this country have been compiled by the United States Geological Survey from confidential reports from each zinc-smelting company in operation during 1917. Statistics of the recovery of secondary zinc were collected from all the important secondary smelters and refiners. The statistics of domestic consumption are taken in part from the smelter returns and in part from the records of the Bureau of Foreign and Domestic Commerce, U. S. Department of Commerce, and the tables for foreign production and consumption were compiled from the sources indicated.

Digitized by Google

PRODUCTION.

ANNUAL PRODUCTION, 1873–1917.

The smelting of zinc in the United States began in an experimental way in 1858,[1] and regular production began in 1860 at the Lehigh Zinc Works in the East and at the Matthiesson & Hegeler works in the West. Between 1864 and 1870 nine or ten other zinc smelters were established. Statistics of production are recorded for the years 1873 and 1875 and for the census year ending May 31, 1880. Annual statistics have been collected by the United States Geological Survey since 1882. The progress of the zinc-smelting industry since 1873 is shown in the following table:

Zinc produced in the United States from domestic and foreign ores, 1873–1917, in short tons.

Year.	From foreign ore.	From domestic ore.	Total.	Year.	From foreign ore.	From domestic ore.	Total.
1873	.....	7,343	7,343	1899	.....	129,051	129,051
1875	.....	15,833	15,833	1900	.....	123,886	123,886
1880 (census year)	.....	23,239	23,239	1901	.....	140,822	140,822
1882	.....	33,765	33,765	1902	.....	156,927	156,927
1883	.....	36,872	36,872	1903	.....	159,219	159,219
1884	.....	38,544	38,544	1904	.....	[a] 186,702	186,702
1885	.....	40,688	40,688	1905	.....	[a] 203,849	203,849
1886	.....	42,641	42,641	1906	25,076	199,694	224,770
1887	.....	50,340	50,340	1907	26,115	223,745	249,860
1888	.....	55,903	55,903	1908	19,675	190,749	210,424
1889	.....	58,860	58,860	1909	25,535	230,225	255,760
1890	.....	63,683	63,683	1910	16,705	252,479	269,184
1891	.....	80,873	80,873	1911	14,905	271,621	286,526
1892	.....	87,260	87,260	1912	14,899	323,907	338,806
1893	.....	78,832	78,832	1913	9,424	337,252	346,676
1894	.....	75,328	75,328	1914	9,631	343,418	353,049
1895	.....	89,686	89,686	1915	31,384	458,135	489,519
1896	.....	81,499	81,499	1916	104,005	563,451	667,456
1897	.....	99,980	99,980	1917	84,976	584,597	669,573
1898	.....	115,399	115,399				

[a] Including an unknown quantity smelted from foreign ore, small in 1904, but larger in 1905.

Zinc produced in the United States, 1906–1917, apportioned according to States in which it was made, in short tons.

Year.	Arkansas.	Illinois.	Kansas.	Oklahoma.	Pennsylvania.	Other States.	Electrolytic zinc.	Total.
1906	.....	47,939	129,564	.....	8,659	38,608	.....	224,770
1907	.....	56,056	134,108	5,035	11,266	43,395	.....	249,860
1908	.....	50,244	99,298	14,864	6,818	39,200	.....	210,424
1909	.....	67,653	103,299	28,782	15,222	40,804	.....	255,760
1910	.....	73,038	105,697	34,760	16,459	39,230	.....	269,184
1911	.....	83,130	98,413	46,315	15,337	43,331	.....	286,526
1912	.....	88,397	101,104	76,925	18,254	54,126	.....	338,806
1913	.....	106,654	74,106	83,214	26,984	55,768	.....	346,676
1914	.....	127,946	44,510	91,367	28,095	61,131	.....	353,049
1915	.....	159,958	101,423	109,208	44,167	74,511	252	489,519
1916	7,503	181,433	141,286	168,206	76,545	82,254	10,229	667,456
1917	25,660	172,489	76,048	204,394	86,995	78,778	25,209	669,573

[1] Ingalls, W. R., Lead and zinc in the United States, p. 314, 1908.

Digitized by Google

ROLLED ZINC.

For many years nearly all the sheet zinc made in the United States was produced by two of the older and larger companies—the Matthiessen & Hegeler Zinc Co., of La Salle, Ill., and the Illinois Zinc Co., in the adjoining town of Peru, Ill. Other companies, particularly the manufacturers of glass fruit jars having zinc tops, have rolled zinc for their own use, and some that furnish sheet zinc to lithographers have also rolled their own zinc. The great demand since the beginning of the war for sheet zinc to line packing cases made for shipment overseas, especially cases containing munitions or other material that is likely to be affected by salt air, has led still other firms into the business of rolling zinc. In addition to the two companies mentioned specifically above the following firms now make rolled zinc: Ball Brothers Glass Manufacturing Co., Muncie, Ind.; Hazel Atlas Glass Co., Wheeling, W. Va.; New Jersey Zinc Co., Palmerton, Pa.; American Zinc Products Co., Greencastle, Ind.; Edes Manufacturing Co., Plymouth, Mass.; E. Phillips & Sons, South Hanover, Mass.; and The Platt Brothers & Co., Waterbury, Conn.

The United States Geological Survey has for many years collected statistics showing the production of zinc, but while the output of rolled zinc was practically limited to that of the two companies in Illinois mentioned above the Survey could not publish statistics showing that output without disclosing individual business. The increase in the number of producers, however, has now made it possible to give these figures. A canvass of the industry by the writer gives the statistics presented in the following table. If the figures showing the exports, as published by the Bureau of Foreign and Domestic Commerce, are subtracted from the figures showing the production, the result will represent the domestic consumption. It should be borne in mind, however, that the sheet zinc used by the Government in shipping munitions overseas is not reported as exported.

Zinc rolled in the United States, 1915–1917.

	1915	1916	1917
Zinc sheets:			
Quantity.....pounds..	69,007,725	65,836,170	75,730,006
Value.....	$9,744,026	$12,280,644	$13,854,600
Average value per pound.....	$0.141	$0.187	$0.183
Boiler plates and special sheets:			
Quantity.....pounds..	2,562,856	3,198,693	6,900,293
Value.....	$345,572	$564,814	$1,111,240
Average value per pound.....	$0.135	$0.177	$0.161
Zinc strips:			
Quantity.....pounds..	20,208,058	28,039,105	35,802,652
Value.....	$2,937,213	$5,008,229	$5,738,285
Average value per pound.....	$0.145	$0.179	$0.16
Total rolled zinc.....pounds..	91,778,639	97,073,968	118,432,951
Total value.....	$13,026,811	$17,853,687	$20,704,125
Average value per pound.....	$0.142	$0.184	$0.175
Rolled zinc exported:			
Quantity.....pounds..	.....	25,024,182	33,027,991
Value.....	.....	$4,540,146	$5,730,792
Average value per pound.....	.....	$0.181	$0.174
Domestic consumption of rolled zinc.....pounds..	.....	72,049,786	85,404,960

The New Jersey Zinc Co. made its first output in 1917, and the American Zinc Products Co. in 1918. Additions to capacity amount-

Digitized by Google

ing to nearly 50 per cent are being made at four of the principal mills to meet the increased demand for zinc for war uses and that which will result from the prevailing strong movement to find and establish new uses for sheet zinc and to extend the present uses. Every such extension, especially the substitution of sheet zinc for sheet copper and brass and for tin plate, will stimulate the zinc market and relieve to some extent the shortage of copper and tin. The War Industries Board ordered the use of sheet zinc instead of galvanized iron or steel for refrigerator linings, a use that was expected to require about 10,000 tons of rolled zinc. Sheet zinc can also be substituted for galvanized iron in roofing, spouting, guttering, garages, household utensils, and hospital ware.

Rolled zinc has always been quoted at so much per pound with discounts and extras for different gages and special sizes and shapes. In 1914, according to Metal Statistics, the base price ranged from 7 to 8.75 cents a pound. In 1915 the price began at 8.75 cents and rose to 33 cents on June 9, fell to 15 cents August 23, and rose to 23 cents at the end of the year. In 1916 the price reached 25.5 cents on April 22, but dropped to 15 cents on July 11 and ended the year at 21 cents. In 1917 the base price of sheet zinc remained nearly stationary, declining to 20 cents on April 25 and to 19 cents on April 26. On February 15, 1918, the base price of zinc sheets was fixed by the Government at 15 cents and the price of rolled zinc plates at 14 cents.

Both the production and the value by classes of product given in the table are subject to slight correction because some producers that sell from a single base price do not keep their sales separated according to classes of product (which are arbitrary anyhow) and were to that extent obliged to make estimates; others, who themselves use the greater part of their output, had to estimate values. But the total production, value, and average price given may be considered accurate. The average price agrees closely with the average price shown by the exporters' manifests.

ZINC DUST.

Zinc dust has been marketed by domestic smelters since 1910. The United States Zinc Co., at Pueblo, Colo., was the first to prepare it for the market; the Grasselli Chemical Co. followed later; and one by one other companies began to save zinc dust, until in 1917 all the companies named below reported production, a small part of which consisted of "atomized" zinc dust made by subjecting a small stream of molten zinc to a blast of air. Some of these companies prepared zinc dust for the first time in 1914–1917 by reason of the high price of zinc dust consequent upon the inability of Belgium and Germany to export any to the United States.

American Zinc & Chemical Co., Langeloth, Pa.
Anaconda Copper Mining Co., Great Falls, Mont.
Bartlesville Zinc Co., Bartlesville, Okla.
Clarksburg Zinc Co., Clarksburg, W. Va.
Grasselli Chemical Co., Clarksburg and Meadowbrook, W. Va.
Illinois Zinc Co., Peru, Ill.
Metals Disintegrating Co., New York, N. Y.
National Zinc Co., Bartlesville, Okla., and Springfield, Ill.
New Jersey Zinc Co., Palmerton, Pa.
United States Smelting Co., Altoona, Kans.
United States Zinc Co., Pueblo, Colo.

Digitized by Google

The following table gives the output of zinc dust since its first production in a commercial way in the United States:

Zinc dust produced in the United States, 1910–1917.

	Short tons.		Short tons.
1910	69	1914	1,004
1911	254	1915	1,755
1912	492	1916	2,609
1913	423	1917	5,913

As will be seen from the table of imports of zinc dust given on page 871, the imports fell off about two-thirds in 1915 and were still smaller in 1916 and 1917, on account of the increased domestic production.

ZINC PIGMENTS.

Zinc forms the base, either in whole or in part, of four white pigments—zinc oxide, leaded zinc oxide, zinc-lead oxide, and lithopone. All of these may be and in the United States the first three usually have been made directly from zinc ore. No zinc-lead oxide has been made since 1909, when the plant at Canon City, Colo., was closed. The output of zinc oxide and leaded zinc oxide has not been disclosed, as it was confined to one very large producer and several smaller ones.

Lithopone is an intimate mixture by chemical precipitation of zinc sulphide and barium sulphate. It may be manufactured from zinc ore, or zinc oxide, but in the United States it is generally made from zinc skimmings, zinc ashes, and scrap zinc. The production of lithophone is growing rapidly, as is shown in the following table. The figures for 1906–1914, inclusive, represent marketed product and those for subsequent years give the total quantity produced.

Lithopone produced in the United States, 1906–1917, in short tons.

1906	4,300	1912	24,220
1907	10,275	1913	29,685
1908	8,292	1914	32,819
1909	14,847	1915	43,422
1910	12,655	1916	58,196
1911	16,866	1917	64,260

The zinc content of the various pigments made in the United States from ore, both domestic and foreign, for the period 1908–1917, is given in the table below. On page 860 a portion of the secondary zinc recovered in the form of pigments is given.

Primary zinc content of zinc pigments made in the United States, 1908–1917, in short tons.

1908	48,004	1913	70,622
1909	54,139	1914	70,619
1910	50,592	1915	79,572
1911	46,122	1916	90,276
1912	64,032	1917	97,573

SECONDARY ZINC.

By the ordinary method of galvanizing, in which the material to be coated is dipped into a bath of molten zinc, there is a great loss of zinc in the form of semioxidized skimmings and of hard zinc drosses,

Digitized by Google

consisting of the alloy formed by the zinc with the iron of the tank and the iron of the article that is being galvanized. The larger galvanizing plants have furnaces to resmelt these skimmings and drosses and to recover the zinc. There are also many small plants and some large ones which make a practice of buying galvanizer's skimmings and drosses and of recovering the zinc. A considerable quantity of old metal in the form of various alloys of zinc with copper and other metals is also worked over and brought up to the desired composition by the addition of new metal. At almost every brass foundry and machine shop in the country it is the custom to remelt and use brass filings, grindings, and scrap copper and brass, and it is manifestly impracticable to attempt to take full account of such material. Some of the zinc smelters running on ore find it advantageous to work in a quantity of secondary material, because the loss of zinc in distillation is practically a fixed quantity per charge, whether the charge is of low or high tenor. If secondary material high in zinc is mixed with low-grade ore, the loss per unit of metal recovered is thereby greatly lessened. Where this is done the smelters make proper returns to the United States Geological Survey, and in these reports prior to 1907 account has been taken of such production, the output being recorded as dross or secondary zinc. As such metal has been recovered by redistillation, it is practically indistinguishable in quality from zinc of ordinary grades made from ore. Several secondary smelters recover zinc from drosses by redistillation, and these plants are included in the list of smelters on a later page. In the table below the secondary zinc recovered by redistillation is separated from that recovered by remelting. The canvass of secondary smelters was made by J. P. Dunlop, of the United States Geological Survey.

Secondary zinc produced in the United States, 1912–1917, in short tons.

	1912	1913	1914	1915	1916	1917
Secondary zinc, redistilled	26,064	25,991	20,545	29,764	29,663	16,835
Secondary zinc, remelted	26,187	24,014	22,424	23,136	21,037	14,565
Recovered zinc in alloys, excluding old brass remelted	3,912	3,743	3,914	5,300	2,600	4,800
Recovered zinc in remelted brass	28,426	25,822	24,759	34,375	61,700	80,000
Secondary zinc recovered as metal	84,589	79,570	71,642	92,575	115,000	116,200
Secondary zinc recovered in pigment	4,619	3,705	6,536	8,323	8,749	9,204
Secondary zinc recovered in zinc chloride [a]	4,903	6,253	6,429	7,860	6,319	6,248
Total secondary zinc	94,111	89,528	84,607	108,758	130,000	132,000

[a] These figures include only the quantity of zinc chloride used in wood preservation and were furnished by courtesy of the Forest Service, Department of Agriculture.

COMPARISON OF PRODUCTION BASED ON SMELTER AND ON MINE REPORTS.

The figures of the production of domestic zinc given in the foregoing pages are compiled from reports from individual zinc smelters. Since 1904 statistics of the production of the more valuable metals in the Western States have been obtained by the United States Geological Survey from reports of individual mines, and since 1907 this compilation has been extended over the whole country. In order

Digitized by Google

to put the smelter production on the same basis as the mine figures, all the zinc which is manufactured into pigments directly from ore (exclusive of the quantity in zinc oxide manufactured from metallic zinc, the inclusion of which would entail its duplication in the totals) is added to the production of metallic zinc. The zinc dust ("blue powder" only, not "atomized" zinc dust—made from metallic zinc—for the reason given above) produced during the year is also included here. The zinc recovered from secondary sources is excluded, for it has already been once reckoned as zinc. These facts must be borne in mind in comparing the subjoined table with the table showing the production of zinc.

Comparison of production of domestic zinc by smelters and by mines, 1907–1917, in short tons.

Year.	Totals compiled from smelter reports.	Totals compiled from mine reports.	Smelter excess.	Mine excess.
1907	280,676	259,951	20,725	.....
1908	238,030	234,526	3,504	.....
1909	283,173	305,423	.....	22,250
1910	303,139	327,712	.....	24,573
1911	315,029	345,260	.....	30,231
1912	386,783	378,816	7,967	.....
1913	408,289	406,416	1,873	.....
1914	424,672	406,959	17,713	.....
1915	539,074	586,491	.....	47,417
1916	656,075	703,317	.....	47,242
1917	686,604	713,359	.....	26,755
	4,521,544	4,668,230	.....	146,686

The smelter totals represent actual recovery and are found by summing up the total production reported by all companies and calculating all pigments and zinc dust back to equivalent metallic zinc on the basis of average analysis of product. In compiling the mine totals each producing operator is requested to report actual quantity of zinc ores and concentrates shipped, and from these returns the zinc content is reckoned by assay value. From that zinc content 10 to 20 per cent, according to the character of the ore, is deducted for smelting losses, and the sum of the remainders thus obtained from all the producing properties in each State gives the total for the State. Where the ore is concentrated at a custom mill, proper allowance is also made for the loss of metal in the process. It is clear that by either method the correctness of the totals is dependent upon complete and correct returns from each producing mine and smelter. It is further essential to the correctness of the mine totals that the assay content and the theoretical recovery be correctly estimated. The totals, as compiled from smelter reports and from mine reports, respectively, should be in reasonable agreement. As a matter of fact, for any year they show considerable divergence. These discrepancies, giving rise to "smelter excess" or "mine excess," may be the result of one cause or of a combination of causes, among which are lag in the smelting of the ore, resulting in accumulation of ore stocks at the smelters; lag in the mining, owing to which the smelter depletes its ore stocks; error in calculating metallic content from assay and in estimating recovery.

Digitized by Google

The smelter reports give the exact annual production of zinc and serve as a check on the mine production, and they also give the form in which the zinc was recovered, whether as metal or as pigment. For more exact statements of distribution of zinc production according to origin, recourse must be had to the reports of production by mines.

MINE PRODUCTION.

Mine production of zinc in the United States, 1908–1917, in short tons.

State.	1908	1909	1910	1911	1912	1913	1914	1915	1916	1917
Arizona	339	2,969	2,742	2,281	4,379	4,714	4,896	9,110	9,839	10,447
Arkansas	605	510	994	664	748	478	608	3,209	6,815	6,691
California	.....	.....	.....	1,404	2,173	529	195	6,547	7,628	5,436
Colorado	15,065	25,605	38,545	47,334	66,111	59,673	48,387	52,227	67,143	60,158
Idaho	19	676	2,802	4,170	6,953	11,587	21,006	35,077	43,253	39,927
Illinois	1,717	2,163	3,549	4,219	4,065	2,236	4,811	5,534	3,404	4,267
Iowa	395	35	96	.....	.....	.....	.....	.....	21	18
Kansas	14,119	11,445	13,229	10,272	10,633	10,088	11,284	14,365	12,448	20,249
Kentucky	.....	56	6	158	491	327	230	764	1,096	751
Missouri	107,404	130,162	128,589	122,515	136,551	124,963	105,994	136,300	155,960	132,918
Montana	820	4,630	15,819	21,935	13,459	44,337	55,790	93,573	114,630	93,130
Nevada	558	1,507	1,354	1,774	6,661	7,210	6,490	12,188	16,222	11,154
New Hampshire	.....	.....	.....	.....	.....	15	6	24	36	45
New Jersey	67,165	82,510	68,678	77,445	69,755	72,156	74,253	116,618	112,020	120,846
New Mexico	1,788	6,543	9,044	5,119	6,783	8,262	9,202	12,702	18,285	15,100
New York	.....	.....	.....	81	.....	.....	.....	2,455	4,507	5,192
North Carolina	.....	.....	.....	.....	142	10	.....	.....	.....	.....
Oklahoma	4,529	7,806	6,394	5,159	5,769	11,664	13,992	14,314	28,754	85,835
Tennessee	344	596	966	1,117	2,191	5,583	10,425	16,461	26,428	28,498
Texas	18	.....	.....	.....	119	326	108	15	116	11
Utah	730	4,939	8,184	8,920	8,534	9,429	7,995	12,146	14,786	10,643
Virginia	705	58	794	1,032	249	2,719	174	1,267	2,276	1,703
Washington	.....	.....	.....	10	.....	.....	.....	122	847	598
Wisconsin	18,206	23,152	25,927	29,720	33,050	30,110	31,113	41,403	56,803	59,742
	234,526	305,423	327,712	345,260	378,816	406,416	406,959	586,491	703,317	713,359

The following table shows for each zinc-producing State the total quantity of zinc ore produced and the output of each kind of zinc-bearing ore. The column headed "All other ore" includes lead ore, copper ore, copper-lead ore, and dry or siliceous ore, no zinc of consequence being recovered from any of them except in California and Colorado. "Dry" ores produced in Colorado in 1917 contained 1,549 short tons of recoverable zinc. Copper-zinc ores produced in California contained 3,459 tons of recoverable zinc. These ores, however, were concentrated from parts of the ore from certain counties and were not distributed through the whole of the "All other ore" credited to those States in 1917. The total crude ore yielding either gold, silver, copper, lead, or zinc is given for each zinc-producing State, so that a comparison may be made of the relative extent of deep mining operations for all five metals in these States, the quantity of crude ore raised being the best measure for this purpose. The table discloses the fact that Missouri produced a little more than one-fifth of the crude-ore output of the zinc-producing States, her production being 17,024,000 short tons of crude ore, of which 11,136,100 tons was zinc-lead ore. Exclusive of iron ore, this was the largest production of metalliferous crude ore in the United States. Next in rank was Arizona, with 15,770,193 tons of crude copper ore; Utah ranked third, with 15,358,481 tons of crude ore. Michigan, which formerly ranked second in quantity of crude ore raised, was fourth in 1917, with 12,400,723 tons.

Digitized by Google

The table gives also the quantity of recoverable zinc contained in the crude ores of each State and the quantity of zinc recovered from each kind of zinc ore. The percentage of recoverable zinc contained in the zinc ore and the zinc-lead ore of each State is also shown. The recoverable zinc content of crude-zinc ore ranged from 42.4 per cent for a small quantity produced in California down to 2.1 per cent in Tennessee; the Western States show uniformly the higher percentages. The zinc-lead ore of Missouri averaged 1.2 per cent of recoverable zinc—the leanest average shown by zinc-bearing ore worked in any State in 1917. The average recoverable zinc content of the zinc ore of the United States in 1917 was 9 per cent, and of the zinc-lead ore was 2.2 per cent. Of the total mine production of zinc in 1917, a quantity corresponding to 31.7 per cent was derived from zinc ore, 67.5 per cent from zinc-lead ore, and 0.8 per cent from all other ores. The figures of mine production of zinc are taken from the chapters on gold, silver, copper, lead, and zinc (mine production) in the various States, as indicated in the prefatory note.

Mine production of zinc in the United States in 1917, in short tons.

State.	Zinc ore.			Zinc-lead ore.			All other ore.		Total.	
	Crude ore.	Recoverable zinc content.		Crude ore.	Recoverable zinc content.		Crude ore.	Recoverable zinc content.	Crude ore.	Recoverable zinc content.
		Quantity.	Percentage.		Quantity.	Percentage.				
Arizona	62,839	5,309	8.5	49,071	4,738	9.7	15,658,283	400	15,770,193	10,447
Arkansas	203,600	6,691	3.3						203,600	6,691
California	125	53	42.4	26,501	1,924	7.3	2,976,624	3,459	3,003,250	5,436
Colorado	140,455	23,791	16.9	412,371	34,818	8.4	2,135,880	1,549	2,688,706	60,158
Idaho	19,269	5,412	28.1	1,118,075	34,515	3.1	1,621,163		2,758,507	39,927
Illinois				327,340	4,267	1.3	(a)		a 327,340	4,267
Iowa				b 1,000	18	1.8			b 1,000	18
Kansas				903,400	20,249	2.2			903,400	20,249
Kentucky	b 9,000	751	8.3				(a)		a b 9,000	751
Missouri				11,136,100	132,918	1.2	5,887,900		17,024,000	132,918
Montana	258,846	17,016	6.6	726,280	76,051	10.5	5,322,038	63	6,307,164	93,130
Nevada	18,393	5,909	32.1	27,943	5,245	18.8	6,427,183		6,473,519	11,154
New Hampshire				3,000	45	1.5			3,000	45
New Jersey	727,496	120,846	16.6						727,496	120,846
New Mexico	135,129	14,406	10.7	10,899	694	6.4	4,430,799		4,576,827	15,100
New York	47,961	5,192	10.8						47,961	5,192
Oklahoma				3,523,200	85,835	2.4			3,523,200	85,835
Tennessee	883,341	18,239	2.1	61,638	10,259	16.6	589,004		1,533,983	28,498
Texas	40	11	27.5				52,342		52,382	11
Utah	6,535	1,832	28.0	421,704	8,811	2.1	14,930,242		15,358,481	10,643
Virginia	990	328	33.1	34,211	1,375	4.0	350		35,551	1,703
Washington	114	22	19.3	14,953	576	3.9	157,052		172,119	598
Wisconsin				3,014,800	59,742	2.0			3,014,800	59,742
	2,514,133	225,808	9.0	21,812,486	482,080	2.2	60,188,860	5,471	84,515,479	713,359
Percentage of total zinc derived from each kind of ore		31.7			67.5			0.8		100.0

a Exclusive of fluorspar. b Estimated.

Mining districts are established with little heed to the artificial restrictions of political boundaries and may include parts of adjacent States. The following table has been compiled to show the production of zinc in the principal districts so that they may be compared as to extent of zinc mining operations, as shown by the output of crude ore; as to character of ores, whether sulphide or oxidized; and, finally, as to relative rank as zinc producers.

Digitized by Google

Districts in the United States producing more than 1,000 short tons of recoverable zinc in 1917.

District.	State.	1917								1915
		Crude zinc-bearing ore sold or treated (short tons).	Shipping ore and concentrates (short tons).					Total recoverable zinc content (short tons).	Percentage of total production.	Total recoverable zinc content (short tons).
			Total quantity.	Sulphides.		Carbonates and silicates.				
				Quantity.	Recoverable zinc content.	Quantity.	Recoverable zinc content.			
1. Joplin	Missouri	3,447,850	262,095	231,402	121,742	30,693	10,988	132,730	18.6	.....
	Kansas	903,400	38,787	38,766	20,242	21	7	20,249	2.8	.....
	Oklahoma	3,523,200	159,780	159,656	85,744	124	45	85,789	12.0	.....
		7,874,450	460,662	429,824	227,728	30,838	11,040	238,768	33.4	164,544
2. Franklin Furnace	New Jersey	727,496	609,282	.....	.....	609,282	120,846	120,846	17.0	116,618
3. Butte	Montana	892,362	287,027	287,027	90,158	.....	.....	90,158	12.6	93,281
4. Upper Mississippi Valley	Wisconsin	3,014,800	226,216	223,916	59,190	2,300	552	59,742	8.4	.....
	Illinois	327,340	18,221	18,221	4,267	.....	.....	4,267	.6	.....
	Iowa	600	60	.....	.....	60	18	18	.....	.....
		3,342,740	244,497	242,137	63,457	2,360	570	64,027	9.0	46,937
5. Coeur d'Alene	Idaho	1,126,606	113,802	113,802	38,862	.....	.....	38,862	5.5	34,843
6. Leadville	Colorado	218,183	218,183	148,945	19,569	69,238	10,558	30,127	4.2	36,212
7. East Tennessee	Tennessee	939,052	67,108	35,708	18,202	31,405	10,296	28,498	4.0	16,461
8. Other Colorado[a]	Colorado	196,178	76,511	[b] 76,511	24,330	.....	.....	24,330	3.4	12,489
9. New Mexico	New Mexico	146,028	62,573	[b] 62,573	15,100	.....	.....	15,100	2.1	12,691
10. Yellow Pine	Nevada	88,655	34,386	.....	.....	34,386	10,267	10,267	1.4	10,530
11. Wallapai (Union Basin)	Arizona	101,796	25,309	25,309	8,564	.....	.....	8,564	1.2	8,691
12. Northern Arkansas	Arkansas	203,600	17,969	916	482	17,053	6,209	6,691	1.0	3,209
13. Edwards	New York	47,961	12,466	12,466	5,192	.....	.....	5,192	0.7	2,455
14. Shasta	California	167,146	11,250	11,250	3,160	.....	.....	3,160	0.5	4,199
15. Park City	Utah	133,231	8,211	8,211	2,601	.....	.....	2,601	0.4	3,886
16. Bingham	.....do	175,378	8,880	8,880	2,302	.....	.....	2,302	0.3	2,746
17. San Francisco	.....do	47,883	4,970	4,970	1,769	.....	.....	1,769	0.3	1,412
18. Southern Virginia	Virginia	44,000	9,700	2,841	761	6,859	942	1,703	0.2	1,267
19. Cerro Gordo	California	6,400	6,400	.....	.....	6,400	1,685	1,685	0.2	2,328
20. Cataract	Montana	17,965	6,081	6,081	1,678	.....	.....	1,678	0.2	.....
		16,447,110	2,285,267	1,477,446	523,915	807,821	172,413	696,328	97.6	574,749
All other districts		.....	.....	.....	.....	.....	.....	17,031	2.4	11,742
Total for United States		.....	.....	.....	.....	.....	.....	713,359	100.0	586,491

[a] Red Cliff, Breckenridge, Eureka, and Elk Mountain.

[b] Includes carbonates.

Digitized by Google

ZINC-REDUCTION PLANTS.

ELECTROLYTIC PLANTS.

Electrolytic zinc plants in the United States and Canada at the end of 1917.

Company.	Location of plant.	Daily capacity.	Remarks.
UNITED STATES.			
American Smelting & Refining Co.	Murray, Utah	Experimental	Operated in 1916; idle in 1917.
Anaconda Copper Mining Co.	Anaconda, Mont	25 tons	Idle in 1917.
Do.	Great Falls, Mont	150 tons	Operated in 1917.
Basin Salvage Co.	Basin, Mont.	Experimental	Do.
Ducktown Sulphur, Copper & Iron Co.	Isabella, Tenn.	1 ton	Experimental in 1917.
Electrolytic Zinc Co.	Baltimore, Md	10 tons	Operated in 1917.
Judge Mining & Smelting Co.	Park City, Utah	15 tons	Do.
Mammoth Copper Mining Co.	Kennett, Calif.	25 tons	Began production October, 1917.
River Smelting & Refining Co.	Keokuk, Iowa	10 tons	Operated in 1917.
CANADA.			
Consolidated Mining & Smelting Co. (Ltd.).	Trail, British Columbia	50 tons	Operated in 1917.
Zinc Co. (Ltd.)	Shawinigan Falls, Quebec.	5 tons	Do.
French Complex Ore Reduction Co.	Frank, British Columbia	Experimental	Do.

The output of electrolytic zinc in the United States in 1917 was 26,910 short tons, of which 25,209 tons was made from ore and 1,701 tons was refined from prime western metal. The output in 1916 was 12,916 tons.

The output in Canada in 1917 was 9,985 tons, as compared to 2,974 tons in 1916, the first year of production.

Digitized by Google

ZINC SMELTERS.

The following table gives the zinc-smelting capacity of the United States on December 31, 1916, and June 30, and December 31, 1917, as well as the retorts under construction or contemplated at the end of the year. The plants marked "A" operate sulphuric-acid plants, either at the smelter or elsewhere, as indicated in the footnotes.

Zinc smelters in the United States, 1916 and 1917.

	Location of works.	Retorts at end of 1916.	Retorts, June 30, 1917.	Retorts at end of 1917.
ARKANSAS.				
Arkansas Zinc & Smelting Corporation	Van Buren	3,200	3,200	3,200
Athletic Mining & Smelting Co	Fort Smith	.....	1,664	2,496
Fort Smith Spelter Co	....do	2,560	2,560	2,560
		5,760	7,424	8,256
COLORADO.				
United States Zinc Co	Pueblo	1,984	2,290	1,968
ILLINOIS.				
American Zinc Co. of Illinois (A)	Hillsboro	4,864	4,864	4,864
Collinsville Zinc Smelter	Collinsville	2,304	2,300	2,304
Granby Mining & Smelting Co. (A)	East St. Louis	4,820	5,620	5,620
Hegeler Zinc Co. (A)	Danville	5,400	5,400	5,400
Illinois Zinc Co (A)	Peru	4,640	5,440	5,440
Matthiesson & Hegeler Zinc Co. (A)	La Salle	6,168	6,168	6,168
Missouri Zinc Co	Beckemeyer	352	302	352
Mineral Point Zinc Co (A)[a]	Depue	9,068	9,068	9,068
National Zinc Co. (A)[b]	Springfield	4,480	4,480	4,480
Robert Lanyon Zinc & Acid Co. (A)	Hillsboro	3,200	3,200	3,200
Sandoval Zinc Co	Sandoval	672	672	672
		45,968	47,514	47,568
INDIANA.				
Grasselli Chemical Co (A)	Terre Haute	.....	.....	3,360
KANSAS.				
American Spelter Co	Pittsburg	992	992	992
American Zinc, Lead & Smelting Co	Caney	6,080	6,080	6,080
Do	Dearing	4,480	4,480	4,480
Chanute Spelter Co	Chanute	1,280	1,280	(c)
Cherokee Smelting Co	Bruce	896	896	896
Edgar Zinc Co	Cherryvale	4,800	5,040	5,040
Granby Mining & Smelting Co	Neodesha	3,760	3,760	3,760
Iola Zinc Co	Concreto	1,320	1,320	(c)
Joplin Ore & Spelter Corporation	Pittsburg	1,792	1,992	1,992
Lanyon Smelting Co	....do	448	448	448
Owen Zinc Co	Caney	1,920	1,920	1,920
Pittsburg Zinc Co	Pittsburg	910	910	910
Prime Western Spelter Co. (A)[d]	Iola	2,696	2,696	2,696
Do	Gas	2,170	2,170	2,170
United States Smelting Co	Altoona	4,600	4,600	(c)
Do	Iola	3,440	3,440	3,440
Do	La Harpe	1,926	1,926	(c)
Weir Smelting Co	Weir	288	448	448
		43,800	44,398	35,272

[a] The Mineral Point Zinc Co. also operates an acid plant at Mineral Point, Wis.
[b] The National Zinc Co. has zinc-roasting furnaces at Argentine, Kans., where the sulphur gases are utilized in an acid plant, the roasted concentrates being shipped to the smelter at Springfield, Ill.
[c] Plant dismantled.
[d] The Prime Western Spelter Co. has roasting furnaces and an acid plant at Tiltonville, Ohio.

Digitized by Google

Zinc smelters in the United States, 1916 and 1917—Continued.

	Location of works.	Retorts at end of 1916.	Retorts, June 30, 1917.	Retorts at end of 1917.
MISSOURI.				
Edgar Zinc Co.	St. Louis	2,000	1,982	1,982
Missouri Zinc Smelting Co.	Rich Hill	448	448	448
Nevada Smelting Co.	Nevada	672	672	672
		3,120	3,102	3,102
OKLAHOMA.				
Bartlesville Zinc Co.	Bartlesville	6,336	6,336	6,336
Do.	Blackwell	9,600	9,600	9,600
Do.	Collinsville	13,440	13,440	13,440
Bartlesville Zinc Co. (Lanyon-Starr plant)	Bartlesville	3,456	3,456	3,456
Eagle-Picher Lead Co.	Henryetta	4,000	4,000	4,000
Henryetta Spelter Co.	do.	3,000	3,000	3,000
Kusa Spelter Co.	Kusa	7,720	7,720	7,720
National Zinc Co.	Bartlesville	4,970	4,970	4,970
Oklahoma Spelter Co.	Kusa	1,600	1,600	1,600
Quinton Spelter Co.	Quinton	1,344	2,016	2,016
Tulsa Fuel & Manufacturing Co.	Collinsville	6,232	6,232	6,232
United States Smelting Co.	Checotah	5,120	5,120	5,120
United States Zinc Co.	Sand Springs	8,000	10,992	8,000
Western Spelter Co.	Henryetta	2,400	.....	2,648
		77,218	78,482	78,138
PENNSYLVANIA.				
American Steel & Wire Co. (A)	Donora	9,120	9,120	9,120
American Zinc & Chemical Co. (A)	Langeloth	7,296	7,296	7,296
New Jersey Zinc Co. (of Pennsylvania)	Palmerton	7,200	7,200	7,200
		23,616	23,616	23,616
WEST VIRGINIA.				
Clarksburg Zinc Co.	Clarksburg	3,648	3,648	3,648
Grasselli Chemical Co. (A)[a]	do.	5,760	5,760	5,760
Do.	Meadowbrook	8,544	8,544	8,544
United Zinc Smelting Corporation (A)	Moundsville	.....	.....	1,728
		17,952	17,952	19,680
		219,418	224,778	220,960
PLANTS WITH SPECIAL RETORTS.[b]				
Eastern Zinc Refining Co.	Brooklyn, N. Y.	8	16	16
John Finn Metal Works	San Francisco, Calif.	2	2	2
Michael Hayman & Co.	Buffalo, N. Y.	12	12	12
M. M. S. Metal Co.	Trenton, N. J.	21	15	21
Trenton Smelting & Refining Co.	do.	96	80	60
William Cramp & Sons Ship & Engine Building Co.	Philadelphia, Pa.	32	32	32
Total large retorts.		171	157	143

[a] The Grasselli Chemical Co. operates acid plants in connection with its zinc-roasting furnaces at Grasselli, Ind., Cleveland, Canton, and Lockland (near Cincinnati), Ohio, and Newcastle, Pa., the roasted zinc concentrates being shipped to the smelters at Terre Haute, Ind., and Clarksburg and Meadowbrook, W. Va.

[b] Large graphite retorts yielding 600–800 pounds of zinc per charge.

The foregoing list includes a few retort smelters that treat only secondary materials, such as zinc ashes, skimmings, and galvanizers' drosses; also a few that recover about equal quantities of zinc from ores and from secondary materials, as well as several more that treat minor quantities of secondary materials. Several other zinc-smelting plants in the country obtain zinc by the distillation of zinc ashes

Digitized by Google

and drosses in large graphite crucibles and condensers somewhat similar to those used in the Faber du Faur furnaces for recovering zinc from the zinc crusts in lead desilverization. These are given at the bottom of the list.

ZINC-SMELTING CAPACITY AND CHANGES IN 1917.

The number of retorts at zinc smelters at the end of 1916 was 219,418, and 13,632 additional retorts were being built or were planned, making a total of 233,050. The number of retorts on June 30, 1917, was 224,778, and 11,944 additional retorts were being built or were planned, making a total of 236,722. Of the total number of retorts at smelters on June 30, only 189,561 were reported to be in operation. Of the total 220,960 retorts at the end of the year, 132,794, or 60 per cent, were reported in active operation on December 31, 1917.

Three zinc smelters, having 7,584 retorts, were completed in 1917. These were the plant of the Athletic Mining & Smelting Co., at Fort Smith, Ark., the plant of the Grasselli Chemical Co., at Terre Haute, Ind., and that of the United Zinc Smelting Corporation, at Moundsville, W. Va. The last plant was designed for 6,912 retorts, but only 1,728 were completed and these were not operated until 1918. The acid plant was in operation in 1917, however, the roasted concentrates being smelted at the Clarksburg plant. Another acid unit is planned. One block of 840 retorts was still under construction at Terre Haute at the end of 1917. A block of 800 retorts was added by the Illinois Zinc Co., at Peru, Ill., and another of the same size was added to the East St. Louis plant of the American Zinc, Lead & Smelting Co. A block of 672 retorts was added at Quinton, Okla. In spite of the addition of more than 10,000 retorts the total at the end of 1917 was 220,960 retorts as compared with 219,418 at the close of 1916, a very small net increase, owing to the dismantling of several smelters in Kansas. It is difficult to ascertain at this time whether a zinc smelter is temporarily or permanently abandoned and hence retort totals are to a certain extent unreliable. Announcement has recently been made that the historic plant of the Edgar Zinc Co., at Carondelet, a surburb of St. Louis, Mo., is closed, never to be reopened. This, a combination of the plants of the old Glendale Zinc Co. and the Carondelet Zinc Co., was one of the first zinc smelters to be built in the Mississippi Valley. It is likely that many other plants in Missouri, Kansas, and Oklahoma, now idle, will never be operated again.

TRADE CONDITIONS.

WORLD'S PRODUCTION.

Owing to the disturbed conditions in Europe, complete figures of the world's production of zinc in 1914–1916 can not be given. It is hoped that better figures will be available for the chapter on zinc for 1918.

Digitized by Google

IMPORTS AND EXPORTS.

The following tables of imports and exports of zinc and of zinc remaining in warehouse are made up from the publications and records of the Bureau of Foreign and Domestic Commerce of the Department of Commerce.

WAREHOUSE TRANSACTIONS.

Zinc imported into the United States as metal or in ore may be entered for immediate consumption, in which case the duty is paid and the zinc goes direct to the importer; or it may be entered for warehouse, bond being given for double the amount of the estimated duty. In accordance with the usage of the Bureau of Foreign Commerce, the term "General imports" in the accompanying tables indicates the total zinc imports, including both zinc articles entered for immediate consumption on arrival and zinc articles entered for warehouse, as distinguished from "Imports for consumption," embracing zinc imports entered for immediate consumption and zinc withdrawals from warehouse for consumption. The statement of general imports and the statement of imports for consumption for any period will differ to the extent that the entries for warehouse for the period differ from withdrawals from warehouse for consumption.

From warehouse the zinc ore may be withdrawn for consumption by payment of duty, or it may be exported from warehouse as ore, or it may be melted in bond, the metal finally being either withdrawn for consumption or exported from warehouse with cancellation of bond. In the table of imports for consumption the imports are expressed in the terms under which they were originally entered. The zinc imported for consumption may be actually used in the country or it may be manufactured and exported, in which case the manufacturer is entitled to the benefit of a drawback of 99 per cent of the duties paid. In the table showing foreign zinc exported in manufactures with benefit of drawback the zinc is shown in the form in which it was originally imported, because, on account of diversity of manufactured form, it is not feasible to show the articles actually exported. The foreign zinc given in the table (p. 876) as exported from warehouse is likewise shown in the form in which it was imported and entered for warehouse. Foreign zinc exported from warehouse has, since July 1, 1915, been included by the Bureau of Foreign and Domestic Commerce in the domestic exports as "from foreign ore."

The items foreign zinc exported from warehouse, domestic exports of zinc "from foreign ore," and foreign zinc exported in manufactures with benefit of drawback make up the total foreign zinc going out of the country. For the sake of simplicity this foreign zinc is carried on the records of the bonded customs warehouse in the form in which the zinc was entered until the bond is canceled. It must be clearly understood, therefore, that the zinc listed in the table of foreign exports of zinc, on a later page, was not exported as zinc content of ore but as metal smelted from the ore. This has been shown in the Monthly Summary of the Bureau of Foreign and Domestic Commerce since July, 1915, as noted above.

Digitized by Google

No record is kept of the zinc in the form in which it is actually exported, except for that portion of the articles manufactured from foreign zinc and exported with benefit of drawback. For articles not wholly made of zinc it would be useless to give weights; but each shipment on which drawback is claimed is accompanied by a manifest of the imported zinc used in making the articles and the duty paid thereon. From these manifests is derived the statement of the total quantity of foreign zinc used in manufactures exported with the benefit of drawback. For this reason the zinc is given in the form in which it was imported.

ZINC REMAINING IN WAREHOUSE.

The following table is taken from the reports of the Bureau of Foreign and Domestic Commerce. For the reasons already given the zinc is shown in the terms in which it was imported. For instance, a considerable part of the zinc stated as remaining in ore doubtless represents metal waiting at the bonded zinc smelter for a favorable market for shipment. If this is borne in mind the table gives an idea of the fluctuation of stocks of foreign zinc.

The quantity of zinc remaining in warehouse at the end of each year prior to 1909 has been negligible, but since all zinc ore became dutiable, on August 6, 1909, the quantity of bonded zinc has largely increased. The large imports of foreign zinc ore on account of the demand for munitions greatly swelled the quantity remaining in warehouse December 31, 1915 and 1916, as will be seen in the accompanying tables.

Practically all the zinc in ore remaining in warehouse prior to 1915 was credited to the port of Kansas City, Mo., and was in possession of the bonded zinc smelters of Kansas and Oklahoma. In 1915–1917 eastern zinc smelters were important consumers of foreign ores, and at the end of these years considerable ore remained in warehouse in that section.

Zinc remaining in warehouse in the United States, Dec. 31, 1909–1917.

Year.	Ore and calamine.			Blocks, pigs, and old.		Zinc dust.[a]	
	Quantity (short tons).	Zinc content (pounds).	Value.	Quantity (pounds).	Value.	Quantity (pounds).	Value.
1909	2,813	2,255,341	$36,384	78,667	$4,021	.....	.....
1910	2,603	2,572,122	61,730	61,146	3,406	.....	.....
1911	10,177	6,978,098	137,055	63,454	4,049	.....	.....
1912	3,076	2,479,465	62,089	.....	.....	310,715	$13,072
1913	7,531	1,930,425	68,726	.....	.....	291,613	14,008
1914	6,728	6,087,676	90,257	221,994	11,100	272,915	13,005
1915	63,168	43,691,611	1,628,509	63,892	4,028	115,375	8,815
1916	82,227	57,259,940	2,210,286	180,026	14,301	120,921	12,989
1917	96,560	53,997,636	1,177,680	63,545	3,949	64,812	5,710

[a] Not separately recorded prior to 1912.

The figures for 1910–1912 are exclusive of the zinc contained in certain other ores entered at New York, as explained later in the discussion of the table of general imports of zinc.

Digitized by Google

IMPORTS.

Zinc imported and entered for consumption in the United States, 1902–1917.

Year.	Blocks or pigs.		Sheets.		Old.		Value of manufactures.	Total value.
	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.		
1902	448	$36,536	68	$8,339	157	$8,299	$32,708	$85,882
1903	202	19,161	120	8,537	163	11,772	10,376	49,846
1904	341	34,211	17	2,230	36	3,247	10,304	50,082
1905	428	46,285	14	1,953	86	5,110	8,253	61,611
1906	1,021	240,632	22	3,236	79	7,647	2,904	254,419
1907	1,709	220,474	52	7,158	122	8,582	8,516	244,730
1908	776	78,110	37	4,570	37	2,014	5,645	90,389
1909	9,419	805,087	117	13,510	238	9,999	6,488	835,084
1910	989	95,410	262	36,641	257	17,549	1,526	151,126
1911	323	38,322	296	55,211	104	8,609	7,981	110,123
1912	10,719	1,239,574	728	102,073	147	13,748	8,489	1,363,884
1913	5,165	565,215	223	43,497	275	17,850	5,474	632,036
1914	195	21,140	277	32,004	388	21,512	4,464	84,120
1915	63	16,864	65	14,407	729	103,294	622	135,187
1916	21	4,436	2	432	642	112,254	829	117,951
1917	13	2,279	73	16,570	250	25,974	220	45,073

Zinc dust, zinc oxide, and lithopone imported and entered for consumption in the United States, 1910–1917.

Year.	Zinc dust.		Zinc oxide.				Lithopone.	
			Dry.		In oil.			
	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.
1910	1,403	$136,749	3,069	$365,701	197	$30,874	1,863	$99,954
1911	1,713	177,420	2,506	316,972	274	40,494	3,178	166,199
1912	2,736	306,061	2,675	342,985	262	43,168	2,952	153,303
1913	2,368	248,482	3,291	410,403	142	23,663	2,533	152,980
1914	2,004	191,582	2,461	279,642	168	23,196	4,036	277,822
1915	707	137,474	853	148,220	29	5,929	2,126	144,567
1916	522	230,380	447	181,319	18	4,076	2,372	414,592
1917	233	48,604	119	52,649	5	876	229	35,718

General imports of old brass fit only for remanufacture, 1904–1917.

[Average composition about one-third zinc and two-thirds copper.]

Year.	Quantity (short tons).	Value.	Year.	Quantity (short tons).	Value.
1904	1,330	$310,311	1911	1,803	$445,116
1905	4,838	1,189,320	1912	3,298	689,045
1906	6,469	1,891,126	1913	4,363	907,521
1907	3,979	1,344,753	1914	2,565	487,542
1908	1,357	355,335	1915	8,354	1,809,550
1909	2,336	579,454	1916	22,976	6,578,809
1910	3,072	786,684	1917	27,580	9,931,721

Two tables which show the importation of zinc ores are given below. The first one shows the zinc ores imported and entered for consumption under the tariff act of 1909, when different grades of ore bore different duties, and also shows the imports under the tariff act of 1913, which levies an ad valorem duty, thus making one class of all

Digitized by Google

grades of zinc ore. The other table shows the general imports of zinc by countries. The difference between general imports and imports for consumption has been explained on page 869.

Zinc ore and calamine imported and entered for consumption, 1909–1917.

Year.	Containing less than 10 per cent of zinc (duty free).		Containing from 10 to 20 per cent of zinc (duty, ½ cent per pound).		Containing from 20 to 25 per cent of zinc (duty ½ cent per pound).		Containing 25 per cent or more of zinc (duty, 1 cent per pound).[a]	
	Zinc content (short tons).	Value.	Zinc content (short tons).	Value.	Zinc content (short tons).	Value.	Zinc content (short tons).	Value.
1909[b]			167	$8,690	113	$5,632	4,605	$161,430
1910	16	$698	87	4,053	1,178	25,127	19,961	713,684
1911	39	1,411	189	8,705	564	16,914	3,349	120,756
1912	22	1,141	56	3,045	458	6,734	10,328	433,570
1913			[b] 45	2,067	[c] 309	4,395	[c] 4,093	193,014
1914							5,548	149,503
1915							16,282	1,312,383
1916							55,796	3,836,414
1917							33,517	1,123,534

[a] Includes all classes after Oct. 4, 1913.
[b] For period July 1–Dec. 31 only.
[c] For period Jan. 1–Oct. 3, 1913; Oct. 4–Dec. 31, included in class "containing 25 per cent or more of zinc."

The statistics of general imports as published by the Bureau of Foreign and Domestic Commerce are based on "consular invoice" or "declaration," which is only a close approximation to actual weights and values. The true weights and values of all dutiable articles are determined when the duties are paid, and the correction is applied as "additions by liquidation" or "deductions by liquidation." On free articles this correction is not made. Prior to 1909 zinc ore was in large part undutiable, and in that part of 1909 prior to August 6 a portion of the imports of zinc ore was free. The correction by liquidation for the dutiable zinc ore imported during 1909–1912 is available, but, owing to special instructions followed in one customs district, to apply the correction by liquidation would result in a considerable duplication of imports. The following figures are taken directly from the Monthly Summary of the Bureau of Foreign and Domestic Commerce without the liquidation correction:

General imports of zinc ore into the United States, 1904–1917.

1904–1913.

Year.	Canada.		Mexico.		Total.	
	Ore (short tons).	Zinc content (short tons).	Ore (short tons).	Zinc content (short tons).	Ore (short tons).	Zinc content (short tons).
1904			2,264		2,264	
1905	4,063		18,074		22,137	
1906	423		59,991		55,414	
1907	1,112		102,005		103,117	
1908	7,406		46,351		53,757	
1909	10,024		104,826		114,850	
1910	4,749	1,922	67,818	23,517	72,626	25,439
1911	2,359	947	35,847	14,986	38,116	15,933
1912	8,015	3,661	35,925	14,206	43,940	17,567
1913	8,889	3,498	17,476	6,160	31,406	13,497

Digitized by Google

General imports of zinc ore into the United States, 1904–1917—Continued.

1914–1917.

Country.	1914			1915		
	Ore (short tons).	Zinc content (short tons).	Value.	Ore (short tons).	Zinc content (short tons).	Value.
Canada	11,250	4,467	$143,247	11,992	4,710	$177,868
Mexico	20,705	7,663	239,399	57,699	17,804	2,130,014
France						
Spain						
Italy				5,312	2,125	153,388
French Africa						
French East Indies						
China and Hongkong				5,880	2,738	119,913
Japan				1,369	499	77,899
Australia				76,419	29,723	1,843,801
Other countries	7	2	97	190	69	7,663
	31,962	12,132	382,743	158,852	57,668	4,510,546

Country.	1916			1917		
Canada	21,908	8,790	$567,259	16,589	5,155	$338,668
Mexico	161,271	51,028	5,779,564	145,358	45,697	2,837,211
France	3,884	1,422	56,542			
Spain	55,965	23,081	1,550,334	14,778	6,083	260,922
Italy	12,550	5,783	394,782	5,919	2,411	117,271
French Africa	4,480	1,857	129,153	1,245	623	66,346
French East Indies	1,653	746	55,407			
China and Hongkong	9,641	4,568	344,192			
Japan						
Australia	113,862	50,601	3,223,184	27,730	12,503	753,598
Other countries	750	271	20,968	6	2	42
	385,964	148,147	12,121,385	211,595	72,474	4,374,058

The foregoing figures showing imports of zinc ore in 1910 do not include 10,431 short tons of ore that carried 2,645,111 pounds of zinc as an accessory constituent, an average of less than 13 per cent, which was lost in smelting the ore, and hence for the purpose of this report can not be classed with zinc ore imports so long as the present metallurgic treatment of that ore prevails. Similarly, the figures for 1911 are exclusive of 25,769 tons of other ore, carrying 6,283,437 pounds of zinc, and those for 1912 are exclusive of 18,245 tons of other ore, carrying 4,862,508 pounds of zinc. The duties on the zinc contents of this ore have since been refunded and the bonds canceled. The ore was shipped from South American ports and largely entered through the port of New York. It is shown in the Monthly Summary of the Bureau of Foreign and Domestic Commerce under the heading of "Merchandise remaining in warehouse," mostly at New York. Such ores have entered free and have not been enumerated since 1912.

EXPORTS.

DOMESTIC EXPORTS.

The practice of the Bureau of Foreign and Domestic Commerce is to class all exports of zinc articles made in this country as domestic exports, whether the zinc is of domestic or foreign origin. Hence, the following table of domestic exports is duplicated in part

Digitized by Google

in a later table of foreign zinc in manufactures exported with benefit of drawback. The exports of zinc ore in the table below are of domestic origin and in recent years have all gone from one mine in New Jersey. The exports of plates, sheets, pigs, or slabs are likewise probably wholly domestic, because, as shown later, all the zinc in manufactures going out under drawback came in as blocks, pigs, and sheets, and the only manufacturing process which would put any of these into the class of exports referred to is rolling into sheets. But the zinc rolling mills in this country do not use foreign metal, hence the conclusion that the plates, sheets, pigs, and slabs of the table are of domestic origin. The exports of zinc dross are, no doubt, in part of foreign origin, but in what proportion can not be determined. However, they are not duplicated in the drawback table. The exports of manufactures, of which the value is given, include the whole of the manufactures exported with benefit of drawback, as well as whatever manufactures of domestic zinc may be exported.

Domestic zinc ore and domestic manufactures of zinc exported from the United States, 1902–1917.

Year.	Zinc ore.		Plates, sheets, pigs, or slabs.		Zinc dross.[a]		All other manufactures.[b]	Total value.
	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Quantity (short tons).	Value.	Value.	
1902	55,733	$1,449,104	3,237	$300,557	(a)	(a)	$114,197	$1,863,858
1903	39,411	987,000	1,521	163,379	(a)	(a)	71,354	1,221,733
1904	35,911	905,782	10,147	1,094,490	(a)	(a)	117,957	2,118,229
1905	30,946	848,451	5,516	682,254	(a)	(a)	159,995	1,690,700
1906	27,720	733,300	4,670	583,526	15,887	$1,103,706	204,269	2,624,801
1907	[c] 20,352	579,490	563	75,194	9,593	560,944	186,203	1,401,831
1908	[c] 26,108	877,745	2,640	250,254	8,405	467,408	88,485	1,683,887
1909	[c] 12,455	412,300	2,566	263,010	7,069	477,112	69,751	1,222,173
1910	[c] 19,711	649,425	3,990	426,560	4,729	380,950	101,336	1,558,271
1911	[c] 18,281	642,884	6,872	810,099	4,246	348,176	134,518	1,935,677
1912	[c] 23,349	823,997	6,634	864,292	205	17,985	140,027	1,846,301
1913	[c] 17,713	631,991	7,783	955,667	28	1,457	145,984	1,735,099
1914	[c] 11,110	388,464	64,802	8,540,668	2,536	240,944	210,974	9,381,050
1915	[c] 832	35,276	118,603	29,537,680	4,167	506,956	1,951,949	32,031,861
1916	78	3,992	163,135	51,311,047	48	10,801	574,229	51,900,069
1917	1,320	63,043	153,796	38,336,559	13,302	2,126,909	570,352	41,096,863

[a] Not separately enumerated prior to 1906.
[b] Not including brass.
[c] The exports consisted wholly of high-grade willemite ore from New Jersey.

Zinc oxide exported from the United States, 1902–1917.

Year.	Quantity (short tons).	Value.	Year.	Quantity (short tons).	Value.
1902	5,358	$433,722	1910	13,167	$943,938
1903	7,215	578,215	1911	14,618	1,051,311
1904	8,157	628,494	1912	17,064	1,247,702
1905	11,280	810,203	1913	14,467	1,136,257
1906	15,578	1,149,297	1914	15,592	1,408,525
1907	13,257	1,069,924	1915	19,989	2,068,428
1908	12,008	845,070	1916	13,942	2,394,709
1909	14,846	1,026,377	1917	15,446	3,148,898

Digitized by Google

Domestic brass and brass manufactures exported from the United States, 1911–1917.

[Zinc content approximately 30 per cent by weight.]

Year.	Bars, plates, and sheets.		Scrap and old.		Articles made from (value).	Total value.
	Quantity (short tons).	Value.	Quantity (short tons).	Value.		
1911	1,152	$314,089	9,409	$1,703,131	$5,352,868	$7,370,088
1912	3,431	1,058,560	14,435	3,090,833	5,036,197	9,185,590
1913	3,056	933,949	10,943	2,292,349	4,719,119	7,945,417
1914	3,558	909,153	10,320	2,100,870	3,756,888	6,766,911
1915	33,136	12,435,906	5,628	1,259,638	41,117,771	54,813,315
1916	122,266	72,683,626	3,478	1,305,050	241,668,081	315,656,757
1917	164,173	101,521,426	4,149	1,758,384	136,611,299	239,891,109

This table does not include all the brass exported in munitions. For instance, the large exports of shrapnel are included by the Bureau of Foreign and Domestic Commerce under "All other explosives," which increased in value from $651,601 in 1913 to $95,129,957 in 1915, $394,136,334 in 1916, and $202,252,574 in 1917.

FOREIGN EXPORTS.

Foreign zinc exports are the exports of zinc of foreign origin which has been smelted or manufactured in this country and then shipped abroad. The following table, made up from the records of the Bureau of Foreign and Domestic Commerce, shows the total zinc exported from warehouse during the last 12 years—the exports prior to that period being of insignificant proportions—and also the foreign zinc exported in manufactures with benefit of drawback for the same period. These two items—foreign zinc exported from warehouse and foreign zinc in manufactures exported with benefit of drawback—make up the total foreign zinc going out of the country. Zinc in warehouse and deductions by liquidation being disregarded, the difference between the sum of these two exports of zinc and the total imports of zinc constitutes the foreign zinc consumed in this country. The zinc recorded in this table was not exported as zinc content of ore and blocks, pigs, etc., but as zinc smelted or manufactured from them. The reason for this method of reporting is that the zinc in bonded customs warehouse is carried on the records until the bond is canceled in the same form in which the zinc was entered for warehouse. The zinc content of the foreign ore is, of course, exported as metal and manufactures of zinc. In the Monthly Summary of the Bureau of Foreign and Domestic Commerce since July 1, 1914, the exports of foreign zinc have been wholly classed as metallic zinc—that is, as "blocks, pigs, and old."

Under present customs regulations zinc equivalent in quantity to the total recoverable zinc content must be exported to procure cancellation of bond. The quantities as given of zinc exported from warehouse are exact, but the quantities as given of zinc exported in manufactures under drawback are subject to wastage in manufacturing.

Except for a portion of the articles manufactured from foreign zinc and exported with benefit of drawback, no record is kept of the form in which the zinc is actually exported. Unless the zinc is

Digitized by Google

the constituent of chief value, the actual quantity of zinc is not recorded. But each shipment on which drawback is claimed is accompanied by a manifest of the imported zinc which was used in making the articles, as well as the duty paid thereon. From these manifests is made up the statement of the total quantity of foreign zinc which went into manufactures exported with benefit of drawback, and for this reason the zinc is given in the form in which it was imported.

Foreign zinc exported from the United States in 1905–1917.

Year.	Exported from warehouse.					Exported in manufactures with benefit of drawback: Blocks, pig, sheets, and all other manufactures (short tons).
	Ore and calamine, zinc content.		Blocks, pigs, and old.		All other manufactures (value).	
	Quantity (short tons).	Value.	Quantity (short tons).	Value.		
1905	.....	.....	19	$816	$1,015	.....
1906	.....	.....	1	252	1,962	2
1907	.....	.....	9	1,023	1,504	1,555
1908	.....	.....	8	964	4,635	1,234
1909	[a] 328	[a] $6,429	6	752	521	.....
1910	4,710	182,345	47	4,884	1,121	4,486
1911	10,818	476,233	458	21,141	2,701	3,079
1912	6,778	306,726	48	4,346	30,649	1,219
1913	5,406	214,437	620	66,919	6,231	7,459
1914	140	5,909	5,440	212,236	18,544	9,506
1915	.....	.....	12,775	2,355,557	119,104	255
1916	.....	.....	43,230	8,080,442	574,229	.....
1917	.....	.....	64,678	12,428,830	570,352	1,588

[a] After Aug. 6, 1909.

CONSUMPTION.

The rapidly increasing quantity of secondary material, such as zinc skimmings, ashes, hard zinc, and scrap zinc, from which zinc is recovered in the form of metal, alloy, pigment, or chemical, and so used again, affects the consumption of primary zinc. The total quantity of secondary zinc recovered in 1917, so far as there is available record, was 132,000 tons, as compared with 130,000 tons in 1916. For details of the recovery of secondary zinc in 1917 and previous years, see page 860.

Primary zinc consumed in the United States, 1911–1917, in short tons.

	1911	1912	1913	1914	1915	1916	1917
Supply:							
Stock Jan. 1:							
In bonded warehouses	31	32	48	.....	111	32	90
At smelters	23,201	9,049	4,474	40,659	19,984	14,221	17,508
Production	286,526	338,906	346,676	353,049	489,519	667,456	669,573
Imports	609	11,115	6,100	880	904	684	257
Total available	310,367	359,002	357,298	394,588	510,518	682,393	687,428
Withdrawn:							
Exports, foreign, from warehouse	11,276	6,286	6,027	5,580	12,775	43,230	64,680
Exports, foreign, under drawback	3,079	1,219	7,459	4,961	255	.....	1,588
Exports, domestic	6,872	6,634	7,783	64,807	118,603	163,137	153,706
Stock Dec. 31:							
In bonded warehouses	32	48	.....	111	32	90	32
At smelters	9,049	4,474	40,659	19,984	14,221	17,508	53,689
Total withdrawn	30,308	18,661	61,928	95,463	145,886	223,965	273,785
Apparent consumption	280,059	340,341	295,370	299,125	364,632	458,428	413,643

Digitized by Google

The domestic consumption of zinc of foreign origin, both that made in this country from foreign ore and that imported directly as metal, is a matter of much importance to American zinc producers and smelters. A certain portion of the stocks reported by the smelters as on hand at the end of the year must consist of zinc made from foreign ores, and this has not been taken into consideration in the following table; but, although this omission affects the statistics of consumption for any single year, it does not impair the usefulness of a table covering the length of time here given.

Foreign zinc consumed in the United States, 1911–1917, in short tons.

	1911	1912	1913	1914	1915	1916	1917
Supply:							
Stocks in warehouse Jan. 1	31	32	48	.....	111	32	90
Production from foreign ore	14,905	14,899	9,424	9,631	31,384	104,005	84,976
Imports	609	11,115	6,100	880	904	684	257
Total supply	15,545	26,046	15,572	10,511	32,399	104,721	85,323
Withdrawn:							
Exports from warehouse	11,276	6,286	6,027	5,580	12,775	43,230	64,690
Exports under drawback	3,079	1,219	7,459	4,961	255	.....	1,588
Stocks in warehouse Dec. 31	32	48	.....	111	32	90	32
Total withdrawn	14,387	7,553	13,486	10,672	13,062	43,320	66,300
Consumption of foreign zinc	1,158	18,493	2,086	[a]—161	19,337	61,401	19,023

[a] The excess of withdrawals over supply may be accounted for by exports under drawback of articles manufactured from zinc imported prior to 1914.

This table does not include galvanized wire and galvanized cast or wrought iron or steel articles. The production of galvanized wire must have increased greatly, for the exports of wire were very large in 1915–1917, as shown in the table below taken from the Monthly Summary of the Bureau of Foreign and Domestic Commerce. It is generally understood that the barbed wire used in military entanglements is galvanized; in fact, a large percentage of the wire exported is galvanized.

Galvanized iron and steel sheets, formed products, and tubes produced in the United States, 1913–1917, in short tons.[a]

	1913	1914	1915	1916	1917
Galvanized iron and steel sheets	922,932	903,834	790,785	673,462	636,989
Galvanized form products [b]	64,595	65,802	56,096	65,151	57,451
Galvanized tubes	298,973	296,832	314,657	325,935	308,342
	1,286,500	1,266,468	1,161,538	1,064,548	1,002,782

[a] From annual statistical reports of American Iron and Steel Institute.
[b] Articles formed or stamped from iron or steel sheets and galvanized after shaping.

Domestic wire exported from the United States, 1913–1917, in short tons.

	1913	1914	1915	1916	1917
Barbed wire	91,897	105,108	278,454	469,148	216,687
All other wire	121,222	97,465	251,964	295,839	225,651
	213,119	202,573	530,418	764,987	442,338

Digitized by Google

PRICES AND VALUE.

PRICES.

The price of prime western zinc at St. Louis was 9.75 cents a pound at the beginning of 1917 and after receding to 9 cents at the middle of January rose gradually to 10.75 cents early in March. The price dropped to 8.9 cents late in April, rose gradually to 9.4 cents by the end of May, but, in a series of declines with short recoveries, reached 7.70, at which it closed the year. The average quoted price for the year for prime western zinc at St. Louis was 8.9 cents a pound.

Experience has shown that large sales of zinc for future delivery at considerable reductions in price, as well as the sales of metal of better grades than prime western at much higher prices, render the average price quoted for prime western zinc a very poor guide to the average value of all zinc sold. A canvass of the actual sales of zinc and the prices received gives 10.2 cents a pound as the average selling price of all grades, A, B, C, and prime western. The average selling price of grade A zinc (Army specifications) was 14.0 cents a pound; for grade B zinc it was 12.7 cents; for grade C, 9.4 cents; and for grade D or prime western, 9.0 cents a pound.

In 1916 the average quoted price for prime western zinc was 13.6 cents a pound and the average selling price for all grades was 13.4 cents. In 1915 the corresponding prices were 14.2 cents and 12.4 cents. The reason for the shift in the variation between the quoted price and the selling price is to be found in the declining importance and price of prime western zinc during the war, and the increasing importance and stability of price of metal of the highest grade.

The London official price of zinc started at £50 5s. a long ton (10.6 cents a pound) and, roughly paralleling the St. Louis price, rose to £58 10s. a long ton (12.4 cents a pound) early in March, declined again late in March, rose two-tenths of a cent early in April while the St. Louis price was dropping a cent a pound, and then, owing to Government control, settled back to £54 a long ton (nearly 11.5 cents a pound), at which point the nominal price has since remained. The average London price for the year was £54 2s. a long ton (about 11.5 cents).

In 1917 the base price of sheet zinc remained nearly stationary, starting the year at 21 cents a pound, declining to 20 cents on April 25 and to 19 cents on April 26, at which figure it remained until the end of the year. Prices for 1914–1917, inclusive, are given on page 858. The average price obtained for all rolled zinc sold during the year was 17.5 cents, as compared with 18.4 cents in 1916.

Zinc dust at the beginning of 1917 was quoted at from 20 to 33 cents a pound, depending on quality. The price dropped to 16 to 20 cents by the middle of May and remained nearly stationary until the end of the year, closing at 16 to 17 cents a pound. The average of quotations for the year was 19.9 cents, but the average price obtained for all zinc dust sold during the year was 16.6 cents a pound.

PRICE CURVES, 1914–1917.

Plate VII shows graphically for the years 1914–1917 the relations of the weekly average St. Louis price of zinc, the weekly average London price of zinc, the weekly average price of 60 per cent zinc blende

Digitized by Google



Digitized by Google

Digitized by Google

concentrates at Joplin, Mo., and the weekly sales of concentrates in the Joplin region as a whole. The price of zinc has been taken from market reports, and the price of zinc blende and the figures of weekly sales are those published in the Joplin daily papers. To eliminate the sharp weekly fluctuations and to obtain a curve more easily comparable with the price curves, the weekly sales have been averaged by months, the result being shown by the broken lines.

The curve of the London price of zinc for the first seven months of 1914 shows that zinc was about two-fifths of a cent higher in St. Louis than in London. Through this period the price was about at a level. With the outbreak of the war London became the center of the demand for zinc for munitions and the London price became higher than the St. Louis price except for short intervals. The curve is very irregular, with a sharp rise during the early months of the war, culminating in the week ending June 12, 1915, when zinc quotations for ordinary grades averaged above 25 cents a pound. The curve for the last half of 1915 shows rapid and extreme changes in the price of zinc, due to the changing demands and exigencies of the war, but the price was always rising. This condition continued through more than the first quarter of 1916 but was followed by a great decline in May and June of that year, significant of overbuilt smelting capacity and overproduction in the United States.

Though there was some stiffening of the price in the later part of 1916, it was immediately lost and the price was on the down grade for the greater part of 1917. The curve of the price of zinc in London through the later part of 1917 is a straight line, owing to governmental fixation of price.

VALUE.

The production of primary zinc from domestic ores in 1917 was 584,597 short tons, valued at $119,258,000, based on the average selling price—an increase of 21,146 tons, or about 4 per cent, in quantity and a decrease of $31,747,000, or about 21 per cent, in value, as compared with 1916.

Domestic primary zinc produced in the United States, 1910–1917.

Year.	Quantity (short tons).	Average price at St. Louis.	Value.	Year.	Quantity (short tons).	Average price at St. Louis.	Value.
1910	252,479	$0.054	$27,268,000	1914	343,418	$0.051	$35,029,000
1911	271,621	.057	30,965,000	1915	458,135	[a].124	113,617,000
1912	328,907	.069	44,699,000	1916	563,451	[a].134	151,005,000
1913	337,252	.056	37,772,000	1917	584,597	[a].102	119,258,000

[a] Average value of all grades based on total sales during year.

Digitized by Google

Digitized by Google

LEAD.

By C. E. SIEBENTHAL.

SUMMARY.

Summary statistics of refined lead in the United States, 1912–1917, in short tons.

	1912	1913	1914	1915	1916	1917
Total production of refined primary lead [a] in the United States	480,894	462,460	542,122	550,055	571,134	610,769
Production of desilverized lead in the United States	339,646	330,593	383,903	388,594	403,619	422,266
Production of soft lead in the United States (including desilverized soft)	171,037	161,300	201,725	205,462	235,759	244,771
Production of antimonial lead in the United States	13,552	16,665	16,667	23,224	24,038	18,646
Production of lead from domestic ores	392,517	411,878	512,794	507,026	552,228	548,450
Production of secondary lead in the United States	67,168	72,834	61,062	78,900	96,300	93,500
Consumption of primary lead in the United States (disregarding stocks)	394,113	414,283	451,264	430,252	461,238	517,685

[a] "Primary lead," which is produced directly from ore, is here distinguished from "secondary lead," which is obtained by refining skimmings, drosses, and old metals. The statistics of secondary lead are given on p. 886. Wherever in this report the word "lead" is used without qualification it means primary lead.

The output of refined lead in the United States from domestic ores in 1917 was 548,450 short tons, valued at $94,333,000, at the average sales price of refined lead compared with 552,228 tons, valued at $76,207,000 based on the average "outside" spot quotation at New York in 1916—a loss in quantity of 3,778 tons, or nearly 1 per cent, and a gain in value of $18,126,000, or nearly 24 per cent.

INTRODUCTION.

Though the publication of this chapter has been so greatly delayed by press of work growing out of the war that the report has value chiefly for purposes of statistical record, nevertheless the essential figures have been available since the beginning of 1918. An estimate of the production of refined lead in 1917 was published in the form of a press bulletin on January 10, 1918. This estimate was based on reports received from every lead smelter in operation, giving the actual production for the first 10 or 11 months of 1917 and estimates for the remainder of the year.

The statistics of production of lead in this country in 1917 have been compiled by the United States Geological Survey from confidential reports submitted by each lead-smelting company in operation during the year. The statistics of the recovery of secondary lead were also collected by the Geological Survey. The statistics of domestic consumption are taken in part from the smelter returns and

Digitized by Google

in part from the records of the Bureau of Foreign and Domestic Commerce, of the Department of Commerce, and the statistics of foreign production and consumption are compiled from the sources indicated in connection with the tables here presented.

PRODUCTION.

TOTAL PRODUCTION AND VALUE.

The refined lead produced in the United States from 1720 to 1914 from domestic ores and from foreign ores and base bullion and its value at the average price in New York are shown in the chapter on lead in Mineral Resources for 1914. Details of later years are given below.

Production, price per pound, and value of refined lead in the United States, 1720–1917.

Year.	Desilverized lead.[a,b]	Soft lead.[c]	Total production.[b]	From domestic ores and base bullion.[b]	From foreign ores.	From foreign base bullion.	Price per pound at New York.[d]	Value.
	Short tons.	*Short tons.*	*Short tons.*	*Short tons.*	*Short tons*	*Short tons*		
1720–1905	5,251,079	2,081,836	7,332,915	6,032,383	1,300,532		.....	$634,403,000
1906	313,886	90,860	404,746	336,200	28,803	39,743	$0.057	46,141,000
1907	313,588	99,801	413,389	352,381	24,041	36,967	.053	43,819,000
1908	295,552	101,012	396,564	311,666	11,509	73,389	.042	33,311,000
1909	329,751	117,158	446,909	352,839	21,754	72,316	.043	38,434,000
1910	328,954	141,318	470,272	375,402	18,065	76,805	.044	41,384,000
1911	331,032	155,947	486,979	391,995	10,764	84,220	.045	43,828,000
1912	339,646	141,248	480,894	392,517	11,572	76,805	.045	43,280,000
1913	330,593	131,867	462,460	411,878	13,223	37,359	.044	40,696,000
1914	383,903	158,219	542,122	512,794	7,639	21,689	.039	42,286,000
1915	388,594	161,461	550,055	507,026	9,581	33,448	.047	51,706,000
1916	403,619	167,515	571,134	552,228	6,085	12,821	.069	78,817,000
1917	422,266	188,503	610,769	548,450	15,872	46,447	.086	105,052,000
	9,432,463	3,736,745	13,169,208	11,077,759	2,091,449		.....	1,243,156,000

[a] Desilvered soft lead is included; for quantity see page 884.
[b] Antimonial lead is excluded; for quantity see page 885.
[c] Desilvered soft lead is excluded.
[d] For 1917, average sales price.

PRODUCTION BY STATES.

The production of refined lead can with difficulty be apportioned according to sources of ore, owing to the fact that lead refiners treat products already smelted, whose origin may, as in custom refining, be unknown to them, because the identity of the ore is preserved only as far as the smelter. Accordingly, the following table is compiled, so far as possible, from smelter figures. It includes "pig lead" reported by all smelters running on Mississippi Valley or southeastern lead ores and "work lead" produced at all other lead smelters in this country. The greater part of the product reported by smelters operated in conjunction with refineries is stated in terms of refined lead. A like part of the antimonial lead is thus eliminated from the "work lead" produced and appears only in the figures of production of antimonial lead.

In addition to the domestic lead ores smelted in this country, small quantities of domestic lead ore have been exported to smelters in Canada. In 1912 soft lead amounting to 63 tons was smelted from Wisconsin ores at Canadian smelters, and in 1913 soft lead amounting to 37 tons from Wisconsin ores and desilverized lead amounting to 98 tons from Idaho and Washington ores were smelted in Canadian smelters. The desilverized lead smelted in Canada from Washington ores amounted to 31 tons in 1914, to 137 tons in 1915, and to 2,001 tons in 1916. In 1917 ores from Idaho and Montana, smelters in Canada, yielded 4,570 tons of lead.

Digitized by Google

Primary lead smelted or refined in the United States, 1907–1917, by sources, in short tons.

Source of ore.	1907	1908	1909	1910	1911	1912	1913	1914	1915	1916	1917
Domestic ore:											
Alaska		3	69	75	51	45	6		358	659	884
Arizona	2,418	1,464	1,507	948	3,428	3,891	4,901	5,601	6,953	15,328	7,456
Arkansas [a]	15		14		15			52	51	170	300
California	938	515	977	1,207	615	811	3,294	3,698	5,606	3,633	11,471
Colorado	52,552	28,729	30,865	38,542	30,442	37,039	42,840	41,198	32,352	33,046	29,327
Idaho	123,292	98,464	103,747	109,951	117,335	127,780	137,802	177,827	160,680	170,059	174,045
Illinois [a]	498	362	273	263	308	513	619	427	910	670	867
Iowa [a]	225	110	15					34			
Kansas [a]	1,798	2,293	2,763	1,308	2,522	1,937	1,504	1,043	1,320	1,737	2,663
Kentucky [a]	75			50		91	16	16	95	37	21
Missouri [a]	122,856	122,451	141,105	161,659	182,203	162,610	152,430	194,275	195,634	218,253	218,197
Montana	2,145	2,320	1,451	1,943	2,484	2,517	3,256	4,386	4,853	4,961	5,933
Nevada	3,480	3,796	4,792	2,246	1,082	5,699	6,142	5,996	7,664	11,858	12,334
New Hampshire									3	46	
New Mexico	2,047	586	1,350	1,890	1,371	2,511	1,821	741	2,157	3,290	3,428
North Carolina				2	35	34	10				
Oklahoma [a]	404	1,409	2,268	1,805	1,925	2,500	3,214	3,916	4,346	10,969	19,646
Oregon	5	7	7		11	21	37	17	11	9	
Pennsylvania									6		
South Dakota		13		8	33	12	7	2	5	12	34
Tennessee [a]	16								8		
Texas	12	42	44	36	57	30	108	89	111	26	58
Utah	55,540	42,455	66,648	60,605	54,933	60,664	71,069	88,976	106,105	111,789	82,081
Virginia [a]	83	13		87	400	85	878	143	457	740	147
Washington	341	391	120	339	612	53	9	2	11	217	929
Wisconsin [a]	3,573	4,013	3,252	3,909	3,966	3,301	2,639	1,819	2,632	3,121	2,930
Wyoming									6		22
Undistributed	896	36	317	101	48	120	63	99	116	113	123
Zinc residues	1,890	1,290	1,735	2,237	1,987	3,131	3,765	4,125	4,562	5,478	6,489
	375,099	310,762	363,319	389,211	405,863	415,395	436,430	534,482	537,012	596,221	579,385
Foreign ore:											
Africa	288		3,150	3,310	582	1,774	5,976	2,942		328	1,738
Canada	2,607	162	66	25	122	29	16	2	1,174	1,231	1,100
Central America	23	12	20	3	28				1	7	
Mexico	20,204	10,145	16,944	11,704	7,333	7,407	4,512	2,386	5,437	1,917	7,607
South America	919	1,186	1,536	2,996	2,677	2,332	2,617	1,821	2,829	2,366	1,533
Other foreign		4	38	27	22	80	102	488	140	236	3,894
Foreign base bullion:											
Canada	2,716	179	1,500							1,072	6,750
Mexico	34,251	73,210	70,816	76,805	84,220	76,805	37,359	21,689	33,173	11,598	39,508
South America									275	151	189
	61,008	84,898	94,070	94,870	94,984	88,377	50,582	29,328	43,029	18,906	62,319
Grand total	436,107	395,660	457,389	484,081	500,847	503,772	487,012	563,810	580,041	615,127	641,704

[a] The lead produced by these States is nonargentiferous or soft lead.

Digitized by Google

SOFT LEAD.

The lead ores of the Mississippi Valley are almost free from silver, and the lead produced from them is known as "soft lead."

A little lead ore of this kind is also mined in Washington and other Western States, but in the last few years this ore has been smelted by plants treating argentiferous lead ore and thus the resulting lead has not been distinguished from the desilverized product of those plants. With two exceptions, the smelters running exclusively on these soft-lead ores do not desilverize their product. Their output is shown in the column headed "Soft lead" in the table on page 882, giving the production of refined lead for 1720–1917. However, considerable soft-lead ore has been annually smelted and some purchased pig soft lead has been desilverized by the silver-lead smelters. Since 1904 the St. Louis Smelting & Refining Co. has regularly desilverized its product. In 1915 the St. Joseph Lead Co. installed desilverizing kettles and a part of its product has since been desilverized. This desilverized soft lead, for the years prior to 1906, has not been recorded separately from the lead produced from silver-lead ores, though the lead content of the soft-lead ores so smelted and desilverized has been recorded since 1894. Since 1906 the quantity of soft lead produced by each State has been recorded, as shown in part in the preceding table. In the following table the undesilverized output of the soft-lead smelters is given in the first column and the refined lead output from soft-lead ores smelted and desilverized is given in the second column. The figures do not give the total quantity of lead recovered from soft-lead ores, for the lead recovered in the form of pigments, which are made principally from soft-lead ores, should be taken into account. The lead content of pigments smelted directly from ore in 1917 is given on page 886.

Soft lead produced in the United States, 1907–1917, in short tons.

Year.	Undesilverized.	Desilverized.	Total soft lead.
1907	99,801	29,829	129,630
1908	101,012	29,869	130,881
1909	117,158	32,532	149,690
1910	141,318	27,952	169,270
1911	155,947	35,667	191,614
1912	141,248	29,789	171,037
1913	131,867	29,433	161,300
1914	158,219	43,506	201,725
1915	161,461	44,001	205,462
1916	167,515	68,244	235,759
1917	188,503	56,268	244,771

ANTIMONIAL LEAD.

The output of by-product antimonial lead from argentiferous lead ores derived from all sources, as reported by all lead refineries operating in this country, is shown for the period 1871–1906 (earlier years being estimated from the output of desilverized lead) in a table in the chapter on lead in Mineral Resources, 1914. The figures for later years are given in the table below. Since 1909 producers have been asked to distinguish between the by-product antimonial lead derived from ore and bullion of foreign origin and that from domestic ores. Inasmuch as the antimonial skimmings are worked up in

Digitized by Google

batches, the output of antimonial lead in any one year does not necessarily correspond strictly to the bullion refined during that year, hence the antimonial lead output is distributed as between domestic and foreign in proportion to the lead refined from domestic and from foreign bullion during the year. This method has given fairly consistent results up to 1915. For the period 1909 to 1914, inclusive, the domestic antimonial lead reported amounted to 4.8 per cent of the refined lead produced from domestic bullion and the foreign antimonial lead equaled 4.5 per cent of the lead smelted and refined from foreign ores and bullion. The total antimonial lead produced during the period 1907–1917 was equal to 5.16 per cent of the total lead refined from domestic and foreign bullion during that period. Since the beginning of the war, however, the returns have been inconsistent and it is not believed that they represent accurately the distribution as between domestic and foreign sources. For this reason, only the total production of by-product antimonial lead is given in the table below.

By-product antimonial lead produced in the United States, 1907–1917.

Year.	Total lead refined from base bullion (short tons).	Percentage of by-product antimonial lead.	Antimonial lead.		Antimony content.		Lead content, by difference (short tons).
			Quantity (short tons).	Value.	Quantity (short tons).	Percentage.	
1907	283,759	3.5	9,910	$1,322,985	1,561	15.8	8,349
1908	265,683	5.1	13,629	1,264,771	2,440	17.9	11,189
1909	297,219	4.3	12,896	1,231,019	2,360	18.3	10,536
1910	301,002	4.7	14,069	1,338,000	2,229	15.8	11,840
1911	295,365	4.8	14,078	1,380,556	2,254	16.0	11,824
1912	309,857	4.4	13,552	1,311,348	1,949	14.4	11,603
1913	301,160	5.5	16,665	1,591,854	2,508	15.0	14,157
1914	340,397	4.9	16,667	1,572,167	2,693	16.2	13,974
1915	344,593	6.7	23,224	3,665,736	3,425	14.8	19,799
1916	335,375	7.2	24,038	4,483,682	3,496	14.5	20,542
1917	365,998	5.1	18,646	3,781,660	2,759	14.8	15,887
Average		5.16				15.6	

Details of the production and consumption of antimony in the United States are given in the chapter on antimony in Mineral Resources, 1917.

LEAD PIGMENTS.

PIGMENTS SMELTED DIRECTLY FROM ORE.

In addition to leaded zinc oxide and zinc-lead oxide, which are noted more particularly in connection with the production of zinc pigments, two other lead pigments are made directly from ore namely, sublimed white lead and sublimed blue lead. Sublimed white lead consists of lead sulphate 75 per cent, lead oxide 20 per cent, and zinc oxide 5 per cent. Sublimed blue lead consists of lead sulphate 50 to 53 per cent, lead oxide 41 to 38 per cent, with small proportions of lead sulphide, lead sulphite, and zinc oxide. Zinc-lead oxide contains from 46 to 50 per cent of lead sulphate, from 52 to 46 per cent of zinc oxide, and a small quantity of zinc sulphate. No zinc-lead oxide is made at present. Leaded zinc oxide may vary from 4 to 20 per cent in lead sulphate, the remainder being zinc oxide, with a small portion of zinc sulphate.

Digitized by Google

Lead content of pigments smelted from ore in the United States, 1907–1917, in short tons.

1907	7,099	1913	10,998
1908	8,278	1914	11,914
1909	7,292	1915	12,782
1910	7,603	1916	13,252
1911	7,678	1917	12,870
1912	10,323		

In order to avoid disclosing individual business, the statistics of production of leaded zinc oxide and sublimed lead (basic sulphate white and blue lead) are combined with those of zinc oxide. The sales of these pigments in 1917 amounted to 140,636 short tons, valued at $26,972,137, compared with 135,606 short tons, valued at $23,515,803, in 1916. The output of sublimed lead and of leaded zinc oxide decreased somewhat.

PIGMENTS MANUFACTURED FROM PIG LEAD.

Manufactured lead pigments marketed in 1916–17.

Pigment.	1916			1917		
	Quantity (short tons).	Value.	Average price per ton.	Quantity (short tons).	Value.	Average price per ton.
Basic carbonate white lead:						
In oil	96,041	$16,560,137	$172.43	87,331	$17,608,967	$201.63
Dry	32,938	4,714,343	143.13	27,869	4,920,864	176.57
Red lead	23,035	3,933,566	170.76	25,478	5,523,018	216.78
Orange mineral						
Litharge	37,739	5,853,543	155.11	44,102	8,611,074	195.25
	189,753	31,061,589	.....	184,780	36,663,923	.....

SECONDARY LEAD.

Secondary lead is obtained mainly from skimmings, drosses, old metal, and alloys, such as babbitt, solder, and type metal. The recovery of lead by refining these materials constitutes an integral part of the lead industry. This business is carried on mostly at small refineries scattered over the United States, but the large smelters and refineries working primary lead frequently find it advantageous to incorporate material from secondary sources. The product of such secondary refineries is of two classes—pig lead and lead in alloys. The lead in alloys may have been recovered in the form of pig lead and alloyed at the refinery, or it may have been refined as an alloy, being brought to the desired composition by the addition of the requisite metal.

Secondary lead produced in the United States, 1909–1917, in short tons.

Year.	Pig lead.	Lead in alloys.	Total recovered lead.	Value.
1909	18,360	23,327	41,687	$3,585,000
1910	29,492	25,930	55,422	4,877,000
1911	27,389	26,895	54,284	4,886,000
1912	30,266	36,902	67,168	6,045,000
1913	33,104	39,730	72,834	6,409,000
1914	29,337	31,725	61,062	4,763,000
1915	36,400	42,500	78,900	7,416,000
1916	56,700	39,600	96,300	13,239,000
1917	45,100	48,400	93,500	16,082,000

Digitized by Google

MINE PRODUCTION.

The first table below shows for each lead-producing State the total quantity of lead-bearing ores produced and the output of the chief kinds of lead-bearing ore. The column headed "All other ores" includes copper ore, copper-lead ore, and dry or siliceous ore. "Dry" ores produced in Colorado contained 9,779 short tons of lead, in California 4,437 tons, and in Nevada, 3,739 tons. This lead, as in other States, was concentrated from parts of the ore from certain counties, however, and was not distributed through the whole of the "All other ore." The total crude ore yielding either gold, silver, copper, lead, or zinc is given for each lead-producing State, so that a comparison may be made of the relative extent of deep-mining operations in these States, of which the quantity of crude ore raised is the best measure. As shown by the table, Missouri took a dominating position in the production of crude lead ore and lead-bearing zinc ores, having produced more than two-thirds of the crude lead ore and more than one-half of the crude lead-bearing zinc ore mined in the United States in 1917, and thus occupied the first rank in output of crude ore carrying any or all of the five metals named above.

The table also gives the quantity of lead contained in the crude ores of each State in 1917 and the lead content of each kind of lead-bearing ore. The percentage of lead contained in the lead ore, the lead-zinc ore, and the zinc ore of each State is also given. The lead content of lead ore, in States having a considerable production, ranged from 29.7 per cent in Washington, down to 3.5 per cent in Missouri; the average for all the States was 5.4 per cent. The lead-zinc ores were somewhat richer in lead than the zinc ores, averaging 0.8 per cent, whereas the average lead content of the zinc ores was 0.2 per cent, this low figure being due to the preponderance of low-grade lead-bearing zinc ores in the Central States. Of the total mine production of lead in 1917, a quantity corresponding to 69.1 per cent was derived from lead ores, 26.8 per cent from lead-zinc ores, 0.6 per cent from zinc ores, and 3.5 per cent from all other ores. The figures of mine production of lead are taken from the chapters on gold, silver, copper, lead, and zinc in the various States, as indicated in the prefatory note.

The second of the following tables shows the mine production of lead by individual districts so that they may be compared as to extent of mining operations, shown by the output of crude ore, as to character of ores, whether sulphide or oxidized, whether lean or rich, and as to relative rank as lead producers.

Digitized by Google

Mine production of lead in the United States in 1917, by States and kinds of ore.

State.	Lead ores.			Lead-zinc ores.			Zinc ores.			All other ores.		Total.	
	Crude ore (short tons).	Lead content.		Crude ore (short tons).	Lead content.		Crude ore (short tons).	Lead content.		Crude ore (short tons).	Lead content. (short tons).	Crude ore (short tons).	Lead content (short tons).
		Quantity (short tons).	Percentage.		Quantity (short tons).	Percentage.		Quantity (short tons).	Percentage.				
Alaska	42	8	19.0							4,074,615	844	4,074,657	852
Arizona	82,285	8,145	9.9	49,071	3,081	6.3	62,839	91	0.1	15,575,998	416	15,770,193	11,733
Arkansas							203,600	382	.2			203,600	382
California	29,651	2,694	9.1	26,501	3,803	14.4	125			2,946,973	4,437	3,003,250	10,934
Colorado	103,081	10,344	10.0	412,371	13,372	3.2	140,455	500	.4	2,032,799	9,779	2,688,706	33,995
Idaho	1,448,285	137,510	9.5	1,118,075	58,938	5.3	19,269	301	1.6	172,878	31	2,758,507	196,780
Illinois				327,340	594	0.2				(a)	845	a 327,340	1,439
Iowa				b 1,000	34	3.4						b 1,000	34
Kansas				903,400	3,025	.3						903,400	3,025
Kentucky							b 9,000			(a)	123	a b 9,000	123
Missouri	5,887,900	204,545	3.5	11,136,100	29,611	.3						17,024,000	234,156
Montana	28,923	2,778	10.0	726,280	5,728	.8	258,846	1,770	.7	5,293,115	700	6,307,164	10,976
Nevada	66,614	7,678	11.5	27,943	2,400	8.6	18,393	22	.1	6,360,569	3,739	6,473,519	13,839
New Hampshire				3,000	48	1.6						3,000	48
New Mexico	17,426	2,818	16.2	10,899	542	5.0	135,129	697	.5	4,413,373	497	4,576,827	4,554
North Carolina	32	1	3.1							2,055		2,087	1
Oklahoma				3,523,200	26,358	.8						3,523,200	26,358
South Dakota	369	34	9.2							1,867,941		1,868,310	34
Tennessee				61,638	2,525	4.1	883,341	6	.0006	589,004		1,533,983	2,531
Texas										52,382	1	52,382	1
Utah	638,071	68,623	10.8	421,704	19,394	4.6	6,535	30	.5	14,292,171	1,214	15,358,481	89,261
Virginia				34,211	855	2.5	990	4	.4	350		35,551	859
Washington	16,407	4,870	29.7	14,953	23	.2	114			140,645	2	172,119	4,895
Wisconsin				3,014,800	4,139	.1						3,014,800	4,139
	8,319,086	450,048	5.4	21,812,486	174,470	.8	1,738,636	3,803	.2	57,814,868	22,628	89,685,076	650,949
Percentage of total lead derived from each kind of ore		69.1			26.8			.6			3.5		100.0

a Lead concentrates are obtained as a by-product in milling fluorspar ores in southern Illinois and Kentucky, but the quantity of crude fluorspar would not properly be classified among "All other ores" and is therefore omitted.
b Estimated.

Digitized by Google

Mine production of lead in districts producing more than 1,000 short tons each in 1917.

District.	State.	Crude lead-bearing ore sold or treated.	Shipping ore and concentrates.					Lead content siliceous ore, iron ore, zinc ore, etc.	Total lead content.	Percentage of total production.
			Total quantity.	Sulphides.		Carbonates.				
				Quantity.	Lead content.	Quantity.	Lead content.			
1. Southeastern Missouri	Missouri	5,887,900	306,071	306,071	204,255				204,255	31.4
2. Coeur d'Alene	Idaho	2,470,364	549,359	549,359	185,702			302	186,004	28.6
3. Joplin	Southwestern Missouri	11,136,100	39,040	38,646	29,371	394	240		58,994	9.1
	Southeastern Kansas	903,400	3,929	3,929	3,025					
	Northeastern Oklahoma	3,523,200	32,775	32,775	26,358					
4. West Mountain (Bingham)	Utah	410,089	336,451	336,451	36,609			153	36,762	5.6
5. Tintic	do	152,139	152,139	13,249	1,350	138,890	16,189		17,539	2.7
6. Park City	do	228,289	75,842	55,669	11,019	20,173	5,463	376	16,858	2.6
7. Leadville	Colorado	342,565	275,408	213,738	7,042	16,416	1,429	451	8,922	1.4
8. Aspen	do	124,655	74,389	74,389	7,176				7,176	1.1
9. Ophir and Rush Valley	Utah	90,211	79,679	77,788	6,125	1,891	321	3	6,449	1.0
10. Big Cottonwood and Little Cottonwood	do	36,700	36,700	1,087	172	35,613	5,506	286	5,964	.9
11. Butte	Montana	633,901	6,373	6,373	1,330			3,846	5,176	.8
12. Warren	Arizona	29,863	28,165	2,984	470	25,181	4,393		4,863	.7
13. Upper Mississippi Valley	Wisconsin	3,014,800	5,544	5,544	4,139				4,767	.7
	Illinois	327,340	788	788	594					
	Iowa	500	43	43	34					
14. Northport	Washington	15,788	15,788	1,973	1,357	13,815	3,376		4,733	.7
15. Keeler	California	31,331	31,331	31,331	4,701				4,701	.7
16. Yellowpine	Nevada	44,058	10,228	5,780	2,785	4,448	1,279	585	4,649	.7
17. Pioche	do	21,408	6,359	2,689	381	3,670	536	3,633	4,550	.7
18. Animas	Colorado	74,481	19,256	19,256	3,590				3,590	.5
19. Texas	Idaho	13,995	13,995			13,995	3,258		3,258	.5
20. Priest Lake	do	38,486	5,362	5,362	3,246				3,246	.5
21. Upper San Miguel	Colorado	46,526	29,487	29,487	3,071				3,071	.5
22. Wallapi	Arizona	45,666	11,437	11,358	3,029	79	13	2	3,044	.5
23. Magdalena	New Mexico	41,875	33,828	27,293	1,489	6,535	953		2,442	.4
24. Troy	Montana	61,647	6,083	6,083	1,964				1,964	.3
25. Tecopa	California	24,759	24,759	24,759	1,813				1,813	.3
26. San Francisco	Utah	57,406	15,610	15,537	1,705	73	56	10	1,771	.3
27. Eureka	Colorado	69,204	14,673	14,673	1,667				1,667	.2
28. Red Cliff	do	61,482	20,689	20,689	1,213				1,213	.2
29. Alder Creek	Idaho	12,610	12,610	17	7	12,593	1,171		1,178	.2
30. Central	New Mexico	10,521	9,390	4,556	351	3,655	757	17	1,125	.2
31. Dome	Idaho	4,201	2,113	2,113	1,113				1,113	.2
32. Trona	California	4,401	4,401	4,401	1,071				1,071	.2
33. Georgetown-Silver Plume	Colorado	29,057	7,007	7,007	1,063				1,063	.2
34. Zabriskie	California	5,105	5,105	5,105	1,011				1,011	.1
		30,026,023	2,302,206	1,958,352	561,398	297,421	44,940	9,664	616,002	94.7
All other districts									34,947	5.3
Total for United States									650,949	100.0

Digitized by Google

LEAD SMELTERS.

ACTIVE SMELTERS AND REFINERIES.

UNITED STATES.

(Operated in 1917.)

CALIFORNIA: Selby—Selby Smelting & Lead Co.[1] Refinery also.
COLORADO:
Denver—Globe plant, American Smelting & Refining Co.
Durango—Durango plant, American Smelting & Refining Co.
Leadville—Arkansas Valley plant, American Smelting & Refining Co.
Pueblo—Pueblo plant, American Smelting & Refining Co.
Salida—The Ohio & Colorado Smelting & Refining Co.[2]
IDAHO: Kellogg—Bunker Hill & Sullivan Smelter.
ILLINOIS:
Aurora—Aurora Metal Co.[3]
Chicago—Goldsmith Bros.' Smelting & Refining Co.[3]
Chicago—Great Western Smelting & Refining Co.[3]
Collinsville—St. Louis Smelting & Refining Co.[4] Refinery only.
Federal—Federal Lead Co.[1]
INDIANA:
East Chicago—International Lead Refining Co.[5] Refinery only.
Grasselli—United States Metals Refining Co.[6] Refinery only. Betts electrolytic process.
KANSAS: Galena—Galena Smelting & Manufacturing Co.[7]
MISSOURI:
Granby—Granby Mining & Smelting Co.
Herculaneum—St. Joseph Lead Co.
Joplin—Eagle-Picher Lead Co.
Webb City—Webb City Smelting & Manufacturing Co.[7]
MONTANA: East Helena—East Helena plant, American Smelting & Refining Co.
NEBRASKA: Omaha—Omaha & Grant Smelting Co.[8] Refinery only. Betts electrolytic process.
NEW JERSEY:
Newark—Balbach Smelting & Refining Co.[2] Refinery also.
Perth Amboy—Perth Amboy plant, American Smelting & Refining Co. Refinery also.
NEW MEXICO: Deming—Empire Smelting & Refining Co.
OKLAHOMA: St. Louis—Ontario Smelting Co.
PENNSYLVANIA: Carnegie—Pennsylvania Smelting Co. Refinery also.
TEXAS: El Paso—Kansas City Consolidated Smelting & Refining Co.[1]
UTAH:
Midvale—United States Smelting Co.[6]
Murray—Murray plant, American Smelting & Refining Co.
International—International Smelting Co.[5]
WASHINGTON: Northport—Northport Smelting & Refining Co.[9]

CANADA.

BRITISH COLUMBIA: Trail—Consolidated Mining & Smelting Co. of Canada (Ltd). Refinery also. Betts electrolytic process.
ONTARIO:
Kingston—Kingston Smelting Co. (Ltd.).
Galetta—Estate of James Robertson.

MEXICO.

AGUASCALIENTES: Aguascalientes—American Smelting & Refining Co.
CHIHUAHUA:
Chihuahua—American Smelting & Refining Co.
URUACHIC—Uruáchic Mining & Smelting Co. (Ltd.).

---

[1] Subsidiary of American Smelters Securities Co.
[2] Subsidiary of American Metal Co.
[3] Smelters of secondary materials but treating some lead ores.
[4] Subsidiary of National Lead Co.
[5] Subsidiary of Anaconda Copper Mining Co.
[6] Subsidiary of United States Smelting, Refining & Mining Co.
[7] Subsidiary of Eagle-Picher Lead Co.
[8] Subsidiary of American Smelting & Refining Co.
[9] Affiliated with Pennsylvania Smelting Co.

Digitized by Google

COAHUILA:
Saltillo—Mazapil Copper Co. (Ltd.).
Torreon—Compañía Metalúrgica de Torreón.[1]
DURANGO:
Asarco (Velardena)—American Smelters Securities Co.
Mapimi—Compañía Minera de Penoles.[1]
GUERRERO: Campo Morado—Reforma Mining & Milling Co.
NUEVO LEON: Monterey—American Smelting & Refining Co.
SAN LUIS POTOSI:
Matehuala—American Smelters Securities Co. (National Metallurgical Co.)
San Luis Potosi—Compañía Metalúrgica Mexicana.
SONORA:
Guaymas—Pacific Smelting & Refining Co. (Mexican-American Smelting & Refining Co. (Ltd.).)
Ures—Yaqui Smelting & Refining Co., S. A. Refinery also.
ZACATECAS: Chalchihuites—National Smelting Co.

SMELTER CHANGES IN 1917.

The Bunker Hill Smelter began operating in July, 1917, with one 300-ton blast furnace. By the end of the year three furnaces and the refining plant were in operation. The Empire Smelting & Refining Co. rebuilt the old National (Luna) plant at Deming, N. Mex., in 1917, and treated ore from April until October, when the plant was destroyed by fire. The Ontario Smelting Co. began the construction of a soft-lead smelter at St. Louis, a village in the northeastern part of Oklahoma. The plant is expected to be finished early in 1918 and will be equipped with four Newnam automatic ore hearths, a lead stack, and a bag house.

TRADE CONDITIONS.

WORLD'S PRODUCTION.

Official statistics of the world's output of lead for the period of the war are incomplete, for the reason that many of the belligerent countries did not permit the publication of such information. It is hoped that the data may be sufficiently complete to make the publication of value by the time the lead chapter for 1918 is prepared.

IMPORTS AND EXPORTS.

WAREHOUSE TRANSACTIONS.

Lead imported into the United States as metal or in ore may be entered for immediate consumption, the duty being paid and the lead going direct to the consumer; or it may be entered for warehouse, bond being given for double the amount of the estimated duty. In the accompanying tables the phrase "general imports" indicates the total imports, including both lead entered for immediate consumption and lead entered for warehouse. From warehouse the lead may be withdrawn for consumption by payment of duty, or it may remain in bond for smelting and refining, finally being either withdrawn for consumption or exported from warehouse with cancellation of bond. The lead entered for immediate consumption and that withdrawn from warehouse for consumption make up the "imports for consumption," which are expressed in the same terms as those under which they were imported. The lead imported for consumption may be actually used in this country, or it may be manufactured into articles which are exported; in the latter event the manufacturer is entitled to the benefit of a drawback of 99 per cent of the duties paid. In the

[1] Subsidiary of American Metal Co.

Digitized by Google

table below, showing foreign lead exported in manufactures with benefit of drawback, the lead is shown in the form in which it was originally imported. On account of diversity of form it is not feasible to show the articles exported with benefit of drawback. The foreign lead given in the table below as exported from warehouse is likewise shown in the form in which it was imported and entered for warehouse. Foreign lead exported from warehouse has, since July 1, 1915, been included by the Bureau of Foreign and Domestic Commerce in the domestic exports as "from foreign ore."

The items foreign lead exported from warehouse, domestic exports of lead "from foreign ore," and foreign lead exported in manufactures with benefit of drawback make up the total foreign lead going out of the country. Lead in warehouse and deductions by liquidation being disregarded, the difference between the sum of these exports of foreign lead and the total imports of lead constitutes the foreign lead consumed in this country. For the sake of simplicity this foreign lead is carried on the bonded customs warehouse records in the form in which the lead was entered until the bond is canceled. It must be clearly understood, therefore, that the lead listed in the table of foreign exports of lead, on a later page, was not exported as lead content of ore and base bullion but as refined lead smelted and refined from them. Since 1914, however, all foreign lead exported has been classed as lead, "pigs and bars," except a portion of the articles manufactured from foreign lead and exported with benefit of drawback. For articles not made wholly of lead it would be useless to give weights, but each shipment on which drawback is claimed is accompanied by a manifest of the imported lead used in making the articles and the duty paid thereon. From these manifests is derived the statement of the total quantity of foreign lead used in manufactures exported with the benefit of drawback. For this reason the lead is given in the form in which it was imported.

The following table is taken from the reports of the Bureau of Foreign and Domestic Commerce. For the reasons given above, the lead is shown in the terms in which it was imported. For instance, a considerable part of the lead stated as remaining in ore and base bullion doubtless represents refined lead waiting at the bonded refinery for a favorable market for shipment. If this is borne in mind, the table gives a fair idea of the fluctuations of foreign stock at different times and in different localities.

Lead remaining in warehouse in the United States Dec. 31, 1910–1917, in pounds.

Year.	Form in which lead was entered for warehouse.		Remaining at—					
			New York.		Chicago, Ill.	El Paso, Tex.	St. Louis, Mo.[a]	San Francisco, Calif.
	Lead in ore and base bullion.	Pigs, bars, and old.	Newark, N. J.	Perth Amboy, N. J.				
1910	71,794,443	149,082	7,548,936	36,112,136	21,090,631	6,937,667	.....	.....
1911	8,869,713	93,082	2,777,692	2,308,322	954,884	2,555,733	273,082	.....
1912	20,891,182	93,802	1,880,828	17,666,768	484,671	767,533	91,382	.....
1913	10,620,953	.....	8,785,551		80,880	1,683,091	71,431	.....
1914	15,333,064	3,837	10,309,592		94,775	4,802,961	125,736	.....
1915	24,338,933	.....	8,401,728		165,257	14,678,809	104,922	988,217
1916	23,667,358	1,070,298	8,575,115		4,732,535	6,814,844	3,286,189	258,675
1917	47,853,945	5,370,445	19,015,511		4,757,315	18,951,649	2,306,855	2,822,615

[a] Kansas City before 1914.

Digitized by Google

IMPORTS.

The following tables are taken from the reports and records of the Bureau of Foreign and Domestic Commerce:

Lead imported and entered for consumption in the United States, 1910–1917.

Year.	Lead in ore.		Base bullion.		Pigs, bars, and old.		Sheets, pipe, and shot.		Not otherwise specified.	Total value.
	Quantity (pounds).	Value.	Quantity (pounds).	Value.	Quantity (pounds).	Value.	Quantity, pounds.	Value.		
1910....	7,998,859	$198,196	16,543,167	$337,223	6,776,066	$212,858	39,779	$1,972	$4,843	$755,092
1911....	1,474,254	26,563	17,376,459	352,595	7,112,749	242,423	63,151	2,855	7,218	631,654
1912....	935,861	24,760	22,729,467	462,559	5,191,823	110,459	31,184	2,305	5,468	605,551
1913....	2,306,972	75,835	17,665,227	388,116	4,621,270	105,738	39,171	3,291	12,710	585,690
1914....	5,459,961	188,749	8,904,649	301,195	575,290	12,281	62,552	2,753	81,894	586,872
1915....	2,865,792	96,010	15,496,230	519,355	997,368	32,951	201,510	17,059	107,580	772,955
1916....	10,125,983	368,824	5,242,171	208,277	6,388,097	331,235	532	63	106,560	1,014,959
1917....	5,438,931	207,370	6,965,849	470,539	1,756,223	85,743	12,538	2,699	10,287	776,638

Type metal imported and entered for consumption in the United States, 1904–1917.

Year.	Type metal.		Lead content.[a]	
	Gross weight (pounds).	Value.	Quantity (pounds).	Percentage.
1904	8,143,749	$221,127	6,884,423	84.5
1905	13,932,013	456,155	11,476,629	82.4
1906	19,602,471	900,608	15,896,629	81.1
1907	14,832,673	932,027	12,095,027	81.5
1908	4,110,486	156,847	3,265,815	79.5
1909	13,993,889	532,108	11,339,378	81.0
1910	13,391,199	485,493	11,176,830	84.9
1911	8,390,470	310,658	6,936,711	82.7
1912	581,411	18,668	477,006	82.0
1913	567,004	20,098	467,688	82.5
1914	1,509,538	45,373	1,322,188	87.6
1915	2,768,261	107,607	2,424,306	87.6
1916	1,162,386	83,816	923,473	79.4
1917				
Average lead content, 1904–1917				82.2

[a] Prior to 1904 the lead content of the typo metal was not given. Besides lead, the chief constituent of the type metal is antimony.

General imports of lead into the United States, in ore, base bullion, and refined, 1910–1917, by sources, in pounds.

Country.	1910	1911	1912	1913
United Kingdom	1,874,750	401,686	279,546	404,594
Germany	421,377	56,286	494,237	262,132
Other European countries	418,669	111,189	55,356	143,293
Total from Europe	2,714,796	569,161	829,139	810,019
Canada	206,979	270,947	319,497	338,569
Mexico	203,290,307	172,633,479	159,455,664	95,693,439
South America	6,598,263	4,778,221	3,207,936	8,766,327
Other countries	4,394,421	1,651,544	3,309,356	8,685,612
Total imports	217,204,766	179,903,352	167,121,592	114,293,966

Country.	1914	1915	1916	1917
United Kingdom	245,548	185,236	261,406	8,689,992
Germany	4,529,919			
Other European countries	123,085	32,537	314,353	255,907
Total from Europe	4,898,552	217,773	575,759	8,945,899
Canada	384,007	2,303,170	12,606,216	11,738,379
Mexico	46,282,207	94,247,384	48,395,670	125,782,759
South America	2,417,744	5,420,567	6,235,758	4,556,460
Other countries	2,694,293	802,516	2,845,949	5,520,323
Total imports	56,676,803	102,991,410	70,659,352	156,543,820

Digitized by Google

General imports of lead into the United States, 1910–1917, by classes, in pounds.

Year.	Lead in ore (lead content).	Base bullion.		Pigs, bars, sheets, and old.	Total lead content.
		Gross weight.	Lead content.		
1910	94,751,054	118,061,415	115,483,542	6,970,170	217,204,766
1911	35,686,180	141,481,852	138,952,372	5,264,800	179,903,352
1912	19,577,499	152,420,624	146,999,168	544,925	167,121,592
1913	19,883,313	96,908,170	94,327,654	82,999	114,293,966
1914	23,649,637	33,444,503	32,780,320	296,846	56,676,803
1915	18,185,140	86,247,995	83,986,988	819,282	102,991,410
1916	35,086,100	24,943,660	24,262,435	11,310,817	70,659,352
1917	41,292,876	109,279,997	103,664,970	11,585,974	156,543,820

Basic carbonate white lead, red lead, litharge, and orange mineral, imported and entered for consumption in the United States, 1911–1917.

Year.	Corroded white lead.		Red lead.		Litharge.		Orange mineral.	
	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.
	Pounds.		*Pounds.*		*Pounds.*		*Pounds.*	
1911	741,071	$46,213	1,063,533	$42,471	24,662	$1,196	504,734	$28,515
1912	687,705	46,494	757,908	33,854	32,443	1,550	334,551	20,914
1913	672,109	45,266	99,832	4,903	34,023	1,750	330,525	22,205
1914	596,567	40,203	12,554	2,934	33,651	1,805	240,388	16,388
1915	339,157	21,608	1,968	132	20,650	1,422	171,572	14,061
1916	88,617	8,050	20,467	5,302	1,320	150	70,934	8,281
1917	20,238	1,965	50	13	.....	.....	33,294	4,892

EXPORTS.

DOMESTIC EXPORTS.

The average difference between the prices of lead at New York and at London for the 10 years prior to 1914 was not far from 1¼ cents a pound and the price at New York was the higher. This being the case, exports of domestic pig lead should be expected only under temporary or very unusual circumstances. The practice of the Bureau of Foreign and Domestic Commerce has been to class all exports of lead articles manufactured in this country as domestic exports, whether the lead is of domestic or foreign origin. For this reason no table of exports of domestic lead manufactures has been given, because such a table would duplicate the table showing foreign lead in manufactures exported with benefit of drawback. Since the exports of domestic pig lead began, however, they have been shown separately.

In 1914 the price of lead at London rose above the price at New York early in January and remained between one-fourth and one-half cent a pound above throughout the year. This made it possible to export domestic lead at a profit, and the decrease in imports of lead-ore and bullion from Mexico rendered it necessary to satisfy the foreign demand with domestic lead, the exports of which assumed large proportions. The movement commenced in March, 1914, and by the end of the year 58,722 short tons, valued at $4,501,674, had been exported. Likewise in 1915 the price of lead at London was from one-fourth to 1 cent a pound higher than the price at New York, except for the period of high prices in the United States during June and July. Exports of domestic lead continued heavy throughout the year, reaching a total of 88,306 tons, valued at $7,928,518. In 1916

the exports of domestic lead amounted to 100,500 tons and were valued at $13,494,065.

In 1917 the exports of domestic lead fell to 53,688 tons, valued at $9,560,598.

White lead exported from the United States, 1913–1917.

	Quantity (pounds).	Value.
1913	15,062,384	$905,398
1914	17,645,538	1,017,376
1915	25,310,369	1,409,622
1916	27,435,054	2,137,072
1917	19,737,399	2,089,659

FOREIGN EXPORTS.

By exports of foreign lead are meant the exports of lead of foreign origin which has been smelted, refined, or manufactured in this country and then shipped abroad. The following table, made up from the records of the Bureau of Foreign and Domestic Commerce, shows the total lead exported for a period of years; but it must be borne in mind, as pointed out in a previous page, that prior to 1915 the actual exports were not in the form shown in the table, which is the import form, but instead consisted of refined lead and lead manufactures. Since July 1, 1915, the exports of foreign lead heretofore classed as "ore," "base bullion," and "pigs, bars, and old" are all included in "pigs, bars, and old" as domestic manufactures of lead from foreign ore. The quantities given for lead exported from warehouse are exact, but the quantities given for lead in manufactures are subject to the waste in manufacturing.

Foreign lead exported from the United States, 1910–1917.

Year.	Exported from warehouse.							Exported in manufactures with benefit of drawback.	
	Lead content of ore.		Lead content of base bullion.		Pigs, bars, and old.		All other manufactures.	Lead content of ore.	Pigs, bars, bullion, and old.
	Quantity (pounds).	Value.	Quantity (pounds).	Value.	Quantity (pounds).	Value.	Value.	Quantity (pounds).	Quantity (pounds).
1910	22,508,090	$248,220	117,045,333	$2,262,057	19,507	$703	$870	6,592,294	11,008,604
1911	39,276,820	730,247	151,966,265	3,093,290	12,311,102	244,037	1,504	674,621	23,485,929
1912	12,796,703	219,859	116,907,305	2,478,256	107,170	3,826	2,121	150,617	22,584,221
1913	11,721,714	271,985	77,253,891	1,827,538	111,506	4,851	3,422	74,628	19,484,345
1914	6,724,525	245,206	10,944,350	378,286	25,421,500	913,306	2,242	4,040,924	14,970,689
1915	(a)	.....	(a)	.....	77,236,303	2,738,263	40,112	7,966,372	
1916	(a)	.....	(a)	.....	19,760,086	1,111,653	541	10,341,075	
1917	(a)	.....	(a)	.....	75,304,480	6,650,157	900	15,074,947	

a Since July 1, 1915, the Bureau of Foreign and Domestic Commerce has classed all foreign lead exported as "domestic exports, of pigs, bars, etc., produced from foreign."

CONSUMPTION.

In statements of consumption of lead in these reports prior to 1907 it was the custom to take into account the smelter stocks of lead at the beginning and at the end of the year. It is not to be denied that

Digitized by Google

for the individual year this gives closer figures. It is just as true that account of trade stocks should also be taken to arrive at accurate results; but this is manifestly outside the scope of the work of the Geological Survey. It has been found impossible to obtain a statement of stocks from one large producer since 1906; hence consumption has been calculated without reference to domestic stocks. A very considerable part, however, from one-fourth to one-fifth, of the lead smelted and refined in this country, is lead of foreign origin smelted in bond, and it is possible to obtain statistics of the stocks of this part for they are reported annually by the Bureau of Foreign and Domestic Commerce as "merchandise remaining in warehouse at close of year." A certain element of error is introduced by the fact that the imports, the exports, and the warehouse stocks, as given, include lead in both ore and base bullion. So far as imports are concerned, the relative quantities of lead in ore and of base bullion are shown on a preceding page in the table entitled "Imports of lead, by classes," based upon the records of the Bureau of Foreign and Domestic Commerce, and corroborated in the preceding table giving the "sources of primary lead smelted or refined in the United States," based upon smelter reports. For exports and warehouse stocks no such division can be made, because they are classified according to the condition of the metal when it was imported and no change is made with the reduction of the metal in bond. Nevertheless, it is deemed advisable to use warehouse stocks as giving a better estimate of consumption. It is necessary, therefore, to include all classes of lead imports as well as all classes of lead exports.

In the following table "lead" includes all kinds—lead in ore, base bullion, pigs, bars, and old. The figures of domestic production are based upon the returns by the smelters; all other figures are taken from the records of the Bureau of Foreign and Domestic Commerce. Liquidation changes cover losses in smelting and refining in bond and other corrections. Because warehouse stocks are used in lieu of smelter stocks the result given below is lead "available for consumption." The "apparent consumption" would be this quantity increased or diminished by the increase or decrease of domestic stocks during the year.

Primary lead available for consumption in the United States, 1911–1917, in short tons.

	1911	1912	1913	1914	1915	1916	1917
Supply:							
Stock in bonded warehouses Jan. 1	35,972	4,481	10,492	5,310	7,668	12,169	12,369
Imports—							
For consumption	13,013	14,444	12,316	7,501	9,780	10,878	7,087
For warehouse	76,939	69,117	44,831	20,837	41,716	24,452	71,185
Increase by liquidation					2,250	5,642	
Production from domestic ores	391,995	392,517	411,878	512,794	507,026	552,228	548,450
Apparent supply	517,919	480,559	479,517	546,442	568,440	605,369	639,091
Deduction:							
Export of foreign lead—							
From warehouse	101,787	64,906	44,544	21,545	38,618	9,880	37,652
In manufactures, with benefit of drawback	12,080	11,367	9,757	9,506	3,983	5,171	7,537
Exports of domestic lead				58,722	88,306	100,500	53,688
Decrease by liquidation	14,812	5,692	419	56			297
Stock in bonded warehouses Dec. 31	4,481	10,492	5,310	7,668	12,169	12,369	26,512
Total deduction	133,160	92,457	60,030	97,497	143,076	127,920	125,786
Available for consumption	384,759	388,102	419,487	448,945	425,364	477,449	513,305

Digitized by Google



Digitized by Google

Digitized by Google

PRICES AND VALUE.

At the beginning of 1917 the price of lead in New York was a little over 7.5 cents a pound, but it soon began to rise, reaching 10.5 cents late in February and early in March. The price declined to 9.25 cents early in April, but this decline was followed by a rise to 12.25 cents in the middle of June. A sharp decline then set in, and although there was a partial recovery late in July and early in August, the price went down to 5.5 cents in November. From this point the price gradually rose and at the end of the year lead was selling in New York for 6.6 cents a pound. The average price, as figured from the total sales during the year, was 8.6 cents a pound as compared to 6.9 cents a pound, the average of "outside" spot quotations at New York for 1916. These are the figures used in calculating the value of the lead produced from domestic ores in the United States in those years.

The official price of lead at London remained fixed at £30 10s. a long ton (6.4 cents a pound).

The fluctuations in the price of lead at New York and London are graphically shown in Plate VIII, which gives curves of the average weekly price of lead in those markets for the years 1914 to 1917.

As stated on page 881, the value of the output of refined lead in the United States from domestic ores in 1917 was $94,333,000, at the average sales price of refined lead in New York, as compared with $76,207,000, based on the average "outside" spot quotation at New York in 1916, a gain of $18,126,000, or nearly 24 per cent.

95186°—M R 1917, PT 1——57

Digitized by Google

Digitized by Google

COBALT.

By Frank L. Hess.

GENERAL CONDITIONS.

In 1917, as in former years, the cobalt used in the United States came from Cobalt, Canada, where the metal is obtained as a by-product of silver ores. The larger part of the cobalt is imported as oxide and is reduced in this country. Cobalt mines were being developed at two places in the United States in 1917. The Haynes Stellite Co., of Kokomo, Ind., began mining and erected a 10-stamp mill for experimentation in the narrow valley of Blackbird Creek, Lemhi County, Idaho, and the Missouri Cobalt Co. carried on some work at Fredericktown, Mo.

MINING OPERATIONS.

HAYNES STELLITE CO.

The property taken over by the Haynes Stellite Co. is composed of two groups of claims, 30 claims in all, 21 of which were formerly owned by J. M. Beliel. The main group and the mill, known as Haynes Camp, are on the north side of the main creek, about 4 miles above its mouth and about 2 miles below the old mining camp of Blackbird, now nearly deserted, and the other group is 2 miles southeast, on the West Fork of Blackbird Creek. The claims are 32 miles southwest of Salmon, the nearest railroad point, by a road that has numerous steep grades and makes the hauling of heavy loads difficult.

The deposits are in a banded, thin-bedded, very fine grained gray and black quartzite, with some interbedded dark-green schist. Both rocks are very resistant to weathering, so that the valleys cut through them are narrow, with steep walls buttressed by great accumulations of sharp-edged talus lying at angles as great as 41°. Narrow zones in the quartzite have been shattered, and in these zones solutions have deposited quartz, tourmaline, and minerals containing cobalt combined with arsenic and sulphur, probably mostly cobaltite, the arsenosulphide (CoAsS), as indicated by the pinkish color; there is also some smaltite, the arsenide ($CoAs_2$). It is probable that arsenopyrite (the iron arsenosulphide, FeAsS) is also present, and, as shown by the green efflorescence or "bloom" (annabergite) in some places on the outcrops, nickel is present in small quantity. No careful determinative work has yet been done on the minerals to show the exact proportions of cobalt, nickel, iron, arsenic, and sulphur.

The tourmaline in the veins on these claims is in crystals so minute that they are indistinguishable to the unaided eye; consequently

Digitized by Google

tourmaline was not recognized in the field. It forms so large a part of the gangue that the vein is black and can not ordinarily be told from the country rock. Most of the particles of cobalt minerals are so minute that they can not be seen in the rough rock, and whether ore or barren rock is at hand can be ascertained, at least by the inexperienced, only by crushing and panning. The country rock is hard and dense, but the vein matter is harder and denser, and this in itself gives some guidance to the miner in places where the infiltration of vein matter has been insufficient to make its characteristics visible. Such masses weather more slowly and stand out from the quartzite and schist. Microscopic measurements of the minerals from these claims showed many grains to be less than 0.01 millimeter (0.0004 inch) in diameter; probably most of the grains in specimens collected by the writer are about 0.03 millimeter (0.0012 inch) in diameter, and the larger grains reach 0.25 millimeter (0.01 inch). In places, however, the grains are of the size of popcorn or even larger, but these are exceptional. It is claimed that the ore as mined gave, in an experimental mill run before the property changed hands, more than 1 per cent of cobalt. The problem of milling is difficult, and it would seem probable that the ore should be ground to less than 200 mesh in order to make a reasonable saving. If this is not done, only the occasional large particles and aggregates of smaller mineral particles in tourmaline can be saved. Coarser crushing will leave a large percentage of the particles inclosed in quartz and tourmaline, and they will be lost in the tailings.

At Blackbird a large number of veins carry cobalt minerals. Here the veins are in schists and gneisses as well as in quartzites. They contain less tourmaline, larger particles of cobalt minerals, more nickel, and so much copper that considerable money has been spent in prospecting for that metal. Messrs. Wiley J. Rose, Charles Schultz, and Walter Rose were the only residents at the camp when it was visited in September, 1917, and they were still prospecting the numerous veins. Quartz veins reach a thickness of 10 feet, with subsidiary veins through a further thickness of 5 to 10 feet. Here and there tourmaline is found in visible crystals. No mill test has been made of the numerous properties for cobalt, but it seemed probable that some of the properties, to be selected by sampling, would be well worth testing if there is sufficient demand for cobalt. There is much more nickel as well as very much more copper in the ores immediately around Blackbird, and in most of the deposits the particles of cobalt minerals are very much coarser than at Haynes Camp. At Blackbird the Gray Eagle, owned by Wiley J. Rose, and other claims are located on a vertical crushed zone about 5 to 12 feet thick in schist on the northeast side of and parallel to Meadow Creek, one of the forks of Blackbird Creek. Where cut by a prospect tunnel on the Gray Eagle, this crushed zone strikes N. 40° W. and is in schist impregnated with quartz, which makes a very tough mass 10 to 12 feet thick that carries cobalt minerals. Ten feet southwest, pyrrhotite is found in bunches not over 6 inches thick, but on the St. Joe claim, adjoining the Gray Eagle claim on the northwest (owned by John E. Dubois, Dubois, Pa.), pyrrhotite 6 feet thick is said to have been cut at a depth of 100 feet and again at 250 feet, and is also said to have carried $18 a ton in gold and some

Digitized by Google

cobalt and nickel. The dumps on these claims where wet by Meadow Creek are nearly covered with the beautiful peach-bloom pink erythrite (cobalt arsenate). The workings are caved, for no work has been done in them since 1901.

On the Brown Bear claim, also owned by John E. Dubois, on Meadow Creek a mile above Blackbird, a considerable amount of work was done in 1901 and previous years on an ore body said to carry 2 to 3 per cent of copper, some cobalt and nickel, and also about $1.50 a ton in gold.

No cobalt minerals were seen in the dumps, but the occurrence of cobalt with copper in such a district would seem probable. Around the head of Meadow Creek, northeastward around the head of Little Deer Creek, and below Blackbird along Blackbird Creek there are numerous outcrops of cobalt-bearing veins, in which the aggregate quantity of the metal is large, though the reconnaissance made by the writer did not allow a determination of the quantity exposed in particular properties

Other cobalt-bearing veins are said to have been prospected on the north side of Big Creek 3 or 4 miles north of Blackbird, but they were not examined by the writer. Cobalt minerals have also been reported from localities some miles southeast of Blackbird Creek, but no confirmation of the report has come to hand.

MISSOURI COBALT CO.

The Missouri Cobalt Co. did some work on the deposits near Fredericktown, Mo., and planned to ship its sulphide concentrates to St. Louis to be burned for the manufacture of sulphuric acid, the clinker to be returned and treated for its content of cobalt, nickel, and copper.

USES.

The Haynes Stellite Co., of Kokomo, Ind., is undoubtedly the world's largest user of cobalt. The firm uses it in making the various grades of stellite, part of which have been described by Haynes[1] as follows:

> The malleable [stellite] alloys are composed almost entirely of cobalt and chromium only, though the proportion of the constituents may vary from 10 to 50 per cent of chromium, with a corresponding variation in the cobalt. These alloys are all hard and while they may be scratched by the file none of them is practically workable by this means. They can not be machined, but some of the softest ones may be drilled by means of a hard carbon steel drill or a drill composed of hard stellite. They resist nitric acid almost perfectly, even when boiling, particularly if the chromium content is over 15 per cent. They forge with difficulty at temperatures ranging from 750° to 1,200° C.
>
> They have been forged into the following forms: (*a*) Tableware, such as spoons, forks, knives, ladles, etc.; (*b*) surgical instruments, pocket knives, dental instruments, etc.; (*c*) evaporating dishes, crucible supports, lamp stands, etc.; (*d*) jewelry, including finger rings, cuff buttons, scarfpins, etc.
>
> These malleable alloys are all slowly attacked by either hydrochloric, sulphuric, or hydrofluoric acid, but are nearly immune to all chemical combinations, as well as the fruit acids. As the evaporating dishes made of this metal take a bright polish and can be made of comparatively light section, they will prove suitable for evaporating many chemical salts to dryness, and are particularly suitable for boiling the caustic alkalies. Substances may be evaporated to complete dryness in these vessels without any danger whatever of breaking the vessel, since the tensile strength of the alloy exceeds 100,000

[1] Haynes, Elwood, Stellite as a substitute for platinum: Jour. Ind. and Eng. Chemistry, vol. 9, pp. 974-975, October, 1917.

Digitized by Google

pounds to the square inch, and it also shows considerable elongation before rupture. When a vessel made of this material is struck by a hammer, it emits a clear, musical tone, and continues to vibrate for a considerable length of time. The vessels retain their luster in the chemical laboratory under practically all conditions, since they are not affected in the slightest degree by sulphuretted hydrogen, ammonium chloride, or other vapors. Futhermore, they are practically immune to acid vapors. They give most excellent results in the form of lamp stands, supporting rings, triangles, etc. When these are heated to full redness, they become covered with a deep blue-black film, which does not change either in weight or appearance by repeated heating, and as no scale ever forms, these articles retain their weight, stability, and smooth surface indefinitely under all sorts of use. They can be subjected to temperatures up to 1,200° C., and still retain a considerable amount of strength. In fact, the stellite alloys possess the highest "red hardness" of any of the alloys yet discovered.

The chemist is, as a rule, not much interested in jewelry excepting from a scientific standpoint. He is vitally interested, however, in the fact that the demand for platinum in jewelry has rendered the price of this material so high that it is almost unobtainable. Unfortunately, the demand for platinum in this line is largely based upon its high price. Comparatively a small amount was used in jewelry until after the price of platinum exceeded that of gold. It then became a fad, amounting almost to a mania, to substitute platinum for gold, wherever one's means would permit of doing so. All efforts to produce a substitute for platinum, which would give results equal or superior to that metal in many respects, have proved almost futile, since the very evil which these attempts have sought to remedy is held up by the purveyors of platinum jewelry as a virtue, namely, its high price; and notwithstanding "a rose by any other name would smell as sweet," it must in the eyes of fashion also cost as much, or more; in fact, the more the better. Whether this condition is to continue indefinitely or be limited by a legal enactment is a question for our Government to decide. Fashion, like fortune, is fickle, and may change radically at almost any instant.

Stellite would in many cases substitute to great advantage for platinum in jewelry. It is almost the same color, possesses a higher luster, and retains its luster very much better than platinum, since it is so hard that it is not easily scratched or abraded by ordinary use. It is absolutely immune against tarnish or corrosion in the air, and while it is not nearly so pliable as platinum, it can be worked into many of the forms used in jewelry without special difficulty. Finger rings can be made from it either in the plain form or adapted to the Tiffany setting, so that it may be used in conjunction with any gem desired. If preferable, plain band rings can be made of the cast metal, which are practically file proof, and at the same time possess a beautiful color and permanent luster.

Nonmalleable alloys contain tungsten or molybdenum and are hard enough to cut hard steels. They are sold in competition with high-speed steels, and the business has grown in four or five years until now the sales run into the millions of dollars. In a later paper [1] Haynes gives further details about stellite and briefly describes the hard alloys:

It is extremely desirable to have for use metals or alloys which remain permanent under atmospheric conditions, and at the same time have such physical properties as will enable them to be manufactured into instruments and utensils for daily service.

It was with a view to producing an alloy which would combine the permanence of the noble metals with the strength and hardness of steel that the writer made a long series of experiments, which finally resulted in the production of a series of such alloys.

As early as 1899, an alloy was produced by heating the mixed oxides of chromium and nickel with metallic aluminum. A small button was obtained which showed considerable malleability when cold, and when polished exhibited a bright luster which was not dimmed when the metal was boiled in either strong or dilute nitric acid. Moreover, the acid showed not the faintest color after such test. This alloy was somewhat harder than untempered steel and could be readily worked under the file or in the lathe.

The mixed oxides of cobalt and chromium were afterward reduced by the same method, but the little pellets of the alloy thus produced were thrown from the crucible

[1] Haynes, Elwood, Alloys of cobalt, chromium, tungsten, and molybdenum: Met. and Chem. Eng., May 15, 1918, pp. 541-542.

Digitized by Google

by the violence of the reaction. A few of these were collected and found to be very much harder than the corresponding nickel alloys. They showed the same resistance to nitric acid and were only attacked very slowly by hydrochloric and sulphuric acids.

Later, the mixed oxides were reduced by means of carbon, and it was found possible to cast the alloy into bars which showed remarkable strength, rigidity, and hardness, as well as complete immunity to all atmospheric influences. Polished samples of the alloy were exposed to the fumes of the chemical laboratory for months, and in some cases their surfaces became covered with a deposit of ammonium chloride, but this could be easily rubbed or washed away, and the alloy showed the same brilliant surface as before.

These binary alloys of cobalt and chromium were so hard that they would take a cutting edge and could be used in the place of steel for pocketknife blades and table knives. They were found to be malleable at a bright orange heat, even when the chromium content rose to 45 per cent or more. These high-chromium alloys were very hard to forge, but after forging into pocketknife blades, for example, they showed extremely fine grain, high elasticity, and a hardness equal to that of the best quality of steel pocketknife blades. The permanence, general utility, luster, and color of these blades are very remarkable.

This alloy may be truly termed steel's first rival, since it constitutes the first metallic combination yet discovered, so far as the writer is aware, which takes and holds an edge at least equal to that of the best steel, and at the same time it can be produced in almost any form in which steel is utilized. It is of course much more costly, owing to the high price of its constituents. This, however, does not preclude its use for the following articles: (*a*) Table knife blades; (*b*) pocket cutlery; (*c*) surgical instruments; (*d*) dental instruments; (*e*) small evaporating dishes; (*f*) spoons, forks, and scissors. Lancets made of this hard alloy are now in use by many expert surgeons and are proving highly satisfactory for this purpose, since they are immune to all antiseptic solutions employed in surgical work, and at the same time take a keen edge, equal to that of the best tool steel.

The first paper was read on the binary alloys of cobalt and chromium before the American Chemical Society in 1910 at San Francisco.

These alloys (containing W and Mo) can be readily cast into various forms and melt at a lower temperature than the binary alloys of cobalt and chromium.

The following articles have been made from the hard alloys: Lathe tools, milling cutters, saws, drawing dies, boring tools, drills, etc. These tools must be cast to the proper form, as they can not be forged nor otherwise manipulated by grinding.

Two of the stellite alloys used for cutting steel have been examined by Guillet and Godfroid,[1] whose article is epitomized in Chemical Abstracts thus:

Two constituents may be distinguished. This heterogeneity is one of its chief disadvantages and occasions somewhat inconsistent results. If heated to 1,150° and quenched in oil or hot water, neither its structure is changed nor its hardness, which has always a Brinell number above 512. On attempting to normalize the structure, a preliminary two hours heating at 1,000° was not sufficient, but six hours at the same temperature was. The analyses of two typical specimens of stellite are as follows:

A (1914).		B (1917).	
Carbon	1.79	Carbon	1.48
Silicon	.78	Silicon	.17
Manganese	.72	Sulphur	.01
Cobalt	34.60	Phosphorus	Trace.
Tungsten	12.70	Cobalt	55.6
Molybdenum	9.44	Tungsten	9.15
Vanadium	1.00	Chromium	33.6
Chromium	26.36		

Comparative machine tests with stellite tools of composition B were made upon three steels, including a mild steel, quenched and reheated, a gray cast steel, and a mottled cast steel of pearlite with graphite and a small amount of cementite. The bars tested had an initial diameter of 90 to 120 millimeters and were rotated at varying speeds in a

[1] Guillet, L., and Godfroid, H., Observations on stellite: Rev. metal., vol. 15, pt. 1, pp. 339-346, 1918; abstract by S. L. Chisholm in Chem. Abstracts, vol. 12, p. 2310, Nov. 20, 1918.

Digitized by Google

moderately powerful lathe. The stellite tool had a section 12 square millimeters. The depth of cut was constant at 1.5 millimeters and the advance was constant at 0.33 millimeter. The tests were not watered. With a special tool holder designed for the tests a constant resistance of 100 kilograms was maintained and comparative speeds observed of 66.10 meters, 54 meters, and 30 meters for the mild steel and gray and mottled castings, respectively. Stellite is a very useful alloy in that it can be used without special treatment and even then gives better service than the best high-speed steels actually on the market, of which the above-tested (brand "Double Chevron" of André Citroen) is a fair example. Its great disadvantage is its heterogeneity and consequent somewhat inconsistent results. Work has been undertaken and will later be published on the individual effect of each of its constituents.

In Canada stellite is manufactured by the Deloro Smelting & Manufacturing Co. at Deloro, Ontario.

Cobalt has been used to advantage in high-speed steels and as much as 30 per cent is added to some of the high-grade steels. Cobalt oxide is used in insect poisons, in making blue glasses, and in blue pottery glazes. Cobalt salts have been used in making "invisible" inks that become visible on heating, and for sundry other purposes.

A patent was issued (United States patent No. 1299037, dated June 5, 1917) to Hugh S. Cooper, Cleveland, Ohio, and assigned to the Electro-Metals Products Co. for a substitute for platinum for electrical purposes which consists of 70 per cent silver, 25 per cent palladium, and 5 per cent cobalt. Platinum may be substituted for the palladium and nickel for the cobalt with good results. The alloys are said to be adapted to use in coils, magnetos, and all vibrating instruments.

CONSUMPTION AND PRICES.

The quantity of cobalt used in this country is shown exactly by the imports.

Cobalt metal sold in 1917 for $1.50 to $2 a pound and the oxide for $1 to $1.50 a pound.

IMPORTS.

The following table is made up from statistics compiled by the Bureau of Foreign and Domestic Commerce:

Cobalt, cobalt ore and zaffer, and cobalt oxide imported and entered for immediate consumption in the United States, 1907–1917.

Year.	Cobalt and cobalt ore and zaffer.		Cobalt, oxide of.		Total.	
	Quantity (pounds).	Value.	Quantity (pounds).	Value.	Quantity (pounds).	Value.
1907	5,219	$1,821	42,794	$73,028	48,013	$74,849
1908	217,548	13,982	1,550	3,095	219,098	17,077
1909	2,314	631	9,818	11,065	12,132	11,696
1910	8,811	1,546	6,124	4,806	14,935	6,352
1911	579,520	48,104	22,934	11,047	602,454	59,151
1912	759,394	67,948	31,848	15,132	791,242	83,080
1913	164,119	69,581	45,277	26,154	209,396	95,735
1914	106,670	53,945	227,886	220,593	334,556	274,538
1915	53,375	70,283	154,672	148,828	208,047	219,111
1916	136,770	175,236	206,639	192,009	343,409	367,245
1917	223,794	369,950	276,406	275,821	500,200	645,771

Digitized by Google

CANADIAN PRODUCTION.

The production of cobalt and cobalt oxide in Canada during the last five years is shown in the following table:

Cobalt and cobalt oxides produced in Canada, 1913–1917. [a]

Year.	Metallic cobalt.		Cobalt oxide.		Mixed oxides of cobalt and nickel and other cobalt material.	
	Quantity (pounds).	Value.	Quantity (pounds).	Value.	Quantity (pounds).	Value.
1913	.....	.....	660,079	$525,028	3,216,000	$90,266
1914	.....	.....	899,027	571,710	2,079,001	79,995
1915	211,610	$197,994	423,717	338,273	.....	.....
1916	215,215	200,888	670,760	542,341	.....	.....
1917	393,773	616,633	802,448	1,104,500	.....	740,032

[a] McLeish, John, Annual report on the mineral production of Canada during the calendar year 1917, p. 36, Ottawa, 1919.

PUBLICATIONS.

Among recent patents issued are the following for high-speed steels and other alloys containing cobalt:

American Alloys Co., Metallic alloys: United States patent (to T. B. Brix) No. 1203180, October 31, 1916; British patent No. 108164, April 26, 1916; French patent No. 481659, January 5, 1917. Chem. Abstracts, vol. 11, pp. 3017–3018, November 20, 1917.

The alloy, composed principally of nickel or cobalt in a proportion between 55 and 75 per cent of the weight of the alloy and of one or more metals of the chromium group, such as chromium or chromium and titanium, in a proportion varying in weight between 12 and 23 per cent, together with silicon (about 4 per cent), copper (about 5 per cent), tungsten (0.25 per cent), aluminum (about 2 per cent), and manganese-titanium (about 3 per cent), which can be replaced by manganese and boron in the proportions of 2 per cent of manganese and 1 per cent of boron. The resulting alloy is attacked only by aqua regia, resists temperatures up to about 1,600°, possesses great strength, and is capable of taking and holding a good edge.

Brix, T. B., Alloy for edge tools and other uses: United States patent No. 1203555, October 31, 1916. Chem. Abstracts, vol. 2, p. 32, January 10, 1917.

Nickel or cobalt 60 to 70 is combined with chromium or chromium-tungsten or chromium-titanium 15 to 22 and tungsten 1 to 4 parts, using small quantities of copper and manganese to assist in melting to produce a homogeneous alloy, which is practically unaffected by ordinary acids. Small quantities of silicon, aluminum, and boron may also be used to modify the properties of the alloys.

Furness, Radclyffe (assignor to the Midvale Steel Co.), High-speed tool steel alloy: United States patent No. 1233862, July 17, 1917. Met. and Chem. Eng., vol. 17, p. 191, August 15, 1917.

The patent states that if a certain quantity of both cobalt and uranium be added to an ordinary high-speed tool steel, containing tungsten, chromium, and vanadium, a substantial increase in cutting efficiency is attained. The quantity of uranium is so small that it can not be said to replace the known high-speed tool steel additions, its presence even in apparently negligible proportion improving the efficiency of the tools.

	Preferred analysis.	Limiting proportions.
	Per cent.	*Per cent.*
Cobalt	4.5	3.0 to 7.0
Uranium	.7	.1 to 2.0
Tungsten	13.5	12.0 to 20.0
Chromium	3.5	2.0 to 6.0
Vanadium	1.5	.5 to 2.0
Carbon	.7	.5 to .9

Digitized by Google

PARKER, JAMES H., and DE LONG, B. H. (assigned to Carpenter Steel Co., Reading, Pa.), United States patent No. 1233118, July 10, 1917. Met. and Chem. Eng., vol. 17, p. 191, August 15, 1917.

An alloy high-speed tool steel of the tungsten-chromium-vanadium type with high proportion of cobalt and approximately the following composition:

Carbon	0.35
Vanadium	2.00
Chromium	3.50
Tungsten	12.00
Cobalt	30.00
Iron	52.15
	100.00

The proportions of iron and cobalt correspond with the eutectic proportions. It is claimed that the alloy will give maximum service with increase of possible speed and cut.

SHIGA, K. Alloys: British patent No. 114447, February 26, 1917. Abstract from Chem. Abstracts, vol. 12, p. 1456, 1918. Cf. Chem. Abstracts, vol. 12, p. 1168.

Alloys for surgical instruments and other purposes consist of 80 per cent or more of gold and 20 per cent or less of nickel, or they may consist of gold, nickel, and tungsten, with or without small quantities of other metals such as cobalt, chromium, manganese, or gold. The gold-nickel-tungsten alloy preferably contains more than 65 per cent of gold, less than 20 per cent of nickel, and less than 15 per cent of tungsten. The tungsten, and also the other metals such as cobalt, chromium, or manganese, when these are added, are first alloyed with the nickel. Silver when added is first alloyed with the gold.

Digitized by Google

MOLYBDENUM.

By FRANK L. HESS.

INTRODUCTION.

The molybdenite deposits of the United States are legion. This mineral has probably been found, at least in small quantity, in every State in which there are any considerable outcrops of granite. In the Rocky Mountain and other Western States individual occurrences are too numerous to record. Like gold leaf, molybdenite is apt to be spread so thinly and to make so great a show compared with its real bulk that a much exaggerated impression of its quantity is had unless dependence is placed on assays alone. Molybdenite (the sulphide of molybdenum (MoS_2) and by far the commonest molybdenum mineral) is so attractive when seen in the white quartz in which it is commonly found and so deceptive in its appearance of quantity, and so many stories of its great usefulness and value have been current, all with a touch of the mystery connected with supposed secret uses, that many persons have been induced to invest much more labor and money in molybdenum mining enterprises than careful investigation would warrant.

MINERALS AND ORES.

Molybdenum occurs in three minerals that are found in commercially valuable quantities. The principal mineral is molybdenite, the molybdenum sulphide (MoS_2). It is an original mineral and is found in pegmatite dikes, in quartz veins of all sizes, in masses of granular and porphyritic rocks through which it has been disseminated by fluids following cracks, and in contact-metamorphic deposits. The ores of molybdenite may be rich locally, but probably few large deposits average more than 1 per cent of MoS_2. Some deposits, like that near Climax, Colo., which carries from 0.6 to 1.5 per cent of MoS_2, are very large. The small deposits are innumerable.

Wulfenite, lead molybdate ($PbMoO_4$), is found in the oxidized parts of some lead veins, particularly those in the southwestern parts of the United States and adjoining parts of Mexico. Deposits have been worked in Spain and Austria. The ores carry greatly varying percentages of molybdenum, but the average is probably less than 1 per cent.

Molybdite, the molybdenum-iron oxide, is in a few places abundant enough to be considered an ore mineral, as at Climax, Colo., where considerable quantities of molybdenite have been oxidized.

Ilsemannite, the sulphate, has been found in some quantity in sandstone near Ouray, Utah, and may prove to be rich and extensive enough to be used as an ore.

Digitized by Google

PRODUCTION.

The output of molybdenum in 1917 in the United States was again the largest in the world for the year and amounted to 175 short tons of metal in 1,311 tons of concentrates, valued at approximately $495,350. Compared with that of many other metals, however, the output is insignificant. No molybdenum is known to have been produced in this country in 1911, 1912, or 1913, and very little in 1914, but in 1915 a considerable foreign demand arose and 91 tons of metal in concentrate and ore, valued at $114,866, was marketed, and in 1916, 103 tons in 1,228 tons of concentrates was sold for $205,000.



FIGURE 17.—Diagram showing prices of molybdenum ore and molybdenum in ferromolybdenum, of 1917.

MOLYBDENUM INDUSTRY BY STATES.

ARIZONA.

Arizona produced by far the largest quantity of molybdenum in 1917—344,950 pounds of metal in concentrates and ore shipped, valued at $487,985. As in 1916, most of the molybdenum was in wulfenite.

The Mammoth Development Co., at Shultz, 40 miles north of Tucson, operated the Mammoth mine and took some ore from the adjoining Collins claim. The workings of the Collins and Mammoth claims are connected, and all ore was raised through the Mammoth shaft. The mill is near San Pedro River at Mammoth, about 3 miles east of Shultz. It was enlarged during the year; flotation machinery was added; and experiments were made looking toward the separation of sphalerite and galena from a large vein cut in the course of exploitation work. The shaft timbers and the upper works of the mine were burned in the middle of October, and the mill was closed during the remainder of the year.

The Arizona Rare Metals Co. continued work at Mammoth on the old tailings of the Mammoth mine, made when the mine was

Digitized by Google

operated for gold alone. It was expected that the tailings would all be worked over by May 1, 1918.

Nine miles south of Pantano the Total Wreck mine, under the management of E. L. Vail, was operated for wulfenite and silver-lead ore. The wulfenite from the three workings mentioned was shipped to the Molybdenum Products Co., at Tucson. During the first part of the year this firm treated the wulfenite in a reverberatory furnace with soda ash and made a sodium-molybdate slag and metallic lead. Later a blast furnace was put up and the same products were made in it. For a time it was difficult to sell either the concentrates or the sodium molybdate, and ferromolybdenum was made in small electric furnaces manufactured at the plant. The furnace shells were sheet-steel cylinders lined with a paste of calcined iron-free magnesite with oxide of iron for a binder.

Later the sodium-molybdate slag was sold to the Atlantic Metal & Alloys Co., at Boonton, N. J., which made ferromolybdenum from it. The slags were rather difficult to treat, because the sodium attacked the furnace linings. The slags also contained arsenic and phosphorus, which made the obtaining of a pure ferromolybdenum a difficult process.

The second largest field of molybdenum operations in Arizona was along Copper Canyon, about 25 miles southeast of Yucca. Copper Canyon carries water only at rather long intervals. It drains southeastward in a trough, about 3 miles long, cut in the east side of the Hualpai Mountains and joins Deluge Wash, sloping eastward to Big Sandy River.

Beginning with the claims of the Arizona Molybdenite Consolidated, which are just across the divide (north) from the head of Copper Creek, a succession of groups of claims held for molybdenum extends to Deluge Wash and spreads both up and down the wash. Nearly all workings are on the east side of Copper Creek and are on quartz veins cutting granite. The veins are all similar in character and differ only in size and richness. They were deposited near the surface of a granitic intrusion as comparatively pure white quartz, probably with a small quantity of pyrite, chalcopyrite, sphalerite, and galena and possibly some molybdenite. Movement along the veins continued, the quartz was broken, and in cracks molybdenite and more pyrite and chalcopyrite were deposited. The Arizona Molybdenite Consolidated established a pleasant camp, erected a mill in which a great deal of experimental work was carried on, and drove some hundreds of feet of drifts on molybdenite-bearing quartz veins that have been considerably disturbed by faulting. The company's claims extend southward along the east side of Copper Canyon. The property was held in the names of the Arizona Molybdenite Mining Co., Yucca Molybdenite Co., and H. & S. Molybdenite, but they are now held in the one name—Arizona Molybdenite Consolidated. To the south across the ridge the head of Copper Canyon opens out into an amphitheater a mile or more wide, which is known as Copper Basin.

At the north end of this basin Adam Marsch mined molybdenite-bearing quartz, and next to him the Acme Molybdenum Co. did some prospecting. South of the Acme Molybdenum Co.'s claims J. S. McDonald prospected other veins on the Happy Jack Nos. 1 and 2 claims. His claims strike N. 40° E. and are joined on the northeast

Digitized by Google

by claims of the Arizona Molybdenite Consolidated on the top of the ridge.

The only company producing during the year was the Leviathan Mines Co., in Copper Canyon, about a mile from Deluge Wash. The company had sunk a shaft 220 feet deep on the Leviathan vein, a prominent quartz vein that crosses from one side of the canyon to the other and is as much as 20 feet wide, but in most places is probably nearer 7 feet wide. The shaft, following the vein, has an inclination of 8 feet to the 100 feet. Water was so scarce that the mill could run only two shifts a day. A pipe line had been run 4 miles to a point in Deluge Wash, from which it was expected a plentiful supply would be obtained, but it gave out in August. Water was obtained from the shaft, and a strong taste of pine oil in the water showed that it was receiving the drainage from the mill. Counting the back flow the shaft was furnishing about 5,000 gallons of water a day. The ore carried about 1 per cent of MoS_2, nearly as much copper in chalcopyrite, and less pyrite. Low-grade concentrates carrying 20 to 30 per cent of MoS_2 and 18 to 25 per cent of copper were made by oil flotation. No pay was received for the copper in selling the concentrates. Several hundred feet of drifting had been done on the 100-foot level, and a considerable quantity of ore had been broken down on the stulls.

The American Molybdenum Co.'s mill at the junction of Copper Canyon and Deluge Wash was idle during the year, and both the mill and the claims of the company were in litigation.

Some prospecting was done on molybdenum claims both above and below the junction of the washes.

The Hualpai Mountains contain numerous other molybdenite deposits. Also accessible from Yucca and about 18 miles northeast of it are deposits in a canyon on the west side of the range. This canyon is next north of that in which the Yucca Tungsten Co. has its mine and mill.

In the northeastern part of the range, 19 miles south of east from Kingman, C. O. Erixon and others have a group of claims on Bottleneck Wash. Here a large number of thin veins fill cracks in a closely jointed granite and form a stockwork. With the molybdenite are pyrite and a little zinc and copper sulphides. The molybdenite is leached from the outcrops of the veins, but in some places where the water table comes close to the surface there is an accumulation of molybdite (the hydrous iron-molybdenum oxide). Mr. Erixon says that in a drift at the bottom of a shaft 40 feet deep the material in the first 40 feet without sorting carried 0.5 per cent of molybdenite (MoS_2). The drift cut a fault from which 40 buckets (about 175 pounds each) of ore assayed 0.75 per cent of MoS_2.

About a mile south of Bottleneck Wash the Telluride Chief Mining Co. sunk a shaft and drove drifts on veins in granite carrying copper minerals. At a depth of 200 feet the workings cut quartz-feldspar dikes or veins 2 or 3 inches thick (as shown by the material saved at the mouth of the shaft) carrying blotches and stringers of molybdenite in fine scales. The dikes or veins are said to be close enough together to make a body of rock 26 feet across, carrying a little more than 1 per cent of MoS_2. A small shaft house, a 12-horsepower gasoline engine, and a good head frame are at the workings. Half a mile down the slope are half a dozen neat small buildings for the

Digitized by Google

mine force. The company has reorganized as the Standard Minerals Co.

On Soap Wash, 4 miles by road southwest of Bottleneck Wash, the Jackman claims were worked under bond and lease by Garford & Timkin. The claims are at a higher elevation than the others, and some trees give a pleasing change to the landscape. The group of claims is on a series of quartz veins in coarse granite and deeply cut by Soap Wash. Besides molybdenite the veins carry pyrite, chalcopyrite, sphalerite, and along with these one vein carries a little huebnerite. Another carries sparse needles of huebnerite alone. Work was done on a number of the veins, principally on one near the upper part of the claims, along which a drift was driven about 200 feet. The vein varied considerably in width, nearly pinching in places. At the face it was 3½ feet wide but carried very little molybdenum. Other drifts and a shaft (40 feet deep November 1) were dug on the vein, and crosscuts were run to other veins. The veins cut were not very promising. A few tons of ore carrying 3.5 per cent of MoS_2 is said to have been shipped to a mill operated by the lessees at Wickenburg.

At Copper Basin, 9 miles west of the railroad station of Skull Valley, Yavapai County, the Arizona Mines & Reduction Co. mined molybdenite and shipped the ore to its sampling and experimental plant at Wickenburg (Arizona Sampling & Reduction Co.).

At Duquesne, east of Nogales, the Duquesne Mining & Reduction Co. mined and concentrated molybdenite found with the copper ores worked by the company in contact-metamorphosed limestone. The company had on hand at the end of the year a considerable quantity of concentrates carrying 45 per cent of MoS_2.

At Helvetia, Pima County, the Helvetia Copper Co. mined molybdenite in connection with copper ore in a contact-metamorphic deposit. Part of the ore was shipped to Los Angeles and part to Deming, N. Mex.

In the Blue Tank mining district, 14 miles northeast of Wickenburg, the Arizona Molybdenum Co. mined wulfenite and concentrated it in a dry-process mill. Mrs. M. Walsh and others, who hold a part of the same vein, sunk a shaft 70 feet deep and erected buildings and machinery. The ore in general is said to carry between 1 and 2 per cent of MoS_2, but some is richer.

B. S. Wilson operated a mine 30 miles south of Casa Grande from which a small production of wulfenite concentrates carrying 11 per cent of MoO_3 was made

CALIFORNIA.

Several hundred tons of molybdenite-bearing rock was mined from the Parker & Loftus property on Boulder Creek, near Gibson Spur, on the Southern Pacific Railroad, in Shasta County, Calif. Part of the ore was shipped to Henry E. Wood & Co., Denver, Colo. The property is reached from Dunsmuir.

In the Little Walker district, near Bridgeport, Mono County, Samuel Fales did some prospecting on a molybdenite deposit, and in the northeastern part of the county, 4 miles from Sweetwater, Nev., Amigo & Maclean mined and shipped molybdenite ore, carrying 2.9 to 3.48 per cent of MoS_2.

Digitized by Google

In Tulare County San Francisco men prospected a deposit of molybdenite disseminated in granite high up on Kaweah River. It was visited by E. S. Larsen, of the United States Geological Survey, late in October, but a fall of snow prevented a satisfactory examination.

The Imperial Lode Mining & Reduction Co. did considerable work on a wulfenite-silver property 6 or 7 miles southwest of Lavic, San Bernardino County, but no production of wulfenite was made.

A molybdenum deposit in silicified granite in the New York Mountains, eastern San Bernardino County, was prospected during the year but without production.

Many other deposits, which are, however, unproductive, are known in other parts of the State.

COLORADO.

Active exploitation was begun by two companies, the Climax Molybdenum Co. and the Molybdenum Products Corporation, on different parts of the same large molybdenite deposit at Climax, Summit County, Colo. The Pingrey Mines & Ore Reduction Co., of Leadville, is also interested in the deposit and in 1915 and 1916 milled in an experimental way a considerable quantity of ore. The deposit was formerly covered in large part by claims of Charles J. Senter. The deposit is a huge mass of granite and related porphyries that have been very finely brecciated, then silicified and veined with quartz. Myriads of the thin quartz veinlets carry a little molybdenite. No other molybdenite deposit of comparable size is known. The MoS_2 content is small, 0.6 to 1.5 per cent, averaging probably between 0.7 and 1.0 per cent of MoS_2.

At Kokomo, a few miles north down the valley at the head of which is the large deposit just described, Ross McCausland mined some molybdenite ore from veins and shipped several hundred tons of ore to the Pingrey Mines & Ore Reduction Co.'s mill at Leadville.

The Phoenix Works mined molybdenite ore from a vein near Tincup and shipped it to their concentrating plant in Denver. The vein is 9 miles north of Pitkin. The ore carried between 1 and 2 per cent of MoS_2. There are a number of other molybdenum-quartz veins in the same general locality, on which a little prospecting was done. The concentration plant at Denver was about ready for operation at the end of the year.

At the head of Browns Creek, above the one-time station of Hortense, in Chaffee County, the molybdenite property once owned by H. C. Hayes was operated by Lowry, Deane, and associates (the Molybdenum Mines Co.) of Denver, though no shipments of ore are known to have been made. The deposit seems to be a pegmatitic quartz vein carrying molybdenite in flakes ranging from some an inch across to others that are very small. The vein contains some pyrite and chalcopyrite and is remarkable for the beryl crystals it carries.

The Primos Chemical Co. did not do much work at its deposits at Camp Urad, 12 miles west of Empire, during most of the year but started to build a new flotation mill and other buildings toward the end of the year.

Digitized by Google

MONTANA.

In the Bismarck mine of the Iowa-Montana Development Co., in the Tobacco Root Mountains, Madison County, Mont., 23 miles south of Jefferson Island, developed for copper, molybdenite has been found in a shoot through a depth of 600 feet or more. It is in the cracks of a quartz vein, and movement along the cracks has spread the molybdenite over the quartz like a paint. Some concentration experiments were carried on by J. C. Brown, the superintendent, but no production was made.

In Emigrant Canyon, about 5 miles above Chico, Park County, the Montana Molybdenum Co. drove a prospect tunnel said to be 300 feet long and made an open cut on a molybdenite deposit in which the molybdenite formed very thin veinlets in a greatly decomposed porphyry. The deposit is 500 feet or more above the creek on the steep north side of the valley. A small mill and experimental flotation plant were erected at the portal of the tunnel, and another small mill of a different type was erected in the valley, but the efforts were unsuccessful. The ore is very free from other metallic minerals.

NEVADA.

Near Osgood Mountain, 17 miles north of Golconda, Nev., a little handpicked molybdenite was mined by W. S. Obrien from a contact-metamorphic deposit. The deposit is of the type that in this neighborhood and elsewhere in Nevada carries scheelite.

OREGON.

A mill to concentrate molybdenite from a contact-metamorphic deposit was erected near Greenhorn, Oreg., but no production is known to have been made.

Molybdenite deposits on what are known as the Frazier claims, possibly 18 miles in a direct line south of Joseph, were prospected.

UTAH.

In the spring of 1917 a molybdenum deposit, unique in the United States, was found by E. B. Curtis and Moses Moore in a lenticular Tertiary sandstone on the south side of Duchesne River, 2 miles west of Ouray, Utah. Iron stains found by Mr. Curtis were thought to be carnotite or some related mineral, and excavations were made to investigate the occurrence. After a few feet of digging a sandstone appearing black to the eye was found, and the color was thought to be due to chalcocite. An attempt was made to pan the material, but it immediately turned the water deep blue and no copper minerals could be found. Moses Moore, who had tried to pan it, tested it for dyeing and found that it gave a good blue color to white fabrics, especially to silk. He called it to the attention of Henry J. Arnold, of Denver, and various assayers were asked to analyze the substance. None reported molybdenum in it, but upon submitting it to several dyeing firms for testing, one replied that it "used no molybdenum dyes." The rock was later submitted to the United States Geological Survey and the mineral was identified as ilsemannite, the sulphate of molybdenum (usually called oxide, following Dana), though it had

Digitized by Google

probably been identified by others with the hint afforded by the dyeing firm.

Mr. Arnold, Dr. A. W. Bell, and others undertook the exploitation of the deposit. As seen May 21, 1917, the mineral was found in a bed of sandstone which, in the 60 feet it had been exposed in an open cut and short prospect tunnel, increases from 8 or 10 inches to 3 feet in thickness. When mined the sandstone is black, but after drying in the open air it turns indigo-blue, though the density of the blue, indicating the quantity of ilsemannite present, differs in various parts of the rock indicated by lines parallel to the bedding. Further prospecting was done during the season, and a considerable quantity of the stained rock was said to be found.

Experiments in extracting the molybdenum salt were carried on by several persons, but no commercial product was made during the year.

WASHINGTON.

The Crown Point mine, on Railroad Creek, 19 miles west of Lake Chelan, Wash., produced a small quantity of high-grade ore during the year and a little hand-picked ore was sold. The deposit is a quartz vein high on a steep bluff and lies comparatively flat.

Molybdenite deposits were prospected on Three Fools Creek, in northwestern Whatcom County; near Conconully; and in Devils Canyon, Buena Vista mining district, King County, 26 miles east of Snoqualmie and 8 miles south of Berlin.

DISPOSITION OF MOLYBDENUM.

The Atlantic Metal & Alloys Co., Boonton, N. J.; the Arizona Rare Metals Co., Tucson, Ariz.; the Primos Chemical Co., Primos, Pa.; and the Rose Chemical Co., Los Angeles, Calif., made ferromolybdenum during the year. The Atlantic Metal & Alloys Co. went out of business during the year, and the Tungsten Products Co., of Boulder, took over its slag on hand and produced ferromolybdenum from it.

So far as is known, except for a small quantity used experimentally and another small quantity used by one firm in tool steels, all the ferromolybdenum made was exported, most if not all going to France, and most of the concentrates produced in this country that were not reduced to ferromolybdenum were also exported to France. Small quantities were used for the production of molybdic oxide, molybdic acid, and ammonium molybdate. The molybdic oxide and molybdic acid were used either to make ammonium molybdate or molybdenum (metal).

USES.

The uses of molybdenum are more largely potential than actual. The minerals of the metal and the metal itself are showy and attractive and countless experiments have been made with a view to its profitable utilization. Probably the greatest number of these experiments have been made with a view to utilizing molybdenum in tool steels, either as a substitute for or in conjunction with tungsten. To steel, molybdenum is generally added as a ferro that is made in the electric furnace, as is ferrotungsten. To date the use of molybdenum in tool steels has not been extensive, but some experimenters have great

Digitized by Google

faith in its future use for this purpose. Later efforts have been directed toward the use of molybdenum in fractions of 1 per cent to make steels of high tensile, torsional, and elastic limits, somewhat as vanadium is used, and for these purposes it is finding ardent advocates. Widely current rumors that the Ford Motor Co. was going to use molybdenum in the steels for its cars were generally quoted as a basis for operations. The company was known to have sent representatives through the United States and to points in Canada and Mexico examining deposits. From the fact that one automobile company was said to intend to use molybdenum it was an easy step for the imaginative to the supposition that all automobile companies would quickly be using molybdenum, and although this may or may not eventually take place, far more effort was expended on deposits than the present use and demand warranted.

The current established uses are for making wire to be used for the support of the filament in tungsten incandescent electric lamps, for the ring around the helix in Coolidge (X-ray) tubes, and as ammonium molybdate for the determination of phosphorus.

CONCENTRATION AND REDUCTION.

Molybdenite is usually separated from its gangue, if in large flakes, by hand picking; if in small flakes, by some form of flotation, either by oil or water. Miners in Australia have for a long time used a process of water flotation with primitive appliances. In recent years Henry E. Wood invented a machine by which the process is carried on more effectively. Oxide formed from molybdenite must first be sulphidized before being floated.

Wulfenite is separated from its gangue by table concentration and when in a very fine state by sulphidation and flotation. Separation from cerusite, vanadinite, and other heavy minerals is effected by sulphidation and selective flotation or by a chemical process in which the molybdenum is precipitated as calcium molybdate ($CaMoO_4$).

The pure metal, like tungsten, is prepared by the reduction of the oxide by hydrogen at a red heat and, owing to its high melting point, is obtained as a powder. For wire or other malleable molybdenum forms the powder is formed into bars under tremendous pressure, sintered by an electric current, mechanically swaged, and then rolled or drawn as desired.

Digitized by Google

Digitized by Google

NICKEL.

By FRANK L. HESS.

PRODUCTION.

The United States produces no nickel from domestic materials except as a by-product of copper refining. The production of by-product nickel since 1911 has been as follows:

Nickel content of nickel salts and metallic nickel produced as a by-product in the electrolytic refining of copper, 1911–1917.

Year.	Quantity (short tons).	Value.
1911	445	$127,000
1912	328	93,600
1913	241	79,393
1914	423	313,000
1915	822	538,222
1916	918	671,192
1917	402	331,556

This country depends almost wholly for its supply of nickel on metal from Canada, but a little is brought from New Caledonia. All comes in the form of matte. That from Canada is produced and matted at Copper Cliff, Ontario, by the International Nickel Co. and refined at Bayonne, N. J. Matte made in France from New Caledonian ores is refined by the United States Nickel Co., at New Brunswick, N. J.

CANADA.

As much the greatest part of the nickel for the United States and for the rest of the world comes from Canada, nothing better can be done than quote the report of McLeish[1] on the output in 1917, which reads as follows:

The production of nickel in 1917 amounted to 84,330,280 pounds, valued at $33,732,112, as compared with 82,958,564 pounds, valued at $29,035,497, in 1916, an increase of 1.6 per cent, while in 1916 there had been an increase of 21.4 per cent over that of 1915.

There were mined in 1917, 1,509,841 tons of ore, and smelted 1,453,661 tons, from which were produced 78,897 tons of Bessemer matte carrying approximately 41,887 tons of nickel and 21,196 tons of copper. The net value of the matte, as reported by the operators, was $12,004,141, which is based on an average price of 7.15 cents per pound for the copper and 10.71 cents for the nickel. The average metal recovery in matte from the ores treated was 2.881 per cent nickel and 1.458 per cent copper, as against 2.714 per cent nickel and 1.474 per cent copper in 1916, and 2.675 per cent nickel and 1.541 per cent copper in 1915.

[1] McLeish, John, Annual report on the mineral production of Canada during the calendar year 1917, pp. 99–101, 1919.

Digitized by Google

Production of nickel from the Sudbury district ores,[1] Canada, 1917.

Ore mined	short tons..	1,509,841
Ore smelted	do....	1,453,661
Bessemer matte produced	do....	78,897
Copper content of matte	do....	21,196
Nickel content of matte	do....	41,887
Spot value of matte		$12,004,141
Wages paid miners and smelters		$5,438,830
Men employed		4,517

Annual production of nickel in Canada, 1908–1917.

Year.	Nickel.	Cents per pound.	Value.
	Pounds.		
1908	19,143,111	43	$8,231,538
1909	26,282,991	36	9,461,877
1910	37,271,033	30	11,181,310
1911	34,098,744	30	10,229,623
1912	44,841,542	30	13,452,463
1913	49,676,772	30	14,903,032
1914	45,517,937	30	13,655,381
1915 [a]	68,308,657	30	20,492,597
1916 [a]	82,958,564	35	29,035,497
1917 [a]	84,330,280	40	33,732,112

[a] Includes also the production from the silver ores of Cobalt district.

The nickel-copper ore is reduced in smelters and converters to a Bessemer matte, containing from 77 to 82 per cent of the combined metals; in 1917 it averaged 50.6 per cent nickel and 26.9 per cent copper, as against 51.6 per cent nickel and 28 per cent copper in 1916; 50.3 per cent nickel and 29 per cent copper in 1915; 49 and 31.1, respectively, in 1914; and 52.7 and 27.4, respectively, in 1913.

For the production of monel metal a special matte is produced with contents of about 22 per cent copper and 58 per cent nickel, which is included in the total given. Monel metal is produced directly from this matte without the intermediate refining of either the nickel or the copper.

A paper on the "Manufactures of nickel-copper alloy steel or nicu steel," by G. M. Colvocoresses, was read at the annual meeting of the Canadian Mining Institute in March, 1918. Practical tests of the processes are said to be carried on at present near Sudbury.

The industry based on the mining and metallurgical treatment of the nickel-copper ores of the Sudbury district, Ontario, ranks among the most important of Canada. Not only is there a considerable production of copper, but the nickel, which is the important product, supplies a very large proportion of the world's consumption of the metal.

The past few years' development has very largely increased the known ore reserves of the district. These nickel-copper deposits have been the subject of special reports by the Mines Branch and Geological Survey at Ottawa, by the Ontario Bureau of Mines, Toronto, and recently by the Royal Ontario Nickel Commission.[2]

Refined metallic nickel is now being recovered in Canadian refineries but only in small quantities and as a by-product in the smelting and refining of the silver-cobalt-nickel ores, nickel oxide having been recovered in these smelters for several years. The recovery of nickel sulphate was also reported for the first time in 1915. A considerable amount of nickel is probably contained in ores exported for smelting, for which no payment is received by the mines shipping, and the amount finally recovered is impossible to ascertain.

The total estimated nickel content of the recoveries from silver-cobalt-nickel ores was in 1917, 556,961 pounds, as against 361,702 pounds in 1916 and 231,634 pounds in 1915.

[1] Includes also the production from the Alexo mine, Timiskaming.

[2] Barlow, A. E., Report on nickel and copper deposits of Sudbury, Ontario: Canada Geol. Survey, No. 873, 1901.
Coleman, A. P., The Sudbury nickel region: Ontario Bur. Mines, vol. 14, pt. 3, 1904.
Coleman, A. P., The nickel industry with special reference to the Sudbury region, Ontario: Report by Mines Branch, No. 170, Ottawa, 1913.
Report of the Royal Ontario Nickel Commission, with appendix, Toronto, 1917.

Digitized by Google

The production of metallic nickel during the year was reported as 265,896 pounds, valued by the operators at $108,334, as against 79,360 pounds, valued at $31,538, in 1916; that of nickel oxide and nickel sulphate was 657,549 pounds, valued at $122,963, as against 555,868 pounds, valued at $101,358, in 1916.

The companies engaged in mining and smelting nickel ores are:

The Canadian Copper Co., subsidiary to the International Nickel Co., with smelter at Copper Cliff, Ontario, and refinery at Bayonne, N. J. This company is completing the erection of a new refining plant at Port Colborne, Ontario, which will probably be in operation in July, 1918.

The Mond Nickel Co., of London, England, with smelter at Coniston, Ontario, and refinery at Clydach, Swansea, Wales.

The British America Nickel Corporation (Ltd.), which started erecting a smelter at the Murray mine late in 1916, and early in 1918 a refinery near Lake Deschenes, Hull County, Quebec, although not shipping during the year, actively carried on development.

The Alexo Mining Co. (Ltd.), which operated its mine at Porquis Junction on the Porcupine branch of the Timiskaming & Northern Ontario Railway, shipping nickel-copper ore to the Mond smelter at Coniston.

Nickel was recovered as a by-product in the smelters of the following companies: The Coniagas Reduction Co., Thorold, Ontario; the Deloro Smelting & Refining Co., Deloro, Ontario; the Metals Chemical Co. (Ltd.), Welland, Ontario.

USES.

Nickel is used in most good steels except tool steels, in making white metals, in nickel plating, in resistance wires for electrical work, in contact points, in coinage, and for many minor uses. Monel metal, an alloy of nickel, copper, and iron, is used for valves on high-pressure steam systems and for many articles that must resist sulphuric and other acids. W. B. Lawson, of the International Nickel Co., has estimated that the consumption of nickel is divided as follows: In nickel steel, 60 per cent; in white metals, 30 per cent; in anodes for electroplating, 5 per cent; in miscellaneous uses, 5 per cent.

So far as is known to the United States Geological Survey no substitutes have been offered wholly to replace nickel in steel, though it has been stated that the nickel may be replaced in part by copper and cobalt, with similar results. One steel company is known to have used monel metal in steel in place of pure nickel. Steel without nickel can be used, but no other steel is quite so good.

The white metals may largely be replaced by brass, iron, pewter, or other alloys, the substitute to be employed depending on the use to which the article is to be put. Of course, a substitute nearly always lacks some desirable characteristic of the material replaced, such as ease of working, cheapness, beauty, or durability, else it would not be a substitute but would itself be the preferred substance. For the preservation of surfaces afforded by nickel plating electroplating with cobalt or brass, galvanizing, sherardizing, tin plating, japanning, or painting may be substituted. Brass, bronze, and iron are used in place of monel metal.

The market for nickel largely depends on the briskness of the steel business, and without its support nickel production would subside to a lowly place. In nickel steels for armor plate, for large and small guns, and for some other uses, chromium is also added. Nickel in steels usually ranges between 2 and 3.75 per cent.

In the white metals nickel is alloyed with copper and zinc in various proportions, and to some alloys lead, iron, and tin, any one or all, are added.

Digitized by Google

MODES OF OCCURRENCE.

Nickel is found in two principal types of deposits—(1) pyrrhotite deposits, which carry small quantities of pentlandite, the nickel-iron sulphide (generally not visible unless the rock is polished), and (2) nickel-magnesium silicate (genthite or garnierite), formed through the oxidation and disintegration of dunites, serpentines, and similar rocks. To the first class belong the great deposits at Sudbury, Ontario, and to the second class the deposits of New Caledonia. Besides these, there are veins carrying sulphides, arsenides, and antimonides of nickel, usually in more easily recognizable forms than in the pyrrhotite deposits. Some lateritic iron ores, such as those of Mayari, Cuba, carry about 1 per cent of nickel. The nickel passes into the steel made from this ore and is thus utilized.

At Fredericktown, Mo., nickel is found with sulphides of zinc, lead, iron, copper, and cobalt in sediments. Small quantities of nickel, generally a few pounds per 100 tons of blister copper, are found in the great copper sulphide deposits, and the nickel is saved in the electrolytic refining of the copper. This forms the only present source of nickel in the United States.

Serpentine in large masses carries from 0.25 to 1 per cent of nickel and may some day form a source of the metal.

RECOVERY.

The sulphides are roasted and smelted to a nickel-copper matte, and the matte is then (1) treated so as to slag off most of the iron sulphide, leaving a matte from which the nickel-copper-iron alloy, monel metal, is obtained; (2) treated by the Orford process so as to slag off both iron and copper with sodium sulphide, the resulting nickel sulphide being roasted and reduced with carbon; (3) treated by the Mond process, in which the matte is roasted, the copper extracted with sulphuric acid, the nickel and remaining copper reduced to metal and the nickel made into nickel carbonyl, a gas, and then reduced to a very pure metal; or (4) roasted, as in the Hybinette process, the copper leached out, and the nickel electrolytically separated. The silicate ores are treated with lime and sulphur, either added as such or in the form of gypsum, and thus the silica and iron are slagged off and the nickel is formed into a matte; the matte is oxidized, and from the resulting oxide the nickel is reduced with carbon.

In the United States the nickel produced is a by-product from the electrolytic refining of copper. The nickel goes into solution in the electrolyte, is later separated as sulphate or nickel-ammonium sulphate, and is sold as such or reduced to metal.

GEOGRAPHIC DISTRIBUTION.

Nickel-bearing deposits are widely distributed over the earth, but of those known the deposits at Sudbury, Ontario, far overshadow all others; in fact, it might not be far out of the way to say that they are as large as all others combined. E. P. Matthewson estimated the world's production in 1916 to be approximately as follows:[1]

[1] Matthewson, E. P., Nickel: Canadian Min. Jour., vol. 38, p. 196, May 1, 1917.

Digitized by Google

Estimated world's production of nickel in 1916.

	Quantity (short tons).	Percentage of total.
Canada	42,000	85.8
New Caledonia	4,500	9.2
Norway	1,000	2.0
United States	1,000	2.0
All other countries	500	1.0
	49,000	100.0

The estimated output of the United States is too high, but though, as stated, the figures are approximate only, they show the great preponderance of the Canadian output, which may fairly be considered as in proportion to the size of the deposits.

The nickel content of the Canadian ores varies considerably. The Copper Cliff mine gave large quantities of ore averaging 3.52 per cent of nickel and 5.13 per cent of copper. Hand-picked ore from the Creighton mine carried 4.44 per cent of nickel and 1.56 per cent of copper. Other ores averaged from 2 to 4 per cent of nickel and from 1 to 2 per cent of copper.[1]

The New Caledonian deposits carry hydrous nickel-magnesium silicate, known in this country as genthite but there called garnierite, of which a variety has been called noumeite. Carefully hand-picked ore carries 4.5 to 6.5 per cent of nickel, and from 8 to 10 tons of waste must be handled for each ton of ore.[1]

The Norwegian ore is a pyrrhotite somewhat similar to that found in Ontario, but the deposits are smaller and the ore is leaner. Most hand-sorted ore carries 1.4 to 1.7 per cent nickel. Exceptional lots carry 2 to 2.5 per cent nickel.[2]

Greece has deposits of genthite formed from serpentine at Lokris and Thebes, in the Scropo Neri Mountains, 7 miles southwest of Larmes, from which shipments have been made to Norway. Nickel and cobalt also form 0.1 to 1.2 per cent of iron ores found with serpentines at these and other Grecian localities.[3]

Germany and Austria have comparatively small deposits of sulphide, arsenide, and silicate ores of nickel, from which some ores have been mined in normal times. They cut little figure in the world's output.

CONSUMPTION AND CONTROL.

An American company, the International Nickel Co., owns the largest productive nickel deposits and produced about two-thirds of the Canadian nickel, but as the mines are in the Sudbury region, the disposal of the product has been wholly ruled by Canada. Before 1918 the entire product was refined at Bayonne, N. J., but the Canadian Government compelled the erection of another refinery at Port Colborne, Ontario, that will do part of the refining. The Mond Nickel Co., which produces nearly all of the remaining third of the

[1] Holloway, G. T., Miller, W. G., Young, McGregor, and Gibson, T. W., Report of the Royal Ontario Nickel Commission, chap. 4, 1917.

[2] Beyschlag, F., Krusch, P., and Vogt, J. H. L., Ore deposits, Truscott's translation, p. 297, 1909.

[3] Scott, H. K., Chromiferous iron ores of Greece and their utilization. Iron and Steel Inst. Jour., vol. 87, pp. 447-467, 1913.

Digitized by Google

Canadian output, refines its matte at Clydach, Wales. The New Caledonian ores are partly smelted and refined on the island, partly in France, Belgium, England, Germany, and the United States.

The German and Belgian refineries were cut off by the war, but probably the Belgian refineries, at least, will again take up the work.

The United States is the greatest consumer of nickel, followed probably in order by England, Germany, and France.

The International Nickel Co. is the great commercial force in the nickel industry and handles about three-fourths of the world's output. Politically, however, its output is controlled by Great Britain through Canada. The second large producer, the Mond Nickel Co., is entirely British. The British American Nickel Co., also British, has under way a large plant for the production of nickel.

Control of New Caledonian nickel is politically French, but commercially is French, British, and Belgian.

The output of nickel in the world outside of Canada in 1917 can probably be estimated at 5,000 to 7,000 tons.

PRICES.

According to quotations furnished to the technical press in 1917, the price of refined nickel in New York was 45 to 50 cents a pound until March; from March to August, 50 to 55 cents; and from August to the end of the year, 50 cents, depending on quantity. Electrolytic nickel was 5 cents a pound higher. Large steel companies and companies working on Government contracts obtained their nickel at lower prices.

IMPORTS.

Nickel ores and nickel matte are specifically exempted from duty,[1] but imported "nickel, nickel oxide, alloy of any kind in which nickel is a component material of chief value, in pigs, ingots, bars, rods, or plates" must pay a duty of 10 per cent ad valorem; sheets or strips, 20 per cent.[2]

The imports of nickel for consumption in the United States for several years, as reported by the Bureau of Foreign and Domestic Commerce, have been as follows:

Nickel imported for consumption in the United States, 1910–1917.

Year.	Nickel, nickel ore and matte, nickel oxide, alloys of nickel with copper, etc.[a]		Value of manufactured articles of nickel and nickel sheets and strips.	Total value.
	Quantity.	Value.		
	Pounds.			
1910	32,363,251	$4,213,079	$14,759	$4,227,838
1911	29,829,268	4,022,716	27,314	4,050,030
1912	46,317,078	5,724,431	34,536	5,758,967
1913	47,446,520	6,562,555	38,200	6,600,755
1914	35,068,958	5,000,594	28,224	5,028,818
1915	56,599,381	7,629,686	6,458	7,636,144
1916	72,649,377	9,899,340	25,880	9,925,220
1917	75,526,767	9,617,163	45,248	9,662,411

[a] Includes only the nickel content of ore and matte. No ore is known to have been imported into the United States in 1911, 1912, or 1913.

[1] Tariff act of Oct. 3, 1913, sec. 565.
[2] Idem, sec. 155.

Digitized by Google

Nickel imported for consumption in the United States, 1915–1917, by forms.

Form.	1915		1916		1917	
	Quantity (pounds).	Value.	Quantity (pounds).	Value.	Quantity (pounds).	Value.
Nickel, alloys, pig, bars, etc	31,990	$13,557	29,917	$7,869	48	$19
Ore and matte (nickel content)	56,566,594	7,615,999	72,611,492	9,889,122	75,510,793	9,612,400
Nickel oxide	497	130	7,968	2,349	15,926	4,744
Nickel sheets or strips				4,896		
Nickel, all other manufactures of		6,458		20,984		45,248
	56,599,381	7,636,144	72,649,377	9,925,220	75,526,767	9,662,411

Nickel ore and matte imported into the United States in 1917, by country of origin.

Country.	Quantity.	Nickel content.	Value.
	Short tons.	*Pounds.*	
Canada	65,916	73,530,259	$9,138,994
Australia (Tasmania)	2,463	1,980,534	473,406
French Oceania (New Caledonia)			

EXPORTS.

The United States refines much more nickel than it uses, so that though not a large producer it is a large exporter.

Nickel, nickel oxide, and matte[a] exported from the United States, 1910–1917.

Year.	Quantity (pounds).	Value.	Year.	Quantity (pounds).	Value.
1910	15,244,937	$4,704,088	1914	27,595,152	$9,455,528
1911	25,099,886	8,283,777	1915	26,418,550	10,128,514
1912	25,815,016	8,515,332	1916	33,404,011	12,952,493
1913	29,173,088	9,686,794	1917	21,992,820	8,936,620

[a] No nickel matte is known to have been exported in the years 1911 to 1917, inclusive.

Manufactures of nickel were exported to the value of $1,527,353.

PUBLICATIONS.

In 1917 the most comprehensive and complete volume on nickel yet printed was issued by the Royal Ontario Nickel Commission, composed of George T. Holloway (since deceased), W. G. Miller, McGregor Young, and Thomas W. Gibson. The report proper contains 584 pages, and there is an appendix of 219 pages. The volume treats not only of the nickel deposits of Canada but of all other known deposits of nickel in the world. It also treats of the uses, metallurgy, recovery of by-products, taxation, statistics, and other related subjects. The appendix contains testimony taken by the commission concerning the operation of the various mines and smelters and concerning other matters pertaining to the nickel industry.

Digitized by Google

Among the recent publications and patents issed on nickel are the following:

ADDICKS, LAWRENCE, Impurities in electrolytic copper refining: Met. and Chem. Eng., vol. 16, pp. 687–692, 1917. Abstract by A. Buttes, Chem. Abstracts, vol. 11, pp. 2997–2998, November 20, 1917.

Apart from the blister copper itself, fuel, fluxes, and acids are to be considered as introducing impurities. Of the important insolubles in the electrolyte, gold, silver, selenium, tellurium, more than 99 per cent goes into the slimes, the remainder contaminating the cathodes mechanically. The soluble impurities foul the electrolyte, nickel and arsenic being the controlling ones. Four distinct methods have been used for purifying the electrolyte: (1) The early method was to cement the copper on scrap iron and waste all of the solution. (2) The free acid was neutralized with shot copper, and the copper and acid recovered as bluestone by recrystallization. (3) A portion of the electrolyte in circuit was diverted to a series of 3 tanks with insoluble anodes, plating out the copper and arsenic by steps to below 0.1 per cent. The nickel, if low, was returned in the purified solution to the circuit. (4) Complete cyclical purification is in general use to-day. The steps in (2) are followed by boiling down and crystallization of the nickel as sulphate. The article gives valuable details and analyses.

ANNABLE, H. W. C., Extracting nickel from silicate ores: United States patent No. 1289072, December 31, 1918. Chem. Abstracts, vol. 13, p. 705, April 10, 1919.

Garnierite ore is ground and then intimately mixed with iron pyrites and sodium chloride, sodium carbonate, sodium sulphate, potassium carbonate or potassium sulphate, and the mixture is heated to 650°–800° in contact with steam and with exclusion of air, to form nickel sulphide. The resulting product, containing ferrous sulphide and nickel sulphide, is heated in air to a temperature sufficiently high to oxidize the sulphides to sulphates and to decompose the iron sulphate without decomposing the nickel sulphate and the hot oxidized product is discharged into water which is maintained at a temperature below 30° to dissolve the nickel sulphate. In case basic nickel sulphate has been formed, hydrochloric acid is added to the water to effect its solution. After separation of the nickel sulphate solution, the nickel may be recovered from it by precipitation with a carbonate or sulphide, that is, by adding calcium carbonate to the solution and passing furnace gases from the roasting furnace directly into the solution. The precipitated salt of nickel is dried and heated in the atmosphere to form nickel oxide. If the mixture of sulphides of iron and nickel is heated and sodium chloride is then added to the product to be oxidized, a much lower yield of solution of nickel is obtained. Sea water may be used as a source of sodium chloride in the process.

BONNEFOND, M. F., Les mines de Madagascar en 1918: Soc. ing. civ. France Bull., ser. 8, Nos. 7–9, pp. 369–370, 1918.

There is a very important deposit of nickel (hydrosilicate) at Valozoro, near Ambositra.

Considerable exploratory work was done on this deposit in 1912, which exposed a mass of lean ore (2 to 4 per cent). Some samples attained a tenor of 10 per cent. There are large waterfalls in the neighborhood. This undertaking, which belongs to an English syndicate, will be taken up again after the war.

Another deposit has been discovered 25 kilometers east of Ambatondrazaka. Several adits have been run, about 300 to 400 meters in all, through the serpentine rock and have cut veinlets of rich ore carrying an average of 5 to 6 per cent of nickel. Some samples yielded as much as 12 per cent. The mobilization of the prospector, who returned to France, stopped the exploration, which will be taken up again after the war.

These two deposits, the one at Valozoro and the one at Ambatondrazaka, are near large forests and also near streams having considerable fall which would furnish all the power needed for electrometallurgical or electrochemical treatment. The wood necessary for the reduction of the ores and for timbering the galleries is found almost on the spot.

COLVOCORESSES, G. M. (Humboldt, Ariz.), "Nicu" steel and its manufacture: Canadian Mining Inst. Trans., vol. 21, pp. 48–79, 1918.

COOPER, H. S., Nickel alloy: United States patent No. 1277046, August 27, 1918. Chem. Abstracts, vol. 12, p. 2077, October 20, 1918.

Alloys which are stated to be superior to "high-speed" steel for cutting tools are formed of nickel 71–78, aluminum 7.5–7.9, silicon 3.4–3.8, zirconium 6.1–6.5, and tungsten 4–12 parts. Cobalt may replace nickel, and other metals such as molybdenum, chromium, or uranium may be substituted for tungsten.

Digitized by Google

ER, H. S., Nickel alloy: United States patent No. 1278304, September 10, 1918. hem. Abstracts, vol. 12, p. 2312, November 20, 1918.

An alloy suitable for making machine tools is formed of aluminum 2 to 14, ickel 81 to 88, silicon 1 to 10, and zirconium 0.5 to 15 parts.

BER, M. A., Some quantitative measurements of the minerals of the nickel-uptive at Sudbury: Econ. Geology, vol. 12, pp. 563–580, 1917. Abstract by . B. Peck, Chem. Abstracts, vol. 12, p. 1450, 1918.

Thin sections and polished surfaces were used to determine [quantitatively] the acturing in the minerals composing the rock. From these observations it was ncluded that the schistosity was developed before the norite had entirely lidified, possibly when the Sudbury syncline was formed, giving rise to a filter-pressing" action whereby the more liquid magma and aqueous vapors ere squeezed out, attacked the pyroxenes, and formed the hornblende and ılorite as now found. Differentiation upon cooling is considered to be the ıief source of the ore body, but the idea of filter-pressing is suggested to account r part of the ore and the acid rock near the base of the norite.

ER, W. B., Nickel alloy for spark-plug electrodes: United States patent No. 274395, August 6, 1918. Chem. Abstracts, vol. 12, p. 1951, October 10, 1918.

An alloy for making spark-plug electrodes is formed of manganese 2 per cent, ıromium 3.5 per cent, and nickel or cobalt 94.5 per cent.

CE, C. R., and HUBBARD, BELA, The limonite deposits of Mayaquez Mesa, Porto ico: Am. Inst. Min. Eng. Bull., 1918, pp. 661–676. Abstract by E. T. Wherry hem. Abstracts, vol. 12, p. 891, May 10, 1918.

The location and geology of the region are briefly described. A mantle of bright d soil occurs upon a serpentine rock; analysis of the latter is given and recalcu-ted into a mineral composition. The most interesting features are the presence 1.30 per cent of nickel-serpentine and the apparent existence of some umina in a hydroxide form, calculated for simplicity as gibbsite, aluminum ydroxide, 4.21 per cent. Most of the limonite deposit is loose, porous, and earthy. artial analyses of eight samples are given, with a complete analysis of one. When ıis is recast into mineral composition, there seems to be present 25.67 per cent of auxite, with about 65 per cent of iron oxides. Study of the field relations, of thin ctions, and of the analyses leads to the conclusion that the limonite has formed y decomposition of the serpentine rock in place, under the influence of circulating aters; the chemical changes involved are outlined. Similar deposits in other gions are also discussed for comparison, many analyses being quoted.

s, J. H., Recovering nickel from nickel-copper alloys: United States patent o. 1260661, March 26, 1918. Chem. Abstracts, vol. 12, p. 1443, 1918.

An electric current is passed from a nickel-copper anode to a cathode through ı electrolyte containing a nickel salt. The polarity of the electrodes is reversed ; such intervals and for such periods as to avoid substantial deposition of copper pon the cathode.

s, G. A., Electrodeposition of nickel from a nickel-copper anode: British patent o. 118629, August 14, 1918. Chem. Abstracts, vol. 13, p. 95, January 20, 1919.

A nickel-copper anode in a nickel sulphate solution is maintained in contact ith a reagent which forms with copper sulphate an insoluble copper compound ıd a noninjurious sulphate. The cathode is screened from the reagent and ceives a deposit of nickel. Suitable reagents are limestone, calcium oxide, or milar alkaline earths, which give insoluble sulphates, or nickel carbonate, which rms additional nickel sulphate. The reagent may be kept in suspension, in hich case the cathode is in a porous pot. Alternately pieces of the reagent may e placed in a porous pot around the anode. The electrolyte may be heated to)–80°.

AUME, CHARLES and EDWARD, Substitutes for platinum: Nature, vol. 102, p. 64,)18. Abstract by Albert R. Merz, Chem. Abstracts, vol. 12, p. 2466, December), 1918.

Platinum has been used in France since 1800. Details of its applications are ven in Guillaume's "Les applications des aciers au nickel," published in 1904. lloys of nickel high in chromium were first made in France and their properties e described in L. Dumas's "Recherches sur les aciers au nickel à haute teneur,")02. Nichrome is much used in America for electrical heating of laboratory)paratus.

ELD, R. A., Iron alloys: British patent No. 126362, January 10, 1917. Chem. bstracts, vol. 13, No. 18, p. 2193, September 20, 1919.

Iron-nickel alloys are made by alloying from about 5 to 38 per cent of nickel ith cast iron containing from about 2 to 5 per cent of carbon. An example con-

Digitized by Google

tains 2.58 per cent of carbon, 0.79 per cent of silicon, 0.04 per cent of sulphur, 0.04 per cent of phosphorus, 0.31 per cent of manganese, and 37.2 per cent of nickel. The nickel used is preferably of high quality, such as Mond nickel. One or more other metals, such as chromium, cobalt, vanadium, tungsten, titanium, aluminum, manganese, or copper, may be present.

HONDA, KÓTARÓ, A theory of invar: Tokyo Math. Phys. Soc. Proc., vol. 2, No. 9, p. 348, 1918. Abstract by F. P. Phelps, Chem. Abstracts, vol. 12, p. 2530, December 10, 1918.

In the present theory invar (35.4 per cent nickel steel) is considered as an irreversible nickel steel and its remarkable property of nonexpansibility as the result of the retarded $A_{2\text{-}3}$ transformation during cooling. Hence the invar is in an unstable condition and tends to elongate very slowly after months or years.

JONES, C. L., Alloy: French patent No. 485674, January 29, 1918. Chem. Abstracts, vol. 13, p. 1817, August 20, 1919.

An alloy is specified as of the composition nickel 67.8 per cent, copper 28 per cent, manganese 2.5 per cent, iron 1.5 per cent, and vanadium 0.2 per cent. These constituents are alloyed by heating in a furnace or crucible. The product has the luster of silver and the strength of steel, does not corrode in moist air nor when exposed to the action of other agents which commonly corrode metals, and resists the action of most acids. The alloy takes a high polish, may be molded or rolled into bars or sheets, forged, or worked up into any desired shape. It is very compact and may be made into springs, etc.

PARRAVANO, N., Theoretical and experimental investigations on metallic alloys (Firenze, Italy): Ann. chim. applic., vol. 9, pp. 1–86, 1918. Abstract by Robert S. Posmontier, Chem. Abstracts, vol. 12, p. 1164, June 10, 1918.

A monograph, based on investigations carried out by the author, alone, and with others. He takes up the following binary alloys: Tin-arsenic, antimony-arsenic, antimony-selenium, bismuth-selenium, manganese-zinc, manganese-bismuth, antimony-potassium, copper-zinc, antimony-bismuth, antimony-copper, manganese-copper, nickel-manganese, nickel-gold. He discusses the general laws of solidification of ternary alloys, and treats of the following: Nickel-manganese-copper, iron-nickel-manganese, copper-gold-silver, nickel-copper-gold, iron-manganese-copper, nickel-gold-silver, nickel-copper-silver, nickel-copper-lead, copper-zinc-lead, silver-lead-tin, copper-antimony-bismuth. Similarly with quarternary alloys, of which the following are discussed: Lead-tin-cadmium-bismuth, iron-nickel-manganese-copper, nickel-copper-gold-silver. Many diagrams of state are given and interpreted in great detail. A bibliography is appended of papers on which the monograph is based.

PERRIS, B., Projector arc lamps: Canadian patent No. 184914, June 11, 1918. Chem. Abstracts, vol. 12, p. 1951, October 10, 1918.

The negative electrode of the arc lamp has a heavy copper coating which is itself covered with a coating of nickel to prevent the beads of molten metal from collecting on the tip of the electrode and spattering the lens of the condenser, when the arc springs therefrom.

PROCTOR, C. H., Government specifications for copper and nickel plating: Metal Industry, vol. 16, p. 407, 1918.

RAND, F. R., and VAUTIN, C. T. J., Aluminum alloy: British patent No. 122870, January 7, 1918. Chem. Abstracts, vol. 13, p. 1299, June 20, 1919.

An aluminum alloy contains 85 to 97.5 per cent of aluminum and the remainder, a copper-nickel alloy, is composed of 75 to 80 per cent of copper and 20 to 25 per cent of nickel. In making the alloy a small quantity of aluminum phosphide or copper phosphide may be added as a cleansing agent.

ROBERTS, H. M., and LONGYEAR, R. D., Genesis of Sudbury nickel-copper ores as indicated by recent explorations: Canadian Min. Inst. Trans., vol. 21, pp. 80–126, 1918. Am. Inst. Min. Eng. Bull., pp. 555–584, 1918. Abstract by J. W. Bowers, Chem. Abstracts, vol. 12, p. 668, April 10, 1918.

A possible succession of events which produced the Sudbury ores is outlined as follows: A laccolithic mass of molten rock was intruded along a plane of unconformity beneath the Animikie sediments. Through some process of differentiation, the nature of which is uncertain, this mass separated and consolidated into two distinct but intergrading types, micropegmatite and norite. The sulphides were carried downward with the norite. As the norite consolidated, the sulphides remained in solution and were concentrated in association with an acid component of the magma. This segregation or "extract" made its way to the base of the norite under the influence of complex chemical and physical forces. At the very last stage in the consolidation of the norite, the sulphides were precipitated from the "extract" along the contact and, at the same time, the acid com-

Digitized by Google

ponent solidified into granite. The presence of water, sulphur, and possibly other mineralizers in the magma gave this "extract" somewhat the character of a solution, enabling it to replace the wall rock to some extent. But it was still so intimately related to the magma that it was unable to carry the sulphides any great distance into the footwall, unless also accompanied by the molten norite. It is pointed out that the dominant factor controlling the deposition of the Sudbury ores is magmatic segregation in place. Hot solutions may have been active, but only served to influence the local character and position of the ores.

SANDELL, H. K., Nickel-tungsten composition for electrical contact points: United States patent No. 1268495, June 4, 1918. Chem. Abstracts, vol. 12, p. 1762, September 10, 1918.

A cast metal composition for contact points of electrical apparatus is formed of nickel 80, tungsten 20, and graphitic carbon 2.5 to 7 parts.

SOERABAYA HANDELSBLAD (Java). Quoted in the Algemeen Handelsblad (Amsterdam), from which a translation was reprinted in Commerce Repts., p. 196, October 15, 1918.

States that in the Malili district on the island of Celebes large deposits of rich nickel ores have been found.

United States Nickel Co., Extracting nickel: British patent No. 122335, April 11, 1918. Chem. Abstracts, vol. 13, p. 1299, June 20, 1919.

Copper-nickel matte is roasted until it contains 8 to 12 per cent of sulphur, and is then reduced by gases, coke, or other means. If the matte is sufficiently low in sulphur, the roasting step is unnecessary. The reduced product is leached with sulphuric acid or hydrochloric acid or copper sulphate to dissolve the nickel and nickel sulphide without dissolving the copper. Some of the partly-roasted matte or some metallic nickel may be added to prevent solution of copper or to insure precipitation of any copper which may have been dissolved. The solution of nickel salt may be treated in any way for the extraction of nickel, for instance, by the addition of calcium oxide and the subsequent reduction of the hydroxide. Cf. British patents No. 17974, 1894, and No. 15850, 1911. Chem. Abstracts, vol. 7, p. 63.

Digitized by Google

Digitized by Google

TITANIUM.

By Frank L. Hess.

PRODUCTION.

Rutile (titanium dioxide) and ilmenite (titanium-iron oxide) were produced in 1917 by the American Rutile Co., at Roseland, Nelson County, Va., and ilmenite was produced by Buckman & Pritchard (Inc.), 4 miles south of Pablo Beach, Fla. For years the American Rutile Co. has been the only producer of rutile in the United States, and until 1916 the only company producing ilmenite, although some highly titaniferous iron ore has been produced in the Adirondacks of New York. During 1917 the production was 206 short tons of rutile concentrates carrying 93 per cent of TiO_2, valued at $32,960, and 1,339 short tons of ilmenite concentrates carrying 53–55 per cent of TiO_2, valued at about $12,677.

OCCURRENCE AND USES.

The American Rutile Co. quarries and crushes a coarse-grained rock composed of feldspar, blue quartz, and in places hypersthene, mostly altered to hornblende. The feldspar is mostly andesine, largely intergrown with orthoclase (microcline). The rock also contains a considerable quantity of apatite. Part of the rock is somewhat decayed so that it crushes easily, but other parts are fresh and hard. The rock as mined contains from 4 to 5 per cent of rutile and about the same quantity of ilmenite, so that electromagnetic separation is necessary. The rutile as separated has a pleasing reddish color. It is used in the making of electrodes for arc lamps and in less quantity for ferrotitanium, ceramic glazes, and chemicals for dyeing leather and cloth. The ilmenite from this quarry seems to be peculiarly adapted to the making of electrodes for arc lamps and gives better satisfaction than other ilmenites that have been tried.

The market for both substances is small, and the quantity of rutile produced by the American Rutile Co. is practically a measure of the total market in this country and in part of the foreign market. The market for ilmenite is likewise small, although experiments in the making of pigments with titanium dioxide (TiO_2) derived from ilmenite have long been carried on and may provide an outlet for the product.

Rutile is found near Custer, S. Dak., in an amphibolite that carries perhaps 1 per cent of rutile in very small prisms. At Magnet Cove, Ark., titanium dioxide in the form of rutile, octahedrite, and brookite is found in connection with nephelite syenite, and rutile is frequently found in considerable quantity in the stream beds of the old metamorphic rocks of the southern Appalachian region. Rutile also is

Digitized by Google

found in lenticular pegmatite, dikes of which are crushed to gneiss in Hanover and Goochland Counties, Va. All these properties have been prospected, but none have been found to be serious rivals of the deposits at Roseland, where the quantity available is very large. The ilmenite obtained near Pablo Beach, Fla., is in the form of a fine sand concentrated along high-tide line on the beautiful sloping beach at that place. Accompanying it is a small quantity of rutile, zircon, and monazite.

The only known foreign deposits of rutile that may be competitors are near Baie St. Paul, Quebec, where it is found in ilmenite with sapphirine, but these deposits apparently can not be mined profitably in competition with the Roseland deposits. Fine specimens of rutile-bearing rock have come from Sonora, Mexico, apparently from a quartz vein or pegmatite, but little is known of the occurrence. Near Adelaide, South Australia, rutile is found in what appear to be crushed pegmatite dikes. A very dark rutile is found in granitic rocks at Kragerö, in southern Norway, where it has been mined and the rutile placed on the European market for a number of years. Rutile in fair quantity is found in placers in Queensland, whence a little has been marketed, and also in Western Australia.

RECENT PATENTS.

A British patent (No. 127922) was issued December 31, 1917, to the United States Alloys Corporation for an alloy containing titanium. The notice in Chemical Abstracts, volume 13, p. 2334, October 10, 1919, is as follows:

An alloy for use in freeing molten iron or steel from slag or oxide distributed in its mass consists of iron, titanium, and silicon, the iron being in the largest proportion, and the silicon in such less proportion than the titanium that, on oxidation in contact with the iron or steel, easily fusible silico-titanates are formed. The alloy contains 15 to 25 per cent of titanium, 3 to 5 per cent of silicon, and some carbon, and is made from mixtures of rutile, titaniferous iron ore, or ilmenite, quartz, charcoal, and scrap, preferably in an electric furnace having a carbon crucible and a carbon electrode.

Other recent patents dealing with the use of titanium in alloys are noted under cobalt in this volume under the names of American Alloys Co.; Radclyffe Furness; James H. Parker and B. H. De Long; K. Shiga; and United States Alloys Corporation.

Digitized by Google

TUNGSTEN.

By Frank L. Hess.

GENERAL CONDITIONS.

The tungsten concentrates and ore mined and marketed in the United States in 1916, equivalent to 5,923 short tons of concentrates carrying 60 per cent of tungsten trioxide (WO_3), had broken all previous records for any country, and the records were again broken by the output of 1917, during which 6,144 tons, valued at $6,783,000, was produced.

The excessive prices of the early part of 1916, when a peak of $93.50 per unit was reached, and the high prices following induced a great number of men to operate known tungsten deposits that could not be worked profitably at the prices prevailing in normal times and to prospect for new deposits. It also caused an increase in the output of properties already in operation. Prices were high all through that year, though low when compared with their highest point. By 1917 operations on many of the smaller properties had ceased, but on deposits on which machinery had been installed and which had been proved to carry more tungsten-bearing rock the impetus received in 1916 carried production on at a faster rate. Practically all fields gave a lower production except the established fields of California, Colorado, and South Dakota, and these showed an increase sufficient to overcome the decrease in the other States.

PRODUCTION.

The production of tungsten ores in the United States since 1900 has been as shown in the table below; the production before 1900 was negligible.

Concentrated tungsten ores produced in the United States, 1900–1917.[a]

Year.	Quantity (short tons).	Value.	Year.	Quantity (short tons).	Value.
1900	46	$11,040	1909	1,619	$614,370
1901	179	27,720	1910	1,821	832,992
1902	184	34,040	1911	1,139	407,985
1903	292	43,639	1912	1,330	502,158
1904	740	184,000	1913	1,537	672,118
1905	803	268,676	1914	990	435,000
1906	928	348,367	1915	2,332	4,100,000
1907	1,640	890,048	1916	5,923	12,074,000
1908	671	229,955	1917	6,144	6,783,000

[a] The production of tungsten ores in this country from year to year, except in 1900, can be fairly compared in this table only since and beginning with 1906, as before that date no effort was made to reduce the ores to a common basis of concentration. For the five years 1901 to 1905, inclusive, the concentrates probably carried a little more than 60 per cent of WO_3. Since 1906 the ores have been, as far as possible, reduced to an equivalent of ore carrying 60 per cent of tungsten trioxide (WO_3), which is the ordinary commercial basis in the United States.

Digitized by Google

Tungsten ores carrying 60 per cent of tungsten trioxide (WO_3) produced in the United States in 1916 and 1917, in short tons.

State.	Ore mineral.								Total.	
	Scheelite.		Ferberite.		Wolframite.		Huebnerite.			
	1916	1917	1916	1917	1916	1917	1916	1917	1916	1917
Alaska	47	32							47	32
Arizona	6	71			144	60	68	19	218	150
California	2,129	2,779			30	[a] 2	12	2	2,171	2,781
Colorado			2,329	2,704	1		71	3	2,401	2,707
Idaho	71	1	1				29	1	101	2
Nevada	516	141					173	2	689	143
New Mexico				[b]			16		16	[b]
South Dakota					239	270			239	270
Utah	20	33							20	33
Connecticut [c]										
Missouri [c]										
Montana	5	15			10	8	6	3	21	26
Oregon										
Washington										
	2,794	3,072	2,330	2,704	424	338	375	30	5,923	6,144

[a] Unsold and not added in total.
[b] Less than 1 ton.
[c] No production in 1917.

The items of the wolframite group (ferberite, wolframite, and huebnerite) necessarily encroach upon one another. Some of the ferberite from Boulder County, Colo., probably should be classed as wolframite, but that is true of only a small part of the output; similarly some of the wolframites grade into huebnerite, and vice versa.

The production from the Boulder field is represented by the Colorado production of ferberite, which exceeded the California output in 1916 but was slightly smaller in 1917. The Atolia Mining Co.'s property at Atolia, Calif., remains the largest single tungsten mine in the world.

The statement of the production of tungsten by States only partly expresses the production by fields. Thus Colorado has two distinct tungsten fields—though the output of one is negligible—the Boulder field, northeast of the center of the State, which has had the largest known ferberite deposits, and the Silverton region, in the southwestern part of the State, where huebnerite is found with deposits of gold, silver, lead, and zinc.

Digitized by Google

The matter is not so simple in California, Nevada, and Utah. Looked at casually, California seems to have four to five nuclei of deposits or centers of production—Grass Valley, Bishop, Randsburg, and the south end of the Sierra Nevada and the Clark and New York mountains of eastern San Barnardino County. Nevada has as many, and Utah at least two small centers, one in Box Elder County, 15 miles northeast of Lucin, and the other in the Deep Creek Mountains, near Gold Hill, Tooele County. Under closer examination, it will be found that there is a family relationship between nearly all, if not all these deposits. A great batholith of granite, only partly uncovered, has apparently risen under Nevada and parts of California and Utah, and the contact-metamorphic deposits of all three States are a visible result. The vein deposits of Nevada and of Atolia, Calif., probably those of Grass Valley and of the New York and Clark mountains, Calif., and the replacement deposits of the Deep Creek Mountains, Utah, are all related phenomena, but their relations to the one great cause are not immediately apparent. The output of these three States would therefore probably be fairly treated as from one field—broad and thinly spread, with many lean and small deposits and here and there a rich vein or a large deposit.

The bulk of the production, as may be surmised from the foregoing statement, has been derived from lode deposits. A comparatively small quantity of tungsten ore was produced from placers in 1917 at the following places: On Sofia Gulch, a small tributary of Rock Creek, 10 or 12 miles northwest of Nome, Alaska, the Pioneer Mining Co. sluiced the residual débris from some small scheelite-bearing veins and obtained a few tons of concentrates. The scheelite placers in the "Spud Patch" at Atolia, Calif., furnished an equivalent of possibly 200 tons of concentrates carrying 60 per cent of WO_3. At Dragoon, Ariz., about 19 tons of huebnerite was mined, a part of which was taken from the veins. No ore is known to have been mined from placers in Boulder County, Colo., from which there was some production in 1916.

SUPPLY.

Supplies of tungsten ores in the United States, 1912–1917, in short tons.

Year.	Production.	Imports (for consumption).			Exports.[a]		Apparent consumption.[b]
		Ore.	Tungsten and ferrotungsten.	Estimated equivalent in ore carrying 60 per cent of tungsten trioxide.[c]	Tungsten and ferrotungsten.	Estimated equivalent in ore carrying 60 per cent of tungsten trioxide.	
12	1,330	824	323	1,620	.....	.....	2,950
13	1,537	449	740	2,151	.....	.....	3,688
14	990	299	218	814	.....	.....	1,804
15	2,332	1,776	8	1,942	.....	.....	4,274
16	5,923	3,973	43	4,401	287	580	9,744
17	6,144	4,876	1	5,284	1,162	2,420	9,008

No record of tungsten ore exported is at hand, although it is known that some has been shipped abroad.
Production plus imports minus estimated equivalent in ore of the exports of tungsten and ferrotungsten. The apparent consumption is at best only an approximation.
These items include the ore (considered as carrying 65 per cent of tungsten trioxide) and the tungsten in ferrotungsten (considered as equivalent to 2½ times their weight in ore carrying 60 per cent of tungsten trioxide). Chinese ore imported (195 tons) has been considered as 67½ per cent of tungsten trioxide.

Digitized by Google

Tungsten-bearing ore imported into the United States, 1917, in short tons.

Country.	January.		February.		March.		April.		May.		June.	
	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.
Japan	29	$42,909	11	$15,726	.....	.....	.....	.....	22	$30,433	.....	.....
China	.....	.....	.....	.....	.....	.....	.....	.....	35	20,866	.....	.....
Hongkong	.....	.....	.....	.....	.....	.....	.....	$150	.....	.....	.....	.....
Siam	17	14,540	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
Mexico	52	30,279	30	19,728	19	$9,739	54	8,888	78	35,095	12	$13,562
Panama	.....	.....	.....	.....	.....	.....	.....	.....	157	144,558	.....	.....
Ecuador	.....	.....	.....	.....	6	5,300	.....	.....	.....	.....	.....	.....
Peru	199	170,592	58	46,547	136	98,677	84	74,392	76	62,476	85	81,993
Bolivia	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
Chile	483	454,337	152	183,390	129	103,318	1	2,000	66	58,000	262	280,066
Argentina	9	25,155	144	149,563	.....	.....	.....	.....	.....	.....	10	8,160
British South Africa	1	1,100	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....
Portugal	.....	.....	.....	.....	11	11,154	.....	.....	18	15,340	15	14,513
	790	738,912	395	414,954	301	228,188	139	85,430	452	366,768	384	398,294

Country.	July.		August.		September.		October.		November.		December.		Total.	
	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.	Quantity.	Value.
Japan	45	$55,537	39	$42,774	84	$97,848	142	$126,612	218	$198,5[illegible]	11	$12,305	601	$622,691
China	33	22,522	45	36,120	.....	.....	50	34,417	11	8,202	21	15,141	195	136,268
Hongkong	.....	.....	.....	.....	.....	.....	33	20,844	.....	.....	.....	.....	33	20,994
Siam	.....	.....	.....	.....	11	8,583	.....	.....	.....	.....	.....	.....	28	23,123
Mexico	23	13,258	2	2,543	1	1,134	84	19,559	34	20,192	1	2,867	340	176,849
Panama	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....	2	3,084	159	147,592
Ecuador	6	2,580	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....	12	7,880
Peru	65	52,959	100	94,277	132	149,077	113	130,183	114	126,990	36	38,430	1,198	1,126,593
Bolivia	.....	.....	3	3,247	.....	.....	.....	.....	.....	.....	42	41,795	45	45,042
Chile	93	77,842	105	107,266	98	85,129	83	81,091	306	256,348	153	120,066	1,930	1,808,853
Argentina	17	14,459	.....	.....	.....	.....	28	36,536	.....	.....	9	10,920	217	244,793
British South Africa	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....	.....	1	1,100
Portugal	.....	.....	29	33,516	16	12,497	.....	.....	13	11,010	18	7,800	120	105,830
	281	239,157	323	319,748	342	354,268	483	449,242	696	621,289	293	251,358	4,879	4,467,608

PRICES.

Tungsten ores sold during the first three months of the year at about $17.50 a short-ton unit of ore carrying 60 per cent of WO_3, the price rising to $20 in April and May, to $25 in August and September, and falling to about $23 in November and December.

Ferrotungsten was somewhat more unsteady but followed in general the same sort of a curve. Tungsten contained in ferrotungsten ranged during the first half of the year between $2.10 and $2.30 a pound and in the second half of the year between $2.70 and $2.30, at which the year closed.

The prices are shown on the accompanying figure.

Digitized by Google

MINING BY STATES.

ALASKA.[1]

The production of tungsten in Alaska in 1917 consisted of scheelite concentrates lued at about $45,000. The Fairbanks district and Seward Peninsula were the ncipal producers of tungsten in Alaska in 1917. In the Fairbanks district two ngsten mines are in course of development. At one of these mines one unit of a ton mill is in operation and late in the summer was turning out several hundred unds of scheelite concentrates daily. At the other mine a similar mill was in rse of construction. Underground work was in progress at both mines. The esent indications give promise of a large increase in the production of tungsten in e Fairbanks district. In Seward Peninsula tungsten was produced principally by icing the residual scheelite-bearing lode material in Sophie Gulch. Smaller quanies were recovered as the result of placer mining at other localities.

As a result of the examination of placer concentrates by the United States Geological rvey, scheelite was determined in a number of concentrates from the vicinity of me and from Bonanza Creek at the base of Seward Peninsula. These localities are t new but are nevertheless of importance, as there appears to be a possibility of the oduction of scheelite as a valuable by-product of placer gold mining. A new locality Jack Wade Creek, in the Fortymile district, was found for this mineral.



FIGURE 18.—Graph showing prices for tungsten ore carrying 60 per cent of WO_3 and for tungsten in ferrotungsten carrying 72 to 78 per cent of tungsten. Adapted from graph of Foote Mineral Co.

The deposits near Nome and Fairbanks were described by J. B. Hertie in a report published in 1917 in the Geological Survey's Bulletin 662, the Nome deposits on pages 436 and 437 and the Fairbanks deposits on pages 418 to 424.

ARIZONA.

Most of those who had flocked to the tungsten camps in Arizona in 1916 left with the lowering of prices toward the end of the year and most of the camps were comparatively deserted in 1917. In a few, however, mining continued.

At Dragoon, in the northwestern quarter of Cochise County, dry placering was carried on, but less extensively than in 1916. This locality has been noted in a previous paragraph. Two small mills, one owned by the Primos Chemical Co. and one known as the Banks mill were in operation part of the year 1917.

[1] Martin, G. C., The Alaskan mining industry in 1917: U. S. Geol. Survey Bull. 692, pp. 20–21, 1919.

Digitized by Google

About 6 miles northwest of Dragoon station and 14 miles northeast of Benson J. J. Wien did some work on a scheelite vein along a fault contact between granite and gneiss.

In the Huachuca Mountains, a short range trending northwestward across the southwest corner of Cochise County, considerable prospecting was done for scheelite. The field is reached from Hereford, a station on the El Paso & Southwestern Railroad about 25 miles distant. Most of the prospects were on the northeast side of the range, but two were on the southwest side.

E. S. Larsen, of the United States Geological Survey, found that granite forms the lower slopes on the east side of the range and is overlain by a great thickness of Paleozoic and later sediments that dip at considerable angles to the west. At the base of the section is about 300 feet of quartzite, and this is overlain by a great thickness of limestones, which are in turn overlain on the west side of the range by a thick series of red sandstones and shales, including some volcanic rocks, probably in part intrusive. Scheelite-bearing veins are found in all the rocks. The rocks are probably much the same as those at Bisbee[1] on the east and at Duquesne[2] on the west.

Beginning at the southeast end of the mountains, Ben Morgan, Lou Kelly, and John Kelley did some work on veins in the granite. A little farther north O. T. Smith & Son worked a vein near the top of the quartzite, which is below the limestone, and erected a mill. In the limestone the Huachuca Mining & Milling Co. did some work near the crest of the range at the head of Browns Canyon. Also near the crest of the range "high-graders" gouged some scheelite from the outcrops of veins in the limestone on the Fort Huachuca Military Reservation, lying along the northeast side of the mountains near the northwest end, where no title could be obtained to mining claims.

On the southwest side of the range, D. M. Peoples and, farther north, Allen & Son prospected veins in sandstone and conglomerate.

The veins of the district are numerous, and some are large, though of low grade. The output of the year was small, and the total production from the Huachucas formed a little more than one-third of the State's output.

Wolframite in quartz was found a few miles southeast of Bisbee during the year, but no production is known to have been made.

In Gila County, about 26 miles northwest of Globe and 4 miles northwest of the Horrell ranch, a number of claims were located by R. Prescott in the name of H. E. Fox on quartz veins a few inches wide, cutting a highly porphyritic flesh-colored biotite granite. The veins carry wolframite with a very little molybdenite, and in one place bismuth. Only a little work had been done on the veins.

On the northwest side of Pinto Creek, 6 miles above the Apache Trail, Wade Sotel, Carter Norris, H. E. Kemp, and others have a group of claims on irregular faulted wolframite-bearing quartz veins and one fine-grained pegmatite. Considerable prospecting was done on the veins, which, in the principal workings near the creek, were difficult to follow on account of the faulting.

[1] Ransome, F. L., The geology and ore deposits of the Bisbee quadrangle, Ariz.: U. S. Geol. Survey Prof. Paper 21, 1904.

[2] Schrader, F. C., Mineral deposits of the Santa Rita and Patagonia mountains, Ariz.: U. S. Geol. Survey Bull. 582, 1915.

Digitized by Google

In Mohave County the Yucca Tungsten Co., a subsidiary of the York Metal & Alloys Co., of York, Pa., developed a mine at the head of Tungsten Canyon in the west side of the Hualpai Mountains about 17 miles northeast of Yucca, a station on the Santa Fe Railway. The deposit is a compound vein of gray quartz interleaved with fissile gray mica schist standing at an angle ranging from 68° to vertical and striking nearly northeast. The schist is a large remnant possibly 10 miles long and a quarter of a mile wide included in granite. At one place eight quartz veins 2 to 3 inches thick were intercalated through 5 feet of schist, and at another two veins 8 inches thick were separated by 10 feet of schist. The vein cuts the hill, which is only a few hundred feet through, and can be followed for nearly a mile on the other side.

Down the canyon, or southwest from the workings, the vein is said to have been found at intervals for 9,000 feet. Drifts were driven into the hill at three levels, and a gravity tram carried the ore to the crusher, whence another gravity tram conveyed the crushed ore to the mill, which was completed during the year. The water supply is scanty, and is pumped from a well in the canyon a mile or more below the mill. The ore carries, besides wolframite, some gray and white scheelite, a little cuprotungstite, and about as much chalcopyrite as wolframite. All the concentrates were shipped to the parent company at York, Pa.

More than a mile down the canyon the Edmaier Mining Co. did some unprofitable work on what is apparently an extension of the same vein.

In Pima County Bramwell & Sullivan located scheelite-bearing quartz veins in the Meyers mining district, 18 miles southeast of Ajo. The veins also carry gold, silver, vanadinite, and wulfenite. The country rock is biotite granite.

On the claims of the Tungsten Mines Co., on the west side of the Aquarius Range, 70 or 80 miles south and east of Kingman, some work was done, but the output was small. The claims were originally owned by Williams & Pittman and have been productive in a small way for years.

In Pinal County some prospecting was done in the Old Hat or Oracle district by Tibbals & Neale. The mine, formerly operated by the Cody-Dyer Mining & Milling Co., was not worked during the year. It is near the faulted end of a quartz vein that has filled cracks in and also replaced limestone, the quartz reaching a thickness of 20 feet or more. Here and there bunches of creamy or yellow scheelite are found in the quartz, which has been prospected for half a mile or more, but no rich pockets have been found. The Cody-Dyer Mining & Milling Co. several years before erected a mill, which must have been of rather low efficiency.

In Yavapai County, in the Eureka district, in what would be, if surveyed, T. 15 N., R. 7 W., 45 miles west of Prescott, Connors, Lawler & Wood mined some very pure hand-picked wolframite from quartz veins, in which a little bismuth is found.

In the Humbug district, south of Prescott, near the Maricopa County line, J. D. Gardner took out a small quantity of wolframite.

In the Tip Top or Bradshaw Mountains district a little wolframite was recovered from the old Tip Top silver mine and from some other veins in the district.

Digitized by Google

CALIFORNIA.

Tungsten mining and prospecting in California was nearly all for scheelite, but was done under widely varying conditions, and workings were scattered from Grass Valley, in Nevada County, to Aguanga, on the southern edge of Riverside County—a distance of more than 450 miles in a direct line south by east—and to the New York Mountains, in eastern San Bernardino County—almost equally distant in a south-southeast line.

Beginning at the north, scheelite was mined by the Union Hill Mining Co. at Grass Valley, where the scheelite is found in veins worked for gold. A total of 22 dry tons carrying 28,392 pounds of WO_3 was produced. The concentrate carried a large quantity of pyrite, and to separate it the ore was slowly roasted, making a porous iron oxide that was easily separated on Wilfley tables.

In Mariposa County a little wolframite was taken from quartz veins near the top of the Sierra Nevada. The country is so rough, however, and transportation is so difficult that it seems doubtful whether the veins can be made to give a profit at ordinary prices.

In Inyo County a large amount of work was done on the contact-metamorphic deposits. The Standard Tungsten Co., the Round Valley Tungsten Co., and the Tungsten Mines Co. all operated during the year. Each had its own mill. The rock contains garnet, quartz, epidote, calcite, hornblende, diopside, and mica and a little sphalerite and pyrite, besides scheelite. The garnet contains enough iron to be comparatively easily lifted out by an electromagnet, and a much cleaner separation and a larger saving could probably have been made had electromagnetic separators been installed.

The operations at the Round Valley Tungsten Co.'s property are thus described by the superintendent, H. C. Miller:

> The mine has been opened and developed through two main adits, 50 feet apart vertically. The lower adit or tunnel is 250 feet vertically below the uppermost cropping and is the main haulage way through which all ore is trammed to the mill. A shaft is being sunk and new levels started at 50-foot intervals. Mining is being carried on by the shrinkage system in the stopes and the "glory hole" method on the surface.
>
> The main ore body is 90 feet long and ranges in thickness from 25 to 35 feet and averaged 1 per cent of tungsten trioxide. At the north end of the ore body the scheelite is inclosed in a gangue consisting mainly of garnet and epidote. The scheelite crystals are very small and are well scattered throughout the ore. A green copper stain is prominent in this part of the ore body. Near the surface the copper stain becomes more prominent and furnishes an excellent guide in following the ore. The ore body trends northeast and southwest and stands at an angle of 45°, following the stratification of the inclosing rocks. The footwall of this particular ore body is a fine-grained dense calc-hornfels. The hanging wall is a much-altered sediment, carrying a small percentage of tungsten but not enough to pay for its extraction.
>
> Toward the south end of the ore body the ore gradually becomes darker in color, the characteristic green copper stain almost completely disappears, and dark mica is much in evidence. Here the scheelite occurs in roughly banded rock composed chiefly of dark mica (phlogopite). Epidote, apatite, and quartz are also present. Small ribs of dense fine-grained barren calc-hornfels are found throughout the ore body.
>
> From the mine the ore is trammed to the mill in 1-ton cars and dumped over a grizzly to the rock crusher below. Here it is crushed to 2 inches and stored in the mill ore bin. Entering the mill the ore passes over a Colorado shaker screen equipped with a 7-mesh screen, the oversize going to a No. 53 Marcy mill, where it is crushed to pass through $\frac{5}{16}$-inch openings in the mill grates. A 3-inch sand pump elevates the discharge from the Marcy mill back over the screen, the oversize returning for further crushing. The minus 7-mesh ore all of which has had to pass through the

Digitized by Google

shaker screen goes to a 4 by 4 foot cone, the overflow of which enters an 8 by 8 foot Callow cone, where it is thickened in the ratio of 14 to 1. The spigot discharge from the Callow cone goes to an Overstrom slime table, while the overflow runs direct to the tailings launder. This slime table does exceptionally good work. The spigot discharge from the small cone goes to a Deister-Overstrom rougher, the concentrate going direct to the concentrate bin, the tails being re-treated on two Overstrom universal tables. The middlings product from these two tables being re-treated on one of them. The entire process of scheelite concentration is comparatively simple, the prevention of slimes being the most important factor. The concentrates are dried, sacked, and shipped.

Electric power is furnished by the Southern Sierras Power Co., from its plants on Bishop Creek, 5 miles distant. It is brought to the mill over a 33,000-volt transmission line and there stepped down to 440 volts, the voltage of the mill motors. For a lighting circuit it is again stepped down to 110 volts.

A little ore was also produced by Frank Harris, of Keeler. Altogether the Bishop district marketed 845,381 pounds of scheelite carrying 536,968 pounds of WO_3 and valued at $503,620.

The large contact-metamorphic deposit on Pine Creek, 30 miles northwest of Bishop, was sold by Vaughan, Beauregard & Sproule to the Pine Creek Tungsten Co., but little work was done.

In the Atolia district the Atolia Mining Co. continued to be the largest operator. The Randsburg Mining Co. and others worked numerous smaller veins, and a considerable number of men worked in the Spud Patch—the scheelite-bearing placer ground southeast of the Atolia Mining Co.'s mill. A little work was done also on the Sunset claims on the west side of the Rand Mountains, 6 or 7 miles west of Atolia. Several companies sunk shafts and drove drifts in the hope of striking veins parallel to those of the Atolia Mining Co., but with little success.

The Atolia Mining Co. sold during the year for $2,155,505 an equivalent of 1,938 tons of scheelite concentrates carrying 60 per cent of WO_3.

Shafts were sunk on the Rainstorm and Acaley claims and a 2-compartment inclined shaft was sunk on the Union No. 1 vein, over which a steel head frame was erected. The shaft was 725 feet deep and cost $29,342, or $40.47 a foot. Change houses were erected at mine and mill. A boardinghouse, a reading room at Union No. 1 mine, a staff house, and many miner's cabins were also erected.

During the year 23,053 tons of ore was mined at a cost of $6.61 a ton. From this ore 1,140 tons of waste was sorted and the remaining 21,913 tons carried 6.187 per cent of WO_3. Besides the ore that went to the mill 103.6 tons of high-grade ore averaging 63 per cent of WO_3, and containing 6,526 units was mined and sacked in the mine. Milling costs were $6.041 a ton, and the extraction was 78.892 per cent, the tailings carrying 1.306 per cent of WO_3. The mill concentrates amounted to 1,843.6 tons carrying 60.117 per cent of WO_3, or 106,968 units.

The company had trouble with phosphorus and sulphur in the ore and a treatment plant was erected in order to remove the phosphorus. It is understood that the phosphate is dissolved by hydrochloric acid. The phosphorus is thought to come from apatite in the country rock. The sulphur comes from pyrite, most of which is from the country rock alongside the vein, into which it was introduced from the vein-depositing solutions. A roasting plant to get rid of the sulphur was also erected and put into operation.

Digitized by Google

Of the concentrates 737.6 tons were treated for phosphorus at a cost of $18,389, or $24.93 a ton, and 259.3 tons were roasted at a cost of $1,862, or $7.16 a ton. Both treatments are included in the milling costs. The gangue of the ore is quartz and calcite, so that in the acid treatment there is a large loss in weight owing to the formation of soluble calcium chloride. In the treatment of the 737.6 tons there was a loss of 65.9 tons and a consequent rise in grade from from 46.25 per cent of WO_3 to 50.7 per cent.

During the year 60 cars of concentrates carrying 60 per cent of WO_3, 5 cars of 30 per cent, and 1 car of 50 per cent were shipped—a total of 1,957.6 tons carrying 116,306.6 units, sold for $2,155,505. The average cost per unit, including all expenses for the year, was $5.05, and the profit for the year was $1,565,573.

The richest shoot of ore ever found by the company was worked in 1916 and 1917. From it a very fine specimen of scheelite ore weighing a ton or more was extracted and generously sent to the United States National Museum in order that it might be preserved for the benefit of those who could not see the ore in place.

Dividends paid by the Atolia Mining Co., 1907–1917.

1907	$7,500	1912	$70,000	1917	$1,300,000
1908		1913	77,000		
1909	40,000	1914			4,564,500
1910	135,000	1915	180,000		
1911	50,000	1916	2,705,000		

There can be little doubt that the Atolia Mining Co.'s property at Atolia is the best tungsten mine so far developed.

The placers of the Spud Patch could not be operated profitably after the price fell much below $20 a unit, so that by the end of the year they were deserted.

The Red Dog mill at Johannesburg, operated by A. F. Hazeltine, representing H. L. Hollis, of Chicago, also ceased operations during the year. It had bought many small lots of ore.

North of Atolia, in the Greenhorn Mountains, a western ridge near the south end of the Sierra Nevada, Charles Guzman and others operated a small mill on Cedar Creek on ore taken from small contact-metamorphic deposits in the vicinity. Prospecting was done on other contact-metamorphic deposits at Weldon, where a small mill had been erected by the Kelso Mining Co. Dietrich & Bemenderfer had a small mill at Lorraine, erected some years before on a gold-scheelite vein. The King Tungsten Co. erected a small mill at Bodfish to operate on ore from a vein.

Some prospecting was done by the United Copper-Tungsten Mines on contact-metamorphic scheelite deposits carrying some bismuth in the Morongo district, 45 miles southeast of Victorville. The deposits as exposed give little promise of large ore bodies. Bert Simmons and associates prospected contact-metamorphic deposits at the north edge of San Diego County, near Aguanga.

Small mining operations for huebnerite were carried on in the New York Mountains, in eastern San Bernardino County, and for wolframite in the Clark Mountains, a short distance to the north.

Digitized by Google

COLORADO.

Operations in tungsten mining and milling in Colorado were confined almost wholly to the Boulder field. As in other fields, a considerable part of the impetus received in 1916 was carried forward into 1917 by the larger companies, though the persons and firms of small capital were mostly compelled to stop mining with the lowering of prices.

The same large companies previously operating in the field continued in 1917, with the Wolf Tongue Mining Co., the leading producer. Its properties lay on the mesa north and east of Nederland. It continued its broad policy of cooperation with lessees in the development of prospects, paying a part of the expense for sinking shafts and other work, furnishing electrical machinery and compressed air from a central plant.

The Primos Chemical Co. itself and through lessees operated on a large number of deposits north and northwest of Nederland and at Sugar Loaf, milling the ore at Lakewood. It also operated during a part of the year the Copeland claim, on South Boulder Creek, about 10 miles southwest across the mountains from Boulder, but only 1½ miles northwest of Crescent, on the Moffat Railroad. A mill was erected in 1916, but the ferberite occurs in such exceedingly fine grains (part less than one five-hundredth of an inch in diameter) and the "hornrock" (fine-grained quartz) in which it occurs is so hard and tough that it can be profitably worked only at very high prices.

The Vasco Mining Co. in part worked its property (a part of the Rogers tract) at Tungsten, in the valley of Middle Boulder Creek, 1½ miles east of Boulder, and in part operated through lessees who sold all the ore mined to the company, on much the same plan as the Wolf Tongue Mining Co. From one vein a piece of ore weighing more than a ton, probably the largest piece of ferberite ore ever mined, was taken by Messrs. Stevens & Holland and by them and the company was sent to the United States National Museum for preservation, where it forms a remarkable exhibit. The company operated a mill at Tungsten and another at Boulder.

A lot of ore from the No. 10 mine of the company showed the following results from analysis: WO_3, 48.4 per cent; Fe, 27.05 per cent; P, 0.042 per cent. The lot was run through an electromagnetic separator and produced 83⅓ per cent of concentrate carrying WO_3, 55.1 per cent; Fe, 21.2 per cent; P, 0.036 per cent. The part picked out by the electromagnet (16⅔ per cent) carried WO_3, 30.10 per cent; Fe, 55.2 per cent; P, 0.101 per cent.

The mines of the Rogers tract probably in general show an excess of iron in the ore, as do also some between Nederland and Beaver Creek. The iron seems to be present as specular hematite intergrown with the ferberite, and the phosphorus mineral (hamlinite?) appears to be more closely associated with the hematite than with the ferberite.

The Boulder County Tungsten Production Co. also operated a mill at Tungsten, both on ores mined on its property and on purchased ore.

Lower down Boulder Creek several properties were operated at Ferberite. On the Red Signe claim of the Tungsten Metals Corpora-

Digitized by Google

tion a vein carries both rich telluride of gold and ferberite. The two minerals evidently are not of the same age, being distinctly separated in specimens, but the mine could not be entered and the relations could not be studied. A mill was operated on the claim.

At Boulder Falls the Luckie 2 Mining Co. operated on the west side of the falls and the Mojave Colorado Mining Co. on the east side. The Luckie 2 Mining Co. operated in close cooperation with the Tungsten Products Co. at Boulder and had a mill in Boulder. The Lookout Mining Co. was operating up the hill above the Luckie 2 mine. The Mojave Colorado Mining Co. had a mill on its property.

On the north slope of the hill between Boulder Creek and North Boulder Creek a vein reaching 3 feet in thickness was mined on the Dorothy claim, near the head of Millionaire Gulch, by the Tungsten Metals Corporation, and lower down the gulch a thicker body of ore was mined on the Katie claim.

About 1½ miles south of Nederland, on the summit between Nederland and Beaver Creek, the Long Chance Mining Co. found a good body of ore at 120 feet in depth after the mine had been considered nearly worthless. The company operated a small mill on Beaver Creek.

At Rollinsville the Rare Metals Mining Co. operated a mill on ores obtained from the Nuggett and other claims mined by the company and on ore purchased from other operators. This company did considerable prospecting on Michigan Hill, in Gilpin County (T. 2 S., R. 73 W.), on a vein 12 feet wide that in places carried 2.5 per cent of WO_3 but would not return a profit on the whole.

A number of veins were prospected in the northern part of Gilpin County at the old camp of Hughesville or Hard Money, 1½ miles north of Black Hawk, at Apex, and at one or two other points, but no ore of consequence was developed.

One mile northeast of Sunshine, on Lee Hill, a point overlooking the Great Plains, small veins were prospected by the Denver-Boulder Tungsten Production & Development Co. A shaft was sunk (40 feet deep when visited in March, 1917), but little ore was shown. The veins were remarkable in that many beautiful little glassy crystals of scheelite measuring as much as $\frac{3}{16}$ of an inch in thickness have formed with the ferberite. Some other lean veins were prospected nearer Sunshine.

Although the production of the Boulder field exceeded that of California in 1916, California's was slightly larger in 1917, the Boulder field producing an equivalent of 2,707 tons of concentrates carrying 60 per cent of WO_3 against 2,781 tons from California.

The production of the Boulder field from 1900 to 1917, as nearly as can be ascertained, is shown on page 943. Perhaps it should be explained that as used here "Boulder field" means all the tungsten-bearing territory that lies in a comparatively compact area between North Boulder and Boulder creeks but extending southward into Gilpin County and northward to Lee Hill.

Digitized by Google

Tungsten ore produced in Colorado, 1900–1917.

Year.	Quantity (short tons).	Value.	Percentage of United States' production.	Percentage of world's production.
1900	46	$11,040	100	(a)
1901	b 179	27,720	(b)	(a)
1902	b 184	34,040	(b)	(a)
1903	b 292	43,639	(b)	(a)
1904	b 740	184,000	(b)	(a)
1905	b 803	268,676	(b)	19.9
1906	565	221,627	60.9	12.9
1907	1,146	573,643	69.9	18.7
1908	584	204,465	87.0	14.2
1909	993	391,160	61.3	17.2
1910	1,221	535,567	67.1	16.3
1911	730	234,513	64.1	9.7
1912	812	297,533	61.1	8.4
1913	953	428,760	62.0	10.6
1914	467	182,013	47.2	5.7
1915	963	2,311,200	41.3	8.1
1916	2,401	4,666,301	40.5	10.3
1917	2,707	2,994,000	44.1	9.6

a Figures for the world's production of tungsten ores in the years 1900 to 1904 are unavailable.
b The figures given are for the production of the United States, but it was mostly from the Boulder field. Prior to 1906, except in 1900, no attempt was made to reduce ores to a common percentage, so that the figures before that year represent only ores shipped.

During the year the Black Metal Reduction Co. made H_2WO_3 and WO_3 from low grade and other ores and the Tungsten Products Co. made tungsten and ferrotungsten at Boulder.

IDAHO.

A little mining was done on the Ima Mining & Milling Co.'s property on Patterson Creek, Lemhi County, Idaho, but the output was small. A few hundred pounds of scheelite was mined near Murray.

MONTANA.

Scheelite was produced from the gold and scheelite bearing quartz vein of the Jardine Gold Mining & Milling Co. at Jardine, Mont., and a very small quantity from Crevice, 5 miles southeast. A little scheelite was produced by the Rose Consolidated Mining Co. at Libby, and a little wolframite by the National Silver & Tungsten Co. a few miles northwest of Anaconda. The entire production amounted to 16.3 tons of concentrates carrying 60 per cent of WO_3.

NEVADA.

There was a lull in tungsten mining in Nevada in 1917. Only a little was done in the eastern part of the State, and large operators closed down at other points. In the second half of the year Copley, McFadden & Baker shipped some contact-metamorphic ore from Mill City to the mill of the Humboldt County Mining & Milling Co. at Toulon for treatment and gave an option on their claims to W. J. Loring, who also shipped several cars of ore to the same mill for treatment. The Mill City Tungsten Mining Co., the Nevada Humboldt Tungsten Mines Co., and Forg & Stank shipped similar ore from

Digitized by Google

adjoining claims; Thomas de Armond shipped some similar ore from Wrights Canyon; and E. J. Mackedon, Edward Henning, and Lewis Savage took out some ore under lease from the property of the Humboldt County Tungsten Mining & Milling Co., which had ceased operation in 1916, its mining having apparently been undertaken without a thorough understanding of the geology of contact-metamorphic ore deposits. A few tons of concentrates were also produced by the Silver Dyke Mining Co.

The entire production of the State amounted to an equivalent of 143 tons of concentrates carrying 60 per cent of WO_3, much the larger part of which was from the contact-metamorphic deposits

SOUTH DAKOTA.

In South Dakota the Homestake Mining & Milling Co. mined wolframite from replacement deposits in dolomite on claims adjoining its great gold mine; a little wolframite was also produced from Two Bit Gulch, near Deadwood; and a very little wolframite was mined from quartz veins in the southern part of the Black Hills, near Hill City.

UTAH.

Scheelite was mined in Utah from contact-metamorphic deposits at the south end of the Grouse Creek Mountains, 15 miles northeast of Lucin, and from replacement deposits in monzonite in the Deep Creek Mountains, near Gold Hill, Tooele County.

On Trout Creek, 20 miles south of Gold Hill, operations were begun on thin scheelite-bearing veins in mica schist. A mill is said to have been built.

Tungsten sulphide, a long sought mineral, was found in the Little Emma mine, near Alta, during the year. A piece was sent to the United States Geological Survey, where it was analyzed by R. C. Wells and described under the name of tungstenite by him and B. S. Butler.[1] The mineral looks very much like finely divided molybdenite. Not a great quantity was found. The mine closed soon afterward, probably before thorough examination was made.

The tungsten concentrates sold in Utah during 1917 amounted to an equivalent of 33.2 tons carrying 60 per cent of WO_3.

OTHER STATES.

In New Mexico W. C. Paterson produced a little ferberite from thin veins on Willow Creek, near Elizabethtown, Colfax County. In New Hampshire, at North Groton, a little wolframite was saved as a by-product in mining a pegmatite dike for mica. A little ore was also mined in Oregon and Washington.

TUNGSTEN MILLS OF THE UNITED STATES.

The great activity in tungsten mining in 1916 and 1917 is shown by the number of mills in existence in 1917. The following list is probably not wholly complete, and many of the mills are small.

[1] Wells, R. C., and Butler, B. S., Tungstenite, a new mineral: Washington Acad. Sci. Jour., vol. 7, pp. 596–599, Dec. 4, 1917.

Digitized by Google

ARIZONA.

1. Cody-Dyer Mining & Milling Co., Campo Bonita, near Oracle. Not operating.
2. International Tungsten Co., Tucson. Mill at Arivaca. Not operating.
3. Primos Chemical Co., Boulder, Colo. Mill at Dragoon.
4. H. L. Hollis, Chicago, Ill. Mill at Dragoon.
5. Banks mill, Dragoon.
6. Tip Top-Heath Mining & Milling Co., Prescott. Mill at Tip Top. Not operating.
7. Tungsten Mines Co., Aquarius Mountains, 80 miles southeast of Kingman.
8. Yucca Tungsten Mining Co., Yucca. Subsidiary of York Metal & Alloys Co., York, Pa. Mill 17 miles northeast of Yucca.

CALIFORNIA.

9. Atolia Mining Co., Humboldt Bank Building, San Francisco. Mill at Atolia.
10. Charles Guzman, Glenville. Mill on the west side of Greenhorn Mountains.
11. Kelso Mining Co., Weldon.
12. Dietrich & Bemenderfer, Lorraine.
13. King Tungsten Co., Bodfish.
14. Mojave Tungsten Co., 74 Broadway, New York, N. Y. New York Mountains, 20 miles north of Nipton. Not operating.
15. Red Dog Mill, Johannesburg. A custom mill.
16. Round Valley Tungsten Co., Bishop.
17. Standard Tungsten Co., Bishop.
18. Tungsten Mines Co., Bishop.
19. Union Hill Mining Co., Crocker Building, San Francisco. Mill at Grass Valley.

COLORADO.

20. Black Metal Reduction Co., Boulder. Reduced ores bought from other companies.
21. Boulder County Tungsten Production Co., Boulder. Mill at Tungsten.
22. Black Prince Mill, Ferberite.
23. Black Swan Mill, Salina.
24. Colorado Metals Co., Silverton.
25. Colorado Tungsten Mines Co., Dr. W. M. Long, president, Boulder. Mill in Carrie Nation Park.
26. Degge & Clarke, Boulder. Mill on Boulder Creek.
27. Dora Consolidated Mining Co., Silverton.
28. Guy Duncan, Ferberite.
29. Long Chance Mining Co. Mill on Beaver Creek near Nederland. Office, A. C. Foster Building, Denver.
30. Luckie 2 Tungsten Co., Boulder. Mill in Boulder.
31. Mojave Tungsten Co., 74 Broadway, New York, N. Y. Mill near Boulder Falls, Boulder.

32 and 33. Primos Chemical Co., Boulder. Mills at Lakewood and Crescent.

34. Rare Metals Ore Co., Rollinsville.
35. Rattle, W. H., Commercial Bank Building, Cleveland, Ohio. Mill at Silverton.
36. Tungsten Metals Corporation, Boulder. Owners of the Red Signe mill at Ferberite.
37. Tungsten Products Co., Boulder.

38 and 39. Vasco Mining Co., Boulder. Mills at Tungsten and Boulder.

40. Wolf Tongue Mining Co., Boulder. Mill at Nederland.
41. Wood, Henry E., 1734 Arapahoe Street, Denver. Custom work only.

IDAHO.

42. Vivian Green, 45 West Thirty-fourth Street, New York, N. Y. Mill at Murray.
43. Ima Mining & Milling Co., Patterson.

MISSOURI.

44. Madison Mining Corporation, Silver Mine.

MONTANA.

45. Jardine Gold Mining & Milling Co., Silver Bow Building, Butte. Mill at Jardine.
46. National Tungsten & Silver Co., of Boston., W. J. Hunter, manager, 202 East Park Avenue, Anaconda. Reported to be building a mill.

Digitized by Google

NEVADA.

47. Humboldt County Mining & Milling Co. (H. M. Byllesby & Co.), Chicago, Ill. Mill at Toulon, 14 miles southwest of Lovelock.
48. George Doyle, Ely. Mill at Sacramento Pass. Idle.
49. Nevada Scheelite Co., care of Col. Duncan McVichie, Walker Building, Salt Lake City, Utah. Mill on Willard Creek near Osceola, Nev. Idle.
50. St. Anthony Mines Co., subsidiary of the Atolia Mining Co., Humboldt Bank Building, San Francisco, Calif. Mill at Fanning, Nev., 18 miles southwest of Lovelock. Idle.
51. Salt Lake-Tungstonia Mines Co., Tungstonia.
52. Tilford Bros., Osceola. Mill on Willard Creek.
53. J. D. Tilford, jr., 20 miles southwest of Baker. Mill on Snake Creek, 20 miles southwest of Baker.
54. Silver Dyke Mining Co. (Atkins, Kroll & Co., San Francisco, Calif.)., Mina, Nev. Mill dismantled during the year.
55. Tungstonia Mines (Inc.), Tungstonia.
56. United States Tungsten Co., Tungsten, 45 miles east of Ely. Dismantled.
57. Utah & Nevada Mining & Milling Co., Parker. Mill partly built.

SOUTH DAKOTA.

58. American Tungsten Mining Co., Hill City. Not operating.
59. Hill City Tungsten Production Co., Hill City. Not operating.
60. Homestake Mining Co., Lead.
61. Wasp No. 2 Mining Co., Flatiron. Idle.

UTAH.

62. Frank Edison, Lucin.
63. Trout Creek Mining & Milling Co., Trout Creek.

WASHINGTON.

64. Bilrowe Alloys Co., Tacoma. Have milled ores bought at Fairbanks, Alaska.
65. Deer Park Mining Co., Deer Park.
66. Herbert Curtis, Loomis. Mill 35 miles northwest of Loomis.
67. C. S. Cullen, Ocala, Fla. Mill at Deer Trail, Stevens Co. Not operating.

The processes of concentration of tungsten ores as followed in the Boulder field were described in 1917 by S. Fischer, jr., in Metallurgical and Chemical Engineering, vol. 16, pages 559–565, and vol. 17, pages 73–78. An addition to his article is made on page 207 of vol. 17, as follows:

The step generally considered most important at all mills is the prevention of sliming at the start of milling operations. While this trend was felt early in this year, it at present amounts practically to a mania among the mill men, and stamps and sliming mills are being rapidly replaced by nonsliming rolls. The saving of the maximum amount of the values before fine grinding is now one of the constant endeavors of the operators of the Boulder district.

At present several mills are contemplating a separate treatment of all middlings. The middlings are collected in bins and when a sufficient quantity of this material has accumulated it will be treated in a distinct department. This is a very wise move. Previous practice has been to return these middlings to the head of the mill and let them pass through a second time, which, as is readily seen, is a useless waste of power and capacity.

The Vasco mill has materially cut down the feed to the rag plant by a concentration on Deister tables. These tables give a 60 per cent concentrate, which is shipped directly. The management has not yet decided what to do with the middlings, but in all probability they will be collected and treated in a separate unit. Only the tailings from the Deisters go to the rag plant, enabling the company to cut down its rag plant area.

An entirely new method is used by the Tungsten Products Co. This company treats custom ores, jig concentrates, table concentrates, or any other material they can purchase. The material is first very carefully graded by screening on 20, 40, 60, 80, and +150 mesh sieves of the impact type. All sized material is then treated by a 3-magnet Wetherill separator. The flux used varies somewhat, depending on the size and the nature of the product.

Digitized by Google

The material is fed to the belt by a mechanical feeder and evenly distributed by means of a rotating brush. The feed is rather thin, due principally to the small amount of available material; the plant handles only 5 tons per day. The ore then passes under the first magnet, which operates on a low amperage, and which eliminates most of the iron contained on the belt at its two poles. The amperage passing through the second magnet is about 3.5 amperes. At its leading pole an iron silicate is removed, while at the other pole some of the tungsten is caught. Most of the tungsten, however, is obtained from poles of a third magnet whose amperage is 7. The tailings drop over the end of the belt and consist mainly of silica and pyrites. Between and underneath the second and third magnets are brushes which assist in removing the small quantities of tungsten retained on the belt. The concentrates obtained from this magnetic separation are of a high grade, low in magnetic iron oxide, pyrites, and silica.

WORLD'S PRODUCTION.

The world's production of tungsten ores continued to climb in 1917. China, which produced, so far as the uncertain data on hand show, about 120 tons in 1916, probably produced 1,500 tons in 1917—a decided addition to the world's production. Burma and Bolivia made nearly equal increases in output and many other countries made small increases in their production, so that the total production was more than 21 per cent larger than in 1916, or approximately 28,300 short tons of concentrates carrying 60 per cent of tungsten trioxide (WO_3).

PUBLICATIONS.

Among the patents and literature concerning tungsten that were issued during 1916 and 1917 were the following:

BEDER, ROBERTO, Los yacimientos de los minerales de wolfram en la República Argentina: Dirección gen. de minas, geol. é hidr. Argentina Bol. 12, 31 pp., 1 map, 1916.

Gives a general description of tungsten minerals and deposits and details of the Argentine deposits, in some of which tin and tourmaline accompany wolframite. Gives analyses of wolframites, several of which carry columbium, and of scheelite. A bibliography of Argentine tungsten deposits is appended and a map shows the location of the deposits.

BÖTTGER, W., Manufacture of filiform tungsten crystals (crystalline wire for incandescent lamps) by the method of J. Pintsch Aktien-Gesellschaft: Chem. Zeitung, vol. 41, p. 10, 1917; through Soc. Chem. Industry Jour., vol. 36, p. 541, 1917. Abstract by J. H. Moore from Chem. Abstracts, vol. 11, pp. 2754–2755, Oct. 20, 1917.

Filaments prepared from a mixture of tungsten and a little thoria by extrusion and heat treatment consist of numerous crystals which are flexible in themselves, but the filaments are brittle at the interfaces of the crystals. Relatively long crystals are obtained by very intimately mixing the tungsten and thoria powders with a binding agent, extruding the paste, and passing the threads through a zone heated to 2,400°–2,600° at a rate which is less than the rate of crystallization. Unlike some of the drawn filaments, these do not recrystallize even after 1,000 hours of incandescence; they are softer in the cold than some of the drawn wire, and are fairly rigid at high temperatures.

CRAGOE, A. S., Wolfram in Cornwall: Min. Mag. (London), vol. 16, p. 259, May, 1917.

Discusses the production of tungsten ore in Cornwall and states that Cornwall and southwestern Devon could well turn out 1,200 to 1,500 tons of concentrate yearly, or five times the maximum production in 1916. Furthermore, as to at least 1,000 to 1,200 tons of this total, it would come, not as a small by-product from the tin mines, but as the sole or certainly major and most valuable product of wolfram-bearing and other tungsten-ore deposits, which might be expected to show yields of 20 to 25 or more pounds of wolfram, plus a little tin, per ton crushed.

DEBYE, P., The arrangement of atoms in tungsten: Physikal. Zeitschr., vol. 18, pp. 483–488, 1917; Chem. Soc. Jour., vol. 112, No. 11, pp. 574–575. Abstract by S. C. Lind from Chem. Abstracts, vol. 12, p. 1613, 1918.

The X-ray method for the investigation of crystal structures, described previously (Chem. Abstracts, vol. 11, p. 1786) has been applied in the investigation of samples of powdered tungsten. In spite of the fact that X-rays are very strongly

Digitized by Google

absorbed by the metal, it has been found possible to obtain interference figures, from which it is clear that tungsten crystallizes in cubic forms, and that the elementary space lattice is a cube with a centrally situated point, the length of the edge of the cube being 3.10×10^{-8} cm.

Doss, B., A new tungsten ore-deposit in Saxon Vogtland: Abstract by F. W. Smither, from Chem. Abstracts, vol. 11, p. 2182; Aug. 10, 1917; Zeitschr. prakt. Geologie vol. 23, pp. 138–149, 1915; Chem. Centralbl. vol. 1, p. 1095, 1916; cf. Chem. Abstracts, vol. 9, p. 2858.

The deposit occurs in Eich in the contact schists under clay, about 600 to 800 meters distant from the granite; with this is associated also (perhaps locally) a tourmaline-quartz vein, carrying tungsten. The vein material consists of quartz partly pneumatolytic), tourmaline (often broken and partly recemented with chalcedony, whose original gel character may throw some light on the genesis of pneumatolytic quartz), wolframite (with quartz in fine to coarse scales, the cavities occasionally showing fine crystal aggregates), psilomelane (probably of different origin, through transformation of wolframite, leaching of adjoining rocks, perhaps also pneumatolysis), molybdenite, pyrite, etc. The pneumatolytic transformation of the adjoining rock is discussed in the original. The tungsten-bearing tourmaline-quartz veins are apparently wider south of Eich. The property is owned and is being developed by the Krupps.

Engineering, Tungsten manufacturing works at Widnes: Vol. 104, pp. 432–443, 4 photo. reps., 1917.

Describes the works and, in a general way, the processes of the High Speed Alloys (Ltd.), at Widnes, England. The works can turn out 3 tons of tungsten (powder) per day.

See reference under "Mining Journal."

Griffiths, H. D., The wolfram deposits of Burma: Min. Mag. (London), vol. 17, pp. 60–66, August, 1917, sketch map of Burma.

Considers Burma the largest producer of tungsten ores and that Great Britain controls 50 per cent of the world's output. Intimates a desire for a prohibitive export tax on tungsten ores in order to give Great Britain control of the world's market, as with tin.

Says wages are 2s. 4d. and wants them reduced by the Government. Says the Chinese are the only reliable miners and wishes drastic laws creating conditions amounting practically to slavery for a given period. Complains much of the high cost of mining. (P. 63) Most lodes carry besides wolframite, a little cassiterite and some carry bismuth and molybdenite. Two venis below oxidized zone (depth not given) showed a small increase in wolframite, very little chalcopyrite, pyrite, bismuthine, cassiterite, and molybdenite. (P. 64) A number of lodes mined to a depth of more than 150 feet gave 34,000 long tons of ore yielding 42 per cent of concentrates. The dumps contained 11 per cent of concentrates and were afterwards worked at a profit. The tailings (from the 11 per cent dump?) assayed 7 to 8 per cent. (The first saving was 79.2 per cent and with the addition of that saved by the second milling 85.9 per cent, but he probably means 67.50 per cent of concentrates saved, reducing the saving to 53.5 per cent and 58.3 per cent, respectively. The per cent of WO_3 in the ore was apparently 2.6.) One thousand tons of quartz from five lodes gave 50.4 per cent of wolframite [concentrates?]. (Apparently 34.3 pounds of WO_3, or 1.53 per cent.)

Deplores lack of deep mining and development.

No stream gravels in lower Burma carry wolframite, but it is in residual placers. It may be dissolved or ground up before reaching streams. The residual placers may be worked profitably if water is plentiful. They have produced one-third of the output. Alluvial deposits will yield a large output for a long time to come. (P. 61) "The price of production will assuredly increase enormously when the wolfram has to be looked for in depth instead of being mostly quarried from the surface.

"It is thought that if the export of tungsten ores from British colonies or dependencies to any country except England were prohibited a good hold would be secured on probably half the world's output, and the United Kingdom would be assured of its requirements. The chief consumers of tungsten produce practically none in their own country and would become dependent to some extent on the British product, because it must be remembered that for many reasons countries like Spain and Portugal, Bolivia, etc., are not likely to keep up their lately inflated output. The metallurgical treatment of tungsten ores is now almost entirely in British hands and is likely to remain so for a long time.

"In this connection it may be well to recall what took place some years ago in the Federated Malay States when attempt on the part of some American interests

Digitized by Google

to secure more than 40 per cent of world's output of tin was frustrated by the imposition of an absolutely prohibitive export tax on tin ore shipped to any country but the United Kingdom."

GRIFFITHS, H. D., Kanbauk Wolfram mine, Lower Burma: Min. Mag. (London), vol. 17, pp. 211–219, November, 1917, 7 figures, including geologic map and cross section.

(P. 211) Property worked sporadically for tin, which was found on banks of the creek by Chinese workers. No notice seems to have been taken of the wolfram which was found in connection with the tin, nor of the lode outcrops showing wolfram in abundance on the slopes of the hills, until property was taken under prospecting license in 1912 by Col. Radcliff and a few friends. Attention was given to the prospecting of the wolfram outcrops, which yielded more than sufficient ore to pay expenses. In 1913 the property was incorporated by Radcliff & Co. (Ltd.) as the Kanbauk (Burma) Wolfram Mines (Ltd.), registered in Burma with an issued capital of 2,100,000 rupees in shares of 15 rupees each and 750,000 rupees in convertible debentures.

The map shows the mine to be on a stream called "Y Nye Chang," flowing north. Radcliff names "Wong Sun's" and "Kanbauk West" reefs.

The country rock consists of a series of schists, dipping sharply to the east toward the granite, and varying from fine-grained schists to fairly coarse sandstones. Contrary to the usual occurrences the mineralized zone carrying the lodes runs east and west at right angles to the strike of the schists, or the line of contact of these with the granite, instead of being parallel to them. The actual granite contact has not been exposed, but a dioritic body has intervened between the granite and the schists. This dioritic body shows the peculiarity of being tungsten-bearing. This has been found in almost every sample in quantities varying from traces up to 1½ per cent of WO_3. On crushing, no wolframite concentrate was obtainable, but the wet assay almost invariably resulted in WO_3 being obtained. Twenty outcrops of quartz carrying wolframite have been traced and prospected or mined in many places. Most of them dip to the south and a few to the north, and a few cross reefs have also been encountered in depth. (P. 213.) The lodes are well defined and fairly regular, from 3 to 24 inches thick, and average about 10 inches in thickness. The mineralized zone apparently occurs only on the rising ground, and on the eastern slope of that ground and extending as far as the granite there exists talus of considerable thickness and extent which carries detrital wolfram in considerable quantities. The lodes have been opened at shallow depths and stoped out for a number of years. Prior to the installation of a crushing plant, all the crushing was done by hand and only portions which carried wolframite in large quantities were treated. On completion of the crushing plant all the quartz was mined, the only portions left being barren, so that the original returns of over 3 per cent from picked ore have not been maintained. The average yield has been 1½ per cent, or 34 pounds of wolframite per ton.

The results obtained from the lode workings have been as follows:

Tungsten ore crushed from Kanbauk mine, Lower Burma, 1912–1916.

	Tons.
1912, crushed by hand	206.75
1913, crushed by hand	254.75
1914, crushed by battery	86.75
1915, crushed by battery	70.50
1916, crushed by battery	55.85

Total ore from Kanbauk mine, Lower Burma, 1912–1916.

Year.	Mine ore (tons).	Sluicing ore (tons).	Total output (tons).
1912	206.75	.....	206.75
1913	254.75	.....	254.75
1914	86.75	37.00	123.75
1915	70.50	101.75	172.25
1916	55.85	249.50	305.35
	674.60	388.25	1,062.85

Digitized by Google

(P. 213.) The mill has been handicapped through want of water during dry seasons and by difficulties as to fuel and power. These drawbacks will be completely eliminated, and it is estimated that in the near future the battery should yield 350 tons of wolfram concentrate per annum. The latest costs total per ton milled 22s. 3d., and including general expenses these costs should not exceed 25s. In 1916 the crushing operations resulted as follows:

Hours run, 259.5 hours per month, equal to 35.4 per cent only.
Mine ore crushed, 6,075.6 tons.
Mullock crushed, 1,600.4 tons (value one-fourth per cent).
Total ore crushed, 7,676 tons.
Stamp duty, 5.8 tons.
Mill concentrates (58 per cent of WO_3) 43.7 tons.
Mill concentrates (70 per cent of WO_3) 25.35 tons.
Hand-picked concentrates (71 per cent of WO_3) 8.02 tons.
Average return of mine ore, 19 pounds (of concentrates) per ton.
Average assay of tailing, 7.1 pounds per ton (70 per cent ore).

(P. 214.) The mill recovery is about 70 per cent. The tailing contained only fine ore and slime and the WO_3 carried by the tungsten ocher which occurs in appreciable quantities in the decomposed portions of the lodes. Of late the mill concentrate has shown 10 per cent of cassiterite and a small percentage of bismuth. The latter is sorted out of the hand-picked ore. The concentrates are not separated before shipment, this being done in England and the purchasers paying market rates for any cassiterite present. Magnetic separation on a large scale is now undertaken in Tavoy but is not yet done in great perfection. The total cost of drilling on this work is as follows:

2 boys at 1 rupee 12 annas.....3 rupees 8 annas.[1]
2 gallons of petrol.....1 rupee 2 annas.
Sundries, drills, lubrication, etc.....1 rupee 4 annas.
Total, 6 rupees for 16 feet drilled equal to 6.24 pence per foot.

Underground in a drive 6 feet 6 inches by 4 feet 6 inches in a fairly hard ground one of these drills, manned by 6 coolies working on three shifts, is capable of an advance of 30 to 40 feet a month. (P. 215.) The maximum amount of backs will be about 400 feet, and the adits will enable the property to be exploited for some years before shaft sinking becomes necessary. Talus shafts are sunk at intervals of 2½ chains or less. The area of talus exceeds 173 acres and gives 8,000,000 cubic yards capable of being worked at a profit. The values in wolframite vary considerably, as would be expected in that class of deposit, and start practically from the surface, so that it can not be said that any barren overburden exists. As the talus extends away from the hill the wolfram contents diminish, but are almost replaced by corresponding values in cassiterite, until the clearing is reached where only cassiterite is found. It had been computed that the average quantity of wolfram or cassiterite would be 1¼ pounds per cubic yard, but the extensive sluicing done during the last three years has yielded very much better results, as appears below:

Year.	Cubic yards.	Pounds per cubic yard.
1914	52,000	1.38
1915	80,000	2.59
1916	128,000	4.28
	362,000	3.31

The wolframite content that had been indicated by the 50 pits and bores inclosed in the area was 1.78 pounds per cubic yard, whereas the actual return was 3.31 pounds. (P. 216.) The estimated realizable net value of output is £38,697. The mine cost of producing 1 ton of wolframite is £27 [1916]. With additional plant hand-sluicing will be abolished, and it is calculated that the mine costs for hydraulicking will not exceed 8d. and that a ton of wolframite on a return of only 1¼ pounds per cubic yard (p. 217) will cost less than £33. The price of wolfram will have to come down to 9s. 6d. per unit before the work becomes unprofitable.

Gives considerable detailed information on the work done, labor employed (mostly Chinese), rainfall, and estimates for new water and power system.

[1] The rupee is equal to about 33 cents; the anna is one-sixteenth of the rupee.

Digitized by Google

HESS, F. L., Tungsten minerals and deposits: U. S. Geol. Survey Bull. 652, 85 pp., 2. figs., 25 pl. (10 colored), 1917.

A general article describing tungsten minerals, accompanying minerals, and characteristics of tungsten deposits, with other data on tungsten. Intended to be of service to prospectors and others interested in the subject. The work is illustrated with colored and black and white plates.

HEYCK, Z., Comparative study of arc lamps and gas-filled tungsten glow lamps: Ver. deutsch. Ing., vol. 61, pp. 625–630, 1917. Science Abs., vol. 20B, pp. 392–393, 1917. Abstract (by A. L. Field) from Chem. Abstracts, vol. 12, p. 1271, 1918.

Discussion of costs and merits of the two types of lamps. Both have advantages and disadvantages for lighting large areas. Data are given on watts per lux and per m.² floor surface in a room 10 by 6 meters. With white ceiling and gray walls for open arc with plain carbons, inclosed arc with plain carbons, and half-watt gas-filled tungsten lamp, for alternating current and direct current and with (*a*) direct lighting, (*b*) semidirect, (*c*) indirect lighting. Polar distribution in lighting large workshops is discussed, and a number of Rousseau curves are given. The following efficiencies in watts per candle are given: (*a*) Half-watt lamp, 0.55 to 0.9. (*b*) Direct current, open, plain carbon arc, 0.68 to 1.0 with 2 lamps in series on 110 volts; 0.57 to 0.73 with 3 lamps in series on 110 volts. (*c*) Inclosed arc, 0.8 to 1.1 working singly on 110 volts and 0.7 to 0.8 with 3 in series on 220 volts. (*d*) Open flame arcs, carbons side-by-side, yellow light, 0.24 to 0.17 for direct current and 0.16 to 0.19 for alternating current. (*e*) Inclosed flame arcs, vertical carbons, white light, 0.2 for direct current and 0.25 to 0.3 for alternating current (mean lower hemispherical candle power in all cases). Carbon and bulb renewals are generally about equal.

INSULL, M. J., Tungsten: British patent No. 113835, March 8, 1917. Abstract from Chem. Abstracts, vol. 12, pp. 1377–1378, 1918.

Tungsten ingots and the like, particularly ingots of compressed tungsten particles, are welded or sintered by heating the ingots held in suspension preferably in a substantially horizontal position to a temperature which may be but little below the melting point of tungsten and simultaneously subjecting the ingots to a continual longitudinal compressive stress between electrodes whose ends are permanently maintained in parallelism during longitudinal movement of the electrodes. The process may be carried out in an inert atmosphere, such as one of hydrogen, or in a vacuum. Constructional details are specified.

INSULL, M. J., Tungsten, etc.: British patent No. 113836, March 8, 1917. Abstract from Chem. Abstracts, vol. 12, p. 1377, 1918.

Unsintered tungsten powder is subjected to pressure, preferably greater than 130 tons per square inch, to obtain a solid having a density greater than 15 and, in some cases, above 17. Articles such as chemical dishes, for use in melting substances of high melting point, may be made out of the solid so prepared. After the compressing process, the pressure upon the tungsten powder is relieved so as to allow the powder to expand substantially in all directions. Constructional details of apparatus are specified.

JONES, E. H., Electrically fusing and depositing metals: British patent No. 116308, Apr. 12, 1917. [Cf. British patent No. 3762, 1911 (Chem. Abstracts, vol. 6, p. 2036), and British patent No. 109652 (Chem. Abstracts, vol. 12, p. 123)]. Chem. Abstracts, vol. 13, p. 9, Jan. 10, 1919.

An arc electrode contains all the constituents requisite for the deposition of high-speed steel and is covered with slag-forming material—that is, the electrode may consist of a mild-steel trough filled with a mixture of 1.3 parts of carbon, 22 of tungsten, 9 of chromium, and 0.25 of vanadium, the iron trough amounting to 67.45 parts. In some cases the steel only requires 6 per cent of tungsten. Molybdenum may partly replace tungsten, and other materials, such as nickel and cobalt may be added. The whole is wound with asbestos yarn. Cutting parts of tools may be made or renewed by deposition from such an electrode; or the steel may be received by a mold at the bottom of which is the second electrode.

KNOPF, ADOLPH, Tungsten deposits of northwestern Inyo County, Calif.: U. S. Geol. Survey Bull. 640, pp. 229–249, 1917.

Describes the contact-metamorphic deposits that have been extensively worked.

KNOX, N. B., Solubility of tungsten: Min. and Sci. Press, vol. 115, p. 818, Dec. 8, 1917.

In the Phoenicia mines in Galicia, northwestern Spain, wolframite occurs in three parallel quartz veins cutting chlorite schist that has been intruded by pegmatite dikes 1 to 25 meters wide. Ore carries from 2 parts cassiterite to 1 of wolframite to equal quantities. Where the veins cut dikes more cassiterite than

Digitized by Google

wolframite is found, and where feldspars are highly kaolinized, only cassiterite is found. "It would appear that in the kaolinization of the feldspars the wolfram has been dissolved."

On old dumps, possibly Phoenician, more wolframite than cassiterite is found, and the author thinks they may represent the beginning of decay. There are no detached crystals of cassiterite. [This would seem natural, as the veins were probably worked formerly for tin.—F. L. H.]

Notes that at Mawchi, South Shan States, Burma, the proportion of cassiterite to wolframite in gravels was larger than in the veins.

KOERNER, W. E., Electrolytic behavior of tungsten: Met. and Chem. Eng., vol. 16, pp. 40–47, Jan. 1, 1917.

An elaborate study of the behavior of tungsten in various electrolytes.

Tungsten apparently can not be deposited electrolytically though several German patents assume to cover such processes. Experiments following the processes indicated gave deposits of tungsten oxides.

Finds a use for tungsten in voltaic cells, with mercury or silver as a cathode.

MACLAREN, MALCOLM, Geology of the East Pool mine at Camborne, Cornwall: Min. Mag. (London), vol. 16, pp. 245–252, May, 1917, 1 plan and 1 cross section.

The veins of the East Pool mine cross the East Pool and Agar "sets." The lodes are of three classes, north dipping, south dipping, and vertical. A new lode, the Rogers, was struck in the slate at the 160-fathom level and in the granite at the 240-fathom level. Tin, copper, arsenic, and tungsten are mined. The veins carry cassiterite, wolframite, chalcopyrite, mispickel, bismuthinite, azurite, stannite, scheelite, fluorspar, and some cobalt ore. In the Rogers lode at the 196-fathom level a remarkable secondary occurrence of scheelite, developed along cleavage cracks and veins in wolfram, has been recently noted. Apparently the same secondary development of scheelite occurred in the upper workings of the Great lode, for similar occurrences from the Great lode were described by J. H. Collins as long ago as 1878. [That the scheelite is secondary seems doubtful.—F. L. H.]

The tungsten zone occurs near the top of the tin zone. In the Great lode wolframite was most plentiful from the 140 to the 196 fathom levels, a solid bunch of wolframite 4 feet thick being encountered below the 140-fathom level. In the Rogers lode, so far as it has been explored, wolframite is most abundant on the 196-fathom level. In the latter lode, however, the top of the tin zone is some 25 to 30 fathoms lower than in the Great lode.

MINING JOURNAL (London): Cornish Wolfram Mines (Ltd.): Vol. 116, pp. 151–152, March 17, 1917.

In a report given by the chairman, he stated that it was hoped to make a recovery of 1 per cent of concentrates carrying 65 per cent of WO_3. With an output of 1,600 long tons of ore a month (25 work days) and a price of £180 per long ton of concentrates carrying 65–66 per cent of WO_3, he estimated a yearly profit of £11,520 to £13,248.

MINING JOURNAL (London): Thermoelectric Ore Reduction Corp. (Ltd.); visit to the Luton works: Vol. 115, p. 787, Dec. 2, 1916.

The firm started in 1911 as The Electric Furnace Smelters (Ltd.), and the present company was formed in 1912. The firm makes ferrotungsten, ferromolybdenum, ferrovanadium, ferrochromium, ferromanganese, ferrosilicon, and ferrotantalum. It treats ores carrying both tin and scheelite, saving both. It recently has been turning out 140 tons of tungsten a month. Ferrotungsten carries about 87 per cent of tungsten. Supplies ordinarily tungsten powder of 98 per cent purity and of higher quality for filaments. The powder is produced by the soda fusion process, as at Widnes.

Claims losses of tungsten are small. Have to remove charge from furnace as a whole and break up.

MINING JOURNAL (London): High Speed Steel Alloys (Ltd.); visit of inspection to the works: Vol. 115, p. 779, 1916.

A general description of the works at Widnes, near Liverpool, England. Thirty-one steel manufacturing firms are stockholders and the Government is also interested. Use the soda fusion process for producing tungsten (powder).

MINING JOURNAL (London): Thermit (Ltd.); a visit to the works: Vol. 116, p. 21, 1917.

Gives a very general description of the plant of Thermit (Ltd.), where tungsten and other metals are reduced by the alumino-thermic method.

ROSENSTEIN, L., and SIMONDS, E. H., Tungsten trioxide from ores: United States patent No. 1244082, Oct. 23, 1917. Abstract from Chem. Abstracts, vol. 12, p. 207, 1918.

Powdered tungsten ore is boiled with water, soda ash, and caustic soda, forming sodium tungstate, the liquid is filtered, and lime hydrate is added to the filtrate

Digitized by Google

to free it from any excess soda ash. The precipitated lime carbonate is removed and the liquid is boiled with barium chloride, forming barium tungstate. The last is treated with hydrochloric acid to form tungsten trioxide.

SHIGA, K., Gold alloy: French patent No. 484873, Nov. 20, 1917. Abstract from Chem. Abstracts, vol. 12, p. 1168, 1918.

Gold is alloyed with nickel alone, or with nickel and tungsten. The proportions specified are gold 95–80 per cent and nickel 5 to 20 per cent, with resulting hardness of 55 to 85 on the Shore scleroscope (gold being 23 and nickel being 40); and, when tungsten is also used, the proportions specified are gold 90–60 per cent, nickel 5 to 20 per cent, and tungsten 5 to 20 per cent, with hardness of 58 to 86.

SUSCHINSKII, P. P., Geological structure of the Sherlovaya Mountain in the Transbaikal and the minerals found in this region: Bull. Acad. Sci., Petrograd, 1917, pp. 507–520. Abstract by H. M. Gordin from Chem. Abstracts, vol. 11, p. 2653, Oct. 10, 1917.

Maps and geologic data of the Sherlovaya Mountain and descriptions of the minerals occurring on it are given. Of chief interest is the occurrence of wolframite, topaz, and aquamarine.

WELLS, R. C., and BUTLER, B. S., Tungstenite, a new mineral: Washington. Acad. Sci. Jour., vol. 20, pp. 596–599, Dec. 4, 1917.

Describe a sulphide of tungsten, WS_2, found by J. J. Beeson, geologist for the Emma Consolidated Copper Co., in the Emma mine at Alta in the Little Cottonwood district and Canyon, 25 miles southeast of Salt Lake City, Utah.

Two specimens were analyzed, but the analyses were imperfect—7.5 per cent was undetermined. Gives details of analytical methods.

The country rocks are a series of Paleozoic limestones, shales, and quartzites and Upper Paleozoic quartzite and shales. The Emma ore body occurs as a replacement of a brecciated zone in Paleozoic limestone, where it is crossed by a mineralizing fissure. The ore shoot follows the intersection of the brecciated zone and the fissure, pitching rather steeply to the northeast. About 450 feet below the outcrop the ore shoot is cut off by a strong fault, the continuation on the opposite side of the fault being about 250 feet lower. There is very little oxidized material in the portion of the shoot below the fault from which the tungstenite was taken.

The important vein minerals are quartz, galena, pyrite, tetrahedrite, argentite, and possibly some other silver minerals not yet determined.

Pyrite was the earliest metallic mineral to form in the deposit and this was followed by galena, tetrahedrite, silver minerals, and tungstenite. The tungstenite is apparently in part contemporaneous with and in part later than the galena. The fact that the specimens containing most of this mineral have been found near a minor faulted zone suggests that there may have been an enrichment in tungsten along that zone, though that is not certain.

The hardness appears to be about 2.5. Particles which are very easily cut from the massive piece with a knife blade appear under the microscope to consist of feathery leaves or flakes resembling graphite. The mineral is opaque. It marks paper, soils the fingers slightly, and rubs up between a mortar and pestle like graphite. The cleavage and fracture could not be determined. The luster varies from dull to brilliant metallic; the color is dark lead gray; and the streak is dark gray. The actual specific gravity of the second specimen mentioned was 6.43. The impurities and undetermined material being allowed for as well as possible, the specific gravity of the tungstenite is calculated to be about 7.4.

Tungstenite appears to be unattacked by hydrochloric acid or nitric acid. It is decomposed by aqua regia or by fusion with sodium nitrate. Its behavior in a bulb tube and on charcoal can not be stated definitely because of the impurities, though it appears to be a rather stable compound, not even being oxidized by roasting in the air. It burns with incandescence in oxygen (p. 598).

ZEALLEY, A. E. V., The tungsten deposits of southern Rhodesia: Sci. Am. Suppl. No. 2192, pp. 10–11, Jan. 5, 1918. Reprinted from Roy. Soc. Arts Jour., which had copied it from the Bulawayo Chronicle, May 18, 1917. Also reprinted by the Southern Rhodesia Geological Survey under the title "Report on the tungsten deposits of Essexvale, Umzingwane district." Bulawayo, 1917. Abstract, Min. Mag. (London), vol. 17, p. 92, 1917.

Sixteen veins, on 11 of which a little work has been done, are known in an area of 9.5 square miles, extending 2¾ miles northwest and 1½ miles southeast of Essexvale Siding, Rhodesia, and 20 miles east of Bulawayo. Spasmodic production has been made since 1906. None in 1914-15. In 1916 2½ tons, valued at £467. Total, 85 tons concentrates, valued at £7,165. The production seems to have been from "rubble"—that is, residual débris.

Digitized by Google

The area is part of an oval mass of coarse-textured hornblende granite, 8 miles northwest-southeast by 5 miles northeast-southwest, containing inclusions of epidiorite and felsite dikes.

The tungsten reefs consist of greisen composed chiefly of a soft greenish-yellow mica, or of mica, fluorspar, topaz, and secondary feldspar. The greisen has been formed by the action of vapors on a porphyry or aplite (fine-textured white granite free from hornblende and mica). With the greisen is a variable amount of feldspar, chlorite, mica, fluorspar, topaz, tourmaline, wolframite scheelite, galena (rather rare), and pyrrhotite.

No tungsten reefs have been found without the quartz, although it is quite conceivable that such exist.

The quartz strings expand into lenses exceeding 20 feet in width, and thus make low hillocks such as those at "The Ranche" homestead.

The reefs vary from 200 yards to about 1 mile in length.

With one exception the reefs examined strike east to west and dip north at angles varying between 30° and 55°. The reef on plot 4 strikes northwest to southeast and dips northeast at 53°.

The width of the reefs is, of course, variable, owing to the lenses of quartz. Apart from the quartz lenses, the width averaged 3 feet and is surprisingly constant.

At the Union Jack the intrusion exceeds 6 feet in width, but about a third of it consists of white aplite apparently ungreisenized. The richest deposit, on Tungsten Kopje, is a stockwork of similar "reefs" nowhere more than 1 foot thick.

The country rock is without signs of shearing or faulting between it and the reef. It appears, therefore, that the aplite was injected along master-joint planes and not in fissures caused by faulting.

Considerable magnetite and ilmenite are found in the placer concentrates. Wolframite has been found in masses of 157, 172, and 235 pounds. (The second specimen is in the Rhodesia Museum). "Groups of pale pinkish scheelite measuring 3 or 4 inches are to be found."

Scheelite and wolframite are commonly intergrown, but the scheelite was commonly thrown away by miners. Would suggest that the "reefs" are in "normal greisen," but somewhat of the character of gold quartz veins and seem to form a connecting link. The rock inclosing the "reef" is pyritized (pyrite and pyrrhotite) and the feldspars are sericitized. The residual deposits are richest within 300 feet of the "greisen" on this steeper ground and within 75 feet on the flat ground. They carry 2 pounds to 8 pounds of wolframite per ton, the scheelite being rejected. The estimate does not include large lumps of wolframite or fine wolframite and scheelite in rock. On the Lunar Block reef in 1916 1,600 pounds of wolframite were picked up by hand after being gone over once.

The coarse and medium concentrate is remarkably clean wolframite. The finest concentrate consists of wolframite and scheelite, with a certain amount of other minerals from the weathered rocks, including a trace of gold. The finest concentrate is rejected under existing circumstances, but on a larger scale of operations concentrating tables and magnetic separators may be expected to give profitable results.

Digitized by Google

RADIUM, URANIUM, AND VANADIUM.

By FRANK L. HESS.

PRODUCTION.

In 1917 there were produced and shipped, sold, or reduced in the United States 33,404 short tons of uranium and vanadium ores carrying 103 tons of uranium oxide (U_3O_8), or 87.4 tons of uranium and 26.4 grams of radium. There was actually isolated 11.96 grams of radium (Ra) contained in salts, mostly, if not all, chloride. The vanadium contained in the carnotite ores and in the roscoelite-bearing sandstone mined in southwestern Colorado amounted to 484 tons. In 1916 the figures were: Ores, 20,300 tons containing 10 grams of radium, 33.7 tons uranium (77,600 pounds U_3O_8), and 460 tons of vanadium.

The uranium ore was mostly carnotite (hydrous potassium-uranium vanadate) largely from the west side of Montrose and Mesa counties, Colo., with a little from the La Sal Mountains in the adjoining part of Utah (Grand County). The ore also included some uvanite (hydrous uranium vanadate) from Temple Rock, Emery County, 45 miles southwest of Green River, Utah. Most of the ore was mined by the companies isolating radium salts or by their representatives, but a small part was produced by prospectors and others who sold their ore to the companies.

The following companies were engaged in the isolation of radium during the year:

Carnotite Reduction Co. (Dr. H. N. McCoy), 2600 Iglehart Court, Chicago, Ill.
Chemical Products Co., 616 Majestic Building, Denver, Colo.
Colorado Radium Co., P. O. Box 1316, Denver, Colo.
W. L. Cummings Chemical Co., Lansdowne, Pa.
Radium Luminous Materials Corporation, 55 Liberty Street, New York, N. Y.
Standard Chemical Co., Pittsburgh, Pa.

Of these by far the largest is the Standard Chemical Co. The Chemical Products Co., of Denver, started work during the year on the uvanite ores from Temple Mountain and had radium salts ready for crystallization. The United States Metals Reduction Co. shipped a carload of ore from its mine in the Dolores River valley, Utah, northeast of the La Sal Mountains, to an experimental plant at Cheswick, Pa. The Radium Co. of America did no work at its plant at Sellersville, Pa., during the year.

Vanadium was produced principally in this country by the Primos Chemical Co. at Vanadium (formerly Newmire), Colo., where the company operated its reduction plant on the roscoelite-bearing sandstone found along Bear and Fall creeks and San Miguel River. The vanadium is separated from the ore as hydrous ferric vanadate and shipped to the Eastern States for reduction to ferrovanadium. The

Digitized by Google

company is the second largest producer of vanadium and is surpassed only by the American Vanadium Co., of Pittsburgh, which draws its ores from Minasragra, Peru.

Each of the radium companies saved vanadium oxide as a by-product, and toward the end of the year the demand became strong for all vanadium-bearing substances that might be used as a source of the metal. The vanadium saved by the radium companies comes in part from the carnotite itself, but practically all if not all the ores carry an excess of vanadium over that required for the carnotite present. Possibly a part of the excess vanadium is present as roscoelite, the vanadium-bearing mica; a part is present as hewettite or metahewettite (hydrous calcium vanadates), calciovolborthite (hydrous calcium copper vanadate), and other less well-known minerals.

Some work was done on vanadinite and related mineral deposits in the Southwest during the year. Some ore (psittacinite or mottramite, lead-copper vanadate) was reported shipped by the Christmas Consolidated Mining Co., from Goodsprings, Nev. Near Kelvin, Ariz., the United States Vanadium Co. did considerable work on a vanadinite-bearing claim and made arrangements to erect a mill in which a dry separation process was to be used.

The vanadium deposits of the Southwest are all in the oxidized portions of lead-bearing veins. The lead is usually accompanied by a number of other sulphides, particularly those of zinc and copper. Phosphorus and arsenic also generally accompany the veins so that in the oxidized portions not only lead vanadate (vanadinite) but vanadates of copper and zinc are also present. These are not present as separate minerals, but take the form of a combined vanadate of lead and zinc or of lead, zinc, and copper, and the proportion of the metals may vary considerably. The minerals may vary also by containing in whole or in part either phosphorus or arsenic in place of vanadium. Nearly all deposits contain wulfenite, the lead molybdate, and most of them contain a small quantity of tungsten. This probably does not occur as the lead tungstate (stolzite), but seems to be a component of the wulfenite. Stolzite may occur, but it is not at all common, and has rarely been recognized. The percentage of tungsten rarely, if ever, exceeds 2 per cent. The deposits are generally small, so that no single one now known is large enough to furnish ore for a plant of considerable size.

USES, DEMAND, AND TRADE.

The demand for radium had a considerable setback after the United States entered the war but soon increased greatly, though the purposes for which it was to be used were those with the minimum permanent value. The greatest demand for radium since early in 1916 has been for use in the illumination of watch faces. Many thousands of the cheapest watches, the life of which is ordinarily not more than two or three years, were thus equipped, and oddly enough the illumination of the more expensive watches has followed much more slowly. Gun sights, compass faces, and airplane dials of various kinds were also [illegible] From those articles the radium is not recoverable.

V[illegible]n illuminant a radium salt is mixed with artificial zin[illegible] a cementing material, such as amyl acetate ("l[illegible]he alpha rays (helium atoms) given off by the

Digitized by Google

radium strike the particles of zinc sulphide and make them luminescent. The degree of luminescence depends on the quality of the zinc sulphide and on the quantity of radium present.

Radium has proved itself so valuable in the treatment of human disease in ways for which no acceptable substitute is known that every effort should be made to conserve it.

Experienced surgeons say that if radium were useful for nothing else, the relief from pain it gives in certain forms of cancer makes it worth its whole cost. Radium cures some tumors which before it was discovered were successfully treated only by severe operations, and it is otherwise so useful that it can not well be dispensed with. That it does not cure all cancers or all tumors is beside the mark. Its value is sufficiently proved without claiming for it universal application.

The uses for uranium have not grown much. Many attempts have been made to use uranium in steel either as a substitute for tungsten or otherwise, and a little high-speed steel containing uranium is manufactured. Uranium is used in a small way for coloring yellow glass, such as that used in automobile headlights, for chemical reagents, and in the coloring of pottery; but the uses are small and the sodium uranate or other compounds made by the radium manufacturers is mostly awaiting buyers.

The principal use of vanadium is still in steels, especially where resistance to repeated strains is desired, and in tool steels.

PRICES.

The price of radium was from $90 to $120 a milligram for the element contained in a salt, such as the chloride or bromide, in a material containing 50 per cent or more of the pure salt.

Prices for carnotite were nominal and a subject of individual bargaining but ran about $2.50 a pound for the U_3O_8, in ore carrying 2 per cent of U_3O_8, with a bonus for richer ore and a penalty for lower grades. Uranium in ferrouranium, carrying 30 to 40 per cent of uranium, was quoted at $7.50 a pound. Sodium uranate was quoted at $2 to $2.50 a pound.

Vanadium in ferrovanadium, carrying 35 to 50 per cent of vanadium, was sold for $2.50 to $5.50, the larger price being obtained for small lots near the end of the year. The National Radium Institute sold iron vanadate in November, 1917, at 61 cents a pound for the V_2O_5 contained; in December it sold similar material at 75 cents a pound.

IMPORTS.

Uranium salts and oxide, including some radium salts, imported for consumption, 1913–1917.

Year.	Value.	Year.	Value.
1913	$34,319	1916	$5,065
1914	63,055	1917	2,930
1915	17,288		

EXPORTS.

Although figures are not available, it is known that a considerable quantity of radium salts was exported during the year.

Digitized by Google

LITERATURE AND PATENTS.

Among the literature and patents issued during 1917 that have to do with radium, uranium, and vanadium are the following:

ELECTRICAL WORLD, Uranium calcium arc lamp: Vol. 70, p. 1002, 1917. Abstract by C. G. Fink, Chem. Abstracts, vol. 12, p. 252, February 10, 1918.

Comments on a recent patent (United States patent No. 1235996) by W. R. Mott (Chem. Abstracts, vol. 11, p. 2641). Uranium in the electric arc probably gives more lines in the spectrum than any other known element. Uranium has the distinction of giving 50 per cent more photographic power when used in the arc than rare-earth fluorides or titanium oxide. When uranium is mixed with calcium fluoride in making up an arc-lamp electrode, it fully blends with the yellow rays of the fluoride to produce an intense snow-white light of extraordinary photographic power.

GRIFFITHS, F. J., The rôle of chrome-vanadium in alloy steels: Am. Soc. Test. Materials Proc., vol. 17, pp. 11, 33–44, 55–57, 1917. Chem. Abstracts, vol. 12, p. 352, February 20, 1918.

KEENEY, R. M., and VOGT, L. F., Uranium alloys: United States patents No. 1240054 and No. 1240055, September 11, 1917. Abstract from Chem. Abstracts, vol. 11, pp. 3233–3234, 1917.

Fluorspar is stated to be the best slag-forming material for use in making ferrouranium alloys containing a high per cent of uranium. A charge for the production of ferrouranium is formed of steel turnings 10, uranium oxide 7.5, coke 6, and calcium fluoride 8 parts. At least 76 per cent of the uranium in this charge will be contained in the finished alloy and 100 pounds of the charge will produce approximately 40 pounds of ferrouranium, and by resmelting the residue approximately 85 per cent of the uranium may be alloyed with the steel and about 45 pounds of ferrouranium thus obtained. The ferrouranium produced has the composition uranium 29.2, carbon 5.12, silicon 2.68, and iron 63 per cent. If finely divided nickel is substituted for steel turnings in the specified charge, and alloy of otherwise similar composition containing 63 per cent nickel is produced in the same manner.

KITHIL, K. L., and DAVIS, J. A., Mining and concentration of carnotite ores: Bur. Mines Bull. 103, 83 pp., 1917. Abstract by F. W. Smither, Chem. Abstracts, vol. 12, p. 1451, 1918.

A detailed account, with numerous illustrations, tables, flow sheets, etc., of the methods used in mining and concentrating the carnotite treated at Denver under a cooperative agreement with the National Radium Institute. The matter is presented in four chapters bearing the captions (1) The mining of carnotite ores by the National Radium Institute; (2) Grinding and sampling of shipping ore before chemical treatment; (3) Concentration of milling ore; (4) Costs of production.

NORRIS, G. L., The rôle of vanadium in alloy steels: Am. Soc. Test. Materials Proc., vol. 17, pp. 11, 33–44, 55–57, 1917. Iron Age, vol. 100, pp. 134–137, 1917. Abstract by W. T. Hall, Chem. Abstracts, vol. 11, p. 2573, September 20, 1917.

The remarkable effects of vanadium in steel are not due, as many have supposed, to the action of this element as deoxidizer and scavenger, but rather to the actual beneficial effect of the vanadium that remains in the steel. A few hundredths of 1 per cent of vanadium combined with ferrite appears to increase the strength, toughness, hardness, and resistance to abrasion. Nearly all the vanadium in steel, however, is present in the pearlite as a compound carbide of vanadium, iron, and other metals present.

PARSONS, C. L., For the preparation of uranium oxides: United States patent No. 1224013, April 24, 1917.

Dedicated to the American people.

PARSONS, C. L., For purifying compounds of uranium: United States patent No. 1224014, April 24, 1917.

Dedicated to the American people.

PLUM, H. M., Extraction and separation of the radioactive constituents of carnotite: Mon. Sci., vol. 7, pp. 270–274, 1917. Abstract by G. L. Wendt, Chem. Abstracts, vol. 12, p. 648, 1918.

A critical review of the various commercial methods in use. Boiling with soda solution is the method recommended, and detailed directions are given for the separation of radium, polonium, radioactive lead, ionium, and actinium.

Digitized by Google

ROLLASON, A., Refining metals and alloys: British patent No. 110860, March 2, 1917. Abstract, Chem. Abstracts, vol. 12, p. 470, March 10, 1918.

Uranium is used for removing oxygen from molten metals and alloys and increasing their density. The uranium is used either in the solid or molten state, preferably in the proportion of 1–1.5 per cent and combines with the oxygen without combining with the metal treated.

SCHMIDT, C., Device for viewing radioactive substances: United States patent No. 1242377, October 9, 1917.

Radioactive salt preparations: Soc. anon. de traitements chimiques. French patent No. 482894, May 2, 1917. Abstract, Chem. Abstracts, vol. 12, p. 117, 1917.

The radioactive salts are intimately mixed with certain substances such as collodion, enamel, etc.; the liquid mass is poured into the desired forms and allowed to cool.

STOCKHOLMS DAGBLAD (Sweden), Our vanadium requirements secured: Issue of November 7, 1917.

A company consisting of Uddeholms Co., the Swedish Credit Co., and a Mr. Nathorst, has applied for concession to work the vanadium-bearing coal [This "coal" is usually referred to as culm and is possibly asphaltic. It is not coal in the sense in which the word is usually used. F. L. H.] strata on Billingen, Skaraborg Län. According to samples taken, the coal is of excellent quality, fully as good as the best English coal, but the vanadium contained is of greater value than the coal itself. This precious metal has heretofore been imported from America. It is on the market as ferrovanadium, which is of the greatest importance in the manufacture of the best grade of steel. It seems possible that all the needs for ferrovanadium are secured, so that we shall be independent of import from abroad for our steel manufacture. Even the export of vanadium is contemplated.

The occurrence of coal in Västergotland has been known for several years; that it carried vanadium was discovered as early as 1907 by State Geologist Dr. H. Hedstrom through investigations carried on by him in the vicinity of Tidaholm. However, the coal strata there were thin.

In 1914 Baron Essen asked for a concession to mine these, but no work was done. That the strata now to be worked carried vanadium was discovered last year (1916). As far as is now known the quantity of coal that could be taken out might reach 10,000 tons a year. The coal beds are only 0.1 to 0.2 of a meter in thickness. How much of the area may carry coal is not known, but it is intended to begin extensive surveys and borings. The coal is of very fine quality, much better than the coal from the province of Skane, and contains only 1 per cent of ash, against 4 per cent to 8 per cent in that from Skane. However, whenever the coal does not contain vanadium the mining will hardly be of any importance. The quantity of coal that is expected to be mined at present is, of course, of practically no importance, although it is not to be despised under the present conditions of coal shortage. Vanadium is naturally the important element. The ash left in the burning of the coal contains 40 to 50 per cent vanadic acid. One should therefore obtain about 2 kilograms of vanadium per ton of coal, or altogether about 20 tons of vanadium a year, as far as we can now know. So far as at present can be judged, working these deposits will be profitable even should they be no more extensive than they are now known to be, for the price of vanadium is at present abnormally high.

VIOL, C. H., and KAMMER, G. D., The application of radium in warfare: Am. Electrochem. Soc. Trans., vol. 32, pp. 133–140, 1917. Chem. Abstracts, vol. 12, p. 114, 1917.

The chief uses are in therapy and luminous paints, especially for the dials of airplane instruments. The luminosity, which is due to the bombardment of zinc sulphide by X-rays, depends on the quality of the sulphide and the proportion of radium used in the paint. Crystalline hexagonal zinc sulphide prepared by a special method (not described) and with 0.215 milligrams of radium per gram of mixture is stated to give the best results. Other commercial mixtures contain 0.025 to 0.400 milligrams per gram. The zinc sulphide has apparently a definite capacity of total light emission, since the rate of decay of luminescence is proportionate to the amount of radium content and to the initial intensity of the light. Paints of suitable luminosity for many purposes but of shorter life can be made from cheaper radium substitutes, as mesothorium or radiothorium.

Digitized by Google

Digitized by Google

INDEX.

A. Page.

Abrasive bauxite 9
Adirondack district, iron ore 561–563
Africa, antimony 659
chromite 42
copper 726, 796
gold 613
iron ore 579, 583
lead 883
manganese ore 674, 686
quicksilver 399
exports to 382
silver 615
tin 69
tungsten 934
zinc 873
Alabama, bauxite 1, 3–4
cooperation 25a
alloys 598
gold 56, 605, 619, 627, 634
gold, silver, copper, lead, and zinc (mines report) 56–57
iron ore 560–561, 567–568, 585
manganese ore 669–671, 682
pig iron 586–587, 588
silver 56, 605, 619, 639
value of mineral products 46a, 48a
Alaska, antimony 657
chromite 38
copper 132, 136, 725, 738–740, 742, 746–747
gold 132, 605, 619, 621, 634, 642, 646
gold, silver, copper, and lead (mines report) by G. C. Martin 18a, 131–145
lead 132, 137, 883, 888
platinum 13
quicksilver 385, 399–400, 404
silver 132, 605, 619, 622, 629, 642, 646
tin 63–64
tungsten 932–933, 935
value of mineral products 46a, 48a
Algeria, iron ore 583
quicksilver 399
Alum 7–8
imports 8
Aluminum 5–9
(*See also* Bauxite and aluminum.)
Aluminum Co. of America 7
bauxite abrasives 9
British Aluminum Co 7
consumption 6
exports 35a, 6
imports 35a, 6
industry 7
market 6
prices 6
production and consumption 5–6

Page.

Aluminum, refractories 9
salts, production 7–8
imports 35a, 8
prices 8, 9
secondary 6, 7, 312, 327–329
summary 18a, 35a
uses 7
value 6
American Iron and Steel Institute, statistics of pig iron and steel 586, 601
Analyses, cobalt 903, 905
stellite 903
Anthracite, summary 36a, 38a
pig iron 593
Antimonial lead 656, 658, 884–885
summary 30a
Antimony, by Edson S. Bastin 653–663
diagram showing imports of antimony, 1914–1918 654
diagram showing stocks of metallic antimony 654
exports 661
foreign sources 661–663
imports 35a, 654, 659–661
type metal 660
ore 656, 658
prices 654, 661
production, mine 656–658
smelter 658
antimonial lead 658
salts, imports 35a, 660
secondary 312, 330, 659
situation 653–655
stocks 661
summary 18a, 35a
supply 656
uses 655–656
peace 655
war 655
Argentina, antimony 659
bismuth 31
copper 726
gold 613
manganese 674
imports 673
pig iron, exports to 595
quicksilver, exports 382
silver 615
tungsten 934
Arizona, copper 509, 725, 738–740, 742, 748–758
gold 509, 605, 619, 622, 634, 637, 642, 646
gold, silver, copper, lead, and zinc (mines report), by V. C. Heikes 18a, 509–556

Digitized by Google

Page.
Arizona, lead ... 509, 883, 888
manganese ore ... 669–671, 682
manganiferous ore ... 675
molybdenum ... 908–911
quicksilver ... 370, 372, 373, 385, 402, 404–405
silver ... 509, 605, 619, 622, 639, 642, 646
tungsten ore ... 932–933, 935–937
mills ... 945
value of mineral products ... 46a, 49a
vanadium ore ... 956
zinc ... 509, 862–863, 864
Arkansas, antimony ... 657
bauxite ... 1, 3–5
iron ore ... 560–561, 568
lead ... 77, 79, 883, 888
manganese ore ... 669–671, 683
rutile ... 929
silver, copper, lead, and zinc (mines report), by J. P. Dunlop ... 78–82
value of mineral products ... 46a, 49a
zinc ... 77, 79, 856, 862–863, 864, 866
Arsenic, by J. B. Umpleby ... 23–27
condition of industry ... 23–24
development ... 24
imports ... 36a, 25–26
outlook for 1918 ... 27
prices ... 26–27
production ... 24–25
summary ... 18a, 36a
Asbestos, summary ... 19a, 36a
Ashland, shipments of iron ore ... 573
Ashtabula, Ohio, receipts of iron ore ... 573
stocks of iron ore ... 575
Asphalt summary ... 20a, 36a
Australasia, copper ... 795–796
gold ... 613
silver ... 615
Australia, antimony ... 663
bismuth ... 31
chromic iron ore ... 42
copper ... 726, 795
imports from ... 779
iron ore, production ... 583
manganese ore ... 674
imports ... 673
nickel, imports from ... 923
pig iron, exports to ... 595
imports from ... 594
platinum ... 13, 14
quicksilver ... 399
exports to ... 382
tin ... 66, 69
titanium (rutile) ... 930
zinc ... 873
Austria, copper ... 726, 793
exports to ... 780
molybdenum in ores ... 907
nickel ... 921
quicksilver ... 372, 395
Austria-Hungary, gold ... 613
iron ore ... 583
manganese ore ... 674
pig iron ... 595
exports to ... 595
imports from ... 594
quicksilver ... 372, 395, 396
silver ... 615

B.

Page.
Banca, tin ... 69
Baraboo range, iron ore ... 571–572
Barium compounds, imports ... 36a
Barytes, summary ... 19a, 36a
Basic pig iron, production ... 591
Bastin, E. S., paper on antimony ... 653–663
Bauxite and aluminum, by James M. Hill ... 1–9
Bauxite ... 1–5
abrasives ... 7, 9
Alabama ... 1, 3, 4
Arkansas ... 1, 3, 4
brick ... 7, 9
British and Dutch Guiana ... 3
consumption ... 1
exports ... 35a, 1
Georgia ... 1, 3, 5
imports ... 35a, 1
industry, by States ... 4–5
market ... 2
occurrence and character ... 3–4
prices ... 3
production by States ... 1
products ... 7, 9
summary ... 18a, 35a
Tennessee ... 1, 3, 5
uses ... 2
world's production ... 3
Belgian Kongo, copper ... 796
silver ... 615
tin ... 69
Belgium, arsenic ... 26
copper, exports to ... 780
iron ore ... 583
imports from ... 579
manganese ore, imports from ... 673
pig iron ... 595
exports to ... 595
imports from ... 594
Beneficiated iron ore ... 583–585
Bessemer iron ore, price ... 576
pig iron, production ... 591
steel ... 600–601
Billiton, tin ... 69
Birmingham district, iron ore ... 561–563
Bismuth, by J. B. Umpleby ... 29–31
imports ... 35a, 31
prices ... 29
production ... 29
summary ... 18a, 35a
uses ... 29–31
Blast furnaces, by States ... 591
Bolivia, antimony ... 659, 663
bismuth ... 31
copper ... 726
gold ... 613
silver ... 615
tin ... 66, 69
tungsten ... 934, 947
Borax, summary ... 20a, 36a
Borneo, platinum ... 13, 14
Bosnia, manganese ore ... 674
Boyne City, Mich., iron-ore receipts ... 574
Brass, old, exports of ... 35a
imports ... 35a
remelted ... 312, 313–317

Digitized by Google

Page.

Brazil, gold 613
iron ore, exports to 580
manganese ore 666, 674, 687
imports from 666, 673
pig iron, exports to 595
platinum 15–16
quicksilver, exports to 382
silver 615
Briquets (fuel) 20a
British East Indies, gold 613
manganese ore, imports from 673
pig iron, imports from 594
quicksilver, exports to 382
British Guiana, bauxite 3
gold 613
quicksilver, exports to 382
silver 615
British Honduras, arsenic 26
British India, gold 613
silver 615
British Protected Malay States, tin 69
British South Africa, chromic iron ore 42
quicksilver, exports to 382
tungsten ore, imports from 934
Bromine, summary 20a
Brown iron ore 560–562
Buffalo, N. Y., receipts of Lake Superior iron ore 573
stocks of iron ore 575
Burchard, Ernest F., paper on iron ore, pig iron, and steel 557–603
Bureau of the Mint 606, 607
Burma, tungsten 19a, 36a, 947
Burrstones and millstones, summary 36a
Butler, B. S., paper on copper 723–796
on silver, copper, lead, and zinc in Central States (Michigan) (mines report) 92–100

C.

Cadmium, by C. E. Siebenthal 49–53
alloys 51
bibliography 53
exports 52
imports 52
introduction 49
prices 50, 52–53
production 49–50
in Germany 50
salts of 51
sources 50
summary 18a
uses 51
value 53
Calcium chloride, summary 20a
California, antimony 657, 658
chromic iron ore 38
copper 208, 725, 738–740, 742, 758–761
ferroalloys 598
gold 208, 605, 619, 623, 634, 642, 646
gold, silver, copper, lead, and zinc (mines report), by C. G. Yale 18a, 203–239
iron ore 560–561, 567, 568
lead 208, 883, 888
magnesium 149, 151
manganese ore 669–671, 683

Page.

California, molybdenum 911–912
pig iron 586–587, 588
platinum 13, 17–19
quicksilver 370, 372, 373, 378, 385, 400–401, 405–414
silver 208, 605, 619, 623, 639, 642, 646
tungsten 932–933, 938–940
mills 945
value of mineral products 46a, 50a
zinc 208, 862–863, 864
Canada, antimony 659
arsenic 26, 27
chromic iron ore 42
cobalt 905
copper 726, 785–788
exports to 780
imports from 779
gold 613
iron ore 583
exports to 580
imports from 579
lead 883, 893
magnesium 149, 151
manganese ore 674
imports from 673
nickel 917–919, 921–922, 923
imports from 923
pig iron 595
exports to 595
imports from 594
platinum 13, 14, 15, 20
quicksilver 400
exports to 382
rutile 930
silver 615
tin 63
zinc, electrolytic plants 865
ore, imports from 872–873
Cape Colony, manganese ore 674
silver 615
Carbonate iron ore 560–562
Cement, summary 20a, 36a, 38a
Central America, gold 613
lead 883
quicksilver 403
exports to 382
silver 615
Central States, mine production 18a, 77
Charcoal pig iron, production 593
Chattanooga district, iron ore 562
Chile, antimony 659
bismuth 31
copper 726, 789–792
imports from 779
gold 613
iron ore 583
exports to 580
imports from 579
manganese ore 674
imports from 673
pig iron, exports to 595
platinum 15
quicksilver, exports to 382
silver 615
tungsten ore 934
China, antimony 659, 661

Digitized by Google

Page.

China, gold ... 613
iron ore ... 583
manganese ore ... 686
pig iron, imports from ... 594
platinum ... 15
quicksilver ... 382, 398
silver ... 615
tin ... 66, 69
tungsten ore ... 934, 947
zinc ... 873
Chosen (Korea), gold ... 613
iron ore, production of ... 583
quicksilver, exports to ... 382
silver ... 615
Chromite, by J. S. Diller ... 37–47
composition and uses ... 37
consumption, needs for ... 42
ferrochromium ... 597–599
foreign sources ... 42–43
imports ... 35a, 42, 599
occurrence in North America ... 39
map of North America showing known deposits ... 39
ore ... 40–41, 44–47
concentration of ... 41
grade of domestic ... 40
owners of domestic deposits ... 44–47
prices ... 39–40, 42
production ... 38, 43
recommendations ... 43
salts ... 42
summary ... 18a, 35a
supplies ... 37–38
uses ... 37
Clark, M. B., Summary of mineral production ... 27a–76a
(*See also* Mineral production of the United States.)
Clay, summary ... 20a, 36a, 38a
Clay products, summary ... 36a
Cleveland, Ohio, receipts of iron ore ... 573
stocks of iron ore ... 575
Coal, briquets, summary ... 20a
bunker ... 38a
summary ... 20a, 36a, 38a
Cobalt, by Frank L. Hess ... 899–906
bibliography (patents) ... 905–906
consumption ... 904
general conditions ... 899
imports ... 35a, 904
mining operations ... 899–901
Haynes Stellite Co ... 899–901
Missouri Cobalt Co ... 901
prices ... 904
production ... 899, 901
Canadian ... 905
stellite ... 899–904
analyses ... 903
uses ... 901–904
substitute for platinum ... 904
summary ... 35a
Coke, summary ... 20a, 37a, 38a
pig iron ... 593
Colombia, antimony ... 659
gold ... 613

Page.

Colombia, platinum ... 13, 14, 15, 17, 20
quicksilver, exports to ... 382
silver ... 615
Colorado, copper ... 725, 738–740, 742, 761, 798
ferroalloys ... 598
gold ... 605, 619, 623, 634, 642, 646, 798
gold, silver, copper, lead, and zinc (mines report), by C. W. Henderson ... 18a, 797–853
iron ore ... 560–561, 568
lead ... 798, 883, 888
manganese ore ... 669–671, 683
manganiferous iron ore ... 669–671
silver ore ... 675
molybdenum ... 907, 912
pig iron ... 586–587, 588
quicksilver ... 385
radium ... 955
silver ... 605, 619, 624, 639, 642, 646, 798
tungsten ... 932–933, 941–943
mills ... 945
uranium ... 955
value of mineral products ... 46a, 51a
vanadium ... 955
zinc ... 798, 862–863, 864, 866
Conneaut, Ohio, Lake Superior iron ore, receipts ... 573
stocks of iron ore ... 575
Connecticut, iron ore ... 560–561, 568, 585
pig iron ... 586–587, 588
tungsten ... 932
value of mineral products ... 46a, 52a
Copper, by B. S. Butler ... 723–796
casting copper ... 724, 775, 778
condition of industry ... 726
domestic ... 730
consumption ... 724, 726–730, 781–782
costs ... 785
electrolytic copper ... 724, 776, 778
exports ... 35a, 724, 730, 780–781
by countries ... 781
foreign production, review of ... 785–796
imports ... 35a, 724, 730, 779–780
by countries ... 779
introduction ... 723
labor efficiency ... 732–735
Lake copper ... 724, 776, 778
mine production ... 18a, 55, 77, 132, 136, 154, 161, 167, 208, 245, 253, 331, 457, 493, 509, 697, 721, 732–734, 741, 798
mines according to labor efficiency ... 733
ore ... 724
copper-bearing ... 742–746
gold in ... 742, 744
percentage of copper, by States ... 742
quantity, by States ... 742–745
silver in ... 742, 744
yield ... 724, 742, 744, 745
pig copper ... 775–776, 778
prices ... 724
average yearly ... 730, 731, 732
at New York in 1917 ... 783–784
1850–1917 ... 79a
production ... 724, 730, 732
by countries ... 726
from 1845 to 1917 ... 735, 740
by principal districts ... 741

Digitized by Google

Page.
Copper, production, by States..... 725, 739–742
production, total by States..... 740
costs..... 785
mine..... 724, 732–734, 741
mine returns..... 737–738
quantity of ore..... 724, 742
quantity and yield of ores..... 724, 742
refinery..... 724, 738, 775–776
refined copper, total..... 730, 778
review, by States..... 746–775
secondary..... 312–317, 730, 776–777, 778
smelter..... 724, 730, 735–737
smelter returns..... 738
smelting plants..... 736
sulphate..... 779
reduction plants in 1917..... 736–737
review of foreign production..... 785–796
stocks..... 779
summary..... 18a, 35a
of statistics..... 724
uses..... 782–783
value..... 724
in gold and silver, per ton..... 742, 744
world's production..... 724–730
Copper-lead and copper-zinc ores..... 743–744
Cornwall, tin..... 69
Corundum and emery, summary..... 37a
Costa Rica, manganese ore..... 674, 689
imports from..... 673
pig iron, exports to..... 595
quicksilver, exports to..... 382
Crucible steel..... 601
Cryolite, summary..... 20a, 37a
Crystal Falls area, iron ore..... 578
Cuba, chromic iron ore..... 42
copper..... 726, 788–789
imports from..... 779
gold..... 613
iron ore..... 581, 582, 583
imports from..... 579
manganese ore..... 674, 689
imports from..... 673
pig iron, exports to..... 595
imports from..... 594
quicksilver, exports to..... 382
Cuyuna range, iron ore..... 571–572, 578
manganiferous iron ores..... 675
Cyanides, consumption of..... 648–651

D.

Delaware, value of mineral products..... 46a, 52a
Denmark, pig iron, exports to..... 595
Detroit, Mich., receipts of iron ore..... 573
Diatomaceous (infusorial) earth, summary... 37a
Director of the Mint..... 606, 607
Diller, J. S., paper on chromite..... 37–47
District of Columbia, value of mineral products..... 46a, 52a
Dominican Republic, quicksilver, exports to. 382
Duluth, shipments of iron ore..... 573
Dunlop, J. P., paper on silver, copper, lead, and zinc in the Central States (mines reports)..... 73–92, 100–130
on gold and silver (general report)..... 605–651
on secondary metals..... 299–330
Dutch East Indies, gold..... 613
Page.
Dutch East Indies, platinum..... 15
quicksilver, exports to..... 382
silver..... 615
tin..... 66
Dutch Guiana, bauxite..... 3
cadmium..... 52
gold..... 613

E.

East Indies, quicksilver..... 398
East Jordan, Mich., iron-ore receipts..... 574
Eastern States, mine production..... 55
Economic limits to domestic independence in minerals, by George Otis Smith.. 1a–6a
Ecuador, gold..... 613
quicksilver, exports to..... 382
silver..... 615
tungsten ore..... 934
Egypt, iron-ore imports from..... 579
silver..... 615
Electric steel..... 600, 601
Elk Rapids, Mich., iron-ore receipts..... 574
Emery, summary..... 37a
England, antimony..... 659
arsenic..... 26
bismuth..... 31
cadmium..... 50
chromite..... 42
copper..... 726, 780
iron ore, exports to..... 580
pig iron, exports to..... 595
imports from..... 594
platinum..... 15
quicksilver, exports to..... 382
tin..... 66
Erie, Pa., receipts of Lake Superior iron ore. 573
stocks of iron ore..... 575
Escanaba, shipments of iron ore..... 573
Evans, I. P., bibliography of quicksilver. 425–455
Exports, aluminum..... 35a, 6
abrasives..... 38a
antimony..... 661
asbestos..... 38a
asphalt..... 37a
bauxite..... 35a, 1
brass, old..... 35a
cadmium..... 52
cement..... 38a
clay..... 38a
coal..... 38a
coke..... 38a
copper..... 35a, 780–781
ferromanganese..... 36a
ferrosilicon..... 36a
ferrotungsten..... 36a
ferrovanadium..... 36a
fertilizers..... 38a
gasoline..... 38a
gold..... 610
graphite..... 38a
iron ore..... 36a, 570, 580–581
lead..... 36a, 894–895
lime..... 38a
magnesium..... 148

Digitized by Google

Page.

Exports, marble and stone 39a
mica 38a
nickel 36a, 923
paints 38a
paraffin 38a
petroleum 38a
phosphate, crude 38a
pig iron 36a, 595
plaster 38a
platinum 36a
potash 38a
quicksilver 36a, 381–382
salt 38a
sand and gravel 38a
silver 610
slate 39a
soda 38a
steel 603
sulphur 39a
tin 36a
tungsten 36a, 934
zinc 30a, 873–875
foreign 875–876
oxide 874

F.

Fairport, Ohio, receipts of Lake Superior iron ore 573
stocks of iron ore 575
Federated Malay States, gold 613
tin 66, 69
Feldspar, summary 20a
Ferroalloys 596–599
exports 36a
imports 35a, 599
manufactures of, by States 598
prices 597, 598
shipments and value 596–597
summary 35a–36a
Ferrocerium 597
Ferrochromium 597–599
imports 599
summary 35a
Ferromanganese 591, 597
(*See also* Manganese ore.)
imports 35a, 599
plants making ferromanganese 679
prices 598
production 597
summary 35a, 36a
Ferromolybdenum 597–598
imports 599
Ferrophosphorus 597–599
imports 599
summary 35a
Ferrosilicon 591, 597–599
imports 599
summary 35a, 36a
Ferrotitanium 597–599
imports 599
summary 35a
Ferrotungsten 597–599
imports 599
summary 35a, 36a
Ferrouranium 597

Page.

Ferrovanadium 597
summary 36a
Fertilizers, summary 37a, 38a
Finland, gold 613
Flint pebbles, summary 20a, 37a
Florida, cooperation 25a
ilmenite 929
value of mineral products 46a, 53a
Fluorspar, summary 20a, 37a
Forge and foundry iron, production 591
Formosa, gold 613
silver 615
France, antimony 663
arsenic 26
bauxite 3
cadmium 52
copper, exports to 780
gold 613
iron ore 583
manganese ore 674
imports from 673
pig iron 595
exports to 595
imports from 594
platinum 15
quicksilver 395
exports to 382
silver 615
zinc 873
French Africa, iron ore 579, 583
zinc ore 873
French East Africa, silver 615
French East Indies, zinc 873
French Guiana, gold 613
quicksilver, exports to 382
French Indo-China, gold 613
silver 615
French Oceania, chromite 42
iron ore, imports from 579
nickel, imports from 923
Fuller's earth, summary 37a

G.

Garnet (abrasive), summary 20a
Gary, Ind., iron-ore receipts 574
Gas (artificial) and by-products 20a
Gas (natural) 20a
Gasoline, summary 37a, 38a
Gems and precious stones, summary 20a, 37a
Georgia, bauxite 1, 3–5
cooperation 25a
copper 56, 58, 725, 738, 742, 775
gold 56, 58, 605, 619, 627, 642, 646
gold, silver, copper, lead, and zinc (mines report) 57–58
iron ore 560–561, 567, 568, 585
manganese ore 669–671
pig iron 586–587
silver 56, 58, 605, 619, 639, 642, 646
value of mineral products 46a, 53a
German Southwest Africa, tin 69
Germany, arsenic 26
cadmium 50
imports from 50
copper 726, 793

Digitized by Google

Page.
Germany, copper, exports to 780
copper, imports from 779
gold 613
iron ore 583
imports 579
lead, imports from 893
manganese ore 674
imports from 673
nickel 921
pig iron 595
exports to 595
imports from 594
quicksilver 395
silver 615
tin 69
Gerry, C. N., paper on gold, silver, copper, lead, and zinc in Idaho (mines report) 457–492
in Washington (mines report) 493–507
Glass sand, summary 21a, 32a
Gogebic range, iron ore 571–572, 578
Gold and silver, paper by H. D. McCaskey and John P. Dunlop 605–651
acknowledgments 605
copper ores 632, 634, 638, 639, 640, 641
copper-lead ores 634, 639, 641
curves showing production and value of gold and silver and price per fine ounce of silver in the United States, 1871–1917 609
Director of the Mint 606, 607
distribution, by States and sources, of production of gold in 1917 633–639
production of silver in 1917 639–642
by methods of treatment 642–645
percentage of output by processes. 645
consumption of cyanides 648–651
of quicksilver 648
domestic supply of gold and silver 610
dry and siliceous ores 632, 634, 636, 638, 639, 640, 641
exports 610
gold and silver in the war 616–617
imports 610
increase and decrease, by States 606, 619
larger producers of gold 620
of silver 621
lead ores 632, 634, 639, 641
lead-zinc ores 632, 634, 639, 641
mines report 18a, 618–651
comparison of mint report and mines report 618–619
consumption of cyanides and quicksilver 648–651
method of collecting statistics 618–619
mine production of gold and silver 55, 132, 154, 161, 167, 208, 245, 253, 331, 457, 493, 509, 619, 697, 721, 798
number of producing mines 629–631
by States and Territories 621–629
ore, production, classification, and average value of 631–633
quantity of 637–638
placers 634, 640, 641, 645
dredges 635–636
Page.
Gold and silver, prices of silver 607
prices of silver, 1850–1917 ..... 79a
production, by States, in 1917 ..... 605, 619
at mills 645–648
since 1792 607
since 1880 608
summary 30a
units of measurement 619
value, average per ton of ore 632
world's production of gold 611–614
decline in 611
value 611, 613
of silver, 1860–1917 614
by countries, 1905–1917 615
zinc ores 632, 634, 639, 641
Gold, silver, copper, lead, and zinc in Eastern States (mines report), by J. M. Hill 18a, 55–62
mine production 55–57
review by States 57–62
Alabama 517
Georgia 57–58
Maine 58
Maryland 58
New Hampshire 58
New Jersey 59
New York 59
North Carolina 59–60
Pennsylvania 60
South Carolina 60
Tennessee 60–61
Vermont 61
Virginia 61–62
Gold, silver, copper, lead, and zinc in Western States (mines reports):
Alaska, by G. C. Martin 18a, 131–145
Arizona, by V. C. Heikes 18a, 509–556
California, by C. G. Yale 18a, 203–241
Colorado, by C. W. Henderson 18a, 797–853
Idaho, by C. N. Gerry 18a, 457–492
Montana, by V. C. Heikes 18a, 331–366
Nevada, by V. C. Heikes 18a, 253–298
New Mexico, by C. W. Henderson. 18a, 697–720
Oregon, by C. G. Yale 18a, 243–252
South Dakota, by C. W. Henderson 18a, 153–160
Texas, by C. W. Henderson 18a, 721–722
Utah, by V. C. Heikes 19a, 167–202
Washington, by C. N. Gerry 19a, 493–507
Wyoming, by C. W. Henderson 19a, 161–165
Gold Coast, manganese ore 674, 686
Granite, summary 37a
Graphite, summary 20a, 37a, 38a
Great Britain, antimony 659
arsenic 26
bauxite 3
bismuth 31
chromic iron ore 42
copper exports to 780
imports from 779
gold 613
iron ore 583
exports to 580
imports from 579
lead, imports from 893

Digitized by Google

Great Britain—Continued. Page.
pig iron 595
platinum 15
quicksilver, exports to 382
silver 615
Greece, chromic iron ore 42
iron ore 583
imports from 579
manganese ore 674
imports from 673
nickel 921
pig iron, exports to 595
silver 615
Grindstones, summary 37a, 39a
Guatemala, quicksilver, exports to 382
chromic iron ore 42
Guiana, bauxite 3
gold 613
silver 615
Gypsum, summary 21a, 37a

H.

Haynes Stellite Co. 899, 901–904
Heikes, V. C., gold, silver, copper, lead, and zinc in Arizona (mines report). 509–556
Montana (mines report) 331–366
Nevada (mines report) 253–298
Utah (mines report) 167–202
Hematite 560–562
Henderson, Charles W., gold, silver, copper, lead, and zinc in Colorado (mines report) 797–853
New Mexico (mines report) 697–720
South Dakota (mines report) 153–160
Texas (mines report) 721–722
Wyoming (mines report) 161–165
Herzegovina, manganese ore 674
Hess, Frank L., paper on cobalt 899–906
molybdenum 907–915
nickel 917–927
radium, uranium, and vanadium 955–959
titanium 929–930
tungsten 931–954
Hewett, D. F., paper on manganese and manganiferous ores 665–696
High-alumina refractories 9
Hill, J. M., paper on bauxite and aluminum 1–9
gold, silver, copper, lead, and zinc in Eastern States (mines reports) 55–62
platinum and allied metals 11–21
Honduras, antimony 659
manganese ore 690
quicksilver, exports to 382
Hones, oilstones, summary 37a
Hongkong, antimony 659
pig iron, imports from 594
quicksilver, exports to 382
tin 66
tungsten ore 934
zinc 873
Hungary, iron ore 583
manganese ore 674
quicksilver 372, 396
Huron, Ohio, receipts of iron ore 573
stocks of iron ore 575

I.

Ichthyol, summary 37a
Idaho, antimony 657
cobalt 899–901
copper 457, 725, 738–740, 742, 761
gold 457, 605, 619, 624, 634, 637, 642, 646
gold, silver, copper, lead, and zinc (mines report), by C. N. Gerry 18a, 457–492
lead 457, 833, 838
quicksilver 370, 372, 373, 385, 401, 414–415
silver 457, 605, 619, 624, 639, 642, 646
tungsten 932, 943
mills 945
value of mineral products 46a, 54a
zinc 457, 862–863, 864
Illinois, cooperation 25a
ferroalloys 598
lead 77, 83, 883, 888
pig iron 586–587, 588
silver, copper, lead, and zinc (mines report), by J. P. Dunlop 82–86
silver 77, 83, 605, 619, 625, 639
steel 600
value of mineral products 46a, 54a
zinc 77, 83, 856, 862–863, 864, 866
Ilmenite 73a, 929, 930
Imports, aluminum 35a, 6
salts 35a, 8
antimony 35a, 654, 659–661
salts 35a, 660
arsenic sulphides 36a, 25–26
arsenious oxide 36a
asbestos 36a
asphalt 36a
barium compounds 36a
barytes 36a
bauxite 35a, 1
bismuth 35a, 31
borax 36a
brass, old 35a
burrstones 36a
cadmium 52
cement 36a
cerium 35a
chalk 36a
chromite 35a, 42
chromium salts 35a, 42
clay 36a
clay products 36a
coal 36a
cobalt oxide 35a, 904
coke 37a
copper 35a, 779–780
corundum 37a
cryolite 37a
diatomaceous (infusorial) earth, rotten stone, and tripoli 37a
emery 37a
explosives 37a
ferroalloys 35a, 599
ferrochromium 35a, 599
ferromanganese 35a, 599, 666
ferromolybdenum 599
ferrophosphorus 599

Digitized by Google

Page.
Imports, ferrosilicon 35a, 599
ferrotitanium 35a, 599
ferrotungsten 35a, 599
ferrovanadium 36a
fertilizers 37a
flint pebbles 37a
fluorspar 37a
fuller's earth 37a
gasoline 37a
gems and precious stones 37a
gold 610
granite 37a
graphite 37a
grindstones 37a
guano 37a
gypsum 37a
hones, whetstones 37a
ichthyol 37a
iridium 35a, 15
iron ore 35a, 570, 579–580
kainite 37a
kaolin 36a
lead 35a, 892–894
pigments 37a, 894
lime 37a
lithographic stone 37a
magnesia 37a
magnesite 37a
magnesium 148
manganese ore 35a, 666
by countries 673
manure salts 37a
marble and stone 37a
mica 37a
mineral salts 37a
mineral waters 37a
molybdenum 599
monazite and thorium oxide 37a
nickel 35a, 922–923
ocher 37a
oilstones 37a
osmium 35a, 15
osmiridium 35a, 15
ozokerite 37a
palladium 35a, 15
paraffin 37a
peat 37a
petroleum 37a
phosphates 37a
pig iron 594
platinum 35a, 15
potassium chloride 37a
sulphate 37a
pottery 36a
pumice 37a
pyrite 37a
quicksilver 35a, 381, 382
radium salts 35a, 957
rhodium 35a
ruthenium 35a
salt 37a
sand and gravel 37a
selenium 37a
sheep dip 36a
sienna 37a

Page.
Imports, silver 610
slate 37a
sodium nitrate 37a
spiegeleisen 35a, 599, 666
steel 602
strontium salts 37a
sulphur 37a
talc 37a
thorium nitrate 37a
tin 36a, 66–67
titanium 35a
tungsten 35a, 933, 934
type metal 35a, 660
umber 37a
uranium salts 35a, 957
venetian red 37a
zinc 35a, 869–873
brass, old 35a, 871
dust 35a, 871
ore 35a, 870, 872–873
oxide 37a, 871
India, bauxite 3
gold 613
iron ore 583
mangnese ore 674, 687
imports from 666, 673
silver 615
tin 69
zinc 873
Indiana, cobalt 899, 901–904
pig iron 586–587, 588
steel 600
stellite 899, 901–904
value of mineral products 46a, 55a
zinc smelter 866
Indiana Harbor, Ind., iron-ore receipts 574
Indo-China, gold 613
silver 615
tin 69
zinc 873
Infusorial earth. (*See* Diatomaceous earth.)
International control of minerals, by C. K. Leith 7a–16a
changes brought about by the war 8a–9a
general conclusions as to the international control of minerals from the standpoint of the United States 12a–16a
international control as a war measure 9a
movements of minerals under pre-war conditions 8a
position of the United States 11a–12a
possibility of post-war international control 9a–10a
specific plans of international control 10a
world movement of minerals 7a
Iowa, cooperation 25a
ferroalloys 598
iron ore 560–566, 567, 568, 585
lead 77, 87, 883, 888
pig iron 586
silver, copper, lead, and zinc (mines report), by J. P. Dunlop 86–87
Iowa, value of mineral products 46a, 55a
zinc 77, 87, 869–873, 864

Digitized by Google

Page.
Iridium 35a, 11-12, 14, 15, 16
(*See also* Platinum and allied metals.)
summary 19a, 35a
uses 11-12
Iridosmine 19a, 35a, 11, 14, 15, 16
Iron. (*See* Pig iron and steel.)
Iron ore 35a
Iron ore, pig iron, and steel, by Ernest F. Burchard 557-603
apparent annual consumption compared with production of pig iron 569-570
Baraboo area 571-572
beneficiated ore, statistics 583-585
Bessemer ores, prices 576
Cuba, shipments from 581-582
curve showing production of iron ore, pig iron, and steel, 1870-1917 559
exports 36a, 570, 580-581
foreign trade 579-581
imports, by countries 35a, 570, 579-580
introduction 557
iron-ore industry, Lake Superior district 562, 571-578
beneficiation of ores 583-585
mining developments 576-578
labor conditions 577
wages 577
reserves in Michigan and Minnesota 578
prices 575-576
production by ranges 571-572
ranges 571
shipments, by ports 572-573
1854-1917 574
ore mined and shipped in 1917 558-567
mined by mining districts 562-563
by States 560-561
by varieties 561-563
mined and shipped, by States 558-560
shipments by States 560
increase or decrease 560
percentage of 560
percentage of pig iron to iron ore 570
price per ton, by States and varieties 567-568, 575-576
principal iron-ore mines 564-567
production in principal countries 582-583
total output in the United States, 1810-1817 563
comparative output of iron ore, pig iron, and steel 559
receipts at Lake Erie ports 573
at Lake Michigan ports 574
stocks at Lake Erie ports 570, 575
at mines, by States 567, 570
summary 19a, 35a, 36a
value, by States 560
world's production 583
zinc residuum 570
Iron Ridge area, iron ore 571-572
Iron River area, iron ore 578
Italy, bauxite 3
cadmium 52
copper 726, 793
exports to 780
gold 613
iron ore 583
manganese ore 674
pig iron 595
exports to 595
imports from 594
quicksilver 372, 396-397
silver 615
tin 69
zinc 873

J.

Jamaica, quicksilver, exports to 382
Japan, antimony 659, 662
arsenic 26
chromic iron ore 42
copper 726, 795
imports from 779
gold 613
iron ore 583
manganese ore 674
imports from 673
pig iron, exports to 595
imports from 594
quicksilver 398
exports to 382
silver 615
tin 69
tungsten 934
zinc 873

K.

Kansas, lead 77, 87, 883, 888
silver, copper, lead, and zinc (mines report), by J. P. Dunlop 87-90
value of mineral products 46a, 56a
zinc 77, 87, 856, 862-863, 864, 866
Kaolin, imports, summary 36a
Katanga, copper 796
Kentucky, ferroalloys 598
lead 77, 91, 883, 888
pig iron 586-587, 588
silver, copper, lead, and zinc (mines report), by J. P. Dunlop 90-92
silver 625
value of mineral products 46a, 56a
zinc 77, 91, 862-863
Knopf, Adolph, paper on tin 63-72
Kongo, Belgian, copper 796
silver 615
Korea (Chosen), gold 613
iron ore 583
quicksilver exports to 382
silver 615

L.

Labrador, antimony 659
iron ore, imports from 579
pig iron, imports from 594
Lake Erie ports, iron ore 573, 575
Lake Michigan ports, iron ore 574
Lake Superior, copper 71-80, 667-668, 695, 716
iron ore 562, 571-578
prices 575-576
production by ranges 571
1854-1917 572

Digitized by Google

Page.
Lake Superior, iron ore, ranges..... 571-572
iron ore, shipments and receipts..... 572-574
stocks..... 575
manganiferous iron ore..... 34-36
mining district..... 562, 571-578
Lead, by C. E. Siebenthal..... 881-897
antimonial..... 881, 884-885
consumption..... 881, 895-896
desilverized..... 881, 882, 884
exports, domestic..... 36a, 894-895
foreign..... 895
from foreign ore and base bullion..... 882
imports..... 35a, 893-894
by classes..... 894
by countries..... 893
warehouse transactions..... 891-892
introduction..... 881
mine production..... 18a, 55, 77, 132, 154, 167, 208, 245, 253, 331, 457, 493, 509, 697, 721, 798, 887-889
by districts..... 889
percentage by districts..... 889
mined in 1917, by States and ores..... 888
ore..... 888-889
percentage of lead by ores..... 888
pigments..... 885-886
from ore..... 885-886
from pig lead..... 886
summary..... 37a
prices..... 882, 897
at New York in 1917..... 882
curves, showing weekly price..... 896
1850-1917..... 79a
production..... 882-889
1720-1917..... 882
by States..... 882-883
from domestic ore..... 881, 882
of refined or pig..... 881
of soft lead..... 881, 882, 884
secondary..... 312, 317-319, 881, 886
smelters..... 890-891
changes..... 891
source of lead, by ore and States..... 883
summary..... 19a, 35a, 36a
of statistics..... 881
trade conditions..... 891
type metal, imports..... 35a
value..... 881, 882, 897
warehouse transactions..... 891-892
world's production..... 891
Lead pigments..... 37a, 885-886
Leaded zinc oxide..... 850, 886
Leith, C. K., international control of minerals 7a-16a
Lime, summary..... 21a, 37a, 38a
Litharge..... 886, 894
Lithium minerals, summary..... 21a
Lithopone..... 859
Lorain, Ohio, receipts of iron ore..... 573
stocks of iron ore..... 575
Louisiana, value of mineral products..... 46a, 57a
Low-phosphorus iron, production..... 591
Luxemburg, iron-ore production..... 583

M.

Madagascar, silver..... 615
Magnesite, summary..... 21a, 37a
Page.
Magnesium, paper on, by Ralph W. Stone.. 147-151
character..... 149
demand and supply..... 151
exports..... 148
imports..... 148
prices..... 148
producers..... 148
production..... 147
source..... 149
summary..... 37a
supply raw material..... 151
uses..... 149-151
Magnetite ore..... 560-562
Maine, copper..... 56, 58, 725, 738, 742
gold, silver, copper, lead, and zinc (mines report)..... 56, 58
value of mineral products..... 46a, 57a
Malay States, gold..... 613
tin..... 66, 69
Malleable pig iron..... 591
Manganese and manganiferous ores, by D. F. Hewett..... 665-696
bibliography..... 691-696
ferromanganese..... 591, 597, 666, 678-682
consumption per ton of steel..... 682
imports..... 35a, 599, 666, 681
prices..... 598, 681
ferruginous manganese ores..... 668, 674-675
imports..... 35a, 666
by countries..... 666, 673
introduction..... 665
notes on domestic deposits..... 682-686
foreign deposits..... 686-690
ore..... 666, 667-669
prices..... 676-678
production..... 591, 597, 666, 669-671, 672
by countries..... 674
by States..... 669-671
1838-1917..... 672
1890-1917..... 666
shipments..... 669-671
sources of manganese..... 666
list of principal minerals..... 667
spiegeleisen..... 591, 597, 666, 678-682
consumption per ton of steel..... 682
imports..... 599, 666, 681
prices..... 598, 681
steel..... 666
summary..... 19a, 35a
value of ores..... 669-671, 675-678
world's production..... 673-674
Manganiferous ores..... 668, 674, 678
iron ore..... 668
manganiferous zinc residuum..... 669, 678
production by States..... 675
silver ore..... 675
zinc residuum..... 570, 669, 678
silver ores..... 669, 675
summary..... 19a, 35a
Marble and stone, summary..... 22a, 37a, 39a
Marquette, shipment of iron ore..... 573
Marquette range, iron ore..... 571-572, 578
Martin, G. C., paper on gold, silver, copper, and lead in Alaska (mines report)..... 131-145

Digitized by Google

Page.
Maryland, chromite 38
cooperation 25a
copper 56, 58, 725, 738, 743
ferroalloys 598
gold 56, 619, 627
gold, silver, copper, lead, and zinc (mines report) 56, 58
iron ore 560–561, 567, 568, 585
pig iron 586–587, 588
silver 56, 58, 619, 627
value of mineral products 46a, 58a
Massachusetts, iron ore 560–561, 567, 568, 585
pig iron 586–587, 588
value of mineral products 46a, 58a
McCaskey, H. D., paper (with John P. Dunlop) on gold and silver in United States 605–651
mineral production of the United States in 1917—a summary 17a–76a
prefatory note to the general and mines reports on gold, silver, copper, lead, and zinc in 1917 ..... 77a
Menominee range, iron ore 571–572, 578
Mercury. (*See* Quicksilver.)
Mesabi range, iron ore 571–572, 578
Mexico, antimony 659, 662–663
arsenic 24, 26, 27
copper 726, 788
imports from 779
gold 613
iron ore, exports to 580
lead 883
imports from 893
manganese ore 674
imports 672
molybdenum in ores 907
pig iron, exports to 595
platinum 15
quicksilver 372, 402–403
exports to 382
rutile 930
silver 615
tungsten 934
zinc ore, imports from 872, 873
Mica, summary 21a, 37a, 38a
Michigan, cooperation 25a
copper 77, 93, 725, 738–740, 742, 761–766
iron ore 560–561, 567, 568, 585
magnesium 149
manganese ore 671, 683
pig iron 586–587, 588
silver 77, 93, 605, 619, 625
silver, copper, lead, and zinc (mines report), by B. S. Butler 92–100
value of mineral products 46a, 59a
Millstones and burrstones, summary 36a
Milwaukee, Wis., iron-ore receipts 574
Mineral paints, summary 21a, 37a
Mineral production of the United States in 1917—a summary, by H. D. McCaskey and M. B. Clark 17a–76a
acknowledgments 23a
Mineral production, cooperation with State geological surveys 25a–26a

Page.
Mineral production, etc.—Continued.
curves showing value of the mineral production, 1880–1917 ..... 34a
imports and exports, 1916–17 ..... 35a–39a
increase or decrease 30a
introduction 17a
mineral production, 1880–1917 ..... 33a
mineral products, 1917, in order of value 40a–41a
Mineral Resources volumes, 1908–1917, containing full reviews 18a–22a
organization 23a–25a
production, by States, 1916–17 ..... 40a–76a
of principal metals, fuels, structural materials 42a–43a
rank of States in value of production 44a–45a
scope of report 17a
summary 27a–76a
general remarks 27a–29a
metallic products 30a, 33a
nonmetallic products 30a–32a, 33a
value assigned to production 22a–23a
by States 46a–76a
total 32a, 33a
Mines reports, production of copper 18a, 55, 56, 77, 132, 136, 154, 161, 167, 208, 245, 253, 331, 457, 493, 509, 697, 721, 798
gold 18a, 55, 56, 132, 154, 208, 245, 253, 331, 457, 493, 509, 619, 697, 721, 798
lead 18a, 55, 57, 77, 132, 154, 167, 206, 245, 253, 331, 457, 493, 509, 697, 721, 798, 888
silver 18a, 55, 56, 77, 132, 154, 161, 167, 208, 245, 253, 331, 457, 493, 509, 619, 697, 721, 798
zinc 18a, 55, 57, 77, 167, 208, 253, 331, 457, 493, 509, 697, 721, 798
Mineral waters, summary 21a, 37a
Minnesota, cooperation 25a
iron ore 560–561, 567, 568, 585
reserves 578
manganese ores 669–671, 684
manganiferous ores 670–671
pig iron 586–587, 588
value of mineral products 46a, 59a
Mississippi, value of mineral products 46a, 60a
Missouri, cooperation 25a
cobalt 901
copper 77, 101, 725, 738, 742
gold 605
iron ore 560–561, 567, 568, 585
lead 77, 104, 883, 888
manganese ore 684
nickel 901, 920
pig iron 586–587, 588
silver 77, 101, 605, 619, 625
silver, copper, lead, and zinc (mines report), by J. P. Dunlop 100–118
tungsten 932
mills 945
value of mineral products 46a, 60a
zinc 77, 104, 862–863, 864, 867
Molybdenum, by Frank L. Hess 907–915
concentration and reduction 915
disposition 914
industry by States 908–914

Digitized by Google

Page.
Molybdenum, imports 599
introduction 907
minerals and ores 907
prices 908
production 908
uses 914–915
Monazite and zircon, summary 21a, 22a, 37a
Montana, arsenic 24
copper 331, 725, 738–740, 742, 763–766
gold 331, 605, 619, 625, 634, 637, 642, 646
gold, silver, copper, lead, and zinc (mines report), by V. C. Heikes 18a, 331–366
iron ore 560–561, 568
lead 331, 883, 888
manganese ore 670–671, 684
molybdenum 913
quicksilver 385, 402, 415
silver 331, 605, 619, 625, 639, 642, 646
tungsten 932, 943
mills 945
value of mineral products 46a, 61a
zinc 331, 862–863, 864
Morocco, iron ore 583
Mottled pig iron 591

N.

Natal, silver 615
Natural gas, summary 21a
Nebraska, value of mineral products 46a, 61a
Netherlands, copper, exports to 780
manganese ore, imports from 673
pig iron, exports to 595
imports from 594
platinum 15
quicksilver, exports to 382
Nevada, antimony 657
copper 253, 725, 738–740, 742, 766–769
gold 253, 605, 619, 626, 634, 637, 642, 646
gold, silver, copper, lead, and zinc (mines report), by V. C. Heikes 18a, 253–298
iron ore 560–561, 568
lead 253, 883, 888
manganese ore 669–671, 684
manganiferous ore 675
molybdenum 913
platinum 20
quicksilver 370, 372, 373, 385, 401, 415–418
silver 253, 605, 619, 626, 639, 642, 646
tin 64–65
tungsten ore 932–933, 943–944
mills 946
value of mineral products 46a, 62a
vanadium ore 956
zinc 253, 862–863, 864
New Caledonia, chromic iron ore 42
nickel 917, 920, 921, 923
quicksilver 399
Newfoundland, antimony 659
copper 726
iron ore 583
imports from 579
pig iron, imports from 594
quicksilver, exports to 382
New Hampshire, gold, silver, copper, lead, and zinc in Eastern States (mines report) 56, 58

Page.
New Hampshire, lead 57, 58, 883, 888
silver 56, 605, 619, 625, 639
tungsten ore 944
value of mineral products 46a, 62a
zinc 57, 58, 862–863
New Jersey, antimony, smelters 658
cooperation 25a
copper 725, 738
ferroalloys 598
gold, silver, copper, lead, and zinc (mines report) 57, 59
iron ore 560–561, 567, 568, 585
district 562
pig iron 586–587, 588
steel 600
value of mineral products 46a, 63a
zinc 57, 59, 862–863, 864, 867
residuum 570
New Mexico, copper 697, 725, 738–740, 742, 769–770
gold 605, 619, 626, 634, 642, 646, 697
gold, silver, copper, lead, and zinc (mines report), by C. W. Henderson 18a, 697–720
iron ore 560–561, 567, 568, 585
lead 697, 883, 888
manganese ore 670–671, 685
manganiferous ore 674
quicksilver 385
silver 605, 619, 626, 639, 642, 646, 697
tungsten 932, 944
value of mineral products 46a, 63a
zinc 697, 862–863, 864
New South Wales, platinum 13, 14
New York, aluminum 7
cooperation 25a
ferroalloys 598
gold, silver, copper, lead, and zinc (mines report) 57, 59
iron ore 560–561, 567, 568, 585
district 562
titaniferous 929
pig iron 586–587, 588
steel 600
value of mineral products 46a, 64a
zinc 57, 59, 862–863, 864, 867
New Zealand, manganese ore 690
pig iron, exports to 595
quicksilver 399
exports to 382
Nicaragua, quicksilver, exports to 382
Nickel, by Frank L. Hess 917–927
Canada 917–919, 921
consumption and control 921–922
exports 36a, 923
geographic distribution 920–921
imports 35a, 922–923
modes of occurrence 920
prices 922
production 917
publications 923–927
recovery 920
secondary 312, 329–330
summary 19a, 35a, 36a
Nickel, world's production 921
Nigeria, tin

Digitized by Google

Page.

North Carolina, aluminum 7
chromite 38
cooperation 25a
copper 56, 59, 725, 738, 742
gold 56, 59, 605, 619, 627, 634
gold, silver, copper, lead, and zinc (mines report) 56, 59–60
iron ore 560–561, 567, 568, 585
lead 57, 59, 883, 888
manganese ore 671
silver 56, 59, 605, 619, 639
tin 65
value of mineral products 46a, 65a
North Dakota, value of mineral products 46a, 65a
Norway, copper 726, 793
gold 613
iron ore 583
imports from 579
nickel 921
pig iron, exports to 595
imports from 594
quicksilver, exports to 382
rutile 930
silver 615

O.

Ocher, summary 37a
Ohio, ferroalloys 598
iron ore 560, 567, 568
pig iron 586–587, 588
steel 600
value of mineral products 46a, 66a
Oilstones and whetstones, summary 21a, 37a
Oklahoma, lead 77, 118, 883, 888
silver, copper, lead, and zinc (mines report), by J. P. Dunlop 118–125
silver 606, 625
value of mineral products 46a, 67a
zinc 77, 118, 856, 862–863, 864, 867
Ontario, cobalt 905
nickel 917, 920, 923
Open-hearth steel 600, 601
Orange mineral 886, 894
Oregon, chromite 38
cooperation 25a
copper 245, 725, 738–740, 743, 775
ferroalloys 598
gold 245, 605, 619, 626, 634, 642, 646
gold, silver, copper, lead, and zinc (mines report), by C. G. Yale 18a, 243–252
lead 245, 883
molybdenum 913
platinum 13, 17–19, 21
quicksilver 370, 372, 373, 385, 400, 418–421
silver 245, 605, 619, 627, 639, 642, 646
tungsten 932, 944
value of mineral products 46a, 67a
Osmium, imports 35a, 15
summary 19a, 35a
uses 12
Osmiridium, imports 35a, 15
production 14
summary 19a, 37a
Ozokerite, summary 37a

P.

Page.

Palladium 12, 14, 15, 16
(*See* Platinum and allied metals.)
summary 19a, 35a
Panama, manganese ore 674
imports from 673
pig iron, exports to 595
platinum 15
quicksilver, exports to 382
tungsten ore, imports 934
Paraffin, summary 37a, 38a
Paris green 25
Peat, summary 21a, 37a
Pennsylvania, cooperation 25a
copper 56, 60, 725, 738, 743
ferroalloys 598
gold 625
gold, silver, copper, lead, and zinc (mines report) 56, 60
iron ore 560–561, 567, 568, 585
lead 883
manganese ore 670
pig iron 586–587, 588
silver 605, 619, 625
steel 600
value of mineral products 46a, 68a
zinc 856, 867
Peru, antimony 659
copper 726, 792
imports from 779
gold 613
pig iron, exports to 595
quicksilver, exports to 382, 403
silver 615
tungsten 934
vanadium 956
Petroleum, summary 21a, 37a, 38a
Philippine Islands, gold and silver 605, 619, 629
iron ore 583
quicksilver, exports to 382
Phosphate rock, summary 21a, 37a, 38a
Pig iron and steel 586–603
(*See also* Iron ore, pig iron, and steel.)
blast furnaces 590–591
curve showing prices of basic pig iron 589
curve showing production of coke and anthracite pig iron, by months 592
exports 36a, 594–595
ferroalloys, shipments and value 596–598
imports 35a, 599
manufacture of, by States 598
(*See also* Ferroalloys.)
imports 594
percentage of pig iron to iron ore 570
prices 587–590
production, by States 586–587
according to fuel used 593
by grades 591
1889–1917 570
monthly 591
total 593
shipments, by States 587
increase or decrease 587
percentage of change 587
value 587
world's production 595

Digitized by Google

Page.

Pig iron and steel, steel, production..... 599–601
steel, Bessemer ingots and castings.... 600, 601
crucible..... 601
electric..... 600–601
exports..... 603
foreign trade..... 602–603
imports..... 602
open-hearth ingots and castings.... 600, 601
total..... 601
summary..... 19a, 35a, 36a
Pigments, lead..... 37a, 38a, 885–886
Platinum and allied metals, by J. M. Hill... 11–21
allied metals..... 11–12
imports..... 35a, 36a, 15
market..... 16–17
notes on platinum deposits..... 17–21
Alaska..... 13, 19
Borneo..... 13, 14, 15
California..... 13, 17–19
Canada..... 13, 14, 15, 20
Colombia..... 13, 14, 15, 17, 20
general conditions in United States..... 17–19
mining..... 18–19
Nevada..... 20
New South Wales..... 13, 14
Oregon..... 13, 17–19, 20
Russia..... 13, 14, 17, 21
Tasmania..... 13, 14
Washington..... 13, 20
Wyoming..... 20
prices..... 16, 17
production, domestic, crude..... 13
refined..... 14
secondary..... 14
total..... 13
substitute for..... 904
composition..... 904
summary..... 19a, 35a, 36a
supply..... 12–13
uses..... 11–12
world's production..... 12–13, 14
Port Colborne, Canada, receipts of iron ore... 573
Porto Rico, gold and silver..... 605, 619
manganese ore..... 674, 690
manganese ore, imports from..... 623
Portugal, antimony..... 659
copper..... 792
gold..... 613
iron ore..... 583
manganese ore, imports from..... 673
quicksilver..... 395
silver..... 615
tin..... 69
tungsten..... 934
Portuguese Africa, antimony..... 659
chromic iron ore..... 42
quicksilver, exports to..... 382
silver..... 615
Potassium salts, summary..... 21a, 37a, 38a
Prefatory note, by H. D. McCaskey..... 77a–79a
Prices, aluminum..... 6
salts..... 8, 9
antimony..... 654, 661
arsenic..... 26–27
bauxite..... 3

Page.

Prices, bismuth..... 29
cadmium..... 50, 52–53
chromite..... 39
salts..... 42
cobalt..... 904
copper..... 724, 783–784
ferroalloys..... 597, 598
ferromanganese..... 598, 681
iridium..... 16
iridosmine..... 16
iron ore..... 567–568, 575–576
Lake Superior..... 575–576
lead..... 882, 896, 897
magnesium..... 148
manganese ore..... 676–678, 681
manganiferous ore..... 678
manganiferous zinc residuum..... 678
molybdenum..... 908
nickel..... 922
palladium..... 16
pig iron..... 587–590
platinum..... 16, 17
quicksilver..... 371, 377, 379–381
radium..... 957
selenium..... 33
silver..... 607
1850–1917..... 79a
spiegeleisen..... 598
tellurium..... 35
tin..... 67–68
tungsten..... 934, 935
uranium..... 957
vanadium..... 957
zinc..... 878–879
1850–1917..... 79a
dust..... 878
Principal iron-ore mines..... 564–567
Pumice, summary..... 37a
Pyrite, summary..... 21a, 37a

Q.

Quartz, summary..... 32a
Queensland, iron ore..... 583
Quicksilver, by F. L. Ransome..... 367–455
bibliography of quicksilver in North America, compiled by Isabel P. Evans..... 425–455
index to bibliography..... 426–432
select bibliography..... 432–455
serials examined..... 425–426
consumption of quicksilver in gold and silver mining..... 385–386, 648–651
costs..... 376–378
general geographic and geologic relations of quicksilver deposits..... 386–389
in the world as a whole..... 386–387
map showing location of productive quicksilver deposits..... 386
in the United States..... 387–389
map showing location of known deposits of the United States.. 388
imports and exports..... 381–382
introduction..... 367–368
methods of treatment of ore..... 373–376

Digitized by Google

Quicksilver—Continued. Page.
mineralogy of quicksilver ores..... 390-393
general character of ores..... 390
minerals containing mercury..... 390-393
tenor..... 393
prices..... 371, 377, 379-381
diagram showing variations of monthly average market, quotations at San Francisco, 1913-1917..... 377
diagram showing prices in London, New York, and San Francisco in 1917..... 380
production..... 369-372
domestic production..... 369-371
by States..... 370
diagram showing quantity and value of quicksilver produced in the United States, 1850-1917. 369
quantity and tenor of ore treated..... 372-373
quicksilver-mining industry by States. 404-424
Alaska..... 404
Arizona..... 404-405
California..... 405-414
Idaho..... 414-415
Montana..... 415
Nevada..... 415-418
Oregon..... 418-421
Texas..... 421-424
Utah..... 424
Washington..... 424
review of quicksilver deposits of the world..... 394-404
Africa..... 399
Asia..... 397-398
Turkey..... 397-398
Russia..... 397
China..... 398
Japan..... 398
East Indies..... 398
Europe..... 394-397
Spain..... 394-395
Portugal..... 395
France..... 395
Germany..... 395
Austria-Hungary..... 395-396
Italy..... 396-397
Russia..... 397
Serbia..... 397
North America..... 399-403
Alaska..... 399-400
Canada..... 400
Washington..... 400
Oregon..... 400
California..... 400-401
Nevada..... 401
Idaho..... 401
Montana..... 402
Utah..... 402
Arizona..... 402
Texas..... 402
Mexico..... 402-403
Central America..... 403
Oceania..... 399
Australia..... 399
New Zealand..... 399
New Caledonia..... 399
South America..... 403-404

Quicksilver—Continued. Page.
statistical summary..... 367
summary..... 19a, 35a, 36a
uses..... 383-385
value..... 370-371
world's production..... 371-372

R.

Radium, uranium, and vanadium, by Frank L. Hess..... 955-959
exports..... 957
imports..... 35a, 957
prices..... 957
production..... 955-956
publications..... 958-959
summary..... 19a, 35a, 36a
uses, demand, and trade..... 956-957
Ransome, F. L., paper on quicksilver..... 367-455
Red lead..... 21a, 37a, 38a, 886, 894
Rhode Island, value of mineral products... 46a, 69a
Rhodesia, copper..... 726
silver..... 615
Rhodium, imports..... 35a
summary..... 19a, 35a
uses..... 12
Rottenstone, summary..... 37a
Russia, copper..... 726, 794
exports to..... 786
gold..... 613
iron ore..... 583
manganese ore..... 674, 687
imports from..... 666, 673
pig iron..... 595
exports to..... 595
platinum..... 13, 14, 17, 21
quicksilver..... 372, 397, 398
exports to..... 382
silver..... 615
Ruthenium, summary..... 35a
Rutile..... 929-930
summary..... 35a, 73a
(*See also* Titanium.)

S.

Salt, summary..... 21a, 37a, 38a
Salvador, quicksilver, exports to..... 382
Sand and gravel, summary..... 21a, 37a, 38a
Sand-lime brick, summary..... 32a
Sandusky, Ohio, stocks of iron ore..... 575
Santo Domingo (Dominican Republic), quicksilver exports to..... 382
Scotland, aluminum..... 7
Secondary metals, by J. P. Dunlop..... 299-330
aluminum..... 6-7, 312, 327-329
antimony..... 312, 320
brass, remelted..... 312
copper..... 312-317, 730
introduction..... 299-312
classification for old metals..... 307-309
industry in 1917..... 309-311
metals recovered..... 312
recovery of waste material..... 299-305
Army reclamation division..... 300
economics by Navy Department. 301
need of conserving waste..... 299
scrap-iron dealers..... 302
sources of information..... 304
scope of report..... 299
warring on waste, by W. C. Hirsch. 305-307

Digitized by Google

Page.
Secondary metals, lead 312, 317–319
nickel 312, 329–330
platinum 14
recovery of metals 312
summary 19a
tin 312, 320–327
value 312
zinc 312, 319–320
Selenium, by J. B. Umpleby 33
prices 33
production 33
summary 19a, 37a
uses 33
Serbia, copper 726, 793
gold 613
quicksilver 397
silver 615
Siam, gold 613
tin 69
tungsten 934
Siebenthal, C. E., paper on cadmium 49–53
on lead 881–897
on zinc 855–879
Siberia, gold 613
Sienna and umber, summary 37a
Silica, summary 32a
Silver 30a
(*See also* Gold and silver.)
mine production 18a, 55, 77, 132, 154, 161, 167, 208, 245, 253, 331, 457, 493, 509, 619, 697, 721, 798
production 605, 619, 645–648
summary 30a
Silver, copper, lead, and zinc in the Central States (mines reports), by B. S. Butler and J. P. Dunlop 73–130
introduction, by J. P. Dunlop 73–74
lead and zinc, production, by regions 77–79
production 75–77
publications 129–130
summary of production, by States 77
tenor of copper, lead, and zinc ores 74–75
Arkansas, by J. P. Dunlop 78–82
Illinois, by J. P. Dunlop 82–86
Iowa, by J. P. Dunlop 86–87
Kansas, by J. P. Dunlop 87–90
Kentucky, by J. P. Dunlop 90–92
Michigan, by B. S. Butler 92–100
Missouri, by J. P. Dunlop 100–118
Oklahoma, by J. P. Dunlop 118–125
Wisconsin, by J. P. Dunlop 125–129
Singkep, tin 69
Slate, summary 21a, 37a, 39a
Smith, George Otis, paper on economic limits to domestic independence in minerals 1a–6a
Soapstone, summary 22a
Sodium nitrate, summary 37a
Sodium salts, summary 22a
South Africa, chromic iron ore 42
copper 726
quicksilver, exports to 382
tin 69
tungsten 934
South America, gold 613
lead 883
Page.
South America, lead, imports from 893
manganese ore 674, 687
quicksilver 403–404
silver 615
South Australia, iron ore 583
South Carolina, copper 725, 738
gold 56, 60, 605, 619, 627, 634
gold, silver, copper, lead, and zinc (mines report) 56, 60
manganese ore 671, 685
silver 56, 60, 619, 639
tin 65
value of mineral products 46a, 69a
South Chicago, Ill., iron-ore receipts 574
copper 154, 738, 743
South Dakota, gold 154, 605, 619, 627, 634, 642, 646
gold, silver, copper, and lead (mines report), by C. W. Henderson 18a, 153–160
lead 154, 883, 888
quicksilver 385
rutile 929
silver 154, 605, 619, 627, 639, 642, 646
tin 65
tungsten ore 932, 944
mills 946
value of mineral products 46a, 70a
Spain, copper 726, 792
imports from 779
gold 613
iron ore 583
imports from 579
manganese ore 674
molybdenum in ores 907
pig iron 595
exports to 595
quicksilver 372, 394–395
silver 615
tin 69
zinc 873
Spiegeleisen, imports 35a, 599
plants making spiegeleisen 679
prices 598
production 591, 597
summary 35a
(*See also* Manganese ore.)
Steel .....
(*See* Pig iron and steel.)
Stellite 899–904
Stone, Ralph W., paper on magnesium 147–151
Stone, summary 22a, 37a, 39a
Straits Settlements, tin 66
Strontium, summary 22a, 37a
Sudbury, Canada, nickel 917–919, 921–923
Sublimed blue and white lead 31a, 885–886
Sulphur, summary 22a, 37a, 39a
Sulphuric acid from smelters, summary 22a
Sumatra, platinum 14
Summary of mineral production, by M. B. Clark 27a–76a
(*See also* Mineral production of the United States in 1917—a summary.)
Superior, shipments of iron ore 573
Swaziland, tin 69
Sweden 726
gold 613
iron ore 583
imports from 579

Digitized by Google

Page.
Sweden, manganese ore ... 674
pig iron ... 595
exports to ... 595
imports from ... 594
quicksilver, exports to ... 382
silver ... 615
zinc ... 595
Switzerland, pig iron, exports to ... 595
imports from ... 594

T.

Talc and soapstone, summary ... 22a, 37a
Tantalum, summary ... 35a
Tariff, lead ... 891–892
nickel ... 922
quicksilver ... 381
zinc ... 869
Tasmania, copper, imports from ... 779
nickel, imports from ... 923
platinum ... 13, 14
Tellurium, by J. B. Umpleby ... 35
prices ... 35
production ... 35
summary ... 19a
Tennessee, aluminum ... 7
bauxite ... 1, 3–5
copper ... 56, 61, 725, 738, 743, 770, 772
ferroalloys ... 598
gold ... 56, 61, 605, 619, 627, 634, 642, 646
gold, silver, copper, lead, and zinc (mines report) ... 56, 60–61
iron ore ... 560–561, 567, 568, 585
lead ... 57, 61, 883, 888
manganese ore ... 669–671, 685
pig iron ... 586–587, 588
silver ... 56, 61, 605, 619, 639, 642, 646
value of mineral products ... 46a, 70a
zinc ... 57, 61, 862–863, 864
Texas, copper ... 721, 725, 738, 743
gold ... 605, 619, 628, 634, 642, 646, 721
gold, silver, copper, lead, and zinc (mines report), by C. W. Henderson ... 18a, 721–722
lead ... 721, 883, 888
manganese ore ... 669–671, 685
quicksilver ... 370, 372, 373, 378, 402, 421–424
silver ... 605, 619, 628, 639, 642, 646, 721
tin ... 65
value of mineral products ... 46a, 71a
zinc ... 721, 862–863
Thorium oxide, summary ... 37a
Tin, by Adolph Knopf ... 63–72
Alaska ... 63–64
California ... 63
curve showing average yearly prices ... 68
exports ... 36a
general statement ... 63
imports ... 35a, 66–67
Nevada ... 64–65
North Carolina ... 65
prices ... 67–68
production ... 63–65
publications ... 71
secondary ... 312, 320–327
smelting ... 65–66
South Carolina ... 65
South Dakota ... 65
Tin, summary ... 19a, 35a, 36a
Texas ... 65
world's output ... 68–71
map of, in 1916 ... 70
Titanium, by Frank L. Hess ... 929–930
imports ... 35a, 599
occurrence and uses ... 929–935
production ... 929
recent patents ... 930
summary (rutile) ... 30a, 35a, 73a
Toledo, Ohio, receipts of iron ore ... 573
stocks of iron ore ... 575
Transvaal silver ... 615
Tripoli, summary ... 37a
Tungsten, by Frank L. Hess ... 931–954
consumption ... 933
exports ... 36a, 933
general conditions ... 931
imports ... 36a, 599, 933
by countries ... 934
tungsten mills ... 944–947
mining, by States ... 935–944
ore ... 35a
prices ... 934
production ... 931–933
by States ... 932–933
publications ... 947–954
summary ... 19a, 35a, 36a
supply ... 933
world's production ... 947
Tunis, iron ore ... 583
manganese ores ... 674, 686
Turkey, chromic iron ore ... 42
copper ... 726
gold ... 613
quicksilver ... 397
silver ... 615
Two Harbors, shipments of iron ore ... 573
Type metal, imports ... 35a, 660, 893

U.

Umber, summary ... 37a
Umpleby, Joseph B., paper on arsenic, bismuth, selenium, and tellurium ... 23–35
Union of South Africa, manganese ore ... 674, 690
United Kingdom, aluminum ... 7
antimony ... 659
bauxite ... 3
cadmium ... 50
chromic iron ore ... 42
copper, exports to ... 780
imports from ... 779
iron ore ... 583
exports to ... 580
imports from ... 579
lead, imports from ... 893
manganese ore ... 674
imports from ... 673
pig iron ... 595
exports to ... 595
imports from ... 594
quicksilver, exports to ... 382
Uranium and vanadium ... 955–959
(*See also* Radium, uranium, and vanadium.)
Uranium and vanadium, ore ... 955, 956
summary ... 19a, 35a

Digitized by Google

Page.
Uruguay, bismuth ... 31
gold ... 613
silver ... 615
Utah, antimony ... 658
copper ... 167, 725, 738–740, 743, 772–775
gold ... 167, 605, 619, 628, 634, 637, 642, 646
gold, silver, copper, lead, and zinc (mines report), by V. C. Heikes ... 19a, 167–202
iron ore ... 560–561, 568
lead ... 167, 883, 888
manganese ore ... 669–671, 685
manganiferous silver ore ... 675
molybdenum ... 907, 913–914
quicksilver ... 385, 424
silver ... 167, 605, 619, 628, 639, 642, 646
tungsten ... 932–933, 944
mills ... 946
uranium ... 955
value of mineral products ... 47a, 72a
vanadium ... 955, 956
zinc ... 167, 862–863, 864

V.

Value of mineral products, by substances, 1916-17 ... 30a–32a
total, 1880–1917 ... 33a
Vanadium ... 955–959
(*See also* Radium, uranium, and vanadium.)
ore ... 955–956
summary ... 19a, 36a
Venetian red, summary ... 37a
Venezuela, copper ... 726
gold ... 613
iron ore ... 583
imports from ... 579
platinum ... 15
quicksilver, exports to ... 382
silver ... 615
Vermilion range, iron ore ... 571–572, 578
Vermont, copper ... 56, 61, 725, 738, 743, 775
gold ... 605, 619, 625
gold, silver, copper, lead, and zinc (mines report) ... 56, 61
silver ... 56, 605, 619, 625, 639, 642, 646
value of mineral products ... 47a, 73a
Virginia, arsenic ... 23, 24
cooperation ... 25a
copper ... 56, 62, 725, 738, 743, 775
ferroalloys ... 598
gold ... 56, 62, 605, 619, 627, 634, 642, 646
gold, silver, copper, lead, and zinc (mines report) ... 56, 61–62
iron ore ... 560–561, 567, 568, 585
lead ... 57, 62, 883, 888
manganese ore ... 669–671, 685
manganiferous ore ... 670–671
pig iron ... 586–587, 588
silver ... 56, 62, 605, 619, 639, 642, 646
titanium (rutile) ... 73a, 929, 930
value of mineral products ... 47a, 73a
zinc ... 57, 62, 862–863, 864

W.

Washington, arsenic ... 23, 24
chromite ... 38
cooperation ... 25a
copper ... 493, 725, 738–740, 743, 775
Page.
Washington, ferroalloys ... 598
gold ... 493, 605, 619, 629, 634, 637, 642, 646
gold, silver, copper, lead, and zinc (mines report), by C. N. Gerry ... 19a, 493–507
lead ... 493, 883, 888
magnesium ... 151
manganese ore ... 669–671
molybdenum ... 914
pig iron ... 586–587, 588
platinum ... 13, 20
quicksilver ... 385, 400, 424
silver ... 493, 605, 619, 629
tungsten ore ... 932, 944
mills ... 946
value of mineral products ... 47a, 74a
zinc ... 493, 862–863
West Virginia, iron ore ... 560–561, 568
pig iron ... 586–587, 588
value of mineral products ... 47a, 75a
zinc smelters ... 867
Whetstones, summary ... 37a
White lead ... 37a, 886, 894, 895
Wisconsin, cooperation ... 25a
iron ore ... 560–561, 567, 568
lead ... 77, 126, 883, 888
manganiferous iron ore ... 669–671
pig iron ... 586–587, 588
silver, copper, lead, and zinc (mines report), by J. P. Dunlop ... 125–129
value of mineral products ... 47a, 75a
zinc ... 77, 126, 862–863, 864
World's production, bauxite ... 3
copper ... 725–726
gold ... 611–614
iron ore ... 583
lead ... 891
manganese ore ... 673–674
nickel ... 921
pig iron ... 595
platinum ... 13, 14
quicksilver ... 371–372
silver ... 614–615
tin ... 68–71
tungsten ... 947
zinc ... 868
Wyoming, copper ... 161, 725, 738–740, 743, 775
gold ... 161, 605, 619, 629, 634, 642, 646
gold, silver, and copper (mines report), by C. W. Henderson ... 19a, 161–165
iron ore ... 560–561, 568
lead ... 883
manganese ore ... 671, 686
platinum ... 20
silver ... 161, 605, 619, 629, 639, 642, 646
value of mineral products ... 47a, 76a

Y.

Yale, Charles G., paper on gold, silver, copper, lead, and zinc in California (mines report) ... 203–239
Oregon (mines report) ... 241–252

Z.

Zinc, by C. E. Siebenthal ... 855–879
brass, exports ... 875
imports, old ... 871
remelted ... 312

Digitized by Google

Page.
Zinc, comparison of smelter and mine reports ... 860–862
consumption ... 855, 876–877
in United States ... 876–877
content of pigments ... 859
dross, exports of ... 36a, 874
dust ... 858, 859, 870, 871, 878
exports, domestic ... 36a, 873–875
foreign ... 875–876
imports ... 35a, 869–873
introduction ... 855
lithopone ... 859
imports ... 871
mine and smelter totals ... 860–862
mine production ... 18a, 55, 77, 167, 208, 253, 331, 457, 493, 509, 697, 721, 798, 862–864
mined in 1917, by States and ores ... 863
ore ... 863–864, 870, 872–873, 874
imports from Canada and Mexico ... 872
oxide ... 859
exports ... 874
leaded zinc ... 859
zinc-lead ... 859
imports ... 37a, 871
summary ... 37a
pigments ... 859
prices ... 878–879
at St. Louis in 1914–1917 ... 878, 879
curves ... 878
dust ... 878

Pa
Zinc, prices, 1850–1917 ...
production ... 855–
annual, 1873–1917 ...
by districts ...
by location of smelter ...
by States ... 856, 862–
electrolytic ... 856,
reduction plants ... 865–
electrolytic plants ...
smelters, list of ... 866–
smelting capacity and changes ...
remaining in warehouse ...
residues ...
residuum ... 570, 669,
rolled zinc ... 857–
secondary zinc ... 312, 319–320, 859–
smelter and mine totals ... 860–
summary ... 19a, 35a, 36a,
tariff ...
trade conditions ... 868–
value ... 855,
warehouse transactions ... 869–
world's production ...
Zinc-lead ... 859,
ore ...
Zinc oxide ... 859,
(*See also* Zinc.)
summary ... 3
Zinc residuum, manganiferous ... 570, 669, 6
Zircon, summary ... 2

Digitized by Google

Digitized by Google

Digitized by Google

Digitized by Google

Digitized by Google